

(12) STANDARD PATENT
(19) AUSTRALIAN PATENT OFFICE

(11) Application No. **AU 2006201443 B2**

(54) Title
Method of manufacturing a bituminous coated material with pre-coating

(51) International Patent Classification(s)
E01C 19/10 (2006.01) **E01C 7/18** (2006.01)
C09D 195/00 (2006.01)

(21) Application No: **2006201443** (22) Date of Filing: **2006.04.06**

(30) Priority Data

(31) Number (32) Date (33) Country
0503527 2005.04.08 FR

(43) Publication Date: **2006.10.26**
(43) Publication Journal Date: **2006.10.26**
(44) Accepted Journal Date: **2012.06.28**

(71) Applicant(s)
LEA-CO International

(72) Inventor(s)
Antoine, Jean-Pierre;Olard, Francois;Huon, Patrick

(74) Agent / Attorney
A J PARK, Level 11 60 Marcus Clarke Street, Canberra, ACT, 2601

(56) Related Art
US2104410
FR2479299
EP0552574

Abstract**Method of manufacturing a bituminous coated material with pre-coating**

A first part of the solid fragments containing fines is dried and coated, whereupon the remaining part of the solid fragments, having retained its initial humidity, is added to the mix obtained.

Application to road building.

- 1 -
(followed by page 1a)

Regulation 3.2

**AUSTRALIA
PATENTS ACT, 1990**

COMPLETE SPECIFICATION

FOR A STANDARD PATENT

ORIGINAL

Name of Applicant:	EIFFAGE TRAVAUX PUBLICS
Actual Inventors:	ANTOINE, Jean-Pierre; OLARD, François; and HUON, Patrick
Address for service in Australia:	A J PARK, Level 11, 60 Marcus Clarke Street, Canberra ACT 2601, Australia
Invention Title:	METHOD OF MANUFACTURING A BITUMINOUS COATED MATERIAL WITH PRE-COATING

The following statement is a full description of this invention, including the best method of performing it known to us.

20576/617175_1.DOC

2006201443 06 Apr 2006

2006201443 06 Apr 2006

Method of manufacturing a bituminous coated material with pre-coating

The invention relates to a method of manufacturing a coated material comprising solid fragments coated with a binder, the method comprising a stage of drying of the solid fragments followed by a stage of coating of the entirety of the solid fragments with binder, in particular with hot binder.

"Solid fragments" is taken to mean all solid fragments usable for forming coated materials in particular for road building, comprising in particular natural mineral granular materials and aggregates of coated materials resulting from the recycling of materials recovered from the repairing of roads.

"Binder" is taken to mean any hydrocarbon binder of fossil or vegetable origin which is usable for the formation of coated materials, in particular pure bitumen or bitumen with fluxing agents and/or liquefying agents added and/or bitumen modified by the addition of polymers, this binder being possibly presented in the form of an emulsion or foam.

In the conventional method for hot coating, the drying stage is carried out so as to eliminate substantially entirely the humidity in the granular materials, which requires a considerable expense of energy due to the large quantity of water initially contained in the granular materials. Moreover, the drying and increase in temperature bring about the release of vapours containing steam charged with dusts. Taking into account their large quantity, these vapours are difficult to process and the application of the method therefore leads to substantial pollution of the environment.

To solve this problem, EP 1 469 038 proposes to apply the drying stage to a first part of the granular materials, substantially devoid of fines, then to coat this

2006201443 31 May 2012

first part with hot bitumen, and then to add to the mix thus obtained a second part of the granular materials comprising sands and fines.

This method requires two fractions of granular materials to be available, one devoid of fines and the other containing fines, which may lead to problems. Moreover, this method cannot be put into practice efficiently in certain existing coating installations, and may therefore necessitate costly adaptation thereof.

In this specification where reference has been made to patent specifications, other external documents, or other sources of information, this is generally for the purpose of providing a context for discussing the features of the invention. Unless specifically stated otherwise, reference to such external documents is not to be construed as an admission that such documents, or such sources of information, in any jurisdiction, are prior art, or form part of the common general knowledge in the art.

The object of at least preferred embodiments of the invention is to eliminate all or some of these disadvantages, and/or to at least provide the public with a useful choice.

In accordance with an aspect of the invention, there is provided a method of manufacturing a coated material comprising solid fragments coated with a binder consisting of: drying a first part of the solid fragments, coating the dried first part of the solid fragments with the binder, thereby obtaining a mix, adding to the mix the remaining part of the solid fragments, retaining its initial humidity, wherein at least the first part of the solid fragments contains fines.

2006201443 31 May 2012

2a

Optional, additional or alternative features of the invention are given below:

- The drying stage only affects a first part of the solid fragments, which is then mixed, before the coating stage, to the remaining part which has retained its initial humidity.
- The drying stage is carried out at a temperature higher than 100°C, preferably at a temperature of about 130°C.
- The upper limit of the grain size of the remaining part is lower than, equal to or higher than the upper limit of the grain size of the first part.
- The upper limit of the grain size of the remaining part is lower than or equal to the lower limit of the grain size of the first part.
- The grain size of the remaining part is selected from 0/2 and 0/4.
- The drying stage applies to the entirety of the solid fragments and is carried out in conditions which allow a fraction of the humidity thereof to remain.
- The drying stage is carried out at a temperature lower than 100°C, preferably at a temperature of about 90°C.

2006201443 06 Apr 2006

- A controlled quantity of water is added to the solid fragments between the stages of drying and coating and/or after the coating stage.
- The binder is applied at a temperature of between 100 and 200°C, preferably of about 160°C, or between 30 and 90 °C in the case of a binder in the form of an emulsion.

In a modification of the method according to the invention the drying stage is applied only to a first part of the solid fragments, which is then coated, then the remaining part having retained its initial humidity is added to the mix obtained, at least the first part containing fines.

The invention is illustrated below by examples. In these examples, the solid fragments are mineral granular materials having a grain size of 0/10 mm, the binder is bitumen with a penetrability of 35/50 according to the standard NF EN 1426, and drying is carried out at 130 °C when it is applied to only a first part of the granular materials and at 90 °C when it is applied to the entirety of the granular materials. The proportions indicated are by mass.

Example 1

The solid fragments are formed of 98 % granular materials having a grain size of 0/10 mm and of 2 % calcareous fines. The 98 % of 0/10 granular materials are formed of porphyry and have the following grain size distribution:

6/10	44
2/6	22
0/2	32.

The 6/10 and 2/6 fractions and fines are mixed and dried at 130 °C, then the 0/2 fraction is added at ambient temperature, its degree of humidity being 4 %. Then 5.6 % 35/50 bitumen is added at 160 °C, to carry out coating.

2006201443 06 Apr 2006

Example 2

The composition of solid fragments and the quantity of binder are the same as in Example 1.

Drying is carried out on the entirety of the solid fragments, whereupon 1.5 % water is added in proportion by mass before carrying out coating by adding binder at 160°C.

Example 3

The type and distribution of grain sizes of the solid fragments and the quantity of binder are the same as in Examples 1 and 2.

The entirety of the solid fragments is divided homogeneously into a first part representing 65 % by mass and a second part representing 35 % by mass. The first part is dried at 130 °C, then the second part is added at ambient temperature, its degree of humidity being 4 %. Then 5.6 % 35/50 bitumen is added at 160 °C in order to carry out coating.

Example 4

The type and grain size distribution of the solid fragments and the quantity of binder are the same as in Examples 1, 2 and 3.

The entirety of solid fragments is divided in a homogenous manner into a first part representing 80 % by mass and a second part representing 20 % by mass. Drying is carried out on the first part, which is then coated with the binder added at 160 °C, whereupon the second part is added which is at ambient temperature and which has a degree of humidity of 4 %.

2006201443 06 Apr 2006

Example 5

In this example, the solid fragments are composed by mass of 2 % calcareous fines, as in the previous examples, and of 98 % siliceous limestone granules with a grain size of 0/10 mm, the grain size distribution of these being the following:

6/10 29

4/6 28

0/4 41.

The procedure is as for Example 3, except that the two parts of the solid fragments do not have the same grain size composition, the first part comprising the entirety of the 6/10 and 4/6 fractions and fines and a proportion of the 0/4 fraction corresponding to 16 % of the total of solid fragments, and the second part being formed of the remaining 25 % of the 0/4 fraction, having a degree of humidity of 4 %. Furthermore, the quantity of binder is brought to 5.9 % of the mass of the solid fragments.

The table below gives for each of these examples the final temperature of the coated material and various properties thereof. By way of comparison, the corresponding data are supplied for reference coated materials obtained from the same components by the conventional method consisting of drying the entirety of the solid fragments at 160 °C before coating.

Example	1	2	3	4	Reference
Final T (°C)	≈ 85	≈ 90	≈ 85	≈ 90	160
PCG temp.	95	95	95	95	160
PCG %	7.1	6.8	7.1	8.8	9.3
% water	0.3	0.3	0.4	0.2	-
% voids	5.7	7.4	9.2	7.4	6.2
Rutting	6.4	9.6	6.2	5.2	6.4
r/R	0.84	0.81	0.80	0.82	0.90

2006201443 06 Apr 2006

Example	5	Reference
Final T (°C)	≈ 90	160
PCG temperature	95	160
PCG %	9.9	10.8
% water	0.1	-
% voids	8.0	5.8
Rutting	5.7	6.4
r/R	0.70	0.88

In the table:

- "PCG Temperature" represents the temperature in °C to which the coated material is brought in order to carry out the PCG test according to the French Standard P 98-252,
- "PCT %" represents the percentage of voids obtained for 60 gyrations during the test with the gyratory shearing press (PCG) according to the French Standard P 98-252,
- "% water" represents the content of water by mass of the coated material after coating,
- "% voids" represents the initial percentage of voids of the test piece subjected to the rutting test,
- "rutting" represents the percentage of voids after 30,000 cycles during the rutting test according to the French Standard P 98-253-1,
- "r/R" represents the ratio r/R obtained during the Duriez test according to French Standard P 98-251-1.

Throughout this specification, the word "comprise", or variations such as "comprises" or "comprising", means the inclusion of a stated element, integer or step, or group of elements, integers or steps, but does not necessarily mean the exclusion of any other element, integer or step or group of elements, integers or steps.

THE CLAIMS DEFINING THE INVENTION ARE AS FOLLOWS:

1. Method of manufacturing a coated material comprising solid fragments coated with a binder, the method consisting of:
drying a first part of the solid fragments,
coating the dried first part of the solid fragments with the binder, thereby obtaining a mix,
adding to the mix the remaining part of the solid fragments, retaining its initial humidity,
wherein at least the first part of the solid fragments contains fines.
2. Method according to claim 1, wherein the entirety of the solid fragments is divided homogeneously into the first part and the second part.
3. Method according to either of claims 1 or 2, wherein the first and second parts represent respectively 80 % and 20 % by mass of the solid fragments.
4. Method according to any one of the preceding claims, wherein the drying stage is carried out at a temperature higher than 100°C.
5. Method according to claim 4, wherein the drying stage is carried out at a temperature of about 130°C.
6. Method according to any one of the preceding claims, further comprising adding a controlled quantity of water to the solid fragments between the drying and coating stages and/or after the coating.
7. Method according to one of the preceding claims, wherein the binder is applied at a temperature of between 100 and 200°C.
8. Method according to claim 7, wherein the binder is applied at a temperature of about 160°C.
9. Method according to any one of claims 1 to 6, wherein the binder is

2006201443 31 May 2012

applied at a temperature of between 30°C and 90°C in the case of a binder in the form of an emulsion.

10. Method according to claim 1 and substantially as herein described with reference to any embodiment disclosed.

11. Method of manufacturing a coated material comprising solid fragments coated with a binder, substantially as herein described with reference to any one of the Examples.

12. A coated material when manufactured by the method of any one of the preceding claims.

LEA-CO INTERNATIONAL
By the authorized agents
A J Park
Per

