



(86) Date de dépôt PCT/PCT Filing Date: 2011/06/21
(87) Date publication PCT/PCT Publication Date: 2012/01/05
(45) Date de délivrance/Issue Date: 2015/07/28
(85) Entrée phase nationale/National Entry: 2012/12/19
(86) N° demande PCT/PCT Application No.: GB 2011/000932
(87) N° publication PCT/PCT Publication No.: 2012/001343
(30) Priorité/Priority: 2010/06/28 (US12/825,004)

(51) Cl.Int./Int.Cl. *C09K 8/46* (2006.01),
C04B 14/16 (2006.01), *C04B 18/16* (2006.01),
C09K 8/467 (2006.01)

(72) Inventeurs/Inventors:
BRENNEIS, D. CHAD, US;
RODDY, CRAIG WAYNE, US;
BENKLEY, JAMES R., US;
DEPLACIDO, PRESTON, US;
CAVENY, WILLIAM J., US;
MORGAN, RICKEY L., US;
MORGAN, RONNIE G., US

(73) Propriétaire/Owner:
HALLIBURTON ENERGY SERVICES, INC., US

(74) Agent: NORTON ROSE FULBRIGHT CANADA

(54) Titre : COMPOSITIONS DE CIMENT SOLUBLES DANS DE L'ACIDE COMPRENANT DE LA POUSSIERE DE FOUR
A CIMENT ET/OU UNE POZZOLANE NATURELLE ET LEURS PROCEDES D'UTILISATION
(54) Title: ACID-SOLUBLE CEMENT COMPOSITIONS COMPRISING CEMENT KILN DUST AND/OR A NATURAL
POZZOLAN AND METHODS OF USE

(57) **Abrégé/Abstract:**

The present invention relates to acid-soluble cement compositions that comprise cement kiln dust ("CKD") and/or a natural pozzolan and associated methods of use. An embodiment includes a method of cementing comprising: placing an acid-soluble cement composition in a subterranean formation, wherein the acid-soluble cement composition comprises a hydraulic cement, a component selected from the group consisting of CKD, pumicite, and a combination thereof, and water; allowing the acid-soluble cement composition to set; and contacting the set acid-soluble cement composition with an acid to dissolve the set acid-soluble cement composition.



(74) **Agent(suite/continued):** LLP/S.E.N.C.R.L., S.R.L.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
5 January 2012 (05.01.2012)

PCT

(10) International Publication Number
WO 2012/001343 A1

(51) International Patent Classification:

C09K 8/46 (2006.01) *C04B 14/16* (2006.01)
C09K 8/467 (2006.01) *C04B 18/16* (2006.01)

(21) International Application Number:

PCT/GB2011/000932

(22) International Filing Date:

21 June 2011 (21.06.2011)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

12/825,004 28 June 2010 (28.06.2010) US

(71) Applicant (for all designated States except US): **HAL-LIBURTON ENERGY SERVICES, INC.** [US/US]; P O Box 1431, Duncan, OK 73536 (US).

(71) Applicant (for MW only): **CURTIS, Philip, Anthony** [GB/GB]; A A Thornton & Co, 235 High Holborn, London WC1V 7LE (GB).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **BRENNEIS, D., Chad** [US/US]; 4408 Medcalf Road, Marlow, OK 73055 (US). **RODDY, Craig Wayne** [US/US]; 2906 Timber Ridge Drive, Duncan, OK 73533 (US). **BENKLEY, James, R.** [US/US]; 1810 Terrace Drive, Duncan, OK 73533 (US). **DEPLACIDO, Preston** [US/US]; 151 HCR 4118, Itasca, TX 76055 (US). **CAVENY, William, J.** [US/US]; Rt 2 Box 282, Rush Springs, OK 73082 (US). **MORGAN, Rickey, L.** [US/US]; 1494 East Elk Street,

Duncan, OK 73533 (US). **MORGAN, Ronnie, G.** [US/US]; Rt 2 Box 282, Rush Springs, OK 73082 (US).

(74) Agent: **COTTRILL, Emily, Elizabeth, Helen**; A A Thornton & Co, 235 High Holborn, London WC1V 7LE (GB).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: ACID-SOLUBLE CEMENT COMPOSITIONS COMPRISING CEMENT KILN DUST AND/OR A NATURAL POZZOLAN AND METHODS OF USE

(57) Abstract: The present invention relates to acid-soluble cement compositions that comprise cement kiln dust ("CKD") and/or a natural pozzolan and associated methods of use. An embodiment includes a method of cementing comprising: placing an acid-soluble cement composition in a subterranean formation, wherein the acid-soluble cement composition comprises a hydraulic cement, a component selected from the group consisting of CKD, pumicite, and a combination thereof, and water; allowing the acid-soluble cement composition to set; and contacting the set acid-soluble cement composition with an acid to dissolve the set acid-soluble cement composition.




WO 2012/001343 A1

ACID-SOLUBLE CEMENT COMPOSITIONS COMPRISING CEMENT KILN DUST AND/OR A NATURAL POZZOLAN AND METHODS OF USE

BACKGROUND

[0002] The present invention relates to cementing operations and, more particularly, in certain embodiments, to acid-soluble cement compositions that comprise cement kiln dust ("CKD") and/or a natural pozzolan and associated methods of use.

[0003] Cement compositions may be used in a variety of subterranean applications. For example, in subterranean well construction, a pipe string (e.g., casing, liners, expandable tubulars, etc.) may be run into a well bore and cemented in place. The process of cementing the pipe string in place is commonly referred to as "primary cementing." In a typical primary cementing method, a cement composition may be pumped into an annulus between the walls of the well bore and the exterior surface of the pipe string disposed therein. The cement composition may set in the annular space, thereby forming an annular sheath of hardened, substantially impermeable cement (i.e., a cement sheath) that may support and position the pipe string in the well bore and may bond the exterior surface of the pipe string to the subterranean formation. Among other things, the cement sheath surrounding the pipe string



functions to prevent the migration of fluids in the annulus, as well as protecting the pipe string from corrosion. Cement compositions also may be used in remedial cementing methods, for example, to seal cracks or holes in pipe strings or cement sheaths, to seal highly permeable formation zones or fractures, to place a cement plug, and the like. Cement compositions also may be used in surface applications, for example, construction cementing.

[0004] In some applications, it may be desirable for the cement composition to be acid soluble. For instance, an acid-soluble cement composition may be desirable in applications where it is anticipated that the hardened cement will be removed in subsequent well bore operations. One particular application includes use of an acid-soluble cement composition to plug permeable zones in a formation that may allow the undesired flow of fluid into, or from, the well bore. For example, the permeable zones may result in the loss of circulation of fluids, such as a drilling fluid or a cement composition, in the well bore or an undesired influx of gas or water into the well bore. The permeable zones include, for example, vugs, voids, fractures (natural or otherwise produced) and the like. Other applications for acid-soluble cement compositions include, for example, the formation of annular plugs and isolation of gravel-packed well bore intervals. Examples of acid-soluble cement compositions include those comprising Sorel cements and Portland cements.

SUMMARY

[0005] The present invention relates to cementing operations and, more particularly, in certain embodiments, to acid-soluble cement compositions that comprise CKD and/or a natural pozzolan and associated methods of use.

[0006] According to one aspect of the present invention there is provided a method of cementing. The method may comprise placing an acid-soluble cement composition in a subterranean formation. The acid-soluble cement composition may comprise a hydraulic cement, a component selected from the group consisting of cement kiln dust, pumicite, and a combination thereof, and water. The method may further comprise allowing the acid-soluble cement composition to set. The method may further comprise contacting the set acid-soluble cement composition with an acid to dissolve the set acid-soluble cement composition.

[0007] According to one aspect of the present invention there is provided a method of cementing. The method may comprise placing an acid-soluble cement composition in a subterranean formation. The acid-soluble cement composition may comprise Portland cement, cement kiln dust, an acid-soluble filler, and water. The method may further comprise

allowing the cement composition to set. The method may further comprise contacting the set acid-soluble cement composition with an acid to dissolve the set acid-soluble cement composition.

[0008] According to another aspect of the present invention there is provided a cement composition comprising: hydraulic cement; a component selected from the group consisting of cement kiln dust, pumicite, and a combination thereof; and water. The cement composition may be acid-soluble.

[0009] The features and advantages of the present invention will be readily apparent to those skilled in the art. While numerous changes may be made by those skilled in the art, such changes are within the scope of the invention.

DESCRIPTION OF PREFERRED EMBODIMENTS

[0010] The present invention relates to cementing operations and, more particularly, in certain embodiments, to acid-soluble cement compositions that comprise CKD and/or a natural pozzolan and associated methods of use.

[0011] There may be several potential advantages to the methods and compositions of the present invention, only some of which may be alluded to herein. One of the many potential advantages of embodiments of the present invention is that the inclusion of the CKD and/or natural pozzolan in the acid-soluble cement composition should reduce the amount of, or potentially eliminate, a higher cost additive, such as Portland or Sorel cement, resulting in a more economical cement composition. Another potential advantage of embodiments of the present invention is that reduction of the amount of Portland cement should reduce the carbon footprint of the acid-soluble cement composition.

[0012] Embodiments of the acid-soluble cement compositions of the present invention may comprise: a hydraulic cement; a component selected from the group consisting of CKD, a natural pozzolan, and a combination thereof; and water. In an embodiment, the hydraulic cement may comprise Sorel cement. In an embodiment, the cement compositions may further comprise an acid-soluble filler. In an embodiment, the cement compositions may further comprise a source of calcium ions (*e.g.*, hydrated lime). Other optional additives may also be included in embodiments of the cement compositions of the present invention as desired, including, but not limited to, fly ash, slag cement, metakaolin, shale, zeolite, combinations thereof, and the like. Additionally, embodiments of the cement compositions of the present invention may be foamed and/or extended as desired by those of ordinary skill in the art.

[0013] The acid-soluble cement compositions of the present invention should have a density suitable for a particular application as desired by those of ordinary skill in the art, with the benefit of this disclosure. In some embodiments, the cement compositions of the present invention may have a density in the range of from about 8 pounds per gallon (“ppg”) [959 kg/m³] to about 16 ppg [1917 kg/m³]. In other embodiments, the cement compositions may be foamed to a density in the range of from about 8 ppg [959 kg/m³] to about 13 ppg [1558 kg/m³].

[0014] Embodiments of the acid-soluble cement compositions of the present invention may comprise a hydraulic cement. A variety of hydraulic cements may be utilized in accordance with the present invention, including, but not limited to, those comprising calcium, aluminum, silicon, oxygen, iron, and/or sulfur, which set and harden by reaction with water. Suitable hydraulic cements include, but are not limited to, Sorel cements, Portland cements, pozzolana cements, gypsum cements, high alumina content cements, slag cements, silica cements, and combinations thereof. In certain embodiments, the hydraulic cement may comprise a Portland cement. In some embodiments, the Portland cements that are suited for use in the present invention are classified as Classes A, C, G, and H cements according to American Petroleum Institute, API Specification for Materials and Testing for Well Cements, API Specification 10, Fifth Ed., July 1, 1990. In addition, in some embodiments, cements suitable for use in the present invention may be classified as ASTM Type I, II, or III. As will be discussed in more detail below, acid-soluble fillers can be used with hydraulic cements (such as Portland cement) that do harden into an acid-soluble mass.

[0015] Where present, the hydraulic cement generally may be included in the acid-soluble cement compositions in an amount sufficient to provide the desired compressive strength, density, and/or cost. In accordance with embodiments, at least a portion of the hydraulic cement may be replaced with CKD and/or a natural pozzolan. In an embodiment, at least a portion of the hydraulic cement is replaced with CKD and/or a natural pozzolan. In some embodiments, the hydraulic cement may be present in the cement compositions of the present invention in an amount in the range of 0% to about 99% by weight of cementitious components. Cementitious components include those components or combinations of components of the cement compositions that hydraulically set, or otherwise harden, to develop compressive strength, including, for example, Sorel cement, Portland cement, CKD, fly ash, pumice, slag, lime, shale, and the like. The hydraulic cement may be present, in

certain embodiments, in an amount of about 5%, about 10%, about 15%, about 20%, about 25%, about 30%, about 35%, about 40%, about 45%, about 50%, about 55%, about 60%, about 65%, about 70%, about 75%, about 80%, about 90%, or about 95%. In an embodiment, the hydraulic cement may be present in an amount in the range of 0% to about 95% by weight of cementitious components. In another embodiment, the hydraulic cement may be present in an amount in the range of about 20% to about 95% by weight of cementitious components. In yet another embodiment, the hydraulic cement may be present in an amount in the range of about 50% to about 90% by weight of cementitious components. One of ordinary skill in the art, with the benefit of this disclosure, will recognize the appropriate amount of the hydraulic cement to include for a chosen application.

[0016] An example of a suitable hydraulic cement comprises a Sorel cement. Sorel cements typically include magnesia-based cement systems formed from a mixture of magnesium oxide and magnesium chloride. However, as used herein, the term “Sorel cement” is intended to encompass any of a variety of metal oxides and soluble salts which together form a hydraulic cement. In the presence of water, the metal oxide and the soluble salt forming the Sorel cement should solidify into an acid-soluble mass. Embodiments of the Sorel cements should rapidly develop a desirable compressive strength. In accordance with embodiments, at least a portion of the Sorel cement may be replaced with CKD and/or a natural pozzolan. In an embodiment, at least a portion of the soluble salt is replaced with CKD and/or a natural pozzolan.

[0017] In an embodiment, the Sorel cement comprises a metal oxide. In one particular embodiment, the Sorel cement comprises an alkaline earth metal oxide, such as magnesium oxide. A suitable metal oxide is THERMATEK™ LT additive, available from Halliburton Energy Services, Inc. The metal oxide present in the Sorel cement should have an activity level sufficient to provide the desired reactivity. For example, the higher the activity level of the metal oxide, the faster the reaction of the metal oxide with the other components of the Sorel cement to form the hardened mass. The activity level of the metal oxide may vary based on a number of factors. For example, the particle size differential of the metal oxide particles may affect the activity level. A smaller particle size differential may result in a higher activity level due, inter alia, to a greater surface area. Another factor that may affect the activity level of the metal oxide is a sintering process. By varying the heat applied during, and time of, the sintering process, metal oxide with varying activity levels may be provided. Metal oxide that

has not been treated by a sintering process may have a very high activity level, and thus it may be highly reactive in the Sorel cements. In an embodiment, a relatively more reactive metal oxide may be desired, such as where it may be desired to have a cement composition with a relatively short set time, for example, when desired to rapidly seal off a permeable zone. In an alternative embodiment, a relatively less reactive metal oxide may be desired, for example, where a delay may be desired between mixing the cement composition and the formation of a hardened mass.

[0018] A wide variety of soluble salts are suitable for use in the Sorel cement, including metal chlorides. In one embodiment, the Sorel cement comprises an alkaline earth metal chloride, such as magnesium chloride. An example of a suitable magnesium chloride is C-TEK additive, available from Halliburton Energy Services, Inc. In an alternative embodiment, the Sorel cement comprises magnesium sulfate or ammonium mono or dibasic phosphate.

[0019] In an embodiment, the Sorel cement may comprise the metal oxide and the soluble salt in a metal-oxide-to-soluble-salt ratio of about 3:1 to about 1:3. In another embodiment, the metal-oxide-to-soluble-salt ratio may range from about 2:1 to about 1:2. In yet another embodiment, the metal-oxide-to-soluble-salt ratio may range from about 1.5:1 to about 1:1.5. One of ordinary skill in the art will recognize the appropriate ratio of the metal oxide and soluble salt to include for a particular application.

[0020] Embodiments of the acid-soluble cement compositions generally may comprise CKD, which is a material generated in the manufacture of cement. CKD, as that term is used herein, refers to a partially calcined kiln feed which is removed from the gas stream and collected, for example, in a dust collector during the manufacture of cement. Usually, large quantities of CKD are collected in the production of cement that are commonly disposed of as waste. Disposal of the CKD as waste can add undesirable costs to the manufacture of the cement, as well as the environmental concerns associated with its disposal. The chemical analysis of CKD from various cement manufactures varies depending on a number of factors, including the particular kiln feed, the efficiencies of the cement production operation, and the associated dust collection systems. CKD generally may comprise a variety of oxides, such as SiO_2 , Al_2O_3 , Fe_2O_3 , CaO , MgO , SO_3 , Na_2O , and K_2O . The term "CKD" is used herein to mean cement kiln dust made as described above and equivalent forms of cement kiln dust made in other ways.

[0021] The CKD generally may exhibit cementitious properties, in that it may set and harden in the presence of water. In accordance with embodiments of the present invention, the CKD may be used, among other things, to replace higher cost cementitious components, such as Portland cement and/or Sorel cement, resulting in more economical cement compositions. In addition, substitution of the CKD for the Portland and/or Sorel cement should result in a cement composition with a reduced carbon footprint.

[0022] The CKD may be included in the acid-soluble cement compositions in an amount sufficient to provide the desired compressive strength, density, cost reduction, and/or reduced carbon footprint. In some embodiments, the CKD may be present in the cement compositions of the present invention in an amount in the range of from about 1% to about 100% by weight of cementitious components. For example, the CKD may be present in an amount of about 5%, about 10%, about 15%, about 20%, about 25%, about 30%, about 35%, about 40%, about 45%, about 50%, about 55%, about 60%, about 65%, about 70%, about 75%, about 80%, about 90%, or about 95%. In one embodiment, the CKD may be present in an amount in the range of from about 5% to about 99% by weight of cementitious components. In another embodiment, the CKD may be present in an amount in the range of from about 5% to about 80% by weight of cementitious components. In yet another embodiment, the CKD may be present in an amount in the range of from about 50% to about 80% by weight of cementitious components. One of ordinary skill in the art, with the benefit of this disclosure, will recognize the appropriate amount of CKD to include for a chosen application.

[0023] Embodiments of the acid-soluble cement compositions may further comprise a natural pozzolan. Natural pozzolans are generally present on the Earth's surface and set and harden in the presence of hydrated lime and water. Examples of natural pozzolans include pumicite, diatomaceous earth, volcanic ash, opaline shale, tuff, and combinations thereof. Generally, pumicite is a volcanic rock that exhibits cementitious properties, in that it may set and harden in the presence of a source of calcium ions and water. Hydrated lime may be used in combination with the pumicite, for example, to provide sufficient calcium ions for the pumicite to set. The natural pozzolan may be used, among other things, to replace higher cost cementitious components, such as Portland or Sorel cement, in embodiments of the sealant compositions, resulting in more economical sealant compositions. In addition, substitution of

the natural pozzolan for the Portland cement and/or Sorel cement should result in a cement composition with a reduced carbon footprint.

[0024] Where present, the natural pozzolan may be included in an amount sufficient to provide the desired compressive strength, density, cost reduction and/or reduced carbon footprint for a particular application. In some embodiments, the natural pozzolan may be present in the acid-soluble cement compositions of the present invention in an amount in the range of from about 1% to about 100% by weight of cementitious components. For example, the natural pozzolan may be present in an amount of about 5%, about 10%, about 15%, about 20%, about 25%, about 30%, about 35%, about 40%, about 45%, about 50%, about 55%, about 60%, about 65%, about 70%, about 75%, about 80%, about 90%, or about 95%. In one embodiment, the natural pozzolan may be present in an amount in the range of from about 5% to about 99% by weight of cementitious components. In another embodiment, the natural pozzolan may be present in an amount in the range of from about 5% to about 80% by weight of cementitious components. In yet another embodiment, the natural pozzolan may be present in an amount in the range of from about 10% to about 50% by weight of cementitious components. In yet another embodiment, the natural pozzolan may be present in an amount in the range of from about 25% to about 50% by weight of cementitious components. One of ordinary skill in the art, with the benefit of this disclosure, will recognize the appropriate amount of the natural pozzolan to include for a chosen application.

[0025] The water that may be used in embodiments of the cement compositions may include, for example, freshwater, saltwater (*e.g.*, water containing one or more salts dissolved therein), brine (*e.g.*, saturated saltwater produced from subterranean formations), seawater, or combinations thereof. Generally, the water may be from any source, provided that the water does not contain an excess of compounds that may undesirably affect other components in the cement composition. In some embodiments, the water may be included in an amount sufficient to form a pumpable slurry. In some embodiments, the water may be included in the cement compositions of the present invention in an amount in the range of about 40% to about 200% by weight of cementitious components. In some embodiments, the water may be included in an amount in the range of about 40% to about 150% by weight of cementitious components. One of ordinary skill in the art, with the benefit of this disclosure, will recognize the appropriate amount of water to include for a chosen application.

[0026] Embodiments of the cement compositions may further comprise a source of calcium ions, such as lime. In certain embodiments, the source of calcium ions may include hydrated lime. The source of calcium ions may be included in embodiments of the cement compositions, for example to, form a hydraulic composition with other components of the cement compositions, such as the pumice, fly ash, slag, and/or shale. Where present, the lime may be included in the cement compositions in an amount sufficient for a particular application. In some embodiments, the lime may be present in an amount in the range of from about 1% to about 40% by weight of cementitious components. For example, the lime may be present in an amount of about 5%, about 10%, about 15%, about 20%, about 25%, about 30%, or about 35%. In one embodiment, the lime may be present in an amount in the range of from about 5% to about 20% by weight of cementitious components. One of ordinary skill in the art, with the benefit of this disclosure, will recognize the appropriate amount of the lime to include for a chosen application.

[0027] Embodiments of the acid-soluble cement compositions may further comprise an acid-soluble filler. The acid-soluble filler may be used, for example, in compositions that comprise Portland cement with the acid-soluble filler providing an acid-soluble component so that the compositions can be dissolved and removed. In an embodiment, the acid-soluble filler is present in a cement composition comprising a Sorel cement. Examples of suitable acid-soluble filler include dolomite, magnesium carbonate, calcium carbonate, and zinc carbonate. Where used, the acid-soluble filler may present in the acid-soluble cement composition in an amount of from about 0.1% to about 300% by weight of the cementitious component. In an embodiment, the acid-soluble filler is present in an amount of from about 50% to about 400% by weight of the cementitious component. In an embodiment, the acid-soluble filler is present in an amount of from about 100% to about 300% by weight of the cementitious component. One of ordinary skill in the art, with the benefit of this disclosure, will recognize the appropriate amount of the acid-soluble filler to include for a chosen application.

[0028] Embodiments of the acid-soluble cement compositions may further comprise fly ash. A variety of fly ashes may be suitable, including fly ash classified as Class C and Class F fly ash according to American Petroleum Institute, API Specification for Materials and Testing for Well Cements, API Specification 10, Fifth Ed., July 1, 1990. Class C fly ash comprises both silica and lime so that, when mixed with water, it should set to form a

hardened mass. Class F fly ash generally does not contain sufficient lime, so an additional source of calcium ions is required for the Class F fly ash to form a hydraulic composition. In some embodiments, lime may be mixed with Class F fly ash in an amount in the range of about 0.1% to about 25% by weight of the fly ash. In some instances, the lime may be hydrated lime. Suitable examples of fly ash include, but are not limited to, POZMIX[®] A cement additive, commercially available from Halliburton Energy Services, Inc., Duncan, Oklahoma.

[0029] Where present, the fly ash generally may be included in the acid-soluble cement compositions in an amount sufficient to provide the desired compressive strength, density, and/or cost. In some embodiments, the fly ash may be present in the cement compositions of the present invention in an amount in the range of about 5% to about 75% by weight of cementitious components. In some embodiments, the fly ash may be present in an amount in the range of about 10% to about 60% by weight of cementitious components. One of ordinary skill in the art, with the benefit of this disclosure, will recognize the appropriate amount of the fly ash to include for a chosen application.

[0030] Embodiments of the acid-soluble cement compositions may further comprise a slag cement. In some embodiments, a slag cement that may be suitable for use may comprise slag. Slag generally does not contain sufficient basic material, so slag cement may further comprise a base to produce a hydraulic composition that may react with water to set to form a hardened mass. Examples of suitable sources of bases include, but are not limited to, sodium hydroxide, sodium bicarbonate, sodium carbonate, lime, and combinations thereof.

[0031] Where present, the slag cement generally may be included in the acid-soluble cement compositions in an amount sufficient to provide the desired compressive strength, density, and/or cost. In some embodiments, the slag cement may be present in the cement compositions of the present invention in an amount in the range of about 0.1% to about 99% by weight of cementitious components. In some embodiments, the slag cement may be present in an amount in the range of about 5% to about 75% by weight of cementitious components. One of ordinary skill in the art, with the benefit of this disclosure, will recognize the appropriate amount of the slag cement to include for a chosen application.

[0032] Embodiments of the acid-soluble cement compositions may further comprise metakaolin. Generally, metakaolin is a white pozzolan that may be prepared by heating kaolin clay, for example, to temperatures in the range of about 600°C to about 800°C. In

some embodiments, the metakaolin may be present in the cement compositions of the present invention in an amount in the range of about 5% to about 95% by weight of cementitious components. In some embodiments, the metakaolin may be present in an amount in the range of about 10% to about 50% by weight of cementitious components. One of ordinary skill in the art, with the benefit of this disclosure, will recognize the appropriate amount of the metakaolin to include for a chosen application.

[0033] Embodiments of the acid-soluble cement compositions may further comprise shale. Among other things, shale included in the cement compositions may react with excess lime to form a suitable cementing material, for example, calcium silicate hydrate. A variety of shales may be suitable, including those comprising silicon, aluminum, calcium, and/or magnesium. An example of a suitable shale comprises vitrified shale. Suitable examples of vitrified shale include, but are not limited to, PRESSUR-SEAL FINE LCM material and PRESSUR-SEAL COARSE LCM material, which are commercially available from TXI Energy Services, Inc., Houston, Texas. Generally, the shale may have any particle size distribution as desired for a particular application. In certain embodiments, the shale may have a particle size distribution in the range of about 37 micrometers to about 4,750 micrometers.

[0034] Where present, the shale may be included in the acid-soluble cement compositions of the present invention in an amount sufficient to provide the desired compressive strength, density, and/or cost. In some embodiments, the shale may be present in the cement compositions of the present invention in an amount in the range of about 5% to about 75% by weight of cementitious components. In some embodiments, the shale may be present in an amount in the range of about 10% to about 35% by weight of cementitious components. One of ordinary skill in the art, with the benefit of this disclosure, will recognize the appropriate amount of the shale to include for a chosen application.

[0035] Embodiments of the acid-soluble cement compositions may further comprise zeolite. Zeolites generally are porous alumino-silicate minerals that may be either a natural or synthetic material. Synthetic zeolites are based on the same type of structural cell as natural zeolites, and may comprise aluminosilicate hydrates. As used herein, the term "zeolite" refers to all natural and synthetic forms of zeolite. Examples of suitable zeolites are described in more detail in U.S. Patent No. 7,445,669. An example of a suitable source of zeolite is available from the C2C Zeolite Corporation of Calgary, Canada. In some embodiments, the

zeolite may be present in the cement compositions of the present invention in an amount in the range of about 5% to about 65% by weight of cementitious components. In certain embodiments, the zeolite may be present in an amount in the range of about 10% to about 40% by weight of cementitious components. One of ordinary skill in the art, with the benefit of this disclosure, will recognize the appropriate amount of the zeolite to include for a chosen application.

[0036] Embodiments of the acid-soluble cement compositions may further comprise a set retarding additive. As used herein, the term "set retarding additive" refers to an additive that retards the setting of the acid-soluble cement compositions of the present invention. Examples of suitable set retarding additives include, but are not limited to, ammonium, alkali metals, alkaline earth metals, metal salts of sulfoalkylated lignins, organic acids (e.g., hydroxycarboxy acids), copolymers that comprise acrylic acid or maleic acid, and combinations thereof. One example of a suitable sulfoalkylate lignin comprises a sulfomethylated lignin. Suitable set retarding additives are disclosed in more detail in United States Patent No. Re. 31,190. Suitable set retarding additives are commercially available from Halliburton Energy Services, Inc. under the trademarks HR[®]4, HR[®]5, HR[®]7, HR[®]12, HR[®]15, HR[®]25, HR[®]601, SCR[™] 100, and SCR[™] 500 retarders. Generally, where used, the set retarding additive may be included in the cement compositions of the present invention in an amount sufficient to provide the desired set retardation. In some embodiments, the set retarding additive may be present in the cement compositions of the present invention an amount in the range of about 0.1% to about 5% by weight of cementitious components. One of ordinary skill in the art, with the benefit of this disclosure, will recognize the appropriate amount of the set retarding additive to include for a chosen application.

[0037] Optionally, other additional additives may be added to the acid-soluble cement compositions of the present invention as deemed appropriate by one skilled in the art, with the benefit of this disclosure. Examples of such additives include, but are not limited to, strength-retrogression additives, set accelerators, weighting agents, lightweight additives, gas-generating additives, mechanical property enhancing additives, lost-circulation materials, filtration-control additives, dispersants, fluid loss control additives, defoaming agents, foaming agents, oil-swellable particles, water-swellable particles, thixotropic additives, and combinations thereof. Specific examples of these, and other, additives include crystalline

silica, amorphous silica, fumed silica, salts, fibers, hydratable clays, microspheres, rice husk ash, elastomers, elastomeric particles, resins, latex, combinations thereof, and the like. A person having ordinary skill in the art, with the benefit of this disclosure, will readily be able to determine the type and amount of additive useful for a particular application and desired result.

[0038] As will be appreciated by those of ordinary skill in the art, the acid-soluble cement compositions of the present invention may be used in subterranean operations in accordance with embodiments of the present invention. Without limitation, the cement composition may be used to seal off one or more subterranean zones from a well bore; to plug a void or crack in a conduit disposed in the well bore; to plug a void or crack in a cement sheath disposed in the well bore; to plug an opening between the cement sheath and the conduit; to prevent the loss of fluid from the well bore into loss circulation zones such as a void, vug, or fracture; to form an annular plug; to isolate a gravel packed interval of the well bore; or combinations thereof. In an embodiment, the acid-soluble cement composition may be used to form a selectively removable barrier (*e.g.*, a plug, a seal, etc.) in a subterranean formation.

[0039] An example of a method of the present invention comprises placing an acid-soluble cement composition in a subterranean formation, and allowing the acid-soluble cement composition to set in the formation. It is intended to be understood that the phrase "placing an acid-soluble cement composition in the subterranean formation" encompasses placement of the cement composition in the well bore and/or placement of the cement composition in rock surrounding the well bore with the well bore penetrating the subterranean formation. The cement composition should form a hardened mass in the subterranean formation. The hardened mass can be left in the subterranean formation permanently or can be removed. Removal of the hardened mass may be desired so that the subterranean formation can be utilized in subsequent hydrocarbon production in accordance with embodiments of the present invention. In an embodiment, removal of the hardened mass includes contacting the hardened mass with an aqueous acid composition to dissolve the hardened mass. The aqueous acid composition may include, for example, from about 7.5% to about 28% hydrochloric acid by weight of the composition. In an embodiment, the aqueous acid composition includes hydrochloric acid in an amount of about 15% by weight.

[0040] To facilitate a better understanding of the present invention, the following examples of certain aspects of some embodiments are given. In no way should the following examples be read to limit, or define, the scope of the invention.

EXAMPLE 1

[0041] A series of acid-soluble cement compositions was prepared at room temperature and subjected to crush strength and solubility testing. Each of the samples contained sufficient water to provide the density provided in the table below and comprised various quantities of Class H Portland cement, Holcim CKD, and/or calcium carbonate, as indicated in the table below.

[0042] Solubility Testing: For the solubility testing, each sample was poured into a 2-inch [0.0508 m] cube and allowed to cure in a water bath at 150°F [65.56 °C] for either 48 hours (Samples 1-5) or 72 hours (Samples 6-10). After curing, the sample cubes are placed in an 80°F [26.67 °C] water bath for at least 30 minutes and then weighed to determine an initial weight. Each sample cube was then submerged in 2,000 milliliters of a 15% by weight hydrochloric acid solution in a 3,000 milliliter beaker. The sample cube was supported in the acid solution above a magnetic stir bar. The magnetic stir bar was rotated to create a slight vortex on the surface of the acid solution. After 30 minutes, the sample cube was removed from the acid solution and weighted to determine a final weight. The acid solubility of each composition was calculated by the following formula:

$$\text{Acid Solubility} = \text{Final Weight} / (\text{Initial Weight} - \text{Final Weight}) \times 100$$

[0043] Crush Strength Testing: For the crush strength testing, each sample was poured into a 2-inch cube [0.0508 m], allowed to cure in a water bath at 150°F [65.56 °C] for 48 hours (Samples 1-5) or 72 hours (Samples 6-10), and then crushed. The crush strengths were determined using a Tinius Olson tester in accordance with API Specification 10.

[0044] The results of the tests are set forth in the table below. In the following table, percent by weight is based on the weight of the cement and the CKD in the samples.

TABLE 1
Crush Strength Tests:
Cement, CKD, and CaCO₃

Sample	Density (ppg) [kg/m ³]	Portland Cement (% by wt)	CKD (% by wt)	CaCO ₃ (% by wt)	Dissolution Time in 15% HCl (min)	Acid Solubility (%)	Crush Strength (psi) [kPa]	
							48 Hr	72 Hr
1	15 [1797]	75	25	100	30	82.72	736 [5075]	--
2	15 [1797]	50	50	100	30	99.01	523 [3606]	--
3	15 [1797]	25	75	100	30	99.88	353 [2434]	--
4	15 [1797]	0	100	100	20	99.25	67.2 [463]	--
5	15 [1797]	100	0	100	30	66.46	1004 [6922]	--
6	14.5 [1737]	75	25	300	30	90.97	--	152 [1048]
7	14.5 [1737]	50	50	300	30	92.61	--	108 [745]
8	14.5 [1737]	25	75	300	30	93.55	--	61 [421]
9	14.5 [1737]	0	100	300	30	99.38	--	20 [138]
10	14.5 [1737]	100	0	300	30	93.45	--	188 [1296]

[0045] Example 1 thus indicates that acid-soluble cement compositions containing from 25% to 100% CKD by weight, from 0% to 75% Portland cement by weight, and from 100% to 300% calcium carbonate by weight may have properties suitable for use in acid-soluble operations.

EXAMPLE 2

[0046] An additional series of acid-soluble cement compositions was prepared and subjected to thickening time, force resistance, and rheological tests. Each of the samples contained sufficient water to provide the density provided in the table below and comprised various quantities of Class H Portland cement, Holcim CKD, calcium carbonate, a dispersant (CFRTM-3 cement friction reducer), and/or a set retarding additive, as indicated in the table below. In the following tables, percent by weight is based on the weight of the cement and the CKD in the samples.

[0047] The samples were prepared at room temperature with thickening time tests conducted at 140°F [60°C] on a portion of each composition in accordance with API Specification 10. The crush strength of Sample 12 was determined by pouring the sample into a 2-inch [0.0508 m] cube, allowing it to cure in a water bath at 160°F [71.1 °C] for 72 hours, and then crushing the cured cube. The crush strength was determined using a Tinius Olson tester in accordance with API Specification 10. The results of the thickening time and force resistance tests are provided in the table below.

TABLE 2
Thickening Time Tests:
Cement, CKD, and CaCO₃

Sample	Density (ppg) [kg/m ³]	Portland Cement (% by wt)	CKD (% by wt)	CaCO ₃ (% by wt)	Dispersant (% by wt)	Retarder (% by wt)	Thickening Time to 70 bc (hr:min)	72-Hr Crush Strength (psi) [kPa]
11	15 [1797]	50	50	100	--	0.25% HR [®] -5	2:31	--
12	15 [1797]	50	50	100	--	0.5% HR [®] -5	3:27	545 [3758]
13	16 [1917]	75	25	100	0.5	0.5% SCR-5 TM	1:41	--
14	16 [1917]	75	25	100	--	1% HR [®] -12	8:42	--

Bc = Bearden units of consistency

[0048] For the rheological tests, additional portions of the acid-soluble cement compositions were conditioned in an atmospheric consistometer to the test temperature. After conditioning, the rheology of the compositions was determined using a Fann Model 35 viscometer at the temperature indicated in the table below using a bob and sleeve and spring #1 in accordance with the procedure set forth in API Specification 10. The results of the rheological tests are set forth in the table below. In the following table, percent by weight is based on the weight of the cement and the CKD in the samples.

TABLE 3
Rheological Tests:
Cement, CKD, and CaCO₃

Sample	Density (ppg) [kg/m ³]	Portland Cement (% by wt)	CKD (% by wt)	CaCO ₃ (% by wt)	Dispersant (% by wt)	Retarder (% by wt)	Temp. (°F) [°C]	Rotations Per Minute						
								600	300	200	100	60	30	6
12	15 [1797]	50	50	100	--	0.5 % HR®-5	80 [26.7]	76	41	30	18	14	9	6
							140 [60]	48	27	21	15	12	9	8
13	16 [1917]	75	25	100	0.5	0.5% SCR-5™	80 [26.7]	167	79	54	27	16	8	2
							140 [60]	52	21	12	6	4	2	1
14	16 [1917]	75	25	100	--	1% HR®-12	80 [26.7]	207	115	80	47	33	22	12
							140 [60]	98	47	32	18	12	8	4

[0049] Example 2 thus indicates that acid-soluble cement compositions containing from 25% to 50% CKD by weight, from 50% to 75% Portland cement by weight, and 100% calcium carbonate by weight may have properties suitable for use in acid-soluble operations.

EXAMPLE 3

[0050] An additional acid-soluble cement composition was prepared to determine force resistance properties of compositions comprising pumicite. The composition contained sufficient water to provide the density provided in the table below and comprised Class H Portland cement, 200-mesh pumicite, calcium carbonate, a set retarding additive (HR[®]-5 retarder), and hydrated lime, as indicated in the table below. For the acid solubility testing, the composition was poured into a 2-inch [0.0508 m] cube and cured at 180°F [82.2°C] for 24 hours. The acid solubility of the composition was then determined by submerging the cured cube in a 15% by weight hydrochloric acid solution in accordance with the procedure described above in Example 1. For the crush strength testing, the composition was poured into a 2-inch [0.0508 m] cube, allowed to cure in a water bath for 24 hours at 180°F [82.2°C], and then crushed. The 24-hour crush strength was determined using a Tinius Olson tester in accordance with API Specification 10. The results of the tests are set forth in the table below. In the following table, percent by weight is based on the weight of the cement and the CKD in the samples.

TABLE 4
Crush Strength Tests:
Cement, Pumicite, and CaCO₃

Sample	Density (ppg) [kg/m³]	Portland Cement (% by wt)	Pumicite (% by wt)	CaCO₃ (% by wt)	Retarder (% by wt)	Hydrated Lime (% by wt)	Dissolution Time in 15% HCl (min)	Acid Solubility (%)	24-Hr Crush Strength (psi) [kPa]
15	15 [1797]	50	50	100	0.5% HR [®] -5	5	30	98.62	1400 [9652]

[0051] Example 3 thus indicates that acid-soluble cement compositions containing Portland cement, pumicite, and calcium carbonate may have properties suitable for use in acid-soluble operations.

EXAMPLE 4

[0052] An additional series of acid-soluble cement compositions was prepared at room temperature to determine force resistance properties of compositions comprising Sorel cement (e.g., a mixture of magnesium chloride and magnesium oxide), CKD, and/or pumicite. Each of the samples contained water, magnesium chloride (C-TEK), magnesium oxide (THERMATEK™ LT additive), Holcim CKD, 200-mesh pumicite, and/or hydrated lime, as indicated in the table below. The crush strength of the compositions was determined by pouring each composition into a 2-inch [0.0508 m] cube, allowing the cube to cure in a water bath at 140°F [60°C] for either 24 or 48 hours, and then crushing the cured cube. The crush strengths were determined using a Tinius Olson tester in accordance with API Specification 10. The results of the tests are set forth in the table below.

TABLE 5
Crush Strength Tests:
Sorel Cement, CKD, and/or Pumicite

Sample	Water (g)	MgCl ₂ (g)	MgO (g)	CKD (g)	Pumicite (g)	Hydrated Lime (g)	Crush Strength (psi) [kPa]	
							24 Hr	72 Hr
16	200	300	300	--	--	--	3460 [23856]	--
17	200	300	285	15	--	--	--	2430 [16754]
18	200	300	270	30	--	--	--	2280 [15720]
19	200	300	225	75	--	--	1116 [7695]	--
20	200	200	225	12.5	12.5	10	--	1822 [12562]
21	200	300	300	75	--	--	1864 [12851]	--

22	200	300	285	--	15	--	3080 [21235]	--
23	200	300	270	--	30	--	2790 [19236]	--
24	200	300	225	--	75	--	2360 [16271]	--
25	200	300	225	--	75	7.5	2360 [16271]	--

[0053] Example 4 thus indicates that acid-soluble cement compositions containing Sorel cement, cement kiln dust, and/or pumicite may have properties suitable for use in acid-soluble operations.

EXAMPLE 5

[0054] An additional series of acid-soluble cement compositions was prepared at room temperature to determine force resistance properties of lightweight compositions comprising Sorel cement (e.g., a mixture of magnesium chloride and magnesium oxide) and CKD. Each of the samples contained water, magnesium chloride (C-TEK additive), magnesium oxide (THERMATEK™ LT additive), Holcim CKD, a set retarding additive (R-TEK inhibitor), and glass bubbles (HGS 2000 glass bubbles), as indicated in the table below. The crush strength of the compositions was determined by pouring each composition into a 2-inch [0.0508 m] cube, allowing the cube to cure in a water bath at 140°F [60°C] for 24 hours, and then crushing the cured cube. The crush strengths were determined using a Tinius Olson tester in accordance with API Specification 10. The results of the tests are set forth in the table below.

TABLE 6
Crush Strength Tests:
Sorel Cement and CKD

Sample	Density (ppg) [kg/m ³]	Water (g)	MgCl ₂ (g)	MgO (g)	CKD (g)	Retarder (g)	Glass Bubbles (g)	24-Hr Crush Strength (psi) [kPa]
26	11.23 [1346]	200	300	300	--	18	50	923 [6364]
27	10.84 [1299]	200	300	225	75	18	50	663 [4571]

[0055] Example 5 thus indicates that acid-soluble cement compositions having a lightweight and containing Sorel cement and cement kiln dust may have properties suitable for use in acid-soluble operations.

EXAMPLE 6

[0056] An additional series of acid-soluble cement compositions was prepared at room temperature and subjected to thickening time tests at 140°F in accordance with API Specification 10. Each of the samples contained water, magnesium chloride (C-TEK additive), magnesium oxide (THERMATEK™ LT additive), Holcim CKD, and a retarder (R-TEK inhibitor) as indicated in the table below. The results of the tests are set forth in the table below.

TABLE 7**Thickening Time Tests: Sorel Cement and CKD**

Sample	Water (g)	MgCl₂ (g)	MgO (g)	CKD (g)	Retarder (g)	Thickening Time to 70 bc (hr:min)
28	200	300	225	75	5	00:36
29	200	300	225	75	9	1:13
30	200	300	225	75	18	1:11

Bc = Bearden units of consistency

[0057] Example 6 thus indicates that acid-soluble cement compositions containing Sorel cement and cement kiln dust may have properties suitable for use in acid-soluble operations.

[0058] Therefore, the present invention is well adapted to attain the ends and advantages mentioned as well as those that are inherent therein. The particular embodiments disclosed above are illustrative only, as the present invention may be modified and practiced in different but equivalent manners apparent to those skilled in the art having the benefit of the teachings herein. Although individual embodiments are discussed, the invention covers all combinations of all those embodiments. Furthermore, no limitations are intended to the details of construction or design herein shown, other than as described in the claims below. It is therefore evident that the particular illustrative embodiments disclosed above may be altered or modified and all such variations are considered within the scope of the present invention. While compositions and methods are described in terms of “comprising,” “containing,” or “including” various components or steps, the compositions and methods can also “consist essentially of” or “consist of” the various components and steps. Whenever a numerical range with a lower limit and an upper limit is disclosed, any number and any included range falling within the range is specifically disclosed. In particular, every range of values (of the form, “from about a to about b,” or, equivalently, “from approximately a to b,” or, equivalently, “from approximately a-b”) disclosed herein is to be understood to set forth every number and range encompassed within the broader range of values. Also, the terms in the claims have their plain, ordinary meaning unless otherwise explicitly and clearly defined by the patentee.

CLAIMS:

1. A method of cementing comprising:
placing an acid-soluble cement composition in a subterranean formation, the acid-soluble cement composition comprising:
hydraulic cement,
a component selected from the group consisting of cement kiln dust, pumicite, and a combination thereof, and
water;
allowing the acid-soluble cement composition to set; and
contacting the set acid-soluble cement composition with an acid to dissolve the set acid-soluble cement composition.
2. A method according to claim 1 wherein the hydraulic cement comprises a hydraulic cement selected from the group consisting of a Portland cement, a pozzolana cement, a gypsum cement, a high alumina content cement, a slag cement, a silica cement, and any combination thereof.
3. A method according to claim 1 wherein the hydraulic cement comprises a Sorel cement.
4. A method according to claim 1 wherein the hydraulic cement comprises a magnesium oxide and a magnesium chloride.
5. A method according to any one of claims 1 to 4 wherein the component comprises the cement kiln dust in an amount of about 20% to about 95% by weight of cementitious components in the acid-soluble cement composition.
6. A method according to any one of claims 1 to 4 wherein the component comprises the pumicite in an amount of about 20% to about 95% by weight of cementitious components in the acid-soluble cement composition.

- 26 -

7. A method according to any one of claims 1 to 6 wherein the acid-soluble cement composition further comprises an acid-soluble filler.
8. A method according to claim 1 wherein the cement composition comprises:
Portland cement,
cement kiln dust,
an acid-soluble filler, and
water.
9. A method according to any one of claims 1 to 8 wherein the acid-soluble cement composition has a density of about 8 pounds per gallon [959 kilograms per cubic metre] to about 16 pounds per gallon [1917 kilograms per cubic metre].
10. A method according to any one of claims 1 to 9 wherein the hydraulic cement is present in an amount of about 5% to about 20% by weight of cementitious components.
11. A method according to any one of claims 1 to 10 wherein the acid-soluble cement composition further comprises a source of calcium ions.
12. A method according to any one claims 1 to 11 wherein the water is selected from the group consisting of freshwater, saltwater, brine, seawater, and any combination thereof.
13. A method according to any one of claims 1 to 12 wherein the water is present in an amount of about 40% to about 200% by weight of cementitious components.
14. A method according to any one of claims 1 to 13 wherein the acid-soluble cement composition further comprises hydrated lime in an amount of about 1% to about 40% by weight of cementitious components.
15. A method according to any one of claims 1 to 14 wherein the acid-soluble cement composition further comprises an additive selected from the group consisting of fly

- 27 -

ash, slag cement, metakaolin, shale, zeolite, crystalline silica, amorphous silica, fumed silica, salt, fiber, hydratable clay, microsphere, rice husk ash, elastomer, elastomeric particle, resin, latex, and any combination thereof.

16. A method according to any one of claims 1 to 15 wherein the acid-soluble cement composition further comprises an additive selected from the group consisting of a set retarding additive, a strength-retrogression additive, a set accelerator, a weighting agent, a lightweight additive, a gas-generating additive, a mechanical property enhancing additive, a lost-circulation material, a filtration-control additive, a dispersant, a fluid loss control additive, a defoaming agent, a foaming agent, an oil-swellable particle, a water-swellable particle, a thixotropic additive, and any combination thereof.

17. A method according to any one of claims 1 to 16 wherein contacting the set acid-soluble cement composition with an acid comprises contacting the set acid-soluble cement composition with an aqueous acid composition, wherein the acid comprises hydrochloric acid present in the aqueous acid composition in an amount of about 7.5% to about 28% by weight of the aqueous acid composition.

18. A method according to any one of claims 1 to 17 wherein acid-soluble cement composition is allowed to set in a lost circulation zone in the subterranean formation.

19. A method according to any one of claims 1 to 18 wherein the acid-soluble cement composition is allowed to set and form an annular plug in a well bore penetrating the subterranean formation.

20. A method according to claim 8 or any one of claims 9 to 19 when dependent on claim 8, wherein the cement kiln dust is present in an amount of about 20% to about 95% by weight of cementitious components.

- 28 -

21. A method according to claim 7 or claim 8 or any one of claims 9 to 20 when dependent on claim 7 or claim 8, wherein the acid-soluble filler comprises a material selected from the group consisting of dolomite, magnesium carbonate, calcium carbonate, zinc carbonate, and any combination thereof.