



(86) **Date de dépôt PCT/PCT Filing Date:** 2008/02/15
(87) **Date publication PCT/PCT Publication Date:** 2008/08/28
(45) **Date de délivrance/Issue Date:** 2015/12/08
(85) **Entrée phase nationale/National Entry:** 2009/09/23
(86) **N° demande PCT/PCT Application No.:** US 2008/002039
(87) **N° publication PCT/PCT Publication No.:** 2008/103289
(30) **Priorité/Priority:** 2007/02/16 (US60/902,025)

(51) **Cl.Int./Int.Cl. C08L 91/06** (2006.01)
(72) **Inventeurs/Inventors:**
LEMKE, DANIEL WAYNE, US;
THIEDE, MICHAEL C., US
(73) **Propriétaire/Owner:**
ELEVANCE RENEWABLE SCIENCES, INC., US
(74) **Agent:** SMART & BIGGAR

(54) **Titre : COMPOSITIONS DE CIRE ET LEURS PROCEDES DE FABRICATION**
(54) **Title: WAX COMPOSITIONS AND METHODS OF PREPARING WAX COMPOSITIONS**

(57) **Abrégé/Abstract:**

Described are morphology stable wax composition comprising the (trans)esterification product of a wax-forming composition comprising: (a) a triglyceride stock, a fatty acid stock, or a mixture thereof; and (b) a glycerol-based composition comprising glycerol, polyglycerol, or a mixture thereof. Methods of making the waxes are also described. The wax compositions may be used in candles, stack waxes, jell candles, cosmetics, food coatings, adhesives, board manufacturing (e.g., particle board and oriented strand board), urethane foams or coatings, alkyd coatings, coating formulation additives, printing additives, polymer processing agents, extrusion processing aids, polymer plasticizers, mold releases, polishes, and stick markers.



(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
28 August 2008 (28.08.2008)

PCT

(10) International Publication Number
WO 2008/103289 A1

(51) International Patent Classification:
C08L 91/06 (2006.01)

(74) Agent: **PIOLI, Janet, A.**; Brinks Hofer Gilson & Lione,
P.O. Box 10087, Chicago, IL 60610 (US).

(21) International Application Number:
PCT/US2008/002039

(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(22) International Filing Date:
15 February 2008 (15.02.2008)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/902,025 16 February 2007 (16.02.2007) US

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (*for all designated States except US*): **ELEVANCE RENEWABLE SCIENCES, INC.** [US/US];
3333 Warrenville Rd. Suite 218, Lisle, Illinois 60532 (US).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **LEMKE, Daniel, Wayne** [US/US]; 3277 Quimby Avenue SW, Cokato, Minnesota 55321 (US). **THIEDE, Michael, C.** [US/US]; 6740 Polaris Lane N, Maple Grove, Minnesota 55311 (US).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

(54) Title: WAX COMPOSITIONS AND METHODS OF PREPARING WAX COMPOSITIONS

(57) Abstract: Described are morphology stable wax composition comprising the (trans)esterification product of a wax-forming composition comprising: (a) a triglyceride stock, a fatty acid stock, or a mixture thereof; and (b) a glycerol-based composition comprising glycerol, polyglycerol, or a mixture thereof. Methods of making the waxes are also described. The wax compositions may be used in candles, stack waxes, jell candles, cosmetics, food coatings, adhesives, board manufacturing (e.g., particle board and oriented strand board), urethane foams or coatings, alkyd coatings, coating formulation additives, printing additives, polymer processing agents, extrusion processing aids, polymer plasticizers, mold releases, polishes, and stick markers.



WO 2008/103289 A1

**WAX COMPOSITIONS AND METHODS OF PREPARING WAX
COMPOSITIONS**

5

FIELD

10 The present invention relates generally to wax compositions and to methods of preparing wax compositions.

BACKGROUND

 Candles have been known and used for illumination since early civilization. For years, beeswax was commonly used as a natural wax for candles, cosmetics and food preservation sealing waxes. A typical candle is formed of a solid or semi-solid
15 body of combustible waxy material, such as paraffin wax or beeswax, and contains a combustible fibrous wick embedded within the waxy material. When the wick of a candle is lit, the generated heat melts the solid wax, and the resulting liquid flows up the wick by capillary action and is combusted. At present, although many advanced
20 illuminating devices are available, candles are still popularly used for decoration, as a scent-dispensing vehicle or on a special situation such as a holiday.

 Over one hundred years ago, paraffin came into existence, parallel with the development of the petroleum refining industry. Paraffin is simply the leftover residue from refining gasoline and motor oils. Paraffin was introduced as a
25 bountiful and low cost alternative to beeswax. In recent years, paraffin has become more costly and in less supply. Paraffin is presently the primary industrial wax for the following three uses: candles, cosmetics and sealing waxes.

 Conventional candles are made from a wax material, such as paraffin. Such candles typically emit a smoke and can produce a bad smell when burning. Many
30 people cannot accept such smell. In addition, a small amount of particles (“particles”) are often created when the candle burns. These particles may affect the health of a human when inhaled. Paraffin soot particles are similar to particles given

- 2 -

off by burning diesel fuel, which include a number of polycyclic aromatic hydrocarbons that have been deemed toxic air contaminants.

In addition to these issues, paraffin wax is diminishing in supply as consumer demand increases. New petroleum technology does not produce by-product petro-waxes. This decrease in supply requires importation of petroleum waxes. This coincides with a huge (\$2.5 billion) decorative candle market in the U.S..

There is a strong consumer need and demand for alternative natural waxes as an option to paraffin waxes that can be produced at a rate that is cost competitive with paraffin. Accordingly, it would be advantageous to have other materials that can be used to form clean burning base materials for forming candles. If possible, such materials would preferably be biodegradable and be derived from renewable raw materials. The candle base materials should preferably have physical characteristics, e.g., in terms of melting point, hardness and/or malleability, that permit the material to be readily formed into candles having a pleasing appearance and/or feel to the touch, as well as having desirable olfactory properties.

There are fundamental differences in the inherent properties of the renewable saturated triglycerides when they are compared to the petroleum based straight chain aliphatic hydrocarbons that make up paraffin wax. Triglycerides exhibit well-documented polymorphic behavior where as the aliphatic hydrocarbons of paraffin does not. Polymorphism means that there are multiple crystal forms of the material that can exist. In general under rapid cooling, less stable lower melting less dense crystals form initially, but given time and heat cycles the mobility of the molecules allow their rearrangement to higher melting, more stable and more dense crystal forms. This rearrangement can lead to the problems of cracking and blooming in candle produced from vegetable wax.

The inventions disclosed herein represent approaches to resolving the physical property limitations associated with vegetable and animal-based triglycerides when used as alternatives to paraffin waxes.

30

SUMMARY

It has been observed that hydrogenated soybean oil that is slowly cooled from a liquid state has an undesirable tendency to crack, is undesirably brittle, and

65902-229

3

tends to exhibit more “blooming” than is commercially acceptable. The incorporation of glycerol-based compositions, for example, through esterification or transesterification can stabilize the fat morphology, thereby limiting the transition of the fat from one crystal form to another. The resulting morphology stable waxes display, in various embodiments, reduced
5 cracking, friability, and bloom formation.

In one aspect, the invention relates to a morphology stable wax composition comprising the (trans)esterification product of a wax-forming composition comprising: (a) a triglyceride stock, a fatty acid stock, or a mixture thereof; and (b) a glycerol-based composition comprising 0 to 70 wt% glycerol; 20 to 40 wt% diglycerol; 5 to 30 wt%
10 triglycerol; 0 to 20 wt% tetraglycerol; 0 to 10 wt% pentaglycerol; 0 to 10 wt% hexaglycerol; 0 to 5 wt% heptaglycerol; and 0 to 5 wt% cyclic polyglycerol.

According to another aspect, the invention relates to a wax article comprising the morphology stable wax composition described herein.

According to yet another aspect, the invention relates to a method of making a
15 morphology stable wax composition comprising the steps of: (a) providing a composition comprising a triglyceride stock, a fatty acid stock, or a mixture thereof; (b) providing a glycerol-based composition comprising 0 to 70 wt% glycerol; 20 to 40 wt% diglycerol; 5 to 30 wt% triglycerol; 0 to 20 wt% tetraglycerol; 0 to 10 wt% pentaglycerol; 0 to 10 wt% hexaglycerol; 0 to 5 wt% heptaglycerol; and 0 to 5 wt% cyclic polyglycerol; and (c)
20 (trans)esterifying the composition of step (a) with the composition of step (b) to produce the morphology stable wax composition.

In many embodiments, the triglyceride stock comprises a vegetable oil. The vegetable oil may be partially- or fully-hydrogenated, or may be used without hydrogenation. Examples of vegetable oils include soybean oil, cottonseed oil, sunflower oil, canola oil,
25 rapeseed oil, corn oil, peanut oil, safflower oil, palm oil, palm oil, coconut oil, jatropha oil, algal oil, castor oil, or mixtures thereof.

65902-229

3a

In some embodiments, the triglyceride stock comprises animal-based oils such as tallow, fish oil, chicken fat (or yellow grease), or a mixture thereof. The animal-based oils may be partially- or fully-hydrogenated, or may be used without hydrogenation.

The triglyceride stock or fatty acid typically comprises a majority of the wax-forming composition, for example, typically ranging from about 60 wt% to about 99.9 wt% of the wax-forming composition.

The glycerol-based composition comprises species of glycerol and/or polyglycerol. In some embodiments, the glycerol-based composition comprises one or more polyglycerol species selected from the group consisting of diglycerol, triglycerol, tetraglycerol, pentaglycerol, and cyclic polyglycerol. The glycerol-based composition typically comprises about 0.1 wt% to about 35 wt% of the wax-forming composition or about 5 wt% to about 30 wt% of the wax-forming composition.

The (trans)esterification is typically conducted in the presence of a catalyst, for example, lithium, sodium, potassium, magnesium, calcium, oxide, methyl oxide, antimony oxides, hydroxide, carbonate, phosphate, phosphite, hypophosphite, and

- 4 -

salts thereof. Other examples include potassium hydroxide, sodium hydroxide, calcium hydroxide, or a combination thereof.

The morphology stable wax composition typically has a melting point ranging from about 43°C to about 121°C, or from about 51° C to about 72°C. In
5 some embodiments, the wax has a melting point and a congeal point that have a temperature difference of about 10°C or less or about 5°C or less.

In some embodiments, the wax-forming composition further comprises a diamine compound in order to alter the melting temperature of the wax. The diamine compound transamidates with the triglyceride stock in the wax-forming
10 composition. Useful diamine compounds include, for example, hexamethylene diamine, ethylene diamine, or a mixture thereof.

In some embodiments, the wax-forming compositions further comprise a diacid, polyacid, or anhydride (e.g., trimellitic anhydride). The acid or anhydride builds molecular weight with the polyglycerol during the transesterification reaction
15 adding flexibility to the resulting wax.

In another aspect, the invention provides a method of making a morphology stable wax composition. The method comprises the steps of:

(a) providing a composition comprising a triglyceride stock, a fatty acid stock, or a mixture thereof;

20 (b) providing a glycerol-based composition comprising glycerol, polyglycerol, or a mixture thereof; and

(c) (trans)esterifying the composition of step (a) with the composition of step (b).

The (trans)esterification reaction is typically conducted under an inert
25 atmosphere (e.g., nitrogen) in the presence of a catalyst and at an elevated temperature, for example, ranging from about 90°C to about 232°C.

Wax compositions of the invention are suitable for use in candles and other wax-based articles. Examples include candles, stack waxes, jell candles, cosmetic, food coating, adhesive, board manufacturing (e.g., particle board and oriented strand
30 board), urethane foams or coatings, alkyd coatings, coating formulation additive (e.g., paint, waterproof coatings, etc.), printing additives, polymer processing agent,

extrusion processing aid, polymer plasticizer, mold release, polish, and stick markers.

DETAILED DESCRIPTION

The invention relates to morphology stable wax compositions and to
5 methods of making the morphology stable wax compositions. In many
embodiments, the morphology stable wax compositions comprise a fat source (e.g.,
a triglyceride stock (hydrogenated soybean oil) or fatty acid, or mixture thereof) that
has been esterified or transesterified (i.e., (trans)esterified) with a glycerol-based
composition.

10 As employed herein, the term "triglyceride stock" is used to refer to
materials that comprise one or more triglyceride compounds. Commonly, the
triglyceride stock comprises a mixture of triglyceride compounds, which very often
are derivatives of C16 and/or C18 fatty acids. The triglyceride stock, whether altered
or not, are generally derived from various plant and animal sources, such as oil seed
15 sources. The term triglyceride stock includes, for example, (a) materials which have
not been altered after isolation; (b) materials which have been refined, bleached
and/or deodorized after isolation; (c) materials obtained by a process which includes
fractionation of a triglyceride oil; and, also, (d) oils obtained from plant or animal
sources and altered in some manner, for example through partial or full
20 hydrogenation.

It will be understood that a triglyceride stock may include a mixture of
triglycerides, and a mixture of triglyceride isomers. By the term "triglyceride
isomers," reference is meant to triglycerides which, although including the same
esterified carboxylic acid residues, may vary with respect to the location of the
25 residues in the triglyceride. For example, a triglyceride oil such as a vegetable oil
stock can include both symmetrical and unsymmetrical isomers of a triglyceride
molecule which includes two different fatty acyl chains (e.g., includes both stearate
and oleate groups).

As indicated above, any given triglyceride molecule includes glycerol
30 esterified with three carboxylic acid molecules. Thus, each triglyceride includes
three fatty acid residues. In general, oils extracted from any given plant or animal
source comprise a mixture of triglycerides, characteristic of the specific source. The

- 6 -

mixture of fatty acids isolated from complete hydrolysis of the triglycerides in a specific source is referred to herein as a "fatty acid profile." By the term "fatty acid profile" reference is made to the identifiable fatty acid residues in the various triglycerides. The distribution of specific identifiable fatty acids is characterized
5 herein by the amounts of the individual fatty acids as a weight percent (wt%) of the total mixture of fatty acids obtained from hydrolysis of the particular oil stock. The distribution of fatty acids in a particular oil or fat may be readily determined by methods known to those skilled in the art, such as by gas chromatography.

Palmitic acid ("16:0") and stearic acid ("18:0") are saturated fatty acids
10 and triglyceride acyl chains formed by the esterification of either of these acids do not contain any carbon-carbon double bonds. The nomenclature in the above abbreviations refers to the number of total carbon atoms in fatty acid followed by the number of carbon-carbon double bonds in the chain. Many fatty acids such as oleic acid, linoleic acid and linolenic acid are unsaturated (i.e., contain one or more
15 carbon-carbon double bonds). Oleic acid is an 18 carbon fatty acid with a single double bond (i.e., an 18:1 fatty acid), linoleic acid is an 18 carbon fatty acid with two double bonds or points of unsaturation (i.e., an 18:2 fatty acid), and linolenic is an 18 carbon fatty acid with three double bonds (i.e., an 18:3 fatty acid).

In many embodiments, the triglyceride stock comprises a vegetable oil. The
20 vegetable oil may be partially- or fully-hydrogenated, or may be used without hydrogenation. Examples include soybean oil, cottonseed oil, sunflower oil, canola oil, rapeseed oil, corn oil, olive oil, peanut oil, safflower oil, palm oil, coconut oil, jatropha oil, algal oil, castor oil, or mixtures thereof.

In some embodiments, the triglyceride stock comprises an animal-based oils
25 such as tallow, fish oil, chicken fat (or yellow grease), or a mixture thereof. The animal-based oils may be partially- or fully-hydrogenated, or may be used without hydrogenation.

In many embodiments high in soybean oil, the fatty acid profile of the triglyceride stock typically comprises predominantly fatty acids having 16 and 18
30 carbon atoms. The amount of shorter chain fatty acids, for example, fatty acids having 14 carbon atoms or less in the fatty acid profile of the triglycerides is generally low, for example, in some embodiments no more than about 1.0 wt%. The

- 7 -

triglyceride stock may include a moderate amount of saturated 16 carbon fatty acid, for example, typically about 14 wt% to about 25 wt%. Suitable triglyceride stocks may about 15 wt% to about 20 wt% saturated 16 carbon fatty acid.

In many embodiments high in soybean oil, the fatty acid profile of the triglyceride stock commonly includes a significant amount of C18 fatty acids. The fatty acid profile typically includes a mixture of saturated (18:0-stearic acid) and monounsaturated fatty acids (18:1). The unsaturated fatty acids are commonly monounsaturated fatty acids (18:1), such as oleic acid. In some embodiments, the triglycerides have a fatty acid profile which includes about 14 to 25 wt% 16:0 fatty acid; about 35 to 45 wt% 18:0 fatty acid; and about 35 to 45 wt% 18:1 fatty acid.

In embodiments comprising coconut oil, the fatty acid profile of the triglyceride stock may include up to about 15 wt% of fatty acids having 14 or less carbon atoms. Embodiments comprising palm oil may have up to about 50 wt% of fatty acids having 16 or less carbon atoms.

Also useful in the morphology stable waxes of the invention are tropical oils such as palm and coconut, which have fatty acid profiles that are different than those described above. Algae oils have a wider range of fatty acid composition including longer chain fatty acids. Castor oil would be different as well and contains predominantly ricolenic acid.

Useful triglyceride stocks for use in the wax compositions of the invention have generally been neutralized and bleached. The triglyceride stock may have been processed in other ways prior to use, e.g., via fractionation, hydrogenation, refining, and/or deodorizing. Preferably, the feedstock is a refined, bleached triglyceride stock. The processed feedstock material may be blended with one or more other triglyceride feedstocks to produce a material having a desired distribution of fatty acids, in terms of carbon chain length and degree of unsaturation. In some embodiments, the triglyceride stock is hydrogenated (e.g., partially- or fully-hydrogenated) to reduce the overall degree of unsaturation in the material and provide a triglyceride stock having physical properties which are desirable for a candle-making base material.

The triglyceride stock may be hydrogenated to obtain a desired set of physical characteristics (e.g., in terms of melting point, solid fat content and/or

- 8 -

Iodine value). The hydrogenation is typically carried out at elevated temperature, such as 400° F to 450° F (about 205° C to about 230 °C), and relatively low hydrogen pressure (e.g., no more than about 25 psi) in the presence of a hydrogenation catalyst. One example of a suitable hydrogenation catalyst, is a nickel catalyst, such as a powdered nickel catalyst provided as a 20-30 wt. % in a solid vegetable oil.

In an exemplary embodiment of the invention, the triglyceride stock comprises fully-hydrogenated soybean oil. Fully hydrogenated soybean oil typically has an iodine value (IV) that ranges from about 0 to about 5.

Glycerol-based compositions that are used in the present invention may be obtained from any suitable source. In many embodiments, the glycerol-based composition is derived from a renewable, natural source. Given the anticipated abundance of glycerol that is expected to be available as a byproduct of biodiesel production, naturally derived glycerol is expected to be abundant for the foreseeable future and may be used to form suitable glycerol-based compositions for use in the present invention.

In many embodiments, the glycerol-based composition comprises a majority of linear polymers of glycerol. Linear polymers of glycerol may be represented structurally by the formula:



where n ranges typically ranges from about 2 to about 10.

In addition to polyglycerol, the glycerol-based compositions typically also include glycerol and a minor amount of cyclic polyglycerol species.

Glycerol-based compositions may be characterized by their hydroxyl value. In many embodiments of the invention, the glycerol-based compositions have a hydroxyl value (i.e., OH value) that ranges from about 800 to about 1800. In other embodiments, the hydroxyl value ranges from about 1500 to about 1600. In some embodiments, the glycerol-based composition is fractionated to produce a desired distribution of glycerol polymers and a desired OH value.

In some embodiments, the glycerol-based composition comprises one or more polyglycerol species selected from the group consisting of diglycerol,

65902-229

- 9 -

triglycerol, tetraglycerol, pentaglycerol, and cyclic polyglycerol. In other embodiments, the glycerol-based composition comprises glycerol and one or more polyglycerol species selected from the group consisting of diglycerol, triglycerol, tetraglycerol, pentaglycerol, and cyclic polyglycerol.

5 In some embodiments, the glycerol-based composition comprises: about 75 wt% or greater total of polyglycerol species comprising diglycerol, triglycerol, and tetraglycerol; and up to about 10 wt% or less total of polyglycerol species of hexaglycerol and greater.

In some embodiments, the glycerol-based composition comprises about 20
10 wt% to about 40 wt% diglycerol. In some embodiments, the glycerol-based composition comprises about 5% to about 30 wt% triglycerol. In some embodiments, the glycerol-based composition comprises about 1 wt% to about 65 wt% glycerol. In some embodiments, the glycerol-based composition comprises about 1 wt% to about 20 wt% tetraglycerol. In some embodiments, the glycerol-
15 based composition comprises about 30 wt% to about 65 wt% glycerol.

Also useful are glycerol-based compositions comprising: (i) about 0 to about 70 wt% glycerol; about 20 to 40 wt% diglycerol; about 5 to 30 wt% triglycerol; about 0 to 20 wt% tetraglycerol; about 0 to 10 wt% pentaglycerol; about 0 to 10 wt% hexaglycerol; about 0 to 5 wt% hexaglycerol; and about 0 to 5 wt% cyclic
20 polyglycerol; (ii) about 55 to 65 wt% glycerol; about 20 to 30 wt% diglycerol; about 5 to 15 wt% triglycerol; about 1 to 10 wt% tetraglycerol; and up to about 5 wt% pentaglycerol; (iii) about 30 to 35 wt% glycerol; about 25 to 35 wt% diglycerol; about 15 to 20 wt% triglycerol; about 5 to 10 wt% tetraglycerol; up to about 5 wt% pentaglycerol; up to about 5 wt% hexaglycerol; and up to about 5 wt%
25 cyclic glycerol; or (iv) up to about 5 wt% glycerol; about 30 to 40 wt% diglycerol; about 20 to 30 wt% triglycerol; about 10 to 20 wt% tetraglycerol; about 5 to 15 wt% pentaglycerol; up to about 10 wt% hexaglycerol; up to about 10 wt% heptaglycerol and higher order oligomers; and up to about 5 wt% cyclic glycerol. Mixtures of the foregoing may also be used.

30 In an exemplary embodiment, the glycerol-based composition comprises about 60 wt% glycerol; about 24 wt% diglycerol; about 10 wt% triglycerol; about 5 wt% tetraglycerol; and about 1 wt% pentaglycerol. In another exemplary

embodiment, the glycerol-based composition comprises about 33 wt% glycerol; about 30 wt% diglycerol; about 18 wt% triglycerol; about 8 wt% tetraglycerol; about 4 wt% pentaglycerol; about 2 wt% hexaglycerol; and about 5 wt% cyclic glycerol.

In yet another exemplary embodiment, the glycerol-based composition comprises
5 about 3 wt% glycerol; about 37 wt% diglycerol; about 26 wt% triglycerol; about 14 wt% tetraglycerol; about 8 wt% pentaglycerol; about 6 wt% hexaglycerol; about 2 wt% heptaglycerol and higher order oligomers; and about 4 wt% cyclic glycerol.

Examples of processes suitable for the production of glycerol-based composition include the method reported in WO 2007/092407 entitled "Process
10 for Preparing Polyglycerol and Mixed Ethers" and the method reported in U.S. Patent No. 6,620,904 (Lemke) entitled "Processes for Preparing Linear Polyglycerols and Polyglycerol Esters". The distribution of polymers of glycerol in the glycerol-based composition may represent, for example, any of the mixtures typically achieved by an alkali catalyzed process.

15 Examples of polyglycerol compositions include those commercially available under the trade designation "POLYGLYCEROL-3" from Solvay. POLYGLYCEROL-3 comprises about 15 to 30 wt% diglycerol; about 35 to 55 wt% triglycerol; about 10 to 25 wt% tetraglycerol; up to about 10 wt% pentaglycerol; and up to about 5 wt% hexaglycerol and higher order oligomers.

20 In many embodiments, glycerol-based composition is incorporated into a triglyceride stock or fatty acid composition (e.g., hydrogenated soybean fatty acid, coconut fatty acid, etc.) by esterification or transesterification (i.e., (trans)esterification) to yield a first composition.

Polyglycerol compositions may be incorporated into the triglyceride stock
25 and/or fatty acid composition in a variety of known processes including transesterification, esterification, or by a combination of these processes. Suitable catalysts for the reaction include lithium, sodium, potassium, magnesium, calcium, etc. oxide, methyl oxide, antimony oxides, hydroxide, carbonate, phosphate, phosphite, hypophosphite, etc. salts. Potassium, sodium, and calcium hydroxides or
30 oxides are preferred catalysts. Appropriate operating conditions using such catalysts are known to those skilled in the art.

- 11 -

The morphology stable wax composition of the invention typically comprises a majority by weight of a triglyceride, fatty acid, or mixture thereof, and a minor amount of the glycerol-based composition. The amount of the glycerol-based composition that is incorporated typically ranges from about 0.1 wt% to about 35 wt%, for example, more typically ranging from about 5 wt% to about 30 wt%. A range of about 8 wt% to about 20 wt% is typical for many applications. The remainder of the mixture typically comprises a triglyceride stock, fatty acids, or mixtures thereof. In many implementations, the triglyceride stock comprises a majority of the mixture, typically about 60 wt% to about 99.9 wt%, for example, about 70 wt% to about 95 wt%.

(Trans)esterification causes the hydroxyl number of the polyglycerol composition to be reduced as the triglyceride stock and/or fatty acid reacts with the polyglycerol composition to form ester groups. In many embodiments, the resulting wax has a hydroxyl number that is about 600 mg KOH/gram or less, more typically about 200 mg KOH/gram or less.

In one exemplary embodiment about 10 wt% glycerol composition is mixed with about 90 wt% hydrogenated soybean oil and about 500 ppm sodium hydroxide. The mixture is then heated to a temperature of about 230°C under a nitrogen sparge. The mixture is then held at temperature until it turns clear, and then for about 0.5 hours additional time. The resulting composition is then cooled to about 100°C fairly quickly, followed by cooling at slower rate. For example, the mixture may be cooled to less than about 100°C, transferred to a container (e.g., a jar), and the container placed into a preheated oven at about 80°C. Turning off the oven allows the composition to cool slowly to room temperature. The resulting product is a homogeneous wax that is free of bloom and cracks, and is resilient to chipping when hit or picked at.

Stack candles that were prepared from blends comprising hydrogenated soybean oil and the transesterification product of hydrogenated soybean oil and glycerol or the transesterification product of hydrogenated soybean oil and a glycerol/polyglycerol composition showed that the candles prepared with glycerol yielded free glycerol in the hot wax when the candle was burned, whereas the

- 12 -

candles that were prepared from glycerol/polyglycerol showed good phase stability with no apparent phase separation.

It was also observed that the congeal point of the wax prepared with glycerol/polyglycerol was about 5°C cooler than the melting point of the wax. This is desirable since it is similar to the performance of paraffin waxes. By contrast, fully-hydrogenated soybean oil typically has a congealing point that is about 12°C cooler than its melting point. Accordingly, embodiments of the morphology stable wax compositions of the invention have a congeal point that is about 10°C cooler (or less) than the melting point of the wax, or about 8°C cooler (or less) than the melting point of the wax, or about 6°C cooler (or less) than the melting point of the wax, or about 5°C cooler (or less) than the melting point of the wax.

Wax compositions of the invention may be alone or may be used in blends with other waxes. Examples of waxes include petroleum-based waxes (e.g., paraffin wax), or other esters, amides, triglyceride waxes with varying levels of hydrogenation, metathesized waxes, fatty acids with varying levels of hydrogenation, fatty acid soaps (sodium, potassium, etc), alkyl esters (methyl ester), metathesis side streams, FFA, FAME, FAEE, and the like.

Morphology stable waxes of the invention may be produced using batch or continuous processes. In a continuous process the raw materials are continuously injected and product is continuously removed. For example, polyglycerol and triglyceride can be continuously injected into a high sheer mixer and heated to 100°C to 275°C, preferably between 230°C to 260°C. The mixture is held either by the volume of the mixer or by the length of the heat exchanger and is allowed to transesterify. The catalyst, pumping rate of the raw materials into the mixer, the sheer applied by the mixer and the heat exchanger volume and hold times may be varied to optimize the rate of through-put through the system.

In some embodiments of the invention, a morphology stable wax of the invention is prepared in a one step process by mixing glycerol, triglyceride stock (e.g., hydrogenated soybean oil) and/or a fatty acid composition along with a transesterification catalyst (e.g., potassium hydroxide or calcium hydroxide, etc.). The resulting composition is then heated (e.g., to a temperature of about 200°C to 250°C) under nitrogen sparge and vacuum (e.g., 150 mmHg to atmospheric). Under

- 13 -

these conditions, at least a portion of the glycerol polymerizes to form polyglycerol. The resulting polyglycerol reacts with the triglyceride and/or fatty acid composition in an esterification/transesterification reaction to provide a morphology stable wax of the invention. Typically, the amount of triglyceride or fatty acid in the composition ranges from about 80 wt% to about 93 wt%, and the amount of glycerol ranges from about 7 wt% to about 20 wt%. The amount of transesterification catalyst typically ranges from about 200 to about 2000 ppm.

In an exemplary embodiment, glycerol (e.g., about 12 wt%), hydrogenated soybean oil (e.g., about 87.8 wt%), and potassium hydroxide (e.g., about 0.2 wt%) are charged into a reaction vessel. Under nitrogen sparge, the charge is heated to about 230°C and vacuum is applied (e.g., to about 160 mmHg). The OH value of the composition is monitored and the morphology stable wax is considered functional when the OH has dropped by about 20-50 units, preferably about 20-30 units.

In some embodiments of the invention, the melting point of the wax may be increased by modifying the process to include a diamine compound. Examples of suitable diamine compounds include hexamethylene diamine and ethylene diamine, although other diamine compounds may also be suitable. Diamine may be added to the composition until the desired melting point is achieved. Typical high melting points waxes prepared in this manner have melting points ranging from about 76°C to about 122°C.

In some embodiments of the invention, the flexibility of the wax may be modified by including a diacid, polyacid, or anhydride (e.g., trimellitic anhydride) in the initial reactant charge. The acid or anhydride builds molecular weight with the polyglycerol during the transesterification reaction adding flexibility to the resulting wax.

Morphology stable wax compositions of the invention may be used in various embodiments including, for example, candle waxes, stick waxes, jell candles (a diamine and/or diacid may be used to control the viscosity), cosmetics, food coatings (e.g., for coating fruit, cheese, or vegetables), adhesives, board manufacturing (e.g., particle board and oriented strand board), urethane foams or

- 14 -

coatings, alkyd coatings, coating formulation additive (e.g., paint, waterproof coatings, etc.), printing additives, and stick markers.

Candles can be produced from the wax of the invention using a number of different methods. In one typical process, the wax is heated to a molten state. If
5 other additives such as colorants and/or fragrance oils are to be included in the candle formulation, these may be added to the molten wax or mixed with the wax prior to heating. The molten wax is then solidified around a wick. For example, the molten wax can be poured into a mold which includes a wick disposed therein. The molten wax is then cooled to solidify the wax in the shape of the mold. Depending
10 on the type of candle being produced, the candle may be unmolded or used as a candle while still in the mold. Examples of molded candles include container candles which typically include an outer glass or metal container. Examples of unmolded candles include pillar candles and taper candles. Where the candle is designed to be used in unmolded form, it may also be coated with an outer layer of
15 higher melting point material.

Alternatively, the wax can be formed into a desired shape, e.g., by pouring molten wax into a mold and removing the shaped material from the mold after it has solidified. A wick may then be inserted into the shaped wax material using techniques known to those skilled in the art (e.g., using a wicking machine such as a
20 Kurschner wicking machine).

The candle wax may be fashioned into a variety of forms, commonly ranging in size from powdered or ground wax particles approximately one-tenth of a millimeter in length or diameter to chips, flakes or other pieces of wax approximately two centimeters in length or diameter. Where designed for use in
25 compression molding of candles, the waxy particles are generally spherical, prilled granules having an average mean diameter no greater than about one (1) millimeter.

Prilled wax particles may be formed conventionally, by first melting the wax in a vat or similar vessel and then spraying the molten waxy material through a nozzle into a cooling chamber. The finely dispersed liquid solidifies as it falls
30 through the relatively cooler air in the chamber and forms prilled granules that, to the naked eye, appear to be spheroids about the size of grains of sand. Once formed, the prilled wax can be deposited in a container and, optionally, combined with the

coloring agent and/or scenting agent.

Wax compositions of the invention may include other components, as well, such as coloring agents, scenting agents, paraffin, migration inhibitors, and the like. A variety of such additives are disclosed, for example, in U.S. Patent Nos. 6,770,104
5 and 6,824,572:

A wide variety of coloring and scenting agents, well known in the art of candle making, are available for use with waxy materials. Typically, one or more dyes or pigments is employed provide the desired hue to the color agent, and one or more perfumes, fragrances, essences or other aromatic oils is used provide the
10 desired odor to the scenting agent. The coloring and scenting agents generally also include liquid carriers which vary depending upon the type of color- or scent-impacting ingredient employed. The use of liquid organic carriers with coloring and scenting agents is preferred because such carriers are compatible with petroleum-
15 based waxes and related organic materials. As a result, such coloring and scenting agents tend to be readily absorbed into waxy materials. It is especially advantageous if a coloring and/or scenting agent is introduced into the waxy material when it is in the form of prilled granules.

The colorant is an optional ingredient and is commonly made up of one or more pigments and dyes. Colorants are typically added in a quantity of about 0.001-
20 2 wt. % of the waxy base composition. If a pigment is employed, it is typically an organic toner in the form of a fine powder suspended in a liquid medium, such as a mineral oil. It may be advantageous to use a pigment that is in the form of fine particles suspended in a vegetable oil, e.g., a natural oil derived from an oilseed source such as soybean or corn oil. The pigment is typically a finely ground, organic
25 toner so that the wick of a candle formed eventually from pigment-covered wax particles does not clog as the wax is burned. Pigments, even in finely ground toner forms, are generally in colloidal suspension in a carrier.

If a dye constituent is utilized, it may be dissolved in an organic solvent. A variety of pigments and dyes suitable for candle making are listed in U.S. Pat. No.
30 4,614,625 . The preferred carriers for use with organic dyes are organic solvents, such as relatively low molecular weight, aromatic hydrocarbon solvents; e.g. toluene and xylene. The dyes

ordinarily form true solutions with their carriers. Since dyes tend to ionize in solution, they are more readily absorbed into the prilled wax granules, whereas pigment-based coloring agents tend to remain closer to the surface of the wax.

Candles often are designed to appeal to the olfactory as well as the visual
5 sense. This type of candle usually incorporates a fragrance oil in the waxy body material. As the waxy material is melted in a lighted candle, there is a release of the fragrance oil from the liquefied wax pool. The scenting agent may be an air freshener, an insect repellent or more serve more than one of such functions.

The air freshener ingredient commonly is a liquid fragrance comprising one
10 or more volatile organic compounds which are available from perfumery suppliers such IFF, Firmenich Inc., Takasago Inc., Belmay, Noville Inc., Quest Co., and Givaudan-Roure Corp. Most conventional fragrance materials are volatile essential oils. The fragrance can be a synthetically formed material, or a naturally derived oil such as oil of Bergamot, Bitter Orange, Lemon, Mandarin, Caraway, Cedar Leaf,
15 Clove Leaf, Cedar Wood, Geranium, Lavender, Orange, Origanum, Petitgrain, White Cedar, Patchouli, Lavandin, Neroli, Rose and the like.

A wide variety of chemicals are known for perfumery such as aldehydes, ketones, esters, alcohols, terpenes, and the like. A fragrance can be relatively simple in composition, or can be a complex mixture of natural and synthetic chemical
20 components. A typical scented oil can comprise woody/earthy bases containing exotic constituents such as sandalwood oil, civet, patchouli oil, and the like. A scented oil can have a light floral fragrance, such as rose extract or violet extract. Scented oil also can be formulated to provide desirable fruity odors, such as lime, lemon or orange.

25 Synthetic types of fragrance compositions either alone or in combination with natural oils such as described in U.S. Pat. Nos. 4,314,915; 4,411,829; and 4,434,306. Other artificial liquid fragrances include geraniol, geranyl acetate, eugenol, isoeugenol, linalool, linalyl acetate, phenethyl alcohol, methyl ethyl ketone, methylionone, isobornyl acetate, and the
30 like. The scenting agent can also be a liquid formulation containing an insect repellent such as citronellal, or a therapeutic agent such as eucalyptus or menthol. Once the coloring and scenting agents have been formulated, the desired quantities

- 17 -

are combined with waxy material which will be used to form the body of the candle. For example, the coloring and/or scenting agents can be added to the waxy materials in the form of prilled wax granules. When both coloring and scenting agents are employed, it is generally preferable to combine the agents together and then add the
5 resulting mixture to the wax. It is also possible, however, to add the agents separately to the waxy material. Having added the agent or agents to the wax, the granules are coated by agitating the wax particles and the coloring and/or scenting agents together. The agitating step commonly consists of tumbling and/or rubbing the particles and agent(s) together. Preferably, the agent or agents are distributed
10 substantially uniformly among the particles of wax, although it is entirely possible, if desired, to have a more random pattern of distribution. The coating step may be accomplished by hand, or with the aid of mechanical tumblers and agitators when relatively large quantities of prilled wax are being colored and/or scented.

The invention will now be described with reference to the following non-
15 limiting examples.

EXAMPLES

EXAMPLE 1:

Preparation of polyglycerol ester from polyglycerol and fully hydrogenated soybean oil. Polyglycerol (39.0 lbs., 10.0 wt%) and fully
20 hydrogenated soybean oil (Cargill "Stable Flake", Iodine Value <2, 351 lbs, 90.0 wt%) were charged into a stainless steel fifty gallon reactor equipped with nitrogen sparge, over head condenser, and agitation. The distribution of the polyglycerol by GC area count was: glycerol (60.8%); diglycerol (22.6%); triglycerol (9.5%); tetraglycerol (3.4 wt%); pentaglycerol (1.1 wt%) and total cyclic polyglycerol (1.6
25 wt%). The nitrogen sparge was set at 1.9 l/min during the addition and through out the reaction. The agitator was turned on and set at 60 rpm. The batch was heated to 235°C at a rate of 1.5°C/min. The batch was sampled at 1 hour (two-phase product), at 1.5 hours (product clearing with slight haze) and 2.0 hours (product was clear). The batch was held for an additional fifteen minutes and then cooled to 80°C. The
30 batch cooled was from 235°C to 205°C in 15 minutes, from 205°C to 181°C in a second 15 minutes, and 181°C to 160°C in a further fifteen minutes, totaling forty-

five minutes. The final product was flaked and analyzed and had the properties shown in TABLE 1.

TABLE 1

Property	Value
Gardner Color	<1
Acid Value	0.1
Hydroxyl Value	147
Density	0.97 g/ml (solid) 0.89 g/ml (liquid)
Appearance in Melt	Clear

5

EXAMPLE 2:

This example reports the evaluation and comparison of esters prepared from various polyglycerol and glycerol streams. The glycerol and polyglycerol esters were prepared in the same fashion as described in Experiment 1. All charges were based on a 90 wt% fully hydrogenated soybean oil and 10 wt% polyol reaction. The paraffin example is a blended paraffin specifically developed for the preparation of candles.

Test Method (Melting and Congeal Points): The melting and congeal points were collected on a Perkin Elmer Differential Scanning Calorimeter DSC 7.

Test Method (Blooming/Cracking): The wax was melted in an oven at approximately 73° C. 100 mL of each wax was poured into a plastic cup at room temperature and allowed to cool on the countertop. The next day, samples were inspected visually for any cracks. They were also inspected visually for any signs of fat bloom which is normally indicated by a white powdery film on the surface or by bumps in the wax. The bumps can sometimes look like small pieces of cauliflower. The samples were re-checked the samples for fat bloom after 1 month of aging at room temperature. For samples indicated as not having fat bloom, they were still free from any signs after 1 month of room-temperature aging.

25

The testing is summarized in TABLE 2.

TABLE 2

Description	Blooming Properties	Cracking Properties	Glass Adhesion	Melting Point (°C)	Congeval Point (°C)	Comments And Polyglycerol Distribution
Paraffin	None	None	Good	63	55	Test sample supplied by Hanna Inc.
Hydrogenated Soybean oil (IV<2)	Severe	Severe	Poor	69	42	Notable shrinkage on congeal
Wax prepared using glycerol	None	Some on surface	Good	62	50	After a burn cycle in a candle test glycerol was seen pooling in the liquid wax on top of the candle.
Wax prepared using polyglycerol 2-1	None	None	Good	63	55	Product is most like paraffin. No glycerol pooling was seen after a candle burn test. Polyglycerol 2-1 distribution: glycerol 60%; diglycerol 24%; triglycerol 10%; tetraglycerol 5%; and pentaglycerol and higher 1%
Wax prepared using polyglycerol 2-2	None	Some on surface	Good			Polyglycerol 2-2 distribution: glycerol 30.0%;

						diglycerol 30.4%; triglycerol 19.6%; tetraglycerol 9.5%; pentaglycerol 5.4%; hexaglycerol 4.2%; heptaglycerol 0.7%; and octaglycerol and higher 0.2%
Wax prepared using polyglycerol 2-3	Moderate	Moderate	Good			Polyglycerol 2-3 distribution: Glycerol 3.0%; diglycerol 42.4%; triglycerol 27.1%; tetraglycerol 13.0%; pentaglycerol 7.4%; hexaglycerol 5.8%; heptaglycerol 1.0%; octaglycerol 0.4%; and nonaglycerol and higher 0.1%

EXAMPLE 3:

Sample 1: 90% X-155 (fatty acid distribution of about 0.1 myristic acid; 11.0% palmitic acid; 0.1 palmitoleic acid; 87.8% stearic acid; 0.5% oleic acid; 0.1%
5 linoleic acid; 0.3% arachidic acid; and 0.1% behenic acid) was transesterified with 10% glycerol to provide a wax composition (Wax 3-1). A wax composition suitable for candles was made by combining 35 wt% of Wax 3-1 and 65 wt% fully

- 21 -

hydrogenated soybean oil. The resultant wax yielded both container and pillar candles with an excellent appearance and good control of fat bloom. However, after a burn, free glycerol pools formed at the surface where the melted wax was re-congealing. Wiping away the pools of glycerol caused a pock-marked surface, suggesting phase separation is occurring at elevated temperatures.

Sample 2: 90% X-155 was transesterified with 10% polyglycerol (distribution: glycerol 60%; diglycerol 24%; triglycerol 10%; tetraglycerol 5%; and pentaglycerol and higher 1%) to provide a morphology stable wax composition (Wax 3-2). A wax composition suitable for candles was made by combining 30 wt% of Wax 3-2 and 70 wt% fully hydrogenated soybean oil. The resultant wax composition yielded impressive container candles. In addition to a pleasing appearance, the candles showed good control of fat bloom. When cooling in the mold, the candles are preferably fan-cooled instead of air cooled, to avoid leaving a film on the mold. The difference between the melt point and the congeal point of this composition was only 5°C, which has positive implications for industrial uses in addition to candle wax.

EXAMPLE 4:

A transesterified wax (Wax 4-1) was prepared by transesterifying 10 wt% polyglycerol (OC-500) with 90 wt% X-155. The resulting wax had a hydroxyl value of 160. Into a two liter round bottom flask fitted with an agitator, nitrogen sparge, Dean Stark trap and condenser was placed 681.2 grams of Wax 4-1 and phthalic anhydride (108.9 g). With slow agitation the mixture was heated to 195°C and the temperature maintained till the acid value was less than five. After ten hours at 195°C an Acid Value of 4.9 was reached. The product was cooled. Analysis showed it to have a melt point of 61°C and a congeal point of 49°C. The wax showed no signs of cracking or bloom formation. When struck, it acted much like that of paraffin.

The above-detailed embodiments and examples are intended to be illustrative, not exhaustive, and those skilled in the art will recognize that various equivalent modifications are possible within the scope of the invention. For example, whereas steps are presented in a given order, alternative embodiments may

perform steps in a different order. The various embodiments described herein can be combined to provide further embodiments.

In general, the terms used in the following claims should not be construed to limit the invention to the specific embodiments disclosed in the specification unless
5 the preceding description explicitly defines such terms. The inventors reserve the right to add additional claims after filing the application to pursue additional claim forms for other aspects of the invention.

74230-70

23

CLAIMS:

1. A morphology stable wax composition comprising the (trans)esterification product of a wax-forming composition comprising:
 - (a) a triglyceride stock, a fatty acid stock, or a mixture thereof; and
 - 5 (b) a glycerol-based composition comprising 0 to 70 wt% glycerol; 20 to 40 wt% diglycerol; 5 to 30 wt% triglycerol; 0 to 20 wt% tetraglycerol; 0 to 10 wt% pentaglycerol; 0 to 10 wt% hexaglycerol; 0 to 5 wt% heptaglycerol; and 0 to 5 wt% cyclic polyglycerol.
2. The wax composition of claim 1, wherein the wax comprises a triglyceride stock.
- 10 3. The wax composition of claim 2, wherein the triglyceride stock comprises vegetable oil, animal-based oil, or mixtures thereof.
4. The wax composition of claim 2, wherein the triglyceride stock is a vegetable oil selected from soybean oil, cottonseed oil, sunflower oil, canola oil, corn oil, peanut oil, safflower oil, palm oil, palm kernel oil, coconut oil, algal oil, jatropha oil, castor oil, or
15 mixtures thereof.
5. The wax composition of claim 4, wherein the triglyceride stock comprises fully-hydrogenated soybean oil.
6. The wax composition of claim 1, wherein the glycerol-based composition comprises glycerol and a polyglycerol species selected from the group consisting of
20 diglycerol, triglycerol, tetraglycerol, pentaglycerol, and cyclic polyglycerol.
7. The wax composition of claim 1, wherein the glycerol-based composition comprises: 75 wt% or greater total of polyglycerol species comprising diglycerol, triglycerol, and tetraglycerol; and up to 10 wt% or less total of polyglycerol species of hexaglycerol and greater.

74230-70

24

8. The wax composition of claim 1, wherein the glycerol-based composition comprises 1 wt% to 65 wt% glycerol.
9. The wax composition of claim 1, wherein the glycerol-based composition comprises 1 wt% to 20 wt% tetraglycerol.
- 5 10. The wax composition of claim 1, wherein the glycerol-based composition comprises 55 to 65 wt% glycerol; 20 to 30 wt% diglycerol; 5 to 15 wt% triglycerol; 1% to 10 wt% tetraglycerol; and up to 5 wt% pentaglycerol.
11. The wax composition of claim 1, wherein the glycerol-based composition comprises 30 to 35 wt% glycerol; 25 to 35 wt% diglycerol; 15 to 20 wt% triglycerol; 5
10 to 10 wt% tetraglycerol; up to 5 wt% pentaglycerol; up to 5 wt% hexaglycerol; and up to 5 wt% cyclic glycerol.
12. The wax composition of claim 1, wherein the glycerol-based composition comprises up to 5 wt% glycerol; 30 to 40 wt% diglycerol; 20 to 30 wt% triglycerol; 10
15 to 20 wt% tetraglycerol; 5 to 15 wt% pentaglycerol; up to 10 wt% hexaglycerol; up to 10 wt% heptaglycerol and higher order oligomers; and up to 5 wt% cyclic glycerol.
13. The wax composition of claim 1, wherein the wax has a melting point and a congeal point; and wherein the difference between the melting point and the congeal point is 10°C or less.
14. The wax composition of claim 1, wherein the wax-forming composition further
20 comprises a diamine compound.
15. The wax composition of claim 1, wherein the triglyceride stock, the fatty acid stock, or the mixture thereof is 60 wt% to 99.9 wt% of the wax composition; and the glycerol-based composition is 0.1 wt% to 35 wt% of the wax composition.
16. A wax article comprising the morphology stable wax composition of claim 1.
- 25 17. A method of making a morphology stable wax composition comprising the

74230-70

25

steps of:

(a) providing a composition comprising a triglyceride stock, a fatty acid stock, or a mixture thereof;

5 (b) providing a glycerol-based composition comprising 0 to 70 wt% glycerol; 20 to 40 wt% diglycerol; 5 to 30 wt% triglycerol; 0 to 20 wt% tetraglycerol; 0 to 10 wt% pentaglycerol; 0 to 10 wt% hexaglycerol; 0 to 5 wt% heptaglycerol; and 0 to 5 wt% cyclic polyglycerol; and

(c) (trans)esterifying the composition of step (a) with the composition of step (b) to produce the morphology stable wax composition.

10 18. The method of claim 17, wherein the (trans)esterification is conducted in the presence of a catalyst.

19. The method of claim 18, wherein the catalyst comprises lithium, sodium, potassium, magnesium, calcium, oxide, methyl oxide, antimony oxides, hydroxide, carbonate, phosphate, phosphite, hypophosphite, and salts thereof.

15 20. The method of claim 18, wherein the catalyst comprises potassium hydroxide, sodium hydroxide, calcium hydroxide, or a combination thereof.

21. The method of claim 17, wherein the triglyceride stock, the fatty acid stock, or the mixture thereof is 60 wt% to 99.9 wt% of the wax composition; and the glycerol-based composition is 0.1 wt% to 35 wt% of the wax composition.