




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: D01F 6/62, D01D 10/02, 5/08, D02G 1/18, 1/00, D01D 5/22, 5/24, D01F 8/14, 8/12	A1	(11) International Publication Number: WO 96/16206 (43) International Publication Date: 30 May 1996 (30.05.96)
(21) International Application Number: PCT/US94/13189 (22) International Filing Date: 21 November 1994 (21.11.94) (71) Applicant: E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US). (72) Inventors: FRANKFORT, Hans, Rudolf, Edward; 747 Colony Place, Kinston, NC 28501-2780 (US). KNOX, Benjamin, Hughes; 40 Oregon Road, Wilmington, DE 19808-5420 (US). PAI, Girish, Anant; 2322 Kilkenney Hill, Matthews, NC 28105-8843 (US). (74) Agents: HIGGS, W., Victor et al.; E.I. du Pont de Nemours and Company, Legal/Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).		(81) Designated States: CN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>

(54) Title: IMPROVEMENTS IN CONTINUOUS FILAMENTS, YARNS, AND TOWS**(57) Abstract**

Polyester filaments of high shrinkage and high shrinkage tension may be prepared by heat treatment of undrawn crystalline filaments of low shrinkage and shrinkage tension, and may be used for making polyester yarns of mixed shrinkage and bulky polyester yarns and fabrics therefrom.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

TITLE

Improvements in Continuous Filaments, Yarns, and Tows

This invention concerns improvements in and relating to polyester (continuous) filaments, especially those prepared as-spun in the form of flat yarns, a capability to provide from the same feed stock such polyester continuous filament yarns of various differing deniers, shrinkage properties, tensiles, dyeability and of other useful properties as desired; polyester flat yarns, as well as filaments, generally, including tows, resulting from such processes; mixed-filament yarns, bicomponent filament yarns, biconstituent filament yarns and bulky yarns prepared therefrom; and downstream products from such filaments and yarns, including textured products, and including new processes for preparation of these new filaments and products therefrom.

It may be helpful, in view of differences in terminology in various literature, to indicate that the terminology, symbols and expressions used herein are intended generally to follow those in USP 5,250,245, the disclosure of which is incorporated herein by reference, including, e.g., the listing of such near the end of the description therein.

BACKGROUND OF PARENT USP 5,066,447

Textile designers are very creative. This is necessary because of seasonal factors and because the public taste continually changes, so the industry continually demands new products. Many designers in this industry would like the ability to custom-make their own yarns, so their products would be more unique, and so as to provide more flexibility in designing textiles.

Polyester (continuous) filament yarns have for many years had several desirable properties; but, hitherto, there has been an important limiting factor in

the usefulness of most polyester flat yarns to textile designers, because only a limited range of yarns has been available from fiber producers, and the ability of any designer to custom-make his own particular polyester flat
5 yarns has been severely limited in practice. The fiber producer has generally supplied only a rather limited range of polyester yarns because it would be more costly to make a more varied range, e.g. of deniers per filament (dpf), shrinkage properties, tensiles, and dyeability, and
10 to stock an inventory of such different yarns.

Conventional flat polyester filament yarns used to be typically prepared, for example, by melt-spinning at low or moderate speeds to make undrawn yarns and then drawing and heating to increase tensiles (especially,
15 modulus and yield point) and to decrease shrinkage. Conventional polyester filaments have combinations of properties that, for certain end-uses, could desirably be improved, as will be indicated hereinafter. It is important to recognize that what is important for any
20 particular end-use is the combination of all the properties of the specific yarn (or filament), sometimes in the yarn itself during processing, but also in the eventual fabric or garment of which it is a component. It is easy, for instance, to reduce shrinkage by a processing
25 treatment, but this modification is generally accompanied by other changes, so it is the combination or balance of properties of any filament (or staple fiber) that is important.

Generally, we refer herein to untextured
30 filament yarns as "flat" yarns and to undrawn flat yarns as "feed" or as "draw-feed" yarns. Filament yarns which can be used as a "textile" yarn without need for further drawing and/or heat treatment are referred herein as
"direct-use" yarns. For textile purposes, a "textile"
35 yarn must have certain properties, such as sufficiently high modulus and yield point, and sufficiently low shrinkage, which distinguish these yarns from conventional feed yarns that require further processing before they

have the minimum properties for processing into textiles and subsequent use. It will be recognized that, where appropriate, the technology may apply also to polyester filaments in other forms, such as tows, which may then be converted into staple fiber, and used as such in accordance with the balance of properties that is desirable and may be achieved as taught hereinafter.

From the parent USP No. 5,066,447, the disclosure of which is hereby incorporated herein by reference, it is known that conventional polyester undrawn spin-oriented yarns (SOY) (and SOF, i.e., spin-oriented filaments) draw by a necking operation; i.e., that the undrawn polyester filaments have a natural draw-ratio NDR (and that drawing such polyester filaments at draw-ratios less than the NDR (herein referred to as partial-drawing) produces irregular "thick-thin" filaments which are considered inferior for most practical commercial purposes (unless a specialty yarn is required, to give a novelty or special effect). For filament yarns, the need for uniformity is particularly important, more so than for staple fiber. Fabrics from flat yarns show even minor differences in uniformity from partial drawing of conventional polyester undrawn SOY as defects, especially when dyeing these fabrics. Thus, uniformity in flat filament yarns is extremely important. Undrawn polyester filaments have been unique in this respect because nylon filaments and polypropylene filaments have not had this defect. Thus, it has been possible to take several samples of a nylon undrawn yarn, all of which have the same denier per filament, and draw them, using different draw-ratios, to obtain correspondingly different deniers in the drawn yarns, as desired, without some being irregular thick-thin filament yarns, like partially drawn polyester filament yarns.

So far as is known, it had not previously been suggested, prior to the parent application, that a draw process be applied to a polyester textile yarn, i.e., one that was itself already a direct-use yarn, such as having

shrinkage and tensile properties that made it suitable for direct use in textile processes such as weaving and knitting without first drawing and heat setting. Indeed, to many skilled practitioners, it might have seemed a contradiction in terms to subject such a yarn to draw-warping, for example, because such a yarn was already a textile yarn, not a feed yarn that needed a drawing operation to impart properties useful in textile processes such as weaving or knitting.

According to the parent application, processes were provided for improving the properties of feed yarns of undrawn polyester filaments (especially undrawn polyester filament feed yarns that have the shrinkage behavior of spin-oriented polyester filaments such as have been disclosed by Knox in U.S. Patent No. 4,156,071, and by Frankfort & Knox in U.S. Patent Nos. 4,134,882 and 4,195,051 (discussed hereinafter). Such processes (according to the parent application) involve drawing with or without heat and with or without post heat-treatment, and are most conveniently adapted for operation using multi-end drawing, such as draw-warping; but such benefits may be extended to other drawing operations, such as preparing drawn flat yarns by split and coupled drawing of single-ends (or of a small number of ends, typically corresponding to the number of spin packages per winder or spin position of a small unit of winders) and to various draw (and no-draw) texturing processes for providing bulky filament yarns, such as by draw false-twist and air-jet texturing and no draw air-jet and stuffer-box texturing.

BACKGROUND OF THE PRESENT INVENTION

It has long been desired to make filaments of differing shrinkage behaviors, such as boil-off shrinkage (S), maximum shrinkage tension (ST_{max}), shrinkage power (P_S), and shrinkage modulus (M_S), especially from one and the same filament feed stock; and especially of P_S sufficient to overcome the high internal fabric matrix restraints and permitting the development of the desired

level of shrinkage even when the filaments are in a fabric; e.g., such as being used as a high shrinkage filament yarn in a form-fitting fabric used in upholstery, as a component in a mixed-shrinkage filament yarn such as
5 would be capable of developing bulk by differential filament length (DFL) on heating, as a component in a bicomponent polyester filament yarn and as a component in a biconstituent polyester/nylon filament yarn such as would be capable of developing bulk by torque-free helical
10 crimping of the filaments on heating, even in tightly-woven fabrics. There has been a long-standing need for a practical way to make filaments, differing in shrinkage and tensile properties from a single feed stock, and previous suggestions have not been satisfactory.

15 Shrinkage power (P_s) herein is the product of the boil-off shrinkage (S) $\times$ (ST_{max}), the maximum shrinkage tension, whereas shrinkage modulus (M_s) is 100 times the maximum shrinkage tension divided by the shrinkage, i.e. $(ST_{max}/S)\times 100$.

20 Shrinkage of undrawn SOY initially increases with increasing spin speed (i.e., with increasing stress-induced orientation (SIO) as represented, in part, by decreasing elongation-to-break, E_B), and then beyond a critical SIO level, shrinkage decreases at higher spin
25 speeds due to the onset of stress-induced crystallization (SIC) which prevents the maximum shrinkage potential (S_m) for a given level of SIO from developing (see discussion of Figures 2A and 2B hereinafter). Increased shrinkage of SOY may be accomplished by changing known process
30 parameters; such as, lower polymer LRV, increased polymer temperature, increased capillary shear rate (smaller capillary diameter), increased capillary pressure drop (increased capillary L/D), lower extensional "Trouton" viscosity (hotter quench air, lower quench air velocity,
35 delay quench, longer convergence distance), higher denier per filament, reduced spin-orientation (lower spin speeds), reduced crystallization rate with modified copolymers, and other process parameters. However,

increasing shrinkage by reducing the SIC, has resulted in undesirable changes in other properties, such as lower tensiles (e.g., T_7) and lower ST_{max} ; higher values of both are desirable so that the desired fabric aesthetics can be developed during dyeing and finishing (see discussion of Figures 4 and 5 hereinafter).

A process to prepare polyester filaments of high shrinkage S and high P_s directly in as-spun filaments, i.e., merely by melt spinning, without drawing, has not been disclosed in the prior art. Prior art processes that incorporate drawing, such as "cold drawing" of SOY and aerodynamic "space-draw" of SOY may offer routes to high P_s yarns of sufficient tensiles but have had serious disadvantages. Such draw processes have not provided the desired combination of properties, i.e., a desirable balance of shrinkage S and ST_{max} , as expressed by M_s and P_s , as will be discussed hereinafter (Example XIX). Also, and importantly, these draw processes have not provided yarns with good dyeability (i.e., high relative disperse dye rates, RDDR), and drawn polyester yarns have had poor thermal stability (herein defined by high shrinkage differential (ΔS_1) as measured by rapid increase in dry heat shrinkage with increasing temperature and also expressed by a significant difference (ΔS_2) between the dry heat shrinkage (DHS) at elevated temperatures (180 C) and the boil-off-shrinkage (S); drawn yarns, therefore, have required use of high fabric finishing treatment temperatures for proper fabric stabilization (e.g. at least to temperatures of $T(ST_{max})$, e.g., about 150-180 C). Also these draw processes have not provided simple direct routes to mixed-shrinkage, bicomponent and biconstituent filament yarns.

Crystalline SOY used as "direct-use" textile yarns, such as those prepared by Knox, Frankfort & Knox, and Collins et al (referred to hereinbefore) are characterized by good dyeability (high RDDR), good thermal stability (characterized herein by low ΔS_1 and ΔS_2 -values, and reach ST_{max} at $T(ST_{max})$ typically less than about 100

C (i.e., that can be achieved during boil-off, such in a dyebath); i.e., properties that are generally very desirable for "textile" yarns; but such crystalline SOY do not have "high shrinkage power", but are of low shrinkage S and low ST_{max} . Thus, the prior art has not taught how to solve the problem of providing polyester SOY having the combination of high values of shrinkage S, ST_{max} , P_S , and low values of M_S combined with the desirable dyeability (RDDR), thermal stability (ΔS_1 and ΔS_2), and other properties associated with crystalline SOY.

SUMMARY OF THE INVENTION

The present invention provides such long-desired high shrinkage spin-oriented filaments, SOF (herein referred to as B-filaments, filaments (B) or as filaments Type B), by novel and simple direct processes involving essentially increasing the shrinkage of crystalline low shrinkage SOF capable of being used as direct-use "textile" filaments (herein referred to as A-filaments, filaments (A) or as filaments Type A), such as were used as "feed" yarns in the parent application. Such processes can transform the crystalline low shrinkage SOF (Type A) into new SOF (Type B), characterized by high P_S and low M_S without reducing other desirable properties, including thermal stability (low ΔS_1 and ΔS_2) and dyeability (RDDR). We believe that no one has previously suggested that the long-standing problem could be solved by using crystalline low shrinkage direct-use textile SOF as "feed" filaments (i.e., as intermediates) for preparing SOF of the desired high shrinkage S and high ST_{max} . Indeed, to many skilled practitioners, it might have seemed a contradiction in terms to begin with crystalline thermally "stable" SOF as intermediate for obtaining a precursor of high shrinkage SOF (i.e., that are not so stable thermally). It may indeed seem very surprising that the shrinkage can be increased while maintaining such desirable properties. It may seem especially surprising to some practitioners that the shrinkage values can be increased, while maintaining

thermal stability (i.e., low ΔS_1 and ΔS_2 values) and without reducing dyeability (i.e., low RDDR values).

According to a first aspect of the invention, a treatment process is provided for preparing polyester SOF of high shrinkage (S), high ST_{max} , high P_S and low M_S by treating the crystalline low shrinkage SOF (Type A) by rapidly heating the A-filaments to a temperature above the polyester polymer glass-transition temperature T_g (defined herein by $\{0.65(T_m^0+273)-273\}$) and temperature T_3 , defined as the mid-point between the onset temperature of crystallization (T_c^0) and the onset temperature of major crystallization, $T_{c, \frac{1}{2}}$ as measured on the polyester polymer and expressed by $[\{0.75(T_m^0+273)-273\} + \{0.80(T_m^0+273)-273\}]/2 = \{0.775(T_m^0+273)-273\}$, and then immediately and rapidly cooling the treated filaments to below the polymer T_g , and ensuring that the heating and cooling are carried out at rates sufficiently rapid to provide the desired B-filaments [shown as Areas A and B in Figure 1] having:

1) a residual draw-ratio (RDR) of about 1.4 to about 1.9, a post-yield modulus (M_{py} of less than about 12 g/dd, and a high shrinkage S such that the value of $(1-S/S_m)$ is between about 0.25 and about 0.9; where RDR is defined by $(1+100/EB, \%)$ and S_m is defined by $[(6.5-RDR)/6.5] \times 100\%$;

2) a high ST_{max} of about 0.1 g/d to about 0.5 g/d at a $T(ST_{max})$ between about the polymer T_g and about temperature T_1 (defined herein by $\{0.725(T_m^0+273)-273\}$);

3) a M_S upto about 5 g/d; and a P_S of about 1.5 to 12 (g/d)%;

it being important that the A-filaments (before such heat treatment process) be low shrinkage spin-oriented crystalline undrawn A-filaments characterized by:

1) a RDR between about 1.4 and about 1.9 and a shrinkage S such that the value of $(1-S/S_m)$ is at least about 0.9;

2) a ST_{max} less than about 0.15 g/d at a $T(ST_{max})$ between about the polymer T_g and the polymer liquid-liquid transition temperature T_{ll} defined herein by $\{0.70(T_m^0+273)-273\}$;

5 and desirably having,

3) a M_s less than about 5 g/d; and a P_s less than about 1.5 (g/d)%.

One embodiment of the treatment process of the invention (herein called Type I) is characterized by
10 rapidly heating said A-filaments to temperatures between the T_{ll} and about temperature T_2 , defined herein as the mid-point between T_{ll} and the onset of crystallization T_c^0 , i.e. $\{0.725(T_m^0+273)-273\}$, and then immediately and rapidly cooling the treated filaments to below the polymer
15 T_g ; wherein said heating and cooling are carried out at rates sufficiently rapid to provide B-filaments from said A-filaments.

Another variation of the treatment process of the invention (herein called Type II) is characterized by
20 rapidly heating said A-filaments to a temperature between about T_2 and about T_3 ; and then immediately and rapidly cooling the treated filaments to below T_g ; wherein said heating and cooling are carried out at rates sufficiently rapid to provide B-filaments from said A-filaments.

25 Treatment processes Type I and Type II of the invention may be carried out in a split process (sp), such as in air-jet texturing, and in the form of a weftless warp sheet, provided that the heating and cooling are carried out at rates sufficiently rapid to provide B-
30 filaments from said A-filaments

Treatment processes Type I and Type II may be coupled (cp) with first preparing polyester A-filaments by melt-extruding and rapid attenuating and quenching the polymer melt streams at withdrawal speeds in the range of
35 about 2 to about 6 km/min to provide filaments (Type A) at

temperatures below the polymer T_g and then treating the A-filaments by either process Type I or Type II to provide B-filaments, followed by high speed winding into packages.

B-filaments of the invention as prepared by Type I and Type II treatment processes of the invention, as described hereinabove, have a P_S between about 1.5 and about 12 (g/d)%, a M_S less than 5 g/d, and shrinkage S , such that $(1-S/S_m)$ is at least about 0.25 and less than about 0.9 for RDR values between about 1.4 to about 1.9; a $T(ST_{max})$ between about the T_g and about the T_1 of the polyester polymer; and a ST_{max} between about 0.1 and 0.5 g/d (as indicated by Areas A and B in Figure 1); and the B-filaments of the invention are further characterized by a tenacity-at-10% extension (T_{10}) less than about 3 g/d, a post-yield modulus (M_{py}), defined by $\{(1.2T_{20}-1.07T_7)/(1.2-1.07)\}$ between about 2 and about 12 g/dd (where g/dd is grams per drawn denier) which approximately corresponds to a birefringence (Δ_n) between about 0.04 and about 0.12 providing good dyeability as indicated by RDDR values of at least about 0.08; and sufficient tensiles for use as textile filaments as indicated by an initial yield point T_y (herein approximated by the value of the tenacity-at-7% extension T_7) of at least about 0.1 g/d.

Preferred B-filaments of the invention as prepared by Type I and Type II treatment processes of the invention, as described hereinabove, are further characterized by a shrinkage S , such that $(1-S/S_m)$ is at least about 0.4 and less than about 0.9; a $T(ST_{max})$ between about the T_g and about the T_{11} of the polyester polymer; a T_{10} less than about 2.5 g/d, a M_{py} between about 2 and about 10 g/dd which approximately corresponds to a birefringence (Δ_n) between about 0.04 and about 0.10 providing good dyeability as indicated by RDDR values of at least about 0.10; and sufficient tensiles for use as textile filaments as indicated by T_7 of at least about 0.15 g/d.

Especially preferred B-filaments of the invention are further characterized by a ΔS_1 value of less than 5 degrees over the temperature range of the polymer T_{11} and $T_{C,max}$; and a ΔS_2 less than +3%.

5 The invention also provides B-filaments being especially suitable for improved draw texturing feed yarns [Area A in Figure 1] for developing higher bulk at conventional texturing speeds or maintaining current levels of bulk at higher texturing speeds; wherein the B-
10 filaments are prepared by heat treatment Type I of Type A filaments; wherein the B-filaments are characterized by having a RDR between about 0.4 and 0.9; a shrinkage S , such that $(1-S/S_m)$ is less than about 0.25 and at least about 0.9 with a ST_{max} between about 0.1 and 0.15 g/d and
15 a M_s less than about 1.5 g/d; and further characterized by a $T(ST_{max})$ between about the T_g and about the T_{11} of the polyester polymer.

 The invention also provides for B-filaments of enhanced tensiles (such as a T_7 of at least about 0.15 g/d and an initial modulus M_i of at least about 60 g/d) by low
20 temperature drawing without post heat treatment (herein referred to as process Type III) of B-filaments (as represented by Areas A and B in Figure 1 and described hereinbefore) at draw temperatures T_D between temperatures
25 T_g and T_1 of the polyester polymer; wherein the drawn B-filaments of higher tensiles are further characterized by a $T(ST_{max})$ between about T_g and about T_2 of the polyester polymer, with a ST_{max} between about 0.5 and 0.7 g/d; and a shrinkage S such that $(1-S/S_m)$ is at least about 0.4 and
30 less than about 0.9; a P_s between about 5 and 12 (g/d)% and a M_s between about 1.5 and about 5 g/d; while retaining a M_{py} less than about 12 g/dd which approximately corresponds to RDDR-values greater than about 0.08.

35 The invention also provides improved flat "A-filament" yarns, especially suitable for tightly constructed woven fabrics [Area D in Figure 1], by

treating thermally stable Type A' filaments by Type II process of the invention (herein referred to as process Type IV) wherein the changes in the thermal properties on the "thermally stable" A'-filaments are small, but
5 sufficient to make the filaments suitable for both knitting and weaving where untreated A'-filaments were only suitable for knit fabrics); wherein the improved flat yarns are characterized by having a RDR between about 1.4 and 1.9, a T_g of at least about 0.15 g/d; a shrinkage S, such that $(1-S/S_m)$ is between about 0.95 and 0.9 and a ST_{max} between about 0.15 and 0.5 g/d such to provide a P_s between about 1.5 and 5 (g/d)% with a M_s between about 1.5 and 5 g/d; and further characterized by a $T(ST_{max})$ between about the T_g and about the T_1 of the polyester polymer.

15 The process of the invention also provides a simple route to mixed-shrinkage filament yarns (herein denoted as AB and as A'B yarns) comprised of A(or A') filaments and B-filaments wherein the A (or A') filaments and the B-filaments may be co-mingled, for example in a
20 separate split process to form a mixed filament bundle (e.g., prior to air-jet texturing) or may be formed in a coupled spin/treatment process (cp) wherein the freshly spun A-filaments are, for example, divided into two bundles with one bundle being treated by process Type I or
25 Type II to form B-filaments which are then combined with the untreated A-filament bundle to form a mixed-shrinkage AB filament yarn; or by treating in a split or coupled process a mixed A'A-filament bundle comprised of A' and A-filaments, where A' filaments are of such thermal
30 stability that their shrinkage properties are not significantly affected by the treatment step (Type I or Type II) of the invention, while the A-filaments are transformed, as described hereinbefore, to B-filaments, such that treatment of the A'A mixed-filament bundle
35 provides an A'B mixed-shrinkage filament yarn. The A' filaments achieve their thermally stability, for example, by being of lower denier, odd cross section of significant surface-to-volume ratio; or the A and A'-filaments may be

of the same dpf and cross-section, but are differentiated by their extrusion conditions; e.g., prior to extrusion, the polyester melt stream is divided into two melt streams, wherein one of the two melt streams is treated, 5 for example, via injection of an agent into the melt stream that either enhances crystallization thus forming A'-filaments from A-filaments or injection of any agent that suppresses crystallization and thus forming A-filaments from A'-filaments on extrusion and attenuation, 10 or alternatively, one the melt streams may be of different melt viscosity by use of higher shear spinneret extrusion capillaries fitted with metering capillaries such that the total pressure drop of the A forming capillaries is equal to that of the A' forming capillaries in order to maintain 15 the same dpf of A and A'-filaments. The filaments extruded at the lower melt viscosity will achieve lower SIC and become the A-filaments, while the filaments extruded at the higher melt viscosity will achieve higher SIC and become the A'-filaments. Spinning of melt streams 20 which differ in polymer RV or in the degree to which they are modified by copolyester units may also be used to form A and A'-filaments.

The process of the invention also provides for mixed-filament post-bulkable BC'-yarns comprised of B- 25 filaments and of companion thermally stable C'-filaments of a different polymer substrate, such as of nylon by a coupled melt spinning/treatment process wherein the mixed filament bundle of B and C'-filaments may be prepared by co-spinning A and C'-filaments, forming a mixed-filament 30 AC' bundle followed by co-treating the mixed-filament AC' bundle wherein in the A-filaments are transformed into B-filaments according to the invention and the nylon C'-filaments remain of low shrinkage.

Alternatively the B and C'-filament bundles may 35 be formed in separate steps and co-mingled to provide a post-bulkable BC' mixed-filament yarn. The bulking of these mixed-filament yarns (AB, A'B, BC') occurs on heat relaxation at temperatures above about T_{11} but less than

$T_{c,max}$ (preferably less than about $T_{c,\frac{1}{2}}$) of the polyester polymer; and may take place in yarn form, such as in a hot air-jet texturing process or in the form of a weftless warp sheet in a warping process wherein the weftless warp sheet is permitted to hot relax before winding onto a beam or prior to being fed directly into a warp knitting machine or into a weaving loom or the bulk may be developed in fabric or garment form during dyeing and finishing.

10 The processes of the invention may be extended to bicomponent filaments comprised of one component being thermally stable under the conditions of either process Type I or Type II and a second component being less thermal stability; e.g., an (A'/A) bicomponent filament
15 which when treated according to the treatment processes of the invention (Type I or Type II) provides a (A'/B) bicomponent filaments which on exposure to heat will spontaneously provide filaments of torque-free helical crimp. An analogous biconstituent filament is also
20 provided by the process of the invention wherein the thermally stable component is of polyamide polymer (C') and the second component of lesser thermal stability is of polyester polymer (A) to provide a (A/C') biconstituent filaments which when treated according to the treatment
25 processes of the invention (Type I or Type II) provide (B/C') biconstituent filaments which on exposure to heat will spontaneously provide filaments of torque-free helical crimping. The bicomponent and biconstituent filaments may be of a side-by-side (SBS) or of a
30 sheath/core (S/C) configuration. Further, mixed deniers and/or cross-sections may be used to disrupt the tendency of helical crimped filament yarns from forming "follow-the-leader crimp" and thereby by provide for improved bulk and coverage (opacity).

35 The treatment processes of the invention (Type I through IV) may incorporate a pretreatment step, wherein the untreated A, A', A/A', A/C', AA', and AC' filament bundles are passed under sufficient tension and velocity

over a surface of selected roughness to provide sufficient thermal fictional heat to provide the treated filaments with asymmetric thermal stability (as described in part by Frankfort in USP Nos. 3,816,992, 3,861,133, and
5 3,905,077). The treated filaments having irregular and asymmetric shrinkage behavior along-end are then treated by Type I, II, or III processes of the invention to provide on heat relaxation along-end filament crimping and filament bulk of a different nature than that achieved by
10 mixed shrinkage filament yarns and by bicomponent or by biconstituent filament yarns This pretreatment process used in conjunction with Type I, II, or III processes of the invention is herein referred to as process Type V.

The treatment processes (Type I, II, or III) of
15 the invention may be applied to filaments of asymmetric cross-section, such as a "lop-sided peanut-shaped" filament wherein one side being larger has the shrinkage characteristics more like that of an A-filament while the smaller side has the shrinkage characteristics more like
20 that of a thermally stable A'-filament such that the asymmetric filament is likened to an A/A' bicomponent filament yarn in its shrinkage behavior.

The treatment processes (Type I, II, or III) of the invention may be applied to filaments of symmetric or
25 asymmetric cross-section being comprised of an off-center longitudinal void of at least 10% (preferably at least 20%) by volume of the filament; wherein, the "solid" side of the filament has the shrinkage characteristics more like that of an A-filament while the side of the filament
30 containing the void has the shrinkage characteristics more like that of a thermally stable A'-filament such that the hollow filament is likened to an A/A' bicomponent filament yarn in its shrinkage behavior. Refer to Example G for details

35

DESCRIPTION OF DRAWINGS

Figure 1 is a log-log (base 10) plot of percent shrinkage (S) versus the maximum shrinkage tension ST_{max} expressed in mg/d (i.e., g/d x1000), wherein the left diagonal grid dashed lines represent different values of shrinkage power $P_S [= (ST_{max})(S\%)]$ increasing from bottom left to top right of the plot; and the right diagonal grid dashed lines represent different values of shrinkage modulus $M_S [= (ST_{max}/S\%)x100\%]$ increasing from top left to bottom right. The solid lines outline combinations of shrinkage properties that characterize various spin-oriented B-filaments of the invention (Areas A and B); B-filaments of higher tensiles through low temperature drawing of spin-oriented B-filaments of Areas A and B (Area C); and low shrinkage flat filaments of improved tensiles by treatment of A'-filaments by process Type IV (Area D). B-filaments of Area B are especially suited for use in mix-shrinkage post-bulkable filament yarns, draw texturing feed yarns for improved bulk development, and where high shrinkage filament yarns for developing fabrics of more tight constructions than are possible by direct knitting or weaving of conventional flat textile filament yarns. B-filaments of Area A are especially suited for use as draw texturing feed yarns where higher bulk is desirable. Low temperature drawn B-filaments of Area C are of higher tensiles without loss in dyeability as indicated by RDDR-values of at least 0.08. Improved low shrinkage flat yarns formed by treating Type A' filament yarns by process IV (Area D) are especially suited for woven fabrics and for obtaining fabrics of tighter construction than possible by direct knitting or weaving of conventional low shrinkage flat yarns.

Various conventional spin-oriented filaments spun over a spin speed range of about 500 m/min to about 7500 m/min are represented in Fig. 1 as follows: Area I for high shrinkage spin-oriented yarns (e.g., commercial POY); Area II for low shrinkage high speed spun direct-use yarns according to Knox; Area III for especially thermally stable highly oriented yarns, HOY (indicative of Type A'-

filaments, described hereinbefore) as taught by Frankfort and Knox, and Collins et al.; Area IV for highly annealed (and/or relaxed) spun, drawn and draw-textured yarns; Area V for conventional spin/drawn (fully drawn yarns, FDY) textile yarns; Area VI for high shrinkage modulus "space-drawn" yarns, such as those disclosed by Davis et al in USP 4,195,161; and Area VII for high shrinkage filament yarns with high orientation (and thereby poor dyeability), such as disclosed by, Teijin (Shimazu et al) in EPA-0207489

Figure 2A is a representative plot of percent shrinkage S versus percent elongation-to-break (E_B) wherein Lines 1, 2, 3, 4, 5, and 6 represent $(1-S/S_m)$ -values of 0.9, 0.7, 0.6, 0.4, 0.25 and 0, respectively; and the curve shaped Line 7 represents a typical shrinkage versus elongation-to-break relationship for a series of yarns formed by increasing spinning speed, for example, wherein all other process variables remain unchanged. Changing other process variables (such as dpf, polymer viscosity, capillary L/D^4) produces a "family" of similar S-shaped curves, essentially parallel to each other. The spin-oriented B-filaments of the invention are denoted by the "widely-spaced" /////-area bordered by E_B -values between about 40% and about 90% and $(1-S/S_m)$ values at least about 0.25(Line 5) and less than about 0.9 (Line 1). The A-filaments used to form the B-filaments of the invention are denoted by the "densely-spaced" /////- area bordered by E_B -values between about 40% and 90% and $(1-S/S_m)$ values at least about 0.9 (Line 1). The A'-filaments typically have $(1-S/S_m)$ values greater than 0.95 (i.e., are further below Line 1).

Figure 2B (Curve I) is a representative plot of shrinkage S of SOF having a wide range of elongations-to-break E_B from about 160% to about 40% (corresponding to RDR-values of 2.6 to 1.4), spun using a wide range of process conditions (e.g., filament denier and cross-section, spin speed, polymer LRV, quenching, capillary dimensions, and polymer temperature T_p), versus percent

volume crystallinity (X_v) from measured density, corrected for density of % pigment). The singular relationship between S and X_v (i.e., extent of stress-induced crystallization SIC) obtained for SOF prepared by such differing process parameters supports the view that the degree of SIC is the primary structural event and that the degree of SIO is a secondary structural event in this range of E_B -values for determining the degree of shrinkage S . Curve II is a plot of the reciprocal of shrinkage $[(1/S) \times 100\%]$ and plotted versus percent crystallinity providing a linear relationship that is useful in estimating percent crystallinity from shrinkage.

Figure 3A is a representative plot of the peak temperature of "cold crystallization" (T_{CC}), as measured by Differential Scanning Calorimetry (DSC) at a heating rate of 20 C per minute (refer to Fig.12), versus amorphous birefringence (as defined in Frankfort and Knox); thus, the value of T_{CC} is a useful measure of the amorphous birefringence (orientation) for filaments where measurement of birefringence is difficult. The A-filaments used herein to prepare the B-filaments of the invention have T_{CC} values between about 90 C and about 110 C.

Figure 3B Line 1 is a representative plot of the M_{py} versus total birefringence (Δ_n); thus, for M_{py} values above about 2 g/d, the M_{py} is a useful measure of total birefringence of spin-oriented, drawn, and textured filaments. The break in the linear relationship between M_{py} and total birefringence is found to correspond to onset of major crystallization for spun yarns with increasing spin speed; but for a series of cold drawn yarns, the break represents the onset of significant increase in interchain order as noted by an increase in trans isomer content in the amorphous phase (determined by polarized infrared spectroscopy).

Line 2 is a plot of RDDR values, normalized to 1 dpf after-boil-off and to an amorphous density of 1.335

g/cc, versus total birefringence (Δn). Filaments of the invention have birefringence values between about 0.04 and 0.12, and RDDR-values at least about 0.08. The RDDR-values may be greater than the linear relationship of Line 2 because of the affect of crystal size and percent crystallinity, in addition to orientation (i.e., birefringence) on dyeability of polyester yarns.

Figure 4A is a plot of percent shrinkage S (or ST_{max} for Curve 4) versus spin speed (mpm), taken as a measure of increasng SIO; where Curve 1 represents increasing shrinkage (i.e., S_m) in absence of SIC; Curve 2 represents shrinkage S versus spin speed with shrinkage decreasing (i.e., departing from Curve 1) at the onset of SIC which reduces shrinkage with increasing spin speed (typical of commercial POY); and Curve 3 represents shrinkage S versus spin speed wherein process conditions have been selected to "force" the onset of SIC at lower levels of SIO and is typical of the process used to form the A-filaments of the invention. Curve 4 is representative of the ST_{max} for Curves 1, 2 and 3 versus spin speed. Curve 5 is representative of the shrinkage of nylon 66 spun yarns after equilibrated to standard relative humidity of 65% at 70 F. The shrinkage of nylon 66 modified with 5-10% copolyamides and of nylon 6 homopolymer spun yarns is slightly higher than that represented by Curve 5. Even higher shrinkages are possible with increasing modification with copolyamides as described by Knox et al in USP No. 5,137,666 and by Boles, et in USP No. 5,219,503.

Figure 4B is a semi-log (base 10) plot of the log of shrinkage modulus (M_S) and of shrinkage power (P_S) calculated from Curves 3 and 4 of Fig.4A, versus spin speed (mpm); wherein M_S (Curve 1) is defined, herein, as the result of dividing the values of Curve 4 by those of Curve 3 (of Fig.4A) and plotting the result versus spin speed; and wherein P_S (Curve 2) is defined, herein, as the result of the product of values of Curve 3 and of Curve 4 (of Fig.4A) and plotting the results versus spin speed.

The values of P_S are observed to reach a maximum at spin speeds of about 3500-4000 mpm and then decrease rapidly with increasing spin speed, while M_S increases with spin speed throughout this spin speed range. No spin-oriented
5 filaments have been found to have the combination of shrinkage properties of the B-filaments of the invention. The fiber structure of the filaments represented by a decreasing P_S with increasing speed (and decreasing elongation-to break) are characteristic of the A-filaments
10 used herein for forming the B-filaments of the invention.

Figure 5A is an analogous plot to Fig.4A for B-filaments formed by treatment of A-filaments by Type I and II processes of the invention; wherein Curve 1 is the plot of shrinkage S for B-filament yarns formed by treating A-
15 filaments at temperature T_3 versus the spin speed (mpm) used in the preparation of the A-filament yarns; and Curve 2 is representative of the ST_{max} for the B-filaments corresponding to Curve 1 versus spin speed.

Figure 5B is an analogous semi-log (base 10) plot of the log of M_S and of P_S to that of Fig.4B; wherein the M_S (Curve 1) is defined, herein, as the result of dividing the values of Curve 2 by those of Curve 1 (both from Fig.5A) and plotting the result versus spin speed; and wherein P_S (Curve 2) is defined, herein, as the result
25 of the product of values of Curve 1 and of Curve 2 (both from Fig.5A) and plotting the results versus spin speed. The values of P_S are observed to reach a maximum as in Fig.4B, but also is followed by an apparent minimum not observed in Fig.4B; while M_S (Curve 1) increases with spin
30 speed throughout this speed range as it did for B-filaments in Fig.4B (Curve 1). The minimum for P_S is believed to be associated with the thermal stability of the B-filaments formed by treating of the A'-filaments; wherein A-filaments $\rightarrow$ A'-filaments with increasing spin
35 speed (i.e. SIC); but where ST_{max} continues to increase with spin speed by the process treatments of the invention.

Figure 6 is a plot of the logarithm of the modulus (stiffness) of a thermoplastic material, such as polyester, versus temperature. The modulus initially is relatively insensitive to temperature (denoted as the "glass" region (I) and begins to decrease at the (primary) glass-transition temperature T_g and levels off at the secondary glass-transition temperature (T_{ll}), where the region between T_g and T_{ll} is often referred to as the "leather" region (II) and the secondary glass-transition temperature T_{ll} is more commonly called the liquid-liquid transition temperature in open literature and also herein, and denotes the onset of the "ideal" rubber-like elastic region (III) and at higher temperatures the polymer begins to melt, noted as region IV. Polyester may be drawn between T_g and T_{ll} without significant crystallization. Crystallization, however, occurs in region III making the crystalline yarns of region III not "ideal" as to their elastic properties.

Figure 7 is a superimposed plot of dynamic shrinkage tension (ST) values versus treatment temperature (T, C) for an undrawn POY (curve A) and for the corresponding drawn yarn (Curve B); wherein the undrawn POY (curve A) has a characteristic $T(ST_{max})$ below about 100 C and the drawn product (curve B) has a characteristic $T(ST_{max})$ typically between about 150 C and about 180 C (that is, in the range of the $T_{c, \frac{1}{2}}$ and $T_{c, max}$, where $T_{c, \frac{1}{2}}$ is the temperature where the rate of crystallization is one-half of that at $T_{c, max}$ (refer to Fig.14 for a more detailed discussion).

Figure 8 is a similar superimposed plot, as in Fig.7, of dynamic shrinkage tension (ST) versus treatment temperature (T) for undrawn A-filaments (Curve A); Curve B is of B-filaments prepared by treating A-filaments of Curve A per the invention at T_c^0 (i.e., about 120 C); and Curve C is of undrawn B-filaments prepared by treating A-filaments at $T_{c, \frac{1}{2}}$ (i.e., about 150 C). The yarns represented by Curves B and C are indicative of the B-filaments prepared by process Type I and II, respectively.

Figure 9 shows the relationship between the relaxation/heat setting temperature (T_R) (where T_R is measured in degrees C) and the residual draw-ratio of the drawn yarns $(RDR)_D$ for nylon 66 graphically by a plot of
5 $[1000/(T_R+273)]$ vs. $(RDR)_D$ as described by Boles et al in USP No.5,219,503. Drawn filaments, suitable for critically dyed end-uses are obtained by selecting conditions met by the regions I (ABCD) and II (ADEF). Acceptable along-end dye uniformity is achieved if the
10 extent of drawing and heat setting are balanced as described by the relationship: $1000/(T_R + 273) \geq [4.95 - 1.75(RDR)_D]$. This relaxation temperature vs. $(RDR)_D$ relationship is also preferably applied when co-drawing and heat treating or heat treating previous drawn co-
15 mingled mixed-filament yarns comprised of nylon and polyester filaments.

Figure 10 is a representative plot of the elongations-to-break (E_B) of spin-oriented undrawn nylon 66 and polyester filament yarns versus spinning speed.
20 Between about 3.5 Km/min and 6.5 Km/min (denoted by region ABCD) and especially between about 4 and 6 Km/min, the elongations of undrawn polyester and nylon filaments are of the same order. The elongation of the undrawn nylon filaments may be increased by increasing polymer RV
25 (Chamberlin USP Nos. 4,583,357 and 4,646,514), by use of chain branching agents (Nunning USP No. 4,721,650), or by use of selected copolyamides and higher RV (Knox et al in USP No. 5,137,666). The elongation of the undrawn polyester may be increased by lower intrinsic viscosity
30 and use of copolyesters (Knox in USP No. 4,156,071 and Frankfort and Knox USP Nos. 4,134,882 and 4,195,051), and by incorporating minor amounts of chain branching agents (MacLean USP No. 4,092,229, Knox in USP No. 4,156,051 and Reese in USP Nos. 4,883,032, 4,996,740, and 5,034,174).
35 The elongation of polyester filaments is especially responsive to changes in filament denier and shape, with elongation decreasing with increasing filament surface-to-

volume (i.e., with either or both decreasing filament denier and non-round shapes).

Figure 11A is a representative dynamic Thermal Mechanical Analyzer (TMA) percent extension (ΔL) vs. temperature plot (also referred to in the literature as "creep") under a 300 mg/d load for A-filament yarn showing approximate values of the fiber T_g , T_g , T_{CC} , T_C^0 , $T_{C,\frac{1}{2}}$ and $T_{C,max}$.

Figure 11B is a representative plot of the derivative $(\Delta L)/\Delta T$ of the ΔL (extension under load of 300 mg/d) value from Fig. 11A plotted versus temperature to show various thermal transition temperatures. Fig. 11B provides a very useful technique to visualize thermal changes occurring prior to major crystallization ($T_{C,\frac{1}{2}}$).

Figure 12 is a representative DSC temperature scan of a Type A filament to show the glass-transition temperature (T_g), the peak temperature of cold crystallization (T_{CC}), the temperature of the onset of crystallization (T_C^0), the temperature of maximum rate of crystallization ($T_{C,max}$), the onset of melting (T_m') and the zero-shear melting point (T_m^0).

Figure 13 is a representative dynamic shrinkage tension (ST) versus temperature scan of an A-filament; wherein the approximate values of the fiber T_g , $T(ST_{max})$, and T_C^0 are easily discernable and $T_{C,\frac{1}{2}}$ and $T_{C,max}$ are marked for reference. At very high levels of SIO and SIC, the ST vs. T scans look more like a rounded "table top" wherein the thermal transitions between $T(ST_{max})$ and $T_{C,max}$ are not so easily determined from such a plot without sophisticated peak resolution computer analysis.

Figure 14 is a representative plot of the crystallization rate versus temperature of polycondensation type polymers, such as polyesters and polyamides; wherein the values of T_g and T_m^0 are marked and the values of T_C^0 , $T_{C,\frac{1}{2}}$, and $T_{C,max}$ correspond to temperatures along the x-axis T'_1 , T_1 and T_C ,

respectively. For 2GT polyester polymer of nominal textile viscosity (intrinsic viscosity of 0.65 and LRV of 20.8), the values of T_g , T_{11} , T_c^0 , $T_{c,\frac{1}{2}}$, $T_{c,max}$, and T_m^0 are approximately: 65-70 C, 95-100, 120-130, 150-160 C, 180-190 C, and 250-260 C, respectively.

Figure 15 is a representative plot of shrinkage (S) for B-filaments versus hot tube treatment temperature (not necessarily equal to yarn temperature due to less than perfect heat-transfer) for A-filament yarns spun at 4000 mpm (Curve 1); 4500 mpm (Curve 2) and 5000 mpm (Curve 3).

Figure 16 is similar plot, but of STmax (g/d) for B-filaments versus hot tube temperature for A-filament yarns spun at 4000 mpm (Curve 1); 4500 mpm (Curve 2) and 5000 mpm (Curve 3).

Figure 17 is a representative plot of shrinkage (S) versus spin speed for A-filaments (curve 1 - control, without steam) and of B-filaments (curves 2 to 4) treated at 3 different pressures of superheated steam at 245 C; thus curve 1 = 0 psi (0 kg/cm²); curve 2 = 160 psi (54.6 kg/cm²); curve 3 = 140 psi (47.7 kg/cm²); and curve 4 = 120 psi (40.9 kg/cm²).

Figure 18 is a representative plot of shrinkage S of B-filaments versus on-line steam treatment pressure expressed in units of psi (where 1 psi = 0.314 kg/cm²) spun at 4700 ypm (4296 mpm) - Curve 1; and at 4900 ypm (4479 mpm) - Curve 2. The peak shrinkage S vs. steam pressure appears to be obtained at higher steam pressures at high spinning speeds (e.g., reduced exposure times).

Figure 19 is a similar plot of shrinkage (S) versus on-line steam treatment pressure expressed in units of psi (where 1 psi = 0.341 kg/cm²) for B-filaments spun at 4900 ypm (4479 mpm); where curve 1 is indicative of low dpf B-filaments and curve 2 is indicative of higher dpf B-filaments. The peak pressure moves upwards as dpf

increases, most likely because of limits of heat transfer rates for the larger cross-section filaments.

Figure 20 is a similar plot, but of ST_{max} (g/d) versus on-line steam treatment pressure in units of psi (1 psi = 0.341 kg/cm²) for B-filaments spun at 4900 ypm (4479 mpm); where curve 1 is indicative of low dpf B-filaments and curve 2 is indicative of higher dpf B-filaments. As in Fig.19 the peak moves to higher psi-values for the higher dpf B-filaments.

Figure 21 is a schematic representation of a 3-phase fiber structure model to show crystalline regions (C), amorphous regions (A) and interface regions (B), herein referred to as "mesophase" which are meta stable, i.e., sensitive to low temperature treatments and may be either incorporated into the amorphous phase (A) or into the crystalline phase (C), depending on the treatment temperature, time at the treatment temperature, and the tension (or lack of tension) during the treatment.

Figure 22 shows different schematics of the fiber structure shown in Fig.21. On the left, schematic I represents high speed spun crystalline filaments of Type A comprised of a primary crystal phase (C), a secondary crystal phase (B), referred to as mesophase, above and amorphous phase (A). Under the thermal treatments (ΔH) of the invention it is believed the mesophase is melted-out, providing a thermally unstable amorphous phase held together by a primary crystal phase as represented in the center schematic II. On further heating (ΔH), this structure is transformed into a re-crystallized phase represented in schematic III on the right. Under conventional heat treatments of A-filaments, the metastable phase (B) is not isolated, but readily goes to a conventional stable crystalline structure. The invention permits the isolation of this metastable phase B, and consequently the formation of the novel B-filaments that have surprising new properties.

Figure 23 represents an application of the existence of this metastable phase B. In Fig.23 the FTT Yarn Bulk (i.e., of false-twist textured yarns) is plotted versus the spin speed of various precursor undrawn feed
5 yarns. Despite an increase in crystallinity (density) and decrease in shrinkage S, the textured yarn bulk continually increases with increasing spin speed (Curve 1) with increasing spin speed. If the extent of crystallization is "totally" suppressed by use of water
10 quenching (as described by Vassilatos in USP No. 4,425,293), higher bulk levels are obtained (curve 5) Intermediate levels of bulk can be obtained as the degree of shrinkage is suppressed (herein by higher spin temperatures and use of delay quench) so to provide lower
15 spinline "extensional viscosity" and thereby lower SIC of the SOY as represented by Curves 2 through 4.

Surprisingly, the bulk increases (up to a point) (not shown here in Fig.23) with increased texturing speed (i.e., shorter residence time). We believe this maybe
20 associated with the lack of thermal stability of the "B" phase. If the treatment (e.g., texturing in this case) is too slow, then the re-crystallization of "B" phase begins prior to full twist insertion. This has been confirmed by in-line pre-setting high speed spun yarns of amorphous
25 phase "A" prior to texturing and resulting in reduced bulk. On the other hand, if the extent of the "B" phase can be increased as indicated by an increase in the shrinkage of the feed yarn, there is observed an increase in textured yarn bulk as represented by points 1 -> 2-> 3->
30 > 4->5. The process of the invention provides uniform feed yarns of high shrinkage and shrinkage power especially suitable for high speed (low residence time) texturing. Alternatives, such as use of long delay quench zones and "too" hot polymer (used in Fig. 23) provide
35 higher bulk but unacceptable along-end uniformity.

Figure 24A is a plot of measured shrinkage S of a AB mixed filament yarn comprised of 70/17 denier B-filaments and 70/100 denier A-filaments versus the

shrinkage of the B-filament component. Line 1 is the expected trend and Line 2 is observed for high shrinkage filaments of undesireably low ST_{max} , i.e., being incapable of overcoming the inter-filament friction and entanglements to develop the expected high shrinkage in a mixed AB filament yarn.

Figure 24B (line 1) is the expected plot of measured ST_{max} for AB mixed filament yarns vs. the ST_{max} of the B-filament component; line 2 is a plot of calculated ST_{max} values (weight average ST -values based on total denier of each component) versus the observed ST_{max} -values. Line 2 shows that the expected ST_{max} of a composite yarn is less than that of a single high ST_{max} filament yarn and is well represented by the weighted average of A and B components.

Figure 25 is a representative plot of the initial modulus of 65 RV Nylon 66 SOY (Line 1) and of 21 LRV 2GT polyester SOY (Line 2), wherein the zero-shear (Newtonian) melt viscosity of 21 LRV polyester polymer is about the same 65 RV Nylon 66 polymer. Line 3 is a plot of the initial modulus of polyester filaments heat treated according to Type II process of the invention. Lines 4 and 5 are plots of the percent of the polyester core vs. spin speed required to obtain a 30 g/d composite nylon sheath/polyester core filament yarn corresponding to polyester filaments of Lines 2 and 3, respectively; where the composite modulus (M_C) is a linear weighted average of the modulus of the polyester (M_p) and nylon (M_n) components; i.e., $M_C = XM_p + (1-X)M_n$, where X is volume percent of the polyester component. By incorporating the higher modulus polyester phase into the nylon filament, the desired modulus of the nylon sheath SOY may be obtained at a lower spin speed or a higher modulus may be obtained at the same spin speed.

The polyester polymer used for preparing spin-oriented filaments of the invention is selected to have an intrinsic viscosity IV in the range of 0.5 to 0.7, the IV

is related to the relative viscosity (LRV) through the expression:

$$IV = 0.07238[1.28(LRV+1.2)]^{0.658};$$

a zero-shear melting point (T_m^0) in the range about 240 C to about 280 C; and a glass-transition temperature (T_g) in the range about 40 C to about 80 C (wherein T_m^0 and T_g are measured from the second DSC heating cycle under nitrogen gas at a heating rate of 20 C per minute). The said polyester polymer is a linear condensation polymer composed of alternating A and B structural units, where the A's are hydrocarbylenedioxy units of the form $[-O-R'-O-]$ and the B's are hydrocarbylenedicarbonyl units of the form $[-C(O)-R''-C(O)-]$, wherein R' is primarily $[-C_2H_4-]$, as in the ethylenedioxy (glycol) unit $[-O-C_2H_4-O-]$, and R'' is primarily $[-C_6H_4-]$, as in the 1,4-benzenedicarbonyl unit $[-C(O)-C_6H_4-C(O)-]$, such to provide a sufficient number of ethylene terephthalate, $[-O-C_2H_4-O-C(O)-C_6H_4-C(O)-]$ repeat groups so to maintain the T_m^0 between about 240 C and about 280 C. Suitable poly(ethylene terephthalate), herein denoted as PET or 2GT, based polymer may be formed by a DMT-process, e.g., as described by H. Ludewig in his book "Polyester Fibers, Chemistry and Technology", John Wiley and Sons Limited (1971), or by a TPA-process, e.g., as described in Edging USP No. 4,110,316. Included are also copolyesters in which, for example, up to about 15 percent of the hydrocarbylenedioxy and/or hydrocarbylenedicarbonyl units are replaced with different hydrocarbylenedioxy and hydrocarbylenedicarbonyl units to provide enhanced low temperature disperse dyeability, comfort, and aesthetic properties. Suitable replacement units are disclosed, e.g., in Most USP No. 4,444,710 (Example VI), Pacofsky USP No. 3,748,844 (Col. 4), and Hancock, et al. USP No. 4,639,347 (Col. 3).

Polyester polymers, used herein, may, if desired, be modified by incorporating ionic dye sites, such as ethylene-5-M-sulfo-isophthalate residues, where M

is an alkali metal cation, for example in the range of about 1 to about 3 mole percent, and representative chain branching agents used herein to affect shrinkage and tensiles, especially of polyesters modified with ionic dye sites and/or copolyesters, are described in part by Knox in USP No. 4,156,071, MacLean in USP No. 4,092,229, and Reese in USP Nos. 4,883,032; 4,996,740; and 5,034,174. To obtain undrawn feed yarns of low shrinkage from modified polyesters, it is generally advantageous to increase polymer viscosity by about +0.5 to about +1.0 LRV units and/or add minor amounts of chain branching agents (e.g., about 0.1 mole percent). To adjust the dyeability or other properties of the spin-oriented filaments and the drawn filaments therefrom, some diethylene glycol (DEG) may be added to the polyester polymer as disclosed by Bosley and Duncan USP No. 4,025,592 and in combination with chain-branching agents as described in Goodley and Taylor USP No. 4,945,151.

The treatment process of the invention improves (transforms) the shrinkage properties of low shrinkage crystalline spin-oriented (undrawn) direct-use filament yarns (Type A), by post-treating the A-filaments in split or coupled (on-line) processes by anyone of the hereinbefore mentioned processes ($I_{cp,sp}$ or $II_{cp,sp}$) to provide spin-oriented Type B filament yarns; i.e., yarns of high P_g with all of the desired characteristics listed hereinbefore. The treatment process consists of rapidly heating followed by rapidly cooling Type A-filaments under tension prior to winding up the newly formed B-filament yarns into packages or into a beam of many yarns. During the treatment processes of Type I and II an increase tension is observed with essentially no permanent change in filament denier, wherein the increase in process tension is in the range of about the improvement in shrinkage tension (ST_{max}) of the treated A-filaments; i.e., about $ST_{max}(B) - ST_{max}(A)$. The "heat" may be provided by steam jets, hot tubes, microwave, low friction heated surfaces, etc. Each will require careful selection of

process variables (steam pressure and temperature, hot tube temperature, diameter, length, etc.) to achieve the desired rapid heat transfer (heating and cooling) necessary to transform Type A-filaments into Type B-
5 filaments of desired shrinkage properties.

It is conjectured that the combination of high rate of heating followed immediately by a high rate of cooling "selectively melts" the "small" crystals, leaving a "strained" network held together by "large" thermally
10 stable crystals (structure B in Fig.22B) formed previously by the high speed spin orientation process used in the preparation of the low shrinkage crystalline Type A-filaments (structure A of Fig.22A). The "strained" network, essentially free of the small crystals (or
15 interchain order), provides for the combination of high shrinkage (S) and high ST_{max} , i.e., high P_s , as defined by the product of percent shrinkage (S) and ST_{max} . Conceptually, it is believed that the process of the invention provides a careful selection of heat treatment
20 temperature and rates of heating and cooling that destabilize the crystalline structure of the A-filaments and prevents re-stabilization of the newly formed fiber structure (of the B-filaments). At conventional slow rates of heating and cooling, it is believed that the
25 ongoing process of re-crystallization re-stabilizes the "intermediate" structure" (herein referred to as a "meso-structure") of the B-filaments such that the high shrinkage power of the treated A-filaments is not realized. The processes of the invention develop the
30 desired "meso-structure" of the B-filaments and inhibit the rapid re-stabilization of the "meso-structure" from occurring and thereby improving the properties of undrawn low shrinkage power A-filaments to provide undrawn high shrinkage power B-filaments.

35 The Type I and Type II B-filaments differ in their $T(ST_{max})$ and in their RDDR values. Type I B-filaments typically are of higher RDDR and $T(ST_{max})$ of less than about 100 C (i.e. less than about the polymer

T_{11}); while Type II B-filaments typically have lower RDDR than the A-filaments from which they were formed and $T(ST_{max})$ values are about 10 C higher. Combining Type I and Type II B-filaments provides a simplified route to differential shrinkage and dye rate mixed $B_I B_{II}$ -filament yarns when dyed under atmospheric conditions without dye carriers.

The high shrinkage B-filament yarns according to the invention may be used as direct-use textile yarns, but may also be used as preferred draw feed yarns as in draw-warping, draw air-jet texturing, and draw false-twist texturing wherein Type I B-filaments are selected if high dyeability is important and Type II B-filaments are selected where high ST_{max} and $T(ST_{max})$ values are important for providing for improved stability in especially high speed textile processing. The Type of B-yarn is selected based on specific needs of the textile processing and the end-use fabric requirements. The level of filament bundle interlace and type/level of finish are also selected based on the downstream processing needs and aesthetics desired.

Soft bulky yarns (and fabrics therefrom) are provided from use of mixed-filament yarns comprised of high shrinkage B-filaments of "high" dpf (typically about 2 dpf for top weight fabrics) and low shrinkage A'-filaments of "low" dpf (preferably less than about 1; e.g. about 0.2 to 0.8 dpf) with the low shrinkage fine denier A'-filaments providing the soft surface of the bulky yarn and the heavier dpf "core" filaments providing the fabric with improved "body" and "drape" (i.e., less "mushy"). Increasing the dpf of the B-filaments increases the firmness of the fabric made from the mixed A'B-filament yarns. The frictional characteristics may be enhanced to be more silk-like by use of silicon dioxide versus titanium dioxide delusterants. Other inert metal oxides may be used as delusterants. The hydrophilicity of the filaments may be enhanced by using undrawn filaments

treated during spinning with caustic spin finish as taught by Grindstaff and Reese in USP No. 5,069,844).

Other variations of the invention are possible; for example, undrawn polyester/nylon mixed-filament yarns
5 may be treated according to the invention to provide for polyester filaments of high shrinkage and high shrinkage tension, while the high speed spin-oriented nylon 66 filaments typically have shrinkages in the range of about 3-6%. On shrinkage, the low modulus nylon filaments will
10 provide predominately form the surface of a bulky polyester/nylon filament yarn. Further, heat treating according to the processes of the invention of undrawn A/A'-bicomponent filaments provides a simple route to helical crimped bulky A'/B-bicomponent filament yarns by
15 using filament components of different thermal stability (e.g., A/A' polyester bicomponent filaments and A/C' polyester/nylon biconstituent filaments (especially wherein the polyester (A) is modified per the teachings of Jennings in USP No. 4,702,875 which reduces the tendency
20 of the polyester (A) and nylon (C) components to separate.

Single polymer torque-free helical crimp filaments may be provided by asymmetrically heating via localized friction, as described by Frankfort (USP No. 3,905,077) of crystalline low shrinkage polyester SOF and
25 then passing said asymmetrically heated filaments through one of the heat treatment steps according to the invention or by providing asymmetric filaments such that they are characterized by differing radial shrinkage power and then passing such a filament yarn through one of the heat
30 treatment step of the invention.

Advantageously, if desired, mixed-filament yarns may be prepared according to the invention from undrawn feed yarns by incorporating filaments of different deniers and/or cross-sections (including filaments of one or more
35 longitudinal voids) to reduce filament-to-filament packing and thereby improve tactile aesthetics and comfort. Unique dyeability effects may be obtained by co-mingling

filaments of differing polymer modifications, such as homopolymer polyester dyeable with disperse dyes and ionic copolymer polyester dyeable with cationic dyes or disperse dyeable polyester and acid dyeable nylon or cationic dyeable polyester and acid dyeable nylon. Sheath/core A/A' bicomponent filaments may be used to provide the desired helical crimp formation on treatment according to the invention, but also provide a surface of desired dye chemistry (e.g., acid-dyeable nylon sheath and disperse dyeable polyester core or cationic-dyeable polyester sheath and acid-dyeable core). Chemically active liquid-film and plasmas may be incorporated in the treatment step of the invention to provide modified filament surfaces, e.g., for increase in hydrophilicity and stain resistance.

The fine filament yarns of this invention are also suitable for warp-drawing, air-jet texturing, false-twist texturing, gear crimping, and stuffer-box crimping, for example; and the improved low shrinkage filament yarns are desirable for use as direct-use flat textile yarns and as feed yarns for air-jet texturing and stuffer-box crimping wherein no draw need be taken and the low shrinkage is desirable so as not to lose tensiles during such no-draw texturing. The filaments (and tows made therefrom) may also be crimped (if desired) and cut into staple and flock. The fabrics made from these improved yarns may be surface treated by conventional sanding and brushing to give suede-like tactility. The filament surface frictional characteristics may be changed by selection of cross-section, delusterants, and through such treatments as alkali-etching. The improved combination of filament strength and uniformity makes these filaments, especially suited for end-use processes that require fine filament yarns without broken filaments (and filament breakage) and uniform dyeing with critical dyes. The fine denier filament polyester yarns of the invention are especially suitable for making of high-end density moisture-barrier fabrics, such as rainwear and medical garments.

The fine filament yarns, especially those capable of being cationic dyeable, may also be used as covering yarns of elastomeric yarns (and strips), preferably by air entanglement as described by Strachan in
5 USP No. 3,940,917. The fine filaments of the invention may be co-mingled on-line in spinning or off-line with higher denier polyester (or nylon) filaments to provide for cross-dyed effects and/or mixed-shrinkage post-bulkable potential, where the bulk may be developed off-
10 line, such as over feeding in presence of heat while beaming/slashing or in fabric form, such as in the dye bath. The degree of interlace and type/amount of finish applied during spinning is selected based on the textile processing needs and final desired yarn/fabric aesthetics.

15 Indeed, further modifications will be apparent, especially as these and other technologies advance. For example, any type of draw winding machine may be used; post heat treatment of the feed and/or drawn yarns, if desired, may be applied by any type of heating device
20 (such as heated godets, hot air and/or steam jet, passage through a heated tube, microwave heating, etc.); finish application may be applied by convention roll application, herein metered finish tip applicators are preferred and finish may be applied in several steps, for example during
25 spinning prior to heat treatment and after said heat prior to winding; interlace may be developed by using heated or unheated entanglement air-jets and may be developed in several steps, such as during spinning and after heat treatment and other devices may be used, such by use of
30 tangle-reeds on a weftless warp sheet of yarns.

TEST METHODS

The polyester parameters and measurements mentioned herein are fully discussed and described in the aforesaid Knox, Knox and Noe, and Frankfort and Knox
35 patents, all of which are hereby specifically incorporated herein by reference, so further detailed discussion, herein would, therefore be redundant. The thermodynamic

transition temperatures, such as T_g are calculated according to the method of R. F. Boyer ["Order in the Amorphous State of Polymers", ed. S. E. Keinath, R. L. Miller, and J. K. Riecke, Plenum Press (New York), 1987];

5 i.e, $T_x(\text{degrees C}) = \{K_x(T_m^0 + 273) - 273\}$, where the constant " K_x " is 0.65, 0.7, 0.7125, 0.725, 0.75, 0.775, 0.80, 0.825, and 0.85, respectively for T_x corresponding to: T_g , T_{11} , T_1 , T_2 , T_c^0 , T_3 , $T_{c, \frac{1}{2}}$, T_4 , and $T_{c, \max}$; wherein T_m^0 is the polymer zero-shear melting point

10 measured by DSC at a heating rate of 20 C/min. Test methods used herein for characterizing companion nylon polymer and filaments are given in Knox et al in USP No. 5,137,366 and in Boles et al in USP. No. 5,219,503.

Abbreviations used in the Tables are: initial

15 modulus (MOD), boil-off shrinkage (S); dry-heat shrinkage (DS), tenacity-at-7% elongation (T7); tenacity-at-20% elongation (T_{20}); textile tenacity (TEN); break tenacity (TBK); post-yield modulus (PM); DPF = denier per filament; EB = percent elongation-to-break; RDR = residual draw-

20 ratio; YPM = yards per minute; MPM = meters per minute; G/D or GPD = grams per denier; G/DD = grams per drawn denier; V = spin speed; C = degrees centigrade; K = degrees Kelvin; density (DEN. and also ρ) in units of g/cc = grams per cubic centimeter; SV = sonic velocity in units

25 of KM/SEC = kilometers per second; M_{sonic} = sonic modulus in units of 10^{10} dynes per cm^2 ; COA = crystalline orientation angle in degrees; CS = average crystal size (width) in Angstroms; LPS = long period spacing in Angstroms; X_v = percent volume crystallinity by density;

30 R(or RND)= round; T(or TRI) = trilobal; LRV = laboratory relative viscosity; IV (and also $[\eta]$) = intrinsic viscosity; DDR = as measured disperse dye-rate; RDDR = relative disperse dye rate as defined in Knox (but normalized to 1 dpf); K/S = measure of dye depth by

35 reflectance; Δ_n = total birefringence; T_p = polymer melt temperature (C); DxL = capillary dimensions, diameter and length; XF = cross-flow quench; RAD = radial quench; DQ = delay quench; L_D = length of delay zone (cm); L_C = length

of convergence zone (cm); DT = draw tension (g/d); DR = draw-ratio; Plate = heater plate (C); psi = pounds per square inch (= 1 psi = 0.07 kg/cm²); DS = denier spread (%); OFF = no heat applied; RT = room temperature (taken
5 as 21 C, unless specified); NA = not applicable ; "----" = no data available. The Letter "C" when used with an Item No., as in Item 1C denotes a control or comparative yarn not of the invention

For convenience, the different process types
10 described herein before are listed below:

Type I and II: A-filament -> B-filament (Areas A and B in Fig. 1).

Type III: B-filament + low temp. draw -> higher tensile B-filaments (Area C in Fig.1).

15 Type IV: A'-filament -> A' filament of higher shrinkage and shrinkage tension, but still having a $(1 - S/S_m)$ value greater than 0.9, via treatment by Process Type II.

Type V: Pretreatment of A, A/A', A/C, AC'
20 filaments by asymmetric surface heating followed by Process Types I, II, or III.

Type VI: Relaxation of B, A'/B, B/C', A'B, BC' filaments followed by redraw and second relaxation.

Type VII: Drawing of Type A-filaments at draw
25 temperatures between the polymer T_g and T_{11} without post-heat treatment to provide uniform partially or fully drawn B-filaments.

The invention lends itself to further variations and ways to take advantage of the benefits of the yarns of
30 the invention in various drawing and/or heat treatment processes as described hereinafter. The following examples further illustrate the invention and are not intended to be limiting.

EXAMPLE I

In Example I undrawn crystalline SOF yarns of Type A are prepared over a wide range of melt spinning process conditions and before winding up into a package of yarn, the A-filaments are rapidly heated by passing through a superheated steam chamber of varying temperatures and pressures. In Example I the polyester polymer of 20.8 LRV (0.65 IV) was melted to a temperature T_p of 293-295 C, approximately 40 C above the polymer melting point T_m of about 254-256 C. The polymer contained 0.3% TiO_2 as a delusterant. The filament yarns were spun using 17-hole spinnerets of DXL of 15 mils (0.381 mm) x 60 mils (1.905 mm). The mass flow rate (w, grams per minute) is metered to provide filaments of denier 2.1, 2.9, and 4.1 at withdrawal spin speeds (V) of 4500 ypm (4115 mpm) to 5300 ypm (4846 mpm). The freshly extruded filaments are protected with an unheated short 2-inch (5 cm) shroud to protect the face of the spinneret from being cooled by stray air currents and then rapidly quenched using radially directed room temperature air at a flow rate of 18.5 mpm using a radial quench chamber, as described in Knox, and the fully quenched filaments are converged into a filament bundle using a metered finish tip applicator guide at a distance L_c of 32 inches (81 cm). The low shrinkage crystalline filament bundle at a temperature below the polymer T_g is passed through a steam chamber of varying temperature and pressure, wherein the filaments are rapidly heated and then rapidly cooled; followed by application of interlace and then wound up into packages. Detailed process and product results are summarized in Tables 1A through 1E.

The shrinkage of the crystalline low shrinkage A-filaments is observed to increase with steam pressure and reach a maximum and then decrease with increasing pressure. The peak steam pressure increases as the spin speed increases for a given filament denier and increases with filament denier at a given spin speed. Except for Item 1A-8, all filaments have a $T(ST_{max})$ of less than 100

C; i.e., less than about the calculated thermal transition T_{11} of about 96 C for a polyester polymer T_m^0 of 254 C, and herein are said to have been treated by Process Type I versus Item 1A-8 filaments which are said to have been
5 treated by Process Type II.

EXAMPLE II

Example II repeats Example I except for use of 27-hole spinnerets. In general the finer filaments provided by the 27-hole spinneret at the same mass flow
10 rate provides for higher ST_{max} , but also lower shrinkage S ; hence giving comparable P_S , but higher M_S .

COMPARATIVE EXAMPLE III

In Example III the low shrinkage crystalline SOY were prepared according to Example I, except 34-capillary
15 spinnerets were used to extrude polymer at T_p of 290 C and quenched by a cross-flow quench chamber fitted with an unheated 2-inch (5 cm) screen mesh shroud, and the filament bundle being converged at 30-inches (76 cm). Process details are given in Table 3. None of the items
20 of Example III had ST_{max} -value greater than 0.15 g/d and are not considered as preferred high shrinkage power yarns of the invention; but Items 3-2 and 3-3 are considered as useful as improved draw filament yarns of the invention for draw texturing with a combination of shrinkage
25 parameters; namely, ST_{max} of at least about 0.1 g/d, M_S of at least about 0.2 g/d, and P_S values of at least about 1.5 (g/d)% (as represented by Area A in Figure 1)

COMPARATIVE EXAMPLE IV

Example IV repeats Example III, but at lower
30 steam pressures and steam temperatures. Most of the conditions did not supply sufficient heat to alter the crystalline feed filament yarns (Type A). For good quality of steam (i.e., no condensation) steam temperature of 245 C was selected. It is possible that if the
35 residence time was increased that the conditions in

Example 3 may have provided B-filaments. Detailed summary is given in Table 4.

EXAMPLE V

In Example V 20.1 LRV (0.64 IV) homopolymer polyester polymer containing about 0.3% TiO_2 as a delusterant was extruded at a T_p of 297 C through 48 capillaries of diameter (D) of 0.25 mm and of length (L) of 0.50 mm and the filaments were rapidly quenched using cross-flow air at 18 C and the fully quenched filaments were converged into a filament bundle using a metered finish tip applicator guide and withdrawn at speeds between 3750 to 6000 mpm and then prior to winding into packages, the filament bundle at a temperature below the polymer T_g was passed through a 200 cm hot air tube at temperatures from 120 C to 180 C. Thermocouples indicated that for this particular tube design that for the exiting air (at these high withdrawal speeds) to reach 160 C, a 250 cm tube would be required and to reach 180 C that a 300 cm tube would be required. It is believed that filament bundles treated at process temperatures in excess of about 150 C were heated to temperatures of at least about $T_{C, \frac{1}{2}}$; and are not of the invention with an inferior combination of shrinkage and dyeability properties. The tension increase for filament bundles reaching temperatures less than about $T_{C, \frac{1}{2}}$ was on the order of the improvement in $ST_{\max}$ versus the untreated crystalline SOY. The tension increase for filament bundles reaching temperatures in excess of $T_{C, \frac{1}{2}}$ of the yarn is greater than the improvement of the shrinkage tensions and suggests significant "aerodynamic draw" is taking place which decreases yarn dyeability and raises $T(ST_{\max})$ to values greater than $T_{C, \frac{1}{2}}$, making these yarns very similar to fully drawn yarns (FDY) as described by Davis et al in USP No. 4,195,161; and not considered as yarns of the invention. The length of the hot tube, temperature of the air (especially the exiting temperature), diameter of the tube, spinning speed, total yarn denier, number of filaments, and percent finish-on-yarn (FOY) determines if

the filaments are exposed to temperatures of at least about $T_{C, \frac{1}{2}}$ and therefore it is not readily possible to assume that based on tube temperature alone that the yarn has been treated at filament temperatures greater than $T_{C, \frac{1}{2}}$. Detailed summary is given in Table 5.

EXAMPLE VI

In Example VI, filament yarns were spun using conditions similar to that of Example V, except that a short 100 cm tube was used for treatment of the fully quenched yarns. Other process details are given in Table 6. All the items are characterized by $T(ST_{max})$ values less than 100 C and therefore indicate that even at hot tube temperatures of 180 C, the actual filament temperatures most likely did not exceed T_C^0 (at least not for sufficient length of time) and did not exceed filament temperatures of $T_{C, \frac{1}{2}}$ and therefore all items of Example VI are considered to be of Process Type I.

EXAMPLE VII

In Example VII the treated yarns of Example VI were further improved by cold drawing to final elongations in the range of 30% to 50%. Low shrinkage yarns (i.e., characterized by a $(1-S/S_m)$ value of at least about 0.9) could be uniformly cold drawn to elongations over the entire range without "neck-drawing" as taught in Knox and Noe in USP No. 5,066,447; while high shrinkage treated yarns had to be cold drawn to elongations less than about 40% and preferably to about 20-40% to avoid the possibility of thick-thin sections leading to dye nonuniformities. Although the drawing increased the treated yarns shrinkage S and ST_{max} values, their $T(ST_{max})$ -values remained essentially unchanged. This process of coupling Process Type I followed by cold drawing without post heat treatment is designated, herein as Process Type III of the invention. Process III can be coupled with the on-line spin/treatment process of Type I_{cp} or may be carried out in a separate step as in cold

drawing of Type I_{cp} B-filaments in the form of a weftless warp sheet or in air-jet texturing. The Process Type III yarns may be pre-bulked if desired, such as overfeeding in a heated relaxation step as part of the warp-draw and air-jet texturing processes.

EXAMPLE VIII

In Example VIII selected B-filaments formed in Examples 1 and 2 are warp-drawn using a wide range of conditions. Cold drawing increased ST_{max}, but did not significantly increase shrinkage S. This cold-drawing B-filaments provides a simple route to flat yarns of very high ST_{max} at low shrinkage S values versus conventional spin/draw technology. Details are summarized in Table 8.

COMPARATIVE EXAMPLE IX

Example IX is a summary of results of drawing Type A filament yarns (DUY) from Tables I-III in parent case, now a Patent USP 5,066,447. Warp-drawing results offer direct-use yarns. The conditions selected in the parent case did not provide B-filament yarns. Details are given in Table 9.

EXAMPLE X

In Example X Type A-filaments are drawn at speeds in the range of 200 to 300 mpm without post heat treatment. If the draw temperature T_D is between about the polymer T_g and the polymer T_c⁰ (preferably about the polymer T₁₁), then improvements in the shrinkage properties of the low shrinkage crystalline Type A filaments are observed. However, if the draw temperature is above the cold crystallization temperature T_{cc} of the filaments, which decreases with spin orientation of the amorphous regions (see Figure 2A) and is between about T₁₁ and T_c⁰ of the polymer, then the improvement in shrinkage properties is reduced. Type B filaments formed by this drawing process are designated herein as Type VII and is especially suited for warp-drawing and for air-jet

texturing. Process and product data are summarized in Table 10.

COMPARATIVE EXAMPLE XI

In Example XI a low shrinkage A'-filament yarn
5 formed by spinning at 6000 ypm (5486 mpm) per Frankfort
and Knox teachings was treated at various temperatures in
the relaxed and taut conditions. Various fiber structure
parameters were measured. None of the conditions
transformed the spun A' filament yarn into a B filament
10 yarn and the filaments of this example are considered to
be of sufficient thermal stability that it would also not
be affected significantly by Processes of Type I-V and
hence are designated as A' filaments. The fiber structure
data suggests that an A' filament is characterized by a
15 density of at least about 1.38 g/cm^3 and an average
crystal size of at least about 60 angstroms and a
shrinkage less than about 4-5%. Details are summarized in
Table 11.

COMPARATIVE EXAMPLE XII

20 In Example XII Type A filaments prepared
according to Knox were relaxed and taut annealed over the
temperature range of 60 to 240 C dry heat; and relaxed and
taut annealed in hot water. None of these treatments
transformed the A filaments into B filaments supporting
25 that rapid heating/cooling is required to "catch" the
intermediate metastable mesophase structure, herein
referred to as "B", before being stabilized into a A'-
state (see Fig.22 - I,II,and III. Details are summarized
in Table 12A and 12B.

30

COMPARATIVE EXAMPLE XIII

In Example XIII the A-filaments of Example XII
were drawn at draw-ratios (DR) of 1.0, 1.05, and 1.1 to
simulate commercial hot aqueous slashing and tenter frame
finishing process steps. None of the conditions
35 transformed the Type A-filaments into Type B-filaments.

confirming the results of Example XII. Details are summarized in Table 13.

COMPARATIVE EXAMPLE XIV

In Example XIV various spin-oriented filament yarns were spun to provide different levels of shrinkage S and cospun mixed-filament yarns comprised of filaments differing in shrinkage. These mixed-shrinkage filament spin-oriented yarns did not have sufficient P_S to develop bulk in tight knit and woven fabric constructions and such filament yarns are not considered to be yarns of the invention. Results are summarized in Tables 14A and 14B, respectively.

EXAMPLE XV

In Example XV various mixed-filament yarns were prepared of the type A'A and treated to transform the mixed-filament yarns into Type A'B yarns. The difference in shrinkage S and ST_{max} were measured. The yarns were knit into circular tubing and boiled off to develop bulk via mixed-shrinkage. A'B yarns having P_S values of at least about 1.5 g/d was required to develop significant bulk. The B-filaments of the invention used for mix-shrinkage yarns are characterized by P_S values of at least about 1.5 g/d. Results are summarized in Table 15.

EXAMPLE XVI

In Example XVI mixed-filament yarns of varying filaments deniers were provided by combining filament bundles of two spin packs into a single bundle for ease of experimentation. Commercially, the mixed-filaments would be provided by use of a single spinneret where in the capillary dimensions (diameter D and Length L) are selected to prove the desired filament and yarn deniers by using the following relationship:

$$(dpf)_1 \times (L/D^4)_1 = (dpf)_2 \times (L/D^4)_2$$

$$N_1(dpf)_1 + N_2(dpf)_2 = \text{yarn denier.}$$

Maximum shrinkage S and ST_{max} are found to depend of filament dpf, but in general for 0.65 IV homopolymer, the maximum S and ST_{max} is in the spinning speed range of about 4500-5000 rpm. Because these
5 filaments were predominately of high dpf, e.g., values of ST_{max} were less than 0.2 g/d and many had values less than 0.15 g/d making them not suitable for developing bulk in wovens, but can be used for developing bulk in knits and are especially suited for use as improved draw feed yarns
10 for texturing. Details are given in Table 16.

EXAMPLE XVII

In Example 17 mixed-filaments yarns are warp-draw or permitted to relax to demonstrate pre-bulking of the mixed-filament A'/B yarns. Yarns that were relaxed by
15 0.93 provided bulk. Yarns that were relaxed and then slightly drawn in a second step so that the net draw is less than about 0.98, also provided bulk, but yarns with a net draw ratio of greater than about 1.02-1.03 did not provide bulk on heat relaxation. Drawing did provide for
20 greater shrinkage yarns which, if permitted to relax in a 3rd step (i.e., in the fabric) would have generated bulk (such as Item 17A-4 with a net draw of 1.2 and a shrinkage of 19.3% and a P_S of about 7.5 (g/d)%. If the warp (draw/relax) machine had been provided with 3 or more
25 draw/relax zones, then bulk can be developed and enhanced by a relax-redraw-relax process (herein called provess Type VI). Such a process also is known to provide for increase in dyeability. Details are given in Table 17A,B.

EXAMPLE XVIII

30 In Example XVIII fabrics using 50 denier 47 filament textured yarns in the warp with a 70 denier 102 filament filling yarn comprised of 35 denier 34 filament high shrinkage component (Type B) having a 17% shrinkage and a 35 denier 68 filament low shrinkage microdenier
35 component having a 4% shrinkage (Type A') and a 150 denier 168-filament filling comprised of 75 denier 68 filament

high shrinkage component having a 15% shrinkage (Type B) and a 75 denier 100-filament microdenier low shrinkage component of about 4% (Type A'). The fabrics were relaxed scoured at 212 degrees F to allow development of bulk from the shrinkage of the mixed shrinkage filaments of the mixed-filament filling yarns. The fabrics were then dyed in a jet dyeing machine using normal polyester dyeing conditions necessitated by the higher dpf polyester warp . Heat setting at width was carried out at a lower than normal temperatures to maintain the bulk developed during scouring and jet dyeing and to enhance the overall aesthetics. Evaluation of fabric handle of these fabrics shows that the mixed-dpf mixed-shrinkage properties of the yarns add to the stiffness, bounce, crispness, and scroop, properties much desired in a microdenier fabric to simulate silk like handle. The bulk of the fabrics are the comparable to that of fabrics made with 100 % textured warp and filling yarns. Data for the spinning of the various yarns are given in Table 18. Further improvements may be made by using three component A'B₁B₂ mixed-shrinkage yarn so to provide a wider (and uniform) distribution of shrinkage.

EXAMPLE XIX

In Example XIXA-D nylon POY are spun and warp-drawn to different elongations showing the feasibility of uniformly partial drawing of nylon, making it an acceptable co-draw companion yarns with A-filaments of the invention or as undrawn companions for treatment by processes of Type I or II followed by co-drawing by process Type III to given uniform mixed-shrinkage polyester/nylon filament yarns (Table XIX is taken from co-pending application Boles 07/532,529 and 07/753/769.

EXAMPLE XX

In Example XX, the RDDR as defined in Knox, but normalized herein to a dpf of 1 instead of 2.25 (Knox RDDR-values x 1.5 = values herein), were measured for

different spin speeds (items 1-6 and items 7-23), steam pressures (Items 24-31), hot tube temperatures (Items 1-23) and for drawn B-filament yarns (Items 13-23). The post-yield modulus based on T_{20} and T_7 -values were
5 calculated for Items 1-12 and 24-31; but were calculated based on T_{10} and T_7 -values for Items 13-23 as noted by the *. The PYM-values from T_{10} and T_7 are more variable than those from T_{20} and T_7 -values; but both show a general trend of increase in PYM a decrease in RDDR where there
10 was not such a trend using T_7 , T_{10} , or T_{20} as a single parameter to estimate dye rate. The values for the various B-filaments (1-23) are compared to commercial yarns and in general are found to be greater. A value of RDDR of at least about 0.1 is preferred and a value at
15 least about 0.150 is especially preferred. Such values (especially 0.150 and greater), are considered to be atmospheric dyeable without carriers for most shades, especially with low to medium energy dyes. Very deep shades (e.g., blacks) and use of high energy dyes for
20 critical end-uses requiring excellent wash and light fastness, pressure dyeing without carriers may be required, but shorter dye cycles and/or lower pressures may be used for cost savings over that of convention spin/drawn yarns. The results of this analysis indicates
25 that the dyeability decreases as the $T(ST_{max})$ increases and especially if greater than $T_{C, \frac{1}{2}}$; hence the yarns of the invention have a $T(ST_{max})$ less than about T_{C^0} and preferably less than T_1 and especially less than about T_{11} ; wherein the values of $T_{C, \frac{1}{2}}$, T_{C^0} , and T_{11} are
30 calculated hereinbefore from the zero-shear melting point (T_m^0) of the polyester polymer. Details are summarized in Table 20.

EXAMPLE XXI

In Example XXI one mode of the process of the
35 invention (i.e., using a heated tube) for providing high shrinkage polyester filament is compared to a prior art hot tube process, also for providing high shrinkage polyester filaments; namely as described in EPA-0207489 (referred to in this Example XXI as Shimazu). Shimazu

taught use of polyester polymer of intrinsic viscosity (IV) broadly covering the range of 0.4 to 0.9, but also taught that his polymer should be melted at a temperature T_p higher than 290 C (page 12, line 25). In the process
5 of the invention the polymer melt temperature (T_p) is selected based on the polymer's melting point (T_m^0), which is in turn dependent on the polymer composition, e.g., IV, whether modified with copolyesters or by the addition of ionic monomeric units for ionic dyeability, etc, and our
10 polymers are of IV in the range of 0.5 to 0.7, and the T_p is controlled within the range of 20 C to 50 C above the selected polyester polymer's melting point (T_m^0).

Shimazu extruded his melt directly into a heated zone (shroud) of about 15 cm in length for a delayed
15 quench environment at temperatures at least about 200 C (typically 250 C to 285 C was used in his Examples) before blowing cooling air (at 20 to 10 C) along a length of 100 to 150 cm to cool his filaments to a preferred temperature lower than $T_g + 40$ C (i.e., less than about 105-110 C for
20 the 0.64 IV polyester used in Examples - his teaching permits selection of yarn temperatures T_y covering the range of T_g to T_{11} , i.e., the "leather" region as represented in our Figure 6 and which may be above the $T(ST_{max})$ of the yarn - in our opinion an unstable and
25 variable structural condition for further processing).

In contrast, in the process of our invention, the polymer melt is extruded directly into a cooling chamber (preferably a radial cooling chamber fitted with a thin non-heat conductive gasket such that the distance
30 between the point of extrusion, the face of spinneret (that is usually recessed slightly), and the point of air impingement is minimized to about 2-5 cm) where the cooling medium is typically air in the range of 10C to 25 C. We have found that attenuation is essentially
35 completed prior to our A filaments (or A' filaments) exiting such cooling chamber into a "second quench zone" comprised of a protective open air chamber at room temperature or into a cross-flow air chamber to insure

complete attenuation to temperatures less than the polymer T_g (i.e., to a final stable structural state prior to convergence and application of finish and/or prior to any additional processing, i.e., by Type I or Type II heating and cooling. We believe the heated shroud used by Shimazu, retards crystallization and favors orientation, thereby providing filaments of higher orientation but of lower dyeability than filaments prepared by our process without such heated shroud.

After attenuation is complete (as defined by reaching a constant withdrawal speed only, rather than by the usual definition of constant withdrawal speed and yarn temperature less than T_g), Shimazu's filaments are "conditioned" in a heated chamber. Shimazu's conditioning chamber is a tube of 80 to 200 cm in length heated to 120 to 160C. This is similar to one of the methods used in our process, except that our tube temperature and length are adjusted to maintain a yarn temperature T_y between about T_{11} and about T_3 to favor the kinetics of melting out intercrystalline small nuclei and permit the amorphous chains to assume higher orientation, as measured by higher shrinkage tension and reduced elongation to break, without eliminating the larger crystalline network formed by the combination of high withdrawal speeds and rapid filament quenching (e.g., by selection of air temperature, filament dpf/cross-section and filament to filament spacing). The yarns of both processes may be wound up at speeds in an overlapping range of 4000 to 6000 mpm, but the process of the invention may use lower withdrawal speeds, e.g., as low as 2000 mpm for spinning micro-denier filaments (e.g., less than 1 dpf).

The process differences from Shimazu's process include our further requirement that the yarn entering the conditioning zone, not only be at a temperature for structural stability and uniformity (i.e., less than polymer T_g), but also be a stabilized "textile yarn" (denoted herein as an A-filament yarn) of shrinkage S , such that $(1-S/S_m)$ is at least about 0.9. (i.e., less than

about a nominal shrinkage S of about 10%). No such structural condition is required or disclosed by Shimazu.

Numerous and various applications are possible for the high shrinkage power "B" filaments and other higher shrinkage filaments of the invention, and the following Examples indicate some of these.

EXAMPLE A

In Example A the shrinkages S and $ST_{\max}$ for the high P_s B-filaments are compared with AB mixed-filament yarns. As expected the shrinkage S is determined by the higher shrinkage component (Fig. 24A-Line 1); but if the high shrinkage component has very low shrinkage tension, such as conventional POY, then the observed shrinkage S for the AB-filament yarns is significantly less than predicted from that of the high shrinkage component (Fig. 24A-Line 2). Shrinkage tension, however, is a weighted average of the contributions of A and B-filaments; that is, the expected $(ST_{\max})_{AB} = [(\text{denier})_A \times (ST_{\max})_A + (\text{denier})_B \times (ST_{\max})_B] / [(\text{denier})_A + (\text{denier})_B]$. In Figure 24B the "scattered" data assumes that the shrinkage tension of a AB-filament yarn is equal to that of the filaments of the highest $ST_{\max}$ -values (Line 1); and Line 2 represents the calculated $(ST_{\max})_{AB}$ values based on weighted values of the $ST_{\max}$ values of the individual components. The mixed-filament yarns of the invention are characterized by a yarn average $ST_{\max}$ of at least 0.1 g/d wherein the individual B-filaments have a $ST_{\max}$ of at least about 0.15 g/d; preferably a yarn average $ST_{\max}$ of at least about 0.15 g/d wherein the individual B-filaments have a $ST_{\max}$ of at least about 0.2 g/d.

EXAMPLE B

In Example B filament yarns spun between 3000 and 6500 mpm were drawn false-twist textured at 220 C and bulk of the textured yarns were measured according to Frankfort and Knox and plotted versus spinning speed of the draw feed yarn (See Figure 23). Bulk is found to

increase with spinning speed as previous taught by Frankfort and Knox. The bulk also increased with texturing speeds (at least for the case presented here from 700 to 800 mpm). The increase in bulk with spin speed is attributed to higher stress-induced orientation (SIO) which decreases the cold crystallization temperature T_{cc} of the feed yarn (see Figure 3A) and increases the rate of crystallization; further the crystal size increases 8-16X in volume providing larger inter-crystalline regions which permits greater mobility of the amorphous chains (i.e., of greater free-volume as supported by a decrease in the filament T_g as measured by rheovibron and discussed in detail in Frankfort and Knox) and the increase in mobility of the amorphous chains facilitates crystallization (and thereby bulk development) in high speed texturing. The increase in bulk from going from 700 to 800 mpm is believed to be associated with a "pre-setting" phenomenon..If the structure has too low a T_{cc} , too high a rate of crystallization and too large of an intercrystalline region for a given residence time, the draw feed yarns under go "pre-setting" prior to development of the fully twisted state. This can be easily demonstrated by purposefully pre-treating the draw feed yarns to temperatures above T_c^0 prior to draw twisting. At some higher texturing speed the enhanced crystallization potential of the high speed spun yarns matches that of the process residence time (which is also dependent of temperature and textured draw stress levels) and no further shrinkage is observed. However, if the high speed spun low shrinkage crystalline spin-oriented yarns (Type A) are treated such to increase their shrinkage S levels then further increases in bulk are possible (see Figure 23). It is therefore believed that the B-filament yarns of the invention with the proper level of interlace and spin finish would be superior draw texturing feed yarns especially at the higher texturing speeds (e.g., greater than 800 mpm).

EXAMPLE C

In Example C the A-filaments used as feed filaments in this invention may be combined with high speed spun nylon filaments (such as those prepared according to Knox et al in 5,137,666 and Boles et al in USP No.5,219,503 to provide a mixed polyester (A)/nylon (C') filament yarn which may be uniformly drawn with or without heat as taught by Boles et al in co-pending applications 07/753/529 and 07/753/769. A mixed-shrinkage post-bulkable yarn (BC') may be provided by treating the AC' mixed-filament yarn according to either Type I or Type II processes. The mixed-shrinkage BC' filament yarn could be pre-bulked, if desired, in a warping/slashing operation prior to winding onto a beam or directly being fed as a weftless warp sheet into the warp knit and weaving operations. Also the BC' yarns may be used as feed yarn in air-jet texturing wherein the combination of mixed-shrinkage and loop formation by the air-jet entanglement process would provide new aesthetic possibilities. If the polyester filaments are modified for dyeing with cationic dyes, then the polyester/nylon BC' mixed filament yarns would be compatible with the dyeing of elastomeric containing yarns and fabrics; e.g., as a covering or alternate course yarn in women's hosiery or to provide a "drier" hand in sports wear.

25

EXAMPLE D

In Example D the thermal properties of A, A', B, and C' filaments can be incorporated in a single filament, such as in an A'/A bicomponent polyester filament yarn that on treatment by either process Type I or Type II of the invention would yield an A'/B bicomponent filament yarn that on heat relaxation would provide a yarn comprised of torque-free helically crimped filaments; and such as in an A/C' biconstituent polyester/nylon filament yarn that on treatment by either process Type I or Type II of the invention would yield an B/C' biconstituent polyester/nylon filament yarn that on heat relaxation

would provide a yarn comprised of torque-free helically crimped filaments. To further enhance the shrinkage power, the A'/B and B/C' filaments may be drawn by Processes Type III of the invention prior to heat relaxation. To "de-register" the helically coiled-filaments (i.e., to break-up the "follow-the-leader crimp" configuration) bicomponent and biconstituent filaments of different deniers and/or cross-section symmetry may be used. The bicomponent and biconstituent filament may have a side-by-side (SBS) or a sheath/core (S/C) structure. In the case of a sheath/core structure, a mixed-filament yarn comprised of polyester/nylon sheath core filaments and of nylon/polyester filaments may be prepared (especially for polyester modified for cationic dyeing) to provide for cross-dye effects. When spinning polyester/nylon SBS biconstituent filaments it is preferred to use antimony-free polyester as disclosed by Jennings in USP No. 4,702,875 or by incorporating in the polyamide dicarboxybenzene ($-OC-C_6H_4-CO-$) groups, for example, to improve the chemical compatibility at the polyester/polyamide interface so to prevent splitting of the filaments. Applying the theory of solubility parameters (e.g., additivity of group cohesive energy densities) may be used to design the chemical compositions of both the polyester and polyamide polymers in a more structured fashion versus empirical testing to provide the required surface tension for good adhesion of the dissimilar polymers.

In the case of the A'/A bicomponent filaments, the thermal stability of A' component may be increased over that of the A component by use of higher polymer LRV or the incorporation of chain branching agents in the A' polymer feed. Alternatively, for example the A' polymer feed may be modified to lessen its thermal stability (i.e., make A from A') by incorporating minor amounts of copolymer, for example, to reduce slightly the degree of crystallinity between A and A'. As higher spin speeds are used to prepare the A'/A biconstituent filaments, greater

RV, chain branching, or copolymer modifications will be required to achieve the difference in thermal stability such that on treatment by process Type I or Type II A'/B bicomponent yarns may be prepared that on heat relaxation
5 will provide torque-free helical crimped filaments. The A'/A and A/C' may be drawn at temperatures near the T_{11} transition temperature of the polyester component to provide A'/B and B/C' filaments (as designated herein before as Process Type VII).

10

EXAMPLE E

In Example E filaments having an asymmetric structure are formed by first providing A-filaments by melt spinning at withdrawal speeds between 2 km/min to 6 km/min and treating the fully quenched filaments by a
15 thermal deformation treatment, such as by pin as described in Frankfort USP Nos. 3,816,992, 3,861,133, and 3,905,077 or a heated surface may be used if residence time or lower surface friction is preferred. The treating of the thermally deformed A-filaments by treatment processes of
20 Type I or Type II of the invention provides a filament comprised of "random" components of Type A' and of Type B shrinkage behavior. On heat relaxation the filaments will self-crimp forming torque-free helical crimped filaments. The frequency and amplitude of the helical crimped
25 filaments may be changed by treating a yarn comprised of filaments of different deniers, for example.

EXAMPLE F

Spin-oriented polyester filaments of Type B, which on exposure to temperatures above $\{0.70(T_m^0 + 273) - 273\}$ will self-helically crimp, may be provided from
30 filaments of Type A by either heat treatment Type I or Type II; wherein the Type A filaments are of asymmetric hollow cross-section and are prepared by extruding the polyester polymer melt from a spinneret capillary orifice
35 comprised of multiple segments arranged in a configuration such to form multiple melt streams which are withdrawn from the spinneret into a quench zone under conditions

which cause self-coalescence of the multiple melt streams into a filament having an off-center longitudinal void of at least 10% by volume, preferably at least 20% by volume. The void side of the filament has shrinkage characteristics of a thermally Type A' filament, while the solid side of the filament may be prepared to have shrinkage S characteristic of a Type A filament. Heat treatments Type I or Type II transforms the asymmetric hollow "A/A'-filament" into a hollow "B/A'-filament" which on exposure to temperatures greater than about $\{0.70(T_m^0 + 273) - 273\}$ will self helically crimp. Forming a multi-filament yarn of mixed dpf, cross-sectional shape, and void content, for example, will lead to crimped filaments of different helical frequency and amplitude and thereby disrupt the "follow-the-leader" crimp characteristic of helically crimped filament yarns and provide higher yarn bulk and fabric cover (opacity).

EXAMPLE G

In Example G sheath/core filaments may be used as flat yarns (i.e., with little tendency to form along-end crimp) provided that the sheath/core configuration is used and is symmetric along-end. For example, a spin-oriented flat nylon-like filament may be prepared by forming a biconstituent filament having a nylon sheath and a polyester core. The polyester core serves at least two functions; 1) it reduces the ingredient costs of the "flat" filament and 2) provides filaments of a higher modulus than possible by spin-orientation of 100% nylon, at least at speeds less than about 8000-10,000 mpm.

Spin-oriented polyester filaments have a higher modulus for a spin speed than nylon spin-oriented filaments. Coupling the modulus of the the polyester core (M_p) and of the nylon sheath (M_n) provides a composite filament modulus (M_c) that falls between M_p and M_n . Side-by-side and sheath/core configurations are well represented by the "parallel" model of coupling of two phases; that is, $M_c = XM_n + (1-X)M_p$, where X is the volume fraction of the sheath and (1-X) is the volume fraction of

the core. For example, if $M_p = 60$ g/d and $M_n = 15$ g/d and the sheath (X) comprises 40% of the filament, the expected composite modulus $M_c = \{0.4(15) + 0.6(60)\} = 42$ g/d.

Direct spinning of of 65 RV nylon 66 polymer at
5 5300 mpm and a T_p of 290 C provides a nylon filaments
having a modulus of about 15 g/d and a boil-off shrinkage
of about 3-4%, while spinning a 21 LRV 2GT polyester under
the same conditions provides polyester filaments of about
60 g/d modulus and a boil-off shrinkage of about 2-4%. If
10 the moduli are additive according to the "parallel"
coupling model, then to obtain a composite filament having
a 30 g/d modulus, about 35% polyester core would be
required; however, if the spun biconstituent S/C
nylon/polyester filaments are treated according to the
15 invention at temperatures about the $T_{c, \frac{1}{2}}$ of the polyester
polymer, then lonly about 17% polyester core would be
required or the same modulus with 35% polyester could
could be obtained by spinning at a lower spin speed;
e.g., about 3500 mpm to obtain the same composite modulus
20 of 30 g/d. This process of the invention permits for the
first time to obtain "hard yarn" like nylon filaments at
spin speeds in the 4000-5000 mpm range; nearly half the
spin speed required for 100% nylon.

For textile uses as a flat yarn in warp
25 knitting, for example, a modulus of at least 20 g/d is
required (as based on ranking of nylon fabrics.critically
dyed with a large molecule acid dye as described by Boles,
et al in USP. No. 5,219,503 and 25 g/d is preferred and 30
g/d is especially preferred.

30 To obtain the desired shrinkage for a given end-
use; for example, high speed spin-oriented nylon 66
filament yarns have 3-6% and high speed spin-oriented
nylon 6 filament yarns have 8-12% shrinkage. Commercial
warp knit flat yarns are prepared by slow speed spin/draw
35 processes giving about 6-8% shrinkage for nylon 66. To
increase the shrinkage of the composite nylon/polyester
filament yarns the nylon 66 may be modified with

copolyamides, such as with 2-methyl pentadamine (MPMD) as disclosed in USP. Nos. 5,137,447 and in USP No.5,219,503.

5 The polyester component treated at the higher temperatures of about $T_{C, \frac{1}{2}}$ will have similar shrinkage levels to that of drawn nylon 66 and 6. If lower shrinkages are required than the polyester RV many be increased slightly or higher spin speeds may be used. To maintain the balance between the shrinkage of the nylon sheath and the polyester core so to minimize along-end crimp development (for even uniform symmetric sheath/core cross-section filaments have a finite long-end variability), quenching air flow rates, patterns, and the convergence length are all carefully controlled to minimize threadline movement.

15

EXAMPLE H

In Example H several copolyesters are compared as to their elongation (E_B), shrinkage (S) and RDDR for spin speeds of 4100 and 4530 mpm. In this first set of samples, all filaments were spun at 4530 mpm using 15 x 60 mil capillaries at a spin pack temperature of 305 C (the actual polymer temperature was not measured, but is expected to be about 10 C lower from previous studies) to provide 150 denier 80-filament SOY. The copolymers used were: 1 (control - no modifiers); 2 - 3% Glutarate; 3- 8% Glutarate; 4- 8% Glutarate with 0.06% TMP; 5- 5% PEO with 0.06% TMP; 6- 2% Cationic moiety; 7 - 1% trimethyl tetramesicate; and 8- 0.04% TMP (trimethyl propionate). The summary of the details are given in Table 21. Although low shrinkage and excellent dyeability were obtained for the polyester A-filaments for use as precursors of the B-filaments of the invention, many of the copolyesters have RDR-values greater than 1.9. Higher spin speeds would be required if lower RDR-values are desired. For copolyesters the range of acceptable RDR-values is about 2.2 to 1.4 versus 1.9 to 1.4 for homopolymer.

EXAMPLE I

In Example I nylon 66 copolyamides were spun at 4000 and at 5000 mpm. All yarns were 50 denier 13-
filaments spun at a nominal T_p of 290 C using 10 x 19 mil
5 capillary spinnerets and quenched using cross-flow air and
converged at about 135 cm from the spinneret. Details are
given in Table 22. All the yarns had insufficient modulus
for use as a direct-use flat yarn, but may be used as the
sheath in a sheath/core polyamide/polyester to provide
10 flat SOY according to the invention.

EXAMPLE J

In Example J the DSC data for heat treated A-
filaments of nominal 1.5 dpf and spun 4500 mpm. Details
are given in Table 23. The decrease in the fiber T_m with
15 increasing tube temperature is consistent with a decrease
in average crystal size and the melting out of the primary
crystal structure (C) in addition to the mesophase (B) as
represented in Figure 21.

TABLE NO.		TABLE 1A																			
ITEM NO.	1C	2C	3	4	5	6	7	8	9C	10C	11C	12	13	14	15	16	17C	18C	19	20	
V, YPM	4500	4500	4500	4500	4500	4500	4500	4500	4700	4700	4700	4700	4700	4700	4700	4700	4900	4900	4900	4900	
V, MPM	4115	4115	4115	4115	4115	4115	4115	4115	4298	4298	4298	4298	4298	4298	4298	4298	4481	4481	4481	4481	
ANNEAL TYPE	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	
, °C	245	245	245	245	245	245	245	245	245	245	245	245	245	245	245	245	245	245	245	245	
, LBS/IN ²	OFF	40	60	80	100	120	140	160	OFF	40	60	80	100	120	140	160	OFF	40	60	80	
, KG/CM ²	OFF	2.8	4.2	5.6	7.0	8.4	9.8	11.2	OFF	2.8	4.2	5.6	7.0	8.4	9.8	11.2	OFF	3	4	6	
YARN DENIER	35	35	35	35	35	35	35	35	35	35	35	35	35	35	35	35	35	35	35	35	
FILS/YARN	17	17	17	17	17	17	17	17	17	17	17	17	17	17	17	17	17	17	17	17	
DPF	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	
T70%, G/D	--	0.99	1.18	1.32	1.41	1.46	1.69	1.74	0.94	1.23	1.17	1.16	1.36	1.44	1.60	1.74	1.05	1.18	1.10	--	
T200%, G/D	--	1.23	1.43	1.71	1.88	2.00	2.36	2.44	1.25	1.60	1.47	1.45	1.78	1.94	2.20	2.41	1.40	1.51	1.43	--	
PYM, G/D	--	3.2	3.5	4.9	5.7	6.4	7.8	8.2	3.79	4.63	3.92	4.32	5.21	6.03	7.11	7.89	4.3	4.2	4.1	--	
EB, %	--	63.8	45.4	41.8	43.8	41.4	35.6	41.6	60.8	43.8	42.2	51.0	52.9	40.0	39.7	31.2	61.7	53.0	66.9	--	
RDR	--	1.638	1.454	1.418	1.438	1.414	1.356	1.416	1.608	1.438	1.422	1.510	1.529	1.400	1.397	1.312	1.62	1.53	1.67	--	
TEN, G/D	--	2.64	2.33	2.84	3.12	3.17	3.20	3.58	2.57	2.33	2.25	2.58	3.46	3.03	3.21	3.03	2.78	2.72	3.03	--	
TBK, G/DD	--	4.32	3.39	4.03	4.49	4.48	4.34	5.07	4.13	3.35	3.20	3.90	5.29	4.24	4.48	3.98	4.50	4.16	5.06	--	
S, %	--	8.0	18.5	59.0	48.0	30.0	14.0	12.0	3.5	5.5	8.5	13.0	46.5	31.5	22.0	13.5	3.8	6.5	10.0	7.5	
DHS, %	3.9	7.7	38.3	49.0	35.5	19.9	13.1	11.3	3.6	7.3	12.0	15.8	35.8	19.9	13.6	10.2	3.8	5.0	5.5	7.5	
DHS-S, %	--	-0.3	19.8	-10.0	-12.5	-10.1	-0.9	-0.7	0.1	1.8	3.5	2.8	46.5	-11.6	-8.4	-3.3	0.0	-1.5	-4.5	0.0	
STmax, MG/D	--	--	--	--	--	--	176	153	89	131	144	166	158	166	137	157	54	126	156	138	
Ti(STmax),C	--	--	--	--	--	--	92	126	84	83	80	79	79	86	88	100	86	80	81	81	
NST,(G/D)/K	--	--	--	--	--	--	0.48	0.38	0.25	0.37	0.41	0.47	0.45	0.46	0.38	0.42	0.15	0.36	0.44	0.39	
Ms, G/D	--	--	--	--	--	--	1.3	1.3	2.54	2.38	1.69	1.28	0.34	0.53	0.62	1.16	1.4	1.9	1.6	1.8	
Ps, G/D	--	--	--	--	--	--	2.5	1.8	0.3	0.7	1.2	2.2	7.3	5.2	3.0	2.1	0.20	0.82	1.56	1.04	

TABLE NO.		TABLE 1B									
ITEM NO.		1	2	3	4	5C	6C	7C	8	9C	10
V, YMP		4900	4900	4900	5300	5300	5300	5300	5300	5300	5300
V, MPM		4481	4481	4481	4481	4846	4846	4846	4846	4846	4846
ANNEAL TYPE		STEAM	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM
, °C	245	245	245	245	245	245	245	245	245	245	245
, LBS/IN ²	100	120	120	130	160	OFF	40	60	80	100	120
, KG/CM ²	7	8	8	10	11	OFF	3	4	6	7	8
YARN DENIER		35	35	35	35	50	50	50	50	50	50
FILS/YARN		17	17	17	17	17	17	17	17	17	17
DPF		2.1	2.1	2.1	2.1	2.9	2.9	2.9	2.9	2.9	2.9
. T7%, G/D		1.12	1.64	1.87	1.93	--	--	--	--	--	--
T20%, G/D		1.45	2.25	2.58	2.70	--	--	--	--	--	--
PYM, G/D		4.1	7.2	8.4	9.0	--	--	--	--	--	--
EB, %		66.6	32.0	33.9	28.4	--	--	--	--	--	--
RDR		1.666	1.320	1.339	1.284	--	--	--	--	--	--
TEN., G/D		3.07	2.91	3.31	3.20	--	--	--	--	--	--
TBK, G/DD		5.11	3.84	4.43	4.11	--	--	--	--	--	--
S, %		11.5	35.0	18.5	17.0	4.0	7.9	5.9	7.2	7.1	10.5
DHS, %		8.8	24.6	14.3	10.0	4.5	5.0	5.4	6.9	7.1	11.1
DHS-S, %		-3.7	-10.4	-4.2	-7.0	0.5	-2.9	-0.5	-0.3	0.0	0.6
STmax, HG/D		161	151	179	145	130	160	170	210	200	230
T(STmax), C		82	83	94	100	81	78	79	79	81	83
NST, (G/D)/K		0.45	0.42	0.49	0.39	0.37	0.46	0.48	0.60	0.56	0.65
Ms, G/D		1.4	0.4	1.0	0.9	3.25	2.03	2.88	2.92	2.82	2.19

TABLE 1B (CONT.)												
11	12	13C	14	15	16	17	18	19	20C	21C		
5300	5300	4500	4500	4500	4500	4500	4700	4500	4700	4700		
V, YPM												
4846	4846	4115	4115	4115	4115	4115	4115	4115	4298	4298		
STEAM	STEAM	OFF	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM	OFF	STEAM		
245	245	245	245	245	245	245	245	OFF	245	245		
, °C												
, LBS/IN ²	140	160	40	60	80	100	120	140	140	140		40
, KG/CM ²	10	11	2.8	4.2	5.6	7.0	8.4	9.8	11.2	11.2		2.8
YARN DENIER	50	50	50	50	50	50	50	50	50	50		50
FILS/YARN	17	17	17	17	17	17	17	17	17	17		17
DPF	2.9	2.9	2.94	2.94	2.94	2.94	2.94	2.94	2.94	2.94		2.94
T7%, G/D	--	0.82	0.90	1.14	1.46	1.61	1.15	1.25	0.89	0.95		0.95
T20%, G/D	--	0.99	1.02	1.41	1.93	2.14	1.52	1.72	1.13	1.16		1.16
PYM, G/D	--	2.4	2.0	3.6	5.8	6.5	4.6	4.8	3.1	2.89		2.89
EB, %	--	74.7	71.5	57.2	47.7	44.1	56.3	50.1	77.1	71.9		71.9
RDR	--	1.747	1.715	1.572	1.477	1.441	1.563	1.501	1.771	1.719		1.719
TEN., G/D	--	2.65	2.69	3.14	3.48	3.51	3.27	3.22	2.96	2.92		2.92
TBK, G/DD	--	4.63	4.61	4.94	5.14	5.06	5.11	4.83	5.24	5.02		5.02
S, %	13.6	--	--	44.5	55.7	N/A	N/A	20.0	3.6	8.1		8.1
DHS, %	10.8	11.6	12.7	47.2	58.0	47.0	27.7	19.3	6.0	5.7		5.7
DHS-S, %	-2.8	0.8	--	2.7	2.3	--	--	-0.7	2.4	-2.4		-2.4
STmax, HG/D	190	190	200	180	140	140	200	160	80	100		100
T(STmax), C	87	90	72	71	71	73	84	81	82	76		76
NST, (G/D)/K	0.53	0.52	0.58	0.52	0.41	0.41	0.56	0.45	0.22	0.29		0.29
Ms, G/D	0.64	1.76	--	0.4	0.3	--	--	0.8	2.2	1.23		1.23

TABLE NO.		TABLE 1C																			
ITEM NO.		1	2	3	4	5	6	7C	8C	9C	10	11	12	13	14	15C	16C	17C	18C	19	20
V, YPM	4700	4700	4700	4700	4700	4700	4700	4900	4900	4900	4900	4900	4900	4900	4900	5100	5100	5100	5100	5100	5100
V, MPM	4298	4298	4298	4298	4298	4298	4298	4481	4481	4481	4481	4481	4481	4481	4481	4663	4663	4663	4663	4663	4663
ANNEAL	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM
, °C	245	245	245	245	245	245	245	245	245	245	245	245	245	245	245	245	245	245	245	245	245
, LBS/IN ²	60	80	100	120	140	160	180	OFF	40	60	80	100	120	140	160	OFF	40	60	80	100	120
, KG/CM ²	4.2	5.6	7.0	8.4	9.8	11.2	12.6	OFF	2.8	4.2	5.6	7.0	8.4	9.8	11.2	OFF	2.80	4.20	5.60	7.00	8.40
DENIER	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50
NO. FILS	17	17	17	17	17	17	17	17	17	17	17	17	17	17	17	17	17	17	17	17	17
DPF	2.94	2.94	2.94	2.94	2.94	2.94	2.94	2.94	2.94	2.94	2.94	2.94	2.94	2.94	2.94	2.94	2.94	2.94	2.94	2.94	2.94
T7%, G/D	0.96	1.03	1.19	1.18	1.24	1.37	0.94	0.95	1.02	1.10	1.13	1.13	1.13	1.30	1.36	--	1.05	1.07	1.06	1.20	1.22
T20%, G/D	1.17	1.23	1.56	1.58	1.68	1.93	1.24	1.22	1.28	1.36	1.42	1.42	1.42	1.75	1.88	--	1.33	1.39	1.37	1.51	1.57
PYM, G/D	2.90	2.88	4.61	4.87	5.30	6.54	3.7	3.4	3.4	3.5	3.8	3.8	3.8	5.4	6.1	--	2.60	4.01	3.90	4.04	4.43
EB, %	66.6	66.1	50.9	49.1	54.2	41.2	65.8	68.4	75.5	61.4	52.3	62.1	62.1	55.9	52.9	--	62.6	67.6	71.6	63.1	58.3
RDR	1.666	1.661	1.509	1.491	1.542	1.412	1.658	1.684	1.755	1.614	1.523	1.621	1.621	1.559	1.529	--	1.626	1.676	1.716	1.631	1.583
TEN., G/D	2.79	3.03	3.12	3.00	3.41	3.02	2.78	2.90	3.18	2.88	2.78	3.24	3.24	3.53	3.48	--	2.92	3.12	3.21	3.23	3.26
TBK, G/DD	4.65	5.03	4.71	4.47	5.26	4.26	4.61	4.88	5.58	4.65	4.23	5.25	5.25	5.50	5.32	--	4.75	5.23	5.51	5.27	5.16
S, %	19.5	22.6	54.9	35.4	24.1	10.7	3.5	5.5	6.5	14.0	20.1	26.7	23.5	15.0	15.0	3.9	4.5	7.8	7.5	15.1	21.6
DHS, %	11.3	23.2	48.7	29.3	15.1	10.2	4.3	6.6	7.8	9.8	16.1	25.6	17.3	10.2	4.5	0.6	4.4	5.9	6.9	11.3	16.7
DHS-S, %	-8.2	0.6	-6.2	-6.1	-9.0	-0.5	0.8	1.1	1.3	-4.2	-4.0	-1.1	-6.2	-4.8	-4.8	0.6	-0.1	-1.9	-0.6	-3.8	-4.9
STmax, HG/D	130	150	140	150	120	170	90	120	130	160	180	160	160	130	120	120	120	170	160	190	170
T(STmax), C	77	74	75	77	85	93	88	89	77	72	77	79	79	86	97	85	80	78	78	80	82
NST, (G/D)/K	0.37	0.43	0.40	0.43	0.34	0.46	0.25	0.33	0.37	0.46	0.51	0.45	0.45	0.36	0.32	0.34	0.34	0.48	0.46	0.54	0.48
Ms, G/D	0.67	0.66	0.26	0.42	0.50	1.59	2.6	2.2	2.0	1.1	0.9	0.6	0.6	0.6	0.8	3.1	2.7	2.2	2.1	1.3	0.8
Ps, G/D	2.5	3.4	7.9	5.3	2.9	1.8	0.3	0.7	0.8	2.2	3.6	4.3	4.3	3.1	1.8	0.5	0.5	1.3	1.2	2.9	3.7

TABLE NO.

ITEM NO.

V, YPM

V, MPM

ANNEAL TYPE

, °C

, LBS/IN², KG/CM²

YARN DENIER

FILS/YARN

DPF

S, %

DHS, %

DHS-S, %

STmax, HG/D

T(STmax), C

NST, (G/D)/K

Ms, G/D

Ps, G/D

TABLE 1D

1	2	3C	4C	5C	6	7C	8	9	10	11C	12C	13	14	15	16	17	18
5100	5100	5300	5300	5300	5300	5300	5300	5300	5300	4500	4500	4500	4500	4500	4500	4500	4500
4663	4663	4846	4846	4846	4846	4846	4846	4846	4846	4115	4115	4115	4115	4115	4115	4115	4115
245	245	245	245	245	245	245	245	245	245	245	245	245	245	245	245	245	245
140	160	Off	40	60	80	100	120	140	160	Off	40	60	80	100	120	140	160
9.80	11.20	Off	3	4	6	7	8	10	11	Off	2.8	4.2	5.6	7.0	8.4	9.8	11.2
50	50	50	50	50	50	50	50	50	50	70	70	70	70	70	70	70	70
17	17	17	17	17	17	17	17	17	17	17	17	17	17	17	17	17	17
2.94	2.94	2.9	2.9	2.9	2.9	2.9	2.9	2.9	2.9	4.1	4.1	4.1	4.1	4.1	4.1	4.1	4.1
19.8	15.5	4.0	7.9	5.9	7.2	7.1	10.5	13.6	10.8	16.5	17.5	21.5	51.5	58.5	41.5	31.0	13.0
15.7	11.7	4.5	5.0	5.4	6.9	7.1	11.1	10.8	11.6	8.5	14.1	19.3	52.9	56.3	34.9	23.5	11.7
-4.1	-3.8	0.5	-2.9	-0.5	-0.3	0.0	0.6	-2.8	0.8	-8.0	-3.4	-2.2	1.4	-2.2	-6.6	-7.5	-1.3
200	220	130	160	170	210	200	230	190	190	90	80	90	100	110	100	100	190
83	92	81	78	79	79	81	83	87	90	80	77	75	72	72	78	78	88
0.56	0.60	0.37	0.46	0.48	0.60	0.56	0.65	0.53	0.52	0.25	0.23	0.26	0.29	0.32	0.28	0.28	0.52
1.0	1.4	3.25	2.03	2.88	2.92	2.82	2.19	0.64	1.76	0.55	0.46	0.42	0.19	0.19	0.24	0.32	1.46
4.0	3.4	0.52	1.26	1.00	1.51	1.42	2.42	2.58	2.05	1.49	1.40	1.94	5.15	6.44	4.15	3.10	2.47

TABLE NO.		TABLE 1E													
ITEM NO.		1C	2C	3C	4C	5C	6	7	8	9C	10C	11C	12C		
V, YPM		4900	4900	4900	4900	4900	4900	4900	4900	5100	5100	5100	5100		
V, MPM		4481	4481	4481	4481	4481	4481	4481	4481	4663	4663	4663	4663		
ANNEAL TYPE		Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam		
°C		245	245	245	245	245	245	245	245	245	245	245	245		
, LBS/IN ²		Off	40	60	80	100	120	140	160	Off	40	60	80		
, KG/CM ²		Off	2.8	4.2	5.6	7.0	8.4	9.8	11.2	Off	2.8	4.2	5.6		
YARN DENIER		70	70	70	70	70	70	70	70	70	70	70	70		
FILS/YARN		17	17	17	17	17	17	17	17	17	17	17	17		
DPF		4.1	4.1	4.1	4.1	4.1	4.1	4.1	4.1	4.1	4.1	4.1	4.1		
S, ‰		6.0	6.0	6.0	5.5	10.5	16.0	23.0	17.0	5.8	5.5	6.0	6.5		
DHS, ‰		5.5	5.6	5.6	6.3	7.0	13.0	16.6	13.8	5.2	5.5	5.5	5.7		
DHS-S, ‰		-0.5	-0.4	-0.4	0.8	-3.5	-3.0	-6.4	-3.2	-0.6	0.0	-0.5	-0.8		
STmax, HG/D		90	90	90	110	110	130	120	110	110	100	100	110		
T(STmax), C		84	83	84	81	82	84	83	94	88	86	84	82		
NST, (G/D)/K		0.25	0.25	0.24	0.31	0.31	0.36	0.34	0.30	0.30	0.28	0.28	0.31		
Ms, G/D		1.50	1.50	1.50	2.00	1.05	0.81	0.52	0.65	1.90	1.82	0.17	1.69		
Ps, G/D		0.54	0.54	0.54	0.61	1.16	2.08	2.76	1.87	0.64	0.64	0.60	0.72		

TABLE NO. ITEM NO.	TABLE 1E (CONT.)													
	13C	14	15	16	17C	18C	19C	20C	21C	22C	23	24C		
V, YPM	5100	5100	5100	5100	5300	5300	5300	5300	5300	5300	5300	5300	5300	5300
V, MPM	4663	4663	4663	4663	4846	4846	4846	4846	4846	4846	4846	4846	4846	4846
ANNEAL TYPE	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam
°C	245	245	245	245	245	245	245	245	245	245	245	245	245	245
, LBS/IN ²	100	120	140	160	Off	40	60	80	100	120	140	160	160	160
, KG/CM ²	7.0	8.4	9.8	11.2	Off	2.8	4.2	5.6	7.0	8.4	9.8	11.2	11.2	11.2
YARN DENIER	70	70	70	70	70	70	70	70	70	70	70	70	70	70
FILS/YARN	17	17	17	17	17	17	17	17	17	17	17	17	17	17
DPF	4.1	4.1	4.1	4.1	4.1	4.1	4.1	4.1	4.1	4.1	4.1	4.1	4.1	4.1
S, %	6.5	13.0	23.0	16.0	3.4	4.2	5.5	4.5	7.0	8.0	7.4	7.3	7.3	7.3
DHS, %	6.3	10.2	13.2	11.5	3.8	4.8	5.4	5.0	6.6	7.0	6.7	7.0	7.0	7.0
DHS-S, %	-0.2	-2.8	-9.8	-4.5	0.4	0.6	-0.1	0.5	-0.4	-1.0	-0.7	-0.3	-0.3	-0.3
STmax, HG/D	120	140	140	130	90	120	130	120	190	150	210	160	160	160
T(STmax), C	84	82	86	89	92	86	85	84	85	83	88	87	87	87
NST, (G/D)/K	0.34	0.39	0.39	0.36	0.25	0.33	0.36	0.34	0.53	0.42	0.58	0.44	0.44	0.44
Ms, G/D	1.85	1.08	0.61	0.81	2.65	2.86	2.36	2.67	2.71	1.88	2.84	2.19	2.19	2.19
Ps, G/D	0.78	1.82	3.22	2.08	0.30	0.50	0.72	0.54	1.33	1.20	1.55	1.17	1.17	1.17

TABLE NO.		TABLE 2A																			
ITEM NO.		1C	2C	3	4	5	6	7	8	9C	10C	11	12	13	14	15	16	17C	18C	19C	20C
V, YPM		4500	4500	4500	4500	4500	4500	4500	4500	4700	4700	4700	4700	4700	4700	4700	4700	4900	4900	4900	4900
V, MPM		4115	4115	4115	4115	4115	4115	4115	4115	4298	4298	4298	4298	4298	4298	4298	4298	4481	4481	4481	4481
ANNEAL TYPE		Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam
.°C		245	245	245	245	245	245	245	245	245	245	245	245	245	245	245	245	245	245	245	245
.LBS/IN ²		Off	40	60	80	100	120	140	160	Off	40	60	80	100	120	140	160	Off	40	60	80
.KG/CM ²		Off	2.8	4.2	5.6	7.0	8.4	9.8	11.2	Off	2.8	4.2	5.6	7.0	8.4	9.8	11.2	Off	3	4	6
YARN DENIER		35	35	35	35	35	35	35	35	35	35	35	35	35	35	35	35	35	35	35	35
FILS/YARN		27	27	27	27	27	27	27	27	27	27	27	27	27	27	27	27	27	27	27	27
DPF		1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3	1.3
S, %		4.0	4.0	10.5	17.5	25.0	17.0	16.0	13.0	3.0	6.5	10.5	12.0	12.0	14.0	13.0	11.0	3.8	5.5	6.5	7.0
DHS, %		3.7	5.1	10.4	14.2	28.8	15.1	12.4	11.0	3.5	5.0	15.9	9.2	9.1	10.9	12.2	11.1	3.8	5.1	6.4	8.2
DHS-S, %		-0.3	1.1	-0.1	-3.3	3.8	-1.9	-3.6	-2.0	0.5	-1.5	4.4	-2.8	-2.9	-3.1	-0.8	0.1	0.0	-0.4	-0.1	1.2
STmax, MG/D		-	-	-	-	-	-	256	174	87	111	164	161	207	286	189	237	109	119	184	167
T(STmax), C		-	-	-	-	-	-	92	90	91	79	81	80	84	88	87	99	83	79	82	81
NT, (G/D)/K		-	-	-	-	-	-	0.70	0.48	0.24	0.32	0.46	0.46	0.58	0.79	0.53	0.83	0.31	0.34	0.52	0.47
Ms, G/D		-	-	-	-	-	-	1.60	1.34	2.90	1.71	1.56	1.34	1.73	2.04	1.45	2.15	2.87	2.16	2.83	2.39
Ps, (g/d)%		-	-	-	-	-	-	4.1	2.3	0.26	0.72	1.72	1.93	2.48	4.00	2.46	2.61	0.41	0.65	1.20	1.17

TABLE NO.		TABLE 2B																			
ITEM NO.		1	2	3C	4	5C	6	7	8	9	10	11	12C	13	14	15	16	17	18	19C	
V, YPM		4900	4900	4900	4900	4500	4500	4500	4500	4500	4500	4500	4700	4700	4700	4700	4700	4700	4700	4700	
V, MPM		4481	4481	4481	4481	4115	4115	4115	4115	4115	4115	4115	4298	4298	4298	4298	4298	4298	4298	4298	
ANNEAL TYPE		Steam	Steam	Steam	Steam	Off	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	
, °C		245	245	245	245	NA	245	245	245	245	245	245	245	245	245	245	245	245	245	245	
, LBS/IN ²		100	120	140	160	NA	40	60	80	100	120	140	Off	40	60	80	100	120	140	160	
, KG/CM ²		10	11	9.8	11.2	NA	2.8	4.2	5.6	7.0	8.4	9.8	Off	2.8	4.2	5.6	7.0	8.4	9.8	11.2	
YARN DENIER		35	35	35	35	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	
FILS/YARN		27	27	27	27	27	27	27	27	27	27	27	27	27	27	27	27	27	27	27	
DPF		1.3	1.3	1.3	1.3	1.85	1.85	1.85	1.85	1.85	1.85	1.85	1.85	1.85	1.85	1.85	1.85	1.85	1.85	1.85	
S, %		9.5	11.5	8.5	8.0	--	--	58.6	49.2	--	--	30.0	3.3	8.4	9.9	14.6	27.9	36.9	17.0	13.4	
DHS, %		9.1	8.2	10.1	7.9	4.5	12.1	68.0	51.8	41.2	33.0	19.4	3.9	9.9	9.4	12.8	22.6	23.1	14.3	12.8	
DHS-S, %		-0.4	-3.3	1.6	-0.1	--	--	9.4	2.6	--	--	-10.6	0.6	1.5	-0.4	-1.8	-5.3	-13.8	-3.7	-0.6	
STmax, MGD		202	156	140	217	90	130	160	220	220	130	160	100	160	210	210	230	210	160	100	
T(STmax), C		86	85	91	94	80	86	73	76	76	77	82	86	75	76	78	81	86	94	98	
NST, (G/D)/K		0.56	0.44	0.38	0.59	0.00	0.36	0.46	0.63	0.63	0.37	0.45	0.28	0.46	0.60	0.60	0.65	0.58	0.44	0.27	
Ms, G/D		2.13	1.36	1.65	2.71	2.0	1.1	0.3	0.4	0.5	0.4	0.5	3.0	1.9	2.1	1.4	0.8	0.6	0.9	0.0	
Ps, G/D		2.77	1.79	1.19	1.74	(0.4)	(1.6)	9.4	10.8	(9.1)	(4.3)	3.1	0.3	1.3	2.1	1.8	6.4	7.7	2.7	1.3	

TABLE NO.	ITEM NO.	1C	2	3	4	5	6	7	8	9C	10C	11C	12	13	14	15	16C	17C	18C	19	20	21
V, YPM	4900	4900	4900	4900	4900	4900	4900	4900	4900	5100	5100	5100	5100	5100	5100	5100	5300	5300	5300	5300	5300	5300
V, MPM	4481	4481	4481	4481	4481	4481	4481	4481	4481	4663	4663	4663	4663	4663	4663	4663	4846	4846	4846	4846	4846	4846
ANNEAL TYPE	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Off	Steam	Steam	Steam	Steam	Steam	Steam	Off	Steam	Steam	Steam	Steam	Steam
°C	245	245	245	245	245	245	245	245	245	NA	245	245	245	245	245	245	Off	245	245	245	245	245
.LBS/IN ²	Off	40	60	80	100	100	120	140	160	NA	40	80	100	120	140	160	Off	40	60	80	100	120
.KG/CM ²	Off	3	4	6	10	10	11.2	8.4	9.8	NA	3.0	5.60	7.00	8.4	9.8	11.2	Off	2.8	4.2	5.6	7.0	8.4
YARN DENIER	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50
FILSNARN	27	27	27	27	27	27	27	27	27	27	27	27	27	27	27	27	27	27	27	27	27	27
DPF	1.85	1.85	1.85	1.85	1.85	1.85	1.85	1.85	1.85	1.85	1.85	1.85	1.85	1.85	1.85	1.85	1.85	1.85	1.85	1.85	1.85	1.85
S, %	4.0	12.5	60.0	9.5	13.4	15.2	15.6	15.3	15.3	3.0	5.3	7.0	10.8	11.3	10.9	10.6	3.4	5.0	5.7	7.0	7.3	11.3
DHS, %	4.0	5.4	66.0	8.0	13.1	14.8	14.8	12.2	12.2	4.3	5.1	8.2	10.2	10.4	10.2	10.2	3.9	4.9	6.0	6.5	8.5	9.4
DHS-S, %	0.0	-7.1	6.0	-1.5	-0.3	-0.4	-0.8	-3.1	-3.1	1.3	-0.2	1.2	-0.8	-0.7	-0.7	-0.4	-0.5	-0.1	0.3	1.5	1.2	1.9
STmax, MG/D	130	180	180	210	210	230	250	220	220	130	170	190	270	190	240	260	150	210	250	210	300	290
T(STmax), C	85	79	78	80	82	87	89	95	95	87	81	78	84	86	89	94	84	80	80	81	82	86
NST,(GD)/K	0.36	0.51	0.51	0.59	0.59	0.64	0.69	0.60	0.60	0.36	0.48	0.54	0.76	0.75	0.66	0.71	0.42	0.59	0.71	0.59	0.85	0.81
Ms, G/D	3.3	1.4	0.3	2.2	1.6	1.5	1.6	1.4	1.4	4.3	1.1	2.71	2.5	1.7	2.2	2.5	4.4	4.2	4.4	3.0	4.1	8.8
Ps, G/D	0.5	2.3	10.8	2.0	2.8	3.5	3.9	3.4	3.4	0.4	0.9	1.3	2.9	2.1	2.6	2.8	0.5	1.1	1.4	1.5	2.2	3.3

TABLE NO.		TABLE 2D																				
ITEM NO.		1	2	3	4	5C	6	7C	8	9	10	11	12	13C	14C	15	16	17	18	19C	20	21C
V, YPM		5300	5300	4500	4500	4500	4500	4500	4500	4500	4500	4700	4700	4700	4700	4700	4700	4700	4700	4900	4900	4900
V, MPM		4846	4846	4115	4115	4115	4115	4115	4115	4115	4115	4298	4298	4298	4298	4298	4298	4298	4298	4481	4481	4481
ANNEAL TYPE		245	245	Off	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Off	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam	Steam
°C		140	160	NA	40	60	80	100	120	140	160	NA	40	60	80	100	120	140	160	Off	40	60
°F		98	11	NA	2.8	4.2	56.0	7.0	8.4	9.8	11.2	NA	2.8	4.2	5.6	7.0	8.4	9.8	11.2	Off	2.8	4.2
KG/CM ²		50	50	70	70	70	70	70	70	70	70	70	70	70	70	70	70	70	70	70	70	70
DENIER		27	27	27	27	27	27	27	27	27	27	27	27	27	27	27	27	27	27	27	27	27
NO. FILS		1.85	1.85	2.59	2.59	2.59	2.59	2.59	2.59	2.59	2.59	2.59	2.59	2.59	2.59	2.59	2.59	2.59	2.59	2.59	2.59	2.59
DPF		10.7	12.0	5.5	11.5	16.5	53.0	56.5	37.0	24.5	16.5	4.0	7.5	8.0	16.5	27.0	35.0	26.0	22.0	3.5	11.5	5.0
S, %		11.2	10.7	4.8	7.8	12.2	37.5	54.0	23.7	13.9	13.1	4.8	6.3	8.5	12.5	21.2	21.0	15.4	14.5	4.3	6.1	8.4
DHS, %		0.5	-1.3	-0.7	-4.7	-4.3	-15.5	-1.5	-13.3	-10.6	-2.4	-0.8	-0.8	-0.5	-4.0	-5.8	-14.0	-10.6	-7.5	0.8	-5.40	3.40
DHS-S, %		290	280	80	100	140	130	150	130	110	110	90	140	150	180	160	150	140	130	90	130	160
STmax, MG/D		88	93	82	79	73	72	73	84	85	91	83	76	76	76	77	76	77	85	90	77	78
T(STmax), C		0.80	0.77	0.23	0.28	0.40	0.38	0.43	0.36	0.31	0.30	0.25	0.40	0.43	0.52	0.46	0.43	0.40	0.36	0.25	0.37	0.46
NST, (G/D)/K		27.1	23.3	1.5	0.9	0.8	0.3	0.3	0.4	0.4	0.7	2.3	1.87	1.88	1.09	0.59	0.43	0.54	5.91	2.57	1.13	3.20
Ms, G/D		3.2	3.4	0.4	1.2	2.3	4.9	1.7	4.8	2.7	1.8	0.4	1.1	1.2	3.0	4.32	5.25	3.64	2.86	0.32	1.50	0.80
Ps, G/D		4.32	5.25	3.64	2.86	0.32	1.50	0.80	2.47	2.21	3.04	1.92	2.08	0.41	0.70	4.32	5.25	3.64	2.86	0.32	1.50	0.80

TABLE NO.		TABLE 2E										
ITEM NO.		1	2	3	4	5	6C	7C	8C	9	10C	11
V, YPM	4900	4900	4900	4900	4900	5100	5100	5100	5100	5100	5100	5100
V, MPM	4481	4481	4481	4481	4481	4663	4663	4663	4663	4663	4663	4663
ANNEAL	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM
°C	245	245	245	245	245	245	245	245	245	245	245	245
lbs/in ²	80	100	120	140	160	OFF	40	60	80	100	120	120
KG/CM ²	5.6	7.0	8.4	9.8	11.2	OFF	2.8	4.2	5.6	7.0	8.4	8.4
DENIER	70	70	70	70	70	70	70	70	70	70	70	70
NO. FILS	27	27	27	27	27	27	27	27	27	27	27	27
DPF	2.59	2.59	2.59	2.59	2.59	2.59	2.59	2.59	2.59	2.59	2.59	2.59
S, %	14.5	13.0	19.0	12.0	16.0	3.7	5.0	5.0	6.5	6.5	6.5	15.0
DHS, %	14.6	10.9	14.2	11.6	10.2	4.8	9.6	9.6	5.1	10.8	7.6	16.5
DHS-S, %	0.10	-2.10	-4.80	-0.40	-5.80	1.10	4.60	4.60	0.10	4.70	1.10	1.50
STmax, MG/D	170	170	160	160	130	110	140	140	150	150	160	200
T(STmax),C	79	80	86	85	97	88	81	81	78	81	83	84
NST,(G/D)/K	0.48	0.48	0.45	0.45	0.35	0.30	0.40	0.40	0.43	0.42	0.45	0.56
MS, G/D	1.17	1.31	0.84	1.33	8.13	2.97	2.80	2.80	3.00	2.31	2.46	1.33
PS, G/D	2.47	2.21	3.04	1.92	2.08	0.41	0.70	0.70	0.75	0.98	1.0	3.0

TABLE NO. ITEM NO.	TABLE 2E (CONT.)											
	12	13	14C	15C	16C	17C	18C	19C	20C	21C		
V, YPM	5300	5300	5300	5300	5300	5300	5300	5300	5300	5300		
V,MPM	4846	4846	4846	4846	4846	4846	4846	4846	4846	4846		
ANNEAL	STEAM	STEAM	OFF	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM	STEAM		
°C	245	245	NA	245	245	245	245	245	245	245		
,LBS/IN ²	140	160	NA	40	60	80	100	120	140	160		
,KG/CM ²	9.8	11.2	NA	2.8	4.2	5.6	7.0	8.4	9.8	11.2		
DENIER	70	70	70	70	70	70	70	70	70	70		
NO. FILS	27	27	27	27	27	27	27	27	27	27		
DPF	2.59	2.59	2.59	2.59	2.59	2.59	2.59	2.59	2.59	2.59		
S, %	17.0	14.0	4.9	4.6	4.8	4.4	5.4	4.8	9.0	9.0		
DHS, %	13.0	11.3	4.8	4.7	5.0	5.8	5.5	5.7	8.2	9.0		
DHS-S, %	-4.00	-2.70	-0.1	0.1	0.2	1.4	0.1	0.9	0.8	0.0		
STmax, MG/D	190	160	100	90	100	90	120	120	130	130		
T(STmax),C	85	92	89	86	85	84	85	83	88	86		
NST,(G/D)/K	0.53	0.44	0.28	0.25	0.28	0.25	0.34	0.34	0.36	0.36		
Ms, G/D	1.12	1.14	2.04	1.96	2.08	2.05	2.22	2.50	1.44	1.44		
Ps, G/D	3.23	2.24	0.49	0.41	0.48	0.40	0.65	0.58	1.17	1.17		

TABLE NO.	ITEM NO.	1C	2	3C	4	5	6	7C	8	9	10	11C	12C	13C	14C
V, MPM	3600	NA	3600	NA	4100	4100	4100	NA	4600	4600	4600	5000	5000	5000	5000
ANNEAL	NA	NA	STEAM	NA	STEAM	STEAM	STEAM	NA	STEAM	STEAM	STEAM	NA	STEAM	STEAM	STEAM
°C	250	NA	250	NA	245	245	245	NA	245	245	245	NA	245	245	245
°C	80	NA	80	NA	60	80	80	NA	40	60	80	NA	40	60	80
°C	5.6	NA	5.6	NA	4.2	5.6	5.6	NA	2.8	4.2	5.6	NA	2.8	4.2	5.6
DENIER	72.6	73.0	72.6	68.8	70.5	70.3	69.3	70.0	70.0	70.1	69.7	69.9	70.5	69.9	70.3
NO. FILS	34	34	34	34	34	34	34	34	34	34	34	34	34	34	34
DPF	2.15	2.14	2.14	2.02	2.07	2.07	69.33	2.06	2.06	2.06	2.05	2.06	2.07	2.06	2.07
EB, %	95.0	95.0	95.0	88.0	68.0	68.0	60.0	85.0	63.0	60.0	53.0	66.0	66.0	65.0	62.0
RDR	1.95	1.51	1.51	1.88	1.68	1.68	1.60	1.85	1.63	1.60	1.53	1.66	1.66	1.65	1.62
TEN, G/D	2.90	2.90	2.90	3.10	3.20	3.30	3.40	3.0	3.60	3.70	3.60	3.80	3.60	3.70	3.60
TBK, G/DD	5.66	4.38	4.38	5.83	5.38	5.54	5.44	6.11	5.87	5.92	5.51	6.31	5.98	6.11	5.83
S, %	40.0	48.0	48.0	7.0	70.0	71.0	67.0	7.0	53.0	60.0	64.0	5.0	8.2	8.9	12.6
DHS, %	32.0	31.0	31.0	5.1	67.0	67.0	69.0	5.0	50.0	46.0	45.0	5.0	7.9	8.4	11.5
DHS-S, %	-8.0	-17.0	-17.0	-1.9	-3.0	-4.0	2.0	-2.0	-3.0	-14.0	-19.0	0.0	-0.3	-0.5	-1.1
STmax, MG/D	122	81	81	87	127	141	143	101	85	161	168	101	210	240	251
T(STmax), C	73	73	73	83	69	70	73	73	72	74	75	91	80	81	81
NST (G/D)/K	0.23	0.34	0.34	0.24	0.37	0.41	0.41	0.29	0.54	0.46	0.48	0.28	0.59	0.68	0.71
Ms, G/D	0.20	0.25	0.25	1.24	0.18	0.20	0.21	44	0.35	0.27	0.26	2.02	2.56	2.70	1.99
Ps, G/D	3.20	5.86	5.86	0.61	8.89	10.01	9.58	0.71	9.81	9.66	10.75	0.51	1.72	2.14	3.16
DEN, G/CC	1.3486	1.3560	1.3560	1.3583	1.3476	1.3484	1.3499	1.3650	1.3510	1.3496	1.3520	1.3817	1.3676	1.3678	1.3601
BIREF., X1000	547	1030	1030	---	---	---	---	---	---	---	---	---	---	---	---

TABLE NO.	ITEM NO.	1C	2C	3	4	5C	6C	7C	8C	9C	10C
SPIN (YPM)	4500	4500	4500	4500	4500	5000	5000	5000	5000	5500	6000
SPIN (MPM)	4115	4115	4115	4115	4115	4572	4572	4572	STEAM	5029	5486
ANNEAL	NA	STEAM	STEAM	STEAM	STEAM	NA	STEAM	STEAM	STEAM	NA	NA
TEMP.	NA	245	245	245	245	NA	245	245	245	NA	NA
PSI	NA	40	60	80	80	NA	40	60	80	NA	NA
Kg/CM ²	NA	2.8	4.2	5.6	5.6	NA	2.8	4.2	5.6	NA	NA
YARN DENIER	74.0	75.9	73.2	74.6	74.5	74.5	75.3	73.5	72.2	73.3	76.2
# FII.S	34	34	34	34	34	34	34	34	34	34	34
DPF	2.18	2.23	2.15	2.19	2.19	2.19	2.21	2.16	2.12	2.16	2.24
MOD, G/D	34.4	32.7	35.9	38.0	41.4	41.4	37.4	38.3	41.1	48.5	47.0
T7%, G/D	0.76	0.75	0.94	0.95	0.95	0.95	0.85	0.89	0.97	1.16	1.15
EB, %	79.3	79.3	63.2	64.5	70.2	75.7	75.7	73.3	72.5	62.1	63.6
RDR	1.793	1.793	1.632	1.645	1.702	1.757	1.757	1.733	1.725	1.621	1.636
TEN., G/D	3.09	3.07	2.99	3.11	3.44	3.25	3.25	3.29	3.45	3.67	3.70
THK, G/DD	5.54	5.50	4.88	5.12	5.85	5.71	5.71	5.70	5.95	5.95	6.06
S, %	7.0	8.5	68.7	62.7	3.9	5.7	5.7	6.3	5.8	3.7	3.4
DIHS, %	5.2	6.1	63.9	67.0	4.3	4.9	4.9	5.1	5.4	4.2	4.0
DIHS-S, %	-1.8	-2.4	-4.8	4.3	0.4	-0.8	-0.8	-1.2	-0.4	0.5	0.6
STmax, G/D	71	101	147	132	92	89	89	96	125	107	101
T(STmax), C	82	72	64	66	83	79	79	78	79	91	94
NST, (G/D)/	0.20	0.29	0.44	0.39	0.26	0.25	0.25	0.27	0.36	0.25	0.28
Ms, G/D	1.0	1.2	0.2	0.2	2.4	1.6	1.6	1.5	2.2	2.9	3.0
Ps, G/D	0.50	0.86	10.10	8.28	0.36	0.51	0.51	0.60	0.73	0.40	0.38
DEN., G/CC	1.3618	1.3596	1.3480	1.3493	1.3716	1.3645	1.3645	1.3651	1.3711	1.3783	1.4022

TABLE NO.		ITEM NO.		ANNEAL.		°C		, LBS/IN ²		, KG/CM ²		DENIER		NO. FILS		DPF		EB, %		RDR		TEN., G/D		TBK, G/DD		S, %		DHS, %		DHS-S, %		STmax, MG/D		NST, (G/D)/K		MS, G/D		PS, G/D		DEN., G/CC		BREF., X1000	
1	4100	NA	250	NA	250	NA	80	NA	5.6	NA	71.2	34	34	2.09	58.0	1.58	3.00	4.74	25.0	20.0	-5.0	99	76	0.28	0.40	2.48	1.3563	638															
2	4100	NA	250	NA	250	NA	80	NA	5.6	NA	71.0	34	34	2.08	58.0	1.58	3.00	4.74	25.0	20.0	-5.0	99	76	0.28	0.40	2.48	1.3574	1079															
3C	4600	NA	250	NA	250	NA	80	NA	5.6	NA	71.0	34	34	2.08	58.0	1.58	3.00	4.74	25.0	20.0	-5.0	99	76	0.28	0.40	2.48	1.3571	1184															
4C	4600	NA	250	NA	250	NA	80	NA	5.6	NA	71.0	34	34	2.08	58.0	1.58	3.00	4.74	25.0	20.0	-5.0	99	76	0.28	0.40	2.48	1.3571	1184															
5C	4100	NA	250	NA	250	NA	80	NA	5.6	NA	71.0	34	34	2.08	58.0	1.58	3.00	4.74	25.0	20.0	-5.0	99	76	0.28	0.40	2.48	1.3512																
6C	4100	NA	250	NA	250	NA	80	NA	5.6	NA	71.0	34	34	2.08	58.0	1.58	3.00	4.74	25.0	20.0	-5.0	99	76	0.28	0.40	2.48	1.3472																
7C	4100	NA	250	NA	250	NA	80	NA	5.6	NA	71.0	34	34	2.08	58.0	1.58	3.00	4.74	25.0	20.0	-5.0	99	76	0.28	0.40	2.48	1.3472																
8	4100	NA	250	NA	250	NA	80	NA	5.6	NA	71.0	34	34	2.08	58.0	1.58	3.00	4.74	25.0	20.0	-5.0	99	76	0.28	0.40	2.48	1.3475																
9	4100	NA	250	NA	250	NA	80	NA	5.6	NA	71.0	34	34	2.08	58.0	1.58	3.00	4.74	25.0	20.0	-5.0	99	76	0.28	0.40	2.48	1.3491																
10	5000	NA	250	NA	250	NA	80	NA	5.6	NA	71.0	34	34	2.08	58.0	1.58	3.00	4.74	25.0	20.0	-5.0	99	76	0.28	0.40	2.48	1.3670																
11C	5000	NA	250	NA	250	NA	80	NA	5.6	NA	71.0	34	34	2.08	58.0	1.58	3.00	4.74	25.0	20.0	-5.0	99	76	0.28	0.40	2.48	1.3670																
12C	5000	NA	250	NA	250	NA	80	NA	5.6	NA	71.0	34	34	2.08	58.0	1.58	3.00	4.74	25.0	20.0	-5.0	99	76	0.28	0.40	2.48	1.3670																
13C	5000	NA	250	NA	250	NA	80	NA	5.6	NA	71.0	34	34	2.08	58.0	1.58	3.00	4.74	25.0	20.0	-5.0	99	76	0.28	0.40	2.48	1.3653																
14	5000	NA	250	NA	250	NA	80	NA	5.6	NA	71.8	34	34	2.11	66.0	1.66	3.60	5.90	7.4	6.2	6.7	6.7	6.7	7.3	79	80	0.51	1.3738															
15	4100	NA	250	NA	250	NA	80	NA	5.6	NA	71.8	34	34	2.11	66.0	1.66	3.60	5.90	7.4	6.2	6.7	6.7	6.7	7.3	79	80	0.51	1.3481															
16C	4600	NA	250	NA	250	NA	80	NA	5.6	NA	71.8	34	34	2.11	66.0	1.66	3.60	5.90	7.4	6.2	6.7	6.7	6.7	7.3	79	80	0.51	1.3582															
17C	5000	NA	250	NA	250	NA	80	NA	5.6	NA	71.8	34	34	2.11	66.0	1.66	3.60	5.90	7.4	6.2	6.7	6.7	6.7	7.3	79	80	0.51	1.3738															
17C	5000	NA	250	NA	250	NA	80	NA	5.6	NA	71.8	34	34	2.11	66.0	1.66	3.60	5.90	7.4	6.2	6.7	6.7	6.7	7.3	79	80	0.51	1.3738															

TABLE NO.	ITEM NO.	TABLE SA															
		1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16
V, MPM	3750	Air	3750	Air	3750	Air	3750	Air	3750	Air	4000	Air	4000	Air	4000	Air	4000
ANNEAL	120	150	150	120	135	150	180	120	150	120	150	120	135	150	180	120	150
ANNEAL, °C	40	40	40	60	60	60	60	80	80	40	40	60	60	60	60	80	80
DENIER	1.18	1.18	1.18	1.76	1.76	1.76	1.76	2.35	2.35	1.18	1.18	1.76	1.76	1.76	1.76	2.35	2.35
DPF	51.1	65.0	43.2	43.5	58.7	59.2	59.2	34.6	58.4	49.1	68.0	43.0	51.1	63.5	59.2	36.7	58.1
MOD., G/D	1.76	3.00	1.25	1.27	2.55	2.82	2.82	0.99	2.24	1.66	3.23	1.29	1.33	2.72	2.82	1.08	2.38
T7%, G/D	43.5	32.9	59.3	59.8	36.3	33.4	33.4	72.6	41.9	41.5	28.3	57.4	60.8	35.5	33.4	67.2	42.2
EB, %	1.435	1.329	1.593	1.598	1.363	1.334	1.334	1.726	1.419	1.415	1.283	1.574	1.608	1.355	1.334	1.672	1.422
RDR	3.54	4.57	3.39	3.41	4.27	4.55	4.55	3.24	4.23	3.29	4.62	3.47	3.74	4.46	4.55	3.37	4.46
TEN., G/D	5.08	6.07	5.40	5.45	5.82	6.07	6.07	5.59	6.00	4.66	5.93	5.46	6.01	6.04	6.07	5.63	6.34
TBK, G/DD	51.9	8.2	52.0	48.1	8.7	5.5	5.5	49.3	10.3	44.7	8.2	47.4	51.1	9.2	5.5	48.9	10.8
S, %	60.7	9.5	72.4	73.6	9.8	7.7	7.7	68.1	10.6	57.7	9.9	62.1	66.9	10.0	7.7	58.3	11.0
DHS, %	8.8	1.3	20.4	25.5	0.9	2.2	2.2	36.8	0.3	13.0	1.7	14.7	15.8	0.8	2.2	9.6	0.2
DHS-S, %	200	390	130	140	290	340	340	110	240	210	340	160	150	330	340	130	200
STmax, MG/D	77	150	72	73	141	170	170	73	133	72	160	73	72	147	170	73	133
T(STmax),C	0.57	0.92	0.38	0.40	0.70	0.77	0.77	0.32	0.59	0.61	0.79	0.46	0.43	0.79	0.77	0.27	0.49
NST,(G/D)/K	0.39	4.76	0.25	0.29	3.33	6.18	6.18	0.23	1.29	0.47	0.41	0.34	0.29	0.36	3.09	0.49	1.85
Ms, G/D	10.4	3.2	6.8	6.7	2.5	1.9	1.9	5.4	2.5	9.4	2.8	7.6	7.7	3.3	2.6	7.6	2.2
Ps, G/D																	

TABLE NO.		TABLE 5B																			
ITEM NO.		1	2	3	4	5C	6	7	8	9	10	11	12	13	14C	15	16	17	18	19	
V, YPM		4500	4500	4500	4500	4500	4500	4500	4500	5000	5000	5000	5000	5000	5000	5500	5500	5500	6000	6000	
ANNEAL		Air	Air	Air	Air	Air	Air	Air	Air	Air	Air	Air	Air	Air	Air	Air	Air	Air	Air	Air	
ANNEAL, °C		120	150	120	135	150	180	120	150	120	120	135	150	180	120	120	135	180	120	135	
YARN DENIER		40	40	60	60	60	60	80	80	40	60	60	60	60	80	80	80	80	80	80	
DPF		1.18	1.18	1.76	1.76	1.76	1.76	2.35	2.35	1.18	1.76	1.76	1.76	1.76	2.35	2.35	2.35	2.35	2.35	2.35	
MOD., G/D		53.1	70.4	48.2	48.3	59.4	61.7	60.5	59.4	67.0	53.3	53.2	60.5	70.7	47.9	70.5	65.3	80.5	61.8	78.3	
T7%, G/D		1.90	3.60	1.50	1.59	2.95	3.12	2.63	2.95	2.29	1.76	1.79	2.63	3.00	1.57	2.56	2.47	3.17	3.03	2.95	
EB, %		44.3	25.4	53.5	54.1	28.9	31.6	37.1	28.9	40.9	51.5	54.1	37.1	33.3	53.8	31.0	34.3	28.4	23.8	24.6	
RDR		1.443	1.254	1.535	1.541	1.289	1.316	1.371	1.289	1.409	1.515	1.541	1.371	1.333	1.538	1.310	1.343	1.284	1.238	1.246	
TEN., G/D		3.68	4.85	3.44	3.79	4.47	4.87	4.56	4.47	3.91	3.75	3.79	4.56	4.75	3.64	3.79	3.96	4.44	3.90	3.95	
TBK, G/DD		5.31	6.08	5.28	5.84	5.76	6.41	6.25	5.76	5.51	5.68	5.84	6.25	6.33	5.60	5.0	5.3	5.7	4.83	4.92	
S, %		23.6	8.6	23.9	28.7	10.0	6.1	11.4	10.0	13.5	10.6	11.0	11.4	5.2	6.2	15.7	12.6	5.7	11.4	12.5	
DHS, %		24.7	9.6	22.8	28.6	10.6	7.4	11.8	10.6	11.5	9.2	9.5	11.8	6.8	5.6	13.3	12.5	7.3	9.8	11.9	
DHS-S, %		1.1	1.0	-1.1	-0.1	0.6	1.3	0.4	0.6	-2.0	-1.4	-1.5	0.4	1.6	-0.6	-2.4	-0.1	1.6	-1.6	-0.6	
STmax, MG/D		200	430	200	200	110	380	310	360	330	170	230	310	440	160	460	310	540	410	380	
T(STmax),C		77	172	77	75	150	177	138	150	80	84	83	138	177	85	80	81	153	84	80	
NST,(G/D)/K		0.57	0.97	0.57	0.57	0.38	0.54	0.75	0.85	0.93	0.48	0.65	0.75	0.98	0.45	1.30	0.88	1.27	1.15	1.08	
Ms, G/D		0.8	5.0	0.8	0.7	1.1	6.2	2.7	3.6	2.4	1.6	2.1	2.7	8.5	2.6	2.9	2.5	9.5	3.6	3.0	
Ps, G/D		4.7	3.7	4.6	5.7	1.1	2.3	3.5	3.6	4.5	1.8	2.5	3.5	2.3	1.0	7.2	3.9	3.1	4.7	4.8	

TABLE NO.		TABLE 6																						
ITEM NO.		1C	2C	3C	4	5	6C	7	8	9	10C	11	12	13	14C	15C	16C	17	18C	19	20C	21C	22	
V, MPM		3000	3000	3000	3500	3500	4000	4000	4000	4000	4550	4550	4550	4550	5060	5060	5060	5060	5060	5060	5060	5610	5610	
ANNEAL, °C		Air	Air	Air	Air	Air	Air	Air	Air	Air	Air	Air	Air	Air	Air	Air	Air	Air	Air	Air	Air	Air	Air	
ANNEAL, °C		Off	Off	Off	Off	Off	Off	Off	Off	Off	Off	Off	Off	Off	Off	Off	Off	Off	Off	Off	Off	Off	Off	
DENIER		62.2	63.0	62.4	62.7	62.9	62.0	61.6	60.0	62.6	62.4	62.2	61.8	62.0	62.0	62.0	62.0	61.7	62.2	62.2	61.7	62.3	61.9	
EB, %		122.9	71.0	66.7	105.4	59.2	90.7	56.0	55.7	56.9	85.0	63.3	53.3	50.9	71.4	76.6	76.5	73.2	69.9	70.8	67.1	61.1	63.4	
RDR		223	1.71	1.62	2.05	1.59	1.91	1.56	1.56	1.57	1.85	1.63	1.53	1.51	1.71	1.77	1.77	1.73	1.70	1.71	1.67	1.61	1.63	
TEN, G/D		2.78	3.62	3.42	3.00	2.96	3.05	3.97	3.95	3.94	3.30	3.45	3.85	4.06	3.28	3.25	3.37	3.41	3.37	3.57	3.63	3.22	3.64	
TBK, G/DD		6.20	3.74	5.70	6.15	4.71	5.83	6.19	6.15	6.18	6.11	5.63	5.90	6.13	5.61	5.74	5.95	5.91	5.73	6.10	6.07	5.18	5.89	
S, %		38.3	6.4	8.6	22.4	8.4	7.5	31.5	15.1	9.3	5.3	22.0	23.9	11.3	4.1	3.7	4.2	5.6	6.1	10.2	12.3	4.4	8.0	
DHS, %		40.4	6.8	8.1	18.2	8.1	6.3	32.8	13.8	9.0	5.0	22.2	21.3	11.4	4.1	4.0	4.6	5.6	6.5	9.3	11.3	5.0	8.0	
DHS-S, %		1.9	0.4	-0.5	-4.2	-0.3	-1.2	0.7	-1.3	-0.3	0.2	-2.6	0.1	0.0	0.0	0.3	0.4	0.0	0.4	-0.9	-1.0	0.6	0.0	
STmax, MG/D		69	140	157	95	170	128	210	219	228	180	257	285	257	187	166	220	268	227	288	306	197	315	
T(STmax), C		72	92	86	71	90	75	77	89	92	75	79	82	94	80	82	78	77	81	83	87	86	88	
NST, (G/D)/K		0.20	0.38	0.44	0.28	0.47	0.37	0.60	0.60	0.62	0.52	0.73	0.80	0.70	0.53	0.47	0.63	0.77	0.64	0.81	0.85	0.55	0.87	
NS, G/D		2.64	2.19	1.83	0.42	2.02	1.71	0.67	1.45	2.45	3.40	1.17	1.19	2.27	4.56	4.49	5.24	4.79	3.72	2.82	3.14	4.48	3.94	
Ps, G/D		0.18	0.90	1.35	2.13	1.43	0.96	6.62	3.31	2.12	0.95	5.65	6.81	2.90	0.77	0.61	0.92	1.50	1.38	2.94	3.76	0.87	2.52	

TABLE NO.	TABLE 7	TABLE 8	TABLE 9	TABLE 10	TABLE 11	TABLE 12	TABLE 13C	TABLE 14C	TABLE 15C
ITEM NO.	7	8	9	10	11	12	13C	14C	15C
SPEED, MPH	3658	3658	4115	4115	4115	4115	4572	4572	4572
TREAT., °C	180	180	135	135	135	135	120	120	120
DR(1)	1.11	1.19	1.00	1.09	1.18	1.22	1.00	1.02	1.06
DRAW TEMP.	Off	Off	Off	Off	Off	Off	Off	Off	Off
RELAX, °C	Off	Off	Off	Off	Off	Off	Off	Off	Off
DENIER	60.0	55.4	59.8	56.6	51.8	50.7	58.3	60.1	58.8
MOD., G/D	44.4	70.1	54.1	56.6	51.8	50.7	58.3	81.0	84.8
EB, %	53.3	29.3	52.6	43.5	33.6	28.7	32.5	33.7	32.9
RDR	1.533	1.293	1.526	1.435	1.336	1.287	1.325	1.337	1.329
TEN., G/D	3.18	4.36	3.81	3.87	4.28	4.49	4.47	4.47	4.41
T7, G/D	1.29	2.70	1.86	2.17	2.90	3.26	3.09	3.09	3.19
S, %	43.6	42.7	9.7	12.7	16.0	16.1	5.5	5.1	4.9
DHS, %	73.6	36.6	8.6	11.0	13.4	14.2	7.3	8.6	8.6
DHS-S, %	30.0	-4.4	-0.9	-1.7	-2.6	-1.9	1.8	3.5	3.7
STmax, MG/D	98	174	199	190	399	404	377	304	240
T(STmax), C	72	72	83	83	79	77	166	172	158
NST,(G/D)/K	0.28	0.54	0.70	0.53	1.13	1.15	0.86	0.68	0.56
Ms, G/D	0.22	0.42	2.05	1.50	2.49	2.51	6.85	5.96	4.90
Ps, G/D	4.27	8.34	1.93	2.53	6.38	6.50	2.07	1.55	1.18

TABLE 8

TABLE NO.	ITEM NO.	1C	2C	3C	4C	5C	6C	7	8	9	10	11	12	13C	14C	15	16	17	18	19C	20C	21C
SPEED, MPM		NA	200	200	200	200	NA	200	NA	200	NA	200	NA	200	200	NA	200	200	NA	200	300	400
DR(1)		NA	1.01	1.03	1.01	1.03	NA	1.10	1.20	NA	1.10	1.20	NA	1.10	1.20	NA	1.10	1.20	NA	0.91	0.91	0.91
DR(2)		NA	1.00	1.00	1.00	1.00	NA	1.00	1.00	NA	1.00	1.00	NA	1.00	1.00	NA	1.00	1.00	NA	1.00	1.00	1.00
DR(1)xDR(2)		NA	1.01	1.03	1.01	1.03	NA	1.10	1.20	NA	1.10	1.20	NA	1.10	1.20	NA	1.10	1.20	NA	0.91	0.91	0.91
PLATE 1, °C		NA	110	110	180	180	NA	180	180	NA	180	180	NA	180	180	NA	180	180	NA	200	200	200
PLATE 2, °C		NA	27	27	27	27	NA	27	27	NA	27	27	NA	27	27	NA	27	180	NA	27	27	27
DENIER		35.0	34.6	31.1	34.7	34.0	---	32.3	29.7	---	---	32.2	---	32.2	29.8	---	---	29.8	---	75.5	75.4	75.6
EB, %		---	59.4	60.0	59.7	57.5	---	32.8	32.5	---	53.1	40.3	---	33.8	23.5	---	27.8	14.5	---	51.7	48.1	49.2
DPF		---	1.59	1.600	1.597	1.575	---	1.328	1.325	---	1.531	1.403	---	1.338	1.235	---	1.278	1.145	---	1.517	1.481	1.492
S, %		4.0	4.7	6.5	3.2	2.9	4.0	3.9	4.0	10.5	4.0	3.8	17.0	4.3	4.0	16.0	4.9	3.9	14.0	2.5	2.9	3.4
DHS, %		3.7	4.9	5.0	4.0	4.3	7.7	5.5	5.6	10.4	6.7	6.1	15.1	6.1	6.4	12.4	7.7	8.0	10.9	3.8	4.9	4.4
DHS-S, %		-0.3	0.2	-1.5	0.8	1.4	3.7	1.6	1.6	-0.1	2.7	2.3	-1.9	1.8	2.4	-3.6	2.8	4.1	-3.1	1.3	2.0	1.0
STmax, MG/D		(80)	129	157	128	140	---	209	251	---	402	467	---	357	490	---	590	647	286	60	73	46
T(STmax), C		91	84	82	85	90	---	110	188	---	155	194	---	173	192	---	172	192	---	84	86	84
NST, (G/D)/K		(0.22)	0.50	0.44	0.36	0.39	---	0.55	0.54	---	0.94	1.00	---	0.80	0.11	---	1.33	1.39	---	0.17	0.20	0.13
Ms, G/D		(0.32)	0.6	1.0	0.4	0.4	---	0.8	1.0	---	1.6	1.8	---	1.5	2.0	---	28.9	25.2	---	0.2	0.2	0.2
Ps, G/D		(2.0)	2.7	2.4	4.0	4.8	---	5.4	6.3	---	10.0	12.3	---	8.3	12.3	---	12.0	16.6	---	2.4	2.5	1.4

TABLE NO.
ITEM NO.
YARN TYPE
DRAW-RATIO
DRAW, C
SET, C
RELAX, C
DENIER
T7, G/D
EB, %
S2, %
S, %
STmax, MG/D
Ms, G/D
Ps, (G/D)%
DEN., G/CC
CS, Angstrom
RDDR, X1000
(1 dpf)

1C	DUY	1.00	Off	Off	Off	Off	108.0	0.90	74.90	-0.3	3.4	70	2.06	0.24	1.3624	66	237
2C	FDY	1.34	95	170	Off	Off	81.8	2.20	25.40	1.2	5.9	420	7.12	2.48	1.3810	75	140
3C	PDY	1.18	95	170	Off	Off	91.5	1.70	42.80	0.7	4.4	240	5.45	1.06	1.3869	73	148
4C	PDY	1.18	95	195	Off	Off	92.2	1.80	40.00	1.2	2.3	220	9.57	0.51	1.3988	71	182
5	PDY	1.18	Off	Off	Off	Off	93.9	1.40	48.40	-0.6	8.9	170	0.35	1.51	1.3815	64	231
6C	PDY	1.30	Off	Off	Off	Off	93.2	1.30	45.40	0.2	2.0	30	15.00	0.06	1.3864	71	194
7C	FDY	1.47	Off	Off	Off	Off	83.6	4.00	30.70	1.1	1.7	40	23.53	0.07	1.3880	72	98
8C	FDY	1.54	95	170	Off	Off	70.6	3.40	24.20	6.8	6.8	410	6.03	2.79	1.3838	58	74
9C	PDY	1.34	Off	Off	Off	Off	81.4	1.40	48.10	-7.2	25.8	180	0.70	4.64	1.3590	<30	186
10C	FDY	1.00	Off	Off	Off	Off	70.0	3.10	25.20	5.3	7.0	220	3.14	1.54	1.3764	44	66

TABLE 10

YARN ID DPF	ITEM NO	DRAW RATIO	DRAW TEM	BOS %	STmax MG/D	Tmax DEG. C	Ps (G/D)%	Ms (G/D)
A - 0.80	1	1.60	25	40.3	----	----	----	----
	2	1.60	115	8.7	----	----	----	----
	3	1.60	180	4.4	----	----	----	----
B - 0.64	4	1.40	25	21.2	----	----	----	----
	5	1.40	115	7.8	----	----	----	----
	6	1.40	180	3.8	----	----	----	----
C - 0.86	7A	1.00	OFF	49.9	----	----	----	----
	7	1.64	25	48.1	395	74	19.00	0.82
	9	1.64	110	11.7	371	110	4.33	0.94
	10	1.64	115	10.3	425	124	4.38	4.13
	11	1.64	120	9.8	365	152	3.58	3.72
	12	1.64	130	8.3	357	140	2.96	4.30
	13	1.64	140	7.4	447	152	3.31	6.04
	14	1.64	150	6.6	385	156	2.54	5.83
	15	1.64	160	6.2	384	170	2.15	6.19
	16	1.64	170	5.6	408	160	2.28	7.29
	17	1.64	180	5.4	376	175	2.03	6.96
D - 3.44	17A	1.00	OFF	56.4	----	----	----	----
	18	1.64	25	60.8	260	72	15.81	0.43
	19	1.64	110	46.8	150	76	4.02	0.32
	20	1.64	115	32.5	169	85	5.49	0.52
	21	1.64	120	20.5	141	88	2.89	0.69
	22	1.64	130	18.1	185	108	3.35	1.02
	23	1.64	140	10.3	206	115	2.11	2.00
	24	1.64	150	8.5	213	110	1.81	2.51
	25	1.64	160	7.4	207	120	1.53	2.80
	26	1.64	170	6.7	205	132	1.37	1.97
	27	1.64	180	6.5	157	117	1.02	1.80

TABLE NO. ITEM NO.	TABLE 11										
	1C OFF	2C FREE	3C FREE	4C FREE	5C FREE	6C FREE	7C TAUT	8C TAUT	9C TAUT	10C TAUT	11C TAUT
ANNEALED											
TEMP., C	RT	60	100	120	160	220	60	100	120	160	220
DENIER	196	200	203	203	206	211	198	197	194	192	184
MOD., G/D	79.4	67.4	57.1	69.5	69.5	59.2	70.2	74.9	75.5	77.9	86.6
T20%, G/D	1.87	1.78	1.79	1.74	1.87	1.86	1.85	2.08	2.11	2.40	2.88
EB, %	51.6	51.9	53.5	53.6	57.6	57.9	53.4	51.7	50.6	46.0	40.8
RDR	1.516	1.519	1.535	1.536	1.576	1.579	1.534	1.517	1.506	1.460	1.408
TEN., G/D	3.76	3.27	3.18	3.13	3.43	3.34	3.43	3.48	3.62	3.60	3.85
TBK, G/DD	5.70	4.97	4.88	4.81	5.41	5.27	5.26	5.28	5.45	5.26	5.42
DHS, %	3.5	3.5	3.2	3.0	5.3	5.3	1.0	0.6	-1.1	-2.1	-6.5
S, %	3.6	0.2	0.1	-0.2	-0.1	-0.2	3.7	3.2	3.0	1.6	1.3
DEN., G/CC	1.3810	1.3794	1.3852	1.3875	1.3941	1.4044	1.3794	1.3859	1.3873	1.3949	1.4040
SV, KM/SEC	2.70	2.76	2.84	2.82	2.78	2.61	2.78	2.91	2.97	3.12	3.23
Msonic*	10.1	10.5	11.2	11.0	10.8	9.6	10.7	11.7	12.2	13.6	14.7
COA, °	11.0	13.5	13.0	13.5	12.0	14.0	12.5	13.0	13.5	13.0	14.0
CS, A	73	66	61	64	75	75	74	65	70	70	76
LPS, A	374	318	318	116	117	145	318	318	318	120	146

* 10^{10} Dynes/cm²; A = Angstroms

TABLE 12A

Yarn Code	Treatment Temp., °C	Density gm/cm ³	X _p	Δn	Δna*	%S	Den.	Mod. gpd	Ten. gpd	Elong. %	T ₇ gpd	Rec. %	Sh. Ten. gpd
A60	60	1.3710	.319	.0773	.024	0.6	76.0	38.8	2.87	91.0	0.85	83.5	.018
A70	70	1.3794	.391	.0844	.016	2.2	77.2	43.5	3.04	94.2	0.95	86.6	.013
A100	100	1.3877	.461	.1024	.027	3.2	77.9	40.7	2.88	86.9	1.02	80.1	.018
A140	140	1.3964	.534	.1192	.037	3.2	77.9	53.6	3.05	84.2	1.18	80.5	.016
A160	160	1.3977	.544	.1218	.039	1.9	76.9	53.5	2.90	85.4	1.05	81.6	.012
1A	120	1.3832	.423	.0908	.017	2.0	77.0	42.5	2.85	83.0	0.94	81.7	.020
2A	160	1.3907	.486	.1154	.044	1.7	76.8	50.8	2.86	81.4	1.13	82.3	.018
3A	180	1.3936	.510	.1220	.050	2.1	77.1	51.0	2.86	76.5	1.18	80.9	.019
4A	220	1.4052	.606	.1380	.057	2.1	77.1	51.3	3.10	78.2	1.22	80.8	.017
5A	240	1.4132	.676	.1481	.061	4.2	78.7	54.2	2.95	72.1	1.16	75.7	.010

TABLE I2B

Yarn Code	Treatment Temp., °C	Density gm/cm ³	X _p	Δn	Δn^*	Mod. gpd	Ten. gpd	Elong. %	T ₇ gpd	Rec. %	Sh. Ten. gpd
B60	60	1.3822	.415	.0923	.022	47.3	2.75	67.6	1.05	--	.016
B70	70	1.3850	.438	.0990	.027	44.2	2.72	79.3	1.07	88.6	.021
B100	100	1.3862	.448	.1006	.027	46.0	2.92	85.2	1.09	86.9	.020
B140	140	1.3947	.520	.1191	.040	48.8	2.89	81.4	1.13	85.6	.018
B160	160	1.3988	.554	.1262	.046	52.4	2.75	72.9	1.18	85.6	.024
1	120	1.3772	.372	.0803	.015	43.5	2.81	81.0	0.93	86.2	.044
2	160	1.3884	.467	.1044	.029	51.3	2.99	78.9	1.13	85.7	.043
3	180	1.3908	.487	.1087	.031	52.8	2.99	81.2	1.16	87.8	.034
4	220	1.3951	.523	.1198	.042	55.6	3.12	81.4	1.23	87.9	.034
5	240	1.4020	.580	.1357	.060	60.1	3.05	72.3	1.30	86.2	.036

TABLE I3

	1	2	3	4	5	6	7	8	9
Draw Ratio	--	RELAX	RELAX	TAUT	TAUT	1.05	1.05	1.10	1.10
Draw Temperature (°C)	--	100	180	100	180	95	180	95	180
Wet/Dry	--	WET	DRY	WET	DRY	WET	DRY	WET	DRY
Density, ρ (g/cm ³)	1.3719	1.3877	1.3936	1.3862	1.3908	1.3756	1.3976	1.3801	1.397
Birefringence (Δn)	0.071	0.102	0.122	0.101	0.109	0.081	0.121	0.099	0.127
Crystal Size, CS (Å)	72	75	72	66	72	68	75	--	--
Modulus, M (g/d)	48.5	40.7	51.0	46.0	52.8	48.4	58.3	54.6	66.6
Tenacity at 7%, T ₇ (g/d)	0.9	1.0	1.2	1.1	1.2	1.1	1.3	1.3	1.3
Elongation, E _B (%)	89.9	86.9	76.5	85.2	81.2	66.7	60.2	56.1	47.8
Tenacity, T (g/d)	3.0	2.9	2.9	2.9	3.0	2.9	3.0	3.0	3.0
Shrinkage Tension, ST (g/d)	0.07	0.02	0.02	0.02	0.03	0.14	0.09	0.20	0.17
Dye Uptake (K/S)	17.7	--	--	15.6	16.3	16.7	12.2	16.8	10.7

TABLE 14A

SPIN SPEED, YPM	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15
	4500	4500	4000	4000	5000	5000	4500	4500	4500	4500	4500	4500	4500	5500	5500
SPIN SPEED, MPM (n)	4115	4115	3659	3659	4572	4572	4115	4115	4115	4115	4115	4115	4115	5029	5029
	0.65	0.65	0.73	0.73	0.59	0.59	0.65	0.65	0.65	0.65	0.65	0.65	0.65	0.65	0.65
T p, °C	302	302	302	302	302	302	302	302	302	296	296	302	302	305	297
CAP. (DxL), MILS	10x40	15x60	10x40	15x60	10x40	10x40	9x50	15x72	15x72	9x50	15x72	10x40	15x60	9x50	9x36
NO. FILAMENTS	34	34	34	34	34	34	34	34	34	68	34	40	34	34	34
DPF	2.88	2.90	2.86	2.89	2.89	2.90	2.89	2.92	4.34	2.22	3.06	2.45	2.90	5.20	4.90
SHAPE	RND	RND	RND	RND	RND	RND	RND	TRI	TRI	RND	OCTA	RND	RND	RND	RND
QUENCH	XF	XF	XF	XF	XF	XF	XF	XF	XF	4RAD	2RAD	XF	XF	4XF	XF
MODULUD, G/D	44.7	48.2	40.6	45.1	53.3	51.6	42.0	46.4	43.4	36.9	51.1	43.8	48.2	53.3	45.6
ELNG. (Eb), %	76.3	78.8	88.4	84.2	68.4	68.5	80.6	73.0	73.8	87.0	71.4	78.8	78.8	60.8	65.8
TENACITY, G/D	3.12	3.23	3.04	3.07	3.34	3.32	3.15	2.88	2.82	3.04	2.98	3.18	3.23	3.96	3.56
SI, %	13.8	5.4	9.2	4.8	13.1	5.5	30.0	4.7	15.3	20.1	3.4	7.6	5.4	9.1	3.4
DHS, %	9.0	4.4	7.1	4.3	9.4	4.5	24.6	4.0	10.1	13.6	3.3	6.9	4.4	8.0	3.7
(DHS-SI), %	-4.8	-1.0	-2.1	-0.5	-3.7	-1.0	-5.5	-0.7	-5.2	-6.5	-0.1	-0.7	-1.0	-1.1	0.3
STmax, MG/D	91	85	52	65	87	92	73	72	62	78	75	76	85	65	76
M _s , G/D	0.60	1.57	0.57	1.35	0.66	1.67	0.53	1.53	0.41	0.39	2.21	1.00	1.57	0.71	2.24
P _s , G/D	1.26	0.46	0.48	0.31	1.14	0.51	1.01	0.34	0.95	1.57	0.26	0.58	0.46	0.59	0.26
DENSITY, G/CC	1.353	1.359	1.353	1.356	1.351	1.356	1.348	1.359	1.352	1.352	1.371	1.356	1.359	1.354	1.371
RRDDR, x1000	120	98	145	139	109	99	119	147	115	139	202	101	98	N/A	100

TABLE 14B

	1	2	3	4	5	6	7	8	9
YARN TYPE	1-HIGH	1-LOY	1-MIX	2-HIGH	2-LOY	2-MIX	3-HIGH	3-LOY	3-MIX
SPIN SPEED, YPM	4500	4500	4500	4500	4500	4500	4000	4000	4000
SPIN SPEED, MPM	4115	4115	4115	4115	4115	4115	3658	3658	3658
(η)	0.65	0.65	0.65	0.65	0.65	0.65	0.65	0.65	0.65
Tp, °C	302	302	302	302	302	302	288	288	288
CAP. (DxL), MILS	9X50	15X72	N/A	9X50	15X72	N/A	9X12	15X60	N/A
NO. FILAMENTS	34+34	40+40	34+40	34+34	34+34	34+34	17+17	34+34	17+34
DPF	2.2	1.9	N/A	2.2	2.2	N/A	3.9	2.0	N/A
SHAPE	RND	OCTA	N/A	RND	TRI	N/A	RND	RND	RND
QUENCH	XF	XF	XF	XF	XF	XF	XF	XF	XF
MODULUS, G/D	43.3	53.8	50.5	43.4	49.7	49.7	30.9	38.6	28.8
ELNG. (Eb), %	82.0	80.9	76.6	82.0	71.7	72.7	98.0	90.0	102.0
TENACITY, G/D	3.15	3.39	3.07	3.15	2.96	2.92	2.80	2.90	2.80
Sl, %	12.5	3.9	11.0	12.5	3.9	10.6	16.7	5.9	16.5
DHS, %	9.4	3.7	8.8	9.4	4.2	7.4	16.3	5.3	16.0
(DHS-Sl), %	-3.1	-0.2	-2.2	-3.1	0.3	-3.2	-0.4	-0.6	-0.5
STmax, MG/D	75	86	81	75	77	76	77	97	73
Ms, G/D	0.60	2.21	0.74	0.60	1.97	0.72	0.46	1.64	0.44
Ps, G/D	0.94	0.34	0.89	0.94	0.30	0.81	1.29	0.57	1.20
DENSITY, G/CC	1.3514	1.3627	1.3570	1.3514	1.3620	1.3573	1.3484	1.3600	1.3561
RDDR X 1000	119	126	123	119	139	129	---	---	195
DFL (DHS), %	0.0	0.0	5.1	0.0	0.0	5.2	0.0	0.0	11.0
BEL, BULK, %	3.1	0.2	8.8	3.1	0.3	8.3	0.4	0.6	11.4

TABLE 15

ITEM NO.	YARN COUNT	DPF	BOS, %	STmax (G/D)	Ps (G/D) %	BULK-IN FABRIC
1A	75-34	2.20	12.00	0.15	1.80	YES
1B	50-34	1.47	11.00	0.21	2.31	YES
2A	75-68	1.10	9.50	0.13	1.24	NO
2B	50-68	0.73	12.00	0.17	2.04	YES
2C	35-68	0.51	9.00	0.20	1.80	YES
3A	75-100	0.75	11.00	0.11	1.21	NO
3B	50-100	0.50	12.00	0.19	2.28	YES
4A	75-68	1.10	11.00	0.10	1.10	NO
4B	50-68	0.73	8.00	0.12	0.96	NO
4C	35-68	0.51	6.00	0.32	1.96	YES
5A	50-68R	0.73	9.00	0.14	1.26	NO
5B	50-50T	1.00	11.00	0.14	1.54	YES

R - ROUND; T - TRILOBAL

TABLE 16

Yarn Count (A+B) Bundle Denier A Bundle Denier B	Steam Pressure (psi)	← Boil-Off Shrinkage (S), % →				← Shrinkage Tension (ST _{max}), G/D →			
		140/85	140/95	140/117	140/17	140/85	140/95	140/117	140/127
		70/68 70/17	70/68 70/27	70/100 70/17	70/100 70/27	70/68 70/17	70/68 70/27	70/100 70/17	70/100 70/27
4500 ypm	40	18	18	23	9	90	90	100	90
	60	31	16	27	28	80	80	90	100
	80	61	57	60	58	80	90	80	100
	100	55	54	59	55	100	90	90	90
	120	54	29	48	43	90	100	90	90
	140	34	32	30	32	90	80	90	90
	160	12	17	18	29	90	90	90	100
4700 ypm	40	10	8	8	7	90	100	80	90
	60	11	9	11	12	90	100	100	100
	80	26	27	17	15	110	120	90	90
	100	50	11	28	39	150	110	90	110
	120	35	11	21	32	130	130	90	90
	140	24	12	10	23	140	110	80	110
	160	12	12	4	16	140	90	90	110
4900 ypm	40	4	7	15	6	110	90	130	110
	60	7	7	17	6	100	100	160	120
	80	7	9	19	11	130	100	170	120
	100	8	24	24	13	120	100	160	130
	120	30	26	22	30	120	150	180	140
	140	32	10	23	4	150	160	150	140
	160	4	5	4	4	100	100	100	100
5100 ypm	40	5	3	8	5	100	110	90	110
	60	4	4	5	5	100	120	100	120
	80	6	5	8	7	100	120	90	120
	100	8	5	22	15	110	120	10	120
	120	9	13	29	13	100	150	10	150
	140	10	9	23	13	110	130	90	130
	160	12	9	18	13	110	140	100	140
5300 ypm	40	5	4	5	4	110	80	100	80
	60	5	4	5	4	90	100	90	100
	80	5	5	4	3	10	90	100	90
	100	6	6	7	9	90	110	90	110
	120	5	5	7	5	110	130	100	130
	140	6	8	8	8	140	100	140	100
	160	8	12	6	4	130	100	110	100

TABLE NO. 17A																
ITEM NO.	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16
SPEED, MP/M	NA	200	200	200	200	200	200	200	NA	200	200	NA	200	200	NA	200
DR(1)	1.00	1.00	1.03	1.20	0.93	0.93	0.93	0.93	1.00	1.10	1.20	1.00	1.10	1.20	1.00	0.91
DR(2)	1.00	1.00	1.00	1.00	1.00	1.03	1.05	1.10	1.00	1.06	1.00	1.00	1.00	1.00	1.00	1.00
DR(1)xDR(2)	1.00	1.00	1.03	1.20	0.93	0.96	0.98	1.02	1.00	1.10	1.20	1.00	1.10	1.20	1.00	0.91
PLATE 1, °C	OFF	110	110	27	200	180	180	180	OFF	180	180	OFF	180	180	OFF	200
PLATE 2, °C	OFF	27	27	27	27	27	27	27	OFF	27	27	OFF	27	27	OFF	200
DENIER	70.0	68.9	67.9	59.5	73.6	75.4	72.0	69.7	35.0	63.3	63.6	35.0	32.2	29.8	35.0	75.5
EB, %	52.0	51.8	44.1	36.1	61.0	70.8	60.6	57.3	56.0	53.1	40.3	41.2	27.8	14.5	66.7	51.7
RDR	1.520	1.518	1.441	1.361	1.610	1.708	1.606	1.573	1.560	1.531	1.403	1.412	1.278	1.145	1.667	1.517
TEN, G/D	2.9	3.1	3.1	3.4	3.1	2.8	3.1	3.2	3.0	00	4.1	3.7	4.7	5.2	2.8	3.3
THK, G/DD	4.5	4.6	4.5	4.7	5.0	4.8	4.9	5.0	4.7	--	5.7	5.2	6.0	6.0	4.6	4.9
S, %	36.1	7.4	8.0	19.3	2.1	3.3	4.2	6.6	16.9	6.7	6.1	16.0	7.7	8.0	14.0	3.8
DHS, %	31.0	7.6	7.6	15.2	3.5	2.7	5.0	6.4	19.3	4.0	3.8	13.1	4.9	3.9	10.9	2.5
STmax, MG/D	32.0	32.0	32.0	32.0	32.0	32.0	32.0	32.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
T(STmax), C	153	187	278	392	76	64	124	257	210	402	467	250	590	647	286	60
INST, (G/D)/K	88	98	98	77	86	80	85	83	81	155	194	98	172	192	88	84
Ms, G/D	0.42	0.50	0.75	1.12	0.21	0.18	0.35	0.72	0.59	0.94	1.00	0.67	1.33	1.39	0.79	0.17
	0.5	2.5	3.5	2.0	3.6	1.9	3.0	3.9	1.2	10.0	12.3	1.6	7.7	8.1	2.0	1.6

TABLE NO.

TABLE 17B

ITEM NO.	1	2	3	4	5	6	7	9	10	11	12	13	14
SPEED, MPM	100	150	200	200	200	200	200	200	200	200	200	200	200
DR (1)	0.93	0.93	0.93	0.93	0.93	0.93	0.93	1.10	1.10	1.00	1.20	1.20	1.20
DR (2)	1.00	1.00	1.00	1.00	1.05	1.10	1.20	1.00	0.93	1.02	1.00	0.93	1.02
DR (1)xDR (2)	1.00	0.93	0.93	0.93	0.98	1.02	1.12	1.10	1.02	1.02	1.20	1.12	1.22
PLATE 1, °C	110	150	200	180	180	180	180	27	27	27	27	27	27
PLATE 2, °C	27	27	27	27	27	27	27	27	180	110	27	180	110
DENIER	71.4	72.0	73.3	72.1	70.9	68.5	63.3	63.6	64.4	61.5	58.6	61.1	56.5
EB, %	68.4	65.5	64.6	62.8	59.0	54.2	40.7	46.4	44.5	39.5	34.5	39.2	30.6
RDR	1.684	1.655	1.646	1.628	1.590	1.542	1.407	1.464	1.445	1.395	1.345	1.392	1.306
S, %	6.2	2.9	2.6	2.9	3.9	6.6	8.1	4.7	7.3	19.5	20.0	5.3	6.3
DHS, %	4.8	3.3	3.2	3.2	4.4	6.6	8.6	2.1	5.9	15.7	16.1	2.9	8.3
DHS-S, %	-1.4	0.4	0.6	0.3	0.5	0.0	0.5	-2.6	-1.4	-3.8	-3.9	-2.4	2.0
STmax, MG/D	73	76	75	68	142	282	385	365	50	413	340	102	621
NST, (G/D)/K	0.50	0.21	0.21	0.19	0.40	0.79	1.08	1.04	0.13	1.06	0.96	0.28	1.59
T (STmax), °C	77	84	82	82	82	82	84	77	100	118	80	96	118
Ms, G/D	1.2	2.6	2.9	2.3	3.6	4.3	4.8	7.8	0.7	2.1	1.7	1.9	9.9
Ps, G/D	0.5	0.2	0.2	0.2	0.6	1.9	3.1	1.7	0.4	8.1	6.8	0.5	3.9

TABLE 18

ITEM NO.	1	2	3
SPIN SPEED, MPM	4526	4526	4526
WIND-UP, MPM	4115	4115	4115
POLYMER TEMP., C	293	293	298
SPRT - A	68	68	34
SPRT - B	100	47	68
DENIER - A	75	50	35
DENIER - B	75	50	35
UNTREATED			
AVG. BOS, . %	<-----	4.5	----->
AVG. STmax, G/D	<-----	0.190	----->
AVG. Ps, (G/D)%	<-----	0.86	----->
AVG. Ms, G/D	<-----	4.2	----->
TREATED			
(245C, 80 PSI)			
AVG. BOS, %	19.0	17.0	17.0
AVG. STmax, G/D	0.30	0.30	0.31
AVG. Ps, (G/D)%	5.70	5.10	5.30
AVG. Ms, G/D	1.00	1.76	1.82
T(STmax), C	< 100	< 100	< 100
AVG. EB, %	77.0	77.9	70.1
AVG. TEN., G/D	3.17	3.33	3.15
AVG. WORK, G*CM	3650	3880	1603

TABLE 19A

	1	2	3	4
FEED YARN ID.	A	B	C	D
POLYMER	N66	N66	66	N6/66
POLYMER RV	50	50	65	65
SPIN SPEED, MPM	3909	3954	5300	5300
YARN DENIER	55	52	50.5	50
DPF	3.23	3.05	3.84	3.84
CROSS-SECTION	TRI	RND	RND	RND
E _b , %	85	78	73.5	76.1

TABLE 19B

	1	2	3	4	5	6
DRAW RATIO	1.316	1.316	1.447	1.447	1.608	1.608
HTR TEMP., °C	130	160	130	OFF	OFF	130
RELAX (T _r), °C	118	143	118	22	22	118
DENIER	43.8	43.7	40.0	40.2	36.1	35.8
E _b , %	53.1	51.9	39.8	43.6	30.5	22.8
MOD., GPD	15.2	16.2	17.9	29.2	23.9	47.0
S ₁ , %	6.1	6.2	7.4	6.6	7.3	7.6
DYE RATING	+	+	+	+	+	-

TABLE 19C

	1	2	3	4	5	6	7	8	9	10	11
DRAW RATIO	1.15	1.15	1.30	1.30	1.30	1.45	1.45	1.45	1.45	1.60	1.60
HTR TEMP., °C	160	OFF	160	130	OFF	160	130	100	OFF	160	OFF
RELAX (T _r), °C	143	22	143	118	22	118	118	94	22	143	22
DENIER	49	49.5	44	43.5	44.5	40	39	39.5	40	35.5	35.5
E _b , %	64	71	39	44	45	27	34	38.5	30	23	22
S ₁ , %	4.0	NA	6.6	5.9	7.0	7.3	6.2	6.7	8.3	6.9	6.6
DYE RATING	+	+	-	+	+	-	-	+	+	-	-

TABLE 19D

	1	2	3	4	5	6	7	8
DRAW RATIO	1.15	1.15	1.30	1.30	1.35	1.35	1.45	1.45
HTR TEMP., °C	160	OFF	160	OFF	160	OFF	160	OFF
RELAX (T _r), °C	143	22	143	22	143	22	143	22
DENIER	46	46.5	41.1	41.9	40	40.2	36.8	37.2
E _b , %	58.9	47	39.1	41.6	36	41.2	28.3	29.5
MOD., GPD	19	20.9	25.3	22.8	26	23.4	28.6	30.7
S ₁ , %	4.9	5.9	6.7	5.9	6.9	6.4	7.2	6.9
DYE RATING	+	+	+	+	-	+	+	+

TABLE 19E

	1	2	3	4	5	6	7
DRAW RATIO	1.15	1.30	1.30	1.30	1.45	1.45	1.45
HTR TEMP., °C	160	OFF	130	160	OFF	130	160
RELAX (T _r), °C	143	22	118	143	22	118	143
DENIER	44.7	40.5	39.5	39.8	36.5	35.6	35.4
E _b , %	60.3	49.8	41.7	43.2	36.4	33.2	30.5
MOD., GPD	18.4	21.8	21.8	23.5	21.3	29.2	26.6
S ₁ , %	5.9	6.9	7.5	7.6	8.1	8.6	8.3
DYE RATING	-	-	+/-	-	+	+	-

TABLE 20

ITEM NO.	SPIN MPM	PROCESS			T7%	T20%	PYM G/D	DDR x1000	RDDR x1000
		PSI	DEG. C	BOS %					
1	3750	OFF	120	52.0	1.23	1.56	4.27	106	169
2	4000	OFF	120	47.4	1.29	1.66	4.70	134	205
3	4500	OFF	120	23.9	1.56	2.20	5.80	163	207
4	5000	OFF	120	10.6	1.76	2.31	6.83	165	194
5	5500	OFF	120	15.7	2.36	3.06	8.81	144	174
6	6000	OFF	120	11.4	3.07	3.81	9.88	124	146
7	4000	OFF	150	9.2	2.75	3.64	10.95	75	87
8	4500	OFF	150	10.0	2.91	3.92	12.22	69	81
9	5000	OFF	150	9.8	3.33	4.44	13.60	68	79
10	4000	OFF	180	5.5	2.92	3.87	11.70	69	79
11	4500	OFF	180	6.1	3.06	3.91	10.90	76	87
12	5000	OFF	180	5.7	3.20	4.04	10.94	86	98
13*	3750	OFF	135	75.0	1.50	1.55	3.33	79	175
14*	3750	OFF	135	73.9	2.04	2.15	6.07	83	194
15*	3750	OFF	135	70.7	2.27	2.47	9.60	98	200
16*	4000	OFF	180	5.1	2.84	3.09	12.00	57	65
17*	4000	OFF	180	4.9	2.97	3.19	11.00	62	72
18*	4500	OFF	135	44.6	2.13	2.20	4.69	112	215
19*	4500	OFF	135	42.7	2.70	2.86	8.56	122	167
20*	4500	OFF	135	40.3	3.07	3.23	8.93	133	175
21*	5000	OFF	120	12.7	2.17	2.17	8.32	117	130
22*	5000	OFF	120	16.0	2.90	3.05	8.40	123	139
23*	5000	OFF	120	16.1	3.26	3.31	12.10	131	149
24	4700	OFF	245	3.5	0.89	0.99	7.30	96	165
25	4700	40	245	8.1	0.95	1.16	2.90	109	193
26	4700	60	245	19.5	0.96	1.17	2.90	126	239
27	4700	80	245	22.6	1.03	1.23	2.90	125	242
28	4700	100	245	54.9	1.19	1.56	2.90	126	320
29	4700	120	245	35.9	1.18	1.58	4.12	110	234
30	4700	140	245	24.1	1.24	1.68	5.10	104	203
31	4700	160	245	10.70	1.37	1.93	6.50	88	158

* = PYM BASED ON T10% AND T7%

FDY 1000 YPM 3.5X DRAW COMMERCIAL YARN	55
FDY 4750 MPM POY 1.2X DRAW RATIO PER 4,134,882	105
HOY SPUN AT 6400 MPM PER USP 4,134,882	130
FTT/HOY PER USP 4,134,882	110
FTT/POY 3000 MPM COMMERCIAL YARN PER USP 3,772,872	90
DRAW-RELAX-REDRAW FDY PER USP 4,134,882	115
DUY SPUN AT 4100 MPM PER USP 4,156,071	150
COMMERCIAL LOW SPEED SPUN/DRAWN STAPLE	55
UNDRAWN, CRIMPED HOY SPUN AT 6500 MPM PER USP 4,134,882	160

TABLE 21

Item No.	1	2	3	4	5	6	7	8
LRV	20.9	22.5	23.9	21.8	21.4	10.0	21.0	21.9
T _m [°] , C	258	249	239	243	250	243	---	---
E _B , %	74.2	75.8	79.0	111	115	115	116	101
S, %	4	5	6.7	7	5.7	6	6.7	3.7
Δn, x1000	97	74	68	48	66	66	51	65
DDR, x1000	117	109	214	200	210	210	---	---
RDDR, x1000	245	158	312	293	309	305	---	---

TABLE 22

Polymer	1A	1B	2	3	4	5
RV	43.9	43.9	---	42.5	48.1	42.7
	49.7	49.7	51.1	47.5	50.7	45
	55.8	55.8	---	57.4	61.3	51.9
	66.5	66.5	62.6	65.5	73.0	62.5
Eb, %	98.4	55.8	---	113.2	96.5	75.9
	101.	96.5	94.8	103	96.8	83.8
	61.1	49.7	---	92.4	73.2	95.3
	102.1	43.3	97.9	112.9	72.5	94.7
Modulus, g/d	9.9	12.2	---	15.7	10.6	12.1
	15.7	15.4	14.0	13.7	12.9	13.2
	15.4	12.7	---	13.8	16.1	11.0
	7.3	9.8	17.1	11.6	23.4	10.1

1A = 4000 mpm/66 w/ 0.075% TREN/5% MPMD

1B = 5000 mpm/66/w/ 0.075% TREN/5% MPMD

2 = 66 w/ 3% Isophthalate/2% MPMD

3 = 66 w/ 3% Isophthalate/2% MPMD/0.075% TREN

4 = 66 w/ 5% 6T

5 = 66 w/ 4.4% 612

TABLE 23

ITEM NO.	1	2	3	4
Tube, C	120	135	150	180
T _c , onset C	84.8	82.3	73.6	78.6
T _c , peak C	100.8	101.0	101.4	107.9
ΔH_C , J/g	5.87	11.2	10.2	11.3
T _m , onset C	249.3	258.5	250.5	248.6
T _m , peak C	262.5	262.2	256.5	260
ΔH_m , J/g	40.7	40.9	42.5	44.3
S, %	24	29	10	6.1
ST _{max} , mg/d	200	200	360	380
T(ST _{max}), C	77	73	150	177

WHAT IS CLAIMED IS:

1. A process for preparing spin-oriented polyester filaments (B), that are of high boil-off shrinkage (S) and high shrinkage power (P_S), involving
5 first melt-spinning a polyester polymer having a glass transition temperature (T_g) of 40 to 80 C and a zero-shear polymer melting point (T_M°) of 240 to 280 C at a withdrawal speed in the range of 2 to 6 Km/min, and quenching to a temperature below said temperature (T_g), to
10 form polyester filaments (A) of low shrinkage (S), characterized by treating said filaments (A) by rapidly heating to a treatment temperature above said temperature (T_g) and up to $[0.775(T_M^\circ + 273) - 273]$, and then immediately and rapidly cooling the filaments to below
15 said temperature (T_g), wherein said heating and cooling are carried out at rates sufficiently rapid to provide filaments (B) having:

i) a residual draw-ratio (RDR) of 1.4 to 1.9, a post yield modulus (M_{py}) of less than 12 g/dd, and high
20 shrinkage (S) such that the value of $(1-S/S_m)$ is between 0.25 and 0.9; where RDR is $(1+100/E_B, \%)$, E_B being the elongation-to-break, and S_m is $[(6.5-RDR)/6.5] \times 100\%$;

ii) a high maximum shrinkage tension (ST_{max}) of
25 0.1 g/d to 0.5 g/d at a peak shrinkage tension temperature $T(ST_{max})$ between $[0.65(T_M^\circ + 273) - 273]$ and $[0.725(T_M^\circ + 273) - 273]$; and

iii) a shrinkage modulus (M_S) of up to 5 g/d;
30 and high shrinkage power (P_S) of 1.5 to 12 (g/d)%;

and wherein said filaments (A) are characterized by:

iv) a residual draw-ratio (RDR) between 1.4 and
35 1.9 and low shrinkage (S) such that the value of $(1-S/S_m)$ is at least 0.9; and

v) a maximum shrinkage tension (ST_{max}) less than 0.15 g/d at a peak shrinkage tension temperature $T(ST_{max})$ less than $[0.70(T_M^\circ + 273) - 273]$.

5 2. A process according to Claim 1, characterized in that said filaments (A) are melt spun at said withdrawal speed and are immediately treated in a coupled process by said rapidly heating and cooling to provide said filaments (B) that are wound up at a speed
10 between about 2 and 6 km/min.

 3. A process according to Claim 1 or 2, characterized by melt-spinning said filaments (A) from a spinneret capillary orifice comprised of multiple segments
15 arranged in a configuration such as to form multiple melt streams which are withdrawn from the spinneret into a quench zone under conditions which cause self-coalescence of the multiple melt streams into a filament having an off-center longitudinal void of at least 10% by volume.
20

 4. A process according to any of the preceeding claims, characterized by passing said filaments (A) over a surface of sufficient friction to provide irregular, asymmetric filaments before they are rapidly
25 heated.

 5. A process according to any of the preceeding claims, characterized in that filaments (A), having an asymmetric cross-section with one side larger
30 than the other, are spun through a capillary of configuration selected to provide such asymmetric cross-section.

 6. A process according to any of the preceeding claims, characterized by drawing the resulting
35 filaments (B) at a temperature T_D between $[0.65(T_M^\circ + 273) - 273]$ and $[0.725(T_M^\circ + 273) - 273]$ to a drawn residual draw ratio $(RDR)_D$ between 1.2 and 1.4 under conditions selected to maintain $T(ST_{max})$ in the range

{ $0.65(T_M^0+273)-273$ } and { $0.725(T_M^0+273)-273$ }, shrinkage modulus (M_s) less than 5 g/d, and $(1-S/S_m)$ greater than 0.7; and to provide a maximum shrinkage tension (ST_{max}) of 0.3 to 0.7 g/d, shrinkage power (P_s) of 5 to 12 (g/d)% and
5 post-yield modulus (M_{py}) less than 12 g/dd.

7. A process according to any of the preceeding claims, characterized by draw-texturing said filaments (B) at a draw ratio selected so as to provide a
10 textured yarn of residual elongation E_B 15% to 45%.

8. A process according to any of the preceeding claims, characterized by spinning a bundle of filaments (A) and splitting said bundle into two smaller
15 filament bundles, treating one of said smaller filament bundles by said rapidly heating and cooling to provide said filaments (B), and later recombining into a single bundle so as to provide a mixed-shrinkage polyester filament yarn comprising filaments (A) and filaments (B).
20

9. A process according to any of Claims 1 to 7, characterized in that, before said filaments (A) are rapidly heated, they are mixed with filaments selected from the group consisting of thermally stable polyester
25 filaments (A') and polyamide filaments (C') to form a mixed-filament yarn that is treated by being rapidly heated and cooled to provide a mixed-shrinkage filament yarn comprising said filaments (B) and filaments selected from the group consisting of thermally stable polyester
30 filaments (A') and polyamide filaments (C').

10. A process according to any of Claims 1 to 7, characterized by splitting a melt stream of said polyester polymer into at least two, modifying the polymer
35 in one of the resulting split streams to change its ability to undergo stress-induced crystallization, spinning both the resulting modified polymer and the polyester polymer that has not been so modified to form filaments (A') from the modified polymer and of filaments

(A) from such unmodified polymer at a withdrawal speed in the range of 2 to 6 Km/min, and quenching to a temperature below said temperature (T_g), to form a bundle of said polyester filaments (A) of low shrinkage (S) and of
5 thermally stable polyester filaments (A') of low shrinkage (S) from the said modified polymer, heating said bundle to a treatment temperature above said temperature (T_g) and up to $[0.775 (T_M^\circ + 273) - 273]$, and then immediately and rapidly cooling to below said temperature (T_g), to provide
10 a mixed-shrinkage polyester filament yarn comprising filaments (A') and filaments (B), wherein said heating and cooling are carried out at rates sufficiently rapid to convert said filaments (A) into filaments (B) characterized by:

15 i) a residual draw-ratio (RDR) of 1.4 to 1.9, a post yield modulus (M_{py}) of less than 12 g/dd, and high shrinkage (S) such that the value of $(1 - S/S_m)$ is between 0.25 and 0.9; where RDR is $(1 + 100/E_B, \%)$, E_B being
20 the elongation-to-break, and S_m is $[(6.5 - RDR)/6.5] \times 100\%$;

ii) a high maximum shrinkage tension (ST_{max}) of 0.1 g/d to 0.5 g/d at a peak shrinkage tension temperature $T(ST_{max})$ between $[0.65(T_M^\circ + 273) - 273]$ and $[0.725(T_M^\circ + 273) - 273]$; and
25

iii) a shrinkage modulus (M_S) of up to 5 g/d; and high shrinkage power (P_S) 1.5 to 12 (g/d)%;

30 and wherein said filaments (A) and (A') are characterized by:

iv) a residual draw-ratio (RDR) between 1.4 and 1.9 and low shrinkage (S) such that the value of $(1 - S/S_m)$
35 is at least 0.90; and

v) a maximum shrinkage tension (ST_{max}) less than 0.15 g/d at a peak shrinkage tension temperature $T(ST_{max})$ less than $[0.70(T_M^\circ + 273) - 273]$.

11. A process according to any of Claims 8 to 10, characterized by heat-relaxing said mixed-shrinkage filament yarn to provide a mixed-filament bulky yarn.

5

12. A process according to Claim 11, characterized by air-jet texturing said mixed-shrinkage filament yarn and heat-relaxing during or after air-jet texturing to provide a textured yarn.

10

13. A process according to any of Claims 8-12, characterized by drawing the mixed-shrinkage filament yarn at a temperature T_D between $[0.65(T_M^\circ + 273) - 273]$ and $[0.725(T_M^\circ + 273) - 273]$ to a drawn residual draw ratio $(RDR)_D$ between 1.2 and 1.4 under conditions selected to maintain $T(ST_{max})$ in the range $\{0.65(T_M^\circ + 273) - 273\}$ to $\{0.725(T_M^\circ + 273) - 273\}$, shrinkage modulus (M_S) less than 5 g/d, and $(1 - S/S_m)$ greater than 0.7; and to provide a maximum shrinkage tension (ST_{max}) of 0.3 to 0.7 g/d, shrinkage power (P_S) of 5 to 12 (g/d)% and post-yield modulus (M_{py}) less than 12 g/dd.

14. A process according to any of Claims 8-13, characterized by draw-texturing said mixed-shrinkage filament yarn at a draw ratio selected so as to provide a textured yarn of residual elongation E_B of 15% to 45%.

15. A process for preparing thermally stable spin-oriented polyester filaments (A'), involving first melt-spinning a polyester polymer having a glass transition temperature (T_g) of 40 to 80 C and a zero-shear polymer melting point (T_M°) of 240 to 280 C at a withdrawal speed in the range of 2 to 6 Km/min, and quenching to a temperature below said temperature (T_g), to form polyester filaments (A) of low shrinkage (S), characterized by treating said filaments (A) by rapidly heating to a treatment temperature above said temperature (T_g) and up to $[0.775(T_M^\circ + 273) - 273]$, and then immediately and rapidly cooling the filaments to below

said temperature (T_g), wherein said heating and cooling are carried out at rates sufficiently rapid to provide filaments (A') having:

- 5 i) a residual draw-ratio (RDR) of 1.4 to 1.9, a post yield modulus (M_{py}) of less than 12 g/dd, and shrinkage (S) such that the value of $(1-S/S_m)$ is between 0.95 and 0.9; where RDR is $(1+100/E_B, \%)$, E_B being the elongation-to-break, and S_m is $[(6.5-RDR)/6.5] \times 100\%$;
- 10 ii) a high maximum shrinkage tension (ST_{max}) of 0.15 g/d to 0.5 g/d at a peak shrinkage tension temperature $T(ST_{max})$ between $[0.65(T_M^\circ + 273) - 273]$ and $[0.725(T_M^\circ + 273) - 273]$; and
- 15 iii) a shrinkage modulus (M_S) of 1.5 to 5 g/d; and high shrinkage power (P_S) of 1.5 to 5 (g/d)%;

and wherein said filaments (A) are characterized by:

- 20 iv) a residual draw-ratio (RDR) between 1.4 and 1.9 and low shrinkage (S) such that the value of $(1-S/S_m)$ is at least 0.9; and
- 25 v) a maximum shrinkage tension (ST_{max}) less than 0.15 g/d at a peak shrinkage tension temperature $T(ST_{max})$ less than $[0.70(T_M^\circ + 273) - 273]$.

30 16. A process according to Claim 15, characterized in that said filaments (A) are melt spun at said withdrawal speed and are immediately treated in a coupled process by said rapidly heating and cooling to provide said filaments (A') that are wound up at a speed between about 2 and 6 km/min.

35 17. A process for preparing spin-oriented polyester bicomponent filaments (A'B) from a polyester polymer having a glass transition temperature (T_g) of 40 to 80 C and a zero-shear polymer melting point (T_M°) of 240 to 280 C, characterized by splitting a melt stream of

said polyester polymer into at least two, modifying the polymer in one of the resulting split streams to change its ability to undergo stress-induced crystallization, recombining the split stream in an adjoining relationship
5 into a single melt stream, spinning the single melt stream into filaments at a withdrawal speed in the range of 2 to 6 Km/min, and quenching to a temperature below said temperature (T_g), to form polyester bicomponent filaments (A'A) of low shrinkage (S) followed by rapidly heating
10 said bicomponent filaments (A'A) to a treatment temperature above said temperature (T_g) and up to $[0.775(T_M^\circ + 273) - 273]$, and then immediately and rapidly cooling the filaments to below said temperature (T_g), wherein said heating and cooling are carried out at rates
15 sufficiently rapid to provide bicomponent filaments (A'B) characterized by:

i) a residual draw-ratio (RDR) of 1.4 to 1.9, and high shrinkage (S) such that the value of $(1 - S/S_m)$ is greater than 0.7, where RDR is $(1 + 100/E_B, \%)$, E_B being the
20 elongation-to-break, and S_m is $[(6.5 - RDR)/6.5] \times 100\%$;

ii) a high maximum shrinkage tension (ST_{max}) of 0.1 g/d to 0.5 g/d at a peak shrinkage tension temperature $T(ST_{max})$ between $[0.65(T_M^\circ + 273) - 273]$ and $[0.725(T_M^\circ +$
25 $273) - 273]$; and

iii) a shrinkage modulus (M_S) of up to 5 g/d; and high shrinkage power (P_S) of 1.5 to 12 (g/d)%;

30 and wherein said bicomponent filaments (A'A) are characterized by:

iv) a residual draw-ratio (RDR) between 1.4 and 1.9 and low shrinkage (S) such that the value of $(1 - S/S_m)$
35 is at least 0.9; and

v) a maximum shrinkage tension (ST_{max}) less than 0.15 g/d at a peak shrinkage tension temperature $T(ST_{max})$ less than $[0.70(T_M^\circ + 273) - 273]$.

18. A process for preparing spin-oriented polyester/polyamide bicomponent filaments (BC') that are of high boil-off shrinkage (S) and high shrinkage power (P_S), characterized by first melt-spinning bicomponent filaments (AC') of low shrinkage (S) from a polyester polymer having a glass transition temperature (T_g) of 40 to 80 C and a zero-shear polymer melting point (T_M°) of 240 to 280 C, and from a polyamide polymer, in an adjoining relationship, at a withdrawal speed in the range of 2 to 6 Km/min, and quenching said filaments (AC') to a temperature below said temperature (T_g), followed by treating said filaments (AC') by rapidly heating to a treatment temperature above said temperature (T_g) and up to $[0.775(T_M^\circ + 273) - 273]$, and then immediately and rapidly cooling the filaments to below said temperature (T_g), wherein said heating and cooling are carried out at rates sufficiently rapid to provide filaments (BC') having:

i) a residual draw-ratio (RDR) of 1.4 to 1.9, a post yield modulus (M_{py}) of less than 12 g/dd, and high shrinkage (S) such that the value of $(1 - S/S_m)$ is greater than 0.7, where RDR is $(1 + 100/E_B, \%)$, E_B being the elongation-to-break, and S_m is $[(6.5 - RDR)/6.5] \times 100\%$;

ii) a high maximum shrinkage tension (ST_{max}) of 0.1 g/d to 0.5 g/d at a peak shrinkage tension temperature $T(ST_{max})$ between $[0.65(T_M^\circ + 273) - 273]$ and $[0.75(T_M^\circ + 273) - 273]$; and

iii) a shrinkage modulus (M_S) of up to 5 g/d; and high shrinkage power (P_S) of 1.5 to 12 (g/d)%;

and wherein said filaments (AC') are characterized by:

iv) a residual draw-ratio (RDR) between 1.4 and 1.9 and low shrinkage (S) such that the value of $(1 - S/S_m)$ is at least 0.9; and

v) a maximum shrinkage tension ($ST_{\max}$) less than 0.15 g/d at a peak shrinkage tension temperature $T(ST_{\max})$ less than $[0.70(T_M^\circ + 273) - 273]$.

5 19. A process according to Claim 18, characterized by spinning said polymers into a symmetric sheath/core bicomponent filament relationship, with a sheath of nylon 66 polyamide and a core of poly(ethylene terephthalate) polyester, from melt at a polymer
10 temperature (T_p) that is 20 to 50 C above the melting point (T_M°), and wherein the polyester and polyamide polymers are selected to have similar melt flow viscosities of the same order of magnitude at the polymer temperature (T_p).

15 20. A process according to Claim 18 or 19 for preparing symmetric sheath/core, respectively polyamide/polyester, bicomponent spin-oriented filaments characterized by melt-spinning such biconstituent
20 filaments from a polyamide polymer and from a polyester polymer having a glass transition temperature (T_g) of 40 to 80 C, and a zero-shear polymer melting point (T_M°) of 240 to 280 C, in a symmetric sheath/core adjoining relationship, at a withdrawal speed in the range of 2 to 6
25 Km/min, and quenching said filaments to a temperature below said temperature (T_g), wherein the compositions of said polymers and the spinning and quenching conditions are so selected to provide both sheath and core elements having boil-off shrinkages that are approximately the same
30 and between 3 and 30%, and to provide filaments having:

i) a residual draw-ratio (RDR) of 1.4 to 1.9, an initial modulus (M_i) greater than 20 g/d, and shrinkage (S) such that the value of $(1 - S/S_m)$ is greater than 0.7,
35 where RDR is $(1 + 100/E_B, \%)$, E_B being the elongation-to-break;

ii) a high maximum shrinkage tension ($ST_{\max}$) of 0.1 g/d to 0.5 g/d at a peak shrinkage tension temperature

$T(ST_{\max})$ between $[0.65(T_M^\circ + 273) - 273]$ and $[0.75(T_M^\circ + 273) - 273]$; and

- iii) a shrinkage modulus (M_S) of up to 5 g/d;
5 and high shrinkage power (P_S) of 1.5 to 12 (g/d)%;

21. A process according to any of Claims 17 to 20, characterized by drawing the resulting bicomponent
10 filaments at a temperature T_D between $[0.65(T_M^\circ + 273) - 273]$ and $[0.725(T_M^\circ + 273) - 273]$ to a drawn residual draw ratio $(RDR)_D$ between 1.2 and 1.4 under conditions selected to maintain $T(ST_{\max})$ in the range $\{0.65(T_M^\circ + 273) - 273\}$ to $\{0.725(T_M^\circ + 273) - 273\}$, shrinkage modulus (M_S) less than 5
15 g/d, and $(1 - S/S_m)$ greater than 0.7; and to provide a maximum shrinkage tension ($ST_{\max}$) of 0.3 to 0.7 g/d, shrinkage power (P_S) of 5 to 12 (g/d)% and post-yield modulus (M_{py}) less than 12 g/dd.

20 22. Spin-oriented polyester filaments having:

i) a shrinkage (S), such that the value of $(1 - S/S_m)$ is between 0.25 and 0.9, where S_m is $[(6.5 - RDR/6.5) \times 100\%]$, an elongation-to-break (E_B) between
25 40% and 90%, a post yield modulus (M_{py}) of less than 12 g/dd, and a residual draw ratio (RDR) between 1.4 and 1.9, where RDR is $(1 + E_B/100)$;

ii) a maximum shrinkage tension ($ST_{\max}$) between
30 0.1 g/d and 0.7 g/d at a peak shrinkage tension temperature $T(ST_{\max})$ between $[0.65(T_M^\circ + 273) - 273]$ and $[0.725(T_M^\circ + 273) - 273]$, where T_M° is the zero-shear polymer melting point and is between 240 C and 280 C;

35 iii) a shrinkage power P_S of 1.5 to 12 (g/d)% and a shrinkage modulus M_S up to 5 g/d.

23. A mixed-shrinkage filament yarn, characterized by comprising high shrinkage filaments

according to Claim 22, and low shrinkage filaments that are selected from the group consisting of polyester filaments and polyamide filaments, and having:

- 5 i) a low boil off shrinkage (S), such that the value of $(1-S/S_m)$ is at least 0.9, where S_m is $\{(6.5-RDR)/6.5\} \times 100\%$, and where RDR is $(1+100/E_B, \%)$ and E_B is the elongation-to-break;
- 10 ii) a maximum shrinkage tension (ST_{max}) less than 0.15 g/g at a peak shrinkage tension temperature $T(ST_{max})$ between $[0.65(T_m^\circ)+273]-273$ and $[0.70(T_m^\circ)+273]-273$
- 15 iii) a shrinkage power P_S of less than 1.5 (g/d)% and a shrinkage modulus M_S up to 5 g/d.

24. Spin-oriented polyester bicomponent filaments having 2 polyester components, characterized by:

- 20 i) a residual draw-ratio (RDR) of 1.4 to 1.9, and shrinkage (S) such that the value of $(1-S/S_m)$ is greater than 0.7, where RDR is $(1+100/E_B, \%)$ and E_B is elongation-to-break;
- 25 ii) a high maximum shrinkage tension (ST_{max}) of 0.1 g/d to 0.5 g/d at a peak shrinkage tension temperature $T(ST_{max})$ between $[0.65(T_m^\circ)+273]-273$ and $[0.725(T_m^\circ)+273]-273$, wherein T_m° is the weighted average
- 30 value of the zero-shear melting point of the polyester polymers comprising the bicomponent filaments,

 iii) a shrinkage modulus (M_S) up to 5 g/d; and a shrinkage power (P_S) of at least 1.5 (g/d)%;

35

25. Spin-oriented bicomponent filaments having a polyester component and a polyamide component, characterized by:

i) a residual draw-ratio (RDR) of 1.4 to 1.9; and shrinkage (S) such that the value of $(1-S/S_m)$ is greater than 0.7, where RDR is $(1+100/E_B, \%)$, and E_B being the elongation-to-break, and S_m is $[(6.5-RDR)/6.5] \times 100\%$;

5


ii.) a high maximum shrinkage tension (ST_{max}) of 0.1 g/d to 0.5 g/d at a peak shrinkage tension temperature $T(ST_{max})$ between $[0.65(T_m^\circ)+273]-273$ and $[0.75(T_m^\circ)+273]-273$, where T_m° is the polymer zero-shear melting point of the polyester component.

10

iii) a shrinkage modulus (M_S) up to 5 g/d; and a shrinkage power (P_S) of at least 1.5 (g/d)%

1/20

FIG. 1



2/20




FIG. 2A




FIG. 2B






FIG. 3B



4/20

FIG. 4A



5/20

FIG. 4B




FIG. 5A






FIG. 5B



2/20

7/20



8/20

FIG. 7






FIG. 8




9/20

FIG. 9



10/20

FIG. 10



11/20

FIG. 11A





FIG. 11B



12/20

FIG. 12






FIG. 13



13/20

FIG. 14



14/20

FIG. 15





FIG. 16



15/20

FIG. 17





FIG. 18



16/20

FIG. 19





FIG. 20



17/20

FIG. 21






FIG. 22



18/20

FIG. 23



19/20

FIG.24A






FIG.24B



20/20

FIG. 25



INTERNATIONAL SEARCH REPORT

Intern. Appl. No.
PCT/US 94/13189

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 D01F6/62 D01D10/02 D01D5/08 D02G1/18 D02G1/00
D01D5/22 D01D5/24 D01F8/14 D01F8/12

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 D01F D01D D02G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
E	US,A,5 384 082 (FRANKFORT HANS R E ET AL) 24 January 1995 see the whole document ---	1-25
A	EP,A,0 013 101 (FIBER INDUSTRIES, INC.) 9 July 1980 see the whole document ---	1,2,8, 11,22,23
A	EP,A,0 207 489 (TEIJIN LTD) 7 January 1987 cited in the application see the whole document ---	1,2,8, 11,22,23
A	US,A,5 066 447 (KNOX BENJAMIN H ET AL) 19 November 1991 cited in the application ---	
A	WO,A,93 10292 (E.I. DU PONT DE NEMOURS AND COMPANY) 27 May 1993 ---	
-/--		

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

27 July 1995

Date of mailing of the international search report

3. 08. 95

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+ 31-70) 340-3016

Authorized officer

Tarrida Torrell, J

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 94/13189

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO,A,94 03660 (E.I. DU PONT DE NEMOURS AND COMPANY) 17 February 1994 ---	
A	US,A,2 999 296 (ALVIN L. BREEN ET AL.) 12 September 1961 see example IV ---	3
A	US,A,3 905 077 (FRANKFORT HANS R E ET AL) 16 September 1975 cited in the application see the whole document ---	4
A	US,A,3 219 739 (ALVIN L. BREEN ET AL.) 23 November 1965 see the whole document ---	5
A	US,A,3 454 460 (BOSLEY DAVID EMERSON) 8 July 1969 see the whole document ---	17,24
A	US,A,4 439 487 (JENNINGS UEL D) 27 March 1984 see the whole document ---	18,25
A	EP,A,0 311 386 (TORAY INDUSTRIES) 12 April 1989 see the whole document -----	19,20,25

INTERNATIONAL SEARCH REPORT

Information on patent family members

Inter. Application No

PCT/US 94/13189

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-5384082	24-01-95	US-A- 5364701	15-11-94
		US-A- 5229060	20-07-93
		US-A- 5261472	16-11-93
		US-A- 5066447	19-11-91
		US-A- 5288553	22-02-94
		US-A- 5250245	05-10-93
		US-A- 5223198	29-06-93
		US-A- 5244616	14-09-93
		US-A- 5223197	29-06-93
		US-A- 5356582	18-10-94
		US-A- 5417902	23-05-95
		US-A- 5145623	08-09-92
		US-A- 5407621	18-04-95
		AU-B- 653207	22-09-94
		AU-A- 1231092	27-08-92
		BR-A- 9205719	26-04-94
		EP-A- 0646189	05-04-95
		JP-T- 6507212	11-08-94
		WO-A- 9213119	06-08-92

EP-A-13101	09-07-80	US-A- 4246747	27-01-81
		CA-A- 1125488	15-06-82

EP-A-0207489	07-01-87	JP-A- 62191511	21-08-87

US-A-5066447	19-11-91	US-A- 5364701	15-11-94
		US-A- 5384082	24-01-95
		US-A- 5417902	23-05-95
		US-A- 5229060	20-07-93
		US-A- 5261472	16-11-93
		US-A- 5244616	14-09-93
		US-A- 5145623	08-09-92
		US-A- 5223197	29-06-93
		US-A- 5223198	29-06-93
		US-A- 5356582	18-10-94

WO-A-9310292	27-05-93	NONE	

WO-A-9403660	17-02-94	AU-B- 4790293	03-03-94
		CN-A- 1092483	21-09-94

INTERNATIONAL SEARCH REPORT

Information on patent family members

Intern. Application No

PCT/US 94/13189

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A-9403660		US-A- 5417902	23-05-95
		US-A- 5356582	18-10-94
US-A-2999296	12-09-61	NONE	
US-A-3905077	16-09-75	US-A- 3861133	21-01-75
US-A-3219739	23-11-65	NONE	
US-A-3454460	08-07-69	NONE	
US-A-4439487	27-03-84	CA-A- 1204568	20-05-86
		DE-A- 3345634	20-06-84
		FR-A, B 2538007	22-06-84
		GB-A, B 2132550	11-07-84
		JP-A- 59116417	05-07-84
EP-A-0311386	12-04-89	JP-A- 2074612	14-03-90
		JP-A- 1097212	14-04-89
		JP-A- 1097230	14-04-89
		AU-B- 606462	07-02-91
		CA-A- 1314673	23-03-93
		DE-D- 3889282	01-06-94
		DE-T- 3889282	11-08-94
		US-A- 4987030	22-01-91