




(86) Date de dépôt PCT/PCT Filing Date: 2013/10/01
(87) Date publication PCT/PCT Publication Date: 2014/04/10
(45) Date de délivrance/Issue Date: 2017/12/05
(85) Entrée phase nationale/National Entry: 2014/11/13
(86) N° demande PCT/PCT Application No.: JP 2013/076665
(87) N° publication PCT/PCT Publication No.: 2014/054619
(30) Priorité/Priority: 2012/10/02 (JP2012-220250)

(51) Cl.Int./Int.Cl. *C01B 3/58* (2006.01),
B01D 53/22 (2006.01), *B01D 67/00* (2006.01),
B01D 69/00 (2006.01), *C01B 3/56* (2006.01)

(72) Inventeurs/Inventors:
OKADA, OSAMU, JP;
HANAI, NOBUAKI, JP;
YAN, PENG, JP;
MIYATA, JUNYA, JP;
KIYOHARA, YASATO, JP;
ISHII, SAYAKA, JP;
NAGANO, MEGUMI, JP

(73) Propriétaire/Owner:

(54) Titre : MEMBRANE DE TRANSPORT DE CO₂ SIMPLIFIEE ET SON PROCEDE DE FABRICATION, ET PROCEDE
ET APPAREIL PERMETTANT DE SEPARER LE CO₂
(54) Title: FACILITATED CO₂ TRANSPORT MEMBRANE AND METHOD FOR PRODUCING SAME, AND METHOD AND
APPARATUS FOR SEPARATING CO₂



(57) Abrégé/Abstract:

Provided is a facilitated CO₂ transport membrane having improved CO₂ permeance and CO₂/H₂ selectivity. The facilitated CO₂ transport membrane is equipped with a separation-functional membrane that comprises a hydrophilic polymer gel membrane and a CO₂ carrier and a CO₂ hydration reaction catalyst both contained in the hydrophilic polymer gel membrane. More preferably, the CO₂ hydration reaction catalyst has at least a catalytic activity at a temperature equal to or higher than 100°C, or has a melting point of 200°C or higher, or is soluble in water.



(73) **Propriétaires(suite)/Owners(continued):**RENAISSANCE ENERGY RESEARCH CORPORATION, JP

(74) **Agent:** GOWLING WLG (CANADA) LLP

PCAC0052A7-SPE3.doc

ABSTRACT

Provided is a facilitated CO₂ transport membrane having an improved CO₂ permeance and an improved CO₂/H₂ selectivity. The facilitated CO₂ transport membrane includes a separation-functional membrane that includes a hydrophilic polymer gel membrane containing a CO₂ carrier and a CO₂ hydration catalyst. Further preferably, the CO₂ hydration catalyst at least has catalytic activity at a temperature of 100°C or higher, has a melting point of 200°C or higher, or is soluble in water.

PCAC0052A7-SPE3.doc

FACILITATED CO₂ TRANSPORT MEMBRANE AND METHOD FOR
PRODUCING SAME, AND METHOD AND APPARATUS FOR
SEPARATING CO₂

TECHNICAL FIELD

[0001]

The present invention relates to a facilitated CO₂ transport membrane that is used for separating carbon dioxide (CO₂), particularly to a facilitated CO₂ transport membrane that separates carbon dioxide produced as a by-product in a hydrogen production process or the like at a high selection ratio to hydrogen. The present invention further relates to a method for producing the facilitated CO₂ transport membrane, and a method and an apparatus for separating CO₂ using the facilitated CO₂ transport membrane.

BACKGROUND ART

[0002]

In a hydrogen production process, it is necessary that CO₂ produced as a by-product in the course of producing hydrogen be separated and removed from a hydrogen gas.

[0003]

A chemical absorption method that is used in a decarbonation processes in existing large-scale plants such as hydrogen production plants and ammonia production plants requires a huge CO₂ absorption tower and a huge regeneration tower for a CO₂ absorbing liquid in order to separate

PCAC0052A7-SPE3.doc

CO₂, and in a regeneration step for the CO₂ absorbing liquid, requires a large amount of steam for heating the CO₂ absorbing liquid to remove CO₂ therefrom so that the liquid absorbing CO₂ can be reused, and therefore energy is wastefully consumed.

[0004]

In recent years, as a countermeasure for global warming, natural energy that does not emit CO₂ has been expected to come into wide use, but natural energy has a significant problem in terms of cost. Thus, attention has been paid to a method called CCS (Carbon dioxide Capture and Storage) in which CO₂ is separated and collected from waste gases from thermal power plants, ironworks and the like, and buried in the ground or sea. Currently, even CCS is based on application of the chemical absorption method. In this case, for separating and collecting CO₂ from thermal power plants, not only large-scale CO₂ separation equipment is required, but also a large amount of steam should be fed.

[0005]

On the other hand, a CO₂ separation and collection process using a membrane separation method is intended to separate a gas by means of a difference in velocity of gases passing through a membrane using a partial pressure difference as driving energy, and is expected as an energy-saving process because the pressure of a gas to be separated can be utilized as energy and no phase change is involved.

[0006]

Gas separation membranes are broadly classified into organic membranes and inorganic membranes in terms of a difference in membrane

PCAC0052A7-SPE3.doc

material. The organic membrane has the advantage of being inexpensive and excellent in moldability as compared to the inorganic membrane. The organic membrane that is used for gas separation is generally a polymer membrane prepared by a phase inversion method, and the mechanism of separation is based on a solution-diffusion mechanism in which a gas is separated by means of a difference in solubility of the gas in the membrane material and diffusion rate of the gas in the membrane.

[0007]

The solution-diffusion mechanism is based on the concept that a gas is first dissolved in the membrane surface of a polymer membrane, and the dissolved molecules diffuse between polymer chains in the polymer membrane. Where for a gas component A, the permeability coefficient is P_A , the solubility coefficient is S_A , and the diffusion coefficient is D_A , the relational expression: $P_A = S_A \times D_A$ holds. The ideal separation factor $\alpha_{A/B}$ is expressed as $\alpha_{A/B} = P_A/P_B$ by taking the ratio of permeability coefficients between components A and B, and therefore $\alpha_{A/B} = (S_A/S_B) \times (D_A/D_B)$ holds. Here, S_A/S_B is referred to as solubility selectivity, and D_A/D_B is referred to as diffusivity selectivity.

[0008]

Since the diffusion coefficient increases as the molecular diameter decreases, and the contribution of diffusivity selectivity is generally greater than that of solubility selectivity in gas separation, it is difficult to allow selective passage of gases having a larger molecular diameter by suppressing passage of gases having a smaller molecular diameter among multi-component gases having different molecular diameters.

PCAC0052A7-SPE3.doc

[0009]

Therefore, it is extremely difficult to prepare a CO₂ selective permeable membrane that separates, particularly from a mixed gas containing H₂ and CO₂, CO₂ with high selectivity to H₂ having the smallest molecular diameter among gas molecules. It is still more difficult to prepare a CO₂ selective permeable membrane that is capable of being put to practical use in a decarbonation process in a hydrogen production plant or the like and that functions at a high temperature of 100°C or higher.

[0010]

Thus, studies are conducted on a permeable membrane called a facilitated transport membrane that allows selective permeation of a gas by a facilitated transport mechanism, in addition to a solution-diffusion mechanism, using a substance called a “carrier” which selectively and reversibly reacts with CO₂ (see, for example, Patent Document 1 below). The facilitated transport mechanism has a structure in which a membrane contains a carrier which selectively reacts with CO₂. In the facilitated transport membrane, CO₂ passes not only physically by the solution-diffusion mechanism but also as a reaction product with the carrier, so that the permeation rate is accelerated. On the other hand, gases such as N₂ and H₂, which do not react with the carrier, pass only by the solution-diffusion mechanism, and therefore the separation factor of CO₂ with respect to these gases is extremely high. Energy generated during the reaction of CO₂ with the carrier is utilized as energy for releasing CO₂ by the carrier, and therefore there is no need to supply energy from outside, so that an essentially energy-saving process is provided.

PCAC0052A7-SPE3.doc

PRIOR ART DOCUMENT

PATENT DOCUMENT

[0011]

Patent Document 1: International Publication No. WO 2009/093666

SUMMARY OF THE INVENTION

PROBLEMS TO BE SOLVED BY THE INVENTION

[0012]

Patent Document 1 proposes a facilitated CO₂ transport membrane having a CO₂ permeance and a CO₂/H₂ selectivity feasible at a high temperature condition of 100°C or higher by using as a carrier a specific alkali metal salt such as cesium carbonate or rubidium carbonate.

[0013]

The facilitated CO₂ transport membrane has a higher CO₂ permeation rate as compared to a membrane based on a solution-diffusion mechanism, but the number of carrier molecules that react with CO₂ molecules becomes less sufficient as the partial pressure of CO₂ increases, and therefore improvement is required for accommodating the membrane to carrier saturation even at such a high CO₂ partial pressure.

[0014]

Further, there are expectations for provision of a facilitated CO₂ transport membrane that is applicable at a high temperature of 100°C or higher and has an improved CO₂ permeance and an improved CO₂/H₂ selectivity in a decarbonation step in a hydrogen production process or the

PCAC0052A7-SPE3.doc

like.

[0015]

In view of the above-mentioned problems, it is an object of the present invention to stably supply a facilitated CO₂ transport membrane having an improved CO₂ permeance and an improved CO₂/H₂ selectivity.

MEANS FOR SOLVING THE PROBLEMS

[0016]

For achieving the above-mentioned object, the present invention provides a facilitated CO₂ transport membrane comprising a separation-functional membrane that includes a hydrophilic polymer gel membrane containing a CO₂ carrier and a CO₂ hydration catalyst. It is to be noted that the CO₂ hydration catalyst is a catalyst that increases the reaction rate of the CO₂ hydration reaction shown in the following (Chemical Formula 1). The symbol “ $\rightleftharpoons$ ” in the reaction formulae shown herein indicates that the reaction is a reversible reaction.

[0017]

(Chemical Formula 1)



[0018]

The reaction of CO₂ with the CO₂ carrier is expressed by the following (Chemical Formula 2) as an overall reaction formula. It is to be noted that the (Chemical Formula 2) is based on the assumption that the CO₂ carrier is a carbonate. The CO₂ hydration reaction, one of elementary reactions of the above-mentioned reaction, is an extremely slow reaction

PCAC0052A7-SPE3.doc

under a catalyst-free condition, and addition of a catalyst accelerates the elementary reaction, so that the reaction of CO₂ with the CO₂ carrier is accelerated, and as a result, improvement of the permeation rate of CO₂ is expected.

[0019]

(Chemical Formula 2)



[0020]

Thus, since the facilitated CO₂ transport membrane having the above-mentioned features contains a CO₂ carrier and a CO₂ hydration catalyst in a separation-functional membrane, the reaction of CO₂ with the CO₂ carrier is accelerated, so that a facilitated CO₂ transport membrane having an improved CO₂ permeance and an improved CO₂/H₂ selectivity can be provided. Further, since the CO₂ hydration catalyst effectively functions even at a high CO₂ partial pressure, the CO₂ permeance and CO₂/H₂ selectivity at a high CO₂ partial pressure are each improved. Further, since the separation-functional membrane is composed of a gel membrane rather than a liquid membrane or the like, high selective permeability to hydrogen can be stably exhibited even under pressure.

[0021]

Further, in the facilitated CO₂ transport membrane having the above-mentioned features, the CO₂ hydration catalyst preferably has catalytic activity at a temperature of 100°C or higher. The reaction of CO₂ with the CO₂ carrier is thereby accelerated at a temperature of 100°C or higher, so that a facilitated CO₂ transport membrane having an improved

PCAC0052A7-SPE3.doc

CO₂ permeance and an improved CO₂/H₂ selectivity can be provided under such a temperature condition.

[0022]

Further, in the facilitated CO₂ transport membrane having the above-mentioned features, the CO₂ hydration catalyst preferably has a melting point of 200°C or higher, and is preferably soluble in water.

[0023]

Further, in the facilitated CO₂ transport membrane having the above-mentioned features, the CO₂ hydration catalyst preferably contains an oxo acid compound, particularly preferably an oxo acid compound of at least one element selected from group 6 elements, group 14 elements, group 15 elements and group 16 elements.

[0024]

Further, in the facilitated CO₂ transport membrane having the above-mentioned features, the CO₂ hydration catalyst preferably contains at least one of a tellurous acid compound, a selenious acid compound, an arsenious acid compound, an orthosilicic acid compound and a molybdic acid compound.

[0025]

Particularly, when the melting point of the CO₂ hydration catalyst is 200°C or higher, the catalyst can exist in the separation-functional membrane while being thermally stable, so that performance of the facilitated CO₂ transport membrane can be maintained over a long period of time. Further, when the CO₂ hydration catalyst is soluble in water, a hydrophilic polymer gel membrane containing a CO₂ hydration catalyst can

PCAC0052A7-SPE3.doc

be easily and stably prepared. When a tellurous acid compound, a selenious acid compound, an arsenious acid compound, an orthosilicic acid compound or a molybdic acid compound is used as the CO₂ hydration catalyst, stable improvement of membrane performance can be expected because all of these compounds are water soluble and have a melting point of 200°C or higher.

[0026]

Further, in the facilitated CO₂ transport membrane having the above-mentioned features, the gel membrane is preferably a hydrogel, further preferably a polyvinyl alcohol-polyacrylic acid (PVA/PAA) salt copolymer gel membrane.

[0027]

The hydrogel is a three-dimensional network structure formed by crosslinking a hydrophilic polymer, and has a nature of being swollen when absorbing water. Here, a person skilled in the art may call the polyvinyl alcohol-polyacrylic acid salt copolymer occasionally a polyvinyl alcohol-polyacrylic acid copolymer.

[0028]

Even when the amount of water in the membrane is small, carbon dioxide is facilitatively transported, but its permeation rate is generally low, and therefore a large amount of water should be held in the membrane for achieving a high permeation rate. Further, when the gel membrane as a separation-functional membrane is composed of a hydrogel having a high water-holding capacity in the facilitated CO₂ transport membrane having the above-mentioned features, a maximum possible amount of water can be held in the membrane even at a high temperature that causes a reduction in

PCAC0052A7-SPE3.doc

the amount of water in the separation-functional membrane, so that high selective permeability of CO₂ to hydrogen can be achieved at a high temperature of 100°C or higher.

[0029]

Further, in the facilitated CO₂ transport membrane having the above-mentioned features, the CO₂ carrier preferably contains at least one of a carbonate of an alkali metal, a bicarbonate of an alkali metal and a hydroxide of an alkali metal, and further the alkali metal is preferably cesium or rubidium. High selective permeability of CO₂ to hydrogen can be thereby achieved more reliably at a high temperature of 100°C or higher.

[0030]

Here, a reaction expressed by the above (Chemical Formula 2) occurs when the CO₂ carrier is a carbonate of an alkali metal, while a reaction expressed by the following (Chemical Formula 3) occurs when the CO₂ carrier is a hydroxide of an alkali metal. The (Chemical Formula 3) shows a case where the alkali metal is cesium as an example.

[0031]

(Chemical Formula 3)



[0032]


The reactions in the above (Chemical Formula 3) can be united into a reaction expressed by the (Chemical Formula 4). That is, this shows that added cesium hydroxide is converted into cesium carbonate. Further, it is apparent from the above (Chemical Formula 3) that a similar effect can be

PCAC0052A7-SPE3.doc

obtained when as a CO₂ carrier, a bicarbonate is added in place of a carbonate of an alkali metal.

[0033]

(Chemical Formula 4)



[0034]

Further, in the facilitated CO₂ transport membrane having the above-mentioned features, the separation-functional membrane is preferably supported on a hydrophilic porous membrane.

[0035]

First, when the separation-functional membrane is supported on a porous membrane, the strength of the facilitated CO₂ transport membrane at the time of use is improved. As a result, in the case where the facilitated CO₂ transport membrane is applied to a CO₂ permeable membrane reactor (shift converter including a facilitated CO₂ transport membrane), a sufficient membrane strength can be secured even when a pressure difference between both sides (inside and outside of a reactor) of the facilitated CO₂ transport membrane is large (e.g. 2 atm or larger).

[0036]

Further, when the porous membrane supporting a separation-functional membrane as a gel membrane is hydrophilic, a gel membrane having reduced defects can be stably prepared, so that high selective permeability to hydrogen can be maintained. In general, when the porous membrane is hydrophobic, it is supposed that penetration of water contained in the gel membrane into the pores of the porous membrane and

PCAC0052A7-SPE3.doc

the resulting reduction of membrane performance can be prevented at 100°C or lower, and a similar effect may be expected at 100°C or higher where the amount of water in the gel membrane is small. Therefore, use of a hydrophobic porous membrane is recommended. However, in the case of the facilitated CO₂ transport membrane having the above-mentioned features, high selective permeability to hydrogen can be maintained with reduced defects by using a hydrophilic porous membrane for the following reason.

[0037]

When a cast solution including an aqueous solution containing a hydrophilic polymer such as a PVA/PAA salt copolymer and a CO₂ carrier is cast on a hydrophilic porous membrane, pores of the porous membrane are filled with the solution, and a surface of the porous membrane is coated with the cast solution. When a separation-functional membrane is prepared by gelling the cast solution, not only a surface but also pores of the porous membrane are filled with the gel membrane, and therefore defects are hard to occur, leading to an increase in gel membrane production success rate.

[0038]

When considering the ratio of pore portions (porosity) and the situation in which the pore does not extend straight perpendicularly to the membrane surface but bends many times (bending rate), the gel membrane in pores provides a great resistance to gas permeation, leading to a reduction in gas permeance due to low permeability as compared to the gel membrane on the surface of the porous membrane. On the other hand, when a cast solution is cast on a hydrophobic porous membrane, pores of the

PCAC0052A7-SPE3.doc

porous membrane are not filled with the solution but only a surface of the porous membrane is coated with the cast solution, so that pores are filled with a gas, and therefore gas permeance in the gel layer on the hydrophobic porous membrane is considered to be higher for both H₂ and CO₂ as compared to a hydrophilic porous membrane.

[0039]

However, minute defects easily occur in the gel membrane on the membrane surface as compared to the gel membrane in pores, leading to a reduction in membrane production success rate. H₂ is much smaller in molecular size than CO₂, and therefore at a minute defect part, the permeance of H₂ is remarkably larger than that of CO₂. At a part other than the defect part, the permeance of CO₂ passing by the facilitated transport mechanism is considerably larger than the permeance of H₂ passing by the physical solution-diffusion mechanism.

[0040]

As a result, when a hydrophobic porous membrane is used, selectivity to hydrogen (CO₂/H₂) is reduced as compared to when a hydrophilic porous membrane is used. Therefore, stability and durability of the facilitated CO₂ transport membrane are very important from the viewpoint of practical use, and it is more advantageous to use a hydrophilic porous membrane having high selectivity to hydrogen (CO₂/H₂).

[0041]

Further, the separation-functional membrane supported on the hydrophilic porous membrane is preferably covered with a hydrophobic porous membrane. The separation-functional membrane is thereby

PCAC0052A7-SPE3.doc

protected by the hydrophobic porous membrane, leading to a further increase in strength of the facilitated CO₂ transport membrane at the time of use. The separation-functional membrane is covered with the hydrophobic porous membrane, and therefore even when steam is condensed on the membrane surface of the hydrophobic porous membrane, water is repelled and thereby prevented from penetrating the separation-functional membrane because the porous membrane is hydrophobic. Accordingly, the hydrophobic porous membrane can prevent a situation in which the CO₂ carrier in the separation-functional membrane is diluted with water, and the diluted CO₂ carrier flows out of the separation-functional membrane.

[0042]

A cause which hinders downsizing and reduction of the startup time in conventional shift converters is that a large amount of a shift catalyst is required due to the restriction from chemical equilibrium of the CO shift reaction expressed by the following (Chemical Formula 5). As an example, a reforming system for a 50 kW PAFC (phosphoric acid fuel cell) requires 20 L of a reforming catalyst, whereas the shift catalyst is required in an amount of 77 L, about 4 times the amount of the reforming catalyst. This is a major factor of hindering downsizing and reduction of the startup time in the shift converter.

[0043]

(Chemical Formula 5)



[0044]

PCAC0052A7-SPE3.doc

Thus, when the facilitated CO₂ transport membrane having the above-mentioned features is applied to a CO₂ permeable membrane reactor, carbon dioxide on the right side, which is produced through the CO shift reaction of the above (Chemical Formula 5), is efficiently removed to outside the shift converter, so that chemical equilibrium can be shifted to the hydrogen production side (right side) to obtain a high conversion rate at the same reaction temperature, and resultantly carbon monoxide and carbon dioxide can be removed beyond the limit imposed by equilibrium restriction. As a result, downsizing, reduction of the startup time and velocity enhancement (SV enhancement) in the shift converter can be achieved.

[0045]

Further, the present invention provides a method for producing the facilitated CO₂ transport membrane having the above-mentioned features, the method comprising the steps of: preparing a cast solution including an aqueous solution containing the hydrophilic polymer, the CO₂ carrier and the CO₂ hydration catalyst that is soluble in water; and casting the cast solution on a hydrophilic porous membrane and then gelling the cast solution to prepare the separation-functional membrane.

[0046]

According to the method for producing the facilitated CO₂ transport membrane having the above-mentioned features, since a cast solution is prepared beforehand in which the relative amounts of the CO₂ carrier and the water-soluble CO₂ hydration catalyst to the hydrophilic polymer is properly adjusted, proper adjustment of the blending ratio of the CO₂ carrier and the CO₂ hydration catalyst in the final gel membrane can be easily and

PCAC0052A7-SPE3.doc

conveniently achieved, so that performance of the membrane can be enhanced.

[0047]

Further, the present invention provides a method for separating CO₂ using the facilitated CO₂ transport membrane having the above-mentioned features, with the CO₂ hydration catalyst having catalytic activity at a temperature of 100°C or higher, wherein a mixed gas containing CO₂ and H₂ and having a temperature of 100°C or higher is supplied to the facilitated CO₂ transport membrane, and the CO₂ passing through the facilitated CO₂ transport membrane is separated from the mixed gas.

[0048]

Further, the present invention provides a CO₂ separation apparatus comprising the facilitated CO₂ transport membrane having the above-mentioned features, with the CO₂ hydration catalyst having catalytic activity at a temperature of 100°C or higher, wherein a mixed gas containing CO₂ and H₂ and having a temperature of 100°C or higher is supplied to the facilitated CO₂ transport membrane, and the CO₂ passing through the facilitated CO₂ transport membrane is separated from the mixed gas.

EFFECTS OF THE INVENTION

[0049]

According to the facilitated CO₂ transport membrane having the above-mentioned features and the method for producing the same, a facilitated CO₂ transport membrane having an improved CO₂ permeance

PCAC0052A7-SPE3.doc

and an improved CO₂/H₂ selectivity can be stably supplied. Particularly, the CO₂ hydration catalyst has catalytic activity at a temperature of 100°C or higher, so that a facilitated CO₂ transport membrane that is applicable at a high temperature of 100°C or higher and capable of achieving high selective permeability to hydrogen can be stably supplied in a decarbonation step in a hydrogen production process or the like.

[0050]

Further, according to the CO₂ separation method and apparatus having the above-mentioned features, a facilitated CO₂ transport membrane having high selective permeability to hydrogen at a high temperature of 100°C or higher is used, so that CO₂ can be selectively separated with high efficiency from a mixed gas containing CO₂ and H₂ and having a temperature of 100°C or higher.

BRIEF DESCRIPTION OF THE DRAWINGS

[0051]

Fig. 1 is a sectional view schematically showing a structure in one embodiment of a facilitated CO₂ transport membrane according to the present invention.

Fig. 2 is a flow chart showing a method for producing a facilitated CO₂ transport membrane according to the present invention.

Fig. 3 is a table showing a list of constitutional conditions and membrane performance for separation-functional membranes of Examples 1 to 7 and Comparative Examples 1 and 2 used in experiments for evaluation of membrane performance of a facilitated CO₂ transport membrane

PCAC0052A7-SPE3.doc

according to the present invention.

Fig. 4 is a graph showing a CO₂ permeance and a CO₂/H₂ selectivity in Examples 1 to 5 and Comparative Example 1 shown in Fig. 3.

Fig. 5 is a graph showing a CO₂ permeance and a CO₂/H₂ selectivity in Examples 1 and 6 and Comparative Examples 1 and 2 shown in Fig. 3.

Fig. 6 is a graph showing a CO₂ permeance and a CO₂/H₂ selectivity in Examples 1 and 7 and Comparative Example 1 shown in Fig. 3.

Fig. 7 is a table showing a list of constitutional conditions and membrane performance for separation-functional membranes of Examples 2, and 8 to 10 and Comparative Examples 1, 4 and 5 used in experiments for evaluation of membrane performance of a facilitated CO₂ transport membrane according to the present invention.

Fig. 8 is a graph showing a CO₂ permeance and a CO₂/H₂ selectivity in Examples 2 and 8 and Comparative Examples 1 and 4 shown in Fig. 7.

Figs. 9A and 9B are configuration diagrams each schematically showing an outlined configuration in one embodiment of a CO₂ separation apparatus according to the present invention.

DESCRIPTION OF EMBODIMENTS

[0052]

By extensively conducting studies, the inventors of the present application have found that when a gel membrane of a facilitated CO₂ transport membrane, which contains a CO₂ carrier and in which a reaction of CO₂ with the CO₂ carrier as expressed by the above (Chemical Formula 2) occurs, contains a catalyst for a CO₂ hydration reaction as expressed by the

PCAC0052A7-SPE3.doc

above (Chemical Formula 1), one of elementary reactions of the above-mentioned reaction, the catalyst being capable of maintaining catalytic activity without being deactivated at a high temperature of 100°C or higher, the CO₂ permeance is dramatically improved with respect to the H₂ permeance even at such a high temperature, and the CO₂/H₂ selectivity is considerably improved as compared to a conventional facilitated CO₂ transport membrane that does not contain the catalyst. Based on the above-mentioned new finding, the inventors of the present application have completed the invention of a facilitated CO₂ transport membrane and a method for producing the same, and a method and an apparatus for separating CO₂ as shown below.

[0053]

[First Embodiment]

First, one embodiment of a facilitated CO₂ transport membrane and a method for producing the same according to the present invention (hereinafter, referred to as “the present facilitated transport membrane” and “the present production method” as appropriate) will be described with reference to the drawings.

[0054]

The present facilitated transport membrane is a facilitated CO₂ transport membrane including a separation-functional membrane that includes a water-containing hydrophilic polymer gel membrane containing a CO₂ carrier and a CO₂ hydration catalyst having catalytic activity at a temperature of 100°C or higher, the facilitated CO₂ transport membrane serving at a temperature of 100°C or higher and having a high CO₂

PCAC0052A7-SPE3.doc

permeance and a high CO₂/H₂ selectivity, and the facilitated CO₂ transport membrane being applicable to a CO₂ permeable membrane reactor or the like. Further, for stably achieving a high CO₂/H₂ selectivity, the present facilitated transport membrane includes a hydrophilic porous membrane as a support membrane that supports a gel membrane containing a CO₂ carrier and a CO₂ hydration catalyst.

[0055]

Specifically, the present facilitated transport membrane includes a polyvinyl alcohol-polyacrylic acid (PVA/PAA) salt copolymer as a membrane material of the separation-functional membrane, a carbonate of an alkali metal such as cesium carbonate (Cs₂CO₃) or rubidium carbonate (Rb₂CO₃) as the CO₂ carrier, and an oxo acid compound as the CO₂ hydration catalyst. More specifically, for the CO₂ hydration catalyst, an oxo acid compound of at least one element selected from group 6 elements, group 14 elements, group 15 elements and group 16 elements is used, and particularly preferably a tellurous acid compound, a selenious acid compound, an arsenious acid compound, an orthosilicic acid compound or a molybdic acid compound is used. All of CO₂ hydration catalysts used in this embodiment are soluble in water, and extremely thermally stable with a melting point of 400°C or higher, and have catalytic activity at a high temperature of 100°C or higher. The melting point of the CO₂ hydration catalyst is only required to be higher than the upper limit of temperature variations in steps in a method for producing the present facilitated transport membrane as described later (e.g. the temperature in the drying step or thermal crosslinking temperature). When the melting point is, for example, about 200°C or

PCAC0052A7-SPE3.doc

higher, a situation is avoided in which the CO₂ hydration catalyst is sublimed in the course of the production process, leading to a reduction in concentration of the CO₂ hydration catalyst in the separation-functional membrane.

[0056]

As an example, the present facilitated transport membrane is configured as a three-layer structure in which a hydrophilic porous membrane 2 supporting a separation-functional membrane 1 is held between two hydrophobic porous membranes 3 and 4 as schematically shown in Fig. 1. The separation-functional membrane 1 as a gel membrane is supported on the hydrophilic porous membrane 2 and has a certain level of mechanical strength, and therefore is not necessarily required to be held between the two hydrophobic porous membranes 3 and 4. The mechanical strength can also be increased by, for example, forming the hydrophilic porous membrane 2 in a cylindrical shape. Therefore, the present facilitated transport membrane is not necessarily a flat plate-shaped one.

[0057]

The separation-functional membrane contains the PVA/PAA salt copolymer in an amount falling within a range of about 10 to 80% by weight, and the CO₂ carrier in an amount falling within a range of about 20 to 90% by weight based on the total weight of the PVA/PAA salt copolymer and the CO₂ carrier in the separation-functional membrane.

[0058]

Further, the separation-functional membrane contains the CO₂ hydration catalyst, for example, in an amount of 0.01 times or more,

PCAC0052A7-SPE3.doc

preferably 0.02 times or more, further preferably 0.025 times or more the amount of the CO₂ carrier in terms of molar number.

[0059]

The hydrophilic porous membrane preferably has heat resistance to a temperature of 100°C or higher, mechanical strength and adhesion with the separation-functional membrane (gel membrane) in addition to hydrophilicity, and preferably has a porosity (void ratio) of 55% or more and a pore size falling within a range of 0.1 to 1 μm. In this embodiment, a hydrophilized tetrafluoroethylene polymer (PTFE) porous membrane is used as a hydrophilic porous membrane that satisfies the above-mentioned requirements.

[0060]

The hydrophobic porous membrane preferably has heat resistance to a temperature of 100°C or higher, mechanical strength and adhesion with the separation-functional membrane (gel membrane) in addition to hydrophobicity, and preferably has a porosity (void ratio) of 55% or more and a pore size falling within a range of 0.1 to 1 μm. In this embodiment, a non-hydrophilized tetrafluoroethylene polymer (PTFE) porous membrane is used as a hydrophobic porous membrane that satisfies the above-mentioned requirements.

[0061]

One embodiment of a method for producing the present facilitated transport membrane (the present production method) will now be described with reference to Fig. 2. The following descriptions are based on the assumption that a PVA/PAA salt copolymer is used as the hydrophilic

polymer, cesium carbonate (Cs_2CO_3) is used as the CO_2 carrier, and a tellurite (e.g. potassium tellurite (K_2TeO_3)) is used as the CO_2 hydration catalyst. The amounts of the hydrophilic polymer, the CO_2 carrier and the CO_2 hydration catalyst are illustrative, and show amounts used in sample preparation in examples described below.

[0062]

First, a cast solution including an aqueous solution containing a PVA/PAA salt copolymer, a CO_2 carrier and a CO_2 hydration catalyst is prepared (step 1). More specifically, 2 g of a PVA/PAA salt copolymer (e.g. provisional name: SS Gel manufactured by Sumitomo Seika Chemicals Company Limited), 4.67 g of cesium carbonate, and a tellurite in an amount of 0.025 times the amount of cesium carbonate in terms of molar number are added to 80 g of water, and the resultant mixture is stirred until they are dissolved, thereby obtaining a cast solution.

[0063]

Next, the cast solution obtained in step 1 is cast on a hydrophilic PTFE porous membrane side surface of a layered porous membrane by an applicator (step 2), the layered porous membrane being obtained by joining two membranes: a hydrophilic PTFE porous membrane (e.g. WPW-020-80 manufactured by SUMITOMO ELECTRIC FINE POLYMER, INC.; thickness: 80 μm ; pore size: 0.2 μm ; void ratio: about 75%) and a hydrophobic PTFE porous membrane (e.g. FLUOROPORE™ FP010 manufactured by SUMITOMO ELECTRIC FINE POLYMER, INC.; thickness: 60 μm ; pore size: 0.1 μm ; void ratio: 55%). The casting thickness in samples of examples and comparative examples described later is 500

PCAC0052A7-SPE3.doc

μm. Here, the cast solution penetrates pores in the hydrophilic PTFE porous membrane, but is inhibited from penetrating at the boundary surface of the hydrophobic PTFE porous membrane, so that the cast solution does not permeate to the opposite surface of the layered porous membrane, and there is no cast solution on a hydrophobic PTFE porous membrane side surface of the layered porous membrane. This makes handling easy.

[0064]

Next, the hydrophilic PTFE porous membrane after casting is naturally dried at room temperature, and the cast solution is then gelled to produce a separation-functional membrane (step 3). Here, gelation means that the cast solution as a polymer dispersion liquid is dried into a solid form, and the gel membrane is a solid membrane produced by the gelation, and is clearly distinguished from a liquid membrane.

[0065]

In the present production method, the cast solution is cast on a hydrophilic PTFE porous membrane side surface of the layered porous membrane in step 2, and therefore the separation-functional membrane is not only formed on a surface (cast surface) of the hydrophilic PTFE porous membrane but also formed so as to fill pores in step 3, so that defects (minute defects such as pinholes) are hard to occur, leading to an increase in membrane production success rate of the separation-functional membrane. It is desirable to further thermally crosslink the naturally dried PTFE porous membrane at about 120°C for about 2 hours in step 3. All of samples in examples and comparative examples described later are thermally crosslinked.

PCAC0052A7-SPE3.doc

[0066]

Next, a hydrophobic PTFE porous membrane identical to the hydrophobic PTFE porous membrane of the layered porous membrane used in step 2 is superimposed on a gel layer side surface of the hydrophilic PTFE porous membrane obtained in step 3 to obtain the present facilitated transport membrane of three layer structure including a hydrophobic PTFE porous membrane / a separation-functional membrane supported on a hydrophilic PTFE porous membrane / a hydrophobic PTFE porous membrane as schematically shown in Fig. 1 (step 4). Fig. 1 schematically and linearly shows a state in which the separation-functional membrane 1 fills pores of the hydrophilic PTFE porous membrane 2.

[0067]

In the present production method, the blending ratio of the CO₂ carrier and the CO₂ hydration catalyst can be adjusted in step 1 of producing a cast solution, and therefore, as compared to a case where after formation of a gel membrane that does not contain at least one of the CO₂ carrier and the CO₂ hydration catalyst, at least one of the CO₂ carrier and the CO₂ hydration catalyst is added into the gel membrane, adjustment of the blending ratio can be more accurately and easily performed, leading to enhancement of membrane performance.

[0068]

Thus, the present facilitated transport membrane prepared by following steps 1 to 4 can exhibit extremely high selective permeability to hydrogen even at a high temperature of 100°C or higher, for example a CO₂ permeance of about 3×10^{-5} mol/(m²·s·kPa) (= 90 GPU) or more and a

PCAC0052A7-SPE3.doc

CO₂/H₂ selectivity of about 100 or more.

[0069]

Hereinafter, specific membrane performance of the present facilitated transport membrane is evaluated by comparing Examples 1 to 7 in which the separation-functional membrane contains a CO₂ hydration catalyst with Comparative Examples 1 and 2 in which the separation-functional membrane does not contain a CO₂ hydration catalyst.

[0070]

The samples in Examples 1 to 7 and Comparative Examples 1 and 2 below were prepared in accordance with the present production method described above. The weights of the solvent (water), the hydrophilic polymer and the CO₂ carrier in the cast solution prepared in step 1 are the same among Examples 1 to 7 and Comparative Examples 1 and 2. As the hydrophilic polymer, a PVA/PAA salt copolymer was used. As the CO₂ carrier, cesium carbonate (Cs₂CO₃) is used except for Example 6, and the weight ratio of cesium carbonate to the total weight of the PVA/PAA salt copolymer and cesium carbonate (carrier concentration) is 70% by weight in each of the examples and comparative examples. In Example 6, rubidium carbonate (Rb₂CO₃) is used as the CO₂ carrier, and the weight ratio of rubidium carbonate to the total weight of the PVA/PAA salt copolymer (2 g) identical to that in Example 1 and rubidium carbonate (4.67 g) (carrier concentration) is 70% by weight.

[0071]

In Examples 1, 6 and 7, potassium tellurite (melting point: 465°C) was used as the CO₂ hydration catalyst. In Examples 2 to 5, lithium

PCAC0052A7-SPE3.doc

tellurite ($\text{Li}_2\text{O}_3\text{Te}$, melting point: about 750°C), potassium selenite ($\text{K}_2\text{O}_3\text{Se}$, melting point: 875°C), sodium arsenite (NaO_2As , melting point: 615°C) and sodium orthosilicate ($\text{Na}_4\text{O}_4\text{Si}$, melting point: 1018°C) were used, respectively, as the CO_2 hydration catalyst. The molar ratio of the CO_2 hydration catalyst to the CO_2 carrier is 0.025 in Examples 1 to 5, 0.05 in Example 6, and 0.2 in Example 7.

[0072]

The sample in Comparative Example 1 was prepared in the same manner as in Example 1 except that the cast solution prepared in step 1 in the production method described above did not contain a CO_2 hydration catalyst. The sample in Comparative Example 2 was prepared in the same manner as in Example 6 except that the cast solution prepared in step 1 in the production method described above did not contain a CO_2 hydration catalyst.

[0073]

An experiment method for evaluating membrane performance of the samples in Examples 1 to 7 and Comparative Examples 1 and 2 will now be described.

[0074]

Each sample was used while being fixed between a supply side chamber and a permeate side chamber in a stainless steel flow type gas permeation cell using a fluororubber gasket as a seal material.

Experimental conditions are the same for the samples, and the temperature of the inside of the cell is fixed at 130°C .

[0075]

PCAC0052A7-SPE3.doc

The supply side gas supplied to the supply side chamber is a mixed gas including CO₂, H₂ and H₂O (steam), and the ratio (mol%) among them is CO₂ : H₂ : H₂O = 23.6 : 35.4 : 41.0. The flow rate of the supply side gas is 3.47×10^{-2} mol/min, and the supply side pressure is 600 kPa (A). (A) means an absolute pressure. Accordingly, the CO₂ partial pressure on the supply side is 142 kPa (A). The pressure of the supply side chamber is adjusted with a back pressure regulator provided on the downstream side of a cooling trap at some midpoint in an exhaust gas discharging passage.

[0076]

On the other hand, the pressure of the permeate side chamber is atmospheric pressure, H₂O (steam) is used as a sweep gas made to flow into the permeate side chamber, and the flow rate thereof is 7.77×10^{-3} mol/min. For sending the sweep gas discharged from the permeate side chamber to a gas chromatograph on the downstream side, an Ar gas is in-poured, steam in the gas containing the Ar gas is removed by the cooling trap, the composition of the gas after passing through the cooling trap is quantitatively determined by the gas chromatograph, the permeance [mol/(m²·s·kPa)] of each of CO₂ and H₂ is calculated from the composition and the flow rate of Ar in the gas, and from the ratio thereof, the CO₂/H₂ selectivity is calculated.

[0077]

In the evaluation experiment described above, the experiment apparatus has a pre-heater for heating the gas and the flow type gas permeation cell with a sample membrane fixed therein is placed in a thermostatic oven in order to keep constant the use temperature of the

PCAC0052A7-SPE3.doc

present facilitated transport membrane of each sample and the temperatures of the supply side gas and the sweep gas.

[0078]

Next, comparison of membrane performance obtained in experiment results in Examples 1 to 7 and Comparative Examples 1 and 2 is made. Fig. 3 shows a list of constitutional conditions (CO₂ carrier, CO₂ hydration catalyst, molar ratio of CO₂ carrier to CO₂ hydration catalyst, hydrophilic polymer) and membrane performance (CO₂ permeance, H₂ permeance and CO₂/H₂ selectivity) for separation-functional membranes of the samples in Examples 1 to 7 and Comparative Examples 1 and 2.

[0079]

First, comparison of membrane performance is made among Examples 1 to 5 and Comparative Example 1. Here, comparison of membrane performance associated with presence/absence of the CO₂ hydration catalyst and the type thereof is made. Fig. 4 shows, in the form of a graph, the CO₂ permeance and CO₂/H₂ selectivity in Examples 1 to 5 and Comparative Example 1. It is apparent from Figs. 3 and 4 that since the separation-functional membrane contains a CO₂ hydration catalyst, the CO₂ permeance increases by a factor of 1.14 to 1.76, while the H₂ permeance increases by a factor of 0.72 to 1.29, and the increasing rate of CO₂ permeance is greater than that of H₂ permeance, so that the CO₂/H₂ selectivity is improved to fall within a range of 104 to 135 as compared to a CO₂/H₂ selectivity of 79.2 in Comparative Example 1.

[0080]

While from Fig. 4, all of the CO₂ hydration catalysts are confirmed to

PCAC0052A7-SPE3.doc

improve both the CO₂ permeance and CO₂/H₂ selectivity, the CO₂ permeance is remarkably improved when a tellurite is used.

[0081]

Since the CO₂ hydration catalyst is a catalyst for increasing the reaction rate of a CO₂ hydration reaction expressed by the above (Chemical Formula 1), it is considered that when the separation-functional membrane contains a CO₂ hydration catalyst, a reaction of CO₂ with a CO₂ carrier, which includes the CO₂ hydration reaction as one of elementary reactions and which is expressed by the above (Chemical Formula 2), is accelerated, leading to an increase in CO₂ permeance by the facilitated transport mechanism. This is consistent with the experiment results shown in Fig. 3. However, since H₂ does not react with the CO₂ carrier as described above, the H₂ permeation mechanism may be based on the solution-diffusion mechanism rather than the facilitated transport mechanism, and it is considered that the H₂ permeance is not directly affected by presence/absence of the CO₂ hydration catalyst, the blending ratio and type thereof, and the like. Further, the samples in Examples 1 to 7 and Comparative Examples 1 and 2 are different in constitutional conditions for the separation-functional membrane, and are therefore each individually prepared. Therefore, differences in measurement value of H₂ permeance among the samples are considered to mainly result from individual differences (variations) in membrane quality of the hydrophilic polymer gel membrane. It is to be noted that the H₂ permeance may be indirectly affected by influences on membrane quality of the hydrophilic polymer gel membrane given by differences in amount, type and the like of the CO₂

PCAC0052A7-SPE3.doc

carrier and the CO₂ hydration catalyst in addition to the individual differences in membrane quality.

[0082]

Next, comparison of membrane performance is made among Examples 1 and 6 and Comparative Examples 1 and 2. Here, comparison of membrane performance associated with presence/absence of the CO₂ hydration catalyst and the type the CO₂ carrier is made. Fig. 5 shows, in the form of a graph, the CO₂ permeance and CO₂/H₂ selectivity in Examples 1 and 6 and Comparative Examples 1 and 2. Fig. 5 shows that when the separation-functional membrane does not contain a CO₂ hydration catalyst, there is no significant difference in performance due to a difference in CO₂ carrier with the separation-functional membrane having a CO₂ permeance of 2.83 to 2.84×10^{-5} (mol/(m²·s·kPa)), a H₂ permeance of 3.05 to 3.58×10^{-7} (mol/(m²·s·kPa)) and a CO₂/H₂ selectivity of 79.2 to 93.1 in both cases where the CO₂ carrier is cesium carbonate and where the CO₂ carrier is rubidium carbonate. When the CO₂ carrier is cesium carbonate, performance is greatly improved with the CO₂ permeance increasing by a factor of 1.53 , the H₂ permeance increasing by a factor of 1.02 and the CO₂/H₂ selectivity increasing by a factor of 1.50 because the separation-functional membrane contains a CO₂ hydration catalyst. When the CO₂ carrier is rubidium carbonate, performance is greatly improved as in the case where the CO₂ carrier is cesium carbonate, with the CO₂ permeance increasing by a factor of 1.68 , the H₂ permeance increasing by a factor of 0.83 and the CO₂/H₂ selectivity increasing by a factor of 2.04 . The reason why in Example 6, the H₂ permeance decreases to 0.83 times that in

Comparative Example 2 may be because of individual differences in membrane quality of the hydrophilic polymer gel membrane.

[0083]

Next, comparison of membrane performance is made among Examples 1 and 7 and Comparative Example 1. Here, comparison of membrane performance associated with presence/absence of the CO₂ hydration catalyst, and the blending ratio thereof (molar ratio to cesium carbonate) is made. Fig. 6 shows, in the form of a graph, the CO₂ permeance and CO₂/H₂ selectivity in Examples 1 and 7 and Comparative Example 1.

[0084]

When comparison is made among Comparative Example 1 and Examples 1 and 7, it is apparent that both the CO₂ permeance and CO₂/H₂ selectivity are improved as the blending ratio of the CO₂ hydration catalyst (potassium tellurite) increases.

[0085]

As a result of measuring the CO₂ permeance with another sample in which the molar ratio of the CO₂ hydration catalyst to the CO₂ carrier is decreased to 0.01 when the hydrophilic polymer is a PVA/PAA salt copolymer, the CO₂ carrier is cesium carbonate and the CO₂ hydration catalyst is potassium tellurite, aside from Examples 1 and 7, it has been confirmed that the CO₂ permeance was improved to 3.74×10^{-5} (mol/(m²·s·kPa)), i.e. 1.32 times the CO₂ permeance in Comparative Example 1.

[0086]

PCAC0052A7-SPE3.doc

While all of the separation-functional membranes in Examples 1 to 7 and Comparative Examples 1 and 2 are gel membranes, Comparative Example 3 having a liquid membrane (aqueous solution) as a separation-functional membrane was prepared as another comparative example. The aqueous solution of a separation-functional membrane in Comparative Example 3 does not contain the PVA/PAA salt copolymer used in Examples 1 to 7 and Comparative Example 1. In Comparative Example 3, cesium carbonate was used as a CO₂ carrier and potassium tellurite was used as a CO₂ hydration catalyst similarly to Example 1. Hereinafter, a method for preparing Comparative Example 3 will be described.

[0087]

To an aqueous cesium carbonate solution having a molar concentration of 2 mol/L was added potassium tellurite in an amount of 0.025 times the amount of cesium carbonate in terms of molar number, and the resultant mixture was stirred until potassium tellurite was dissolved, thereby obtaining an aqueous solution for a separation-functional membrane (liquid membrane). Thereafter, instead of the casting method using an applicator in step 2 in the present production method, a hydrophilic PTFE porous membrane was immersed in the aqueous solution for a separation-functional membrane (liquid membrane) for 30 minutes, and the hydrophilic PTFE membrane soaked with the aqueous solution was then placed on a hydrophobic PTFE membrane, and dried at room temperature for half a day or longer. Similarly to Examples 1 to 7 and Comparative Examples 1 and 2, another hydrophobic PTFE membrane is placed on the hydrophilic PTFE membrane to form a three-layer structure

PCAC0052A7-SPE3.doc

with the hydrophilic PTFE porous membrane and the separation-functional membrane (liquid membrane) held between the hydrophobic PTFE membranes at the time of an experiment for evaluation of membrane performance.

[0088]

However, in the case of the liquid membrane sample of Comparative Example 3, it was impossible to set the supply side pressure of 600 kPa (A), i.e. an experimental condition similar to that in Examples 1 to 7 and Comparative Examples 1 and 2, and membrane performance could not be evaluated. That is, it became evident that a necessary differential pressure cannot be maintained because the difference in pressure between the supply side and the permeate side in the separation-functional membrane (liquid membrane) cannot be endured.

[0089]

Thus, by comparing membrane performance between Examples 1 to 7 in which the separation-functional membrane contains a CO₂ hydration catalyst and Comparative Examples 1 and 2 in which the separation-functional membrane does not contain a CO₂ hydration catalyst, an effect of considerably improving the CO₂ permeance and CO₂/H₂ selectivity was confirmed as the present facilitated transport membrane includes a CO₂ hydration catalyst in the separation-functional membrane. Here, the facilitated CO₂ transport membrane has such characteristics that in a certain thickness range, thickness dependency is kept low, so that the permeation rate of CO₂ hardly decreases even when the thickness increases. On the other hand, H₂ passes through the separation-functional membrane

PCAC0052A7-SPE3.doc

by the solution-diffusion mechanism as described above, and therefore its permeation rate tends to be inversely proportional to the membrane thickness. Therefore, further improvement of the CO₂/H₂ selectivity is expected due to the synergistic effect of the advantage that the effect of improving the CO₂ permeance due to presence of a CO₂ hydration catalyst in the separation-functional membrane is attained without depending on the membrane thickness and the advantage that the H₂ permeance is reduced as the thickness is increased.

[0090]

Results of evaluating membrane performance in Examples 8 and 9 in which the separation-functional membrane prepared with a thickness that is about 2 times the thickness in Examples 1 to 7 and Comparative Examples 1 and 2 contains a CO₂ hydration catalyst and Comparative Example 4 in which the separation-functional membrane does not contain a CO₂ hydration catalyst will now be described.

[0091]

The samples in Examples 8 and 9 and Comparative Example 4 were prepared in accordance with the present production method described above. It is to be noted that a series of steps including step 2 and step 3 were repeated twice for increasing the thickness of the separation-functional membrane. The weights of the solvent (water), the hydrophilic polymer and the CO₂ carrier in the cast solution prepared in step 1 are the same among Examples 8 and 9 and Comparative Example 4, and identical to those in Examples 1 to 7 and Comparative Examples 1 and 2. In each of Examples 8 and 9 and Comparative Example 4, cesium carbonate (Cs₂CO₃) is used as

the CO₂ carrier, and the weight ratio of cesium carbonate to the total weight of the PVA/PAA salt copolymer and cesium carbonate (carrier concentration) is 70% by weight.

[0092]

In Examples 8 and 9, lithium tellurite and potassium molybdate (K₂O₄Mo, melting point: about 919°C) were used in this order as the CO₂ hydration catalyst. The molar ratio of the CO₂ hydration catalyst to the CO₂ carrier is 0.025 in Example 8, and 0.1 in Example 9. The sample in Comparative Example 4 was prepared in the same manner as in Example 8 except that the cast solution prepared in step 1 in the production method described above did not contain a CO₂ hydration catalyst.

[0093]

An experiment method for evaluating membrane performance of the samples in Examples 8 and 9 and Comparative Example 4 is identical to the experiment method for evaluating membrane performance of the samples in Examples 1 to 7 and Comparative Examples 1 and 2 described above including the gas composition and ratio of the supply side gas, the gas flow rate, the pressure, the use temperature and so on.

[0094]

Fig. 7 shows a list of constitutional conditions (CO₂ carrier, CO₂ hydration catalyst, molar ratio of CO₂ carrier to CO₂ hydration catalyst, hydrophilic polymer) and membrane performance (CO₂ permeance, H₂ permeance and CO₂/H₂ selectivity) for separation-functional membranes of the samples in Examples 2, 8 and 9 and Comparative Examples 1 and 4. Fig. 8 shows, in the form of a graph, the CO₂ permeance and CO₂/H₂

PCAC0052A7-SPE3.doc

selectivity in Examples 2 and 8 and Comparative Examples 1 and 4.

[0095]

First, when comparison of membrane performance is made between Comparative Example 4 and Comparative Example 1, the membrane thickness in Comparative Example 4 is about 2 times the membrane thickness in Comparative Example 1, but there is no difference in other constitutional conditions of the separation-functional membrane, and therefore there is substantially no difference in CO₂ permeance as it is not significantly influenced by the membrane thickness, whereas the H₂ permeance is much lower in Comparative Example 4 than in Comparative Example 1 due to the about 2-fold difference in membrane thickness. As a result, the CO₂/H₂ selectivity is higher in Comparative Example 4 than in Comparative Example 1. Similarly, when comparison of membrane performance is made between Example 8 and Example 2, the membrane thickness in Example 8 is about 2 times the membrane thickness in Example 2, but there is no difference in other constitutional conditions of the separation-functional membrane, and therefore there is substantially no difference in CO₂ permeance as it is not significantly influenced by the membrane thickness, and an effect of improving the CO₂ permeance by the CO₂ hydration catalyst is similarly attained, whereas the H₂ permeance is much lower in Example 8 than in Example 2 due to the about 2-fold difference in membrane thickness. As a result, the CO₂/H₂ selectivity is higher in Example 8 than in Example 2. When comparison of membrane performance is made between Example 8 and Comparative Example 4, it is apparent that similarly to considerable improvement of the CO₂ permeance

PCAC0052A7-SPE3.doc

and CO₂/H₂ selectivity in Example 2 as compared to Comparative Example 1, the CO₂ permeance and CO₂/H₂ selectivity are considerably improved even when the thickness of the separation-functional membrane is large. That is, it has become evident that the effect of improving the CO₂ permeance due to presence of a CO₂ hydration catalyst in the separation-functional membrane is attained without depending on the thickness of the separation-functional membrane in a certain thickness range.

[0096]

Next, when comparison is made between Example 9 and Comparative Example 4, an effect of improving the CO₂ permeance and CO₂/H₂ selectivity due to presence of a CO₂ hydration catalyst in the separation-functional membrane can be confirmed even with a membrane thickness that is about 2 times the membrane thickness in Examples 1 to 7 also when the CO₂ hydration catalyst is potassium molybdate.

[0097]

Here, the CO₂ hydration catalyst in each of Examples 1 to 3 and 6 to 8 and Example 10 described later is an oxo acid compound of a group 16 element, the CO₂ hydration catalyst in Example 4 is an oxo acid compound of a group 15 element, the CO₂ hydration catalyst in Example 5 is an oxo acid compound of a group 14 element, and the CO₂ hydration catalyst in Example 9 is an oxo acid compound of a group 6 element. Accordingly, from the results of evaluating membrane performance, it is apparent that at least oxo acid compounds of group 6 elements, group 14 elements, group 15 elements and group 16 elements suitably include a CO₂ hydration catalyst which is soluble in water and extremely thermally stable with a melting

PCAC0052A7-SPE3.doc

point of 200°C or higher, and has catalytic activity at a high temperature of 100°C or higher. However, this does not mean that all the oxo acid compounds of group 6 elements, group 14 elements, group 15 elements and group 16 elements have catalytic activity as a CO₂ hydration catalyst, and the possibility is not ruled out that oxo acid compounds other than those of group 6 elements, group 14 elements, group 15 elements and group 16 elements include those which have catalytic activity as a CO₂ hydration catalyst and can be used for the present facilitated transport membrane.

[0098]

Further, as substances having catalytic activity as a CO₂ hydration catalyst, there are many substances other than oxo acid compounds, such as enzymes. Therefore, the CO₂ hydration catalyst is not limited to the oxo acid compounds used in Examples 1 to 9 as long as it can be suitably used for the present facilitated transport membrane. Here, as an example of conditions suitable for the present facilitated transport membrane as a CO₂ hydration catalyst, the substance is soluble in water, and extremely thermally stable with a melting point of 200°C or higher, and has catalytic activity at a high temperature of 100°C or higher.

[0099]

In the above-mentioned embodiment, as an example of a suitable configuration of the present facilitated transport membrane, a configuration has been shown in which a hydrogel of a PVA/PAA salt copolymer as a hydrophilic polymer is used as a membrane material of a separation-functional membrane, and a hydrophilic porous membrane is used as a porous membrane that supports the separation-functional membrane.

PCAC0052A7-SPE3.doc

However, since the hydrophilic polymer gel membrane contains a CO₂ hydration catalyst, the effect of improving the CO₂ permeance and CO₂/H₂ selectivity can also be exhibited, although varying in level, when a hydrophilic polymer other than PVA/PAA salt copolymers, such as, for example, polyvinyl alcohol (PVA) or a polyacrylic acid (PAA) salt is used, or when a hydrophobic porous membrane is used as a porous membrane that supports the separation-functional membrane.

[0100]

Results of evaluating membrane performance in Example 10 in which the separation-functional membrane contains a CO₂ hydration catalyst and Comparative Example 5 in which the separation-functional membrane does not contain a CO₂ hydration catalyst, with polyvinyl alcohol (PVA) being used as a hydrophilic polymer in both Example 10 and Comparative Example 5, will now be described.

[0101]

The samples in Example 10 and Comparative Example 5 were prepared in accordance with the present production method described above. It is to be noted that similarly to Examples 8 and 9 and Comparative Example 4, a series of steps including step 2 and step 3 were repeated twice for increasing the thickness of the separation-functional membrane. The weights of the solvent (water), the hydrophilic polymer and the CO₂ carrier in the cast solution prepared in step 1 are the same between Example 10 and Comparative Example 5. In each of Example 10 and Comparative Example 5, cesium carbonate (Cs₂CO₃) is used as the CO₂ carrier, and the weight ratio of cesium carbonate to the total weight of PVA and cesium

PCAC0052A7-SPE3.doc

carbonate (carrier concentration) is 46% by weight. The polymerization degree of polyvinyl alcohol used is about 2000, and the porous membrane supporting the separation-functional membrane is a PTFE porous membrane having a pore size of 0.1 μm and a thickness of 50 μm .

[0102]

In Example 10, potassium tellurite is used as a CO_2 hydration catalyst, and the molar ratio of the CO_2 hydration catalyst to the CO_2 carrier is 0.2. The sample in Comparative Example 5 was prepared in the same manner as in Example 10 except that the cast solution prepared in step 1 in the production method described above did not contain a CO_2 hydration catalyst.

[0103]

An experiment method for evaluating membrane performance of the samples in Example 10 and Comparative Example 5 is identical to the experiment method for evaluating membrane performance of the samples in Examples 1 to 9 and Comparative Examples 1, 2 and 4 described above except for the ratio of gas components of the supply side gas, the supply side gas flow rate, the supply side pressure and the use temperature. The ratio (mol%) among CO_2 , H_2 and H_2O (steam) in the supply side gas supplied to the supply side chamber is $\text{CO}_2 : \text{H}_2 : \text{H}_2\text{O} = 5.0 : 48.7 : 46.3$. The flow rate of the supply side gas is 6.14×10^{-2} mol/min, the supply side pressure is 300 kPa (A), and the temperature of the inside of the flow type gas permeation cell is fixed at 120°C.

[0104]

Fig. 7 shows a list of constitutional conditions (CO_2 carrier, CO_2

PCAC0052A7-SPE3.doc

hydration catalyst, molar ratio of CO₂ carrier to CO₂ hydration catalyst, hydrophilic polymer) and membrane performance (CO₂ permeance, H₂ permeance and CO₂/H₂ selectivity) for separation-functional membranes of the samples in Example 10 and Comparative Example 5.

[0105]

When comparison of membrane performance is made between Example 10 and Comparative Example 5, it is apparent that the CO₂ permeance and CO₂/H₂ selectivity are considerably improved. From this result, it has become evident that the effect of improving the CO₂ permeance due to presence of a CO₂ hydration catalyst in the separation-functional membrane is attained also when polyvinyl alcohol is used as the hydrophilic polymer. Accordingly, it is well conceivable that the effect of improving the CO₂ permeance is attained irrespective of the composition of the hydrophilic polymer. Therefore, the hydrophilic polymer that forms the separation-functional membrane of the present facilitated transport membrane is not limited to the PVA/PAA salt copolymer and polyvinyl alcohol (PVA) shown as examples in the above-mentioned embodiment.

[0106]

[Second Embodiment]

A CO₂ separation apparatus and a CO₂ separation method, to which the facilitated CO₂ transport membrane described in the first embodiment is applied, will now be described with reference to Figs. 9A and 9B.

[0107]

Figs. 9A and 9B are each a sectional view schematically showing an outlined structure of a CO₂ separation apparatus 10 of this embodiment. In

PCAC0052A7-SPE3.doc

this embodiment, as an example, a facilitated CO₂ transport membrane modified into a cylindrical structure is used instead of the facilitated CO₂ transport membrane of flat plate structure described in the first embodiment. Fig. 9A shows a cross section structure at a cross section perpendicular to the axial center of a facilitated CO₂ transport membrane (the present facilitated transport membrane) 11 of cylindrical structure, and Fig. 9B shows a cross section structure at a cross section extending through the axial center of the present facilitated transport membrane 11.

[0108]

The present facilitated transport membrane 11 shown in Figs. 9A and 9B has a structure in which a separation-functional membrane 1 is supported on the outer circumferential surface of a cylindrical hydrophilic ceramic porous membrane 2. Similarly to the first embodiment, the separation-functional membrane 1 includes a polyvinyl alcohol-polyacrylic acid (PVA/PAA) salt copolymer as a membrane material of the separation-functional membrane, a carbonate of an alkali metal such as cesium carbonate (Cs₂CO₃) or rubidium carbonate (Rb₂CO₃) as the CO₂ carrier, and a tellurous acid compound, a selenious acid compound, an arsenious acid compound and an orthosilicic acid compound as the CO₂ hydration catalyst. The membrane structure in this embodiment is different from the membrane structure in the first embodiment in that the separation-functional membrane 1 and the hydrophilic ceramic porous membrane 2 are not held between two hydrophobic porous membranes. The method for producing the separation-functional membrane 1 and membrane performance thereof in this embodiment are basically similar to those in the

PCAC0052A7-SPE3.doc

first embodiment except for the above-mentioned difference, and therefore duplicate explanations are omitted.

[0109]

As shown in Figs. 9A and 9B, the present cylindrical facilitated transport membrane 11 is housed in a bottomed cylindrical container 12, and a supply side space 13 surrounded by the inner wall of the container 12 and the separation-functional membrane 1 and a permeate side space 14 surrounded by the inner wall of the ceramic porous membrane 2 are formed. A first feeding port 15 for feeding a source gas FG into the supply side space 13 and a second feeding port 16 for feeding a sweep gas SG into the permeate side space 14 are provided on one of bottom portions 12a and 12b on opposite sides of the container 12, and a first discharge port 17 for discharging a CO₂-separated source gas EG from the supply side space 13 and a second discharge port 18 for discharging from the permeate side space 14 a discharge gas SG' including a mixture of a CO₂-containing permeate gas PG passing through the present facilitated transport membrane 11 and the sweep gas SG are provided on the other of the bottom portions 12a and 12b on opposite sides of the container 12. The container 12 is made of, for example, stainless steel, and although not illustrated, the present facilitated transport membrane 11 is fixed in the container 12 with a fluororubber gasket interposed as a seal material between opposite ends of the present facilitated transport membrane 11 and the inner walls of the bottom portions 12a and 12b on opposite sides of the container 12 similarly to the experiment apparatus described in the first embodiment as an example. The method for fixing the present facilitated transport membrane 11 and

PCAC0052A7-SPE3.doc

the sealing method are not limited to the methods described above.

[0110]

In Fig. 9B, each of the first feeding port 15 and the first discharge port 17 is provided in each of the supply side spaces 13 illustrated separately on the left and the right in Fig. 9B. However, since the supply side spaces 13 annularly communicate with each other as shown in Fig. 9A, the first feeding port 15 and the first discharge port 17 may be provided in one of the left and right supply side spaces 13. Further, Fig. 9B shows as an example a configuration in which the first feeding port 15 and the second feeding port 16 are provided on one of the bottom portions 12a and 12b, and the first discharge port 17 and the second discharge port 18 are provided on the other of the bottom portions 12a and 12b, but a configuration may be employed in which the first feeding port 15 and the second discharge port 18 are provided on one of the bottom portions 12a and 12b, and the first discharge port 17 and the second feeding port 16 are provided on the other of the bottom portions 12a and 12b. That is, the direction along which the source gases FG and EG flow and the direction along which the sweep gas SG and the discharge gas SG' flow may be reversed.

[0111]

In the CO₂ separation method of this embodiment, the source gas FG including a mixed gas containing CO₂ and H₂ and having a temperature of 100°C or higher is fed into the supply side space 13 and thereby supplied to the supply side surface of the present facilitated transport membrane 11, so that a CO₂ carrier contained in the separation-functional membrane 1 of the present facilitated transport membrane 11 is reacted with CO₂ in the source

PCAC0052A7-SPE3.doc

gas FG to allow selective passage of CO₂ at a high selection ratio to hydrogen, and the CO₂-separated source gas EG having an increased H₂ concentration is discharged from the supply side space 13.

[0112]

The reaction of CO₂ with the CO₂ carrier requires supply of water (H₂O) as shown in the above reaction formula of (Chemical Formula 2), and as the amount of water contained in the separation-functional membrane 1 increases, chemical equilibrium is shifted to the product side (right side), so that permeation of CO₂ is facilitated. When the temperature of the source gas FG is a high temperature of 100°C or higher, the separation-functional membrane 1 that is in contact with the source gas FG is also exposed to a high temperature of 100°C or higher, so that water contained in the separation-functional membrane 1 is evaporated and passes into the permeate side space 14 similarly to CO₂, and therefore it is necessary to supply steam (H₂O) to the supply side space 13. The steam may be contained in the source gas FG, or may be supplied to the supply side space 13 independently of the source gas FG. In the latter case, steam (H₂O) passing into the permeate side space 14 may be separated from the discharge gas SG' and circulated into the supply side space 13.

[0113]

For the CO₂ separation apparatus shown in Figs. 9A and 9B, a configuration example has been described in which the supply side space 13 is formed at the outside while the permeate side space 14 is formed at the inside of the present cylindrical facilitated transport membrane 11, but the supply side space 13 may be formed at the inside while the permeate side

PCAC0052A7-SPE3.doc

space 14 may be formed at the outside. The present facilitated transport membrane 11 may have a structure in which the separation-functional membrane 1 is supported on the inner circumferential surface of the cylindrical hydrophilic ceramic porous membrane 2. Further, the present facilitated transport membrane 11 used in the CO₂ separation apparatus is not necessarily cylindrical, but may be in the form of a tube having a cross-sectional shape other than a circular shape, and the present facilitated transport membrane of flat plate structure as shown in Fig. 1 may be used.

[0114]

As an application example of the CO₂ separation apparatus described in this embodiment, a shift converter (CO₂ permeable membrane reactor) including the present facilitated transport membrane will now be briefly described.

[0115]

For example, when a CO₂ permeable membrane reactor is formed using the CO₂ separation apparatus 10 shown in Figs. 9A and 9B, the supply side space 13 can be used as a shift converter by filling the supply side space 13 with a shift catalyst.

[0116]

The CO₂ permeable membrane reactor is an apparatus in which, for example, a source gas FG produced in a steam reforming device and having H₂ as a main component is received in the supply side space 13 filled with a shift catalyst, and carbon monoxide (CO) contained in the source gas FG is removed through a CO shift reaction expressed by the above (Chemical Formula 5). CO₂ produced through the CO shift reaction is allowed to

PCAC0052A7-SPE3.doc

permeate to the permeate side space 14 selectively by means of the present facilitated transport membrane 11 and removed, whereby chemical equilibrium can be shifted to the hydrogen production side, so that CO and CO₂ can be removed beyond the limit imposed by equilibrium restriction with a high conversion rate at the same reaction temperature. A source gas EG freed of CO and CO₂ and having H₂ as a main component is taken out from the supply side space 13.

[0117]

Since the performance of the shift catalyst used for the CO shift reaction tends to decrease with a decrease in temperature, the use temperature is considered to be 100°C at minimum, and the temperature of the source gas FG supplied to the supply side surface of the present facilitated transport membrane 11 is 100°C or higher. Therefore, the source gas FG is adjusted to a temperature suitable for catalytic activity of the shift catalyst, then fed into the supply side space 13 filled with the shift catalyst, subjected to the CO shift reaction (exothermic reaction) in the supply side space 13, and supplied to the present facilitated transport membrane 11.

[0118]

On the other hand, the sweep gas SG is used for maintaining the driving force for the permeation through the present facilitated transport membrane 11 by lowering the partial pressure of the CO₂-containing permeate gas PG which permeates the present facilitated transport membrane 11 and for discharging the permeate gas PG to the outside. It is to be noted that when the partial pressure of the source gas FG is

PCAC0052A7-SPE3.doc

sufficiently high, it is not necessary to feed the sweep gas SG because a partial pressure difference serving as the driving force for permeation is obtained even if the sweep gas SG is not fed. As a gas species used for the sweep gas, steam (H_2O) can also be used as in the case of the experiment for evaluation of membrane performance in the first embodiment, and further an inert gas such as Ar can also be used. The sweep gas SG is not limited to a specific gas species.

[0119]

[Other Embodiments]

Hereinafter, other embodiments will be described.

[0120]

<1> The above-mentioned embodiments have been described based on the assumption that a carbonate, a bicarbonate or a hydroxide of an alkali metal such as cesium or rubidium is used as a CO_2 carrier. However, since the present invention is characterized in that a hydrophilic polymer gel membrane that forms a separation-functional membrane contains a CO_2 carrier and a CO_2 hydration catalyst having catalytic activity at a high temperature of 100°C or higher, the CO_2 carrier is not limited to a specific CO_2 carrier as long as it is such a CO_2 carrier that a reaction of CO_2 with the CO_2 carrier can be accelerated by a CO_2 hydration catalyst to attain membrane performance comparable to or higher than the membrane performance (selective permeability of CO_2 to hydrogen) shown as an example in the first embodiment.

[0121]

<2> The above-mentioned embodiments have been described based

PCAC0052A7-SPE3.doc

on the assumption that the CO₂ hydration catalyst contains at least one of a tellurous acid compound, a selenious acid compound, an arsenious acid compound, an orthosilicic acid compound and a molybdic acid compound, but the CO₂ hydration catalyst is not limited to a specific CO₂ hydration catalyst as long as it is a CO₂ hydration catalyst which has catalytic activity for the CO₂ hydration reaction of the above (Chemical Formula 1) at a high temperature of 100°C or higher, preferably 130°C or higher, more preferably 160°C or higher and which can attain membrane performance comparable to or higher than the membrane performance (selective permeability of CO₂ to hydrogen) shown as an example in the first embodiment when combined with a CO₂ carrier. When used in the separation-functional membrane of the present facilitated transport membrane, the CO₂ hydration catalyst is preferably one that has a melting point of 200°C or higher and is soluble in water similarly to the above-mentioned compounds. While the upper limit of the range of temperatures at which the CO₂ hydration catalyst exhibits catalytic activity is not particularly limited, there is no problem as long as it is higher than the upper limit of the range of temperatures such as the use temperature of the present facilitated transport membrane in an apparatus including the present facilitated transport membrane, and the temperature of a source gas supplied to the supply side surface of the present facilitated transport membrane. The hydrophilic porous membrane or the like that forms the present facilitated transport membrane is also required to have resistance in a similar temperature range as a matter of course. When the present facilitated transport membrane is used at a temperature lower than 100°C, the CO₂ hydration catalyst is not necessarily required to have

PCAC0052A7-SPE3.doc

catalytic activity at a high temperature of 100°C or higher.

[0122]

<3> In the first embodiment, the present facilitated transport membrane is prepared by a method in which a cast solution including an aqueous solution containing a hydrophilic polymer (PVA/PAA salt copolymer, polyvinyl alcohol (PVA) or the like), a CO₂ carrier and a CO₂ hydration catalyst is cast on a hydrophilic PTFE porous membrane, and then gelled, but the present facilitated transport membrane may be prepared by a preparation method other than the above-mentioned preparation method. For example, the present facilitated transport membrane may be prepared by forming a hydrophilic polymer gel membrane that does not contain a CO₂ carrier and a CO₂ hydration catalyst, followed by impregnating the gel membrane with an aqueous solution containing a CO₂ carrier and a CO₂ hydration catalyst.

[0123]

<4> In the first embodiment, the present facilitated transport membrane has a three-layer structure including a hydrophobic PTFE porous membrane, a separation-functional membrane supported on a hydrophilic PTFE porous membrane and a hydrophobic PTFE porous membrane, but the support structure of the present facilitated transport membrane is not limited to such a three-layer structure. For example, the present facilitated transport membrane may have a two-layer structure including a hydrophobic PTFE porous membrane and a separation-functional membrane supported on a hydrophilic PTFE porous membrane. In the first embodiment, a case has been described where the separation-functional

PCAC0052A7-SPE3.doc

membrane is supported on the hydrophilic PTFE porous membrane, but the separation-functional membrane may be supported on the hydrophobic PTFE porous membrane.

[0124]

<5> In the second embodiment, a CO₂ permeable membrane reactor has been described as an application example of the CO₂ separation apparatus including the present facilitated transport membrane, but the CO₂ separation apparatus including the present facilitated transport membrane can also be used in a decarbonation step in a hydrogen production process other than that in the membrane reactor, and is further applicable to processes other than the hydrogen production process, and the CO₂ separation apparatus is not limited to the application example shown in the above-mentioned embodiment. The supply side gas (source gas) supplied to the present facilitated transport membrane is not limited to the mixed gas shown as an example in the above-mentioned embodiments.

[0125]

<6> The mixing ratios of the components in the composition of the present facilitated transport membrane, the dimensions of the portions of the membrane and the like as shown as examples in the above-mentioned embodiments are examples given for easy understanding of the present invention, and the present invention is not limited to facilitated CO₂ transport membranes having such values.

INDUSTRIAL APPLICABILITY

[0126]

PCAC0052A7-SPE3.doc

A facilitated CO₂ transport membrane according to the present invention can be used for separating CO₂ from a mixed gas including CO₂ and H₂ at a high selection ratio to hydrogen in a decarbonation step in a hydrogen production process, a CO₂ permeable membrane reactor, and so on, and is useful particularly for separation of CO₂ at a high temperature of 100°C or higher.

DESCRIPTION OF SYMBOLS

[0127]

- | | |
|----------|---|
| 1 | separation-functional membrane |
| 2 | hydrophilic porous membrane |
| 3, 4 | hydrophobic porous membrane |
| 10 | CO ₂ separation apparatus |
| 11 | facilitated CO ₂ transport membrane |
| 12 | container |
| 12a, 12b | bottom portion (upper bottom portion and lower bottom portion) of container |
| 13 | supply side space |
| 14 | permeate side space |
| 15 | first feeding port |
| 16 | second feeding port |
| 17 | first discharge port |
| 18 | second discharge port |
| FG | source gas |
| EG | CO ₂ -separated source gas |

PCAC0052A7-SPE3.doc

PG permeate gas

SG, SG' sweep gas

CLAIMS

1. A facilitated CO₂ transport membrane comprising a separation-functional membrane that includes a hydrophilic polymer gel membrane containing a CO₂ carrier and a CO₂ hydration catalyst, wherein
the CO₂ hydration catalyst is an oxo acid compound of at least one element selected from group 6 elements and group 14 elements.
2. The facilitated CO₂ transport membrane according to claim 1, wherein the CO₂ hydration catalyst has catalytic activity at a temperature of 100°C or higher.
3. The facilitated CO₂ transport membrane according to claim 1 or 2, wherein the CO₂ hydration catalyst has a melting point of 200°C or higher.
4. The facilitated CO₂ transport membrane according to any one of claims 1 to 3, wherein the CO₂ hydration catalyst is soluble in water.
5. The facilitated CO₂ transport membrane according to any one of claims 1 to 4, wherein the CO₂ hydration catalyst contains at least an orthosilicic acid compound.
6. The facilitated CO₂ transport membrane according to any one of claims 1 to 4, wherein the CO₂ hydration catalyst contains a molybdic acid compound.

7. The facilitated CO₂ transport membrane according to claim 5, wherein the CO₂ hydration catalyst further contains a molybdic acid compound.

8. The facilitated CO₂ transport membrane according to any one of claims 1 to 7, wherein the gel membrane is a hydrogel.

9. The facilitated CO₂ transport membrane according to any one of claims 1 to 8, wherein the gel membrane is a polyvinyl alcohol-polyacrylic acid salt copolymer gel membrane.

10. The facilitated CO₂ transport membrane according to any one of claims 1 to 9, wherein the CO₂ carrier contains at least one of a carbonate of an alkali metal, a bicarbonate of an alkali metal and a hydroxide of an alkali metal.

11. The facilitated CO₂ transport membrane according to claim 10, wherein the alkali metal is cesium or rubidium.

12. The facilitated CO₂ transport membrane according to any one of claims 1 to 11, wherein the separation-functional membrane is supported on a hydrophilic porous membrane.

13. A method for producing the facilitated CO₂ transport membrane according to any one of claims 1 to 12, the method comprising the steps of:

preparing a cast solution including an aqueous solution containing the hydrophilic polymer, the CO₂ carrier and the CO₂ hydration catalyst that is an oxo acid compound of at least one element selected from group 6 elements and group 14 elements and is soluble in water; and

casting the cast solution on a hydrophilic porous membrane and then gelling the cast solution to prepare the separation-functional membrane.

14. A method for separating CO₂ using the facilitated CO₂ transport membrane according to any one of claims 1 to 12, with the CO₂ hydration catalyst having catalytic activity at a temperature of 100°C or higher, wherein a mixed gas containing CO₂ and H₂ and having a temperature of 100°C or higher is supplied to the facilitated CO₂ transport membrane, and the CO₂ passing through the facilitated CO₂ transport membrane is separated from the mixed gas.

15. A CO₂ separation apparatus comprising the facilitated CO₂ transport membrane according to any one of claims 1 to 12, with the CO₂ hydration catalyst having catalytic activity at a temperature of 100°C or higher, wherein a mixed gas containing CO₂ and H₂ and having a temperature of 100°C or higher is supplied to the facilitated CO₂ transport membrane, and the CO₂ passing through the facilitated CO₂ transport membrane is separated from the mixed gas.

16. A method for separating CO₂ using a facilitated CO₂ transport membrane, the facilitated CO₂ transport membrane comprising a separation-functional membrane that includes a hydrophilic polymer gel membrane containing a CO₂ carrier with a CO₂ hydration catalyst having catalytic activity at a temperature of 100°C or higher,

wherein a mixed gas containing CO₂ and H₂ and having a temperature of 100°C or higher is supplied to a supply side of the facilitated CO₂ transport membrane under a condition that a pressure difference between the supply side and a permeate side of the facilitated CO₂ transport membrane is not less than 202.65 kPa, and the CO₂ passing through the facilitated CO₂ transport membrane is separated from the mixed gas, and

wherein the CO₂ hydration catalyst contains at least one of a tellurous acid compound, a selenious acid compound, an orthosilicic acid compound and a molybdic acid compound.

17. The method of claim 16, wherein the gel membrane is a hydrogel.

18. The method of claim 16 or 17, wherein the gel membrane is a polyvinyl alcohol-polyacrylic acid salt copolymer gel membrane.

19. The method of any one of claims 16 – 18, wherein the CO₂ carrier contains at least one of a carbonate of an alkali metal, a bicarbonate of an alkali metal and a hydroxide of an alkali metal.

20. The method of claim 19, wherein the alkali metal is cesium or rubidium.

21. The method of any one of claims 16 – 20, wherein the separation-functional membrane is supported on a hydrophilic porous membrane.

22. A CO₂ separation apparatus comprising a facilitated CO₂ transport membrane, the facilitated CO₂ transport membrane comprising a separation-functional membrane that includes a hydrophilic polymer gel membrane containing a CO₂ carrier and a CO₂ hydration catalyst having catalytic activity at a temperature of 100°C or higher,

wherein the apparatus is configured to supply a mixed gas containing CO₂ and H₂ and having a temperature of 100°C or higher to a supply side of the facilitated CO₂ transport membrane under a condition that a pressure difference between the supply side and a permeate side of the facilitated CO₂ transport membrane is not less than 202.65 kPa, and the CO₂ passing through the facilitated CO₂ transport membrane is separated from the mixed gas, and

wherein the CO₂ hydration catalyst contains at least one of a tellurous acid compound, a selenious acid compound, an orthosilicic acid compound and a molybdic acid compound.

23. The apparatus of claim 22, wherein the gel membrane is a hydrogel.

24. The apparatus of claim 22 or 23, wherein the gel membrane is a polyvinyl alcohol-polyacrylic acid salt copolymer gel membrane.

25. The apparatus of any one of claims 22 – 24, wherein the CO₂ carrier contains at least one of a carbonate of an alkali metal, a bicarbonate of an alkali metal and a hydroxide of an alkali metal.

26. The apparatus of claim 25, wherein the alkali metal is cesium or rubidium.

27. The apparatus of any one of claims 22 – 26, wherein the separation-functional membrane is supported on a hydrophilic porous membrane.




Fig. 1




Fig. 2

Sample	Constitutional conditions of separation-functional membranes				Membrane performance		
	CO ₂ hydration reaction catalyst	CO ₂ carrier	Molar ratio of CO ₂ carrier to CO ₂ hydration reaction catalyst	Hydrophilic polymer	CO ₂ permeance (mol/(m ² ·s·kPa))	H ₂ permeance (mol/(m ² ·s·kPa))	CO ₂ /H ₂ selectivity
Example 1	Potassium tellurite	Cesium carbonate	1 : 0.025	PVA/PAA salt copolymer	4.33×10 ⁻⁵	3.64×10 ⁻⁷	119
Example 2	Lithium tellurite	Cesium carbonate	1 : 0.025	PVA/PAA salt copolymer	4.98×10 ⁻⁵	4.61×10 ⁻⁷	108
Example 3	Potassium selenite	Cesium carbonate	1 : 0.025	PVA/PAA salt copolymer	3.52×10 ⁻⁵	2.61×10 ⁻⁷	135
Example 4	Sodium arsenite	Cesium carbonate	1 : 0.025	PVA/PAA salt copolymer	4.09×10 ⁻⁵	3.94×10 ⁻⁷	104
Example 5	Sodium orthosilicate	Cesium carbonate	1 : 0.025	PVA/PAA salt copolymer	3.24×10 ⁻⁵	2.95×10 ⁻⁷	110
Example 6	Potassium tellurite	Rubidium carbonate	1 : 0.05	PVA/PAA salt copolymer	4.78×10 ⁻⁵	2.52×10 ⁻⁷	190
Example 7	Potassium tellurite	Cesium carbonate	1 : 0.2	PVA/PAA salt copolymer	5.49×10 ⁻⁵	4.15×10 ⁻⁷	132
Comp. Ex. 1	none	Cesium carbonate	—	PVA/PAA salt copolymer	2.83×10 ⁻⁵	3.58×10 ⁻⁷	79.2
Comp. Ex. 2	none	Rubidium carbonate	—	PVA/PAA salt copolymer	2.84×10 ⁻⁵	3.05×10 ⁻⁷	93.1

Fig. 3




Fig. 4




Fig. 5




Fig. 6

Sample	Constitutional conditions of separation-functional membranes				Process Condition	Membrane performance		
	CO ₂ hydration reaction catalyst	CO ₂ carrier	Molar ratio of CO ₂ carrier to CO ₂ hydration reaction catalyst	Hydrophilic polymer		CO ₂ permeance (mol/(m ² ·s·kPa))	H ₂ permeance (mol/(m ² ·s·kPa))	CO ₂ /H ₂ selectivity
Example 2	Lithium tellurite	Cesium carbonate	1 : 0.025	PVA/PAA salt copolymer	1	4.98×10 ⁻⁵	4.61×10 ⁻⁷	108
Example 8	Lithium tellurite	Cesium carbonate	1 : 0.025	PVA/PAA salt copolymer	2	4.72×10 ⁻⁵	2.04×10 ⁻⁷	231
Example 9	Potassium molybdate	Cesium carbonate	1 : 0.1	PVA/PAA salt copolymer	2	3.28×10 ⁻⁵	2.56×10 ⁻⁷	128
Example 10	Potassium tellurite	Cesium carbonate	1 : 0.2	PVA	2	3.63×10 ⁻⁵	2.62×10 ⁻⁷	138
Comp. Ex. 1	none	Cesium carbonate	—	PVA/PAA salt copolymer	1	2.83×10 ⁻⁵	3.58×10 ⁻⁷	79.2
Comp. Ex. 4	none	Cesium carbonate	—	PVA/PAA salt copolymer	2	2.77×10 ⁻⁵	2.31×10 ⁻⁷	120
Comp. Ex. 5	none	Cesium carbonate	—	PVA	2	2.84×10 ⁻⁵	3.05×10 ⁻⁷	93.1

Fig. 7




Fig. 8




Fig. 9A




Fig. 9B

