



(12)

# Oversættelse af europæisk patent

Patent- og  
Varemærkestyrelsen

- (51) Int.Cl.: **A 61 L 15/22 (2006.01)** **A 61 L 15/44 (2006.01)** **A 61 L 15/60 (2006.01)**
- (45) Oversættelsen bekendtgjort den: **2019-07-29**
- (80) Dato for Den Europæiske Patentmyndigheds  
bekendtgørelse om meddelelse af patentet: **2019-04-24**
- (86) Europæisk ansøgning nr.: **10747385.2**
- (86) Europæisk indleveringsdag: **2010-08-20**
- (87) Den europæiske ansøgnings publiceringsdag: **2012-06-27**
- (86) International ansøgning nr.: **US2010046209**
- (87) Internationalt publikationsnr.: **WO2011022680**
- (30) Prioritet: **2009-08-21 US 235948 P** **2009-08-21 US 235927 P**
- (84) Designerede stater: **AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO SE SI SK SM TR**
- (73) Patenthaver: **Novan, Inc., 4105 Hopson Road, Morrisville, North Carolina 27560, USA**
- (72) Opfinder: **STASKO, Nathan, 4008 Kettering Drive, Durham, North Carolina 27713, USA**  
**BAUMAN, Susanne, 1101 Exchange Place Apt. 724, Durham, North Carolina 27713, USA**  
**JOSHI, Pranav R., 1200 Laurel Springs Drive, Durham, North Carolina 27713, USA**
- (74) Fuldmægtig i Danmark: **Marks & Clerk (Luxembourg) LLP, 44 rue de la Vallée, B.P. 1775, L-1017 Luxembourg, Luxembourg**
- (54) Benævnelse: **SÅRBANDAGER, FREMGANGSMÅDER TIL ANVENDELSE HERAF OG FREMGANGSMÅDER TIL DANNELSE DERAFF**
- (56) Fremdragne publikationer:  
**WO-A1-03/026717**  
**WO-A2-2006/128121**  
**US-A- 5 405 919**  
**NORIO IWAKIRI ET AL: "Synthesis of amphiphilic polysiloxanes and their properties for formation of nano-aggregates", COLLOID AND POLYMER SCIENCE ; KOLLOID-ZEITSCHRIFT UND ZEITSCHRIFT FÜR POLYMERE, SPRINGER, BERLIN, DE, vol. 287, no. 5, 13 February 2009 (2009-02-13), pages 577-582, XP019712758, ISSN: 1435-1536**  
**JAE HO SHIN ET AL: "Synthesis of Nitric Oxide-Releasing Silica Nanoparticles", JOURNAL OF THE AMERICAN CHEMICAL SOCIETY, vol. 129, no. 15, 1 April 2007 (2007-04-01), pages 4612-4619, XP055089359, ISSN: 0002-7863, DOI: 10.1021/ja0674338**  
**HETRICK E M ET AL: "Anti-biofilm efficacy of nitric oxide-releasing silica nanoparticles", BIOMATERIALS, ELSEVIER SCIENCE PUBLISHERS BV., BARKING, GB, vol. 30, no. 14, 1 May 2009 (2009-05-01), pages 2782-2789, XP025970945, ISSN: 0142-9612, DOI: 10.1016/J.BIOMATERIALS.2009.01.052 [retrieved on 2009-02-23]**  
**HRABIE JOSEPH ET AL: "Chemistry of the nitric oxide-releasing diazeniumdiolate (nitrosohydroxylamine) functional group and its oxygen-substituted derivatives", CHEMICAL REVIEWS, AMERICAN CHEMICAL**

SOCIETY, US, vol. 102, no. 4, 1 April 2002 (2002-04-01) , pages 1135-1154, XP002512904, ISSN: 0009-2665, DOI: 10.1021/CR000028T [retrieved on 2002-02-09]

KEITH M. DAVIES ET AL: "Chemistry of the Diazeniumdiolates. 2. Kinetics and Mechanism of Dissociation to Nitric Oxide in Aqueous Solution", JOURNAL OF THE AMERICAN CHEMICAL SOCIETY, vol. 123, no. 23, 1 June 2001 (2001-06-01) , pages 5473-5481, XP055136341, ISSN: 0002-7863, DOI: 10.1021/ja002899q

# DESCRIPTION

## CROSS-REFERENCE TO RELATED APPLICATIONS

**[0001]** This application claims priority from U.S. Provisional Application Serial No. 61/235,927, filed August 21, 2009, and U.S. Provisional Application Serial No. 61/235,948, filed August 21, 2009, the disclosures of which are hereby incorporated by reference herein in their entirety.

## STATEMENT OF GOVERNMENT FUNDING

**[0002]** Research for this application was partially funded through a Phase I NIH SBIR grant entitled "Nitric Oxide-Releasing Antibacterial Wound Dressing" (grant number 5R43AI074098-02). The government may have certain rights to this application.

## FIELD OF THE INVENTION

**[0003]** The present invention relates to materials that may be used as wound dressings that may release nitric oxide. The present invention also relates to methods of making and using wound dressings that may release nitric oxide.

## BACKGROUND OF THE INVENTION

**[0004]** An important aspect for wound care is the control of infection, which may facilitate the healing process. Wound dressings are one of the most commonly used tools to protect the wound from infection. Antimicrobial agents are often incorporated into the wound dressing to treat and prevent infection. However, there are several disadvantages associated with use of antimicrobial agents. It has been observed that an increasing number of pathogens have developed resistance to the conventional antibiotic treatment. According to statistics, antibiotic-resistant pathogens are the primary reason for a majority of all lethal nosocomial infections. See Robson et al., *Surg. Clin. N. Am.* 77, 637-650 (1977). Furthermore, many antiseptic agents not only kill pathogens, but also impose a threat to the proliferating granulation tissue, fibroblasts and keratinocytes that may help with the wound healing process. Additionally, some antimicrobial agents may cause allergic reactions in some patients.

**[0005]** It is known that nitric oxide possesses a broad-spectrum of antimicrobial activity and may be used as an alternative to conventional antibiotics for drug resistant bacteria. Furthermore, some recent studies have demonstrated that nitric oxide may also play an important role in the wound healing process by promoting angiogenesis through stimulation of

vascular endothelial growth factor (VEGF) and increased fibroblast collagen synthesis. See Schaffer MR, et al., Diabetes-impaired healing and reduced wound nitric oxide synthesis: A possible pathophysiologic correlation. *Surgery* 1997;121(5):513-9; and Shi HP, et al., The role of iNOS in wound healing. *Surgery* 2001;130 (2):225-9. Thus, nitric oxide presents a promising addition and/or alternative to the conventional antibiotic treatment for wound care.

**[0006]** WO 03/026717 (Fitzhugh et al) described a method for preparing a nitric oxide-releasing substrate.

**[0007]** Shin et al (J. Am. Chem. Soc. 2007, 129, 4612-2619) describe NO-releasing silica nanoparticles prepared from amine-functionalized silica nanoparticles.

**[0008]** Hetrick et al (Biomaterials 30 (2009) 2782-2789) describe the use of NO-releasing silica nanoparticles to kill biofilm-based microbial cells.

**[0009]** Hrabie et al (Chem. Rev. 2002, 102, 1135-1154) and Davies et al (J. Am. Chem. Soc. 2001, 123, 5473-5481) describe the chemistry of NO-releasing diazeniumdiolate functional groups.

**[0010]** Nitric oxide is a gas at ambient temperature and atmospheric pressure, and it has a short half-life in a physiological milieu. Several small molecule nitric oxide donor prodrugs have been developed which have contributed greatly to the understanding of nitric oxide in a number of disease states. However, due to issues with stability, indiscriminate NO-release, monotypical nitric oxide release kinetics, and inability to target specific tissue types no clinically viable solutions currently exist for administering nitric oxide outside of its gaseous form. Reproducibly delivering the appropriate levels of nitric oxide for a given therapeutic indication is important because release of large amounts of nitric oxide may be toxic or create undesirable side effects such as decreases in angiogenesis or increased inflammation. Therefore, it has been challenging to use nitric oxide in the wound care field, other than via exogenous application, particularly in topical wound healing applications wherein nitric oxide has concentration dependent effects and benefits from delivery in a controlled and targeted manner.

**[0011]** Thus, the need exists for wound treatments and dressings that can release nitric oxide by a controlled delivery method.

#### **SUMMARY OF THE INVENTION**

**[0012]** In an aspect of the present invention there is provided a wound dressing according to the appended claims. In some embodiments, the NO-releasing polysiloxane macromolecules may include S-nitrosothiol functional groups.

**[0013]** In some embodiments of the invention, the concentration of the NO-releasing

polysiloxane macromolecules may be in a range of about 0.1 to about 20 weight percent.

**[0014]** The wound dressings may include additional additives. For example, the wound dressings may include a water-soluble porogen such as sodium chloride, sucrose, glucose, lactose, sorbitol, xylitol, polyethylene glycol, polyvinylpyrrolidone, polyvinyl alcohol and mixtures thereof. The wound dressings may also include at least one therapeutic agent such as antimicrobial compounds, anti-inflammatory agents, pain-relievers, immunosuppressants, vasodilators, wound healing agents, anti-biofilm agents and mixtures thereof.

**[0015]** In some embodiments, the polymer matrix may include a hydrophilic polyurethane, such as, for example, an aliphatic polyether polyurethane that absorbs water in an amount ranging from 10 percent to 60 percent of its dry weight.

**[0016]** In some embodiments, the NO-releasing macromolecules may be present within, and optionally crosslinked to, the polymer matrix of the polymer foam.

**[0017]** In some embodiments, the storage of nitric oxide in the wound dressing may be in a range of 0.1 pmol NO cm<sup>-2</sup> to 100 pmol NO cm<sup>-2</sup>, in some embodiments, in a range of 100 pmol NO cm<sup>-2</sup> to 1000 pmol NO cm<sup>-2</sup> and in some embodiments, in a range of 1 nmol NO cm<sup>-2</sup> to 10 µmol NO cm<sup>-2</sup>.

**[0018]** In other aspects of the invention, there are provided a wound dressing for use in a method of treating a wound, and a method of forming wound dressings according to the appended claims.

#### **BRIEF DESCRIPTION OF THE DRAWINGS**

**[0019]** The accompanying drawings, which are included to provide a further understanding of the invention and are incorporated in and constitute a part of this application, illustrate certain embodiment(s) of the invention.

**Figure 1** depicts a cross-sectional view of a wound dressing according to an embodiment of the invention.

**Figures 2A and 2B** depict cross-sectional views of wound dressings according to embodiments of the invention.

**Figures 3A and 3B** depict cross-sectional views of wound dressings according to embodiments of the invention.

**Figures 4A and 4B** depict cross-sectional views of wound dressings according to embodiments of the invention.

**Figures 5A and 5B** depict cross-sectional views of wound dressings according to

embodiments of the invention.

**Figures 6A and 6B** depict cross-sectional views of wound dressings according to embodiments of the invention.

**Figure 7** shows water uptake of particular polyurethane polymer matrices over time.

**Figure 8** shows water uptake for Tecophilic® Aliphatic thermoplastic polyurethane HP-60D-20 ("T20") loaded with increasing weight percent of poly(ethylene glycol) 8000 MW as a porogen.

**Figure 9** shows the water uptake for Tecophilic® Hydrogel thermoplastic polyurethane TG-2000 solvent cast into polymer films thin film dressings and soaked in phosphate buffered saline at physiological temperature and pH.

**Figure 10** illustrates the covalent storage of nitric oxide on the aminosilane N-methylaminopropyltrimethoxysilane as a diazeniumdiolate NO donor, followed by co-condensation with a backbone alkoxy silane, tetraethoxysilane, to form Nitricil™ composition 70.

**Figure 11** depicts the chemiluminescent detection of NO release from Nitricil™ 70 silica particles free in solution, wound dressing Composition J, and wound dressing Composition D measured at physiological buffer, pH, and temperature.

**Figure 12** shows the efficacy of various NO-releasing wound dressing compositions on both the levels of planktonic bacteria flushed from the wound and the levels of biofilm bacteria scrubbed from the wound are shown in comparison to Tegaderm™ covered controls.

**Figures 13A and 13B** depict the NO behavior of the finished device soaked in buffer at physiological temperature and pH (37° C, 7.4).

**Figure 14** depicts the % complete re-epithelialization versus time for wound dressings according to embodiments of the invention in comparison to Tegaderm™ covered controls.

#### DETAILED DESCRIPTION OF EMBODIMENTS OF THE INVENTION

**[0020]** The foregoing and other aspects of the present invention will now be described in more detail with respect to the description and methodologies provided herein.

**[0021]** The terminology used in the description of the invention herein is for the purpose of describing particular embodiments only and is not intended to be limiting of the invention. As used in the description of the embodiments of the invention and the appended claims, the singular forms "a", "an" and "the" are intended to include the plural forms as well, unless the context clearly indicates otherwise. Also, as used herein, "and/or" refers to and encompasses any and all possible combinations of one or more of the associated listed items. Furthermore,

the term "about," as used herein when referring to a measurable value such as an amount of a compound, dose, time, temperature, and the like, is meant to encompass variations of 20%, 10%, 5%, 1%, 0.5%, or even 0.1% of the specified amount. It will be further understood that the terms "comprises" and/or "comprising," when used in this specification, specify the presence of stated features, integers, steps, operations, elements, and/or components, but do not preclude the presence or addition of one or more other features, integers, steps, operations, elements, components, and/or groups thereof. Unless otherwise defined, all terms, including technical and scientific terms used in the description, have the same meaning as commonly understood by one of ordinary skill in the art to which this invention belongs.

### ***Chemical Definitions***

**[0022]** As used herein the term "alkyl" refers to C<sub>1-20</sub> inclusive, linear (i.e., "straight-chain"), branched, or cyclic, saturated or at least partially and in some cases fully unsaturated (i.e., alkenyl and alkynyl) hydrocarbon chains, including for example, methyl, ethyl, propyl, isopropyl, butyl, isobutyl, *tert*-butyl, pentyl, hexyl, octyl, ethenyl, propenyl, butenyl, pentenyl, hexenyl, octenyl, butadienyl, propynyl, butynyl, pentynyl, hexynyl, heptynyl, and allenyl groups. "Branched" refers to an alkyl group in which a lower alkyl group, such as methyl, ethyl or propyl, is attached to a linear alkyl chain. Exemplary branched alkyl groups include, but are not limited to, isopropyl, isobutyl, *tert*-butyl. "Lower alkyl" refers to an alkyl group having 1 to about 8 carbon atoms (i.e., a C<sub>1-8</sub> alkyl), e.g., 1, 2, 3, 4, 5, 6, 7, or 8 carbon atoms. "Higher alkyl" refers to an alkyl group having about 10 to about 20 carbon atoms, e.g., 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, or 20 carbon atoms. In certain embodiments, "alkyl" refers, in particular, to C<sub>1-5</sub> straight-chain alkyls. In other embodiments, "alkyl" refers, in particular, to C<sub>1-5</sub> branched-chain alkyls.

**[0023]** Alkyl groups can optionally be substituted (a "substituted alkyl") with one or more alkyl group substituents, which can be the same or different. The term "alkyl group substituent" includes but is not limited to alkyl, substituted alkyl, halo, arylamino, acyl, hydroxyl, aryloxyl, alkoxy, alkylthio, arylthio, aralkyloxyl, aralkylthio, carboxyl, alkoxycarbonyl, oxo, and cycloalkyl. There can be optionally inserted along the alkyl chain one or more oxygen, sulfur or substituted or unsubstituted nitrogen atoms, wherein the nitrogen substituent is hydrogen, lower alkyl (also referred to herein as "alkylaminoalkyl"), or aryl.

**[0024]** Thus, as used herein, the term "substituted alkyl" includes alkyl groups, as defined herein, in which one or more atoms or functional groups of the alkyl group are replaced with another atom or functional group, including for example, alkyl, substituted alkyl, halogen, aryl, substituted aryl, alkoxy, hydroxyl, nitro, amino, alkylamino, dialkylamino, sulfate, and mercapto.

**[0025]** The term "aryl" is used herein to refer to an aromatic substituent that can be a single aromatic ring, or multiple aromatic rings that are fused together, linked covalently, or linked to a

common group, such as, but not limited to, a methylene or ethylene moiety. The common linking group also can be a carbonyl, as in benzophenone, or oxygen, as in diphenylether, or nitrogen, as in diphenylamine. The term "aryl" specifically encompasses heterocyclic aromatic compounds. The aromatic ring(s) can comprise phenyl, naphthyl, biphenyl, diphenylether, diphenylamine and benzophenone, among others. In particular embodiments, the term "aryl" means a cyclic aromatic comprising about 5 to about 10 carbon atoms, e.g., 5, 6, 7, 8, 9, or 10 carbon atoms, and including 5- and 6-membered hydrocarbon and heterocyclic aromatic rings.

**[0026]** The aryl group can be optionally substituted (a "substituted aryl") with one or more aryl group substituents, which can be the same or different, wherein "aryl group substituent" includes alkyl, substituted alkyl, aryl, substituted aryl, aralkyl, hydroxyl, alkoxy, aryloxy, aralkyloxy, carboxyl, acyl, halo, nitro, alkoxycarbonyl, aryloxycarbonyl, aralkoxycarbonyl, acyloxy, acylamino, aroylamino, carbamoyl, alkylcarbamoyl, dialkylcarbamoyl, arylthio, alkylthio, alkylene, and -NR<sup>1</sup>R", wherein R<sup>1</sup> and R" can each be independently hydrogen, alkyl, substituted alkyl, aryl, substituted aryl, and aralkyl.

**[0027]** Thus, as used herein, the term "substituted aryl" includes aryl groups, as defined herein, in which one or more atoms or functional groups of the aryl group are replaced with another atom or functional group, including for example, alkyl, substituted alkyl, halogen, aryl, substituted aryl, alkoxy, hydroxyl, nitro, amino, alkylamino, dialkylamino, sulfate, and mercapto. Specific examples of aryl groups include, but are not limited to, cyclopentadienyl, phenyl, furan, thiophene, pyrrole, pyran, pyridine, imidazole, benzimidazole, isothiazole, isoxazole, pyrazole, pyrazine, triazine, pyrimidine, quinoline, isoquinoline, indole, carbazole, and the like.

**[0028]** "Cyclic" and "cycloalkyl" refer to a non-aromatic mono- or multicyclic ring system of about 3 to about 10 carbon atoms, e.g., 3, 4, 5, 6, 7, 8, 9, or 10 carbon atoms. The cycloalkyl group can be optionally partially unsaturated. The cycloalkyl group also can be optionally substituted with an alkyl group substituent as defined herein, oxo, and/or alkylene. There can be optionally inserted along the cyclic alkyl chain one or more oxygen, sulfur or substituted or unsubstituted nitrogen atoms, wherein the nitrogen substituent is hydrogen, alkyl, substituted alkyl, aryl, or substituted aryl, thus providing a heterocyclic group. Representative monocyclic cycloalkyl rings include cyclopentyl, cyclohexyl, and cycloheptyl. Multicyclic cycloalkyl rings include adamantyl, octahydronaphthyl, decalin, camphor, camphane, and noradamantyl.

**[0029]** "Alkoxy" refers to an alkyl-O- group wherein alkyl is as previously described. The term "alkoxy" as used herein can refer to, for example, methoxyl, ethoxyl, propoxyl, isopropoxyl, butoxyl, t-butoxyl, and pentoxy. The term "oxyalkyl" can be used interchangeably with "alkoxy". In some embodiments, the alkoxy has 1, 2, 3, 4, or 5 carbons.

**[0030]** "Aralkyl" refers to an aryl-alkyl group wherein aryl and alkyl are as previously described, and included substituted aryl and substituted alkyl. Exemplary aralkyl groups include benzyl, phenylethyl, and naphthylmethyl.

**[0031]** "Alkylene" refers to a straight or branched bivalent aliphatic hydrocarbon group having from 1 to about 20 carbon atoms, e.g., 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, or 20 carbon atoms. The alkylene group can be straight, branched or cyclic. The alkylene group also can be optionally unsaturated and/or substituted with one or more "alkyl group substituents." There can be optionally inserted along the alkylene group one or more oxygen, sulfur or substituted or unsubstituted nitrogen atoms (also referred to herein as "alkylaminoalkyl"), wherein the nitrogen substituent is alkyl as previously described. Exemplary alkylene groups include methylene (-CH<sub>2</sub>); ethylene (-CH<sub>2</sub>-CH<sub>2</sub>); propylene (-(CH<sub>2</sub>)<sub>3</sub>); cyclohexylene (-C<sub>6</sub>H<sub>10</sub>); -CH=CH-CH=CH-; -CH=CH-CH<sub>2</sub>-; wherein each of q and r is independently an integer from 0 to about 20, e.g., 0, 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, or 20, and R is hydrogen or lower alkyl; methylenedioxyl (-O-CH<sub>2</sub>-O-); and ethylenedioxyl (-O-(CH<sub>2</sub>)<sub>2</sub>-O-). An alkylene group can have about 2 to about 3 carbon atoms and can further have 6-20 carbons.

**[0032]** "Arylene" refers to a bivalent aryl group. An exemplary arylene is phenylene, which can have ring carbon atoms available for bonding in ortho, meta, or para positions with regard to each other, i.e., respectively. The arylene group can also be naphthylene. The arylene group can be optionally substituted (a "substituted arylene") with one or more "aryl group substituents" as defined herein, which can be the same or different.

**[0033]** "Aralkylene" refers to a bivalent group that contains both alkyl and aryl groups. For example, aralkylene groups can have two alkyl groups and an aryl group (i.e., -alkyl-aryl-alkyl-), one alkyl group and one aryl group (i.e., -alkyl-aryl-) or two aryl groups and one alkyl group (i.e., -aryl-alkyl-aryl-).

**[0034]** The term "amino" and "amine" refer to nitrogen-containing groups such as NR<sub>3</sub>, NH<sub>3</sub>, NHR<sub>2</sub>, and NH<sub>2</sub>R, wherein R can be alkyl, branched alkyl, cycloalkyl, aryl, alkylene, arylene, aralkylene. Thus, "amino" as used herein can refer to a primary amine, a secondary amine, or a tertiary amine. In some embodiments, one R of an amino group can be a cation stabilized diazeniumdiolate (i.e., NONO<sup>-</sup>X<sup>+</sup>).

**[0035]** The terms "cationic amine" and "quaternary amine" refer to an amino group having an additional (i.e., a fourth) group, for example a hydrogen or an alkyl group bonded to the nitrogen. Thus, cationic and quartemary amines carry a positive charge.

**[0036]** The term "alkylamine" refers to the -alkyl-NH<sub>2</sub> group.

**[0037]** The term "carbonyl" refers to the -(C=O)- group.

**[0038]** The term "carboxyl" refers to the -COOH group and the term "carboxylate" refers to an anion formed from a carboxyl group, i.e., -COO<sup>-</sup>.

**[0039]** The terms "halo", "halide", or "halogen" as used herein refer to fluoro, chloro, bromo,

and iodo groups.

**[0040]** The term "hydroxyl" and "hydroxy" refer to the -OH group.

**[0041]** The term "hydroxyalkyl" refers to an alkyl group substituted with an-OH group.

**[0042]** The term "mercapto" or "thio" refers to the -SH group. The term "silyl" refers to groups comprising silicon atoms (Si).

**[0043]** As used herein the term "alkoxysilane" refers to a compound comprising one, two, three, or four alkoxy groups bonded to a silicon atom. For example, tetraalkoxysilane refers to  $\text{Si}(\text{OR})_4$ , wherein R is alkyl. Each alkyl group can be the same or different. An "alkylsilane" refers to an aloxysilane wherein one or more of the alkoxy groups has been replaced with an alkyl group. Thus, an alkylsilane comprises at least one alkyl-Si bond. The term "fluorinated silane" refers to an alkylsilane wherein one of the alkyl groups is substituted with one or more fluorine atoms. The term "cationic or anionic silane" refers to an alkylsilane wherein one of the alkyl groups is further substituted with an alkyl substituent that has a positive (*i.e.*, cationic) or a negative (*i.e.* anionic) charge, or can become charged (*i.e.*, is ionizable) in a particular environment (*i.e.*, *in vivo*).

**[0044]** The term "silanol" refers to a Si-OH group.

**[0045]** Provided according to some embodiments of the invention are wound dressings that include a polymer matrix and nitric oxide (NO)-releasing polysiloxane macromolecules within and/or on the polymer matrix. The appropriate combination of polymer matrix and NO-releasing polysiloxane macromolecules may allow for a wound dressing that stably stores NO and may provide for controlled release of NO to the wound.

#### ***The Polymer Matrix***

**[0046]** As used herein, the term "polymer matrix" is meant to encompass any natural or synthetic polymeric material that may retain at least some of the NO-releasing polysiloxane macromolecules therein or thereon. As such, the polymer matrix may be a homopolymer, heteropolymer, random copolymer, block copolymer, graft copolymer, mixture or blend of any suitable polymer(s), and it may be in any suitable physical form, such as a foam, film, woven or non-woven material, hydrogel, gel matrix, mixtures and blends thereof, and the like. As described in further detail below, the choice of polymeric matrix and its physico-chemical properties for a particular wound dressing may depend on factors such as the NO-releasing polysiloxane macromolecules within and/or on the polymer matrix, and the type of therapeutic action desired.

**[0047]** In some embodiments of the invention, the polymer matrix includes at least one of

hydrophilic polyurethanes, hydrophilic polyacrylates, co-polymers of carboxymethylcellulose and acrylic acid, N-vinylpyrrolidone, poly(hydroxy acids), polyanhydrides, polyorthoesters, polyamides, polycarbonates, polyalkylenes (e.g., polyethylene and polypropylene), polyalkylene glycols (e.g., poly(ethylene glycol)), polyalkylene oxides (e.g., polyethylene oxide), polyalkylene terephthalates (e.g., polyethylene terephthalate), polyvinyl alcohols, polyvinyl ethers, polyvinyl esters, polyvinyl halides (e.g., poly(vinyl chloride)), polyvinylpyrrolidone, polysiloxanes, poly(vinyl acetates), polystyrenes, polyurethane copolymers, cellulose, derivatized celluloses, alginates, poly(acrylic acid), poly(acrylic acid) derivatives, acrylic acid copolymers, methacrylic acid, methacrylic acid derivatives, methacrylic acid copolymers, poly(butyric acid), poly(valeric acid), poly(lactide-co-caprolactone), copolymers thereof and blends thereof.

**[0048]** In some embodiments of the invention, the polymer matrix may include a superabsorbent polymer (SAP). A polymer is considered superabsorbent, as defined per IUPAC, as a polymer that can absorb and retain large amounts of water relative to its own mass. SAPs may absorb water more than 500 times their own weight and may swell more than 1000 times their original volume. Exemplary SAPs include sodium polyacrylate, the polyurethane Tecophilic® TG-T2000, polyacrylamide copolymer, ethylene maleic anhydride copolymer, cross-linked carboxy-methyl-cellulose, polyvinyl alcohol copolymers, and cross-linked polyethylene oxide.

**[0049]** In some embodiments of the invention, polymers that are relatively hydrophobic, as defined by a water uptake value less than 10% by weight, may be used. Any suitable hydrophobic polymer may be used. However, exemplary polymers that are relatively hydrophobic include aromatic polyurethanes, silicone rubber, polycaprolactone, polycarbonate, polyvinylchloride, polyethylene, poly-L-lactide, poly-DL-glycolide, polyether etherketone (PEEK), polyamide, polyimide and polyvinyl acetate.

**[0050]** In addition, in some embodiments of the invention, the polymer matrix is modified to reduce swelling of the polymer and therefore prevent macromolecule leaching (e.g., NO-releasing polysiloxane macromolecule migration from the polymer matrix to the wound bed). Such modifications may include crosslinking of the polymer chains. The polymer matrix may also be modified by reacting the polymer with additional reagents. For example, the polymer may be modified to add hydrophilic groups, such as anionic, cationic and/or zwitterionic moieties, or to add hydrophobic groups such as silicone moieties, to the polymer chain.

**[0051]** In some embodiments, the polymer matrix includes polymer foam. The term "polymer foam" is meant to encompass any natural or synthetic polymer that is present as a foam and that may retain at least some NO-releasing polysiloxane macromolecules therein or thereon. In some embodiments, the polymer foam has an average cell size in a range of 50 $\mu$ m and 600 $\mu$ m. Furthermore, in some embodiments, the foam may be an open-celled foam. In some embodiments, the open cell walls of the foam may include pores of average size smaller than 100 $\mu$ m, with the individual pore sizes between 10 and 80  $\mu$ m. As used herein, the term "open-celled foam" refers to a foam that has cells that are substantially interconnected, such as

foams wherein at least 50%, at least 60%, at least 70%, at least 80%, or at least 90% of the cells are connected to at least one other cell. In some embodiments, the foam may be flexible. As used herein, the term "flexible" refers to foam that has a flexural strength of at least 40 MPa.

**[0052]** In some embodiments of the invention, the polymer foam is polyurethane foam. Any suitable polyurethane foam may be used. However, in some embodiments, the polyurethane foam may include at least one polyisocyanate segment and at least one polyol segment. Polyurethanes may be formed from the reaction of polyisocyanates and polyols. The polyisocyanate segment refers to a portion of the polyurethane formed from at least one polyisocyanate.

**[0053]** In some embodiments of the invention, the at least one polyisocyanate segment is formed from at least one of tolylene diisocyanate, methylphenylene diisocyanate, modified diisocyanates (e.g., uretdiones, isocyanurates, allophanates, biurets, isocyanate prepolymers and carbodiimide-modified isocyanates) and/or mixtures thereof. Exemplary diisocyanate include toluene diisocyanate; 1,4-tetramethylene diisocyanate; 1,4-hexamethylene diisocyanate; 1,6-hexamethylene diisocyanate; 1,12-dodecane diisocyanate; cyclobutane-1,3-diisocyanate; cyclohexane-1,3-diisocyanate; cyclohexane-1,4-diisocyanate; 1-isocyanato-3,3,5-trimethyl-5-isocyanatomethyl cyclohexane; 2,4-hexahydrotolylene diisocyanate; 2,6-hexahydrotolylene diisocyanate; 2,6-hexahydro-1,3-phenylene diisocyanate; 2,6-hexahydro-1,4-phenylene diisocyanate; per-hydro-2,4'-diphenyl methane diisocyanate; per-hydro-4,4'-diphenyl methane diisocyanate; 1,3-phenylene diisocyanate; 1,4-phenylene diisocyanate; 2,4-tolylene diisocyanate, 2,6-toluene diisocyanates; diphenyl methane-2,4'-diisocyanate; diphenyl methane-4,4'-diisocyanate; naphthalene-1,5-diisocyanate; 1,3-xylylene diisocyanate; 1,4-xylylene diisocyanate; 4,4'-methylene-bis(cyclohexyl isocyanate); 4,4'-isopropyl-bis-(cyclohexyl isocyanate); 1,4-cyclohexyl diisocyanate; 3-isocyanatomethyl-3,5,5-trimethylcyclohexyl isocyanate (IPDI); 1-methoxy-2,4-phenylene diisocyanate; 1-chlorophenyl-2,4-diisocyanate; p-(1-isocyanatoethyl)-phenyl isocyanate; m-(3-isocyanatobutyl)-phenyl isocyanate; 4-(2-isocyanate-cyclohexyl-methyl)-phenyl isocyanate; and mixtures thereof.

**[0054]** The polyol segment refers to a portion of the polyurethane foam formed from at least one polyol. The polyols may include polyether polyols and/or polyester polyols. Polyether polyols may have a significant amount of ether linkages in their structure, whereas the polyester polyols may have ester linkages within their structure. Any suitable polyol may be used. However, in some embodiments of the invention, the at least one polyol segment is formed from a diol having from 2 to 18 carbon atoms, and in some embodiments, a diol having 2 to 10 carbon atoms. Exemplary diols include 1,2-ethanediol, 1,3-propanediol, 1,4-butanediol, 1,6-hexanediol, 1,5-pentanediol, 1,10-decanediol, 2-methyl-1,3-propanediol, 2-methyl-2-butyl-1,3-propanediol, 2,2-dimethyl-1,3-propanediol, 2,2-dimethyl-1,4-butanediol, 2-ethyl-2-butyl-1,3-propanediol, neopentyl glycol hydroxypivalate, diethylene glycol and triethylene glycol. Triols and polyols of higher functionality may also be used and include compounds having 3 to 25, and in some embodiments, 3 to 18, and, in particular embodiments, 3 to 6 carbon atoms. Examples of triols which can be used are glycerol or trimethylolpropane. As polyols of higher

functionality, it is possible, for example, to employ erythritol, pentaerythritol and sorbitol. In some embodiments, low molecular mass reaction products of the polyols may be used, for example, those of trimethylolpropane with alkylene oxides, such as ethylene oxide and/or propylene oxide. These low molecular mass polyols can be used individually or as mixtures.

**[0055]** Examples of polyether polyols include the commercially available polyols PETOL28-3B, PETOL36-3BR, and PETOL56-3MB, Multranol®, Arcol® and Acclaim® (Bayer Material Science), and the Caradol® family of polyols (Shell Chemical Corporation).

**[0056]** Examples of polyester polyols that can be suitably used in the current invention include diethylene glycol adipate diol, dicaprylate diol, and in general, the esters of dicarboxylic and hydroxyl acids with glycol, and glycol functionalized polyester oligomers polylactate, polglycolate, polycaprylate, PET, and commercial formulations such as Desmophen® C polycarbonate diols and Desmophen® polyacrylate diols (Bayer).

**[0057]** In some embodiments, certain polyols or mixtures thereof specifically formulated for manufacture of high resiliency flexible polyurethane foams may be used. Examples of such polyols include a polyol having an ethylene oxide content in a range of 50% to 80%, a primary hydroxyl content of at least 40% and a molecular weight in a range of 2500 and 6000; a polymer polyol prepared by in situ polymerization of a high-functionality poly(oxyethylene)-poly(oxypropylene) oligomer, with a second poly(oxyethylene) polyol oligomer with a molecular weight ranging from 450 to 30,000 and an poly(oxyethylene) content greater than 70%; and biobased polyols derived from soybean oil, castor oil, palm oil, linseed oil and canola oil.

**[0058]** Other polyisocyanates and polyols may be used, including polyols and polyisocyanates having other functional groups therein. As such, in some embodiments, the polyisocyanates and polyols may include other functional groups such as ether, ester, urea, acrylate, pyrrolidone, vinyl, phenyl, and amino linkages, provided that the resulting polyurethane is suitable for forming a foam.

**[0059]** In some embodiments of the invention, the polymer foam includes a superabsorbent polymer (SAP). The superabsorbancy can be introduced in the foam structure by the inclusion of polymer segments that have superabsorbency in the polyol or the 'soft' segment of the foam. Examples of polymer segments having superabsorbency may include polyacrylamide copolymer, ethylene maleic anhydride copolymer, cross-linked carboxy-methyl-cellulose, polyvinyl alcohol copolymers, and cross-linked polyethylene oxide.

**[0060]** In some embodiments of the invention, polymer foams that are relatively hydrophobic may be used. Any suitable hydrophobic polymer may be used. Hydrophobicity can be introduced by selection of the polyisocyanate or the 'soft' segment of the polyurethane foam. Choosing highly hydrophobic polyisocyanates may results in a rigid foam, while lack of adequate hydrophobicity may prevent the formation of the foam structure.

**[0061]** Commonly used polyisocyanates for hydrophobic foams include diphenylmethane

diisocyanate and its isomers, toluene diisocyanate, hexamethylene diisocyanate and mixtures thereof. In some embodiments, the polyisocyanates may also include copolymers of the diisocyanates previously mentioned. In some embodiments, the isocyanate groups may also be introduced at the termini of polymer segments of relatively hydrophobic polymers to provide a better control of the foam. Other polymers that are relatively hydrophobic include silicone rubber, polycaprolactone, polycarbonate, polyvinylchloride, polyethylene, poly-L-lactide, poly-DL-glycolide, polyetheretherketone (PEEK), polyamide, polyimide and polyvinyl acetate.

**[0062]** The polymer to be foamed may also be modified by reacting the polymer with additional reagents. For example, the polymer may be modified to add hydrophilic groups, such as anionic, cationic and/or zwitterionic moieties, or to add hydrophobic groups, such as silicone groups, to the polymer chain.

**[0063]** The polymer foam may be prepared by the reaction between the isocyanate moieties of the polyisocyanate 'hard' segments and the nucleophilic terminal groups of the polyols or 'soft' segments. The nucleophilic groups may include hydroxyl, amine and/or carboxylic groups.

**[0064]** In some embodiments, the foam may also contain chain extending segments in addition to the polyols and polyisocyanate building blocks. Polyamine co-reactants, due to their reactivity with isocyanates, are the most commonly used chain extenders used to increase the chain length and flexibility of the foam. The most commonly used polyamines are polyaspartic esters, polyaldimines, butylenes diamines, and other short chain alkyl diamines.

#### ***Nitric Oxide-Releasing Polysiloxane Macromolecules***

**[0065]** The term "NO-releasing polysiloxane macromolecules" refers to a structure synthesized from monomeric silane constituents that results in a larger molecular framework with a molar mass of at least 500 Da and a nominal diameter ranging from 0.1 nm - 100 µm and may comprise the aggregation of two or more macromolecules, whereby the macromolecular structure is further modified with an NO donor group. For example, in some embodiments, the NO donor group may include diazeniumdiolate nitric oxide functional groups. In some embodiments, the NO donor group may include S-nitrosothiol functional groups.

**[0066]** In some embodiments of the invention, the NO-releasing polysiloxane macromolecules may be in the form of NO-releasing particles, such as those described in U.S. Publication No. 2009/0214618. Such particles may be prepared by methods described therein.

**[0067]** As an example, in some embodiments of the invention, the NO-releasing particles include NO-loaded precipitated silica ranging from 20 nm to 10 µm in size. The NO-loaded precipitated silica may be formed from nitric oxide donor modified silane monomers into a co-condensed siloxane network. In some embodiments of the invention, the nitric oxide donor is an N-diazeniumdiolate.

**[0068]** In some embodiments of the invention, the nitric oxide donor may be formed from an aminoalkoxysilane by a pre-charging method, and the co-condensed siloxane network may be synthesized from the condensation of a silane mixture that includes an alkoxy silane and the aminoalkoxysilane to form a nitric oxide donor modified co-condensed siloxane network. As used herein, the "pre-charging method" means that aminoalkoxysilane is "pretreated" or "precharged" with nitric oxide prior to the co-condensation with alkoxy silane. In some embodiments, the precharging nitric oxide may be accomplished by chemical methods. In another embodiment, the "pre-charging" method can be used to create co-condensed siloxane networks and materials more densely functionalized with NO-donors.

**[0069]** The co-condensed siloxane network can be silica particles with a uniformed size, a collection of silica particles with a variety of size, amorphous silica, a fumed silica, a nanocrystalline silica, ceramic silica, colloidal silica, a silica coating, a silica film, organically modified silica, mesoporous silica, silica gel, bioactive glass, or any suitable form or state of silica.

**[0070]** The composition of the siloxane network, (e.g., amount or the chemical composition of the aminoalkoxysilane) and the nitric oxide charging conditions (e.g., the solvent and base) may be varied to optimize the amount and duration of nitric oxide release. Thus, in some embodiments, the composition of the silica particles may be modified to regulate the half-life of NO release from silica particles.

**[0071]** In some embodiments, the alkoxy silane is a tetraalkoxysilane having the formula  $\text{Si}(\text{OR})_4$ , wherein R is an alkyl group. The R groups can be the same or different. In some embodiments the tetraalkoxysilane is selected as tetramethyl orthosilicate (TMOS) or tetraethyl orthosilicate (TEOS). In some embodiments, the aminoalkoxysilane has the formula:  $\text{R}''-(\text{NH}-\text{R}')_n-\text{Si}(\text{OR})_3$ , wherein R is alkyl, R' is alkylene, branched alkylene, or aralkylene, n is 1 or 2, and R'' is selected from the group consisting of alkyl, cycloalkyl, aryl, and alkylamine.

**[0072]** In some embodiments, the aminoalkoxysilane can be selected from *N*-(6-aminohexyl)aminopropyltrimethoxysilane (AHAP3); *N*-(2-aminoethyl)-3-aminopropyltrimethoxysilane (AEAP3); (3-trimethoxysilylpropyl)diethylenetriamine (DET3); (aminoethylaminomethyl)phenethyltrimethoxysilane (AEMP3); [3-(methylamino)propyl]trimethoxysilane (MAP3); *N*-butylamino-propyltrimethoxysilane(n-BAP3); *t*-butylamino-propyltrimethoxysilane(*t*-BAP3); *N*-ethylaminoisobutyltrimethoxysilane(EAiB3); *N*-phenylamino-propyltrimethoxysilane (PAP3); and *N*-cyclohexylaminopropyltrimethoxysilane (chAP3).

**[0073]** In some embodiments, the aminoalkoxysilane has the formula:  $\text{NH} [\text{R}'-\text{Si}(\text{OR})_3]_2$ , wherein R is alkyl and R' is alkylene. In some embodiments, the aminoalkoxysilane can be selected from bis(3-triethoxysilylpropyl)amine, bis-[3-(trimethoxysilyl)propyl]amine and bis-[3-(trimethoxysilyl)propyl]ethylenediamine.

**[0074]** In some embodiments, as described herein above, the aminoalkoxysilane is

precharged for NO-release and the amino group is substituted by a diazeniumdiolate. Therefore, in some embodiments, the aminoalkoxysilane has the formula: R"-N(NONO<sup>-</sup>X<sup>+</sup>)-R'-Si(OR)<sub>3</sub>, wherein R is alkyl, R' is alkylene or aralkylene, R" is alkyl or alkylamine, and X<sup>+</sup> is a cation selected from the group consisting of Na<sup>+</sup>, K<sup>+</sup> and Li<sup>+</sup>.

**[0075]** In some embodiments of the invention, the co-condensed siloxane network further includes at least one crosslinkable functional moiety of formula (R<sub>1</sub>)<sub>x</sub>(R<sub>2</sub>)<sub>y</sub>SiR<sub>3</sub>, wherein R<sub>1</sub> and R<sub>2</sub> is each independently C<sub>1-5</sub> alkyl or C<sub>1-5</sub> alkoxy, X and Y is each independently 0, 1, 2, or 3, and X+Y equal to 3, and R<sub>3</sub> is a crosslinkable functional group. In a further embodiment, R<sub>1</sub> is C<sub>1-3</sub> alkoxy, and R<sub>2</sub> is methyl. In another embodiment, R<sub>3</sub> is selected from the group consisting of acrylo, alkoxy, epoxy, hydroxy, mercapto, amino, isocyano, carboxy, vinyl and urea. R<sub>3</sub> imparts an additional functionality to the silica which results in a multifunctional device. Yet, in another embodiment, the crosslinkable functional moiety is selected from the group consisting of methacryloxyethyltrimethoxysilane, methacryloxypropyltrimethoxysilane, methacryloxypropyltriethoxysilane, 3-acryloxypropyltrimethoxysilane, N-(3-methacryloxy-2-hydroxypropyl)-3-aminopropyltriethoxysilane, 5,6-epoxyhexyltriethoxysilane, 2-(3,4-epoxycyclohexyl)ethyl trimethoxysilane, 3-glycidoxypropyltrimethoxysilane, 3-aminopropyltrimethoxysilane, 3-aminopropyltriethoxysilane, 3-isocyanatopropyltriethoxysilane, 3-mercaptopropyltrimethoxysilane, mercaptopropyltriethoxysilane, 11-mercaptoundecyltrimethoxysilane, 2-cyanoethyltriethoxysilane, ureidopropyltriethoxysilane, ureidopropyltrimethoxysilane, vinylmethyldiethoxysilane, vinylmethyldimethoxysilane, vinyltriethoxysilane, vinyltrimethoxysilane, vinyltrisopropoxysilane and vinyltris(2-methoxyethoxy)silane. In some embodiments, R<sub>3</sub> may be used to cross-link the NO-donor modified silica with or within polymeric matrices.

**[0076]** The NO-releasing polysiloxane macromolecules may be present within and/or on the polymer matrix at any suitable concentration, but in some embodiments, the NO-releasing polysiloxane macromolecules are present within the polymer matrix at a concentration sufficient to increase the rate of wound healing, decrease inflammation and/or exert an antimicrobial effect. In particular embodiments, the concentration of the NO-releasing polysiloxane macromolecules may be in a range of about 0.1 to about 20 weight percent.

**[0077]** In some embodiments, the NO-releasing polysiloxane macromolecules may be uniformly distributed within the polymer matrix. Thus, in such embodiments, the concentration of NO-releasing polysiloxane macromolecules is substantially constant throughout the polymer matrix.

#### *Interaction between the Polymer Matrix and NO-releasing Polysiloxane Macromolecules*

**[0078]** Wound healing occurs in several different phases, and may take place over 0-12 (or more) months. Wound healing phases include:

1. (i) Clotting
2. (ii) Cell Proliferation
3. (iii) Granulation Tissue Formation
4. (iv) Epithelialization
5. (v) Neovascularization or angiogenesis
6. (vi) Wound Contraction
7. (vii) Matrix deposition including collagen synthesis
8. (viii) Tissue Remodeling, including scar formation and scar remodeling

**[0079]** The phase of wound healing plays a role in the selection of the NO-releasing polysiloxane macromolecules and the polymer matrix chosen. Nitric oxide may play a role in wound healing by a number of different mechanisms. First, extended exposure to low concentrations of nitric oxide may promote wound healing whereby nitric oxide acts as a signaling molecule in a number of wound healing cascades. Additionally, nitric oxide may also play a role in mitigating inflammation following injury. Modulation of inflammatory cytokines and cells of the inflammatory response via nitric oxide may significantly alter the wound healing phases described above. Additionally, wound complications and pain may be significantly reduced with topical administration of nitric oxide as an anti-inflammatory agent. Furthermore, nitric oxide may act as a broad spectrum antimicrobial agent, particularly at relatively high concentrations. The antimicrobial effects of nitric oxide are broad ranging and different wound types may be colonized with different wound pathogens (e.g., gram negative bacteria, gram positive bacteria, fungi, etc.). Additionally, different pathogens may be more sensitive to nitric oxide than other pathogens. In some embodiments, nitric oxide may act as an antimicrobial agent by directly killing planktonic bacteria and other organisms; directly killing biofilm embedded bacteria and other organisms; indirectly killing microorganisms through nitrosative/oxidative stress; increasing drug permeability across microbial membranes; and/or preventing recurrence of infection or biofilm formation.

**[0080]** Therefore, in some embodiments, the nitric oxide released from a particular wound dressing may provide a particular therapeutic action, such as act as a signaling molecule in a wound healing cascade, act as an anti-inflammatory agent and/or act as an antimicrobial agent. The desired therapeutic action may determine which NO-releasing polysiloxane macromolecules and polymer matrix are used in a particular wound dressing. For example, two particular classes of nitric oxide donors are diazeniumdiolates and nitrosothiols. Both of these nitric oxide donors have at least one mechanism for the release of nitric oxide. Diazeniumdiolate may be triggered to release nitric oxide by exposure to water or another proton source, and an O<sup>2</sup>-protected diazeniumdiolate may be triggered to release nitric oxide by exposure to light, enzymatic action and/or pH adjustment. Nitrosothiols may be triggered to release nitric oxide via thermal and radiative processes, and/or via interaction with copper and other thiols (e.g., glutathione). Therefore, the mechanism of release of nitric oxide from the NO-releasing polysiloxane macromolecules may affect which polymer matrix is chosen.

**[0081]** Specifically, because different NO-releasing polysiloxane macromolecules may release nitric oxide by different mechanisms, the polymer matrix chosen should complement the particular NO-releasing macromolecule employed. Several properties of the polymer matrix may be tailored based on the NO-releasing polysiloxane macromolecules used and the desired therapeutic action of the wound dressing. Such properties include:

**(i) Moisture Uptake/Retention**

**[0082]** The rate of moisture uptake may be tunable to meet the requirements of the NO-release kinetics of the macromolecule in order to achieve the desired therapeutic action of the wound dressing. The equilibrium moisture retention can vary from 5 percent for certain aliphatic polymers to over 2000 percent for hydrogels and superabsorbent polymers. Thus, in some embodiments, the polymer matrix has a low equilibrium moisture retention in a range of 0 to 10 percent. In some embodiments, the polymer matrix has a moderate equilibrium moisture retention in a range of 10 to 100 percent. Further, in some embodiments, the polymer matrix has a high equilibrium moisture retention of 100 percent or higher.

**(ii) Moisture Vapor Transfer Rate (MVTR)**

**[0083]** The MVTR may be tunable in breathable polymer films to match the requirements of a water reactive NO-releasing polysiloxane macromolecules in a thin film yet still maintain adequate MVTR for the desired wound or injury area. Wound dressings that maintain a moist wound bed are termed as occlusive. An optimum MVTR maintains a moist wound environment which activates debriding enzymes and growth factors that promote wound healing. Occlusive dressings also act as a barrier towards exogenous microbes, thereby preventing infection. Occlusive dressings are characterized by an MVTR of less than 35 g water/m<sup>2</sup>/h.

**(iii) Ability to swell**

**[0084]** The ability of the wound dressing to swell without dissolution upon contact with wound moisture is beneficial in highly exudating wounds. The wound dressing serves to imbibe excess moisture that may otherwise cause wound maceration and foul odor.

**(iv) Surface Energy**

**[0085]** Hydrophobic wound dressings are characterized by low surface energy whereas charged and/or hydrophilic wound dressings have a high surface energy. Low surface energy is desirable to allow easy removal of the dressing without damaging the wound bed.

**(v) Oxygen Permeability**

**[0086]** Adequate oxygen level facilitates neovascularization, aids in collagen synthesis, and may prevent or minimize microbial infection of the wound. Due to damaged vasculature in wounds, there may be a low oxygen tension in the wound bed, leading to hypoxia and anaerobic metabolism that can delay the healing process. Wound dressings may be oxygen permeable so that the wound receives adequate topical oxygen for healing.

**(vi) Nitric Oxide Permeability**

**[0087]** The polymer matrix of the wound dressing may have adequate permeability towards nitric oxide such that the nitric oxide generated by the NO-releasing polysiloxane macromolecules is available to the wound bed at a desired therapeutic rate. Hydrophilic materials typically have a lower NO permeability towards nitric oxide as compared to hydrophobic materials. The NO permeability of the dressing may be matched to the release kinetics of the NO-releasing polysiloxane macromolecules and the rate of water uptake by the polymer, in order to provide for optimal release of NO from the dressing.

**(vii) Biodegradability/Bioabsorbability**

**[0088]** Biodegradability refers to the property of the wound dressing to break down into smaller molecular weight components under physiological conditions. Bioresorbability refers to the property by which the wound dressing can break down into smaller molecular weight segments and the segments are completely taken into the body without any biological reaction. This property is desirable if the dressing is to be used over a long-term for cavity-type wounds.

**(viii) Tensile strength**

**[0089]** Tensile strength is the ability of the wound dressing to withstand breakage upon elongation in any direction. The wound dressing material needs to have adequate tensile strength in order to withstand stresses occurring as a result of normal patient wear.

**(ix) Biocompatibility**

**[0090]** The polymer matrix of the wound dressing may be biocompatible, non-toxic, and non-irritable.

**(x) Ionic Character**

**[0091]** The ionic character of the dressing may affect the dressing surface energy and biocompatibility. The ionic character of the dressing can be quantified by measurement of the zeta potential of the wound dressing material under physiological conditions. In some embodiments, the zeta potential of surfaces may be between -30 mV and +20 mV, and in some embodiments, between -10 mV and +10 mV, and in some embodiments, approximately zero. Surfaces with highly negative (< -30 mV) or highly positive (> + 20 mV) zeta potential may be undesirable as they may have an anti- or pro-coagulant effect on the wound and may increase dressing surface energy.

**(xi) Transparency**

**[0092]** The ability of the wound dressing material to allow passage of visible light may allow for visual monitoring of the wound healing process. As used herein, a wound dressing or polymer matrix is transparent if it has an optical transparency value of 80 percent or more transmittance as measured via solid state spectrophotometry.

**[0093]** As moisture facilitates nitric oxide release from diazeniumdiolate-functionalized polysiloxane macromolecules, a wound dressing that includes diazeniumdiolate-modified polysiloxane macromolecules within and/or on a hydrophilic polymer will allow for the release of nitric oxide to a wound at a greater rate than would a hydrophobic polymer. Thus, the level of nitric oxide desired to be applied to the wound can be tailored by increasing or decreasing the hydrophilicity of the polymer. Therefore, by combining a hydrophilic polymer with a diazeniumdiolate-modified macromolecule, a concentrated dose of nitric oxide may be provided to a wound, and by combining a diazeniumdiolate-modified macromolecule with a relatively hydrophobic polymer, an "extended release" dose of nitric oxide may be provided to the wound. An extended release formulation may allow for release of nitric oxide over a predetermined time, such as 0 -7 days. Additionally, as thermal and/or light energy may facilitate nitrosothiol modified polysiloxane macromolecule decomposition, the polymer matrix and/or additional layers above the polymer matrix including the nitrosothiol-modified polysiloxane macromolecules may be transparent so that light may facilitate nitric oxide release from the nitrosothiol. The transparency may be modified to control the level of nitric oxide release.

**[0094]** Thus, the polymer matrix and the NO-releasing polysiloxane macromolecules may be selected based on at least one property of the polymer matrix and at least one property of the NO-releasing polysiloxane macromolecules such that the interaction of the properties of the polymer matrix and the NO-releasing polysiloxane macromolecules provides a predetermined characteristic to the wound dressing. In some embodiments of the invention, the at least one property of the polymer matrix may include moisture uptake/retention, moisture vapor transfer

rate (MVTR), surface energy, oxygen permeability, nitric oxide permeability, pore size biodegradability/bioabsorbability, tensile strength, biocompatibility, ionic character and/or transparency. In some embodiments of the invention, the at least one property of the NO-releasing polysiloxane macromolecules may include the nitric oxide release mechanism (e.g., water, heat, light, enzymatic, pH, and the like), total quantity of nitric oxide stored in moles NO/mg silica, the hydrophobicity/hydrophilicity of the co-condensed silica, and the biodegradability/bioresorbability of the macromolecular framework. The predetermined characteristic may be the ability of the nitric oxide in the wound dressing to signal one or more wound healing cascades, to act as an anti-inflammatory agent and/or to act as an antimicrobial agent.

**[0095]** As used herein, the term "interaction of the properties" refers to the ability of particular properties of the polymer matrix and particular properties to the NO-releasing polysiloxane macromolecules to combine to produce a wound dressing that has a predetermined characteristic, as defined herein. For example, the particular hydrophilicity of the polymer matrix may interact with a particular concentration of water reactive NO-releasing polysiloxane macromolecules to produce the desired release rate of nitric oxide from the polymer matrix.

**[0096]** An exemplary calculation of the reaction rate of the nitric oxide release as a function of the rate of a dressing's water uptake, is shown below. In this calculation, the absorption of water over time in the wound dressing is modeled. It is assumed that the release of NO from the NO-releasing polysiloxane macromolecules commences immediately upon contact with the diffused water.

**[0097]** Referring to FIG. 1, for a thin film **100** (of thickness **2a**) of a polymer matrix including uniformly dispersed NO-releasing polysiloxane macromolecules at a percent loading concentration of G (100 x g NO-releasing silica/g polymer), when the film is immersed in water, water diffuses into the film at a rate given by the unsteady state diffusion expression:

$$\frac{C(t)}{C_\infty} = \left( \frac{8}{\pi^2} \right) e^{-\frac{Dt^2}{4a^2}}$$

wherein D = diffusion coefficient of water in the polymer matrix, C(t) = concentration of water at time t, and C<sub>∞</sub> is the concentration of water at equilibrium, which is the surrounding concentration (55 M). In a given time, t, the water diffuses only up to a certain thickness into the polymer film, thereby 'activating' the NO-releasing polysiloxane macromolecules up to that depth, z(t). The concentration of water in the film is the concentration of water only up to this depth and is equal to the mass of water diffused up to that depth, divided by volume of the penetration, thus

$$C(t) = \frac{m_{water}(t)}{\Lambda z(t) \epsilon}$$

where • is the porosity of the polymer film, which is considered because the water will only penetrate into the interconnecting pores between the polymer chains. The mass of water in the film at given time (t) can be calculated by measuring the rate of water uptake (U) by the bulk polymer, which can be determined experimentally, and is defined as:

$$U(t) = \frac{100 \times m_{water}}{M}$$

where  $M_{poly}$  = mass of the polymer film. Thus substituting this expression for the mass of water, in the expression for depth of penetration as defined above,

$$z(t) = \frac{0.01U(t)M_{poly}}{A\epsilon C_\infty}$$

$$z(t) = \frac{0.01U(t)M_{poly}}{A\epsilon C_\infty} \left( \frac{\pi^2}{8} \right) e^{\frac{Dt\pi^2}{4a^2}}$$

If the intrinsic rate of NO release of the NO-releasing polysiloxane macromolecules is known as a function of time,  $f(t)$ , the rate of NO release from the silica in the polymer that have been 'activated' at time  $t$  is given by:

$$NO(t) = m_{NO}(t) \times f(t)$$

Where  $[NO(t)]$  = micromoles of NO released at time  $t$ ,  $m_{NO}$  = mass of NO-releasing silica activated at time  $(t)$ . By definition the NO-releasing co-condensed silica loading in the polymer wound dressing is expressed as,

$$G = \frac{100 \times m_{NO}}{M_{poly}}$$

where  $M_{poly}$  = mass of the entire polymer film, of which only  $M_{poly}(t)$  has been 'wet' by the water at time  $(t)$ . Therefore,

$$m_{NO}(t) = 0.01GM_{poly}(t)$$

$$m_{NO}(t) = 0.01GA\rho_{poly}z(t)$$

and hence,

$$NO(t) = 0.01GA\rho_{poly} \times \frac{0.01U(t)M_{poly}}{A\epsilon C_\infty} \left( \frac{\pi^2}{8} \right) e^{\frac{Dt\pi^2}{4a^2}}$$

Therefore, the overall rate of NO release from the polymer is given by

$$NO(t) = 10^{-4} \frac{GU(t)}{\epsilon C_\infty} \rho_{poly} M_{poly} \left( \frac{\pi^2}{8} \right) f(t) e^{\frac{Dt\pi^2}{4a^2}}$$

**[0098]** In some embodiments of the invention, the storage of nitric oxide in the dressing is in a range of 0.1 pmol NO cm<sup>-2</sup> to 100 pmol NO cm<sup>-2</sup>. In some embodiments, the storage of nitric oxide release in the dressing is in a range of 10 pmol NO cm<sup>-2</sup> to 1 nmol NO cm<sup>-2</sup>. In some embodiments, the storage of nitric oxide in the dressing is in a range of 1 nmol NO cm<sup>-2</sup> to 10 μmol NO cm<sup>-2</sup>. Total nitric oxide storage ( $t[NO]$ ) and surface flux can be measured in real-time via the chemiluminescent detection of nitric oxide reviewed by Hetrick et al. (Hetrick et al. Analytical Chemistry of Nitric Oxide, Annu. Rev. Anal. Chem. 2009, 2, 409-433). Additional kinetic parameters for nitric oxide release that can be measured during this technique are the time to release the maximum flux of NO ( $t_m$ ), quantity of NO at the maximum flux ( $[NO]_m$ ), half-life of nitric oxide release ( $t_{1/2}$ ), and nitric oxide release duration ( $t_d$ ).

**[0099]** In some embodiments of the invention, the instantaneous flux of nitric oxide release

from the hydrated dressing surface is in a range of 0.1 pmol NO cm<sup>-2</sup> s<sup>-1</sup> to 100 pmol NO cm<sup>-2</sup> s<sup>-1</sup> and constitutes a slow initial rate of release. In some embodiments, the instantaneous flux of nitric oxide release from the hydrated dressing surface is in a range of 100 pmol NO cm<sup>-2</sup> s<sup>-1</sup> to 1000 pmol NO cm<sup>-2</sup> s<sup>-1</sup> and constitutes an intermediate rate of release. In some embodiments, the instantaneous flux of nitric oxide from the hydrated dressing surface is in a range of 1 nmol NO cm<sup>-2</sup> s<sup>-1</sup> to 10 µmol NO cm<sup>-2</sup> s<sup>-1</sup> and constitutes a rapid burst or fast NO-release kinetics.

### ***Stability***

**[0100]** According to some embodiments of the invention, the wound dressings can stably store the NO so that NO is not released prior to its intended therapeutic use. In some embodiments, 95 percent or more of the original NO loading is retained after one week at 25 °C. Furthermore, in some embodiments, 85 percent of the NO loading is retained up to 2 years at 25 °C.

**[0101]** In some embodiments of the invention, the wound dressings form a stable matrix whereby the leaching of silica particles is minimized. The thermodynamics of particulate leaching from polymeric matrices has not been a challenge previously encountered in the prior art. Leaching of siloxane based macromolecules can be determined via static light scattering or elemental analysis for Si in the soak solutions. In some embodiments, greater than 98 percent of the embedded NO-releasing polysiloxane macromolecules is retained following incubation under physiological conditions (pH = 7.4, 37 °C, phosphate buffered saline) for 48 hours. In other embodiments, greater than 95 percent of the embedded NO-releasing polysiloxane macromolecules is retained following incubation under physiological conditions (pH = 7.4, 37 °C, phosphate buffered saline) for greater than 30 days.

### ***Example Embodiments***

**[0102]** In some embodiments, the NO-releasing polysiloxane macromolecule is Nitricil™ (Novan, Inc.), which is a diazeniumdiolate-modified precipitated silica.

**[0103]** In some embodiments, the polymer matrix is an aliphatic polyether polyurethane that absorbs water in an amount of about 6 percent to about 100 percent of its dry weight. In some embodiments, the aliphatic polyether polyurethane absorbs water in an amount of about 10 to 60 percent of its dry weight, and in some embodiments, 10 to 20 percent of its dry weight.

**[0104]** In some embodiments, the polymer matrix is a superabsorbent polymer that absorbs water in an amount of at least 100 percent and ranging up to 5000 percent of its dry weight. In some embodiments, the polymer matrix includes Tecophilic® Aliphatic thermoplastic

polyurethane from Lubrizol, Inc.

### **Additives**

**[0105]** In addition to the NO-releasing polysiloxane macromolecules, other additives may be present within and/or on the polymer matrix. Such additives may alter the properties of the polymeric matrix. For example, in some embodiments, the wound dressing may further include a water-soluble porogen. The water-soluble porogen is an additive that may facilitate water uptake and diffusion in the polymer matrix. Any suitable porogen may be used, but in some embodiments, the porogen may include sodium chloride, sucrose, glucose, lactose, sorbitol, xylitol, polyethylene glycol, polyvinylpyrrolidone, polyvinyl alcohol and mixtures thereof.

**[0106]** The properties of the polymer matrix and water uptake may also affect the release of nitric oxide, and so additives that affect the properties of the polymer matrix and/or water uptake may in turn affect the rate of release of nitric oxide from the NO-releasing polysiloxane macromolecules.

**[0107]** Additives may also be included in the polymer foam that directly affect the release of nitric oxide from the NO-releasing macromolecules. For example, in some embodiments, basic or other anionic species may be used to buffer the pH of the polymer foam to slow diazeniumdiolate decomposition and resulting nitric oxide release. In other embodiments, chelating agents may be used to scavenge metal ions like  $Fe^{2+}$ ,  $Cu^{2+}$  and  $Cu^+$  to preserve nitrosothiol NO donor stability and prevent rapid nitric oxide release. In some embodiments, additives may be added to enhance NO donor decomposition given the inherently slow NO-release kinetics of the NO-releasing polysiloxane macromolecule. For example, acidic or carboxylic acid functionalized additives may be added to the foam to create a low internal foam pH upon hydration and accelerate the decomposition of N-diazeniumdiolate donors. In another embodiment, cysteine or glutathione may be impregnated into the foam matrix to facilitate transnitrosation and subsequent thiol mediated decomposition of nitrosothiol containing macromolecules.

**[0108]** In addition, other additives useful for foam formation and processing may be included. For example, surface-active agents may be added to enhance mixing, act as mold-release agents and/or to influence the final cellular structure of the foam. Furthermore, blowing agents, and byproducts therefrom, may also be present within the polymer foam. Blowing agents are described in further detail below. Additives that may be useful in forming foams include surface-active agents to enhance mixing as well as to influence the final foam structure, and mold-release agents. Exemplary surface active agents may be found in U.S. Patent No. 6,316,662, the disclosure of which is incorporated herein in its entirety.

**[0109]** Additives may be present in the polymer matrix that may act to provide additional therapeutic effects to the wound dressing, either acting synergistically or separately from the

NO-releasing polysiloxane macromolecules. For example, in some embodiments, the wound dressings may also include at least one therapeutic agent such as antimicrobial agents, anti-inflammatory agents, analgesic agents, anesthetic agents, antihistamine agents, antiseptic agents, immunosuppressants, antihemorrhagic agents, vasodilators, wound healing agents, anti-biofilm agents and mixtures thereof.

**[0110]** Examples of antimicrobial agents include penicillins and related drugs, carbapenems, cephalosporins and related drugs, erythromycin, aminoglycosides, bacitracin, gramicidin, mupirocin, chloramphenicol, thiamphenicol, fusidate sodium, lincomycin, clindamycin, macrolides, novobiocin, polymyxins, rifamycins, spectinomycin, tetracyclines, vanomycin, teicoplanin, streptogramins, anti-folate agents including sulfonamides, trimethoprim and its combinations and pyrimethamine, synthetic antibacterials including nitrofurans, methenamine mandelate and methenamine hippurate, nitroimidazoles, quinolones, fluoroquinolones, isoniazid, ethambutol, pyrazinamide, para-aminosalicylic acid (PAS), cycloserine, capreomycin, ethionamide, prothionamide, thiacetazone, viomycin, evemomycin, glycopeptide, glycycline, ketolides, oxazolidinone; imipenem, amikacin, netilmicin, fosfomycin, gentamycin, ceftriaxone, Ziracin, Linezolid, Synercid, Aztreonam, and Metronidazole, Epioprim, Sanfetrinem sodium, Biapenem, Dynemicin, Cefluprenam, Cefoselis, Sanfetrinem celexetil, Cefpirome, Mersacidin, Rifaxin, Kosan, Lenapenem, Veneprim, Sulopenem, ritipenam acoyl, Cyclothialidine, micacocidin A, carumonam, Cefozopran and Cefetamet pivoxil. Examples of antihistamine agents include diphenhydramine hydrochloride, diphenhydramine salicylate, diphenhydramine, chlorpheniramine hydrochloride, chlorpheniramine maleate isothipendyl hydrochloride, tripeleamine hydrochloride, promethazine hydrochloride, methdilazine hydrochloride, and the like. Examples of local anesthetic agents include dibucaine hydrochloride, dibucaine, lidocaine hydrochloride, lidocaine, benzocaine, p-butylaminobenzoic acid 2-(diethylamino) ethyl ester hydrochloride, procaine hydrochloride, tetracaine, tetracaine hydrochloride, chlorprocaine hydrochloride, oxyprocaine hydrochloride, mepivacaine, cocaine hydrochloride, piperocaine hydrochloride, dyclonine and dyclonine hydrochloride.

**[0111]** Examples of antiseptic agents include alcohols, quaternary ammonium compounds, boric acid, chlorhexidine and chlorhexidine derivatives, iodine, phenols, terpenes, bactericides, disinfectants including thimerosal, phenol, thymol, benzalkonium chloride, benzethonium chloride, chlorhexidine, povidone iodine, cetylpyridinium chloride, eugenol and trimethylammonium bromide.

**[0112]** Examples of anti-inflammatory agents include nonsteroidal anti-inflammatory agents (NSAIDs); propionic acid derivatives such as ibuprofen and naproxen; acetic acid derivatives such as indomethacin; enolic acid derivatives such as meloxicam, acetaminophen; methyl salicylate; monoglycol salicylate; aspirin; mefenamic acid; flufenamic acid; indomethacin; diclofenac; alclofenac; diclofenac sodium; ibuprofen; ketoprofen; naproxen; pranoprofen; fenoprofen; sulindac; fenclofenac; clidanac; flurbiprofen; fentiazac; bufexamac; piroxicam; phenylbutazone; oxyphenbutazone; clofezone; pentazocine; mepirizole; tiaramide hydrochloride; steroids such as clobetasol propionate, bethamethasone dipropionate, halbetasol propionate, diflorasone diacetate, fluocinonide, halcinonide, amcinonide,

desoximetasone, triamcinolone acetonide, mometasone furoate, fluticasone propionate, betamethasone dipropionate, triamcinolone acetonide, fluticasone propionate, desonide, fluocinolone acetonide, hydrocortisone valerate, prednicarbate, triamcinolone acetonide, fluocinolone acetonide, hydrocortisone and others known in the art, prednisolone, dexamethasone, fluocinolone acetonide, hydrocortisone acetate, prednisolone acetate, methylprednisolone, dexamethasone acetate, betamethasone, betamethasone valerate, flumetasone, fluorometholone, beclomethasone dipropionate, fluocinonide, topical corticosteroids, and may be one of the lower potency corticosteroids such as hydrocortisone, hydrocortisone-21-monoesters (e.g., hydrocortisone-21-acetate, hydrocortisone-21-butyrate, hydrocortisone-21-propionate, hydrocortisone-21-valerate, etc.), hydrocortisone-17,21-diesters (e.g., hydrocortisone-17,21-diacetate, hydrocortisone-17-acetate-21-butyrate, hydrocortisone-17,21-dibutyrate, etc.), alclometasone, dexamethasone, flumethasone, prednisolone, or methylprednisolone, or may be a higher potency corticosteroid such as clobetasol propionate, betamethasone benzoate, betamethasone dipropionate, diflorasone diacetate, fluocinonide, mometasone furoate, triamcinolone acetonide.

**[0113]** Examples of analgesic agents include alfentanil, benzocaine, buprenorphine, butorphanol, butamben, capsaicin, clonidine, codeine, dibucaine, enkephalin, fentanyl, hydrocodone, hydromorphone, indomethacin, lidocaine, levorphanol, meperidine, methadone, morphine, nicomorphine, opium, oxybuprocaine, oxycodone, oxymorphone, pentazocine, pramoxine, proparacaine, propoxyphene, proxymetacaine, sufentanil, tetracaine and tramadol.

**[0114]** Examples of anesthetic agents include alcohols such as phenol; benzyl benzoate; calamine; chloroxylenol; dyclonine; ketamine; menthol; pramoxine; resorcinol; troclosan; procaine drugs such as benzocaine, bupivacaine, chloroprocaine; cinchocaine; cocaine; dexivacaine; diamocaine; dibucaine; etidocaine; hexylcaine; levobupivacaine; lidocaine; mepivacaine; oxethazaine; prilocaine; procaine; proparacaine; propoxyacaine; pyrrocaaine; risocaine; rodocaine; ropivacaine; tetracaine; and derivatives, such as pharmaceutically acceptable salts and esters including bupivacaine HCl, chloroprocaine HCl, diamocaine cyclamate, dibucaine HCl, dyclonine HCl, etidocaine HCl, levobupivacaine HCl, lidocaine HCl, mepivacaine HCl, pramoxine HCl, prilocaine HCl, procaine HCl, proparacaine HCl, propoxyacaine HCl, ropivacaine HCl, and tetracaine HCl.

**[0115]** Examples of antihemorrhagic agents include thrombin, phytonadione, protamine sulfate, aminocaproic acid, tranexamic acid, carbazochrome, carbaxochrome sodium sulfanate, rutin and hesperidin.

### ***Wound Dressing Devices***

**[0116]** Any suitable configuration of wound dressing device may be used. Referring to **FIG. 2A**, in some embodiments, the wound dressing **101** is a single layer that includes a polymer matrix **103** and NO-releasing polysiloxane macromolecules **105** therein and/or thereon. Referring to **FIG. 2B**, in some embodiments, the single layer wound dressing may include a medical-grade

adhesive **107** on the surface of the wound dressing that contacts the wound bed. Referring to **FIGS. 3-5**, in some embodiments, the wound dressing may include two or more layers. For example, referring to **FIG 3A**, in some embodiments, the wound dressing **101** has two layers, a first layer **109** that includes a polymer matrix **103** and NO-releasing polysiloxane macromolecules **105** within and/or on the polymer matrix **103**; and a second layer **111** on the first layer **109**. Furthermore, referring to **FIG. 3B**, in some embodiments, a medical-grade adhesive **107** may be on the surface of the first layer **109** that contacts the wound bed. Referring to **FIG. 4A**, in some embodiments, the polymer matrix **103** and NO-releasing polysiloxane macromolecules **105** within and/or on the polymer matrix **103** is included in the second layer **111**, which may provide an anti-microbial barrier to the wound dressing **101**. Thus, the first layer **109** may or may not include a polymer matrix **103** and NO-releasing polysiloxane macromolecules **105** within and/or on the polymer matrix **103**. Regardless of whether the first layer **109** includes a polymer matrix **103** and NO-releasing polysiloxane macromolecules **105** within and/or on the polymer matrix **103**, a medical-grade adhesive **107** may be on the surface of the first layer **109** that contacts the wound bed. Additionally, in some embodiments, the first layer **109** or second layer **111** may be substantially free of NO-releasing polysiloxane macromolecules **105**.

**[0117]** Referring to **FIGS. 5A** and **5B**, as another example, in some embodiments, the wound dressing **101** has three layers, a first layer **109** that contacts the wound bed, a second layer **111** on the first layer **109**, and a third layer **113** on the second layer **111**. A medical-grade adhesive **107** may be on the surface of the first layer **109** (**FIG. 5B**). The polymer matrix **103** and NO-releasing polysiloxane macromolecules **105** within and/or on the polymer matrix **103** may be present in the first layer **109**, the second layer **111** and/or the third layer **113**. In some embodiments, at least one of the first layer **109**, the second layer **111** and the third layer **113** is substantially free of NO-releasing polysiloxane macromolecules **105**. However, as shown in **FIG. 5**, in some embodiments, the polymer matrix **103** and NO-releasing polysiloxane macromolecules **105** within and/or on the polymer matrix **103** are present only in the second layer **111**. The first layer **109** may act as a wound contact layer that prevents NO-releasing polysiloxane macromolecules **105** from leaching into the wound and/or provides a hydrophobic or non-stick wound contact surface. The third layer **113** may act to contain nitric oxide within the wound dressing **101** and may control the MVTR, oxygen diffusion and/or microbial penetration into the wound dressing **101**.

**[0118]** Referring to **FIG. 6A**, in some embodiments, at least one layer of the wound dressing **101** includes a perforated layer **115**. A "perforated layer" **115** includes at least one hole **117** defined within polymer matrix **103**. In some embodiments, the polymer matrix **103** includes an array of holes **117** defined therein. The holes **117** in the polymer matrix **103** may have any suitable width **119**, but in some embodiments, the holes **117** have a width **119** in a range of about 200 to about 5000 microns. The term "width" **119** refers to the largest distance across the hole. For a cylindrical hole **117**, the width **119** is the diameter. The width **119** of the holes **117** may be chosen based on a variety of parameters, such as moisture of the wound, polymer matrix, thickness of the layer and/or dressing, whether adhesive is used and/or whether it is being used with negative pressure wound therapy (NPWT). In some embodiments, the NO-

releasing polysiloxane macromolecules **105** may be present in the polymer matrix **103** of the perforated layer **115**. Such perforated layers **115** may be used with other perforated layers **115** and/or with non-perforated layers, in any suitable combination. Additionally, the perforated layers **115** may not include NO-releasing polysiloxane macromolecules **105** and/or may be used in combination with other layers that include a polymer matrix **103** and NO-releasing polysiloxane macromolecules **105** within and/or on the polymer matrix **103**. Furthermore, as shown in **FIG. 6B**, a medical-grade adhesive **107** may be on the surface of the perforated layer **115** that contacts the wound bed. The use of a perforated layer **115** may allow for moisture from the wound to interact with NO-releasing silica in a layer on the perforated layer **115**, may increase gas (e.g., nitric oxide) diffusion to the wound bed, and provide a suitable material for use with NPWT.

**[0119]** The perforated layer **115** may be formed by any suitable method. However, in some embodiments, the perforated layer **115** is formed by using a mold, or by pressing an object into the polymer matrix **103** to form at least one hole **117**, wherein the hole edges may also be melted and fused depending on the nature of the polymer matrix **103**. Additionally, in some embodiments, the holes **117** of the perforated layers **115** may be formed by curing the polymer matrix **103** in a mold, e.g., in an anhydrous and/or low temperature process, and then peeled out or packaged in individual perforated trays.

**[0120]** According to some embodiments of the invention, additional therapeutic agents, such as those described herein, may be present in any of the layers of the wound dressing. As an example, in some embodiments, a layer that is substantially free of NO-releasing polysiloxane macromolecules may include at least one therapeutic agent. As an additional example, a layer that includes NO-releasing polysiloxane macromolecules may also include at least one additional therapeutic agent.

**[0121]** In some embodiments, the wound dressing may further include a polymer backing layer that contacts the polymer matrix or a polymer layer on the polymer matrix. In some embodiments, the wound dressing is an island wound dressing, and the polymer backing layer, and optionally at least a portion of the polymer matrix that contacts the wound bed, may include a medical grade adhesive thereon. For example, the wound dressing may include a polymer backing layer and a polymer matrix layer including a polymer matrix having NO-releasing polysiloxane macromolecules therein or thereon, wherein the polymer matrix layer is attached to a portion of the polymer backing layer, and wherein at least a portion of the polymer backing layer that is facing but not attached to the polymer matrix layer is coated with a medical grade adhesive. Such wound dressings may also include additional layers, such as a wound contact layer, wherein the wound contact layer is on the face of the polymer matrix layer that is not attached to the polymer backing layer.

**[0122]** Each layer of wound dressing according to embodiments of the invention may have any suitable thickness. However, in some embodiments, one or more layers of the wound dressing may have a thickness in a range of about 10 to about 5000 microns. In some embodiments of the invention, at least one layer of the wound dressing may be substantially transparent.

Further, in some embodiments, the wound dressing as a whole may be substantially transparent. The term "substantially transparent" refers to a material that has a percent transmittance of 80 percent or more, as determined using a solid state spectrophotometer. Additionally, as described above, in some embodiments, at least one layer of the wound dressing has a medical-grade adhesive thereon. For example, the surface of the wound dressing that contacts the wound may have a medical-grade adhesive thereon.

**[0123]** Examples of medical grade adhesives that can be safely used on skin are acrylate-based adhesives, such as 2-ethylhexyl acrylate, isoctyl acrylate or n-butyl acrylate copolymerized with polar functional monomers such as acrylic acid, methacrylic acid, vinyl acetate, methyl acrylate, N-vinylcaprolactam, or hydroxyethyl methacrylate. Additional examples include octylcyanoacrylate, AcrySure™ adhesives (MACtac), adhesives based on silk protein, silicone gel based adhesives (Silbione® by Bluestar Silicones) and polyurethane based adhesive blends.

### ***Wound Dressing Kits***

**[0124]** As described above, wound healing may be effected through prolonged low concentrations of nitric oxide administration whereby nitric oxide acts as a signaling molecule in a number of wound healing cascades. In some embodiments, the instantaneous flux of nitric oxide release from hydrated dressing surface necessary to promote wound healing may be in the range of  $0.5 \text{ pmol NO cm}^{-2} \text{ s}^{-1}$  to  $20 \text{ pmol NO cm}^{-2} \text{ s}^{-1}$  upon initial application to the patient and constitutes a slow rate of release. An intermediate NO-releasing wound dressing may mitigate the inflammatory phase immediately following injury, following debridement of a chronic wound, in stalled wounds, or in infected wounds. In the inflammatory phase, the flux of nitric oxide released from the hydrated dressing surface is in a range of  $20 \text{ pmol NO cm}^{-2} \text{ s}^{-1}$  to  $1000 \text{ pmol NO cm}^{-2} \text{ s}^{-1}$  upon initial application to the patient and constitutes an intermediate rate of release. High levels of NO-released from a third matrix/ NO-releasing polysiloxane macromolecule composition may be necessary to effect antimicrobial activity, using the rapid burst of nitric oxide to kill microorganisms through oxidative/nitrosative intermediates. In these embodiments, the flux of nitric oxide released from the hydrated dressing surface is in a range of  $1 \text{ nmol NO cm}^{-2} \text{ s}^{-1}$  to  $1 \mu\text{mol NO cm}^{-2} \text{ s}^{-1}$  upon initial application and may constitute the rapid burst of nitric oxide necessary to provide a one or more log reduction against a broad range of microorganisms.

**[0125]** Therefore, provided according to some embodiments of the invention are kits that include wound dressings directed to a course of therapy with three unique dressing types of compositions designed to target these three wound processes. For a particular wound, a regimen may be implemented for a specified number of days whereby the three unique dressings are administered in sequence or repeated at some frequency (e.g., to keep microbial burden low).

***Methods of Treating a Wound***

**[0126]** In some embodiments of the invention, provided are methods of treating a wound by applying a wound dressing according to an embodiment of the invention. Such methods may be used in combination with any other known methods of wound treatment, including the application of medicaments, such as those that have anti-inflammatory, pain-relieving, immunosuppressant, vasodilating, wound healing and/or anti-biofilm forming properties. For the methods used herein, additional therapeutic agents and methods may be used prior to, concurrently with or after application with a gel according to embodiments of the invention. Wound dressings according to embodiments of the invention may also be used in combination with other wound dressings known to those of skill in the art.

**[0127]** In some embodiments of the invention, the wound dressings provided herein may be used in conjunction with at least one agent that can disrupt biofilm macrostructure prior to or in conjunction with the application of the wound dressing. In some embodiments, the anti-biofilm agent may disrupt the extracellular matrix of the biofilm. Examples of anti-biofilm agents that may act in this manner include lactoferrin, periodate, xylitol, DNase, protease, and an enzyme that degrades extracellular polysaccharides. In some embodiments of the invention, the formulation of the anti-biofilm agent may be acidic to promote enzyme activity of the DNase (e.g., mammalian DNases such as DNase II) and the acidic conditions simultaneously may also enhance the rate NO release from diazeniumdiolate modified silica. In some embodiments, the protease may include at least one of proteinase K, trypsin, Pectinex Ultra SP (PUS) and pancreatin. In some embodiments, enzymes that degrade extracellular polysaccharides may include N-acetylglucosaminidases (e.g., dispersin B).

**[0128]** In some embodiments of the invention, the anti-biofilm agent may act by affecting the transcriptional, translational and/or post-translational regulation of quorum-sensing genes or gene products in the infecting organism(s). For example, the anti-biofilm agents may include at least one of hamamelitannin, cyclic di-GMP and sublethal concentrations of nitric oxide.

**[0129]** The anti-biofilm agents may also act by other mechanisms. For example, the anti-biofilm agent may cause the infecting organism to transition from a sessile state to a metabolically active state. As another example, the anti-biofilm agent may act by causing the infecting organism(s) to transition from a non-motile state to a motile phenotype.

**[0130]** In some embodiments of the invention, the wound dressings provided herein may be used in conjunction with a wound debridement procedure. For example, in some embodiments, wounds may first be treated with a debridement procedure; and then a wound dressing according to an embodiment of the invention may be applied to the debrided wound. The wound dressings according to embodiments of the invention may increase the rate of wound healing, decrease inflammation and/or exert an antimicrobial effect. The wound dressings according to embodiments of the invention may be used in conjunction with any

suitable debridement procedure. For example, the debridement procedure may be selective or nonselective.

**[0131]** In some embodiments, the debridement procedure may include at least one of surgical, enzymatic, autolytic, sharp, mechanical and biological processes. Any suitable surgical method may be used, but in some embodiments, the surgical method may involve a surgeon cutting away nonviable tissue in the wound. Any suitable enzymatic method may be used, but in some embodiments, the enzymatic method may involve the use of one or more proteases, their required cofactors, and optionally any enhancing agents, to digest the nonviable tissue in the wound. Exemplary proteases include trypsin, papain or other vegetable-derived proteases and collagenase. Any suitable autolytic method may be used, but in some embodiments, the autolytic method may involve maintaining a moist wound environment in order to promote the breakdown of nonviable tissue by enzymes that are naturally produced by the body. Any suitable mechanical method may be used, but in some embodiments, the mechanical methods may include wet-to-dry gauze, irrigation, pulsatile lavage, whirlpool therapy and/or low frequency ultrasound. Any suitable sharp method may be used, but in some embodiments, the sharp method may involve cutting away nonviable tissue by qualified clinical staff (e.g. RN or nurse practitioner). Any suitable biological method may be used, but in some embodiments, the biological method may involve the use of maggots, which selectively digest the nonviable tissue in the wound. These debridement methods may be used alone or in combination.

**[0132]** After the wound is debrided, a wound dressing according to an embodiment of the invention may be applied. Additional processes may be performed and therapeutic agents may be applied. For example, after wound debridement, an anti-biofilm agent may be applied to the wound prior to or in conjunction with the application of the wound dressing. Exemplary anti-biofilm agents include acetylsalicylic acid (aspirin), cyclic di-GMP, lactoferrin, gallium, selenium, as described above. Other compounds, such as hamamelitannin (witch hazel extract), arginine and c-di-GMP, may also be applied.

**[0133]** Also provided according to some embodiments of the invention are methods of using a wound dressing according to an embodiment of the invention in conjunction with negative pressure wound therapy (NPWT).

**[0134]** Subjects suitable to be treated with wound dressings or methods according to an embodiments of the invention include, but are not limited to, avian and mammalian subjects. Mammals of the present invention include, but are not limited to, canines, felines, bovines, caprines, equines, ovines, porcines, rodents (e.g. rats and mice), lagomorphs, primates, humans, and the like, and mammals *in utero*. Any mammalian subject in need of being treated according to the present invention is suitable. Human subjects are preferred. Human subjects of both genders and at any stage of development (i.e., neonate, infant, juvenile, adolescent, adult) can be treated according to the present invention.

**[0135]** Illustrative avians according to the present invention include chickens, ducks, turkeys, geese, quail, pheasant, ratites (e.g., ostrich) and domesticated birds (e.g., parrots and

canaries), and birds *in ovo*.

**[0136]** The invention can also be carried out on animal subjects, particularly mammalian subjects such as mice, rats, dogs, cats, livestock and horses for veterinary purposes, and for drug screening and drug development purposes.

### ***Methods of Forming Wound Dressings***

**[0137]** The wound dressings described herein may be formed by any suitable method. However, provided according to some embodiments of the invention are methods of forming wound dressings. In some embodiments, incorporation of NO-releasing polysiloxane macromolecules can be achieved through physically embedding the particles into polymer surfaces, via electrostatic association of particles onto polymeric surfaces, and/or by covalent attachment or cross-linking of particles onto reactive groups on the surface of a polymer, within the polymer and/or within cells of a foam. In some embodiments, methods of forming wound dressings include combining NO-releasing polysiloxane macromolecules and at least one monomer; and polymerizing the at least one monomer to form a polymer matrix comprising the NO-releasing polysiloxane macromolecules. The monomer may be polymerized by any suitable method, but in some embodiments, the monomer is polymerized by photocuring and/or moisture curing, with or without an initiator. In some embodiments, the monomer may be polymerized upon contact with the wound environment, e.g., via the moisture in the wound. In some embodiments, a single layer wound dressing may be formed by a method that includes solvent casting a solution of polymer and NO-releasing polysiloxane macromolecules.

**[0138]** In some embodiments, the polymerization occurs via liquid casting or molten polymer extrusion. In some embodiments, a liquid monomer, NO-releasing polysiloxane macromolecules and an initiator are deposited on a surface and polymerization proceeds upon activation of the initiator. Polymerizable groups can also be used to functionalize the exterior of the particles, whereupon, the particles can be co-polymerized into a polymer during the polymerization process.

**[0139]** In some embodiments of the invention, methods of forming the wound dressings include dispersing the NO-releasing polysiloxane macromolecules in a mixture of foam forming monomers; polymerizing the foam forming monomers to form a polymer; and then foaming the polymer.

**[0140]** In some embodiments, methods of forming wound dressings include reacting functional groups on the NO-releasing polysiloxane macromolecules with at least one foam forming monomer; polymerizing the at least one foam forming monomer to form a polymer including the NO-releasing polysiloxane macromolecules therein; and then foaming the polymer.

**[0141]** In some embodiments, polyurethane foam dressings may be prepared by the reaction of polyols with polyisocyanates added in stoichiometric excess, with other co-reactants added

as required. In conventional foam manufacture, a stoichiometric amount of water is added to the reactant mix. The water may react with the isocyanate groups to form CO<sub>2</sub> which bubbles through the polymerizing mass, creating a cellular structure of flexible foams.

**[0142]** For water reactive NO-releasing polysiloxane macromolecules, water may not be used in the preparation of NO-releasing foam dressings as water may activate the NO-releasing polysiloxane macromolecules, resulting in a premature release of NO and a decrease in the therapeutic value of the foam dressing.

**[0143]** Entirely non-aqueous foams may be synthesized by substituting or complementing the polyhydrols with amino alcohols or alkanolamines. Exemplary amino alcohols and alkanolamines may be found in U.S. Patent No. 5,859,285, the disclosure of which is incorporated herein in its entirety. The alkanolamines may chemically store CO<sub>2</sub> on their amine groups, and this CO<sub>2</sub> may be released by heating. The alkanolamines may be dissolved in a polar solvent, preferably a diol or a triol, and contacted with CO<sub>2</sub> to form carbamates. In some embodiments, the polar solvent may be the polyol itself that can be the soft segment in the foam dressing.

**[0144]** The carbamate solution may be used to react with polyisocyanate to form the polyurethane foams. The carbamates may act as catalysts in foam formation, thereby avoiding the necessity of using other catalysts.

**[0145]** While any suitable alkanolamines may be used to produce carbamates, in some embodiments, the carbamates may be produced by using the following alkanolamines: 2-(2-aminoethylamino)ethanol, (3-[(2-aminoethyl)amino]propanol), (2-[(3-aminopropyl)amino]ethanol), (1-[(2-aminoethyl)amino]-2-propanol), (2-[(3-aminopropyl)methylamino]ethanol, 1-[(2-amino-1-methylethyl)amino]-2-propanol, 2-[(2-amino-2-methylpropyl)amino]-2-methyl-1-propanol, 2-[(4-amino-3-methylbutyl)amino]-2-methyl-1-propanol, 17-amino-3,6,9,12,15-pentaazaheptadecan-1-ol and/or 3,7,12,16-tetraazaoctadecane-1,18-diol, in particular those based on 2-(2-aminoethylamino)ethanol as alkanolamine. The carbamate solution can be further blended with polyhydroxyl or polyamine containing compounds that have been pre-charged with NO and as a result, possess single or multiple NO-releasing functional group.

**[0146]** In addition to chemically storing the CO<sub>2</sub> blowing agent in the above manner, physical blowing agents may also be used in foam production. Examples of physical blowing agents include: hydrohalo-olefin (See U.S. Patent Application Publication No. 20090099272, the contents of which are incorporated herein by reference in their entirety); alkanes, such as 2-methylbutane, pentane, heptanes (See U.S. Patent No 5,194,325), and other inert, low-boiling compounds such as pentene and acetone. Carbon dioxide, including supercritical carbon dioxide, may be used as a physical blowing agent as well.

**[0147]** In some embodiments of the invention, provided are methods of forming multilayer

wound dressings that include combining one or more polymeric layers, wherein one or more polymer layers may include a polymer matrix and NO-releasing polysiloxane macromolecules therein or thereon. The combining of polymeric layers may be achieved by any suitable method, but in some embodiments, the polymer layers are laminated to each other. Exemplary laminating techniques include ultrasonic welding, annealing with anhydrous organic solvents and application of a pressure sensitive adhesive.

**[0148]** The present invention will now be described in more detail with reference to the following examples. However, these examples are given for the purpose of illustration and are not to be construed as limiting the scope of the invention.

### **EXAMPLES**

#### **EXAMPLE 1**

**[0149]** The water uptake for three hydrophilic polyurethanes thin film dressings soaked in phosphate buffered saline at physiological temperature and pH is shown in **FIG. 7**. Tecophilic® Aliphatic thermoplastic polyurethanes HP-60D-20 ("T20"), HP-60D-60 ("T60"), and HP93A-100 ("T100") from Lubrizol, Inc. gradually displayed an increase in weight percentage overtime.

#### **EXAMPLE 2**

**[0150]** The water uptake for Tecophilic® Aliphatic thermoplastic polyurethane HP-60D-20 ("T20") loaded with increasing weight percent of poly(ethylene glycol) 8000 MW as a porogen is shown in **FIG. 8**. The weight of the thin polymer films increases over time as the hydrophilicity of the polymer matrix is increased as a function of percent PEG loading.

#### **EXAMPLE 3**

**[0151]** The water uptake for Tecophilic® Hydrogel thermoplastic polyurethane TG-2000 solvent cast into polymer films thin film dressings and soaked in phosphate buffered saline at physiological temperature and pH is shown in **FIG. 9**. The weight of this superabsorbent polymer (SAP) rapidly increases upon exposure to moisture and swells to store water exceeding 2000 percent of its initial weight.

#### **EXAMPLE 4**

[0152] FIG. 10 illustrates the covalent storage of nitric oxide on the aminosilane N-methylaminopropyltrimethoxysilane as a diazeniumdiolate NO donor, followed by co-condensation with a backbone alkoxy silane, tetraethoxysilane, to form Nitricil™ composition 70. The Nitricil™ 70 was incorporated with several of the hydrophilic polyurethanes from the previous examples and tested for their antimicrobial activity against a gram negative bacterium, *P. aeruginosa*. A  $10^6$  inoculum of bacteria was deposited onto the surface of the NO-releasing wound dressings in an agar slurry and incubated for 24 h. The percent reduction of *P. aeruginosa* versus control polyurethane materials for each composition is shown in TABLE 1. The water uptake of the polymer and the corresponding NO-release kinetics from the Nitricil™ 70 directly affect the bactericidal activity.

TABLE 1

Composition	Polymer	Nitricil 70 % Loading (wt/wt)	% Reduction <i>P. aeruginosa</i> ATCC 15442
A	T20	2.5	31
B	T20	4	58
C	T20	8	>99.9999
D	T20	10	> 99
E	T20	14	>99.9999
F	T20	16	>99.9999
G	T20	20	>99.9999
H	T60	2.5	49
I	T60	10	>99.99
J	T100	10	98.7
K	T100	16	ND
L	TG2000	10	ND

## EXAMPLE 5

[0153] FIG. 11 depicts the chemiluminescent detection of NO release from Nitricil™ 70 silica particles free in solution, wound dressing Composition J, and wound dressing Composition D measured at physiological buffer, pH, and temperature. The flux of NO release from the dressing surfaces are reported as PPB/mg of Nitricil™ loaded. As an example of how the polymer matrix governs resulting NO release, the initial levels of NO release from Composition D are 20X lower than the Nitricil™ alone. Composition D also maintains a more consistent level of NO-release over the first 60 min in comparison to Composition J at the equivalent 10% Nitricil™ loading ratio.

## EXAMPLE 6

**[0154]** Upon application to the wound, the polyurethane material of the wound dressing comes in contact with moisture in the wound bed. The polyurethane has some affinity for moisture due to the presence of polyether soft-chain segments in its structure, which results in a finite amount of water being taken up by the dressing. This inward diffusion of moisture within the polymer matrix leads to an increase in distance between the polymer chains and is observed as swelling of the polymer. The increasing distance between the chains and the concentration gradient between the water in the polymer and the bulk water in the wound bed, allow greater space of movement for the embedded silica particles. As a result, the particles may diffuse out of the polymer, with the smaller particles having a greater propensity. This phenomenon manifests itself as particle leaching.

**[0155]** Wound dressings comprising NO-releasing silica particles were engineered to minimize leaching upon exposure to moisture in the wound bed. The dressing polymer composition and silica loading wt/wt both affect the cumulative amount leached. Light scattering is a commonly used technique to characterize particle suspensions, particularly to measure the size and polydispersity of micrometer and nanometer particle sizes. In static light scattering mode, the time-averaged intensity of light scattered by a particle suspension is measured and is highly dependent upon the particle size, its concentration, and molecular weight. Thus, for a dilute suspension of fairly monodisperse particles, the time averaged light intensity should be directly proportional to the particle concentration, and the static light scattering is said to occur in the Rayleigh mode. A plot of scattering intensity vs. particle concentration yields a straight line and provide an accurate method for determining unknown particle concentrations that leach into solution from wound dressing prototypes.

**[0156]** To measure the potential concentrations of NO-releasing silica that accumulate in solution following incubation under physiologically buffered solutions for 24 and 48 hr, the light scattering intensity of each unknown particle sample was measured and converted to its concentration using a calibration curve. Nitric oxide-releasing silica-loaded polyurethane dressings were cut into three 0.75" x 0.75" square samples. The samples were weighed and placed into polypropylene vials and 10 mL of filtered phosphate buffered saline (PBS, 10mM sodium dihydrogen phosphate, 137mM NaCl, 2.3mM KCl, pH 7.4) pre-warmed at 37 °C was added to each. The vials were then incubated in a water bath maintained at 37 °C. After 24 hours, each of the vials were agitated and an aliquot was removed, which was transferred to a polystyrene cuvette. The static light scattering intensity of this aliquot was determined against filtered PBS as blank. The silica concentration of the leachate was then determined using the calibration curve to convert the obtained kcps value to mg/ml, and the obtained mg/ml values were expressed as a percentage of the amount of silica calculated to be initially loaded in the dressing sample.

**[0157]** The leaching values for representative compositions are shown below and illustrate the dependence on polymer hydrophilicity and homogeneity of the silica polyurethane composition: 5% w/v T20 in tetrahydrofuran, 80 mg silica/g polymer, slurry prepared via magnetic stirring

(TABLE 2), 5% w/v T20 in tetrahydrofuran, 80 mg silica/g polymer, slurry prepared via sonication, (TABLE 3), 10% w/v T100 in tetrahydrofuran, 160 mg silica/g polymer, slurry prepared via magnetic stirring (TABLE 4), 10% w/v T20 in tetrahydrofuran, 160 mg silica/g polymer, slurry prepared via sonication (TABLE 5). All wound dressing polymers were solvent cast into thin films and dried under vacuum.

TABLE 2

Day	Average	Stdev
1	11.01%	1.58%
2	9.23%	1.37%

TABLE 3

Day	Average	Stdev
1	0.62%	0.31%
2	0.34%	0.01%

TABLE 4

Day	Average	Stdev
1	21.1%	6.73%
2	23.72%	9.14%

TABLE 5

Day	Average	Stdev
1	0.50%	0.22%
2	1.23%	0.65%

## EXAMPLE 7

[0158] *P. aeruginosa* biofilms were grown for 48 h in partial thickness wounds in a porcine animal model. After 2 days of growth, the baseline levels of bacteria from a flush of the wound with sterile buffer and a vigorous scrub of the wound with bacteria/tissue in sterile buffer were recorded. The planktonic bacteria were approximately  $10^8$  CFU/mL and the biofilm embedded bacteria were above  $10^{10}$  CFU/mL prior to treatment with NO-releasing wound dressings. The efficacy of various NO-releasing wound dressing compositions on both the levels of planktonic bacteria flushed from the wound and the levels of biofilm bacteria scrubbed from the wound are shown in comparison to Tegaderm™ covered controls in FIG. 12. The wound dressings comprising different polymer matrices and variable percentages of Nitricil™ loading elicited different outcomes when tested against an in vivo biofilm model.

## EXAMPLE 8

**[0159]** A medical grade, aliphatic polyether polyurethane that absorbs a small amount of water in the amount of 20% of its dry weight is combined with 14% w/w Nitricil™ 70 (nitric oxide-loaded precipitated silica) such that the Nitricil™ is permanently incorporated throughout the polyurethane matrix. The resulting polyurethane film device is transparent. The polymer blend is cast onto a transparent, siliconized PET release liner (FRA-308, Fox River Associates, LLC), which is pre-printed with a 1" square grid.

**[0160]** The testing performed to evaluate design and technical characteristics is summarized in the **TABLE 6** below.

**TABLE 6**

Performance Characteristic	Measured Value
Film Thickness	98 ± 10 µm
Water Uptake [%]	6.8 ± 2.9 %
MVTR	31 ± 16 g/m <sup>2</sup> ·24 h
Oxygen Permeability	206 ± 91 mL O <sub>2</sub> @ STP/100 in <sup>2</sup>
Tensile Strength	9.57 ± 2.02 kg/in <sup>2</sup>
Residual solvent	3.31 µL THF/g
Nitric Oxide Storage	1.2 ± 0.1 µmoles NO/cm <sup>2</sup>
Leaching Analysis	<0.5% (<3 ppm)

**[0161]** Chemiluminescent detection of NO was used to characterize the nitric oxide release behavior from the polyurethane film device. The nitric oxide in the device is liberated upon exposure to moisture. FIGS. 13A and 13B depict the NO behavior of the finished device soaked in buffer at physiological temperature and pH (37° C, 7.4). The maximum flux at the device surface never exceeds 850 pmol NOcm<sup>-2</sup> s<sup>-1</sup> (FIG. 13A), and the total NO loaded in the device averaged 1.2 ± 0.1µmoles NO/cm<sup>2</sup> (FIG. 13B) for all devices tested. The surface flux of nitric oxide from the proposed device was optimized to assist in providing a barrier to microbial penetration.

#### **EXAMPLE 9**

**[0162]** The nitric oxide-releasing wound dressing of Example 9 was used to treat partial thickness wounds in a porcine model. This study was designed to assess healing potential and whether or not the proposed device has a negative impact on normal wound repair in comparison to topical nitric oxide formulations previously reported (evidenced by delayed wound healing or significant erythema/edema). 160 rectangular wounds measuring 10mm x 7mm x 0.5mm deep were divided into four treatment groups (40 wounds each). Wounds were dressed immediately after wounding and dressings were changed on days 2, 3, 5, and 7. Five

wounds from each of the four groups were excised each day beginning on Day 4 after wounding and prepared according to the sodium bromide salt-split technique to assess epidermal migration. Epithelialization is considered complete (healed) if no defects or holes are present after the separation of the dermis and epidermis. Wounds in each of the groups were evaluated until 100% complete epithelialization was observed. The test materials were non-adherent to wound bed upon removal (no re-injury was observed) and none of the wounds from any of the treatment groups developed erythema, swelling or signs of infection. On Day 4, none of the treatment groups were completely re-epithelialized but Day 6, 100% of the wounds in the nitric oxide treated group were re-epithelialized in comparison to only 60% of the Tegaderm covered occlusive wound environment (**FIGURE 14**). The average MVTR of the wound dressing in Example 9 across n=6 batches is  $31 \pm 16 \text{ g/m}^2\text{-24h}$ , representing a 9 fold greater MVTR than that of 3M Tegaderm Barrier Wound Dressing, measured under identical conditions ( $3.34 \text{ g/m}^2\text{-24h}$ ). Furthermore, the wound dressing in Example 9 has an MVTR <4% of the  $840 \text{ g/m}^2\text{-24h}$  value below which dressings are considered to be occlusive and is <1% of the 3000 to 5000  $\text{g/m}^2\text{-24h}$  MVTR of damaged skin (Rennekampff, 1996). Untreated controls (air exposed) did not completely heal until Day 10 illustrating the importance of maintaining a moist wound environment.

#### **EXAMPLE 10**

**[0163]** Testing has been performed by an independent laboratory, in accordance with Good Laboratory Practices, to evaluate the biocompatibility of the wound dressing in Example 9, as recommended by FDA's *Blue Book Memo*, G95-1, *Use of International Standards ISO-10993, and Biological Evaluation of Medical Devices Part 1: Evaluation and Testing*. Following are the tests that have been conducted along with a brief summary of results.

- **Cytotoxicity (in vitro): NON-TOXIC**

**[0164]** MEM Elution extract was prepared from the dressing extracts and applied to mouse fibroblasts. Fibroblasts were scored for signs of cytotoxicity over a 72-hour test period. The wound dressing extract received a cytotoxicity score of 0 at all time points.

- **Sensitization (in vivo): NO SENSITIZATION**

**[0165]** Normal saline and cotton seed oil extracts were prepared from the dressing extracts and tested using the Guinea Pig Maximization Sensitization Test. Both extracts elicited a 0% sensitization response.

- **Irritation/Intracutaneous Reactivity (in vivo): NON-IRRITANT**

**[0166]** Normal saline and cotton seed oil extracts were prepared from the wound dressing and injected into rabbits. Injection sites were scored for reactivity over a 72-hour test period. For each extract, the difference between the mean reactivity score for the wound dressing extract and the mean reactivity score for the vehicle control was < 1.0.

- **Systemic (Acute) Toxicity (in vivo): NON-TOXIC**

**[0167]** Normal saline and cotton seed oil extracts were prepared from the wound dressing and injected into mice. Animals were observed for mortality and signs of pharmacological and toxicological effects over a 72-hour test period. Both extracts resulted in zero animal fatalities, zero animals exhibiting clinical signs of toxicity, and zero animals with body weight changes outside acceptable parameters.

- **Sub-acute (Sub-chronic) Toxicity (in vivo): NON-TOXIC**

**[0168]** Normal saline and cotton seed oil extracts were prepared from the wound dressing and injected intravenously (saline) or intraperitoneally (oil) into mice once daily for 14 days. Animals were observed for mortality and signs of toxicity during the test period. There were no fatalities, no statistically significant weight differences between control and test animals, and no abnormal clinical signs noted for any of the animals during the test period. No clinically abnormal findings were noted during animal necropsies. Clinical chemistry and hematology data were not indicative of a pattern of toxicity.

- **Implantation (in vivo): NON-IRRITANT**

**[0169]** Two implantation studies have been completed for the wound dressing in which pieces of were implanted intramuscularly in albino rabbits for either a one or four week study. At the end of the one-week implantation, the irritant ranking score for the wound dressing was calculated to be 1.2. At the end of the four-week implantation, the irritant ranking score for the wound dressing was calculated to be 2.6.

- **LAL Endotoxin Test for Pyrogens (in vitro, GMP): PASS**

**[0170]** The kinetic chromogenic LAL test system was validated for use with the wound dressing. Samples from three production lots of the sterilized, finished device all contained <0.200 EU/device.

**[0171]** The wound dressing of Example 9 passed the requirements of all biocompatibility tests; thus it can be concluded that the product is biocompatible and non-toxic, providing a topical nitric oxide releasing solution with proven safety and effectiveness.

#### EXAMPLE 11

**[0172]** This example describes a process of manufacturing NO-releasing flexible polyurethane foam starting from 100 kg of 2-(2-aminoethylamino) ethanol as a basis. The foam is prepared using Desmodur N-100 (22% NCO groups, Bayer Material Science, Pittsburgh, PA) as the polyisocyanate and Desmodur N-and Desmophen-R-221-75 (3.3% OH groups, Bayer Material Science, Pittsburgh, PA) as the polyol. Nitricil™-70 (Novan, Inc.) as an NO-releasing macromolecule is incorporated in the foam at a loading of 1% (w/w).

1. 1.  $\text{CO}_2$  is bubbled into the 100 kg 2-(2-aminoethylamino) ethanol to prepare 2-(2-aminoethylamino)ethanol carbamate
2. 2. The 2-(2-aminoethylamino)ethanol carbamate is dissolved in 200 kg of Desmophen-R-221-75 polyol
3. 3. Nitricil™-70, the blowing agent, and gel catalysts are added to the mixture (see USP 4173691)
4. 4. The mixture is reacted with a stoichiometric excess of Desmodur N-100, under agitation and heating at 50° C.
5. 5. The reaction mixture is cured at 50° C to release the chemically bound  $\text{CO}_2$ .

#### Calculations for:

##### [0173]

1. 1. Amount of  $\text{CO}_2$  needs to be bubbled
2. 2. Amount of Desmodur N-100 be added
3. 3. Amount of Nitricil™-70 to be added for a nominal 1% w/w loading

#### *Calculation for $\text{CO}_2$ addition*

**[0174]** There are two moles of NH per mole of 2-(2-aminoethylamino)ethanol. The number of moles of 2-(2-aminoethylamino) ethanol in 100 kg = 961.54. The number of moles of NH = 2 \* 961.54 = 1923.07 moles. Thus, the weight of  $\text{CO}_2$  required = 1923.07 moles \* 44 g/mol = 84.6 kg. A 1.2 fold excess gas to ensure complete conversion to carbamates. Thus, the amount of

$\text{CO}_2$  required = 101.52 kg.

***Calculation for catalyst addition***

**[0175]** Two types of catalyst are used in combination, a gel catalyst to accelerate the urethane formation reaction, and a blowing catalyst to reduce the rising time of the foam. The gel catalyst (e.g., stannous octoate) is present as 0.3 parts per 100 parts polyol (w/w). The blowing catalyst (e.g., antimony tris 2-ethylhexoate) is present as 0.3 parts per 100 parts polyol (w/w). Therefore, the catalyst calculation is based on the total mass of reacting hydroxyl compounds, and includes the hydroxyls in 2-(2-aminoethylamino) ethanol. Thus, the weight of gel catalyst = 300 kg /100kg\* 0.3 = 9 kg. The weight of blowing catalyst = 9 kg.

***Calculation for Desmodur N-100 addition***

**[0176]** Enough Desmodur N-100 needs to be added such that the NCO are adequate to react with OH in 2-(2-aminoethylamino) ethanol and in Desmophen. The equivalent of OH groups in Desmophen-R-221-75 (3.3% OH) =  $17 * 100/3.3 = 515$ . The moles of OH groups in 100kg 2-(2-aminoethylamino)ethanol = 961.54. The equivalents in 200 kg =  $200/515 = 0.388$ . The equivalent NCO groups in Desmodur N-100 (22% NCO) =  $42 * 100/22 = 191$ . The equivalents of NCO required for 1:1 reaction with 200kg Desmophen-R-221-75 =  $191 * 0.388 = 74.2$  kg. The percent OH in 2-(2-aminoethylamino)ethanol =  $17/104 = 16.3\%$ . The equivalent of OH groups =  $17 * 100/16.3 = 104$ . The equivalents in 100 kg =  $100/104 = 0.9615$ . The equivalents of NCO required for 1:1 reaction =  $0.9615 * 191 = 183.65$  kg. Thus, the total required =  $183.65 + 74.2 = 257.83$  kg. A 2% excess is used to ensure complete reaction. Therefore, the Desmodur N-100 total requirement =  $1.02 * 257.83 = 262.985$  kg.

***Calculation for Nitricil™-70***

**[0177]** The total reactant weight (not including  $\text{CO}_2$ ) = 262.985 kg (Desmodur N-100) + 200 kg (Desmophen-R-221-75 polyol) + 100 kg (2-(2-aminoethylamino) ethanol) + 18 kg (weight of blowing catalyst and gel catalyst) = 580.985 kg. Thus, 1% Nitricil™-70 = 5.81kg.

***Summary:***

**[0178]**

Material	Amount to be used (kg)
2-(2-aminoethylamino) ethanol	100
Desmophen-R-221-75	200

Material	Amount to be used (kg)
Desmodur N-100	262.985
Nitricil™-70	5.81
Stannous octoate	9
Antimony tris 2-ethylhexoate	9

## REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

### Patent documents cited in the description

- [US61235927A \[0001\]](#)
- [US61235948A \[0001\]](#)
- [WO03026717A \[0006\]](#)
- [US20090214618A \[0066\]](#)
- [US6316662B \[0108\]](#)
- [US5859285A \[0143\]](#)
- [US20090099272A \[0146\]](#)
- [US5194325A \[0146\]](#)
- [USP4173691A \[0172\]](#)

### Non-patent literature cited in the description

- **ROBSON et al.** Surg. Clin. N. Am., 1977, vol. 77, 637-650 [\[0004\]](#)
- **SCHAFFER MR et al.** Diabetes-impaired healing and reduced wound nitric oxide synthesis: A possible pathophysiologic correlation *Surgery*, 1997, vol. 121, 5513-9 [\[0005\]](#)
- **SHI HP et al.** The role of iNOS in wound healing *Surgery*, 2001, vol. 130, 2225-9 [\[0005\]](#)
- **SHIN et al.** J. Am. Chem. Soc., 2007, vol. 129, 4612-2619 [\[0007\]](#)
- **HETRICK et al.** Biomaterials, 2009, vol. 30, 2782-2789 [\[0008\]](#)
- **HRABIE et al.** Chem. Rev., 2002, vol. 102, 1135-1154 [\[0009\]](#)

- **DAVIES et al.** J. Am. Chem. Soc., 2001, vol. 123, 5473-5481 [\[0009\]](#)
- **HETRICK et al.** Analytical Chemistry of Nitric Oxide, Annu. Rev. Anal. Chem., 2009, vol. 2, 409-433 [\[0098\]](#)

SÅRBANDAGER, FREMGANGSMÅDER TIL ANVENDELSE HERAFTIL FREMGANGSMÅDER  
TIL DANNELSE DERAF


PATENTKRAV

1. Sårbandage, der omfatter:
  - 5 en polymermatrix og  
nitrogenoxid- (NO) frigørende polysiloxanmakromolekyler inde i og/eller på polymermatricen,  
hvor polymermatricen er et fleksibelt, åbencellet polyurethanskum, der omfatter mindst ét  
polyisocyanatsegment og mindst ét polyolsegment og de NO-frigørende polysiloxanmakromolekyler  
omfatter N-diazeniumdiolat-funktionelle grupper, og
  - 10 hvor sårbandagen er ikke-toksisk og stabilt lagrer NO.
  2. Sårbandage ifølge krav 1, hvor koncentrationen af de NO-frigørende polysiloxanmakromolekyler  
ligger i et interval fra ca. 0,1 til ca. 20 vægtprocent.
  3. Sårbandage ifølge krav 1 eller krav 2, der endvidere omfatter:
    - 15 en vandopløselig porogen, der er udvalgt fra gruppen bestående af natriumchlorid, saccharose,  
glucose, lactose, sorbitol, xylitol, polyethylenglycol, polyvinylpyrrollidon, polyvinylalkohol og blandinger  
deraf; og/eller  
mindst ét terapeutisk middel, der er udvalgt fra gruppen bestående af antimikrobielle forbindelser,  
anti-inflammatoriske midler, smertelindrende midler, immunosuppressive stoffer, vasodilatorer, sårhelende  
midler, anti-biofilmmidler og blandinger deraf.
  - 20 4. Sårbandage ifølge et hvilket som helst foregående krav, hvor sårbandagen er:
    - et enkelt lag med en tykkelse i intervallet fra 10 til 5000 mikron og/eller  
sårbandagen i alt væsentligt er transparent.
    5. Sårbandage ifølge et hvilket som helst foregående krav, hvor strømmen af nitrogenoxid, der  
frigøres fra den hydrerede bandageoverflade er:
      - 25 i et interval fra 100 pmol NO cm<sup>-2</sup> s<sup>-1</sup> til 1000 pmol NO cm<sup>-2</sup> s<sup>-1</sup> eller  
i et interval fra 1 nmol NO cm<sup>-2</sup> s<sup>-1</sup> til 10 µmol NO cm<sup>-2</sup> s<sup>-1</sup>.
      6. Sårbandage ifølge et hvilket som helst foregående krav, hvor sårbandagen bevarer mindst 95 % af  
den originale NO-belastning efter én uge ved 25 °C.
      7. Sårbandage ifølge et hvilket som helst foregående krav, hvor mere end 98 % af de NO-frigørende  
30 polysiloxanmakromolekyler bevares i sårbandagen efter inkubation af sårbandagen i phosphatbufferet  
saltvandsopløsning ved pH 7,4 i 48 timer ved 37 °C.
      8. Sårbandage ifølge krav 1 til anvendelse i en fremgangsmåde til behandling af et sår, hvilken  
fremgangsmåde omfatter anvendelse af sårbandagen på et sår.
      9. Sårbandage ifølge krav 8 til anvendelse ifølge krav 8, der endvidere omfatter:
        - 35 debridering af såret før anvendelse af sårbandagen og/eller  
udførelse af sårbehandling med negativ trykterapi mod såret før, samtidigt med eller efter  
anvendelse af sårbandagen; og/eller

behandling af såret med et anti-biofilmmiddel før eller i kombination med anvendelsen af sårbandagen.

10. Sårbandage ifølge krav 9 til anvendelse ifølge krav 9, hvor en anordning til udførelse af sårbehandling med negativ trykterapi og sårbandagen ifølge krav 1 er udformet som én anordning.
- 5 11. Fremgangsmåde til dannelse af en sårbandage, hvilken fremgangsmåde omfatter:
  - 10 kombinering af NO-frigørende polysiloxanmakromolekyler og mindst én monomer og polymerisering af den mindst ene monomer for at danne en polymermatrix, der omfatter de NO-frigørende polysiloxanmakromolekyler,
    - 15 hvor polymermatricen er et fleksibelt, åbencellet polyurethanskum, der omfatter mindst ét polyisocyanatsegment og mindst ét polyolsegment og de NO-frigørende polysiloxanmakromolekyler omfatter N-diazeniumdiolat-funktionelle grupper.
  12. Fremgangsmåde ifølge krav 11, hvor:
    - 15 monomeren polymeriseres ved fotohærdning og/eller polymeriseringen sker ved en fremgangsmåde, der omfatter aflejring af flydende monomer, NO-frigørende polysiloxanmakromolekyler og en initiator; og polymerisering af den flydende monomer.
  13. Fremgangsmåde ifølge krav 11 eller 12, hvor kombinering af NO-frigørende polysiloxanmakromolekyler og mindst én monomer omfatter:
    - 20 dispergering af de NO-frigørende makromolekyler i en blanding af skumdannende monomerer eller omsætning af funktionelle grupper på de NO-frigørende makromolekyler med mindst én skumdannende monomer, og hvor polymerisering af den mindst ene monomer for at danne en polymermatrix omfatter polymerisering af de skumdannende monomerer for at danne en polymer, og opskumning af polymeren for at danne polymermatricen.

# DRAWINGS






FIG. 2A




FIG. 2B




FIG. 3A




FIG. 3B




FIG. 4A




FIG. 4B




FIG. 5A






FIG. 5B






FIG. 7




FIG. 8





FIG. 9



&lt;div[](img/1000px-FIG\_10.svg)




FIG. 11




FIG. 12




FIG. 13A




FIG. 13B




FIG. 14