

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
22 May 2008 (22.05.2008)

PCT

(10) International Publication Number
WO 2008/058769 A1

(51) International Patent Classification:
C08B 37/00 (2006.01)

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(21) International Application Number:
PCT/EP2007/053710

(22) International Filing Date: 17 April 2007 (17.04.2007)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
VA2006A000069
17 November 2006 (17.11.2006) IT

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **BALDARO, Eva** [IT/IT]; Via Pria Forà, 6, I-20127 Milano (IT). **PELIZ-ZARI, Raffaella** [IT/IT]; Via Leopardi, 105, I-20013 Magenta (MI) (IT). **TENCONI, Mauro** [IT/IT]; Via Manzoni 2, I-21045 Gazzada (VA) (IT). **LI BASSI, Giuseppe** [IT/IT]; Via Stretti, 4, I-21026 Gavirate (VA) (IT).

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))
- of inventorship (Rule 4.17(iv))

Published:

- with international search report

WO 2008/058769 A1

(54) Title: PROCEDURE FOR THE PREPARATION OF PURIFIED CATIONIC GUAR

(57) **Abstract:** Procedure for the preparation of cationic guar having DS comprised between 0.01 and 3, free from boron and suitable for the use in the cosmetic field and in household cleaning products, comprising the following steps: a) 100 parts by weight of guar flour are reacted with 3-chloro-2-hydroxypropyl trimethylammonium chloride and sodium hydroxide in from 5 to 500 parts by weight of a water and alcohol mixture containing from 20 to 50% by weight of water; b) the amount of water and alcohol is regulated in order to obtain a dispersion containing from 65 to 95% by weight of a water and alcohol mixture containing from 30 to 50% by weight of water and the dispersion is maintained under stirring at temperature comprised between 15 and 40 °C for at least 10 minutes; c) the mixture is filtered under vacuum and dried to obtain the purified cationic guar.

Description

PROCEDURE FOR THE PREPARATION OF PURIFIED CATIONIC GUAR

Technical Field

[0001] The present invention relates to a procedure for the preparation of purified cationic guar free from boron and suitable for the use in the cosmetic field and in household cleaning products.

[0002] The cationic guar obtained by the procedure of the present invention has the technologically useful property, to be soluble in water both at acidic and basic pH, and therefore to develop viscosity in aqueous solutions having a very wide interval of pH; moreover it possesses a degree of purity that renders it suitable for the cosmetic field.

[0003] Cationic polysaccharides are derivatives of natural origins very used as industrial additives due to their conditioning properties (i.e. they improve the characteristics of the substrate, generally paper, skin, hair or fabric, to which they are applied on).

[0004] This characteristic renders them industrially useful for the preparation of shampoos, hair conditioners, creams, personal or household care detergents and softeners that confer a soft touch and antistatic properties to fabrics (see as an example Conditioning Agents for Hair & Skin, Ed. R. Schueller and P. Romanowski, Marcel Dekker Inc, NY, 1999).

[0005] Beside their conditioning power, the capability of these polysaccharides to thicken and regulate the rheology of the solutions in which they are dissolved is industrially useful.

[0006] In particular, cationic polygalactomannans, and among these cationic derivatives of guar gum, have shown optimal results in improving the wet and dry combability of hairs washed with a shampoo formulated therewith.

[0007] It is well known that, in cosmetic formulations, the presence of materials not expressly added and controlled, not predicted and variable from batch to batch, even if in minimal amounts, can create problems during the preparation of the formulation, such as phase separation and variations of the viscosity.

[0008] Moreover, during the last few years, particular attention has been placed to the toxicity of raw materials used for the fabrication of cosmetic

products. The EC Directive 76/768/EEC and following modifications, as an example, limits or prohibits the presence of certain substances in raw materials for cosmetics, with the aim of safeguarding the consumer health.

- [0009] In particular, the above cited directive prohibits the presence in cosmetic products of several substances, listed in the Attachment II, and classified as carcinogenic, mutagenic or toxic for reproduction, pertaining to categories CMR 1, CMR 2 or CMR 3, according to the EEC Directive 67/548/EEC; the presence of other substances, not necessarily present as ingredients, but only as impurities deriving from the process of production of the raw materials, is subjected to amount limitations according to the same EEC Directive 76/768/EEC (substances listed in Attached III).
- [0010] It is therefore of fundamental importance that, for the use in cosmetic formulations and in formulations that come to direct contact with skin, such as in household cleaning products, the cationic derivatives of guar are as much as possible devoid of impurities, both for the consumer's health and for technological problems connected with the production of cosmetics.
- [0011] Moreover the pH of cosmetic formulations and household detergents is very varied, ranging from the decidedly acid pH of scale preventers to the decidedly basic pH of hair dyes; it is therefore industrially convenient to use in these products ingredients that are soluble in water at all pHs.

Background Art

- [0012] Cationic guar derivatives are known since the early '70s, when their use is cited in the production of waterproof paper (see US 3,589,978).
- [0013] The first use of cationic guar derivatives in cosmetics goes back to 1977, when a cationic derivative of guar was used in the preparation of a so-called "two in one" shampoo, having hair conditioning characteristics beside the normal detergent power (see US 4,061,602).
- [0014] The cationic guar derivative used in cosmetic is known with the INCI name of Guar Hydroxypropyltrimonium Chloride and, chemically, is guar 2-hydroxy-3-(trimethylammonium)propyl ether chloride.
- [0015] Its synthesis, described as an example in the cited
- [0016] US 3,589,978 patent, requires the reaction of 2,3-epoxypropyl trimethylammonium chloride or (3-chloro-2-hydroxypropyl)

trimethylammonium chloride on the hydroxyl groups of guar, in the presence of basic catalysts (such as sodium hydroxide).

- [0017] The reagent 2,3-epoxypropyl trimethyl ammonium chloride is classified as a carcinogenic substance CMR 2; the reagent 3-chloro-2-hydroxypropyl trimethylammonium chloride, even if less toxic than the corresponding epoxide, is classified as CMR 3 and in alkaline medium is converted into 2,3-epoxypropyl trimethyl ammonium chloride.
- [0018] According to what is described in US 3,589,978, the reaction can be carried out in a solvent such as isopropanol, methanol, ethanol and tert-butanol, at temperatures between 30 and 60°C; in the Example A of the same patent, at the end of the reaction and after neutralisation of the alkali excess, the product is dried, milled and washed with methanol, in the attempt to eliminate the un-reacted quaternary reagent.
- [0019] Nothing is reported in US 3,589,978 on the residual quantities of the cationic reagent (2,3-epoxypropyl trimethyl ammonium chloride) in the final product; but we can observe that methanol is itself a toxic product.
- [0020] In US 4,031,307 the preparation of cationic derivatives of guar in a biphasic system is described, by reacting solid guar with a cationising reagent in a mixture of water and water soluble solvent that contains the basic catalyst; after the reaction, the obtained product is separated by centrifugation or filtration and preferably purified by means of a first washing with the water-solvent mixture used in synthesis, and with a second washing with a more anhydrous form of the same solvent.
- [0021] In US 2001051143, the preparation of guar cationic derivatives comprising at the end of the reaction a first washing with 85% by weight aqueous isopropanol and a second washing with pure isopropanol is described; in US 2001051140 the preparation of guar cationic derivative comprising, at the end of the reaction, two washings with 85% aqueous isopropanol is described.
- [0022] In all these publications, neither the type nor the amount of impurities present in the obtained cationic guar derivative is mentioned, impurities that will become part of the final cosmetic product in case the cationic guar derivative is used as a cosmetic raw material.

- [0023] The greatest part of cationic guar derivatives currently on the market, in order to obviate to the difficulty and to the burden connected with the purification by washings with water and solvents, are purified by washing the product, previously cross-linked with borates, with water only, as described for example in CA 2,023,324, where in the reaction phase borax is added; the cationic guar derivatives so obtained contain small amounts of boron (borated guars).
- [0024] The aim of the cross-linking with boric acid is to form bonds, through the borate anion, between the polysaccharides chains, that render the product insoluble in water.
- [0025] These bonds are stable at basic pH, and therefore in such conditions the product can be washed from by-products.
- [0026] In acidic conditions the bonds with the borate are removed, the product is soluble and can perform its thickening and conditioning properties.
- [0027] The reaction with borates is reversible with pH changes; therefore, even if the product is pre-solubilised at acidic pH, bringing it back to alkaline conditions may cause a change in the viscosity of the formulate, varying as a consequence the quality of the product.
- [0028] The limit of borated cationic guar derivatives is therefore their exclusive applicability to products to be used at acidic or slightly acidic pH, because products treated with borates are not soluble at pH greater than 7.
- [0029] Furthermore, it must be observed that boric acid derivatives are classified as substances toxic for reproduction of category CMR 2.
- [0030] Hair dyes represent one of the sector of the home & personal care in the greatest expansion; they are generally formulated at pH higher than 8 and therefore it is not possible to formulate them with cationic guar derivatives purified by cross-linking with boric acid.
- [0031] The preparation of solid soap bars, generally having pH higher than 7.5 in aqueous solution and normally containing softening and conditioning agents for the skin, represent another field of great interest for the use of non borated cationic guar derivatives.
- [0032] The preparation of depilatory creams and the production of fabric powder detergents, having generally basic pH and possibly advantageously

containing a co-formulating agent having skin protective function, are further formulations in which non-borated cationic guar derivatives can be used.

[0033] The Applicant has now found a procedure for the preparation of purified cationic guar, soluble at all pHs, free from boron and with a reduced content of other impurities that can compromise the stability or the toxicological characteristics of the cosmetic formulations in which it is used as an ingredient.

Disclosure of Invention

[0034] It is therefore a fundamental object of the present invention a procedure for the preparation of cationic guar having DS comprised between 0.01 and 3 comprising the following steps: a) 100 parts by weight of guar flour are reacted with 3-chloro-2-hydroxypropyl trimethylammonium chloride and sodium hydroxide in from 5 to 500 parts by weight of a water and alcohol mixture containing from 20 to 50% by weight of water; b) the amount of water and alcohol is regulated in order to obtain a dispersion containing from 65 to 95% by weight of a of water and alcohol mixture containing from 30 to 50% by weight of water and the dispersion is maintained under stirring at temperature comprised between 15 and 40 °C for at least 10 minutes; c) the mixture is filtered under vacuum and dried to obtain the purified cationic guar.

[0035] The guar flour utilisable for the invention is any commercially available guar flour, preferably containing 10% by weight maximum of water.

[0036] With the expression "cationic guar" in the present text we mean guar 2-hydroxy-3-(trimethylammonium)propyl ether chloride.

[0037] In order to obtain a cationic guar having a degree of substitution (DS) comprised between 0.01 and 3 in step a) the reaction is carried out, under stirring, using from 2 to 600 parts by weight of 3-chloro-2-hydroxypropyltrimethylammonium chloride, and from 0.4 to 160 parts by weight of sodium hydroxide (or equivalent amount of other strong base).

[0038] In the present text, with the expression "degree of substitution" (DS) we mean the substitution of the cationic group on the hydroxyl groups of guar measured by means of ¹H-NMR.

- [0039] To regulate the amount of water and alcohol in step b) it is possible to add water and/or alcohol, or to remove excess water and alcohol by distillation, or to both add and distillate, or it can be neither necessary to add nor to remove anything.
- [0040] In order to avoid the distillation, in step a) it is preferably to use an amount of water and alcohol mixture inferior or equal to the amount present in the dispersion of step b).
- [0041] Preferably, in step a) of the procedure, from 50 to 200 parts by weight of water and alcohol mixture are used.
- [0042] According to a preferred form of realisation of the present invention, in step a) of the reaction from 10 to 100 parts by weight of 3-chloro-2-hydroxypropyl trimethylammonium chloride and from 2 to 27 parts by weight of sodium hydroxyde are used, obtaining at the end of the preparation a cationic guar having a DS comprised between 0.05 and 0.5; this degree of substitution permits to obtain the best conditioning performances.
- [0043] Usually, according to what is well known in the field, in step a) the reaction is carried out at a temperature comprised between 40 and 80 °C for 0.5-4 hours, regulating the pH at the end of the reaction between 4 and 10; the drying of step c) is carried out at a temperature comprised between 60 and 90 °C, and after the filtration the purified cationic guar is milled.
- [0044] The alcohol useful for the procedure of the invention is ethanol, isopropanol, or mixtures thereof.
- [0045] According to a particularly advantageous aspect, the procedure of the invention comprises a single washing and a single filtration, and the use of relatively small amounts of water and alcohol; the cationic guar obtained is free from boron, toxic solvents and substances classified as carcinogenic, mutagenic or toxic for reproduction of category CMR 1, CMR 2 or CMR 3.
- [0046] In particular the purified cationic guar obtained by means of the procedure of the invention is free from 3-chloro-2-hydroxypropyltrimethylammonium chloride and has minimum contents of 2,3-dihydroxypropyl trimethylammonium chloride (possibly formed by the reaction of 3-chloro-

2-hydroxypropyltrimethylammonium chloride with water during the cationising reaction).

- [0047] An advantage of the procedure according the invention is that it allows to obtain the purified cationic guar with high yields, due to the fact that the product is completely insoluble in the mixtures of water and alcohol used.
- [0048] The use of the reported amount of water and alcohol is essential for this purpose, because beside guaranteeing the complete insolubility of the cationic guar, also allow to obtain of a purified product.
- [0049] The determination of the cationising reagent residue and its correlated glycol is carried out by means of ion exchange chromatography, by the use of a cationic exchange column and elution with methanesulphonic acid solution.
- [0050] With the expression "free from 3-chloro-2-hydroxypropyl trimethylammonium chloride" we mean that in the cationic guar of the invention the concentration of from 3-chloro-2-hydroxypropyl trimethylammonium chloride is below the detection limit of the above described method (in this case below 0.15%).
- [0051] The product obtained by means of the procedure of the invention is rapidly and completely soluble at whichever pH; it can be used in the most different cosmetic formulations, where its capability to bind through its positive charges to substrates having weak negative charges, together with its capability to thicken and to regulate the rheology of water solutions are exploited.
- [0052] A further advantage of the procedure of the invention is that the cationic guar so obtained contains less than 3% by weight of inorganic salts (amount determined by calcination at 700°C) and in particular, less of 2% by weight of sodium chloride, whose presence, as it is well known, influences the effectiveness of the thickeners commonly used in the cosmetic field.
- [0053] It is believed that in the procedure of the invention the use of guar in the form of flour is fundamental in order to obtain the characteristics of purity which are typical of the cationic guar of the invention.

[0054] The cationic guar of the invention is also useful in other industrial fields, where the purity characteristics of the product are of particular importance, as for example in the house care

[0055] and in all those products that may come into contact with skin.

[0056] EXAMPLE 1

[0057] In a 5 litres stirred reactor, 800 g of guar flour are loaded at room temperature, the reaction atmosphere is made inert by means of vacuum/nitrogen washings, and under vigorous stirring 50 g of sodium hydroxide dissolved in 450 g of a 1/9 water/isopropanol solution are added. The stirring is continued for 30 minutes at a temperature of 50-60°C; 224 g of 3-cloro-2-hydroxypropyl trimethylammonium chloride 85% diluted in 100 g of water are added. After 2 hours at the same temperature the reaction is cooled off to 40°C and gaseous carbon dioxide is added until the pH is about 8.

[0058] EXAMPLE 2

[0059] A reaction mixture obtained as described in Example 1 is dispersed under stirring in 8000 g of a water and isopropanol mixture (60% by weight of alcohol); the obtained dispersion is left under stirring for 30 minutes and filtered under vacuum (0.4-0.5 atm) on a fabric filter.

[0060] The so obtained purified cationic guar is dried on a fluid bed dryer with warm air until a humidity content of approximately 3% by weight, milled and analysed.

[0061] The analytical results are reported in Table 1.

[0062] EXAMPLE 3

[0063] A reaction mixture obtained as described in Example 1 is dispersed under stirring in 8000 g of a water and ethanol mixture (60% by weight); the obtained dispersion is left under stirring for 30 minutes and filtered under vacuum (0.4-0.5 atm) on a fabric filter.

[0064] The so obtained purified cationic guar is dried on a fluid bed dryer with warm air until a humidity content of approximately 3% by weight, milled and analysed.

[0065] The analytical results are reported in Table 1.

[0066] EXAMPLE 4

- [0067] A reaction mixture obtained as described in Example 1 is dispersed under stirring in 8000 g of a water and ethanol mixture (60% by weight); the obtained dispersion is left under stirring for 30 minutes and filtered under vacuum (0.4-0.5 atm) on a fabric filter.
- [0068] The purified so obtained cationic guar is dried on a fluid bed dryer with warm air until a humidity content of approximately 3% by weight, milled and analysed.
- [0069] The analytical results are reported in Table 1.
- [0070] EXAMPLE 5 (COMPARATIVE)
- [0071] A reaction mixture obtained as described in Example 1 is dispersed under stirring in 8000 g of a water and acetone mixture (60% by weight of acetone); the obtained dispersion is left under stirring for 30 minutes and filtered under vacuum (0.4-0.5 atm) on a fabric filter.
- [0072] The so obtained cationic guar is dried on a fluid bed dryer with warm air until a humidity content of approximately 3% by weight, milled and analysed.
- [0073] The analytical results are reported in Table 1.
- [0074] EXAMPLE 6 (COMPARATIVE)
- [0075] A reaction mixture obtained as described in Example 1 is dispersed under stirring in 8000 g of a water and isopropanol mixture (90% by weight of alcohol); the obtained dispersion is left under stirring for 30 minutes and filtered under vacuum (0.4-0.5 atm) on a fabric filter.
- [0076] The so obtained cationic guar is dried on a fluid bed dryer with warm air until a humidity content of approximately 3% by weight, milled and analysed.
- [0077] The analytical results are reported in Table 1.
- [0078] EXAMPLE 7 (COMPARATIVE)
- [0079] A reaction mixture obtained as described in Example 1 is dispersed under stirring in 2400 g of a water and isopropanol mixture (60% by weight of alcohol); the obtained dispersion is left under stirring for 30 minutes and filtered under vacuum (0.4-0.5 atm) on a fabric filter.

[0080] The cationic guar therefore obtained is dried on a fluid bed dryer with warm air until a humidity content approximately 3% by weight, it is therefore milled, and analysed.

[0081] The analytical results are reported in Table 1.

[0082]

Table 1

Ex.	Solvent	Guar/ mixture	Water/ solvent	Ashes	Chloridrine*	Glycol*
1	-	-	-	8%	0.4%	2.7%
2	i-PrOH	1/10	40/60	2.7%	absent	0.5%
3	EtOH	1/10	40/60	2.1%	absent	0.3%
4	i-PrOH	1/5	40/60	2.9%	absent	0.7%
5**	Acetone	1/10	40/60	5%	absent	1.9%
6**	i-PrOH	1/10	10/90	7%	absent	1.6%
7**	i-PrOH	1/3	40/60	4.5%	absent	1.3%

[0083] *Chloridrine=3-chloro-2-hydroxypropyl trimethylammonium chloride

[0084] Glycol=2,3-dihydroxypropyl trimethylammonium chloride **Comparative examples

[0085]

Claims

1. Procedure for the preparation of cationic guar having DS comprised between 0.01 and 3 comprising the following steps: a) 100 parts by weight of guar flour are reacted with 3-chloro-2-hydroxypropyl trimethylammonium chloride and sodium hydroxide in from 5 to 500 parts by weight of a water and alcohol mixture containing from 20 to 50% by weight of water; b) the amount of water and alcohol is regulated in order to obtain a dispersion containing from 65 to 95% by weight of a of water and alcohol mixture containing from 30 to 50% by weight of water and the dispersion is maintained under stirring at temperature comprised between 15 and 40 °C for at least 10 minutes; c) the mixture is filtered under vacuum and dried to obtain the purified cationic guar.
2. Procedure according to claim 1., wherein in step a) the reaction is carried out, under stirring, using from 2 to 600 parts by weight of 3-chloro-2-hydroxypropyltrimethylammonium chloride and from 0.4 to 160 parts by weight of sodium hydroxide at temperature comprised between 40 and 80 °C for 0.5-4 hours, adjusting the pH between 4 and 10 at the end of the reaction; the drying of step c) is performed at temperature comprised between 60 and 90 °C.
3. Procedure according to claim 1. or 2., where the reaction of step a) is performed in from 50 to 200 parts by weight of the water and alcohol mixture.
4. Procedure according to claim 3., where the alcohol is ethanol or isopropanol, or mixtures thereof.
5. Procedure according to claim 4., where in step a) from 10 to 100 parts by weight of 3-chloro-2-hydroxypropyltrimethylammonium chloride and from 2 to 27 parts by weight of sodium hydroxide are used.
6. Procedure according to claim 5. wherein after the filtration the purified cationic guar is milled.

INTERNATIONAL SEARCH REPORT

International application No

PCT/EP2007/053710

A. CLASSIFICATION OF SUBJECT MATTER
INV. C08B37/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C08B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 2003/044479 A1 (WIELINGA WILLEM COR [CH] ET AL) 6 March 2003 (2003-03-06) claims 14,15; example V -----	1-6
A	EP 0 375 126 A (HI TEK POLYMERS INC [US]) 27 June 1990 (1990-06-27) page 3, lines 32,33,40-51 -----	1-6
A	GB 1 136 842 A (GEN MILLS INC) 18 December 1968 (1968-12-18) examples II,I -----	1-6
A	EP 0 943 627 A (NAT STARCH CHEM INVEST [US]) 22 September 1999 (1999-09-22) example 1 -----	1-6
A	EP 0 686 643 A1 (RHONE POULENC INC [US] RHODIA [US]) 13 December 1995 (1995-12-13) example 6 -----	1-6

 Further documents are listed in the continuation of Box C. See patent family annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

6 July 2007

Date of mailing of the international search report

20/07/2007

Name and mailing address of the ISA/
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Gerber, Myriam

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2007/053710

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
US 2003044479	A1	06-03-2003	NONE		
EP 0375126	A	27-06-1990	AU	619147 B2	16-01-1992
			AU	4283089 A	10-05-1990
			JP	2173001 A	04-07-1990
			US	4959464 A	25-09-1990
GB 1136842	A	18-12-1968	BE	677852 A	01-08-1966
EP 0943627	A	22-09-1999	AU	2122999 A	30-09-1999
			BR	9915415 A	28-08-2001
			CA	2266171 A1	18-09-1999
			CN	1229800 A	29-09-1999
			JP	11315102 A	16-11-1999
EP 0686643	A1	13-12-1995	AT	201883 T	15-06-2001
			AU	684006 B2	27-11-1997
			AU	2058395 A	21-12-1995
			BR	9502720 A	30-04-1996
			CA	2151349 A1	10-12-1995
			DE	69521170 D1	12-07-2001
			DE	69521170 T2	04-10-2001
			JP	8085702 A	02-04-1996
			MX	PA95002536 A	30-10-2002
			NZ	272306 A	25-06-1996