




US 20010000184A1

(19) **United States**(12) **Patent Application Publication** (10) **Pub. No.: US 2001/0000184 A1****Konishi et al.**(43) **Pub. Date: Apr. 5, 2001**(54) **DIMETHYLFURANCARBOXYANILIDE
DERIVATIVES**(57) **ABSTRACT**(75) Inventors: **Kiyoshi Konishi**, Tokyo (JP); **Toshiaki Yanai**, Yokohama-shi (JP); **Akio Saito**, Chiba-shi (JP)

A dimethylfurancarboxyanilide compound of the formula (I):

Correspondence Address:
**FRISHAUF, HOLTZ, GOODMAN,
LANGER & CHICK, P.C.**
25th Floor
767 Third Avenue
New York, NY 10017-2023 (US)



(I)

(73) Assignee: **Sankyo Company, Limited**(21) Appl. No.: **09/729,546**(22) Filed: **Dec. 4, 2000****Related U.S. Application Data**

(60) Continuation of application No. 09/306,170, filed on May 6, 1999, which is a division of application No. 08/999,547, filed on Dec. 29, 1997, which is a continuation-in-part of application No. 08/730,751, filed on Oct. 15, 1996, now abandoned, which is a continuation of application No. PCT/JP94/00631, filed on Apr. 15, 1994.

Publication Classification(51) **Int. Cl.⁷ C07D 307/02**
(52) **U.S. Cl. 549/487**

wherein R¹ and R² are the same or different and each is hydrogen, (C₂-C₆)-alkyl, (C₃-C₆)-cycloalkyl, (C₃-C₆)-alkenyl, (C₂-C₆) alkynyl, (C₁-C₃)-halogenoalkyl, (C₂-C₆)-alkoxy, (C₁-C₆)-alkoxy-(C₁-C₆)-alkyl, cyano, substituted amide, (C₁-C₆)-alkoxy-carbonyl, benzoyl which is unsubstituted or has 1 to 2 substituents, benzoylamino which is unsubstituted or has 1 to 2 substituents; (C₂-C₆)-alkanoylamino, (C₃-C₆)-cycloalkylcarbonylamino, benzyl which is unsubstituted or has 1 to 2 substituents, phenyl which is unsubstituted or has 1 to 2 substituents, or (C₁-C₆)-alkoxy-carbonyl-(C₂-C₃)-alkenylene; and R¹ and R² do not both represent hydrogen at the same time. A wood preservative containing the dimethylfurancarboxyanilide compound as an active ingredient. A method of preserving wood by applying the dimethylfurancarboxyanilide compound to wood. A wood preservative composition in which the dimethylfurancarboxyanilide compound is combined with at least one of 3-bromo-2,3-diiodo-2-propenylethylcarbamate, 3-iodo-2-propynylbutylcarbamate and 4-chlorophenyl-3-iodopropargylformal.




FIG.1A




FIG.1B




FIG.1C




FIG.1D




FIG.1E




FIG.1F




FIG.2A




FIG.2B




FIG.2C




FIG.2D




FIG.2E




FIG.2F

DIMETHYLFURANCARBOXYANILIDE DERIVATIVES

[0001] This is a continuation-in-part application of Ser. No. 08/730,751 filed Oct. 15, 1996, which is a continuation application of International application PCT/JP94/00631 filed Apr. 15, 1994.

BACKGROUND OF THE INVENTION


[0002] 1. Technological Field

[0003] The present invention is concerned with novel dimethylfurancarboxyanilide derivatives exhibiting an excellent antimicrobial effect, a wood preservative containing the dimethylfurancarboxyanilide derivative as the active ingredient, and a wood preservative composition in which the dimethylfurancarboxyanilide derivative as one of the active ingredients is combined with any commercially available wood preservative the effect of which has been already confirmed.

[0004] 2. Background Technology

[0005] Various kinds of inorganic or organic compounds have previously been employed to preserve timber against decay due to various wood-rotting fungi. However, these chemicals have faults such as affecting the human body because of their high toxicity, showing environmental pollution, requiring a high concentration thereof when employed and being expensive.

[0006] As for compounds relating to the dimethylfurancarboxyanilide derivatives of the present invention, compounds represented by the formula below have been disclosed in Japanese Patent Kokai Application Sho 50-10376 as a chemical for preventing plant injury; in which, however, R is limited to phenyl, nitro-substituted phenyl, carboxy-substituted phenyl, phenyl-substituted phenyl, methyl-substituted phenyl, halogen-substituted phenyl or methoxy-substituted phenyl. In addition, this patent is silent on the other derivatives, and no activity of these compounds on wood-rotting fungi has been described.




SUMMARY OF THE INVENTION

[0007] The object of the present invention exists in providing a novel wood preservative which is safer, and is possible to use effectively at a low concentration and/or at a low price.

[0008] In consideration of such situation as mentioned above, the present inventors considered furancarboxyanilide derivatives, and studied eagerly. Our study resulted in finding that novel dimethylfurancarboxyanilide derivatives represented by the general formula (I) below are very useful as a wood preservative and furthermore, if the dimethylfurancarboxyanilide derivative as the active ingredient is com-

bined with any other commercially available wood preservative, potentiation effect can be observed and a wood preservative composition can be prepared.

[0009] The compounds of the present invention are the dimethylfurancarboxyanilide derivatives represented by the general formula



[0010] In this formula, R¹ and R² are the same or different and each represents hydrogen atom; an alkyl group having from 2 to 6 carbon atoms; a cycloalkyl group having from 3 to 6 carbon atoms; an alkenyl group having from 3 to 6 carbon atoms; an alkynyl group having from 2 to 6 carbon atoms; a halogenoalkyl group having from 1 to 3 carbon atoms; an alkoxy group having from 2 to 6 carbon atoms; an alkoxyalkylene group having from 1 to 6 carbon atoms in the alkoxy moiety and having from 1 to 6 carbon atoms in the alkylene moiety; a cyano group; a substituted amide group; an alkoxy carbonyl group having from 1 to 6 carbon atoms in the alkoxy moiety; a benzoyl group which may have optionally from 1 to 2 substituents; a benzoylamino group which may have optionally from 1 to 2 substituents; an alkanoylamino group having from 2 to 6 carbon atoms; a cycloalkylcarbonylamino group having from 3 to 6 carbon atoms in the cycloalkyl moiety; a benzyl group which may have optionally from 1 to 2 substituents; a phenyl group which may have optionally from 1 to 2 substituents; or an alkoxy carbonylalkenylene group having from 1 to 6 carbon atoms in the alkoxy moiety and having from 2 to 5 carbon atoms in the alkenylene moiety; and R¹ and R² do not represent hydrogen atoms at the same time]. The present invention concerns the compounds mentioned above, a wood preservative and a wood preservative composition each containing the dimethylfurancarboxyanilide derivative as the active ingredient.

BRIEF DESCRIPTION OF THE DRAWINGS

[0011] FIGS. 1A to 1F show the minimum inhibitory concentrations (ppm) of Compound of Example 1 in combination with various wood preservatives. FIGS. 2A to 2F show the minimum inhibitory concentrations (ppm) of Compound of Example 2 in combination with various wood preservatives.

DETAILED DESCRIPTION OF THE INVENTION

[0012] In the general formula (I) above, as an alkyl group having from 2 to 6 carbon atoms, which is included in the definitions for R¹ and R², there may be mentioned a straight or branched chain alkyl group such as ethyl, propyl, isopropyl, butyl, isobutyl, sec-butyl, tert-butyl, pentyl, isopentyl, neo-pentyl, hexyl, isohexyl or sec-hexyl; particularly preferably an alkyl group having from 2 to 6 carbon atoms.

[0013] In the general formula (I) above, as a cycloalkyl group having from 3 to 6 carbon atoms, which is included in the definitions for R^1 and R^2 , there may be mentioned a cycloalkyl group such as cyclopropyl, cyclobutyl, cyclopentyl, or cyclohexyl; preferably a cycloalkyl group having from 3 to 6 carbon atoms; and more preferably a cycloalkyl group having from 5 to 6 carbon atoms.

[0014] In the general formula (I) above, as an alkenyl group having from 3 to 6 carbon atoms, which is included in the definitions for R^1 and R^2 , there may be mentioned an alkenyl group such as allyl, isopropenyl, metallyl, 2-butenyl, 3-butenyl, 1,3-butadienyl, 2-pentenyl, or 2-hexenyl; preferably an alkenyl group having from 3 to 4 carbon atoms; and more preferably isopropenyl.

[0015] In the general formula (I) above, as an alkynyl group having from 2 to 6 carbon atoms, which is included in the definitions for R^1 and R^2 , there may be mentioned an alkynyl group such as ethynyl, propargyl, 2-butenyl, 4-pentynyl, or 2-hexynyl; preferably an alkynyl group having from 2 to 4 carbon atoms; and more preferably ethynyl.

[0016] In the general formula (I) above, as a halogenoalkyl group having from 1 to 3 carbon atoms, which is included in the definitions for R^1 and R^2 , there may be mentioned a halogenoalkyl group such as trifluoromethyl, trichloromethyl, pentafluoroethyl, 2,2,2-trichloroethyl or 2,4-dichloropropyl; preferably a halogenoalkyl group having from 1 to 2 carbon atoms; and more preferably trifluoromethyl.

[0017] In the general formula (I) above, as an alkoxy group having from 2 to 6 carbon atoms, which is included in the definitions for R^1 and R^2 , there may be mentioned a straight or branched chain alkoxy group such as ethoxy, propoxy, isopropoxy, butoxy, pentoxy or hexyloxy; preferably an alkoxy group having from 2 to 4 carbon atoms; and more preferably an alkoxy group having from 2 to 3 carbon atoms.

[0018] In the general formula (I) above, as an alkoxy group having from 1 to 6 carbon atoms contained in an alkoxyalkyl group having from 1 to 6 carbon atoms in the alkoxy moiety and having from 1 to 6 carbon atoms in the alkyl moiety, which is included in the definitions for R^1 and R^2 , there may be mentioned a straight or branched chain alkoxy group such as methoxy, ethoxy, propoxy, isopropoxy, butoxy, pentoxy, neo-pentoxy or hexyloxy; preferably an alkoxy group having from 1 to 5 carbon atoms; and more preferably an alkoxy group having from 1 to 3 carbon atoms or having 5 carbon atoms.

[0019] In the general formula (I) above, as an alkylene group contained in an alkoxyalkylene group having from 1 to 6 carbon atoms in the alkoxy moiety and from 1 to 6 carbon atoms in the alkylene moiety which is included in the definitions for R^1 and R^2 , there may be mentioned a straight or branched chain alkylene group such as methylene, ethylene, propylene, trimethylene, tetramethylene, pentamethylene or hexamethylene; preferably an alkylene group having from 1 to 2 carbon atoms; and more preferably methylene.

[0020] In the general formula (I) above, as a substituted amide group, which is included in the definitions for R^1 and R^2 , there may be mentioned a monoalkylamide group such as methylamide, ethylamide, isopropylamide, butylamide, sec-butylamide; a dialkylamide group such as dimethyla-

mid, diethylamide, diisopropylamide, dibutylamide, di-sec-butylamide, methylethylamide, methylisopropylamide, methylbutylamide, methyl-sec-butylamide, ethylisopropylamide, isopropylbutylamide, pyrrolidylamide or piperidylamide; an optionally substituted phenylamide such as phenylamide, 2-chlorophenylamide, 2,4-dichlorophenylamide, 2-methylphenylamide, 2-ethylphenylamide or 4-methoxyphenylamide; preferably methylamide, piperidylamide or phenylamide.

[0021] In the general formula (I) above, as an alkoxycarbonyl group having from 1 to 6 carbon atoms in the alkoxy moiety, which is included in the definitions for R^1 and R^2 , there may be mentioned a group which is formed from the aforementioned alkoxy group having from 1 to 6 carbon atoms contained in an alkoxyalkyl group having from 1 to 6 carbon atoms in the alkoxy moiety and having from 1 to 6 carbon atoms in the alkyl moiety and from a carbonyl group, such as methoxycarbonyl, ethoxycarbonyl, isopropoxycarbonyl, butoxycarbonyl, sec-butoxycarbonyl, tert-butoxycarbonyl, pentyloxycarbonyl or hexyloxycarbonyl; preferably an alkoxycarbonyl group having from 1 to 3 carbon atoms in the alkoxy moiety.

[0022] In the general formula (I) above, as a benzoyl group which may have optionally from 1 to 2 substituents, which is included in the definitions for R^1 and R^2 , there may be mentioned an optionally substituted benzoyl group such as benzoyl, 2-chlorobenzoyl, 2,4-dichlorobenzoyl, 2-methylbenzoyl, 2,4-dimethylbenzoyl, 4-ethylbenzoyl or 4-methoxybenzoyl; preferably benzoyl.

[0023] In the general formula (I) above, as a benzoylamino group which may have optionally from 1 to 2 substituents, which is included in the definitions for R^1 and R^2 , there may be mentioned an optionally substituted benzoylamino group which is formed by substitution of amino group(s) to the aforementioned benzoyl group which may have optionally from 1 to 2 substituents such as benzoylamino, 2-chlorobenzoylamino, 2,4-dichlorobenzoylamino, 2,4-dimethylbenzoylamino, 4-methylbenzoylamino, 4-ethylbenzoylamino or 4-methoxybenzoylamino; preferably benzoylamino.

[0024] In the general formula (I) above, as an alkanoylamino group having from 2 to 6 carbon atoms, which is included in the definitions for R^1 and R^2 , there may be mentioned acetylamino, propionylamino, butyrylamino, isobutyrylamino, valerylamino, isovalerylamino, caproylamino or isocaproylamino; preferably acetylamino.

[0025] In the general formula (I) above, as a cycloalkylcarbonylamino group having from 3 to 6 carbon atoms in the cycloalkyl moiety, which is included in the definitions for R^1 and R^2 , there may be mentioned cyclopropylcarbonylamino, cyclobutylcarbonylamino, cyclopentylcarbonylamino or cyclohexylcarbonylamino; preferably cyclohexylcarbonylamino.

[0026] In the general formula (I) above, as a benzyl group which may have optionally from 1 to 2 substituents, which is included in the definitions for R^1 and R^2 , there may be mentioned benzyl, 2-methylbenzyl, 2,4-dimethylbenzyl, 2-chlorobenzyl, 4-methoxybenzyl or 4-ethoxybenzyl; preferably benzyl.

[0027] In the general formula (I) above, as an alkoxycarbonylalkenylene group having from 1 to 6 carbon atoms in the alkoxy moiety and having from 2 to 5 carbon atoms in

the alkenylene moiety, which is included in the definitions for R¹ and R², there may be mentioned methoxycarbonylvinylene, ethoxycarbonyl-2-propenylene, methoxycarbonyl-2-butenylene or ethoxycarbonyl-2-pentenylene; preferably methoxycarbonylvinylene.

[0028] Preferred compounds having the general formula (I) above include ones in which:

[0029] (1) R¹ and R² are the same or different and each represents a hydrogen atom; an alkyl group having from 2 to 6 carbon atoms; an alkenyl group having from 3 to 4 carbon atoms; an alkynyl group having from 2 to 4 carbon atoms; a cycloalkyl group having from 3 to 6 carbon atoms; an alkoxycarbonyl group having from 1 to 6 carbon atoms in the alkoxy moiety; an alkoxyalkylene group having from 1 to 6 carbon atoms in the alkoxy moiety and having from 1 to 2 carbon atoms in the alkylene moiety; a cycloalkylcarbonylamino group having from 3 to 6 carbon atoms in the cycloalkyl moiety; an alkoxy group having from 2 to 4 carbon atoms; a benzoyl group which may have optionally from 1 to 2 substituents; a benzyl group which may have optionally from 1 to 2 substituents; or an alkoxycarbonylalkenylene group having from 1 to 6 carbon atoms in the alkoxy moiety and having from 2 to 5 carbon atoms in the alkenylene moiety; and R¹ and R² do not represent hydrogen atoms at the same time. More preferred ones include those in which:

[0030] (2) R¹ and R² are the same or different and each represents a hydrogen atom; an alkyl group having from 2 to 6 carbon atoms; an alkenyl group having from 3 to 4 carbon atoms; a cycloalkyl group having from 5 to 6 carbon atoms; an alkoxycarbonyl group having from 1 to 3 carbon atoms in the alkoxy moiety; an alkoxymethylene group having from 1 to 6 carbon atoms in the alkoxy moiety; a cycloalkylcarbonylamino group having from 4 to 6 carbon atoms in the cycloalkyl moiety; a benzoyl group; a benzyl group which may have optionally 1 substituent; or an alkoxycarbonylalkenylene group having from 1 to 3 carbon atoms in the alkoxy moiety and having from 2 to 4 carbon atoms in the alkenylene moiety; and R¹ and R² do not represent hydrogen atoms at the same time. Particularly preferred ones include those in which:

[0031] (3) R¹ is a 3-alkyl group having from 2 to 6 carbon atoms; a 3-alkoxycarbonyl group having from 1 to 3 carbon atoms in the alkoxy moiety; a 3-alkoxymethylene group having from 1 to 3 carbon atoms in the alkoxy moiety; a cycloalkylcarbonylamino group having from 4 to 6 carbon atoms in the cycloalkyl moiety; a benzyl group which may be substituted by a methoxy group; a benzoyl group; or an alkoxycarbonylalkenylene group having from 1 to 3 carbon atoms in the alkoxy moiety and having from 2 to 3 carbon atoms in the alkenylene moiety; and

[0032] (4) R² is a hydrogen atom.

[0033] Novel dimethylfurancarboxyanilide derivatives which may be used as an active ingredient of the wood preservative of the present invention are exemplified in the following table.

[0034] In Table 1 below, abbreviations are used as follows.

Bz	Benzyl
Bu	Butyl
Et	Ethyl
Hx	Hexyl
Me	Methyl
Ph	Phenyl
Pip	Piperidyl
Pn	Pentyl
Pr	Propyl
i	iso
s	secondary
t	tertiary
c	cyclo

[0035]




TABLE 1		
Compound No.	R ¹	R ²
1	3-CF ₃	H
2	4-CF ₃	H
3	3-CH ₂ OMe	H
4	4-CH ₂ OMe	H
5	2-Et	H
6	3-Et	H
7	4-Et	H
8	3-C≡CH	H
9	4-C≡CH	H
10	3-CH ₂ OEt	H
11	4-CH ₂ OEt	H
12	2-Et	3-Et
13	2-Et	4-Et
14	2-Et	5-Et
15	2-Et	6-Et
16	3-Et	4-Et
17	3-Et	5-Et
18	3-Et	6-Et
19	3-Pr	H
20	4-Pr	H
21	2- <i>i</i> Pr	H
22	3- <i>i</i> Pr	H
23	4- <i>i</i> Pr	H
24	3- <i>g</i> Pr	H
25	4- <i>g</i> Pr	H
26	3-CH ₂ OPr	H
27	3-CH ₂ O <i>i</i> Pr	H
28	4-CH ₂ O <i>i</i> Pr	H
29	3-CH ₂ C=CH ₂	H
30	4-CH ₂ C=CH ₂	H
31	3-CH ₂ C≡CH	H
32	4-CH ₂ C≡CH	H
33	3-Pr	4-Pr
34	2- <i>i</i> Pr	4- <i>i</i> Pr
35	3- <i>i</i> Pr	5- <i>i</i> Pr
36	3-CH ₂ OBu	H
37	4-CH ₂ OBu	H
38	3-CH ₂ O <i>i</i> Bu	H
39	4-CH ₂ O <i>i</i> Bu	H
40	3-CH ₂ O <i>s</i> Bu	H
41	4-CH ₂ O <i>s</i> Bu	H
42	3-Bu	H
43	4-Bu	H
44	3- <i>i</i> Bu	H
45	3- <i>s</i> Bu	H
46	3- <i>g</i> Bu	H
47	4- <i>g</i> Bu	H
48	3- <i>t</i> Bu	H
49	3-CH ₂ CH=CHMe	H
50	3-CH ₂ C≡CMe	H
51	3-CH ₂ MeCH=CH ₂	H
52	4-CH ₂ MeCH=CH ₂	H

TABLE 1-continued

Compound No.	R ¹	R ²
53	3-Pn	H
54	4-Pn	H
55	3-iPn	H
56	3-gPn	H
57	3-neoPn	H
58	3-CH ₂ OPn	H
59	3-CH ₂ O _{neo} -Pn	H
60	3-Hx	H
61	3-iHx	H
62	3-gHx	H
63	3-CN	H
64	3-OEt	H
65	3-O _i Pr	H
66	3-CONHMe	H
67	3-(CO-1-Pip)	H
68	3-CONHPh	H
69	3-COOMe	H
70	3-COOEt	H
71	3-COOPr	H
72	3-COO _i Pr	H
73	3-COOBu	H
74	3-COO _t Bu	H
75	3-COPh	H
76	3-CO(2-MePh)	H
77	3-NHCOPh	H
78	3-NHCOMe	H
79	3-NHCOBu	H
80	3-NHCO _g Pn	H
81	3-NHCO _g Hx	H
82	3-Bz	H
83	3-(4-MeOBz)	H
84	3-(4-MeBz)	H
85	3-CH=CHCOOMe	H
86	3-Ph	H
87	3-(2-MePh)	H

[0036] Among the compounds above, preferred ones include Compounds Nos. 3, 4, 5, 6, 7, 8, 10, 11, 15, 16, 17, 18, 19, 20, 21, 22, 23, 24, 25, 26, 27, 28, 29, 31, 33, 35, 36, 38, 40, 42, 43, 44, 45, 46, 48, 49, 50, 51, 53, 54, 55, 56, 57, 58, 59, 60, 61, 62, 64, 69, 70, 71, 72, 75, 80, 81, 82, 83 and 85; and more preferred ones include Compounds Nos. 3, 6, 10, 19, 22, 24, 26, 27, 33, 35, 36, 38, 40, 42, 44, 45, 46, 48, 53, 55, 60, 61, 69, 70, 81, 83 and 85.

[0037] The compounds of the said general formula (I) may be prepared according to the procedure summarized in either the following Method A or Method B.



[0038] In the above formulae, R¹ and R² are as defined above. R^{1'} represents a C₁-C₆ alkyl, C₃-C₆ cycloalkyl or benzyl group which may optionally have 1 or 2 substituents. The compound of formula (Ia) is that of a general formula (I), in which R¹ is R^{1'} and R² signifies a hydrogen atom. The compound of formula (V) is iodine-substituted aniline. X signifies a halogen atom such as chlorine, bromine or iodine, preferably chlorine. X' signifies a halogen atom such as a chlorine, bromine or iodine, preferably bromine or iodine.

[0039] The compounds of the present invention may be prepared by well-known procedure.

[0040] Step A1 consists of the preparation of a compound of general formula (I) by reacting a compound of general formula (III) with a compound of general formula (IV) in an inert solvent in the presence of a dehydrohalogenating agent.

[0041] A compound of formula (III) used as a starting material in this step may be prepared by hydrolyzing 2,5-dimethylfuran-3-carboxylate, which may be prepared by condensing chloroacetone with acetoacetate, followed by halogenation.

[0042] A compound of formula (IV) used as a starting material in this step is an aniline derivative which is commercially available or may be prepared by well-known methods.

[0043] Examples of the inert solvents used include, for example, ethers such as ether, isopropyl ether, tetrahydrofuran or dioxane; aromatic hydrocarbons such as benzene, toluene or xylene; halogenated hydrocarbons such as dichloromethane, chloroform or carbon tetrachloride; and mixtures of two or more of these solvents; preferably aromatic hydrocarbons (particularly toluene).

[0044] Examples of dehydrohalogenating agents used include, for example, tertiary amines such as triethylamine, N,N-dimethylaminopyridine or the like and pyridines. This reaction can be carried out in the presence or absence of a solvent. In order to perform the reaction smoothly, using a solvent, the reaction is carried out at a temperature of 0° C. to reflux temperature of the solvent used, preferably from room temperature to 100° C. The time required for the reaction takes generally from 30 minutes to 5 hours, preferably from 30 minutes to 2 hours.

[0045] Step B1 consists of the preparation of a compound having general formula (VI) by reacting a compound having general formula (III) with a compound having general formula (V) in an inert solvent in the presence of a dehydrohalogenating agent.

[0046] A compound of formula (IV) used as a starting material in this step is an aniline derivative which is commercially available or may be prepared by well-known methods.

[0047] The reaction conditions employed in this step are similar to those employed in Step A1.

[0048] Step B2 consists of the preparation of a compound having general formula (Ia) by reacting a compound having general formula (VI) with a Grignard reagent having general formula: R^1MgX^1 in an inert solvent in the presence of a catalyst.

[0049] Examples of preferred inert solvents used include, for example, ethers such as diethyl ether, isopropyl ether, tetrahydrofuran or dioxane; particularly preferably diethyl ether.

[0050] As a particularly preferred catalyst there may be used [1,1'-bis(diphenylphosphino)ferrocene]palladium(II) chloride.

[0051] The Grignard reagents used in this process are commercially available or can be prepared by reacting magnesium with an alkyl halide represented by formula: R^1X^1 (wherein R^1 and X^1 are as defined above) according to well-known methods.

[0052] The reaction is normally carried out at a temperature of 0° C. to 50° C., preferably at room temperature. Although the time required for the reaction varies depending upon the nature of the solvent and reagent to be used, the reaction is normally complete within a period of 10 hours to 10 days.

[0053] The compounds having the said general formula (I) in according with the invention have potent wood preservative activity at low concentration, compared with the activity shown by existing wood preservatives. A composition consisting of a combination of the foregoing compound (I) with a known wood preservative gives a synergistic effect, lower concentrations of each compound being required than would be expected from the activity shown by

each singly, such that the composition shows efficient wood preservative activity at a low concentration. Therefore, novel dimethylfurancarboxyanilide derivatives are extremely effective as a wood preservative in low concentration so as to solve one of the problems in the quality of life.

[0054] The following Examples illustrate the preparation and the formulation of the compound of the invention in more detail. Such examples are not to be construed as being limitative of the scope of the invention.

EXAMPLE 1

2,5-Dimethylfuran-3-carboxy(3-acetylaminooanilide)

[0055] To a solution of 0.50 g of 2,5-dimethylfuran-3-carbonyl chloride in 10 ml of dichloromethane were added 0.44 ml of triethylamine and 0.47 g of 3-acetylaminooaniline under ice-cooling, and the resulting mixture was stirred at room temperature for 2.5 hours followed by heating under reflux for 4.5 hours. After the reaction mixture was cooled, it was diluted by adding 10 ml of dichloromethane. The diluted mixture was successively washed with 1 N sodium hydroxide, 1 N hydrochloric acid and a saturated aqueous solution of sodium chloride and dried over sodium sulfate followed by distilling off the solvent. The residue was purified by column chromatography through silica gel and the desired fractions were recrystallized from ethyl acetate to give 0.51 g of the desired compound as white crystals in a 59.4% yield.

[0056] m.p.: 172.0-172.5° C.

[0057] 1H NMR ($CDCl_3$ +DMSO) δ ppm: 8.4 (1H, b), 7.95 (1H, b), 7.88 (1H, m), 7.4 (1H, m), 7.32 (1H, m), 7.25 (1H, t, J=8 Hz), 6.25 (1H, s), 2.55 (3H, s), 2.25 (3H, s), 2.15 (3H, s)

[0058] IR (KBr) cm^{-1} : 3306, 1672, 1651, 1086, 781

[0059] Elemental analysis (%): Calc'd for $C_{15}H_{16}N_2O_3$: C, 66.16; H, 5.92; N, 10.29. Found: C, 66.30; H, 5.98; N, 10.32.

[0060] Following the similar procedure as above, but using an appropriate aniline derivative instead of 3-acetylaminooaniline, there were obtained the following compounds.

EXAMPLE 2

2,5-Dimethylfuran-3-carboxy[3-(N-methylcarbamoyl)anilide]

[0061] Yield: 42.0%

[0062] m.p.: 212.0-213.0° C.

[0063] 1NMR ($CDCl_3$ +DMSO) δ ppm: 8.5 (1H, b), 8.05 (1H, m), 7.88 (1H, m), 7.52 (1H, m), 7.38 (1H, t, J=8 Hz), 6.8 (1H, b), 6.35 (1H, s), 2.95 (3H, d, J=1.4 Hz), 2.55 (3H, s), 2.25 (3H, s).

[0064] IR (KBr) cm^{-1} : 3293, 1638, 1581, 1074, 689

[0065] Elemental analysis (%): Calc'd for $C_{15}H_{16}N_2O_3$: C, 66.16; H, 5.92; N, 10.29. Found: C, 66.08; H, 6.20; N, 10.28.

EXAMPLE 3

2,5-Dimethylfuran-3-carboxy[3-(1-piperidylcarbonyl)anilide]

[0066] Yield: 50.0%

[0067] m.p.: 183.0-185.0° C.

[0068] ¹H NMR spectrum (CDCl₃) δ ppm: 7.68 (1H, m), 7.55 (2H, m), 7.35 (1H, t, J=8 Hz), 7.1 (1H, m), 6.15 (1H, s), 3.7 (2H, b), 3.35 (2H, b), 2.55 (3H, s), 2.25 (3H, s), 2.75-1.4 (6H, m)[0069] IR (KBr) cm⁻¹: 3302, 1663, 1615, 1065, 808[0070] Elemental analysis (%): Calc'd for C₁₉H₂₂N₂O₃: C, 69.92; H, 6.79; N, 8.58. Found: C, 69.52; H, 6.88; N, 8.48.

EXAMPLE 4

2,5-Dimethylfuran-3-carboxy[3-(N-phenylcarbamoyl)anilide]

[0071] Yield: 53.5%

[0072] m.p.: 182.5-184.0° C.

[0073] ¹H NMR (CDCl₃+DMSO) δ ppm: 8.48 (1H, b), 8.2 (1H, b), 8.1 (1H, s), 7.95 (1H, m), 7.7 (2H, d, J=8 Hz), 7.65 (1H, d, J=8 Hz), 7.45 (1H, t, J=8 Hz), 7.35 (2H, t, J=8 Hz), 7.15 (1H, t, J=8 Hz), 6.28 (1H, s), 2.55 (3H, s), 2.25 (3H, s)[0074] IR (KBr) cm⁻¹: 3282, 1646, 1080, 755, 691[0075] Elemental analysis (%): Calc'd for C₂₀H₁₈N₂O₃: C, 71.84; H, 5.43; N, 8.38. Found: C, 71.87; H, 5.64; N, 8.34.

EXAMPLE 5

2,5-Dimethylfuran-3-carboxy(3-tert-butoxycarbonyl anilide)

[0076] Yield: 92.0%

[0077] m.p.: 117.0-118.0° C.

[0078] ¹H NMR (CDCl₃) δ ppm: 8.05 (1H, m) 7.88 (1H, m) 7.75 (1H, m), 7.4 (1H, t, J=8 Hz), 7.35 (1H, b), 6.1 (1H, s), 2.55 (3H, s), 2.25 (3H, s), 1.65 (9H, s)[0079] IR (KBr) cm⁻¹: 3362, 1687, 1672, 1067, 757[0080] Elemental analysis (%): Calc'd for C₁₈H₂₁NO₄: C, 68.55; H, 6.71; N, 4.44. Found: C, 68.04; H, 7.00; N, 4.40.

EXAMPLE 6

2,5-Dimethylfuran-3-carboxy(3-methoxycarbonyl anilide)

[0081] Yield: 77.1%

[0082] m.p.: 104.0-106.0° C.

[0083] ¹H NMR (CDCl₃) δ ppm: 8.05 (1H, m), 7.98 (1H, m), 7.8 (1H, m), 7.42 (1H, t, J=8 Hz), 7.38 (1H, b), 6.1 (1H, s), 3.92 (3H, s), 2.55 (3H, s), 2.25 (3H, s)[0084] IR (KBr) cm⁻¹: 3437, 1704, 1675, 1070, 759[0085] Elemental analysis (%): Calc'd for C₁₅H₁₅NO₄: C, 65.92; H, 5.53; N, 5.13. Found: C, 66.02; H, 5.60; N, 5.08.

EXAMPLE 7

2,5-Dimethylfuran-3-carboxy(3-benzoylanilide)

[0086] Yield: 69.1%

[0087] m.p.: 137.0-139.0° C.

[0088] ¹H NMR (CDCl₃) δ ppm: 8.05 (1H, m), 7.85-7.7 (3H, m), 7.6 (1H, m), 7.55-7.35 (5H, m), 6.1 (1H, s), 2.55 (3H, s), 2.25 (3H, s)[0089] IR (KBr) cm⁻¹: 3386, 1672, 1647, 1069, 707[0090] Elemental analysis (%): Calc'd for C₂₀H₁₇NO₃: C, 75.22; H, 5.37; N, 4.39. Found: C, 75.38; H, 5.43; N, 4.38.

EXAMPLE 8

2,5-Dimethylfuran-3-carboxy(3-benzoylaminoanilide)

[0091] Yield: 46.0%

[0092] m.p.: 194.5-195.0° C.

[0093] ¹H NMR (CDCl₃+DMSO) δ ppm: 8.7 (1H, b), 8.1 (1H, m), 7.95 (1H, b), 7.9 (2H, m), 7.6-7.4 (5H, m), 7.3 (1H, t, J=8 Hz), 6.25 (1H, s), 2.55 (3H, s), 2.25 (3H, s)[0094] IR (KBr) cm⁻¹: 3283, 1642, 1074, 791, 705[0095] Elemental analysis (%): Calc'd for C₂₀H₁₈N₁O₃: C, 71.84; H, 5.43; N, 8.38. Found: C, 71.96; H, 5.53; N, 8.28.

EXAMPLE 9

2,5-Dimethylfuran-3-carboxy(3-valeryl aminoanilide)

[0096] Yield: 70.3%

[0097] m.p.: 104.0-105.0° C.

[0098] ¹H NMR (CDCl₃) δ ppm: 7.9 (1H, b), 7.45-7.1 (5H, m), 6.1 (1H, s), 2.55 (3H, s), 2.35 (2H, t, J=7 Hz), 2.25 (3H, s), 1.7 (2H, m), 1.4 (2H, m), 0.95 (1H, t, J=7 Hz)[0099] IR (KBr) cm⁻¹: 3250, 1660, 1644, 1074, 781[0100] Elemental analysis (%): Calc'd for C₁₈H₂₂N₂O₃: C, 68.77; H, 7.05; N, 8.91. Found: C, 68.73; H, 7.17; N, 8.90.

EXAMPLE 10

2,5-Dimethylfuran-3-carboxy(3-cyclohexylcarbonyl aminoanilide)

[0101] Yield: 45.1%

[0102] m.p.: 212.5-213.0° C.

[0103] ¹H NMR (CDCl₃) δ ppm: 7.92 (1H, b), 7.88 (1H, b), 7.45-7.35 (2H, m), 7.25 (1H, t, J=8 Hz), 6.22 (1H, s), 2.55 (3H, s), 2.25 (3H, s), 2.25-2.2 (1H, m), 2.0-1.2 (10H, m)[0104] IR (KBr) cm⁻¹: 3238, 1651, 1639, 1076, 781[0105] Elemental analysis (%): Calc'd for C₂₀H₂₄N₂O₃: C, 70.57; H, 7.11; N, 8.23. Found: C, 70.56; H, 7.26; N, 8.16

EXAMPLE 11

2,5-Dimethylfuran-3-carboxy(3-methoxymethylanilide)

[0106] Yield: 73.3%

[0107] m.p.: 102.5-103.5° C.

[0108] ^1H NMR (CDCl_3) δ ppm: 7.55 (1H, m), 7.52 (1H, d, J=8 Hz), 7.32 (1H, t, J=8 Hz), 7.32 (1H, b), 6.9 (1H, d, J=8 Hz), 6.1 (1H, s), 4.45 (2H, s), 3.4 (3H, s), 2.55 (3H, s), 2.25 (3H, s)[0109] IR (KBr) cm^{-1} : 3278, 1645, 1237, 1107, 784[0110] Elemental analysis (%): Calc'd for $\text{C}_{15}\text{H}_{17}\text{NO}_3$: C, 69.48; H, 6.61; N, 5.40. Found: C, 69.22; H, 7.02; N, 5.37.

EXAMPLE 12

2,5-Dimethylfuran-3-carboxy(3-ethoxymethylanilide)

[0111] Yield: 64.4%

[0112] m.p.: 85.0-85.5° C.

[0113] ^1H NMR (CDCl_3) δ ppm: 7.65-7.55 (2H, m), 7.38 (1H, t, J=8 Hz), 7.35 (1H, b), 7.15 (1H, d, J=8 Hz), 6.15 (1H, s), 4.55 (2H, s), 3.58 (2H, q, J=8 Hz), 2.55 (3H, s), 2.25 (3H, s), 1.3 (3H, t, J=8 Hz)[0114] IR (KBr) cm^{-1} : 3279, 1646, 1115, 785[0115] Elemental analysis (%): Calc'd for $\text{C}_{16}\text{H}_{19}\text{NO}_3$: C, 70.31; H, 7.01; N, 5.12. Found: C, 70.14; H, 7.27; N, 5.06.

EXAMPLE 13

2,5-Dimethylfuran-3-carboxy(3-isopropoxyethyl anilide)

[0116] Yield: 92.7%

[0117] m.p.: 68.0-69.50° C.

[0118] ^1H NMR (CDCl_3) δ ppm: 7.55 (1H, d, J=8 Hz), 7.5 (1H, m), 7.3 (1H, t, J=8 Hz), 7.3 (1H, b), 7.12 (1H, d, J=8 Hz), 6.1 (1H, s), 4.5 (2H, s), 3.7 (1H, m), 2.55 (3H, s), 2.25 (3H, s), 1.25 (6H, d, J=7 Hz)[0119] IR (Liquid film) cm^{-1} : 3321, 1651, 1072, 785[0120] Elemental analysis (%): Calc'd for $\text{C}_{17}\text{H}_{21}\text{NO}_3$: C, 71.06; H, 7.37; N, 4.87. Found: C, 70.35; H, 7.14; N, 4.91.

EXAMPLE 14

2,5-Dimethylfuran-3-carboxy[3-(4-methoxybenzyl) anilide]

[0121] Yield: 86.8%

[0122] m.p.: 100.0-102.5° C.

[0123] ^1H NMR (CDCl_3) δ ppm: 7.45 (1H, m), 7.35 (1H, m), 7.25 (1H, t, J=8 Hz), 7.25 (1H, b), 7.1 (2H, d, J=8 Hz), 6.92 (1H, d, J=8 Hz), 6.88-6.75 (1H, m), 6.82 (2H, d, J=8 Hz), 6.05 (1H, s), 3.9 (2H, s), 3.75 (3H, s), 2.55 (3H, s), 2.25 (3H, s)[0124] IR (KBr) cm^{-1} : 3345, 1656, 1246, 1074, 694[0125] Elemental analysis (%): Calc'd for $\text{C}_{21}\text{H}_{21}\text{NO}_3$: C, 75.20; H, 6.31; N, 4.18. Found: C, 75.28; H, 6.32; N, 4.21.

EXAMPLE 15

2,5-Dimethylfuran-3-carboxy[3-(2-methoxycarbonyl vinyl)anilide]

[0126] Yield: 63.3%

[0127] m.p.: 159.5-161.5° C.

[0128] ^1H NMR (CDCl_3) δ ppm: 7.82 (1H, m), 7.7 (1H, d, J=15 Hz), 7.58 (1H, m), 7.38 (1H, b), 7.35 (1H, t, J=8 Hz), 7.28 (1H, m), 6.48 (1H, d, J=15 Hz), 6.12 (1H, s), 3.82 (3H, s), 2.55 (3H, s), 2.25 (3H, s)[0129] IR (KBr) cm^{-1} : 3387, 1685, 1670, 1068, 800[0130] Elemental analysis (%): Calc'd for $\text{C}_{17}\text{H}_{17}\text{NO}_4$: C, 68.22; H, 5.72; N, 4.68. Found: C, 67.55; H, 5.64; N, 4.62.

EXAMPLE 16

2,5-Dimethylfuran-3-carboxy(3-phenylanilide)

[0131] Yield: 50.0%

[0132] m.p.: 90.0-92.0° C.

[0133] ^1H NMR (CDCl_3) δ ppm: 7.82 (1H, s), 7.6 (2H, d, J=8 Hz), 7.55 (1H, d, J=8 Hz), 6.48-6.3 (6H, m), 6.12 (1H, s), 2.55 (3H, s), 2.25 (3H, s)[0134] IR (KBr) cm^{-1} : 3367, 1646, 1074, 755[0135] Elemental analysis (%): Calc'd for $\text{C}_{19}\text{H}_{17}\text{NO}_2$: C, 78.33; H, 5.88; N, 4.81. Found: C, 78.17; H, 6.00; N, 4.72.

EXAMPLE 17

2,5-Dimethylfuran-3-carboxy(3-neopentyloxymethyl anilide)

[0136] Yield: 50.0%

[0137] m.p.: 95.5-97.0° C.

[0138] ^1H NMR (CDCl_3) δ ppm: 7.48 (2H, m), 7.32 (1H, t, J=8 Hz), 7.3 (1H, b), 7.12 (1H, d, J=8 Hz), 4.52 (2H, s), 3.12 (2H, s), 2.55 (3H, s), 2.25 (3H, s), 0.95 (9H, s)[0139] IR (KBr) cm^{-1} : 3324, 1646, 1091, 700[0140] Elemental analysis (%): Calc'd for $\text{C}_{19}\text{H}_{25}\text{NO}_3$: C, 72.35; H, 7.99; N, 4.44. Found: C, 72.38; H, 8.03; N, 4.20.

EXAMPLE 18

2,5-Dimethylfuran-3-carboxy(3-isopropenylanilide)

[0141] Yield: 50.0%

[0142] m.p.: 71.0-72.0° C.

[0143] ^1H NMR (CDCl_3) δ ppm: 7.65 (1H, m), 7.5 (1H, m), 7.3 (1H, b), 7.3 (1H, t, J=8 Hz), 7.22 (1H, m), 6.12 (1H, s), 5.4 (1H, s), 5.1 (1H, s), 2.6 (3H, s), 2.55 (3H, s), 2.25 (3H, s)[0144] IR (KBr) cm^{-1} : 3275, 1641, 1580, 1078, 790[0145] Elemental analysis (%): Calc'd for $\text{C}_{16}\text{H}_{17}\text{NO}_2$: C, 75.27; H, 6.71; N, 5.49. Found: C, 75.29; H, 6.88; N, 5.48.

EXAMPLE 19

2,5-Dimethylfuran-3-carboxy(3-ethynylanilide)

[0146] Yield: 50.0%

[0147] m.p.: 83.0-84.0° C.

[0148] ¹H NMR (CDCl₃) δ ppm: 7.7 (1H, m), 7.6 (1H, m), 7.32-7.2 (3H, m), 6.1 (1H, s), 3.05 (1H, s), 2.55 (3H, s), 2.25 (3H, s)

[0149] IR (KBr) cm⁻¹: 3245, 1644, 1079, 796

[0150] Elemental analysis (%): Calc'd for C₁₅H₁₃NO₂: C, 75.30; H, 5.48; N, 5.85. Found: C, 75.50; H, 5.46; N, 5.96.

EXAMPLE 20

2,5-Dimethylfuran-3-carboxy(3-ethylanilide)

[0151] Yield: 91.0%

[0152] m.p.: 113-115° C.

[0153] Mass (m/z): 243 (M⁺), 123.94

[0154] ¹H NMR (CDCl₃) δ ppm: 7.47-6.95 (4H, m), 6.1 (1H, s), 2.66 (3H, q), 2.60 (3H, s), 2.29 (3H, s), 1.25 (3H, t)

EXAMPLE 21

2,5-Dimethylfuran-3-carboxy(3-isopropylanilide)

[0155] Yield: 84.0%

[0156] m.p.: 79-80° C.

[0157] Mass (m/z): 257 (M⁺), 149.135

[0158] ¹H NMR (CDCl₃) δ ppm: 7.47-6.98 (4H, m), 6.11 (1H, s), 2.91 (1H, q,q), 2.60 (3H, s), 2.29 (3H, s), 1.26 (d, 6H)

EXAMPLE 22

2,5-Dimethylfuran-3-carboxy(2,6-diethylanilide)

[0159] Yield: 85.2%

[0160] m.p.: 128.0-131.0° C.

[0161] Mass (m/z): 271 (M⁺), 242.228

[0162] ¹NMR (CDCl₃) δ ppm: 7.28-7.12 (3H, m), 6.82 (1H, b), 6.16 (1H, s), 2.63 (4H, q), 2.58 (3H, s), 2.31 (3H, s), 1.20 (6H, t)

EXAMPLE 23

2,5-Dimethylfuran-3-carboxy(3-hexylanilide)

[0163] (Step 1)

[0164] To a solution of 3.95 g of 2,5-dimethylfuran-3-carbonyl chloride in 60 ml of dichloromethane were added 3.45 ml of triethylamine and 2.99 ml of m-iodoaniline under ice-cooling, and the resulting mixture was stirred at room temperature for 6.5 hours. After the reaction mixture was cooled, it was diluted by adding 50 ml of dichloromethane. The diluted mixture was successively washed with 1 N sodium hydroxide, 1 N hydrochloric acid and a saturated aqueous solution of sodium chloride and dried over sodium sulfate followed by distilling off the solvent. The residue

was subjected to column chromatography through silica gel to give 7.64 g of 2,5-dimethylfuran-3-carboxy(3-iodoanilide) as pale-yellow crystals in a 89.9% yield.

[0165] (Step 2)

[0166] To a solution of 0.68 g of the crystals obtained in Step 1 in 8 ml of diethyl ether were added 29.3 mg of [1,1'-bis(diphenylphosphino)ferrocene]palladium(II) chloride and 11 ml of 1 M hexylmagnesium bromide, prepared from hexyl bromide and magnesium, divided into six equal parts, and the resulting mixture was stirred at room temperature for 47 hours. After adding 2 N hydrochloric acid to the reaction mixture, the catalyst was filtered off and the filtrate was extracted with diethyl ether. The extract was successively washed with an aqueous solution of sodium bicarbonate and a saturated aqueous solution of sodium chloride and dried over sodium sulfate. After distilling off the solvent, the residue was purified by chromatography through silica gel and then D-ODS-5, YMC-packed column to give 316 mg of the desired compound as white crystals in a 52.8% yield.

[0167] m.p.: 71.5-72.0° C.

[0168] ¹H NMR (CDCl₃) δ ppm: 7.45 (1H, m), 7.35 (1H, m), 7.25 (1H, b), 7.22 (1H, t, J=8 Hz), 6.95 (1H, d, J=8 Hz), 6.1 (1H, s), 2.65-2.5 (2H, m), 2.55 (3H, s), 2.25 (3H, s), 1.7-1.5 (2H, m), 1.4-1.2 (6H, m), 0.85 (3H, t, J=7 Hz)

[0169] IR (KBr) cm⁻¹: 3310, 1643, 1077, 788

[0170] Elemental analysis (%): Calc'd for C₁₉H₂₅NO₂: C, 76.22; H, 8.42; N, 4.68. Found: C, 76.15; H, 8.54; N, 4.55

[0171] Following the similar procedure as above, but using an appropriate Grignard reagent instead of hexylmagnesium bromide, there were obtained the following compounds.

EXAMPLE 24

2,5-Dimethylfuran-3-carboxy (3-butylanilide)

[0172] Yield: 36.4%

[0173] m.p.: 77.0-80.0° C.

[0174] ¹H NMR (CDCl₃) δ ppm: 7.45 (1H, m), 7.35 (1H, m), 7.25 (1H, b), 7.22 (1H, t, J=6 Hz), 6.95 (1H, d, J=8 Hz), 6.1 (1H, s), 2.65-2.55 (2H, m), 2.55 (3H, s), 2.25 (3H, s), 1.6 (2H, m), 1.35 (2H, m), 0.92 (1H, t, J=7 Hz)

[0175] IR (KBR) cm⁻¹: 3285, 1646, 1075, 702

[0176] Elemental analysis (%): Calc'd for C₁₇H₂₁NO₂: C, 75.25; H, 7.80; N, 5.16. Found: C, 75.13; H, 7.87; N, 5.13

EXAMPLE 25

2,5-Dimethylfuran-3-carboxy(3-sec-butylanilide)

[0177] Yield: 38.1%

[0178] m.p.: 80.0-81.0° C.

[0179] ¹H NMR (CDCl₃) δ ppm: 7.4 (1H, m), 7.38 (1H, m), 7.25 (1H, b), 7.22 (1H, t, J=8 Hz), 6.95 (1H, d, J=8 Hz), 6.1 (1H, s), 2.65-2.5 (1H, m), 2.55 (3H, s), 2.25 (3H, s), 1.68-1.5 (2H, m), 1.25 (3H, d, J=7 Hz), 0.85 (3H, t, J=7 Hz)

[0180] IR (KBr) cm⁻¹: 3255, 1647, 1078, 791

[0181] Elemental analysis (%): Calc'd for $C_{17}H_{21}NO_2$: C, 75.25; H, 7.80; N, 5.16. Found: C, 75.19; H, 7.68; N, 5.14

EXAMPLE 26

2,5-Dimethylfuran-3-carboxy(3-pentylanilide)

[0182] Yield: 18.3%

[0183] m.p.: 97.0-97.5° C.

[0184] 1H NMR ($CDCl_3$) δ ppm: 7.45 (1H, m), 7.35 (1H, m), 7.28 (1H, b), 7.25 (1H, t, J=8 Hz), 6.95 (1H, d, J=8 Hz), 6.1 (1H, s), 2.65-2.5 (2H, m), 2.55 (3H, s), 2.25 (3H, s), 1.7-1.5 (2H, m), 1.4-1.2 (4H, m), 0.88 (3H, t, J=7 Hz)

[0185] IR (KBr) cm^{-1} : 3304, 1644, 1077, 710

[0186] Elemental analysis (%): Calc'd for $C_{18}H_{23}NO_2$: C, 75.76; H, 8.12; N, 4.91. Found: C, 75.77; H, 8.18; N, 5.06

EXAMPLE 27

2,5-Dimethylfuran-3-carboxy-(3-cyclohexylanilide)

[0187] Yield: 52.7%

[0188] m.p.: 113.0-114.5° C.

[0189] 1H NMR ($CDCl_3$) δ ppm: 7.48 (1H, m), 7.35 (1H, m), 7.28 (1H, b), 7.25 (1H, t, J=8 Hz), 6.98 (1H, d, J=8 Hz), 6.1 (1H, s), 2.55 (3H, s), 2.55-2.45 (1H, m), 2.25 (3H, s), 1.95-1.68 (5H, m), 1.55-1.15 (5H, m)

[0190] IR (KBr) cm^{-1} : 3324, 1646, 1230, 1074, 791

[0191] Elemental analysis (%): Calc'd for $C_{19}H_{23}NO_2$: C, 76.74; H, 7.80; N, 4.71. Found: C, 76.62; H, 7.78; N, 4.67

EXAMPLE 28

2,5-Dimethylfuran-3-carboxy(3-cyclopentylanilide)

[0192] Yield: 35.9%

[0193] m.p.: 92.0-93.0° C.

[0194] 1H NMR ($CDCl_3$) δ ppm: 7.45 (1H, m), 7.35 (1H, m), 7.25 (1H, b), 7.22 (1H, t, J=8 Hz), 7.00 (1H, d, J=8 Hz), 6.1 (1H, s), 3.08-2.9 (1H, m), 2.55 (3H, s), 2.25 (3H, s), 2.15-1.95 (2H, m), 1.9-1.5 (6H, m)

[0195] IR (KBr) cm^{-1} : 3322, 1647, 1232, 1076, 700

[0196] Elemental analysis (%): Calc'd for $C_{18}H_{21}NO_2$: C, 76.30; H, 7.47; N, 4.94. Found: C, 76.21; H, 7.56; N, 4.93

EXAMPLE 29

2,5-Dimethylfuran-3-carboxy(3-benzylanilide)

[0197] Yield: 59.8%

[0198] m.p.: 123.0-125.0° C.

[0199] 1H NMR ($CDCl_3$) δ ppm: 7.45 (1H, m), 7.38 (1H, m), 7.35-7.15 (7H, m), 6.95 (1H, d, J=8 Hz), 3.98 (2H, s), 2.55 (3H, s), 2.25 (3H, s)

[0200] IR (KBr) cm^{-1} : 3314, 1640, 1078, 777, 701

[0201] Elemental analysis (%): Calc'd for $C_{21}H_{19}NO_2$: C, 78.66; H, 6.27; N, 4.59. Found: C, 77.76; H, 6.28; N, 4.55

REFERENTIAL EXAMPLE 1

Ethyl 2,5-dimethylfuran-3-carboxylate

[0202] To a suspension of 2.4 g of sodium hydride (60% dispersion in mineral oil) in 10 ml of N,N-dimethylformamide (hereinafter, abbreviated as DMF) a solution of 6.5 ml of ethyl acetoacetate in 5 ml of DMF was added dropwise with stirring under ice-cooling, and 5.97 ml of chloroacetone were added dropwise thereto with stirring under ice-cooling. After stirring at room temperature for 3 hours, the reaction mixture was poured into water and the aqueous mixture was extracted with ethyl acetate. The extract was washed with a saturated aqueous solution of sodium chloride and dried over anhydrous sodium sulfate. After distilling off the solvent under reduced pressure, the residue was distilled in vacuo to give 8.01 g of ethyl α -acetoneitrile-acetoacetate having b.p. 105° C./2 mmHg in a 86% yield.

[0203] To a solution of the ester thus obtained in 20 ml of ethanol were added 2 g of p-toluenesulfonic acid, and the resulting mixture was heated under reflux for 2 hours. The reaction mixture was allowed to cool to room temperature and the solvent was distilled off under reduced pressure. The residue was dissolved in ethyl acetate and the solution was washed with a saturated aqueous solution of sodium chloride followed by drying over anhydrous magnesium sulfate. After distilling off the solvent under reduced pressure, the residue was purified by column chromatography through silica gel using a 10:1 mixture of n-hexane and ethyl acetate as an eluent to give 5.14 g of ethyl 2,5-dimethylfuran-3-carboxylate in a 71% yield.

REFERENTIAL EXAMPLE 2

2,5-Dimethylfuran-3-carboxylic Acid

[0204] A mixture of 3.2 g of ethyl 2,5-dimethylfuran-3-carboxylate, 35 ml of ethanol and 20 ml of 2 N sodium hydroxide was stirred at room temperature for 1.5 hours followed by heating under reflux for an hour. After the reaction mixture was allowed to cool to room temperature, it was concentrated under reduced pressure. The residue was dissolved in water and acidified with diluted sulfuric acid. Precipitated crystals were collected by filtration, washed with water and dried to give 2.27 g of 2,5-dimethylfuran-3-carboxylic acid in a 85% yield.

[0205] The compound having the general formula (I) mentioned above and the composition containing the compound (I) as the active ingredient, with which the present invention are concerned, can be employed by mixing with carriers or, if necessary, with any other additives, followed by the preparation of formulations usually employed such as oil solution, emulsifiable concentrate, solubilizer, paste, wettable powder, flowable, dry flowable, spray and paint, and then the formulation can be used according to any known method for wood preservative treatment. As the additives which are employed suitably to improve the property of the formulation and to strengthen the wood preserving effect, there may be mentioned cationic, anionic and non-ionic surfactants, various high polymer compounds such as methylcellulose and vinyl acetate resin and water-repellents such as silicon oil and paraffin. It is needless to say that combined use may be possible with other wood preservatives, fungicides and bacteriocides including organic

iodine compounds such as Sanplas, IF-1000 and Troysan, azole compounds such as Propiconazole and Tebuconazole, Thiabendazole, Dichlofluanid and quaternary ammonium salt compounds; with insecticides including pyrethroids such as Permethrin, Etofenprox, Cypermethrin, Sila-neophen, Tralomethrin, organic phosphor compounds such as Chloropyrifos, Phoxim and Propetamphos, and Imidac-roprid; and with potentiators such as bis-(2,3,3,3-tetrachlo-rrpropyl) ether. An increased effect can be expected by combined use in this manner. In a real case of application, though the content of the compound of the present invention can be changed within a wide range depending on the formulation or on the object, it may usually be suitable to use from 0.1 to 95 weight percent, preferably from 0.2 to 60 weight percent. These formulations are employable in usual methods for wood treatment: for example, coating, dis-persal, dipping treatment, mixing, impreganation, or mixing treatment with an adhesive.

[0206] Several formulation examples of the compound of the present invention will be shown below, in which it is needless to say that the combination ratio and the kind of additives can be changed widely (in the descriptions below, part means weight part in all cases).

FORMULATION EXAMPLES OF THE WOOD PRESERVATIVES

Formulation Example 1 Emulsifiable Concentrate

[0207] Twenty parts of the Compound of Example 20 were dissolved in 70 parts of xylene, and then 10 parts of polyoxyethylene nonyl phenyl ether were added and mixed enough to obtain the emulsifiable concentrate.

[0208] Thus obtained emulsifiable concentrate is diluted with a suitable amount of water at use, and can be applied to a wood material to be treated by coating, dipping or spraying, and in addition, employable by mixing with adhe-sives which are used for plywood, particle board and hard-board.

Formulation Example 2 Oil Solution

[0209] Two parts of the Compound of Example 21 were added with 98 parts of kerosene oil to obtain the oil solution.

[0210] Thus obtained oil solution can be applied to a wood material to be treated by spraying, coating, dipping or impregantion.

Formulation Example 3 Coating Formulation

[0211] Ten parts of the Compound of Example 20, 20 parts of Barite dust, 10 parts of vinyl resin, 25 parts of pine resin and 35 parts of xylene were mixed homogeneously to obtain the coating formulation.

Formulation Example 4 Wettable Powder

[0212] Forty parts of the Compound of Example 22, 56 parts of clay, 3 parts of sodium lauryl alcohol sulfonate and 1 part of polyvinyl alcohol were mixed homogeneously in a mixer, and pulverized by use of a hammer-mill to obtain the wettable powder.

TEST EXAMPLES OF WOOD PRESERVATION

[0213] The effectiveness of the wood preservative of the present invention will be explained concretely by the fol-lowing examples.

[0214] (1) According to the test method for wood preser-vation described in the Japan Industrial Standards [JIS A-9201 (1991)], each of the test compounds was dissolved to a defined concentration in methanol. The solution was impregnated under a reduced pressure into a Sugi (Japanese cedar) sapwood (2×2×1) cm and then air-dried. Weathering test was repeated 10 times in which one cycle of the treatment was stirring in water for 8 hours, and then heating for 16 hours at 60° C. The test material was placed on the flora of *Serpula lacrymans* which had been previously grown on a quartz sand medium (malt extract 2%, glucose 1%, peptone 0.3% and yeast 0.2%), and forcedly decayed at 20° C. for 12 weeks. From the difference between the dry weight of the test material before the test and that after test, the degree of decrease in weight was obtained. Table 2 shows the results. The test was carried out by use of 9 samples for each condition, and the values shown in Table 2 are the mean values calculated from 9 samples.

TABLE 2

Sample drugs decrease	Impregnant concentration (%)	Mean weight by decay (%)
Example 20	0.01	0
	0.005	0.1
Example 21	0.01	0
	0.005	0
Control compound 1	0.01	9.7
	0.005	18.6
Without treatment		18.4

Control compound 1: 4-Chlorophenyl-3-iodopropargylformal Product of Nagase Co., Ltd.: IF-1000

[0215] From the data shown above, the compound having the general formula (I) prevented decay of the wood samples due to wood-rotting fungi to a significant extent.

[0216] (2) Each of 0.1 w/v % methanol solutions of the compound of the present invention and the control drug was impregnated into the test material [a Sugi (Japanese cedar) sapwood, 2×2×0.5 cm] under a reduced pressure and then air-dried. Weathering test was repeated twice in which one cycle of the treatment was washing (about 2 liter per minute supply) with water for 5 hours, and then heating for 19 hours at 60° C. After dry air sterilization, the test samples were prepared.

[0217] The test materials were placed on the flora of *Coriolus versicolor* which is a lignin-decomposing fungus, and of *Tyromyces palustris* which is a cellulose-decompos-ing fungus, and both of which are designated fungal species for assay of wood preservating effect. Both fungi had been previously grown on an agar medium (malt extract 2%, glucose 1% and peptone 0.5%) After the wood samples were forcedly deteriorated at 26° C. for 3 weeks, the effectiveness was determined from the degree of hyphal growth on the test material and the presence or absence of lowered maximum crushing strength. Table 3 shows the result.

[0218] The wood preventive efficacy was judged by the following criteria.

[0219] +: No hyphal growth was observed on the test material, and no difference was found in the maximum crushing strength from the healthy wood sample.

[0220] ±: A little hyphal growth was observed on the test material, or a little decrease was found in the maximum crushing strength.

[0221] -: Hyphal growth was observed on the test material, or clear decrease was found in the maximum crushing strength.

TABLE 3

Test drug	<i>Coriolus versicolor</i>	<i>Tyromyces palustris</i>
Example 1	±	-
Example 2	-	-
Example 3	-	-
Example 4	-	-
Example 5	-	-
Example 6	+	+
Example 7	+	-
Example 8	±	-
Example 9	-	-
Example 10	+	-
Example 11	+	±
Example 12	±	±
Example 13	+	+
Example 14	+	+
Example 15	+	-
Example 20	+	+
Example 21	+	+
Example 23	+	+
Example 24	+	+
Example 25	+	+
Example 26	+	+
Control compound 2	+	+
Without treatment	-	-

Control compound 2: 3-Bromo-2,3-diiodo-2-propenylethylcarbonate
Product of Sankyo Co., Ltd.: Sanplas

[0222] When the composition of the present invention is desired to be employed, the combination ratio may be suitably selected depending on the kind of wood and the kind of wood material to be treated with the wood preservative, or the means for treatment (for example, coating, dipping, dispersal, impregnation, mixing and mixing with an adhesive). Usually, the combination ratio of dimethylfuran-carboxyanilide and any other wood preservative may be from 240:1 to 1:35, preferably from 30:1 to 1:10, and more preferably from 5:1 to 1:5.

[0223] The content of the composition of the present invention may be changed within a wide range depending on the formulation. In general, the content may be from 0.1 to 95%, preferably from 0.2 to 60%, in the formulation.

[0224] Several formulation examples of the compound of the present invention will be shown below, in which it is needless to say that the combination ratio and the kind of additives can be changed widely.

FORMULATION EXAMPLES OF THE WOOD PRESERVATIVE COMPOSITION

Formulation Example 1 Emulsifiable Concentrate

[0225] Ten parts of the Compound of Example 20 were dissolved in 30 parts of Sanplas and 50 parts of xylene, 10 parts of polyoxyethylene nonyl phenyl ether were then added and mixed enough to obtain the emulsifiable concentrate.

[0226] Thus obtained emulsifiable concentrate is diluted with a suitable amount of water at the time of use, and can be applied to a wood material to be treated by coating, dipping or spraying, and in addition, employable by mixing with adhesives which are used for plywood, particle board and hardboard.

Formulation Example 2 Oil Solution

[0227] Two parts of the compound of Example 21 and 1 part of troysan were dissolved in 96 parts of kerosene oil to obtain the oil solution.

Formulation Example 3 Wettable Powder

[0228] Fifteen parts of the compound of Example 22, 25 parts of IF-1000, 56 parts of clay, 3 parts of sodium lauryl alcohol sulfonate and 1 part of polyvinyl alcohol were mixed homogeneously in a mixer, and pulverized by use of a hammer-mill to obtain the wettable powder.

[0229] The effect of the wood preservative composition of the present invention will be explained concretely by the following examples.

TEST EXAMPLES OF WOOD PRESERVATIVE COMPOSITIONS

[0230] Assay of minimum inhibitory concentration by the agar dilution method.

[0231] According to the agar dilution method, on sterilized media (potato dextrose agar medium; potato extract powder 0.4%, glucose 2%, agar 1.5%) prepared to contain certain concentrations of a test sample, flora (about 4 mm in diameter) of wood rotting fungi, *Coriolus versicolor* and *Tyromyces palustris*, which had been cultured previously on the same kind of medium, were inoculated. After culture at 25° C. for 5 days, hyphal growth was observed to determine the minimum inhibitory concentration.

[0232] Whether there is any potentiation or not has been described in Applied Microbiology 9, 538-541 (1961) by F. C. Kull et al. The assay was carried out according to the method usually employed.

[0233] Table 4 and FIGS. 1A to 1F show the results obtained by combination of Example 20 with each of Sanplas, Troysan and IF-1000.

TABLE 4

MIC (ppm) of Example 20 combined with several other active agents				
<u>1</u>				
Test fungus	Example 20	A	Example 20 + A	(Combined ratio) Example 20:A
<i>Coriolus Versicolor</i>	2.5	15	1.30 + 3.0	(1:2.3)
			0.8 + 5.0	(1:6.3)
			0.4 + 9.0	(1:22.5)
<i>Tyromyces Palustris</i>	200	25	110.0 + 5.0	(22:1)
			70.0 + 9.0	(7.8:1)
			40.0 + 14.0	(2.9:1)
<u>2</u>				
Test fungus	Example 20	B	Example 20 + B	(Combined ratio) Example 20:B
<i>Coriolus Versicolor</i>	2.5	25	1.25 + 5.0	(1:4)
			0.8 + 7.5	(1:9.4)
			0.4 + 12.5	(1:31.3)
<i>Tyromyces Palustris</i>	200	2.5	120.0 + 0.6	(200:1)
			80.0 + 1.0	(80:1)
			40.0 + 1.5	(26.7:1)

TABLE 4-continued

MIC (ppm) of Example 20 combined with several other active agents				
3				
Test fungus	Example 20	C	Example 20 + C	(Combined ratio) Example 20:C
<i>Coriolus</i>	2.5	6	1.25 + 1.2	(1.0:1)
<i>Versicolor</i>			0.8 + 1.8	(1:2.3)
			0.5 + 3.0	(1:6)
<i>Tyromyces</i>	200	2	120.0 + 0.5	(240:1)
<i>Palustris</i>			80.0 + 0.8	(100:1)
			40.0 + 1.2	(33:1)

A: Sanplas
B: Troysan
C: IF-1000

[0234] Then, the same test as above was carried out for Example 21. Table 5 and FIGS. 2A to 2F show the result.

TABLE 5

MIC (ppm) of Example 21 combined with several other active agents				
1				
Test fungus	Example 21	A	Example 21 + A	(Combined ratio) Example 21:A
<i>Coriolus</i>	10.0	15	6.0 + 3.0	(2:1)
<i>Versicolor</i>			3.5 + 5.0	(1:1.4)
			2.0 + 8.0	(1:4)
<i>Tyromyces</i>	200	25	120.0 + 5.0	(24:1)
<i>Palustris</i>			75.0 + 9.0	(8.3:1)
			40.0 + 15.0	(2.7:1)

2				
Test fungus	Example 21	B	Example 21 + B	(Combined ratio) Example 21:B
<i>Coriolus</i>	10.0	25	5.5 + 5.0	(1.1:1)
<i>Versicolor</i>			3.0 + 8.0	(1:2.7)
			1.5 + 12.5	(1:8.3)
<i>Tyromyces</i>	200	2.5	120.0 + 0.7	(171.4:1)
<i>Palustris</i>			90.0 + 1.0	(90:1)
			40.0 + 1.75	(22.9:1)

3				
Test fungus	Example 21	C	Example 20 + C	(Combined ratio) Example 21:C
<i>Coriolus</i>	10.0	6	6.0 + 1.6	(3.6:1)
<i>Versicolor</i>			4.0 + 2.4	(1.7:1)
			2.0 + 3.6	(1:1.8)
<i>Tyromyces</i>	200	2	120.0 + 0.5	(240:1)
<i>Palustris</i>			90.0 + 1.0	(90:1)
			40.0 + 1.4	(28.6:1)


A: Sanplas
B: Troysan
C: IF-1000

[0235] Each of the minimum inhibitory concentration curves shown in FIGS. 1A to 1F and FIGS. 2A to 2F lies under the diagonal line shown by broken line.

[0236] This data exhibits that the furancarboxyanilide derivative potentiates the effect of each of Sanplas, Troysan and IF-1000 by combination.

We claim:

1. A dimethylfurancarboxyanilide compound of the formula (I):



wherein R¹ and R² are the same or different and each is a hydrogen atom; an alkyl group having from 2 to 6 carbon atoms; a cycloalkyl group having from 3 to 6 carbon atoms; an alkenyl group having from 3 to 6 carbon atoms; an alkynyl group having from 2 to 6 carbon atoms; a halogenoalkyl group having from 1 to 3 carbon atoms; an alkoxy group having from 2 to 6 carbon atoms; an alkoxyalkyl group having from 1 to 6 carbon atoms in the alkoxy moiety and from 1 to 6 carbon atoms in the alkyl moiety; a cyano group; a substituted amide group; an alkoxycarbonyl group having from 1 to 6 carbon atoms in the alkoxy moiety; a benzoyl group which may have optionally from 1 to 2 substituents; a benzoylamino group which may have optionally from 1 to 2 substituents; an alkanoylamino group having from 2 to 6 carbon atoms; a cycloalkyl-carbonylamino group having from 3 to 6 carbon atoms in the cycloalkyl moiety; a benzyl group which is unsubstituted or has from 1 to 2 substituents; a phenyl group which is unsubstituted or has from 1 to 2 substituents; or an alkoxycarbonylalkenylene group having from 1 to 6 carbon atoms in the alkoxy moiety and from 2 to 5 carbon atoms in the alkenylene moiety; provided that:

- (i) R¹ and R² do not both represent hydrogen atoms;
- (ii) one of R¹ and R² does not represent an unsubstituted phenyl group when the other represents a hydrogen atom; and
- (iii) one of R¹ and R² does not represent, in the ortho position on the aniline ring, an alkyl group having from 2 to 6 carbon atoms or a cycloalkyl group having from 3 to 6 carbon atoms, when the other is a hydrogen atom.

2. The dimethylfurancarboxyanilide compound of claim 1, wherein R¹ and R² are the same or different and each is a hydrogen atom; a (C₂-C₆)-alkyl group, a (C₁-C₆)-alkoxy-(C₁-C₆)-alkyl group; a cyano group; a substituted amide group; a (C₁-C₆)-alkoxycarbonyl group; a benzoyl group which is unsubstituted or has 1 to 2 substituents; a benzoylamino group which is unsubstituted or has 1 to 2 substituents; a (C₂-C₆)-alkanoylamino group; a (C₃-C₆)-cycloalkyl-carbonylamino group; a benzyl group which is unsubstituted or has 1 to 2 substituents; or a (C₁-C₆)-alkoxycarbonyl-(C₂-C₆)-alkenylene group; and R¹ and R² do not both represent hydrogen atoms at the same time; and when one of R¹ and R² is a hydrogen atom and the other is a (C₂-C₆)-alkyl group substituent, the C₂-C₆-alkyl group substituent is not at position-2.

3. The dimethylfurancarboxyanilide compound of claim 1, wherein R¹ and R² are the same or different and each is


a hydrogen atom; a (C₂-C₆)-alkyl group, a (C₁-C₆)-alkoxy-(C₁-C₆)-alkyl group; a (C₁-C₆)-alkoxycarbonyl group; or a benzyl group which is unsubstituted or has 1 to 2 substituents; and R¹ and R² do not both represent hydrogen atoms at the same time; and when one of R¹ and R² is a hydrogen atom and the other is a (C₂-C₆)-alkyl group substituent, the C₂-C₆-alkyl group substituent is not at position-2.

4. The dimethylfurancarboxyanilide compound of claim 1, wherein the compound is 2,5-dimethylfuran-3-carboxy(3-isopropylanilide).

5. A wood preservative composition comprising an effective wood preserving amount of the dimethylfurancarboxyanilide compound of claim 1 as an active ingredient together with a carrier.

6. The wood preservative composition of claim 5, wherein the compound is 2,5-dimethylfuran-3-carboxy(3-isopropylanilide).

7. A method of preserving wood comprising applying to the wood a composition comprising an effective amount of a compound having the formula (I):



wherein R¹ and R² are the same or different and each is a hydrogen atom; an alkyl group having from 2 to 6 carbon atoms; a cycloalkyl group having from 3 to 6 carbon atoms; an alkenyl group having from 3 to 6 carbon atoms; an alkynyl group having from 2 to 6 carbon atoms; a halogenoalkyl group having from 1 to 3 carbon atoms; an alkoxy group having from 2 to 6 carbon atoms; an alkoxyalkyl group having from 1 to 6 carbon atoms in the alkoxy moiety and from 1 to 6 carbon atoms in the alkyl moiety; a cyano group; a substituted amide group; an alkoxycarbonyl group having from 1 to 6 carbon atoms in the alkoxy moiety; a benzoyl group which is unsubstituted or has from 1 to 2 substituents; a benzoylamino group which is unsubstituted or has from 1 to 2 substituents; an alkanoylamino group having from 2 to 6 carbon atoms; a cycloalkylcarbonylamino group having from 3 to 6 carbon atoms in the cycloalkyl moiety; a benzyl group which is unsubstituted or has from 1 to 2 substituents; a phenyl group which is unsubstituted or has from 1 to 2 substituents; or an alkoxycarbonylalkenylene group having from 1 to 6 carbon atoms in the alkoxy moiety and from 2 to 5 carbon atoms in the alkenylene moiety; provided that:

R¹ and R² do not both represent hydrogen atoms.

8. The method of claim 7, wherein R¹ and R² are the same or different and each represents a hydrogen atom; a (C₂-C₆)-alkyl group, a (C₁-C₆)-alkoxy-(C₁-C₆)-alkyl group; a cyano group; a substituted amide group; a (C₁-C₆)-alkoxycarbonyl group; a benzoyl group which is unsubstituted or has 1 to 2 substituents; a benzoyl-amino group which is unsubstituted or has 1 to 2 substituents; a (C₂-C₆)-alkanoy-

lamino group; a (C₃-C₆)-cycloalkylcarbonylamino group; a benzyl group which is unsubstituted or has 1 to 2 substituents; or a (C₁-C₆)-alkoxycarbonyl-(C₂-C₆)-alkenylene group; and R¹ and R² do not both represent hydrogen atoms at the same time; and when one of R¹ and R² is a hydrogen atom and the other is a (C₂-C₆)-alkyl group substituent, the C₂-C₆ alkyl group substituent is not at position-2.


9. The method of claim 7, wherein R¹ and R² are the same or different and each represents a hydrogen atom; a (C₂-C₆)-alkyl group, a (C₁-C₆)-alkoxy-(C₁-C₆)-alkyl group; a (C₁-C₆)-alkoxycarbonyl group; or a benzyl group which is unsubstituted or has 1 to 2 substituents; and R¹ and R² do not represent hydrogen atoms at the same time; and when one of R¹ and R² is a hydrogen atom and the other is a (C₂-C₆)-alkyl group substituent, the C₂-C₆ alkyl group substituent is not at position-2.

10. The method of claim 7, wherein the compound is 2,5-dimethylfuran-3-carboxy(3-isopropylanilide).

11. A wood preservative composition comprising:

(a) at least one compound selected from the group consisting of 3-bromo-2,3-diiodo-2-propenylethylcarbamate, 3-iodo-2-propynylbutylcarbamate and 4-chlorophenyl-3-iodopropargylal, and

(b) at least one dimethylfurancarboxyanilide compound of the following formula (I):



wherein R¹ and R² are the same or different and each is a hydrogen atom; an alkyl group having from 2 to 6 carbon atoms; a cycloalkyl group having from 3 to 6 carbon atoms; an alkenyl group having from 3 to 6 carbon atoms; an alkynyl group having from 2 to 6 carbon atoms; a halogenoalkyl group having from 1 to 3 carbon atoms; an alkoxy group having from 2 to 6 carbon atoms; an alkoxyalkyl group having from 1 to 6 carbon atoms in the alkoxy moiety and from 1 to 6 carbon atoms in the alkyl moiety; a cyano group; a substituted amide group; an alkoxycarbonyl group having from 1 to 6 carbon atoms in the alkoxy moiety; a benzoyl group which is unsubstituted or has 1 to 2 substituents; a benzoylamino group which is unsubstituted or has 1 to 2 substituents; an alkanoylamino group having from 2 to 6 carbon atoms; a cycloalkylcarbonylamino group having from 3 to 6 carbon atoms in the cycloalkyl moiety; a benzyl group which has 1 to 2 substituents; a phenyl group which is unsubstituted or has 1 to 2 substituents; or an alkoxycarbonylalkenylene group having from 1 to 6 carbon atoms in the alkoxy moiety and from 2 to 5 carbon atoms in the alkenylene moiety; provided that:

R¹ and R² do not both represent hydrogen atoms.

12. The wood preservative composition of claim 11, wherein R^1 and R^2 are the same or different and each is a hydrogen atom; a (C_2-C_6) -alkyl group, a (C_1-C_6) -alkoxy- (C_1-C_6) -alkyl group; a cyano group; a substituted amide group; a (C_1-C_6) -alkoxycarbonyl group; a benzoyl group which is unsubstituted or has 1 to 2 substituents; a benzoylamino group which is unsubstituted or has 1 to 2 substituents; a (C_2-C_6) -alkanoylamino group; a (C_3-C_6) -cycloalkylcarbonylamino group; a benzyl group which is unsubstituted or has 1 to 2 substituents; or a (C_1-C_6) -alkoxycarbonyl- (C_2-C_6) -alkenylene group; and R^1 and R^2 do not both represent hydrogen atom at the same time; and when one of R^1 and R^2 is a hydrogen atom and the other is a (C_2-C_6) -alkyl group substituent, the C_2-C_6 alkyl substituent is not at position-2.

13. The wood preservative composition of claim 11, wherein R^1 and R^2 are the same or different and each is a hydrogen atom; a (C_2-C_6) -alkyl group, a (C_1-C_6) -alkoxy- (C_1-C_6) -alkyl group; a (C_1-C_6) -alkoxycarbonyl group; or a benzyl group which is unsubstituted or has 1 to 2 substituents; and R^1 and R^2 do not both represent hydrogen atoms at the same time; and when one of R^1 and R^2 is a hydrogen atom and the other is a (C_2-C_6) -alkyl substituent, the C_2-C_6 alkyl substituent is not at position-2.

14. The wood preservative composition of claim 11, wherein the at least one dimethylfurancarboxyanilide compound is 2, 5-dimethylfuran-3-carboxy(3-isopropylanilide).

15. The wood preservative composition of claim 11, wherein the at least one dimethylfurancarboxyanilide of the formula (I) and the at least one compound (a) are contained in a ratio of 240:1 to 1:35.

16. The wood preservative composition of claim 11, wherein the at least one dimethylfurancarboxyanilide compound of the formula (I) and the at least one compound (a) are contained in a ratio of 30:1 to 1:10.

17. The wood preservative composition of claim 11, wherein the at least one dimethylfurancarboxyanilide compound of the formula (I) and the at least one compound (a) are contained in a ratio of 5:1 to 1:5.

18. The wood preservative composition of claim 10, wherein the at least one compound (a) consists essentially of 3-bromo-2,3-diiodo-2-propenylethylcarbamate.

19. The wood preservative composition of claim 18, wherein the at least one dimethylfurancarboxyanilide compound of the formula (I) consists essentially of 2,5-dimethylfuran-3-carboxy(3-isopropylanilide).

* * * * *