



(86) Date de dépôt PCT/PCT Filing Date: 2012/07/26
(87) Date publication PCT/PCT Publication Date: 2013/03/07
(85) Entrée phase nationale/National Entry: 2014/02/25
(86) N° demande PCT/PCT Application No.: EP 2012/064664
(87) N° publication PCT/PCT Publication No.: 2013/029887
(30) Priorité/Priority: 2011/09/02 (US61/530,570)

(51) Cl.Int./Int.Cl. *C08G 18/08* (2006.01),
C08G 18/28 (2006.01), *C08G 18/32* (2006.01),
C08G 18/48 (2006.01), *C08G 18/66* (2006.01),
C08G 18/72 (2006.01), *C08G 18/76* (2006.01),
C08G 18/80 (2006.01)
(71) Demandeur/Applicant:
CONSTRUCTION RESEARCH & TECHNOLOGY
GMBH, DE
(72) Inventeurs/Inventors:
WANG, CHIA L., US;
DAVIS, JOHN, US;
LIENKE, BRYAN, US
(74) Agent: GOWLING LAFLEUR HENDERSON LLP

(54) Titre : SYSTEMES POLYURETHANES PEIGNABLES ET SANS FLUAGE
(54) Title: POLYURETHANE SYSTEMS HAVING NON-SAG AND PAINTABILITY

(57) **Abrégé/Abstract:**

A two part construction sealant or adhesive is provided with the properties of non-sag, low modulus, high elongation, and good paint adhesion. The sealant or adhesive is prepared using at least one of a secondary amine or an acrylate monomer, and a diol, triol and/or tetrol having a nominal weight average molecular weight of between 1,000 and 6,000 in the base component of the formulation, and aromatic diisocyanate monomer or polyisocyanate and an isocyanate terminated prepolymer of aromatic diisocyanate or polyisocyanate and polyol in the activator component, the components of Part A to Part B mixed at a weight ratio of 5:1 to 1.8:1.



(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)
(19) World Intellectual Property Organization
International Bureau
(43) International Publication Date
7 March 2013 (07.03.2013)



(10) International Publication Number
WO 2013/029887 A3

(51) **International Patent Classification:**
C08G 18/08 (2006.01) *C08G 18/66* (2006.01)
C08G 18/28 (2006.01) *C08G 18/72* (2006.01)
C08G 18/32 (2006.01) *C08G 18/76* (2006.01)
C08G 18/48 (2006.01) *C08G 18/80* (2006.01)

(21) **International Application Number:**
PCT/EP2012/064664

(22) **International Filing Date:**
26 July 2012 (26.07.2012)

(25) **Filing Language:** English

(26) **Publication Language:** English

(30) **Priority Data:**
61/530,570 2 September 2011 (02.09.2011) US

(71) **Applicant** (*for all designated States except US*): **CONSTRUCTION RESEARCH & TECHNOLOGY GMBH** [DE/DE]; Dr.-Albert-Frank-Str. 32, 83308 Trostberg (DE).

(72) **Inventors; and**

(75) **Inventors/Applicants** (*for US only*): **WANG, Chia, L.** [US/US]; 1586 Coventry Lane, Shakopee, Minnesota 55379 (US). **DAVIS, John** [US/US]; 8200 West Park Hills Drive, Bloomington, Minnesota 55438 (US). **LIENKE, Bryan** [US/US]; 18225 Emerald Trail, Farmington, Minnesota 55024 (US).

(81) **Designated States** (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM,

AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) **Designated States** (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- *with international search report (Art. 21(3))*
- *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments (Rule 48.2(h))*

(88) **Date of publication of the international search report:**
2 May 2013

(54) **Title:** POLYURETHANE SYSTEMS HAVING NON-SAG AND PAINTABILITY

(57) **Abstract:** A two part construction sealant or adhesive is provided with the properties of non-sag, low modulus, high elongation, and good paint adhesion. The sealant or adhesive is prepared using at least one of a secondary amine or an acrylate monomer, and a diol, triol and/or tetrol having a nominal weight average molecular weight of between 1,000 and 6,000 in the base component of the formulation, and aromatic diisocyanate monomer or polyisocyanate and an isocyanate terminated prepolymer of aromatic diisocyanate or polyisocyanate and polyol in the activator component, the components of Part A to Part B mixed at a weight ratio of 5:1 to 1.8:1.

WO 2013/029887 A3

POLYURETHANE SYSTEMS HAVING NON-SAG AND PAINTABILITY

Polyurethanes have suitable properties for many useful products, including elastomeric sealants prepared from the reaction of hydroxy-functional components with isocyanate-functional components. Polyurethanes have utility as high performance sealants having high elongation and low modulus are suitable for commercial building and construction for exterior sealing.

It is desirable that the sealant or adhesive exhibit non-sag characteristics, i.e., be substantially free from or resistant to sagging or slumping after application to vertical substrate surfaces. The known methods of enhancing the non-sag properties of polyurethane sealant or adhesive formulations can have drawbacks. Non-sag additives, such as polyamines, primary or secondary amines and diamines, are reactive with isocyanate groups, and therefore, polyurethane products formulated with such additives have limited storage stability which impacts their usefulness. Other methods of improving non-sag performance include using castor oil, amide or other thixotropic products. However, the non-sag properties of such formulations can be adversely affected after high shear force mixing, and such formulations have short "pot-life" or working time due to the very high reactivity of most amine compounds towards isocyanates. Incorporating fillers to increase the sag resistance also increases the viscosity of the components containing the filler and makes it difficult to mix the components and then spread the composition on a substrate. It is known to add urea paste prepared by mixing aromatic isocyanate and a primary amine, such as butylamine, into one-part or two-part systems for non-sag and adhesion performance, and for its increased tolerance to more shear force. However, urea paste is difficult to manufacture, requires high speed grinding during the preparation step to remove grainy particles, and represents an additional step in the process.

Thus, the need exists for a high performance, two part construction sealant or adhesive that exhibits sag resistance immediately upon mixing the two parts, Part A (Base) and Part B (activator), thus creating urea paste immediately and saving the time and expense of an initial urea paste preparation step. There is also a need for a non-sag, two part construction sealant or adhesive in which the base and activator components have sufficiently low viscosity for easy mixing, and which upon mixing the base and activator do not result in the mixture having a grainy surface. What is desired in the art are two part construction sealants and adhesives that exhibit paintability, and that are low modulus and have high elongation with high movement capability.

Short chain diols and triols may be added to sealant formulations for good paint adhesion, but have resulted in sealants with poor elongation, strong tensile strength and high modulus. Long chain diols and triols are useful in preparing low modulus sealants, but result in very poor paint adhesion.

5

Two component polyurethane systems were not previously known, having non-sag, low modulus, high elongation, good tensile properties, and good paint adhesion properties of at least about 3B when tested according to ASTM D3359 and a non-sag value of between about 0.0-0.1 B/S when tested according to ASTM D-2202.

10

A two part construction sealant or adhesive is provided comprising a base component Part A and an activator component Part B, wherein Part A comprises at least one of a secondary amine or an acrylate monomer, and a diol, triol and/or tetrol having a nominal weight average molecular weight of between 1,000 and 6,000; and Part B comprises an aromatic diisocyanate monomer or polyisocyanate and an isocyanate terminated prepolymer of aromatic diisocyanate or polyisocyanate and polyol; the components of Part A to Part B provided to be mixed at a weight ratio of 5:1 to 1.8:1; wherein the construction sealant or adhesive exhibits a paint adhesion of at least about 3B when tested according to ASTM D3359; a non-sag value of about 0.0-0.1 B/S when tested according to ASTM D-2202; and at least one of the following: a 100% modulus of less than about 830 kPa (120 psi) in the presence of a plasticizer when tested according to ASTM D412; a tensile strength of about 620 kPa (90 psi) or greater when tested according to ASTM D412; or an elongation to break of about 250% or greater when tested according to ASTM D412.

For purposes of illustration but not by way of limitation, the secondary amine may comprise at least one of piperazine, ethylenediamine, naphthalenediamine or mixtures thereof. In certain embodiments, the secondary amine may have a molecular weight in the range of 60 to 250, and in some embodiments up to about 220. In certain embodiments, the secondary amine comprises piperazine. Secondary amines have slower reactivity than primary amines, allowing easier control of the in situ formation of urea paste in the reaction product after mixing Parts A and B together. The amount of secondary amine that may be used may be about 0.3 % to about 1.2%, in certain embodiments about 0.6 % to about 0.8 % by weight, based on the total weight of Part A and Part B components.

For purposes of illustration but not by way of limitation, the acrylate monomer may comprise at least one of trimethylol propane triacrylate, triacrylate, mixtures of triacrylate and

diacrylate, or mixtures thereof. In certain embodiments, the acrylate monomer is trimethylol propane triacrylate. The amount of acrylate monomer that may be used may be about 2% to about 6%, in certain embodiments about 3% to about 4% by weight, based on the total weight of Part A and Part B components.

5

The diol, triol or tetrol has a nominal weight average molecular weight of between 1,000 and 6,000, in certain embodiments, between 3,000 and 6,000. For purposes of illustration but not by way of limitation, the diol, triol or tetrol having a nominal weight average molecular weight of between 1,000 and 6,000 may be a polyether or a polyester triol or tetrol. In certain
10 embodiments, the diol, triol or tetrol having a nominal weight average molecular weight of between 1,000 and 6,000 comprises at least one primary hydroxyl terminated polyol. In certain embodiments, Part A comprises an additional diol or triol or tetrol having a nominal weight average molecular weight of between 400 and 6,000. The amount of polyol that may be used in Part A may be about 25% to about 45%, in certain embodiments about 30% to about 40% by
15 weight, based on the total weight of Part A components.

The molecular weight may be a weight average molecular weight which may be calculated by a formula based on gel permeation chromatography (GPC).

20 The diol, triol or tetrol having a nominal weight average molecular weight of between 1,000 and 6,000 may comprise at least one of polyether polyol, propoxylated ethylenediamine polyol, polypropylene glycol, propylene oxide adduct of glycerine, amine-based polyether polyol, or mixtures thereof.

25 In certain embodiments, suitable diols, triols or tetrols may comprise, but are not limited to, Pluracol® 726 and Pluracol® P1010, which are commercially available from BASF Corporation. Pluracol® 726 polyol is a 3,000 molecular weight propylene oxide adduct of glycerin having a nominal functionality of 3, and a hydroxyl number of 57 – 59, available from BASF Corporation, Wyandotte, MI. Pluracol® P1010 polyol is a 1000 molecular weight
30 polypropylene glycol formed by adding propylene oxide to a propylene glycol nucleus, having a nominal functionality of 2, and a hydroxyl number of 102-112 available from BASF Corporation, Wyandotte, MI. In certain embodiments, the diol or triol or tetrol having a nominal weight average molecular weight of between 1,000 and 6,000 may comprise Multranol 9168, a polyether polyol from Bayer Material Science, LLC having a molecular weight of 3,740 and a functionality
35 of 4. In certain embodiments, the triol is Pluracol® 220 from BASF Corporation (Wyandotte,

MI), a 6000 nominal molecular weight primary hydroxyl terminated polyol, having a nominal functionality of 3 and a hydroxyl number (mg KOH/gm) of 25.6 - 27.6.

5 In certain embodiments, Part A additionally comprises a plasticizer. In some embodiments, the plasticizer may comprise dipropyl heptyl phthalate ester, diisooctyl phthalate, diisononyl phthalate, diisodecyl phthalate, and/or 1,2-cyclohexanedicarboxylic acid diisononyl ester.

10 Part B comprises aromatic diisocyanate monomer and an isocyanate terminated prepolymer. The prepolymer comprises the reaction product of an aromatic diisocyanate or polyisocyanate and polyol. For purposes of illustration but not by way of limitation, the polyisocyanate used in part B may have an average functionality equal to about 2.

15 For purposes of illustration but not by way of limitation, the aromatic diisocyanate or polyisocyanate may comprise at least one of toluene diisocyanates (TDI), methylene diphenyl diisocyanates (MDI), phenylene diisocyanate, diphenylmethane diisocyanate, polyphenylmethane polyisocyanate (Polymeric MDI), naphthalene diisocyanate, triphenylmethane triisocyanate, diphenyl sulfone diisocyanate, dimers or trimers of these diisocyanates, or mixtures thereof.

20

For purposes of illustration but not by way of limitation, in certain embodiments, the isocyanate may comprise at least one of toluene 2,4-diisocyanate, toluene 2,6-diisocyanate, naphthylene 1,5-diisocyanate, 4,4'-methylene diphenyl diisocyanate, 2,4'-methylene diphenyl diisocyanate, urethodione diisocyanate, hexahydrotolylene diisocyanate (and isomers), 1-methoxyphenyl-2,4-diisocyanate, diphenylmethane-4,4'-diisocyanate, 4,4'-biphenylene diisocyanate, 3,3'-dimethoxy-4,4'-biphenyl diisocyanate, 3,3'-dimethyl-4,4'-biphenyl diisocyanate, 3,3'-dimethyldiphenylmethane-4,4'-diisocyanate, dimers or trimers of these isocyanates, or mixtures thereof. In some embodiments, the Part B aromatic diisocyanate monomer may comprise at least one of toluene diisocyanate (TDI), methylene diphenyl diisocyanate (MDI), or mixtures thereof.

30

For purposes of illustration but not by way of limitation, in certain embodiments, the isocyanate is toluene diisocyanate (TDI) that is an 80% -20% mixture of the 2,4 and 2,6 isomers of toluene diisocyanate, commercially available as Lupranate® T80 marketed by BASF Corporation. In certain embodiments, the isocyanate is pure 2,4 diphenylmethane diisocyanate, commercially available as Lupranate® MI commercially available from BASF Corporation. The

35

amount of isocyanate that may be used in Part B may be about 16% to about 35%, in certain embodiments about 22% to about 28% by weight, based on the total weight of the Part B components.

5 For purposes of illustration but not by way of limitation, the Part B polyol component may comprise at least one diol, triol or tetrol having a nominal weight average molecular weight of between 1,000 and 6,000, and is present in an amount of from about 35% to about 60% by weight, based on the total weight of the Part B components. In certain embodiments, the theoretical % NCO content of Part B is in the range of from about 2% to about 10%, as measured
10 by 0.1N HCl Titration using automatic titrator, as per ASTM D-2572-90 (Test method for Isocyanate Groups in Urethane Prepolymers).

In certain embodiments, the Part B polyol component may comprise at least one of a polyester polyol or a polyether polyol. In certain embodiments, the polyol comprises Pluracol®
15 726 or Pluracol® P1010, which are commercially available from BASF Corporation, and which are described in detail above.

The polyether polyols may be formed with an initiator, as is known in the art, and may be at least one of, but not limited to, ethylene glycol, diethylene glycol, propylene glycol,
20 dipropylene glycol, butane diol, glycerol, trimethylolpropane, triethanolamine, pentaerythritol or sorbitol.

In certain embodiments, Part A additionally comprises at least one of any of conventional, commercially available catalyst, inorganic filler, plasticizers, colorant, antioxidant,
25 UV light absorber, free radical initiator, adhesion promoter, calcium oxide, expandable microspheres (including Expancel® products available from AkzoNobel), drying agents, or mixtures thereof. In certain embodiments, Part A additionally comprises at least one of any of conventional, commercially available organic fillers, chain extenders, UV stabilizers, light stabilizers, fungicides, mildewcides, biocides, fire retardants, surface additives, mineral oils,
30 dispersing agents, defoaming agents, storage stabilizers, latent hardeners, cure retarders, antifoaming agents, solvents, or mixtures thereof.

In certain embodiments, the total amount of such additives may be from about 10 to about 55 weight percent; and in certain embodiments about 30 to about 50 weight percent, based on the
35 total weight of the Part A formulation.

By way of example, but not of limitation, the sealant and adhesive formulations may contain from 0 to about 5 percent by weight of UV absorbers, from 0 to 5 percent by weight of antioxidants, from 0 to about 2 percent by weight of mildewcides, from 0 to about 2 percent by weight of biocides, from 0 to about 2 percent by weight of fungicides, from 0 to about 20 percent by weight of fire or flame retardants, from 0 to about 10 percent by weight of pigments, from 0 to about 2 percent by weight of catalysts, from 0 to about 5 percent by weight of adhesion promoters, from 0 to about 10 percent by weight of flow and leveling additives, from 0 to about 2 percent by weight of wetting agents, from 0 to about 2 percent by weight of antifoaming agents, from 0 to about 2 percent by weight of storage stabilizers, from 0 to about 10 percent by weight of latent hardeners, from 0 to about 30 percent by weight of plasticizers, from 0 to about 5 percent by weight of dispersing agents, from 0 to about 10 percent by weight solvents, and in certain embodiments from 3 to about 10 percent by weight solvents, from about 20 to about 50 percent by weight of fillers, from 0 to about 5 percent by weight of drying agents, and/or from 0 to about 5 percent by weight of rheology modifiers.

For purposes of illustration but not by way of limitation, the plasticizer may comprise adipate, azelinate, sebacate, sulfonate, trimellitate, phosphate, fumarate, or maleate ester or diester, or mixtures thereof. For illustration purposes but not by way of limitation, the plasticizer may comprise at least one of dioctyl adipate, 2-ethylhexyl adipate, diisononyl adipate, or diisodecyl adipate, di(2-ethylhexyl)azelinate, di(2-ethylhexyl)sebacate, phenyl alkylsulfonates, tri(2-ethylhexyl)trimellitate, triphenyl phosphate, tricresyl phosphate, trixylenyl phosphate, cresyl diphenyl phosphate, xylenyl diphenyl phosphate, butyl fumarate, bis(2-methylpropyl) fumarate, diisobutyl fumarate, or bis(2-ethylhexyl) fumarate, dimethyl maleate or diethyl maleate, di-(2-propyl heptyl) phthalate, or mixtures thereof. The plasticizer may comprise Palatinol® DPHP (di-(2-propyl heptyl) phthalate ester) from BASF Corporation. The amount of plasticizer typically used may be about 0% to about 8%, in certain embodiments, about 2% to about 7% by weight, based on the total weight of the prepolymer.

In certain embodiments, adhesion promoters may also be used in the adhesive or sealant formulations. For purposes of illustration but not by way of limitation, adhesion promoters may include, but are not limited to, at least one of 2-aminoethyl-dimethylmethoxysilane, 6-aminoethyl-tributoxysilane, 3-aminopropyl-trimethoxysilane, 3-aminopropyl-triethoxysilane, 3-aminopropyl-methyldimethoxysilane, 3-aminopropyl-methyldiethoxysilane, 5-aminopentyl-trimethoxysilane, 5-aminopentyl-triethoxysilane, 3-aminopropyl-triisopropoxysilane, γ -glycidoxypentyltrimethoxysilane, γ -glycidoxypentyltriethoxysilane,

γ -mercaptopropyltrimethoxysilane, γ -mercaptopropyltriethoxysilane,
 γ -ureidopropyltrimethoxysilane, γ -ureidopropyltriethoxysilane, 1-[3-
 (trimethoxysilyl)propyl]urea, 1-[3-(triethoxysilyl)propyl]urea, [3-(2-
 aminoethylamino)propyl]trimethoxysilane, [3-(2-aminoethylamino)propyl]triethoxysilane, 2-
 5 (3,4-epoxycyclohexyl)ethyl-trimethoxysilane, 2-(3,4-epoxycyclohexyl)ethyl-triethoxysilane, 3-
 (phenylamino)propyl-trimethoxysilane, 3-(phenylamino)propyl-triethoxysilane, bis[3-
 (trimethoxysilyl)propyl] amine, bis[3-(triethoxysilyl)propyl]amine, 3-mercaptopropyl-
 methyldimethoxysilane, 3-mercaptopropyl-methyldiethoxysilane, [3-(2-
 aminoethylamino)propyl]methyl dimethoxysilane, [3-(2-aminoethylamino) propyl]methyl
 10 diethoxysilane, 3-glycidoxypropyl methyldimethoxysilane, or 3-glycidoxypropyl-
 methyldiethoxysilane, or combinations thereof.

In certain embodiments, one or more storage stabilizers can be used in Part A or Part B of
 the adhesive or sealant formulations, including but not limited to, para toluene sulfonyl
 15 isocyanate (PTSI).

In certain embodiments, one or more conventional catalysts which accelerate the
 isocyanate-polyol reaction may be used. In certain embodiments, one or more conventional
 tertiary amine catalysts may be used. For purposes of illustration but not by way of limitation,
 20 tertiary amines may include triethylenediamine, dimethylethanolamine, triethanolamine, N-ethyl
 morpholine, N-methyldicyclohexylamine, N,N-dimethyl cyclohexylamine, N,N,N',N'-
 tetramethyl-1,3-butanediamine, ether and the like. Suitable tertiary amine catalysts may include
 Dabco® 33LV, available from Air Products & Chemicals, Inc., Dabco® T-12 catalyst, or
 mixtures thereof.

25 The amount of catalysts, if used, may be in certain embodiments about 0.02 to about 1
 weight percent and in certain embodiments about 0.06 to about 0.4 weight percent, based on the
 total weight of the prepolymer.

30 In certain embodiments, to avoid the inclusion of water during processing, an alkaline
 earth metal oxide, such as calcium oxide or calcium sulfate, may be included in the formulation
 as a de-watering agent, i.e., drying agent, for scavenging water from the formulation. For
 purposes of illustration but not by way of limitation, the drying agent may comprise para toluene
 sulfonyl isocyanate (PTSI). The amount of drying agent typically used usually may be about

0.05% to about 3%, in certain embodiments, about 0.1% to about 1% by weight, based on the total weight of the prepolymer.

The additional components for the polyurethane reaction product may be incorporated separately or may be combined with any reaction component. The additional ingredients may be mixed by conventional means, such as in an inert, dry atmosphere. The ingredients may be mixed together all at one time (in a "one stage" process); alternatively, some ingredients and/or portions of ingredients may be mixed together in one operation (or "stage"), with other ingredients and/or portions of ingredients added in an additional stage or stages.

In certain embodiments, the viscosity of the sealant or adhesive may be in the range of about 600 Pa·s (6,000 poise) to about 4,000 Pa·s (40,000 poise) at 24°C (72°F), and in certain embodiments from about 600 Pa·s (6,000 poise) to about 1,500 Pa·s (15,000 poise) at 24°C (72°F), as measured by Brookfield viscometer.

Also provided is a method of making a two part construction sealant or adhesive comprising Part A and Part B, the method comprising: a) providing a base component Part A and an activator component Part B, wherein Part A comprises at least one of a secondary amine or an acrylate monomer, and a diol, triol and/or tetrol having a nominal weight average molecular weight of between 1,000 and 6,000; and Part B comprises aromatic diisocyanate monomer or polyisocyanate and an isocyanate terminated prepolymer of aromatic isocyanate or polyisocyanate and polyol; and b) mixing the components of base component Part A to activator component Part B at a weight ratio of 5:1 to 1.8:1 to form a polyurethane reaction product; wherein the reaction product (construction sealant) exhibits a paint adhesion of at least about 3B when tested according to ASTM D3359 and a non-sag value of about 0.0-0.1 B/S when tested according to ASTM D-2202; and at least one of a 100% modulus of less than about 830 kPa (120 psi) in the presence of a plasticizer when tested according to ASTM D412; a tensile strength of about 620 kPa (90 psi) or greater when tested according to ASTM D412; or an elongation to break of about 250% or greater when tested according to ASTM D412.

In certain embodiments, the sealants or adhesives are suitable for the adhesive bonding of substrates including, but not limited to, at least one of concrete, stone, metal, ceramic, glass, plastic, wood, asphalt, thermoplastic materials, thermoset materials, rubber, or composite materials.

Part A Base samples were combined with Part B Activator samples according to the following examples. Once the experimental NCO% is close to theoretical NCO%, the batch is allowed to cool and drying agent is added. The formulations were evaluated with respect to paintability, non-sag and viscosity properties, and tensile and elongation properties.

5

Performance capabilities can be expressed in terms of measured physical properties such as tensile strength (kPa/psi), elongation percentage, and tensile stress at 100% elongation, often referred to as 100% modulus. This is measured by a standard test method such as ASTM D 412 Standard Test Methods for Vulcanized Rubber and Thermoplastic Elastomers – Tension, with the polyurethane sealants demonstrating high elongations of at least 250% or greater, and low moduli of about 275-690 kPa (40-100 psi). Non-sag properties were evaluated using according to ASTM D-2202, (that is, using a Frazier (Boeing) Flow Test Jig, i.e. Boeing Slump Gage or Jig, where 0.0 = no slump, 0.254 = slump of 0.254 cm (0.1 = slump of 0.1 inch), demonstrating a non-sag value of about 0.0-0.1 B/S. The viscosity of the sealant may be in the range of 500 Pa·s (5,000 poise) to 3,500 Pa·s (35,000 poise) at 24°C, as measured by a Brookfield viscometer. The sealant provides very good tensile properties, and may be characterized as having relatively low modulus.

In certain embodiments, a polyurethane sealant or adhesive is provided, wherein the sealant or adhesive may have a 100 percent modulus of less than about 690 kPa (100 psi). In other embodiments, the polyurethane sealant may have a 100 percent modulus of about 345 kPa (50 psi) to about 690 kPa (100 psi). In yet other embodiments, the polyurethane sealant may have a 100 percent modulus of about 410 kPa (60 psi) to about 550 kPa (80 psi).

In certain embodiments, the polyurethane sealant may have a tensile strength of about 620 kPa (90 psi) or greater. In other embodiments, the polyurethane sealant may have a tensile strength of about 690 kPa (100 psi) or greater. In yet other embodiments, the polyurethane sealant may have a tensile strength of about 830 kPa (120 psi) or greater.

In certain embodiments, the polyurethane sealant may have an elongation at break of about 250 percent or greater. In other embodiments, the polyurethane sealant may have an elongation of about 300 percent or greater. In yet other embodiments, the polyurethane sealant may have an elongation of about 350 percent or greater.

Improved performance is typically obtained for clean and dry substrate surfaces. Surface preparation before sealant application can include water-blasting, sandblasting, cleaning, and drying of concrete surfaces, cleaning of metal surfaces with organic solvents, scuff-sanding and organic solvent wiping of composite surfaces, flame-etching of plastic surfaces, and the like.

5 When applied to a substrate, in certain embodiments, a polyurethane sealant is provided that is at least about 0.64 cm (0.25 inch) thick. In other embodiments, the polyurethane sealant is from about 0.64 cm (0.25 inch) to about 3.2 cm (1.25 inch) thick.

Paint adhesion was evaluated using a standard paint adhesion test method such as ASTM
10 D3359 Standard Test Method for Measuring Adhesion by Tape Test. Using this crosshatch adhesion test method, a rating of 5B is given to the sample if the edges of the cuts are completely smooth and none of the squares of the lattice is detached, therefore 0% adhesion failure. A rating of 4B applies if small flakes of the coating are detached at intersections of cuts, and less than 5% of the area is affected, therefore 5% adhesion failure. A rating of 3B applies if small flakes of the
15 coating are detached along edges and at intersections of cuts, and the adhesion failure area is 5 to 15% of the lattice. A rating of 2B applies if the coating has flaked along the edges and on parts of the squares, and the adhesion failure area is 15 to 35% of the lattice. A rating of 1B applies if the coating has flaked along the edges of cuts in large ribbons and whole squares have detached, and the adhesion failure area is 35 to 65% of the lattice. A rating of 0B applies if flaking and
20 detachment is worse than Grade 1B, corresponding to adhesion failure area of greater than 65% of the lattice.

The subject sealant or adhesive provides excellent paintability, defined as a high level adhesion between the sealant and an applied paint that can be measured by ASTM D 3359. In
25 certain embodiments, the polyurethane sealant reaction product is paintable such that paint adheres to the surface of the sealant with a rating of at least 3B when tested according to the paint adhesion test ASTM D3359. The paint may be a latex paint, solvent-borne paint, or solvent-free paint. Polyurethane sealants made according to the foregoing description demonstrate non-sag, high elongations, low modulus, and good paint adhesion for construction sealants.

30

When Parts A and B are mixed together, non-sag is created immediately as urea paste is immediately formed. Typically, when the base is mixed with the activator, the mixed product exhibits a grainy surface. The surface of the mixed product is typically difficult to process, particularly if a large amount of amine is added, such as greater than 1.2%. If smaller quantities

of amine are added such as 0.1-0.5%, the product exhibits poor non-sag properties and little improvement in terms of paintability and adhesion on substrates.

It is desirable to use from about 0.6 weight percent to about 0.8 weight percent of secondary amines such as piperazine, or from about 3 weight percent to about 4 weight percent of acrylate monomers, based on the weight of Part A and Part B in the formulation, in order to achieve paintability and good adhesion on various substrates. It has been found that depending on the type and amount of isocyanate blended into Part B, such as pure MDI or Lupranate® MI isocyanates, having a functionality of about 2, in the amount of from about 1% to about 4%, the surface condition of the mixed product may be improved, i.e., a less grainy, slightly textured or smooth surface can be achieved, while at the same time the resulting product exhibits paintability and good non-sag. Piperazine, a secondary amine, exhibits slower reactivity than a primary amine, and when added into the Base, it results in longer open time and an easy to form urea paste.

It was not previously known to enhance the paint adhesion of two component polyurethane systems by controlling the levels of aromatic isocyanate such as MDI in order to obtain very good paint adhesion. The addition of monomeric diisocyanate to the isocyanate terminated prepolymer (Activator) introduces more polar groups for hydrogen bonding and results in a less grainy, smoother surface after mixing Parts A and B, as it prevents too much of the secondary amine, such as piperazine, from reacting with the isocyanate terminated prepolymer. It was found that Lupranate® MI (MDI) performed well, as Lupranate® MI reacted with the secondary amine and formed a linear structure of urea paste which improved sag resistance and is good for paintability. Thus, modification of the Activator (Part B) to provide more linear structure by adding monomeric diisocyanate to the isocyanate terminated prepolymer results in a less grainy surface of mixed sealants.

Addition of short chain diols (i.e., Pluracol® P1010 having a molecular weight of 1,000), triols (i.e., Pluracol® 726 having a molecular weight of 3,000), and tetrols (i.e., Multranol® 9168, having a molecular weight of 3,740) was found to improve the paintability of the sealant. The paintability of sealants is further improved by introducing polar groups, i.e., formation of urea paste from the reaction of piperazine and isocyanates, and/or the introduction of an acrylate network into the sealants such as by low speed vacuum mixing, which also improves sealant sag resistance (acrylate thickening).

It was not previously known to improve non-sag, easy mixability and paintability of two component polyurethane sealant and adhesive systems by modification of polyol structure, addition of aromatic diisocyanate monomer into the activator Part B, and introduction of polar groups such as acrylate and urea paste formed insitu.

5

Test Methods:

Paintability was measured according to ASTM D3359 Standard Test Methods for Measuring Adhesion by Tape Test.

ASTM D412 Standard Test Methods for Vulcanized Rubber and Thermoplastic
10 Elastomers – Tension

Non-sag test method: ASTM D-2202.

The following specific examples are provided to illustrate, but not limit, the preparation of the adhesive and sealant formulations as discussed above. Examples were prepared using
15 various combinations of the following components:

Pluracol® 220, Pluracol® P1010, Pluracol® 726: polyols (BASF Corp., Wyandotte, MI).

Multranol® 9168 polyether polyol (Bayer Material Science, Pittsburgh, PA).

Piperazine diethylenediamine secondary amine (BASF SE, Germany).

Palatinol® DPHP decyl phthalate plasticizer (BASF Corporation, Houston, TX).

20 Hexamoll® DINCH 1,2-cyclohexanedicarboxylic acid, diisononyl ester (BASF SE, Germany)

Ultra-Pflex® precipitated calcium carbonate (Specialty Minerals, Inc., Bethlehem, PA).

Supercoat® surface modified calcium carbonate (Imerys Pigments, Roswell, GA).

Lowinox® 44B25 antioxidant (Chemtura Corp., Middlebury, CT).

25 Tinuvin® 328 benzotriazole light stabilizer (BASF Corporation, Florham Park, NJ).

Tinuvin® XT850 light stabilizers (BASF Corporation, Florham Park, NJ).

TMPTMA (Trimethylolpropane trimethacrylate) (Sartomer Company, Inc., Exton, PA).

Aerosil® 200 fumed silica (Evonik Industries).

Vazo® 52 free radical initiator (Dupont; Wilmington, DE).

30 Silquest A-187®, Silquest A-1100® adhesion promoters (Crompton Corp., Middlebury, CT).

Dabco® 33LV tertiary amine catalyst (Air Products and Chemicals, Inc.) and Dabco® T-12 catalyst (dibutyltindilaurate, DBTDL) (Air Products & Chemicals, Inc., Allentown, PA).

Lupranate® MI isocyanate (pure diphenylmethane diisocyanate); Lupranate® T-80 toluene diisocyanate (TDI) (80%-20% mixture of the 2,4 and 2,6 isomers of toluene diisocyanate);

Lupranate® M10 polymeric methylene diphenyl diisocyanate ; (BASF Corporation, Wyandotte, MI).

1,4-Butanediol (BASF Corporation, Geismar, LA)

m-Cresol (Sigma-Aldrich., St. Louis, MO.)

5 TiO₂ - titanium dioxide (DuPont, Wilmington, DE).

BzCl (Benzoyl Chloride): (Sigma-Aldrich Corp., St. Louis, MO).

PTSI (p-Toluenesulfonyl Isocyanate) storage stabilizer (VanDeMark Chemical, Inc., Lockport, NY).

Expancel® 551DE microspheres (AkzoNobel, Duluth, GA).

10 2, 5-Xylenol 2,5-dimethylphenol (Sichuan Hongguang and Taizhou Hiday, China).

BYK W-966/W-980 wetting and dispersing additives (BYK Chemie, Germany).

A100®: Acrylic latex primer (Sherwin-Williams, Inc., Cleveland, OH).

Colorflex™ acrylic elastomeric coating (BASF Corporation, Shakopee, MN).

Thoro® 20 acrylic copolymer waterproofing sealer (BASF Corporation, Shakopee, MN).

15 Thoro® 35 waterborne high-build acrylic copolymer waterproofing sealer (BASF Corporation, Shakopee, MN).

Z6106® Silane (Glycidoxypyl trimethoxysilane) (Dow Corning, Midland MI).

20 For some formulations, intermediate prepolymers and/or silane adducts were prepared as follows.

Preparation Of Intermediate 1

<u>Intermediate 1 Components</u>		Wt. %
1	Lupranate® M10	32.46
2	Hexamoll® DINCH	43.14
3	m-Cresol	24.35
4	Dabco® 33LV, 50% in Palatinol® DINCH	0.05
Total Weight		100.00
NCO% Final		0.87

Synthesis Procedure for Intermediate 1:

25 Lupranate® M10 and DINCH were added, mixed, and nitrogen purged. Then m-Cresol and Dabco® 33LV (50%) were added, mixed, and heated to 85°C to react for 2-5 hours. The mixture was then packaged.

Preparation Of Intermediates 2 and 3:

		Intermediate 2	Intermediate 3
<u>Components</u>		<u>Wt %</u>	<u>Wt %</u>
1	2, 5-Xylenol	26.84	22.24
2	Palatinol® DPHP	42.00	51.98
3	Lupranate® M10	31.10	25.54
4	Dabco® 33LV, 50% in Palatinol® DPHP	0.030	0.04
5	Dabco® 33LV, 50% in Palatinol® DPHP	0.030	0.04
6	PTSI	0.0	0.17
Total Weight		100.000	100.00
NCO% Final		0.82	0.52

5 Synthesis Procedure for Intermediate 2 and 3:

Xylenol and DPHP were added, mixed, and nitrogen purged. Lupranate® M10 and Dabco® 33LV (50%) were added, mixed, heated to 85°C to react for 2-5 hours, and cooled down. PTSI was added if necessary, mixed, and the mixture packaged.

TABLE 1: Silane Adduct Formulation

10

Component	Wt. %
Lupranate® T80	26.13
Palatinol® DPHP	50.42
15 Silquest A-1100® Silane	23.45
Total Weight	100.00
NCO/NH Ratio	1.41
NCO% Final	3.70

20

Synthesis Procedure for Silane Adduct:

Lupranate® T80 and DPHP were added, mixed, and nitrogen purged. Silane was added slowly, mixed, and heated, reacted for 2-5 hours, and cooled down, and the mixture packaged.

25

The exemplified Part A Base formulations are listed in Tables 2A and 2B.

TABLE 2A: Base Formulations (Part A)

Sealant Base Type	Urea	Urea	Acrylate	Acrylate	Acrylate Kit Mix #1	Acrylate Kit Mix #2
Base	1	2	3	4	5	6
Component	Wt. %	Wt. %	Wt. %	Wt. %	Wt. %	Wt. %
Pluracol® 220	26.81	--	29.75	--	28.1	28.1
Pluracol® P-726	--	32.5	--	35.8	8.8	8.8
Multranol® 9168	5.36	--	11.79	--	2.75	2.75
Palatinol® DPHP	11.01	11.1	6	9.1	8	8.46
Piperazine	1.6	1.7	--	--	--	--
Tinuvin® 328	0.32	0.34	0.33	0.33	0.35	0.35
Tinuvin® XT850	0.55	--	--	--	--	--
Lowinox® 44B25	0.32	0.34	0.33	0.33	0.35	0.35
TiO ₂ , Dried	3.83	4.08	3.89	3.89	--	4
Ultra-Pflex®, Dried	19.4	20.67	19.3	20.5	22.83	22.83
Supercoat®, Dried	30.25	25.31	22.83	23.91	20.28	20.26
Aerosil® 200	--	--	0.85	0.85	--	--
A-187	0.51	0.54	0.52	0.52	--	--
TMPTMA	--	--	4.3	4.65	4.5	4.05
Vazo® 52	--	--	0.047	0.049	0.046	0.041
T-12 Catalyst	0.049	0.07	0.07	0.08	0.02	0.02
Total Weight	100.00	100.00	100.00	100.00	100.02	100.00

TABLE 2B: Base Formulations (Part A)

Sealant Base Type	Urea	Urea	Urea	Urea
Base	7	8	9	10
Component	Wt. %	Wt. %	Wt. %	Wt. %
Pluracol® 220	25.87	30.1	26.24	25.55
Pluracol® P-726	3.4	3.46	3.44	3.44
Multranol® 9168	1.6	1.67	1.85	1.66
Palatinol® DPHP	17.74	16.38	14.29	14.17
Piperazine	1.23	1.27	1.1	1.09
Tinuvin® 328	0.35	0.35	0.36	0.35
Lowinox® 44B25	0.35	0.35	0.36	0.35
TiO ₂ , Dried	4	4	4.05	--
Ultra-Pflex®, Dried	24.97	24.97	27.27	28.91
Supercoat®, Dried	20.47	17.45	20	21.1
T-12 Catalyst	0.015	0.015	0.07	0.05
BYK W-980	--	--	--	1.09
BYK W-966	--	--	0.99	--
Expancel® 551DE	--	--	2.2	2.24
Total Weight	100.00	100.00	100.00	100.00

5 Part A Base samples were prepared according to the following procedures:

Synthesis Procedure for Urea containing Bases 1 and 2:

Polyols, DPHP, piperazine, antioxidant, UV absorbers, and TiO₂ were added, mixed to wet out, Ultra-Pflex® and Supercoat® were added, heated to 85°C, mixed, and cooled to 43°C. Silane
 10 and catalyst were added and mixed well, and the mixture packaged.

Synthesis Procedure for acrylate containing Bases 3 through 6:

Polyols, DPHP, antioxidant, UV absorbers, fumed silica (if necessary), and TiO₂ were added, mixed to wet out, Ultra-Pflex® and Supercoat® were added and mixed. TMPTMA was added, mixed, Vazo®-52 was added, heated to 77°C, vacuum mixed, and cooled to 43°C. Silane (if necessary) and catalyst were added and mixed well, and the mixture packaged.

Synthesis Procedure For urea containing Bases 7 through 10:

Polyols, DPHP, antioxidant, UV absorbers, and TiO₂ were added, mixed to wet out, Ultra-Pflex® and Supercoat® were added, heated to 85°C, mixed, and cooled to 43°C. The Piperazine/DPHP premix for Bases 7 through 10 was prepared in a glass container. Piperazine/DPHP premix was added, mixed, the BYK additive and Expancel (used in Bases 9 and 10) were added and mixed, catalyst was added and mixed well, and the mixture packaged.

TABLE 3: Activator Formulations (Part B)

Activator Formulation	1	2	3	4	5	6	7	8
Pluracol® 726, %	70.78	60	26.05	48	33.79	17.83	16.87	16.17
Pluracol® P1010, %	--	18.56	49.45	28.85	42	33.84	32.03	30.7
1,4-Butanediol, %	3.33	--	--	--	--	--	--	--
Lupranate® T80, %	25.21	21.1	21.18	19.51	20.52	14.49	13.72	13.15
Lupranate® MI, %	--	--	3.28	3.35	3.35	2.25	6.8	6.54
BzCl (1% solution in Pluracol® 726), %	0.53	--	--	--	--	--	--	--
BzCl (2% solution in Pluracol® 726), %	--	0.19	0.19	0.19	0.19	0.12	0.12	0.11
Dabco® 33LV (50% solution in Pluracol® 726), %	0.15	0.15	0.15	0.15	0.15	0.09	0.07	0.07
PTSI, %	0.27	0.25	0.25	0.25	0.25	0.16	0.16	0.15
Silane Adduct, %	--	--	--	--	--	10.98	10.68	10.29
Intermediate 1, %	--	--	--	--	--	20.24	--	--
Intermediate 3, %	--	--	--	--	--	--	19.56	22.83
Total	100.34	100.25	100.55	100.3	100.25	100.00	100.00	100.00
% NCO	5.98	6.01	5.96	6.01	4.8	4.81	6.07	5.79
NCO/OH ratio	1.97	2.44	2.14	2.33	1.93	1.88	2.77	2.76

Synthesis Procedure For Activator (prepolymer) 1 through 5:

Polyols and BzCl were added, mixed, and heated. Lupranate® T80 and Dabco® 33LV were added, reacted for 2-5 hours, and cooled down. Lupranate® MI if necessary and PTSI were added, mixed, and packaged.

Synthesis Procedure For Activator (prepolymer) 6 through 8:

Pluracol® 726, Pluracol® P1010, and BzCl were added, mixed, and heated. Lupranate® T80 and Dabco® 33LV were added, reacted for 2-5 hours, and cooled down. Lupranate® MI, PTSI, silane adduct, and Intermediate were added, mixed, and packaged.

5

TABLE 4: Two Part Sealants, Urea and Acrylate Containing Bases

Sealant Base Type	Urea	Urea	Urea	Urea	Acrylate	Acrylate
Example No.	1	2	3	4	5	6
Pluracol® 220, %	--	28.08	21.89	21	--	21.06
Pluracol® P1010, %	11.17	--	--	--	--	--
Pluracol® 726, %	4.6	--	22.04	--	--	--
Multranol® 9168, %	--	5.72	--	4.2	10.32	8.68
Piperazine, %	0.76	1.12	1.24	1.25	--	--
Palatinol® DPHP, %	6.34	--	8.22	8.92	5.14	5.34
TiO ₂ , %	1.97	2.81	2.98	3	3.08	3.2
Ultra-Pflex®, %	15.91	--	15.09	15.2	14.93	15.53
Supercoat®, %	22.66	27.44	22.14	23.4	21.09	21.93
Lowinox® 44B25, %	0.22	0.23	0.25	0.25	0.26	0.27
Tinuvin® 328, %	0.16	0.23	0.25	0.25	0.26	0.27
TMPTMA, %	--	--	--	--	3.32	3.45
Aerosil® 200	0.39	0.56	--	--	0.63	0.66
Vazo® 52, %	--	--	--	--	0.036	0.038
A-187, %	0.27	0.37	0.4	0.4	0.41	0.43
Dabco® 33LV, %	0.09	--	--	--	--	--
T-12, %	0.09	0.02	0.04	0.04	0.06	0.07
Lupranate® MI, %	--	--	2.44	2.46	0.71	0.65
Activator	2	1	2	3	2	2
Activator, %	35.03	33.41	24.51	20.41	18.29	17.19
NCO/(OH+NH) ratio	1.4	1.05	1.5	1.68	1.5	1.5
Non-Sag, B/S	0.09	0.03	0.07	0.03	0.05	0.03
Viscosity, poise	5,320	7,340	15,840	>40,000	12,760	13,260
Viscosity, Pa·s	532	734	1,584	>4,000	1,276	1,326
Surface	grainy	grainy	some texture, not grainy	less texture, not grainy	smooth	smooth
Paint Adhesion, A-100®	4.5B	2.5B	5B	4.2B	4.7B	5B
Tensile Strength, psi	127	228	162	132	121	105
Tensile Strength, kPa	875	1570	1120	910	834	724
100% Modulus, psi	68.3	86.5	85.9	58	65.3	60.2
100% Modulus, kPa	471	596	592	400	450	415
Elongation, %	275	406	232	329	435	420
Hardness Shore A	22.6	30.3	27.1	23.4	24.8	26

In Examples 1 – 4, shown in Table 4, good sag resistance was achieved by the addition of piperazine, although the surface began to exhibit a grainy texture as the amount of piperazine was increased. With the addition of pure diphenylmethane diisocyanate (Lupranate® MI), surface texture decreased and grainy features disappeared. Paintability of these Examples by A-100® acrylic latex primer was good to excellent. Also as shown in Table 4, Examples 5 and 6, to which acrylate monomer was added, achieved good sag resistance, a smooth sealant surface, excellent paintability by A-100® primer, and excellent tensile properties.

Tables 5 shows formulations of urea and acrylate base systems and compares their paintability for the following paints: A-100® Latex, Colorflex™, PVA Primer (grey), Thoro® 20 (brown) and Thoro® 35.

TABLE 5: Two Part Sealants Paintability

Sealant Base Type	Urea	Urea	Urea	Acrylate	Acrylate	Acrylate	Acrylate
Example No.	7	8	9	10	11	12	13
Polyol	P-220	P-726	P-726	P-220	P-220	P-726	P-726
Base	1	2	2	3	3	4	4
Base, %	77.40	71.07	71.61	80.31	77.9	74.52	72.14
Lupranate®	MI	MI	T80	MI	--	MI	MI
Lupranate®, %	2.43	2.46	1.72	0.67	--	0.85	0.67
Activator	5	5	5	4	5	4	5
Activator, %	20.17	26.47	26.67	19.02	22.1	24.63	27.19
A-100®	5B	5B	4B	5B	5B	5B	5B
Colorflex™	4B	5B	5B	4B	5B	5B	5B
PVA primer	5B	5B	5B	4B	4B	5B	5B
Thoro® 20	4B	5B	5B	0B	1B	0B	3B
Thoro® 35	4B	4B	5B	3B	5B	4B	5B
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Non-Sag, B/S	0.16	0.03	0.06	0.02	0.03	0.28	0.28
Surface	smooth	some texture	smooth	smooth	smooth	smooth	smooth

Test results shown in Table 5 illustrated excellent paintability for urea- and acrylate-containing sealant systems, and fair paintability toward Thoro® 20 sealer by the acrylate containing sealants. Thoro® 20 sealer is a difficult paint for sealants, as is seen in Table 6. The results in Table 5 also show that a smooth sealant surface could be achieved for the urea-containing sealant system.

Table 6 below compares the paintability of the present two part construction sealant as compared to sealants of Competitors 1 and 2. The exemplified subject sealants exhibited much better paintability than those of the competitors.

TABLE 6: Paintability Comparison

Paint	Urea	Acrylate	Competitor 1	Competitor 2
A-100® Latex	5B	5B	0.2B	1B
Colorflex™	5B	5B	3.4B	0B
PVA Primer	5B	5B	3.1B	3.5B
Thoro® 20	5B	2-3B	0.3B	0B
Thoro® 35	4B	5B	1.2B	0B

KEY: 0B: >65% failure 1B: 35-65% failure 2B: 15-35% failure
3B: 5-15% failure 4B: <5% failure 5B: 0% failure

TABLE 7: Acrylate Kit Mix

System	Acrylate Kit Mix #1	Acrylate Kit Mix #2
Base	5	6
Activator	6	6
Mix Ratio by Wt. of Base:Activator	3.55:1	3.55:1
A-100®, Colorflex™, PVA Primer & Thoro® 35	all 5B	all 5B
Thoro® 20	3B	2.5B
NCO/OH ratio	1.17	1.24
Non-Sag, B/S	0.0	0.0

Table 7 demonstrates the test results of a two part sealant utilizing two acrylate kit mixes in the Base Formulations. A kit mix is used in the method used by construction contractors to use and apply sealants in the field. A kit mix typically comprises a two gallon pail containing base, activator, and a color pack. Contractors mix the three parts together, and apply it on the construction joints to be sealed. The use of a kit mix enables testing of actual processing performance (such as ease of mixing and application, pot life, surface smoothness and sag resistance) of sealants, as if on a job in the field. The kit mixes demonstrated very good performance such as sag resistance and paintability.

The ethylenediamine (EDA) derived sealant formulations of the examples in Table 8, and the piperazine derived sealant formulations of the examples in Table 9 were prepared by mixing the identified components in the amounts listed therein.

NCO:(OH+NH) Ratio

In certain embodiments, the amount of base component Part A and activator component Part B used is sufficient to provide a ratio of isocyanate equivalents to the sum of polyol and amine equivalents of about 0.9:1 to about 1.7:1. In other embodiments, the NCO/(OH + NH) ratio is about 0.9:1 to about 1.4:1. In still other embodiments, the NCO/(OH + NH) ratio is about 1:1 to about 1.35:1. In some embodiments, the NCO/(OH + NH) ratio ranges from about 1.05:1 to about 1.25:1.

In certain embodiments, the components of Part A to Part B may be provided to be mixed at a weight ratio of about 5:1 to about 1.8:1. In some embodiments, the components of Part A to Part B may be provided to be mixed at a weight ratio of about 4.8:1 to about 2:1, in other embodiments at a weight ratio of about 4.5:1 to about 2.5:1.

TABLE 8: Ethylenediamine (EDA) Derived Sealant Formulations

Effect Of NCO:(OH+NH) Ratio And Various Amounts Of EDA

Example No.	14	15	16	17	18	19
Component	Wt. %	Wt. %	Wt. %	Wt. %	Wt. %	Wt. %
Pluracol® 220	25.6	24.9	26.55	25.9	25.9	25.9
Pluracol® 726	2.5	3	3	3.4	2.75	3.4
Multranol® 9168	2.7	2.9	1.35	1.6	2.25	1.5
Palatinol® DPHP	13.7	13.96	17.11	16.26	15.8	16.7
EDA	1.03	1.06	0.92	1.07	0.93	0.93
Tinuvin® 328	0.35	0.35	0.35	0.35	0.35	0.35
Lowinox® 44B25	0.35	0.35	0.35	0.35	0.35	0.35
TiO ₂ , Dried	4	4	4	4	4	4
Ultra-Pflex®, Dried	28.5	28.24	26	26.4	26.4	25.5
Supercoat®, Dried	21.25	21.22	20.35	20.76	21.25	21.26
T-12	0.008	0.014	0.016	0.024	0.018	0.024
Silane Adduct	3.33	3.35	3.28	3.31	3.31	3.31
Intermediate 2	6.2	6.25	6.09	6.15	6.15	6.15
Lupranate® MI	1.41	1.46	1.59	1.97	1.74	1.82
Activator 3	24.76	26.54	22.98	24.72	24.32	24.2
Total Weight	135.7	137.53	133.94	136.25	135.542	135.48
NCO/(OH+NH)	0.98	1.01	1.04	1.04	1.09	1.10
Non Sag, B/S	0.02	0.03	0.15	0.1	0.01	0.1
Viscosity, poise	63,700	48,300	19,800	38,300	30,900	51,100
Viscosity, Pa·s	6,370	4,830	1,980	3,830	3,090	5,110
Tensile Strength, psi	178	346	371	369	338	332
Tensile Strength, kPa	1,230	2,390	2,560	2,540	2,330	2,290
100% Modulus, psi	74.4	103.4	99.8	100.4	90.4	92.7
100% Modulus, kPa	513	712.9	688	692.2	623	639
Elongation, %	404	600	658	624	639	602
Hardness, Shore A	25.3	30.3	31.9	30.3	28.8	29.4

In the Examples reported in Table 8, ethylenediamine (EDA) was used to replace piperazine in the formulation of the base components. Results using various amounts of EDA, and NCO/(OH+NH) ratio were tested and are reported. The resulting sealants exhibited good sag resistance and excellent elongation. However, it was observed that piperazine may provide better performance than ethylenediamine.

TABLE 9: Effect Of Various NCO:(OH+NH) Ratios On Properties Of Sealants

Example No.	20	21	22	23	24	25
Sealant Base Type	Urea	Urea	Urea	Urea	Urea	Urea
Base	7	7	7	8	8	8
Pluracol® 220, %	19.94	19.65	19.08	22.52	22.11	21.56
Pluracol® 726, %	2.62	2.58	2.5	2.59	2.54	2.48
Multranol® 9168 %	1.23	1.21	1.18	1.25	1.23	1.2
Piperazine, %	0.95	0.94	0.91	0.95	0.93	0.91
Palatinol® DPHP %	13.67	13.47	13.08	12.25	12.03	11.73
TiO ₂	3.08	3.03	2.95	2.99	2.94	2.86
Ultra-Pflex®, %	19.25	18.96	18.41	18.68	18.35	17.89
Supercoat®, %	15.78	15.55	15.1	13.05	12.82	12.5
Lowinox® 44B25 %	0.27	0.27	0.26	0.26	0.26	0.25
Tinuvin® 328, %	0.27	0.27	0.26	0.26	0.26	0.25
T-12, %	0.015	0.015	0.015	0.015	0.015	0.015
Activator	7	7	7	7	7	7
Activator, %	22.92	24.07	26.27	25.20	26.54	28.36
Total	100.00	100.00	100.00	100.00	100.01	100.00
NCO/(OH+NH) ratio	0.91	0.97	1.09	0.97	1.04	1.14
Non-Sag, B/S	0.05	0.03	0.07	0.03	0.02	0.03
Viscosity, poise	12,500	12,600	9,760	16,200	22,100	15,400
Viscosity, Pa·s	1,250	1,260	976	1,620	2,210	1,540
Tensile Strength, psi	140	179	241	78.6	115	164
Tensile Strength, kPa	965	1,230	1,660	542	793	1,130
100% Modulus, psi	38.3	48.8	56.8	29	37.5	49.2
100% Modulus, kPa	264	336	392	200	259	339
Pot Life, hrs.	4	4	4	3.5	3	3
Surface	OK	OK	OK	Sticky	OK	OK
Elongation, %	503	533	642	358	427	480
Hardness	20	20.8	23.8	>15	19.3	21.7

The effect of a slight off-mix ratio for NCO/(OH+NH) was tested to determine whether the subject two part sealant might suffer adverse performance results during processing on the job, in the field. Test results for two batches of urea based sealants, containing Base Formulations 7 and 8, are reported in Table 9. Test results indicate that the performance remained good even with a mix ratio difference $\pm 10\%$.

TABLE 10: Effect of Various Additives

Example No.	26	27	28	29	30
Base	10	9	9	7	7
Activator	8	8	3	3	8
NCO/(OH+NH) ratio	1.28	1.28	1.18	1.14	1.28
Expancel®, volume %	34	34	34	34	34
BYK additive, %	W-966	W-980	W-980	--	--
Z6106® silane, %	--	--	1.31	1.35	--
Silane adduct, %	2.89	2.91	--	--	3.04
Color Pack, %	6.16	6.1	6.1	--	--
A-100	4.3B	5B	5B	4.2B	3.2B
Colorflex	5B	5B	5B	4B	5B
PVA Primer	3B	5B	5B	5B	5B
Thoro 20	5B	5B	5B	5B	5B
Thoro 35	1.3B	3.2B	5B	5B	5B
Tensile Strength, psi	189	125	72.9	152	130
Tensile Strength, kPa	1,300	862	503	1,050	896
100% Modulus, psi	93.7	63.7	34	77.5	72.1
100% Modulus, kPa	646	439	230	534	497
Elongation, %	266	281	429	280	233
Hardness, Shore A	27.1	20.8	18	24	22.3

Expancel® microspheres were blended into the base component, and Color Pack, a mixture of high molecular weight polyether polyols and pigments which give sealants various colors, was added also. Various adhesion promoters (silane adduct or Z-6106® silane) and BYK® (W-966 or W-980) wetting and dispersing additives were also added. The resulting sealants were tested for paintability and tensile properties, which remained very acceptable as reported in Table 10.

It will be understood that the embodiment(s) described herein is/are merely exemplary. Further, all embodiments disclosed are not necessarily in the alternative, as various embodiments may be combined to provide the desired result.

CLAIMS

We Claim:

1. A two part construction sealant or adhesive comprising a base component Part A and an
5 activator component Part B; wherein

Part A comprises:

at least one of a secondary amine or an acrylate monomer, and
a diol, triol and/or tetrol having a nominal weight average molecular weight of
between 1,000 and 6,000;

10 Part B comprises:

an aromatic diisocyanate monomer or polyisocyanate, and
an isocyanate terminated prepolymer of aromatic diisocyanate or polyisocyanate

and polyol;

the components of Part A to Part B provided to be mixed at a weight ratio of 5:1 to 1.8:1;

15 wherein the construction sealant or adhesive exhibits a paint adhesion of at least about 3B
when tested according to ASTM D3359; and a non-sag value of about 0.0-0.1 B/S when tested
according to ASTM D-2202; and at least one of: a 100% modulus of less than about 690 kPa
(100 psi) in the presence of a plasticizer when tested according to ASTM D412; a tensile strength
of about 690 kPa (100 psi) or greater when tested according to ASTM D412; or an elongation to
20 break of about 250% or greater when tested according to ASTM D412.

2. The sealant or adhesive according to claim 1, wherein the diol, triol or tetrol has a
nominal weight average molecular weight of between 3,000 and 6,000.

25 3. The sealant or adhesive according to claim 1, wherein the secondary amine comprises at
least one of piperazine, ethylenediamine, naphthalenediamine or mixtures thereof.

4. The sealant or adhesive according to claim 1, wherein the acrylate comprises at least one
of trimethylol propane triacrylate, triacrylate, mixtures of triacrylate and diacrylate, or mixtures
30 thereof.

5. The sealant or adhesive according to claim 1, wherein Part A comprises at least one
additional diol, triol or tetrol having a nominal weight average molecular weight of between
1,000 and 6,000.

6. The sealant or adhesive according to claim 5, wherein the diol or triol or tetrol having a nominal weight average molecular weight of between 1,000 and 6,000 comprises at least one of polyether polyol, propoxylated ethylenediamine polyol, polypropylene glycol, propylene oxide adduct of glycerine, or amine-based polyether polyol.

5

7. The sealant or adhesive according to claim 1, wherein the diol, triol or tetrol having a nominal weight average molecular weight of between 1,000 and 6,000 comprises at least one primary hydroxyl terminated polyol.

10 8. The sealant or adhesive according to claim 1, wherein the Part B aromatic diisocyanate monomer or polyisocyanate comprises at least one of toluene diisocyanate (TDI), methylene diphenyl diisocyanate (MDI), phenylene diisocyanate, diphenylmethane diisocyanate, polyphenylmethane polyisocyanate (polymeric MDI), naphthalene diisocyanate, triphenylmethane triisocyanate, diphenyl sulfone diisocyanate, toluene 2,4-diisocyanate, toluene
15 2,6-diisocyanate, naphthylene 1,5-diisocyanate, 4,4'-methylene diphenyl diisocyanate, 2,4'-methylene diphenyl diisocyanate, urethodione diisocyanate, hexahydrotolylene diisocyanate, 1-methoxyphenyl-2,4-diisocyanate, diphenylmethane-4,4'-diisocyanate, 4,4'-biphenylene diisocyanate, 3,3'-dimethoxy-4,4'-biphenyl diisocyanate, 3,3'-dimethyl-4,4'-biphenyl diisocyanate; 3,3'-dimethyldiphenylmethane-4,4'-diisocyanate, isomers, dimers and/or trimers of
20 these diisocyanates, or mixtures thereof.

9. The sealant or adhesive according to claim 1, wherein the Part B prepolymer comprises the reaction product of at least one diol, triol or tetrol having a nominal weight average molecular weight of between 1,000 and 6,000 and aromatic diisocyanate or polyisocyanate.

25

10. The sealant or adhesive according to claim 1, wherein the Part B prepolymer comprises at least one of ethylene glycol, diethylene glycol, propylene glycol, dipropylene glycol, butane diol, glycerol, trimethylolpropane, triethanolamine, pentaerythritol or sorbitol.

30 11. The sealant or adhesive according to claim 1 wherein the theoretical % NCO of Part B is in the range of about 2 to about 10%.

12. The sealant or adhesive according to claim 1, wherein Part A additionally comprises a plasticizer.

13. The sealant or adhesive according to claim 1, wherein Part A additionally comprises at least one of catalyst, inorganic filler, colorant, antioxidant, UV light absorber, free radical initiator, adhesion promoter, calcium oxide, expandable microspheres, drying agent, organic filler, chain extender, UV stabilizer, light stabilizer, fungicide, mildewcide, biocide, fire retardant, surface additive, mineral oil, dispersing agent, defoaming agent, storage stabilizer, latent hardener, cure retarder, antifoaming agent, solvent, or mixtures thereof.

14. The sealant or adhesive according to claim 1, wherein the NCO/(OH+NH) ratio is about 0.9:1 to about 1.7:1.

15. A method of making a two part construction sealant or adhesive of any of claims 1-14 comprising Part A and Part B, the method comprising:

a) providing a base component Part A and an activator component Part B, wherein Part A comprises at least one of a secondary amine or an acrylate monomer, and a diol, triol and/or tetrol having a nominal weight average molecular weight of between 1,000 and 6,000; and Part B comprises aromatic diisocyanate monomer or polyisocyanate and an isocyanate terminated prepolymer of aromatic diisocyanate or polyisocyanate and polyol; and

b) mixing the components of base component Part A with activator component Part B at a weight ratio of 5:1 to 1.8:1 to form a polyurethane sealant or adhesive reaction product;

wherein the sealant or adhesive reaction product exhibits a paint adhesion of at least about 3B when tested according to ASTM D3359; a non-sag value of about 0.0-0.1 B/S when tested according to ASTM D-2202; and at least one of a 100% modulus of less than about 690 kPa (100 psi) in the presence of a plasticizer when tested according to ASTM D412; a tensile strength of about 690 kPa (100 psi) or greater when tested according to ASTM D412; or an elongation to break of about 250% or greater when tested according to ASTM D412.

16. The method of claim 15, further comprising applying the reaction product to a substrate.

17. The method of claim 16, wherein said applying is at least one of spraying, brushing, rolling, squeegeeing, scraping, troweling, or combinations thereof.

18. The method of claim 16, wherein the substrate is at least one of concrete, stone, metal, ceramic, glass, plastic, wood, asphalt, thermoplastic materials, thermoset materials, rubber, or composite materials.

19. The method of claim 15, further comprising applying paint to the surface of the sealant or adhesive, wherein the paint adheres to the surface of the sealant or adhesive with a rating of at least 3B when tested according to paint adhesion test ASTM D3359.
- 5 20. The method of claim 19, wherein the paint is at least one of latex paint, solvent-borne paint, or solvent-free paint.