

(19)



INTELLECTUAL PROPERTY
OFFICE OF SINGAPORE

(11) Publication number:

SG 172674 A1

28.07.2011

(43) Publication date:

(51) Int. Cl:

;

(12)

Patent Application

(21) Application number: 2011040649

(71) Applicant:

CABOT MICROELECTRONICS
CORPORATION LEGAL DEPARTMENT,
870 NORTH COMMONS DRIVE,
AURORA, ILLINOIS 60504 UNITED
STATES OF AMERICA IN US

(22) Date of filing: 07.06.2007

(72) Inventor:

DYSARD, JEFFREY C/O
LEGAL DEPARTMENT, CABOT
MICROELECTRONICS CORPORATION,
870 NORTH COMMONS DRIVE,
AURORA, ILLINOIS 60504 UNITED
STATES OF AMERICA US

(30) Priority: US 11/448,205 07.06.2006

ANJUR, SRIRAM C/O LEGAL
DEPARTMENT, CABOT
MICROELECTRONICS CORPORATION,
870 N. COMMONS DRIVE, AURORA,
ILLINOIS 60504 UNITED STATES OF
AMERICA US

JOHNS, TIMOTHY C/O LEGAL
DEPARTMENT, CABOT
MICROELECTRONICS CORPORATION,
870 NORTH COMMONS DRIVE,
AURORA, ILLINOIS 60504 UNITED
STATES OF AMERICA US

CHEN, ZHAN C/O LEGAL
DEPARTMENT, CABOT
MICROELECTRONICS CORPORATION,
870 NORTH COMMONS DRIVE,
AURORA, ILLINOIS 60504 UNITED
STATES OF AMERICA US

(54) Title:

COMPOSITIONS AND METHODS FOR POLISHING SILICON
NITRIDE MATERIALS

(57) Abstract:

21 COMPOSITIONS AND METHODS FOR POLISHING
SILICON NITRIDE MATERIALS ABSTRACT The present
invention provides a method for polishing silicon nitride-
containing substrates. The method comprises abrading a
surface of a silicon nitride substrate with a polishing
composition, which comprises colloidal silica, at least one acidic
component, and an aqueous carrier. The at least one acidic
component has a pKa in the range of 1 to 4.5. The composition
has a pH in the range of 0.5 pH units less than the pKa of the
at least one acidic component to 1.5 pH units greater than the
pKa. No Figure

**COMPOSITIONS AND METHODS FOR POLISHING SILICON NITRIDE
MATERIALS**

ABSTRACT

The present invention provides a method for polishing silicon nitride-containing substrates. The method comprises abrading a surface of a silicon nitride substrate with a polishing composition, which comprises colloidal silica, at least one acidic component, and an aqueous carrier. The at least one acidic component has a pKa in the range of 1 to 4.5. The composition has a pH in the range of 0.5 pH units less than the pKa of the at least one acidic component to 1.5 pH units greater than the pKa.

No Figure

COMPOSITIONS AND METHODS FOR POLISHING SILICON NITRIDE MATERIALS

FIELD OF THE INVENTION

[0001] This invention relates to polishing compositions and methods. More particularly, this invention relates to methods for polishing silicon nitride-containing substrates and compositions therefor.

BACKGROUND OF THE INVENTION

[0002] Compositions and methods for chemical-mechanical polishing (CMP) of the surface of a substrate are well known in the art. Polishing compositions (also known as polishing slurries, CMP slurries, and CMP compositions) for CMP of surfaces of semiconductor substrates (e.g., integrated circuits) typically contain an abrasive, various additive compounds, and the like.

[0003] In general, CMP involves the concurrent chemical and mechanical abrasion of surface, e.g., abrasion of an overlying first layer to expose the surface of a non-planar second layer on which the first layer is formed. One such process is described in U.S. Patent No. 4,789,648 to Beyer et al. Briefly, Beyer et al., discloses a CMP process using a polishing pad and a slurry to remove a first layer at a faster rate than a second layer until the surface of the overlying first layer of material becomes coplanar with the upper surface of the covered second layer. More detailed explanations of chemical mechanical polishing are found in U.S. Patents No. 4,671,851, No. 4,910,155 and No. 4,944,836.

[0004] In conventional CMP techniques, a substrate carrier or polishing head is mounted on a carrier assembly and positioned in contact with a polishing pad in a CMP apparatus. The carrier assembly provides a controllable pressure to the substrate, urging the substrate against the polishing pad. The pad and carrier, with its attached substrate, are moved relative to one another. The relative movement of the pad and substrate serves to abrade the surface of the substrate to remove a portion of the material from the substrate surface, thereby polishing the substrate. The polishing of the substrate surface typically is further aided by the chemical activity of the polishing composition (e.g., by oxidizing agents, acids, bases, or other additives present in the CMP composition) and/or the mechanical activity of an abrasive suspended in the

polishing composition. Typical abrasive materials include silicon dioxide, cerium oxide, aluminum oxide, zirconium oxide, and tin oxide.

[0005] U.S. Patent No. 5,527,423 to Neville, et al., for example, describes a method for chemically-mechanically polishing a metal layer by contacting the surface of the metal layer with a polishing slurry comprising high purity fine metal oxide particles suspended in an aqueous medium. Alternatively, the abrasive material may be incorporated into the polishing pad. U.S. Patent No. 5,489,233 to Cook et al. discloses the use of polishing pads having a surface texture or pattern, and U.S. Patent No. 5,958,794 to Bruxvoort et al. discloses a fixed abrasive polishing pad.

[0006] A semiconductor wafer typically includes a substrate, such as silicon or gallium arsenide, on which a plurality of transistors have been formed. Transistors are chemically and physically connected to the substrate by patterning regions in the substrate and layers on the substrate. The transistors and layers are separated by interlevel dielectrics (ILDs), comprised primarily of some form of silicon oxide (SiO_2). The transistors are interconnected through the use of well-known multilevel interconnects. Typical multilevel interconnects are comprised of stacked thin-films consisting of one or more of the following materials: titanium (Ti), titanium nitride (TiN), tantalum (Ta), aluminum-copper (Al-Cu), aluminum-silicon (Al-Si), copper (Cu), tungsten (W), doped polysilicon (poly-Si), and various combinations thereof. In addition, transistors or groups of transistors are isolated from one another, often through the use of trenches filled with an insulating material such as silicon dioxide, silicon nitride, and/or polysilicon.

[0007] The traditional technique for forming interconnects has been improved by the method disclosed in U.S. Patent No. 4,789,648 to Chow et al., which relates to a method for producing coplanar multilevel metal/insulator films on a substrate. This technique, which has gained wide interest and produces multilevel interconnects, uses chemical mechanical polishing to planarize the surface of the metal layers or thin-films during the various stages of device fabrication.

[0008] Although many of the known CMP slurry compositions are suitable for limited purposes, the conventional tend to exhibit unacceptable polishing rates and corresponding

selectivity levels to insulator materials used in wafer manufacture. In addition, known polishing slurries tend to produce poor film removal traits for the underlying films or produce deleterious film-corrosion, which leads to poor manufacturing yields.

[0009] As the technology for integrated circuit devices advances, traditional materials are being used in new and different ways to achieve the level of performance needed for advanced integrated circuits. In particular, silicon nitride, silicon oxide, and polysilicon are being used in various combinations to achieve new and ever more complex device configurations. In general, the structural complexity and performance characteristics vary across different applications. There is an ongoing need for methods and compositions that allow for the removal rates of silicon nitride, silicon oxide and polysilicon materials to be adjusted or tuned during CMP to meet the polishing requirements for particular IC devices.

[0010] For example, there is a continuing need to achieve rapid silicon nitride removal rates for many IC device applications. Traditional polishing slurries have been designed for "stop on silicon nitride" applications, such as in shallow trench isolation (STI). Typical STI slurries utilize silica abrasives at high pH and high abrasive concentrations to achieve reasonable silicon nitride removal rates. The use of high abrasive particle concentrations has been associated with a high level of scratch defects in the polished devices.

[0011] Co-owned, co-pending U.S. Patent Application Serial No. 11/374,238 to Chen et al. describes novel polishing compositions having a pH of 1 to 6 including an abrasive in combination with certain acidic components (e.g., combinations of malonic acid and an aminocarboxylic acid; stannate salts; uric acid; phenylacetic acid; or combinations of malonic acid, an aminocarboxylic acid, and sulfate) to polish silicon nitride substrates.

[0012] There is an ongoing need to develop new polishing methods and compositions that provide relatively high rates of removal of silicon nitride. The present invention provides such improved polishing methods and compositions. These and other advantages of the invention, as well as additional inventive features, will be apparent from the description of the invention provided herein.

BRIEF SUMMARY OF THE INVENTION

[0013] The present invention provides methods for polishing a silicon nitride-containing surface and polishing compositions useful in such methods. In a preferred embodiment, the present invention provides a method for polishing a silicon nitride-containing substrate. The method comprises abrading a surface of a silicon nitride-containing substrate with a polishing composition comprising colloidal silica, at least one acidic component having a pKa in the range of 1 to 4.5, and an aqueous carrier. The pH of the polishing composition is in the range of 0.5 pH units less than the pKa of the at least one acidic component to 1.5 pH units greater than the pKa.

[0014] The acidic component preferably is an inorganic acid, a carboxylic acid, an organic phosphonic acid, an acidic heterocyclic compound, a salt thereof, or a combination of two or more of the foregoing.

[0015] The composition comprises 0.01 to 15% by weight of colloidal silica and 10 to 100,000 ppm (0.001 to 10% by weight) of at least one acidic component.

[0016] In some preferred embodiments, the removal rate for silicon oxide obtained when polishing a silicon oxide wafer is less than the corresponding silicon nitride removal rate, obtained when polishing a silicon nitride wafer with the same slurry under the same polishing condition, particularly for compositions comprising relatively low levels of colloidal silica (i.e., 0.05 to 4% by weight). Typically the silicon nitride removal rate exceeds the silicon oxide removal rate by a factor of 2 or more, more typically by a factor of 10 or more, for compositions comprising 0.1 to 4% by weight of colloidal silica. In addition, similar selectivity can be obtained for silicon nitride versus polysilicon.

[0017] In another aspect, the present invention provides a chemical-mechanical polishing method for polishing a silicon nitride-containing substrate. The method comprises the steps of contacting a surface of a silicon nitride-containing substrate with a polishing pad and an aqueous polishing composition, and causing relative motion between the polishing pad and the substrate while maintaining a portion of the polishing composition in contact with the surface between the pad and the substrate for a time period sufficient to abrade at least a portion of the substrate surface. The polishing composition comprises 0.01 to 15% by weight of colloidal

silica, 10 to 100,000 ppm of at least one acidic component having a pKa in the range of 1 to 4.5, and an aqueous carrier. The pH of the polishing composition is in the range of 0.5 pH units less than the pKa of the at least one acidic component to 1.5 pH units greater than the pKa.

DETAILED DESCRIPTION OF THE INVENTION

[0018] The present invention provides methods for polishing a silicon nitride-containing surface. In a preferred embodiment, the method comprises abrading a surface of a silicon nitride-containing substrate with a polishing composition comprising colloidal silica, at least one acidic component having a pKa in the range of 1 to 4.5, and an aqueous carrier. The pH of the polishing composition is in the range of 0.5 pH units less than the pKa of the at least one acidic component to 1.5 pH units greater than the pKa.

[0019] The colloidal silica is present in the polishing composition in an amount in the range of 0.01 to 15% by weight. Preferably, the colloidal silica is present in the CMP composition in an amount in the range of 0.05 to 8% by weight, more preferably 0.1 to 4% by weight. The colloidal particles preferably have a mean particle size in the range of 1 nm to 500 nm, more preferably 10 nm to 50 nm, as determined by laser light scattering techniques, which are well known in the art.

[0020] The colloidal silica desirably is suspended in the polishing composition, more specifically in the aqueous carrier component of the polishing composition. When the silica is suspended in the polishing composition, it preferably is colloidally stable. The term "colloid" refers to the suspension of abrasive particles in the liquid carrier. "Colloidal stability" refers to the maintenance of that suspension over time. In the context of this invention, a silica suspension is considered colloidally stable if, when the silica is placed into a 100 mL graduated cylinder and allowed to stand without agitation for a time of 2 hours, the difference between the concentration of particles in the bottom 50 mL of the graduated cylinder ([B] in terms of g/mL) and the concentration of particles in the top 50 mL of the graduated cylinder ([T] in terms of g/mL) divided by the total concentration of particles in the abrasive composition ([C] in terms of g/mL) is less than or equal to 0.5 (i.e., $([B] - [T])/[C] \leq 0.5$). The value of $([B] - [T])/[C]$ desirably is less than or equal to 0.3, and preferably is less than or equal to 0.1.

[0021] As used herein and in the appended claims, the term "colloidal silica" refers to silicon dioxide that has been prepared by condensation polymerization of Si(OH)_4 . The precursor Si(OH)_4 can be obtained, for example, by hydrolysis of high purity alkoxysilanes, or by acidification of aqueous silicate solutions. Such abrasive particles can be prepared in accordance with U. S. Patent 5,230,833 or can be obtained as any of various commercially available products, such as the Fuso PL-1, PL-2, and PL-3 products, and the Nalco 1050, 2327, and 2329 products, as well as other similar products available from DuPont, Bayer, Applied Research, Nissan Chemical, and Clariant.

[0022] As used herein and in the appended claims in reference to the compositions and methods of the invention, the term "at least one acidic component having a pKa in the range of 1 to 4.5" encompasses materials comprising at least one acidic hydrogen that has a dissociation constant corresponding to a pKa in the range of 1 to 4.5. Accordingly, materials having a single acidic hydrogen, as well as materials having two or more acidic hydrogens fall within the scope of the acid component of the compositions. Materials that have two or more acidic hydrogens (e.g., sulfuric acid, phosphoric acid, succinic acid, citric acid, and the like) have a plurality of successive pKa values corresponding to the successive dissociation of each acidic hydrogen. For example, phosphoric acid has three acidic hydrogens, and three pKa values (i.e., 2.1, 7.2, and 12.4) corresponding to dissociation of the first, second, and third hydrogens, respectively. For materials having multiple acidic hydrogens, only one of the pKa values must be in the range of 1 to 4.5. Any other acidic hydrogen in such compounds can have a pKa within the range of 1 to 4.5, can have a pKa less than 1, or can have a pKa greater than 4.5.

[0023] The acidic component comprises 0.001 to 10% by weight (10 ppm to 100,000 ppm) of the polishing composition. Preferably, the acidic component is present in the composition in an amount in the range of 100 to 5000 ppm, more preferably in the range of 500 to 2000 ppm.

[0024] The acidic component can be any inorganic or organic acid having a pKa in the range of 1 to 4.5. In some preferred embodiments, the acidic component can be an inorganic acid, a carboxylic acid, an organophosphonic acid, an acidic heterocyclic compound, a salt thereof, or a combination of two or more of the foregoing. Non-limiting examples of suitable inorganic acids include sulfuric acid (i.e., hydrogen sulfate ion, HSO_4^-), phosphoric acid,

phosphorous acid, pyrophosphoric acid, sulfurous acid, and tetraboric acid). Non-limiting examples of suitable carboxylic acids include, monocarboxylic acids (e.g., benzoic acid, phenylacetic acid, 1-naphthoic acid, 2-naphthoic acid, glycolic acid, formic acid, lactic acid, mandelic acid, and the like), and polycarboxylic acids (e.g., oxalic acid, malonic acid, succinic acid, adipic acid, tartaric acid, citric acid, maleic acid, fumaric acid, aspartic acid, glutamic acid, phthalic acid, isophthalic acid, terephthalic acid, 1,2,3,4-butanetetracarboxylic acid, itaconic acid, and the like). Non-limiting examples of suitable organic phosphonic acids include, include phosphonoacetic acid, iminodi(methylphosphonic acid), DEQUEST® 2000LC brand amino-tri(methylenephosphonic acid), and DEQUEST® 2010 brand hydroxyethylidene-1,1-diphosphonic acid, both of which are available from Solutia. Non-limiting examples of suitable acidic heterocyclic compounds include uric acid, ascorbic acid, and the like. Table 1 provides a non-limiting listing of selected suitable acidic components, along with their reported pKa values. The pKa values of various inorganic and organic acids are compiled in a number of sources familiar to those of ordinary skill in the chemical arts, including, without limitation various editions of The CRC Handbook of Chemistry and Physics, published by The Chemical Rubber Company, and Lange's Handbook of Chemistry, published by McGraw-Hill, to name a few. For acids whose pKa values were not found in the literature, the pKa values were estimated using ACD/pKa dB software (Advanced Chemistry Development, Inc., Toronto, Canada).

[0025] Varying the pH of the compositions, within the limits of the invention (i.e., 0.5 units less than the pKa to 1.5 units greater than the pKa) will generally result in changes in silicon nitride removal rates. For example, a composition comprising 0.5% by weight of colloidal silica, 0.01 mol/L of DEQUEST® 2010 and 0.02 mol/L sulfate afforded a nitride removal rate of 650 Å/min at pH 2.2, while at pH 3, the removal rate was 300 Å/min when measured under the same polishing conditions. In other cases, the removal rate may increase with increasing pH. For example, a composition comprising 0.5% by weight of colloidal silica, 0.01 mol/L of phthalic acid and 0.02 mol/L sulfate afforded a nitride removal rate of 300 Å/min at pH 3, while at pH 4, the removal rate was 400 Å/min when measured under the same polishing conditions.

Table 1. pKa values of various acids.

Acid	pKa	Acid	pKa	Acid	pKa
adipic	4.43; 4.41	itaconic	3.85; 5.45	sulfanilic	3.23
anisic	4.47	lactic	3.08	alpha-tartaric	2.98; 4.34
ascorbic	4.10; 11.79	maleic	1.83; 6.07	meso-tartaric	3.22; 4.82
aspartic	3.86; 9.82	malonic	2.83; 5.69	o-toluic	3.91
benzoic	4.19	mandelic	3.85	m-toluic	4.27
BTC*	3.36; 4.38; 5.45; 6.63	1-naphthoic	3.70	p-toluic	4.36
chloroacetic	2.85	2-naphthoic	4.17	uric	3.89
o-chlorobenzoic	2.92	oxalic	1.23; 4.19	D 2000**	~1-2****
citric	3.14, 4.77; 6.39	phenylacetic	4.28	D 2010***	~1-2****
formic	3.75	phthalic	2.89; 5.51	nitrous	3.37
glutamic	2.19; 9.13	isophthalic	3.54; 4.60	phosphoric	2.12; 7.21; 12.67
glutaric	4.34; 5.41	terephthalic	3.51; 4.82	phosphorous	2.00; 6.59
glycine	2.34; 9.60	quinolinic	2.52	sulfuric	-3; 1.99
glycolic	3.83	salicylic	2.98	sulfurous	1.81; 6.91
hippuric	3.64	succinic	4.16; 5.61	tetraboric	4.0; 9.0

*butane-1,2,3,4-tetracarboxylic acid

**DEQUEST® 2000 (amino-tri(methylenephosphonic acid))

***DEQUEST® 2010LA (hydroxyethylidene-1,1-diphosphonic acid) sold as a 60% aqueous solution.

**** while amino-tri(methylenephosphonic acid) and hydroxyethylidene-1,1-diphosphonic acid) each have more than one pKa value, estimated to be between 1 and 2 as calculated by ACD/pKa dB software (Advanced Chemistry Development, Inc., Toronto, Canada).

[0026] The compositions and methods of the invention provide useful silicon nitride removal rates over a wide range of pH, colloidal silica concentration, and acid component concentration. In some particularly preferred embodiments, the silicon nitride removal rate is 250 Angstroms per minute (Å/min) or greater when polishing a silicon nitride blanket wafer on a table-top CMP polisher at a down force of 3.5 pounds per square inch (psi), a platen speed of 60 revolutions per minute (rpm), a carrier speed of 56 rpm, and a polishing slurry flow rate of

100 milliliters per minute (mL/min). As an added benefit, the compositions of the present invention can also provide for selective removal of silicon nitride in the presence of silicon oxide or polysilicon.

[0027] The polishing compositions of the invention optionally can include one or more oxidizing agent (e.g., to oxidize a component of the semiconductor surface, such as a metal component). Oxidizing agents suitable for use in the polishing compositions and methods of the present invention include, without limitation hydrogen peroxide, persulfate salts (e.g., ammonium monopersulfate, ammonium dipersulfate, potassium monopersulfate, and potassium dipersulfate), periodate salts (e.g., potassium periodate), salts thereof, and a combination of two or more of the foregoing. Preferably, the oxidizing agent is present in the composition in an amount sufficient to oxidize one or more selected metallic or semiconductor material present in the semiconductor wafer, as is well known in the semiconductor CMP art.

[0028] The polishing compositions of the invention can also optionally include suitable amounts of one or more other additive materials commonly included in polishing compositions, such as metal complexing agents, corrosion inhibitors, viscosity modifying agents, biocides, and the like.

[0029] In preferred embodiments, the polishing compositions further comprise a biocidal amount of a biocide (e.g., an isothiazolinone composition such as KATHON® biocide, available from Rohm and Haas).

[0030] The aqueous carrier can be any aqueous solvent, e.g., water, aqueous methanol, aqueous ethanol, a combination thereof, and the like. Preferably, the aqueous carrier is deionized water.

[0031] The polishing compositions of the invention have a pH in the range of 0.5 units less than the pKa of the acidic component (i.e., a pKa which falls within the range of 1 to 4.5) to 1.5 units greater than the pKa. For example, if the acidic component is phosphoric acid (pKa = 2.12, 7.21, 12.67) the pH of the composition can be in the range of 1.6 to 3.6 (i.e., 0.5 less than 2.12 to 1.5 greater than 2.12. Similarly, if the acidic component is oxalic acid (pKa = 1.23, 4.19), the pH of the composition can be in the range of 0.7 to 5.7 (i.e., 0.5 less than 1.23 to 1.5 greater than 4.19), since both pKa values of oxalic acid fall within the range of 1 to 4.5.

[0032] The polishing compositions of the invention can be prepared by any suitable technique, many of which are known to those skilled in the art. The polishing composition can be prepared in a batch or continuous process. Generally, the polishing composition can be prepared by combining the components thereof in any order. The term "component" as used herein includes individual ingredients (e.g., colloidal silica, acids, bases, oxidizing agents, and the like), as well as any combination of ingredients. For example, the colloidal silica can be dispersed in water, and the acidic component can be added, and mixed by any method that is capable of incorporating the components into the polishing composition. Typically, an oxidizing agent, when utilized, is not added to the polishing composition until the composition is ready for use in a CMP process, for example, the oxidizing agent can be added just prior to initiation of polishing. The pH can be further adjusted at any suitable time by addition of an acid or base, as needed.

[0033] The polishing compositions of the present invention also can be provided as a concentrate, which is intended to be diluted with an appropriate amount of aqueous solvent (e.g., water) prior to use. In such an embodiment, the polishing composition concentrate can include the various components dispersed or dissolved in aqueous solvent in amounts such that, upon dilution of the concentrate with an appropriate amount of aqueous solvent, each component of the polishing composition will be present in the polishing composition in an amount within the appropriate range for use.

[0034] The invention also provides a method of chemically-mechanically polishing a silicon nitride substrate. The method comprises (i) contacting a surface of a silicon nitride-containing substrate with a polishing pad and a polishing composition of the invention as described herein, and (ii) moving the polishing pad relative and the surface of the substrate relative to one another, while maintaining at least a portion of the polishing composition between the pad and the surface, thereby abrading at least a portion of the surface to polish the substrate.

[0035] The polishing compositions of the present invention can be used to polish any suitable substrate, and is especially useful for polishing substrates comprising silicon nitride, as well as substrates containing silicon nitride and silicon oxide and/or polysilicon. The

compositions of the present invention provide relatively high silicon nitride removal rates at abrasive levels low enough to avoid excessive scratch defects. In particular, the formulation and pH of the CMP composition can be varied to vary the silicon nitride removal rate. In some preferred embodiments, particularly those including 4 percent or less of colloidal silica, the relative rate of silicon nitride removal exceeds the rate for removal of silicon oxide and/or polysilicon. This selectivity is an additional asset for use in polishing modern semiconductor materials with relatively narrow oxide line widths.

[0036] The polishing compositions of the present invention are particularly suited for use in conjunction with a chemical-mechanical polishing apparatus. Typically, the CMP apparatus comprises a platen, which, when in use, is in motion and has a velocity that results from orbital, linear, and/or circular motion, a polishing pad in contact with the platen and moving relative to the platen when in motion, and a carrier that holds a substrate to be polished by contacting and moving relative to the surface of the polishing pad. The polishing of the substrate takes place by the substrate being placed in contact with the polishing pad and a polishing composition of the invention and then moving the polishing pad relative to the substrate, so as to abrade at least a portion of the substrate to polish the substrate.

[0037] A substrate can be planarized or polished with a polishing composition of the invention using any suitable polishing pad (e.g., polishing surface). Suitable polishing pads include, for example, woven and non-woven polishing pads, grooved or non-grooved pads, porous or non-porous pads, and the like. Moreover, suitable polishing pads can comprise any suitable polymer of varying density, hardness, thickness, compressibility, ability to rebound upon compression, and compression modulus. Suitable polymers include, for example, polyvinylchloride, polyvinylfluoride, nylon, fluorocarbon, polycarbonate, polyester, polyacrylate, polyether, polyethylene, polyamide, polyurethane, polystyrene, polypropylene, coformed products thereof, and mixtures thereof.

[0038] Desirably, the CMP apparatus further comprises an in situ polishing endpoint detection system, many of which are known in the art. Techniques for inspecting and monitoring the polishing process by analyzing light or other radiation reflected from a surface of the workpiece are known in the art. Such methods are described, for example, in U.S. Patent

No. 5,196,353 to Sandhu et al., U.S. Patent No. 5,433,651 to Lustig et al., U.S. Patent No. 5,949,927 to Tang, and U.S. Patent No. 5,964,643 to Birang et al. Desirably, the inspection or monitoring of the progress of the polishing process with respect to a workpiece being polished enables the determination of the polishing end-point, i.e., the determination of when to terminate the polishing process with respect to a particular workpiece.

[0039] The following examples further illustrate the invention but, of course, should not be construed as in any way limiting its scope. As used herein and in the following Examples and claims, concentrations reported as parts per million (ppm) are based on the weight of the active component of interest divided by the weight of the composition (e.g., as milligrams of component per kilogram of composition). For example, DEQUEST® 2010LA is sold as a 60% by weight aqueous solution of hydroxyethylidene-1,1-diphosphonic acid; thus, 2000 ppm of DEQUEST® 2010LA refers to 2000 milligrams of hydroxyethylidene-1,1-diphosphonic acid in one kilogram of the composition on an actives basis, which corresponds to 3300 milligrams of DEQUEST® 2010LA product (60 percent aqueous solution) in 996.7 grams of the CMP composition.

EXAMPLE 1

[0040] This example illustrates the effectiveness of the compositions of the present invention for polishing silicon nitride substrates.

[0041] Ten different polishing compositions were used to separately chemically-mechanically polish similar silicon nitride blanket wafers (Compositions 1A-1J). Each of the polishing compositions comprised 0.5 to 5% by weight of colloidal silica (having a mean particle size of 20 nm). The amount of silica, the amount and type of acid, the pH of the composition, and the pKa of the acid for each composition are shown in Table 2. Examples 1B, 1D, 1F, and 1I are compositions of the invention, while Examples 1A, 1C, 1E, 1G, and 1H are comparative compositions in which the pH of the composition is outside the range of the invention.

[0042] The polishing compositions were utilized on a bench-top polisher to polish blanket wafers of silicon nitride under the following polishing conditions: down-force of 3.5 psi, platen

speed of 60 rpm, carrier speed of 56 rpm, and a slurry feed rate of 100 mL per minute (mL/min). The silicon nitride removal rate ("Nitride RR") obtained for each polishing composition was determined. The results are set forth in Table 2.

Table 2: Effects of acidic components and pH on silicon nitride removal rates

Example	Wt % Silica	Acid Component (Amount, ppm)	pH	pKa	Nitride RR Å/min
1A (comparative)	0.5	D2010 (2000 ppm)*	4	1-2	133
1B (inventive)	0.5	D2010 (2000 ppm)*	2.2	1-2	641
1C (comparative)	0.5	succinic acid (1180 ppm)	2.2	4.19	0
1D (inventive)	0.5	succinic acid (1180 ppm)	5	4.19	259
1E (comparative)	0.5	phthalic acid (1660 ppm)	2.2	2.98	44
1F (inventive)	0.5	phthalic acid (1660 ppm)	4	2.98	383
1G (comparative)	2	5.5 mS nitric acid (to pH 2.2)	2.2	-1.3	32
1H (comparative)	2	70 mS nitric acid (to pH 2.2)	2.2	-1.3	173
1I (inventive)	2	sulfate (2000 ppm)	2.2	1.99	548

*DEQUEST® 2010LA (hydroxyethylidene-1,1-diphosphonic acid)

[0043] As is apparent from the results set forth in Table 2, each of the inventive polishing compositions exhibited a silicon nitride removal rate of greater than 250 Å/min. The comparative compositions exhibited considerably lower removal rates.

EXAMPLE 2

[0044] This example illustrates the importance of colloidal silica in the compositions of the invention for removal of silicon nitride.

[0045] Silicon nitride blanket wafers were polished with a series of different polishing compositions on a bench-top polisher at a down force of 3.5 psi, a platen speed of 60 rpm, a carrier speed of 56 rpm, and a polishing slurry flow rate of 100 mL/min. All of the polishing compositions were prepared in deionized water with 3000 ppm of sulfuric acid as the acidic component, at a pH of 2.2, and with either 4 or 8% by weight of silica. Examples 2A and 2B included fumed silica in place of the colloidal silica, for comparison purposes. The amounts and type of silica are shown in Table 3, along with the silicon nitride removal rate (RR) observed for each composition.

Table 3: Effects of silica type silicon nitride removal rates

Example	Wt % Silica	Silica type (Amount, ppm)	Nitride RR Å/min
2A (comparative)	4	fumed silica	28
2B (comparative)	8	fumed silica	32
2C (inventive)	4	colloidal silica	873
2D (inventive)	8	colloidal silica	1029

[0046] The data in Table 3 clearly indicate the importance of utilizing colloidal silica in the compositions of the present invention, compared to fumed silica, which afforded a low nitride removal rate.

EXAMPLE 3

[0047] This example illustrates the effect of colloidal silica concentration on the removal of silicon nitride.

[0048] Silicon nitride blanket wafers were polished with a series of different polishing compositions on a bench-top polisher at a down force of 3.5 psi, a platen speed of 60 rpm, a carrier speed of 56 rpm, and a polishing slurry flow rate of 100 mL/min. All of the polishing compositions were prepared in deionized water with 2000 ppm of hydroxyethylidene-1,1-diphosphonic acid (DEQUEST® 2010LA) as the acidic component, at a pH of 2.2, and with 0 to 8% by weight of silica. The amounts of silica used are shown in Table 4, along with the silicon nitride removal rate (RR) observed for each composition.

Table 4: Effects of silica concentration on silicon nitride removal rates

Example	Wt % Silica	Nitride RR Å/min
3A (comparative)	0	2
3B (inventive)	0.2	510
3C (inventive)	2	853
3D (inventive)	4	986
3E (inventive)	8	983

[0049] The data in Table 4 demonstrate that effective removal of silicon nitride was observed even with silica levels as low as 0.2% by weight.

EXAMPLE 4

[0050] This example illustrates the effect of acid concentration and colloidal silica concentration on the removal of silicon nitride.

[0051] Silicon nitride blanket wafers were polished with a series of different polishing compositions on a bench-top polisher at a down force of 3.5 psi, a platen speed of 60 rpm, a carrier speed of 56 rpm, and a polishing slurry flow rate of 100 mL/min. All of the polishing compositions were prepared in deionized water with 10 to 1000 ppm of hydroxyethylidene-1,1-diphosphonic acid (DEQUEST® 2010LA) as the acidic component, at a pH of 2.2, and with 0.5 or 5% by weight of silica. The amounts of silica and acid component used are shown in Table 5, along with the silicon nitride removal rate (RR) observed for each composition.

Table 5: Effects of acid concentration on silicon nitride removal rates

Example	Wt % Silica	Acid Component* (Amount, ppm)	Nitride RR Å/min
4A (inventive)	0.5	D2010 (100 ppm)	450
4B (inventive)	0.5	D2010 (200 ppm)	591
4C (inventive)	0.5	D2010 (500 ppm)	612
4D (inventive)	0.5	D2010 (1000 ppm)	695
4E (inventive)	5	D2010 (10 ppm)	238
4F (inventive)	5	D2010 (100 ppm)	705
4G (inventive)	5	D2010 (200 ppm)	805
4H (inventive)	5	D2010 (500 ppm)	783
4I (inventive)	5	D2010 (1000 ppm)	907

*DEQUEST® 2010LA (hydroxyethylidene-1,1-diphosphonic acid)

The data in Table 5 indicate that effective silicon nitride removal can be achieved under a broad range of acid and colloidal silica concentrations.

EXAMPLE 5

[0052] This example illustrates the selectivity for removal of silicon nitride relative to silicon oxide.

[0053] Silicon nitride and silicon oxide blanket wafers were polished with a series of different polishing compositions. All of the polishing compositions were prepared in deionized water including 0.1 and 1% by weight of colloidal silica with 2060 ppm hydroxyethylidene-1,1-diphosphonic acid (DEQUEST® 2010LA) (Ex. 5A and 5B), 1660 ppm phthalic acid (Ex. 5C and 5D), and 2000 ppm sulfuric acid (hydrogen sulfate) (Ex. 5E and 5F) as the acid components as the acid components. These compositions were utilized to polish silicon nitride and silicon oxide blanket wafers on a Mirra polisher at 4 psi down pressure, 93 rpm platen speed, 86 rpm carrier speed, and 150 mL flow rate. The results for these tests are shown in Table 6.

Table 6. Effects of acidic components on silicon nitride and silicon dioxide removal rates

Polishing Composition	Nitride RR (Å/min)	Oxide RR (Å/min)	Selectivity
5A (0.1% silica)	100	19	5.3
5B (1% silica)	500	70	7.1
5C (0.1% silica)	450	27	16.9
5D (1% silica)	680	130	5.2
5E (0.1% silica)	120	14.5	8.2
5F (1% silica)	510	69	7.4

[0054] The results in Table 6 demonstrate very high selectivity for silicon nitride versus silicon oxide under the polishing conditions evaluated.

EXAMPLE 6

[0055] This example illustrates selectivity for removal of silicon nitride relative to polysilicon.

[0056] Silicon nitride and polysilicon blanket wafers were polished with two different polishing compositions of the invention on a table-top CMP polisher at a down force of 3.5 psi, a platen speed of 60 rpm, a carrier speed of 56 rpm, and a polishing slurry flow rate of 100 mL/min. The compositions had a pH of 2.3 and included 500 ppm of hydroxyethylidene-1,1-diphosphonic acid (DEQUEST® 2010LA) and either 0.5 or 5% by weight of colloidal silica. The silicon nitride and polysilicon removal rates for each composition were determined. CMP of polysilicon typically exhibits an initiation time due to removal of a protective oxide coating on the surface of the silicon. Accordingly, the polysilicon removal rate is determined by plotting the amount of polysilicon removed after 10 seconds, 60 seconds and 180 seconds. The polysilicon removal rate in Å/min is then calculated as the amount of polysilicon removed during the one minute interval between 30 seconds of polishing and 90 seconds of polishing, by reference to the plot.

[0057] The composition comprising 0.5% by weight colloidal silica exhibited a silicon nitride removal rate of 600 Å/min, and a polysilicon removal rate of 130 Å/min. The composition including 5% by weight colloidal silica exhibited a nitride removal rate of 780 Å/min and a polysilicon removal rate of less than 100 Å/min. Thus, the composition of the present invention exhibit significant selectivity for removal of silicon nitride versus polysilicon under the same polishing conditions.

CLAIMS

1. A method for polishing a silicon nitride-containing substrate, the method comprising abrading a surface of a silicon nitride-containing substrate with a polishing composition comprising:

- (a) 0.01 to 15% by weight of colloidal silica;
- (b) 10 to 100,000 parts per million (ppm) of at least one acidic component having a pKa in the range of 1 to 4.5; and
- (c) an aqueous carrier therefor;

wherein the polishing composition has a pH in the range of 0.5 pH units less than the pKa of the at least one acidic component to 1.5 pH units greater than the pKa. 1 pH unit greater than the pKa of the at least one acidic component.

2. A chemical-mechanical polishing (CMP) method for polishing a silicon nitride-containing substrate, the method comprising the steps of:

(a) contacting a surface of a silicon nitride-containing substrate with a polishing pad and an aqueous CMP composition, the CMP composition comprising 0.01 to 15% by weight of colloidal silica, 10 to 100,000 ppm of at least one acidic component having a pKa in the range of 1 to 4.5, and an aqueous carrier therefor, wherein the polishing composition has a pH in the range of 0.5 pH units less than the pKa of the at least one acidic component to 1.5 pH units greater than the pKa; and

(b) causing relative motion between the polishing pad and the substrate while maintaining a portion of the CMP composition in contact with the surface between the pad and the substrate for a time period sufficient to abrade silicon nitride from the surface.

3. The method of claim 2 wherein the substrate comprises silicon nitride and silicon oxide.

4. A chemical-mechanical polishing (CMP) method for selectively removing silicon nitride in the presence of silicon oxide in a substrate, the method comprising the steps of abrading a surface of a substrate comprising silicon nitride and silicon oxide with a polishing composition including 0.01 to 15% by weight of colloidal silica, 10 to 100,000 ppm of at least one acidic component having a pKa in the range of 1 to 4.5, and an aqueous carrier

therefor, wherein the polishing composition has a pH in the range of 0.5 pH units less than the pKa of the at least one acidic component to 1.5 pH units greater than the pKa.

5. A chemical-mechanical polishing (CMP) method for selectively removing silicon nitride in the presence of polysilicon in a substrate, the method comprising the steps of abrading a surface of a substrate comprising silicon nitride and polysilicon with a polishing composition including 0.01 to 15% by weight of colloidal silica, 10 to 100,000 ppm of at least one acidic component having a pKa in the range of 1 to 4.5, and an aqueous carrier therefor, wherein the polishing composition has a pH in the range of 0.5 pH units less than the pKa of the at least one acidic component to 1.5 pH units greater than the pKa.

6. The method of any one of claims 1, 2, 4, or 5 wherein the at least one acidic component is selected from the group consisting of an inorganic acid, a carboxylic acid, an organic phosphonic acid, an acidic heterocyclic compound, a salt thereof, and a combination of two or more of the foregoing.

7. The method of any one of claims 1, 2, 4, or 5 wherein the pH of the polishing composition is not more than 1 pH unit greater than the pKa of the at least one acidic component.

8. The method of any one of claims 1, 2, 4, or 5 wherein the pH of the polishing composition is less than 1 pH unit greater than the pKa of the at least one acidic component.

9. The method of any one of claims 1, 2, 4, or 5 wherein the colloidal silica is present in the composition in an amount in the range of 0.1 to 4% by weight.

10. The method of any one of claims 1, 2, 4, or 5 wherein the at least one acidic component is present in the polishing composition in an amount in the range of 500 to 2000 ppm.

11. A polishing composition comprising:

- (a) 0.01 to 15% by weight of colloidal silica;
- (b) 10 to 100,000 ppm of at least one acidic component having a pKa in the range of 1 to 4.5; and
- (c) an aqueous carrier therefor;

wherein the polishing composition has a pH in the range of 0.5 pH units less than the pKa of the at least one acidic component to 1.5 pH units greater than the pKa.

12. The composition of claim 11 wherein the colloidal silica is present in the composition in an amount in the range of 0.1 to 4% by weight.

13. The composition of claim 11 wherein the at least one acidic component is present in the polishing composition in an amount in the range of 500 to 2000 ppm.

14. The composition of claim 11 wherein the at least one acidic component is selected from the group consisting of an inorganic acid, a carboxylic acid, an organic phosphonic acid, an acidic heterocyclic compound, a salt thereof, and a combination of two or more of the foregoing.

15. The composition of claim 11 wherein the pH of the polishing composition is

(a) not more than 1 pH unit greater than the pKa of the at least one acidic component; or

(b) less than 1 pH unit greater than the pKa of the at least one acidic component.