



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C06B 43/00, 47/10, B60R 21/16	A1	(11) International Publication Number: WO 95/18779 (43) International Publication Date: 13 July 1995 (13.07.95)
(21) International Application Number: PCT/US95/00202 (22) International Filing Date: 4 January 1995 (04.01.95) (30) Priority Data: 08/179,150 10 January 1994 (10.01.94) US (71) Applicant: THIOKOL CORPORATION [US/US]; 2475 Washington Boulevard, Odgen, UT 84401 (US). (72) Inventors: DOLL, Dan, W.; 1204 East 2950 North, North Odgen, UT 84414 (US). WALLACE, Ingvar, A., II.; 918 Hillview Drive, Brigham City, UT 84302 (US). LUND, Gary, K.; 1723 Capitol Street, Odgen, UT 84401 (US). HINSHAW, Jerald, C.; 458 West 4125 North, Pleasant View, UT 84401 (US). BLAU, Reed, J.; P.O. Box 476, Richmond, UT 84333 (US). (74) Agents: MADSON, Craig et al.; Madson & Metcalf, Suite 950, 170 So. Main Street, Salt Lake City, UT 84101 (US).		(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MN, MW, MX, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SI, SK, TJ, TT, UA, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ). Published <i>With international search report.</i>
(54) Title: BOROHYDRIDE FUELS IN GAS GENERANT COMPOSITIONS (57) Abstract A sodium-azide-free gas-generating composition includes an oxidizable borohydride fuel and an oxidizing agent containing oxygen and a metal. The fuel and the oxidizing agent are selected such that water vapor is produced upon reaction between the borohydride fuel and the oxidizing agent. Suitable oxidizing agents contain a metal and oxygen and are selected from a metal oxide, a metal oxide hydrate, a metal oxide hydroxide, a metal hydrous oxide, a metal hydroxide, or mixtures thereof. The fuel and oxidizing agent are selected such that water vapor is the major gaseous combustion product.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

BOROHYDRIDE FUELS IN GAS GENERANT COMPOSITIONSField of the Invention

5 The present invention relates to gas generating compositions. More particularly, the present gas generant compositions comprise a borohydride fuel mixed with an appropriate oxidizing agent which, when combusted, generates a large quantity of water vapor.

10 Background of the Invention

 Gas generating chemical compositions are useful in a number of different contexts. One important use for such compositions is in the operation of "air bags." Air bags are gaining in acceptance to the point that many, if not most, new
15 automobiles are equipped with such devices. Indeed, many new automobiles are equipped with multiple air bags to protect the driver and passengers.

 In the context of automobile air bags, sufficient gas must be generated to inflate the device within a fraction of a
20 second. Between the time the car is impacted in an accident, and the time the driver would otherwise be thrust against the steering wheel, the air bag must fully inflate. As a consequence, nearly instantaneous gas generation is required.

 There are a number of additional important design criteria
25 that must be satisfied. Automobile manufacturers and others have set forth the required criteria which must be met in detailed specifications. Preparing gas generating compositions that meet these important design criteria is an extremely difficult task. These specifications require that the gas
30 generating composition produce gas at a required rate. The specifications also place strict limits on the generation of toxic or harmful gases or solids. Examples of restricted gases include carbon monoxide, carbon dioxide, NO_x, SO_x, and hydrogen sulfide. For example, carbon dioxide is limited to about 20 to
35 30 volume percent of the final gas volume produced.

 The gas must be generated at a sufficiently and reasonably low temperature so that an occupant of the car is not burned

upon impacting an inflated air bag. If the gas produced is overly hot, there is a possibility that the occupant of the motor vehicle may be burned upon impacting a deployed air bag. Accordingly, it is necessary that the combination of the gas generant and the construction of the air bag isolates automobile occupants from excessive heat. All of this is required while the gas generant maintains an adequate burn rate. In the industry, burn rates in excess of 0.5 inch per second (ips) at 1000 psi (pounds per square inch), and preferably in the range of from about 1.0 ips to about 1.2 ips at 1000 psi are generally desired. As used herein, 1 pound equals 453.593 grams and 1 inch equals 0.0254 meters.

Another related but important design criteria is that the gas generant composition produces a limited quantity of particulate materials. Particulate materials can interfere with the operation of the supplemental restraint system, present an inhalation hazard, irritate the skin and eyes, or constitute a hazardous solid waste that must be dealt with after the operation of the safety device. In the absence of an acceptable alternative, the production of irritating particulates is one of the undesirable, but tolerated aspects of the currently used sodium azide materials.

In addition to producing limited, if any, quantities of particulates, it is desired that at least the bulk of any such particulates be easily filterable. For instance, it is desirable that the composition produce a filterable slag to prevent the reaction products from escaping into the surrounding environment. This limits interference with the gas generating apparatus and the spreading of potentially harmful dust in the vicinity of the spent air bag which can cause lung, mucous membrane, and eye irritation to vehicle occupants and rescuers.

Both organic and inorganic materials have been proposed as possible gas generants. Such gas generant compositions include oxidizers and fuels which react at sufficiently high rates to produce large quantities of gas in a fraction of a second.

At present, sodium azide is the most widely used and currently accepted gas generating material. Sodium azide nominally meets industry specifications and guidelines. Nevertheless, sodium azide presents a number of persistent problems. Sodium azide is relatively toxic as a starting material, since its toxicity level as measured by oral rat LD₅₀ is in the range of 45 mg/kg. Workers who regularly handle sodium azide have experienced various health problems such as severe headaches, shortness of breath, and other symptoms.

In addition, no matter what auxiliary oxidizer is employed, the combustion products from a sodium azide gas generant include caustic reaction products such as sodium oxide or sodium hydroxide. Molybdenum disulfide or sulfur have been used as oxidizers for sodium azide. However, use of such oxidizers results in toxic products such as hydrogen sulfide gas and corrosive materials such as sodium oxide and sodium sulfide. Rescue workers and automobile occupants have complained about both the hydrogen sulfide gas and the corrosive powder produced by the operation of sodium azide-based gas generants.

Increasing problems are also anticipated in relation to disposal of unused gas-inflated supplemental restraint systems, e.g. automobile air bags, in demolished cars. The sodium azide remaining in such supplemental restraint systems can leach out of the demolished car to become a water pollutant or toxic waste. Indeed, some have expressed concern that sodium azide might form explosive heavy metal azides or hydrazoic acid when contacted with battery acids following disposal.

Sodium azide-based gas generants are most commonly used for air bag inflation, but with the significant disadvantages of such compositions many alternative gas generant compositions have been proposed to replace sodium azide. Most of the proposed sodium azide replacements, however, fail to deal adequately with all of the criteria set forth above.

One group of chemicals that has received attention as a possible replacement for sodium azide includes tetrazoles and triazoles. These materials are generally coupled with conven-

tional oxidizers such as KNO_3 and $\text{Sr}(\text{NO}_3)_2$. Some of the tetrazoles and triazoles that have been specifically mentioned include 5-aminotetrazole, 3-amino-1,2,4-triazole, 1,2,4-triazole, 1H-tetrazole, bitetrazole and several others. However, because of poor ballistic properties and high gas temperatures, none of these materials has yet gained general acceptance as a sodium azide replacement.

It will be appreciated, therefore, that there are a number of important criteria for selecting gas generating compositions for use in automobile supplemental restraint systems. For example, it is important to select starting materials that are not toxic. At the same time, the combustion products must not be toxic or harmful. In this regard, industry standards limit the allowable amounts of various gases produced by the operation of supplemental restraint systems.

It would, therefore, be a significant advance to provide compositions capable of generating large quantities of gas that would overcome the problems identified in the existing art. It would be a further advance to provide a gas generating composition which is based on substantially nontoxic starting materials and which produces substantially nontoxic reaction products. It would be another advance in the art to provide a gas generating composition which produces very limited amounts of toxic or irritating particulate debris and limited undesirable gaseous products. It would also be an advance to provide a gas generating composition which forms a readily filterable slag upon reaction.

Such compositions and methods for their use are disclosed and claimed herein.

Summary and Objects of the Invention

The present invention relates to a novel gas generating composition which is based on borohydride fuels and inorganic oxidizing agents which produce water vapor as the primary gaseous reaction product. The present composition comprises a mixture of finely divided borohydride fuel and an oxidizing agent containing oxygen and a metal comprising at least one

member from the group consisting of a metal oxide, a metal oxide hydrate, a metal oxide hydroxide, a metal hydrous oxide, a metal hydroxide, and mixtures thereof, provided that the borohydride fuel and the oxidizing agent are selected such that water vapor is produced when the composition is combusted.

The combustion reaction involves an oxidation-reduction reaction between the fuel and oxidizing agent. Under the exothermic conditions produced by the reaction, hydrogen from the borohydride reacts with oxygen from the oxidizing agent to produce water vapor and any water precursors in the oxidizing agent are also converted to water vapor. The water vapor is then available for use in deploying supplemental safety restraint devices such as inflating automobile air bags and the like.

It will be appreciated from the foregoing that the compositions of the present invention can generate large quantities of gas while avoiding some of the significant problems identified in the existing art. The gas generating compositions of the present invention are based on starting materials that produce substantially nontoxic reaction products.

These compositions produce only limited, if any, undesirable gaseous products. In addition, upon reaction, the gas generating compositions of the present invention produce only a limited amount, if any, of toxic or irritating debris while yielding a filterable slag.

These compositions combust rapidly and reproducibly to generate the substantially nontoxic gaseous reaction products described above.

Detailed Description of the Invention

The compositions of the present invention include a borohydride fuel, in a fuel-effective amount and an oxidizing agent containing a metal and oxygen, in an oxidizer-effective amount. The fuel and the oxidizing agent combination is selected with the proviso that water vapor is the major gaseous product produced upon reaction between the fuel and the

oxidizing agent and that essentially no, if any, hazardous gaseous reaction products are produced by that reaction. The fuel and the oxidizer are selected so that the combination of oxidizer and borohydride fuel exhibits reasonable thermal compatibility and chemical stability, that is, the combination of fuel and oxidizer does not begin reacting below about 225°F (107°C). The borohydride fuel, oxidizer, or the combustion products therefrom, are preferably not highly toxic.

In the operation of a supplemental restraint device or related safety device according to the present invention, other gases, if any, are produced in concentrations that are low relative to the desired gaseous combustion product, water vapor.

The oxidizable borohydride fuel is selected from known and novel borohydrides, including, for example, BH_4^- , B_3H_8^- , $\text{B}_8\text{H}_8^{2-}\text{B}_9\text{H}_{15}$, $\text{B}_{10}\text{H}_{14}$, $\text{B}_{10}\text{H}_{10}^{2-}$, $\text{B}_{11}\text{H}_{14}^-$, $\text{B}_{12}\text{H}_{12}^{2-}$, etc., and salts, complexes, and mixtures thereof. Currently preferred borohydride fuels include compounds based on BH_4^- , such as LiBH_4 , NaBH_4 , KBH_4 , RbBH_4 , CsBH_4 , $\text{Mg}(\text{BH}_4)_2$, $\text{Ca}(\text{BH}_4)_2$, $\text{Ba}(\text{BH}_4)_2$, $\text{Al}(\text{BH}_4)_3$, $\text{Zn}(\text{BH}_4)_3$, and transition metal complexes of BH_4^- . Other preferred borohydride fuels are based on $\text{B}_{12}\text{H}_{12}^{2-}$, such as $\text{Li}_2\text{B}_{12}\text{H}_{12}$, $\text{K}_2\text{B}_{12}\text{H}_{12}$, $\text{Cs}_2\text{B}_{12}\text{H}_{12}$, and $[(\text{CH}_3)_4\text{N}]_2\text{B}_{12}\text{H}_{12}$.

Both the oxidizable borohydride fuel and the oxidizer are incorporated into the composition in the form of a finely divided powder. Particle sizes typically range from about 0.001 μ to about 400 μ , although the particle sizes preferably range from about 0.1 μ to about 50 μ . The composition is insertable into a gas generating device, such as a conventional supplemental safety restraint system, in the form of pellets or tablets. Alternatively, the composition is insertable in such devices in the form of a multi-perforated, high surface area grain or other solid form which allows rapid and reproducible generation of gas upon ignition.

An oxidizing agent containing a metal and oxygen is paired with the borohydride fuel. In the present context, an oxidizing agent used herein has the following characteristics:

(a) It is a compound or solid state phase containing at least one type of metal and oxygen.

(b) One or more of the metals contained therein can act as an oxidizing agent for the borohydride fuel found in the gas generant formulation.

Given the foregoing, the class of suitable inorganic oxidizers possessing the desired traits includes a metal oxide, a metal oxide hydrate, a metal oxide hydroxide, a metal hydrous oxide, a metal hydroxide, or mixtures thereof wherein the metal species therein can be at least one species selected from elements from among Groups 5, 6, 7, 8, 9, 10, 11, 12, 14 and 15 as listed in the Periodic Table of the Elements according to the IUPAC format (CRC Handbook of Chemistry and Physics, (72nd Ed. 1991)). Examples of metal oxides include, among others, CuO, Co₂O₃, Co₃O₄, Bi₂O₃, Fe₂O₃, and CoFe₂O₄. Examples of metal hydroxides include, among others, Fe(OH)₃, Co(OH)₃, Co(OH)₂, Ni(OH)₂, Cu(OH)₂, and Zn(OH)₂. Examples of metal oxide hydrates and metal hydrous oxides include, among others, Fe₂O₃·xH₂O, SnO₂·xH₂O, and MoO₃·H₂O. Examples of metal oxide hydroxides include, among others, MnO(OH), MnO(OH)₂, FeO(OH), and MnO(OH)₃. In certain instances it will also be desirable to use mixtures of such oxidizing agents in order to enhance ballistic properties or maximize filterability of the slag formed from combustion of the composition. A preferred oxidizing agent is CuO.

In some cases, supplemental oxidizers such as alkali, alkaline earth, or ammonium perchlorates, chlorates, and peroxides in amounts up to about 40% by weight may be combined with the inorganic oxidizer to completely oxidize the fuel or enhance the burn rate.


The gas generant compositions of the present invention comprise a fuel-effective amount of borohydride fuel and an oxidizer-effective amount of at least one oxidizing agent. The present composition, in general, contains about 5 weight percent to about 40 weight percent borohydride fuel and from about 60 weight percent to about 95 weight percent oxidizing agent, and preferably from about 10 weight percent to about

30 weight percent fuel and from about 65 weight percent to about 90 weight percent oxidizing agent. These weight percentages are such that at least one oxidizing agent is present in an amount from about 0.5 to about 3 times the stoichiometric amount necessary to completely oxidize the borohydride fuel present.

Small quantities of other additives may also be included within the compositions if desired. Such additives are well known in the explosive, propellant, and gas generant arts. Such materials are conventionally added in order to modify the characteristics of the gas generating composition. Such materials include ballistic or burn rate modifiers, ignition aids, coolants, release agents or dry lubricants, binders for granulation or pellet crush strength, slag enhancers, anti-caking agents, etc. An additive often serves multiple functions. The additives may also produce gaseous reaction products to aid in the overall gas generation of the gas generant composition.

Ignition aids/burn rate modifiers include metal oxides, nitrates and other compounds such as, for instance, Fe_2O_3 , $\text{K}_2\text{B}_{12}\text{H}_{12} \cdot \text{H}_2\text{O}$, $\text{BiO}(\text{NO}_3)$, Co_2O_3 , CoFe_2O_4 , CuMoO_4 , Bi_2MoO_6 , MnO_2 , $\text{Mg}(\text{NO}_3)_2$, $\text{Fe}(\text{NO}_3)_3$, $\text{Co}(\text{NO}_3)_2$, and NH_4NO_3 . Coolants include magnesium hydroxide, cupric oxalate, boric acid, aluminum hydroxide, and silicotungstic acid. Coolants such as aluminum hydroxide and silicotungstic acid can also function as slag enhancers. Small amounts of polymeric binders, such as polyethylene glycol or polypropylene carbonate can, if desired, be added for mechanical properties reasons or to provide enhanced crush strength. Examples of dry lubricants include MoS_2 , graphite, graphitic-boron nitride, calcium stearate and powdered polyethylene glycol (Avg. MW 8000). The solid combustion products of most of the additives mentioned above will also enhance the filterability of the slag produced upon combustion of a gas generant formulation.

Illustrative examples of reactions involving compositions within the scope of the present invention are set forth in Table 1.

Table 1

5

Computer modeling was performed for gas generant systems based on the reaction of Bi_2O_3 oxidizer, KBH_4 or NaBH_4 fuel, and KClO_4 supplemental oxidizer. The results are set forth below in Table 2.

10

Table 2

<u>Ingredient</u>	<u>Weight Percent</u>								
Bi_2O_3	90	92	94	80	70	60	60	70	70
NaBH_4	10	8	6	10	10	10	--	--	--
15 KClO_4	--	--	--	10	20	30	30	20	15
KBH_4	--	--	--	--	--	--	10	10	15
T(°K)	1828	1819	1805	2026	2197	2147	1768	1773	1984
TP	0.77	0.67	0.55	0.66	0.58	0.62	0.64	0.59	0.58

20 Where T is the flame temperature and TP is the theoretical performance relative to a typical sodium azide based gas generant. Theoretical performance (gas volume and quantity) for a composition according to the present invention is comparable to those achieved by a conventional sodium azide-based gas generant composition. The theoretical performance for a typical sodium azide-based gas generant (68 weight percent NaN_3 ; 30 weight percent of MoS_2 ; 2 weight percent of S) is arbitrarily set equal to 1.0 and is about 0.85 g gas/cc NaN_3 generant.

30 Computer modeling was performed for gas generant systems based on the reaction of $\text{Cu}(\text{OH})_2$ oxidizer, KBH_4 fuel, and KClO_4 supplemental oxidizer. The results are set forth below in Table 3.

Table 3

<u>Ingredient</u>		<u>Weight Percent</u>											
5	Cu(OH) ₂	90	85	80	80	75	70	70	65	60	60	55	50
	KBH ₄	10	15	20	10	15	20	10	15	20	10	15	20
	KClO ₄	--	--	--	10	10	10	20	20	20	30	30	30
	T(°K)	1035	1227	1305	1389	1534	1549	1504	1648	1664	1540	1814	2394
	TP	1.06	1.01	1.01	0.89	0.92	0.93	0.86	0.84	0.88	0.82	0.78	0.69

10 Computer modeling was performed for gas generant systems based on the reaction of CuO oxidizer, KBH₄ fuel, and KClO₄ supplemental oxidizer. The results are set forth below in Table 4.

15

Table 4

	<u>Ingredient Weight Percent</u>			<u>Flame Temp. (°K)</u>	<u>Theoretical Performance</u>
	<u>CuO</u>	<u>KBH₄</u>	<u>KClO₄</u>		
20	90	5	5	1381	0.23
	85	10	5	1555	0.39
	80	15	5	1710	0.55
	75	20	5	1680	0.65
	85	5	10	1512	0.23
25	80	10	10	1613	0.40
	75	15	20	1766	0.54
	70	20	10	1740	0.64
	80	5	15	1560	0.26
	75	10	15	1618	0.45
30	70	15	15	1873	0.52
	65	20	15	1899	0.63
	75	5	20	1571	0.32
	70	10	20	1622	0.49
	65	15	20	1989	0.50
35	60	20	20	2073	0.60

The theoretical flame temperatures of the reaction between the fuel and the oxidizing agent are in the range of from about

1000°K to about 2200°K, with the more preferred range being from about 1500°K to about 1800°K. This is a manageable range for application in the field of automobile air bags and can be adjusted to form non-liquid (e.g., solid) easily filterable slag.

With the reaction characteristics, the compositions and methods of the present invention can produce a sufficient volume and quantity of gas to inflate a supplemental safety restraint device, such as an automobile air bag, at a manageable temperature. The reaction of the compositions within the scope of the invention produce significant quantities of water vapor in a very short period of time. At the same time, the reaction substantially avoids the production of unwanted gases and particulate materials, although minor amounts of other gases may be produced. The igniter formulation may also produce small amounts of other gases.

The present gas generant compositions can be formulated to produce an integral slag to limit substantially the particulate material produced. This minimizes the production of solid particulate debris outside the combustion chamber. Thus, it is possible to substantially avoid the production of a caustic powder, such as sodium oxide/hydroxide or sodium sulfide, commonly produced by conventional sodium azide formulations.

The compositions of the present invention are ignited with conventional igniters. Igniters using materials such as boron/potassium nitrate are usable with the compositions of the present invention. Thus, it is possible to substitute the compositions of the present invention in state-of-the-art gas generant applications.

The gas generating compositions of the present invention are readily adapted for use with conventional hybrid air bag inflator technology. Hybrid inflator technology is based on heating a stored inert gas (argon or helium) to a desired temperature by burning a small amount of propellant. Hybrid inflators do not require cooling filters used with pyrotechnic inflators to cool combustion gases, because hybrid inflators are able to provide a lower temperature gas. The gas discharge

temperature can be selectively changed by adjusting the ratio of inert gas weight to propellant weight. The higher the gas weight to propellant weight ratio, the cooler the gas discharge temperature.

5 A hybrid gas generating system comprises a pressure tank having a rupturable opening, a pre-determined amount of inert gas disposed within that pressure tank; a gas generating device for producing hot combustion gases and having means for rupturing the rupturable opening; and means for igniting the
10 gas generating composition. The tank has a rupturable opening which can be broken by a piston when the gas generating device is ignited. The gas generating device is configured and positioned relative to the pressure tank so that hot combustion gases are mixed with and heat the inert gas. Suitable inert
15 gases include, among others, argon, and helium and mixtures thereof. The mixed and heated gases exit the pressure tank through the opening and ultimately exit the hybrid inflator and deploy an inflatable bag or balloon, such as an automobile air bag. The gas generating device contains a gas generating
20 composition according to the present invention which comprises an oxidizable borohydride fuel and an oxidizing agent selected from basic metal carbonates and basic metal nitrates. The oxidizable borohydride fuel and oxidizing agent being selected so that substantially nontoxic gases are produced such as
25 mixtures of water vapor and either carbon dioxide or nitrogen.

30 The high heat capacity of water vapor produced is an added advantage for its use as a heating gas in a hybrid gas generating system. Thus, less water vapor, and consequently, less generant is needed to heat a given quantity of inert gas to a given temperature.

35 Hybrid gas generating devices for supplemental safety restraint application are described in Frantom, Hybrid Airbag Inflator Technology, Airbag Int'l Symposium on Sophisticated Car Occupant Safety Systems, (Weinbrenner-Saal, Germany, Nov. 2-3, 1992).

 An automobile air bag system can comprise a collapsed, inflatable air bag, a gas generating device connected to the

air bag for inflating the air bag, and means for igniting the gas generating composition. The gas generating device contains a gas generating composition comprising an oxidizable borohydride fuel and an oxidizing agent, wherein said oxidizing agent comprises at least one member selected from the group consisting of a metal oxide, a metal oxide hydrate, a metal oxide hydroxide, a metal hydrous oxide, a metal hydroxide, or mixtures thereof, and wherein water vapor is the major gaseous reaction product generated by reaction between said oxidizable borohydride fuel and said oxidizing agent.

EXAMPLES

The present invention is further described in the following nonlimiting examples. Unless otherwise stated, the compositions are expressed in weight percent.

Example 1

A gas generant composed of 85.5% CuO, 10.0 % NaBH₄, and 5.0% KClO₄ was mixed in hexane at low shear. The hexane was removed under vacuum. The powder was pressed into 0.25 inch by 0.5 inch diameter pellets which exhibit a burning rate of 0.84 ips at 1000 psi. Based on computer modeling, the theoretical performance of this composition was 0.60 with a combustion temperature of 1915°K. The major combustion products were 43.5 mole % liquid Cu, 30.2 mole % H₂O, 15.2 mole % borates, 8.9 mole % liquid Cu₂O, and 1.54 mole % KCl and NaCl.

Example 2

A gas generant composed of 70.0% CuO, 10.0 % NaBH₄, and 20.0% KClO₄ was mixed in hexane at low shear. The hexane was removed under vacuum. The powder was pressed into 0.25 inch by 0.5 inch diameter pellets which exhibit a burning rate of 1.21 ips at 1000 psi. Based on computer modeling, the theoretical performance of this composition was 0.52 with a combustion temperature of 2015°K. The major combustion products were 37.1

mole % H_2O , 28.5 mole % Cu_2O , 18.7 mole % borates, 5.6 mole % liquid Cu, and 6.0 mole % KCl and NaCl.

Example 3

5 A gas generant composed of 75% CuO, 15.0 % NaBH_4 , and 10.0% KClO_4 was mixed in hexane at low shear. The hexane was removed under vacuum. The powder was pressed into 0.25 inch by 0.5 inch diameter pellets which exhibit a burning rate of 1.27 ips at 1000 psi. Based on computer modeling, the theoretical performance of this composition was 0.54 with a combustion temperature of 1766°K. The major combustion products were 41.2 mole % liquid Cu, 32.0 mole % H_2O , 14.7 mole % borates, 7 mole % liquid Cu_2O , and 4.0 mole % KCl.

Example 4

15 A gas generant composed of 55.0% $\text{Cu}(\text{OH})_2$, 15.0% KBH_4 , and 30% KClO_4 was mixed in hexane under low shear. The hexane was removed under vacuum at ambient temperature. The powdered generant was pressed into 0.5 inch pellets which exhibit a burning rate of 0.48 ips at 1000 psi. Based on computer modeling, the theoretical performance of this composition was 0.78 with a combustion temperature of 1814°K. The major combustion products were 58.5 mole % H_2O , 14.9 mole % liquid Cu_2O , 14.1 mole % KBO_2 , 8.83 mole % liquid KCl, and 1.63 mole % KCl vapor.

Example 5

30 A gas generant composed of 65.0% $\text{Cu}(\text{OH})_2$, 15.0% KBH_4 , and 20% KClO_4 was mixed in hexane under low shear. The hexane was removed under vacuum at ambient temperature. The powdered generant was pressed into 0.5 inch pellets which exhibit a burning rate of 0.55 ips at 1000 psi. Based on computer modeling, the theoretical performance of this composition was 0.85 with a combustion temperature of 1648°K. The major combustion products were 56.3 mole % H_2O , 18.9 mole % liquid

Cu, 9.0 mole % KBO_2 , 6.2 mole % liquid Cu_2O , 1.0 mole % liquid $\text{K}_2\text{B}_4\text{O}_7$, and 6.0 mole % KCl .

Example 6

5 A gas generant composed of 64% $\text{Cu}(\text{OH})_2$, 1% Fe_2O_3 , 15% KBH_4 , and 20% KClO_4 was mixed in hexane at low shear. The hexane was removed under vacuum at ambient temperature. The powdered generant was pressed into 0.5 inch pellets which exhibit a burning rate of 0.28 ips at 1000 psi. Based on computer
10 modeling, the theoretical performance of this composition was 0.84 with a combustion temperature of 1649°K. The major combustion products were 56 mole % H_2O , 19.2 mole % liquid Cu, 9.2 mole % KBO_2 , 5.8 mole % liquid Cu_2O , 1.0 mole % liquid $\text{K}_2\text{B}_4\text{O}_7$, 1.4% KOH , and 6.0 mole % liquid KCl .

15

Example 7

A gas generant composed of 63.5% $\text{Cu}(\text{OH})_2$, 15.0% KBH_4 , 1.5% $\text{Li}_2\text{B}_{12}\text{H}_{12}$, and 20% KClO_4 was mixed in hexane at low shear. The hexane was removed under vacuum at ambient temperature. The
20 powdered generant was pressed into 0.5 inch pellets which exhibit a burning rate of 0.72 ips at 1000 psi. Based on computer modeling, the theoretical performance of this composition was 0.86 with a combustion temperature of 1876°K. The major combustion products were 48.7 mole % H_2O , 28.1 mole %
25 liquid Cu, 8.9 mole % KBO_2 , 5.4 mole % H_2 , 1.7 mole % liquid $\text{K}_2\text{B}_4\text{O}_7$, 2.9 mole % liquid KCl , and 2.0 mole % KCl vapor.

Example 8

A gas generant composed of 63.5% $\text{Cu}(\text{OH})_2$, 15.0% KBH_4 , 1.5%
30 $((\text{CH}_3)_4\text{N})_2\text{B}_{12}\text{H}_{12}$, and 20% KClO_4 was mixed in hexane at low shear. The hexane was removed under vacuum at ambient temperature. The powdered generant was pressed into 0.5 inch pellets which exhibit a burning rate of 0.53 ips at 1000 psi. Based on
computer modeling, the theoretical performance of this composition was 0.90 with a combustion temperature of 1842°K. The
35 major combustion products were 49.4 mole % H_2O , 27.7 mole %

liquid Cu, 8.6 mole % KBO_2 , 5.4 mole % H_2 , 1.6 mole % liquid $\text{K}_2\text{B}_4\text{O}_7$, 3.5 mole % liquid KCl, and 1.7 mole % KCl vapor.

Example 9

5 A gas generant composed of 70% Bi_2O_3 , 10% NaBH_4 , and 20% KClO_4 was mixed in hexane at low shear. The hexane was removed under vacuum at ambient temperature. The powdered generant was pressed into 0.5 inch pellets which exhibited a burning rate of 2.3 ips at 1000 psi. Based on computer modeling, the theoretical performance of this composition was 0.58 with a combustion temperature of 2197°K. The major combustion products were 39.8 mole % H_2O , 20.1 mole % liquid Bi, 7.0 mole % KBO_2 , 5.7 mole % NaCl, 4.4 mole % Bi vapor, 3.9 mole % KCl, and 2.3 mole % H_2 .

Example 10

15 Theoretical calculations were conducted on the reaction of KBH_4 , Bi_2O_3 , and KClO_4 , as listed in Table 1, to evaluate its use in a hybrid gas generator. If this formulation is allowed to undergo combustion in the presence of 1.5 times its weight argon gas, the flame temperature decreases from 2123°K to 1440°K, assuming 100% efficient heat transfer. The output gases consist of 87% by volume argon and 10% by volume water vapor.

25 From the foregoing, it will be appreciated that the present invention provides compositions capable of generating large quantities of gas which are based on substantially nontoxic starting materials and which produce substantially nontoxic reaction products. The gas generant compositions of the present invention also produce very limited amounts of toxic or irritating particulate debris and limited undesirable gaseous products. In addition, the present invention provides gas generating compositions which form a readily filterable solid slag upon reaction.

35 The invention may be embodied in other specific forms without departing from its essential characteristics. The

described embodiments are to be considered in all respects only as illustrative and not restrictive. The scope of the invention is, therefore, indicated by the appended claims rather than by the foregoing description.

5 What is claimed is:

1. A solid gas-generating composition comprising an oxidizable borohydride fuel and an oxidizing agent, wherein said oxidizing agent comprises at least one member selected from the group consisting of a metal oxide, a metal oxide hydrate, a metal oxide hydroxide, a metal hydrous oxide, a metal hydroxide, or mixtures thereof, and wherein water vapor is the major gaseous reaction product generated by said solid-gas-generating composition, wherein said oxidizing agent is present in an amount from about 0.5 to about 3 times the stoichiometric amount of oxidizing agent necessary to completely oxidize the borohydride fuel present.

2. A solid gas-generating composition according to claim 1, comprising from about 5 weight percent to about 40 weight percent borohydride fuel and from about 95 weight percent to about 60 weight percent oxidizing agent.

3. A solid gas-generating composition according to claim 1, wherein said oxidizing agent is present in an amount from about 0.5 to about 3 times the stoichiometric amount of oxidizing agent necessary to completely oxidize the borohydride fuel present.

4. A solid gas-generating composition according to claim 1, wherein the oxidizable borohydride fuel is selected from salts or complexes of BH_4^- , B_3H_8^- , $\text{B}_8\text{H}_8^{2-}$, B_9H_{15} , $\text{B}_{10}\text{H}_{14}$, $\text{B}_{10}\text{H}_{10}^{2-}$, $\text{B}_{11}\text{H}_{14}^-$, $\text{B}_{12}\text{H}_{12}^{2-}$, and mixtures thereof.

5. A solid gas-generating composition according to claim 1, wherein the oxidizable borohydride fuel is based on BH_4^- .

6. A solid gas-generating composition according to claim 5, wherein the oxidizable borohydride fuel is selected from LiBH_4 , NaBH_4 , KBH_4 , RbBH_4 , CsBH_4 , $\text{Mg}(\text{BH}_4)_2$, $\text{Ca}(\text{BH}_4)_2$, $\text{Ba}(\text{BH}_4)_2$, $\text{Al}(\text{BH}_4)_3$, $\text{Zn}(\text{BH}_4)_3$, transition metal complexes of BH_4^- , and mixtures thereof.

7. A solid gas-generating composition according to claim 1, wherein the oxidizable borohydride fuel and the oxidizer are in the form of a finely divided powder.

8. A solid gas-generating composition according to claim 7, wherein the particle size range of the powder is from about $0.001\ \mu$ to about $400\ \mu$.

9. A solid gas-generating composition according to claim 1, wherein the oxidizing agent is a metal oxide selected from CuO , Co_2O_3 , Co_3O_4 , Bi_2O_3 , Fe_2O_3 , CoFe_2O_4 , and mixtures thereof.

5 10. A solid gas-generating composition according to claim 1, wherein the oxidizing agent is a metal hydroxide selected from $\text{Fe}(\text{OH})_3$, $\text{Co}(\text{OH})_3$, $\text{Co}(\text{OH})_2$, $\text{Ni}(\text{OH})_2$, $\text{Cu}(\text{OH})_2$, $\text{Zn}(\text{OH})_2$, and mixtures thereof.

10 11. A solid gas-generating composition according to claim 1, wherein the oxidizing agent is a hydrated metal oxide selected from $\text{Fe}_2\text{O}_3 \cdot x\text{H}_2\text{O}$, $\text{SnO}_2 \cdot x\text{H}_2\text{O}$, $\text{MoO}_3 \cdot \text{H}_2\text{O}$, and mixtures thereof.

15 12. A solid gas-generating composition according to claim 1, wherein the oxidizing agent is a metal oxide hydroxide selected from $\text{MnO}(\text{OH})$, $\text{MnO}(\text{OH})_2$, $\text{FeO}(\text{OH})$, $\text{MnO}(\text{OH})_3$, and mixtures thereof.

13. An automobile air bag system comprising:

a collapsed, inflatable air bag;

20 a gas-generating device connected to the air bag for inflating said air bag, said gas-generating device containing a gas-generating composition comprising an oxidizable borohydride fuel and an oxidizing agent, wherein said oxidizing agent comprises at least one member selected from the group consisting of a metal oxide, a metal oxide hydrate, a metal oxide hydroxide, a metal hydrous oxide, a metal hydroxide, or
25 mixtures thereof, and wherein water vapor is the major gaseous reaction product generated by said solid gas-generating composition, wherein said oxidizing agent is present in an amount from about 0.5 to about 3 times the stoichiometric amount of oxidizing agent necessary to completely oxidize the
30 borohydride fuel present; and

means for igniting said gas-generating composition.

14. An automobile air bag system according to claim 13, wherein said gas-generating composition comprises from about 5 weight percent to about 40 weight percent oxidizable
35 borohydride fuel and from about 95 weight percent to about 60 weight percent oxidizing agent.

15. An automobile air bag system according to claim 13, wherein the oxidizing agent of said gas-generating composition is present in an amount from about 0.5 to about 3 times the stoichiometric amount of oxidizing agent necessary to
5 completely oxidize the borohydride fuel present.

16. An automobile air bag system according to claim 13, wherein the oxidizable borohydride fuel is selected from salts or complexes of BH_4^- , B_3H_8^- , $\text{B}_8\text{H}_8^{2-}$, B_9H_{15} , $\text{B}_{10}\text{H}_{14}$, $\text{B}_{10}\text{H}_{10}^{2-}$, $\text{B}_{11}\text{H}_{14}^-$, $\text{B}_{12}\text{H}_{12}^{2-}$, and mixtures thereof.

10 17. An automobile air bag system according to claim 13, wherein the oxidizable borohydride fuel is based on BH_4^- .

18. An automobile air bag system according to claim 17, wherein the oxidizable borohydride fuel is selected from LiBH_4 , NaBH_4 , KBH_4 , RbBH_4 , CsBH_4 , $\text{Mg}(\text{BH}_4)_2$, $\text{Ca}(\text{BH}_4)_2$, $\text{Ba}(\text{BH}_4)_2$, $\text{Al}(\text{BH}_4)_3$,
15 $\text{Zn}(\text{BH}_4)_3$, transition metal complexes of BH_4^- , and mixtures thereof.

19. An automobile air bag system according to claim 13, wherein the oxidizing agent is a metal oxide selected from CuO , Co_2O_3 , Co_3O_4 , Bi_2O_3 , Fe_2O_3 , CoFe_2O_4 , and mixtures thereof.

20 20. An automobile air bag system according to claim 13, wherein the oxidizing agent is a metal hydroxide selected from $\text{Fe}(\text{OH})_3$, $\text{Co}(\text{OH})_3$, $\text{Co}(\text{OH})_2$, $\text{Ni}(\text{OH})_2$, $\text{Cu}(\text{OH})_2$, $\text{Zn}(\text{OH})_2$, and mixtures thereof.

21. An automobile air bag system according to claim 13, wherein the oxidizing agent is a hydrated metal oxide selected from $\text{Fe}_2\text{O}_3 \cdot x\text{H}_2\text{O}$, $\text{SnO}_2 \cdot x\text{H}_2\text{O}$, $\text{MoO}_3 \cdot \text{H}_2\text{O}$, and mixtures thereof.
25

22. An automobile air bag system according to claim 13, wherein the oxidizing agent is a metal oxide hydroxide selected from $\text{MnO}(\text{OH})$, $\text{MnO}(\text{OH})_2$, $\text{FeO}(\text{OH})$, $\text{MnO}(\text{OH})_3$, and mixtures thereof.

23. An automobile air bag system having a hybrid gas-generating system comprising:

a collapsed, inflatable air bag;

5 a pressure tank having a rupturable opening, said pressure tank containing an inert gas;

a gas-generating device for producing hot combustion gases and capable of rupturing the rupturable opening, said gas-generating device being configured in relation to the pressure tank such that hot combustion gases are mixed with and heat the
10 inert gas and wherein said gas-generating device and the pressure tank are connected to the inflatable air bag such that the combustion gases and inert gas are capable of inflating the air bag, said gas-generating device containing a gas-generating composition comprising an oxidizable borohydride fuel and an
15 oxidizing agent, wherein said oxidizing agent comprises at least one member selected from the group consisting of a metal oxide, a metal oxide hydrate, a metal oxide hydroxide, a metal hydrous oxide, a metal hydroxide, or mixtures thereof, and wherein water vapor is the major gaseous reaction product
20 generated by said solid gas-generating composition, wherein said oxidizing agent is present in an amount from about 0.5 to about 3 times the stoichiometric amount of oxidizing agent necessary to completely oxidize the borohydride fuel present; and

25 means for igniting the gas-generating composition.

24. An automobile air bag system according to claim 23, wherein said inert gas is argon or helium.

25. An automobile air bag system according to claim 23, wherein said gas-generating composition comprises from about 5%
30 to about 40% borohydride fuel and from about 95% to about 60% oxidizing agent.

26. An automobile air bag system according to claim 23, wherein the oxidizing agent of said gas-generating composition is present in an amount from about 0.5 to about 3 times the
35 stoichiometric amount of oxidizing agent necessary to completely oxidize the borohydride fuel present.

27. An automobile air bag system according to claim 23, wherein the oxidizable borohydride fuel is selected from salts or complexes of BH_4^- , B_3H_8^- , $\text{B}_8\text{H}_8^{2-}$, B_9H_{15} , $\text{B}_{10}\text{H}_{14}$, $\text{B}_{10}\text{H}_{10}^{2-}$, $\text{B}_{11}\text{H}_{14}^-$, $\text{B}_{12}\text{H}_{12}^{2-}$, and mixtures thereof.

5 28. An automobile air bag system according to claim 23, wherein the oxidizable borohydride fuel is based on BH_4^- .

29. An automobile air bag system according to claim 28, wherein the oxidizable borohydride fuel is selected from LiBH_4 , NaBH_4 , KBH_4 , RbBH_4 , CsBH_4 , $\text{Mg}(\text{BH}_4)_2$, $\text{Ca}(\text{BH}_4)_2$, $\text{Ba}(\text{BH}_4)_2$, $\text{Al}(\text{BH}_4)_3$,
10 $\text{Zn}(\text{BH}_4)_3$, transition metal complexes of BH_4^- , and mixtures thereof.

30. An automobile air bag system according to claim 23, wherein the oxidizing agent is a metal oxide selected from CuO , Co_2O_3 , Co_3O_4 , Bi_2O_3 , Fe_2O_3 , CoFe_2O_4 , and mixtures thereof.

15 31. An automobile air bag system according to claim 23, wherein the oxidizing agent is a metal hydroxide selected from $\text{Fe}(\text{OH})_3$, $\text{Co}(\text{OH})_3$, $\text{Co}(\text{OH})_2$, $\text{Ni}(\text{OH})_2$, $\text{Cu}(\text{OH})_2$, $\text{Zn}(\text{OH})_2$, and mixtures thereof.

20 32. An automobile air bag system according to claim 23, wherein the oxidizing agent is a hydrated metal oxide selected from $\text{Fe}_2\text{O}_3 \cdot x\text{H}_2\text{O}$, $\text{SnO}_2 \cdot x\text{H}_2\text{O}$, $\text{MoO}_3 \cdot \text{H}_2\text{O}$, and mixtures thereof.

25 33. An automobile air bag system according to claim 23, wherein the oxidizing agent is a metal oxide hydroxide selected from $\text{MnO}(\text{OH})_2$, $\text{MnO}(\text{OH})_2$, $\text{FeO}(\text{OH})$, $\text{MnO}(\text{OH})_3$, and mixtures thereof.

34. A vehicle containing a supplemental restraint system having an air bag system comprising:

a collapsed, inflatable air bag,

5 a gas-generating device connected to said air bag for inflating said air bag, said gas-generating device containing a gas-generating composition comprising an oxidizable borohydride fuel and an oxidizing agent, wherein said oxidizing agent comprises at least one member selected from the group consisting of a metal oxide, a metal oxide hydrate, a metal
10 oxide hydroxide, a metal hydrous oxide, a metal hydroxide, or mixtures thereof, and wherein water vapor is the major gaseous reaction product generated by said solid gas-generating composition, wherein said oxidizing agent is present in an amount from about 0.5 to about 3 times the stoichiometric
15 amount of oxidizing agent necessary to completely oxidize the borohydride fuel present; and

means for igniting said gas-generating composition.

35. A vehicle as defined in claim 34, further comprising a pressure tank having a rupturable opening, said pressure tank
20 containing an inert gas; wherein the gas-generating device produces hot combustion gases capable of rupturing the rupturable opening, and wherein the gas-generating device is configured in relation to the pressure tank such that hot combustion gases are mixed with and heat the inert gas and
25 wherein the gas-generating device and the pressure tank are connected to the inflatable air bag such that the mixture of combustion gases and inert gas are capable of inflating the air bag.

INTERNATIONAL SEARCH REPORT

Int ional application No.
PCT/US95/00202

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) : C06B 43/00, 47/10; B60R 21/16

US CL : 149/22; 280/728R

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 149/22; 280/728R

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

APS TEXT SEARCH: AIR BARS, BOROHYDRIDE

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US, A, 3,450,638 (EDWARDS) 17 JUNE 1969.	1-35
A	US, A, 3,484,315 (WAGNER ET AL.) 16 DECEMBER 1969.	1-35
A	US, A, 3,487,084 (EHRlich ET AL.) 30 DECEMBER 1969.	1-35
A	US, A, 3,797,238 (IWANCIOW ET AL.) 19 MARCH 1974.	1-35
A	US, A, 4,468,263 (ARTZ ET AL.) 28 AUGUST 1984.	1-35
A	US, A, 4,673,528 (ARTZ ET AL.) 16 JUNE 1987.	1-35
A	US, A, 5,031,932 (FRANTOM ET AL.) 16 JULY 1991.	1-35

☒ Further documents are listed in the continuation of Box C.
 ☐ See patent family annex.

* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be part of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"E" earlier document published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&" document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means	
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

04 FEBRUARY 1995

Date of mailing of the international search report

05 APR 1995

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

DONALD P. WALSH

Telephone No. 703-308-0513

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US95/00202

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US, A, 5,056,435 (JONES ET AL.) 15 OCTOBER 1991.	1-35
A	US, A, 5,094,475 (OLSSON ET AL.) 10 MARCH 1992.	1-35
A	US, A, 5,100,172 (VANVOORHIES ET AL.) 31 MARCH 1992.	1-35