



(86) **Date de dépôt PCT/PCT Filing Date:** 2009/01/30
(87) **Date publication PCT/PCT Publication Date:** 2009/08/06
(45) **Date de délivrance/Issue Date:** 2016/07/12
(85) **Entrée phase nationale/National Entry:** 2010/07/30
(86) **N° demande PCT/PCT Application No.:** US 2009/000615
(87) **N° publication PCT/PCT Publication No.:** 2009/097142
(30) **Priorités/Priorities:** 2008/01/31 (US61/025,065);
2008/12/16 (US61/201,852)


(51) **Cl.Int./Int.Cl.** **C09D 7/12** (2006.01),
C09D 201/00 (2006.01), **C09D 5/02** (2006.01)

(72) **Inventeurs/Inventors:**
ZHOU, LICHANG, US;
PAKENHAM, DEREK, US;
RUIZ, JOSE, US;
CHEN, PU, SG;
AYMES, CHARLES, US;
MILLER, KERI MARIE, US;
KOLTISKO, BERNARD, US

(73) **Propriétaire/Owner:**
RHODIA OPERATIONS, FR

(74) **Agent:** GOWLING WLG (CANADA) LLP

(54) **Titre : AGENTS COALESCENTS A FAIBLE TENEUR EN COV**
(54) **Title: LOW VOC COALESCING AGENTS**



(57) **Abbrégé/Abstract:**

A coalescent composition for coating compositions such as paints, adhesives, and coatings comprising a blend of dibasic esters, specifically (i) esters of adipic, glutaric, and/or succinic diacids and/or (ii) esters of isomers of adipic acid have advantages, including efficiency and low VOC.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

CORRECTED VERSION

(19) World Intellectual Property Organization
International Bureau

PCT

(10) International Publication Number
WO 2009/097142 A9(51) International Patent Classification:
C08F 2/24 (2006.01) *C08L 69/00* (2006.01)(21) International Application Number:
PCT/US2009/000615(22) International Filing Date:
30 January 2009 (30.01.2009)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
61/025,065 31 January 2008 (31.01.2008) US
61/201,852 16 December 2008 (16.12.2008) US(71) Applicant (for all designated States except US): **RHO-**
DIA INC. [US/US]; 8 Cedar Brook Drive, CN 7500,
Cranbury, NJ 08512 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **ZHOU, Lichang**
[CN/US]; 8 Yorkshire Village Road, Lawrenceville, NJ
08648 (US). **PAKENHAM, Derek** [GB/US]; 3029 E.
State Street Ext., Hamilton, NJ 08619 (US). **RUIZ, Jose**[US/US]; 36 Groom Street, Burlington, NJ 08016 (US).
CHEN, Pu [SG/SG]; Block 51, #07-02 Hillview Avenue,
Hillington Green 669565 (SG). **AYMES, Charles**
[US/US]; 13 Marvin Road, Monmouth Junction, NJ
08852 (US). **MILLER, Keri, Marie** [US/US]; 1808 Kus-
er Road, Apt. 3, Hamilton, NJ 08690 (US). **KOLTISKO,**
Bernard [US/US]; 482 Kings Road, Yardley, PA 19067
(US).(74) Agent: **PACHO, Jericho, B.**; Rhodia Inc., 8 Cedar Brook
Drive, CN 7500, Cranbury, NJ 08512 (US).(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ,
CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ,
EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN,
HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR,
KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME,
MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO,
NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG,
SK, SL, SM, ST, SV, SY, TJ, TM, TN, TR, TT, TZ, UA,
UG, US, UZ, VC, VN, ZA, ZM, ZW.

[Continued on next page]

(54) Title: LOW VOC COALESCING AGENTS




Figure 8

(57) Abstract: A coalescent composition for coating compositions such as paints, adhesives, and coatings comprising a blend of dibasic esters, specifically (i) esters of adipic, glutaric, and/or succinic diacids and/or (ii) esters of isomers of adipic acid have advantages, including efficiency and low VOC.

WO 2009/097142 A9

WO 2009/097142 A9

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— *with international search report (Art. 21(3))*

(48) Date of publication of this corrected version:

8 October 2009

(15) Information about Correction:

see Notice of 8 October 2009

LOW VOC COALESCING AGENTS

FIELD OF THE INVENTION

[0002] This invention relates to the field of coalescing agents and, in particular, coalescing agents utilized in coating compositions, and related methods for use and preparation thereof.

BACKGROUND OF THE INVENTION

[0003] Coalescing agents are high boiling point solvents (that are slow to evaporate) used to reduce the minimum film formation temperature (MFFT) of paints, inks, other coating compositions and the like. In paint formulations in particular, coalescing agents act as *temporary* plasticizers to reduce the glass transition temperature (T_g) of the latex below that of the drying temperature to allow for good film formation.

[0004] Generally, coalescing agents function by softening the polymer particles in a latex, enabling the formation of a continuous film as the coating cures. It is desirable for the coalescing agent to have low water solubility, which increases its effectiveness, and have good hydrolytic stability.

[0005] A typical paint formulation contains between 0.1-10% coalescing agent, which is used to aid in the formation of a continuous film as the paint cures. This market has been historically dominated by Eastman's Texanol™ brand ester alcohol (2,2,4-trimethyl-1,3-pentanediol monoisobutyrate). However, as Texanol™ is not compliant with current volatile organic content (VOC) regulations, there is a need for improved coalescing agents or other systems to achieve coalescence in compliance with low VOC regulations. Generally, "low VOC" coalescing agents is understood to mean about 50% less VOC content as

compared to regular coalescing agents, for example, Texanol[®], which contains 100% VOC content.

[0006] It is an object of the present invention to provide an improved and efficient, low VOC coalescent composition which meets present and future VOC regulations for paints and other coatings.


SUMMARY OF THE INVENTION

[0007] It is desirable to have a low VOC coalescent agent that has a lower evaporation rate (coalescents generally consist of slow evaporating solvents), that can efficiently reduce the Tg of the system, is dispersible in the latex, is compatible with all of the other paint components (pigment, surfactant, freeze-thaw stabilizer, thickeners), has low water solubility (to increase effectiveness), and has good hydrolytic stability. In one aspect, the present invention is a coalescent comprising a blend of esters of adipic, glutaric, and succinic diacids.

[0008] In one aspect, the present invention is a coalescent composition derived from one or more by-products in the production of polyamide, more specifically, polyamide 6,6. Generally, polyamide is a copolymer prepared by a condensation reaction formed by reacting a diamine and a dicarboxylic acid. More specifically, polyamide 6,6 is a copolymer prepared by a condensation reaction formed by reacting a diamine, typically hexamethylenediamine, with a dicarboxylic acid, typically adipic acid.

[0009] In one aspect, the present invention is a coalescent composition derived from one or more by-products in the reaction, synthesis and/or production of adipic acid utilized in the production of polyamide, the coalescent composition comprising a blend of esters of adipic diacids, glutaric diacids, and succinic diacids (herein referred to sometimes as "AGS" or the "AGS blend"). In one embodiment, the blend comprises adducts of alcohol and linear diacids, the adducts having the formula $R_1\text{-OOC-A-COO-R}_2$ wherein R_1 and/or R_2 comprise, individually, a $C_1\text{-C}_{12}$ alkyl, more typically a $C_4\text{-C}_8$ alkyl, and A comprises a mixture of $-(CH_2)_4-$, $-(CH_2)_3-$, and $-(CH_2)_2-$. In another embodiment, the blend comprises adducts of alcohol and linear diacids, the adducts having the formula $R_1\text{-OOC-A-COO-R}_2$ wherein R_1 and/or R_2 comprise, individually, a $C_1\text{-C}_{12}$ alkyl, more typically a $C_4\text{-C}_8$ alkyl, A is selected from the group consisting of $-(CH_2)_4-$, -

(CH₂)₃, and -(CH₂)₂-, and wherein A in the composition is a mixture of -(CH₂)₄-, -(CH₂)₃, and -(CH₂)₂-. R₁ and R₂ can individually comprise a hydrocarbon group originating from fusel oil. In one embodiment, R₁ and R₂ individually can comprise a hydrocarbon group having 3 to 8 carbon atoms, and wherein R₁ and R₂ do not individually comprise an iso-butyl group. In one embodiment, R₁ and R₂ individually can comprise a hydrocarbon group having 5 to 8 carbon atoms, and wherein R₁ and R₂ do not individually comprise an iso-butyl group. In one embodiment, R₁ and R₂ can also individually comprise a glycol ether group. Typically, the glycol ether group comprises the formula:




[0010] R₅ comprises H, or C₁-C₂₀ alkyl, aryl, alkylaryl or arylalkyl groups; “n” is an integer from 1 to 7; and R₆ comprises H or a methyl group. Typically, R₅ is a C₁-C₁₀ group, more typically, a C₁-C₆ group, including but not limited to methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, n-amyl or n-hexyl. Typically, “n” is an integer between 1 to 5, and more typically, “n” is 1 or 2.

[0011] In one embodiment, the coalescent composition of the present invention comprises a blend of esters derived from by-products in the reaction, synthesis and/or production of hexamethylenediamine utilized in the production of polyamide, the coalescent composition comprising a blend of esters of adipic diacids, methylglutaric diacids, and ethylsuccinic diacids (herein referred to sometimes as “MGA” or the “MGA blend”). In one embodiment, the blend comprises adducts of alcohol and branched and/or linear diacids, the adducts having the formula R₁-OOC-A-COO-R₂ wherein R₁ and/or R₂ comprise, individually, a C₁-C₈ alkyl, more typically a C₄-C₈ alkyl, and A comprises a mixture of -(CH₂)₄-, -CH₂CH₂CH(CH₃)-, and -CH₂CH(C₂H₅)-. In another embodiment, the blend comprises adducts of alcohol and branched and/or linear diacids, the adducts having the formula R₁-OOC-A-COO-R₂ wherein R₁ and/or R₂ comprise, individually, a C₁-C₈ alkyl, more typically a C₄-C₈ alkyl, and A is selected from the group consisting of -(CH₂)₄-, -CH₂CH₂CH(CH₃)- and -

$\text{CH}_2\text{CH}(\text{C}_2\text{H}_5)-$, and wherein A in the composition is a mixture of $-(\text{CH}_2)_4-$, $-\text{CH}_2\text{CH}_2\text{CH}(\text{CH}_3)-$ and $-\text{CH}_2\text{CH}(\text{C}_2\text{H}_5)-$.

[0012] R_1 and R_2 can individually comprise an ethyl group. R_1 and R_2 can individually comprise a hydrocarbon group originating from fusel oil. In another embodiment, R_1 and R_2 individually can comprise a hydrocarbon group having 3 to 8 carbon atoms. In one embodiment, R_1 and R_2 individually can comprise a hydrocarbon group having 5 to 8 carbon atoms. In one embodiment, R_1 and R_2 can also individually comprise a glycol ether group. Typically, the glycol ether group comprises the formula:



[0013] R_5 comprises H, or C_1 - C_{20} alkyl, aryl, alkylaryl or arylalkyl groups; “n” is an integer from 1 to 7; and R_6 comprises H or a methyl group. Typically, R_5 is a C_1 - C_{10} group, more typically, a C_1 - C_6 group, including but not limited to methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, n-amyl or n-hexyl. Typically, “n” is an integer between 1 to 5, and more typically, “n” is the integer 1 or 2.

[0014] In a further aspect, the present invention is a coalescent composition comprising a blend of esters of adipic diacids, methylglutaric diacids, and ethylsuccinic diacids, wherein the blend is comprises adducts of alcohol and branched and/or linear diacids, the adducts having the formula $\text{R}^1\text{-OOC-A-COO-R}^2$, wherein at least part of R^1 and/or R^2 are residues of at least one linear alcohol having 2 carbon atoms, or at least one linear or branched alcohol having at least 5 carbon atoms, and wherein A is a divalent linear hydrocarbon. In one embodiment, A is one or a mixture of $-(\text{CH}_2)_4-$, $-\text{CH}_2\text{CH}_2\text{CH}(\text{CH}_3)-$, and $-\text{CH}_2\text{CH}(\text{C}_2\text{H}_5)-$.

[0015] In yet another aspect, the present invention is an ester blend comprising adducts of branched diacids, the adducts having the formula $\text{R}^3\text{-OOC-A-COO-R}^4$ wherein R^3 and R^4 are the same or different alkyl groups and A is a linear or branched hydrocarbon. R^3 and R^4 can be independently selected from the group

consisting of methyl, ethyl, propyl, isopropyl, butyl, n-butyl isoamyl, hexyl, heptyl and octyl.

[0016] In another aspect, the present invention comprises a coalescing aid which achieves at least a 50% reduction in VOC level versus Texanol and equivalent or better to Texanol in all other properties.

[0017] In another aspect, the invention comprises a coating composition including but not limited to paints, coatings, inks, adhesives and the like containing the coalescent or coalescing aid composition of the present invention.

BRIEF DESCRIPTION OF DRAWINGS

[0018] Figure 1 is a graph illustrating the effect of varying concentrations of linear dialkyl glutarate esters of the present invention as well as the benchmark on MFFT (°C).

[0019] Figure 2 is a graph illustrating the effect of varying concentrations of branched dialkyl glutarate esters of the present invention as well as the benchmark on MFFT (°C).

[0020] Figure 3 is a graph illustrating the effect of varying concentrations of alkyl AGS Blend esters of the present invention as well as the benchmark on MFFT (°C) in Styrene/Acrylic Latex.

[0021] Figure 4 is a graph illustrating the effect of varying concentrations of alkyl AGS Blend esters of the present invention as well as the benchmark on MFFT (°C) in pure acrylic latex.

[0022] Figure 5 is a graph illustrating the effect of varying concentrations of alkyl AGS Blend esters of the present invention as well as the benchmark on MFFT (°C) in Vinyl/Acrylic Latex.

[0023] Figure 6 illustrates the VOC content, measured via EPA Method 24, of DNB/M (di-n-butyl MGA esters) and DIA/M (di-isoamyl MGA esters) as compared with the benchmark.

[0024] Figure 7 shows the MFFT results for vinyl-acrylic resin comparing DNB/M and DIA/M with the benchmark.

[0025] Figure 8 shows the relative film formation at 40 °F of the benchmark, DNB/M and DIA/M coalescing agents from a scale of 0 (no film formation) to 10 (excellent film formation without cracking).

[0026] Figure 9 illustrates the residual coalescents of the present invention in dried paint film.

[0027] Figure 10 shows a TGA analysis of the residual coalescent of the present invention (as well as of plasticizers and the benchmark) in paint film.

[0028] Figure 11 is shows a DSC analysis of the residual coalescent of the present invention (as well as of plasticizers and the benchmark) in paint film.

[0029] Figure 12 shows the Persoz Hardness in paint film incorporating the coalescent compositions of the present invention (as well as of plasticizers and the benchmark).

[0030] Figure 13 illustrates the QUV exposure of films incorporating the coalescent compositions of the present invention (as well as of plasticizers and the benchmark).

[0031] Figure 14 is illustrates this effect of coalescing agents level on MFFT of styrene-acrylic latex using DBM and DIA/M in comparison to TMB, triethylene glycol diethylhexanoate (TEGEH, plasticizer), and the blend of plasticizer with TMB.

[0032] Figure 15 illustrates the amount of residual coalescing agents in dried paint film during drying.

[0033] Figure 16 shows the glass transition temperature of paint films during drying.

[0034] Figure 17 illustrates persoz hardness development of paint films during drying.

[0035] Figure 18 illustrates the scrub resistance of semi-gloss interior paint incorporating coalescing compositions of the present invention in comparison to TMB (benchmark), TEGEH, and a blend of plasticizer with TMB.

DETAILED DESCRIPTION

[0036] As used herein, the term "alkyl" means a saturated straight chain, branched chain, or cyclic hydrocarbon radical, including but not limited to, methyl, ethyl, n-propyl, iso-propyl, n-butyl, sec-butyl, t-butyl, pentyl, iso-amyl, n-hexyl, and cyclohexyl.

[0037] As used herein, the term "aryl" means a monovalent unsaturated hydrocarbon radical containing one or more six-membered carbon rings in which the unsaturation may be represented by three conjugated double bonds, which may be substituted on one or more of carbons of the ring with hydroxy, alkyl, alkenyl, halo, haloalkyl, or amino, including but not limited to, phenoxy, phenyl, methylphenyl, dimethylphenyl, trimethylphenyl, chlorophenyl, trichloromethylphenyl, aminophenyl, and tristyrylphenyl.

[0038] As used herein, the term "alkylene" means a divalent saturated straight or branched chain hydrocarbon radical, such as for example, methylene, dimethylene, trimethylene.

[0039] The present invention is a low VOC coalescent composition comprising a blend of dibasic esters, typically dibasic esters derived from one or more by-products in the production of polyamide, for example, polyamide 6,6. In one embodiment, the low VOC coalescent composition comprises a blend of esters of adipic diacids, glutaric diacids, and succinic diacids. In another embodiment, the low VOC coalescent composition comprises a blend of esters of adipic diacids, methylglutaric diacids, and ethylsuccinic diacids

[0040] According to one embodiment of the present invention, the blend of dibasic esters corresponds to one or more by-products in the preparation of adipic acid or hexamethylenediamine, which are monomers utilized in the manufacture of polyamides. For example, the esters are obtained by esterification of one of the by-products, which generally contains, on a weight basis of the blend, from about 15% to about 33% succinic acid, from about 50% to about 75% glutaric acid and from about 5% to about 30% adipic acid. As another example, the dialkyl esters are obtained by esterification of another by-product, which generally contains, on a weight basis, from about 30% to 95% methyl glutaric acid, from about 5% to 20% ethyl succinic acid and from about 1% to about 10% adipic acid. It is understood, however, that the acid portion

may be derived from such dibasic acids such as adipic, succinic, glutaric, oxalic, malonic, pimelic, suberic and azelaic acids, as well as mixtures thereof.


[0041] In most embodiments the blend has a high boiling point and 50% or less VOC as compared to commercially available coalescing agents, e.g., 2,2,4-trimethyl-1,3-pentanediol monoisobutyrate. The boiling point of the blend of the present invention is between the range of about 120°C to 450°C. In one embodiment, boiling point of the blend of the present invention is in the range of about 160°C to 400°C, typically in the range of about 215°C to 400°C, more typically in the range of about 260°C to 390°C, more typically in the range of about 280°C to 390°C, more typically in the range of 295°C to 390°C. In one embodiment, boiling point of the blend of the present invention is in the range of about 215°C to 400°C, typically in the range of about 215°C to 350°C.

[0042] In one embodiment, the blend of dibasic esters has a boiling point range of between about 300°C and 330°C. Typically, the diisoamyl AGS blend is associated with this boiling point range. In another embodiment, the dibasic ester blend of the present invention has a boiling point range of between about 295°C and 310°C. Typically, the di-n-butyl AGS blend is associated with this boiling point range. Generally, a higher boiling point or boiling point range corresponds to lower VOC.

[0043] In some embodiments the blend comprises adducts of alcohol and linear diacids, the adducts having the formula $R-OOC-A-COO-R$ wherein R is ethyl, n-butyl or isoamyl and A is a mixture of $-(CH_2)_4-$, $-(CH_2)_3-$, and $-(CH_2)_2-$. In other embodiments, the blend comprises adducts of alcohol, typically ethanol, and linear diacids, the adducts having the formula $R^1-OOC-A-COO-R^2$, wherein at least part of R^1 and/or R^2 are residues of at least one linear alcohol having 4 carbon atoms, and/or at least one linear or branched alcohol having at least 5 carbon atoms, and wherein A is a divalent linear hydrocarbon. In some embodiments A is one or a mixture of $-(CH_2)_4-$, $-(CH_2)_3-$, and $-(CH_2)_2-$. In other embodiments A is one or a mixture of $-(CH_2)_4-$, $-CH_2CH_2CH(CH_3)-$, and $-CH_2CH(C_2H_5)-$. In another embodiment, R_1 and R_2 individually comprise a hydrocarbon group having 3 to 8 carbon atoms or hydrocarbon group having 4 to 8 carbon atoms; however, R_1 and R_2 do not individually comprise an iso-butyl

group. In another embodiment, R_1 and R_2 individually comprise a hydrocarbon group having 5 to 12 carbon atoms or hydrocarbon group having 5 to 12 carbon atoms

[0044] R_1 and R_2 can also individually comprise a glycol ether group. Typically, the glycol ether group comprises the formula:



[0045] wherein R_5 comprises H, or C_1 - C_{20} alkyl, aryl, alkylaryl or arylalkyl groups; "n" is an integer from 1 to 7; and R_6 comprises H or a methyl group. Typically, R_5 is a C_1 - C_{10} group, more typically, a C_1 - C_6 group, including but not limited to methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, n-amyl or n-hexyl. Typically, "n" is an integer between 1 to 5, and more typically, "n" is the integer 1 or 2.


[0046] In another embodiment, the R^1 and/or R^2 groups can be linear or branched, cyclic or noncyclic, C_1 - C_{20} alkyl, aryl, alkylaryl or arylalkyl groups. Typically, the R^1 and/or R^2 groups can be C_1 - C_8 groups, for example groups chosen from the methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, n-amyl, n-hexyl, cyclohexyl, 2-ethylhexyl and isooctyl groups and their mixtures. For example, R^1 and/or R^2 can both or individually be ethyl groups, R^1 and/or R^2 can both or individually be n-propyl groups, R^1 and/or R^2 can both or individually be isopropyl groups, R^1 and/or R^2 can both or individually be n-butyl groups, R^1 and/or R^2 can individually be isobutyl groups, R^1 and/or R^2 can both or individually be n-amyl groups, or R^1 and/or R^2 can be mixtures thereof (e.g., when comprising a blend of dibasic esters).

[0047] In further embodiments the invention can include blends comprising adducts of branched diacids, these adducts having the formula R^3 -OOC-A-COO- R^4 , wherein R^3 and R^4 are the same or different alkyl groups and A is a branched or linear hydrocarbon. Typically, A comprises isomers of a C_4 hydrocarbon. Examples include those where R^3 and/or R^4 can be linear or branched, cyclic or noncyclic, C_1 - C_{20} alkyl, aryl, alkylaryl or arylalkyl groups. Typically, R^3 and R^4

are independently selected from the group consisting of methyl, ethyl, propyl, isopropyl, butyl, n-butyl, iso-butyl, iso-amyl, and fusel oil.

[0048] Compounds deriving from fusel oil are known and have been described, for example, in "The Use of Egyptian Fusel Oil for the Preparation of Some Plasticizers Compatible with Polyvinyl Chloride", Chuiba et al., Indian Journal of Technology, Vol. 23, August 1985, pp. 309-311, which describes a reaction product of a fusel oil having a boiling point of 110 to 136°C and of pure adipic or sebacic acid.

[0049] R₃ and R₄ can also individually comprise a glycol ether group. Typically, the glycol ether group comprises the formula:



[0050] wherein R₅ comprises H, or C₁-C₂₀ alkyl, aryl, alkylaryl or arylalkyl groups; "n" is an integer from 1 to 7; and R₆ comprises H or a methyl group. Typically, R₅ is a C₁-C₁₀ group, more typically, a C₁-C₆ group, including but not limited to methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, n-amyl or n-hexyl. Typically, "n" is an integer between 1 to 5, and more typically, "n" is the integer 1 or 2.

[0051] In yet another embodiment, the invention comprises a composition based on dicarboxylic acid diester(s) of formula R⁵-OOC-A-COO-R⁶ wherein group A represents a divalent alkylene group typically in the range of, on average, from 2.5 to 10 carbon atoms. R⁵ and R⁶ groups, which can be identical or different, represent a linear or branched, cyclic or noncyclic, C₁-C₂₀ alkyl, aryl, alkylaryl or an arylalkyl group.

[0052] The composition can correspond to a complex reaction product, where mixtures of reactants are used. For example, the reaction of a mixture of HOOC-A^a-COOH and HOOC-A^b-COOH with an alcohol R^a-OH can give a mixture of the products R^aOOC-A^a-COOR^a and R^aOOC-A^b-COOR^a. Likewise, the reaction of HOOC-A^a-COOH with a mixture of alcohols R^a-OH and R^b-OH can give a mixture of the products R^aOOC-A^a-COOR^a and R^bOOC-A^a-COOR^b, R^aOOC-A^a-

COOR^b and R^bOOC-A^a-COOR^a (different from R^aOOC-A^a-COOR^b if A^a is not symmetrical). Likewise, the reaction of a mixture of HOOC-A^a-COOH and HOOC-A^b-COOH with a mixture of alcohols R^a-OH and R^b-OH can give a mixture of the products R^aOOC-A^a-COOR^a and R^bOOC-A^a-COOR^b, R^aOOC-A^a-COOR^b, R^bOOC-A^a-COOR^a (different from R^aOOC-A^a-COOR^b if A^a is not symmetrical), R^aOOC-A^b-COOR^a and R^bOOC-A^b-COOR^b, R^aOOC-A^b-COOR^b and R^bOOC-A^b-COOR^a (different from R^aOOC-A^b-COOR^b if A^b is not symmetrical).

[0053] The groups R¹ and R², can correspond to alcohols R¹-OH and R²-OH (respectively). These groups can be likened to the alcohols. The group(s) A, can correspond to one or more dicarboxylic acid(s) HOOC-A-COOH. The group(s) A can be likened to the corresponding diacid(s) (the diacid comprises 2 more carbon atoms than the group A).


[0054] In one embodiment, group A is a divalent alkylene group comprising, on average, more than 2 carbon atoms. It can be a single group, with an integral number of carbon atoms of greater than or equal to 3, for example equal to 3 or 4. Such a single group can correspond to the use of a single acid. Typically, however, it corresponds to a mixture of groups corresponding to a mixture of compounds, at least one of which exhibits at least 3 carbon atoms. It is understood that the mixtures of groups A can correspond to mixtures of different isomeric groups comprising an identical number of carbon atoms and/or of different groups comprising different numbers of carbon atoms. The group A can comprise linear and/or branched groups.

[0055] According to one embodiment, at least a portion of the groups A corresponds to a group of formula -(CH₂)_n- where n is a mean number greater than or equal to 3. At least a portion of the groups A can be groups of formula -(CH₂)₄- (the corresponding acid is adipic acid). For example, A can be a group of formula -(CH₂)₄-, and/or a group of formula -(CH₂)₃-.

[0056] In one embodiment, the composition comprises compounds of formula R-OOC-A-COO-R where A is a group of formula -(CH₂)₄-, compounds of formula R-OOC-A-COO-R where A is a group of formula -(CH₂)₃-, and compounds of formula R-OOC-A-COO-R where A is a group of formula -(CH₂)₂-.


[0057] In certain more specific embodiments, the blend comprises:

[0058] a diester of formula I:




(I) ;

[0059] a diester of formula II:



(II) ; and

[0060] a diester of formula III:




(III).

[0061] R_1 and/or R_2 can individually comprise a hydrocarbon having from about 4 to about 8 carbon atoms, typically, propyl, isopropyl, butyl, n-butyl or isoamyl. In addition, R_1 and/or R_2 can individually comprise a hydrocarbon group originating from fusel oil. In one embodiment, R_1 and/or R_2 do not individually comprise iso-butyl groups. In one embodiment, R_1 and/or R_2 individually comprise a hydrocarbon group having from about 3 to about 12 carbon atoms.

In one embodiment, R_1 and/or R_2 individually comprise a hydrocarbon group having from about 3 to about 12 carbon atoms. In one embodiment, R_1 and/or R_2 individually comprise a hydrocarbon group having from about 8 to about 12 carbon atoms. The blend typically comprises (by weight of the blend) (i) about 15% to about 35% of the diester of formula I, (ii) about 55% to about 70% of the diester of formula II, and (iii) about 7% to about 20% of the diester of formula III, and more typically, (i) about 20% to about 28% of the diester of formula I, (ii) about 59% to about 67% of the diester of formula II, and (iii) about 9% to about 17% of the diester of formula III. Mention may be made of Rhodiasolv® RPDE (Rhodia Inc., Cranbury, NJ).


[0062] In a further embodiment, R_1 and R_2 can individually comprise a glycol ether group. Typically, the glycol ether group comprises the formula:



[0063] wherein R_5 comprises H, or C_1 - C_{20} alkyl, aryl, alkylaryl or arylalkyl groups; "n" is an integer from 1 to 7; and R_6 comprises H or a methyl group. Typically, R_5 is a C_1 - C_{10} group, more typically, a C_1 - C_6 group, including but not limited to methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, n-amyl or n-hexyl. Typically, "n" is an integer between 1 to 5, and more typically, "n" is the integer 1 or 2.


[0064] In certain other embodiments, the blend comprises:

[0065] a diester of the formula IV:




(IV) ;

[0066] a diester of the formula V:




(V) ; and

[0067] a diester of the formula VI:



(VI).

[0068] R_1 and/or R_2 can individually comprise a hydrocarbon having from about 4 to about 8 carbon atoms, typically, methyl, ethyl, propyl, isopropyl, butyl, isobutyl, n-butyl, or isoamyl. In addition, R_1 and/or R_2 can individually comprise a hydrocarbon group originating from fusel oil. In one embodiment, R_1 and/or R_2 individually comprise a hydrocarbon group having from about 3 to about 12 carbon atoms. In one embodiment, R_1 and/or R_2 individually comprise a hydrocarbon group having from about 4 to about 12 carbon atoms. In one embodiment, R_1 and/or R_2 individually comprise a hydrocarbon group having from about 8 to about 12 carbon atoms. In a further embodiment, R_1 and R_2 can individually comprise a glycol ether group. Typically, the glycol ether group comprises the formula:



[0069] wherein R_5 comprises H, or C_1 - C_{20} alkyl, aryl, alkylaryl or arylalkyl groups; "n" is an integer from 1 to 7; and R_6 comprises H or a methyl group.

Typically, R_5 is a C_1 - C_{10} group, more typically, a C_1 - C_6 group, including but not limited to methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, n-amyl or n-hexyl. Typically, "n" is an integer between 1 to 5, and more typically, "n" is the integer 1 or 2. In such embodiments, the blend typically comprises (by weight of the blend) (i) from about 5% to about 30% of the diester of formula IV, (ii) from about 70% to about 95% of the diester of formula V, and (iii) from about 0% to about 10% of the diester of formula VI.

[0070] In one embodiment, the blend typically comprises (by weight of the blend): (i) from about 9% to about 17% of the diester of formula IV, (ii) from about 80% to about 88% of the diester of formula V, and (iii) from about 0.5% to about 5% of the diester of formula VI.

[0071] In another embodiment, the blend comprises (by weight of the blend): (i) about 13% of the diester of formula IV, (ii) about 84% of the diester of formula V, and (iii) about 2% of the diester of formula VI. Mention may be made of Rhodiasolv® IRIS (Rhodia Inc., Cranbury, NJ).

[0072] It is understood that when describing one or more compositions herein, it can denote a mixture of several compounds made up from a general formula as described herein. A composition can be defined by mentioning all or part of each of the precise chemical formulae of compounds present therein or by mentioning all or part of several general chemical formulae grouping together several compounds (families of compounds), if appropriate using means, or by mentioning a single general formula with means. A composition can comprises at least 50% by weight of compounds corresponding to the chemical formulae (precise formulae, or general formula(e), or mean formula(e)) used to define them, typically at least 75%, more typically at least 90%, and most typically at least 99%.

[0073] The useful compounds or useful compositions of the present invention can be prepared by any appropriate process. A process for preparing the adduct of adipic acid and of fusel oil is, for example, described in the document "The Use of Egyptian Fusel Oil for the Preparation of Some Plasticizers Compatible with Polyvinyl Chloride", Chuiba et al., Indian Journal of Technology, Vol. 23, August 1985, pp. 309-311. Use may be made of a similar process, if appropriate

(for the compounds or material compositions of the invention), by replacing the adipic acid with another diacid or with a mixture of diacids of formula HOOC-A-COOH .

[0074] The compounds or material compositions can, for example, be obtained by a process comprising an "esterification" stage by reaction of a diacid of formula HOOC-A-COOH or of a diester of formula MeOOC-A-COOMe or of an acyl dichloride of formula ClOC-A-COCl or of an imide.

[0075] The reactions can be appropriately catalyzed. In one embodiment, use is made of at least 2 molar equivalents of alcohols per diacid, diester, acyl dichloride or imide. It is possible, for example, to employ from 2 to 2.5 equivalents for the reactions with the diacids, diesters or acyl dichlorides. It is possible, for example, to employ from 5 to 25, for example from 10 to 20, equivalents for the reactions with the imides. The reactions can, if appropriate, be promoted by extraction of the reaction by-products (for example, extraction by evaporation of the methanol during a transesterification starting from the diester).

[0076] The reaction can be followed by stages of filtration and/or of purification, for example by distillation. The alcohol or the mixture of alcohols can be represented by the formula R-OH , where R represents a group R^1 or R^2 or a mixture of groups R^1 and R^2 . Such groups and corresponding alcohols have been described above. Fusel oil has also formed the subject of a description above.

[0077] According to a further embodiment, the operation is carried out by reaction with a diacid or a mixture of diacids. It is also possible to operate by reaction with a "light" diester of formula Me-OOC-A-COOMe .

[0078] Diacids or mixtures of diacids have been described above (by the group A) and are commercially available. Use may in particular be made of a mixture of dibasic esters of adipic acid, glutaric acid and succinic acid, sometimes referred to herein as "AGS". Use may in particular be made of a mixture of dibasic esters of adipic acid, methylglutaric acid and ethylsuccinic acid, sometimes referred to herein as "MGA". A mixture of light diesters, such as a mixture of dimethyl adipate, dimethyl glutarate and dimethyl succinate, can be employed for the transesterification reaction.

[0079] According to another embodiment, use is made, as reactant, of 2-methylglutaric acid, or of a mixture of 2-ethylsuccinic acid and 2-methylglutaric acid, or of a mixture of 2-ethylsuccinic acid, 2-methylglutaric acid and adipic acid, or of the corresponding diesters.

[0080] The latex film forming compositions can be any of the type which benefit from coalescing agents, especially compositions where low VOC is an advantage or necessary and/or efficiency is an advantage. ("Efficiency" generally meaning that less or a lower amount of the coalescing agent of the present invention is needed to achieve the same MFFT as compared with the benchmark in paint. The minimum film formation temperature (MFFT) is used as a key test to measure efficiency of coalescence and reflects the ability of paint to be applied in cold weather, wherein a lower MFFT allows for a paint to be applied at lower temperatures while still maintaining acceptable coalescence properties.) The coatings of the present invention are suitable for use in a variety of architectural and industrial applications, more typically architectural applications, including but not limited to clear coatings or undercoats, floor covering coatings, wall coatings, transportation coatings, maintenance coatings, and the like or any other application where a low VOC coating composition is desired for use on a substrate.

[0081] It is understood that other additives such can be added to the coating composition including but not limited to one or more thickeners, dispersants, defoamers, surfactants, emulsifiers, rheology modifiers, wet-edge additives, whetting agents, humectants, wax, colorants, UV absorbers, pigments, freeze-thaw stabilizers, biocides, anti-oxidants, volatile plasticizers and the like, or a combination thereof.

[0082] The compositions of the present invention can be used as components of other compositions such as paint compositions. In one embodiment, the composition of the present invention is applied to various substrates, for example, wood or wooden surfaces, plastic surfaces, metal surfaces, primed or painted surfaces, and stone or cement substrates, using conventional methods including but not limited to spraying, brushing, rolling and the like.

[0083] The following examples in which all parts and percentages are by weight unless otherwise indicated are presented to illustrate a few embodiments of the invention.

EXAMPLES

[0084] Example 1

[0085] One primary characteristic of a coalescing agent is the efficiency in which it enables a consistent film to form, and this was determined by measuring the MFFT on a MFFT Bar 90. A coalescing agent having a minimum 50% reduction of VOC as analyzed via EPA Method 24 was desired to be developed. Finally, regardless of the product's efficiency or VOC, it was desirable that any additive formulated into a coating have minimal/no effect on the appearance of the film, as determined semi-quantitatively by drawing a film on glass and visually inspecting the surface for defects.

[0086] Experiment 1.1 - Linear Diesters Using Glutaric Acid

[0087] A total of 10 diesters using glutaric acid were synthesized. To gain an understanding of structure vs. function, five linear and five branched alcohols were chosen. The five linear esters were n-dibutyl glutarate, n-dipentyl glutarate, n-dihexyl glutarate, n-diheptyl glutarate, and n-dioctyl glutarate and each was then mixed for one hour in Rhodopas DS-910, a styrene-acrylic latex. The MFFT and VOC results are shown in Figure 1.

[0088] VOC is measured in a variety of way, one of which is EPA method 24. Generally, such method is an indirect measurement of the VOC content. The first step is to determine the non-volatile content of the coating by drying a known weight of coating and determining the amount of dry film left (this is the non-volatile portion). The volatile fraction of sample (including water) is determined by subtracting the non-volatile portion from the initial weight of sample. Other ASTM methods generally known in the art are used to measure the amount of water and exempt solvents in the coating, and these values are subtracted from the volatile matter, leaving what is considered to be the amount of VOC's.

[0089] Table 1: Concentration (%) VOC for Linear Glutarates

	% VOC
n-dibutyl glutarate	51.65
n-dipentyl glutarate	20.64
n-dihexyl glutarate	9.46
n-diheptyl glutarate	4.27
n-dioctyl glutarate	2.80
Texanol	99.81

[0090] As shown in Table 1, the linear glutarates had lower VOC levels as compared to Texanol. The data indicates that the lower molecular weight compounds reduce the MFFT more efficiently than the larger molecular weight diesters. Without being limited by theory, it is believed that the larger molecular weight compounds have more difficulty incorporating themselves into the particles.

[0091] Experiment 1.2 - Branched Glutarates

[0092] The following five branched glutarates were synthesized: di-isobutyl glutarate, di-2-methylbutyl glutarate, di-4-methyl-2-pentyl glutarate, di-2-ethylhexyl glutarate, and pentylol glutarate. The pentylol was chosen because it is a waste stream blend of alcohols that is a cheaper alternative to pentyl alcohol and has a larger average molecular weight thus reducing the VOC level. The MFFT and VOC levels are shown in Figure 2.

[0093] Table 2: % VOC for branched glutarates

	% VOC
di-isobutyl glutarate	76.5

di-(2-methylbutyl) glutarate	28.4
di-(4-methyl-2-pentyl) glutarate	29.3
pentylol glutarate	23.3
di-(2-ethylhexyl) glutarate	2.30
Texanol	99.81

[0094] As shown in Table 2, all of the branched glutarates have lower VOC levels compared to Texanol.

[0095] Experiment 1.3 - Combinations of linear and branched diesters

[0096] Particular diesters from the above Experiments 1.1 and 1.2 were chosen and synthesized into the AGS esters. Another alcohol, isoamyl alcohol, was added and esterified with AGS, due to it being a cheaper alternative than the pentyl alcohol and easier to industrialize than the pentylol diester. These six diesters were analyzed the same way as previous described above. The MFFT and VOC levels are shown in Figure 3.

[0097] Table 3: % VOC for AGS diesters

	% VOC
n-dibutyl AGS	57.28
di-(2-methylbutyl) AGS	28.13
isoamyl AGS	25.49
pentylol AGS	23.27
n-dipentyl AGS	21.34
Texanol	99.81

[0098] Experiment 1.4 - Testing in Pure Acrylic and Vinyl/acrylic Latex

[0099] In order to study the effect of the AGS esters in certain systems, various ester blends, for example, butyl AGS, Pentyol AGS and Isoamyl AGS, were tested in a commercially available pure acrylic latex (referring to Figure 4) and a commercially available vinyl/acrylic latex (referring to Figure 5).

[0100] Without being bound by theory, the efficiency of the butyl AGS in the commercial semi-gloss paint is believed to be the result of improved solubility of the coalescing agent in a butyl acrylate rich polymer.

[0101] Experiment 1.5 - Paint Formulations for AGS diesters

[0102] All four of the AGS diesters were formulated into a commercial semi-gloss paint and into a commercial flat paint. Below is the recipe of each paint formulation with the specifications. In an attempt to ensure that the paints were as similar as possible, a master batch of the grind phase was prepared in a 1 kg steel beaker and then diluted with the appropriate latex. Next, the master batch was split and let down with the various coalescing agent, defoamer, and rheology modifier.

Commercial High Quality Interior Flat Paint, Latex F-9100				
Grind Phase	Control		PVC	44.70%
Water	300.00		Volume, Solids	30.00%
Natrosol 250MR	2.00		Weight, Solids	46.60%
Kathon LX 1.5%	1.80		Viscosity, Initial	89 KU
Tamol 731	6.00		Viscosity, ICI	1.1P
KTPP	1.00		pH	8.7
Rhodoline 643	2.00		VOC	184 g/L
Triton N-101	2.00			
Triton N-57*	2.00			

Propylene Glycol	45.00			
Ti-Pure, R-902	200.00			
Optiwhite	75.00			
Snowflake	75.00			
Grind Sub	711.80			
F-9100	293.90			
Let Down				
<i>Coalescent</i>	13.00			
Rhodoline 643	2.00			
Water	56.90			
Acrysol RM-825	19.00			
28% Ammonia	1.00			
Other Sub	91.90			
Total	1097.60			

Commercial Interior Semigloss, Latex 629				
Grind Phase	Control		PVC	24.00%
Water	148.50		Solids, Weight	48.30%
Water	20.00		Solids, Volume	34.90%
Cellosize HEC	1.00		VOC	78.0 g/L

QP-4400				
Rhodoline 286N	6.20		Stormer, KU	100
Kathon LX 1.5%	1.50		ICI P	1
Strodex PK- OVOC	2.00		Gloss, 60	50
Rhodoline 643	2.00		Gloss, 20	15
Sodium Carbonate	2.00		pH	9
Ti-Pure, R- 706	235.00			
Polygloss 90	35.00			
Rhodoline 643	2.00			
Water	23.30			
Grind Sub	478.50			
Latex 629	500.00			
Let Down				
<i>Coalescent</i>	12.50			
Acrysol RM- 2020	8.50			
Rhodoline 643	2.00			
Water	65.00			
Other Sub	88.00			
Total	1066.50			

[0103] The following properties were tested on each paint formulation (Commercial Interior Semigloss and Commercial High Quality Interior Flat Paint): Stormer and ICI viscosities, pH, and film appearance. The paint was allowed to equilibrate overnight and analyzed the next day. Block resistance and gloss were also tested on the semi-gloss paint. The gloss testing is important due to the fact that is is generally not desirable to include, i.e., paint companies do not want, additives to reduce gloss. Block resistance is desirable as it ensures that after being painted, doorways and window frames will still open after the paint has cured. The Stormer viscosity measures low shear viscosity (e.g. mixing) and the ICI viscosity measures the high shear viscosity (e.g. paint roller, or sprayer).

[0104] Table 4: Data of Commercial High Quality Interior Flat Paint, Latex F-9100

Coalescing	Viscosity		pH	Film
Agent	Stormer (KU)	ICI (P)		Appearance
Texanol	140.8	0.25	9.93	8
n-butyl AGS	138.8	0.25	9.41	9
pentylol AGS	139.4	0.3	9.58	8
isoamyl AGS	140.2	0.3	9.83	9

[0105] Table 5: Data of Commercial Interior Semigloss Paint (Latex 629)

Coalescing	Viscosity		pH	Gloss		Film	Block Resistance	
Agent	Stormer (KU)	ICI (P)		20	60	Appearance	1 day	7 day
Texanol	96.1	0.4	8.31	5.1	35.4	6	8	8
n-butyl AGS	101.4	0.6	8.06	8.8	40.2	6	7	7
pentylol AGS	105.4	0.9	7.76	10.0	42.0	6	7	8
isoamyl AGS	96.3	0.5	8.24	10.8	44.9	9	8	7

[0106] Isoamyl AGS is efficient in reducing the MFFT in all three types of latexes, reduces VOC levels by 75% compared to Texanol, and has excellent performance in semi-gloss paint.

[0107] EXAMPLE 2

[0108] Experiments were conducted on a mixture of esters of adipic acid, methylglutaric acid and ethylsuccinic acid, sometimes referred to as "MGA". Such experiments were conducted at varying weight percent of the coalescent agent of the present invention. As stated above, a primary characteristic of the coalescing agent of the present invention is the efficiency at which it enables a consistent film to form. This was determined by measuring the MFFT on a MFFT Bar 90. The target for the coalescing agent of the present invention is for a minimum 50% reduction of VOC as analyzed via EPA Method 24. Regardless of the product's efficiency or VOC, it is desired that any additive formulated into a coating have minimal/no effect on the appearance of the film and this was determined semi-quantitatively by drawing a film on glass and visually inspecting the surface for defects.

[0109] Referring to Figure 6, it can be seen that the VOC content, measured via EPA Method 24, of Rhodiasolv™ DNB/M (di-n-butyl MGA esters) and Rhodiasolv™ DIA/M (di-isoamyl MGA esters) have a VOC content of less than 50%. Figure 7 shows the MFFT results for vinyl-acrylic resin comparing Rhodiasolv™ DNB/M and Rhodiasolv DIA/M with the benchmark, Texanol™. As shown in the figure, a lower amount of the coalescing agent of the present invention is needed to achieve similar MFFT as the benchmark.

[0110] Figure 8 shows the relative film formation at 40 °F of the benchmark, Rhodiasolv™ DNB/M and Rhodiasolv™ DIA/M coalescing agents from a scale of 0 (no film formation) to 10 (excellent film formation without cracking). The coalescing agents were introduced into semi-gloss paint formulation at various amount (lbs/gal) and measured.

[0111] Table 7: Properties of Semi-Gloss Paint

	Benchmark	DNB/M	DIA/M

Viscosity (KU)	96	96	96
Viscosity (KU) 3 f/t cycles	100	103	102
20 degree Gloss	34.9	35.3	34.7
60 degree Gloss	46.3	55.3	53.6
Scrub resistance ASTM D-2486	377	509	522
Flow/Leveling ASTM D-4062	9	9	9
Adhesion 24 hrs (wet/dry)	4/5	4/5	4/5
Blister 24 hrs dry (10=best)	10	10	10
Block Resistance 1 day (120°F)	6	6	5
Block Resistance 7 day (120°F)	8	8	7

[0112] Table 7 shows improved scrub resistance for Rhodiasolv™ DNB/M (di-n-butyl MGA esters) and Rhodiasolv™ DIA/M (di-isoamyl MGA esters) of 509 and 522, respectively, as compared to the Benchmark Texanol™ of 377.

[0113] Referring to Figure 9, Figure 9 illustrates the residual coalescents in dried paint film, specifically a TGA analysis of paint films with Rhodiasolv™ DNB/M. It was observed that Rhodiasolv™ DNB/M has a similar TGA curve as compared with the benchmark (i.e., TGA analysis of paint films with Texanol™ as the coalescent agent).

[0114] Referring to Figures 10, 11 and 12, analyses are performed with respect to the residual coalescent agents in paint film using TGA Analysis, DSC Analysis, and Persoz hardness, respectively. Rhodiasolv™ DNB/M and DIA/M was compared to the benchmark (i.e., Texanol™) and a control (all of the aforementioned agents being *temporary* plasticizers), as well as to plasticizers

(i.e., “Zero” VOC coalescents) Optifilm™ 400, Archer RC™ and Velate™ 375. Plasticizers such as Optifilm™ 400, Archer RC™ and Velate™ 375 plasticizers are generally used outside of the architectural coating industry and not desirable in architectural coatings because such plasticizers are not temporary plasticizer. Thus, they normally remain in the paint (thus, zero VOC) making the paint susceptible to blocking along with other un-desirable properties.

[0115] Referring back to Figure 10, the “zero” VOC coalescents remained in the paint film at all times. Referring to Figure 11, the “zero” VOC coalescents had a very low Tg that remained consistently low as a function of days of film drying time. Rhodiasolv™ DIA/M and Rhodiasolv™ DNB/M had a lower initial Tg compared with Texanol™. Referring to Figure 12, the hardness of paint films with “zero” VOC coalescents was low as the (permanent) plasticizers are generally remained in the paint film, while the hardness of Rhodiasolv™ DNB/M increased more than both the “zero” VOC coalescents and Texanol™ benchmark.

[0116] Example 3

[0117] Experiments were carried out using the MGA and AGS esters of the present inventions as compared to a combination of the benchmark, Texanol, which is 100% VOC and a plasticizer, e.g., triethylene glycol diethylhexanoate (TEGEH), 0% VOC. (As described above, use of the plasticizer is not desirable as its use imparts poor performance characteristics such as blocking on the film.)

[0118] Because of their very high boiling point and extremely low vapor pressure, the coalescing agents of the present invention, and in particular DBM (di-butyl ester family) and DIA/M (di-iso-amyl ester family), are low VOC materials according to the USA’s EPA method 24, and are VOC free based on European definition and Green Seal 11. The VOC levels of the coalescent composition by different definition, comparing to industrial standard coalescent trimethyl pentanediol monoisobutyrate ester (TMB, Texanol) and triethylene glycol diethylhexanoate (TEGEH, plasticizer), are summarized in Table 8.

Table 8: VOC% measured by various standards					
	TMB	DBM	DIA/M	Plasticizer	Plasticizer/TMB (1:1)

VOC% by EPA method 24	100	41	28	0	50
VOC% by 2004/42/EC	0	0	0	0	0
VOC% by Green Seal 11	100	0	0	0	50

[0119] As shown in Table 8, DBM and DIA/M are low odor coalescing agents and can be used in most types of latex paints and coatings, combining very high boiling point with optimal evaporation rate, without the drawback of plasticizers.

[0120] Experiment 3.1

[0121] Experiment 3.1 evaluated the compatibility and efficiency of DBM and DIA/M coalescing agents with various commercial latexes. The results showed that the coalescing agents of the present invention are more efficient compared to Texanol or Texanol/TEGEH combination, and that the coalescent agents reduced the MFFT for a variety of resin systems. As generally illustrated, roughly 15 – 30% less coalescing agent is needed to achieve the same level of MFFT as compared to industrial standard.

[0122] Figure 14 illustrates this effect of coalescing agents level on MFFT of styrene-acrylic latex using DBM and DIA/M in comparison to TMB, triethylene glycol diethylhexanoate (TEGEH, plasticizer), and the blend of plasticizer with TMB. Referring to Figure 14, the coalescent compositions of the present are highly efficient, meaning less amount are needed as compared to TMB, TEGEH and TMB/TEGEH and, therefore, the cost of formulation is reduced.

[0123] Experiment 3.2

[0124] Experiment 3.2 evaluated the residual coalescent agents of the present invention as compared to commercial coalescing agents in dried paint films. Paint was drawn down on the glass panels at 6 mil wet thickness. The panels were placed in the controlled temperature and humidity room at 50% relative humidity and 23°C and allowed to dry. After the paint film was dried for 24 hours, a small piece of film was carefully removed from the glass panels.

Thermogravimetric Analysis (TGA) and Differential Scanning Calorimetry (DSC)

analysis were carried out. Same analysis was run after the paint film was dried at certain intervals up to 12 weeks.

[0125] The residual coalescing agent level in the paint films was calculated based on the TGA analysis, and the results are given in Figure 15. The residual amount of plasticizer didn't represent the true value that was left in the paint film since it didn't evaporate under the test conditions. However, note that the residual plasticizer remained at the same level in the film through drying. Additives such as TEGEH that claim to be as "zero" VOC coalescing agents via EPA method 24 are actually true plasticizers, i.e., did not leave the paint film. Use of TEGEH resulted in relatively softer films resulted in poor hardness and blocking resistance. It was observed the presence of residual TMB in the paint film even after 2 - 3 months drying.

[0126] The Tg of the paint films were analyzed by DSC and the hardness (Persoz Hardness) development during paint drying was monitored. The results are shown in Figures 16 and 17. It is very clear that the hardness and Tg of paint film containing plasticizer barely changed after the initial increase which is apparently due to the evaporation of water. Unlike plasticizers, which permanently stay in the paint film and make it softer with a lower Tg, Rhodiasolv coalescing agents leave the paint film gradually and enable the hardness and Tg of the paint to recover faster, which resulted in better paint performance such as blocking resistance. Especially Rhodiasolv DBM had much quicker Tg and hardness development than the plasticizer and its blend with TMB (1/1), while the latter and Rhodiasolv DBM had the same VOC level measured by EPA method 24.

[0127] Experiment 3.3

[0128] Experiment 3.3 evaluated the coalescing agents of the present invention (e.g., DBM and DIAM) in paints as compared to TMB, TEGEH and TMB/TEGEH. The following data summarized the results of commercial semi-gloss latex paint using DBM and DIAM coalescing agents in comparison to industrial standard coalescent TMB and plasticizer TEGEH as well as their blend. The usage level of coalescing agents is around 4.6% based on the total solids of the paint.

[0129] Table 9. Paint formulation – interior semi gloss


Ingredients		TMB	Rhodiasolv DBM	Rhodiasolv DIAM	Plasticizer	Plasticizer /TMB (1:1)
Ti-Pure R-746		362.0	362.0	362.0	362.0	362.0
<i>Premix the following and add to letdown</i>						
Propylene glycol		25.8	25.8	25.8	25.8	25.8
Tamol 165		6.6	6.6	6.6	6.6	6.6
Kathon LX 1.5%		1.7	1.7	1.7	1.7	1.7
<i>Continue with letdown</i>						
Rhoplex SG 20		525.0	525.0	525.0	525.0	525.0
Aqueous ammonia (28%)		2.0	2.0	2.0	2.0	2.0
Acrysol RM 2020NPR		19.4	19.4	19.4	19.4	19.4
Acrysol RM 8W		1.7	1.7	1.7	1.7	1.7
Triton GR 7M		2.1	2.1	2.1	2.1	2.1
Foamaster VL		2.2	2.2	2.2	2.2	2.2
Water		93.7	93.7	93.7	93.7	93.7
TMB		23.8				
Rhodiasolv DBM			23.8			
Rhodiasolv DIAM				23.8		
Plasticizer					23.8	
Plasticizer/TMB (1:1)						23.8
TOTAL		1066.0	1066.0	1066.0	1066.0	1066.0

[0130] Scrub Scrub resistance was measured according to ASTM D2486 and the results are given in Figure 18. It was observed that Rhodiasolv DBM and DIA/M showed scrub resistance of 607 and 518, respectively, in comparison to TMB (454), plasticizer (396) and their blend (471).

[0131] The present invention, therefore, is well adapted to carry out the objects and attain the ends and advantages mentioned, as well as others inherent therein. While the invention has been depicted and described and is defined by reference to particular embodiments of the invention, such references do not imply a limitation on the invention, and no such limitation is to be inferred. The invention is capable of considerable modification, alteration and equivalents in form and function, as will occur to those ordinarily skilled in the pertinent arts. The depicted and described embodiments of the invention are exemplary only and are not exhaustive of the scope of the invention. Consequently, the invention is intended to be limited only by the spirit and scope of the appended claims, giving full cognizance to equivalents in all respects.


What is claimed is :

1. A low VOC coalescent agent composition comprising:
a diester of formula (I):



(I); and


a diester of formula (II):



(II),

wherein R₁ and R₂ are independently a C₄-C₈ alkyl group.

2. The low VOC coalescent agent composition of claim 1 further comprising a diester of formula (III)




(III).

3. The composition of claim 2 wherein the composition is characterized by a boiling point range of about 280°C to about 390°C.
4. The composition of claim 2 wherein the composition is characterized by a boiling point range of about 295°C to about 390°C.
5. The composition of claim 2 wherein the composition is characterized by a boiling point range of about 300°C to about 330°C.
6. The composition of claim 2 wherein R₁ and R₂ are independently butyl, n-butyl, isoamyl, hexyl, heptyl, or octyl.

7. The composition of claim 2 wherein R_1 and R_2 are independently n-butyl, isoamyl, fusel oil or a mixture thereof.
8. A latex coating composition comprising:
 - (a) at least one latex polymer;
 - (b) water; and
 - (c) the low VOC coalescent agent composition of claim 2.


1/18

FIG. 1
EFFECT OF LINEAR DIALKYL GLUTARATE ESTERS ON MFFT




2/18

FIG. 2
EFFECT OF BRANCHED DIALKYL GLUTARATE ESTERS ON MFFT




3/18

FIG. 3
EFFECT OF AGS BLENDS ON MFFT IN STYRENE/ACRYLIC LATEX




4/18

FIG. 4
EFFECT OF AGS BLENDS ON MFFT PURE ACRYLIC



5/18

FIG. 5
EFFECT OF AGS BLENDS ON MFFT IN A VINYL/ACRYLIC LATEX



6/18




Figure 6: Rhodiasolv DNB/M and DIA/M have VOC of less than 50%

7/18

FIG. 7
MFFT RESULTS FOR VINYL-ACRYLIC RESIN






FIG. 8
LOW TEMPERATURE FILM FORMATION - SEMI-GLOSS PAINT




9/18

FIG. 9
RESIDUAL COALESCENTS IN DRIED PAINT FILM




10/18

FIG. 10
RESIDUAL COALESCENT IN PAINT FILM - TGA ANALYSIS



11/18

FIG. 11
RESIDUAL COALESCENT IN PAINT FILM - DSC ANALYSIS



12/18

FIG. 12
PERSOZ HARDNESS






FIG. 13
QUV EXPOSURE (1100 HOURS)



14/18

FIG. 14
EFFECTS OF COALESCENTS ON MFFT OF LATEX



15/18




Figure 15

16/18




Figure 16

17/18




Figure 17

18/18





Figure 18

LOW TEMPERATURE FILM FORMATION - SEMI-GLOSS PAINT



RHODIASOLV® DNB/M AND DIA/M
 FILM FORMATION (40 F) SCALE
 10 = NO CRACKING (EXCELLENT FILM FORMATION)
 0 = COMPLETE FAILURE (NO FILM FORMATION)

9.5
 11.9
 14.3
 16.7