



Europäisches Patentamt
European Patent Office
Office européen des brevets



Publication number:

0 317 046 B1

EUROPEAN PATENT SPECIFICATION

- (45) Date of publication of patent specification: 28.07.93 (51) Int. Cl.⁵: B41M 1/36, D21H 19/36
(21) Application number: 88303892.9
(22) Date of filing: 29.04.88

(54) Recording paper and ink jet recording method by use thereof.

(30) Priority: 20.11.87 JP 293579/87

(43) Date of publication of application:
24.05.89 Bulletin 89/21

(45) Publication of the grant of the patent:
28.07.93 Bulletin 93/30

(84) Designated Contracting States:
AT BE CH DE ES FR GB IT LI NL SE

(56) References cited:
FR-A- 2 485 578 GB-A- 2 088 777
US-A- 4 446 174 US-A- 4 478 910
US-A- 4 636 409 US-A- 4 636 410

PATENT ABSTRACTS OF JAPAN, vol. 8, no.
140 (M-305)[1577], 29th June 1984; JP-A-59 38
087 (CANON K.K.) 01-03-1984

(73) Proprietor: CANON KABUSHIKI KAISHA
30-2, 3-chome, Shimomaruko, Ohta-ku
Tokyo(JP)

(72) Inventor: Akiya, Takashi
2-3-1001, Konandal 2-chome Konan-ku
Yokohama-shi Kanagawa-ken(JP)
Inventor: Arai, Ryuichi
15-11-301, Matsugae-cho

Sagamihara-shi Kanagawa-ken(JP)

Inventor: Sakaki, Mamoru

17-10, Kamitsuruma 4-chome

Sagamihara-shi Kanagawa-ken(JP)

Inventor: Morohoshi, Naoya

2595-16, Ohkami

Hiratsuka-shi Kanagawa-ken(JP)

Inventor: Munakata, Megumi

18-9, Asahi-cho 3-chome

Atsugi-shi Kanagawa-ken(JP)

Inventor: Saito, Masako

16-4, Ohsone 2-chome Kohoku-ku

Yokohama-shi Kanagawa-ken(JP)

(74) Representative: Beresford, Keith Denis Lewis
et al

BERESFORD & Co. 2-5 Warwick Court High

Holborn

London WC1R 5DJ (GB)

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid (Art. 99(1) European patent convention).

Description

This invention relates to a recording paper and an ink jet recording method which comprises impinging aqueous ink droplets onto the recording paper. The paper exhibits good absorptivity for aqueous ink, permits good image resolution and colour forming characteristics by the colourant in the ink.

In the prior art there has been known as recording paper for ink jet recording:

(1) A recording paper such as filter paper and blotting paper which is prepared by making a paper mainly composed of pulp into a sheet having low degree of sizing;

(2) A recording paper prepared using a substrate paper which has been subjected to considerable sizing and on which is coated a filler which is porous and has large oil absorption e.g. silica or zeolite to form an ink absorption layer;

(3) A recording paper having a coating layer provided on a substrate with a low degree of sizing as disclosed in Japanese laid open patent application numbers 53012/1977, 11829/1980 and 38087/1984 and US patent number 4478910.

Although the recording paper (1) exhibits good ink absorptivity, ink penetrates deep into the fibrous layer of the paper and therefore the colour forming characteristics of the colourant in the ink is poor. Since the ink is also absorbed along the fibres at the surface of the paper, a phenomenon called feathering occurs in which the dots formed are not circular but irregular in shape which reduces the resolution available and the quality of the resulting image.

In the recording paper (2), good dot shapes and resolution can be obtained because the ink absorbing layer is porous and uniform. However, a relatively thick ink absorption layer is required to give sufficient ink absorptivity and the problem therefore arises that a single coating is insufficient, and a plurality of coatings have to be applied. Furthermore, if the ratio of the pigment to the binder (P/B) in the ink absorbing layer is increased in order to increase the ink absorptivity, there is a risk of the pigment dropping off the paper (powder drop-off) and this can cause slippage of delivery rollers for the paper or clogging of the nozzles of the ink jet printer.

The recording paper (3) has the advantage of providing a recording medium having good ink absorptivity and good colour forming characteristics as compared with the recording paper (2) even where the coating layer provided is relatively thin. However, it is difficult with this kind of paper to simultaneously satisfy the requirements of ink absorptivity, good resolution and good attachment density of the ink. The reason is that although the ink absorptivity of the paper may be good, a considerable amount of ink will penetrate into the substrate paper so that the intensity of colour produced by the colourant and the resolution available will be reduced. Furthermore, a problem arises called "cockling" in which the pulp fibres becomes swollen with ink and regions of printing are subject to wavy deformation, and there is also the so called "backthrough" problem in which ink printed onto one face of the paper reaches the reverse surface of the paper. These problems not only reduce the quality of the recorded image, but cockling can cause the recording head to scrape the surface of the recording paper which impairs the quality of the recording images. Where the "backthrough" phenomenon has occurred, when one sheet of recording paper is superimposed on another, the unwanted image appearing at the back surface of one face may become transferred onto the front face of the underlying sheet. Thus both of these problems are serious. These phenomena are inherent in the recording paper (3) which as a whole receives ink, and they have become particularly apparent with increasing use of high resolution ink jet recording. However, although the above problems are inherent in the recording paper (3) they have not been subject of detailed research. The present invention provides a recording paper comprising a fibrous substrate coated with 2-10g/m² dry weight of a coating containing a silicon-containing pigment which has an oil absorption according to JIS K 5101 in the range 80-300ml/100g, the paper having:

(a) a basis weight of 90 to 200 g/m²;

(b) a Stöckigt sizing degree of 0 to 15 sec; and

(c) both the pigment and fibres of the substrate paper present on the surface of the recording paper.

The above recording paper exhibits little powder drop off, is inexpensive to produce and exhibits good ink absorptivity and good colour forming properties. It can produce images at high resolution and does not give rise to significant "cockling" or "backthrough" problems at regions where printed images appear.

The invention further provides a method for making a recording paper as aforesaid, which comprises coating the fibrous paper substrate at a speed of 60 to 200 m/min with an aqueous coating liquid comprising the silicon-containing pigment and a binder, the liquid having a viscosity at 30° C measured at 60 rpm by a B-type viscometer of 60-200 cps, and subsequently drying the coated paper.

The invention further provides an ink jet recording method which comprises impinging aqueous ink droplets onto the aforesaid recording paper.

Next, to describe in detail about the present invention, the substrate paper to be used in the present invention is a sheet containing fibrous material and, if necessary, a pigment, having a Stöckigt sizing degree according to JIS P8122 in the range of 0 to 15 sec. (based on the basis weight of 65 g/m²), and any paper made to a sizing degree of 0 to 15 sec. by a suitable sizing agent according to the acidic sheet making method or the neutral sheet making method known in the art can be used. In aspect of ink absorptivity of the recording paper obtained, the sizing degree of the substrate paper should be preferably in the range of 0 to 10 sec., more preferably in the range of 0 to 5 sec. Also, in aspect of coating stability of the coating liquid, it is preferably one sec. or more.

Also, for accomplishing the desired object of the present invention, the basis weight of the above paper is also an important factor. More specifically, the basis weight of the substrate paper to be used in the present invention is required to be within the range of 80 to 200 g/m². If the basis weight is less than the above range, the so called stiffness of the recording paper is weak to pose a problem in carriage characteristic within the printer during printing, and also to lack ink absorption capacity as the recording paper, and therefore the printing portion causes cockling to pose a problem that sharpness of the image is lowered. Also, when recording is performed by use of a printer having a plural number of recording heads, the convex portion formed by cockling will become in contact with the head during recording, whereby clogging of the head, etc. may be caused to involve the problem that irregularity may be formed in the image obtained.

Further, due to low ink receiving capacity, the ink not received will be subject to back-through, whereby there may be caused the problem that the ink image of the upper recording paper may be back transferred to the image of the lower recording paper when printed matters are placed as superposed on one another, or there may occur the problem that no recording can be performed on the back surface, etc.

On the other hand, if the basis weight exceeds the above range, since the stress applied to the coating layer on the surface becomes stronger during bending of the recording paper obtained, whereby problems such as cracking, powder drop-off or peel-off, etc. of the coating layer may be caused.

More specifically, during the coating step, by repetition of stretching and bending along the rolls of the coating machine, crack may be formed on the coating layer surface, which will later cause image irregularity or powder drop-off. Further, during cutting or storage after manufacturing of the recording paper, there is also the problem that similar drop-off is liable to occur during mounting on the printer or in the printer carriage system. Particularly, powder drop-off which occurs during recording is undesirable, because clogging of the recording head may be caused. Also, it is not preferable to make thicker the thickness of a substrate paper with large stretching and shrinkage degree relative to humidity, because the problem of curling may be caused.

The various problems as described above can be solved by employment of a substrate paper with a basis weight of 80 to 200 g/m².

The thickness of the substrate paper to be used in the present invention may be preferably in the range of 50 to 250 μ m. If the thickness is less than the above range, the so called stiffness of the recording paper obtained is weak, posing a problem in conveying characteristic within the printer during printing and also lacking ink absorption capacity, whereby the printing portion causes cockling to ensue the problem that sharpness of the image is lowered.

The fibrous material constituting the above substrate paper to be used in the present invention is composed mainly of wood pulp, typically LBKP and NBKP, but various synthetic fibers or glass fibers may be mixed, if necessary.

The aqueous coating liquid to be used in the present invention comprises primarily a silicon containing type pigment and an aqueous binder. The silicon containing pigment may be preferably one which is hydrophilic and contains relatively large amount of oil absorption according to JIS K 5101 in aspect of ink absorptivity and color forming property of the colorant, including for example silica, calcium silicate, aluminum silicate, magnesium silicate and the like. Among them, those with oil absorption of 80 to 300 ml/100 g, more preferably 150 to 250 ml/100 g, are preferred.

The above silicon containing type pigment should be preferably one in which all the particles have the above oil absorption, but the pigment is not necessarily constituted of all the particles having uniform oil absorption, and it may also be a mixture of pigment with different oil absorptions. In the case of such a mixture of pigments with different oil absorptions, 60% by weight or more of the whole pigment may have the oil absorption within the above range.

When the oil absorption of the pigment according to JIS K5101 is less than 80 ml/100 g, the ink absorptivity when incorporated into a recording paper is poor, and the colorant in the ink on the surface of the coated layer cannot be ensured, whereby there is the tendency such that the ink may be penetrated deep into the recording paper to make color formation of the colorant bad. On the other hand, when it

exceeds 300 ml/100 g, powder drop-off will occur at the same level of binder and, if a binder necessary for prevention of powder drop-off is employed, lowering in ink absorptivity will be undesirably brought about.

As the aqueous binder, there may be used, for example, one or a mixture of two or more kinds selected from water-soluble polymers such as polyvinyl alcohol, starch, oxidized starch, cationized starch, casein, carboxymethyl cellulose, gelatin, hydroxyethyl cellulose, etc. and water-dispersed polymers such as SBR latex, MBR latex, vinyl acetate emulsion, etc.

The present inventors have studied variously about the characteristics of the aqueous coating liquid during coating, and consequently found that a recording paper having good ink jet recording characteristics can always be obtained stably when the liquid viscosity of the aqueous coating liquid at 30°C is in the range of 60 to 200 cps.

The viscosity in the present invention is measured under the condition of 60 r.p.m. by B-type viscometer, and thixotropic characteristic, dilatant characteristic, etc. can be also evaluated by changing the rotational number.

If the viscosity of the aqueous coating liquid is less than 60 cps, the aqueous coating liquid will be penetrated deep into the substrate paper to fill the voids possessed by the substrate paper for absorption of ink, with the result that lowering in ink absorptivity may be brought about.

On the other hand, if the viscosity exceeds 200 cps, coating irregularity may be undesirably caused due to too high a viscosity. Also, only water in the aqueous coating liquid is absorbed by the substrate paper to lower the strength of the surface layer, whereby powder drop-off, etc. may be caused.

The viscosity of the aqueous coating liquid as described above can be controlled easily by the kinds of the above pigment and binder, combination thereof, their proportions used, the respective concentrations and the total concentration of the both, etc. In the present invention, the ratio of the silicon containing pigment to the binder used may be generally in the range of 3/1 to 1/1 (weight ratio), and an aqueous coating liquid with the total solid content ranging from about 3 to 70% by weight is preferred.

If the binder amount is more than the above range, ink absorptivity, particularly initial absorption speed of ink will be lowered. This problem is pronounced as the sizing degree of the substrate paper is higher even within the sizing degree of 0 to 15 sec. and the basis weight is lower. On the other hand, if the content of the pigment is larger than the above range, there ensues the problem of powder drop-off due to shortage in adhesive force even when a thin coating layer may be provided. Particularly, in the present invention where a substrate with low sizing degree and high basis weight is used, since the binder in the coating liquid will be readily absorbed by the substrate paper, it is essentially required that the proportion of the pigment should not exceed the above range. The problem of powder drop-off is more pronounced, particularly as the sizing degree of the substrate paper is lower.

Further, the viscosity of the above aqueous coating liquid is also intimately correlated with the coating speed. More specifically, the above aqueous coating liquid comprising a filler which is hydrophilic and has an oil absorption of 80 to 300 ml/100 g according to JIS K5101 and an aqueous binder frequently exhibits thixotropic viscosity like coating liquids in general.

Accordingly, if the coating speed is too quick, coating irregularity will be liable to occur even if the viscosity may be lower, while if it is too slow, the time required for scraping off the coating liquid to a given coated amount after coating is too long, whereby the aqueous coating liquid will be penetrated deep into the substrate to lower undesirably ink absorptivity. Therefore, as the balance between the viscosity of the aqueous coating liquid and the coating speed, the coating speed may be preferably 60 to 200 m/min. when the viscosity is 60 to 200 cps. A coating speed quicker or slower than this range is not desirable, because various problems as described above will occur.

As the coating machine to be used in the present invention, all known in the art may be used, but the coater suitably used in the present invention may include an air knife coater and a bar coater, etc.

The amount of the aqueous coating liquid coated may be suitably within the range of 2 to 10 g/m² as the coated amount on drying and, if it is less than 2 g/m², the coating will not function as the coated layer. In other words, when the coated amount is less than 2 g/m², the ink colliding against the recording surface will be feathered along the fibers to be disturbed in dot shape, and at the same time the dye will be penetrated deep into the inner portion of the paper, whereby coloring density of the image will be lowered. On other hand, if the coated amount exceeds 10 g/m², the merit of making the sizing degree of the substrate paper 0 to 15 sec. will be lost, and also there exists no more fibrous material of the substrate paper on the recording paper surface, whereby ink absorptivity, color forming characteristic, etc. become unsatisfactory and also feeling as the paper is lowered, also with attendant problem of powder drop-off.

In the present invention, after coating of the aqueous coating liquid under the condition in the present invention, the recording paper is dried according to the drying method known in the art such as drying by hot air drying furnace, drying drum, etc. to provide a recording paper. As an additional step, surface

smoothing by super calendering may be also performed.

As described above, the recording paper of the present invention having a Stöckigt sizing degree of 0 to 15 sec. and a basis weight of 90 to 200 g/m² is obtained, but more preferably the Stöckigt sizing degree is in the range of 0 to 10 sec., optimally 0 to 5 sec. and the preferable range of the basis weight is in the range of 90 to 160 g/m².

If the Stöckigt sizing degree of the recording paper exceeds 15 sec., ink absorptivity, particularly initial absorptivity will undesirably lowered.

When the basis weight of the recording paper is less than 90 g/m², the stiffness of the recording paper obtained is weak to pose a problem in carriage characteristic and or lack ink absorption capacity as the recording paper, whereby the printing portion may cause cockling or back-through, thus causing various problems as described above.

If the basis weight exceeds 200 g/m², there is involved the problem of powder drop-off or the problem of curling in the recording paper obtained.

The recording paper of the present invention, which contains a large amount of a silicon containing type pigment with high ink absorbing capacity in the surface layer of the recording paper, has high probability of the ink droplets being trapped and absorbed by the pigment, and therefore feathering and diffusion of the ink can be inhibited, whereby it may be considered that dot shape is improved and also the coloring density enhanced.

Also, since the substrate paper itself has ink absorptivity, the ink can be rapidly absorbed into the recording paper, whereby there is no such phenomenon such as flow-out or feathering of ink even when inks with different colors may be attached on one site within a short time, and therefore recorded images with excellent color forming characteristic can be obtained.

Further, in the range of the coating amount in the recording paper of the present invention, the fibrous material on the surface of the substrate paper will not be completely covered with the silicon containing type pigment in the aqueous coating liquid, and the recording paper surface is under the state where the silicon containing type pigment and the fibrous material are mixed with each other. For this reason, not only the recording paper has the sufficient characteristics as the ink jet recording paper, but also it has a texture approximate to plain paper with little powder drop-off from the coated layer as additional advantage.

The present invention is described in more detail by referring to Examples and Comparative examples. In the sentences, parts and % are based on weight unless otherwise particularly noted.

Examples 1 - 5, Comparative examples 1 - 5

As the substrate paper, a hand-made sheet with low sizing degree was controlled to the basis weight as shown below, and to the substrate paper was applied by coating an aqueous coating liquid with the following composition at the coating amounts on drying, respectively, followed by drying at 120 °C for 5 minutes, to obtain recording media of the present invention and for comparative purpose. The basis weight of the substrate paper, coating amounts on drying of coating layers, the basis weights of recording media and Stöckigt sizing degrees of recording media are shown in Table 1.

(Coating liquid composition)	
Synthetic silica (Syloid 620, produced by Fuji Davison Chemical Ltd.)	10 parts
Polyvinyl alcohol (PVA-117), produced by Kuraray)	4 parts
Water	100 parts

Comparative example 6

As an example of the recording paper (2) as described in the Description of the Related Art, a wood free paper with a basis weight of 80 g/m², was coated with the above coating liquid at a coating amount on drying of 6 g/m², dried similarly as above to obtain a recording medium K for comparison. The recording medium obtained had a Stöckigt sizing degree of 25 sec.

Table 1

Sample No.	Basis weight of Substrate Paper	Amount of Coating on Coating Layer	Basis weight of Recording Paper	Stöckigt Sizing Degree of Recording Paper
A	40g/m ²	6g/m ²	46g/m ²	4sec. (Comparative example 1)
B	63	2	65	4sec. (Comparative example 2)
C	63	6	69	4sec. (Comparative example 3)
D	85	2	87	4sec. (Comparative example 4)
E	85	6	91	4sec. (Example 1)
F	110	2	112	4sec. (Example 2)
G	110	6	116	5sec. (Example 3)
H	150	2	152	5sec. (Example 4)
I	150	6	156	5sec. (Example 5)
J	400	6	406	6sec. (Comparative example 5)

The ink jet recording adaptability of each of the above recording papers A - K was evaluated for ink absorptivity, resolution and color forming characteristic by performing ink jet recording with the use of inks having the compositions shown below by means of an ink jet printer having ink jet heads with four colors of Y, M, C, BK each provided with 128 nozzles at nozzle interval of 1/16 mm(16 nozzles per 1mm).

Y (yellow) ink composition	
C.I. Direct Yellow 86	2 parts
Glycerine	15 parts
Diethylene glycol	15 parts
Water	70 parts

M (magenta) ink composition	
C.I. Acid Red 35	2 parts
Glycerine	15 parts
Diethylene glycol	15 parts
Water	70 parts

C (cyan) ink composition	
C.I. Direct Blue 199	2 parts
Glycerine	15 parts
Diethylene glycol	15 parts
Water	70 parts

BK (black) ink composition	
C.I. Food Black 2	2 parts
Glycerine	15 parts
Diethylene glycol	15 parts
Water	70 parts

Evaluation items

(1) Dot density was measured for black dots by means of Sakura Microdensitometer PDM-5 (produced by Konishiroku Photo Industry K.K.) by applying JIS K 7505 to plinting microdot.

(2) Ink absorptivity was evaluated by means of a bubble jet system printer having ink jet recording heads of four colors of Y, M, C and BK each provided with 128 nozzles at nozzle interval of 1/16mm. One with a line being much bolder at the mixed portion of two color inks of the recorded image than at the monochromatic portion was rated as X, one with occurrence of feathering, etc. at the color mixed portion and unclear edge as Δ, one with clear edge also at the mixed color portion similarly to at the monochromatic portion as O.

(3) For powder drop-off, one which gave paper powder attached to finger when the coating layer surface was touched with finger and one which gives rise to paper powder through peel-off or cracking of the coated layer when the recording paper was folded were rated as x, and one which is not so as O.

(4) For back-through, one in which back-through was confirmed during printing by the same printer as in (2) was rated as x, one which was not so as O, and the middle range as Δ.

(5) For cockling, one having scraping generated on the recording paper surface through cockling with head was rated as x, one without generation of scraping but with cockling being confirmed by visual observation and inferior in image quality as Δ, and one without noticeable cockling as O.

The evaluation results are shown in Table 2.

Table 2

Sample No.	(1) Dot density	(2) Ink absorptivity	(3) Powder drop-off	(4) Back-through	(5) Cockling	(6) Overall evaluation
A	1.1	Δ	O	X	X	X
B	1.1	Δ	O	X	X	X
C	1.2	O	O	X	Δ	x
D	1.1	O	O	Δ	Δ	x
E	1.2	O	O	O	O	o
F	1.1	O	O	O	O	o
G	1.2	O	O	O	O	o
H	1.1	O	O	O	O	o
I	1.2	O	O	O	O	o
J	1.2	O	X	O	O	x
K	1.0	X	O	O	O	x

Examples 6 - 9

On the substrate paper used in Example 1, the compositions shown below were used, following otherwise the same procedure as in Example 1, recording media L and M of the present invention were obtained. Similarly, according to the same procedure as in Example 3 except for using the compositions shown below on the same substrate paper used in Example 3, recording media N and O of the present

invention were obtained. Then, by use of these recording media, recording was performed in the same manner as in Example 1 and evaluation was performed. The results are shown in Table 3.

	Example 6	Example 7	Example 8	Example 9
	L	M	N	O
Silica (Syloid 620)	8	7	8	7
Polyvinyl alcohol (PVA-117)	4	5	4	5
Water	100	100	100	100
Sizing degree	4	6	5	7

Table 3

Evaluation results	(1)	(2)	(3)	(4)	(5)	(6)
Example 6	1.2	0	0	0	0	0
Example 7	1.2	0	0	0	0	0
Example 8	1.2	0	0	0	0	0
Example 9	1.2	0	0	0	0	0

Claims

1. A recording paper comprising a fibrous substrate coated with 2-10gm² dry weight of a coating containing a silicon-containing pigment which has an oil absorption according to JIS K 5101 in the range 80-300ml/100g, the paper having:
 - (a) a basis weight of 90 to 200 g/m²;

(b) a Stöckigt sizing degree of 0 to 15 sec; and

(c) both the pigment and fibres of the substrate paper present on the surface of the recording paper.

2. A recording paper according to Claim 1 wherein the Stöckigt sizing degree is in the range of 0 to 10 sec.
3. A recording paper according to Claim 2, wherein the Stöckigt sizing degree is in the range of 0 to 5 sec.
4. A recording paper according to Claim 1, 2 or 3, wherein the basis weight is in the range of 90 to 160 g/m².
5. A recording paper according to any preceding claim, wherein said silicon containing pigment is silica, calcium silicate, aluminum silicate or magnesium silicate.
6. A recording paper according to any preceding claim, wherein the coating contains the silicon-containing pigment and an aqueous binder at a weight ratio of 1/1-3/1.
7. An ink jet recording method, which comprises impinging aqueous ink droplets onto a recording paper according to any preceding claim.
8. An ink jet recording method according to Claim 7, wherein said aqueous ink contains an aqueous dye.
9. A method for making a recording paper as claimed in any of claims 1 to 7, which comprises coating the fibrous paper substrate at a speed of 60 to 200 m/min with an aqueous coating liquid comprising the silicon-containing pigment and a binder, the liquid having a viscosity at 30 °C measured at 60 rpm by a B-type viscometer of 60-200 cps, and subsequently drying the coated paper.

Patentansprüche

1. Aufzeichnungspapier, das ein faseriges Substrat umfaßt, welches mit 2 - 10 gm² Trockenmasse einer Aufstrichmasse, die ein siliziumhaltiges Pigment enthält, das eine Ölabsorption nach JIS K 5101 im Bereich von 80 bis 300 ml/100 g hat, beschichtet ist, wobei das Papier:
 - (a) ein Basisgewicht von 90 bis 200 g/m² hat;
 - (b) einen Stöckigt-Leimungsgrad von 0 bis 15 Sekunden hat; und
 - (c) sowohl das Pigment als auch die Fasern des Substratpapiers an der Oberfläche des Aufzeichnungspapiers vorhanden sind.
2. Aufzeichnungspapier nach Anspruch 1, bei welchem der Stöckigt-Leimungsgrad im Bereich von 0 bis 10 Sekunden liegt.
3. Aufzeichnungspapier nach Anspruch 2, bei welchem der Stöckigt -Leimungsgrad im Bereich von 0 bis 5 Sekunden liegt.
4. Aufzeichnungspapier nach Anspruch 1, 2 oder 3, bei welchem das Basisgewicht im Bereich von 90 bis 160 g/m² liegt.
5. Aufzeichnungspapier nach irgendeinem vorhergehenden Anspruch, bei welchem das siliziumhaltige Pigment Siliziumdioxid, Kalziumsilikat, Aluminiumsilikat oder Magnesiumsilikat ist.
6. Aufzeichnungspapier nach irgendeinem vorhergehenden Anspruch, bei welchem die Streichmasse das siliziumhaltige Pigment und ein wäßriges Bindemittel in einem Maseverhältnis von 1/1 - 3/1 enthält.
7. Tintenstrahl-Aufzeichnungsverfahren, das das Auftreffenlassen von wäßrigen Tintentröpfchen auf ein Aufzeichnungspapier nach irgendeinem vorhergehenden Anspruch umfaßt.
8. Tintenstrahl-Aufzeichnungsverfahren nach Anspruch 7, bei welchem die wäßrige Tinte einen wäßrigen Farbstoff enthält.

9. Verfahren zur Herstellung eines Aufzeichnungspapiers nach irgendeinem der Ansprüche 1 bis 7, das das Beschichten des faserigen Papiersubstrats mit einer wäßrigen Aufstrichflüssigkeit, die ein siliziumhaltiges Pigment sowie ein Bindemittel enthält, bei einer Geschwindigkeit von 60 bis 200 m/min, wobei die Flüssigkeit eine Viskosität von 60 - 200 cps bei 30 °C, gemessen bei 60 U/min mittels eines B-Viskosimeters, hat, und ein anschließendes Trocknen des beschichteten Papiers umfaßt.

Revendications

1. Papier d'enregistrement comprenant un substrat fibreux revêtu avec 2 à 10 g/m², en poids sec, d'un revêtement contenant un pigment renfermant du silicium qui présente une absorption d'huile, conformément à la norme JIS K 5101, comprise dans l'intervalle de 80 à 300 ml/100 g, papier possédant :
 - (a) un grammage de 90 à 200 g/m² ;
 - (b) un degré de collage Stöckigt de 0 à 15 secondes ; et
 - (c) le pigment et les fibres du papier servant de substrat présents sur la surface du papier d'enregistrement.
2. Papier d'enregistrement suivant la revendication 1, dans lequel le degré de collage Stöckigt est compris dans l'intervalle de 0 à 10 secondes.
3. Papier d'enregistrement suivant la revendication 2, dans lequel le degré de collage Stöckigt est compris dans l'intervalle de 0 à 5 secondes.
4. Papier d'enregistrement suivant la revendication 1, 2 ou 3, dans lequel le grammage est compris dans l'intervalle de 90 à 160 g/m².
5. Papier d'enregistrement suivant l'une quelconque des revendications précédentes, dans lequel le pigment contenant du silicium est la silice, le silicate de calcium, le silicate d'aluminium ou le silicate de magnésium.
6. Papier d'enregistrement suivant l'une quelconque des revendications précédentes, dans lequel le revêtement contient le pigment contenant du silicium et un liant aqueux en un rapport pondéral de 1/1 à 3/1.
7. Procédé d'enregistrement par jet d'encre, qui consiste à frapper un papier d'enregistrement suivant l'une quelconque des revendications précédentes, avec des gouttelettes d'une encre aqueuse.
8. Procédé d'enregistrement par jet d'encre suivant la revendication 7, dans lequel l'encre aqueuse contient un colorant aqueux.
9. Procédé de production d'un papier d'enregistrement suivant l'une quelconque des revendications 1 à 7, qui comprend le revêtement du papier fibreux servant de substrat à une vitesse de 60 à 200 m/minute avec un liquide aqueux de revêtement comprenant le pigment contenant du silicium et un liant, le liquide ayant une viscosité à 30 °C, mesurée à 60 tr/min au moyen d'un viscosimètre de type B, comprise dans l'intervalle de 60 à 200 cps, et le séchage ultérieur du papier revêtu.

REGISTER ENTRY FOR EP0317046

European Application No EP88303892.9 filing date 29.04.1988

Priority claimed:

20.11.1987 in Japan - doc: 62293579

Designated States BE CH DE ES FR GB IT LI NL SE AT

Title RECORDING PAPER AND INK JET RECORDING METHOD BY USE THEREOF.

Applicant/Proprietor

CANON KABUSHIKI KAISHA, 30-2, 3-chome, Shimomaruko, Ohta-ku Tokyo, Japan
[ADP No. 50366384002]

Inventors

TAKASHI AKIYA, 2-3-1001, Konandai 2-chome Konan-ku, Yokohama-shi
Kanagawa-ken, Japan [ADP No. 53934428001]

RYUICHI ARAI, 15-11-301, Matsugae-cho, Sagamihara-shi Kanagawa-ken, Japan
[ADP No. 53934444001]

MAMORU SAKAKI, 17-10, Kamitsuruma 4-chome, Sagamihara-shi Kanagawa-ken,
Japan [ADP No. 54036983001]

NAOYA MOROHOSHI, 2595-16, Ohkami, Hiratsuka-shi Kanagawa-ken, Japan
[ADP No. 56566540001]

MEGUMI MUNAKATA, 18-9, Asahi-cho 3-chome, Atsugi-shi Kanagawa-ken, Japan
[ADP No. 55625461001]

MASAKO SAITO, 16-4, Ohsone 2-chome Kohoku-ku, Yokohama-shi Kanagawa-ken,
Japan [ADP No. 56566557001]

Classified to
B41M D21H

Address for Service

KEITH DENIS LEWIS BERESFORD, BERESFORD & Co. 2-5 Warwick Court High
Holborn, London WC1R 5DJ, United Kingdom [ADP No. 50583137001]

EPO Representative

KEITH DENIS LEWIS BERESFORD, BERESFORD & Co. 2-5 Warwick Court High
Holborn, London WC1R 5DJ, United Kingdom [ADP No. 50583137001]

Publication No EP0317046 dated 24.05.1989
Publication in English

Examination requested 14.10.1989

Patent Granted with effect from 28.07.1993 (Section 25(1)) with title
RECORDING PAPER AND INK JET RECORDING METHOD BY USE THEREOF.

REGISTER ENTRY FOR EP0317046 (Cont.)

PAGE: 2

28.06.1993 Notification from EPO of change of Applicant/Proprietor details
from

CANON KABUSHIKI KAISHA, 30-2, 3-chome, Shimomaruko, Ohta-ku Tokyo,
Japan [ADP No. 50366384002]

to

CANON KABUSHIKI KAISHA, 30-2, 3-chome, Shimomaruko, Ohta-ku, Tokyo,
Japan [ADP No. 50366384002]

Entry Type 25.14 Staff ID. RD06 Auth ID. EPT

**** END OF REGISTER ENTRY ****

OA80-01
EP

OPTICS - PATENTS

01/11/93 10:53:57
PAGE: 1

RENEWAL DETAILS

PUBLICATION NUMBER

EP0317046

PROPRIETOR(S)

CANON KABUSHIKI KAISHA, 30-2, 3-chome, Shimomaruko, Ohta-ku, Tokyo,
Japan

DATE FILED

29.04.1988

DATE GRANTED

28.07.1993

DATE NEXT RENEWAL DUE

29.04.1994

DATE NOT IN FORCE

DATE OF LAST RENEWAL

YEAR OF LAST RENEWAL

00

STATUS

PATENT IN FORCE