

(19)



(11)

EP 1 816 113 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

08.08.2007 Bulletin 2007/32

(51) Int Cl.:

C06D 5/06 *(2006.01)*

C06B 23/00 *(2006.01)*

(21) Application number: **07000356.1**

(22) Date of filing: **09.01.2007**

(84) Designated Contracting States:

**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IS IT LI LT LU LV MC NL PL PT RO SE SI
SK TR**

Designated Extension States:

AL BA HR MK YU

(30) Priority: **26.01.2006 JP 2006017386**

(71) Applicant: **DAICEL CHEMICAL INDUSTRIES, LTD.**

Sakai-shi

Osaka (JP)

(72) Inventors:

• **Kitayama, Kenji**

Ibogawacho

Tatsuno-shi

Hyogo (JP)

• **Tomiyama, Shogo**

Ibogawacho

Tatsuno-shi

Hyogo (JP)

(74) Representative: **Grünecker, Kinkeldey,**

Stockmair & Schwanhäusser

Anwaltssozietät

Maximilianstrasse 58

80538 München (DE)

(54) **Gas generating composition**

(57) The present invention provides a gas generating composition comprising a light rare earth compound.

EP 1 816 113 A1

Description**BACKGROUND OF INVENTION**

5 Field of Invention

[0001] The present invention relates to a gas generating composition suitable for airbag restraint systems of automobiles or the like.

10 Description of Related Art

[0002] Gas generating agents typically generate a large amount of fine combustion residue and mist (solid components (for example, metal components) in the gas generating agent that are generated by combustion of the gas generating agent) after the combustion. Combustion residue that has been just generated bears heat. If the combustion residue is released into an air bag, the air bag is damaged and there is a risk of inflicting burns to a vehicle occupant. Further, if the airbag is damaged, the mist is released into the vehicle cabin. In order to avoid such danger, a fine-mesh metal filter is disposed inside an inflator.

[0003] However, because the filter has the highest weight ratio among the inflator components, although the filter purifies the gas, the use thereof causes the increase in weight and size of the inflator.

[0004] Decreasing the combustion temperature of the gas generating agent can be considered as a method for reducing the size and weight of the filter. JP-A No. 2003-525106 and JP-A No. 2005-126262 describes adding the components for decreasing the combustion temperature.

SUMMARY OF THE INVENTION

[0005] The present invention provides a gas generating composition including a light rare earth compound.

DETAILED DESCRIPTION OF INVENTION

[0006] The present invention provides a gas generating composition that purifies the gas by using a rare earth compound that is not described in JP-A No. 2003-525106 and JP-A No. 2005-126262 and generates hardly any mist during combustion.

[0007] The light rare earth compound is preferably a compound of a rare earth element selected from scandium, yttrium, lanthanum, cerium, praseodymium, and neodymium. The preferred light rare earth compound is selected from oxides, hydroxides, halogenides (halides), nitrates, sulfates, acetates, phosphates, and carbonates of rare earth elements. The light rare earth compound preferably has a mean particle size within a range of 0.5 to 500 μm .

[0008] The gas generating composition in accordance with the present invention generates but a small amount of carbon monoxide or nitrogen oxide during combustion and generates hardly any mist during combustion.

40 Embodiments of Invention

[0009] The gas generating composition in accordance with the present invention includes a light rare earth compound. Other components can be selected from fuels, oxidizing agents, binders, and additives that are used in the known gas generating compositions. The light rare earth compound acts to decrease the generated amount of toxic nitrogen oxide and carbon monoxide after the combustion and also act to convert the generated mist into a slag residue inside the gas generator.

[0010] The light rare earth compound is a compound of a rare earth element selected from scandium, yttrium, lanthanum, cerium, praseodymium and neodymium. The compound can be selected from oxides, hydroxides, halogenides, nitrates, sulfates, acetates, phosphates, and carbonates of rare earth elements.

[0011] Among them, oxides and hydroxides of lanthanum, cerium, praseodymium, and neodymium are preferred.

[0012] The light rare earth compound preferably has a mean particle size within a range of 0.5 to 500 μm , more preferably within a range of 0.5 to 100 μm , and even more preferably within a range of 0.7 to 20 μm .

[0013] The mean particle size is measured by a particle size distribution method based on laser light scattering. The measurement sample is prepared by dispersing a basic metal nitrate in water and irradiating for three minutes with ultrasonic waves. Then, a 50% accumulated value (D_{50}) of the number of particles is found and the mean value obtained in two cycles of measurements is taken as a mean particle size.

[0014] The content of the rare earth compound in the gas generating composition is preferably 0.1 to 20 mass%, more preferably 0.5 to 15 mass%, and even more preferably 0.5 to 10 mass%.

[0015] At least one selected from among tetrazole compounds, guanidine compounds, triazine compounds, and nitroamine compounds can be used as the fuel.

[0016] The preferred tetrazole compounds include 5-aminotetrazole and bitetrazole ammonium salt. The preferred guanidine compounds are guanidine nitrate, aminoguanidine nitrate, nitroguanidine, and triaminoguanidine nitrate. The preferred triazine compounds are melamine, cyanuric acid, ammeline, ammelide, and ammeland. The preferred nitroamine compound is cyclo-1,3,5-trimethylene-2,4,6-trinitramine.

[0017] As the oxidizing agent, at least one selected from among basic metal nitrates, nitrates, ammonium nitrate, perchlorates, and chlorates can be used.

[0018] As basic metal nitrate, at least one selected from among basic copper nitrate, basic cobalt nitrate, basic zinc nitrate, basic manganese nitrate, basic iron nitrate, basic molybdenum nitrate, basic bismuth nitrate, and basic cerium nitrate can be used.

[0019] For the basic metal nitrate to increase the burning rate, the mean particle size thereof is preferably 30 μm or less, more preferably 10 μm or less. The mean particle size is measured by a particle size distribution method based on laser light scattering. The measurement sample is prepared by dispersing a basic metal nitrate in water and irradiating for three minutes with ultrasonic waves. Then, a 50% accumulated value (D_{50}) of the number of particles is found and the mean value obtained in two cycles of measurements is taken as a mean particle size.

[0020] Examples of the nitrate include alkali metal nitrates such as potassium nitrate and sodium nitrate and alkaline earth metal nitrates such as strontium nitrate.

[0021] Perchlorates and chlorates are compounds also producing both the oxidizing action and the combustion enhancing action. The oxidizing action means the action that efficiently advances combustion by generating oxygen during combustion and decreases the generation amount of toxic gases such as ammonia and carbon monoxide. On the other hand, the combustion enhancing action means the action that improves the ignition ability of the gas generating composition or increases the burning rate.

[0022] At least one selected from among ammonium perchlorate, potassium perchlorate, sodium perchlorate, potassium chlorate, and sodium chlorate can be used as the perchlorates and chlorates.

[0023] Examples of the binder include at least one selected from among carboxymethyl cellulose, carboxymethyl cellulose sodium salt, carboxymethyl cellulose potassium salt, carboxymethyl cellulose ammonium salt, cellulose acetate, cellulose acetate butyrate, methyl cellulose, ethyl cellulose, hydroxyethyl cellulose, ethylhydroxyethyl cellulose, hydroxypropyl cellulose, carboxymethylethyl cellulose, microcrystalline cellulose, polyacrylamide, polyacrylamide amino compound, polyacryl hydrazide, acrylamide - acrylic acid metal salt copolymers, polyacrylamide - polyacrylic acid ester compound copolymers, polyvinyl alcohol, acrylic rubber, guar gum, starch, and silicone.

[0024] Examples of the additive include at least one selected from among copper (for example, electrolytic copper powder), metal oxides such as copper oxide, iron oxide, zinc oxide, cobalt oxide, manganese oxide, molybdenum oxide, nickel oxide, bismuth oxide, silica, and alumina, metal carbonates and basic metal carbonates such as cobalt carbonate, calcium carbonate, basic zinc carbonate, and basic copper carbonate, complex compounds of metal oxides or hydroxides such as Japanese acid clay, kaolin, talc, bentonite, deatomaceous earth, and hydrotalcite, aluminum hydroxide, magnesium hydroxide, metallic acid salts such as sodium silicate, mica molybdenic acid salt, cobalt molybdate, and ammonium molybdate, molybdenum disulfide, calcium stearate, silicon nitride, and silicon carbide.

[0025] No specific limitation is placed on the contents of components other than the rare earth compound. For example, they can be selected within the range identical to that of an additive selected from among organic compounds as fuels, oxygen-containing oxidizing agents, binders, metal oxide, and metal carbonates as described in JP-A No. 2005-126262.

[0026] The gas generating composition in accordance with the present invention can be molded to any desired shape such as a single-perforated cylindrical shape, a porous cylindrical shape, or a pellet.

[0027] Such a molded article can be manufactured by adding water or an organic solvent to the gas generating composition, mixing them and extruding (in the case of a molded article having a single-perforated cylindrical shape or a porous cylindrical shape) or by compression-molding (by using a palletizer (in the case of molded article in the form of a pellet)). In a molded article having a single-perforated cylindrical shape or a porous cylindrical shape, the hole can be either of a through hole which pierces in the longitudinal direction or a recess which does not pierce.

[0028] The gas generating composition in accordance with the present invention or a molded article obtained therefrom can be applied, for example, to an airbag inflator of a driver side, an airbag inflator for a passenger side next to a driver, a side airbag inflator, an inflatable curtain inflator, a knee bolster inflator, an inflatable seat belt inflator, a tubular system inflator, and a pretensioner gas generator of various vehicles.

[0029] The inflator using the gas generating composition in accordance with the present invention or a molded article obtained therefrom may be of a pyrotechnic type in which gas is supplied only from the gas generating agent, or of a hybrid type, gas is supplied from both the gas generating agent and a compressed gas such as argon.

[0030] Furthermore, the gas generating composition in accordance with the present invention or a molded article obtained therefrom can be also used as an ignition agent called an enhancer agent (or booster) for transmitting the energy of a detonator or squib to the gas generating agent.

[0031] When a gas generating agent burns during the actuation of the airbag gas generator, a mist (solid components, such as a metal component, included in the gas generating agent that are generated by combustion of the gas generating agent) is generated. If the generated amount of mist is large, the filter is heavily damaged and the mist that passed through the filter flows into the air bag. When this problem is solved by increasing the filter thickness (or increasing the bulk density thereof), the weight of the entire gas generator is increased and the demand for weight reduction cannot be met.

[0032] In the gas generating composition in accordance with the present invention, due to the action of the light rare earth compound that is a component thereof, mist generation is made difficult and the generated mist can be caused to remain inside the gas generator as a slag (residue) (the slag is a mist that was retained and solidified inside the gas generator, without passing through the filter). If the generation of mist is thus inhibited and the mist is caused to remain as the slag, the filter is prevented from being damaged by the mist, and the mist does not flow through the filter into the airbag. Therefore, the filter thickness or bulk density can be decreased. As a result, the air bag gas generator employing the gas generating composition in accordance with the present invention can be reduced in weight.

Examples

[0033] The present invention will be described below in greater detail based on Examples, but the present invention is not limited thereto.

Examples and Comparative Examples

[0034] A total of 5000 g of the components shown in Table 1 and 737 g of water were charged into a mixer and mixed. The mixture was extruded with an extruder, cut, and dried to obtain a gas generating composition in the form of a single-perforated pellet having an outer diameter of 3.8 mm, an inner diameter of 1.1 mm, and a length of 4.1 mm.

(Composition of generated gas)

[0035] A total of 2 g of the gas generating composition (powdered) including the components shown in Table 1 was used and molded to obtain a strand. The strand was attached to a tightly closed cylinder having an inner capacity of one liter, and the atmosphere inside the cylinder was replaced with nitrogen. Then, the inside of the cylinder was pressurized up to 6860 kPa with nitrogen, and the strand was ignited by passing an electric current via a nichrome wire to cause the complete combustion. In about twenty seconds after the electric current was passed, the combustion gas was sampled into a gas sampling bag, and the concentrations of NO, CO, and NH₃ (ppm; mass standard) was analyzed with a detection tube.

(Evaluation of slag state)

[0036] A total of 2 g of the gas generating composition (powdered) including the components shown in Table 1 was used and molded to obtain a strand. The strand was attached to tightly closed cylinder having an inner capacity of one liter, and the atmosphere inside the cylinder was replaced with nitrogen. Then, the inside of the cylinder was pressurized up to 6860 kPa with nitrogen, and the strand was ignited by passing an electric current via a nichrome wire to cause complete combustion. Upon completion of combustion, the combustion residue (slag) was sampled and the state thereof was evaluated according to the following criteria.

○ : has a lump-like shape and is not fractured when pressed with a finger.

△ : has a lump-like shape, but is fractured when pressed with a finger.

× : has a powder shape.

(Measurement of slag amount)

[0037] The slag remaining inside the tightly sealed cylinder after the test for evaluating the slag state was sampled and sieved via a sieve having a mesh size of 3.3 mm. The mass of the slag remaining on the sieve was measured. A large amount of the slag remaining on the sieve means that the amount of mist that came into contact with the filter and passed therethrough is small.

(Detailed description of components shown in Tables 1, 2)

[0038] La(OH)₃: manufactured by Taiyo Koko Co., Ltd., lanthanum hydroxide - 100.

Nd (OH)₃: manufactured by Taiyo Koko Co., Ltd., neodymium hydroxide - 98.

EP 1 816 113 A1

La(NO₃)₃[La(NO₃)₃·6H₂O]: Kohnan Muki Ltd., lanthanum nitrate hexahydrate.

Cu: electrolytic copper powder, manufactured by Nikko Materials Co., Ltd., #6.

Glass powder: phosphate glass [P₂O₅ (54 to 56 mass%), Al₂O₃ (9 to 11 mass%), Na₂O (19 to 21 mass%), K₂O (14 to 16 mass%), softening point about 400°C.

5

GN: guanidine nitrate.

BCN: basic copper nitrate.

CeO₂: particle size 0.6 μm.

Nd₂O₃: particle size 6 μm.

10 La₂O₃: particle size 6 μm.

Pr₆O₁₁: particle size 15 μm.

La(OH)₃: particle size 1.2 μm.

Nd(OH)₃: particle size 1 μm

15

20

25

30

35

40

45

50

55

EP 1 816 113 A1

Table 1

		Gas generating composition (mass%)					Composition of generated gas (ppm)			Slag state (g)
		GN	BCN	CMCNa	Al (OH) ₃	Light rare earth compound-additive	NO	CO	NH ₃	
Example	1	41.20	49.80	5.00	-	La(OH) ₃ (4.00)	200	350	5	○
	2	39.00	48.00	5.00	-	La(OH) ₃ (8.00)	210	300	6	○
	3	37.00	46.00	5.00	-	La(OH) ₃ (12.00)	150	270	11	○
	4	42.50	50.50	5.00	-	La(OH) ₃ (2.00)	80	370	7	○
	5	43.80	49.20	5.00	-	La(NO ₃) ₃ (2.00)	50	450	6	○
	6	44.00	47.00	5.00	-	La(NO ₃) ₃ (4.00)	80	410	5	○
	7	44.50	42.50	5.00	-	La(NO ₃) ₃ (8.00)	55	420	5	○
	8	42.80	48.20	5.00	-	La(OH) ₃ (2.00)/ La (NO ₃) ₃ (2.00)	50	400	7	○
	9	41.20	46.80	5.00	-	La(OH) ₃ (500)/ La (NO ₃) ₃ (2.00)	60	390	4	○
	10	41.50	44.50	5.00	-	La(OH) ₃ (5.00)/ La (NO ₃) ₃ (4.00)	60	380	6	○
	11	31.50	41.50	5.00	4.00	La(OH) ₃ (3.00)	75	300	5	Δ
	12	36.00	45.00	5.00	4.00	La(OH) ₃ (10.00)	125	180	7	Δ
	13	31.00	41.00	5.00	-	La(OH) ₃ (8.00)/ Cu (15.00)	150	210	9	○
	14	34.50	43.50	5.00	-	La(OH) ₃ (12.00)/ Cu (5.00)	110	300	13	○
	15	41.20	49.80	5.00	-	Nd(OH) ₃ (4.00)	85	400	13	○
	16	39.00	48.00	5.00	-	Nd(OH) ₃ (8.00)	65	360	11	○
	17	37.00	46.00	5.00	-	Nd(OH) ₃ (12.00)	150	240	8	○

(continued)

		Gas generating composition (mass%)					Composition of generated gas (ppm)			Slag state (g)
		GN	BCN	CMCNa	Al (OH) ₃	Light rare earth compound-additive	NO	CO	NH ₃	
Comparative Example	1	40.71	49.29	5.00	5.00	-	55	340	6	×
	2	40.71	49.29	5.00	4.00	Glass powder (1.00)	60	370	11	×

Table 2

		Gas generating composition (mass%)					Composition of generated gas (ppm)			Slag amount (g)
		GN	BCN	CMCNa	Al (OH) ₃	Light rare earth compound - additive	NO	CO	NH ₃	
Embodiment 18		37.00	46.00	5.00	-	La(OH) ₃ (12.00)	4	73	33	8.55
Embodiment 19		34.50	43.50	5.00	-	La(OH) ₃ (12.00)/Cu (5.00)	3	60	29	10.33
Comparative Example 3		43.22	46.78	3.00	6.00	Glass powder (1.00)	7	60	9	2.92

[0039] As is clear from Tables 1 and 2, with the gas generating composition of the Examples, generation of NO and the like was suppressed, and a solid-lump-like slag was formed. Because the mist thus remained in the form of solid slag, the problems associated with the filter being damaged by the mist and the mist passing through the filter can be resolved. A contribution is also made to the decrease in the weight of gas generator because the thickness or bulk density of the filter can be reduced.

[0040] With the gas generating composition of the Comparative Examples, the slag remains in the powdered form. Therefore, the amount of mist that came into contact with the filter and passed therethrough was larger than that in the case of the Examples, provided that the same amount of mist was generated.

[0041] The invention thus described, it will be obvious that the same may be varied in many ways. Such variations are not to be regarded as a departure from the spirit and scope of the invention, and all such modifications as would be obvious to one skilled in the art are intended to be included within the scope of the following claims.

Claims

1. A gas generating composition comprising a light rare earth compound.
2. The gas generating composition according to claim 1, wherein the light rare earth compound is a compound of a rare earth element selected from the group consisting of scandium, yttrium, lanthanum, cerium, praseodymium, and neodymium.
3. The gas generating composition according to claim 1 or 2, wherein the light rare earth compound is selected from the group consisting of oxides, hydroxides, halogenides, nitrates, sulfates, acetates, phosphates, and carbonates of rare earth elements.

EP 1 816 113 A1

4. The gas generating composition according to any one of claims 1 to 3, wherein a mean particle size of the light rare earth compound is within a range of 0.5 to 500 μm .

5

10

15

20

25

30

35

40

45

50

55



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 07 00 0356

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IPC)
X	EP 0 952 131 A1 (NIPPON KAYAKU KK [JP]; KOBE STEEL LTD [JP]) 27 October 1999 (1999-10-27) * page 9, line 12 - line 39 * * paragraph [0081]; claims; examples * -----	1-4	INV. C06D5/06 C06B23/00
X	US 5 035 757 A (POOLE DONALD R [US]) 30 July 1991 (1991-07-30) * column 4, line 19 - line 64 * * column 6, line 10 - line 26; claim 1 * -----	1-4	
X	WO 00/64839 A2 (ATLANTIC RES CORP [US]) 2 November 2000 (2000-11-02) * page 8, line 15 - page 9, line 20; claims * -----	1-4	
X	US 6 328 906 B1 (LUNDSTROM NORMAN H [US] ET AL) 11 December 2001 (2001-12-11) * column 7, line 14 - line 21; claims * -----	1-4	
X	WO 01/34516 A (PRIMEX AEROSPACE COMPANY [US]; ITALIANE JOHN R [US]; STYNER JAMES M [U]) 17 May 2001 (2001-05-17) * page 3, line 8 - line 18; claim 7 * -----	1-4	TECHNICAL FIELDS SEARCHED (IPC) C06B C06D
The present search report has been drawn up for all claims			
Place of search The Hague		Date of completion of the search 31 May 2007	Examiner Schut, Robert
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

4
EPO FORM 1503 03.82 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 07 00 0356

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

31-05-2007

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
EP 0952131	A1	27-10-1999	WO	9829361 A1	09-07-1998
			US	6416599 B1	09-07-2002

US 5035757	A	30-07-1991	AU	629512 B2	01-10-1992
			AU	8580991 A	30-04-1992
			CA	2052966 A1	26-04-1992
			DE	69106667 D1	23-02-1995
			DE	69106667 T2	24-05-1995
			EP	0482852 A1	29-04-1992
			JP	2609385 B2	14-05-1997
			JP	4265292 A	21-09-1992

WO 0064839	A2	02-11-2000	US	6277221 B1	21-08-2001

US 6328906	B1	11-12-2001	US	6435552 B1	20-08-2002

WO 0134516	A	17-05-2001	AU	1758201 A	06-06-2001
			JP	2003525106 T	26-08-2003

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- JP 2003525106 A [0004] [0006]
- JP 2005126262 A [0004] [0006] [0025]