



(86) Date de dépôt PCT/PCT Filing Date: 2013/06/28
(87) Date publication PCT/PCT Publication Date: 2014/01/03
(85) Entrée phase nationale/National Entry: 2014/12/29
(86) N° demande PCT/PCT Application No.: ES 2013/070442
(87) N° publication PCT/PCT Publication No.: 2014/001595
(30) Priorité/Priority: 2012/06/29 (EP12382262.9)

(51) Cl.Int./Int.Cl. *B01J 23/00* (2006.01),
B01J 23/08 (2006.01), *B01J 23/62* (2006.01),
B01J 35/10 (2006.01), *B01J 37/02* (2006.01),
B01J 37/03 (2006.01), *B01J 37/08* (2006.01),
B01J 37/18 (2006.01), *C07C 29/00* (2006.01),
C07C 31/02 (2006.01), *C07C 31/12* (2006.01)

(71) Demandeur/Applicant:
ABENGOA BIOENERGIA NUEVAS TECNOLOGIAS, S.
A., ES

(72) Inventeurs/Inventors:
ARJONA ANTOLIN, RICARDO, ES;
SANZ YAGUE, JUAN LUIS, ES;
CORMA CANOS, AVELINO, ES; ...

(54) Titre : CATALYSEUR POUR L'OBTENTION D'ALCOOLS SUPERIEURS
(54) Title: CATALYST FOR OBTAINING HIGHER ALCOHOLS

(57) Abrégé/Abstract:

The invention relates to a method for the production of catalysts of metal oxide comprising gallium, capable of synthesising higher alcohols from lower alcohols. The invention also relates to the method for the production of said catalysts.

(72) Inventeurs(suite)/Inventors(continued): DOMINE, MARCELO EDUARDO, ES

(74) Agent: BERESKIN & PARR LLP/S.E.N.C.R.L.,S.R.L.

ABSTRACT

Catalyst for obtaining higher alcohols

- 5 The present invention relates to a process for obtaining metal oxide catalysts comprising gallium which are capable of synthesising higher alcohols from lower alcohols. The process for obtaining said catalysts is also disclosed.

CATALYST FOR OBTAINING HIGHER ALCOHOLS

The present invention relates to hydrotalcite-derived catalysts that comprise gallium and a noble metal, as well as the process for obtaining them and the use thereof in reactions designed to obtain higher alcohols. Therefore, the present invention belongs to the field of catalysts designed to obtain higher alcohols.

BACKGROUND OF THE INVENTION

10

The synthesis of high-molecular-weight alcohols (containing between 4 and 8 carbon atoms) from low-molecular-weight alcohols (e.g. methanol and ethanol) has acquired considerable interest in recent years due to the potential use of these oxygenated compounds in the preparation of automotive fuels and also additives for the latter.

15

In particular, n-butanol (n-ButOH), with a worldwide production of approx. 4-5 million tons per year, is primarily used as an additive for liquid fuels, as a starting chemical reagent in the plastics industry and also as an extraction agent in the aroma and fragrance industry. N-butanol is primarily produced through the petrochemical pathway. Methods for producing n-butanol by fermentation are also widely known.

20

Alternatively, n-butanol can be obtained by means of the well-known Guerbet reaction, which makes it possible to convert a low-molecular-weight alcohol (e.g. ethanol) into a linear or branched alcohol with a higher molecular weight in the presence of a metal alkoxide dissolved in the alcohol to be transformed. The main disadvantages associated with the Guerbet reaction are: i) the production of water, which must be eliminated from the reaction medium in order to favour the formation of the desired compounds, ii) the production of carboxylic acids, and iii) the use of homogeneous catalysts, which cause both corrosion in the reactors and final separation problems.

25
30

Patent US5300695 discloses K, Na, Ba and Cs cations exchanged zeolites, amongst others, as catalysts in the condensation of low-molecular-weight alcohols, to obtain selectivities to iso-butanol of 30%-35% at a 45% methanol conversion rate. Several basic oxides containing Cu, commonly used in the production of high-molecular-weight alcohols from syn-gas (CO/H₂), have also been assayed in methanol and ethanol condensation reactions, to produce high-molecular-weight alcohols, albeit with a relatively low production of C₄ alcohols (US5387570). Another group of catalysts used are calcium-phosphate-based materials of the hydroxyapatite type (US20070255079). These catalysts have been tested in fixed-bed continuous reactors at 300°C with very short contact times. The best results were obtained for materials with a Ca/P molar ratio of 1.5-1.7, with ethanol conversion of 12% and selectivities to C₄ alcohols (primarily iso-butanol) close to 78%. Oxides of alkaline-earth metals, particularly materials based on MgO with supported transition metals, have also been used for the transformation of ethanol into n-butanol.

In recent years, numerous scientific publications and patents have appeared on the use of hydrotalcite-type materials as catalysts in alcohol condensation reactions, such as the Guerbet reaction, in both batch systems and fixed-bed continuous reactors. The studies performed with these mixed Mg-Al oxides revealed that the catalytic activity of these materials is dependent on the nature, density and strength of the basic surface sites, which, in turn, are dependent on the molar Mg/Al composition in the solid. For example, international application WO2009026510 discloses a process for synthesising n-butanol by means of a material derived from the thermal decomposition of a hydrotalcite which preferably comprises magnesium and aluminum. Moreover, WO2009097312, US20100160693 and WO2009097310 disclose materials obtained by the thermal decomposition of hydrotalcites modified by the inclusion of metal carbonates and ethylenediamine-tetraacetates, which have been developed by DU PONT as catalysts in alcohol condensation reactions operating in a fixed bed at 300°C and atmospheric pressure. The best results

under these conditions have been achieved with a material derived from Mg-Al-based hydrotalcite (containing OH⁻ as the anion), which presents high ethanol conversion ($\approx 44\%$) with moderate selectivities ($\approx 44\%$) to n-butanol. When these same materials were assayed in the catalytic conversion of ethanol into n-butanol in the presence of hydrogen in the reaction system, the yields of n-butanol obtained were significantly lower in all cases.

Given the importance of higher alcohols, new, improved catalysts are still needed for the synthesis thereof.

10

DESCRIPTION OF THE INVENTION

The present invention relates to a new metal oxide catalyst that comprises gallium and which is capable of obtaining higher alcohols from lower alcohols.

15

The invention presents the following advantages with respect to the catalysts in the state of the art:

- at a given concentration of palladium, the hydrotalcite-derived catalysts that comprise gallium in their structure provide higher yields of n-butanol than their analogues without gallium,

- moreover, they also show a greater catalytic activity (measured through the TON, Turnover Number, parameter) than catalysts that present the same concentration of Pd but do not have gallium in their structure, which means that the catalysts are more stable under the reaction conditions, performing a greater number of catalytic cycles in a given reaction time,

- a lower temperature is required in order to perform the process.

30

Therefore, one aspect of the present invention relates to a process for obtaining a catalyst (hereinafter process of the invention), which comprises the following

steps:

a) thermal decomposition of a hydrotalcite with formula $[M1_{1-(x+y)}M2_xM3_y(OH)_2][A^{m-}_{(x+y)/m} \cdot nH_2O]$ to obtain a metal oxide, wherein:

- 5 M1 is at least one bivalent metal selected from the list that comprises Mg, Zn, Cu, Co, Mn, Fe, Ni and Ca,
 M2 is at least one trivalent metal selected from the list that comprises Al, La, Fe, Cr, Mn, Co and Ni,
 M3 is trivalent Ga,
- 10 A is at least one anion selected from the list that comprises hydroxide, chloride, fluoride, bromide, iodide, nitrate, perchlorate, chlorate, bicarbonate, acetate, benzoate, methanesulfonate, p-toluenesulfonate, phenoxide, alkoxide, carbonate, sulfate, terephthalate, phosphate, hexacyanoferrate (III) and hexacyanoferrate (II),
- 15 x is a value between 0 and 0.5, preferably, x is a value between 0.1 and 0.5, and, even more preferably, between 0.1 and 0.4; y is a value between 0.00001 and 0.49, preferably between 0.00005 and 0.45, and, even more preferably, between 0.0001 and 0.4; m is an integer between 1 and 4; and n is greater than 0, preferably n is a value between 0 and 100, and, even more preferably,
- 20 between 0 and 20. n indicates the number of crystallisation water molecules and is dependent on the composition of the hydrotalcite cations.

b) addition of at least one noble metal selected from the list that comprises Pd, Ru, Rh and Re to the solid obtained in step (a).

25

“Bivalent metal” or “trivalent metal” is understood to mean a metallic cation with a +2 or +3 charge, respectively.

30 “Hydrotalcite” is understood to mean the structural family of laminar mixed hydroxides with the formula described above. The general structure of hydrotalcites is well-known to persons skilled in the art.

The term "thermal decomposition" is understood to mean a chemical decomposition or structural change caused by the action of heat. This decomposition may be total or partial, depending on whether said decomposition is performed to completion or, on the contrary, is partially
5 performed. This thermal decomposition may be performed at temperatures greater than 150°C and in the presence of an oxidising or a non-oxidising gas.

In a preferred embodiment of the process of the invention, there is a step (a') prior to (a), where the hydrotalcite is synthesised by the co-precipitation of at
10 least one M1 compound and at least one compound of a trivalent metal selected from the list that comprises M2 and M3; preferably, the hydrotalcite is obtained by the co-precipitation of M1, M2 and M3 compounds. The best results have been obtained when M3 is incorporated into the catalyst by co-precipitation simultaneously with M1 and M2. Preferably, the co-precipitation is
15 performed in the aqueous phase. The co-precipitation is preferably performed following the addition of a solution of at least one anion A selected from the list that comprises hydroxide, chloride, fluoride, bromide, iodide, nitrate, perchlorate, chlorate, bicarbonate, acetate, benzoate, methanesulfonate, p-toluenesulfonate, phenoxide, alkoxide, carbonate, sulfate, terephthalate,
20 phosphate, hexacyanoferrate (III) and hexacyanoferrate (II) to a solution of at least one M1 compound and at least one compound of a trivalent metal selected from the list that comprises M2 and M3, preferably a solution of M1, M2 and M3 compounds. This anion A may be introduced between the sheets of the resulting hydrotalcite. In order to obtain solutions of anion A, sodium and/or
25 potassium salts thereof may be used. Preferably, A is at least one anion selected from the list that comprises carbonate, bicarbonate and hydroxide. The best results are obtained when the co-precipitation is performed at a pH higher than 7, preferably between 10 and 14. In order to regulate the pH, sodium and/or potassium hydroxide are preferably used.

30

Preferably, prior to the precipitation of said compounds, there is a dissolution of at least one M1 compound and at least one compound of a trivalent metal

selected from the list that comprises M2 and M3, preferably a solution of M1, M2 and M3 compounds. Soluble M1, M2 and M3 compound is understood to mean any salt which, when in contact with a solvent, preferably water, is dissociated. Examples of soluble M1, M2 and M3 compounds may be nitrates, halides, sulfates, carboxylates and, in general, oxoacids that comprise M1, M2
5 or M3.

In a preferred embodiment of the process of the invention, M1 is Mg. Moreover, M2 is preferably Al. As regards the anion, A is preferably at least one anion
10 selected from the list that comprises CO_3^{2-} , HCO_3^- , O_2^- , OH^- , Cl^- , NO_3^{2-} , Cl^- , F^- , Br^- , I^- , ClO_4^- , CH_3COO^- , $\text{C}_6\text{H}_5\text{COO}^-$, and SO_4^{2-} ; even more preferably, CO_3^{2-} , HCO_3^- , O_2^- and OH^- .

In a preferred embodiment of the process of the invention, the thermal
15 decomposition of hydrotalcite is performed by air calcination at a temperature ranging between 250°C and 650°C, preferably between 350°C and 550°C. The thermal decomposition of hydrotalcite is preferably performed for an interval ranging between 0.5 and 48 hours, preferably between 1 and 24 hours, and, more preferably, between 1 and 6 hours. This process may be performed by
20 heating the hydrotalcite in a gaseous atmosphere and may be performed in a static oven or a calcination reactor with a controlled gas flow, the latter being the preferred system. The gas may be an oxidising gas or a non-oxidising gas. Examples of oxidising gases may include air and oxygen. Examples of non-oxidising gases may be inert gases, such as nitrogen, argon, helium and
25 reducing gases, such as, for example, carbon dioxide, hydrogen and ammonia. Preferably, the calcination is performed in the presence of oxygen, nitrogen or mixtures thereof, and, even more preferably, in the presence of oxygen and nitrogen.

30 The gels resulting from the co-precipitation as described above are filtered, washed with water and adequately dried. The presence of a hydrotalcite-type structure may be corroborated by means of X-ray diffraction analysis (XRD),

whilst the composition (quantity and type of constituent) of the hydrotalcite or the corresponding mixed oxide obtained by the thermal decomposition of the aforementioned hydrotalcite may be determined by means of inductively coupled plasma mass spectrometry (ICP-MS) and chemical analysis, amongst
5 others.

In a preferred embodiment of the process of the invention, the addition of the noble metal of step (b) is performed by wet impregnation, incipient volume impregnation or deposition-precipitation, preferably by incipient volume
10 impregnation. The incipient volume impregnation method, also called incipient wetness impregnation method, is based on the use of a minimum quantity of liquid for the impregnation, only that which is necessary to reach the maximum saturation of the corresponding solid.

15 Another embodiment of the present invention is the process as described above, where the concentration of the noble metal in the metal oxide ranges between 0.001% and 10% by weight with respect to the total metal oxide, preferably between 0.01% and 5%.

20 In a particular embodiment of the present invention, in the event that M3 has not been incorporated into the hydrotalcite in the co-precipitation step, M3 may be incorporated into the metal oxide in a step subsequent to the synthesis by means of wet impregnation, incipient volume impregnation and/or deposition-precipitation. This incorporation may be performed prior to or simultaneously
25 with the addition of at least one noble metal selected from the list that comprises Pd, Ru and Rh, preferably Pd.

At a given concentration of palladium, the hydrotalcite-derived catalysts that comprise gallium in their structure provide higher yields of n-butanol in a
30 nitrogen atmosphere than their analogues without gallium. Furthermore, they also show a higher TON than catalysts that present the same concentration of Pd but do not have gallium in their structure. This fact is an indication of the

greater stability of the catalysts of the invention under the reaction conditions.

Moreover, as may be observed in Figs. 1 and 2, the catalysts of the invention present higher selectivities to butanol at a given ethanol conversion than the
5 catalysts in the state of the art.

In a preferred embodiment of the process of the invention, M1 is Mg. Moreover, M2 is preferably Al. As regards the anion, A is preferably at least one anion selected from the list that comprises CO_3^{2-} , HCO_3^- , O_2^- , OH^- , Cl^- , NO_3^{2-} , Cl^- , F^- ,
10 Br^- , I^- , ClO_4^- , CH_3COO^- , $\text{C}_6\text{H}_5\text{COO}^-$, and SO_4^{2-} ; even more preferably, CO_3^{2-} , HCO_3^- , O_2^- and OH^- .

In a preferred embodiment of the process of the invention, the noble metal that is added in step (b) is Pd. The best yields of n-butanol have been obtained
15 when the hydrotalcites containing Ga are impregnated with Pd.

In a preferred embodiment, the process of the invention further comprises a step (c), subsequent to (b), where the product obtained in step (b) is calcined. Preferably, this calcination is calcination in an atmosphere of oxygen, nitrogen
20 or any mixture thereof. The calcination is preferably performed at a temperature ranging between 250°C and 650°C, and, even more preferably, between 350°C and 550°C. This calcination is preferably performed for an interval ranging between 0.5 and 48 hours, preferably between 1 and 24 hours, and, even more preferably, between 1 and 6 hours. This process may be performed by heating
25 the hydrotalcite in a gaseous atmosphere and may be performed in a static oven or a calcination reactor with a controlled gas flow, the latter being the preferred system. The gas may be an oxidising gas or a non-oxidising gas. Examples of oxidising gases may include air and oxygen. Examples of non-oxidising gases may be inert gases, such as nitrogen, argon, helium and
30 reducing gases, such as, for example, carbon dioxide, hydrogen and ammonia. Preferably, the calcination is performed in the presence of oxygen, nitrogen or mixtures thereof, and, even more preferably, in the presence of oxygen and

nitrogen.

In a preferred embodiment, the process of the invention further comprises a reduction step (d), subsequent to (c). During the reduction, the noble metal, which acts as one of the main active sites in the process, is reduced. The reduction is preferably performed in an H₂ atmosphere at a temperature ranging between 200°C and 500°C, even more preferably between 250°C and 450°C. This reduction is preferably performed for an interval ranging between 0.5 and 48 hours, more preferably between 1 and 24 hours, and, even more preferably, between 1 and 6 hours. The reduction takes place immediately prior to the contact step with the reagent.

Another aspect of the present invention relates to a catalyst obtained by means of the process as described above (hereinafter catalyst of the invention).

15

At a given concentration of palladium, the catalysts of the invention provide higher yields of n-butanol than their analogues without gallium. Moreover, they show a higher TON (Turnover Number) than the catalysts that present the same concentration of Pd but do not have gallium in their structure, which means that the catalysts are more stable under the reaction conditions, performing a greater number of catalytic cycles prior to the deactivation thereof. Furthermore, they require a lower temperature to perform the process for obtaining higher alcohols.

25 Another aspect of the present invention relates to the use of the catalyst of the invention to obtain C₃-C₁₅ higher alcohols, preferably C₃-C₈.

The term "C₃-C₁₅ higher alcohols" is understood to mean any linear or branched alkyl chain with at least one hydroxyl functional group which has between 3 and 15 carbon atoms. Likewise, the term "C₃-C₈ higher alcohols" is understood to mean any linear or branched alkyl chain with at least one hydroxyl functional group which has between 3 and 8 carbon atoms. Thus, the higher alcohol will

30

preferably be a C₃, C₄, C₅, C₆, C₇ or C₈. Non-limiting examples would be propanol, isopropanol, n-butanol, 2-butanol, 2-methyl-2-butanol, 3-methyl-1-butanol-1-pentanol, 2-pentanol, 3-pentanol, 2,2-dimethyl-1-propanol, 3-methyl-2-butanol, 1,5-pentanediol, 2,4-pentanediol, 2,2-dimethyl-1,3-propanediol, 1,2-
5 butanediol, 1,3-butanediol, 1,4-butanediol, 2,3-butanediol, 1-heptanol, 2-heptanol, 3-heptanol, 4-heptanol, 2-methyl-2-hexanol, 2,2-dimethyl-3-pentanol-1-octanol, 2-octanol, 3-octanol, 4-octanol, 2-ethyl-1-hexanol, 3-ethyl-1-hexanol and 2,2-dimethyl-3-hexanol. Obviously, when the reagent is a C₃, the higher alcohol obtained will be at least a C₄, preferably a C₄, C₅, C₆, C₇ or C₈.

10

In a preferred embodiment of the use of the catalyst of the invention, the higher alcohol is preferably a C₄, more preferably n-butanol.

The obtainment of these higher alcohols is preferably performed by means of a
15 process that comprises a contact step between at least one reagent selected from the list that comprises methanol, ethanol (EtOH), propanol and isopropanol, and the catalyst of the invention. Obviously, when the reagent is a C₃, the higher alcohol obtained will be at least a C₄, preferably a C₄, C₅, C₆, C₇ or C₈. Preferably, the reagent is ethanol.

20

Amongst other by-products, in the process for obtaining higher alcohols, C₃-C₂₀
higher primary alcohols, preferably C₄-C₁₂, are also obtained. Moreover, C₃-C₂₀
higher secondary alcohols, preferably C₃-C₁₁, may also be obtained. The
hydroxyl function of said higher secondary alcohols will be preferably located at
25 the C₂. C₂-C₆ aldehydes may also be obtained. In particular, the main by-products are preferably ethanal, 2-butanol, butanal, 1-hexanol, 2-hexanol, hexanal, 1-octanol, 2-octanol and octanal.

In a preferred embodiment of the process for obtaining higher alcohols, the
30 contact between the reagent and the catalyst is performed in a reactor selected from the list that comprises discontinuous reactor, continuous stirred-tank reactor, fixed-bed continuous reactor and fluidized-bed continuous reactor,

preferably a continuous reactor.

In the particular embodiment wherein the reactor is a discontinuous reactor, contact between the reagent and the catalyst is performed at a temperature
5 ranging between 50°C and 450°C, preferably between 100°C and 300°C. In this process, the weight ratio between the reagent and the catalyst is preferably between 2 and 200, preferably between 5 and 100. Moreover, it is performed for a time interval ranging between 2 minutes and 200 hours, preferably between 1 hour and 100 hours.

10

In another preferred embodiment of the process for obtaining higher alcohols, contact between the reagent and the catalyst is performed in an atmosphere of nitrogen, argon, hydrogen or any mixture thereof, preferably in a nitrogen-hydrogen atmosphere. Usually, higher selectivities to n-butanol are obtained in
15 the presence of hydrogen.

In another preferred embodiment of the process for obtaining higher alcohols, contact between the reagent and the catalyst is performed at a pressure of up to 120 bars, preferably between 20 and 80 bars.

20

Throughout the description and the claims, the word "comprises" and the variants thereof are not intended to exclude other technical characteristics, additives, components or steps. For persons skilled in the art, other objects, advantages and characteristics of the invention will arise partly from the
25 description and partly from the practise of the invention. The following examples and figures are provided for illustrative purposes, and are not intended to limit the scope of the present invention.

BRIEF DESCRIPTION OF THE FIGURES

30

Fig. 1. Shows a comparative graph of the selectivities of the Pd/HT-4 and Pd/Ga-HT-4 catalysts in an N₂ atmosphere as a function of the conversion.

S(%): Selectivity to butanol in mole %; C(%): ethanol conversion in mole %; 2: 1%Pd/HT-4 (Ex. 2); 3: 0.5%Pd/HT-4 (Ex. 3); 4: 0.25%Pd/HT-4 (Ex. 4); 7: 1%Pd/0.29%Ga-HT-4 (Ex. 7); 8: 0.50%Pd/0.29%Ga-HT-4 (Ex. 8); 9: 0.24%Pd/0.29%Ga-HT-4 (Ex. 9).

5

Fig. 2. Shows a comparative graph of the selectivities of the Pd/HT-4 and Pd/Ga-HT-4 catalysts in an N₂-H₂ atmosphere as a function of the conversion. Legend same as in Fig. 1.

10 EXAMPLES

Below we will illustrate the invention by means of assays performed by the inventors, which demonstrate the efficacy of the hydrotalcite-derived catalysts that comprise gallium in their structure in the obtainment of higher alcohols.

15

Example 1. Synthesis of the HT-4 catalyst (Mg/Al molar ratio \approx 4)

It was prepared by means of a standard co-precipitation process using two solutions. The first solution contained 36.45 g of Mg(NO₃)₂·6H₂O and 13.60 g
 20 of Al(NO₃)₃·9H₂O, dissolved in 67.79 g of Milli-Q water, with a molar concentration of Al + Mg of 1.5. The second solution contained 12.53 g of NaOH and 16.16 g of Na₂CO₃ in 89.63 g of Milli-Q water, and was used to produce the adequate precipitation of the Al and Mg species, and to set the pH of the total mixture at \approx 13. Both solutions were added, at a total flow
 25 velocity of 30 ml/h for approx. 4 h, to a container under vigorous stirring at room temperature. The gel formed was aged at room temperature for 1-2 h; thereafter, it was filtered and washed with distilled water until the carbonate was not detected in the filtered liquid (at pH \approx 7). Subsequently, the solid was dried in an oven at 60°C for 14-16 h, and a mixed oxide called HT-4 was
 30 obtained, with a Mg/Al molar ratio \approx 3.8 and a surface area (BET method) of 257 m²/g. The BET method refers to the Brunauer-Emmett-Teller isotherm method.

Example 2. Synthesis of the 1%Pd/HT-4 catalyst

It was prepared from the material prepared as described in Example 1,
5 wherein the incorporation of Pd (1.0% by weight, theoretical) into the HT-4
material was performed by means of the incipient wetness impregnation
method, using, in this case, 0.030 g of Pd(NH₃)₄Cl₂.6H₂O dissolved in 2.000
g of Milli-Q water, to impregnate 1.014 g of HT-4. Once impregnated, the
10 solid obtained was dried in an oven at 100°C for 14-16 h; thereafter, it was
calcined in air at 450°C for 3-4 h, and, subsequently, it was reduced at 350°C
in an H₂ atmosphere for 3 h prior to the catalytic application thereof. The
resulting Pd/HT-4 material, characterised by chemical analysis and ICP-MS,
contained ≈ 1.00% by weight of Pd.

15 Example 3. Synthesis of the 0.5%Pd/HT-4 catalyst

It was prepared from the material prepared as described in Example 1,
wherein the incorporation of Pd (0.5% by weight, theoretical) into the HT-4
material was performed by means of the incipient wetness impregnation
20 method, using, in this case, 0.015 g of Pd(NH₃)₄Cl₂.6H₂O dissolved in 2.000
g of Milli-Q water, to impregnate 1.023 g of HT-4. Once impregnated, the
solid obtained was dried in an oven at 100°C for 14-16 h; thereafter, it was
calcined in air at 450°C for 3-4 h, and, subsequently, it was reduced at 350°C
in an H₂ atmosphere for 3 h prior to the catalytic application thereof. The
25 resulting Pd/HT-4 material, characterised by chemical analysis and ICP-MS,
contained ≈ 0.50% by weight of Pd.

Example 4. Synthesis of the 0.25%Pd/HT-4 catalyst

30 It was prepared from the material prepared as described in Example 1,
wherein the incorporation of Pd (0.3% by weight, theoretical) into the HT-4
material was performed by means of the incipient wetness impregnation

method, using, in this case, 0.008 g of $\text{Pd}(\text{NH}_3)_4\text{Cl}_2 \cdot 6\text{H}_2\text{O}$ dissolved in 2.000 g of Milli-Q water, to impregnate 1.023 g of HT-4. Once impregnated, the solid obtained was dried in an oven at 100°C for 14-16 h; thereafter, it was calcined in air at 450°C for 3-4 h, and, subsequently, it was reduced at 350°C in an H_2 atmosphere for 3 h prior to the catalytic application thereof. The resulting Pd/HT-4 material, characterised by chemical analysis and ICP-MS, contained $\approx 0.25\%$ by weight of Pd.

Example 5. Synthesis of the 0.80%Pt/HT-4 catalyst

10

It was prepared from the HT-4 material prepared as described in Example 1, wherein the incorporation of Pt (1.0% by weight, theoretical) into the HT-4 material was performed by means of the incipient wetness impregnation method, using 0.025 g of $\text{H}_2\text{Cl}_6\text{Pt} \cdot 6\text{H}_2\text{O}$ dissolved in 2.000 g of Milli-Q water, to impregnate 1.025 g of HT-4. Once impregnated, the solid obtained was dried in an oven at 100°C for 14-16 h; thereafter, it was calcined in air at 450°C for 3-4 h, and, subsequently, it was reduced at 350°C in an H_2 atmosphere for 3 h prior to the catalytic application thereof. The resulting Pt/HT-4 material, characterised by chemical analysis and ICP-MS, contained $\approx 0.80\%$ by weight of Pt.

20

Example 6. Synthesis of the 0.29%Ga-HT-4 catalyst

It was prepared by means of a standard co-precipitation process using two solutions. The first solution contained 29.89 g of $\text{Mg}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$, 10.90 g of $\text{Al}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$ and 0.06 g of $\text{Ga}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$, dissolved in 55.18 g of Milli-Q water, with a molar concentration of (Al + Mg + Ga) of 1.5. The second solution contained 12.52 g of NaOH and 10.52 g of Na_2CO_3 in 72.60 g of Milli-Q water, and was used to produce the adequate precipitation of the Mg, Al and Ga species, and to set the pH of the total mixture at ≈ 13 . Both solutions were added, at a total flow velocity of 30 ml/h for approximately 4 h, to a container under vigorous stirring at room temperature. The gel formed

30

was aged at room temperature for 1-2 h; thereafter, it was filtered and washed with distilled water until the carbonate was not detected in the filtered liquid (at pH \approx 7). Subsequently, the solid was dried in an oven at 60°C for 14-16 h. The hydrotalcite (Ga-HT-4) obtained was calcined in air at 450°C for 3-4 h, to obtain a mixed oxide with a Mg/Al molar ratio \approx 3.8, a Ga content of 0.29% by weight (measured by chemical analysis and ICP-MS), and a surface area (BET method) of 262 m²/g.

Example 7. Synthesis of the 1%Pd/0.29%Ga-HT-4 catalyst

10

It was prepared from the material prepared as described in Example 6, wherein the incorporation of Pd (1.0% by weight, theoretical) into the Ga-HT-4 material was performed by means of the incipient wetness impregnation method, using, in this case, 0.030 g of Pd(NH₃)₄Cl₂.6H₂O dissolved in 1.700 g of Milli-Q water, to impregnate 1.100 g of 0.29%Ga-HT-4. Once impregnated, the solid obtained was dried in an oven at 100°C for 14-16 h; thereafter, it was calcined in air at 450°C for 3-4 h, and, subsequently, it was reduced at 350°C in an H₂ atmosphere for 3 h prior to the catalytic application thereof. The resulting Pd/0.29%Ga-HT-4 material, characterised by chemical analysis and ICP-MS, contained \approx 1.00% by weight of Pd.

20

Example 8. Synthesis of the 0.50%Pd/0.29%Ga-HT-4 catalyst

It was prepared from the material prepared as described in Example 6, wherein the incorporation of Pd (0.5% by weight, theoretical) into the Ga-HT-4 material was performed by means of the incipient wetness impregnation method, using, in this case, 0.016 g of Pd(NH₃)₄Cl₂.6H₂O dissolved in 1.800 g of Milli-Q water, to impregnate 1.129 g of 0.29%Ga-HT-4. Once impregnated, the solid obtained was dried in an oven at 100°C for 14-16 h; thereafter, it was calcined in air at 450°C for 3-4 h, and, subsequently, it was reduced at 350°C in an H₂ atmosphere for 3 h prior to the catalytic application thereof. The resulting Pd/0.29%Ga-HT-4 material, characterised by chemical analysis and

30

ICP-MS, contained $\approx 0.50\%$ by weight of Pd.

Example 9. Synthesis of the 0.24%Pd/0.29%Ga-HT-4 catalyst

5 It was prepared from the material prepared as described in Example 6,
wherein the incorporation of Pd (0.3% by weight, theoretical) into the Ga-HT-
4 material was performed by means of the incipient wetness impregnation
method, using, in this case, 0.008 g of $\text{Pd}(\text{NH}_3)_4\text{Cl}_2 \cdot 6\text{H}_2\text{O}$ dissolved in 1.800
10 g of Milli-Q water, to impregnate 1.011 g of 0.29%Ga-HT-4. Once
impregnated, the solid obtained was dried in an oven at 100°C for 14-16 h;
thereafter, it was calcined in air at 450°C for 3-4 h, and, subsequently, it was
reduced at 350°C in an H_2 atmosphere for 3 h prior to the catalytic
application thereof. The resulting Pd/0.29%Ga-HT-4 material, characterised
by chemical analysis and ICP-MS, contained $\approx 0.24\%$ by weight of Pd.

15

Example 10. Synthesis of the 1.06Pt/0.29%Ga-HT-4 catalyst

It was prepared from the material prepared as described in Example 6, wherein
the incorporation of Pt (1.0% by weight, theoretical) into the Ga-HT-4 material
20 was performed by means of the incipient wetness impregnation method, using,
in this case, 0.045 g of $\text{H}_2\text{Cl}_6\text{Pt} \cdot 6\text{H}_2\text{O}$ dissolved in 1.700 g of Milli-Q water, to
impregnate 1.003 g of Ga-HT-4. Once impregnated, the solid obtained was
dried in an oven at 100°C for 14-16 h; thereafter, it was calcined in air at 450°C
for 3-4 h, and, subsequently, it was reduced at 350°C in an H_2 atmosphere for 3
25 h prior to the catalytic application thereof. The resulting Pt/0.29%Ga-HT-4
material, characterised by chemical analysis and ICP-MS, contained $\approx 1.06\%$
by weight of Pt.

Example 11. Synthesis of the 0.74%Pd/0.48%Ga/HT-4 catalyst

30

It was prepared from the HT-4 material prepared as described in Example 1,
wherein the incorporation of Ga (0.7% by weight, theoretical) into the HT-4

material was performed by means of the incipient wetness impregnation method, using, in this case, 0.026 g of $\text{Ga}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$ dissolved in 1.920 g of Milli-Q water, to impregnate 1.000 g of HT-4. Once impregnated, the solid obtained was dried in an oven at 100°C for 14-16 h. The incorporation of Pd (1.0% by weight, theoretical) into the solid obtained was performed by means of the incipient wetness impregnation method, using, in this case, 0.095 g of $\text{Pd}(\text{NH}_3)_4\text{Cl}_2 \cdot 6\text{H}_2\text{O}$ dissolved in 1.400 g of Milli-Q water, to impregnate 1.540 g of the solid obtained in the first impregnation. Once impregnated, the final solid was dried in an oven at 100°C for 14-16 h; thereafter, it was calcined in air at 450°C for 3-4 h, and, subsequently, it was reduced at 350°C in an H_2 atmosphere for 3 h prior to the catalytic application thereof. The resulting Pd/Ga/HT-4 material, characterised by chemical analysis and ICP-MS, contained $\approx 0.74\%$ by weight of Pd and $\approx 0.48\%$ by weight of Ga.

15 **Example 12. Synthesis of the 0.74%Pd/0.29%Ga/HT-4 catalyst**

It was prepared from the HT-4 material prepared as described in Example 1, wherein the incorporation of Ga (0.4% by weight, theoretical) into the HT-4 material was performed by means of the incipient wetness impregnation method, using, in this case, 0.015 g of $\text{Ga}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$ dissolved in 1.920 g of Milli-Q water, to impregnate 1.000 g of HT-4. Once impregnated, the solid obtained was dried in an oven at 100°C for 14-16 h. The incorporation of Pd (1.0% by weight, theoretical) into the solid obtained was performed by means of the incipient wetness impregnation method, using, in this case, 0.095 g of $\text{Pd}(\text{NH}_3)_4\text{Cl}_2 \cdot 6\text{H}_2\text{O}$ dissolved in 1.500 g of Milli-Q water, to impregnate 1.540 g of the solid obtained in the first impregnation. Once impregnated, the final solid was dried in an oven at 100°C for 14-16 h; thereafter, it was calcined in air at 450°C for 3-4 h, and, subsequently, it was reduced at 350°C in an H_2 atmosphere for 3 h prior to the catalytic application thereof. The resulting Pd/Ga/HT-4 material, characterised by chemical analysis and ICP-MS, contained $\approx 0.74\%$ by weight of Pd and $\approx 0.29\%$ by weight of Ga.

Example 13. Synthesis of the 5.0%Cu-HT-4 catalyst

This catalyst was synthesised to illustrate hydrotalcite-type catalysts containing Cu, such as those cited in application WO2009026523. Various catalysts were
5 synthesised with different concentrations of Cu, and the catalyst that provided the best results, in terms of selectivity and conversion, was selected in order to be compared to the catalysts of the invention.

It was prepared by means of a standard co-precipitation process using two
10 solutions. The first solution contained 28.73 g of $\text{Mg}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$, 10.50 g of $\text{Al}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$ and 1.20 g of $\text{Cu}(\text{NO}_3)_2 \cdot 3\text{H}_2\text{O}$, dissolved in 56.25 g of Milli-Q water, with a molar concentration of (Al + Mg + Cu) of 1.5. The second solution contained 12.72 g of NaOH and 10.25 g of Na_2CO_3 in 73.71 g of Milli-Q water, and was used to produce the adequate precipitation of the Mg,
15 Al and Cu species, and to set the pH of the total mixture at ≈ 13 . Both solutions were added (total flow velocity = 30 ml/h for approximately 4 h) to a container under vigorous stirring at room temperature. The gel formed was aged at room temperature for 1-2 h; thereafter, it was filtered and washed with distilled water until the carbonate was not detected in the filtered liquid
20 (at pH ≈ 7). Subsequently, the solid was dried in an oven at 60°C for 14-16 h. The hydrotalcite (Cu-HT-4) obtained was calcined in air at 450°C for 3-4 h, to obtain a mixed oxide with a Mg/Al molar ratio ≈ 3.8 , a Cu content of $\approx 5.0\%$ by weight, characterised by chemical analysis and ICP-MS.

25 Example 14. Synthesis of the 3.5%Co-HT-4 catalyst

This catalyst was synthesised to illustrate hydrotalcite-type catalysts containing Co, such as those cited in application US20100160693. Various catalysts were
30 synthesised with different concentrations of Co, and the catalyst that provided the best results, in terms of selectivity and conversion, was selected in order to be compared to the catalysts of the invention.

It was prepared by means of a standard co-precipitation process using two solutions. The first solution contained 28.82 g of $\text{Mg}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$, 14.05 g of $\text{Al}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$ and 1.17 g of $\text{Co}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ dissolved in 58.54 g of Milli-Q water, with a molar concentration of (Al + Mg + Cu) of 1.5. The second
5 solution contained 13.81 g of NaOH and 10.87 g of Na_2CO_3 in 77.91 g of Milli-Q water, and was used to produce the adequate precipitation of the Mg, Al and Cu species, and to set the pH of the total mixture at ≈ 13 . Both solutions were added (total flow velocity = 30 ml/h for approximately 4 h) to a container under vigorous stirring at room temperature. The gel formed was
10 aged at room temperature for 1-2 h; thereafter, it was filtered and washed with distilled water until the carbonate was not detected in the filtered liquid (at pH ≈ 7). Subsequently, the solid was dried in an oven at 60°C for 14-16 h. The hydrotalcite (Co-HT-4) obtained was calcined in air at 450°C for 3-4 h, to obtain a mixed oxide with a Mg/Al molar ratio ≈ 3.8 , a Co content of $\approx 3.5\%$
15 by weight, characterised by chemical analysis and ICP-MS.

Example 15. Synthesis of the 2.5%Ni-HT-4 catalyst

This catalyst was synthesised to illustrate hydrotalcite-type catalysts containing
20 Ni, such as those cited in application US20100160693. Various catalysts were synthesised with different concentrations of Ni, and the catalyst that provided the best results, in terms of selectivity and conversion, was selected in order to be compared to the catalysts of the invention.

25 It was prepared by means of a standard co-precipitation process using two solutions. The first solution contained 29.71 g of $\text{Mg}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$, 10.81 g of $\text{Al}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$ and 0.78 g of $\text{Ni}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$, dissolved in 56.54 g of Milli-Q water, with a molar concentration of (Al + Mg + Cu) of 1.5. The second solution contained 12.85 g of NaOH and 10.37 g of Na_2CO_3 in 74.33 g of Milli-Q water,
30 and was used to produce the adequate precipitation of the Mg, Al and Ni species, and to set the pH of the total mixture at ≈ 13 . Both solutions were added (total flow velocity = 30 ml/h for approximately 4 h) to a container under

vigorous stirring at room temperature. The gel formed was aged at room temperature for 1-2 h; thereafter, it was filtered and washed with distilled water until the carbonate was not detected in the filtered liquid (at pH \approx 7). Subsequently, the solid was dried in an oven at 60°C for 14-16 h. The hydrotalcite (Ni-HT-4) obtained was calcined in air at 450°C for 3-4 h, to obtain a mixed oxide with a Mg/Al molar ratio \approx 3.8, a Co content of \approx 2.5% by weight, characterised by chemical analysis and ICP-MS.

Example 16. Comparative catalytic activity of the catalysts of Examples 1, 2, 5, 7 and 13-15 under N₂ atmosphere

3500 mg of ethanol and 200 mg of one of the catalytic materials of Examples 1, 2, 5, 7 and 13-15 were introduced into a 12-ml stainless steel autoclave reactor, with a Teflon-coated inside and a magnetic stirrer. The reactor was hermetically closed, and the system contained a connector to a pressure meter (manometer), another connector for the loading of gases and a third outlet which made it possible to take samples at different time intervals. The reactor was initially pressurised with 24 bars of N₂, and heated to 200°C under continuous stirring, until the total system pressure reached approx. 30 bars (reaction time = 0). Liquid samples (\approx 50 μ l) were taken at different time intervals until 17-24 hours of reaction. The samples were filtered and diluted in a 2% by weight of chlorobenzene in acetonitrile standard solution, and analysed by means of gas chromatography in a GC-3900 Varian equipped with an FID detector and a 60-m TRB-624 capillary column; the ethanol conversion, in molar percentage (EtOH conv.), was calculated from the composition of the mixture obtained:

$$\text{(initial moles of reagent - final moles of reagent) / (initial moles of reagent * 100)}$$

The selectivities to n-butanol obtained were also calculated in molar percentage (Select. n-ButOH):

(moles of n-butanol / moles of total products) * 100

The total yield of n-butanol (Yield n-ButOH) was calculated as:

5

(EtOH conv. * Select. n-ButOH) / 100

In this manner, the following results were obtained:

Ex.	Catalyst	T (h)	EtOH conv.	Select. n-ButOH	Yield n-ButOH	TON ^a
1	HT-4	5	3.6	50.5	1.82	1
2	1.00%Pd/HT-4	5	15.5	76.9	11.9	629
5	0.80%Pt/HT-4	5	13.0	82.0	10.7	1268
7	1%Pd/0.29%Ga-HT-4	5	15.8	76.5	12.1	630
13	5.0%Cu-HT-4	5	8.3	68.8	5.92	42
14	3.5%Co-HT-4	5	1.2	76.2	0.91	8
15	2.5%Ni-HT-4	5	2.0	65.2	1.304	19

Table 1. Catalytic activity of different mixed metal oxides in the transformation of ethanol into n-butanol under nitrogen atmosphere. ^aTON = Turn Over Number in (mol/mol Pd or Pt).

5

These results show that the catalyst impregnated with Pd or Pt give better yields than the catalyst comprising co, Ni or Cu.

10 **Example 17. Comparative catalytic activity of the catalysts of Examples 2-5 and 7-12 under N₂ atmosphere**

3500 mg of ethanol and 200 mg of one of the catalytic materials of Examples 2-5 to 7-12 were introduced into a 12-ml stainless steel autoclave reactor, with a Teflon-coated inside and a magnetic stirrer. The reactor was hermetically closed, and the system contained a connector to a pressure meter (manometer), another connector for the loading of gases and a third outlet which made it possible to take samples at different time intervals. The reactor was initially pressurised with 24 bars of N₂, and heated to 200°C under continuous stirring, until the total system pressure reaches approx. 30 bars (reaction time = 0). Liquid samples (≈ 50 µl) were taken at different time intervals until 17-24 hours of reaction. The samples were filtered and diluted in a 2% by weight of chlorobenzene in acetonitrile standard solution, and analysed by means of gas chromatography in a GC-3900 Varian equipped with

15

20

an FID detector and a 60-m TRB-624 capillary column; the ethanol conversion, in molar percentage (EtOH conv.), was calculated from the composition of the mixture obtained:

$$5 \quad (\text{initial moles of reagent} - \text{final moles of reagent}) / (\text{initial moles of reagent} * 100)$$

The selectivities to n-butanol obtained were also calculated in molar percentage (Select. n-ButOH):

10

$$(\text{moles of n-butanol} / \text{moles of total products}) * 100$$

The total yield of n-butanol (Yield n-ButOH) was calculated as:

$$15 \quad (\text{EtOH conv.} * \text{Select. n-ButOH}) / 100$$

In this manner, the following results were obtained:

Ex.	Catalyst	T (h)	EtOH conv.	Select. n-ButOH	Yield n-ButOH	TON ^a
2	1%Pd/HT-4	5	15.5	76.9	11.9	629
		17	17.2	75.8	13.0	695
3	0.5%Pd/HT-4	5	14.1	82.5	11.7	1145
		17	16.8	80.6	13.5	1359
4	0.25%Pd/HT-4	5	10.2	79.0	8.1	2073
		17	12.2	77.5	9.4	2460
5	0.80%Pt/HT-4	5	13.0	82.0	10.7	1268
		17	14.2	50.5	7.2	1385
7	1%Pd/0.29%Ga-HT-4	5	15.8	76.5	12.1	630
		17	20.4	75.5	15.4	825
8	0.5%Pd/0.29%Ga-HT-4	5	14.8	79.3	11.7	1195
		17	17.7	78.6	13.9	1435

9	0.24%Pd/0.29%Ga-HT-4	5	12.5	76.4	9.6	2539
		17	16.0	74.8	12.0	3237
10	1.06%Pt/0.29%Ga-HT-4	5	12.0	69.0	8.3	881
		17	13.8	56.6	7.8	1013
11	0.74%Pd/0.48%Ga/HT-4	5	14.5	65.0	9.4	829
		17	18.1	62.1	11.2	1034
12	0.74%Pd/0.29%Ga/HT-4	5	13.0	63.0	8.2	743
		17	16.3	60.0	9.8	931

Table 2. Catalytic activity of different mixed metal oxides in the transformation of ethanol into n-butanol under nitrogen atmosphere. ^aTON = Turn Over Number in (mol / mol Pd or Pt).

- 5 These results show that, at a given concentration of palladium, the hydrotalcite-derived catalysts that comprise gallium in their structure provide higher yields of n-butanol under nitrogen atmosphere than their analogues without gallium. Moreover, they also show a higher TON than the catalysts possessing the same concentration of Pd but without gallium in their structure. This fact is an
10 indication of the greater stability of the catalysts of the invention under the reaction conditions.

Moreover, as can be observed in Fig. 1, the catalysts of the invention show higher selectivities to butanol under N₂ atmosphere at a given ethanol
15 conversion value than the catalysts in the state of the art.

Another fact worth mentioning is that the catalysts of the invention make it possible to achieve lower concentrations of Pd whilst maintaining high yields of n-butanol, as compared to the catalysts in the state of the art.

20

Example 18. Comparative catalytic activity of the catalysts of Examples 2-5 and 7-12 under N₂-H₂ atmosphere

3500 mg of ethanol and 200 mg of one of the catalytic materials of Examples 2-

5 and 7-12 were introduced into a 12-ml stainless steel autoclave reactor, with a Teflon-coated inside and a magnetic stirrer. The reactor was hermetically closed, and the system contained a connector to a pressure meter (manometer), another connector for the loading of gases and a third outlet which made it possible to take samples at different time intervals. The reactor was initially pressurised with 10 bars of hydrogen, and, thereafter, was taken to a total pressure of 24 bars by adding N₂. Subsequently, it was heated to 200°C under constant stirring, until the total system pressure reaches approx. 32-33 bars (reaction time = 0). Liquid samples (≈ 50 µl) were taken at different time intervals until 17-24 hours of reaction. The samples were filtered and diluted in a 2% (W/W) of chlorobenzene in acetonitrile standard solution, and analysed by means of gas chromatography in a GC-3900 Varian equipped with an FID detector and a 60-m TRB-624 capillary column; the ethanol conversion, in molar percentage (EtOH conv.), was calculated from the composition of the mixture obtained:

$$\text{(initial moles of reagent - final moles of reagent) / (initial moles of reagent * 100)}$$

The selectivities to n-butanol obtained were also calculated in molar percentage (Select. n-ButOH):

$$\text{(moles of n-butanol / moles of total products) * 100}$$

The total yield of n-butanol (Yield n-ButOH) was calculated as:

$$\text{(EtOH conv. * Select. n-ButOH) / 100}$$

In this manner, the following results were obtained:

Ex.	Catalyst	T (h)	EtOH conv.	Select. n-ButOH	Yield n-ButOH	TON ^a

2	1%Pd/HT-4	5	12.1	95.8	11.6	488
		17	13.8	83.2	11.5	560
3	0.5%Pd/HT-4	5	10.5	93.0	9.8	849
		17	12.5	93.3	11.7	1015
4	0.25%Pd/HT-4	5	7.8	96.0	7.5	1585
		17	10.0	96.0	9.6	2025
5	0.80%Pt/HT-4	5	5.0	87.0	4.4	488
		17	8.0	85.0	6.8	780
7	1%Pd/0.29%Ga-HT-4	5	11.7	90.9	10.6	472
		17	15.1	92.8	14.0	612
8	0.5%Pd/0.29%Ga-HT-4	5	11.6	94.0	10.9	937
		17	14.1	92.0	13.0	1141
9	0.24%Pd/0.29%Ga-HT-4	5	10.1	94.0	9.4	2034
		17	14.3	93.0	13.3	2888
10	1.06%Pt/0.29%Ga-HT-4	5	8	96.0	7.7	587
		17	10.4	95.0	9.9	763
11	0.74%Pd/0.48%Ga/HT-4	5	7.0	85.0	6.0	400
		17	9.7	85.1	8.3	554
12	0.74%Pd/0.29%Ga/HT-4	5	6.0	87.0	5.2	343
		17	10.8	87.6	9.5	617

Table 3. Catalytic activity of different mixed metal oxides in the transformation of ethanol into n-butanol under nitrogen and hydrogen atmosphere. ^aTON = Turn Over Number in (mol / mol Pd or Pt).

- 5 These results show that, at a given concentration of palladium, the hydrotalcite-derived catalysts that comprise gallium in their structure provide higher yields of n-butanol under nitrogen and hydrogen atmosphere than their analogues without gallium. Moreover, they also show a higher TON than the catalysts possessin the same concentration of Pd but without gallium in their structure.
- 10 This fact is an indication of the greater stability of the catalysts of the invention under the reaction conditions. On the other hand, it is worth noting that

incorporating hydrogen into the reaction mixture increases the selectivities to butanol.

Moreover, as can be observed in Fig. 2, the catalysts of the invention show
5 higher selectivities to butanol in an N₂-H₂ atmosphere at a given ethanol conversion value than the catalysts in the state of the art.

Another fact worth mentioning is that the catalysts of the invention make it
possible to achieve lower concentrations of Pd whilst maintaining high yields of
10 n-butanol, as compared to the catalysts in the state of the art.

CLAIMS

1.- Process for obtaining a catalyst, which comprises the following steps:

5 a) thermal decomposition of a hydrotalcite with the formula

$[M1_{1-(x+y)}M2_xM3_y(OH)_2][A^{m-}_{(x+y)/m} \cdot nH_2O]$, to obtain a metal oxide, wherein:

M1 is at least one bivalent metal selected from the list that comprises Mg, Zn, Cu, Co, Mn, Fe, Ni and Ca,

10 M2 is at least one trivalent metal selected from the list that comprises Al, La, Fe, Cr, Mn, Co and Ni,

M3 is trivalent Ga,

A is at least one anion selected from the list that comprises hydroxide, chloride, fluoride, bromide, iodide, nitrate, perchlorate, chlorate, bicarbonate, acetate, benzoate, methanesulfonate, p-toluenesulfonate, phenoxide, alkoxide, carbonate, sulfate, terephthalate, phosphate, hexacyanoferrate (III) and
15 hexacyanoferrate (II),

x is a value between 0 and 0.5; y is a value between 0.00001 and 0.49; m is an integer between 1 and 4; and n is greater than 0,

20 b) addition of at least one noble metal selected from the list that comprises Pd, Ru, Rh and Re to the solid obtained in step (a).

2.- The process according to the preceding claim, characterised in that it further comprises a step (a') prior to step (a), where the hydrotalcite is synthesised by
25 the co-precipitation of at least one M1 compound and at least one compound of a trivalent metal selected from the list that comprises M2 and M3; preferably, the hydrotalcite is obtained by the co-precipitation of M1, M2 and M3 compounds

30 3.- The process according to the preceding claim, wherein the co-precipitation is performed by the addition of a solution of at least one compound selected from the list that comprises carbonate, bicarbonate and hydroxide to a solution

of at least one M1 compound and at least one compound of a trivalent metal selected from the list that comprises M2 and M3, preferably to a solution of M1, M2 and M3 compounds.

- 5 4.- The process according to any of the preceding claims, wherein the thermal decomposition of step (a) is calcination in an atmosphere of oxygen, nitrogen or any mixture thereof at a temperature ranging between 250°C and 650°C, preferably between 350°C and 550°C.
- 10 5.- The process according to any of the preceding claims, wherein the addition of the noble metal of step (b) is performed by wet impregnation, incipient volume impregnation or deposition-precipitation.
- 6.- The process according to any of the preceding claims, wherein M1 is Mg.
- 15 7.- The process according to any of the preceding claims, wherein M2 is Al.
- 8.- The process according to any of the preceding claims, where A is at least one anion selected from the list that comprises CO_3^{2-} , HCO_3^- , O_2^- and OH^- .
- 20 9.- The process according to any of the preceding claims, wherein the noble metal that is added in step (b) is Pd.
- 10.- The process according to any of the preceding claims, which further comprises a step (c), subsequent to (b), where the product obtained in step (b) is calcined.
- 25 11.- The process according to the preceding claim, which further comprises a reduction step (d), subsequent to (c).
- 30 12.- A catalyst obtained by means of the process according to any of the preceding claims.

- 13.- Use of the catalyst described according to the preceding claim, to obtain C₃-C₁₅ higher alcohols.
- 5 14.- Use of the catalyst according to the preceding claim, where the higher alcohol is C₄, preferably n-butanol.

Fig. 1




Fig. 2

