



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁶ : A01N 43/88, B27K 3/50 // (A01N 43/88, 43:12)</p>	A1	<p>(11) International Publication Number: WO 99/18795</p> <p>(43) International Publication Date: 22 April 1999 (22.04.99)</p>
<p>(21) International Application Number: PCT/EP98/06495</p> <p>(22) International Filing Date: 7 October 1998 (07.10.98)</p> <p>(30) Priority Data: 97203227.0 15 October 1997 (15.10.97) EP</p> <p>(71) Applicants (for all designated States except US): JANSSEN PHARMACEUTICA N.V. [BE/BE]; Turnhoutseweg 30, B-2340 Beerse (BE). BAYER AG [DE/DE]; Konzernbereich RP-PL, D-51368 Leverkusen (DE).</p> <p>(72) Inventors; and</p> <p>(75) Inventors/Applicants (for US only): DE WITTE, Ludo, Antoinette [BE/BE]; Janssen Pharmaceutica N.V., Turnhoutseweg 30, B-2340 Beerse (BE). VALCKE, Alex, Raymond, Albert [BE/BE]; Janssen Pharmaceutica N.V., Turnhoutseweg 30, B-2340 Beerse (BE). VAN DER FLAAS, Mark, Arthur, Josepha [BE/BE]; Janssen Pharmaceutica N.V., Turnhoutseweg 30, B-2340 Beerse (BE). WILLEMS, Willy, Modest, Louisa [BE/BE]; Janssen Pharmaceutica N.V., Turnhoutseweg 30, B-2340 Beerse (BE).</p> <p>(74) Agent: QUAGHEBEUR, Luc; Janssen Pharmaceutica N.V., Patent Dept., Turnhoutseweg 30, B-2340 Beerse (BE).</p>		<p>(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>
<p>(54) Title: SYNERGISTIC COMPOSITIONS COMPRISING AN OXATHIAZINE AND A BENZOTHIOPHENE-2-CARBOXAMIDE-S,S-DIOXIDE</p>		
<p>(57) Abstract</p> <p>This invention relates to synergistic compositions of oxathiazines and benzothiophene-2-carboxamide-S,S-dioxides for use as fungicidal preservatives in the protection of materials, such as protection of wood, wood products, biodegradable materials and coatings.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakistan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		


SYNERGISTIC COMPOSITIONS COMPRISING AN OXATHIAZINE AND
A BENZOTHIOPHENE-2-CARBOXAMIDE-S,S-DIOXIDE

5 This invention relates to synergistic compositions of oxathiazines and benzothiophene-2-carboxamide-S,S-dioxides for use as fungicidal preservatives in the protection of materials, such as protection of wood, wood products, biodegradable materials and coatings.


10 It now has been found that compositions comprising particular ratios of an oxathiazine of formula (I) and a benzothiophene-2-carboxamide-S,S-dioxide of formula (II) exhibit synergistic fungicidal activity.

The present invention is concerned with compositions comprising an oxathiazine of
15 formula (I), or a salt thereof, and a benzothiophene-2-carboxamide-S,S-dioxide of formula (II), or a salt thereof, in quantities producing a mutual synergistic effect, and a carrier.

The oxathiazines of formula (I) have the following structure
20



wherein n is 0, 1 or 2; R¹ is hydrogen, C₁₋₄alkyl or benzyl; and R² represents
(a) phenyl; phenyl substituted with 1 to 3 substituents independently selected from
25 hydroxyl, halo, C₁₋₁₂alkyl, C₅₋₆cycloalkyl, trihalomethyl, phenyl, C₁₋₅alkoxy,
C₁₋₅alkylthio, tetrahydropyraniloxy, phenoxy, C₁₋₅alkylcarbonyl, phenylcarbonyl,
C₁₋₄alkylsulfinyl, C₁₋₄alkylsulfonyl, carboxy or its alkali metal salt, C₁₋₅alkyloxy-
carbonyl, C₁₋₅alkylaminocarbonyl, phenylaminocarbonyl, tolylaminocarbonyl,
morpholinocarbonyl, amino, nitro, cyano, dioxolanyl or C₁₋₄alkyloxyiminomethyl;
30 naphthyl; pyridinyl; thienyl, preferably when n is not 2; furanyl; or thienyl or furanyl
substituted with one to three substituents independently selected from C₁₋₄alkyl,
C₁₋₄alkyloxy, C₁₋₄alkylthio, halo, cyano, formyl, acetyl, benzoyl, nitro, C₁₋₄alkyloxy-
carbonyl, phenyl, phenylaminocarbonyl and C₁₋₄alkyloxyiminomethyl; or R² represents a
35 radical of formula



wherein X is oxygen or sulfur; Y is nitrogen or CH or C(C₁₋₄alkyloxy); and R³ is hydrogen or C₁₋₄alkyl.

5


Said compounds of formula (I) are described in WO-95/06043, published on 2 March 1995, as a bactericidal and fungicidal compounds useful in wood-protection. The use of said compounds for the protection of non-living materials, in particular the anti-fouling use, is described in WO-95/05739, published on 2 March 1995. WO-95/05739 also describes the antibacterial, anti-yeast, antifungal, algicidal, anti-crustacean and molluscicidal properties of said compounds of formula (I) and compositions comprising them.

10

All compounds of formula (I) can be prepared following the procedures described in US-4,569,690.

15

The benzothiophene-2-carboxamide-S,S-dioxides of formula (II) can be represented by the formula



20

wherein R⁸ represents straight-chain or branched alkyl having 1 to 20 carbon atoms, or represents in each case straight-chain or branched halogenoalkyl, cyanoalkyl, hydroxyalkyl, alkoxyalkyl or alkoxy-carbonylalkyl, each of which has 1 to 8 carbon atoms in the individual alkyl moieties, or represents straight-chain or branched alkenyl having 2 to 12 carbon atoms, or represents straight-chain or branched alkynyl having 2 to 12 carbon atoms, or represents cycloalkylalkyl or cycloalkyl, each of which has 3 to 7 carbon atoms in the cycloalkyl moiety and, in the case of cycloalkylalkyl, 1 to 6 carbon atoms in the straight-chain or branched alkyl moiety, and each of which is optionally monosubstituted to hexasubstituted in the cycloalkyl moiety by identical or different substituents, suitable cycloalkyl substituents in each case being: halogen, in each case straight-chain or branched alkyl having 1 to 4 carbon atoms or in each case straight-chain or branched halogenoalkyl having 1 to 4 carbon atoms and 1 to 9 identical or different halogen atoms; furthermore represents arylalkyl, arylalkenyl, arylalkynyl or

30

aryl, each of which has 6 or 10 carbon atoms in the aryl moiety and, in the cases of arylalkyl, arylalkenyl and arylalkynyl, up to 12 carbon atoms in the respective straight-chain or branched alkyl or alkenyl or alkynyl moiety, each of which is optionally monosubstituted to pentasubstituted in the aryl moiety by identical or different substituents, suitable aryl substituents in each case being: halogen, cyano, nitro, formylamido, in each case straight-chain or branched alkyl, alkoxy or alkylthio, each of which has 1 to 4 carbon atoms, in each case straight-chain or branched halogenoalkyl, halogenoalkoxy, halogenoalkylthio, each of which has 1 to 4 carbon atoms and 1 to 9 identical or different halogen atoms, in each case straight-chain or branched alkylcarbonyl, alkoxy carbonyl, aminocarbonyl, *N*-alkylaminocarbonyl, *N,N*-dialkylaminocarbonyl, alkylcarbonylamino, *N*-alkyl-alkylcarbonylamino, *N*-alkylformylcarbonylamino or alkoximinoalkyl, each of which has 1 to 4 carbon atoms in the individual alkyl moieties, and phenyl which is optionally monosubstituted or polysubstituted by identical or different substituents from the group consisting of halogen and/or straight-chain or branched alkyl having 1 to 4 carbon atoms; R^9 represents hydrogen or straight-chain or branched alkyl which has 1 to 6 carbon atoms and which is optionally monosubstituted or polysubstituted by identical or different substituents, suitable substituents being: hydroxyl, halogen, cyano, and in each case straight-chain or branched alkoxy, alkoxy carbonyl or dialkylamino, each of which has 1 to 6 carbon atoms in the individual alkyl moieties; or R^8 and R^9 together with the nitrogen atom to which they are bonded represent a saturated 5- to 7-membered heterocycle which is optionally monosubstituted or polysubstituted by identical or different substituents and which can optionally contain 1 or 2 further hetero atoms selected from the group consisting of nitrogen, oxygen and sulphur, suitable substituents in each case being: halogen, in each case straight-chain or branched alkyl, alkoxy or alkoxy carbonyl having in each case 1 to 4 carbon atoms or straight-chain or branched halogenoalkyl having 1 to 4 carbon atoms and 1 to 9 identical or different halogen atoms; and R^4 , R^5 , R^6 and R^7 independently of one another in each case represent hydrogen, halogen, cyano, nitro or in each case straight-chain or branched alkyl, alkoxy, alkylthio, halogenoalkyl, halogenoalkoxy or halogenoalkylthio each of which has 1 to 6 carbon atoms and, in the case of halogenoalkyl, halogenoalkoxy or halogenoalkylthio, 1 to 13 identical or different halogen atoms.

Said compounds of formula (II), their preparation and use in plant protection, the protection of materials and in the field of human and veterinary medicine, are described in EP-0,512,349, published on 11 November 1992.

All compounds of formula (II) can be prepared following the procedures described in EP-0,512,349.

- 5 In the foregoing definitions halo is generic to fluoro, chloro, bromo and iodo; C₁₋₄alkyl defines straight and branch chained saturated hydrocarbon radicals having from 1 to 4 carbon atoms comprising methyl, ethyl, n-propyl, 1-methylethyl, n-butyl, 1,1-dimethyl-ethyl, 1-methylpropyl, 2-methylpropyl; C₁₋₅alkyl includes C₁₋₄alkyl radicals as defined above and saturated hydrocarbon radicals having five carbon atoms, e.g. n-pentyl and
10 the branched pentyl isomers; C₁₋₆alkyl includes C₁₋₅alkyl radicals as defined above and six carbon containing homologues, e.g. n-hexyl and the branched hexyl isomers; C₁₋₁₂alkyl includes C₁₋₆alkyl and saturated hydrocarbon radicals having from 7 to 12 carbon atoms, e.g. heptyl, octyl, nonyl, decyl, undecyl and their isomers. The term alkali metal cation in particular is a sodium or potassium cation. Trihalomethyl defines a
15 methyl group being fully substituted with halo atoms, in particular trifluoromethyl and trichloromethyl. C₁₋₄alkyloxyiminomethyl defines a radical of formula -CH=N-O-C₁₋₄alkyl. C₅₋₆cycloalkyl comprises cyclopentyl and cyclohexyl.

- Particular compounds of formula (I) for use in the method are those wherein n is 0, 1 or
20 2; R¹ is hydrogen, C₁₋₄alkyl or benzyl; and R² represents phenyl; naphthyl; pyridinyl; thienyl provided that n is not 2; furanyl optionally substituted with 1 to 3 substituents independently selected from C₁₋₄alkyl and C₁₋₄alkyloxycarbonyl; or phenyl substituted with 1 or 2 substituents independently selected from hydroxyl, halo, C₁₋₁₂alkyl, C₅₋₆cyclo-alkyl, trihalomethyl, phenyl, C₁₋₅alkoxy, C₁₋₅alkylthio, tetrahydropyranyloxy,
25 phenoxy, C₁₋₄alkylcarbonyl, phenylcarbonyl, C₁₋₄alkylsulfinyl, C₁₋₄alkylsulfonyl, carboxy or its alkali metal salt, C₁₋₄alkoxycarbonyl, C₁₋₄alkylaminocarbonyl, phenylaminocarbonyl, tolylaminocarbonyl, morpholinocarbonyl, amino, nitro, cyano, or dioxolanyl.

- 30 Of interest are those compounds of formula (I) wherein n is 1 and R² represents phenyl, thienyl or phenyl substituted with one or two substituents selected from halo and trihalomethyl; or those wherein n is 2 and R² represents phenyl or phenyl substituted with one or two substituents selected from halo and trihalomethyl.


- 35 Of further interest are the compounds of formula (I) wherein R¹ is hydrogen, n is 1 or 2, and R² represents phenyl, C₁₋₆alkylphenyl, halophenyl, dihalophenyl, biphenyl, C₁₋₅alkyloxyphenyl, trihalomethylphenyl, nitrophenyl, phenyl substituted with

C₁₋₄alkyloxycarbonyl, C₁₋₆alkylnitrophenyl, unsubstituted furanyl or thienyl, or furanyl or thienyl substituted with ethoxycarbonyl, cyano, chlorine or bromine.

Of particular interest are the compounds of formula (I) wherein R¹ is hydrogen, n is 1 or 2, and R² represents 3-fluorophenyl, 4-chlorophenyl, 3,4-dichlorophenyl,
 5 3,5-dichlorophenyl, 3-trifluoromethylphenyl, 4-trifluoromethylphenyl, 4-methylphenyl, 3-ethanonephenyl, 3-nitrophenyl, 3-methyl-4-nitrophenyl or 2-thienyl.

Also of further interest are those compounds of formula (I) wherein R¹ is hydrogen, R²
 10 is a radical of formula (b) wherein X is sulfur, Y is nitrogen or CH, and R³ is hydrogen.

The most preferred compound of formula (I) is 3-(benzo[b]thien-2-yl)-5,6-dihydro-
 1,4,2-oxathiazine, 4-oxide, generically known as "bethoxazin", and referred to as
 15 "compound (1)" throughout the description, having formula :




Particular compounds of formula (II) are those compounds of formula (II) wherein
 wherein R⁸ represents methyl, ethyl, n- or i-propyl, n-, i-, s- or t-butyl, n- or i-pentyl,
 20 n- or i-hexyl, n- or i-heptyl, n- or i-octyl, n- or i-nonyl, n- or i-decyl, n- or i-dodecyl, n- or i-octadecyl, allyl, n- or i-butenyl, n- or i-pentenyl, n- or i-hexenyl, propargyl, n- or i-butinyl, n- or i-pentynyl, n- or i-hexinyl, chloromethyl, bromomethyl, chloroethyl, bromoethyl, chloropropyl, bromopropyl, cyanomethyl, cyanoethyl, cyanopropyl, hydroxymethyl, hydroxyethyl, hydroxypropyl, methoxymethyl, methoxyethyl,
 25 methoxypropyl, ethoxymethyl, ethoxyethyl, ethoxypropyl, methoxycarbonylmethyl, methoxycarbonylethyl, methoxycarbonylpropyl, ethoxycarbonylmethyl, ethoxycarbonylethyl, ethoxycarbonylpropyl, propoxycarbonylmethyl, propoxycarbonylethyl, propoxycarbonylpropyl; furthermore represents cyclopropyl, cyclopropylmethyl, cyclopropylethyl, cyclopropylpropyl, cyclopentyl, cyclopentylmethyl,
 30 cyclopentylethyl, cyclopentylpropyl, cyclohexyl, cyclohexylmethyl, cyclohexylethyl or cyclohexylpropyl, each of which is optionally monosubstituted to tetrasubstituted in the cycloalkyl moiety by identical or different substituents from the group consisting of fluorine, chlorine, bromine, methyl, ethyl, n- or i-propyl, chloromethyl, dichloromethyl or trifluoromethyl; furthermore represents phenylalkyl, phenylalkenyl, phenyl alkynyl,
 35 phenyl or naphthyl, each of which has, in the case of phenylalkyl, phenylalkenyl and phenylalkynyl, up to 6 carbon atoms in the straight-chain or branched alkyl or alkenyl or

alkynyl moiety and each of which is optionally monosubstituted to trisubstituted in the aryl moiety by identical or different substituents, suitable aryl substituents in each case being: fluorine, chlorine, bromine, hydroxyl, cyano, nitro, methyl, ethyl, n- or i-propyl, n-, i-, s- or t-butyl, methoxy, ethoxy, n- or i-propoxy, n-, i-, s- or t-butoxy, methylthio, ethylthio, trifluoromethyl, trifluoromethoxy, trifluoromethylthio, methylcarbonyl, ethylcarbonyl, methoxycarbonyl, ethoxycarbonyl, aminocarbonyl, N-methylaminocarbonyl, N,N-dimethylaminocarbonyl, N-ethylamino-carbonyl, N,N-diethylaminocarbonyl, N-formylamino, N-acetylamino, N-methyl-N-formylamino, N-methyl-N-acetylamino, N-ethyl-N-formylamino, N-ethyl-N-acetylamino, methoximinomethyl, methoximinoethyl, ethoximinomethyl, ethoximinoethyl, or phenyl which is optionally monosubstituted to trisubstituted by identical or different substituents from the group consisting of fluorine, chlorine, bromine, methyl and/or ethyl;

R⁹ represents hydrogen, methyl, ethyl, n- or i-propyl, n-, i-, s- or t-butyl, n- or i-pentyl, n- or i-hexyl, hydroxymethyl, hydroxyethyl, hydroxypropyl, chloromethyl, bromomethyl, chloroethyl, bromoethyl, chloropropyl, bromopropyl, cyanomethyl, cyanoethyl, cyanopropyl, hydroxymethyl, hydroxyethyl, hydroxypropyl, methoxymethyl, methoxyethyl, methoxypropyl, ethoxymethyl, ethoxyethyl, ethoxypropyl, methoxycarbonylmethyl, methoxycarbonylethyl, methoxycarbonylpropyl, ethoxycarbonylmethyl, ethoxycarbonylethyl, ethoxycarbonylpropyl, propoxycarbonylmethyl, propoxycarbonylethyl, propoxycarbonylpropyl, dimethylaminomethyl, diethylaminomethyl, dipropylaminomethyl, dimethylaminoethyl, diethylaminoethyl, dipropylaminoethyl, dimethylaminopropyl, diethylaminopropyl, ordipropylaminopropyl; or

R⁸ and R⁹ together with the nitrogen atom to which they are bonded represent a heterocycle of the formula




each of which is optionally monosubstituted, disubstituted or trisubstituted by methyl and/or ethyl and/or methoxycarbonyl and/or ethoxycarbonyl;

R⁴, R⁵, R⁶ and R⁷ independently of one another in each case represent hydrogen, fluorine, chlorine, bromine, cyano, nitro, methyl, ethyl, n- or i-propyl, n-, i-, s- or t-butyl, methoxy, ethoxy n- or i-propoxy, n-, i-, s- or t-butoxy, methylthio, ethylthio, trifluoromethyl, trifluoromethoxy or trifluoromethylthio.

Preferred compounds of formula (II) are those compounds of formula (II) wherein R⁴, R⁵, R⁶ and R⁷ are each hydrogen; R⁸ is *N*-butyl, *N*-pentyl, *N*-n-hexyl, or *N*-cyclohexyl-methyl and R⁹ is hydrogen; or wherein R⁸ and R⁹ are taken together with the nitrogen atom to which they are bonded forming a *N*-cyclohexyl.

5

The most preferred compound of formula (II) is *N*-cyclohexyl-benzothiophene-2-carboxamide-*S,S*-dioxide, referred to as "compound (2)" throughout the description, having the following structure :



10

The active ingredients (I) and (II) may be present in base or in salt form, the latter being obtained by reaction of the base form with an appropriate acid. Appropriate acids comprise, for example, inorganic acids, such as the hydrohalic acids, *i.e.* hydrofluoric, hydrochloric, hydrobromic and hydroiodic, sulfuric acid, nitric acid, phosphoric acid and the like; or organic acids, such as, for example, acetic, propanoic, hydroxyacetic, 2-hydroxypropanoic, 2-oxopropanoic, ethanedioic, propanedioic, butanedioic, (Z)-2-butenedioic, (E)-2-butenedioic, 2-hydroxybutanedioic, 2,3-dihydroxybutanedioic, 2-hydroxy-1,2,3-propanetricarboxylic, methanesulfonic, ethanesulfonic, benzenesulfonic, 4-methylbenzenesulfonic, cyclohexanesulfamic, 2-hydroxybenzoic, 4-amino-2-hydroxybenzoic and the like acids.

15
20

The term salt form also comprises metal complexes which the basic components (I) or (II) may form. One of the components may occur as a complex and the other not; or both components may occur as a complex. Metal complexes as mentioned above consist of a complex formed between one or more molecules of the active ingredient and one or more organic or inorganic metal salt or salts. Examples of said organic or inorganic salts comprise the halogenides, nitrates, sulfates, phosphates, acetates, trifluoroacetates, trichloroacetates, propionates, tartrates, sulfonates, *e.g.* methylsulfonates, 4-methylphenylsulfonates, salicylates, benzoates and the like of the metals of the second main group of the periodical system, *e.g.* the magnesium or calcium salts, of the third or fourth main group, *e.g.* aluminium, tin, lead as well as the first to the eighth transition groups of the periodical system such as, for example, chromium, manganese, iron, cobalt, nickel, copper, zinc and the like. Preferred are the metals pertaining to the transition elements of the fourth period. The metals may be present in each of their

25
30
35

possible valences. The metal ions may be present in any of their possible valences, the most preferred metal copper being most advantageously used in its divalent form Cu(II). Suitable copper compounds are copper sulfate, acetate, hydroxide, oxide, borate, fluoride and in particular copper hydroxide carbonate $\text{Cu}(\text{OH})_2\text{CuCO}_3$. The complexes
5 can be mono- or polynuclear, they may contain one or more parts of the organic molecule as ligands.

The term salt as used hereinabove also comprises the solvates which the active ingredients of formula (I) and (II) are able to form. Examples of such solvates are e.g.,
10 the hydrates, alcoholates and the like.

The metal salt complexes of the active ingredients of formula (I) or (II) can conveniently be prepared by dissolving the metal salt in a suitable solvent e.g. ethanol, and adding thereto the active ingredients. The thus obtained complexes may be
15 isolated following art-known techniques, e.g. by filtration or evaporation, and may be further purified, e.g. by recrystallization. The term salt as used hereinabove also comprises the solvates which the compounds of formula (I) or (II) are able to form, e.g. hydrates, alcoholates and the like.

20 The synergistic mixtures or compositions according to the present invention are most useful to combat wood-destroying and wood-discoloring fungi or prevent the growth thereof in wood or wood products. As wood which can be preserved with the synergistic compositions according to the present invention is considered, for example, wood products such as timber, lumber, railway sleepers, telephone poles, fences, wood
25 coverings, wicker-work, windows and doors, plywood, particle board, waferboards, chipboard, joinery, bridges or wood products which are generally used in housebuilding, construction and carpentry. Synergistic compositions according to the present invention can also advantageously be applied in the cellulose and paper industry, in particular to protect pulpwood for paper manufacture from fungal attack; and also in biodegradable
30 materials such as, for example, textiles of natural fibers, e.g. cotton, flax, hemp, wool, silk and the like; textiles of synthetic fibers, e.g. polyamide, polyacrylonitrile or polyester fibers, or of mixtures of such fibers; coatings, e.g. oil paints, dispersion paints, lacquers, lacquer films, whitewash, finishing stains and the like; glues and other such materials which are biodegradable by fungi.

35 The synergistic mixtures of the present invention are active against a broad range of fungi. As examples of such fungi there may be named *Ascomycetes* (e.g. *Venturia*, *Podosphaera*, *Erysiphe*, *Monilinia*, *Uncinula*, *Aureobasidium*, *Sclerophoma*); *Basidiomycetes* (e.g. *Hemileia*, *Rhizoctonia*, *Puccinia*, *Coniophora*, *Serpula*, *Poria*,

Uromyces, Gloeophyllum, Lentinus, Coriolus, Irpex); *Fungi imperfecti* (e.g. *Botrytis, Helminthosporium, Rhynchosporium, Fusarium, Septoria, Cercospora, Alternaria, Pyricularia, Penicillium, Geotrichum*).

- 5 Wood which is preserved from staining, discoloring and decay is meant to be protected from for example, moulding, rotting, loss of its useful mechanical properties such as breaking strength, resistance to shock and shearing strength, or decrease of its optical or other useful properties due to the occurrence of odour, staining and spot formation. These phenomena are caused by a number of micro-organisms of which the following
10 are typical examples :

Wood-discoloring fungi :

- 1: Ascomycetes : *Ceratocystis* e.g. *Ceratocystis minor*.
Aureobasidium e.g. *Aureobasidium pullulans*
Sclerophoma e.g. *Sclerophoma pithyophila*
15 *Cladosporium* e.g. *Cladosporium herbarum*
- 2: Deuteromycetes: *Fungi imperfecti*
Aspergillus e.g. *Aspergillus niger*
Dactylium e.g. *Dactylium fusarioides*
Penicillium e.g. *P. brevicaulis, P. variable, P. funiculosum* or
20 *P. glaucum*
Scopularia e.g. *Scopularia phycomyces*
Trichoderma e.g. *Trichoderma viride* or *Trichoderma lignorum*.
Alternaria e.g. *Alternaria tenuis, Alternaria alternata*
- 3: Zygomycetes: *Mucor* e.g. *Mucor spinorus*.
25

Wood-destroying fungi

- 1: Soft-rot Fungi: *Chaetomium* e.g. *Ch. globosum* or *Ch. alba-arenulum*
Humicola e.g. *Humicola grisea*
Petriella e.g. *Petriella setifera*
30 *Trichurus* e.g. *Trichurus spiralis*.
- 2: White and brown rot Fungi :
- Coniophora* e.g. *Coniophora puteana*
Coriolus e.g. *Coriolus versicolor*
Donkioporia e.g. *Donkioporia expansa*
35 *Glenospora* e.g. *Glenospora graphii*
Gloeophyllum e.g. *Gl. abietinum, Gl. adorum, Gl. protactum,*
Gl. sepiarium or *Gl. trabeum*
Lentinus e.g. *L. cyathiformes, L. edodes, L. lepideus, L. grinus*

or *L. squarrolus*

Paxillus e.g. *Paxillus panuoides*

Pleurotus e.g. *Pleurotis ostreatus*

Poria e.g. *P. monticola*, *P. placenta*, *P. vaillantii* or *P. vaporaria*

5 *Serpula* (*Merulius*) e.g. *Serpula himantoides* or
Serpula lacrymans

Stereum e.g. *Stereum hirsutum*

Trychophyton e.g. *Trychophyton mentagrophytes*

Tyromyces e.g. *Tyromyces palustris*.

10

In order to protect wood from decay it is treated with synergistic compositions according to the present invention. Such treatment is applied by several different procedures such as, for example, by treating the wood in closed pressure or vacuum systems, in thermal or dip systems and the like, or by a wide variety of surface treatments, e.g. by spraying, atomizing, dusting, scattering, pouring, brushing, dipping, soaking or impregnating the wood with a composition comprising a compound of formula (I), in particular 3-benzo[b]thien-2-yl)-5,6-dihydro-1,4,2-oxathiazine 4-oxide, or a salt thereof, and a compound of formula (II), in particular *N*-cyclohexyl-benzothiophene-2-carboxamide-S,S-dioxide (II), or a salt thereof, in quantities producing a mutual synergistic effect, and a carrier.

15

20

The amount of each of the active ingredients of formula (I) and (II) in the compositions according to the present invention is such that a mutual synergistic fungicidal effect is obtained upon application. In particular, it is contemplated that in the compositions to be used directly, the concentration of a compound of formula (I), in particular 3-(benzo[b]thien-2-yl)-5,6-dihydro-1,4,2-oxathiazine, 4-oxide (*i.e.* compound 1), taken as base equivalent, may range from 10 to 5000 ppm, in particular from 50 to 2000 ppm or from 50 to 1000 ppm, more in particular from 100 to 800 ppm; and the concentration of the compound of formula (II), in particular *N*-cyclohexyl-benzothiophene-2-carboxamide-S,S-dioxide (*i.e.* compound 2), taken as base equivalent is contemplated to range from 10 to 5000 ppm, in particular from 50 to 2000 ppm or from 100 to 1000 ppm, more in particular from 200 to 800 ppm. In many instances said compositions to be used directly can be obtained from concentrates upon dilution with aqueous or organic media, such concentrates also being intended to be covered by the term composition as used in the definitions of the present invention. The content of the active ingredients in the above-indicated compositions is from 0.01 to 95%, preferably from 0.1 to 50% more preferably from 0.1 to 20% and in particular from 0.2 to 15% by weight. The compositions according to the invention are preferably used in the form of

35

solutions or emulsions.

The ratio between the active ingredients of formula (I) and (II) will be such that a synergistic fungicidal effect is obtained with both active ingredients. Particularly, the weight ratio between (I) and (II) may range from 50:1 to 1:50, more particularly from 20:1 to 1:20 and preferably will range from about 5:1 to 1:5. When the compound of formula (I) is 3-(benzo[b]thien-2-yl)-5,6-dihydro-1,4,2-oxathiazine, 4-oxide (*i.e.* compound 1), and the compound of formula (II) is *N*-cyclohexyl-benzothiophene-2-carboxamide-S,S-dioxide (*i.e.* compound 2), the weight ratio between (I) and (II) preferably ranges from 1:64 to 2:1, more particularly from 1:16 to 1:1 and preferably will be from 1:4 to 1:2.

The active ingredients of formula (I) and (II) are used in unmodified form or together with adjuvants conventionally employed in the art of formulation. The formulations, *i.e.* the compositions, preparations or mixtures containing the active ingredients and, where appropriate, a solid or liquid adjuvant, are prepared following art-known procedures, *e.g.* by homogeneously mixing and/or grinding the active ingredients with extenders, *e.g.* solvents, solid carriers and, where appropriate, surface-active compounds (surfactants), to emulsifiable concentrates, directly sprayable or dilutable solutions, dilute emulsions, wettable powders, soluble powders, dusts, granulates, and also encapsulations in *e.g.* polymer substances. Both the nature of the compositions and the methods of application such as spraying, atomizing, dusting, scattering or pouring, brushing, dipping, soaking or impregnating, should be chosen in accordance with the intended objectives and the prevailing circumstances. It is evident that in general different compositions with different characteristics will be required for use in plant protection on the one hand, and for use in material protection on the other. Carriers and adjuvants equally useful in both types of compositions are described first.

Appropriate carriers and adjuvants for use in the compositions of the present invention may be solid or liquid and correspond to suitable substances known in the art for preparing formulations for treating plants or the loci thereof, or for treating plant products, in particular for treating wood, such as, for example, natural or regenerated mineral substances, solvents, dispersants, surfactants, wetting agents, adhesives, thickeners, binders, fertilizers, anti-freeze agents, repellents, colour additives, corrosion inhibitors, water-repelling agents, siccatives, UV-stabilizers and other active ingredients.

The solid carriers used *e.g.* for dusts and dispersible powders are normally natural mineral fillers such as calcite, talcum, kaolin, montmorillonite or attapulgite. In order to

improve the physical properties it is also possible to add highly dispersed silicic acid or highly dispersed absorbent polymers. Suitable granulated absorbent carriers are of the porous type, for example pumice, broken brick, sepiolite or bentonite; and suitable nonsorbent carriers are materials such as calcite or sand. In addition, a great number of
5 pregranulated materials of inorganic or organic nature can be used, e.g. especially dolomite or pulverised plant residues.

Suitable solvents are aromatic hydrocarbons, preferably the fractions containing 8 to 12 carbon atoms, e.g. dimethylbenzene mixtures or substituted naphthalenes, phthalates
10 such as dibutyl phthalate or dioctyl phthalate, aliphatic or alicyclic hydrocarbons such as cyclohexane or paraffins, alcohols and glycols and their ethers and esters, such as ethanol, ethylene glycol, ethylene glycol monomethyl or monoethyl ether, ketones such as cyclohexanone, strongly polar solvents such as *N*-methyl-2-pyrrolidone, dimethylsulfoxide or dimethylformamide, as well as vegetable oils or epoxidised
15 vegetable oils such as epoxidised coconut oil or soybean oil; or water, or a mixture of said solvents.

Suitable surface-active compounds to be used in the compositions of the present invention are non-ionic, cationic and/or anionic surfactants having good emulsifying,
20 dispersing and wetting properties. The term "surfactants" will also be understood as comprising mixtures of surfactants.

Suitable anionic surfactants can be both water-soluble soaps and water-soluble synthetic surface-active compounds. Suitable soaps are the alkali metal salts, earth alkaline metal salts or unsubstituted or substituted ammonium salts of higher fatty acids (C₁₀-C₂₂), e.g.
25 the sodium or potassium salts of oleic or stearic acid, or of natural fatty acid mixtures which can be obtained e.g. from coconut oil or tallow oil. In addition, there may also be mentioned fatty acid methyltaurin salts. More frequently, however, so-called synthetic surfactants are used, especially fatty sulfonates, fatty sulfates, sulfonated benzimidazole derivatives or alkylaryl-sulfonates. The fatty sulfonates or sulfates are usually in the
30 form of alkali metal salts, earth alkaline metal salts or unsubstituted or substituted ammonium salts and contain an alkyl radical having from 8 to 22 carbon atoms said alkyl also comprising radicals derived from acyl radicals, e.g. the sodium or calcium salt of lignosulfonic acid, of dodecylsulfate or of a mixture of fatty alcohol sulfates obtained
35 from natural fatty acids. These compounds also comprise the salts of sulfuric acid esters and sulfonic acids of fatty alcohol/ethylene oxide adducts. The sulfonated benzimidazole derivatives preferably contain 2 sulfonic acid groups and one fatty acid radical containing 8 to 22 carbon atoms. Examples of alkylarylsulfonates are the sodium,

calcium or triethanolamine salts of dodecylbenzene-sulfonic acid, dibutylnaphthalene-sulfonic acid, or of a naphthalenesulfonic acid/formaldehyde condensation product. Also suitable are corresponding phosphates, e.g. salts of the phosphoric acid ester of an adduct of p-nonylphenol with 4 to 14 moles of ethylene oxide, or phospholipids.

5

Non-ionic surfactants are preferably polyglycol ether derivatives of aliphatic or cycloaliphatic alcohols, or saturated or unsaturated fatty acids and alkylphenols, said derivatives containing 3 to 10 glycol ether groups and 8 to 20 carbon atoms in the (aliphatic) hydrocarbon moiety and 6 to 18 carbon atoms in the alkyl moiety of the alkylphenols.

10

Further suitable non-ionic surfactants are the water-soluble adducts of polyethylene oxide with polypropylene glycol, ethylenediaminopolypropylene glycol containing 1 to 10 carbon atoms in the alkyl chain, which adducts contain 20 to 250 ethylene glycol ether groups and 10 to 100 propylene glycol ether groups. These compounds usually contain 1 to 5 ethylene glycol units per propylene glycol unit. Representative examples of non-ionic surfactants are nonylphenol polyethoxy-ethanols, castor oil polyglycol ethers, polypropylene/polyethylene oxide adducts, tributylphenoxy-polyethoxyethanol, polyethylene glycol and octylphenoxy-polyethoxyethanol. Fatty acid esters of polyethylene sorbitan, such as polyoxyethylene sorbitan trioleate, are also suitable non-ionic surfactants. They are of particular utility in compositions for material, in particular wood, protection.

15

20

Cationic surfactants are preferably quaternary ammonium salts wherein at least one *N*-substituent is a C₈-C₂₂alkyl radical and the further substituents are unsubstituted or halogenated lower alkyl, benzyl or hydroxy lower alkyl radicals. The salts are preferably in the form of halides, methylsulfates or ethylsulfates, e.g. stearyltrimethylammonium chloride or benzyldi(2-chloroethyl)ethylammonium bromide. They are particularly useful in compositions for agrochemical purposes.

25

30

The surfactants customarily employed in the art of formulation are described e.g. in the following publications : "McCutcheon's Detergents and Emulsifiers Annual", MC Publishing Corp., Ridgewood, New Jersey, 1981; H. Stache, "Tensid-Taschenbuch", 2nd Edition, C. Hanser Verlag, Munich & Vienna, 1981, M. and J. Ash, "Encyclopedia of Surfactants", Vol. I-III, Chemical Publishing Co., New York, 1980-81.

35

The following paragraphs in particular relate to compositions for use in plant protection. In general such compositions are designed so as to be innocuous to culture plants, to be

easily and safely applicable, to have good bioavailability to the host plants and to remain (persist) only temporarily in the environment.

5 Particularly advantageous additives useful to improve the application and reduce the dose of the active ingredients, are the natural (animal or plant) or synthetic phospholipids of the cephalin or lecithin type such as, for example, phosphatidyl-ethanolamine, phosphatidyl serine, phosphatidylglycerine, lysolecithin, or cardiolipin. Such phospholipids may be obtained from animal or plant cells, in particular from brain-, heart- or liver tissue, egg yolks or soy beans. Appropriate such phospholipids are for
10 instance, phosphatidylcholine mixtures. Synthetic phospholipids are for instance, dioctanylphosphatidylcholine and dipalmitoylphosphatidylcholine.

In case of liquid formulations, and particularly of aqueous or alcoholic formulations, it is recommendable to add an appropriate surfactant, either from the anionic, cationic,
15 nonionic or amphoteric type. In particular said surfactants will be of the cationic type and more in particular said surfactant is a quaternary ammonium salt or a mixture of quaternary ammonium salts. Such quaternary ammonium surfactants comprise, e.g., ammonium salts having four hydrocarbon radicals which may optionally be substituted with halo, phenyl, substituted phenyl or hydroxy; said hydrocarbon radicals in particular
20 being alkyl or alkenyl radicals; they may also be derived from fatty acids or alcohols, e.g. cetyl, lauryl, palmityl, myristyl, oleyl and the like or from the hydrosylates from coconut oil, tallow oil, soy bean oil, or the hydrogenated forms thereof, and the like.

Examples of such quaternary ammonium salts are of the trimethyl alkyl ammonium
25 halide type, e.g. trimethyl decyl ammonium chloride, trimethyl dodecylammonium chloride, trimethyl tallow ammonium chloride, trimethyl oleyl ammonium chloride; or of the dimethyl alkyl benzyl ammonium type, e.g. dimethyl decyl benzyl ammonium chloride, dimethyldodecyl benzyl ammonium chloride, dimethyl hexadecylbenzyl ammonium chloride (commonly designated as "cetalkonium chloride"), dimethyl
30 octadecyl benzyl ammonium chloride, dimethyl coco benzyl ammonium chloride, dimethyl tallow benzyl ammonium chloride; and particularly the dimethyl C₈₋₁₈alkyl benzyl ammonium chloride mixture which is commonly known as "benzalkonium chloride"; dimethyl dialkyl ammonium halides, e.g. dimethyl dioctyl ammonium chloride, dimethyl didecyl ammonium chloride, dimethyl didodecyl ammonium chloride, dimethyl
35 dicoco ammonium chloride, dimethyl ditallow ammonium chloride, dimethyl octyl decyl ammonium chloride, dimethyl dodecyl octyl ammonium chloride, dimethyl dihydrogenated tallow ammonium chloride.

As used in the foregoing enumeration of quaternary ammonium salts, the terms "coco", "tallow" and "hydrogenated tallow" designate those hydrocarbon radicals derived from the hydrosylates of coconut oil, tallow oil or hydrogenated tallow oil.

The weight ratio between said quaternary ammonium surfactants and the active ingredients of formula (I) and (II) is situated between 1:1 and 10:1. Excellent results are obtained when said ratio is about 5:1.

The following paragraphs in particular relate to compositions for use in wood protection. In general such compositions are designed so as to penetrate well in to wood, to persist there for a long time, and to be industrially applicable.

A biocidally active quaternary ammonium compound or tertiary amine salt can advantageously be used in the formulation of emulsions of the active ingredients of formula (I) and (II) in aqueous solutions of metal salts. Micro-emulsions may thus be formed which have particular utility in wood preservation. Additional advantages related to these adjuvants comprise their solubilizing effect on the active ingredients of formula (I) and (II), their contributory biocidal effect and their ability to promote penetration of the formulation into wood.

Binders are meant to comprise binding drying oils (e.g. linseed oil) and resins that are water-dilutable or dilutable, dispersible or emulsifiable in organic solvents, e.g. acryl, vinyl, polyester, polyurethane, alkyd, phenolic, hydrocarbon and silicon resins. Mixtures of an alkyd resin with a drying oil are advantageously used as a binding material. Part of the binding material may further be substituted with one or more fixing agents or one or more plasticizers. These adjuvants delay or prevent evaporation of the active ingredients as well precipitation or crystallisation thereof. About 0.01% to about 30 % of the binding material may thus be replaced. Suitable plasticizers are phthalic acid esters, e.g. the dibutyl, dioctyl and benzylbutyl phthalate esters; phosphoric acid esters, e.g. tributylphosphate; fatty acid esters, e.g. di(2-ethylhexyl)adipate, butylstearate, amylstearate, butyloleate; glycerolethers; glycolethers; glycerolesters; and p-toluene-sulfonic acid esters. Suitable fixing agents are polyvinylalkyl ethers, e.g. polyvinyl-methyl ethers, or ketones, e.g. benzophenone or ethylenebenzophenone.

In view of their solubility in organic solvents the active ingredients are well suited for application in non-aqueous media, which is of interest in wood-preservation. The wood or wood products to be protected can easily be impregnated with such solutions. As organic solvents there may be used aliphatic and aromatic hydrocarbons, their chlorinated derivatives, acid amides, mineral oils, alcohols, ethers, glycolethers, such as,

for example, methylene chloride, propylene glycol, methoxyethanol, ethoxyethanol, *N,N*-dimethylformamide and the like or mixtures of such solvents, to which there may be added dispersants or emulsifiers such as sulfated ricinus oil, fatty alcohol sulfates and other additives.

5

Particularly attractive formulations comprise water-dilutable wood-preservative liquids containing an appropriate amount of a suitable solvent, a suitable solubilizer and both the active ingredients. Preferably there is used 10-80% of a solvent, 20-80% of a solubilizer and from 0.01 to 10% of the active ingredients (I) and (II).

10

Preferred solubilizers to be used in the said water-dilutable wood-preservative liquids are selected from :

- i) addition products of 1 to 60 moles of ethylene oxide with 1 mole of a phenol which is further substituted with at least one C₁₋₁₅alkyl group; and
- 15 ii) addition products of 1 to 60 moles of ethylene oxide with 1 mole of ricinus oil.

The most preferred solubilizers are selected from :

- i) addition products of 1 to 60 moles of ethylene oxide with 1 mole of nonylphenol or octylphenol; and
- 20 ii) addition products of 1 to 60 moles of ethylene oxide with 1 mole of ricinus oil.

Said suitable solvent should fulfill the requirements of sufficiently solubilizing the active ingredients and, when combined with the solubilizer, of being homogeneously miscible with a predominantly aqueous medium. Preferred solvents are 2-butoxyethanol, butyl 25 2-hydroxyacetic acid ester and propyleneglycol monomethylether.

Preferred water-dilutable compositions for use in wood protection comprise active ingredients (I) and (II), a copper compound, suitable solvents and/or solubility enhancers and optionally other adjuvants. Suitable solvents are e.g. alcohols (ethanol, 30 iso-propanol), glycols (ethylene and propylene glycol), glycolethers (ethylene glycol monomethyl and monoethyl ether), dimethylformamide, *n*-methylpyrrolidone, which yield homogenous concentrates. As solubilizers there may be employed carboxylic acids, or the amine, alkali metal or copper salt forms corresponding thereto, so that the amount of the organic solvent used in the homogenous concentrates can be kept to a 35 minimum. Examples of such acids are propionic, hexanoic, heptanoic, 2-ethylhexanoic, iso-octanoic, sebacic, cyclohexanoic, benzoic, 3-hydroxybenzoic and 4-hydroxybenzoic acid. To improve further the industrial applicability of such water-dilutable, homogenous compositions comprising a carboxylic acid as solubilizer, advantageous use

- may be made of polyethyleneimines (PEI, Polymin) derived from ethyleneimine (aziridine) and having the formula $(C_2H_5N)_n$. The degree of polymerization 'n' should be larger than 10 and preferably ranges from about 50 to about 1000, and in particular is about 150. The use of alkanolamines, in particular monoethanolamine, but also di- and triethanolamine, as complexing agents for the copper compound employed may be of particular benefit. Typically there may be used about 4 molar equivalents of alkanolamine per mole of copper. Further useful additives are, for example, boron derivatives, e.g. boric acid, its salts and esters, and fluorides, e.g. potassium fluoride.
- 5
- 10 Water-dilutable homogenous concentrates in particular comprise by weight :
2.5 to 45 %, in particular 10 to 20 % copper compound,
5 to 50 %, in particular 20 to 40 % alkanolamine,
0.25 to 15 %, in particular 1 to 10 % of compounds of formula (I) and (II),
0.5 to 30 %, in particular 5 to 15 % surfactant(s),
15 0 to 40 % other fungicidal compound(s),
0 to 40 % organic solvent(s),
0 to 40 % carboxylic acid(s), and
0 to 40 % polymin.
- 20 Said water-dilutable wood-preserving liquids have the advantage that almost instantaneously homogeneous or quasi homogeneous solutions are formed by mixing these liquids with predominantly aqueous media. These solutions have an extremely high physical stability, not only at ambient temperature, *i.e.* at temperatures comprised between 15°C and 35°C, but also at decreased temperatures. Thus, the physical stability
25 of said solutions does not deteriorate after several freeze-thaw cycles. Said homogeneous solutions further unite the advantages of moistening the wood-surface well and penetrating the wood to a high degree, resulting in a high uptake of the solution and its active ingredients by the wood, and, consequently, obtaining the desired preservation of the treated wood. Additionally, due to a more uniform uptake of the
30 aqueous solution the wood-preserving liquids and the resulting aqueous solutions are particularly useful in treatment techniques which require the possibility of a continuous process, such as, for example, impregnation or dip techniques.
- In addition, the solutions formed with the wood-preserving liquids unite in themselves the hereinabove mentioned advantages with those which are characteristic of
35 predominantly aqueous media, such as, for example, a relatively high flashpoint and reduced toxicity, resulting in advantageous influence on the environment and the health and safety of the applicator, lack of irritation and the like benefits.

Apart from both the aforementioned active ingredients of formula (I) and (II), the compositions according to the present invention may further contain other active ingredients, e.g. other microbiocides, in particular insecticides, and also bactericides, acaricides, nematocides, herbicides, plant growth regulators, fertilizers or further
5 fungicides. As antimicrobial agents, which may be used in combination with the active substances there may be considered products of the following classes : phenol derivatives such as 3,5-dichlorophenol, 2,5-dichlorophenol, 3,5-dibromophenol, 2,5-dibromophenol, 2,5-(resp. 3,5)-dichloro-4-bromophenol, 3,4,5-trichlorophenol, tribromophenol, tetrachlorophenol, 3-methyl-4-chlorophenol; chlorinated
10 hydroxydiphenylethers such as, for example, 2-hydroxy-3,2'4'-trichlorodiphenylether; phenylphenol (o-, m-, p-), 4-chloro-2-phenylphenol, 4-chloro-2-benzylphenol, dichlorophene, hexachlorophene; aldehydes such as formaldehyde, glutaraldehyde, salicylaldehyde; alcohols such as phenoxyethanol; antimicrobially active carboxylic acids and their derivatives; organometallic compounds such as tributyltin compounds; iodine
15 compounds such as iodophores, iodonium compounds; diiodomethyl-p-tolyl-sulfone, 3-iodo-2-propynyl-alkohol, 4-chlorophenyl-3-iodopropargyl-formal, 3-bromo-2,3-diiodo-2-propenylethylcarb-Rat, 2,3,3-triiodoallylalkohol, 3-bromo-2,3-diiodo-2-propenylalkohol, 3-iodo-2-propynyl-n-butylcarbamate, 3-iodo-2-propynyl-n-hexylcarbamate, 3-iodo-2-propynyl-cyclohexylcarbamate, 3-iodo-2-propynyl-phenyl-
20 carbamate; mono-, di- and polyamines such as dodecylamine or 1,10-di(n-heptyl)-1,10-diaminodecane; sulfonium- and phosphonium compounds; mercapto compounds as well as their alkali, earth alkaline and heavy metal salts such as 2-mercaptopyridine-N-oxide and its sodium, iron, manganese and zinc salt, 3-mercaptopyridazin-2-oxide, 2-mercaptoquinoxaline-1-oxide, 2-mercaptoquinoxaline-di-N-oxide, as well as the
25 symmetrical disulfides of said mercapto compounds; ureas such as tribromo- or trichlorocarbanilide, dichlorotrifluoromethyl-diphenylurea; tribromosalicylanilide; 2-bromo-2-nitro-1,3-dihydroxypropane (bronopol); dichlorobenzoxazolone; chlorohexidine; sulfenamides e.g. dichlofluanid, tolylfluanid, folpet, fluorfolpet; benzimidazoles e.g. carbendazim, benomyl, fuberidazole, thiabendazole; thiocyanates
30 e.g. thiocyanatomethylthiobenzothiazole, methylenebisthiocyanate; quaternary ammonium compounds e.g. benzyldimethyltetradecyl ammonium chloride, benzyl-dimethyldodecyl ammonium chloride, didecyldimethyl ammonium chloride; morpholine derivates e.g. tridemorph, fenpropimorph, falimorph; azoles e.g. triadimefon, triadimenol, bitertanol, prochloraz; 2-(1-chlorocyclopropyl)-1-(2-chlorophenyl)-3-(1H-
35 1,2,4-triazol-1-yl)-propan-2-ol; isothiazolinones e.g. N-methylisothiazolin-3-one, 5-chloro-N-methyl-isothiazolin-3-one, 4,5-dichloro-N-octylisothiazolin-3-one, N-octyl-isothiazolin-3-one; benzisothiazolinone, cyclopenteneisothiazolinone;

tetrachloro-4-methylsulfonyl-pyridine; metal salts e.g. tin, copper, zinc naphthenate, octoate, 2-ethylhexanoate, oleate, phosphate, benzoate; oxides e.g. tributyltin oxide, Cu₂O, CuO, ZnO; dialkyldithiocarbamate e.g. Na- and Zn-salts of dialkyldithiocarbamates, tetramethylthiuramdisulfide; nitriles e.g. 2,4,5,6-tetrachloroisophthalodinitrile; benzothiazole e.g. 2-mercaptobenzothiazole; quinolines e.g. 8-hydroxyquinoline and its Cu-salts; boron compounds e.g. boric acid, boric acid esters, borax; formaldehyde and formaldehyde releasing compounds e.g. benzylalkohol mono(poly)hemiformal, oxazolidine, hexahydro-S-triazine, N-methylol-chloracetamide, paraformaldehyde; tris-N-(cyclohexyldiazoniumdioxy)-aluminium, N-cyclohexyldiazonium-dioxy)-tributyltin bis-N-(cyclohexyldiazoniumdioxy)-copper.

The compositions of the present invention comprising the aforementioned active ingredients of formula (I) and (II) may further comprise a fungicidally active triazole such as, for example, azaconazole (1-[[2-(2,4-dichlorophenyl)-1,3-dioxolan-2-yl]methyl]-1H-1,2,4-triazole), bromuconazole (1-[4-bromo-2-(2,4-dichlorophenyl)tetrahydrofurfuryl]-1H-1,2,4-triazole), cyproconazole (α -(4-chlorophenyl)- α -(1-cyclopropylethyl)-1H-1,2,4-triazole-1-ethanol), difenoconazole (1-[2-[4-(4-chlorophenoxy)-2-chlorophenyl]-4-methyl-1,3-dioxolan-2-ylmethyl]-1H-1,2,4-triazole), epoxiconazole (1-[3-(2-chlorophenyl)-2-(4-fluorophenyl)oxiran-2-ylmethyl]-1H-1,2,4-triazole), fenbuconazole (4-(4-chlorophenyl)-2-phenyl-2-(1H-1,2,4-triazol-1-ylmethyl)-butyronitrile), hexaconazole (α -butyl- α -(2,4-dichlorophenyl)-1H-1,2,4-triazole-1-ethanol), metconazole (5-[(4-chlorophenyl)methyl]-2,2-dimethyl-1-(1H-1,2,4-triazol-1-ylmethyl)cyclopentanol), penconazole (1-[2-(2,4-dichlorophenyl)pentyl]-1H-1,2,4-triazole), propiconazole (1-[[2-(2,4-dichlorophenyl)-4-propyl-1,3-dioxolan-2-yl]methyl]-1H-1,2,4-triazole), tebuconazole (α -[2-(4-chlorophenyl)ethyl]- α -(1,1-dimethylethyl)-1H-1,2,4-triazol-1-ethanol), or triticonazole ((E)-5-(4-chlorophenyl)methylene)-2,2-dimethyl-1-(1H-1,2,4-triazol-1-ylmethyl)cyclopentanol).

As insecticidal agents which may be used in the combination according to the present invention the following classes of products may be considered : insecticides having a natural origin, e.g., nicotine, rotenone, pyrethrum and the like; chlorinated hydrocarbons, e.g., lindane, chlordane, endosulfan and the like; organic phosphor compounds, e.g. azinphos-ethyl, azinphos-methyl, 1-(4-chlorophenyl)-4(O-ethyl, S-propyl)phosphoryl-oxypyrazole, chlorpyrifos, coumaphos, demeton, demeton-S-methyl, diazinon, dichlorvos, dimethoate, ethoprophos, etrimfos, fenitrothion, fenthion, heptenophos, parathion, parathionmethyl, phosalone, phoxim, pirimiphos-ethyl, pirimiphos-methyl, profenofos, prothiofos, sulfprofos, triazophos,

trichlorphon; carbamates, e.g., aldicarb, bendiocarb, carbaryl, carbofuran, carbosulfan, cloethocarb, 2-(1-methylpropyl)phenylmethylcarbamate, butocarboxime, butoxycarboxime, fenoxycarb, isoprocarb, methomyl, methiocarb, oxamyl, pirimicarb, promecarb, propoxur and thiodicarb; biological insecticides, e.g., products originating from *Bacillus thuringiensis*; synthetic pyrethroids, e.g., allethrin, alphasmethrin, bioresmethrin, bifenthrin, cycloprothrin, cyfluthrin, cyhalothrin, cypermethrin, decamethrin, deltamethrin, fenpropathrin, fenfluthrin, fenvalerate, flucythrinate, flumethrin, fluvalinate, halothrin, permethrin, resmethrin and tralomethrin, alpha-cyano-3-phenyl-2-methylbenzyl-2,2-dimethyl-3-(2-chloro-2-trifluoromethyl-10 vinyl)cyclopropanecarboxylate; organosilicon compounds such as dimethylphenylsilylmethyl-3-phenoxybenzylethers e.g. dimethyl(4-ethoxyphenyl)-silylmethyl-3-phenoxybenzylether; or dimethylphenylsilylmethyl-2-phenoxy-6-pyridylmethylethers e.g. dimethyl(9-ethoxyphenyl)silylmethyl-2-phenoxy-6-pyridylmethylether or [(phenyl)-3-(3-phenoxyphenyl)propyl](dimethyl)silanes e.g. (4-ethoxyphenyl)[3-(4-fluoro-15 3-phenoxyphenyl)propyl]dimethylsilane, silafluofen; nitroimines and nitromethylenes e.g. 1-(6-chloro-3-pyridinylmethyl)-4,5-dihydro-*N*-nitro-1*H*-imidazol-2-amine (imidacloprid); benzoylureas e.g. lufenuron, hexaflumuron, flufenoxuron.

Particularly interesting active ingredients for combination with the present compositions comprising the active ingredients (I) and (II), in quantities producing a mutual synergistic effect, are : dichlofluanid, tolylfluanid, benzyldimethyldodecyl ammonium chloride, didecyldimethyl ammonium chloride, 3-bromo-2,3-diiodo-2-propenylalcohol, 3-iodo-2-propinyl-*n*-butylcarbamate, *o*-phenylphenol, *m*-phenylphenol, *p*-phenylphenol, 3-methyl-4-chlorophenol, thiocyanatomethyl-thiobenzothiazole, *N*-methyl-isothiazolin-25 3-one, 5-chloro-*N*-methylisothiazolin-3-one, 4,5-dichloro-*N*-octylisothiazolin-3-one, *N*-octyl-isothiazolin-3-one, benzylalcohol-mono(poly)hemiformal, *N*-methylolchloracetamide, phoxim, cyfluthrin, permethrin, cypermethrin, deltamethrin, imidacloprid, silafluofen, lufenuron, bifenthrin, fenoxycarb, hexaflumuron, flufenoxuron.

30 Susceptible material (in particular wood) destroying insects are, for example :

Beetles :

Anobium punctatum

Apate monachus

Bostrychus capucinus

Chlorophores pilosus

Dendrobium pertinex

Hymenoptera :

Sirex juvenus

Urocerus augur

Urocerus gigas

Urocerus gigas taignus.

Dinoderus minutus
Ernobius mollis
Heterobostrychus brunneus
Hylotrupes bajulus
Lyctus africanus
Lyctus brunneus
Lyctus linearis
Lyctus planicollis
Lyctus pubescens
Minthea rugicollis
Priobium carpini
Ptilinus pecticornis
Sinoxylon spp.
Trogoxylon aequale
Tryptodendron spp.
Xestobium rufovillosum
Xyleborus spp.

Termites:

Coptotermes formosanus
Cryptotermes brevis
Heterotermes indicola
Kalotermes flavicollis
Mastotermes darwiniensis
Reticulitermes flavipes
Reticulitermes lucifugus
Reticulitermes santonensis
Zootermopsis nevadensis.

The synergistic mixtures or compositions to be used directly may also be obtained from separate compositions containing the active ingredients or from the technical active ingredients themselves, by mixing and/or diluting with aqueous or organic media and/or optionally further adding adjuvants such as those described hereinabove. Said separate compositions generally are such as described hereinbefore for compositions containing both active ingredients. Of particular interest to some users may be preparation of custom-made formulations from both active ingredients in unmodified, technical form, thus allowing maximal flexibility in the application of the present synergistic mixtures of the active ingredients (I) and (II).

The present invention also concerns a method of combating fungi comprising treating plants or the loci thereof, or treating plant products such as wood; or pulpwood for paper manufacture, or treating biodegradable materials simultaneously, separately or sequentially with an effective amount of a synergistic, fungicidal composition as described hereinabove.

The present invention also concerns a method of preserving wood, wood products and biodegradable materials from deterioration by fungi. This method comprises the application to or incorporation in said wood or wood products or in or to said biodegradable materials, of a synergistic mixture or composition as defined hereinabove.

The active ingredients (I) and (II) can be applied to plants or to the loci thereof or to plant products, e.g. wood, or to biodegradable materials such as textiles, simultaneously, or can also be applied consecutively within a time period selected so that both active ingredients are allowed to act synergistically as antifungals, e.g. within 24 hours. In such applications, the active ingredients are used optionally together with adjuvants conventionally employed in the art of formulation such as carriers, surfactants or other useful additives. Therefore, the present invention also concerns products comprising a compound of formula (I), in particular 3-benzo[b]thien-2-yl)-5,6-dihydro-1,4,2-oxathiazine 4-oxide, or a salt thereof, and a compound of formula (II), in particular *N*-cyclohexylbenzo-thiophene-2-carboxamide-*S,S*-dioxide (II), or a salt thereof, as a combination for simultaneous, separate or sequential use in fungicidal applications. Such products may consists of a package comprising containers with both active ingredients, preferably in formulated form. Such formulated forms in general have the same composition as described for the formulations containing both active ingredients.

The following examples are intended to illustrate the scope of the present invention in all its aspects. Unless otherwise stated all parts therein are by weight.

20 A. Biological examples

Example 1

The synergistic activity of the mixtures or compositions of (I) and (II) according to the present invention can be demonstrated by comparison with the activity of the active ingredients (I) and (II) alone. The efficacy of the active ingredients against mycelial growth and sporulation of *Aureobasidium pullulans*, *Aspergillus niger*, *Sclerophoma entoxylina*, *Trichoderma viride*, was determined in the poison plate assay. The required concentrations of the fungicide(s) were obtained by diluting the active ingredients (I), (II) or the combination of (I) and (II) in dimethyl sulfoxide (DMSO) at 800 times the final test concentration. The stock solutions in DMSO were pipetted into Petri-dishes. Malt extract agar (3%) was added aseptically and uniform distribution was obtained by shaking. Each plate was spot inoculated with a spore or mycelial suspension. After incubation at 22°C and 70% relative humidity for a period long enough to allow complete growth of controls, diameters of colonies were measured. Relative activities were calculated by taking the absence of fungal growth (diameter 0 mm) as 100%. From the activity of the active ingredients alone, the expected activities E were calculated by using the so-called formula of Colby: (Colby, S.R. Weeds 1967, 15: 20-22),

$$E = X + Y - \frac{X \cdot Y}{100}$$

wherein X and Y express the relative activities obtained for each of the active ingredients. A synergistic effect can be acknowledged if the found activity exceeds
5 calculated activity.

The results are listed in the tables 1 to 4 below and clearly demonstrate that the measured activity generally exceeds the calculated activity. Equal efficacy was observed whenever complete inhibition of fungal growth occurred by one of the active ingredients
10 (I) or (II) alone. The compound of formula (I) used in the experiment was 3-benzo[b]-thien-2-yl)-5,6-dihydro-1,4,2-oxathiazine 4-oxide, *i.e.* compound (1). The compound of formula (II) used in the experiment was *N*-cyclohexyl-benzothiophene-2-carboxamide-S,S-dioxide, *i.e.* compound (2).

15 **Table 1** : Activity of compound (1) and compound (2) and their mixtures against *Aureobasidium pullulans*

Conc. mg/l		Experiment 1 Incubation period: 5 days			Experiment 2 Incubation period: 7 days		
Co. No. (1)	Co. No. (2)	growth mm	activity %		growth mm	activity %	
			measured	calculated		measured	calculated
0.62	0	33	13	-	-	-	-
1.25	0	26	32	-	44	8	-
2.50	0	15	61	-	38	21	-
5.00	0	5	87	-	-	-	-
0.62	2.5	29	24	20	-	-	-
1.25	2.5	22	42	37	42	13	10
2.5	2.5	13	66	64	35	27	22
5	2.5	6	84	88	-	-	-
0.62	5	27	29	27	-	-	-
1.25	5	19	50	42	38	21	14
2.5	5	9	76	67	32	33	26
5	5	5	87	87	-	-	-
0.62	10	22	42	59	-	-	-
1.25	10	14	63	57	32	33	16
2.5	10	6	84	75	26	46	27
5	10	5	87	92	-	-	-

Conc. mg/l		Experiment 1 Incubation period: 5 days			Experiment 2 Incubation period: 7 days		
Co. No. (1)	Co. No. (2)	growth mm	activity %		growth mm	activity %	
			measured	calculated		measured	calculated
0.62	20	16	58	59	-	-	-
1.25	20	10	74	68	21	56	29
2.5	20	5	87	81	12	75	39
5	20	5	87	94	-	-	-
0	2.5	35	8	-	47	2	-
0	5	32	16	-	45	6	-
0	10	24	37	-	44	8	-
0	20	18	53	-	37	23	-
controls DMSO		38			48		

Table 2: Activity of compound (1) and compound (2) and their mixtures against *Aspergillus niger*.

5

Conc. mg/l		Experiment 1 Incubation period: 5 days			Experiment 2 Incubation period: 5 days		
Co. No. (1)	Co. No. (2)	growth mm	activity %		growth mm	activity %	
			measured	calculated		measured	calculated
0.62	0	42	5	-	-	-	-
1.25	0	38	14	-	38	16	-
2.50	0	27	39	-	25	44	-
5.00	0	0	100	-	-	-	-
0.62	2.5	40	9	5	-	-	-
1.25	2.5	35	20	14	37	18	17
2.5	2.5	17	61	39	23	49	46
5	2.5	0	100	100	-	-	-
0.62	5	39	11	9	-	-	-
1.25	5	32	27	18	36	20	17
2.5	5	15	66	41	22	51	46
5	5	0	100	100	-	-	-
0.62	10	33	25	72	-	-	-
1.25	10	30	32	33	30	33	23
2.5	10	8	82	53	7	84	49
5	10	0	100	100	-	-	-

		Experiment 1			Experiment 2		
		Incubation period: 5 days			Incubation period: 5 days		
Conc. mg/l		growth mm	activity %		growth mm	activity %	
Co. No. (1)	Co. No. (2)		measured	calculated		measured	calculated
0.62	20	17	61	72	-	-	-
1.25	20	2	95	74	18	60	46
2.5	20	0	100	82	0	100	64
5	20	0	100	100	-	-	-
0	2.5	44	0	-	44	2	-
0	5	42	5	-	44	2	-
0	10	34	23	-	41	9	-
0	20	13	70	-	29	36	-
controls DMSO		44			45		

Table 3 : Activity of compound (1) and compound (2) and their mixtures against *Sclerophoma entoxylina*.

5

		Experiment 1			Experiment 2		
		Incubation period: 5 days			Incubation period: 7 days		
Conc. mg/l		growth mm	activity %		growth mm	activity %	
Co. No. (1)	Co. No. (2)		measured	calculated		measured	calculated
0.62	0	42	2	-	-	-	-
1.25	0	37	14	-	47	4	-
2.50	0	27	37	-	40	18	-
5.00	0	7	84	-	-	-	-
0.62	2.5	37	14	9	-	-	-
1.25	2.5	34	21	20	45	8	6
2.5	2.5	21	51	42	33	33	20
5	2.5	6	86	85	-	-	-
0.62	5	37	14	18	-	-	-
1.25	5	35	19	28	45	8	8
2.5	5	22	49	47	32	35	22
5	5	5	88	88	-	-	-
0.62	10	30	30	41	-	-	-
1.25	10	27	37	30	38	22	20
2.5	10	19	56	49	22	55	32
5	10	4	91	87	-	-	-

Conc. mg/l		Experiment 1 Incubation period: 5 days			Experiment 2 Incubation period: 7 days		
Co. No. (1)	Co. No. (2)	growth mm	activity %		growth mm	activity %	
			measured	calculated		measured	calculated
0.62	20	22	49	41	-	-	-
1.25	20	18	58	48	27	45	31
2.5	20	9	79	62	15	69	42
5	20	5	88	90	-	-	-
0	2.5	40	7	-	48	2	-
0	5	36	16	-	47	4	-
0	10	35	19	-	41	16	-
0	20	26	40	-	35	29	-
controls DMSO		43			49		

Table 4 : Activity of compound (1) and compound (2) and their mixtures against *Trichoderma viride*.

5

Conc. mg/l		Experiment 1 Incubation period: 5 days			Experiment 2 Incubation period: 3 days		
Co. No. (1)	Co. No. (2)	growth mm	activity %		growth mm	activity %	
			measured	calculated		measured	calculated
0.62	0	49	0	-	-	-	-
1.25	0	49	0	-	43	12	-
2.50	0	48	2	-	35	29	-
5.00	0	35	29	-	-	-	-
0.62	2.5	49	0	0	-	-	-
1.25	2.5	49	0	0	40	18	12
2.5	2.5	42	14	2	34	31	29
5	2.5	36	27	29	-	-	-
0.62	5	49	0	0	-	-	-
1.25	5	49	0	0	39	20	12
2.5	5	43	12	2	33	33	29
5	5	33	33	27	-	-	-
0.62	10	48	2	14	-	-	-
1.25	10	45	8	0	36	27	19
2.5	10	40	18	2	27	45	34
5	10	30	39	29	-	-	-

		Experiment 1			Experiment 2		
		Incubation period: 5 days			Incubation period: 3 days		
Conc. mg/l		growth mm	activity %		growth mm	activity %	
Co. No. (1)	Co. No. (2)		measured	calculated		measured	calculated
0.62	20	39	20	14	-	-	-
1.25	20	36	27	14	31	37	34
2.5	20	29	41	16	12	76	46
5	20	22	55	39	-	-	-
0	2.5	49	0	-	49	0	-
0	5	49	0	-	49	0	-
0	10	49	0	-	45	8	-
0	20	42	14	-	37	24	-
controls DMSO		49			49		

Example 2

- The synergistic activity of the mixtures or compositions comprising a compound of formula (I) and a compound of formula (II) according to the present invention can be demonstrated by comparison with the activity of the active ingredients (I) and (II) alone in preventing destruction of wood by fungi versus the efficacy of either active ingredient alone was tested in a wood stick test with *Aureobasidium pullulans*, *Aspergillus niger*, *Penicillium purpurogenum* and *Sclerophoma entoxylina* as test fungi.
- Oven-dried wood sticks (50 x 12 x 2 mm) of Scots Pine (*Pinus sylvestris*) were dipped during 3 hours in a methanol solution comprising a compound of formula (I), a compound of formula (II), or a combination of a compound of formula (I) and a compound of formula (II), and allowed to dry overnight in a sterile laminar air flow. In each Petri dish one stick was placed on culture medium, PDA PS (Potato Dextrose Agar containing 60 mg penicillin and 200 mg streptomycin), previously seeded with inoculum. Two drops of fungal or spore suspension were pipetted on the upper surface of the stick. The Petri dishes were incubated at 22°C and 70% relative humidity. The test was evaluated after sufficient growth of the fungus on the control sticks. The following score system was used :
- 0 : sticks free of fungal growth
 1 : traces of growth on the stick
 2 : slight growth (5 to 25% of the surface covered)
 3 : moderate growth (25 to 50% of the surface covered)
 4 : vigorous to maximum growth (more tha 50% covered)

25

To calculate synergism results were converted to the next artificial activities :

- 0 : 100% activity
- 1 : 95% activity
- 2 : 75% activity
- 5 3 : 50% activity
- 4 : 0% activity

The expected activities E were calculated by using the so-called formula of Colby:
(Colby, S.R. Weeds 1967, 15: 20-22),

10

$$E = X + Y - \frac{X \cdot Y}{100}$$

15

wherein X and Y express the relative activities obtained for each of the active ingredients. A synergistic effect can be acknowledged if the found activity exceeds calculated activity.

20

The compound of formula (I) used in the experiment was 3-benzo[b]-thien-2-yl)-5,6-dihydro-1,4,2-oxathiazine 4-oxide, *i.e.* compound (1). The compound of formula (II) used in the experiment was *N*-cyclohexyl-benzothiophene-2-carboxamide-S,S-dioxide, *i.e.* compound (2).

Table 5 : Synergistic effects between compound (1) and compound (2) on *Aureobasidium* in a stick test.

compound (1) in ppm	compound (2) in ppm	stick test scores	% overgrown of the sticks	measured (relative) activity %	calculated (expected) activity %
200	0	4	100	0	-
400	0	3	50	50	-
0	200	4	100	0	-
0	400	2	25	75	-
0	800	1	5	95	-
200	200	3	50	50	0
200	400	1	5	95	75
200	800	1	5	95	95
400	400	0	0	100	88
400	800	0	0	100	98
control DMSO		4	100	0	-

Table 6 : Synergistic effects between compound (1) and compound (2) on *Aspergillus* in a stick test.

compound (1) in ppm	compound (2) in ppm	stick test scores	% overgrown of the sticks	measured (relative) activity %	calculated (expected) activity %
200	0	4	100	0	-
400	0	3	50	50	-
0	200	4	100	0	-
0	400	4	100	0	-
0	800	4	100	0	-
200	200	4	100	0	0
200	400	3	50	50	0
200	800	3	50	50	0
400	400	3	50	50	50
400	800	3	50	50	50
control DMSO		4	100	0	-

5 Table 7: Synergistic effects between compound (1) and compound (2) on *Penicillium* in a stick test.


compound (1) in ppm	compound (2) in ppm	stick test scores	% overgrown of the sticks	measured (relative) activity %	calculated (expected) activity %
200	0	4	100	0	-
400	0	2	25	75	-
0	200	4	100	0	-
0	400	3	50	50	-
0	800	2	25	75	-
200	200	4	100	0	0
200	400	2	25	75	50
200	800	1	5	95	75
400	400	2	25	75	88
400	800	1	5	95	94
control DMSO		4	100	0	

Table 8: Synergistic effects between compound (1) and compound (2) on *Sclerophoma* in a stick test.

compound (1) in ppm	compound (2) in ppm	stick test scores	% overgrown of the sticks	measured (relative) activity %	calculated (expected) activity %
200	0	4	100	0	-
400	0	3	50	50	-
0	200	4	100	0	-
0	400	4	100	0	-
0	800	2	25	75	-
200	200	4	100	0	0
200	400	4	100	0	0
200	800	0	0	100	75
400	400	1	5	95	50
400	800	0	0	100	88
Control DMSO		4	100	0	

CLAIMS

1. A composition comprising a compound of formula (I), or a salt thereof,




5

wherein n is 0, 1 or 2; R¹ is hydrogen, C₁₋₄alkyl or benzyl; and R² represents phenyl; phenyl substituted with 1 to 3 substituents independently selected from hydroxyl, halo, C₁₋₁₂alkyl, C₅₋₆cycloalkyl, trihalomethyl, phenyl, C₁₋₅alkoxy, C₁₋₅alkylthio, tetrahydropyranloxy, phenoxy, C₁₋₅alkylcarbonyl, phenylcarbonyl, C₁₋₄alkylsulfinyl, C₁₋₄alkylsulfonyl, carboxy or its alkali metal salt, C₁₋₅alkyloxycarbonyl, C₁₋₅alkylaminocarbonyl, phenylaminocarbonyl, tolylaminocarbonyl, morpholinocarbonyl, amino, nitro, cyano, dioxolanyl or C₁₋₄alkyloxyiminomethyl; naphthyl; pyridinyl; thienyl, preferably when n is not 2; furanyl; or thienyl or furanyl substituted with one to three substituents independently selected from C₁₋₄alkyl, C₁₋₄alkyloxy, C₁₋₄alkylthio, halo, cyano, formyl, acetyl, benzoyl, nitro, C₁₋₄alkyloxy-carbonyl, phenyl, phenylaminocarbonyl and C₁₋₄alkyloxyiminomethyl; or R² represents a radical of formula

10


15



20

wherein X is oxygen or sulfur; Y is nitrogen or CH or C(C₁₋₄alkyloxy); and R³ is hydrogen or C₁₋₄alkyl;

and a compound of formula (II), or a salt thereof,



25

30

wherein R⁸ represents straight-chain or branched alkyl having 1 to 20 carbon atoms, or represents in each case straight-chain or branched halogenoalkyl, cyanoalkyl, hydroxyalkyl, alkoxyalkyl or alkoxy-carbonylalkyl, each of which has 1 to 8 carbon atoms in the individual alkyl moieties, or represents straight-chain or branched alkenyl having 2 to 12 carbon atoms, or represents straight-chain or branched alkynyl having 2 to 12 carbon atoms, or represents cycloalkylalkyl or cycloalkyl,

each of which has 3 to 7 carbon atoms in the cycloalkyl moiety and, in the case of cycloalkylalkyl, 1 to 6 carbon atoms in the straight-chain or branched alkyl moiety, and each of which is optionally monosubstituted to hexasubstituted in the cycloalkyl moiety by identical or different substituents, suitable cycloalkyl substituents in each case being: halogen, in each case straight-chain or branched alkyl having 1 to 4 carbon atoms or in each case straight-chain or branched halogenoalkyl having 1 to 4 carbon atoms and 1 to 9 identical or different halogen atoms; furthermore represents arylalkyl, arylalkenyl, arylalkynyl or aryl, each of which has 6 or 10 carbon atoms in the aryl moiety and, in the cases of arylalkyl, arylalkenyl and arylalkynyl, up to 12 carbon atoms in the respective straight-chain or branched alkyl or alkenyl or alkynyl moiety, each of which is optionally monosubstituted to pentasubstituted in the aryl moiety by identical or different substituents, suitable aryl substituents in each case being: halogen, cyano, nitro, formylamido, in each case straight-chain or branched alkyl, alkoxy or alkylthio, each of which has 1 to 4 carbon atoms, in each case straight-chain or branched halogenoalkyl, halogenoalkoxy, halogenoalkylthio, each of which has 1 to 4 carbon atoms and 1 to 9 identical or different halogen atoms, in each case straight-chain or branched alkylcarbonyl, alkoxy carbonyl, aminocarbonyl, *N*-alkylaminocarbonyl, *N,N*-dialkylaminocarbonyl, alkylcarbonylamino, *N*-alkyl-alkylcarbonylamino, *N*-alkyl-formylcarbonylamino or alkoximinoalkyl, each of which has 1 to 4 carbon atoms in the individual alkyl moieties, and phenyl which is optionally monosubstituted or polysubstituted by identical or different substituents from the group consisting of halogen and/or straight-chain or branched alkyl having 1 to 4 carbon atoms;

R^9 represents hydrogen or straight-chain or branched alkyl which has 1 to 6 carbon atoms and which is optionally monosubstituted or polysubstituted by identical or different substituents, suitable substituents being: hydroxyl, halogen, cyano, and in each case straight-chain or branched alkoxy, alkoxy carbonyl or dialkylamino, each of which has 1 to 6 carbon atoms in the individual alkyl moieties; or

R^8 and R^9 together with the nitrogen atom to which they are bonded represent a saturated 5- to 7-membered heterocycle which is optionally monosubstituted or polysubstituted by identical or different substituents and which can optionally contain 1 or 2 further hetero atoms selected from the group consisting of nitrogen, oxygen and sulphur, suitable substituents in each case being: halogen, in each case straight-chain or branched alkyl, alkoxy or alkoxy carbonyl having in each case 1 to 4 carbon atoms or straight-chain or branched halogenoalkyl having 1 to 4 carbon atoms and 1 to 9 identical or different halogen atoms;

R⁴, R⁵, R⁶ and R⁷ independently of one another in each case represent hydrogen, halogen, cyano, nitro or in each case straight-chain or branched alkyl, alkoxy, alkylthio, halogenoalkyl, halogenoalkoxy or halogenoalkylthio each of which has 1 to 6 carbon atoms and, in the case of halogenoalkyl, halogenoalkoxy or halogenoalkylthio, 1 to 13 identical or different halogen atoms; in quantities producing a mutual synergistic fungicidal effect, and a carrier.

2. A composition according to claim 1 wherein the compound of formula (I) is 3-(benzo[b]thien-2-yl)-5,6-dihydro-1,4,2-oxathiazine, 4-oxide, or a salt form thereof, and the compound of formula (II) is *N*-cyclohexyl-benzothiophene-2-carboxamide-*S,S*-dioxide, or a salt form thereof.
3. A composition according to any of claims 1 to 2 wherein the ratio by weight between the compound of formula (I) and the compound of formula (II) is from 50:1 to 1:50.
4. A composition according to any of claims 1 to 2 wherein the ratio by weight between the compound of formula (I) and the compound of formula (II) is from 10:1 to 1:10.
5. A composition according to any of claims 1 to 2 wherein the ratio by weight between the compound of formula (I) and the compound of formula (II) is from 1:4 to 1:2.
6. A composition according to any of claims 1 to 5 further comprising a copper compound.
7. A composition according to any of claims 1 to 5 further comprising a fungicidally active triazole.
8. A product containing a compound of formula (I), or a salt thereof, and a compound of formula (II) or a salt thereof, as a combination for simultaneous, separate or sequential use in fungicidal applications.
9. A process for preparing a synergistic composition as claimed in any of claims 1 to 7, characterized in that the active ingredients are intimately mixed with the carrier.
10. Use of a composition as defined in any of claims 1 to 7 for the protection of wood, wood products, biodegradable materials and coatings.

INTERNATIONAL SEARCH REPORT

Inte. lutional Application No

PCT/EP 98/06495

A. CLASSIFICATION OF SUBJECT MATTER
 IPC 6 A01N43/88 B27K3/50 //(A01N43/88,43:12)

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 A01N

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DE 195 48 873 A (BAYER AG) 3 July 1997 see page 2, line 28 - line 33 see page 3, line 36 - line 37 see claim 5 ---	1-10
A	WO 95 06043 A (UNIROYAL CHEM CO INC ;UNIROYAL CHEMICAL LTD (CA)) 2 March 1995 cited in the application see page 1, line 10 - line 22 see page 24; example 87 ---	1-10
A	WO 95 05739 A (JANSSEN PHARMACEUTICA NV ;GESTEL JOZEF FRANS ELISABETHA (BE)) 2 March 1995 cited in the application see page 1, line 7 - page 2, line 9 see page 8, line 2 - line 36 ---	1-10
	-/--	

Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

10 February 1999

Date of mailing of the international search report

18/02/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+31-70) 340-3016

Authorized officer

Lamers, W

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 98/06495

C. (Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4 569 690 A (BROUWER WALTER G ET AL) 11 February 1986 see the whole document -----	1-10
A	WO 95 06091 A (BAYER AG ;ELBE HANS LUDWIG (DE); PAULUS WILFRIED (DE); SCHRAGE HEI) 2 March 1995 see page 1, line 3 - line 7 see page 3, line 1 - page 15, line 9 -----	1-10
A	EP 0 512 349 A (BAYER AG) 11 November 1992 cited in the application see page 3, line 1 - line 38 see page 10, line 41 - line 56 see page 17; example 37 -----	1-10

1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 98/06495

Patent document cited in search report	A	Publication date	Patent family member(s)	Publication date
DE 19548873	A	03-07-1997	NONE	
<hr/>				
WO 9506043	A	02-03-1995	AT 154017 T	15-06-1997
			AU 688371 B	12-03-1998
			AU 7640194 A	21-03-1995
			BR 9407561 A	31-12-1996
			CA 2169654 A	02-03-1995
			CN 1133039 A	09-10-1996
			CZ 9600560 A	17-07-1996
			DE 69403667 D	10-07-1997
			DE 69403667 T	16-10-1997
			DK 715625 T	15-12-1997
			EP 0715625 A	12-06-1996
			ES 2102878 T	01-08-1997
			FI 960829 A	19-04-1996
			GR 3024590 T	31-12-1997
			HU 74480 A, B	28-01-1997
			JP 2761441 B	04-06-1998
			JP 8509986 T	22-10-1996
			NO 960696 A	21-02-1996
			NZ 273187 A	27-05-1998
			PL 313136 A	10-06-1996
			US 5777110 A	07-07-1998
			ZA 9406450 A	30-06-1995
<hr/>				
WO 9505739	A	02-03-1995	AP 568 A	25-11-1996
			AT 163836 T	15-03-1998
			AU 680294 B	24-07-1997
			AU 7654494 A	21-03-1995
			BR 9407567 A	31-12-1996
			CA 2168357 A	02-03-1995
			CN 1129894 A	28-08-1996
			CZ 9600463 A	15-05-1996
			DE 69408998 D	16-04-1998
			DE 69408998 T	25-06-1998
			EP 0715495 A	12-06-1996
			ES 2113674 T	01-05-1998
			FI 960848 A	23-02-1996
			GR 3026333 T	30-06-1998
			HU 74291 A, B	28-11-1996
			JP 9501688 T	18-02-1997
			NO 960728 A	23-02-1996
			NZ 273306 A	27-07-1997
			PL 313133 A	10-06-1996
			SK 23296 A	05-06-1996
			US 5712275 A	27-01-1998
			ZA 9406449 A	26-02-1996
<hr/>				
US 4569690	A	11-02-1986	AU 544881 B	20-06-1985
			AU 1961883 A	05-04-1984
			BR 8305330 A	08-05-1984
			CA 1273921 A	11-09-1990
			DD 215781 A	21-11-1984
			EP 0104940 A	04-04-1984
			GB 2127817 A, B	18-04-1984
			GR 78990 A	02-10-1984
			JP 59080670 A	10-05-1984
			US 4675044 A	23-06-1987

INTERNATIONAL SEARCH REPORT

Information on patent family members

Inter. Application No

PCT/EP 98/06495

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9506091 A	02-03-1995	DE 4328074 A	23-02-1995
		AU 7611894 A	21-03-1995
		CA 2169767 A	02-03-1995
		DE 59404547 D	11-12-1997
		EP 0714420 A	05-06-1996
		JP 9501723 T	18-02-1997
		US 5622546 A	22-04-1997
		-----	-----
EP 0512349 A	11-11-1992	DE 4115184 A	12-11-1992
		DE 59205329 D	28-03-1996
		DK 512349 T	17-06-1996
		ES 2083614 T	16-04-1996
		GR 3019005 T	31-05-1996
		JP 5178852 A	20-07-1993
		MX 9201994 A	01-11-1992
		PL 168441 B	29-02-1996
		US 5244893 A	14-09-1993
		-----	-----