



(86) Date de dépôt PCT/PCT Filing Date: 1995/02/28
(87) Date publication PCT/PCT Publication Date: 1995/08/31
(45) Date de délivrance/Issue Date: 2001/08/07
(85) Entrée phase nationale/National Entry: 1996/07/17
(86) N° demande PCT/PCT Application No.: US 95/02811
(87) N° publication PCT/PCT Publication No.: WO 95/23192
(30) Priorité/Priority: 1994/02/28 (08/203,108) US

(51) Cl.Int.⁶/Int.Cl.⁶ C08K 9/06, C09C 1/36, C09C 3/12,
C08L 23/06
(72) Inventeurs/Inventors:
Musiano, Joseph Anthony, US;
Holtzen, Dwight Alan, US;
Tooley, Patricia Ann, US
(73) Propriétaire/Owner:
E.I. DU PONT DE NEMOURS AND COMPANY, US
(74) Agent: DIMOCK STRATTON CLARIZIO LLP

(54) Titre : AMELIORATION DE L'APTITUDE DE POLYMERES AU TRAITEMENT ET DE LEUR RESISTANCE AU
DEVELOPPEMENT D'IMPERFECTIONS PAR INCORPORATION DE PIGMENTS TRAITES AU SILANE
(54) Title: IMPROVED PROCESSIBILITY AND LACING RESISTANCE WHEN SILANIZED PIGMENTS ARE
INCORPORATED IN POLYMERS

(57) Abrégé/Abstract:

White-pigmented polymers (particularly, polyolefins such as polyethylene) containing white pigments treated with at least one silane or a mixture of at least one silane and at least one polysiloxane are disclosed to improve processibility in compounding and improve performance properties such as lacing resistance in a polymeric matrix.





INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification⁶ : C09C 1/36, C08K 9/06</p>	A1	<p>(11) International Publication Number: WO 95/23192 (43) International Publication Date: 31 August 1995 (31.08.95)</p>
<p>(21) International Application Number: PCT/US95/02811 (22) International Filing Date: 28 February 1995 (28.02.95) (30) Priority Data: 08/203,108 28 February 1994 (28.02.94) US (71) Applicant: E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US). (72) Inventors: TOOLEY, Patricia, Ann; 330 Park Lane, Wilmington, DE 19804-2354 (US). HOLTZEN, Dwight, Alan; 1133 Old Baltimore Pike, Newark, DE 19702-1105 (US). MURIANO, Joseph, Anthony; 3 Fanwood Drive, New Castle, DE 19720-3708 (US). (74) Agents: YUN, Caroline, J. et al.; E.I. du Pont de Nemours and Company, Legal/Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).</p>	<p>(81) Designated States: AM, AU, BB, BG, BR, BY, CA, CN, CZ, EE, FI, GE, HU, JP, KG, KP, KR, KZ, LK, LR, LT, LV, MD, MG, MN, MX, NO, NZ, PL, RO, RU, SG, SI, SK, TJ, TT, UA, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ, UG).</p> <p>Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p> <p style="text-align: center; font-size: 2em;">2181432</p>	
<p>(54) Title: IMPROVED PROCESSIBILITY AND LACING RESISTANCE WHEN SILANIZED PIGMENTS ARE INCORPORATED IN POLYMERS</p>		
<p>(57) Abstract</p> <p>White-pigmented polymers (particularly, polyolefins such as polyethylene) containing white pigments treated with at least one silane or a mixture of at least one silane and at least one polysiloxane are disclosed to improve processibility in compounding and improve performance properties such as lacing resistance in a polymeric matrix.</p>		

2181432

TITLE**IMPROVED PROCESSIBILITY AND LACING RESISTANCE WHEN
SILANIZED PIGMENTS ARE INCORPORATED IN POLYMERS**

5

BACKGROUND OF THE INVENTION

The present invention relates to white-pigmented polymers (particularly, polyolefins such as polyethylene) containing white pigments treated with an organosilicon compound to improve processibility in compounding and improve performance properties such as lacing resistance in a polyolefin matrix.

Treatment of TiO₂ pigment with organosilicon compounds to improve dispersibility in a polymer matrix is well known in the art. For example, U.S. Patents 4,061,503 and 4,151,154 disclose enhanced dispersibility of TiO₂ in paints and plastics. Therein, the TiO₂ is surface treated with a silane possessing at least two hydrolyzable groups bonded to silicon and an organic group containing a polyalkylene oxide group.

In addition, U.S. Patent 4,810,305 discloses a modified hydrophobic pigment or filler containing 0.05 to 10 weight % of an organopolysiloxane, with improved dispersibility in synthetic resins.

However, deficiencies in the prior art include, but are not limited to, (1) unacceptable processibility, i.e., dispersibility of TiO₂ pigment in a polymeric matrix at slow rates; and (2) lacing, i.e., development of imperfections in a polyolefin matrix. Lacing occurs as a result of volatiles released from the pigment during high temperature polyolefin fabrication processes. Lacing may also be attributable to TiO₂ concentrates picking up moisture. A further disadvantage is that higher loadings of TiO₂ pigment in a polymer concentrate result in slower processing rates.

It has been found that the above combined disadvantages of the prior art can be overcome by the present invention.

30

SUMMARY OF THE INVENTION

In accordance with one aspect of the present invention, there is provided a highly loaded polymer matrix comprising polymer resin and 50 to 87 % by weight silanized TiO₂ pigment, based on the weight of the polymer matrix, exhibiting enhanced processibility, wherein the TiO₂ pigment has a coating of 0.1 to 5% by weight, based

35

on the weight of the silanized TiO_2 , of at least one silane compound having the formula: $\text{R}_x\text{Si}(\text{R}')_{4-x}$ wherein, R is a nonhydrolyzable aliphatic, cycloaliphatic or aromatic group having 8-20 carbon atoms; R' is a hydrolyzable group selected from alkoxy, halogen, acetoxy or hydroxy or mixtures thereof; and $x = 1$ to 3.

DETAILED DESCRIPTION

The TiO_2 pigments useful in the present invention generally are in the rutile or anatase crystalline form. It is commonly made by either a chloride process or a sulfate process. TiCl_4 is oxidized to TiO_2 particles in the chloride process. Sulfuric acid and ore containing titanium are dissolved, and the resulting solution goes through a series of steps to yield TiO_2 , in the sulfate process. Both the sulfate and chloride processes are described in greater detail in "The Pigment Handbook", Vol. 1, 2nd Ed., John Wiley & Sons, NY (1988).

The optimum average particle size can range from about 0.005 to about 1 micron. The TiO_2 pigments may also contain ingredients added thereto to further improve dispersibility characteristics or other properties such as durability. Thus, by way of example, but not limited thereto, the pigment may contain additives and/or inorganic oxides, such as aluminum, silicon or tin as well as triethanolamine, trimethylolpropane, phosphates, etc.

"Silanized" TiO_2 is defined herein to refer to TiO_2 treated with either at least one silane, or a mixture of at least one silane and at least one polysiloxane (collectively referred to herein as organosilicon compounds).

Suitable silanes have the formula:



wherein

R is a nonhydrolyzable aliphatic, cycloaliphatic or aromatic group having at least 1 to about 20 carbon atoms;

R' is a hydrolyzable group such as an alkoxy, halogen, acetoxy or hydroxy or mixtures thereof; and

$x = 1$ to 3.

For example, silanes useful in carrying out the invention include octyltriethoxysilane, nonyltriethoxysilane, decyltriethoxysilane,

dodecyltriethoxysilane, tridecyltriethoxysilane, tetradecyltriethoxysilane, pentadecyltriethoxysilane, hexadecyltriethoxysilane, heptadecyltriethoxysilane and octadecyltriethoxysilane. Additional examples of silanes include, R = 8-18 carbon atoms; R' = chloro, methoxy, hydroxy or mixtures thereof; and x = 1 to 3. Preferred silanes are R = 8-18 carbon atoms; R' = ethoxy; and x = 1 to 3. The R = 8-18 carbon atoms is preferred for enhanced processibility. R' = ethoxy is preferred for ease of handling. Surprisingly, lower chain alkyl silanes resulted in longer processing times. Mixtures of silanes are contemplated equivalents. Weight content of the silane, based on total silanized pigmentary TiO₂ is typically about 0.1 to about 5 weight %, preferably about 0.5 to about 1.5 weight %. In excess of 5 weight % may be used but no particular advantage is observed.

In an alternative embodiment, a mixture of at least one silane with at least one polysiloxane is useful in carrying out the invention. Suitable polysiloxanes have the formula:



wherein

R is organic or inorganic groups;

n = 0-3; and

m ≥ 2.

For example, polydimethylsiloxane (PDMS), vinyl phenylmethyl terminated dimethyl siloxanes, divinylmethyl terminated polydimethyl siloxane and the like are suitable polysiloxanes. PDMS is a preferred polysiloxane. The silane useful in the mixture may be the silane described above with R = 1-8 carbon atoms, R' = alkoxy and x = 1 preferred. Weight content of the silane and polysiloxane, based on total silanized pigmentary TiO₂, is about 0.1 to about 5.0 weight %, preferably from about 1 to 3 weight %. Especially preferred is about 0.5 to 1 weight % silane with R = 4 or 8 carbon atoms, R' = alkoxy, and x = 1; and 1 weight % PDMS. The ratio of silane to polysiloxane can be 1 silane:2 polysiloxane up to 2 silane:1 polysiloxane. An especially preferred ratio is 1 silane: 1 polysiloxane.

The silane and polysiloxane are commercially available or can be prepared by processes known in the art such as those described in "Organosilicon Compounds", S. Pawlenko, et al., New York (1980).

The method of addition is not especially critical and the TiO₂ pigment may be treated with the silane in a number of ways. For

example, the silane addition can be made neat or prehydrolyzed to a dry pigmentary base, from a slurry, a filtration step, during drying or at a size operation such as a fluid energy mill, e.g., micronizer, or media mill as described in greater detail in copending application entitled "IMPROVED SLURRY PROCESS FOR
5 PREFARING SILANIZED TiO₂ PIGMENTS, USING A MEDIA MILL", the teachings of which are found in U.S. Patent No. 5,501,732, issued March 26, 1996, or post blending after micronizing. For example, U.S. 3,834,924 describes organosilane and pigment dispersion mixed or blended directly in a suitable solids mixing apparatus. An example of post blending is described in greater detail in U.S. Patents 3,915,735 and
10 4,141,751. The polysiloxane addition can be made in conjunction with the silane or post addition to the silanized pigment. The silane addition and polysiloxane addition is described in greater detail below. If water, either a liquid or vapor (steam), is present as a component of the process stream, hydrolysis of the hydrolyzable groups of the silane will occur and the silane coating will bond to the
15 TiO₂ base. Prehydrolyzing the silane is a preferred step in treating the TiO₂ pigment with the silane. If the silane is added neat to the TiO₂ base, then moisture adsorbed on the TiO₂ will effect the hydrolysis, but at a lower rate than if excess moisture is present. Hydrolysis of silanes is described in greater detail in "Organofunctional Silanes" by Union Carbide (1991).

20
Polymers which are suitable for use in the present invention include, by way of example but not limited thereto, polymers of ethylenically unsaturated monomers including olefins such as polyethylene, polypropylene, polybutylene, and copolymers of ethylene with higher olefins such as alpha olefins containing 4 to 10
25 carbon atoms or vinyl acetate, etc.; vinyls such as polyvinyl chloride, polyvinyl esters such as polyvinyl acetate, polystyrene, acrylic homopolymers and copolymers; phenolics; alkyds; amino resins; epoxy resins, polyamides, polyurethanes; phenoxy resins, polysulfones; polycarbonates; polyether and chlorinated polyesters; polyethers; acetal resins; polyimides; and polyoxyethylenes. The polymers according
30 to the present invention also include various rubbers and/or elastomers either natural or synthetic polymers based on copolymerization, grafting, or physical blending of various diene monomers with the above-mentioned polymers, all as generally known in the art. Thus generally, the present invention is useful for any such white-pigmented plastic or elastomeric compositions (collectively referred to
35 herein as a white-pigmented polymers). For example, but not by way of limitation,

the invention is felt to be particularly useful for polyolefins such as polyethylene, polypropylene, polyvinyl chloride, polyamides and polyesters.

As used herein, "high loaded" TiO₂ may vary widely for each polymeric matrix but will be in a well known range for those skilled in the art. For example, in a polyolefin matrix, a high loaded TiO₂ would be 50 or above % by weight TiO₂ pigment, based on the weight of the polyolefin matrix.

A wide variety of conventional additives may be included in the polymers as is necessary, desirable or conventional for the intended end use. Such additives include, but are not limited to, antioxidants, light stabilizers, lubricants, thermal processing additives and the like.

TiO₂ coated with organosilicon compounds can be incorporated into a melt-fabricable polymer to form the polymer composition of this invention by any melt compounding technique known in the art. Generally, TiO₂ and polymer resin are brought together and then mixed in a blending operation that applies shear to the polymer melt. The polymer resin is usually available in the form of powder, granules, pellets, or cubes. Commonly, TiO₂ and resin are first combined while the resin is in the solid state (not melted) and dry-blended in some way. This can be done in simple ways, such as by shaking in a bag or tumbling in a closed container, or in more sophisticated ways such as by using blenders having agitators or paddles. TiO₂ and polymer resin can be brought together by co-feeding the materials to internal mixers and allowing a screw to mix them together before the resin reaches the molten state. The melt blending of TiO₂ and polymer resin can be done using known equipment, such as single-screw extruders, twin-screw extruders, internal mixers, and the like. Internal mixers are commonly used. The melt blending can be done as part of the process of forming a finished article of the composition, as by melt extrusion. Alternatively, the melt blending can be done in a preliminary step, optionally isolating the polymer composition, e.g., as cubes, followed by forming a finished article in a subsequent process. As one skilled in the art will recognize, there are many possible variations of the technique for preparing polymer compositions of the invention. One may, for example, first prepare a concentrate having high TiO₂ concentration, i.e., one composition of the invention, and then combine the concentrate with polymer resin containing no TiO₂ to obtain another composition of the invention.

The highly loaded polymer concentrates are made as described above with the desirable weight % for the intended end use. For example, in polyolefin

concentrates, about 50-87% by weight concentrate may be used to opacify. The concentrate is "let down" into the polyolefin. Used herein, "let down" refers to a ratio or percent of resin mixed with concentrate. Let down may be accomplished in a number of ways and is described in great detail in "Film Extrusion Manual" (1992).

5 For example, in lacing evaluation, a 50 wt.% to 87 wt.% concentrate may be let down to about 0.2 to about 20 weight % by dry mixing polyolefin and extruding at a specific processing temperature and casting it into a film. Pigment performance is then evaluated in an end use application.

10 The highly loaded silanized pigmentary TiO₂ exhibits outstanding processibility in a polymeric matrix and lacing resistance when incorporated into a polyolefin matrix. Additional advantages observed are increased bulk density, lower viscosity, excellent dispersibility, moisture resistance, and excellent optical properties such as high tint strength.

15 The following examples are construed as illustrative and not limitative of the remainder of the disclosure in any way whatsoever. Farrel BR Banbury®-type mixers (available from Farrel Corp., Ansonia, CT, USA) have been used in the Examples. Broad range internal mixers as known in the art are contemplated equivalents. For example, Farrel Continuous Mixers (FCM) (available from Farrel
20 Corp., Ansonia, CT, USA) and twin screw extruders are equally applicable.

Bulk density is given as grams per cubic centimeter of uncompacted pigment. A pigment bulk density below about 0.6 will result in difficult solids handling in polymer compounding. For rapid compounding of TiO₂ and a polymer in a Banbury®-type mixer, a bulk density above about 0.6 is desirable.

25 Total flux time is a measure of processing time, or time to disperse, in a Banbury®-type mixer.

Viscosity, at 180 degrees Celsius, of product from the Banbury®-type mixer, was measured at a shear rate of 550 1/sec. Viscosity was measured with a Kayeness capillary rheometer (available from Kayeness Corp., Honey Brook, PA,
30 USA).

EXAMPLESPREPARATION OF A CONCENTRATE, i.e., MASTERBATCH

5 In the following examples, a 70 wt.% compound of a dry mix TiO₂
balance polyethylene was prepared in the following manner. First, a dry mix of
TiO₂/balance polyethylene was prepared via blending of 1562 grams of the TiO₂
with 670 grams of polyethylene. The polyethylene used for the experiments was a
low density polyethylene supplied by Quantum U.S.I. Chemicals--Code = NA212
10 (Cincinnati, OH, USA).

The dry mix of TiO₂/polyethylene was added to the feed hopper of a
laboratory Farrel BR Banbury®-type Mixer (chamber capacity = about 1100-about
1200 cc). The dry mix was then discharged into the Mixer. Stock pressure equaled
56 psi, driven rotor speed = 230 rpm, cooling water = 85°F. The Mixer was
15 equipped with recording equipment for batch temperature, power consumption, ram
pressure, and heat loss.

The mixture of TiO₂/polyethylene was subsequently processed until
the TiO₂ dispersed into the melted resin (temperature = for example 220°F) defined
above as total flux time. The compound was then discharged from the mixer.
20

EXAMPLE 1

3000 grams of neutralized pigmentary rutile TiO₂ were weighed into a
pan and sprayed with 30 grams of butyl trimethoxy silane, as supplied by Union
Carbide now Osi Specialty, Inc. (Tarrytown, NY, USA).

25 The treated pigment was ground in a fluid energy mill, e.g., micronizer
with superheated steam.

The micronized pigment was mixed in a Patterson-Kelley V-Blender
with 30 grams of polydimethylsiloxane, as supplied by Petrach now Huls Corp.
(Piscataway, NJ, USA).

30 The treated TiO₂ polyethylene concentrate was prepared as described
above.

EXAMPLE 2

35 Same as Example 1 except that octyl triethoxy silane was used in place
of butyl trimethoxy silane.

EXAMPLE 3

Neutralized pigmentary rutile TiO₂ was treated with about 1 wt% of each of octyl triethoxy silane and polydimethylsiloxane as for Example 1, except that these compounds were added at the micronizer, through existing nozzles in a grinding chamber. The treated pigment and low density polyethylene were then mixed and processed in a Banbury®-type mixer to form a 70 wt% masterbatch, as described above.

EXAMPLE 4

Neutralized pigmentary rutile TiO₂ was treated with about 1 wt% of octyl triethoxy silane, by spraying, as for Example 1. There was no treatment with polydimethylsiloxane. The treated pigment was micronized, and used for processing in a Banbury®-type mixer to a 70 wt% polyethylene masterbatch, as described above.

COMPARATIVE EXAMPLE 5 (C-5)

Pigmentary rutile TiO₂ and low density polyethylene were mixed and processed in a Banbury®-type mixer to form a 70 wt% polyethylene masterbatch, as described above.

The results of the tests on the masterbatches from Examples 1-5 are summarized in the table below.

<u>Example</u>	<u>Bulk Density g/cc</u>	<u>Total Flux (s)</u>	<u>Viscosity (p)</u>
1	0.96	26	3675
2	1.01	26.2	3681
3	0.78	24.5	3479
4	0.97	28.2	3927
C-5	0.54	37.6	4459

This data demonstrated the processing advantages of organosilicon compound treated pigments (Examples 1-4) versus a non-treated pigment (Example C-5) in a 70 wt.% TiO₂/polyethylene masterbatch. Shown in the table

are bulk density improvements realized by the organosilicon compound treatments, total flux time improvements, and viscosity improvements for these materials over non-treated.

5

EXAMPLE 6

Dried, crushed, meshed pigmentary rutile TiO₂ filter cake was sprayed with about 1 wt. % of neat octyl triethoxy silane, as supplied by Osi.

The treated pigment was micronized and used for processing in a Banbury®-type mixer to a 70 wt. % polyethylene masterbatch, as described above.

10

COMPARATIVE EXAMPLE 6A

Same as Example 6 except butyl trimethoxy silane was used in place of octyltriethoxysilane. The results of the tests on the masterbatches from Examples 6-6A are summarized in the table below.

15

<u>Example</u>	<u>Bulk Density g/cc)</u>	<u>Total Flux (s)</u>	<u>Viscosity (p)</u>
6	0.97	28	3927
6A	0.77	48	3921

This data demonstrated the differences for a higher chain alkyl silane (Example 6) versus a lower chain alkyl silane. Surprisingly, the lower chain alkyl silanes resulted in longer processing times. The lower chain alkyl silane realized a 70% increase in processing time over the higher chain alkyl silane.

20

EXAMPLE 7

3000 grams of pigmentary rutile TiO₂ was treated with 1 weight % (30 grams) octyltriethoxysilane via spraying. Material was processed in a Banbury®-type mixer at 70 weight % in a polyethylene masterbatch as described above.

25

COMPARATIVE EXAMPLE 7A

3000 grams of pigmentary rutile TiO₂ was treated with 1 weight % (30 grams) polydimethylsiloxane (PDMS) via spraying. Material was processed in a

30

Banbury®-type mixer at 70 weight % in a polyethylene masterbatch as described above.

EXAMPLE 8

5 Pigmentary rutile TiO₂ was treated with 1 weight % octadecyltriethoxy silane (available from Huls) via spraying. Material was processed in a Banbury®-type mixer at 70 weight % in a polyethylene masterbatch as described above.

10 The results of tests on the masterbatches from Examples 7, 7A and 8 are summarized in the table below.

<u>Example</u>	<u>Bulk Density g/cc)</u>	<u>Total Flux (s)</u>	<u>Viscosity (p)</u>
7	0.63	30.2	2968
7A	0.59	35.3	3491
8	0.58	33	2746

15 This data demonstrated a series of post-blended higher chain alkyl silane (Examples 7 and 8) and siloxane (Comparative Example 7A) treated materials. For the two silane treated materials (Examples 7 and 8) treated with a higher chain alkyl silane, final product viscosities were nearly identical. For the siloxane only (Comparative Example 7A) treated material viscosity and processing time were higher.

EXAMPLE 9

20 Silanized pigment, octyltriethoxysilane, and polyester were dry blended in a double cone blender for 5 minutes to yield a 50/50 mixture. This mixture was added to a feed hopper of a Farrel Continuous Mixer (FCM). The mixture of treated TiO₂/polyester was subsequently processed until the treated
25 TiO₂ dispersed into the melted resin (temperature = 550°F). Observable flow of the concentrate was smooth and continuous.

COMPARATIVE EXAMPLE 9A

An untreated anatase pigment, Kronos 1072 (available from Kronos, Leverkusen, Germany), was dry blended, fed and processed in the FCM as in Example 9. Observable flow of the concentrate was not smooth. Continuous flow was not attained.

LACING

Lacing occurs as a function of pigment volatility at specific wt % pigment loadings and processing temperature. For polyethylene films pigmented with titanium dioxide, 20 wt % TiO₂ in the film processed at temperatures of 620°F or greater will discern readily lacibility of the film. Typically, materials are rated 10 if they do not lace, and below 10 if they begin to lace.

Two materials are compared in the following for lacing.

EXAMPLE 10

By weight, 20% of an octyltriethoxy silane treated TiO₂ was compounded into balance polyethylene. Material was extruded on a Killion single screw extruder through a film die at 620°F. Evaluation of the film on a light box revealed superior integrity with no thin spots or pin-holes. Rating of material equaled 10. Lacing resistance was comparable to the industry standard, Ti-Pure® R-101, available from E. I. du Pont de Nemours and Company, Wilmington, DE, USA.

COMPARATIVE EXAMPLE 10A

By weight, 20% of a siloxane treated pigment RCL-69, (available from SCM, Baltimore, MD, USA) was compounded into balance polyethylene. Material was extruded on a Killion single screw extruder through a film die at 620°F. Material exhibited thin spots under a light box. Material was rated as a 7.

Having thus described and exemplified the invention with a certain degree of particularity, it should be appreciated that the following claims are not to be so limited but are to be afforded a scope commensurate with the wording of each element of the claim and equivalents thereof.

CLAIMS**2 1 8 1 4 3 2****What is Claimed is:**

1. A highly loaded polymer matrix comprising polymer resin and 50 to 87% by weight silanized TiO₂ pigment, based on the weight of the polymer matrix, exhibiting enhanced processibility, wherein the TiO₂ pigment has a coating of 0.1 to 5% by weight, based on the weight of the silanized TiO₂, of at least one silane compound having the formula:



wherein,

R is a nonhydroxlyzable aliphatic, cycloaliphatic or aromatic group having 8-20 carbon atoms;

R' is a hydrolyzable group selected from alkoxy, halogen, acetoxy or hydroxy or mixtures thereof; and

x= 1 to 3.

2. The polymer matrix of Claim 1, wherein R is aliphatic having 8-18 carbons, R' is alkoxy, and x = 1 to 3.

3. The polymer matrix of Claims 1 to 3, wherein the polymer resin is polyethylene.

4. The polymer matrix of any one of Claim 1 or Claim 2, wherein the silanized pigment is present in the amount of about 70 to about 82% by weight.

5. A process for preparing a highly loaded polymer matrix comprising TiO₂ pigment, comprising the steps of:

(a) coating TiO₂ pigment with at least one silane compound having the formula:



wherein,

R is a nonhydroxlyzable aliphatic, cycloaliphatic or aromatic group having 8-20 carbon atoms;

R' is a hydrolyzable group selected from alkoxy, halogen, acetoxy or hydroxy or mixtures thereof; and

x= 1 to 3;

to form coated TiO₂ pigment; and

A

(b) mixing the coated TiO₂ pigment with a polymer resin to form a highly loaded polymer matrix comprising 50 to 87% by weight coated TiO₂ pigment.

6. The process of Claim 5, wherein the silane compound is hydrolyzed and forms a chemical bond with the TiO₂ pigment.

7. A process for silanizing TiO₂ pigment and for highly loading the silanized TiO₂ pigment in a polymer matrix, comprising the steps of:

(a) adding a silane compound to a slurry comprising TiO₂ pigment and water, the silane compound having the formula:



wherein,

R is a nonhydrolyzable aliphatic, cycloaliphatic or aromatic group having 8-20 carbon atoms;

R' is a hydrolyzable group selected from alkoxy, halogen, acetoxy or hydroxy or mixtures thereof; and

x= 1 to 3;

to form silanized TiO₂ pigment; and

(b) mixing the silanized TiO₂ pigment with a polymer resin to form a highly loaded polymer matrix comprising 50 to 87% by weight silanized TiO₂ pigment.

8. A process for silanizing TiO₂ pigment and for highly loading the silanized TiO₂ pigment in a polymer matrix, comprising the steps of:

(a) silanizing TiO₂ pigment in a slurry comprising TiO₂ pigment and water by treating TiO₂ pigment with a mixture of a silane compound and a polysiloxane compound, the silane compound having the formula:



wherein,

R is a nonhydrolyzable aliphatic, cycloaliphatic or aromatic group having 8-20 carbon atoms;

R' is a hydrolyzable group selected from alkoxy, halogen, acetoxy or hydroxy or mixtures thereof; and

x = 1 to 3; and

(b) mixing the silanized TiO₂ pigment with a polymer resin to form a highly loaded polymer matrix comprising 50 to 87% by weight silanized TiO₂ pigment.

9. The process of Claims 7 or 8, wherein the highly loaded polymer matrix comprises 70 to 87% by weight silanized TiO₂ pigment.

10. The process of Claim 9, wherein the polymer resin is polyethylene.

11. The process of Claims 7 or 8, wherein the silane compound is octyltriethoxysilane.

12. The process of Claims 7 or 8, wherein the silane compound is octyltrichlorosilane.

13. The process of Claim 8, wherein the polysiloxane compound has the formula:



wherein,

R is an organic or inorganic group;

n=0-3; and

m≥2.

14. The process of Claims 7 or 8, wherein R is an aliphatic having 8-18 carbons, R' is methoxy, ethoxy, chloro, hydroxy, or mixtures thereof, and x = 1 to 3.

15. The process of Claims 7 or 8, wherein the polymer resin is selected from the group consisting of polyolefins, polyesters, polyvinyl chlorides and polystyrenes.

16. A process for silanizing TiO₂ pigment and for highly loading the silanized TiO₂ pigment in a polymer matrix, comprising the steps of:

(a) treating TiO₂ pigment with a silane compound having the formula:



wherein,

R is a nonhydrolyzable aliphatic, cycloaliphatic or aromatic group having 8-20 carbon atoms;

R' is a hydrolyzable group selected from alkoxy, halogen, acetoxy or hydroxy or mixtures thereof; and

x = 1 to 3; and

(b) mixing the silanized TiO₂ pigment with a polymer resin to form a highly loaded polymer matrix comprising 50 to 87% by weight silanized TiO₂ pigment.

17. A process for silanizing TiO₂ pigment and for highly loading the silanized TiO₂ pigment in a polymer matrix, comprising the steps of:

(a) drying TiO₂ pigment and adding to the pigment during drying a silane compound having the formula:



wherein,

R is a nonhydrolyzable aliphatic, cycloaliphatic or aromatic group having 8-20 carbon atoms;

R' is a hydrolyzable group selected from alkoxy, halogen, acetoxy or hydroxy or mixtures thereof; and

x = 1 to 3; and

(b) mixing the silanized TiO₂ pigment with a polymer resin to form a highly loaded polymer matrix comprising 50 to 87% by weight silanized TiO₂ pigment.

18. A process for silanizing TiO₂ pigment and for highly loading the silanized TiO₂ pigment in a polymer matrix, comprising the steps of:

(a) mixing a silane compound with water, the silane compound having the formula:



wherein,

R is a nonhydrolyzable aliphatic, cycloaliphatic or aromatic group having 8-20 carbon atoms;

R' is a hydrolyzable group selected from alkoxy, halogen, acetoxy or hydroxy or mixtures thereof; and

x = 1 to 3; and;

(b) treating TiO₂ pigment with one or more compounds resulting from mixing the silane compound and water in step (a) to form silanized TiO₂ pigment; and

(c) mixing the silanized TiO₂ pigment with a polymer resin to form a highly loaded polymer matrix comprising 50 to 87% by weight silanized TiO₂ pigment.

19. A process for silanizing TiO₂ pigment and for highly loading the silanized TiO₂ pigment in a polymer matrix, comprising the steps of:

(a) treating TiO₂ pigment with the reaction products of water and a silane compound having the formula:



wherein,

R is a nonhydrolyzable aliphatic, cycloaliphatic or aromatic group having 8-20 carbon atoms;

R' is a hydrolyzable group selected from alkoxy, halogen, acetoxy or hydroxy or mixtures thereof; and

$$x = 1 \text{ to } 3$$

to form silanized TiO₂ pigment; and

(b) mixing the silanized TiO₂ pigment with a polymer resin to form a highly loaded polymer matrix comprising 50 to 87% weight silanized TiO₂ pigment.

20. A highly loaded polymer matrix comprising,

(a) polymer resin; and

(b) 50 to 87% by weight silanized TiO₂ pigment, based on the weight of polymer matrix, wherein the silanized TiO₂ pigment is obtained by treating the pigment with a silane compound having the formula:



wherein,

R is a nonhydrolyzable aliphatic, cycloaliphatic or aromatic group having 8-20 carbon atoms;

R' is a hydrolyzable group selected from alkoxy, halogen, acetoxy or hydroxy or mixtures hereof; and

$$x = 1 \text{ to } 3.$$

21. An article comprising the polymer matrix of Claims 1 or 20, wherein the concentration of the silanized TiO₂ pigment is 0.2 to 20% by weight, based on the weight of the article.

22. The article of Claim 21, wherein the article is a film.