

(19) **DANMARK**



Patent- og
Varemærkestyrelsen

(12)

Oversættelse af europæisk patentskrift

(10) **DK/EP 2401080 T3**

-
- (51) Int.Cl.: *B 01 J 37/02 (2006.01)* *B 01 J 23/75 (2006.01)* *B 01 J 23/89 (2006.01)*
C 07 C 1/04 (2006.01) *C 07 C 5/02 (2006.01)* *C 07 C 5/05 (2006.01)*
C 07 C 51/36 (2006.01) *C 10 G 2/00 (2006.01)* *C 10 G 45/00 (2006.01)*
- (45) Oversættelsen bekendtgjort den: **2015-03-23**
- (80) Dato for Den Europæiske Patentmyndigheds bekendtgørelse om meddelelse af patentet: **2014-12-10**
- (86) Europæisk ansøgning nr.: **10708806.4**
- (86) Europæisk indleveringsdag: **2010-02-23**
- (87) Den europæiske ansøgnings publiceringsdag: **2012-01-04**
- (86) International ansøgning nr.: **IB2010050783**
- (87) Internationalt publikationsnr.: **WO2010097754**
- (30) Prioritet: **2009-02-26 US 155781 P** **2009-02-26 ZA 200901400**
- (84) Designerede stater: **AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO SE SI SK SM TR**
- (73) Patenthaver: **Sasol Technology (Proprietary) Limited, 1 Sturdee Avenue, Rosebank, 2196 Johannesburg, Sydafrika**
- (72) Opfinder: **TERORDE, Robert, Johan, Andreas, Maria, Patrijzenlaan 13, NL-3951 Ae Maarn, Holland KRAMER, Lucas, Laurentius, Hoefslag 29, NL-3471 AJ Kamerik, Holland**
- (74) Fuldmægtig i Danmark: **Chas. Hude A/S, H.C. Andersens Boulevard 33, 1780 København V, Danmark**
- (54) Benævnelse: **Fremgangsmåde til fremstilling af Fischer-Tropsch-katalysatorer og deres anvendelse**
- (56) Fremdragne publikationer:
WO-A1-01/76734
WO-A1-02/089978
WO-A1-2009/127990
US-A- 5 945 459
US-A1- 2003 111 391
US-A1- 2004 048 937
US-A1- 2005 026 776
SUN S ET AL: "Active Co/SiO₂ Catalysts Prepared from Mixing Precursors for Slurry Phase Fischer-Tropsch Synthesis", CHEMISTRY LETTERS, vol. 28, no. 4, 1999, pages 343-344, XP9142959, ISSN: 1348-0715, DOI: 10.1246/cl.1999.343
VAN DE LOOSDRECHT J ET AL: "Preparation and properties of supported cobalt catalysts for Fischer-Tropsch synthesis", APPLIED CATALYSIS A: GENERAL, ELSEVIER SCIENCE, AMSTERDAM, NL, vol. 150, no. 2, 13 March 1997 (1997-03-13), pages 365-376, XP004338059, ISSN: 0926-860X, DOI: DOI:10.1016/S0926-860X(96)00306-7 cited in the application
KRAUM M ET AL: "Fischer-Tropsch synthesis: the influence of various cobalt compounds applied in the

Fortsættes ...

preparation of supported cobalt catalysts on their performance", APPLIED CATALYSIS A: GENERAL, ELSEVIER SCIENCE, AMSTERDAM, NL, vol. 186, no. 1-2, 4 October 1999 (1999-10-04), pages 189-200, XP004271933, ISSN: 0926-860X, DOI: DOI:10.1016/S0926-860X(99)00172-6 cited in the application

MATSUZAKI T ET AL: "Effect of transition metals on oxygenates formation from syngas over Co/SiO₂", APPLIED CATALYSIS A: GENERAL, vol. 105, no. 2, 15 November 1993 (1993-11-15), pages 159-184, XP002616992, DOI: 10.1016/0926-860X(93)80246-M

MATSUZAKI T ET AL: "Hydrogenation of carbon monoxide over highly dispersed cobalt catalysts derived from cobalt(II) acetate", CATALYSIS TODAY, ELSEVIER, NL, vol. 28, 1 January 1996 (1996-01-01), pages 251-259, XP002545697, ISSN: 0920-5861, DOI: DOI:10.1016/0920-5861(95)00245-6

Description**FIELD OF THE INVENTION**

- 5 **[0001]** THIS INVENTION relates to catalysts. It relates in particular to a process for preparing a catalyst precursor, and to a process for preparing a catalyst, which catalyst can be used, for instance, in hydrocarbon synthesis (including Fischer- Tropsch (FT)) and hydrogenation reactions.

BACKGROUND ART

10

- [0002]** Preparation of catalyst precursors by metal impregnation onto catalyst supports using various impregnation techniques, is well known to those skilled in the art. The impregnated supports so obtained are then usually subjected to drying and calcination to provide catalyst precursors, and the precursors are
15 then subjected to reduction to produce, finally, a catalyst.

- [0003]** In particular, the Applicants are aware that, as described in EP 0736326 B1, cobalt impregnated alumina based Fischer-Tropsch synthesis catalysts can, for example, be synthesized by means of aqueous slurry phase impregnation of
20 a cobalt salt, for example cobalt nitrate hexahydrate, onto an alumina support, coupled with drying of the impregnated support, followed by direct fluidized bed calcination of the resultant impregnated support, to obtain a catalyst precursor, and then reducing the precursor to obtain the Fischer-Tropsch synthesis catalysts. The catalysts contain cobalt dispersed on the support. Sufficiently high
25 cobalt loadings to provide a desired high degree of catalyst activity can readily be obtained by means of the cobalt salt impregnation, by repeating, if necessary, the cobalt salt impregnation step.

- [0004]** It has been reported that the use of organic metal compounds or organic
30 additives during the impregnation could assist in increasing the catalyst activity of supported metal catalysts. For example, US 5856260 teaches that using mix-

tures of polyols and metal salts during impregnation results in improved catalyst performance.

[0005] Van de Loosdrecht et.al. (Applied Catalysis A:General, Volume 150, Number 2, 13 March 1997, pp 365-376(12)) reported that the preparation of low loading cobalt catalysts (2.5% Co) by impregnation using Co-EDTA (ethylenediaminetetraacetic acid) or ammonium cobalt citrate resulted initially in the formation of very small cobalt oxide particles. These small oxide particles reacted during thermal treatment in a reducing gas flow with the alumina support to form cobalt aluminate, which was inactive in Fischer-Tropsch synthesis. Higher loading catalysts (5% Co) prepared by a 2 step impregnation process using ammonium cobalt citrate in both steps resulted in a larger cobalt oxide particle size and higher reducibility, culminating in a reasonable activity, but still lower compared to a reference catalyst prepared from impregnation with cobalt nitrate only and having similar cobalt loading.

[0006] The use of organic impregnation compounds tends to result in low metal loadings due to limited solubility and high viscosity of the impregnation solution. For many catalytic reactions, the low loadings of metal do not provide sufficiently high activity, due to, amongst other reasons, the low reducibility of such catalysts.

[0007] Kraum and Baern (Applied Catalysis A:General 186 (1999)189-200) describe studies of the performance of titania supported catalysts containing 12% cobalt, prepared by multiple impregnations with various organic cobalt compounds, including cobalt(III)acetyl acetonate, cobalt acetate, cobalt oxalate and cobalt -EDTA. The multiple impregnations were performed for each particular catalyst using only a single organic cobalt compound. In this study, sufficiently high metal loadings were only achieved by performing multiple impregnation cycles, thereby compensating for the low solubility of the organic cobalt compounds. However, having to use multiple impregnation cycles for the preparation of a catalyst can be economically unattractive.

[0008] US 6822008B2 teaches the use of two different metal precursors loaded separately on to a suitable support, in such manner that the first loaded portion of metal is more easily reduced, than the second loaded portion of metal. For example, cobalt nitrate hexahydrate is loaded first, whereafter cobalt acetate is
5 loaded on to the support. The second cobalt precursor can thus be an organic cobalt salt such as cobalt acetate.

[0009] SUN S ET AL ("Active Co/SiO₂ Catalysts Prepared from Mixing Precursors for Slurry Phase Fischer-Tropsch Synthesis", CHEMISTRY LETTERS, vol.
10 28, no. 4, 1999, pages 343-344) disclose silica supported catalysts and their precursors prepared with various cobalt compounds, including cobalt nitrate, cobalt acetate, cobalt chloride, and combinations of cobalt nitrate and cobalt acetate. Catalysts made by reducing a precursor made in turn by sequentially impregnating cobalt acetate and cobalt nitrate were *inter alia* studied. In each
15 case the catalyst precursors were prepared by incipient wetness, drying in air at 120 °C and then calcining at 450 °C. After calcination, the precursors were reduced in flowing hydrogen at 400 °C.

[0010] WO01/76734 A discloses FT catalysts with homogeneous cobalt distribution, made by two or more sequential impregnations. The first is always an α -hydroxy organic acid (preferably citric), followed by the metal impregnation with cobalt compound (preferably Co(II) nitrate hexahydrate) and preferably a promoter (Pd, Pt), ramped heating to 240 °C and holding there under flowing air, which metal impregnation and calcination sequence is preferably redone. The
20 so-made precursors are then reduced with hydrogen at 300 °C.

[0011] It is thus an object of the present invention to provide a catalyst precursor and/or a catalyst with which some of the disadvantages described above are overcome or at least reduced.

DISCLOSURE OF THE INVENTION

[0012] Thus, according to a first aspect of the invention there is provided a process for preparing a catalyst precursor, as defined in claim 1.

5

[0013] In a preferred embodiment of the invention, the impregnated intermediate of the first preparation step is at least partially dried prior to the calcination thereof. Preferably, the impregnated support of the second preparation step is also at least partially dried prior to the calcination thereof. It will be appreciated
10 that the partial drying will usually take place where the impregnation is slurry phase impregnation.

[0014] The invention is thus characterized thereby that the impregnation is strictly carried out using the sequence of impregnation first with the organic cobalt compound and thereafter, after the calcining of the impregnated intermediate, impregnation with the inorganic cobalt salt. Preferably, none of the inorganic cobalt salt used in the second preparation step is present during the first impregnation step. Preferably, none of the organic cobalt compound of the first preparation step is present during the second preparation step.

20

[0015] The present invention thus provides a process for preparing a cobalt based catalyst precursor from which is obtained a catalyst which may have increased activity. Surprisingly, it was found that after having effected an initial or first preparation step involving an impregnation using an organic cobalt compound such as ammonium cobalt citrate, if in a next or second preparation step cobalt is impregnated using an inorganic cobalt salt such as cobalt nitrate, a high cobalt dispersion is usually obtained and at the same time, a high loading of cobalt may be achieved, usually with an increased catalyst activity compared to the standard manner of preparing such catalysts using only inorganic cobalt salts in two sequential impregnation steps. This increased catalyst activity is
25 achieved at a cobalt loading which is similar to, or even lower than, catalysts prepared using the standard manner of impregnation with inorganic cobalt salts
30 in two sequential impregnation steps. Since the intermediate obtained after the

first preparation or impregnation step only contains an organic cobalt compound and not the usual nitrate, the exothermic decomposition of this compound can be very well controlled.

5 **[0016]** It is believed that the increased catalyst activity may be due to the fact that after the first impregnation with the organic cobalt precursor, a high cobalt dispersion is usually obtained with a limited reducibility, while after the second impregnation with the inorganic cobalt salt, the high dispersion is surprisingly maintained, but the reducibility and cobalt loading are increased, resulting in a
10 catalyst with better dispersion and similar loading and reducibility compared to catalysts prepared using the standard manner of impregnation with inorganic cobalt salts in two sequential impregnation steps. It is thus believed that the higher cobalt dispersion while having the correct cobalt loading and reducibility, has resulted in an increased catalyst activity.

15

[0017] In this specification, the term "organic cobalt compound" means a compound wherein at least one cobalt atom is associated with at least one organic group by means of a bond, for instance, by means of a covalent bond, a cobalt-to-ligand coordination or an ionic interaction. Preferably, the cobalt atom is as-
20 sociated to at least one non-carbon atom of the at least one organic group, in particular to an oxygen atom of the organic group. The organic cobalt compound may also include one or more inorganic groups bound to the metal. Preferably, the one or more inorganic groups are cationic groups.

25 **[0018]** In this specification, the term "inorganic cobalt salt" means a salt wherein at least one metal atom is only associated with one or more inorganic groups, which association is by means of a bond, for instance, by means of a covalent bond, a cobalt-to-ligand coordination or an ionic interaction.

30 **[0019]** The process may include, in the first preparation step, repeating, at least once, the impregnation with the organic cobalt compound. Preferably, also the at least partial drying of the impregnated intermediate is then repeated, that is, when at least partial drying is carried out. Preferably, also the calcination of the

impregnated intermediate is then also repeated. In this fashion, a higher cobalt loading in the calcined intermediate, is obtained.

5 **[0020]** Likewise, the process may include, in the second preparation step, repeating, at least once, the impregnation with the inorganic cobalt salt. Preferably, also the at least partial drying of the impregnated support is then repeated, that is, when at least partial drying is carried out. Preferably, also the calcination of the impregnated support is then repeated. In this fashion, a higher cobalt loading in the catalyst precursor, is obtained.

10

15 **[0021]** Thus, in one embodiment of the invention, the first preparation step may comprise a first impregnation with the organic cobalt compound, at least partial drying (optional) and calcination, as hereinbefore described, followed by a second impregnation with the organic cobalt compound, at least partial drying (optional), and calcination, as hereinbefore described; the second preparation step may then comprise a single impregnation with the inorganic cobalt salt, at least partial drying (optional), and calcination, as hereinbefore described.

20 **[0022]** However, in another embodiment of the invention, the first preparation stage may comprise a single impregnation with the organic cobalt compound, at least partial drying (optional) and calcination, as hereinbefore described; the second preparation step may then comprise a first impregnation with the inorganic cobalt salt, at least partial drying (optional), and calcination, as hereinbefore described, followed by a second impregnation with the inorganic cobalt salt,
25 at least partial drying (optional), and calcination, as hereinbefore described.

30 **[0023]** In a first embodiment of the invention, the catalyst precursor may be a hydrocarbon synthesis catalyst precursor. Preferably, it may then be a Fischer-Tropsch synthesis catalyst precursor. More preferably, it may then be a slurry phase Fischer-Tropsch synthesis catalyst precursor.

[0024] It was found that when a cobalt-based Fischer-Tropsch synthesis catalyst precursor as set out above is converted to a Fischer-Tropsch synthesis ca-

talyst by means of reduction, the catalyst has a high and stable Fischer-Tropsch activity. Furthermore, it was surprisingly found that by using the two-step preparation process as hereinbefore defined, not only is a desired high cobalt loading obtained, but a high degree of cobalt (metal and/or oxide) dispersion is also obtained, resulting in a catalyst with improved Fischer-Tropsch synthesis activity.

10 **[0025]** The inorganic cobalt salt of the second preparation step may, at least in principle, be any inorganic cobalt salt; however, cobalt nitrate, and in particular, $\text{Co}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$, is preferred.

[0026] Preferably the inorganic cobalt salt is at least partly dissolved in the carrier liquid. The carrier liquid may thus be any suitable liquid solvent. Preferably, however, it is water.

15 **[0027]** Likewise, the organic cobalt compound of the first preparation step is preferably at least partly dissolved in the carrier liquid. The carrier liquid may be any suitable liquid solvent. Preferably, however, it is water.

[0028] The organic cobalt compound may be that obtained by reacting a cobalt compound such as cobalt hydroxide, with an organic acid, optionally in the presence of at least one counterion source.

[0029] The cobalt compound preferably is a cobalt basic compound.

25 **[0030]** The counterion source, when present, is preferably an inorganic source, and preferably it is a source of one or more cations. In one embodiment of the invention, the counterion source may be ammonia.

[0031] The organic cobalt compound can be formed *in situ*. Thus, the cobalt compound, e.g. cobalt hydroxide, can be dissolved in a solution of the organic acid in water.

[0032] The organic acid may be a carboxylic acid such as citric acid ($\text{C}_6\text{H}_8\text{O}_7$),

succinic acid ($C_4H_6O_4$), oxalic acid ($C_2H_2O_4$), acetic acid ($C_2H_4O_2$), gluconic acid ($C_6H_{12}O_7$) or EDTA, i.e. ethylenediaminetetraacetic acid. Preferably, the organic acid is citric acid.

5 **[0033]** In the organic cobalt compound solution, the molar ratio of cobalt to organic acid can vary widely, e.g. from 0.1:1 to 10:1. However, it is expected that the molar ratio of cobalt to organic acid will normally be in the range of 0.5:1 to 2:1, typically about 1:1.

10 **[0034]** In preferred embodiments of the invention, the organic cobalt compound of the first preparation step may be cobalt ammonium citrate or cobalt ammonium EDTA.

[0035] Instead, the organic cobalt compound of the first preparation step may
15 be that obtained by reaction of a cobalt compound with acetylacetone ($C_5H_8O_2$).

[0036] The catalyst support may be a particulate porous support.

[0037] The catalyst support may comprise a catalyst support basis and optionally one or more modifying components. The catalyst support basis may be selected from the group consisting of alumina in the form of one or more aluminium oxides; silica (SiO_2); titania (TiO_2); magnesia (MgO); and zinc oxide (ZnO); and mixtures thereof. Preferably the support basis is selected from the group consisting of alumina in the form of one or more aluminium oxides; titania (TiO_2)
20 and silica (SiO_2). Typically, the support basis is alumina in the form of one or more aluminium oxides. The one or more aluminium oxides may be selected from the group including (preferably consisting of) gamma alumina, delta alumina, theta alumina and a mixture of two or more thereof. Preferably the group includes, or, preferably, consists of gamma alumina, delta alumina and a mixture
25 of gamma alumina and delta alumina. The aluminium oxide catalyst support may be that obtainable under the trademark Puralox, preferably Puralox SCCa 2/150 from SASOL Germany GmbH. Puralox SCCa 2/150 (trademark) is a
30

spray-dried aluminium oxide support consisting of a mixture of gamma and delta aluminium oxide.

5 **[0038]** The aluminium oxide is preferably a crystalline compound which can be described by the formula $\text{Al}_2\text{O}_3 \cdot x\text{H}_2\text{O}$ where $0 < x < 1$. The term aluminium oxide thus excludes $\text{Al}(\text{OH})_3$, and $\text{AlO}(\text{OH})$, but includes compounds such as gamma, delta and theta alumina.

10 **[0039]** Preferably, the catalyst support includes one or more modifying components. This is particularly the case where the support basis is soluble in a neutral and/or an acidic aqueous solution, or where the support basis is susceptible to hydrothermal attack as described below.

15 **[0040]** The modifying component may comprise a component that results in one or more of the following:

- (i) decreases the dissolution of the catalyst support in an aqueous environment,
- (ii) suppresses the susceptibility of the catalyst support to hydrothermal attack (especially during Fischer-Tropsch synthesis);
- 20 (iii) increases the pore volume of the catalyst support;
- (iv) increases the strength and/or attrition and/or abrasion resistance of the catalyst support.

25 **[0041]** In a preferred embodiment of the invention, the modifying component decreases the dissolution of the catalyst support in an aqueous environment, i.e. increases the inertness of the catalyst support towards dissolution in an aqueous environment and/or suppresses the susceptibility of the catalyst support to hydrothermal attack, especially during Fischer-Tropsch synthesis. Such an aqueous environment may include an aqueous acid solution and/or an
30 aqueous neutral solution, especially such an environment encountered during an aqueous phase impregnation catalyst preparation step. Hydrothermal attack can cause the sintering of the catalyst support (for example aluminium oxide), dissolution of Al ions or break up of the catalyst particles during hydrocarbon

synthesis, especially Fischer-Tropsch synthesis, due to exposure to high temperature and water.

5 **[0042]** The modifying component is typically present in an amount that results in a level thereof in the catalyst support of at least 0.06 atoms per square nanometer.

10 **[0043]** The modifying component may include or consist of Si, Zr, Co, Ti, Cu, Zn, Mn, Ba, Ni, Na, K, Ca, Sn, Cr, Fe, Li, Ti, Sr, Ga, Sb, V, Hf, Th, Ce, Ge, U, Nb, Ta, W, La and mixtures of two or more thereof.

15 **[0044]** The modifying component may, more particularly, be selected from the group consisting of Si; Zr; Cu; Zn; Mn; Ba; La; W; Ni and mixtures of one or more thereof. Preferably the modifying component is selected from the group consisting of Si and Zr. In a preferred embodiment of the invention the modifying component is Si.

20 **[0045]** When the modifying component is Si, the silicon level in the resultant catalyst support is at least 0.06 Si atoms per square nanometer of the catalyst support, preferably at least 0.13 Si atoms per square nanometer of the catalyst support, and more preferably at least 0.26 Si atoms per square nanometer of the catalyst support.

25 **[0046]** Preferably, the upper level is 2.8 Si atoms/nm² of the catalyst support.

30 **[0047]** In one embodiment of the invention, a catalyst support in the form of one or more aluminium oxides or a silica modified aluminium oxide is preferred over supports such as silica and titania, since it is believed that these supports provide a much more attrition resistant catalyst. The catalyst support in the form of one or more aluminium oxides or a silica modified aluminium oxide may also include La. It is believed that La improves attrition resistance.

[0048] In another embodiment of the invention, a catalyst support in the form of

one or more aluminium oxides or a silica modified aluminium oxide may include titanium, preferably in an amount, expressed as elemental titanium, of at least 500 ppm by weight, preferably from about 1000 ppm to about 2000 ppm by weight. It is believed that the addition of the titanium increases the activity of a catalyst formed from such a support, especially in the case of a cobalt FT catalyst, particularly when no noble metal promoters and preferably no Re or Te promoters are present in the catalyst. Preferably, the titanium is included in the internal structure of the support and, preferably, no titanium is present as a deposit on the support. It is believed that the presence of this titanium in the support also improves the attrition resistance of a catalyst which includes such a support.

[0049] In yet another embodiment of the invention, the catalyst support may be in the form of porous particles coated with carbon. In an alternative embodiment of the invention, the porous particles may, however, be free of such a carbon coating.

[0050] The catalyst support may be modified by introducing a modifying component precursor which includes a modifying component as described hereinabove onto and/or into a catalyst support material.

[0051] When present, the drying during the first and/or the second preparation steps, preferably during both preparation steps, may be carried out under conditions at which the inorganic cobalt salt and the organic cobalt compound will not readily decompose. Preferably, the drying during the first and/or second preparation steps is carried out at above 25°C and preferably at sub-atmospheric pressure.

[0052] The impregnation and, preferably, also the drying during the first preparation step may be effected at above 25°C and preferably at sub-atmospheric pressure. Sufficient of a mixture of the organic cobalt compound in the carrier liquid, which is preferably water as hereinbefore indicated, may be used so that the volume of the mixture exceeds the pore volume of the support, typically by

about 30%. After contacting the support with the organic cobalt salt and carrier liquid mixture, the wet impregnated support may be slowly dried at sub-atmospheric pressure to a temperature in the range 40 to 120°C, typically about 100°C, with the final pressure typically being in the range 50 to 120 mbar(a),
5 typically about 80 mbar(a).

[0053] In the first preparation step, the impregnation may be effected by slurry phase impregnation using a slurry made up of the support and a solution of the organic cobalt compound. Preferably, the solution of the organic cobalt com-
10 pound is an aqueous solution.

[0054] During the second preparation step, the particulate calcined intermediate of the first preparation step, may be subjected to slurry phase impregnation with a slurry made up of the calcined intermediate particles and a solution of the in-
15 organic cobalt salt in the carrier liquid, preferably water. Again, generally, the impregnation and, preferably, the drying may be effected at above 25°C and/or at sub-atmospheric pressure.

[0055] The impregnation during the first and/or the second preparation step
20 may instead be done by means of incipient wetness impregnation using sufficient impregnation solution to fill the pores of the support or the calcined intermediate particles. The impregnated support or intermediate may be dried at above 25°C and if required at sub-atmospheric pressure. It might also be dried at atmospheric pressure under a flow of a gas such as air or nitrogen.

25
[0056] Sufficient organic cobalt compound and inorganic cobalt salt may be used so that the resultant catalyst precursor contains between 5g Co/100g support and 70g Co/100g support, preferably between 15g Co/100g support and 40g Co/100g support.

30
[0057] A dopant may also be introduced onto and/or into the catalyst support. When present, the dopant is preferably one that is capable of enhancing the reducibility of the active catalyst component. The dopant may be introduced as a

dopant compound which is a compound of a metal selected from the group consisting of palladium (Pd), platinum (Pt), ruthenium (Ru), rhenium (Re) and a mixture of one or more thereof. Preferably, the dopant compound is an inorganic salt, and, preferably it is soluble in water. The mass proportion of the metal of the dopant (especially palladium or platinum) to the active component metal (especially cobalt) may be from 0.01:100 to 3:100.

[0058] The nitrogen content in the catalyst precursor may be less than 1 mass%, preferably less than 0.5 mass%.

10

[0059] Calcination is preferably carried out at a temperature above 25°C causing the impregnated cobalt compound and salt to decompose and/or to react with oxygen. Calcination is thus preferably carried out under oxidising conditions. For example, cobalt nitrate may be converted into a compound selected from CoO, CoO(OH), Co₃O₄, Co₂O₃ or a mixture of one or more thereof.

[0060] The calcinations in the first and second preparation steps are typically effected in a fluidized bed, or in a rotary kiln. During the first preparation step, the at least partially dried impregnated support may be calcined using an air/nitrogen mixture. The oxygen content of this gas mixture may range from 0.01% to 20% (by volume), preferably from 0.5 to 20% (by volume). The calcination temperature may be above 95°C, preferably above 120°C, more preferably above 200°C, but not above 400°C. Thus, the calcination temperature may be 250°C-400°C, preferably from 280 to 330 °C. The temperature is normally increased from ambient temperature, typically 25°C, to 250-400°C at a rate of between 0.1 and 10°C/min, preferably between 0.5 and 3°C/min. The oxygen concentration can be kept constant during the calcination or it can be increased from a low oxygen concentration, e.i. i.e. 0.5-2 vol%, to a high concentration, (i.e. 10-20 vol%). The increase in oxygen concentration can be done during the temperature increase or during a hold time at the final temperature (250-400°C). The GHSV during the calcination will normally be in the range of 100 to 3000 h⁻¹, typically about 2000 h⁻¹.

[0061] During the second preparation step, the at least partially dried impregnated intermediate may be calcined in air. The temperature during calcination may then be 200°C to 350°C. The temperature is normally increased from ambient temperature, typically 25°C, to 200-350°C at a rate of between 0.1 and 10°C/min, preferably between 0.5 and 3°C/min. The GHSV during the calcination will normally be in the range of 100 to 3000 h⁻¹, typically about 2000 h⁻¹. More particularly, the calcination conditions in the second preparation step may be selected such that, in the catalyst precursor, substantially all reducible cobalt is present in a calcined state.

10

[0062] The calcination during the first and/or the second preparation step may be carried out by using a heating rate and a space velocity that comply with the following criteria:

- (i) when the heating rate is $\leq 1^\circ\text{C/min}$, the space velocity is at least 0.76 m_n³/(kg CO(NO₃)₂ 6H₂O)/h; and
- (ii) when the heating rate is higher than 1°C/min, the space velocity satisfies the relation :

$$\log(\text{space velocity}) \geq \log 0.76 + \frac{\log 20 - \log 0.76}{2} \log(\text{heating rate})$$

[0063] According to a second aspect of the invention, there is provided a process for preparing a catalyst, which includes reducing a catalyst precursor obtained by the process of the first aspect of the invention, thereby to obtain the catalyst.

[0064] When the catalyst precursor is a cobalt-based Fischer-Tropsch synthesis catalyst precursor as hereinbefore described, the catalyst will naturally be a Fischer-Tropsch synthesis catalyst.

[0065] The catalyst precursor may be activated by reduction by contacting the catalyst precursor with pure hydrogen or with a gaseous mixture containing hydrogen. The gaseous mixture may consist of hydrogen and one or more inert

30

gases which are inert in respect of the active catalyst. The gaseous mixture preferably contains at least 90 volume % hydrogen. The reduction may be carried out at a temperature ranging from 250°C to 550°C, preferably from about 300°C to about 425°C, for a period ranging from 0.5 hour to about 24 hours and
5 at a pressure ranging from ambient to about 40 atmospheres.

EXAMPLES

[0066] The invention will now be described in more detail, with reference to the following non-limiting examples.

10 **EXAMPLE 1 -**

Preparation of comparative Catalyst A

[0067] A 30g Co/0.075g Pt/100g (1.5g Si/100g Puralox SCCa 2/150) slurry phase Fischer-Tropsch synthesis ("FTS") catalyst was prepared on a particulate
15 modified 1.5g Si/100g Puralox SCCa 2/150 (trademark) pre-shaped support using aqueous slurry phase impregnation and drying, followed by direct fluidized bed calcination in air.

[0068] This preparation was done by means of two impregnation and calcina-
20 tion steps, both using an inorganic cobalt compound.

[0069] In particular, the catalyst was prepared as follows:

43.70g $\text{Co}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ were dissolved in 40ml distilled water, and 0.024g of $\text{Pt}(\text{NH}_3)_4 \cdot (\text{NO}_3)_2$ (dissolved in 10ml distilled water) were added
25 to this solution, where after 50.0g of the 1.5g Si/100g Puralox SCCa 2/150 modified pre-shaped support were added to the solution. Aqueous slurry phase impregnation and vacuum drying were effected. This vacuum dried intermediate was directly subjected to a fluidized bed calcination step using a continuous air flow of $1.7 \text{ dm}^3/\text{min}$, while increasing the
30 temperature from 25°C to 250°C at 1°C/min and keeping it at 250°C for 6

hours. 50.0g of this intermediate calcined material were subjected to the following 2nd cobalt/platinum impregnation and calcination step: 23.51g $\text{Co}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ were dissolved in 40ml distilled water and 0.039g of $\text{Pt}(\text{NH}_3)_4 \cdot (\text{NO}_3)_2$ (dissolved in 10ml distilled water) were added to this solution, and 50.0g of the ex 1st cobalt/platinum impregnated and calcined intermediate were added. Aqueous slurry phase impregnation and vacuum drying were effected. This vacuum dried intermediate was directly subjected to a fluidized bed calcination step, according to the following procedure using a continuous air flow of $1.7 \text{ dm}^3/\text{min}$, while increasing the temperature from 25°C to 250°C at 1°C/min and keeping it at 250°C for 6 hours.

[0070] In preparation for laboratory scale slurry phase continuous stirred tank reactor ('CSTR') Fischer-Tropsch synthesis (FTS) runs, this calcined material was reduced and wax coated in accordance with the following procedure: 10g of the catalyst was reduced at 1 bar in pure H_2 (space velocity = $2000 \text{ ml}_n \text{ H}_2/\text{g catalyst/h}$) whilst the temperature was increased from 25°C to 425°C at a rate of 1°C/min where after the temperature was kept constant at this temperature of 425°C for 16 hours. The reduced catalyst was allowed to cool down to room temperature at which stage the hydrogen was replaced by argon, and the catalyst unloaded in molten Fischer-Tropsch wax under the protection of an argon blanket. This wax coated catalyst was then transferred to the slurry reactor.

EXAMPLE 2 -

Preparation of Catalyst B in accordance with the invention

25

[0071] A 24g Co/0.011g Pd/0.061g Pt/100g (1.5g Si/100g Puralox SCCa 2/150) slurry phase Fischer-Tropsch synthesis ("FTS") catalyst was prepared on a particulate modified 1.5g Si/100g Puralox SCCa 2/150 (trademark) pre-shaped support using two sequential aqueous slurry phase preparation steps and drying, followed by direct fluidised bed calcination in an air/nitrogen mixture.

30

[0072] This preparation was done by means of two preparation steps: The first preparation step included a single impregnation step with an organic cobalt compound, while the second preparation step included a single impregnation step with an inorganic cobalt compound.

5

[0073] In particular, the catalyst was prepared as follows:

Preparation of impregnation solution 1

[0074] A cobalt ammonium citrate solution having a density of 1,3 g/ml and containing 125g/l cobalt was prepared by dissolving cobalt hydroxide in a citric acid solution in a water/citric acid/cobalt hydroxide weight ratio of 1/1/0.44. After the cobalt hydroxide was completely dissolved, the pH of the solution was adjusted to 7 using ammonia. To the resulting solution, tetramine palladium nitrate was added to result in a palladium:cobalt weight ratio of 0.0015:1 in the final solution.

15

Impregnation/calcination step 1

[0075] 39.6g of impregnation solution 1 were added to 50.0g of the 1.5g Si/-100g Puralox SCCa 2/150 modified pre-shaped support. Aqueous slurry phase impregnation and vacuum drying were effected.

20

[0076] The dried impregnated support was calcined in a fluidized bed reactor by heating the material up to 300°C at a heating rate of 2°C/min, in a 1.6% (by volume) oxygen in nitrogen flow of 2 dm³_n/min. Under these conditions, the exotherm resulting from combustion of organics was roughly 40°C. As soon as the combustion started, the temperature of the gas inlet was reduced and adjusted to yield a reaction temperature of 300-310°C. The combustion phase took 3.5 hours, after which the calcination was assumed to be completed.

25

Impregnation/calcination step 2

30

[0077] 50.0g of the intermediate calcined material from impregnation/calcina-

tions step 1 were subjected to the following 2nd cobalt/platinum impregnation and calcination step:

37.04g $\text{Co}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ were dissolved in 25ml distilled water and 0.056g of $\text{Pt}(\text{NH}_3)_4(\text{NO}_3)_2$ (dissolved in 10ml distilled water) were added to this solution. 50.0g of the ex 1st step cobalt/palladium impregnated and calcined intermediate were then added. Aqueous slurry phase impregnation and vacuum drying were effected. This vacuum dried intermediate was directly subjected to a fluidized bed calcination step, according to the following procedure using a continuous air flow of $1.6 \text{ dm}^3/\text{min}$, while increasing the temperature from 25°C to 250°C at $1^\circ\text{C}/\text{min}$ and keeping it at 250°C for 6 hours.

[0078] The catalyst precursor (i.e. after the 2nd impregnation and calcination) was activated/reduced to obtain the catalyst by using the procedure described in Example 1, except that the end reduction temperature was 375°C .

EXAMPLE 3 -

Preparation of Catalyst C in accordance with the invention

[0079] A 24g Co/0.072g Pt/100g (1.5g Si/100g Puralox SCCa 2/150) slurry phase Fischer-Tropsch synthesis ("FTS") catalyst was prepared on a particulate modified 1.5g Si/100g Puralox SCCa 2/150 (trademark) pre-shaped support using two sequential aqueous slurry phase impregnation steps and drying, followed by direct fluidised bed calcination in an air/nitrogen mixture.

[0080] This preparation was done by means of two preparation steps: The first preparation step included a single impregnation step with an organic cobalt compound, while the second preparation step included a single impregnation step with an inorganic cobalt compound.

[0081] Catalyst C was prepared in exactly the same manner as Catalyst B except for the preparation of impregnation solution 1.

[0082] The preparation of impregnation solution 1 for Example 3 was done as follows:

5 A cobalt ammonium citrate solution containing 125g/l cobalt was prepared by dissolving cobalt hydroxide in a citric acid solution in a water/-citric acid/cobalt hydroxide weight ratio of 1/1/0.44. After the cobalt hydroxide was completely dissolved, the pH of the solution was adjusted to pH7 using ammonia. To the resulting solution, tetramine platinum nitrate was added to result in a platinum:cobalt weight ratio of 0.0015:1 in the final solution.

10

[0083] All of catalysts A, B, and C were tested for Fischer-Tropsch synthesis performance using a slurry phase CSTR. The following Fischer-Tropsch synthesis reaction conditions were maintained:

Reactor temperature	:	230°C
Reactor pressure	:	15 bar
Catalyst inventory	:	ca. 10 gram
(H ₂ + CO) conversion	:	60%
H ₂ :CO inlet ratio	:	1.6:1
Argon internal standard	:	15 vol%

15 **[0084]** As all FT conditions were the same, the relative FT activity was determined by calculating the FT activity of each catalyst as mole CO converted/g catalyst/s and made relative to catalyst A.

20 **[0085]** Catalysts B and C, as prepared in accordance with the invention using cobalt citrate in the 1st impregnation and cobalt nitrate in the 2nd impregnation, had a relatively 15% lower cobalt loading and showed an activity enhancement of 27% and 30% respectively compared to comparative Catalyst A, which was prepared by using cobalt nitrate in both the 1st and 2nd impregnation step, under the reaction conditions described above.

[0086] Catalysts B and C prepared according to this invention showed a considerably higher dispersion of smaller cobalt crystallites compared to conventionally prepared cobalt nitrate-only impregnated Catalyst A. This improved dispersion is demonstrated by XRD crystallite size determination, as given in Table 1.

TABLE 1: Cobalt content, cobalt oxide crystallite size, and relative Fischer-Tropsch (FT) activity for catalysts A, B, and C

	Catalyst A	Catalyst B	Catalyst C
Cobalt content prior to reduction [m%]	21	18	18
XRD crystallite size of oxide precursor prior to reduction [nm]	15	7	7
Relative FT activity	100	127	130

[0087] The average cobalt oxide crystallite size determined by means of XRD, for catalyst A, was 15 nm., while the average cobalt oxide crystallite size determined for catalysts B and C was significantly smaller.

EXAMPLE 4 -

Preparation of Catalyst D in accordance with the invention

[0088] A 18g Co/0.011g Pd/0.061g Pt/100g (1.5g Si/100g Puralox SCCa 2/150) slurry phase Fischer-Tropsch synthesis ("FTS") catalyst was prepared on a particulate modified 1.5g Si/100g Puralox SCCa 2/150 (trademark) pre-shaped support using two sequential aqueous slurry phase preparation steps and drying, followed by direct fluidised bed calcination in a air/nitrogen mixture.

[0089] This preparation was done by means of two preparation steps: The first preparation step included a single impregnation step with an organic cobalt

compound, while the second preparation step included a single impregnation step with an inorganic cobalt compound.

[0090] In particular, the catalyst was prepared as follows:

5 **Preparation of impregnation solution 1**

[0091] A cobalt ammonium EDTA solution containing 71.4g/l cobalt was prepared by dissolving cobalt hydroxide in a EDTA solution in a water/EDTA/cobalt hydroxide weight ratio of 1/1/0.25. After the cobalt hydroxide was completely
10 dissolved, the pH of the solution was adjusted to 7 using ammonia. To the resulting solution tetramine palladium nitrate was added to result in a palladium:-cobalt weight ratio of 0.0015:1 in the final solution.

Impregnation/calcination step 1

15 [0092] 64.6g of impregnation solution 1 was added to 50.0g of the 1.5g Si/100g Puralox SCCa 2/150 modified pre-shaped support and vacuum drying was effected.

[0093] The dried impregnated support was calcined in a fluidized bed reactor by
20 heating the material up to 330°C with a heating rate of 2°C/min, in a 1.6% (by volume) oxygen in nitrogen flow of 2 dm³_n/min. Under these conditions, the exotherm resulting from combustion of organics is roughly 20°C. As soon as the combustion starts the temperature of the gas inlet is reduced and adjusted to yield in a reaction temperature of 300-330°C. The combustion phase took 5
25 hours, after which the calcination was assumed to be completed.

Impregnation/calcination step 2

[0094] The intermediate cobalt/palladium impregnated and calcined ex-step 1 material was subjected to the following 2nd cobalt impregnation and calcination
30 step:

49.5 of a solution of $\text{Co}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ and $\text{Pt}(\text{NH}_3)_4 \cdot (\text{NO}_3)_2$ in water, having a cobalt content of 142.5g/l, a Pt content of 0.21 g/ml, a density of 1.34g/ml and a pH of 2.8 (adjusted with ammonia) was added to 35.0g of the ex 1st cobalt/palladium impregnated and calcined intermediate. Aqueous slurry phase impregnation and vacuum drying was effected. This vacuum dried intermediate was directly subjected to a fluidized bed calcination step, according to the following procedure using a continuous air flow of $1.6 \text{ dm}^3_{\text{n}}/\text{min}$, while increasing the temperature from 25°C to 250°C at 1°C/min and keeping it at 250°C for 6 hours.

[0095] The catalyst precursor (i.e. after the 2nd impregnation and calcination) was activated/reduced to obtain the catalyst by using the procedure as described in Example 1, except that the end temperature was 375°C.

EXAMPLE 5 -

Preparation of Catalyst E in accordance with the invention

[0096] A 18g Co/0.011g Pd/0.061g Pt/100g (Titanium (IV) Oxide) slurry phase Fischer-Tropsch synthesis ("FTS") catalyst was prepared on a Titanium (IV) Oxide support using two sequential aqueous slurry phase preparation steps and drying, followed by direct fluidised bed calcination in a air/nitrogen mixture.

[0097] This preparation was done by means of two preparation steps: The first preparation step included a single impregnation step with an organic cobalt compound, while the second preparation step included a single impregnation step with an inorganic cobalt compound.

[0098] In particular, the catalyst was prepared as follows:

Preparation of impregnation solution 1

[0099] A cobalt ammonium citrate solution containing 127g/l cobalt was prepared by dissolving cobalt hydroxide in a citric acid solution in a water/citric acid/-
5 cobalt hydroxide weight ratio of 1/1/0.44. After the cobalt hydroxide was completely dissolved, the pH of the solution was adjusted to 7 using ammonia. To the resulting solution, tetramine palladium nitrate was added to result in a palladium:cobalt weight ratio of 0.0015:1 in the final solution.

Impregnation/calcination step 1

10

[0100] 39.1g of impregnation solution 1 was added to 50.0g of the Titanium (IV) Oxide support and vacuum drying was effected.

[0101] The dried impregnated support was calcined in a fluidized bed reactor by
15 heating the material up to 300°C with a heating rate of 2°C/min, in a 1.6% (by volume) oxygen in nitrogen flow of 2 dm³/min. Under these conditions, the exotherm resulting from combustion of organics is roughly 30°C. As soon as the combustion starts the temperature of the gas inlet is reduced and adjusted to yield in a reaction temperature of 300-310°C. The combustion phase took 3.5
20 hours, after which the calcination was assumed to be completed.

Impregnation/calcination step 2

[0102] The intermediate cobalt/palladium impregnated and calcined ex-step 1 material was subjected to the following 2nd cobalt impregnation and calcination
25 step:

36.1 g of a solution of Co(NO₃)₂·6H₂O and Pt(NH₃)₄·(NO₃)₂ in water, having a cobalt content of 139.4g/l, a Pt content of 0.21 g/ml, a density of 1.34g/ml and a pH of 2.9 (adjusted with ammonia) was added to 25.0g of the ex 1st cobalt/palladium impregnated and calcined intermediate.
30 Aqueous slurry phase impregnation and vacuum drying was effected. This vacuum dried intermediate was directly subjected to a fluidized bed

calcination step, according to the following procedure using a continuous air flow of $1.6 \text{ dm}^3/\text{min}$, while increasing the temperature from 25°C to 250°C at $1^\circ\text{C}/\text{min}$ and keeping it at 250°C for 6 hours.

- 5 **[0103]** The catalyst precursor (i.e. after the 2nd impregnation and calcination) was activated/reduced to obtain the catalyst by using the procedure as described in Example 1, except that the end temperature was 375°C .

EXAMPLE 6 -

10 **Preparation of Comparative Catalyst F**

- [0104]** A 21g Co/0.075g Pt/100g (Titanium (IV) Oxide) slurry phase Fischer-Tropsch synthesis ("FTS") catalyst was prepared on a Titanium (IV) Oxide support using two sequential aqueous slurry phase preparation steps and drying,
15 followed by direct fluidised bed calcination in air.

[0105] This preparation was done by means of two impregnation and calcination steps, both using an inorganic cobalt compound.

- 20 **[0106]** In particular, the catalyst was prepared as follows:

Impregnation/calcination step 1

- [0107]** 74.1 of a solution of $\text{Co}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ and $\text{Pt}(\text{NH}_3)_4 \cdot (\text{NO}_3)_2$ in water, having a cobalt content of 151.5g/l , a Pt content of 0.07g/ml , a density of 1.37g/ml and a pH of 2.7 (adjusted with ammonia) and 10g water was added to 50.0g of
25 Titanium (IV) Oxide support and vacuum drying was effected. This vacuum dried impregnated support was directly subjected to a fluidized bed calcination step, according to the following procedure using a continuous air flow of $1.6 \text{ dm}^3/\text{min}$, while increasing the temperature from 25°C to 250°C at $1^\circ\text{C}/\text{min}$ and
30 keeping it at 250°C for 6 hours.

Impregnation/calcination step 2

[0108] The intermediate cobalt/platinum impregnated and calcined ex-step 1 material was subjected to the following 2nd cobalt impregnation and calcination
5 step:

30g of a solution of $\text{Co}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ and $\text{Pt}(\text{NH}_3)_4 \cdot (\text{NO}_3)_2$ in water, having a cobalt content of 140.3g/l, a Pt content of 0.21g/ml, a density of 1.34g/ml and a pH of 2.6 (adjusted with ammonia) was added to 30.6g of the
10 ex 1st cobalt/platinum impregnated and calcined intermediate. Aqueous slurry phase impregnation and vacuum drying was effected. This vacuum dried intermediate was directly subjected to a fluidized bed calcination step, according to the following procedure using a continuous air flow of $1.6 \text{ dm}^3/\text{min}$, while increasing the temperature from 25°C to 250°C at 1°C/min and keeping it at 250°C for 6 hours.

15

[0109] The catalyst precursor (i.e. after the 2nd impregnation and calcination) was activated/reduced to obtain the catalyst by using the procedure as described in Example 1, except that the end temperature was 375°C

EXAMPLE 7 -

20

Preparation of Catalyst G in accordance with the invention

[0110] A 18g Co/0.011g Pd/0.061 g Pt/100g (Silicon dioxide) slurry phase Fischer-Tropsch synthesis ("FTS") catalyst was prepared on a Silicon dioxide
25 support using two sequential aqueous slurry phase preparation steps and drying, followed by direct fluidised bed calcination in a air/nitrogen mixture.

[0111] This preparation was done by means of two preparation steps: The first preparation step included a single impregnation step with an organic cobalt
30 compound, while the second preparation step included a single impregnation step with an inorganic cobalt compound.

[0112] In particular, the catalyst was prepared as follows:

Impregnation/calcination step 1

[0113] 39.1g of impregnation solution 1 from Example 5 (Catalyst E) and 40g
5 water was added to 50.0g of the Silicon dioxide support and vacuum drying was effected.

[0114] The dried impregnated support was calcined in a fluidized bed reactor by heating the material up to 300°C with a heating rate of 2°C/min, in a 1.6% (by
10 volume) oxygen in nitrogen flow of 2 dm_n/min. Under these conditions, the exotherm resulting from combustion of organics is roughly 30°C. As soon as the combustion starts the temperature of the gas inlet is reduced and adjusted to yield in a reaction temperature of 300-310°. The combustion phase took 3.5 hours, after which the calcination was assumed to be completed.

15 **Impregnation/calcination step 2**

[0115] The intermediate cobalt/palladium impregnated and calcined ex-step 1 material was subjected to the following 2nd cobalt impregnation and calcination step:

20 28.9g of a solution of Co(NO₃)₂.6H₂O and Pt(NH₃)₄.(NO₃)₂ in water, having a cobalt content of 139.4g/l, a Pt content of 0.21 g/ml, a density of 1.34g/ml and a pH of 2.9 (adjusted with ammonia) and 10g water was added to 20.0g of the ex 1st cobalt/palladium impregnated and calcined intermediate. Aqueous slurry phase impregnation and vacuum drying
25 was effected. This vacuum dried intermediate was directly subjected to a fluidized bed calcination step, according to the following procedure using a continuous air flow of 1.6 dm³_n/min, while increasing the temperature from 25°C to 250°C at 1 °C/min and keeping it at 250°C for 6 hours.

[0116] The catalyst precursor (i.e. after the 2nd impregnation and calcination) was activated/reduced to obtain the catalyst by using the procedure as described in Example 1, except that the end temperature was 375°C

- 5 **[0117]** Catalysts D, E, F and G were analysed for cobalt content and cobalt oxide crystallite size. The results are given in Table 2.

TABLE 2 Cobalt content, and cobalt oxide crystallite size, for catalysts D, E, F and G

	Catalyst D	Catalyst E	catalyst F	Catalyst G
Cobalt content prior to reduction [m%]	18	18	21	18
XRD crystallite size of oxide precursor prior to reduction [nm]	8	10	32	8

10

[0118] Catalyst D prepared with a different organic precursor (Cobalt EDTA) in the first preparation step to that used for the preparation of Catalyst B (Cobalt citrate) also showed good dispersion of cobalt crystallites compared to the conventionally prepared cobalt nitrate-only impregnated Catalyst A.

15

[0119] Catalysts E and G prepared on different supports (TiO₂, SiO₂) according to this invention showed a considerably higher dispersion of smaller cobalt crystallites compared to conventionally prepared cobalt nitrate-only impregnated comparative Catalyst F. These improved dispersions are demonstrated by XRD

20 crystallite size determination, as given in Table 2.

EXAMPLE 8 -

Preparation of Catalyst H in accordance with the invention

- 25 **[0120]** A 23g Co/0.00375g Pd/0.075g Pt/100g (1.5g Si/100g Puralox SCCa

2/150) slurry phase Fischer-Tropsch synthesis ("FTS") catalyst was prepared on a particulate modified 1.5g Si/100g Puralox SCCa 2/150 (trademark) pre-shaped support using sequential aqueous slurry phase preparation steps and drying, followed by direct fluidised bed calcination in an air/nitrogen mixture.

5

[0121] This preparation was done by means of two preparation steps: The first preparation step used an organic cobalt compound, while the second preparation step used an inorganic cobalt compound. The impregnation with the inorganic cobalt compound in the second preparation step was repeated once (i.e. impregnations 2a and 2b).

10

[0122] In particular, the catalyst was prepared as follows:

Preparation of impregnation solution 1

15 **[0123]** A cobalt ammonium citrate solution containing 125g/l cobalt was prepared by dissolving cobalt hydroxide in a citric acid solution in a water/citric acid/cobalt hydroxide weight ratio of 1/1/0.44. After the cobalt hydroxide was completely dissolved, the pH of the solution was adjusted to 7 using ammonia. To the resulting solution tetramine palladium nitrate was added to result in a
20 palladium:cobalt weight ratio of 0.0015:1 in the final solution.

Impregnation/calcination step 1

[0124] 13,0g of impregnation solution 1 and 40g of water were added to 50.0g of the 1.5g Si/100g Puralox SCCa 2/150 modified pre-shaped support and vacuum drying was effected.
25

[0125] The dried impregnated support was calcined in a fluidized bed reactor by heating the material up to 300°C with a heating rate of 2°C/min, in a 1.6% (by volume) oxygen in nitrogen flow of 2 dm³_n/min. Under these conditions, the exotherm resulting from combustion of organics is roughly 30°C. As soon as the
30 combustion starts the temperature of the gas inlet is reduced and adjusted to

yield in a reaction temperature of 300-310°C. The combustion phase took 2 hours, after which the calcination was assumed to be completed.

Impregnation/calcination step 2a

- 5 **[0126]** The intermediate cobalt/palladium impregnated and calcined ex-step 1 material was subjected to the following 2nd cobalt impregnation and calcination step:

10 59,4g of a solution of $\text{Co}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ and $\text{Pt}(\text{NH}_3)_4 \cdot (\text{NO}_3)_2$ in water, having a cobalt content of 151g/l, a Pt content of 0.21g/ml, a density of 1.37g/ml and a pH of 2.7 (adjusted with ammonia) was added to 40.0g of the ex 1st cobalt/palladium impregnated and calcined intermediate. Aqueous slurry phase impregnation and vacuum drying was effected. This vacuum dried intermediate was directly subjected to a fluidized bed calcination step, according to the following procedure using a continuous

15 air flow of $1.6 \text{ dm}^3/\text{min}$, while increasing the temperature from 25°C to 250°C at 1°C/min and keeping it at 250°C for 6 hours.

Impregnation/calcination step 2b

- 20 **[0127]** The intermediate ex-step 2a cobalt/palladium/platinum impregnated and calcined material was subjected to the following cobalt impregnation and calcination step:

25 40,9g of a solution of $\text{Co}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ and $\text{Pt}(\text{NH}_3)_4 \cdot (\text{NO}_3)_2$ in water, having a cobalt content of 139g/l, a Pt content of 0.53g/ml, a density of 1.34g/ml and a pH of 2.9 (adjusted with ammonia) was added to 40.0g of the ex-step 2a cobalt/palladium/platinum impregnated and calcined intermediate. Aqueous slurry phase impregnation and vacuum drying was effected. This vacuum dried intermediate was directly subjected to a fluidized bed calcination step, according to the following procedure using a

continuous air flow of $1.6 \text{ dm}^3/\text{min}$, while increasing the temperature from 25°C to 250°C at $1^\circ\text{C}/\text{min}$ and keeping it at 250°C for 6 hours.

[0128] The catalyst precursor (i.e. after last impregnation and calcination) was
 5 activated/reduced to obtain the catalyst by using the procedure as described in Example 1, except that the end temperature was 375°C

EXAMPLE 9 -

Preparation of Catalyst I in accordance with the invention

10

[0129] A 18g Co/0.011g Pd/0.023g Pt/100g (1.5g Si/100g Puralox SCCa 2/150) slurry phase Fischer-Tropsch synthesis ("FTS") catalyst was prepared on a particulate modified 1.5g Si/100g Puralox SCCa 2/150 (trademark) pre-shaped support using three sequential aqueous slurry phase preparation steps and dry-
 15 ing, followed by direct fluidised bed calcination in a air/nitrogen mixture.

[0130] This preparation was done by means of two preparation steps: The first preparation step used an organic cobalt compound, while the second preparation step an inorganic cobalt compound. The impregnation with the organic cobalt compound in the first preparation step was repeated once (i.e. impregnations 1 a and 1 b).
 20

[0131] In particular, the catalyst was prepared as follows:

Preparation of impregnation solution 1

25

[0132] A cobalt ammonium citrate solution containing 125g/l cobalt was prepared by dissolving cobalt hydroxide in a citric acid solution in a water/citric acid/cobalt hydroxide weight ratio of 1/1/0.44. After the cobalt hydroxide was completely dissolved, the pH of the solution was adjusted to 7 using ammonia.
 30 To the resulting solution tetramine palladium nitrate was added to result in a palladium:cobalt weight ratio of 0.0015:1 in the final solution.

Impregnation/calcination step 1a

[0133] 13,0g of impregnation solution 1 and 40g of water was added to 50.0g of the 1.5g Si/100g Puralox SCCa 2/150 modified pre-shaped support and vacuum
5 drying was effected.

[0134] The dried impregnated support was calcined in a fluidized bed reactor by heating the material up to 300°C with a heating rate of 2°C/min, in a 1.6% (by volume) oxygen in nitrogen flow of 2 dm³_n/min. Under these conditions, the exo-
10 therm resulting from combustion of organics is roughly 30°C. As soon as the combustion starts the temperature of the gas inlet is reduced and adjusted to yield in a reaction temperature of 300-310°C. The combustion phase took 2 hours, after which the calcination was assumed to be completed.

Impregnation/calcination step 1b

15

[0135] 20,8g of impregnation solution 1 was added to 40.0g of the ex-step1a cobalt/palladium impregnated and calcined intermediate and vacuum drying was effected.

[0136] The dried impregnated support was calcined in a fluidized bed reactor by heating the material up to 300°C with a heating rate of 2°C/min, in a 1.6% (by volume) oxygen in nitrogen flow of 2 dm³_n/min. Under these conditions, the exo-
20 therm resulting from combustion of organics is roughly 30°C. As soon as the combustion starts the temperature of the gas inlet is reduced and adjusted to yield in a reaction temperature of 300-310°C. The combustion phase took 3.5
25 hours, after which the calcination was assumed to be completed.

Impregnation/calcination step 2

[0137] The intermediate ex-step 1 b cobalt/palladium impregnated and calcined
30 material was subjected to the following 3rd cobalt impregnation and calcination step:

42,4g of a solution of $\text{Co}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ and $\text{Pt}(\text{NH}_3)_4 \cdot (\text{NO}_3)_2$ in water, having a cobalt content of 143g/l, a Pt content of 0.54g/ml, a density of 1.34g/ml and a pH of 2.8 (adjusted with ammonia) was added to 30.0g of the ex-step 1 b cobalt/palladium impregnated and calcined intermediate.

- 5 Aqueous slurry phase impregnation and vacuum drying was effected. This vacuum dried intermediate was directly subjected to a fluidized bed calcination step, according to the following procedure using a continuous air flow of $1.6 \text{ dm}^3/\text{min}$, while increasing the temperature from 25°C to 250°C at $1^\circ\text{C}/\text{min}$ and keeping it at 250°C for 6 hours.

10

[0138] The catalyst precursor (i.e. after the last impregnation and calcination) was activated/reduced to obtain the catalyst by using the procedure as described in Example 1, except that the end temperature was 375°C

- 15 **[0139]** Catalysts H and I were tested for Fischer-Tropsch synthesis performance on exactly the same basis as for Catalysts A, B and C hereinbefore described. The results are given in Table 3.

20 **TABLE 3** Cobalt content, cobalt oxide crystallite size, and relative Fischer-Tropsch (FT) activity for catalysts A, H, and I

	Catalyst H	Catalyst I	Catalyst A
Cobalt content prior to reduction[m%]	23	18	21
XRD crystallite size of oxide precursor prior to reduction [nm]	12	7	15
Relative FT activity	143	138	100

- [0140]** It was thus surprisingly found that when, during the first preparation step, an organic cobalt compound/complex is used followed by impregnation, in a second preparation step, with a cobalt salt, a catalyst having an increased Fischer-Tropsch activity is obtained. This is most likely due to the high cobalt
- 25

(metal and/or oxide) dispersion and, at the same time, a desired high cobalt loading.

[0141] The invention thus overcomes problems associated with known processes for preparing Fischer-Tropsch catalysts whereby, on the one hand, high dispersions of cobalt on the catalyst support can be achieved when using low metal loading, while on the other hand, for many Fischer-Tropsch synthesis reactions, low cobalt loadings do not provide a desired high activity. Hitherto, when it has then been attempted to increase the cobalt loading, metal dispersion often decreased to unacceptable levels. It was thus surprisingly found that this problem was avoided with the process of the present invention.

EXAMPLE 10

Preparation of Catalyst J in accordance with the invention.

15

[0142] A 26g Co/0,075Pt/100g (1.5g Si/100g Puralox SCCa 2/150) slurry phase Fischer-Tropsch synthesis ("FTS") catalyst was prepared on a particulate modified 1.5g Si/100g Puralox SCCa 2/150 (trademark) pre-shaped support using two sequential slurry phase preparation steps and drying, followed by direct fluidised bed calcination in air.

20

[0143] This preparation was done by means of two preparation steps: The first preparation step included a single impregnation step with an organic cobalt compound and an organic solvent, while the second preparation step included a single impregnation step with an inorganic cobalt compound and water as a solvent.

25

[0144] In particular, the catalyst was prepared as follows:

Impregnation/calcination step 1

30

[0145] 43 g of $\text{Co}(\text{acac})_2$ (i.e. cobalt acetylacetonate; $\text{Co}(\text{C}_5\text{H}_7\text{O}_2)_2$) and 0,049 g $\text{Pt}(\text{NH}_3)_4.(\text{NO}_3)_2$ were dissolved in 120 ml of Toluene. 100grams of 1.5g Si/100g Puralox SCCa 2/150 modified pre-shaped support was then added to this solution. Organic slurry phase impregnation and vacuum drying were effected.

5

[0146] This vacuum dried intermediate was directly subjected to a fluidized bed calcination step using a continuous air flow of $1.7 \text{ dm}^3/\text{min}$, while increasing the temperature from 25°C to 250°C at $1^\circ\text{C}/\text{min}$ and keeping it at 250°C for 6 hours.

Impregnation/calcination step 2

10

[0147] 100g of this intermediate calcined material were subjected to the following 2nd cobalt/platinum impregnation and calcination step: 69.5g $\text{Co}(\text{NO}_3)_2.6\text{-H}_2\text{O}$ were dissolved in 100ml distilled water and 0.087g of $\text{Pt}(\text{NH}_3)_4.(\text{NO}_3)_2$ (dissolved in 10ml distilled water) were added to this solution, and 100g of the ex 1st cobalt/platinum impregnated and calcined intermediate were added. Aqueous slurry phase impregnation and vacuum drying were effected. This vacuum dried intermediate was directly subjected to a fluidized bed calcination step, according to the following procedure using a continuous air flow of $1.7 \text{ dm}^3/\text{min}$, while increasing the temperature from 25°C to 250°C at $1^\circ\text{C}/\text{min}$ and keeping it at 250°C for 6 hours.

20

[0148] The catalyst precursor (i.e. after the 2nd impregnation and calcination) was activated/reduced to obtain the catalyst by using the same procedure as described in Example 1.

25

TABLE 4 Cobalt content and cobalt oxide crystallite size for catalysts A, B, C and J

	Catalyst A	Catalyst B	Catalyst C	Catalysts J
Cobalt content prior to reduction [m%]	21	18	18	18

	Catalyst A	Catalyst B	Catalyst C	Catalysts J
XRD crystallite size of oxide precursor prior to reduction [nm]	15	7	7	9

EXAMPLE 11**Fatty acid hydrogenation**

5 [0149] The hydrogenating performance of (Catalyst B) was determined by the hydrogenation of 150g of tallow fatty acid (iodine value 50.6). Catalyst runs were conducted in a 300ml autoclave using ~830 mg of prereduced cobalt catalyst such that the cobalt content in the reactor was 0.1 weight percent. Reactions were run at a hydrogen pressure of 20 bar, a temperature of 200 °C and a stirring speed of 1600 rpm.

10

[0150] The hydrogen consumption was monitored for 4 hours. In addition, the end iodine value was measured by the Wijs method as described in A.O.C.S. Official Method Cd 1-25 (1990).

15 [0151] The catalyst afforded a 56% conversion of the fatty acid sample after 4 hour. This resulted in an end iodine value of 22.5.

[0152] The results are set out in Table 5

20 **TABLE 5**

Time (min)	H ₂ consumption (l)	Conversion (%)	Iodine value
0	0,0	0	50,9
20	0,93	14	44
40	1,55	23	39,3
80	2,50	36	32,3

Time (min)	H ₂ consumption (l)	Conversion (%)	Iodine value
160	3,42	50	25,5
240	3,81	56	22,5

Patentkrav

1. Fremgangsmåde til fremstilling af en katalysator-præcursor, hvilken fremgangsmåde indbefatter i et første fremstillingstrin at imprægnere en partikelformet katalysatorbærer med en organisk koboltforbindelse i bærevæske for at danne en imprægneret mellemforbindelse og calcinere den imprægnerede mellemforbindelse ved en calcineringsstemperatur, som ikke er større end 400°C, for at opnå en calcineret mellemforbindelse og derefter i et andet fremstillingstrin at imprægnere den calcinerede mellemforbindelse fra det første fremstillingstrin med et uorganisk koboltsalt i en bærevæske for at opnå en imprægneret understøtning og calcinere den delvist tørrede imprægnerede understøtning i luft ved en calcineringsstemperatur på 200°C til 350°C for at opnå katalysator-prækursoren, hvor fremgangsmåden er **kendetegnet ved**, at intet af det uorganiske anvendte koboltsalt i det andet fremstillingstrin er til stede under det første fremstillingstrin.
2. Fremgangsmåde ifølge krav 1, hvor intet af den organiske koboltforbindelse fra det første fremstillingstrin er til stede under det andet fremstillingstrin.
3. Fremgangsmåde ifølge krav 1 eller 2, hvor den imprægnerede mellemforbindelse af det første fremstillingstrin er i det mindste delvis tørret forud for calcineringen heraf, og/eller hvor den imprægnerede understøtning af det andet fremstillingstrin er mindst delvis tørret forud for calcineringen heraf.
4. Fremgangsmåde ifølge krav 3, som indbefatter i det første fremstillingstrin gentagelse af i det mindste mindst en gang imprægneringen med den organiske koboltforbindelse, den i det mindste delvist tørrede imprægnerede mellemforbindelse og calcineringen af den i det mindste delvist tørrede imprægnerede mellemforbindelse for at opnå et højere koboltindhold i den calcinerede mellemforbindelse.
5. Fremgangsmåde ifølge et vilkårligt af kravene 3 eller 4, som indbefatter i det andet fremstillingstrin gentagelse af mindst en gang imprægneringen med

det uorganiske koboltsalt, den i det mindste delvist tørrede tørring af den imprægnerede understøtning og calcineringen af den delvist tørrede imprægnerede understøtning for at opnå et højere koboltindhold i katalysator-præcursoren.

5 6. Fremgangsmåde ifølge et vilkårligt af kravene 1 til 5 inklusive, hvor en organisk koboltforbindelse og et uorganisk koboltsalt anvendes.

7. Fremgangsmåde ifølge krav 6, hvor det uorganiske koboltsalt fra det andet fremstillingstrin er $\text{Co}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ med $\text{Co}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ opløst i vand som bærevæske.
10

8. Fremgangsmåde ifølge krav 6 eller 7, hvor den organiske koboltforbindelse fra det første fremstillingstrin er det, der opnås ved at omsætte en koboltforbindelse med en organisk syre eventuelt i nærvær af en modionskilde, eller det, der opnås ved omsætning af en koboltforbindelse med acetylacetone ($\text{C}_5\text{H}_8\text{O}_2$) eller er koboltammoniumcitrat.
15

9. Fremgangsmåde ifølge krav 8, hvor med hensyn til den organiske koboltforbindelse fra det første fremstillingstrin er den organiske syre valgt fra citronsyre ($\text{C}_6\text{H}_8\text{O}_7$), ravsyre ($\text{C}_4\text{H}_6\text{O}_4$), oxalsyre ($\text{C}_2\text{H}_2\text{O}_4$), eddikesyre ($\text{C}_2\text{H}_4\text{O}_2$), gluconsyre ($\text{C}_6\text{H}_{12}\text{O}_7$) og EDTA, koboltforbindelsen er kobolthydroxid, og modionskilden, såfremt den er til stede, er ammoniak.
20

10. Fremgangsmåde ifølge et vilkårligt af kravene 6 til 9 inklusive, hvor den organiske koboltforbindelse er opløst i vand som bærevæske.
25

11. Fremgangsmåde ifølge et vilkårligt af kravene 6 til 10 inklusive, hvor imprægneringen og tørringen under det første og det andet fremstillingstrin udføres over 25°C og ved et tryk under atmosfæretryk.

30

12. Fremgangsmåde til fremstilling af en katalysator, som indbefatter fremstilling af en katalysator-præcursor ifølge krav 1, og reduktion af katalysator-præcursoren for derved at opnå katalysatoren.