



- (51) **International Patent Classification:**  
*B23K 9/09* (2006.01) *B23K 9/095* (2006.01)
- (21) **International Application Number:**  
PCT/US2014/017864
- (22) **International Filing Date:**  
22 February 2014 (22.02.2014)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:**  
13/828,040 14 March 2013 (14.03.2013) US
- (71) **Applicant:** ILLINOIS TOOL WORKS INC. [US/US];  
155 Harlem Avenue, Glenview, Illinois 60025 (US).
- (72) **Inventors:** MARSCHKE, Bryan Dustin; c/o Illinois Tool  
Works Inc., 155 Harlem Avenue, Glenview, Illinois 60025  
(US). D'ARCY, Amanda Jean; c/o Illinois Tool Works  
Inc., 155 Harlem Avenue, Glenview, Illinois 60025 (US).
- (74) **Agent:** HAUPTMAN, Benjamin J.; LOWE HAPTMAN  
& HAM LLP, 2318 Mill Rd, Suite 1400, Alexandria, Vir-  
ginia 22314 (US).
- (81) **Designated States** (unless otherwise indicated, for every  
kind of national protection available): AE, AG, AL, AM,  
AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY,

BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM,  
DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT,  
HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR,  
KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME,  
MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ,  
OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA,  
SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM,  
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM,  
ZW.

- (84) **Designated States** (unless otherwise indicated, for every  
kind of regional protection available): ARIPO (BW, GH,  
GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ,  
UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ,  
TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK,  
EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV,  
MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM,  
TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,  
KM, ML, MR, NE, SN, TD, TG).

**Declarations under Rule 4.17:**

- as to applicant's entitlement to apply for and be granted a  
patent (Rule 4.17(ii))
- as to the applicant's entitlement to claim the priority of the  
earlier application (Rule 4.17(iii))

[Continued on next page]


(54) **Title:** ELECTRODE NEGATIVE PULSE WELDING SYSTEM AND METHOD

FIG. 4

(57) **Abstract:** A welding system includes a power source configured to generate power and deliver the power to a welding torch. The power is provided in accordance with an electrode negative pulse welding regime that includes a cyclic peak, followed by a stabilization phase, then a return to a background level. The stabilization phase has a generally parabolic current shape, and is performed in a current-closed loop manner until a transition point, where control becomes voltage-closed loop until the background level is reached. Resulting weld performance is improved, with a globular-like transfer mode, reduced shorts and enhanced arc stability.



---

**Published:**

— with international search report (Art. 21(3))

— before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments (Rule 48.2(h))

## ELECTRODE NEGATIVE PULSE WELDING SYSTEM AND METHOD

### BACKGROUND

[0001] The invention relates generally to welding processes, and more specifically, to methods and systems for controlling electrode transfer in pulsed spray gas metal arc welding (GMAW-P) processes.

[0002] Welding is a process that has become ubiquitous in various industries, and may be used to facilitate many metal construction and assembly applications. For example, one process commonly known as gas metal arc welding (GMAW) is most generally a specific welding process that uses a welding arc between a continuous filler metal electrode and a workpiece. Certain GMAW derivation processes or transfer modes such as spray transfer and pulsed spray transfer (e.g., GMAW-P) may include relatively high voltage levels, high amperage levels, and high wire feed speed (WFS) to transfer droplets of the metal electrode material across the welding arc onto relatively thin metals workpieces. Unfortunately, when using an electrode negative polarity welding arc, the metal electrode may be reluctant to transfer material across the welding arc.

[0003] Thus, while it would be advantageous in many applications to utilize a pulsed electrode negative welding regime, conventional techniques would add too much energy to the weld, create bridging shorts and inconsistent metal transfer, erratic arc length, and may result in unwanted spatter. Improvements in the field that would permit such waveforms to be utilized while improving welding performance would be an advance in the art.

### BRIEF DESCRIPTION

[0004] In one embodiment, a welding system includes [to be completed following initial review].

## DRAWINGS

[0005] These and other features, aspects, and advantages of the present invention will become better understood when the following detailed description is read with reference to the accompanying drawings in which like characters represent like parts throughout the drawings, wherein:

[0006] FIG. 1 is a block diagram of an exemplary GMAW system in accordance with the present disclosure;

[0007] FIG. 2 is an exemplary elevational view of the welding electrode of the GMAW system of FIG. 1 using a direct current electrode negative (DCEN) polarity in an improved pulse welding process;

[0008] FIG. 3 is an exemplary elevational view of the electrode shown in FIG. 2 illustrating material transfer during a peak phase of the pulse welding process;

[0009] FIG. 4 is an exemplary timing diagram of the pulse welding process voltage and amperage waveforms; and

[0010] FIG. 5 is a detailed graphical representation of certain phases of the pulsed welding process.

## DETAILED DESCRIPTION

[0011] Welding processes have become ubiquitous in various industries, and may be used to facilitate metal construction and assembly applications. GMAW is most generally a specific welding process that uses a welding arc between a continuous filler metal electrode and a workpiece. Certain GMAW derived processes or transfer modes such as spray transfer and pulsed spray transfer (GMAW-P) may include relatively high voltage levels, high amperage levels, and high wire feed speed (WFS) to transfer droplets of the metal electrode material across the welding arc to perform welding tasks on

relatively thin metals workpieces. Unfortunately, when using an electrode negative polarity welding arc, the metal electrode may be reluctant to transfer material across the welding arc.

[0012] Accordingly, present embodiments relate to systems and methods useful in adjusting one or more characteristics of voltage and amperage output levels to improve transfer metal electrode across a DCEN pulsing welding arc, as well as arc stability. Specifically, reducing the falling edge transition of each peak pulse in a pulse welding regime creates a “stabilization phase” between the peak and a background phase, allowing sufficient time and slow responsiveness at a current-closed loop output for deposition to settle while avoiding or reducing the change for a “hard short” that requires clearing. In prior techniques, aggressive current control following the peak phase tended to cause rapid voltage changes, arc instability, spatter, and frequent short circuits. Other characteristics of the voltage and amperage output levels such as pulse frequency, background period, and pulse width may also be adjusted to improve arc control. As used herein, “stabilization phase” may refer to control of current (and voltage) following a peak phase of a pulse welding regime, prior to transition to a phase in which voltages (and currents) return to a background level. The stabilization phase will typically be used and with DC electrode negative pulse welding techniques, and may be characterized by a parabolic, current-closed loop decline in welding power output. The stabilization phase may be terminated at a higher programmed current than in conventional pulse welding regimes. Then, in a “return to background” phase following the stabilization phase, a proportional-only gain is used for the voltage-closed loop control. It should be appreciated, however, that the techniques described herein may not be limited to spray transfer and pulsed spray transfer GMAW processes, but may also be extended to other GMAW processes. Indeed, as discussed below, rather than a spray-type transfer, the stabilization phase tends to promote a more globular transfer of filler metal to the weld puddle, particularly when used with an EN polarity.

[0013] With the foregoing in mind, it may be useful to describe an embodiment of an welding system, such as an exemplary GMAW system 10 illustrated in FIG. 1. The system illustrated may be typical for an automated or semi-automated (e.g., robotic) welding system, although the arrangement illustrated may be altered in many ways, and the techniques may also be used in hand-held welding processes. As illustrated, the welding system 10 may include a welding power source 12, a welding wire feeder 14, a gas supply system 16, and a welding torch 18. The welding power source 12 may generally supply welding power for the welding system 10. For example, the power source 12 may couple to the welding wire feeder 14 via a power cable 20, as well as to via a lead cable 22 to a workpiece 24, such as through a clamp 26. In the illustrated embodiment, the welding wire feeder 14 is coupled to the welding torch 18 via a weld cable 28 in order to supply, for example, a metal cored welding electrode and power to the welding torch 18 during operation of the welding system 10. In some arrangements, the wire feeder may be incorporated into the power source. Gas from the gas supply system 16 is also typically routed through the weld cable 28. Regarding the workpiece, it is believed that the present techniques may be particularly well suited to workpieces comprising relatively thin gauge galvanized (or coated) steels, although other materials and sizes of materials may be welded as disclosed. Moreover, various travel speeds may be accommodated by manual, or more typically robotic movement of the torch, the workpiece, or both, such as travel speeds of at least 30 in/min, although other speeds may be utilized as well.

[0014] The welding power source 12 may further generally include power conversion circuitry (not separately shown) that receives input power from a power source 30 (e.g., an AC power grid, an engine/generator set, or a combination thereof), conditions the input power, and provides DC or AC output power for welding. The welding power source 12 will also include output terminals for providing welding power output, and these may allow for connection in accordance with either positive or negative polarity welding regimes. Specifically, the welding power source 12 may power the welding wire feeder 14, and by extension, the welding torch 18 in accordance with demands of the

welding system 10. In certain embodiments contemplated by this disclosure, the welding torch 18 may be coupled to the power supply and wire feeder to implement an EN welding regime, and in particular, a pulse welding process. That is, the power source 12 may be useful in providing a DCEN output, in which the electrical current flows through the completed circuit from the negative to positive direction, and thus affects the welding arc and/or welding process. In addition to a DCEN output, the power source 12 may also include circuit elements (e.g., transformers, rectifiers, switches, and so forth) capable of converting the AC input power to a direct current electrode positive (DCEP) output, DC variable polarity, pulsed DC, or a variable balance (e.g., balanced or unbalanced) AC output to perform one or more welding processes.

[0015] For GMAW embodiments, the welding system 10 also includes the gas supply system 16 to supply a shielding gas or shielding gas mixtures from one or more shielding gas sources to the welding torch 18. The shielding gas may be any gas or mixture of gases that may be provided to the welding arc and/or weld pool in order to provide a particular local atmosphere (e.g., to shield the welding arc, improve arc stability, limit the formation of metal oxides, improve wetting of the metal surfaces, alter the chemistry of the weld deposit, and so forth). For example, the shielding gas may comprise one or a mixture of argon (Ar), helium (He), carbon dioxide (CO<sub>2</sub>), oxygen (O<sub>2</sub>), and nitrogen (N<sub>2</sub>).

[0016] Accordingly, as previously noted, the welding torch 18 generally receives the metal welding electrode from the welding wire feeder 14, and a shielding gas flow from the gas supply system 16 in order to perform a welding operation on the workpiece 24. During operation, the welding torch 18 may be brought near the workpiece 22, such that the welding electrode 32 approaches the workpiece and a welding arc 34 is established. It is further believed that the present techniques may be particularly useful with particular types of electrode wires. For example, the electrode 34 may be a metal cored welding wire suitable for use with a DCEN welding polarity. In such cases, the electrode will include a sheath consisting of metal encircling one or more metal cores. The welding electrode may also include fluxing or alloying components that may act as arc stabilizers

and, further, may become at least partially incorporated into the weld. One metal cored welding wire useful for DCEN pulse welding in accordance with the present techniques is disclosed in U.S. patent application no. 13/743,178, entitled Systems and Methods for Welding Electrodes, filed on January 16, 2013, by Barhorst et al., which is hereby incorporated into the present disclosure by reference.

[0017] In certain embodiments, the welding power source 12, the welding wire feeder 14, and the gas supply system 16 may each be controlled and commanded by a control circuitry 36. The control circuitry 36 will include one or more processors 38 and cooperating data processing and sensing circuitry that may be communicatively coupled to a memory 40 to execute instructions stored in the memory for carrying out the presently disclosed techniques. These instructions may be encoded in programs or code stored in tangible non-transitory computer-readable medium, such as the memory 40 and/or other storage. The pulse welding techniques will typically be pre-programmed for specific wire types and sizes, and the particular process desired may be selected by a welding operator via an interface (not separately shown). The processor 38 may be a general purpose processor, system-on-chip (SoC) device, application-specific integrated circuit (ASIC), or other processor configuration. The processor 38 may also support an operating system capable of supporting applications such as, for example, Pro-Pulse™, Accu-Pulse™, Accu-Curve™, and Profile Pulse™ available from Illinois Tool Works, Inc. Similarly, the memory 40 may include, for example, random-access memory (RAM), read-only memory (ROM), flash memory (e.g., NAND), and so forth. As will be further appreciated, in one embodiment, the memory 40 of the control circuitry 36 may be flash updated (e.g., via wired and/or wireless data transmission, programming, and so forth) to include instructions to vary one or more parameter characteristics of the welding output power, and by extension, the welding arc 34. It should be noted that in many configurations, separate processing and control circuitry may be provided for the power supply and for the wire feeder. The power supply typically performs the processing of the control signals used to control power electronic devices (e.g., SCRs, IGBTs, etc.) for producing desired output. In presently contemplated embodiments, code defining the



DCEN pulse welding process utilizing a stabilization phase is stored in the memory 40 and executed by processing circuitry in the power supply.

[0018] As noted above, components of the control circuitry 36 is communicatively coupled to (or embedded within) the welding power source 12, the welding wire feeder 14, and gas supply system 16, and, as noted provides control of one or more parameters (e.g., voltage and amperage output, wire feed speed, travel speed for automated applications, etc.) associated with each of the aforementioned components.

[0019] FIG. 2 depicts an embodiment of a welding process using a DCEN polarity electrical welding arc 34. As previously noted, the welding electrode 32, once energized and positioned near the workpiece establishes an electrical welding arc 34 to perform a weld of the workpiece 22. Specifically, when using a DCEN polarity welding arc 34, heating will particularly take place in the wire electrode, resulting in less penetration than with DCEP processes. In such processes, the electrode is designated as “negative”, while the workpiece is “positive”. Electron flow, indicated by arrows 42 is from the electrode 32 to the workpiece, and primarily to the weld puddle 44. Such techniques are sometimes referred to as “straight polarity”. In general, an arc length 46 is maintained between the tip of the electrode and the weld puddle 44. This arc length may be determined to some degree, and in many respects controlled by the power input to the electrode, and therethrough to the arc, the weld puddle, and the workpiece. While in many prior art techniques efforts are made to rigorously control the arc length, the present technique, through use of the stabilization phase following pulse peaks, tends to emphasize arc stability over strict control of the arc length.

[0020] Moreover, in conventional GMAW-P processes, transfer of metal from the electrode tends to be in a spray mode. In these techniques, the welding power supply pulses the welding output with high peak currents set at levels that create spray transfer, and low background current levels that maintain the arc, but that are too low for any metal transfer to occur. Because the metal transfer during the background phase of the cycle, the weld puddle may freeze slightly.

[0021] While the present technique may be classified generally as a GMAW-P process, it tends to differ from conventional processes in several important respects. For example, conventional GMAW-P processes control the decline in current levels from the peak based on a linear relationship between current and time (e.g., A/ms). They also tend to close control loops (on current and/or voltage) to more rigorously maintain arc length, and transition to a voltage phase at a current level lower than in the present technique. Moreover, such existing techniques typically use a proportional/integral gain for voltage-closed loop control on the return to background portion of the ramp following the pulse peak. A consequence of these factors is that voltage and currents decline aggressively, which can result in frequent short circuits that may require clearing before the subsequent peak.

[0022] The present technique, particularly when used with EN polarities, generates a “softer” down ramp, emphasizing arc stability and avoiding or reducing the risk of short circuits. Moreover, as illustrated in FIG. 4, the transfer mode tends to be more globular than conventional GMAW-P processes. While transfer occurs during the peak phase, material continues to be melted from the electrode thereafter, and one or more globules 48 tends to remain near or somewhat suspended between the electrode and the weld puddle. The arc length 46 may change, or may be difficult to rigidly qualify, although short circuits, and particularly “hard shorts” are typically avoided and the arc tends to be more stable.

[0023] Here again, while the waveform may be used with electrode positive polarities, it is believed to be particularly useful when welding with electrode negative polarities and processes. For control, the power supply control circuitry may regulate the power output by cyclically transitioning between voltage-closed loop control and current-closed loop control. During the time the welding power output is low (e.g., during a background phase of the pulsed waveform), the welding arc remains established, but will add little energy to the electrode and workpiece, although heating of the electrode and weld puddle will continue. During this background phase, the electrode and pool are

allowed to cool somewhat, and between the peak phase and the background phase a stabilization phase is implemented as discussed more fully below. Again, the majority of metal transferred from the electrode will be transferred during the peak phase of each pulse. This stabilization phase that follows each peak phase reduces weld puddle instability and spatter, reduces the energy input to the weld (at least in part by avoiding “hard shorts”, mitigates porosity, and reduces “burn through” of the workpiece.

[0024] FIG. 4 shows an exemplary DCEN pulsed welding process 50 illustrated in terms of an exemplary voltage trace 52 and current trace 54 over several sequential cycles of pulsed welding. During each cycle, a voltage ramp 56 is the leading edge of a voltage peak 58, followed by a stabilization phase down ramp 60, which is current-closed loop, and a voltage-closed loop ramp 62 back to a background voltage level 64. Corresponding phases may be seen in the current waveform 54. That is, a current-closed loop ramp 66 is implemented rising to the voltage-closed loop controlled peak 68. During the peak, the controller may vary the current to maintain the voltage at the desired level. In practice, a desired voltage command is issued during the peak phase, although the actual voltage may vary based on the dynamics of the arc, occasional shorts that may occur, and so forth. Thereafter, a current-closed loop, generally parabolic stabilization phase ramp 72 drives the current down to a transition to a voltage-closed loop ramp 74 to return to the background level 78. The same cycle is then repeated throughout the welding operation.

[0025] By way of example, in one embodiment, the rising edge portion 66 of the current waveform 54 may be controlled at a ramp rate of approximately 600 A/ms. Upon achieving peak amperage 68, the control circuitry will maintain a desired voltage peak, such as approximately 200 V during a peak period 70. The generally parabolic stabilization phase 72 of current-closed loop control will then be implemented during a time 76 until the current has reached a programmed transition point. Here, and throughout the present disclosure, it should be borne in mind that the particular voltages, currents, ramp rates, and so forth will typically be programmed (“trained”) in advance,

optimized for particular wires and wire sizes, and so forth. Moreover, in some systems, some degree of operator or programmer control of the parameters may be provided.

[0026] FIG. 5 illustrates the peak, stabilization, and return phases of the current waveform in somewhat greater detail. As shown, the current peak 80 begins at a background level 78. At transition point 82, then, a linear ramp 66 is initiated, such as at a rate of between 450 and 650 A/ms to a peak current transition point 84, such as between 210 and 400 A. Of course these ranges are exemplary only, and will typically be different for different wire sizes and wire feed speeds. In a presently contemplated embodiment, the transition at this point may actually occur based on one of two considerations. That is, the current may reach a programmed level, as mentioned, or the voltage may reach a programmed peak value before the current reaches that level, resulting in a transition before the current limit is reached. Thereafter, during the peak phase, the current “floats” to maintain the voltage at a desired level in a voltage-closed loop manner. Following the period for this peak, as indicated by transition point 86, the stabilization phase begins that includes a decline in the current through current-closed loop control.

[0027] The generally parabolic shape of the current waveform during the stabilization phase results from implementation of a current-per-unit-time-squared ( $i/t^2$ ) relationship during the ramped decline in current. Once the current reaches a transition point 88, such as between 25 and 325 A, control again transitions to voltage-closed loop control, and the current waveform will exhibit a shape resulting from the control attempting to maintain the desired voltage decline to the background level. It should be noted, however, that the transition point for exiting the stabilization phase may vary for different wire sizes and ratings, and may be programmable within one or more ranges. For example, for 0.045” wires, the exit point may be programmed between 100 and 325 A; for 0.040” wire it may be programmed between 50 and 275 A; and for 0.035” wire it may be programmed between 25 and 225 A. The programmed value tends to be roughly 25 to 50 A higher than current-control-to-voltage-control transitions in peak down ramps in existing pulse

welding regimes (and where the current begins to regulate during the return to background levels under voltage-closed loop control). Moreover, in a currently contemplated implementation, the gain applied during this “return” phase of voltage-closed loop control is, in a presently contemplated embodiment, proportional only (although other gain relationships may be used). It is believed that the combination of the parabolic stabilization phase, the earlier exit point, and the use of a proportional-only gain for the return to background levels, separately and/or together, produce better control of arc stability (prioritized over arc length), and result in less frequent shorts, and the tendency to avoid “hard shorts”.

[0028] While only certain features of the invention have been illustrated and described herein, many modifications and changes will occur to those skilled in the art. It is, therefore, to be understood that the appended claims are intended to cover all such modifications and changes as fall within the true spirit of the invention.

## CLAIMS:

1. A welding system, comprising:
  - a power source configured to generate welding power and deliver the welding power to a welding torch, wherein the welding torch is coupled to a negative output terminal of the power source;
  - a welding wire feeder configured to advance a metal cored electrode into the welding torch at a rate of advancement; and
  - control circuitry configured to implement an electrode negative pulse welding regime comprising a voltage-closed loop peak phase, a generally parabolic current-closed loop stabilization phase following the peak phase, and a voltage-closed loop return phase following the stabilization phase.
2. The welding system of claim 1, wherein the stabilization phase comprises a down ramp of current defined by a current-per-unit-time-squared relationship.
3. The welding system of claim 1, wherein the return phase comprises a proportional only gain on voltage.
4. The welding system of claim 1, wherein a leading edge of the peak phase comprises a linear current-closed loop ramp to a pre-determined transition point.
5. The welding system of claim 1, wherein a voltage command of the welding power during the peak phase is between 18 and 28 v.
6. The welding system of claim 1, wherein a transition between the stabilization phase and the return phase is programmable between 25 and 325 A.

7. The welding system of claim 6, wherein the transition between the stabilization phase and the return phase is above 50 A.

8. The welding system of claim 8, wherein the transition between the stabilization phase and the return phase is above 100 A.

9. The welding system of claim 1, wherein the pulse welding regime produces a generally globular transfer of molten metal from the electrode to a weld puddle.

10. A welding method, comprising:  
creating a linear current-close loop controlled ramp to a desired peak transition;  
voltage-closed loop regulating welding power during a peak phase;  
creating a non-linear current-closed loop ramp during a stabilization phase to a desired return transition; and  
creating a voltage-closed loop return to a background power level;  
wherein the steps are performed cyclically throughout a welding operation with an electrode negative polarity.

11. The method of claim 10, wherein the wherein the stabilization phase comprises a down ramp of current defined by a current-per-unit-time-squared relationship.

12. The method of claim 10, wherein the return phase comprises a proportional only gain on voltage.

13. The method of claim 10, wherein the method is performed with a metal cored welding wire electrode.

14. The method of claim 10, wherein a voltage command of the welding power during the peak phase is between 18 and 28 v.

15. The method of claim 10, wherein the a transition between the stabilization phase and the return phase is programmable between 25 and 325 A.

16. The method of claim 10, wherein the pulse welding regime produces a generally globular transfer of molten metal from the electrode to a weld puddle.

17. A non-transitory computer-readable medium having computer executable code stored thereon, the code comprising instructions for:

creating a linear current-close loop controlled ramp to a desired peak transition;

voltage-closed loop regulating welding power during a peak phase;

creating a non-linear current-closed loop ramp during a stabilization phase to a desired return transition; and

creating a voltage-closed loop return to a background power level;

wherein the steps are performed cyclically throughout a welding operation with an electrode negative polarity.

18. The non-transitory computer-readable medium of claim 17, wherein the wherein the stabilization phase comprises a down ramp of current defined by a current-per-unit-time-squared relationship.

19. The non-transitory computer-readable medium of claim 17, wherein the return phase comprises a proportional only gain on voltage.

20. The non-transitory computer-readable medium of claim 17, wherein the method is performed with a metal cored welding wire electrode.



21. The non-transitory computer-readable medium of claim 17, wherein a voltage command of the welding power during the peak phase is between 18 and 28 v.

22. The non-transitory computer-readable medium of claim 17, wherein the a transition between the stabilization phase and the return phase is programmable between 25 and 325 A.




FIG. 1

2 / 4




FIG. 2




FIG. 3




FIG. 4

4 / 4




FIG. 5

## INTERNATIONAL SEARCH REPORT

International application No

PCT/US2014/017864

A. CLASSIFICATION OF SUBJECT MATTER  
 INV. B23K9/09 B23K9/095  
 ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
 B23K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, WPI Data

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DE 198 08 383 A1 (VOLKSWAGEN AG [DE]) 2 September 1999 (1999-09-02) column 11; figures 5,6 -----	1-9
X	US 6 051 810 A (STAVA ELLIOTT K [US]) 18 April 2000 (2000-04-18) column 8, line 54 - column 10, line 6; figures 3-5,8 -----	1-22
X	US 2010/176104 A1 (PETERS STEVEN R [US] ET AL) 15 July 2010 (2010-07-15) paragraph [0085] - paragraph [0087]; figure 25 -----	1-22
A	JP 2009 072814 A (DAIHEN CORP) 9 April 2009 (2009-04-09) abstract -----	1-22



Further documents are listed in the continuation of Box C.



See patent family annex.

\* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

13 August 2014

Date of mailing of the international search report

22/08/2014

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2  
 NL - 2280 HV Rijswijk  
 Tel. (+31-70) 340-2040,  
 Fax: (+31-70) 340-3016

Authorized officer

De Backer, Tom

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2014/017864

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
DE 19808383	A1	02-09-1999	NONE
US 6051810	A	18-04-2000	AR 020621 A1 22-05-2002
			AR 040837 A2 20-04-2005
			AT 399613 T 15-07-2008
			AU 729563 B2 01-02-2001
			AU 4888399 A 01-06-2000
			CA 2282880 A1 27-05-2000
			CN 1255418 A 07-06-2000
			EP 1004389 A1 31-05-2000
			ES 2310025 T3 16-12-2008
			ID 23941 A 02-06-2000
			JP 3134197 B2 13-02-2001
			JP 2000158132 A 13-06-2000
			KR 20000034947 A 26-06-2000
			NZ 338005 A 25-08-2000
			RU 2217275 C2 27-11-2003
			SG 82642 A1 21-08-2001
			TW 457164 B 01-10-2001
			US 6051810 A 18-04-2000
			US 6215100 B1 10-04-2001
US 2010176104	A1	15-07-2010	CN 102574233 A 11-07-2012
			EP 2464489 A1 20-06-2012
			JP 2013501626 A 17-01-2013
			US 2010176104 A1 15-07-2010
			WO 2011018693 A1 17-02-2011
JP 2009072814	A	09-04-2009	JP 4950819 B2 13-06-2012
			JP 2009072814 A 09-04-2009