

(19)



(11)

EP 1 842 936 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

10.10.2007 Bulletin 2007/41

(51) Int Cl.:

C22C 32/00 (2006.01)

C22C 38/16 (2006.01)

C22C 38/00 (2006.01)

(21) Application number: **07105839.0**

(22) Date of filing: **10.04.2007**

(84) Designated Contracting States:

**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IS IT LI LT LU LV MC MT NL PL PT RO SE
SI SK TR**

Designated Extension States:

AL BA HR MK YU

(30) Priority: **07.04.2006 JP 2006105801**

(71) Applicant: **Tungaloy Corporation**

**Kawasaki-shi,
Kanagawa 212-8503 (JP)**

(72) Inventors:

- **Okazaki, Takashi**
Kawasaki-shi Kanagawa 212-8503 (JP)
- **Matsumoto, Masaaki**
Kawasaki-shi Kanagawa 212-8503 (JP)

(74) Representative: **Ziebig, Marlene et al**

**Gulde Hengelhaupt Ziebig & Schneider
Wallstrasse 58/59
10179 Berlin (DE)**

(54) **Frictional material**

(57) As the railroad speed becomes higher, frictional materials having magnetic properties, frictional properties, and a resistance to melting and depositing more excellent than those of conventional frictional materials are desired. The present invention provides a frictional material comprising a metal matrix and hard particles, wherein the frictional material contains: 1 to 5% by weight of Cu; 0.1 to 1.0% by weight of P; 1 to 5% by weight of at least one soft metal selected from the group consisting of Bi, Sb, In, and Ag; 1 to 6% by weight of hard particles

of at least one member selected from the group consisting of zircon (ZrSiO_4) and zirconia (ZrO_2); and the balance comprising Fe and an unavoidable impurity. The frictional material of the present invention has excellent magnetic properties and excellent frictional properties as well as excellent resistance to melting and depositing, and exhibits excellent damping properties particularly when used as a magnetic rail brake.

EP 1 842 936 A1

Description

BACKGROUND OF THE INVENTION

Field of the Invention

[0001] The present invention relates to a frictional material for use in a means for arbitrarily controlling the rotation or movement of various machines, specifically a clutch or brake. More particularly, the present invention is concerned with a frictional material advantageously used in a magnetic rail brake or electromagnetic clutch.

Background Art

[0002] A frictional material generally used in a magnetic rail brake is obtained by mixing metal powder forming a matrix with hard particles and sintering the resultant mixture. Examples of conventional frictional materials for magnetic rail brake include a sintered material comprised of a wear-resistant material comprised of at least one member selected from the group consisting of Al_2O_3 , ZrO_2 , Al_2TiO_5 , Y_2O_3 , SiC , Si_3N_4 , WC , Cr_3C_2 , and TiC , and powder of at least one member selected from the group consisting of nodular cast iron, graphite, iron sulfide, manganese sulfide, lead, and molybdenum sulfide (see, for example, Patent document 1).

[0003] [Patent document 1] Japanese Unexamined Patent Publication No. Hei 11-78882

[0004] When a magnetic rail brake operates, a frictional material is pressed against a rail and, simultaneously, the magnetic force causes tension between the frictional material and the rail, so that the friction of the frictional material against the rail causes the train to slow down. In a magnetic field generated from an electromagnet in the magnetic rail brake, the higher the magnetic flux density of the frictional material, the stronger the magnetic force, or the stronger the tension between the frictional material and the rail, that is, the magnetic rail brake increases in damping force. The frictional material has a high coefficient of friction and hence, when the frictional material is unlikely to be melted and deposited, the frictional material achieves higher frictional force, thus increasing the damping force. Further, when the frictional material has excellent wear resistance, the frequency of replacement of the frictional material by another can be reduced. Therefore, it is desired that the frictional material for use in magnetic rail brake has excellent frictional properties evaluated in terms of a wear resistance and a coefficient of friction, excellent resistance to melting and depositing, and excellent magnetic properties evaluated in terms of a magnetic flux density. Accordingly, an object of the present invention is to provide a frictional material having excellent frictional properties and excellent resistance to melting and depositing as well as excellent magnetic properties.

SUMMARY OF THE INVENTION

[0005] The present inventors have made extensive and intensive studies on frictional materials. As a result, they have succeeded in obtaining a frictional material having excellent frictional properties and excellent resistance to melting and depositing as well as excellent magnetic properties. Specifically, the present invention is directed to a frictional material comprising a metal matrix and hard particles, wherein the frictional material contains: 1 to 5% by weight of Cu; 0.1 to 1.0% by weight of P; 1 to 5% by weight of at least one soft metal selected from the group consisting of Bi, Sb, In, and Ag; 1 to 6% by weight of hard particles of at least one member selected from the group consisting of zircon (ZrSiO_4) and zirconia (ZrO_2); and the balance comprising Fe and an unavoidable impurity.

DETAILED DESCRIPTION OF THE INVENTION

[0006] The frictional material of the present invention comprises a metal matrix comprised mainly of Fe containing Cu, P, and Bi, Sb, In, or Ag, and hard particles of at least one member selected from zircon and zirconia.

[0007] In the frictional material of the present invention, when the Cu content is less than 1% by weight, the resistance to melting and depositing is lowered. On the other hand, when the Cu content is more than 5% by weight, the coefficient of friction is lowered, and further the relative Fe content is reduced, so that the magnetic flux density is lowered. Therefore, the Cu content must be 1 to 5% by weight. It is preferred that the Cu content is 2 to 4% by weight.

[0008] In the frictional material of the present invention, when the P content is less than 0.1% by weight, the resistance to melting and depositing is lowered. On the other hand, when the P content is more than 1.0% by weight, the coefficient of friction is lowered, and further the relative Fe content is reduced, so that the magnetic flux density is lowered. Therefore, the P content must be 0.1 to 1.0% by weight. It is preferred that the P content is 0.3 to 0.5% by weight.

[0009] When the content of at least one soft metal selected from the group consisting of Bi, Sb, In, and Ag in the frictional material of the present invention is less than 1% by weight, the resistance to melting and depositing is lowered. On the other hand, when the soft metal content is more than 5% by weight, the coefficient of friction is lowered, and

further the relative Fe content is reduced, so that the magnetic flux density is lowered. Therefore, the soft metal content must be 1 to 5% by weight. It is preferred that the soft metal content is 1.5 to 3.0% by weight.

[0010] When the content of hard particles of at least one member selected from the group consisting of zircon and zirconia in the frictional material of the present invention is less than 1% by weight, both the coefficient of friction and the resistance to melting and depositing are lowered. On the other hand, when the hard particle content is more than 6% by weight, the relative Fe content is reduced, so that the magnetic flux density is lowered. Therefore, the hard particle content must be 1 to 6% by weight. It is preferred that the hard particle content is 2 to 4% by weight.

[0011] As an example of a method for producing the frictional material of the present invention, there can be mentioned the following method.

Commercially available Fe powder having an average particle size of 60 to 140 μm , Cu powder having an average particle size of 30 to 70 μm , Fe-P powder having an average particle size of 60 to 140 μm , Cu-P powder having an average particle size of 60 to 140 μm , Bi powder having an average particle size of 40 to 100 μm , Sb powder having an average particle size of 40 to 100 μm , In powder having an average particle size of 50 to 150 μm , Ag powder having an average particle size of 5 to 15 μm , ZrSiO_4 powder having an average particle size of 100 to 400 μm , ZrO_2 powder having an average particle size of 400 to 800 μm , MoS_2 powder having an average particle size of 3 to 10 μm , C powder having an average particle size of 50 to 350 μm , and SiC powder having an average particle size of 2 to 8 μm are prepared. These powders are weighed and mixed to achieve a desired composition. The resultant mixture is subjected to cold molding under a pressure of 196 and 490 MPa. The cold-molded mixture is placed in a sintering furnace and sintered in a hydrogen gas atmosphere under conditions such that the sintering temperature is 900 to 1,100°C and the sintering time is 0.5 to 2 hours, thus producing the frictional material of the present invention. When the sintering is performed while uniaxial pressing under a pressure of 0.49 to 3.92 MPa, the resultant frictional material advantageously has an improved wear resistance.

[0012] With respect to the frictional material of the present invention, for increasing the tension between the frictional material and a rail, it is preferred that the frictional material has a magnetic flux density of 1.38 to 1.42 T in a magnetic field at a strength of 50 kA/m.

Further, with respect to the frictional material of the present invention, for further increasing the tension between the frictional material and a rail, it is more preferred that the frictional material has a magnetic flux density of 2.05 to 2.09 T in a magnetic field at a strength of 400 kA/m.

[0013] Examples of uses of the frictional material of the present invention include means for arbitrarily controlling the rotation or movement of various machines, such as machine tools, construction machineries, agricultural machineries, automobiles, two-wheeled vehicles, railroads, aircrafts, or marine structures, specifically, so-called clutches and brakes. Of these, more preferred are uses of the frictional material as a magnetic rail brake or an electromagnetic clutch, which fully utilize excellent magnetic properties of the frictional material, i.e., high magnetic flux density, and especially, the most preferred is use of the frictional material as a magnetic rail brake.

[0014] The frictional material of the present invention has excellent frictional properties including wear resistance and coefficient of friction, excellent resistance to melting and depositing, and excellent magnetic properties including magnetic flux density. When the frictional material of the present invention is used as a frictional material for clutch or brake in various machines, such as machine tools, construction machineries, agricultural machineries, automobiles, two-wheeled vehicles, railroads, aircrafts, or marine structures, the frictional material not only exhibits excellent damping properties but also extends the use life. The frictional material of the present invention has excellent magnetic properties and hence, when used as a frictional material for magnetic rail brake or electromagnetic clutch, the frictional material exhibits especially excellent damping properties and extends the use life.

Example 1

[0015] Commercially available Fe powder having an average particle size of 100 μm , Cu powder having an average particle size of 49 μm , Fe-P powder having an average particle size of 100 μm , Cu-P powder having an average particle size of 100 μm , Bi powder having an average particle size of 70 μm , Sb powder having an average particle size of 70 μm , Ag powder having an average particle size of 10 μm , ZrSiO_4 powder having an average particle size of 200 μm , ZrO_2 powder having an average particle size of 600 μm , MoS_2 powder having an average particle size of 7 μm , C powder having an average particle size of 200 μm , and SiC powder having an average particle size of 5 μm were prepared. These raw material powders were weighed and mixed to achieve compositions shown in Table 1. The resultant mixture was subjected to cold molding under a pressure of 392 MPa, and then placed in a sintering furnace. The mixture was sintered using a hot press in a hydrogen gas atmosphere at a sintering temperature of 1,000°C under a pressure for uniaxial pressing of 1.5 MPa for one hour as a sintering time.

[0016]

[Table 1]

	Composition (wt%)											
	Fe	Cu	P	Bi	Sb	Ag	ZrSiO ₄	ZrO ₂	MoS ₂	C	SiC	Total
5	Example 1	91.7	2.9	0.5	2.0	-	-	3.0	-	-	-	100
	Example 2	93.6	1.0	0.5	2.0	-	-	3.0	-	-	-	100
10	Example 3	89.8	4.8	0.5	2.0	-	-	3.0	-	-	-	100
	Example 4	92.1	2.9	0.1	2.0	-	-	3.0	-	-	-	100
	Example 5	91.2	2.9	1.0	2.0	-	-	3.0	-	-	-	100
	Example 6	92.6	2.9	0.5	1.0	-	-	3.0	-	-	-	100
15	Example 7	88.8	2.8	0.5	5.0	-	-	3.0	-	-	-	100
	Example 8	88.8	2.8	0.5	3.0	1.0	1.0	3.0	-	-	-	100
	Example 9	93.6	2.9	0.5	2.0	-	-	1.0	-	-	-	100
20	Example 10	88.8	2.8	0.5	2.0	-	-	6.0	-	-	-	100
	Example 11	91.7	2.9	0.5	2.0	-	-	1.0	2.0	-	-	100
	Comparative Example 1	94.5	-	0.5	2.0	-	-	3.0	-	-	-	100
25	Comparative Example 2	86.9	7.6	0.5	2.0	-	-	3.0	-	-	-	100
	Comparative Example 3	92.2	2.9	-	2.0	-	-	3.0	-	-	-	100
30	Comparative Example 4	90.3	2.9	1.9	2.0	-	-	3.0	-	-	-	100
	Comparative Example 5	93.6	2.9	0.5	-	-	-	3.0	-	-	-	100
35	Comparative Example 6	85.9	2.7	0.4	8.0	-	-	3.0	-	-	-	100
	comparative Example 7	94.6	2.9	0.5	2.0	-	-	-	-	-	-	100
40	Comparative Example 8	86.9	2.7	0.5	2.0	-	-	8.0	-	-	-	100
	Comparative Example 9	77.0	3.0	-	3.0	-	-	-	3.0	7.0	10.0	100
45	Comparative Example 10	93.5	5.0	-	-	-	-	-	0.5	0.5	0.5	100

[0017] A sample obtained by sintering was machined into a test specimen having a size: 10 mm × 10 mm × 8 mm, and a magnetic flux density of the sample was measured using a magnetic property tester (BH analyzer). The results are shown in Table 2. Further, an abrasion test shown below was conducted to measure a coefficient of friction, an abrasion wear, and an amount of melting and deposition. The results are also shown in Table 2.

[0018] Abrasion test

Test machine: Inertia abrasion tester
 Moment of inertia: 7.35 kgm²
 Speed: 33 m/s
 Contact pressure: 980 kPa
 Test specimen size: 25mm × 25mm × 10 mm

Brake starting temperature: 100°C or lower

[0019]

[Table 2]

	Magnetic properties		Frictional properties		Resistance to melting and depositing	Overall judgment (Good, Bad)
	Magnetic flux density (T)		Coefficient of friction (-)	Abrasion wear (mm)	Amount of melting and deposition (Large, Medium, Small, None)	
	In magnetic field at strength of 50 kA/m	In magnetic field at strength of 400 kA/m				
Example 1	1.41	2.09	0.40	0.339	Small	Good
Example 2	1.42	2.09	0.39	0.345	Small	Good
Example 3	1.40	2.08	0.40	0.320	Small	Good
Example 4	1.41	2.09	0.39	0.365	Small	Good
Example 5	1.40	2.05	0.39	0.335	Small	Good
Example 6	1.41	2.08	0.40	0.350	Small	Good
Example 7	1.38	2.06	0.40	0.426	None	Good
Example 8	1.39	2.07	0.40	0.402	Small	Good
Example 9	1.39	2.08	0.39	0.389	Small	Good
Example 10	1.40	2.09	0.38	0.418	Small	Good
Example 11	1.38	2.06	0.40	0.311	None	Good
Example 12	1.41	2.09	0.40	0.352	Small	Good
Comparative Example 1	1.39	2.09	0.39	0.366	Large	Bad
Comparative Example 2	1.36	2.02	0.36	0.388	Large	Bad
Comparative Example 3	1.40	2.07	0.38	0.335	Large	Bad
Comparative Example 4	1.39	2.03	0.37	0.412	Medium	Bad
Comparative Example 5	1.41	2.09	0.40	0.338	Large	Bad
Comparative Example 6	1.34	2.01	0.35	0.456	Small	Bad
Comparative Example 7	1.41	2.07	0.34	0.433	Large	Bad
Comparative Example 8	1.35	2.00	0.40	0.310	Small	Bad
Comparative Example 9	1.23	1.85	0.40	0.341	Small	Bad
Comparative Example 10	1.42	2.09	0.32	0.620	Large	Bad

[0020] Table 2 indicates: that the higher the magnetic flux density, the more excellent the magnetic properties; that the higher the coefficient of friction or the smaller the abrasion wear, the more excellent the frictional properties; and that the smaller the amount of melting and deposition, the more excellent the welding resistance. As can be seen from Table 2, in the Examples of the present invention, the balance between the magnetic properties, frictional properties, and resistance to melting and depositing is excellent and therefore, overall judgments better than those of the Comparative Examples were obtained.

Claims

1. A frictional material comprising a metal matrix and hard particles, wherein said frictional material contains:

1 to 5% by weight of Cu;
0.1 to 1.0% by weight of P;
1 to 5% by weight of at least one soft metal selected from the group consisting of Bi, Sb, In, and Ag;
1 to 6% by weight of hard particles of at least one member selected from the group consisting of zircon (ZrSiO_4) and zirconia (ZrO_2); and
the balance comprising Fe and an unavoidable impurity.

2. The frictional material according to claim 1, which has a magnetic flux density of 1.38 to 1.42 T in a magnetic field at a strength of 50 kA/m.
3. The frictional material according to claim 1 or 2, which has a magnetic flux density of 2.05 to 2.09 T in a magnetic field at a strength of 400 kA/m.
4. Use of the frictional material according to any one of claims 1 to 3 as a frictional material for magnetic rail brake or electromagnetic clutch.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 07 10 5839

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IPC)
X	JP 59 197549 A (MITSUBISHI METAL CORP) 9 November 1984 (1984-11-09) * abstract; table 1 *	1-4	INV. C22C32/00 C22C38/16 C22C38/00
A	EP 0 620 286 A1 (HITACHI LTD [JP]) 19 October 1994 (1994-10-19) * claims 1-20; tables 1,2 *	1-4	
A	JP 2000 277315 A (TOYOTA CENTRAL RES & DEV) 6 October 2000 (2000-10-06) * abstract *	1-4	
A	US 2001/052373 A1 (KANAOKA JYUNJI [JP]) 20 December 2001 (2001-12-20) * abstract; claims 1-6 *	1-4	
A	JP 63 092842 A (TOYOTA MOTOR CORP) 23 April 1988 (1988-04-23) * abstract *	1-4	
A	JP 09 301256 A (TOSHIBA TUNGALOY CO LTD) 25 November 1997 (1997-11-25) * abstract *	1-4	
A	US 4 050 619 A (TARR WALTER R) 27 September 1977 (1977-09-27) * claims 1-6; table 1 *	1-4	C22C
The present search report has been drawn up for all claims			
Place of search Munich		Date of completion of the search 18 July 2007	Examiner Catana, Cosmin
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

1

EPO FORM 1503 03.92 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 07 10 5839

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

18-07-2007

Patent document cited in search report		Publication date		Patent family member(s)		Publication date
JP 59197549	A	09-11-1984	JP	1016906 B		28-03-1989
			JP	1530534 C		15-11-1989

EP 0620286	A1	19-10-1994	DE	69414902 D1		14-01-1999
			DE	69414902 T2		22-04-1999
			JP	2914076 B2		28-06-1999
			JP	6271956 A		27-09-1994
			US	5589652 A		31-12-1996

JP 2000277315	A	06-10-2000	NONE			

US 2001052373	A1	20-12-2001	DE	10127891 A1		07-03-2002
			JP	2001354951 A		25-12-2001

JP 63092842	A	23-04-1988	NONE			

JP 9301256	A	25-11-1997	NONE			

US 4050619	A	27-09-1977	CA	1063333 A1		02-10-1979

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- JP HEI1178882 A [0003]