



(51) International Patent Classification:

C08J5/18 (2006.01) *C08F 210/16* (2006.01)
B32B 27/32 (2006.01) *C08L 23/08* (2006.01)

(21) International Application Number:

PCT/US2018/051704

(22) International Filing Date:

19 September 2018 (19.09.2018)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

62/561,833 22 September 2017 (22.09.2017) US

(71) Applicants: **DOW GLOBAL TECHNOLOGIES LLC** [US/US]; 2040 Dow Center, Midland, Michigan 48674 (US). **PBBPOLISUR S.R.L.** [AR/AR]; Boulevard Cecilia Grierson 355 - Piso 25, Buenos Aires, C1107CPG (AR).

(72) Inventors: **PEREZ MUÑOZ, Maria Laura**; c/o PBBPolisur S.R.L., Boulevard Cecilia Grierson 355 - Dique IV, Piso 25, Buenos Aires, C1107CPG (AR). **GARGALAKA JÚNIOR, Joao**; c/o Dow Brasil Industria e Comercio de Produtos Quimicos Ltda., Av. Andre Costa, 2201 - Pack Studios Jundiai, CEP: 13214-730 Jundiai-Sao Paulo (BR). **MAZZOLA, Nicolas Cardoso**; c/o Dow Brasil Industria e Comercio de Produtos Quimicos Ltda., Av. Andre Costa, 2201 - Pack Studios Jundiai, CEP: 13214-730 Jundiai-Sao Paulo (BR). **BUASZCZYK, Gianna**; c/o Dow Brasil Industria e Comercio de Produtos Quimicos Ltda., Av. Andre Costa, 2201 - Pack Studios Jundiai, CEP: 13214-730 Jundiai-Sao Paulo (BR). **PEREZ, Carmelo Delect**; c/o The Dow Chemical Company, 230 Abner Jackson Parkway, Lake Jackson, Texas 77566 (US). **HANSEN, Sydney E.**; c/o The Dow Chemical Company, 1254 Enclave Parkway, Houston Dow Center, Houston, Texas 77077 (US).

(74) Agent: **MOLLOY, Matthew A.** et al.; c/o Dinsmore & Shohl LLP, One South Main Street, Suite 1300, Dayton, Ohio 45402 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA,

SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(H))
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(Hi))

Published:

- with international search report (Art. 21(3))

(54) Title: THERMOFORMED FILM COMPOSITIONS WITH ENHANCED TOUGHNESS AFTER THERMOFORMING PROCESSES

(57) Abstract: Embodiments of thermoformed monolayer or multilayer films are provided, wherein the thermoformed monolayer multilayer films comprise a first composition comprising at least one ethylene-based polymer, wherein the first composition comprises a Molecular Weighted Comonomer Distribution Index (MWCDI) value greater than 0.9, and a melt index ratio (I10/I2) that meets the following equation: $I10/I2 \geq 7.0 - 1.2 \times \log(\%)$.



-1-

**THERMOFORMED FILM COMPOSITIONS WITH ENHANCED TOUGHNESS
AFTER THERMOFORMING PROCESSES**

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This application claims priority to U.S. Provisional Application Serial No. 62/561,833 filed September 22, 2017, the entire disclosure of which is hereby incorporated by reference.

TECHNICAL FIELD

[0002] Embodiments described herein relate generally to thermoformed film compositions, and more particularly relate to thermoformed film compositions which are imparted with enhanced toughness due to the thermoforming process.

BACKGROUND

[0003] Thermoforming is one of the most frequently used film-forming techniques in many packaging applications. In the process, the film is heated and formed, still solid state, to a specific shape in a mold; then the product is added and finally the lidding film is sealed on the top. The thermoforming film structure needs to meet different requirements in order to fulfill the stages of the process and the end use. As sharp products can be packed a very good puncture resistance is needed.

[0004] Moreover, in order to hold heavy products a certain amount of stiffness is needed but must be balanced with high toughness to protect food products that are packaged inside. Also of importance is improving low temperature resistance as many products are frozen to protect the shelf life.

[0005] That said, many of the toughness properties of conventional polymer compositions are weakened due to the thermoforming process.

[0006] Accordingly, there is a need for improved thermoformable compositions which not only maintain, but improve the toughness properties after thermoforming.

-2-

SUMMARY

[0007] The present compositions meet these needs by providing improved toughness after thermoforming. After thermoforming, the present compositions demonstrated improved puncture resistance, improved dart performance, and improved stiffness.

[0008] According to at least one embodiment of the present disclosure, a thermoformed multilayer film structure is provided. The thermoformed multilayer film comprises a core layer and at least two outer layers disposed externally relative to the core layer. At least one layer of the thermoformed multilayer film structure comprises a first composition comprising at least one ethylene-based polymer, wherein the first composition comprises a Molecular Weighted Comonomer Distribution Index (MWCDI) value greater than 0.9, and a melt index ratio (I_{10}/I_2) that meets the following equation: $I_{10}/I_2 \geq 7.0 - 1.2 \times \log(I_2)$.

[0009] According to another embodiment, a thermoformed monolayer film structure is provided. The thermoformed monolayer film structure comprises the first composition. The thermoformed monolayer film demonstrates an increase in puncture resistance of at least 10% due to thermoforming applications.

[0010] These and other embodiments are described in more detail in the following Detailed Description.

BRIEF DESCRIPTION OF THE DRAWINGS

[0011] The following detailed description of specific embodiments of the present disclosure can be best understood when read in conjunction with the following drawings, where like structure is indicated with like reference numerals and in which:

[0012] Figure 1 depicts the plot of " SCB_f versus IR5 Area Ratio" for ten SCB Standards.

[0013] Figure 2 depicts the several GPC profiles for the determination of IR5 Height Ratio for a sample first composition.

[0014] Figure 3 depicts the plot of " SCB_f versus Polyethylene Equivalent molecular Log Mwi (GPC)" for a sample first composition.

-3-

[0015] Figure 4 depicts a plot of the "Mole Percent Comonomer versus Polyethylene Equivalent Log M_{wi} (GPC)" for a sample first composition.

[0016] Figure 5 is a bar graph depicting puncture resistance for several monolayer films before and after thermoforming in accordance with one or more embodiments of the present disclosure.

[0017] Figure 6 is a bar graph depicting instrumented dart impact for several multilayer films before and after thermoforming in accordance with one or more embodiments of the present disclosure.

[0018] Figure 7 is a bar graph depicting puncture resistance for several multilayer films before and after thermoforming in accordance with one or more embodiments of the present disclosure.

DETAILED DESCRIPTION

[0019] Specific embodiments of the present application will now be described. The disclosure may, however, be embodied in different forms and should not be construed as limited to the embodiments set forth in this disclosure. Rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey the scope of the subject matter to those skilled in the art.

[0020] DEFINITIONS

[0021] The term "polymer" refers to a polymeric compound prepared by polymerizing monomers, whether of the same or a different type. The generic term polymer thus embraces the term "homopolymer," usually employed to refer to polymers prepared from only one type of monomer as well as "copolymer" which refers to polymers prepared from two or more different monomers. The term "interpolymer," as used herein, refers to a polymer prepared by the polymerization of at least two different types of monomers. The generic term interpolymer thus includes copolymers, and polymers prepared from more than two different types of monomers, such as terpolymers.

-4-

[0022] "Polyethylene" or "ethylene-based polymer" shall mean polymers comprising greater than 50% by weight of units which have been derived from ethylene monomer. This includes polyethylene homopolymers or copolymers (meaning units derived from two or more comonomers). Common forms of polyethylene known in the art include Low Density Polyethylene (LDPE); Linear Low Density Polyethylene (LLDPE); Ultra Low Density Polyethylene (ULDPE); Very Low Density Polyethylene (VLDPE); single-site catalyzed Linear Low Density Polyethylene, including both linear and substantially linear low density resins (m-LLDPE); Medium Density Polyethylene (MDPE); and High Density Polyethylene (HDPE).

[0023] The term "LDPE" may also be referred to as "high pressure ethylene polymer" or "highly branched polyethylene" and is defined to mean that the polymer is partly or entirely homopolymerized or copolymerized in autoclave or tubular reactors at pressures above 14,500 psi (100 MPa) with the use of free-radical initiators, such as peroxides (see for example US 4,599,392, which is hereby incorporated by reference). LDPE resins typically have a density in the range of 0.916 to 0.935 g/cm.

[0024] The term "LLDPE", includes resin made using Ziegler-Natta catalyst systems as well as resin made using single-site catalysts, including, but not limited to, bis-metallocene catalysts (sometimes referred to as "m-LLDPE") and constrained geometry catalysts, and resin made using post-metallocene, molecular catalysts. LLDPE includes linear, substantially linear or heterogeneous polyethylene copolymers or homopolymers. LLDPEs contain less long chain branching than LDPEs and includes the substantially linear ethylene polymers which are further defined in U.S. Patent 5,272,236, U.S. Patent 5,278,272, U.S. Patent 5,582,923 and US Patent 5,733,155; the homogeneously branched linear ethylene polymer compositions such as those in U.S. Patent No. 3,645,992; the heterogeneously branched ethylene polymers such as those prepared according to the process disclosed in U.S. Patent No. 4,076,698; and/or blends thereof (such as those disclosed in US 3,914,342 or US 5,854,045). The LLDPE resins can be made via gas-phase, solution-phase or slurry polymerization or any combination thereof, using any type of reactor or reactor configuration known in the art.

[0025] The term "MDPE" refers to polyethylenes having densities from 0.926 to 0.935 g/cc. "MDPE" is typically made using chromium or Ziegler-Natta catalysts or using single-site

catalysts including, but not limited to, bis-metallocene catalysts and constrained geometry catalysts.

[0026] The term "HDPE" refers to polyethylenes having densities greater than about 0.935 g/cc, which are generally prepared with Ziegler-Natta catalysts, chrome catalysts or single-site catalysts including, but not limited to, bis-metallocene catalysts and constrained geometry catalysts.

[0027] The term "ULDPE" refers to polyethylenes having densities of 0.880 to 0.912 g/cc, which are generally prepared with Ziegler-Natta catalysts, single-site catalysts including, but not limited to, bis-metallocene catalysts and constrained geometry catalysts, and post-metallocene, molecular catalysts. The term "propylene-based polymer," as used herein, refers to a polymer that comprises, in polymerized form, refers to polymers comprising greater than 50% by weight of units which have been derived from propylene monomer. This includes propylene homopolymer, random copolymer polypropylene, impact copolymer polypropylene, propylene/a-olefin interpolymers, and propylene/a-olefin copolymer. These polypropylene materials are generally known in the art.

[0028] "Multilayer structure" means any structure having more than one layer. For example, the multilayer structure may have two, three, four, five or more layers. A multilayer structure may be described as having the layers designated with letters. For example, a three layer structure having a core layer B, and two external layers A and C may be designated as A/B/C. Likewise, a structure having two core layers B and C and two external layers A and D would be designated A/B/C/D. In some embodiments, a multilayer film of the present invention comprises up to 11 layers.

[0029] Reference will now be made in detail to monolayer and multilayer film structures embodiments of the present disclosure, wherein the monolayer structure or multilayer film structure comprises a first composition comprising at least one ethylene-based polymer, wherein the first composition comprises a Molecular Weighted Comonomer Distribution Index (MWCDI) value greater than 0.9, and a melt index ratio (I_{10}/I_2) that meets the following equation: $I_{10}/I_2 \geq 7.0 - 1.2 \times \log(I_2)$.

-6-

[0030] Embodiments of the multilayer film structure comprise a core layer and at least two outer layers disposed externally relative to the core layer. At least one layer of the multilayer film structure comprises the first composition. The first composition may be in multiple layers of the multilayer film. For example, the first composition may be present in the core layer, in layers external to the core layer, or combinations thereof.

[0031] First Composition

[0032] Various properties contribute to the improved toughness of the first composition. For example, the first composition has a superior comonomer distribution, which is significantly higher in comonomer concentration in the high molecular weight polymer molecules, and is significantly lower in comonomer concentration in the low molecular weight polymer molecules, as compared to conventional polymers of the art at the same overall density. It has also been discovered that the first composition has low LCB (Long Chain Branches), as indicated by low ZSVR, as compared to conventional polymers. As the result of this distribution of the comonomer, as well as the low LCB nature, the first composition has more tie chains, and thus improved film toughness.

[0033] As discussed above, the first composition comprises a MWCDI value greater than 0.9. In one embodiment, the first composition has an MWCDI value less than, or equal to, 10.0, further less than, or equal to, 8.0, further less than, or equal to, 6.0. In another embodiment, the first composition has an MWCDI value less than, or equal to, 5.0, further less than, or equal to, 4.0, further less than, or equal to, 3.0. In yet another embodiment, the first composition has an MWCDI value greater than, or equal to, 1.0, further greater than, or equal to, 1.1, further greater than, or equal to, 1.2. In a further embodiment, the first composition has an MWCDI value greater than, or equal to, 1.3, further greater than, or equal to, 1.4, further greater than, or equal to, 1.5.

[0034] The first composition has a melt index ratio (I_{10}/I_2) that meets the following equation: $I_{10}/I_2 \geq 7.0 - 1.2 \times \log(I_2)$. In yet another embodiment, the first composition has a melt index ratio I_{10}/I_2 greater than, or equal to, 7.0, further greater than, or equal to, 7.1, further greater than, or equal to, 7.2, further greater than, or equal to, 7.3. In one embodiment, the first composition has a melt index ratio I_{10}/I_2 less than, or equal to, 9.2, further less than, or equal to, 9.0, further less than, or equal to, 8.8, further less than, or equal to, 8.5.

[0035] In one embodiment, the first composition has a ZSVR value from 1.2 to 3.0, or from 1.2 to 2.5, or from 1.2 to 2.0.

[0036] In yet another embodiment, the first composition has a vinyl unsaturation level greater than 10 vinyls per 1,000,000 total carbons. For example, greater than 20 vinyls per 1,000,000 total carbons, or greater than 50 vinyls per 1,000,000 total carbons, or greater than 70 vinyls per 1,000,000 total carbons, or greater than 100 vinyls per 1,000,000 total carbons. Vinyl unsaturation is calculated using the nuclear magnetic resonance (NMR) spectroscopy defined below.

[0037] In one embodiment, the first composition has a density in the range of 0.900 g/cc to 0.960 g/cm³, or from 0.910 to 0.940 g/cm³, or from 0.910 to 0.930, or from 0.910 to 0.925 g/cm³. For example, the density can be from a lower limit of 0.910, 0.912, or 0.914 g/cm³, to an upper limit of 0.925, 0.927, or 0.930 g/cm³ (1 cm³ = 1 cc).

[0038] In a further embodiment, the first composition has a melt index (I₂; at 190°C / 2.16kg) from 0.1 to 50 g/10 minutes, for example from 0.1 to 30 g/10 minutes, or from 0.1 to 20 g/10 minutes, or from 0.1 to 10 g/10 minutes. For example, the melt index (I₂; at 190°C / 2.16 kg) can be from a lower limit of 0.1, 0.2, or 0.5 g/10 minutes, to an upper limit of 1.0, 2.0, 3.0, 4.0, 5.0, 10, 15, 20, 25, 30, 40, or 50 g/10 minutes.

[0039] In another embodiment, the first composition has a molecular weight distribution, expressed as the ratio of the weight average molecular weight to number average molecular weight (M_w/M_n) as determined by conventional Gel Permeation Chromatography (GPC) (conv. GPC) in the range of from 2.2 to 5.0. For example, the molecular weight distribution (M_w/M_n) can be from a lower limit of 2.2, 2.3, 2.4, 2.5, 3.0, 3.2, or 3.4, to an upper limit of 3.9, 4.0, 4.1, 4.2, 4.5, or 5.0.

[0040] In one embodiment, the first composition has a number average molecular weight (M_n) as determined by conv. GPC in the range from 10,000 to 50,000 g/mole. For example, the number average molecular weight can be from a lower limit of 10,000, 20,000, or 25,000 g/mole, to an upper limit of 35,000, 40,000, 45,000, or 50,000 g/mole. In another embodiment, the ethylene-based polymer has a weight average molecular weight (M_w) as determined by conv. GPC in the range from 70,000 to 200,000 g/mole. For example, the number average molecular

weight can be from a lower limit of 70,000, 75,000, or 78,000 g/mole, to an upper limit of 120,000, 140,000, 160,000, 180,000 or 200,000 g/mole.

[0041] In one embodiment, the first composition has a melt viscosity ratio, $\text{Eta}^*_{0.1} / \text{Eta}^*_{100}$, in the range from 2.2 to 7.0, wherein $\text{Eta}^*_{0.1}$ is the dynamic viscosity computed at a shear rate of 0.1 rad/s and Eta^*_{100} is the dynamic viscosity computed at shear rate of 100 rad/s. Further details on the melt viscosity ratio and dynamic viscosity calculations are provided below.

[0042] In one embodiment, the ethylene-based polymer of the first composition is an ethylene/a-olefin interpolmer, and further an ethylene/a-olefin copolymer. The a-olefin may have less than, or equal to, 20 carbon atoms. For example, the α -olefin comonomers may have 3 to 10 carbon atoms, or from 3 to 8 carbon atoms. Exemplary α -olefin comonomers include, but are not limited to, propylene, 1-butene, 1-pentene, 1-hexene, 1-heptene, 1-octene, 1-nonene, 1-decene, and 4-methyl- 1-pentene. The one or more α -olefin comonomers may, for example, be selected from the group consisting of propylene, 1-butene, 1-hexene, and 1-octene; or in the alternative, from the group consisting of 1-butene, 1-hexene and 1-octene, and further 1-hexene and 1-octene.

[0043] The ethylene-based polymers may comprise less than 20 percent by weight of units derived from one or more α -olefin comonomers. All individual values and subranges from less than 18 weight percent are included herein and disclosed herein; for example, the ethylene-based polymers may comprise from less than 15 percent by weight of units derived from one or more α -olefin comonomers; or in the alternative, less than 10 percent by weight of units derived from one or more α -olefin comonomers; or in the alternative, from 1 to 20 percent by weight of units derived from one or more α -olefin comonomers; or in the alternative, from 1 to 10 percent by weight of units derived from one or more α -olefin comonomers.

[0044] Conversely, the ethylene-based polymers may comprise at least 80 percent by weight of units derived from ethylene. All individual values and subranges from at least 80 weight percent are included herein and disclosed herein; for example, the ethylene-based polymers may comprise at least 82 percent by weight of units derived from ethylene; or in the alternative, at least 85 percent by weight of units derived from ethylene; or in the alternative, at least 90 percent by weight of units derived from ethylene; or in the alternative, from 80 to 100

percent by weight of units derived from ethylene; or in the alternative, from 90 to 100 percent by weight of units derived from ethylene.

[0045] Optionally, the first composition further may comprise a second ethylene-based polymer. In a further embodiment, the second ethylene-based polymer is an ethylene/a-olefin interpolmer, and further an ethylene/a-olefin copolymer, or an LDPE. Suitable a-olefin comonomers are listed above.

[0046] In one embodiment, the second ethylene-based polymer is a heterogeneously branched ethylene/a-olefin interpolmer, and further a heterogeneously branched ethylene/a-olefin copolymer. Heterogeneously branched ethylene/a-olefin interpolmers and copolymers are typically produced using Ziegler/Natta type catalyst system, and have more comonomer distributed in the lower molecular weight molecules of the polymer.

[0047] In one embodiment, the second ethylene-based polymer has a molecular weight distribution (M_w/M_n) in the range from 3.0 to 5.0, for example from 3.2 to 4.6. For example, the molecular weight distribution (M_w/M_n) can be from a lower limit of 3.2, 3.3, 3.5, 3.7, or 3.9, to an upper limit of 4.6, 4.7, 4.8, 4.9, or 5.0.

[0048] In one embodiment, the composition further comprises another polymer. In a further embodiment, the polymer is selected from the following: a LLDPE, a MDPE, a LDPE, a HDPE, a propylene-based polymer, or a combination thereof.

[0049] In one embodiment, the first composition further comprises a LDPE. In a further embodiment, the LDPE is present in an amount from 5 to 50 wt%, further from 10 to 40 wt%, further from 15 to 30 wt%, based on the weight of the composition. In a further embodiment, the LDPE has a density from 0.915 to 0.925 g/cc, and a melt index (I_2) from 0.5 to 5 g/10 min, further from 1.0 to 3.0 g/10 min.

[0050] In further embodiments, the first composition may comprise one or more additives. Additives include, but are not limited to, antistatic agents, color enhancers, dyes, lubricants, fillers (for example, TiO_2 or $CaCO_3$), opacifiers, nucleators, processing aids, pigments, primary anti-oxidants, secondary anti-oxidants, UV stabilizers, anti-block agents, slip agents, tackifiers, fire retardants, anti-microbial agents, odor reducer agents, anti-fungal agents, and combinations thereof.

[0051] Additional Components of Thermoformed Films

[0052] Additionally, in one or more embodiments, the thermoformed multilayer film may comprise propylene-based polymers. Various propylene based polymer products are considered suitable, for example, propylene-ethylene copolymer resins such as VERSIFY™ 3000 or 3200, which are both supplied by The Dow Chemical Company, Midland, MI. In some embodiments, the thermoformed multilayer film structure is substantially free of propylene-based polymers. As used herein, "substantially free of propylene-based polymers" means less than 0.5 % by weight of the thermoformed multilayer film, or less than 0.1% by weight, or less than 0.01% by weight.

[0053] Moreover, in further embodiments, the thermoformed monolayer or multilayer film structures consist essentially of ethylene-based polymers. As used herein, "consists essentially" means that the thermoformed monolayer or multilayer film structure may include other additives but is limited to ethylene-based polymer.

[0054] The thermoformed monolayer or multilayer film structures may include additional ethylene-based polymers besides the ethylene-based polymer of the first composition. In one embodiment, the thermoformed multilayer film structure may comprise ethylene-based polymer having a density of from 0.895 to 0.965 g/cm³ and a melt index (I₂) from 0.5 to 6.0 g/10 min when measured according to ASTM D 1238 at a load of 2.16 kg and temperature of 190°C. In further embodiments, the density may be from 0.900 to 0.940 g/cm³, or from 0.900 to 0.925 g/cm³, and the melt index (I₂) is from 0.85 to 3.5 g/10 min, or from 2.0 to 6.0 g/10 min. Examples of may include, but are not limited to, DOW™ low density polyethylenes (LDPE) and linear low density polyethylenes (LLDPE), DOWLEX™ linear low density polyethylenes (LLDPE), ATTANE™ ultra low density polyethylenes (ULDPE), ELITE™ enhanced polyethylenes, each being commercially available from The Dow Chemical Company, Midland, MI.

[0055] In further embodiments, the thermoformed multilayer film may comprise additional compositions in one or more of the layers. In some embodiments, a multilayer film of the present disclosure can comprise one or more barrier layers. In such embodiments, the barrier layer may comprise one or more polyamides (nylons), ethylene vinyl alcohol copolymers (EVOH), and/or malleated polyolefins. EVOH can include a vinyl alcohol copolymer having 27

to 44 mol% ethylene, and is prepared by, for example, hydrolysis of vinyl acetate copolymers. Examples of commercially available EVOH that can be used in embodiments of the present invention include EVAL™ from Kuraray and Noltex™ from Nippon Goshei. In embodiments where the barrier layer comprises polyamide, the polyamide can include polyamide 6, polyamide 9, polyamide 10, polyamide 11, polyamide 12, polyamide 6,6, polyamide 6/66 and aromatic polyamide such as polyamide 61, polyamide 6T, MXD6, or combinations thereof.

[0056] The malleated polyolefins are contemplated for various layers of the thermoformed multilayer film. In some embodiments, the malleated polyolefins may be in a tie layer of the thermoformed multilayer film. The malleated polyolefins may comprise maleic anhydride grafted polyethylene, or maleic anhydride grafted polypropylene. Suitable commercial examples of the maleic anhydride grafted polyethylene is AMPLIFY™ TY 1057H from The Dow Chemical Company (Midland, MI).

[0057] In other embodiments, the multilayer or monolayer films can be free of polyamide. In some such embodiments, the absence of polyamide can result in a less expensive multilayer film with thermoforming properties comparable to multilayer films comprising polyamide. In some embodiments, a multilayer film can comprise less than 5 weight percent polyamide, or less than 3 weight percent polyamide, or less than 1 weight percent polyamide, or less than 0.5 weight percent polyamide, each based on the total weight of the film. However, as indicated above, there are some embodiments (e.g., when polyamide is to be used as a barrier layer), where a multilayer film includes larger amounts of polyamide.

[0058] In some embodiments, the multilayer films can include a tie layer. A tie layer may be used to adhere two layers together during coextrusion particularly where there is an incompatibility between the compositions of the two layers. For example, if a multilayer film comprises an ethylene vinyl alcohol barrier layer, a tie layer may be used to adhere the ethylene vinyl alcohol layer to a layer comprising predominantly polyolefins. Persons of skill in the art can determine whether a tie layer is needed and if so, select an appropriate tie layer, depending on the composition of the layers to be included in the multilayer film based on the teachings herein.

[0059] It should be understood that any of the layers within a multilayer film of the present invention can further comprise one or more additives as known to those of skill in the art

such as, for example, antioxidants, ultraviolet light stabilizers, thermal stabilizers, slip agents, antiblock, pigments or colorants, processing aids, crosslinking catalysts, flame retardants, fillers and foaming agents.

[0060] Multilayer or monolayer films of the present disclosure may have a total thickness (before thermoforming) in the range of from 10 μm to 250 μm , preferably 50 μm to 200 μm , or 100 μm to 180 μm . Individual layer thickness may vary depending on the number of layers available, the type of layer (e.g., skin layer, barrier layer, inner layer, etc.) and the total thickness of the film. Multilayer films of the present disclosure can be coextruded (e.g., using a blown film process or a cast film process) in some embodiments using techniques known to those of skill in the art. Multilayer, collapsed or monolayer films of the present disclosure are well-suited for use in thermoforming applications in some embodiments. In one or more embodiments, the multilayer film may comprise at least 50% based on the percentage overall multilayer film thickness of the first composition. In another embodiment, the multilayer film may comprise at least 60% based on the percentage overall multilayer film thickness of the first composition.

[0061] The present multilayer and monolayer films can be formed into a variety of articles using techniques known to those of skill in the art. For example, the monolayer and multilayer films can be thermoformed into an article in some embodiments. Examples of such articles include rigid containers, flexible trays, and semi-flexible packaging. Such articles can be used, for example, in the packaging of foods such as fruit, cheese, meat, processed meat, processed food, and frozen food.

[0062] Properties of Monolayer and Multilayer Films

[0063] The thermoformed monolayer film may demonstrate an increase in puncture resistance of at least 10% due to thermoforming. In further embodiments, the thermoformed monolayer film may demonstrate an increase in puncture resistance of at least 15%, or at least 20% due to the thermoforming step.

[0064] Additionally, the thermoformed polyolefin multilayer film structure may also demonstrate improved properties. For instance, the thermoformed polyolefin multilayer film

may have an Instrumented Dart Impact of at least 0.6 J, or at least 0.8 J, or at least 1.0 J when measured according to ASTM D3763.

[0065] Polymerization Process for Making the First Composition

[0066] To produce the ethylene based polymer of the first composition, suitable polymerization processes may include, but are not limited to, solution polymerization processes, using one or more conventional reactors, e.g., loop reactors, isothermal reactors, adiabatic reactors, stirred tank reactors, autoclave reactors in parallel, series, and/or any combinations thereof. The ethylene based polymer compositions may, for example, be produced via solution phase polymerization processes, using one or more loop reactors, adiabatic reactors, and combinations thereof.


[0067] In general, the solution phase polymerization process occurs in one or more well mixed reactors, such as one or more loop reactors and/or one or more adiabatic reactors at a temperature in the range from 115 to 250°C; for example, from 135 to 200°C, and at pressures in the range of from 300 to 1000 psig, for example, from 450 to 750 psig.

[0068] In one embodiment, the ethylene based polymer may be produced in two loop reactors in series configuration, the first reactor temperature is in the range from 115 to 200°C, for example, from 135 to 165°C, and the second reactor temperature is in the range from 150 to 210°C, for example, from 185 to 200°C. In another embodiment, the ethylene based polymer composition may be produced in a single reactor, the reactor temperature is in the range from 115 to 200°C, for example from 130 to 190°C. The residence time in a solution phase polymerization process is typically in the range from 2 to 40 minutes, for example from 5 to 20 minutes. Ethylene, solvent, one or more catalyst systems, optionally one or more cocatalysts, and optionally one or more comonomers, are fed continuously to one or more reactors. Exemplary solvents include, but are not limited to, isoparaffins. For example, such solvents are commercially available under the name ISOPAR E from ExxonMobil Chemical. The resultant mixture of the ethylene based polymer composition and solvent is then removed from the reactor or reactors, and the ethylene based polymer composition is isolated. Solvent is typically recovered via a solvent recovery unit, i.e., heat exchangers and separator vessel, and the solvent is then recycled back into the polymerization system.

[0069] In one embodiment, the ethylene based polymer of the first composition may be produced, via a solution polymerization process, in a dual reactor system, for example a dual loop reactor system, wherein ethylene, and optionally one or more α -olefins, are polymerized in the presence of one or more catalyst systems, in one reactor, to produce a first ethylene-based polymer, and ethylene, and optionally one or more α -olefins, are polymerized in the presence of one or more catalyst systems, in a second reactor, to produce a second ethylene-based polymer. Additionally, one or more cocatalysts may be present.

[0070] In another embodiment, the ethylene based polymer may be produced via a solution polymerization process, in a single reactor system, for example, a single loop reactor system, wherein ethylene, and optionally one or more α -olefins, are polymerized in the presence of one or more catalyst systems. Additionally, one or more cocatalysts may be present.

[0071] As discussed above, the invention provides a process to form a composition comprising at least two ethylene-based polymers, said process comprising the following: polymerizing ethylene, and optionally at least one comonomer, in solution, in the present of a catalyst system comprising a metal-ligand complex of Structure I, to form a first ethylene-based polymer; and polymerizing ethylene, and optionally at least one comonomer, in the presence of a catalyst system comprising a Ziegler/Natta catalyst, to form a second ethylene-based polymer; and wherein Structure I is as follows:



[0072]

[0073] wherein:

[0074] M is titanium, zirconium, or hafnium, each, independently, being in a formal oxidation state of +2, +3, or +4; and

[0075] n is an integer from 0 to 3, and wherein when n is 0, X is absent; and


-15-

[0076] each X, independently, is a monodentate ligand that is neutral, monoanionic, or dianionic; or two Xs are taken together to form a bidentate ligand that is neutral, monoanionic, or dianionic; and

[0077] X and n are chosen, in such a way, that the metal-ligand complex of formula (I) is, overall, neutral; and

[0078] each Z, independently, is O, S, N(C₁-C_{4Q})hydrocarbyl, or P(C₁-C_{4o})hydrocarbyl; and

[0079] wherein the Z-L-Z fragment is comprised of formula (1):



[0080] (1);

[0081] R¹ through R¹⁶ are each, independently, selected from the group consisting of the following: a substituted or unsubstituted (C₁-C_{4Q})hydrocarbyl, a substituted or unsubstituted (C₁-C₄₀)heterohydrocarbyl, Si(R^C)₃, Ge(R^C)₃, P(R^P)₂, N(R^N)₂, OR^C, SR^C, NO₂, CN, CF₃, R^CS(O)-, R^CS(O)₂-, (R^C)₂C=N-, R^CC(O)O-, R^COC(O)-, R^CC(O)N(R)-, (R^C)₂NC(O)-, halogen atom, hydrogen atom; and wherein each R^C is independently a (C_i-C₃₀)hydrocarbyl; R^P is a (C₁-C₃₀)hydrocarbyl; and R^N is a (C₁-C₃₀)hydrocarbyl; and wherein, optionally, two or more R groups (from R¹ through R¹⁶) can combine together into one or more ring structures, with such ring structures each, independently, having from 3 to 50 atoms in the ring, excluding any hydrogen atom.

[0082] The process may comprise a combination of two or more embodiments as described herein. In one embodiment, the process comprises polymerizing ethylene, and optionally at least one α-olefin, in solution, in the presence of a catalyst system comprising a metal-ligand complex of Structure I, to form a first ethylene-based polymer; and polymerizing ethylene, and optionally at least one α-olefin, in the presence of a catalyst system comprising a Ziegler/Natta catalyst, to form a second ethylene-based polymer. In a further embodiment, each α-olefin is independently a C_i-C₈ α-olefin.


-16-

[0083] In one embodiment, optionally, two or more R groups from R⁹ through R¹³, or R⁴ through R⁸ can combine together into one or more ring structures, with such ring structures each, independently, having from 3 to 50 atoms in the ring, excluding any hydrogen atom.

[0084] In one embodiment, M is hafnium.

[0085] In one embodiment, R³ and R¹⁴ are each independently an alkyl, and further a C₁-C₃ alkyl, and further methyl.

[0086] In one embodiment, R¹ and R¹⁶ are each as follows:




[0087]

[0088] In one embodiment, each of the aryl, heteroaryl, hydrocarbyl, heterohydrocarbyl, Si(R^C)₃, Ge(R^C)₃, P(R^P)₂, N(R^N)₂, OR^C, SR^C, R^CS(O)-, R^CS(O)₂-, (R^C)₂C=N-, R^CC(O)O-, R^COC(O)-, R^CC(O)N(R)-, (R^C)₂NC(O)-, hydrocarbylene, and heterohydrocarbylene groups, independently, is unsubstituted or substituted with one or more R^S substituents; and each R^S independently is a halogen atom, polyfluoro substitution, perfluoro substitution, unsubstituted (C₁-C₁₈)alkyl, F₃C-, FC_{3/4}O-, F₂HCO-, F₃CO-, R₃Si-, R₃Ge-, RO-, RS-, RS(O)-, RS(O)₂-, R₂P-, R₂N-, R₂C=N-, NC-, RC(O)O-, ROC(O)-, RC(O)N(R)-, or R₂NC(O)-, or two of the R^S are taken together to form an unsubstituted (C[^]-C_{1g})alkylene, wherein each R independently is an unsubstituted (C[^]-C_{1g})alkyl.

[0089] In one embodiment, two or more of R₁ through R₁₆ do not combine to form one or more ring structures.

[0090] In one embodiment, the catalyst system suitable for producing the first ethylene/a-olefin interpolymer is a catalyst system comprising bis((2-oxoyl-3-(dibenzo-1H-pyrrole-1-yl)-5-(methyl)phenyl)-2-phenoxyethyl)-methylene-1,2-cyclohexanediylhafnium (IV) dimethyl, represented by the following Structure: IA:

-17-



[0091]

(IA).

[0092] The Ziegler/Natta catalysts suitable for use in the invention are typical supported, Ziegler-type catalysts, which are particularly useful at the high polymerization temperatures of the solution process. Examples of such compositions are those derived from organomagnesium compounds, alkyl halides or aluminum halides or hydrogen chloride, and a transition metal compound. Examples of such catalysts are described in U.S. Pat Nos. 4,612,300; 4,314,912; and 4,547,475; the teachings of which are incorporated herein by reference.

[0093] Particularly suitable organomagnesium compounds include, for example, hydrocarbon soluble dihydrocarbylmagnesium, such as the magnesium dialkyls and the magnesium diaryls. Exemplary suitable magnesium dialkyls include, particularly, n-butyl-sec-butylmagnesium, diisopropylmagnesium, di-n-hexylmagnesium, isopropyl-n-butyl-magnesium, ethyl-n-hexyl-magnesium, ethyl-n-butylmagnesium, di-n-octylmagnesium, and others, wherein the alkyl has from 1 to 20 carbon atoms. Exemplary suitable magnesium diaryls include diphenylmagnesium, dibenzylmagnesium and ditolylmagnesium. Suitable organomagnesium compounds include alkyl and aryl magnesium alkoxides and aryloxides and aryl and alkyl magnesium halides, with the halogen-free organomagnesium compounds being more desirable.

[0094] Halide sources include active non-metallic halides, metallic halides, and hydrogen chloride. Suitable non-metallic halides are represented by the formula R'X, wherein R' is hydrogen or an active monovalent organic radical, and X is a halogen. Particularly suitable non-metallic halides include, for example, hydrogen halides and active organic halides, such as t-alkyl halides, allyl halides, benzyl halides and other active hydrocarbyl halides. By an active organic halide is meant a hydrocarbyl halide that contains a labile halogen at least as active, i.e., as easily lost to another compound, as the halogen of sec-butyl chloride, preferably as active as t-butyl chloride. In addition to the organic monohalides, it is understood that organic dihalides,

trihalides and other polyhalides that are active, as defined hereinbefore, are also suitably employed. Examples of preferred active non-metallic halides, include hydrogen chloride, hydrogen bromide, t-butyl chloride, t-amyl bromide, allyl chloride, benzyl chloride, crotyl chloride, methylvinyl carbonyl chloride, α -phenylethyl bromide, diphenyl methyl chloride, and the like. Most preferred are hydrogen chloride, t-butyl chloride, allyl chloride and benzyl chloride.

[0095] Suitable metallic halides include those represented by the formula $MR_y-a X_a$, wherein: M is a metal of Groups IIB, IIIA or IVA of Mendeleev's periodic Table of Elements; R is a monovalent organic radical; X is a halogen; y has a value corresponding to the valence of M; and "a" has a value from 1 to y. Preferred metallic halides are aluminum halides of the formula $AlR_{3-a} X_a$, wherein each R is independently hydrocarbyl, such as alkyl; X is a halogen; and a is a number from 1 to 3. Most preferred are alkylaluminum halides, such as ethylaluminum sesquichloride, diethylaluminum chloride, ethylaluminum dichloride, and diethylaluminum bromide, with ethylaluminum dichloride being especially preferred. Alternatively, a metal halide, such as aluminum trichloride, or a combination of aluminum trichloride with an alkyl aluminum halide, or a trialkyl aluminum compound may be suitably employed.

[0096] Any of the conventional Ziegler-Natta transition metal compounds can be usefully employed, as the transition metal component in preparing the supported catalyst component. Typically, the transition metal component is a compound of a Group IVB, VB, or VIB metal. The transition metal component is generally, represented by the formulas: $TrX'_{4-q} (OR)_q$, $TrX'_{4-q} (R_2)_q$, VOX'_3 and $VO(OR)_3$.

[0097] Tr is a Group IVB, VB, or VIB metal, preferably a Group IVB or VB metal, preferably titanium, vanadium or zirconium; q is 0 or a number equal to, or less than, 4; X' is a halogen, and R1 is an alkyl group, aryl group or cycloalkyl group having from 1 to 20 carbon atoms; and R2 is an alkyl group, aryl group, aralkyl group, substituted aralkyls, and the like.

[0098] The aryl, aralkyls and substituted aralkyls contain 1 to 20 carbon atoms, preferably 1 to 10 carbon atoms. When the transition metal compound contains a hydrocarbyl group, R2, being an alkyl, cycloalkyl, aryl, or aralkyl group, the hydrocarbyl group will preferably not contain an H atom in the position beta to the metal carbon bond. Illustrative, but

non-limiting, examples of aralkyl groups are methyl, neopentyl, 2,2-dimethylbutyl, 2,2-dimethylhexyl; aryl groups such as benzyl; cycloalkyl groups such as 1-norbornyl. Mixtures of these transition metal compounds can be employed if desired.

[0099] Illustrative examples of the transition metal compounds include TiCl_4 , TiBr_4 , $\text{Ti}(\text{OC}_2\text{H}_5)_3\text{Cl}$, $\text{Ti}(\text{OC}_2\text{H}_5)\text{Cl}_3$, $\text{Ti}(\text{OC}_4\text{H}_9)_3\text{Cl}$, $\text{Ti}(\text{OC}_3\text{H}_7)_2\text{Cl}_2$, $\text{Ti}(\text{OC}_6\text{H}_{13})_2\text{Cl}_2$, $\text{Ti}(\text{OC}_8\text{H}_{17})_2\text{Br}_2$, and $\text{Ti}(\text{OCi}_2\text{H}_{25})\text{Cl}_3$, $\text{Ti}(\text{O-iC}_3\text{H}_7)_4$, and $\text{Ti}(\text{O-nC}_4\text{H}_9)_4$. Illustrative examples of vanadium compounds include VCl_4 , VOCl_3 , $\text{VO}(\text{OC}_2\text{H}_5)_3$, and $\text{VO}(\text{OC}_4\text{H}_9)_3$. Illustrative examples of zirconium compounds include ZrCl_4 , $\text{ZrCl}_3(\text{OC}_2\text{H}_5)$, $\text{ZrCl}_2(\text{OC}_2\text{H}_5)_2$, $\text{ZrCl}(\text{OC}_2\text{H}_5)_3$, $\text{Zr}(\text{OC}_2\text{H}_5)_4$, $\text{ZrCl}_3(\text{OC}_4\text{H}_9)$, $\text{ZrCl}_2(\text{OC}_4\text{H}_9)_2$, and $\text{ZrCl}(\text{OC}_4\text{H}_9)_3$.

[00100] An inorganic oxide support may be used in the preparation of the catalyst, and the support may be any particulate oxide, or mixed oxide which has been thermally or chemically dehydrated, such that it is substantially free of adsorbed moisture. See U. S. Pat Nos. 4,612,300; 4,314,912; and 4,547,475; the teachings of which are incorporated herein by reference.

[00101] The above described catalyst systems can be rendered catalytically active by contacting it to, or combining it with, the activating co-catalyst, or by using an activating technique, such as those known in the art, for use with metal-based olefin polymerization reactions. Suitable activating co-catalysts, for use herein, include alkyl aluminums; polymeric or oligomeric alumoxanes (also known as aluminoxanes); neutral Lewis acids; and non-polymeric, non-coordinating, ion-forming compounds (including the use of such compounds under oxidizing conditions). A suitable activating technique is bulk electrolysis. Combinations of one or more of the foregoing activating co-catalysts and techniques are also contemplated. The term "alkyl aluminum" means a monoalkyl aluminum dihydride or monoalkylaluminum dihalide, a dialkyl aluminum hydride or dialkyl aluminum halide, or a trialkylaluminum. Aluminoxanes and their preparations are known at, for example, U.S. Patent 6,103,657. Examples of preferred polymeric or oligomeric alumoxanes are methylalumoxane, triisobutylaluminum-modified methylalumoxane, and isobutylalumoxane.

[00102] Exemplary Lewis acid activating co-catalysts are Group 13 metal compounds containing from 1 to 3 hydrocarbyl substituents as described herein. In some embodiments, exemplary Group 13 metal compounds are tri(hydrocarbyl)-substituted-aluminum or tri(hydrocarbyl)-boron compounds. In some other embodiments, exemplary Group 13 metal

-20-

compounds are tri(hydrocarbyl)-substituted-aluminum or tri(hydrocarbyl)-boron compounds are $\text{tri}((\text{C}_1\text{-C}_1\text{Q})\text{alkyl})\text{aluminum}$ or $\text{tri}((\text{C}_1\text{-C}_1\text{g})\text{aryl})\text{boron}$ compounds and halogenated (including perhalogenated) derivatives thereof. In some other embodiments, exemplary Group 13 metal compounds are tris(fluoro-substituted phenyl)boranes, in other embodiments, tris(pentafluorophenyl)borane. In some embodiments, the activating co-catalyst is a $\text{tri}((\text{C}_1\text{-C}_2\text{o})\text{hydrocarbyl})\text{borate}$ (e-g-, trityl tetrafluoroborate) or a $\text{tri}((\text{C}_1\text{-C}_2\text{o})\text{hydrocarbyl})\text{ammonium}$ $\text{tetra}((\text{C}_1\text{-C}_2\text{o})\text{hydrocarbyl})\text{borane}$ (e-g-, bis(octadecyl)methylammonium tetrakis(pentafluorophenyl)borane). As used herein, the term "ammonium" means a nitrogen cation that is a $((\text{C}_1\text{-C}_2\text{Q})\text{hydrocarbyl})_4\text{N}^+$, a $((\text{C}_1\text{-C}_2\text{o})\text{hydrocarbyl})_3\text{N}(\text{H})^+$, a $((\text{C}_1\text{-C}_2\text{o})\text{hydrocarbyl})_2\text{N}(\text{H})_2^+$, $(\text{C}_1\text{-C}_2\text{o})\text{hydrocarbylN}(\text{H})_3^+$, or $\text{N}(\text{H})_4^+$, wherein each $(\text{C}_1\text{-C}_2\text{o})\text{hydrocarbyl}$ may be the same or different.

[00103] Exemplary combinations of neutral Lewis acid activating co-catalysts include mixtures comprising a combination of a $\text{tri}((\text{C}_1\text{-C}_4)\text{alkyl})\text{aluminum}$ and a halogenated $\text{tri}((\text{C}_1\text{-C}_1\text{g})\text{aryl})\text{boron}$ compound, especially a tris(pentafluorophenyl)borane. Other exemplary embodiments are combinations of such neutral Lewis acid mixtures with a polymeric or oligomeric alumoxane, and combinations of a single neutral Lewis acid, especially tris(pentafluorophenyl)borane with a polymeric or oligomeric alumoxane. Exemplary embodiments ratios of numbers of moles of (metal-ligand complex):(tris(pentafluorophenyl)borane):(alumoxane) [e.g., (Group 4 metal-ligand complex):(tris(pentafluorophenyl)borane):(alumoxane)] are from 1:1:1 to 1:10:30, other exemplary embodiments are from 1:1:1.5 to 1:5:10.

[00104] Many activating co-catalysts and activating techniques have been previously taught, with respect to different metal-ligand complexes, in the following USPNs: US 5,064,802; US 5,153,157; US 5,296,433; US 5,321,106; US 5,350,723; US 5,425,872; US 5,625,087; US 5,721,185; US 5,783,512; US 5,883,204; US 5,919,983; US 6,696,379; and US 7,163,907. Examples of suitable hydrocarbyloxides are disclosed in US 5,296,433. Examples of suitable Bronsted acid salts for addition polymerization catalysts are disclosed in US 5,064,802; US 5,919,983; US 5,783,512. Examples of suitable salts of a cationic oxidizing

-21-

agent and a non-coordinating, compatible anion, as activating co-catalysts for addition polymerization catalysts, are disclosed in US 5,321,106. Examples of suitable carbenium salts as activating co-catalysts for addition polymerization catalysts are disclosed in US 5,350,723. Examples of suitable silylium salts, as activating co-catalysts for addition polymerization catalysts, are disclosed in US 5,625,087. Examples of suitable complexes of alcohols, mercaptans, silanols, and oximes with tris(pentafluorophenyl)borane are disclosed in US 5,296,433. Some of these catalysts are also described in a portion of US 6,515,155 B1, beginning at column 50, at line 39, and going through column 56, at line 55, only the portion of which is incorporated by reference herein.

[00105] In some embodiments, the above described catalyst systems can be activated to form an active catalyst composition by combination with one or more cocatalyst, such as a cation forming cocatalyst, a strong Lewis acid, or a combination thereof. Suitable cocatalysts for use include polymeric or oligomeric aluminoxanes, especially methyl aluminoxane, as well as inert, compatible, noncoordinating, ion forming compounds. Exemplary suitable cocatalysts include, but are not limited to, modified methyl aluminoxane (MMAO), bis(hydrogenated tallow alkyl)methyl, tetrakis(pentafluorophenyl)borate(1-) amine, triethyl aluminum (TEA), and any combinations thereof.

[00106] In some embodiments, one or more of the foregoing activating co-catalysts are used in combination with each other. In one embodiment, a combination of a mixture of a tri((C_j-C₄)hydrocarbyl)aluminum, tri(C[^]-C₄)hydrocarbyl)borane, or an ammonium borate with an oligomeric or polymeric alumoxane compound, can be used.

[00107] TESTING METHODS

[00108] The test methods include the following:

[00109] Melt index (I₂)

[00110] Melt index (I₂) were measured in accordance to ASTM D-1238 at 190°C at 2.16 kg. The values are reported in g/10 min, which corresponds to grams eluted per 10 minutes.

[00111] Density

-22-

[00112] Samples for density measurement were prepared according to ASTM D4703 and reported in grams/cubic centimeter (g/cc or g/cm³). Measurements were made within one hour of sample pressing using ASTM D792, Method B.

[00113] Dynamic Shear Rheology

[00114] Each sample was compression-molded into "3 mm thick x 25 mm diameter" circular plaque, at 177°C, for five minutes, under 10 MPa pressure, in air. The sample was then taken out of the press and placed on a counter top to cool.

[00115] Constant temperature, frequency sweep measurements were performed on an ARES strain controlled rheometer (TA Instruments), equipped with 25 mm parallel plates, under a nitrogen purge. For each measurement, the rheometer was thermally equilibrated, for at least 30 minutes, prior to zeroing the gap. The sample disk was placed on the plate, and allowed to melt for five minutes at 190°C. The plates were then closed to 2 mm, the sample trimmed, and then the test was started. The method had an additional five minute delay built in, to allow for temperature equilibrium. The experiments were performed at 190°C, over a frequency range from 0.1 to 100 rad/s, at five points per decade interval. The strain amplitude was constant at 10%. The stress response was analyzed in terms of amplitude and phase, from which the storage modulus (G'), loss modulus (G''), complex modulus (G*), dynamic viscosity (η^* or Eta*), and $\tan \delta$ (or tan delta) were calculated.

[00116] Melt Strength

[00117] Melt strength measurements were conducted on a Gottfert Rheotens 71.97 (Goettfert Inc.; Rock Hill, SC) attached to a Gottfert Rheotester 2000 capillary rheometer. A polymer melt was extruded through a capillary die with a flat entrance angle (180 degrees), with a capillary diameter of 2.0 mm, and an aspect ratio (capillary length/capillary diameter) of 15.

[00118] After equilibrating the samples at 190°C, for 10 minutes, the piston was run at a constant piston speed of 0.265 mm/second. The standard test temperature was 190°C. The sample (about 20 grams) was drawn uniaxially to a set of accelerating nips, located 100 mm below the die, with an acceleration of 2.4 mm/second². The tensile force was recorded, as a function of the take-up speed of the nip rolls. Melt strength was reported as the plateau force

-23-

(cN) before the strand broke. The following conditions were used, in the melt strength measurements: plunger speed = 0.265 mm/second; wheel acceleration = 2.4 mm/s²; capillary diameter = 2.0 mm; capillary length = 30 mm; and barrel diameter = 12 mm.

[00119] Conventional Gel Permeation Chromatography (conv. GPC)

[00120] A GPC-IR high temperature chromatographic system from PolymerChar (Valencia, Spain), was equipped with a Precision Detectors (Amherst, MA), 2-angle laser light scattering detector Model 2040, an IR5 infra-red detector and a 4-capillary viscometer, both from PolymerChar. Data collection was performed using PolymerChar Instrument Control software and data collection interface. The system was equipped with an on-line, solvent degas device and pumping system from Agilent Technologies (Santa Clara, CA).

[00121] Injection temperature was controlled at 150 degrees Celsius. The columns used, were three, 10-micron "Mixed-B" columns from Polymer Laboratories (Shropshire, UK). The solvent used was 1,2,4-trichlorobenzene. The samples were prepared at a concentration of "0.1 grams of polymer in 50 milliliters of solvent." The chromatographic solvent and the sample preparation solvent each contained "200 ppm of butylated hydroxytoluene (BHT)." Both solvent sources were nitrogen sparged. Ethylene-based polymer samples were stirred gently at 160 degrees Celsius for three hours. The injection volume was "200 microliters," and the flow rate was "1 milliliters/minute." The GPC column set was calibrated by running 21 "narrow molecular weight distribution" polystyrene standards. The molecular weight (MW) of the standards ranges from 580 to 8,400,000 g/mole, and the standards were contained in six "cocktail" mixtures. Each standard mixture had at least a decade of separation between individual molecular weights. The standard mixtures were purchased from Polymer Laboratories. The polystyrene standards were prepared at "0.025 g in 50 mL of solvent" for molecular weights equal to, or greater than, 1,000,000 g/mole, and at "0.050 g in 50 mL of solvent" for molecular weights less than 1,000,000 g/mole.

[00122] The polystyrene standards were dissolved at 80°C, with gentle agitation, for 30 minutes. The narrow standards mixtures were run first, and in order of decreasing "highest molecular weight component," to minimize degradation. The polystyrene standard peak molecular weights were converted to polyethylene molecular weight using Equation 1 (as described in Williams and Ward, *J. Polym. Sci., Polym. Letters*, 6, 621 (1968)):

-24-

[00123] $M_{\text{polyethylene}} = A \times (M_{\text{polystyrene}})^B$ (Eqn. 1),

[00124] where M is the molecular weight, A is equal to 0.43 16 and B is equal to 1.0.

[00125] Number-average molecular weight ($M_n(\text{conv gpc})$), weight average molecular weight ($M_w(\text{conv gpc})$), and z-average molecular weight ($M_z(\text{conv gpc})$) were calculated according to Equations 2-4 below.

$$[00126] \quad M_n(\text{conv gpc}) = \frac{\sum_{i=RV \text{ integration start}}^{i=RV \text{ integration end}} (IR_{\text{measurement channel } i})}{\sum_{i=RV \text{ integration start}}^{i=RV \text{ integration end}} \left(IR_{\text{measurement channel } i} / M_{PEi} \right)} \quad (\text{Eqn. 2})$$

$$[00127] \quad M_w(\text{conv gpc}) = \frac{\sum_{i=RV \text{ integration start}}^{i=RV \text{ integration end}} (M_{PEi} IR_{\text{measurement channel } i})}{\sum_{i=RV \text{ integration start}}^{i=RV \text{ integration end}} (IR_{\text{measurement channel } i})} \quad (\text{Eqn. 3})$$

$$[00128] \quad M_z(\text{conv gpc}) = \frac{\sum_{i=RV \text{ integration start}}^{i=RV \text{ integration end}} (M_{PEi}^2 IR_{\text{measurement channel } i})}{\sum_{i=RV \text{ integration start}}^{i=RV \text{ integration end}} (M_{PEi} IR_{\text{measurement channel } i})} \quad (\text{Eqn. 4})$$

[00129] In Equations 2-4, the RV is column retention volume (linearly-spaced), collected at "1 point per second," the IR is the baseline-subtracted IR detector signal, in Volts, from the IR5 measurement channel of the GPC instrument, and M_{PE} is the polyethylene-equivalent MW determined from Equation 1. Data calculation were performed using "GPC One software (version 2.0 13H)" from PolymerChar.

[00130] Creep Zero Shear Viscosity Measurement Method

[00131] Zero-shear viscosities were obtained via creep tests, which were conducted on an AR-G2 stress controlled rheometer (TA Instruments; New Castle, Del), using "25-mm-diameter" parallel plates, at 190°C. The rheometer oven was set to test temperature for at least 30 minutes, prior to zeroing the fixtures. At the testing temperature, a compression molded sample disk was inserted between the plates, and allowed to come to equilibrium for five minutes. The upper plate was then lowered down to 50 $\mu\eta$ (instrument setting) above the desired testing gap (1.5 mm). Any superfluous material was trimmed off, and the upper plate was lowered to the desired gap. Measurements were done under nitrogen purging, at a flow rate

-25-

of 5 L/min. The default creep time was set for two hours. Each sample was compression-molded into a "2 mm thick x 25 mm diameter" circular plaque, at 177°C, for five minutes, under 10 MPa pressure, in air. The sample was then taken out of the press and placed on a counter top to cool.

[00132] A constant low shear stress of 20 Pa was applied for all of the samples, to ensure that the steady state shear rate was low enough to be in the Newtonian region. The resulting steady state shear rates were in the range from 10^{-3} to 10^{-4} s⁻¹ for the samples in this study. Steady state was determined by taking a linear regression for all the data, in the last 10% time window of the plot of "log (J(t)) vs. log(t)," where J(t) was creep compliance and t was creep time. If the slope of the linear regression was greater than 0.97, steady state was considered to be reached, then the creep test was stopped. In all cases in this study, the slope meets the criterion within one hour. The steady state shear rate was determined from the slope of the linear regression of all of the data points, in the last 10% time window of the plot of "ε vs. t," where ε was strain. The zero-shear viscosity was determined from the ratio of the applied stress to the steady state shear rate.

[00133] In order to determine if the sample was degraded during the creep test, a small amplitude oscillatory shear test was conducted before, and after, the creep test, on the same specimen from 0.1 to 100 rad/s. The complex viscosity values of the two tests were compared. If the difference of the viscosity values, at 0.1 rad/s, was greater than 5%, the sample was considered to have degraded during the creep test, and the result was discarded.

[00134] **Zero-Shear Viscosity Ratio (ZSVR)** is defined as the ratio of the zero-shear viscosity (ZSV) of the branched polyethylene material to the ZSV of a linear polyethylene material (see ANTEC proceeding below) at the equivalent weight average molecular weight (M_w(conv gpc)), according to the following Equation 5:

$$\mathbf{[00135]} \quad ZSVR = \frac{\eta_{0B}}{\eta_{0L}} = \frac{\eta_{0B}}{2.29^{-15} M_{w(\text{conv. gpc})}^{3.65}} \quad (\text{Eqn. 5}).$$

[00136] The ZSV value was obtained from creep test, at 190°C, via the method described above. The M_w(conv gpc) value was determined by the conventional GPC method (Equation 3), as discussed above. The correlation between ZSV of linear polyethylene and its M_w(conv

gpc) was established based on a series of linear polyethylene reference materials. A description for the ZSV-Mw relationship can be found in the ANTEC proceeding: Karjala et al., *Detection of Low Levels of Long-chain Branching in Polyolefins*, Annual Technical Conference - Society of Plastics Engineers (2008), 66th 887-891.

[00137] H NMR Method

[00138] A stock solution (3.26 g) was added to "0.133 g of the polymer sample" in 10 mm NMR tube. The stock solution was a mixture of tetrachloroethane-d2 (TCE) and perchloroethylene (50:50, w:w) with 0.001M Cr³⁺. The solution in the tube was purged with N₂, for 5 minutes, to reduce the amount of oxygen. The capped sample tube was left at room temperature, overnight, to swell the polymer sample. The sample was dissolved at 110°C with periodic vortex mixing. The samples were free of the additives that may contribute to unsaturation, for example, slip agents such as erucamide. Each H NMR analysis was run with a 10 mm cryoprobe, at 120°C, on Bruker AVANCE 400 MHz spectrometer.

[00139] Two experiments were run to get the unsaturation: the control and the double presaturation experiments. For the control experiment, the data was processed with an exponential window function with LB=1 Hz, and the baseline was corrected from 7 to -2 ppm. The signal from residual H of TCE was set to 100, and the integral I_{0.5-3} from -0.5 to 3 ppm was used as the signal from whole polymer in the control experiment. The "number of CH₂ group, NCH₂," in the polymer was calculated as follows in Equation 1A:

$$[00140] \quad NCH_2 = I_{total}/2 \quad (\text{Eqn. 1A}).$$

[00141] For the double presaturation experiment, the data was processed with an exponential window function with LB=1 Hz, and the baseline was corrected from about 6.6 to 4.5 ppm. The signal from residual H of TCE was set to 100, and the corresponding integrals for unsaturations (I_{vinylene}, I_{substituted}, I_{vinyl} and I_{vinylidene}) were integrated. It is well known to use NMR spectroscopic methods for determining polyethylene unsaturation, for example, see Busico, V., et al., *Macromolecules*, 2005, 38, 6988. The number of unsaturation unit for vinylene, trisubstituted, vinyl and vinylidene were calculated as follows:

$$[00142] \quad N_{vinylene,e} = I_{vinylene}/2 \quad (\text{Eqn. 2A}),$$

-27-

[00143] $N_{\text{trisubstituted}} = I_{\text{trisubstituted}} / 2$ (Eqn. 3A),

[00144] $N_{\text{vinyli}} = I_{\text{vinyli}} / 2$ (Eqn. 4A),

[00145] $N_{\text{vinyliidene}} = I_{\text{vinyliidene}} / 2$ (Eqn. 5A).

[00146] The unsaturation units per 1,000 carbons, all polymer carbons including backbone carbons and branch carbons, were calculated as follows:

[00147] $N_{\text{vinyli},e} / 1,000C = (N_{\text{vinyli},e} / NCH_2) * 1,000$ (Eqn. 6A),

[00148] $N_{\text{trisubstituted}} / 1,000C = (N_{\text{trisubstituted}} / NCH_2) * 1,000$ (Eqn. 7A),

[00149] $N_{\text{vinyli}} / 1,000C = (N_{\text{vinyli}} / NCH_2) * 1,000$ (Eqn. 8A),

[00150] $N_{\text{vinyliidene}} / 1,000C = (N_{\text{vinyliidene}} / NCH_2) * 1,000$ (Eqn. 9A),

[00151] The chemical shift reference was set at 6.0 ppm for the H signal from residual proton from TCE-d₂. The control was run with ZG pulse, NS=4, DS=12, SWH=10,000 Hz, AQ=1.64s, D1=14s. The double presaturation experiment was run with a modified pulse sequence, with OIP = 1.354 ppm, O2P = 0.960 ppm, PL9 = 57db, PL21 = 70 db, NS = 100, DS = 4, SWH = 10,000 Hz, AQ = 1.64s, D1 = 1 s (where D1 is the presaturation time), D13 = 13s. Only the vinyl levels were reported in Table 2 below.

[00152] ¹³C NMR Method

[00153] Samples are prepared by adding approximately 3g of a 50/50 mixture of tetra-chloroethane-d₂/orthodichlorobenzene, containing 0.025 M Cr(AcAc)₃, to a "0.25 g polymer sample" in a 10 mm NMR tube. Oxygen is removed from the sample by purging the tube headspace with nitrogen. The samples are then dissolved, and homogenized, by heating the tube and its contents to 150°C, using a heating block and heat gun. Each dissolved sample is visually inspected to ensure homogeneity.

[00154] All data are collected using a Bruker 400 MHz spectrometer. The data is acquired using a 6 second pulse repetition delay, 90-degree flip angles, and inverse gated decoupling with a sample temperature of 120°C. All measurements are made on non-spinning samples in locked mode. Samples are allowed to thermally equilibrate for 7 minutes prior to

data acquisition. The ¹³C NMR chemical shifts were internally referenced to the EEE triad at 30.0 ppm.

[00155] C13 NMR Comonomer Content: It is well known to use NMR spectroscopic methods for determining polymer composition. ASTM D 5017-96; J. C. Randall et al., in "NMR and Macromolecules" ACS Symposium series 247; J. C. Randall, Ed., Am. Chem. Soc, Washington, D.C., 1984, Ch. 9; and J. C. Randall in "Polymer Sequence Determination", Academic Press, New York (1977) provide general methods of polymer analysis by NMR spectroscopy.

[00156] Molecular Weighted Comonomer Distribution Index (MWCDI)

[00157] A GPC-IR, high temperature chromatographic system from PolymerChar (Valencia, Spain) was equipped with a Precision Detectors' (Amherst, MA) 2-angle laser light scattering detector Model 2040, and an IR5 infra-red detector (GPC-IR) and a 4-capillary viscometer, both from PolymerChar. The "15-degree angle" of the light scattering detector was used for calculation purposes. Data collection was performed using PolymerChar Instrument Control software and data collection interface. The system was equipped with an on-line, solvent degas device and pumping system from Agilent Technologies (Santa Clara, CA).

[00158] Injection temperature was controlled at 150 degrees Celsius. The columns used, were four, 20-micron "Mixed-A" light scattering columns from Polymer Laboratories (Shropshire, UK). The solvent was 1,2,4-trichlorobenzene. The samples were prepared at a concentration of "0.1 grams of polymer in 50 milliliters of solvent." The chromatographic solvent and the sample preparation solvent each contained "200 ppm of butylated hydroxytoluene (BHT)." Both solvent sources were nitrogen sparged. Ethylene-based polymer samples were stirred gently, at 160 degrees Celsius, for three hours. The injection volume was "200 microliters," and the flow rate was "1 milliliter/s/minute."

[00159] Calibration of the GPC column set was performed with 21 "narrow molecular weight distribution" polystyrene standards, with molecular weights ranging from 580 to 8,400,000 g/mole. These standards were arranged in six "cocktail" mixtures, with at least a decade of separation between individual molecular weights. The standards were purchased from Polymer Laboratories (Shropshire UK). The polystyrene standards were prepared at "0.025

-29-

grams in 50 milliliters of solvent" for molecular weights equal to, or greater than, 1,000,000 g/mole, and at "0.050 grams in 50 milliliters of solvent" for molecular weights less than 1,000,000 g/mole. The polystyrene standards were dissolved at 80 degrees Celsius, with gentle agitation, for 30 minutes. The narrow standards mixtures were run first, and in order of decreasing "highest molecular weight component," to minimize degradation. The polystyrene standard peak molecular weights were converted to polyethylene molecular weights using Equation IB (as described in Williams and Ward, J. Polym. Sci., Polym. Let., 6, 621 (1968)):

$$[00160] \quad M_{\text{polyethylene}} = A \times (M_{\text{polystyrene}})^B \quad (\text{Eqn. IB}),$$

[00161] where M is the molecular weight, A has a value of approximately 0.40 and B is equal to 1.0. The A value was adjusted between 0.385 and 0.425 (depending upon specific column-set efficiency), such that NBS 1475A (NIST) linear polyethylene weight-average molecular weight corresponded to 52,000 g/mole, as calculated by Equation 3B, below:

$$[00162] \quad M_n(\text{LALS gpc}) = \frac{\sum_{i=RV \text{ integration start}}^{i=RV \text{ integration end}} (IR_{\text{measurement channel } i})}{\sum_{i=RV \text{ integration start}}^{i=RV \text{ integration end}} \left(IR_{\text{measurement channel } i} / M_{PEi} \right)} \quad (\text{Eqn. 2B})$$

$$[00163] \quad M_w(\text{LALS gpc}) = \frac{\sum_{i=RV \text{ integration start}}^{i=RV \text{ integration end}} (M_{PEi} \cdot IR_{\text{measurement channel } i})}{\sum_{i=RV \text{ integration start}}^{i=RV \text{ integration end}} (IR_{\text{measurement channel } i})} \quad (\text{Eqn. 3B})$$

[00164] In Equations 2B and 3B, RV is column retention volume (linearly-spaced), collected at "1 point per second." The IR is the baseline-subtracted IR detector signal, in Volts, from the measurement channel of the GPC instrument, and the MPE is the polyethylene-equivalent MW determined from Equation IB. Data calculation were performed using "GPC One software (version 2.0 13H)" from PolymerChar.

[00165] A calibration for the IR5 detector ratios was performed using at least ten ethylene-based polymer standards (polyethylene homopolymer and ethylene/octene copolymers; narrow molecular weight distribution and homogeneous comonomer distribution) of known short chain branching (SCB) frequency (measured by the ¹³C NMR Method, as discussed above), ranging from homopolymer (0 SCB/1000 total C) to approximately 50 SCB/1000 total

-30-

C, where total C = carbons in backbone + carbons in branches. Each standard had a weight-average molecular weight from 36,000 g/mole to 126,000 g/mole, as determined by the GPC-LALS processing method described above. Each standard had a molecular weight distribution (Mw/Mn) from 2.0 to 2.5, as determined by the GPC-LALS processing method described above. Polymer properties for the SCB standards are shown in Table 1.

[00166] Table 1: "SCB" Standards

Wt % Comonomer	IR5 Area ratio	SCB/1000 Total C	Mw	Mw/Mn
23.1	0.2411	28.9	37,300	2.22
14.0	0.2152	17.5	36,000	2.19
0.0	0.1809	0.0	38,400	2.20
35.9	0.2708	44.9	42,200	2.18
5.4	0.1959	6.8	37,400	2.16
8.6	0.2043	10.8	36,800	2.20
39.2	0.2770	49.0	125,600	2.22
1.1	0.1810	1.4	107,000	2.09
14.3	0.2161	17.9	103,600	2.20
9.4	0.2031	11.8	103,200	2.26

[00167] The "IR5 Area Ratio (or "IR5 Methyl Channel Area / IR5 Measurement Channel Area")" of "the baseline-subtracted area response of the IR5 methyl channel sensor" to "the baseline-subtracted area response of IR5 measurement channel sensor" (standard filters and filter wheel as supplied by PolymerChar: Part Number IR5_FWM01 included as part of the GPC-IR instrument) was calculated for each of the "SCB" standards. A linear fit of the SCB frequency versus the "IR5 Area Ratio" was constructed in the form of the following Equation 4B:

[00168]
$$\text{SCB/1000 total C} = A_0 + [A_i \times (\text{IR5 Methyl Channel Area} / \text{IR5 Measurement Channel Area})]$$
 (Eqn. 4B), where A_0 is the "SCB/1000 total C" intercept at an "IR5 Area Ratio" of zero, and A_i is the slope of the "SCB/1000 total C" versus "IR5 Area Ratio," and represents the increase in the "SCB/1000 total C" as a function of "IR5 Area Ratio."

[00169] A series of "linear baseline-subtracted chromatographic heights" for the chromatogram generated by the "IR5 methyl channel sensor" was established as a function of column elution volume, to generate a baseline-corrected chromatogram (methyl channel). A series of "linear baseline-subtracted chromatographic heights" for the chromatogram generated

by the "IR5 measurement channel" was established as a function of column elution volume, to generate a base-line-corrected chromatogram (measurement channel).

[00170] The "IR5 Height Ratio" of "the baseline-corrected chromatogram (methyl channel)" to "the baseline-corrected chromatogram (measurement channel)" was calculated at each column elution volume index (each equally-spaced index, representing 1 data point per second at 1 ml/min elution) across the sample integration bounds. The "IR5 Height Ratio" was multiplied by the coefficient A_i , and the coefficient A_o was added to this result, to produce the predicted SCB frequency of the sample. The result was converted into mole percent comonomer, as follows in Equation 5B:

[00171] Mole Percent Comonomer = $\{SCB_f / [SCB_f + ((1000 - SCB_f * \text{Length of comonomer}) / 2)]\} * 100$ (Eqn. 5B), where "SCB_f" is the "SCB per 1000 total C" and the "Length of comonomer" = 8 for octene, 6 for hexene, and so forth.

[00172] Each elution volume index was converted to a molecular weight value (M_{wi}) using the method of Williams and Ward (described above; Eqn. 1B). The "Mole Percent Comonomer (*y axis*)" was plotted as a function of $\text{Log}(M_{wi})$, and the slope was calculated between M_{wi} of 15,000 and M_{wi} of 150,000 g/mole (end group corrections on chain ends were omitted for this calculation). An EXCEL linear regression was used to calculate the slope between, and including, M_{wi} from 15,000 to 150,000 g/mole. This slope is defined as the molecular weighted comonomer distribution index (MWCDI = Molecular Weighted Comonomer Distribution Index).

[00173] *Representative Determination of MWCDI*

[00174] A plot of the measured "SCB per 1000 total C (= SCB_f)" versus the observed "IR5 Area Ratio" of the SCB standards was generated (*see* Figure 1), and the intercept (A_o) and slope (A_i) were determined. Here, $A_o = -90.246$ SCB/1000 total C; and $A_i = 499.32$ SCB/1000 total C.

[00175] The "IR5 Height Ratio" was determined for a sample composition (*see* integration shown in Figure 2). This height ratio (IR5 Height Ratio) was multiplied by the coefficient A_i , and the coefficient A_o was added to this result, to produce the predicted SCB frequency of this example, at each elution volume index, as described above ($A_o = -90.246$

SCB/1000 total C; and $A_i = 499.32$ SCB/1000 total C). The SCB_f was plotted as a function of polyethylene-equivalent molecular weight, as determined using Equation IB, as discussed above. See FIG. 4 (Log M_{wi} used as the x-axis).

[00176] The SCB_f was converted into "Mole Percent Comonomer" via Equation 5B. The "Mole Percent Comonomer" was plotted as a function of polyethylene-equivalent molecular weight, as determined using Equation IB, as discussed above. See FIG. 5 (Log M_{wi} used for the x-axis). A linear fit was from M_{wi} of 15,000 g/mole to M_{wi} of 150,000 g/mole, yielding a slope of "2.27 mole percent comonomer x mole/g." Thus, the $MWCDI = 2.27$. An EXCEL linear regression was used to calculate the slope between, and including, M_{wi} from 15,000 to 150,000 g/mole.

[00177] *Puncture Resistance*

[00178] Puncture resistance is measured on a dynamometer according to ASTM D5748 in the standard laboratory atmosphere as temperature of $23 \pm 2^\circ\text{C}$.

[00179] *Instrumented Dart Impact*

[00180] Instrumented Dart Impact, which is measured according to ASTM D3763, is the total energy required to puncture a material by impact with a falling dart under specified test conditions. Here, a 12.7 mm (0.5 in) diameter hemispherical head dart was dropped from a height of 66 cm.

[00181] Table 2

Bending Angle	40°
Bending time	5 s
Bending Length	1 mm
Angular velocity	6°/sec
Specimen	80 x 15 mm

[00182] **EXAMPLES**

[00183] The following examples illustrate features of the present disclosure but are not intended to limit the scope of the disclosure.

[00184] Commercial Polymers Used

[00185] The following compositions listed in Table 3 were included in the thermoformed monolayer and multilayer examples discussed below.

[00186] Table 3

<u>Material</u>	<u>Melt Index (I_2) s/10</u> <u>min</u>	<u>Density (s/cc)</u>	<u>Supplier</u>
Inventive First Composition 1	0.85	0.918	n/a
DOWLEX™ NG 2045B (LLDPE)	1.00	0.920	The Dow Chemical Company, Midland, MI
ELITE™ NG 5400B (LLDPE)	1.00	0.916	The Dow Chemical Company, Midland, MI
Inventive First Composition 2	0.85	0.926	n/a
DOWLEX™ NG 2049B (LLDPE)	1.00	0.926	The Dow Chemical Company, Midland, MI
DOW™ LDPE 1321	0.25	0.921	The Dow Chemical Company, Midland, MI
VERSIFY™ 2000 (Propylene-ethylene copolymer)	2.00	0.888	The Dow Chemical Company, Midland, MI
ATTANE™ 4203	0.80	0.905	The Dow Chemical

<u>Material</u>	<u>Melt Index (I₂) s/10</u> <u>min</u>	<u>Density (s/cc)</u>	<u>Supplier</u>
(ULDPE)			Company, Midland, MI
ELITE™ AT 6101 (LLDPE)	0.80	0.905	The Dow Chemical Company, Midland, MI
ELITE™ 5230	4	0.916	The Dow Chemical Company, Midland, MI
ATTANE™ 4404 (ULDPE)	4	0.904	The Dow Chemical Company, Midland, MI
DOWLEX™ 2027 (LLDPE)	4	0.94	The Dow Chemical Company, Midland, MI
DOW™ LDPE 5004i	4.15	0.924	The Dow Chemical Company, Midland, MI
Inventive First Composition 3	0.85	0.915	n/a
DOWLEX™ 2247 (LLDPE)	2.3	0.917	The Dow Chemical Company, Midland, MI
ELITE™ AT 6111 (LLDPE)	0.85	0.912	The Dow Chemical Company, Midland, MI
Tie Resin 1 (Maleic Anhydride Grafted Polyolefin)*	6.9	0.911	n/a
AMPLIFY™ TY 1352	1.0	0.922	The Dow Chemical Company, Midland, MI
Ultramid C40 L Nylon	n/a	n/a	BASF
Soarnol ET 3803R	n/a	1.16	The Nippon Synthetic


<u>Material</u>	<u>Melt Index (I₂) s/10</u> <u>min</u>	<u>Density (s/cc)</u>	<u>Supplier</u>
(EVOH)			Chemical Industry Co., Ltd.
ELITE™ 5401	1.0	0.918	The Dow Chemical Company, Midland, MI

* Tie Resin 1 corresponds to the Inventive Tie Layer 1, which has a composition and method of making described in Table 5 of PCT Publication No. WO2017/053221, which is incorporated by reference herein in its entirety.

[00187] Inventive First Compositions 1-3

[00188] Inventive First Compositions 1-3 each contain two ethylene-octene copolymers. Each composition was prepared, via solution polymerization, in a dual series loop reactor system according to U.S. Pat. No. 5,977,251 (*see* Figure 2 of this patent), in the presence of a first catalyst system, as described below, in the first reactor, and a second catalyst system, as described below, in the second reactor.

[00189] The first catalyst system comprised a bis((2-oxoyl-3-(dibenzo-1H-pyrrole-1-yl)-5-(methyl)phenyl)-2-phenoxyethyl)-methylene-1,2-cyclohexanediylhafnium (TV) dimethyl, represented by the following formula (CAT 1):



[00190] (CAT 1).

[00191] The molar ratios of the metal of CAT 1, added to the polymerization reactor, in-situ, to that of Cocatl (modified methyl aluminoxane), or Cocat2 (bis(hydrogenated tallow alkyl)methyl, tetrakis(pentafluorophenyl)borate(1-) amine), are shown in Table 4 below.

[00192] The second catalyst system comprised a Ziegler-Natta type catalyst (CAT 2). The heterogeneous Ziegler-Natta type catalyst-premix was prepared substantially according to U.S. Pat. No. 4,612,300, by sequentially adding to a volume of ISOPAR E, a slurry of

anhydrous magnesium chloride in ISOPAR E, a solution of EtAlCl_2 in heptane, and a solution of $\text{Ti}(\text{O}-i\text{Pr})_4$ in heptane, to yield a composition containing a magnesium concentration of 0.20M, and a ratio of Mg/Al/Ti of 40/12.5/3. An aliquot of this composition was further diluted with ISOPAR-E to yield a final concentration of 500 ppm Ti in the slurry. While being fed to, and prior to entry into, the polymerization reactor, the catalyst premix was contacted with a dilute solution of Et_3Al , in the molar Al to Ti ratio specified in Table 4, to give the active catalyst.

[00193] The polymerization conditions for the Inventive First Compositions 1-3 are reported in Table 4. As seen in Table 4, Cocat. 1 (modified methyl aluminoxane (MMAO)); and Cocat. 2 (bis(hydrogenated tallow alkyl)methyl, tetrakis(pentafluorophenyl)borate(1-) amine) were each used as a cocatalyst for CAT 1. Additional properties of the Inventive First Compositions 1-3 were measured, and are reported in Table 5. Each polymer composition was stabilized with minor (ppm) amounts of stabilizers.

[00194] Table 4: Polymerization Conditions (Rx1 = reactor 1; Rx2 = reactor 2)

Sample #	Units	Inv. First Comp.1	Inv. First Comp. 2	Inv. First Comp. 3
Reactor Configuration		Dual Series	Dual Series	Dual Series
Comonomer		1-octene	1-octene	1-octene
<i>REACTOR FEEDS</i>				
First Reactor Total Solvent Flow	lb/hr	1122	1067	1240
First Reactor Total Ethylene Flow	lb/hr	190	176	198
First Reactor Total Comonomer Flow	lb/hr	74	43	79
First Reactor Hydrogen Feed Flow	SCCM	6827	4607	4899
Second Reactor Total Solvent Flow	lb/hr	384	447	382
Second Reactor Total Ethylene Flow	lb/hr	173	202	159
Second Reactor Total Comonomer Flow	lb/hr	12	6	10
Second Reactor Hydrogen Feed Flow	SCCM	298	1357	2701
<i>REACTION</i>				
First Reactor Control Temperature	°C	140	150	145
First Reactor Ethylene Conversion	%	86.7	90.9	87.8
First Reactor Viscosity	cP	2400	1658	1469

-37-

Sample #	Units	Inv. First Comp.1	Inv. First Comp. 2	Inv. First Comp. 3
Second Reactor Control Temperature	°C	195	195	195
Second Reactor Ethylene Conversion	%	87.1	84.6	83.0
Second Reactor Viscosity	cP	869	814	521
<i>CATALYST</i>				
First Reactor Catalyst	Type	CAT 1	CAT 1	CAT 1
First Reactor Catalyst Efficiency	g polymer per g catalyst metal	3,681,068	653238	668470
First Reactor Cocatalyst (Cocat. 2) to Catalyst Metal Molar Ratio	Ratio	1.3	1.2	1.1
First Reactor Cocatalyst (Cocat. 1) to Catalyst Metal Molar Ratio	Ratio	20	50.0	50.0
Second Reactor Catalyst Efficiency	g polymer per g catalyst metal	404,385	431113	381486
Second Reactor Al to Ti Molar Ratio	Ratio	4.0	4.0	4.0

[00195] *solvent = ISOPAR E

[00196] Table 5: Properties of Inventive First Compositions 1-3

	Unit	Inv. First Comp.1	Inv. First Comp. 2	Inv. First Comp. 3
Density	g/cc	0.918	0.926	0.915
I ₂	g/10 min	0.85	0.85	0.85
I ₁₀ /I ₂		7.7	7.5	8.1
7.0 – 1.2xlog(I ₂)		7.1	7.1	7.1
Mn (conv.gpc)	g/mol	32,973	32,467	28,130
Mw (conv.gpc)		117,553	112,291	114,384
Mz (conv.gpc)		270,191	262,093	274,682
Mw/Mn (conv.gpc)		3.57	3.46	4.07
Mz/Mw (conv.gpc)		2.30	2.33	2.40
Eta* (0.1 rad/s)	Pa•s	9,496	9,550	10,388
Eta* (1.0 rad/s)	Pa•s	7,693	7,377	8,031
Eta* (10 rad/s)	Pa•s	4,706	4,470	4,634

	Unit	Inv. First Comp.1	Inv. First Comp. 2	Inv. First Comp. 3
rad/s)				
Eta* (100 rad/s)	Pa•s	1,778	1,774	1,669
Eta*0.1/ Eta*100		5.34	5.38	6.22
Eta zero	Pa•s	11,210	11,764	12,828
MWCDI		2.64	1.86	3.17
Vinyls	Per 1000 total Carbons	134	1.89	NM
ZSVR		1.53		1.93

[00197] Example 1: Monolayer Films

[00198] Referring to Table 6 below, several monolayer films were produced on a 5 Layer Collin Coextrusion Blown Film Line in accordance with the following parameters provided on Table 7.

[00199] Table 6

Monolayer Films
Inventive First Composition 1
DOWLEX™ NG 2045B (LLDPE)
ELITE™ NG 5400B (LLDPE)
Inventive First Composition 2
DOWLEX™ NG 2049B (LLDPE)
DOW™ LDPE 1321
VERSIFY™ 2000 (Propylene-ethylene copolymer)
ATTANE™ 4203 (ULDPE)

[00200] Table 7: Monolayer Film

Thickness	100 μ m
Blow Up Ratio (BUR)	3.0
Lay flat width	377 mm
Final width	323 mm
Die Type	80 mm

[00201] The monolayer films were thermoformed using an R145 Multivac thermoforming machine using the following thermoforming parameters provided in Table 8.

[00202] Table 8

Mold size	1 Package
Package size	242 mm x 242 mm.
Temperature	95°C.
Maximum Depth of Tray	110 mm.
Heating time	2 sec.
Forming time	2 sec

[00203] The puncture resistance for the monolayer films pre-thermoforming and post-thermoforming are provided in Figure 5. As shown, the monolayer films comprising the Inventive First Compositions 1 and 2 showed marked improvement (e.g., at least 10%) in puncture resistance after undergoing thermoforming, whereas the comparative conventional monolayer films generally showed a decrease in puncture resistance or a very marginal increase.

[00204] Example 2: Thermoformed Multilayer Films (Cast Film Extrusion)

[00205] The following multilayer films of Table 9 had an ABCDE 5 layer structure produced through cast film extrusion. The thickness percentages of each layer is also provided in Table 9.

[00206] Table 9 - Film Samples 1 and 2 and Comparative Film Samples C1-C3

Sample #	Layer A Resin	Layer B Resin	Layer C Resin	Layer D Resin	Layer E Resin	% A	% B	% C	% D	% E
1	ELITE™ 5230	ATTANE™ 4404	Inventive First Composition 3	ATTANE™ 4404	ELITE™ 5230	20	20	25	20	15
C1*	DOWLEX™ 2027	DOWLEX™ 2247	ELITE™ 5230	DOWLEX™ 2247	ELITE™ 5230	20	20	25	20	15
C2*	DOWLEX™ 2247	DOWLEX™ 2247	ELITE™ 5230	DOWLEX™ 2247	ELITE™ 5230	20	20	25	20	15
2	ELITE™ 5230	Inventive First Composition 2	ATTANE™ 4404	Inventive First Composition 2	ATTANE™ 4404	20	20	25	20	15
C3*	VERSIFY™ 2000	Tie Resin 1	50% DOWLEX™ 2247 + 50% LDPE 5004i	50% DOWLEX™ 2247 + 50% LDPE 5004i	50% DOWLEX™ 2247+ 50% LDPE 5004i	20	20	25	20	15

*C1-C3 represents Comparative Film Samples 1-3

[00207] The multilayer films were produced on a Dow Freeport 5 Layer Cast Extrusion Film Line, with the following characteristics provided in Table 10.

[00208] Table 10

Thickness	7 mil (177.8 μm)
Final width	24.25 in
5 layer die cut	(20/20/20/20/20)

[00209] The multilayer films of Table 9 were thermoformed into pouches using an R145 Multivac thermoforming machine with the following thermoforming parameters provided in Table 8 above.

[00210] The dart performance, specifically, the Instrumented Dart Performance, for pouches after thermoforming are provided in Figure 6. As shown, the Inventive Sample 1, which includes Inventive First Composition 3, has an Instrumented Dart Impact twice the value of Comparative Samples, C2 and C3, and have approximately 10 times the value of Comparative Sample C3.

[00211] Example 3: Thermoformed Multilayer Films (Blown Film Extrusion)

[00212] The following multilayer films of Table 11 had an ABCDE 5 layer structure produced through blown film extrusion. All films had a thickness of 100 μm.

[00213] Table 11 - Film Samples 1 and 2 and Comparative Film Samples C1-C3

Sampl e	Layer A Resin	Layer B Resin	Layer c Resin	Layer D Resin	Layer E Resin	% A	% B	% c	% D	% E
C4*	ELITE™ 5400B	AMPLIFY™ 1352	Nylon (UBE)	AMPLIFY™ 1352	DOWLEX™ 2049B	30	10	20	1	30
3	ELITE™ 5400B	ATTANE™ 4203	Inventive First Composition 1	ATTANE™ 4203	Inventive First Composition 1	20	20	20	20	20
4	ELITE™ 5400B	ATTANE™ 4203	Inventive First Composition 1	ATTANE™ 4203	Inventive First Composition 1	20	10	30	10	30
5	ELITE™ 5400B	ATTANE™ 4203	Inventive First Composition 2	ATTANE™ 4203	Inventive First Composition 2	20	20	20	20	20
6	ELITE™ 5400B	ATTANE™ 4203	Inventive First Composition 2	ATTANE™ 4203	Inventive First Composition 2	20	10	30	10	30
C5*	AMPLIFY™ 1352	Nylon (UBE)	EVOH	Nylon (UBE)	AMPLIFY™ 1352	37	10	6	10	37
7	Inventive First Composition 1	AMPLIFY™ 1352	EVOH	AMPLIFY™ 1352	Inventive First Composition 1	37	10	6	10	37
C6*	ELITE™	AMPLIFY	EVOH	AMPLIFY	ELITE™	37	10	6	10	37

Sample	Layer A Resin	Layer B Resin	Layer C Resin	Layer D Resin	Layer E Resin	% A	% B	% C	% D	% E
	540IB	TM 1352		TM 1352	540IB					

*C4-C6 represents Comparative Examples 4-6

[00214] The multilayer films of Table 11 were produced on a 5 Layer Collin Coextrusion Blown Film Line, with the following characteristics provided in Table 12.

[00215] Table 12

Thickness	100 μm
BUR	3.0
Lay flat width	377 mm
Final width	323 mm
Die Type	80 mm

[00216] The multilayer films of Table 11 were thermoformed using an R145 Multivac thermoforming machine into pouches using the thermoforming parameters provided in Table 8 above with the exception that the depth is 80 mm for the multilayer films of Table 11.

[00217] The puncture resistance for the multilayer films pre-thermoforming and post-thermoforming are provided in Figure 7. As shown, the inventive multilayer films (Samples 3, 4, and 6), which comprise the Inventive First Compositions 1 or 2, showed improvement in puncture resistance after undergoing thermoforming. Sample 5 also showed marginal improvement in puncture resistance; however, Sample 5 already had a high level of puncture resistance prior to thermoforming.

[00218] Comparative Sample 4 (nylon containing multilayer film), Comparative Sample 5 (Nylon and EVOH containing multilayer film), and Comparative Sample 6 (EVOH containing multilayer film) include polyamide, and/or EVOH, which are commonly used in thermoformed packages. The inventive samples (Samples 3-6) achieved comparable puncture resistance, and suitable dart performance, and stiffness, while utilizing a monomaterial (i.e., only ethylene-based polymer) package. In Inventive Sample 7, which combines Inventive First Composition 2

and EVOH, there is a significant increase in puncture resistance after thermoforming, thus indicating synergistic benefits when including EVOH and the inventive first composition.

[00219] Additionally, Samples 5 and 6, which both include Inventive First Composition 2 having a density of 0.926, demonstrated further surprising results. As shown, Sample 5, which included 40% of the overall thickness of Inventive First Composition 2, maintained its puncture resistance after thermoforming. However, for Sample 6, which included 60% of the overall thickness of Inventive First Composition 2, puncture resistance greatly increased after thermoforming.

[00220] It will be apparent that modifications and variations are possible without departing from the scope of the disclosure defined in the appended claims. More specifically, although some aspects of the present disclosure are identified herein as preferred or particularly advantageous, it is contemplated that the present disclosure is not necessarily limited to these aspects.

CLAIMS

1. A thermoformed multilayer film structure comprising:

a core layer and at least two outer layers disposed externally relative to the core layer,

wherein at least one layer of the thermoformed multilayer film structure comprises a first composition comprising at least one ethylene-based polymer, wherein the first composition comprises a Molecular Weighted Comonomer Distribution Index (MWCDI) value greater than 0.9, and a melt index ratio (I_{10}/I_2) that meets the following equation: $I_{10}/I_2 \geq 7.0 - 1.2 \times \log(I_2)$.
2. The thermoformed multilayer film structure of claim 1, wherein the thermoformed multilayer film structure comprises at least one of polyamide, ethylene vinyl alcohol (EVOH), and malleated polyolefins.
3. The thermoformed multilayer film structure of any preceding claim, wherein the thermoformed multilayer film structure is substantially free of propylene-based polymers.
4. The thermoformed multilayer film structure of any preceding claim, wherein the thermoformed multilayer film structure consists essentially of ethylene-based polymers.
5. The thermoformed multilayer film structure of any preceding claim, wherein the core layer comprises the first composition.
6. The thermoformed multilayer film structure of any preceding claim, wherein at least one of the outer layers comprises the first composition.
7. The thermoformed multilayer film structure of claim 6, wherein the ethylene-based polymer is an ethylene- α -olefin interpolymers, where the α -olefin comprises one or more C_3 - C_{12} olefins.
8. The thermoformed multilayer film structure of claim 1 or 2, wherein at least one of the outer layers comprises propylene-based polymers.
9. The thermoformed multilayer film structure of any preceding claim, wherein the thermoformed multilayer film structure has a total thickness of 50 to 250 μm .

10. A thermoformed monolayer film comprising:

a first composition comprising at least one ethylene based polymer, wherein the first composition comprises a Molecular Weighted Comonomer Distribution Index (MWCDI) value greater than 0.9, and a melt index ratio (I_{10}/I_2) that meets the following equation: $I_{10}/I_2 \geq 7.0 - 1.2 \times \log(I_2)$,

wherein the thermoformed monolayer film demonstrates an increase in puncture resistance of at least 10% due to thermoforming applications.

11. The thermoformed monolayer film of claim 10, wherein the thermoformed monolayer film structure consists essentially of ethylene based polymer.

12. The thermoformed monolayer film of claims 10 or 11, wherein the thermoformed monolayer film structure has a total thickness of 50 to 250 μm .

13. An article comprising the thermoformed multilayer film structure of claims 1-9, or the thermoformed monolayer film structure of claims 10-12.

14. The article of claim 13, wherein the article is a flexible packaging material.




FIG. 1




FIG. 2




FIG. 3




FIG. 5




FIG. 6




FIG. 7

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2018/051704

A. CLASSIFICATION OF SUBJECT MATTER
 INV. C08J5/18 B32B27/32 C08F210/16 C08L23/08
 ADD.
 According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED
 Minimum documentation searched (classification system followed by classification symbols)
 C08J C08F B32B C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
 EPO-Internal , WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2017/129229 AI (WANG JIAN [US] ET AL) 11 May 2017 (2017-05-11) claims; examples -----	1-14
X	US 2017/129230 AI (WANG JIAN [US] ET AL) 11 May 2017 (2017-05-11) claims; examples -----	1-14
X	US 2017/226244 AI (GOYAL SHIVENDRA KUMAR [CA] ET AL) 10 August 2017 (2017-08-10) paragraphs [0082] , [0083] ; claims ; examples; tabl e 17 -----	1-14
X	US 2013/046061 AI (HERMEL-DAVIDOCK THERESA J [US] ET AL) 21 February 2013 (2013-02-21) paragraphs [0071] , [0092] - [0094] , [0106] ; claims ; examples -----	1-8, 10, 11, 13, 14

Further documents are listed in the continuation of Box C. See patent family annex.

* Special categories of cited documents :
 "A" document defining the general state of the art which is not considered to be of particular relevance
 "E" earlier application or patent but published on or after the international filing date
 "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
 "O" document referring to an oral disclosure, use, exhibition or other means
 "P" document published prior to the international filing date but later than the priority date claimed
 "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
 "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
 "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
 "&" document member of the same patent family

Date of the actual completion of the international search 14 December 2018	Date of mailing of the international search report 02/01/2019
---	--

Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer Fri son , Cel ine
--	---

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No PCT/US2018/051704
--

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2017129229 AI	11-05-2017	BR 112016029163 A2	22-08-2017
		CN 106457793 A	22-02-2017
		EP 3160740 AI	03-05-2017
		JP 2017522408 A	10-08-2017
		US 2017129229 AI	11-05-2017
		Wo 2015200743 AI	30-12-2015

US 2017129230 AI	11-05-2017	BR 112016029258 A2	22-08-2017
		CA 2952031 AI	30-12-2015
		CN 106470838 A	01-03-2017
		EP 3160742 AI	03-05-2017
		JP 2017522409 A	10-08-2017
		US 2017129230 AI	11-05-2017
Wo 2015200742 AI	30-12-2015		

US 2017226244 AI	10-08-2017	BR 112017003303 A2	28-11-2017
		CA 2956349 AI	25-02-2016
		CN 107075023 A	18-08-2017
		EP 3183277 AI	28-06-2017
		JP 2017525812 A	07-09-2017
		KR 20170046151 A	28-04-2017
		TW 201609827 A	16-03-2016
		US 2017226244 AI	10-08-2017
wo 2016027194 AI	25-02-2016		

US 2013046061 AI	21-02-2013	BR 112012022194 A2	05-07-2016
		CN 103038281 A	10-04-2013
		EP 2542621 A2	09-01-2013
		JP 5858935 B2	10-02-2016
		JP 2013521382 A	10-06-2013
		KR 20130004585 A	11-01-2013
		MX 354078 B	12-02-2018
		RU 2012141894 A	10-04-2014
		US 2013046061 AI	21-02-2013
wo 2011109563 A2	09-09-2011		
