

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
21 July 2005 (21.07.2005)

PCT

(10) International Publication Number
WO 2005/066228 A1

(51) International Patent Classification⁷: **C08F 220/00**,
G02B 1/00, C08F 2/02, 2/06

(21) International Application Number:
PCT/US2004/041553

(22) International Filing Date: 9 December 2004 (09.12.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
10/748,049 30 December 2003 (30.12.2003) US

(71) Applicant: **3M INNOVATIVE PROPERTIES COMPANY** [US/US]; 3M Center, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).

(72) Inventors: **OLSON, David, B.**; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). **BERG, Brandon, T.**; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). **LARSON, Randy, A.**; P.O. Box 33427, Saint Paul, MN 55133-3427 (US).

(74) Agents: **FISCHER, Carolyn A.**, et al.; Office of Intellectual Property Counsel, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM,

AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:


- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for all designations
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for all designations

Published:

- with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: POLYMERIZABLE COMPOSITION FOR OPTICAL ARTICLES



(57) Abstract: Polymerizable compositions particularly useful for brightness enhancing films.

WO 2005/066228 A1

POLYMERIZABLE COMPOSITION FOR OPTICAL ARTICLES

FIELD

5 Polymerizable compositions particularly useful for optical articles such as for example brightness enhancing films.

BACKGROUND

10 Certain microreplicated optical products, such as described in U.S. Pat. Nos. 5,175,030 and 5,183,597, are commonly referred to as a "brightness enhancing films". Brightness enhancing films are utilized in many electronic products to increase the brightness of a backlit flat panel display such as a liquid crystal display (LCD) including those used in electroluminescent panels, laptop computer displays, word processors, desktop monitors, televisions, video cameras, as well as automotive and aviation displays.

15 Brightness enhancing films desirably exhibit specific optical and physical properties including the index of refraction of a brightness enhancing film that is related to the brightness gain (i.e. "gain") produced. Improved brightness can allow the electronic product to operate more efficiently by using less power to light the display, thereby reducing the power consumption, placing a lower heat load on its components, and
20 extending the lifetime of the product.


Brightness enhancing films have been prepared from high index of refraction monomers that are cured or polymerized, as described for example in U.S. Patent Nos. 5,908,874; 5,932,626; 6,107,364; 6,280,063; 6,355,754; as well as EP 1 014113 and WO 03/076528.

25 Although various polymerizable compositions that are suitable for the manufacture of brightness enhancing films are known, industry would find advantage in alternative compositions.

SUMMARY

30 In one embodiment of the present invention, a brightness enhancing film is provided that comprises the reaction product of a polymerizable composition consisting essentially of:


- a) one or more first monomers selected from the group consisting of
- i) a monomer comprising a major portion having the structure



wherein R1 is independently hydrogen or methyl; and

5

- ii) a monomer comprising a major portion having the structure



10

wherein R1 is independently hydrogen or methyl, and

L is a linking group independently selected from the group consisting of

linear C₂-C₁₂ alkyl groups,

branched C₂-C₁₂ alkyl groups and

-CH₂CH(OH)CH₂-;

15

and mixtures thereof;

- b) a second monomer consisting of 2,4,6-tribromophenoxyethyl (meth)acrylate;

- c) a crosslinking agent selected from the group consisting of pentaerythritol tri(meth)acrylate, pentaerythritol tetra(meth)acrylate, trimethylolpropane tri(meth)acrylate, and mixtures thereof;
- d) optionally a monofunctional diluent; and
- 5 e) optionally a photoinitiator.

The first monomer can be present in the polymerizable composition in an amount of at least 20 wt-% and in an amount less than 40 wt-%. The first monomer preferably comprises a major portion of 2-propenoic acid, (1-methylethylidene)bis[(2,6-dibromo-4,1-phenylene)oxy(2-hydroxy-3,1-propanediyl)] ester. The 2,4,6-tribromophenoxyethyl (meth)acrylate monomer can be present in an amount of at least about 25 wt-% and in an amount less than 50 wt-%. The crosslinking agent and/or the optional monofunctional diluent are preferably liquid at ambient temperature. The crosslinking agent can be present in an amount ranging of at least about 5 wt-% and in an amount less than 30 wt-%.

10 The crosslinking agent is preferably pentaerythritol triacrylate. The monofunctional diluent can be present in an amount of at least about 10 wt-% and in an amount less than 20 wt-%. The monofunctional (meth)acrylate diluent can comprise phenoxyethyl (meth)acrylate, benzyl (meth)acrylate, and mixtures thereof and is preferably phenoxyethylacrylate.

20 The polymerizable compositions described herein may also be advantageous for other optical articles.

BRIEF DESCRIPTION OF THE DRAWINGS

25 FIG. 1 is a perspective view of an illustrative microstructure-bearing optical product of the present invention.

FIG. 2 is a schematic view of an illustrative backlit liquid crystal display including the brightness enhancing film of the invention.

DETAILED DESCRIPTION

As used within the present description:

5 "Index of refraction," or "refractive index," refers to the absolute refractive index of a material (e.g., a monomer) that is understood to be the ratio of the speed of electromagnetic radiation in free space to the speed of the radiation in that material, with the radiation being sodium yellow light at a wavelength of about 589.3 nm. Index of refraction can be measured using an Abbe refractometer, available commercially, for
10 example, from Fisher Instruments of Pittsburgh, PA. It is generally appreciated that the measured index of refraction can vary to some extent depending on the instrument.

"(Meth)acrylate" refers to both acrylate and methacrylate compounds.

15 "Polymerizable composition" refers to a chemical composition that contains one or more polymerizable components as described in the present specification, including at least the identified monomers that can be cured or polymerized.

"Brightness enhancing films" include microstructure-bearing articles having a
20 regular repeating pattern of symmetrical tips and grooves. Other examples of groove patterns include patterns in which the tips and grooves are not symmetrical and in which the size, orientation, or distance between the tips and grooves is not uniform. Examples of brightness enhancing films are described in Lu et al., U.S. Pat. No. 5,175,030, and Lu, U.S. Pat. No. 5,183,597.

25 Referring to Figure 1, the brightness enhancing film 30 of the invention generally comprises base layer 2 and optical layer 4. Optical layer 4 comprises a linear array of regular right prisms, identified as prisms 6, 8, 12, and 14. Each prism, for example, prism 6, has a first facet 10 and a second facet 11. The prisms 6, 8, 12, and 14 are formed on base 2 that has a first surface 18 on which the prisms are formed and a second surface 20
30 that is substantially flat or planar and opposite first surface 18. By right prisms it is meant that the apex angle α is typically about 90°. However, this angle can range from 70° to 120° and may range from 80° to 100°. Further the corner can be either sharp or rounded.

The prism facets need not be identical, and the prisms may be tilted with respect to each other. The relationship between the total thickness 24 of the optical article, and the height 22 of the prisms, may vary. However, it is typically desirable to use relatively thinner optical layers with well-defined prism facets. A typical ratio of prism height 22 to total thickness 24 is generally between 25/125 and 2/125.

The base layer of the brightness enhancing film can be of a nature and composition suitable for use in an optical product, i.e. a product designed to control the flow of light. Many materials can be used as a base material provided the material is sufficiently optically clear and is structurally strong enough to be assembled into or used within a particular optical product. Preferably, the base material is chosen that has sufficient resistance to temperature and aging that performance of the optical product is not compromised over time.

The particular chemical composition and thickness of the base material for any optical product can depend on the requirements of the particular optical product that is being constructed. That is, balancing the needs for strength, clarity, temperature resistance, surface energy, adherence to the optical layer, among others. The thickness of the base layer is typically at least about 0.025 millimeters (mm) and more typically at least about 0.075 mm. Further, the base layer generally has a thickness of no more than about 0.5 mm and preferably no more than about 0.175.

Useful base layer materials include cellulose acetate butyrate, cellulose acetate propionate, cellulose triacetate, polyether sulfone, polymethyl methacrylate, polyurethane, polyester, polycarbonate, polyvinyl chloride, syndiotactic polystyrene, polyethylene naphthalate, copolymers or blends based on naphthalene dicarboxylic acids, and glass. Optionally, the base material can contain mixtures or combinations of these materials. For example, the base may be multi-layered or may contain a dispersed phase suspended or dispersed in a continuous phase. Exemplary base layer materials include polyethylene terephthalate (PET) and polycarbonate. Examples of useful PET films include photograde polyethylene terephthalate (PET) and PET commercially available from DuPont Films of Wilmington, Delaware, under the trade designation "Milinex."

The base layer material can be optically active, and can act as a polarizing material. A number of base layer materials are known to be useful as polarizing materials. Polarization of light through a film can be accomplished, for example, by the inclusion of

dichroic polarizers in a film material that selectively absorbs passing light. Light polarization can also be achieved by including inorganic materials such as aligned mica chips or by a discontinuous phase dispersed within a continuous film, such as droplets of light modulating liquid crystals dispersed within a continuous film. As an alternative, a film can be prepared from microfine layers of different materials. The polarizing materials within the film can be aligned into a polarizing orientation, for example, by employing methods such as stretching the film, applying electric or magnetic fields, and coating techniques.

Examples of polarizing films include those described in U.S. Pat. Nos. 5,825,543 and 5,783,120. The use of these polarizer films in combination with a brightness enhancement film has been described in U.S. Pat. No. 6,111,696. Another example of a polarizing film is described in U.S. Pat. No. 5,882,774. One example of such films that are available commercially are the multilayer films sold under the trade designation DBEF (Dual Brightness Enhancement Film) from 3M Company, St. Paul, MN. The use of such multilayer polarizing optical film in a brightness enhancement film has been described in U.S. Pat. No. 5,828,488.


Other polarizing and non-polarizing films can also be useful as the base layer for brightness enhancing films of the invention such as described in U.S. Patent Nos. 5,612,820 and 5,486,949, among others.

The present invention relates to a polymerizable resin composition useful for optical articles and in particular the optical layer of a brightness enhancing film. The polymerizable composition includes at least three monomers. The polymerizable resin composition comprises a first and a second monomer, each having a refractive index of at least 1.54, at least one crosslinking agent, and optionally yet preferably at least one monofunctional reactive diluent. Suitable methods of polymerization are known in the art including solution polymerization, suspension polymerization, emulsion polymerization, and bulk polymerization, for example, in the presence of a free-radical initiator. The composition of the invention is preferably polymerizable by irradiation with ultraviolet or visible light in the presence of a photoinitiator. The first and second monomer, crosslinking agent, and optional diluent preferably comprise (meth)acrylate functional groups. In preferred embodiments the first and second monomer in addition to the

crosslinking agent include only acrylate functionality and thus are substantially free of methacrylate functional groups.


The first monomer comprises a major portion having the general structures:

5 (I)



or

(II)



10

In each of structures I and II, each R1 is independently hydrogen or methyl. Typically, the R1 groups are the same. In structure II, L is a linking group. Each L may independently comprise a branched or linear C₂-C₁₂ alkyl group. Typically, the linking groups are the same alkyl group. Preferably the alkyl group comprises no more than 8 carbon atoms and more preferably no more than 6 carbon atoms. Alternatively, L is -CH₂CH(OH)CH₂-.

15

The first monomer may be synthesized or purchased. As used herein, major portion refers to at least 60-70 wt-% of the monomer containing the specific structure(s)

20

just described. It is commonly appreciated that other reaction products are also typically present as a byproduct of the synthesis of such monomers.

The first monomer is preferably the reaction product of Tetrabromobisphenol A diglycidyl ether and acrylic acid. Preferred first monomers have acrylate functionality and are substantially free of methacrylate functionality. For example, the first monomer may be obtained from UCB Corporation, Smyrna, GA under the trade designation "RDX-51027". This material comprises a major portion of 2-propenoic acid, (1-methylethylidene)bis[(2,6-dibromo-4,1-phenylene)oxy(2-hydroxy-3,1-propanediyl)] ester.

Although, mixtures of such first monomers may also suitably be employed, for ease in manufacturing it is preferred to employ as few different monomers as possible, yet still attain a brightness enhancing film with suitable gain. To meet this end, it is preferred that the brightness enhancing film is comprised of the reaction product of only one of these first monomers and in particular the reaction product of Tetrabromobisphenol A diglycidyl ether and acrylic acid.

The first monomer is preferably present in the polymerizable composition in an amount of at least about 20 wt-% (e.g. 25 wt-%, 30 wt-%). Typically, the amount of the first monomer is less than about 50 wt-%, and preferably less than about 40 wt-%. The first monomer may be present in any amount (e.g. integer) between the minimum and maximum amount just described.

The second monomer is present in the composition at an amount of at least about 25 wt-% (e.g. 26 wt-%, 27 wt-%, 28 wt-%, 29 wt-%). The second monomer is halogenated (i.e. brominated), consisting of 2,4,6-tribromophenoxyethyl (meth)acrylate. The 2,4,6-tribromophenoxyethyl (meth)acrylate monomer is commercially available from Daiichi Kogyo Seiyaku Co. Ltd (Kyoto, Japan) under the trade designation "BR-31".

Typically, the amount of this monomer is no greater than about 50 wt-%. The amount of this monomer is preferably present in amounts ranging from about 30 wt-% to about 45 wt-% (including integers between 30 and 45).

In addition to the first and monomer having high refractive indices, the polymerizable composition of the invention also includes at least one and preferably only one crosslinking agent. Multi-functional monomers can be used as crosslinking agents to increase the glass transition temperature of the polymer that results from the polymerizing of the polymerizable composition. The glass transition temperature can be measured by

methods known in the art, such as Differential Scanning Calorimetry (DSC), modulated DSC, or Dynamic Mechanical Analysis. Preferably, the polymeric composition is crosslinked sufficiently to provide a glass transition temperature that is greater than 45° C. The crosslinking agent comprises at least three (meth)acrylate functional groups. Since methacrylate groups tend to be less reactive than acrylate groups, it is preferred that the crosslinking agent comprises three or more acrylate groups. Suitable crosslinking agents include pentaerythritol tri(meth)acrylate, pentaerythritol tetra(meth)acrylate, trimethylolpropane tri(meth)acrylate, and mixtures thereof. More preferably, the crosslinking agent(s) is free of methacrylate functionality. Pentaerythritol triacrylate (PETA) is particularly preferred. Pentaerythritol triacrylate (PETA) is commercially available from several sources including Sartomer, Exton, PA under the trade designation "SR444"; from Osaka Organic Chemical Industry, Ltd. Osaka, Japan under the trade designation "Viscoat #300"; from Toagosei Co. Ltd., Tokyo, Japan under the trade designation "Aronix M-305"; and from Eternal Chemical Co., Ltd., Kaohsiung, Taiwan under the trade designation "Etermer 235". Trimethylolpropane triacrylate (TMPTA) is commercially available from Sartomer under the trade designation "SR351" and from Toagosei Co. Ltd. under the trade designation "Aronix M-309".

The crosslinking agent is preferably present in the polymerizable composition in an amount of at least about 5 wt-%. Typically, the amount of crosslinking agent is not greater than about 30 wt-%. The crosslinking agent may be present in any amount (i.e. integer) between 5 wt-% and 30 wt-% as well. Preferably, the concentration of the crosslinking agent does not exceed about 20 wt-%.

The polymerizable resin composition optionally, yet preferably comprises up to about 20 wt-% reactive diluents to reduce the viscosity of the polymerizable resin composition. Reduced viscosity is also amenable to improved the processability. Reactive diluents are mono- or di-functional (meth)acrylate-functional monomers typically having a refractive index greater than 1.50. Such reactive diluents are typically non-halogenated (e.g. non-brominated). Suitable reactive diluents include for example phenoxyethyl (meth)acrylate, phenoxy-2-methylethyl (meth)acrylate, phenoxyethoxyethyl (meth)acrylate, 3-hydroxy-2-hydroxypropyl (meth)acrylate, benzyl (meth)acrylate, 4-(1-methyl-1-phenethyl)phenoxyethyl (meth)acrylate and phenylthioethyl (meth)acrylate.

The inclusion of only one diluent is preferred for ease in manufacturing. A preferred diluent is phenoxyethyl (meth)acrylate, and in particular phenoxyethyl acrylate (PEA). Phenoxyethyl acrylate is commercially available from more than one source including from Sartomer under the trade designation "SR339"; from Eternal Chemical Co. Ltd. under the trade designation "Etermer 210"; and from Toagosei Co. Ltd under the trade designation "TO-1166". Benzyl acrylate is commercially available from AlfaAeser Corp, Ward Hill, MA.

Suitable methods of polymerization include solution polymerization, suspension polymerization, emulsion polymerization, and bulk polymerization as are known in the art. Suitable methods include heating in the presence of a free-radical initiator as well as irradiation with electromagnetic radiation such as ultraviolet or visible light in the presence of a photoinitiator. Inhibitors are frequently used in the synthesis of the polymerizable composition to prevent premature polymerization of the resin during synthesis, transportation and storage. Suitable inhibitors include hydroquinone and 4-methoxy phenol at levels of 50-1000 ppm. Other kinds and/or amounts of inhibitors may be employed as known to those skilled in the art.

The composition of the present invention optionally comprises a least one photoinitiator. A single photoinitiator or blends thereof may be employed in the brightness enhancement film of the invention. In general the photoinitiator(s) are at least partially soluble (e.g. at the processing temperature of the resin) and substantially colorless after being polymerized. The photoinitiator may be (e.g. yellow) colored, provided that the photoinitiator is rendered substantially colorless after exposure to the UV light source.

Suitable photoinitiators include monoacylphosphine oxide and bisacylphosphine oxide. Commercially available mono or bisacylphosphine oxide photoinitiators include 2,4,6-trimethylbenzoyldiphenylphosphine oxide, commercially available from BASF (Charlotte, NC) under the trade designation "Lucirin TPO"; ethyl-2,4,6-trimethylbenzoylphenyl phosphinate, also commercially available from BASF under the trade designation "Lucirin TPO-L"; and bis (2,4,6-trimethylbenzoyl)-phenylphosphine oxide commercially available from Ciba Specialty Chemicals under the trade designation "Irgacure 819". Other suitable photoinitiators include 2-hydroxy-2-methyl-1-phenyl-1-propanone, commercially available from Ciba Specialty Chemicals under the trade designation "Darocur 1173" as well as other photoinitiators commercially available from

Ciba Specialty Chemicals under the trade designations "Darocur 4265", "Irgacure 651", "Irgacure 1800", "Irgacure 369", "Irgacure 1700", and "Irgacure 907".

The photoinitiator can be used at a concentration of about 0.1 to about 10 weight percent. More preferably, the photoinitiator is used at a concentration of about 0.5 to about 5 wt-%. Greater than 5 wt-% is generally disadvantageous in view of the tendency to cause yellow discoloration of the brightness enhancing film. Other photoinitiators and photoinitiator may also suitably be employed as may be determined by one of ordinary skill in the art.

Surfactants such as fluorosurfactants and silicone based surfactants can optionally be included in the polymerizable composition to reduce surface tension, improve wetting, allow smoother coating and fewer defects of the coating, etc.

As described in Lu and Lu et al., a microstructure-bearing article (e.g. brightness enhancing film) can be prepared by a method including the steps of (a) preparing a polymerizable composition (i.e. the polymerizable composition of the invention); (b) depositing the polymerizable composition onto a master negative microstructured molding surface in an amount barely sufficient to fill the cavities of the master; (c) filling the cavities by moving a bead of the polymerizable composition between a preformed base and the master, at least one of which is flexible; and (d) curing the composition. The master can be metallic, such as nickel, nickel-plated copper or brass, or can be a thermoplastic material that is stable under the polymerization conditions, and that preferably has a surface energy that allows clean removal of the polymerized material from the master. One or more the surfaces of the base film can be optionally be primed or otherwise be treated to promote adhesion of the optical layer to the base.

The brightness enhancing film of the invention is usefully employed in a display for the purpose of improving the gain. A schematic view of an illustrative backlit liquid crystal display generally indicated at 110 in FIG. 2. In the actual display, the various components depicted are often in contact with the brightness enhancing film. The brightness enhancing film 111 of the present invention is generally positioned between a light guide 118 and a liquid crystal display panel 114. The liquid crystal display panel typically includes an absorbing polarizer on both surfaces. Thus, such absorbing polarizer is positioned adjacent to the brightness enhancing film of the invention. The backlit liquid crystal display can also include a light source 116 such as a fluorescent lamp and a white

reflector 120 also for reflecting light also toward the liquid crystal display panel. The brightness enhancing film 111 collimates light emitted from the light guide 118 thereby increasing the brightness of the liquid crystal display panel 114. The increased brightness enables a sharper image to be produced by the liquid crystal display panel and allows the power of the light source 116 to be reduced to produce a selected brightness. The backlit liquid crystal display is useful in equipment such as computer displays (laptop displays and computer monitors), televisions, video recorders, mobile communication devices, handheld devices (i.e. cellphone, personal digital assistant (PDA)), automobile and avionic instrument displays, and the like, represented by reference character 121.

The display may further include another optical film 112 positioned between the brightness enhancing film and the liquid crystal display panel 114. The other optical film may include for example a diffuser, a reflective polarizer, or a second brightness enhancing film. Other optical films may be positioned between optical film 112 and the liquid crystal display panel 114 or between the brightness enhancing film 111 and the light guide 118, as are known in the art.

Examples of polarizing films include those described in U.S. Pat. Nos. 5,825,543 and 5,783,120, each of which is incorporated herein by reference. The use of these polarizer films in combination with a brightness enhancing film has been described in U.S. Pat. No. 6,111,696. Another example of a polarizing film is described in U.S. Pat. No. 5,882,774. One example of such films that are available commercially are the multilayer films sold under the trade designation DBEF (Dual Brightness Enhancement Film) from 3M Company. Multilayer polarizing optical films have been described, for example in U.S. Pat. No. 5,828,488. If these additional optical films are included as the base layer of the brightness enhancing film, than the thickness of the base layer may be considerably greater than previously described.

The polymerizable composition described herein may be advantageous for other optical materials such as microstructure-bearing optical articles (e.g. films). Exemplary optical materials include optical lenses such as Fresnel lenses, optical films, such as high index of refraction films e.g., microreplicated films such as totally internal reflecting films, or brightness enhancing films, flat films, multilayer films, retroreflective sheeting, optical light fibers or tubes, and others. The production of optical products from high

index of refraction polymerizable compositions is described, for example, in U.S. Pat. No. 4,542,449.

Advantages of the invention are further illustrated by the following examples, but the particular materials and amounts thereof recited in the examples, as well as other conditions and details, should not be construed to unduly limit the invention. All percentages and ratios herein are by weight unless otherwise specified.

EXAMPLES

Test Methods

1. GAIN TEST METHOD

Gain, the difference in transmitted light intensity of an optical material compared to a standard material, was measured on a SpectraScan™ PR-650 SpectraColorimeter available from Photo Research, Inc, Chatsworth, CA. Results of this method for each example formed below are reported in the RESULTS section below. In order to measure the single sheet gain (i.e. "SS") film samples were cut and placed on a Teflon light cube that is illuminated via a light-pipe using a Foster DCR II light source such that the grooves of the prisms are normal to the front face of the Teflon light cube. For crossed sheet gain (i.e. "XS") a second sheet of the same material is placed underneath the first sheet and orientated such that the grooves of the second sheet are parallel to the front face of the Teflon light cube.

Polymerizable resin compositions can be prepared into brightness enhancing films using a master tool that had a 90° apex angles as defined by the slope of the sides of the prisms. In the first set of experiments, the mean distance between adjacent apices was about 24 micrometers and the apex of the prism vertices were sharp. In the second set of experiments, the mean distance between adjacent apices was about 50 micrometers and the apex of the prism vertices were rounded. The polymerizable resin compositions can be heated to a temperature of about 50°C and poured onto the master tool in a sufficient volume to create a continuous film. The master tool and polymerizable resin can be pulled through a coating bar device to create a thickness of polymerizable resin of approximately

13 microns in the first set of experiments and approximately 25 microns in the second set of experiments. After coating, a PET film is laminated onto polymerizable resin. The master tool, polymerizable resin, and PET film can be placed into UV curing machine and exposed at 3000 milijoules/cm². After curing, the polymerized resin and PET are peeled from the master tool.

In the first set of experiments, brightness enhancing films were prepared from polymerizable resin compositions 1-7 along with a control (i.e. Control 1 of Table I). In a second set of experiments brightness enhancing films were prepared from polymerizable resin composition 8 along with a control (i.e. Control 2 of Table II). For each set of experiments the control consisted of a mixture of 12.5 wt-% PEA, 37.5 wt-% BR-31, 30 wt-% RDX-51027, 20 wt-% EB-9220, and 1 pph Darocur 1173.

Table I as follows sets forth the amount of first monomer, kind and amount of monofunctional diluent (i.e. phenoxyethyl acrylate (PEA), benzyl acrylate) kind and amount of crosslinking agent (i.e. PETA, TMPTA) as well as the kind and amount of photoinitiators employed in the examples. The first monomer employed in the examples comprised at least about 60-70 wt-% of 2-propenoic acid, (1-methylethylidene)bis[(2,6-dibromo-4,1-phenylene)oxy(2-hydroxy-3,1-propanediyl)] ester. The second monomer employed in the examples was 2,4,6-tribromophenoxyethyl acrylate. The examples as well as the controls also each contained 0.3 wt-% surfactant, commercially available from 3M Company under the trade designation "FC-430". Each of Examples 1-8 also contained "Darocur 1173" photoinitiator added to the resin in an amount equal to 1% of the sum of the total of the other resin components.

Table I

Polymerizable Resin Composition	% First Monomer	% Second Monomer	% PEA	%PETA	SS Gain	XS Gain
Control 1					1.575	2.111
Example 1	32.7	40.5	13.5	13.0	1.582	2.118
Example 2	32.0	39.7	13.2	14.8	1.579	2.113
Example 3	31.3	38.8	13.0	16.6	1.574	2.104
Example 4	30.6	38.1	12.7	18.3	1.575	2.107
Example 6	30.0	37.4	12.4	19.9	1.575	2.111
Example 6	29.5	36.6	12.2	21.4	1.567	2.093
Example 7	28.9	35.8	12.0	23.0	1.563	2.085
Example 8	30.0	37.4	12.4	19.9 TMPTA	1.571	2.366
Control 2					1.571	2.367


The results show that all the exemplified polymerized compositions have suitable gain for use as brightness enhancing films. Surprisingly, some of the polymerizable compositions exhibit an even higher gain than the control.

5 The complete disclosures of the patents, patent documents, and publications cited herein are incorporated by reference in their entirety as if each were individually incorporated. Various modifications and alterations to this invention will become apparent to those skilled in the art without departing from the scope and spirit of this invention. It should be understood that this invention is not intended to be unduly limited
10 by the illustrative embodiments and examples set forth herein and that such examples and embodiments are presented by way of example only with the scope of the invention intended to be limited only by the claims set forth herein as follows.

What is claimed is:


1. A brightness enhancing film comprising the reaction product of a polymerizable composition consisting essentially of:

- 5 a) one or more first monomers selected from the group consisting of
 i) a monomer comprising a major portion having the structure



wherein R1 is independently hydrogen or methyl; and

- 10 ii) a monomer comprising a major portion having the structure



- 15 wherein R1 is independently hydrogen or methyl, and
 L is a linking group independently selected from the group consisting of
 linear C₂-C₁₂ alkyl groups,
 branched C₂-C₁₂ alkyl groups and
 -CH₂CH(OH)CH₂-;

20

and mixtures thereof;

b) a second monomer consisting of 2,4,6-tribromophenoxyethyl (meth)acrylate;

c) a crosslinking agent selected from the group consisting of pentaerythritol tri(meth)acrylate, pentaerythritol tetra(meth)acrylate, trimethylolpropane tri(meth)acrylate, and mixtures thereof;

d) optionally a monofunctional diluent; and

e) optionally a photoinitiator.

2. The brightness enhancing film of claim 1 wherein the first monomer is present in the polymerizable composition in an amount of at least about 20 wt-%.

3. The brightness enhancing film of claim 1 wherein the first monomer is present in the polymerizable composition in an amount less than about 40 wt-%.

4. The brightness enhancing film of claim 1 wherein the first monomer comprises a major portion of 2-propenoic acid, (1-methylethylidene)bis[(2,6-dibromo-4,1-phenylene)oxy(2-hydroxy-3,1-propanediyl)] ester.

5. The brightness enhancing film of claim 1 wherein the 2,4,6-tribromophenoxyethyl (meth)acrylate is present in an amount of at least about 25 wt-%.

6. The brightness enhancing film of claim 1 wherein the 2,4,6-tribromophenoxyethyl (meth)acrylate is present in an amount less than about 50 wt-%.

7. The brightness enhancing film of claim 1 wherein the crosslinking agent is a liquid at ambient temperature.

8. The brightness enhancing film of claim 1 wherein the crosslinking agent is present in the polymerizable composition in an amount ranging from about 5 wt-% to about 30 wt-%.

9. The brightness enhancing film of claim 1 wherein the crosslinking agent is pentaerythritol triacrylate.

10. The brightness enhancing film of claim 1 wherein the monofunctional diluent is present in the polymerizable composition in an amount ranging from about 10 wt-% to about 20 wt-%.

5

11. The brightness enhancing film of claim 1 wherein the monofunctional (meth) acrylate diluent is a liquid at ambient temperature.

10

12. The brightness enhancing film of claim 11 wherein the monofunctional (meth)acrylate diluent comprises phenoxyethyl (meth)acrylate, benzyl (meth)acrylate, and mixtures thereof.

15

13. The brightness enhancing film of claim 11 wherein the monofunctional (meth)acrylate diluent comprises phenoxyethyl acrylate.

14. An article comprising the brightness enhancing film of claim 1 and a second optical film in contact with the brightness enhancing film.

20

15. The article of claim 14 wherein the second optical film is a diffuser.

16. The article of claim 14 wherein the second optical film is an absorbing polarizer.

17. The article of claim 14 wherein the second optical film is a reflective polarizer.


25

18. The article of claim 14 wherein the second optical film comprises a prismatic structure.

30


19. A polymerizable resin composition comprising comprising the reaction product of a polymerizable composition consisting essentially of:

- a) one or more first monomers selected from the group consisting of
 - i) a monomer comprising a major portion having the structure



wherein R1 is independently hydrogen or methyl; and

ii) a monomer comprising a major portion having the structure



wherein R1 is independently hydrogen or methyl, and

L is a linking group selected from the group consisting of

linear C₂-C₁₂ alkyl groups,

branched C₂-C₁₂ alkyl groups and

-CH₂CH(OH)CH₂-;

and mixtures thereof;

b) a second monomer consisting of 2,4,6-tribromophenoxyethyl (meth)acrylate;

c) a crosslinking agent selected from the group consisting of pentaerythritol tri(meth)acrylate, pentaerythritol tetra(meth)acrylate, trimethylolpropane tri(meth)acrylate, and mixtures thereof;

- d) optionally a monofunctional diluent; and
- e) optionally a photoinitiator.

20. An optical material comprising the reaction product of claim 19.

5

21. The optical material of claim 20 wherein the material is a film.

22. The optical material of claim 21 wherein the film comprises a microstructured surface.

10

15




Fig. 1




Fig. 2

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US2004/041553

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08F220/00 G02B1/00 C08F2/02 C08F2/06

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08F G02B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 5 908 874 A (FONG ET AL) 1 June 1999 (1999-06-01) the whole document	1-22
Y	EP 1 014 113 A (DSM N.V; JSR CORPORATION; JAPAN FINE COATINGS CO., LTD) 28 June 2000 (2000-06-28) the whole document	1-22
Y	WO 03/076528 A (DSM N.V; TAKASE, HIDEAKI; TAKAHASHI, ATSUYA; TANABE, TAKAYOSHI; ITAI,) 18 September 2003 (2003-09-18) the whole document	1-22

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *G* document member of the same patent family

Date of the actual completion of the international search

22 April 2005

Date of mailing of the international search report

02/05/2005

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Trauner, H-G

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US2004/041553

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5908874	A	01-06-1999	AU 7455296 A WO 9748733 A1	07-01-1998 24-12-1997
EP 1014113	A	28-06-2000	EP 1014113 A2 JP 2000239333 A KR 2000048286 A TW 546349 B	28-06-2000 05-09-2000 25-07-2000 11-08-2003
WO 03076528	A	18-09-2003	JP 2003261645 A AU 2003219612 A1 EP 1495078 A2 WO 03076528 A2 JP 2004051941 A	19-09-2003 22-09-2003 12-01-2005 18-09-2003 19-02-2004