




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : G11B 3/70	A1	(11) International Publication Number: WO 99/05672 (43) International Publication Date: 4 February 1999 (04.02.99)
(21) International Application Number: PCT/US98/09900 (22) International Filing Date: 22 May 1998 (22.05.98) (30) Priority Data: 60/053,473 23 July 1997 (23.07.97) US (71) Applicant (for all designated States except US): SEAGATE TECHNOLOGY, INC. [US/US]; 920 Disc Drive, Scotts Valley, CA 95066 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): BOUTAGHOU, Zine-Eddine [US/US]; 307 Lily Pond Lane, Vadnais, MN 55127 (US). HIPWELL, Mary, C. [US/US]; 4214 Queen Avenue S. #1, Minneapolis, MN 55410 (US). (74) Agent: RITTMASER, Ted, R.; Merchant, Gould, Smith, Edell, Welter & Schmidt, Suite 400, 11150 Santa Monica Boulevard, Los Angeles, CA 90025-3395 (US).		(81) Designated States: DE, DE (Utility model), GB, JP, KR, SG, US. Published <i>With international search report.</i>

(54) Title: DISK DRIVE SYSTEM, PROCESS AND COMPONENTS THEREOF FOR IMPROVED DISK STIFFNESS

**(57) Abstract**

A disk drive system includes a disk (20) having a stiffening structure for improved vibration resistance. The stiffening structure is configured to improve stiffness and vibration resistance with respect to the (0,1), (0,2) and (1,1) vibration modes. The stiffening structure includes a rib-stiffening structure composed of a framework of interconnected ribs. The framework (28) includes a plurality of concentric annular ribs (30-35) and a plurality of radially spaced, radial ribs (35-43). One or more annular ribs are disposed at one or more locations along the radial dimension of the disk at which nodes of annular vibrations occur. Also, one or more radial ribs are disposed at one or more locations around annular dimension of the disk at which nodes of radial vibrations occur. The stiffening structure is disposed within a substrate layer (22) of the disk during manufacturing of the disk structure.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakistan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

DISK DRIVE SYSTEM, PROCESS AND COMPONENTS THEREOF FOR IMPROVED DISK STIFFNESS

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates, generally, to disk drive systems, data storage disks and processes of making and using the same with improved vibration inhibiting capabilities and, in preferred embodiments, to such systems, disks and processes
5 which employ a stiffening structure, such as a framework of ribs, disposed within the disk.

2. Back Ground

Modern computers employ various forms of storage systems for storing
10 programs and data. For example, various forms of disk drive systems have been designed to operate under the control of a computer to record information and/or retrieve recorded information on one or more recording disks. Such disk drives include hard disk drives which employ recording disks that have magnetizable (hard)
15 recording material, optical disk drives which employ recording disks that have optically readable recording material, mageneto-optical (MO) disk drives which employ recording disks that have optically readable magenetizable recording material, or the like.

Conventional disk drive systems typically include one or more recording disks supported for relatively high speed rotation on a rotary spindle. For example, Fig. 1a
20 shows a side view of portions of a conventional disk drive system, including a conventional data storage or recording disk 10 supported on a spindle 11. A disk drive motor (not shown) is operatively coupled to the spindle 11 for rotation of the spindle and the disk supported thereon. A recording and/or reading head 12 is supported by suitable head support structure (not shown) adjacent the recording
25 surface of the disk. To simplify the disclosure, Fig. 1 is shown with a single recording disk 10 having a single recording surface and a single head 12. However, other conventional disk drive systems employ multiple disks, double-sided disks (disks with recording surfaces on both surfaces) and multiple heads.

For purposes of illustration, the disk 10 is described herein as an MO disk. As
30 shown in Fig. 1a, the disk 10 has a central hub opening through which the spindle 11 extends, and is formed with multiple layers, including at least one substrate or support layer 14, a recording layer 15 supported on the substrate layer 14 and at least one protective layer 16 on the recording layer. Further layers, such as one or more layers

of dielectric material, may also be included in the layered disk structure, for example, between the protective layer and the recording layer.

The disk 10 and spindle 11 are shown in a top view in Fig. 1b. The spindle 11 extends through a central opening, which defines an inside diameter, of the disk. The disk is secured at its inner diameter (ID), in a fixed relation with the spindle 11, and is supported such that the outer diameter (OD) portion of the disk is free from contact with other components. In this regard, the disk is clamped at its ID to the spindle 11 and is free at its OD. When the spindle 11 is rotatably driven, the disk 10 is caused to rotate with the spindle.

The head 12 is supported for movement in the radial direction of the disk, such that the head may be selectively positioned adjacent any recording location on the recording surface of the disk, as the disk is rotated. In operation, the head 12 is moved in the radial direction to align or register with a desired track location on the recording surface of the disk. Once aligned or registered with the desired track location, the head is operated to read or write information onto the recording surface at the desired track location. It is important to properly register the head with the track location to effect accurate reading or writing operations on the registered track.

Modern advances in disk drive technology have resulted in increased disk storage density and decreased track widths, such that greater amounts of information may be stored per given recording surface area. However, as track widths decrease (and storage density increases), the need for accurate head registration increases. In general, smaller track widths require greater head-to-track registration accuracies and have smaller alignment error tolerances. For example, for a disk with 10,000 tracks per inch, the track width is only about 100 μin and the total allowable (tolerable) off-track mis-registration may be no more than about 10 μin peak-to-peak.

Track mis-registration (TMR) may result from a variety of sources, including, for example, ball bearing non-repeatable run out, spindle-disk rocking vibrations and disk flutter. However, with recent and up-coming advances in disk drive spindle motor technology (including the introduction of hydrodynamic bearing spindle motors), the asynchronous vibrations caused by ball bearing non-repeatable run out and spindle-disk rocking vibration can be dramatically reduced. As a result, disk flutter can be a substantial factor in the cause of TMR.

Disk flutter can be generally characterized as the vibrations encountered by a disk, for example, as a result of fixing and supporting the disk only at its inside diameter to a rotary spindle. During rotation of the disk, the disk tends to vibrate in several modes.

For a given disk inner diameter (ID) to outer diameter (OD) ratio (ID/OD), the natural frequency of a disk is proportional to:

$$\frac{h}{R^2} \sqrt{\frac{E}{\rho(1-\nu^2)}} \quad (1)$$

where h is disk thickness, R is disk outer radius, E is Young's modulus, ρ is density and ν is Poisson ratio. The vibration amplitude per unit force is proportional to:

$$\frac{R^4}{\eta D} \quad (2)$$

where η is disk material loss coefficient and D is disk rigidity and is defined by:

$$D = \frac{Eh^3}{12(1-\nu^2)} \quad (3)$$

Disk vibrations may occur in several modes, depending on the input excitation frequency. Various vibration mode shapes for a disk having its ID clamped and OD free are represented by the top and side view diagrams of Figs. 2a, 2b, 2c and 2d. The upper part of each of those figures shows a top view of a disk, with a shaded region indicating the nodal line(s) between vibration nodes. The bottom part of each of Figs. 2a-2d shows a side-view representation of the vibration wave-shape of the corresponding vibration mode. A (m,n) mode represents the m and n nodal lines in the circumferential and radial directions, respectively. Thus, Fig. 2a represents a (0,0) mode vibration. Fig. 2b represents a (1,0) mode vibration. Fig. 2c represents a (0,1) mode vibration and Fig. 2d represents a (0,2) mode vibration.

Disk flutter may include one or more of the various vibration modes shown in Figs. 2a-2b. MO media are particularly susceptible to the high amplitude of the (0,1), (0,2) and (1,1) vibration modes. These modes can greatly affect servo performance, since most servo systems have a limited bandwidth and rely on low amplitudes of the disk bending modes. Current MO media designs typically require a substantial increase in the disk thickness to reduce the amplitude of the above mentioned modes.

SUMMARY OF THE DISCLOSURE

Accordingly, it is an object of preferred embodiments of the present invention to provide a drive system, disk and process for inhibiting disk vibration during disk reading and/or writing operations.

5 It is a further object of preferred embodiments of the present invention to provide such a system, disk and process which is economical and which may be readily incorporated in disk manufacturing techniques.

10 It is a further object of preferred embodiments of the present invention to provide such a system, disk and process which does not require substantial increases in disk thickness.

In accordance with preferred embodiments of the present invention, a disk is provided with a stiffening structure, for increasing the stiffness of the disk for improved vibration resistance. In more preferred embodiments, the stiffening structure is configured to improve stiffness and vibration resistance with respect to the
15 (0,1), (0,2) and (1,1) vibration modes.

In accordance with one preferred embodiment, the stiffening structure comprises a framework of interconnected ribs. In accordance with more preferred embodiments, the framework of interconnected ribs comprises at least one annular rib (and more preferably, a plurality of concentric annular ribs) and at least one radial rib
20 (and more preferably, a plurality of radially spaced, radial ribs). In accordance with yet further preferred embodiments, one or more annular ribs are disposed at one or more locations along the radial dimension of the disk at which nodes of annular vibrations occur. Also in accordance with such further preferred embodiments, one or more radial ribs are disposed at one or more locations around annular dimension of
25 the disk at which nodes of radial vibrations occur.

A rib-stiffening structure, according to preferred embodiments, is incorporated in the substrate layer of a disk, during manufacture of the disk. The rib stiffening structure may be included within the mold for the disk substrate, during the molding of the disk substrate. In this manner, the rib stiffening structure may be molded into
30 the substrate portion of the disk. Alternatively, the rib stiffening structure may be included within another layer of a multi-layer disk structure or may be provided between layers of the disk structure. By designing the rib pattern of the rib stiffening structure to match shapes of the (0,1), (1,1), (0,2), etc. vibration modes, the rib stiffening structure can substantially reduce the amplitudes of vibrations in these
35 modes, but preferably, does not affect the micro-waviness of the disk media.

BRIEF DESCRIPTION OF THE DRAWINGS

A detailed description of preferred embodiments of the invention will be made with reference to the accompanying drawings, wherein like numerals designate corresponding parts in the several figures.

5 Fig. 1a is a side view of portions of a conventional disk drive system and MO disk.

Fig. 1b is a top view of the MO disk and spindle of the system shown in Fig. 1a.

10 Figs. 2a-2d show top and side view representations of the shapes of (0,0), (1,0), (0,1) and (02) mode vibrations for ID clamped, OD free disks.

Fig. 3a is a side view of a single sided MO disk according to an embodiment of the present invention.

Fig. 3b is a side view of a double sided MO disk according to an embodiment of the present invention.

15 Fig. 4 is a top view of a stiffening structure according to an embodiment of the present invention.

Fig. 5 is a top view of a stiffening structure according to a further embodiment of the present invention.

20 DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

The following detailed description is of the best presently contemplated mode of implementing the invention. This description is not to be taken in a limiting sense, but is made merely for the purpose of illustrating the general principles of the invention. The scope of the invention is best defined by the appended claims.

25 The present invention relates, generally, to disk drive systems, data storage disks and processes of making and using the same with improved vibration inhibiting capabilities and, in preferred embodiments, to such systems, disks and processes which employ a stiffening structure, such as a framework of ribs, disposed within the disk.

30 A side view of a single-sided data storage disk 20 in accordance with a preferred embodiment of the present invention is shown, generally, in Fig. 3a. The disk 20 may be included in a disk drive system in the same manner that disk 10 is shown in such a system in Fig. 1a. Similar to the general structure of the conventional disk 10 of Fig. 1a, the disk 20 includes a center hub opening through which a spindle 35 11 extends, a substrate portion 22, a layer of recording material 24 and one or more protective, dielectric and/or other layers 26.

The embodiment shown in Fig. 3a is a single-sided disk embodiment, wherein the recording material layer is exposed for reading and/or recording of information through only one disk surface (the upward-facing surface in Fig. 3a). However, further embodiments comprise double-sided disks, wherein reading and/or recording of information may occur through both disk surfaces. An example of a double-sided disk embodiment is shown in Fig. 3b, wherein a second layer of recording material 24' and one or more second protective, dielectric and/or other layers 26' are provided on the opposite face of the substrate layer 22 (the downward-directed face in Fig. 3b), with respect to the face on which the first layers 24 and 26 are provided.

In accordance with preferred embodiments of the present invention, the disk is provided with a stiffening structure, for increasing the stiffness of the disk, for improved vibration resistance. In more preferred embodiments, the stiffening structure is configured to improve stiffness and vibration resistance with respect to the (0,1), (0,2) and (1,1) vibration modes. For example, Figs. 3a and 3b show embodiments in which a rib-stiffening structure 28 is disposed within the substrate portion.

In accordance with one preferred embodiment, the stiffening structure comprises a rib-stiffening structure composed of a framework of interconnected ribs. In accordance with more preferred embodiments, the framework of interconnected ribs comprises at least one annular rib (and more preferably, a plurality of concentric annular ribs) and at least one radial rib (and more preferably, a plurality of radially spaced, radial ribs). In accordance with yet further preferred embodiments, one or more annular ribs are disposed at one or more locations along the radial dimension of the disk at which nodes of annular vibrations occur. Also in accordance with such further preferred embodiments, one or more radial ribs are disposed at one or more locations around annular dimension of the disk at which nodes of radial vibrations occur. In this regard, the framework of interconnected ribs is preferably constructed with a predetermined pattern, designed to reduce the amplitude of (0,1), (0,2) and (1,1) mode vibrations.

A first embodiment of a rib pattern for a framework structure 28 is shown in Fig. 4 and includes a plurality of concentric ring-shaped or annular ribs which are interconnected by a plurality of radially disposed ribs. The Fig. 4 embodiment, includes six concentric, annular ribs 30, 31, 32, 33, 34 and 35 of mutually different diameters, and eight radial ribs 36, 37, 38, 39, 40, 41, 42 and 43. However, other embodiments may include more or less than six concentric, annular ribs and/or more or less than eight radial ribs.

In preferred embodiments, each annular rib is located at a node location of an annular vibration wave-shape. Thus, with respect to a single annular vibration wave-shape shown in Fig. 2b, an annular rib is preferably located at the radial position at which the annular vibration wave crosses the horizontal axis (shown as the lower
5 portion of Fig. 2b). As a disk is likely to encounter multiple annular vibration waves, preferred stiffening structure embodiments employ a plurality of annular ribs located at a plurality of disk radii corresponding to the radii at which the nodes of the plural annular vibration wave-shapes are likely to occur.

The ribs are formed of a suitably rigid material, including, but not limited to,
10 metal, ceramic, reinforced laminate, glass, hard plastic, polycarbonate, or the like. The stiffness of the rib material and the arrangement of the ribs in the frame-work pattern are preferably selected to optimize the vibration suppression characteristics of the frame-work. The annular ribs help suppress vibrations having annular node components. The radial ribs help suppress vibrations having radial node components.
15 The connections of the radial ribs with the annular ribs provides a unitary frame-work structure.

In the Fig. 4 embodiment, the plurality of concentric, annular ribs includes an inner annular rib 30 having a diameter at least as large as (and preferably slightly larger than) the outer diameter of the central hub opening 21 of the disk 20 (Fig. 2).
20 The plurality of concentric, annular ribs also includes an outer annular rib 35 having a diameter up to (and preferably slightly less than) the overall diameter of the disk 20. The further concentric, annular ribs 31-34 have diameters between the diameter of the inner rib 30 and the diameter of the outer rib 35 and are spaced between the inner and outer ribs.

25 Each of the radial ribs 36-43 in the Fig. 3 embodiment extends from the inner annular rib 30 to the outer annular rib 35 and is connected to each of the annular ribs 30-35. The radial ribs 36-43 are equally spaced with respect to the circumference of the frame-work and disk.

While a structure as shown in Fig. 4 can provide a generally uniform stiffening
30 resistance to annular and radial vibrations over the entire disk diameter, it has been found that vibration amplitudes tend to be greater at the outer radial dimensions of the disk. Accordingly, further preferred embodiments employ a frame-work of ribs designed to increase stiffness and provide greater resistance to vibrations at the outer disk dimensions than at the inner disk dimensions. For example, Fig. 5 shows a
35 pattern for a framework structure 26 according to a further embodiment designed to enhance disk stiffness at the outer disk dimensions.

The framework shown in Fig. 5 includes a plurality of concentric, annular ribs and a plurality of radial ribs connected with the annular ribs. The concentric, annular ribs in the Fig. 5 embodiment include an inner annular rib 44 and three outer annular ribs 45, 46 and 47 having greater diameters than the inner rib 44. The three outer
5 annular ribs are of mutually different diameters, such that one outer annular rib 45 defines a smaller diameter than the other outer annular ribs, and a further outer annular rib 47 defines a larger diameter than the other outer annular ribs. While the illustrated embodiment includes one inner annular rib 44 and three outer annular ribs 45-47, it will be understood that further embodiments may employ more than one
10 inner annular rib and more or less than three outer annular ribs.

The plurality of radial ribs in the Fig. 5 embodiment includes a first plurality of radial ribs, each of which extend from the smallest diameter outer annular rib 45 to the largest diameter outer annular rib 47. The plurality of radial ribs also includes a second plurality of radial ribs, each of which extend from the inner annular rib 44 to
15 the largest diameter outer annular rib 47. For purposes of simplifying the drawing, the ribs in the first plurality of radial ribs are identified by the common reference character 48 and the ribs in the second plurality of radial ribs are identified by the common reference character 49.

According to one preferred embodiment, a suitable stiffening structure, such as
20 described above, is disposed in the substrate portion 22, during manufacture of the disk 20. The disk 20 may be manufactured by forming an annular, disk-shaped substrate layer from a molded substrate material, for example, but not limited to plastic, glass, or the like.

As part of the molding step, a suitable substrate material is received in a
25 suitably shaped mold. For example, the substrate material may be provided in liquid phase and poured or otherwise communicated into the mold. In addition, a pre-formed stiffening structure, such as a framework of ribs as described above, is also disposed within the mold. The liquid phase substrate material is then solidified (for example, by reducing the material temperature, curing the material or otherwise
30 causing the material to transition from a liquid phase to a solid phase) with the stiffening structure disposed therein.

Once the substrate with the stiffening structure therein is formed, a layer 24 of suitable recording material is formed on at least one surface of the substrate. Various recording materials and processes for forming recording materials on substrate
35 surfaces are well known in the art. In addition, further layers, such as one or more dielectric layer, one or more protective layer or the like are formed on the recording

material and substrate layers, in accordance with well known procedures for forming such layers.

In embodiment in which the stiffening structure is composed of a framework of ribs, such as described above, the framework structure may be formed as a unitary, integral structure, by suitable molding techniques. In further embodiments, the annular and radial ribs may be formed as separate elements by suitable manufacturing techniques (including, but not limited to, molding, extrusion, cutting, stamping or the like) and then interconnected (for example, but not limited to, by adhesives, solder or other molten connecting material, or the like) to form a unitary framework structure.

While preferred embodiments of the present invention are described above with reference to MO disks and MO disk drive systems and processes, other embodiments apply to other forms of recording disks, including but not limited to magnetic recording disks, compact disks (CDs), other forms of optical disks, or the like. Also, it is recognized that certain disk materials, such as plastics, are more susceptible to high amplitude vibrations than other disk materials, such as glass or aluminum and, thus, may benefit more from the present invention than glass or aluminum disks. However, disks formed of even the stiffer materials, such as glass or aluminum, can benefit from further stiffening structures, particularly as track widths decrease and alignment tolerances decrease. Accordingly, while preferred embodiments of the present invention employ plastic disk substrates, other embodiments employ substrates formed of other materials including, but not limited to glass, aluminum, silicon, or the like.

Furthermore, while embodiments discussed above show a stiffening structure disposed within a substrate layer, other embodiments may employ a stiffening structure disposed in other layers of the disk structure, for example, in one or more of the layers 24 and 26, or between layers of the disk structure. If the stiffening structure is disposed in a layer between a disk surface through which reading and/or recording occurs and the recording layer, then the stiffening structure may be either composed of a material which is substantially transparent to the reading and/or writing radiation. Alternatively, the stiffening structure may be configured to expose a substantial portion of the recording layer track locations (for example, between ribs of the framework).

The presently disclosed embodiments are to be considered in all respects as illustrative and not restrictive, the scope of the invention being indicated by the appended claims, rather than the foregoing description, and all changes which come within the meaning and range of equivalency of the claims are therefore intended to be embraced therein.

WHAT IS CLAIMED IS:

1. A recording disk comprising:
a recording material supported on a substrate; and
5 means for minimizing vibration amplitudes during operation.
2. A recording disk comprising:
a substrate layer;
at least one layer of recording material supported on the substrate layer;
10 a stiffening structure fixed with respect to the substrate layer.
3. A recording disk as recited in claim 2, wherein said stiffening structure
is disposed within the substrate layer.
- 15 4. A recording disk as recited in claim 2, wherein said stiffening structure
comprises a framework of ribs.
5. A recording disk as recited in claim 2, wherein said stiffening structure
comprises a plurality of concentric, annular ribs and a plurality of radial ribs.
20
6. A recording disk as recited in claim 2, wherein said stiffening structure
comprises a framework composed of:
a plurality of concentric, annular ribs; and
a plurality of radial ribs, wherein each radial rib is connected with at least one
25 annular rib.
7. A recording disk as recited in claim 2, wherein said stiffening structure
comprises a framework composed of:
a plurality of concentric, annular ribs; and
30 a plurality of radial ribs, wherein each radial rib is connected with each
annular rib.
8. A recording disk as recited in claim 2, wherein said stiffening structure
comprises a unitary structure composed of a plurality of concentric, annular ribs and a
35 plurality of radial ribs.

9. A recording disk as recited in claim 2, wherein said stiffening structure comprises a framework composed of:

at least one inner annular rib;

5 a plurality of outer annular ribs of greater diameter than said at least one inner annular rib and arranged concentric with each other and with said at least one inner annular rib;

at least one radial rib connected to said plurality of outer annular ribs and free of direct connection with said at least one inner annular rib; and

10 at least one radial rib connected to at least one inner annular rib and at least one outer annular rib.

10. A recording disk as recited in claim 2, wherein said stiffening structure comprises a framework composed of:

at least one inner annular rib;

15 a plurality of outer annular ribs of greater diameter than said at least one inner annular rib and arranged concentric with each other and with said at least one inner annular rib;

a first plurality of radial ribs connected to said plurality of outer annular ribs and free of direct connection with said at least one inner annular rib; and

20 a second plurality of radial ribs connected to at least one inner annular rib and said plurality of outer annular ribs.

11. A recording disk as recited in claim 2, wherein said stiffening structure comprises a framework composed of:

25 a plurality of concentric, annular ribs, at least one of said annular ribs disposed at a radii of said disk corresponding to a predetermined likely radial position of a node of an annular vibration wave-shape.

12. A recording disk as recited in claim 11, wherein said stiffening structure further comprises a plurality of radial ribs, wherein each radial rib is
30 connected with at least one of said annular ribs.

13. A disk drive system comprising:
a recording disk having a central hub, a substrate layer extending radially out from the central hub, at least one layer of recording material supported on the substrate layer and a stiffening structure fixed with respect to the substrate layer;
- 5 a rotatable spindle defining a rotation axis, wherein said spindle is coupled to said central hub of said disk for imparting rotary motion to said disk; and
a driver for rotatably driving the spindle and disk about the rotation axis of said spindle.
- 10 14. A disk drive system as recited in claim 13, wherein, upon rotatably driving said disk about the rotation axis, annular and radial vibration forces are imparted on the disk and wherein said stiffening structure is configured to inhibit annular and radial disk vibrations.
- 15 15. A recording disk as recited in claim 13, wherein, upon rotatably driving said disk about the rotation axis, annular and radial vibration forces in at least the (1,0), (0,1) and (0,2) modes are imparted on the disk and define vibration nodes at locations along the disk dimensions, and wherein said stiffening structure comprises a plurality of concentric, annular ribs and a plurality of radial ribs disposed at said
20 vibration node locations.
16. A recording disk as recited in claim 13, wherein said stiffening structure is disposed within the substrate layer.
- 25 17. A recording disk as recited in claim 13, wherein said stiffening structure comprises a framework of ribs.
18. A recording disk as recited in claim 13, wherein said stiffening structure comprises a framework composed of:
30 a plurality of concentric, annular ribs; and
a plurality of radial ribs, wherein each radial rib is connected with at least one annular rib.

19. A recording disk as recited in claim 13, wherein said stiffening structure comprises a framework composed of:

at least one inner annular rib;

5 a plurality of outer annular ribs of greater diameter than said at least one inner annular rib and arranged concentric with each other and with said at least one inner annular rib;

at least one radial rib connected to said plurality of outer annular ribs and free of direct connection with said at least one inner annular rib; and

10 at least one radial rib connected to at least one inner annular rib and at least one outer annular rib.

20. A recording disk as recited in claim 13, wherein said stiffening structure comprises a framework composed of:

at least one inner annular rib;

15 a plurality of outer annular ribs of greater diameter than said at least one inner annular rib and arranged concentric with each other and with said at least one inner annular rib;

a first plurality of radial ribs connected to said plurality of outer annular ribs and free of direct connection with said at least one inner annular rib; and

20 a second plurality of radial ribs connected to at least one inner annular rib and said plurality of outer annular ribs.

1/4




FIG. 1a






FIG. 1b


2/4




(0,0) mode
FIG. 2a



(1,0) mode
FIG. 2b



(0,1) mode
FIG. 2c



(0,2) mode
FIG. 2d




FIG. 3a




FIG. 3b

4/4

FIG. 4





FIG. 5



INTERNATIONAL SEARCH REPORT

International application No.

PCT/US98/09900

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) : G11B 3/70

US CL : 369/272

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 369/272, 277, 283; 360/98.01-98.08

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

APS, search terms: disk, disc, vibration, minimize, reduce

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5,422,776 A (THORSON et al) 6 June 1995, figure 2	1-20
X	US 4,674,356 A (KILGORE) 23 June 1987, figure 2	1-20
X	US 4,622,661 A (HOOGEVEEN et al) 11 November 1986, figures 1-3	1-20
A	US 3,838,464 A (DOYLE) 24 September 1974, figures 2 and 3	1-20
A	US 3,912,282 A (SANO et al) 14 October 1975, column 2, lines 47-64	1-20



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"E" earlier document published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&" document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means	
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

15 SEPTEMBER 1998

Date of mailing of the international search report

21 OCT 1998

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No.

Authorized officer

ALLEN CAO

Telephone No. (703) 305-3796