

⑩



Europäisches Patentamt
European Patent Office
Office européen des brevets

⑪ Publication number:

**0 072 645
B1**

⑫

EUROPEAN PATENT SPECIFICATION

④⑤ Date of publication of patent specification: **07.01.87**

⑤① Int. Cl.⁴: **C 07 D 207/40,
C 10 M 133/16**

⑦① Application number: **82304066.2**

⑦② Date of filing: **02.08.82**

⑤④ **Improved succinimide lubricating oil dispersant.**

③⑥ Priority: **17.08.81 US 293146**

④③ Date of publication of application:
23.02.83 Bulletin 83/08

④⑤ Publication of the grant of the patent:
07.01.87 Bulletin 87/02

⑧④ Designated Contracting States:
DE FR GB IT

⑤⑥ References cited:
**GB-A-1 162 436
US-A-3 415 750
US-A-3 639 242**

⑦③ Proprietor: **Exxon Research and Engineering
Company
P.O.Box 390 180 Park Avenue
Florham Park New Jersey 07932 (US)**

⑦② Inventor: **Wisotsky, Max Jay
54 North 7th Avenue
Highland Park New Jersey (US)
Inventor: Bloch, Ricardo Alfredo
1532 Ashbrook Drive
Scotch Plains New Jersey (US)
Inventor: Brownawell, Darrell William
320 Roberts Lane
Scotch Plains New Jersey (US)
Inventor: Chen, Frank Joung-yei
18 Thornton Lane
Piscataway New Jersey (US)
Inventor: Gutierrez, Antonio
22 Tar Heels Road
Mercerville New Jersey (US)**

⑦④ Representative: **Bawden, Peter Charles et al
ESSO CHEMICAL LIMITED
Esso Chemical Research Centre
PO Box 1
Abingdon Oxfordshire OX13 6BB (GB)**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European patent convention).

Courier Press, Leamington Spa, England.

EP 0 072 645 B1

Description

This invention relates to lubricating oil dispersants which exhibit highly effective dispersant potency in both gasoline and diesel engines. More particularly, the invention relates to lubricating oil compositions for use both in gasoline and diesel engine formulations which meet current performance requirements for both types of engines, the formulations being characterized as containing novel dispersants prepared in a particular reaction sequence.

A current objective in the industry is to provide lubricating oil compositions which meet or exceed engine qualification standards of dispersancy for both gasoline and diesel or compression ignition engines. Heretofore, dispersants have been developed which meet one or the other of these requirements, but development of a dispersant which satisfies the highest service classification requirements of the relevant engine qualification tests for both types of oils has not been entirely successful. It is an object of the present invention to provide lubricating oil compositions containing novel dispersants which meet these goals.

The present invention is within the broad field of improved polyolefin, particularly polyisobutenyl, succinic acid or anhydride-polyamine reaction product dispersants, and such dispersants are disclosed generally, for example, in U.S. Patent 3,172,892 issued March 9, 1965 to LeSuer et al.

U.S. Patent 3,216,936 issued November 9, 1965 to LeSuer shows lubricating oil additives prepared by acylation of an alkylene amine with both a polyolefin succinic anhydride and an aliphatic monocarboxylic acid, preferably a mono acid having more than 12 carbon atoms such as stearic or oleic acid. The products can be prepared by reacting both acidic compounds simultaneously with a polyamine or by first reacting the polyolefin succinic acid with polyamine and subsequently with monocarboxylic acid. The products so formed are said to be particularly useful in improving the thermal stability of lubricating compositions which contain metal phosphorodithioates.

British Patent 1,018,982 (1966) discloses lubricating oil additives which are the reaction products of three components: alkenyl succinic anhydrides, polyamines and carboxylic acids and the products are said to have improved sludge dispersant properties. The alkenyl succinic anhydrides are those similar to the materials of the present invention, i.e., preferably polyisobutenyl succinic anhydrides and the polyamines are also similar, i.e., the alkylene polyamines. The carboxylic acids of this reference are disclosed as being mono- or di-carboxylic acids having 1 to 30, preferably 1 to 18 carbon atoms, with acetic acid being preferred since it forms an imidazoline or pyrimidine with a minimum of carbon atoms. This reference also states that lower molecular weight carboxylic acids are more effective in

promoting the sludge dispersing activity of the final product. The preparative method disclosed in British Patent 1,018,982 comprises either first reacting the carboxylic acid and the polyamine in what is described as an imidazoline or pyrimidine forming reaction with subsequent reaction with alkenyl succinic anhydride or by reacting the three materials simultaneously.

U.S. Patent 3,415,750 issued December 10, 1968 to Anzenberger discloses lubricant additives categorized as imidazolines which are prepared by reacting a polyethylene polyamine with a mono-carboxylic acid or a dicarboxylic acid to form a heterocyclic imidazoline intermediate which is subsequently reacted with a polyalkenyl succinic anhydride to provide a bis-imidazoline which is said to have improved detergency and dispersancy in lubricating oil formulations.

U.S. Patent 3,374,174 issued March 19, 1968 to LeSuer discloses lubricant additives prepared by reacting amines, including alkylene polyamines, with both a high molecular weight saturated monocarboxylic acid and a dicarboxylic acid or anhydride, preferably those having up to 12 carbons. The patent discloses the simultaneous reaction of all three materials or a sequential process whereby there is first formed an acylated amine intermediate with the amine and high molecular weight carboxylic acid which is subsequently reacted with the dicarboxylic acid reactant.

U.S. 4,173,540 discloses the reaction of polyisobutenyl succinic anhydride with polyamines in a molar ratio of 2.0 to 2.5 moles of anhydride per mole of polyamine to provide a diimide dispersant, however, such products will not meet the requirements for both gasoline and diesel engine formulations.

U.S. 3,401,118 discloses reacting tetraethylene pentamine first with polyisobutenyl succinic anhydride (PIBSA) derived from 850—1200 Mn polyisobutylene and then reacting this intermediate with PIBSA derived from polyisobutylene of 400—750 Mn; the 400 Mn corresponding to 29 carbon atoms.

GB—A—1162436 discloses the preparation of an ashless dispersant by the reaction of at least an equivalent amount of an alkylene amine with a substantially aliphatic substituted derivative of succinic acid or anhydride and the product is reacted with a non-critical quantity of a second substantially aliphatic substituted derivative of succinic acid or anhydride.

The present invention distinguishes from these references in requiring a particular two-step reaction sequence characterised by the molar ratio of anhydride to polyamine in the first step, the use of particular dicarboxylic acid anhydride in the final step and an overall mole ratio of anhydride to polyamine within a relatively narrow and critically defined range. These parameters have been found essential to provide lubricating oil compositions which give demonstrated performance values in engine tests required to qualify for the highest grade service classifications for both gasoline and diesel engine lubricating oils. The

reaction sequence is particularly critical; thus products prepared in a simultaneous reaction technique will not meet the objectives of this invention.

In accordance with this invention, there are provided lubricating oil compositions exhibiting improved dispersancy in both gasoline and diesel engines comprising a major amount of lubricating oil and an effective amount of a polyalkenyl succinimide dispersant, said dispersant being prepared in a two-step sequential process comprising (a) first reacting a polyalkenyl succinic anhydride, the polyalkenyl being a polymer of a C_3 or C_4 olefin, and an alkylene polyamine of the formula $H_2N(CH_2)_n(NH(CH_2)_m)_mNH_2$, wherein n is 2 or 3 and m is 0 to 10, and (b) reacting the product of step (a) with a dicarboxylic acid anhydride, there being a molar ratio of from 1.0 to 2.2 moles of succinic anhydride per mole of polyamine in step (a) and the dicarboxylic acid anhydride being selected from the group consisting of maleic anhydride, succinic anhydride and C_1-C_{18} , preferably C_8-C_{18} , alkenyl or alkyl succinic anhydrides in sufficient molar proportion to provide a diimide dispersant having a total mole ratio of from 2.3 to 3.0 moles of anhydride per mole of polyamine.

The polyalkenyl succinic anhydrides useful in the present invention generally comprise those wherein the polyalkenyl group has a $\bar{M}_n$ (number average molecular weight) of 700 to 5,000, preferably 900 to 2,000. The methods of preparation are well known in the art, i.e., reaction of maleic anhydride with either the polyolefin itself or with a chlorinated polyolefin which in either case provides the desired polyalkenyl succinic anhydride. Polyisobutylene is preferred but other polymers of C_3 or C_4 olefins such as polybutene-1 and polypropylene are suitable including mixtures of such polyolefins.

Suitable alkylene polyamines are also well known represented by the formula $NH_2(CH_2)_n(NH(CH_2)_m)_mNH_2$, wherein n is 2 to 3 and m is 0 to 10. Illustrative are ethylene diamine, diethylene triamine, triethylene tetramine, tetraethylene pentamine, pentaethylene hexamine, and the like. Preferred for use is tetraethylene pentamine or a mixture of ethylene polyamines which approximates tetraethylene pentamine such as "DOW E-100" (a commercial mixture available from Dow Chemical Company, Midland, Michigan).

The terms polyalkenyl succinimide dispersant or diimide dispersant as used herein is meant to encompass the completed reaction product of the sequential process and is intended to encompass compounds wherein the product may have amide, amidine or salt linkages in addition to the imide linkage which results from the reaction of the primary amino group and the anhydride moiety.

The third reactant used to prepare the dispersants of the present invention encompasses maleic anhydride, succinic anhydride or an alkenyl or alkyl succinic anhydride having up to

about 18 carbon atoms and preferably at least 8 carbon atoms. Particularly advantageous results in terms of engine performance data have been obtained with dodecenyl succinic anhydride and maleic anhydride and the use of these materials, and the dispersants produced thereby, represent particularly preferred embodiments.

In the present invention, both the reaction sequence and the overall final mole ratio of total succinic anhydride groups to polyamine in the finished product have been found to be essential to meet the objective of passing both engine qualification tests for gasoline and diesel lubricating oil formulations. The reaction sequence requires a first step in the preparation of a polyisobutenyl succinic anhydride-polyamine reaction product. These are reacted in a mole ratio of 1.0 to 2.2 moles of polyisobutenyl succinic anhydride per mole of polyamine. After this reaction is complete, sufficient maleic anhydride, succinic anhydride or alkenyl succinic anhydride is then reacted to provide a final overall mole ratio in the finished dispersant of 2.3 to 3.0, preferably 2.3 to 2.5, moles of anhydride per mole of polyamine.

These reactions are carried out at conventional temperatures of 80°C to 200°C, more preferably 140°C to 165°C, using a conventional solvent media, such as a mineral lubricating oil solvent so that the final product is in a convenient solution in lubricating oil which is entirely compatible with a lubricating oil base stock. Suitable solvent oils are the same as the oils used as a lubricating oil base stock and these generally include lubricating oils having a viscosity (ASTM D-445) of 2 to 40, preferably 5 to 20, mm²/sec at 99°C, with the primarily paraffinic mineral oils being particularly preferred, such as Solvent 150 Neutral.

Lubricating oil compositions are prepared containing the dispersant of the present invention together with conventional amounts of other additives to provide their normal attendant functions such as viscosity index improvers, rust inhibitors, metal detergent additives, antioxidants, and zinc dialkyldithiophosphates anti-wear additives and these compositions meet the objective of passing engine qualification tests for both gasoline and diesel engine usage. For gasoline engine lube oils to meet the current "SF" designation of the American Petroleum Institute, lubricating oil formulations must equal or exceed certain values in the MS Sequence VD Engine Test (ASTM Special Publication 315). For dispersancy, the significant values in this test are a minimum of 9.4 sludge, 6.7 piston skirt varnish and 6.6 average varnish. The Sequence VD uses a 1980 Ford 2.3 liter 4-cylinder engine and is a 192-hour test comprising the cyclic operation at varying engine speeds and temperatures to simulate "stop and go" city driving and moderate turnpike operation. The test is an established industry standard.

For diesel performance the Caterpillar 1-H/2 test is the current standard to evaluate the effects of a crankcase oil on ring sticking and piston deposits. The test simulates high speed, moderately super-

charged engine operation. This test is also Federal Test Method 791—346 and is used to meet military specifications such as MIL-L-21260B and industry specifications such as SAE 183 and General Motors GM6146M. For the 1H-2 Test WTD (Weighted Total Demerits) is the principal value and for a 240-hour test, the target is a value within or below the 90—100 range. This is derived from the published specification value of WTD 140 for a 480-hour test. WTD is a cumulative rating based on observation of deposits in the groove and land areas of the piston and lacquer on piston skirts with all the specific evaluation being rated according to their relative importance and the final WTD being calculated in accordance with the test procedure.

The dispersants prepared according to the invention can be incorporated in a wide variety of lubricants. They can be used in lubricating oil compositions, such as automotive crankcase lubricating oils, automatic transmission fluids, etc. in effective amounts to provide active ingredient concentrations in finished formulations generally within the range of 0.5 to 10 weight percent, for example, 1 to 5 weight percent, preferably 1.5 to 3 weight percent, of the total composition. Conventionally, the dispersants are admixed with the lubricating oils as dispersant solution concentrates which usually contain up to about 50 percent weight of the active ingredient additive compound dissolved in mineral oil, preferably a mineral oil having an ASTM D-445 viscosity of 2 to 40, preferably 5 to 20 centistokes at 99ly 5 to 20 centistokes at 99°C. The lubricating oil includes not only hydrocarbon oils of lubricating viscosity derived from petroleum but also includes synthetic lubricating oils such as polyethylene oils; alkyl esters of dicarboxylic acids, complex esters of dicarboxylic acid, polyglycol and alcohol; alkyl esters of carbonic or phosphoric acids; polysilicones; fluorohydrocarbon oils; and mixtures or lubricating oils and synthetic oils in any proportion, etc. The term "lubricating oil" for this disclosure includes all the foregoing. The useful dispersant may be conveniently dispersed as a concentrate of 10 to 80 weight percent, preferably up to about 50 weight percent, of said dispersant in 20 to 90 weight percent of mineral oil, e.g., Solvent 150 Neutral oil with or without other additives being present and such concentrates are a further embodiment of this invention.

As noted above, such lubricating oil compositions containing the dispersants of the present invention will also contain other well-known additives such as the zinc dialkyl (C_3-C_8) dithiophosphate anti-wear inhibitors, generally present in amounts of about 1 to 5 weight percent. Useful detergents include the oil-soluble normal basic or over-based metal, e.g., calcium, magnesium, barium, etc., salts of petroleum naphthenic acids, petroleum sulfonic acids, alkyl benzene sulfonic acids, oil-soluble fatty acids, alkyl salicylic acids, alkylene bis-phenols and hydrolyzed phosphosulfurized polyolefins. Typical amounts are from 1 to 7 weight percent

with the HD or diesel oils usually containing slightly more of this metal detergent additive. Preferred detergents are the calcium and magnesium normal or overbased phenates, sulfurized phenates or sulfonates. Diesel lubricating oils preferably contain 4—6 percent of this additive.

Oxidation inhibitors include hindered phenols, e.g., 2,6-ditertbutyl-para-cresol, amines, sulfurized phenols and alkyl phenothiazines usually present in amounts of from 0.001 to 1 weight percent.

Pour point depressants which may be present in amounts of from 0.01 to 1 weight percent include wax alkylated aromatic hydrocarbons, olefin polymers and copolymers, acrylate and methacrylate polymers and copolymers.

Viscosity index improvers which may vary from 1 to 15 weight percent depending on the viscosity grade required include olefin polymers such as polybutene, ethylene-propylene copolymers, hydrogenated polymers and copolymers and terpolymers of styrene with isoprene and/or butadiene, polymers of alkyl acrylates or alkyl methacrylates, copolymers of alkyl methacrylates with N-vinyl pyrrolidone or dimethylaminoalkyl methacrylate, post-grafted polymers of ethylene-propylene with an active monomer such as maleic anhydride which may be further reacted with an alcohol or an alkylene polyamine, styrene/maleic anhydride polymers post-treated with alcohols and amines, etc.

Rust inhibition activity can be provided by about 0.01 to 1 weight percent of the aforementioned metal dihydrocarbyl dithiophosphates and the corresponding precursor esters, phosphosulfurized pinenes, sulfurized olefins and hydrocarbons, sulfurized fatty esters and sulfurized alkyl phenols. Preferred are the zinc dihydrocarbyl dithiophosphates which are salts of dihydrocarbyl esters of dithiophosphoric acids.

Other additives include effective amounts of the fuel economy additives or friction reducing additives such as the dimer acid esters, as disclosed in U.S. 4,105,571 to Shaub et al, which are present in amounts of 1 to 5 weight percent with esters of dimerized linoleic acid and diethylene glycol being a preferred material. Glycerol oleates are another example of fuel economy additives and these are usually present in very small amounts, such as 0.05 to 0.2 weight percent based on the weight of the formulated oil.

This invention is further illustrated by the following examples which are not to be considered as limitative of its scope.

Example 1

1500 grams of PIBSA (polyisobutenyl succinic anhydride, Mn=1300, Sap. No. 103) and 170 grams of an ethylene polyamine mixture ("Dow E-100", available from Dow Chemical Company, which approximates tetraethylene pentamine) were reacted in solution in 808 grams of Solvent 150 Neutral, a paraffinic mineral oil, at 160°C for 3 hours. The mole ratio of polyisobutenyl succinic anhydride to polyamine was 1.4:1. Thereafter was

added 225 grams of dodecenyl succinic anhydride which provided a final mole ratio of 2.4 moles of anhydride per mole of polyamine and this was reacted for 2 hours at 160°C. After filtration, the product analyzed at 1.83 percent N.

Example 2

320 grams of the initial PIBSA/polyamine product of Example 1 being the same but having a mole ratio of 2.1 mole of succinic anhydride per mole of polyamine was reacted with 6.0 grams of dodecenyl succinic anhydride in Solvent 150 Neutral at 160°C for 2 hours to provide a product having a final mole ratio of 2.4 moles of anhydride per mole of polyamine. The product analyzed for 1.50 percent N.

Example 3

Example 2 was repeated except that 2.2 grams of maleic anhydride was used to provide a product having a final mole ratio of 2.4 moles of anhydride per mole of polyamine. The product analyzed for 1.53 percent N.

Example 4

The product of Example 3 was included as the dispersant at a concentration of 3.6 weight percent active ingredient in a formulated SAE 10W40 lubricating oil composition and subjected to the ASTM Sequence VD engine test for gasoline engines. The formulation also contained conventional amounts of overbased sulfonate, zinc dialkyl dithiophosphate, antioxidant, olefin copolymer viscosity index improver, rust inhibitor and anti-foam additive. The results were as follows:

Sludge=9.51; piston skirt varnish=7.06 and varnish=6.92. These results exceed the API "SF" minimum values of 9.4 sludge; 6.7 piston skirt varnish and 6.6 varnish and therefore indicate the material is a commercially useful dispersant.

Example 5

The products of Example 2 and Example 3 were included in a 10W30 quality HD (diesel) lubricating oil formulations as the dispersant at 2.5 weight percent active ingredient concentration and the oil was evaluated for diesel dispersancy performance in the Caterpillar 1-H/2 test. The formulation also contained olefin copolymer V.I. improver to provide the 10W30 viscosity grade, 3.1 wt.% of a mixture of overbased and normal metal phenates, 1.5 weight percent of zinc dialkyl dithiophosphate anti-wear additive, and very small proportions of anti-oxidant (0.3%) and anti-foamant (0.2%).

The results for this diesel engine test are given below:

240 Hour caterpillar 1-H/2 test

	Formulation	TGF ²	WTD ³
5	Data Base ¹	16.6	189.1
	Example 3	14	66
10	Example 2	11	98
	Comparison ⁴	1	188

¹Base—These data are an average data base used for comparison in evaluating new diesel oils and are an average of 25 engine tests of conventional formulations.

²TGF—Top groove fill, percent deposits in groove.

³WTD—Weighted total demerits.

⁴Comparison—The same formulation was tested using as the dispersant a conventional polyisobutenyl succinic anhydride (Mn=900)-ethylene polyamine (DOW E-100) reaction product dispersant where the anhydride to amine mole ratio was 1.3 to 1.

Example 6 (Comparison)

The critical nature of the final ratio of anhydride to polyamine was further demonstrated with additional Caterpillar 1-H/2 tests. In 11 tests using products similar to Examples 3 and 4 but having final mole ratios varying between 1.3 and 2.0, an average WTD value of 163 was obtained. Similarly, for an average of four engine tests where the final mole ratio was 2.1 to 2.2, an average value of 128 WTD was obtained.

Claims

1. A lubricating oil composition exhibiting improved dispersancy in both gasoline and diesel engines comprising a major amount of lubricating oil and an effective amount of a dispersant, said dispersant being prepared in a sequential process comprising the steps of:

a) in a first step reacting an oil-soluble polyolefin succinic anhydride, the olefin being a C₃ or C₄ olefin, with an alkylene polyamine of the formula H₂N(CH₂)_n(NH(CH₂)_n)_mNH₂ wherein n is 2 or 3 and m is 0 to 10, and

b) reacting the product of step (a) with a dicarboxylic acid anhydride, characterised in that in step (a) the polyolefin succinic anhydride is reacted with the polyamine in a molar ratio of from 1.0 to 2.2 moles of polyolefin succinic anhydride per mole of polyamine, and in step (b) the dicarboxylic acid anhydride is selected from the group consisting of maleic anhydride, succinic anhydride and C₁₋₁₈ alkenyl or alkyl succinic anhydride and is in sufficient molar proportion to provide a total mole ratio of from 2.3 to 3.0 moles of anhydride compounds per mole of polyamine.

2. The composition of claim 1 wherein the polyolefin is polyisobutylene of Mn 900 to 2,000.

3. The composition of claims 1 or 2 wherein the polyamine is an ethylene polyamine.

4. The composition of claims 1 to 3 wherein the dicarboxylic acid anhydride is maleic anhydride.

5. The composition of claims 1—3 wherein said dicarboxylic acid anhydride is dodecenyl succinic anhydride.

6. The composition of claims 1—5 wherein said total mole ratio is 2,3 to 2,5 to 1.

7. The composition of claims 1—6 wherein there is present 1 to 5 weight percent of the dispersant.

8. The composition of claims 1—7 further comprising a metal detergent additive in an amount of from about 1 to 7 weight percent, a zinc dialkyl dithiophosphate anti-wear additive, 0,001 to 1 weight percent of an anti-oxidant, and 1 to 15 weight percent of a viscosity index improver.

9. The composition of claims 1—8 which is a diesel lubricating oil composition characterized by the presence of about 4 to 6 weight percent of normal or basic metal phenates, sulfurized phenate or sulfonate oil-soluble detergent additive or a mixture of said additives.

10. The composition of claim 1 which is in the form of a lubricating oil solution concentrate, said concentrate containing 20 to 80 weight percent of said dispersant.

11. A process for preparing a dispersant exhibiting improved dispersancy in both gasoline and diesel engine lubricating oil compositions, said dispersant being prepared in a sequential process comprising the steps of:

(a) in a first step reacting an oil-soluble polyolefin succinic anhydride, the olefin being a C₃ or C₄ olefin with an alkylene polyamine of the formula $H_2N(CH_2)_n(NH(CH_2)_m)_mNH_2$ wherein n is 2 or 3 and m is 0 to 10, and

(b) reacting the product of step (a) with a dicarboxylic acid anhydride, characterised in that in step (a) the polyolefin succinic anhydride is reacted with the polyamine in a molar ratio of from 1,0 to 2,2 moles of polyolefin succinic anhydride per mole of polyamine, and in step (b) the dicarboxylic acid anhydride is selected from the group consisting of maleic anhydride, succinic anhydride and C₁—C₁₈ alkenyl or alkyl succinic anhydride and is in sufficient molar proportion to provide a total mole ratio of from 2,3 to 3,0 moles of anhydride compounds per mole of polyamine.

12. The process of claim 11 wherein the polyolefin is polyisobutylene of $\bar{M}_n$ 900 to 2,000, the polyamine is an ethylene polyamine, and the dicarboxylic acid anhydride is maleic anhydride.

Patentansprüche

1. Schmierölzusammensetzung mit verbesserter Dispersionsfähigkeit sowohl in Benzin- als auch Dieselmotoren, die eine größere Menge eines Schmieröls und eine wirksame Menge eines Dispersionsmittels enthält, wobei das Dispersionsmittel in einem Mehrstufenverfahren hergestellt ist, das folgende Stufen umfaßt:

a) Umsetzung in einer ersten Stufe eines öllöslichen Polyolefinbernsteinsäureanhydrids, wobei das Olefin ein C₃- oder C₄-Olefin ist, mit einem Alkylpolyamin der Formel $H_2N(CH_2)_n(NH(CH_2)_m)_mNH_2$, wobei n 2 oder 3 ist und m 0 bis 10 ist, und

b) Umsetzung des Produkts aus Stufe (a) mit einem Dicarbonsäureanhydrid, dadurch gekennzeichnet, daß das Polyolefinbernsteinsäureanhydrid in Stufe (a) mit dem Polyamin in einem molaren Verhältnis von 1,0 bis 2,2 Mol Polyolefinbernsteinsäureanhydrid je Mol Polyamin umgesetzt wird und in Stufe (b) das Dicarbonsäureanhydrid ausgewählt ist aus der Gruppe bestehend aus Maleinsäureanhydrid, Bernsteinsäureanhydrid und C₁—C₁₈-Alkenyl- oder -alkylbernsteinsäureanhydrid und in ausreichendem molaren Anteil vorliegt, um ein Gesamtmolverhältnis von 2,3 bis 3,0 Mol Anhydridverbindungen je Mol Polyamin zu liefern.

2. Zusammensetzung nach Anspruch 1, dadurch gekennzeichnet, daß das Polyolefin Polyisobutylene mit einem $\bar{M}_n$ von 900 bis 2000 ist.

3. Zusammensetzung nach Anspruch 1 oder 2, dadurch gekennzeichnet, daß das Polyamin Ethylenpolyamin ist.

4. Zusammensetzung nach den Ansprüchen 1 bis 3, dadurch gekennzeichnet, daß das Dicarbonsäureanhydrid Maleinsäureanhydrid ist.

5. Zusammensetzung nach den Ansprüchen 1 bis 3, dadurch gekennzeichnet, daß das Dicarbonsäureanhydrid Dodecenylbernsteinsäureanhydrid ist.

6. Zusammensetzung nach den Ansprüchen 1 bis 5, dadurch gekennzeichnet, daß das Gesamtmolverhältnis 2,3 bis 2,5:1 beträgt.

7. Zusammensetzung nach den Ansprüchen 1 bis 6, dadurch gekennzeichnet, daß 1 bis 5 Gew. % des Dispersionsmittels vorhanden sind.

8. Zusammensetzung nach den Ansprüchen 1 bis 7, die weiterhin ein Metalltensidadditiv in einer Menge von etwa 1 bis 7 Gew. %, ein Zinkdialkyldithiophosphat-Antiabriebadditiv, 0,001 bis 1 Gew. % eines Antioxydationsmittels und 1 bis 15 Gew. % eines Viskositätsindexverbesserungsmittels enthält.

9. Zusammensetzung nach den Ansprüchen 1 bis 8, bei der es sich um eine Dieselschmierölzusammensetzung handelt, dadurch gekennzeichnet, daß etwa 4 bis 6 Gew. % normale oder basische Metallphenate, sulfurisierte -phenate oder -sulfonate als öllösliches Tensidadditiv oder eine Mischung dieser Additive vorhanden sind.

10. Zusammensetzung nach Anspruch 1, die in Form eines Schmierölkonzentrats vorliegt, wobei das Konzentrat 20 bis 80 Gew. % des Dispersionsmittels enthält.

11. Verfahren zur Herstellung eines Dispersionsmittels mit verbesserter Dispersionsfähigkeit sowohl in Benzin- als auch in Dieselmotorschmierölzusammensetzungen, bei dem das Dispersionsmittel nach einem Mehrstufenverfahren hergestellt wird, das die folgenden Stufen umfaßt:

(a) Umsetzung in einer ersten Stufe eines

öllöslichen Polyolefinbernsteinsäureanhydrids, wobei das Olefin ein C₃- oder C₄-Olefin ist, mit einem Alkylpolyamin der Formel H₂N(CH₂)_n(NH(CH₂)_m)_mNH₂, in der n 2 oder 3 ist und m 0 bis 10 ist, und

(b) Umsetzung des Produkts aus Stufe (a) mit einem Dicarbonsäureanhydrid, dadurch gekennzeichnet, daß das Polyolefinbernsteinsäureanhydrid in Stufe (a) mit dem Polyamin in einem molaren Verhältnis von 1,0 bis 2,2 Mol Polyolefinbernsteinsäureanhydrid je Mol Polyamin umgesetzt wird und in Stufe (b) das Dicarbonsäureanhydrid ausgewählt ist aus der Gruppe bestehend aus Maleinsäureanhydrid, Bernsteinsäureanhydrid und C₁₋₁₈-Alkenyl- oder -alkylbernsteinsäureanhydrid und in ausreichendem molaren Anteil vorliegt, um ein Gesamtmolverhältnis von 2,3 bis 3,0 Mol Anhydridverbindungen je Mol Polyamin zu liefern.

12. Verfahren nach Anspruch 11, dadurch gekennzeichnet, daß das Polyolefin Polyisobutylen mit einem M_n von 900 bis 2000 ist, das Polyamin ein Ethylenpolyamin ist und das Dicarbonsäureanhydrid Maleinsäureanhydrid ist.

Revendications

1. Composition d'huile lubrifiante présentant des propriétés de dispersion améliorées dans des moteurs à essence et des moteurs diesel, comprenant une quantité dominante d'huile lubrifiante et une quantité efficace d'un additif dispersant, ledit additif dispersant étant préparé dans un procédé séquentiel comprenant les étapes consistant:

a) à faire réagir au cours d'une première étape un anhydride polyoléfine-succinique soluble dans l'huile, l'oléfine étant une oléfine en C₃ ou C₄, avec une alkylène-polyamine répondant à la formule H₂N(CH₂)_n(NH(CH₂)_m)_mNH₂ dans laquelle n est égal à 2 ou 3 et m va de 0 à 10, et

b) à faire réagir le produit de l'étape (a) avec un anhydride d'acide dicarboxylique, caractérisé en ce que, dans l'étape (a) l'anhydride polyoléfine-succinique est amené à réagir avec la polyamine dans un rapport molaire allant de 1,0 à 2,2 moles d'anhydride polyoléfine-succinique par mole de polyamine, et dans l'étape (b) l'anhydride d'acide dicarboxylique est choisi dans le groupe comprenant l'anhydride maléique, l'anhydride succinique et un anhydride alcényl-succinique ou un anhydride alkyl-succinique en C₁ à C₁₈ et est en proportion molaire suffisante pour obtenir un rapport molaire total de 2,3 à 3,0 moles des composés du type anhydride par mole de polyamine.

2. Composition suivant la revendication 1, dans laquelle la polyoléfine est du polyisobutylène ayant une moyenne en nombre du poids moléculaire allant de 900 à 2000.

3. Composition suivant la revendication 1 ou 2, dans laquelle la polyamine est une éthylène-polyamine.

4. Composition suivant l'une quelconque des

revendications 1 à 3, dans laquelle l'anhydride d'acide dicarboxylique est l'anhydride maléique.

5. Composition suivant l'une quelconque des revendications 1 à 3, dans laquelle ledit anhydride d'acide dicarboxylique est l'anhydride dodécényl-succinique.

6. Composition suivant l'une quelconque des revendications 1 à 5, dans laquelle ledit rapport molaire total va de 2,3—2,5 à 1.

7. Composition suivant l'une quelconque des revendications 1 à 6, dans laquelle 1 à 5% en poids de l'additif dispersant sont présents.

8. Composition suivant l'une quelconque des revendications 1 à 7 comprenant en outre un additif détergent métallique en une quantité d'environ 1 à 7% en poids, un additif anti-usure du type dialkyl-dithiophosphate de zinc, 0,001 à 1% en poids d'un anti-oxydant et 1 à 15% en poids d'un agent améliorant l'indice de viscosité.

9. Composition suivant l'une quelconque des revendications 1 à 8 qui est une composition d'huile lubrifiante pour moteur diesel, caractérisée par la présence d'environ 4 à 6% en poids d'un additif détergent soluble dans le carburant du type phénate métallique normal ou basique, sulfonate ou phénate sulfuré ou d'un mélange d'additifs.

10. Composition suivant la revendication 1 qui est sous forme d'un concentré de solution d'huile lubrifiante, ledit concentré contenant 20 à 80% en poids de l'additif dispersant.

11. Procédé de préparation d'un additif dispersant présentant des propriétés de dispersion améliorées dans des compositions d'huile lubrifiante pour moteur à essence et pour moteur diesel, ledit additif dispersant étant préparé dans un procédé séquentiel comprenant les étapes consistant:

(a) à faire réagir au cours d'une première étape un anhydride polyoléfine-succinique soluble dans l'huile, l'oléfine étant une oléfine en C₃ ou C₄, avec une alkylène-polyamine répondant à la formule H₂N(CH₂)_n(NH(CH₂)_m)_mNH₂ dans laquelle n est égal à 2 ou 3 et m va de 0 à 10, et

(b) à faire réagir le produit de l'étape (a) avec un anhydride d'acide dicarboxylique, caractérisé en ce que, au cours de l'étape (a) l'anhydride polyoléfine-succinique est amené à réagir avec la polyamine dans un rapport molaire de 1,0 à 2,2 moles d'anhydride polyoléfine-succinique par mole de polyamine, et au cours de l'étape (b), l'anhydride d'acide dicarboxylique est choisi dans le groupe comprenant l'anhydride maléique, l'anhydride succinique et l'anhydride alcényl-succinique ou alkyl-succinique en C₁ à C₁₈ et est en proportion molaire suffisante pour obtenir un rapport molaire total de 2,3 à 3,0 moles de composés du type anhydride par mole de polyamine.

12. Procédé suivant la revendication 11, dans lequel la polyoléfine est du polyisobutylène ayant une moyenne en nombre du poids moléculaire comprise entre 900 et 2000, la polyamine est l'éthylène-polyamine et l'anhydride d'acide dicarboxylique est l'anhydride maléique.