

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
4 September 2008 (04.09.2008)

PCT

(10) International Publication Number
WO 2008/106045 A1

- (51) International Patent Classification:
G02B 6/036 (2006.01) **G02B 6/02** (2006.01)
- (21) International Application Number:
PCT/US2008/002305
- (22) International Filing Date:
21 February 2008 (21.02.2008)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
60/904,081 28 February 2007 (28.02.2007) US
- (71) Applicant (for all designated States except US): **CORNING INCORPORATED** [US/US]; 1 Riverfront Plaza, Corning, New York 14831 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **BICKHAM, Scott R** [US/US]; 69 E. Fourth Street, Corning, New York 14830 (US). **BOOKBINDER, Dana C** [US/US]; 2675 Davis Road, Corning, New York 14830 (US). **LI, Ming-jun**

[US/US]; 10 Ambrose Drive, Horseheads, New York 14845 (US). **MISHRA, Snigdhraj K** [US/US]; 3509 St. Francis Drive, Wilmington, North Carolina 28409 (US).


(74) Agent: **CARLSON, Robert L**; Corning Incorporated, Intellectual Property Department, SP-TI-3-1, Corning, New York 14831 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,

[Continued on next page]

(54) Title: LARGE EFFECTIVE AREA HIGH SBS THRESHOLD OPTICAL FIBER



(57) Abstract: Microstructured optical fiber for transmitting optical signals comprised of light, the optical fiber including a core region and a cladding region surrounding the core region, the cladding region including at least one annular region having an index of refraction lower than that of the remainder of the cladding. The optical fiber provides an absolute SBS threshold in dBm greater than about $9.3 + 10\log[(1 - e^{-(0.19)(50)/4.343}) / (1 - e^{-(\alpha)(L)/4.343})]$, wherein L is the length in km and α is the attenuation in dB/km at 1550 nm, and a fiber cutoff wavelength of less than 1400 nm.

WO 2008/106045 A1



ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL,
NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG,
CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- *with international search report*
- *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments*

LARGE EFFECTIVE AREA HIGH SBS THRESHOLD OPTICAL FIBER

BACKGROUND OF THE INVENTION

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This application claims the benefit of, and priority to U.S. Provisional Patent Application No. 60/904,081 filed on February 28, 2007, the content of which is relied upon and incorporated herein by reference in its entirety.

FIELD OF THE INVENTION

[0002] The present invention relates to high SBS threshold optical fibers. More preferably, the present invention relates to high SBS threshold optical fibers having large effective area.

TECHNICAL BACKGROUND

[0003] Stimulated Brillouin Scattering (SBS) is a dominant nonlinear penalty in many optical transmission systems. In many systems, the launching of large power to optical fiber while maintaining high signal to noise ratio (SNR) is desirable. However, as the launch power or signal power of an incident signal launched into an optical fiber increases, the launch power may exceed a certain threshold power and part of the signal power gets reflected due to SBS as a reflected signal. An undesirably large amount of the signal power can thus be reflected back toward the transmitter due to SBS. In addition, the scattering process increases the noise level at the signal wavelength. The combination of decrease in signal power and increase in the noise both lower the SNR and lead to performance degradation.

[0004] At finite temperatures, thermal excitations occur in glasses similar to phonons in crystals, and the interaction of these vibrational modes with low intensity signal light produces spontaneous Brillouin scattering. An intense optical field generates pressure or sound waves through electrostriction due to the beating of intense incident and spontaneous reflected light giving rise to pressure or acoustic waves. The change in pressure causes material density to change, thereby resulting in refractive index fluctuations. The net result is that an intense electrical field component of the optical wave generates pressure or sound

waves which cause density fluctuations. The acoustic wave changes the refractive index and enhances the reflected light amplitude through Bragg diffraction. Above the SBS threshold of an optical fiber, the number of stimulated photons is very high, resulting in a strong reflected field which limits the optical power that is transmitted and which reduces the SNR.

SUMMARY OF THE INVENTION

[0005] One aspect of the present invention relates to an optical fiber having a high SBS threshold. The optical fiber guides at least one optical mode and a plurality of acoustical modes, including an L_{01} acoustical mode and an L_{02} acoustical mode. The optical fiber comprises a core having a refractive index profile and a centerline and a cladding layer surrounding and directly adjacent the core. The core comprises a plurality of segments, preferably three segments that include a central segment, a moat segment, and a ring segment. The cladding region of the fiber includes at least one annular region having an index of refraction lower than that of the remainder of the cladding. In some embodiments, the at least one annular region in said cladding comprises fluorine, while in some other embodiments, the at least one annular region in said cladding is formed by non-periodically disposed holes which are located in the annular region. The non-periodically disposed holes cause the refractive index of the hole containing region to be less than that of the remainder (i.e., the portion of the cladding which does not contain holes) of the silica cladding.

[0006] The refractive index profile of the core is selected to result in the fiber exhibiting an absolute SBS threshold in dBm greater than about $9.3 + 10\log[(1 - e^{-(0.19)(50)/4.343}) / (1 - e^{-(\alpha)(L)/4.343})]$, wherein L is the length in km and α is the attenuation in dB/km at 1550 nm wherein the optical fiber has a fiber cutoff of less than 1400 nm. More preferably, the refractive index of the core is selected to provide: an absolute SBS threshold in dBm greater than about $9.8 + 10\log[(1 - e^{-(0.19)(50)/4.343}) / (1 - e^{-(\alpha)(L)/4.343})]$, wherein L is the length in km and α is the attenuation in dB/km at 1550 nm, wherein e is the mathematical constant 2.71828 (shown truncated to 5 decimal places and also sometimes expressed as “exp”),. For comparison, 50 km of standard single mode fiber with a step index core and an attenuation of 0.19 dB/km such as SMF-28e® optical fiber from Corning Incorporated has an SBS threshold of about 6.8 dBm.

BRIEF DESCRIPTION OF THE DRAWINGS

[0007] Figure 1 illustrates a first exemplary optical fiber and refractive index profile in accordance with the invention.

[0008] Figure 2 illustrates the core region of a refractive index profile of an optical fiber (Example 1) in accordance with the invention.

[0009] Figure 3 illustrates another exemplary optical fiber and refractive index profile in accordance with the invention.

[0010] Figure 4 illustrates another exemplary optical fiber and refractive index profile in accordance with the invention.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0011] Additional features and advantages of the invention will be set forth in the detailed description which follows and will be apparent to those skilled in the art from the description or recognized by practicing the invention as described in the following description together with the claims and appended drawings.

[0012] The "refractive index profile" is the relationship between refractive index or relative refractive index and waveguide fiber radius. As used herein, refractive index is expressed as delta or "relative refractive index percent", and is defined as $\Delta\% = 100 \times (n_i^2 - n_c^2) / 2n_i^2$, where n_i is the maximum refractive index in region i , unless otherwise specified, and n_c is the refractive index of the non-doped portion of the cladding region (for example, outer clad region 16 in the embodiment illustrated in Fig. 1). As used herein, the relative refractive index is represented by Δ and its values are given in units of "%", unless otherwise specified.

[0013] "Chromatic dispersion", herein referred to as "dispersion" unless otherwise noted, of a waveguide fiber is the sum of the material dispersion, the waveguide dispersion, and the inter-modal dispersion. In the case of single mode waveguide fibers the inter-modal dispersion is zero. Zero dispersion wavelength is a wavelength at which the dispersion has a value of zero. Dispersion slope is the rate of change of dispersion with respect to wavelength.

[0014] "Effective area" is defined as:

$$A_{eff} = 2\pi \frac{\left(\int_0^{\infty} f^2 r dr \right)^2}{\int_0^{\infty} f^4 r dr}, \quad (\text{Eq. 1})$$

where the integration limits are 0 to ∞ , and f is the transverse component of the electric field associated with light propagated in the waveguide wherein r is the radius from the center of the optical fiber. As used herein, "effective area" or " A_{eff} " refers to optical effective area at a wavelength of 1550 nm unless otherwise noted.

[0015] The mode field diameter (MFD) is measured using the Peterman II method wherein,

$$2w = \text{MFD}, \text{ and } w^2 = 2 \int_0^{\infty} f^2 r dr \bigg/ \int_0^{\infty} \left(\frac{df}{dr} \right)^2 r dr. \quad (\text{Eq. 2})$$

[0016] The bend resistance of a waveguide fiber can be gauged by induced attenuation under prescribed test conditions.

[0017] The 10, 15, and 20 mm macrobend tests consist of wrapping the fiber 5 times around a 10, 15, or 20 mm diameter mandrel, respectively, and measuring the induced attenuation (i.e. the increase in attenuation) caused by wrapping the fiber around the mandrel.

[0018] The theoretical fiber cutoff wavelength, or "theoretical fiber cutoff", or "theoretical cutoff", for a given mode, is the wavelength above which guided light cannot propagate in that mode. A mathematical definition can be found in Single Mode Fiber Optics, Jeunhomme, pp. 39-44, Marcel Dekker, New York, 1990 wherein the theoretical fiber cutoff is described as the wavelength at which the mode propagation constant becomes equal to the plane wave propagation constant in the outer cladding. This theoretical wavelength is appropriate for an ideally perfect fiber that has no attenuation and under the perfectly straight deploy condition without any perturbations (e.g. no diameter variation).

[0019] The effective fiber cutoff is lower than the theoretical cutoff due to losses that are induced by bending and/or mechanical pressure. In this context, the cutoff refers to the higher of the LP11 and LP02 modes. LP11 and LP02 are generally not distinguished in measurements, but both are evident as steps in the spectral measurement, i.e. no power is observed in the mode at wavelengths longer than the measured cutoff. The actual fiber cutoff can be measured by the standard 2 m fiber cutoff test, FOTP-80 (EIA-TIA-455-80), to yield the "fiber cutoff wavelength", also known as the "2 m fiber cutoff" or "measured cutoff". The

FOTP-80 standard test is performed to either strip out the higher order modes using a controlled amount of bending, or to normalize the spectral response of the fiber to that of a multimode fiber.

[0020] The cabled cutoff wavelength, or "cabled cutoff" is even lower than the measured fiber cutoff due to longer fiber length and higher levels of bending and mechanical pressure in the cable environment. The actual cabled condition can be approximated by the cabled cutoff test described in the EIA-445 Fiber Optic Test Procedures, which are part of the EIA-TIA Fiber Optics Standards, that is, the Electronics Industry Alliance--Telecommunications Industry Association Fiber Optics Standards, more commonly known as FOTP's. Cabled cutoff measurement is described in EIA-455-170 Cable Cutoff Wavelength of Single-mode Fiber by Transmitted Power, or "FOTP-170".

[0021] Unless otherwise noted herein, optical properties (such as dispersion, dispersion slope, etc.) are reported for the LP₀₁ mode at a wavelength of 1550 nm.

[0022] A waveguide fiber telecommunications link, or simply a link, is made up of a transmitter of light signals, a receiver of light signals, and a length of waveguide fiber or fibers having respective ends optically coupled to the transmitter and receiver to propagate light signals there between. The length of waveguide fiber can be made up of a plurality of shorter lengths that are spliced or connected together in end to end series arrangement. A link can include additional optical components such as optical amplifiers, optical attenuators, optical isolators, optical switches, optical filters, or multiplexing or demultiplexing devices. One may denote a group of inter-connected links as a telecommunications system.

[0023] Fig. 1 illustrates a cross-section and the refractive index profile of one optical fiber which exhibits a high SBS threshold in accordance with the present invention. The optical fiber guides at least one optical mode and a plurality of acoustical modes, including an L₀₁ acoustical mode and an L₀₂ acoustical mode. The optical fiber comprises a core 10 having a refractive index profile and a centerline and a cladding layer 12 surrounding and directly adjacent the core.

[0024] The cladding region 12 of the fiber includes at least one annular region 14 having an index of refraction lower than that of the remainder of the cladding 12. Preferably down doped annular region 14 is spaced from core 10 by inner cladding region 13. In some embodiments, the at least one annular region in said cladding comprises fluorine, while in

some other embodiments, the at least one annular region in said cladding is formed at least in part by providing non-periodically disposed holes in the annular region. The non-periodically disposed holes cause the refractive index of the hole containing region to be less than that of the remainder (i.e., the portion of the cladding which does not contain holes) of the silica cladding.

[0025] The refractive index profile of the core is selected to result in the fiber exhibiting an absolute SBS threshold in dBm at 1550 nm greater than about $9.3 + 10\log[(1 - e^{-(0.19)(50)/4.343})/(1 - e^{-(\alpha)(L)/4.343})]$, wherein L is the length in km and α is the attenuation in dB/km at 1550 nm wherein the optical fiber has a fiber cutoff of less than 1400 nm. More preferably, the refractive index of the core is selected to provide: an absolute SBS threshold in dBm at 1550 nm greater than about $9.8 + 10\log[(1 - e^{-(0.19)(50)/4.343})/(1 - e^{-(\alpha)(L)/4.343})]$, wherein L is the length in km and α is the attenuation in dB/km at 1550 nm.

[0026] The SBS threshold varies with the length and attenuation of the fiber under test. Generally, a very short length of an optical fiber will tend to have a higher SBS threshold than a very long length of the same fiber. Also, generally, a length of one optical fiber having a higher attenuation will tend to have a higher SBS threshold than the same length of another similar optical fiber having a lower attenuation. An approximate analytical expression is given in "Optical impairments, including Raman and Brillouin Non-Linearities, in Broadband WDM-Overlay Single Fiber PONs – Measurements, Remedies and Design Optimization Guidelines," G. H. BuAbbud et al., NFOEC 2003.

$$P_{th}(L) \approx 21 \frac{\alpha A_{eff}}{g_B^{eff} [1 - \exp(-\alpha L)]} \quad (\text{Eq. 3})$$

where g_B^{eff} is the effective Brillouin gain coefficient, α is the attenuation in dB/Km, L is the fiber length, A_{eff} is the optical effective area and P_{th} is the SBS threshold power. In this simple approximation, the SBS threshold is inversely proportion to the effective length of the fiber. Thus, if the measured threshold for a length L_1 is P_1 , then the threshold at length L_2 is

$$P_2(dBm) \cong P_1(dBm) + 10 \log \left[\frac{1 - \exp^{(-\alpha L_1)}}{1 - \exp^{(-\alpha L_2)}} \right] \quad (\text{Eq. 4})$$

[0027] For example, the values of SBS threshold reported herein correspond to fibers having a length (L_1) of about 50 km and an attenuation at 1550 nm of about 0.19 dB/km. Thus, the SBS threshold P_2 for an optical fiber of the type disclosed herein having a length L_2 and attenuation α_2 in dB/Km can be determined from:

$$P_2(dBm) \cong P_1(dBm) + 10 \log \left[\frac{1 - \exp^{(-(0.19 \cdot 50.5 / 4.343))}}{1 - \exp^{(-\alpha_2 L_2 / 4.343)}} \right] \quad (\text{Eq. 5})$$

[0028] Preferably, the optical fiber disclosed herein has a silica-based core and cladding. In preferred embodiments, the cladding has an outer diameter of about 125 μm . Preferably, the outer diameter of the cladding has a constant diameter along the length of the optical fiber. In preferred embodiments, the refractive index of the optical fiber has radial symmetry.

[0029] Preferably, the refractive index profile of the optical fiber disclosed herein is non-negative from the centerline to the outer radius of the core 10. In preferred embodiments, the optical fiber contains no index-decreasing dopants in the core 10.

[0030] Preferably, the core 10 is comprised of silica doped with germanium, i.e. germania doped silica. Doping of the core, and in particular the central portion of the core, advantageously reduces sound velocity in the optical fiber core relative to its cladding, resulting in total internal reflection of the acoustic field. Dopants other than germanium, singly or in combination, may be employed within the core, and particularly at or near the centerline, of the optical fiber disclosed herein to obtain the desired refractive index and density.

[0031] As best illustrated in Figs. 2-4, the core 10 preferably comprises a plurality of segments, more preferably three segments that include a central region 20, an intermediate region 22, and an outer region 24. For example, as shown in Fig. 2, the core region 10 comprises a central region 20 having a maximum relative refractive index Δ_1 , an intermediate region 22 surrounding and directly adjacent the central region, the intermediate region having

a minimum relative refractive index Δ_2 , and an outer region **24** surrounding and directly adjacent the intermediate region, the outer region having a maximum relative refractive index Δ_3 , wherein $\Delta_1 > \Delta_2$ and $\Delta_3 > \Delta_2$.

[0032] Preferably, the central region of the core extends from the centerline to an outer radius between about 1.5 and 2.5 μm and preferably has a maximum relative refractive index less than 0.7%, more preferably less than 0.6%. Preferably, the minimum refractive index Δ_2 of intermediate region **22** occurs between a radius of about 1.5 and 2.5 μm . Intermediate core region **22** is surrounding and preferably directly adjacent to the central region **20**. The intermediate core region comprises a minimum relative refractive index, Δ_2 , preferably less than 0.4%, more preferably less than 0.35%. Preferably, $(\Delta_1 - \Delta_2) > 0.25\%$. Preferably, the outer core region **24** surrounds and is directly adjacent to the intermediate core region **22**, the outer region **24** extending to the outer core radius of between about 3.5 and 6 μm . The outer core radius is defined herein as the outer region of core **10** where the relative refractive index percent falls to $\Delta = 0.05\%$. In the embodiment illustrated in Fig. 1, this occurs at a radius of about 4.28 μm . In preferred embodiments, at $r = 3.5 \mu\text{m}$, $\Delta_3 >$ about 0.2%, more preferably $>$ about 0.3%, most preferably $>$ about 0.35%. The outer region **24** comprises a maximum relative refractive index Δ_3 which is greater than Δ_2 and less than Δ_1 . Preferably, the difference between Δ_3 and Δ_2 is greater than 0.10%, more preferably greater than 0.15%.

[0033] In each of the embodiments disclosed herein, the core **10** is surrounded by a cladding **12** which includes at least one annular region **14** in the cladding having a lower refractive index than the remainder of the cladding **12**. Preferably, the annular down doped region is displaced from the core (by an inner cladding region **13**) at least 2 μm , more preferably at least 4 μm , and more preferably at least 5 μm . This annular region may be comprised of at least one down dopant such as fluorine, and/or a plurality of randomly distributed holes (the terms holes, seeds, voids and airlines are used herein interchangeably, and mean a gaseous region which is trapped within the glass of the optical fiber).

[0034] The cladding region **12** of the fiber includes at least one annular region **14** having an index of refraction lower than that of the remainder of the cladding **12**. In some embodiments, the at least one annular region in said cladding comprises an elemental down dopant such as fluorine, while in some other embodiments, the at least one annular region in said cladding is formed at least in part by providing non-periodically disposed holes in the

annular region. Alternatively, region 14 could comprise both an elemental down dopant such as fluorine and a plurality of randomly or non-periodically distributed holes. The non-periodically disposed holes cause the average effective refractive index of the hole containing region to be less than that of the remainder (i.e., the portion of the cladding which does not contain holes) of the silica cladding.

[0035] In one embodiment, the annular down doped region 14 in the cladding is achieved using a plurality of non-periodically disposed holes. Preferably the holes have a mean diameter of less than 2000 nm, more preferably less than 1550 nm and most preferably less than 500 nm and greater than 1 nm. The annular hole containing region preferably has the maximum radial width of less than 10 μm , more preferably less than 6 μm and greater than 0.5 μm . The hole containing region also has a regional void area percent of less than 20%, more preferably less than 10% and greater than 0.5%, and most preferably less than 6% and greater than 1%. The annular hole containing region preferably has a radial width which is greater than 0.5 μm and less than 10 μm . The annular hole containing region has a regional void area percent greater than 0.05% and less than 30%.

[0036] When randomly distributed holes are employed in annular region 14, the relative percent index of refraction in annular region 14 fluctuates between a refractive index delta of about -28% (refractive index of void filled gas such as argon, nitrogen or krypton relative to that of pure undoped silica glass silica) and that of the glass surrounding the voids (in the embodiments disclosed herein undoped silica glass, with a relative refractive index delta of about 0%). A typical effective relative refractive index percent for region 14 as a result of the mixed random holes and silica glass regions contained therein will be between about -0.5% and -3%, relative to pure silica glass. It is preferable that the mean distance between the holes be less than 5000 nm, more preferably less than 2000 nm, even more preferably less than 1000 nm, for example 750 nm or 500 nm. The annular region 14 preferably has a regional void area percent (cross sectional area of the voids divided by the cross-sectional area for the region 14) less than 20 percent, more preferably less than 15 percent, and most preferably less than 10 percent and greater than 0.5%. Preferably, at least 80%, and more preferably at least 90% of the voids have a maximum cross-sectional diameter of less than 1550 nm. In some embodiments, the mean diameter of the voids is less than 1000 nm, and even more preferably less than 500 nm and greater than 1 nm. The non-periodically located voids are closed

(surrounded by solid material) and are non-periodic both in radial cross-section, and along the longitudinal axis of the fiber. That is, the voids 15 may have the same size, or may be of different sizes; the distances between voids may be uniform (i.e., the same), or may be different, but because the voids are non-periodic, either their sizes or their distances between the voids are not the same.

[0037] During the manufacture of transmission optical fibers by conventional soot deposition processes such as the outside vapor deposition (OVD) process or the vapor axial deposition (VAD) process, silica and doped silica particles are pyrogenically generated in a flame and deposited as soot. In the case of OVD, silica soot preforms are formed layer-by-layer by deposition of the particles on the outside of a cylindrical target rod by traversing the soot-laden flame along the axis of the cylindrical target. Such porous soot preforms are subsequently treated with a drying agent (e.g., chlorine) to remove water and metal impurities and are then consolidated or sintered into glass blanks at temperatures ranging from 1100-1500°C. Surface energy driven viscous flow sintering is the dominant mechanism of sintering, which results in densification and closing of the pores of the soot, thereby forming a consolidated glass preform. During the final stages of sintering, the gases used in consolidation may become trapped as the open pores are closed. If the solubility and permeability of the trapped gases in the glass are high at the sintering temperature, then the gases are able to migrate through and out of the glass during the consolidation process. Alternatively, gases which are still trapped after the consolidation phase of the fiber manufacturing process may be outgassed by holding the fiber preforms for a period until the gases migrate out through the glass preforms, thereby leaving one or more voids with vacuum therein within the preform. During the draw operation when the optical fiber is drawn from the preform, these voids close, leaving a void-free or essentially void-free optical fiber. In consolidation processes which are employed to make conventional transmission optical fiber, the goal is to achieve an optical fiber that is entirely free of voids in both the core and cladding region of the optical fiber. Helium is often the gas utilized as the atmosphere during the consolidation of conventional optical fiber preforms. Because helium is very permeable in glass, it very easily exits the soot preform and the glass during the consolidation process, so that after consolidating in helium the glass is free of pores or voids.

[0038] One method of making a region **14** having non-periodically distributed holes is to subject that region to preform consolidation conditions which are effective to result in a significant amount of gases being trapped in the consolidated glass blank, thereby causing the formation of non-periodically distributed voids in the consolidated glass optical fiber preform. Rather than taking steps to remove these voids, the resultant preform is purposefully used to form an optical fiber with voids therein. In particular, by utilizing relatively low permeability gases and/or relatively high sintering rates, holes can be trapped in the consolidated glass during the consolidation process. The sintering rate can be increased by increasing the sintering temperature and/or increasing the downfeed rate of the soot preform through the sintering zone of the consolidation furnace. Under certain sintering conditions, it is possible to obtain glasses in which the area fraction of the trapped gases is a significant fraction of the total area or volume of the preform.

[0039] By utilizing the consolidation parameters so that the maximum diameter of the holes or voids is less than the wavelength of the light which is to be transmitted along the length of the fiber (e.g. in the case of optical fibers for use in telecommunications applications, less than 1550 nm), the fiber may be effectively used to transmit information at that particular wavelength.

[0040] Preferred sintering gases which may be used in the consolidation step are those which comprise at least one gas selected from the group consisting of air, nitrogen, argon, CO₂, oxygen, chlorine, CF₄, CO, SO₂, krypton, neon, and mixtures thereof. Each of these gases exhibits a relatively low permeability in silica glass at or below the consolidation temperature which is suitable for forming voids in accordance with the methods present invention.

[0041] Preferably, when randomly distributed holes are employed in region **14**, region **14** comprises a regional void area percent greater than 0.5%, more preferably greater than about 1%, even more preferably greater than 5%, and in some embodiments greater than about 10% and less than 30%. In some embodiments the preferred ranges are greater than 1% and less than 6%.

[0042] Methods for making fibers having randomly distributed holes in annular regions are further described, for example, in U.S. Patent Application Numbers 60/817721, filed June 30, 2006, and 60/845927, filed September 20, 2006, the specifications of which are hereby

incorporated by reference in their entirety. The holes may include a gas such as nitrogen, air. A preferred gas for inclusion in the holes is Argon, nitrogen and krypton.

[0043] The hole-containing region may consist of undoped (pure) silica, thereby completely avoiding the use of any dopants in the hole-containing region, to achieve a decreased refractive index, or the hole-containing region may comprise doped silica e.g. fluorine-doped silica having a plurality of holes.

[0044] As illustrated in Fig. 1, in one set of embodiments, the core region 10 includes doped silica to provide a positive refractive index relative to pure silica, e.g. germania doped silica, and the cladding 12 includes a down doped region 14. The core region is preferably hole-free. In some embodiments, an inner annular hole-free region 13 extends from the core region 10 to a radius R_c , wherein the inner annular hole-free region 13 has a radial width greater than 2 μm . The radial width of the hole free region 16 is preferably greater than 3.5 μm , more preferably greater than 4 μm , and even more preferably greater than 5 μm and less than 20 μm . In the embodiment illustrated in Fig. 1, the down doped region 14 preferably comprises a plurality of randomly distributed holes therein. The intermediate annular hole-containing region 14 extends radially outward. The outer annular region 16 extends radially outward from hole containing region 14, preferably to the outermost radius of the silica portion of the optical fiber. One or more coatings 18 may be applied to the external surface of the silica portion of the optical fiber, starting at the outermost diameter or outermost periphery of the glass part of the fiber. The core region 10 and the cladding region 12 are preferably comprised of silica. The core region 10 is preferably silica doped with one or more dopants. The hole-containing region 14 has an inner radius which is not more than 20 μm . In some embodiments, the inner radius of the hole containing region is not less than 8 μm and not greater than 16 μm . In other embodiments, the inner radius is not less than 9 μm and not greater than 14 μm . The hole-containing region 14 has a radial width which is preferably not less than 0.5 μm , more preferably not less than 0.5 μm and not greater than 10 μm , even more preferably not less than 2 μm and not greater than 8 μm , and most preferably not less than 2 μm and not greater than 10 μm .

[0045] Table 1 lists an illustrative first set of preferred embodiments which employ randomly distributed holes in region 14 of the cladding which is spaced from the core of the optical

fiber. Table 1 sets forth the refractive index delta Δ_0 along the centerline of the optical fiber, the peak refractive index delta Δ_1 and the radial location (R1) of the peak refractive index of the central region 20 of the core, the refractive index delta Δ_2 and the radial location (R2) of the minimum refractive index of the intermediate region 22 of the core, and the refractive index delta Δ_3 and the radial location (R3) of the peak refractive index of the outer region 24 of the core. Also provided is the outer radius R4 of the core (which is also the outer radius of the outer region 24 of the core. The corresponding core structure for Example 1 is also illustrated in Fig. 2. Table 1 also sets forth the location of the inner radius R5 of the down doped annular portion 12 as well as ratio of the radius of the core to the beginning of the annular region 12 (core moat ratio). Also set forth in Table 1, for each of Examples 1 and 2, are measured zero dispersion wavelength, dispersion at 1310 nm, dispersion slope at 1310 nm, dispersion at 1550 nm, measured mode field diameter at 1310 nm, fiber cutoff wavelength as measured using the 2m cutoff test, cable cutoff as measured by the 22m cutoff test, measured 10 mm bend performance (attenuation increase, in dB), measured 15 mm bend performance (attenuation increase, in dB), and measured 20 mm bend performance (attenuation increase, in dB). Also set forth in Table 1 for examples 1 and 2 are the air fill percent of region 14, mean hole diameter of the holes which make up the randomly distributed holes, the approximate number of holes that are seen in a cross section of the optical fiber, and the standard deviation of the hole size diameter. Table 1 also gives the measured SBS threshold for 10 km of fiber. For comparison, 10 km of standard single mode fiber with a step index core and an attenuation of 0.19 dB/km such as SMF-28e® optical fiber from Corning Incorporated has an SBS threshold of about 10.2 dBm.

Table 1

Profile		Example 1	Example 2
Δ_0		0.56	0.53
R_1		0.13	0
Δ_1		0.57	0.53
R_2		1.89	1.91
Δ_2		0.236	0.245
R_3		3.17	3.21
Δ_3		0.49	0.45
R_4		4.28	4.68
R_5		12.59	9.40
W_5		2.5	3
Effective avg. % index in ring 14		-1.49	
R_4/R_5		0.34	0.50

Fiber ID	Measured Zero Dispersion (nm)	1310 Dispersion (ps/nm/km)	1310 Slope (ps/nm ² /km)	1550 Dispersion (ps/nm/km)	Measured 1310 MFD (microns)	1550 attenuation (dB/Km)
Example 1	1321	-0.98	0.087	16.49	9.07	0.192
Example 2	1300	0.95	0.096	19.82	8.74	0.197

Fiber ID	2m Cutoff (nm)	22m Cutoff (nm)	1x10 mm Macrobend (dB/turn)	1x15 mm Macrobend (dB/turn)	1x20 mm Macrobend (dB/turn)	SBS Threshold for 10 km (dBm)
Example 1	1365	1267	0.34	0.21	0.006	13.8
Example 2	1310	1289	0.33	NA	NA	14.2

Fiber ID	Air Fill %	Minimum % index in ring	Mean Hole Diameter, micron	Number of holes in fiber cross-section	Hole Diameter StDev, microns
Example 1	5.9	-28	0.32	192	0.1
Example 2	6	-28	0.3	170	0.1

[0046] The optical fibers illustrated by Examples 1 and 2 have a MFD at 1310 nm not less than about 8.2 μm . Preferably, the 2 m fiber cutoff is less than about 1500 nm. Preferably, cabled cutoff is less than about 1400 nm, more preferably less than about 1300 nm. In some embodiments, the core may comprise a relative refractive index profile having a so-called centerline dip which may occur as a result of one or more optical fiber manufacturing techniques. However, the centerline dip in any of the refractive index profiles disclosed herein is optional. The core comprises a first portion extending from the centerline to a maximum occurring at a radius less than 1 μm .

[0047] In preferred embodiments, optical fibers such as those illustrated by Fig. 1 and Examples 1 and 2 disclosed herein preferably have: a dispersion at 1550 nm of greater than 10 ps/nm-km, more preferably between 10 and 21 ps/nm-km, even more preferably between 16 and 21 ps/nm-km; a dispersion slope at 1550 nm of less than 0.07 ps/nm²-km, more preferably between 0.05 and 0.07 ps/nm²-km; a 20 mm bend loss less than about 0.5 dB/turn, more preferably less than 0.1 dB/turn, even more preferably less than about 0.05 dB/turn; a 10 mm bend loss less than about 5 dB/turn, more preferably less than about 2 dB/turn, even more preferably less than about 1 dB/turn; zero dispersion wavelength less than 1340 nm, more preferably less than 1324 nm, even more preferably between 1300 and 1324 nm; an MFD at 1310 nm greater than 8.2 μm , and in some preferred embodiments greater than 8.8 μm , and in other preferred embodiments between 8.6 μm and 9.5 μm ; a dispersion at 1310 nm having a magnitude less than 5 ps/nm-km, more preferably less than 3 ps/nm-km; and a dispersion slope at 1310 nm of less than 0.10 ps/nm²-km, more preferably less than 0.093 ps/nm²-km.

[0048] Table 2 lists an illustrative set of preferred embodiments (Examples 3-7) which employ a fluorine doped region 14 of the cladding which is spaced from the core of the optical fiber. FIGS. 3 and 4 show the corresponding refractive index profiles of Examples 3 and 7, respectively. Table 2 sets forth the refractive index delta along the centerline of the optical fiber Δ_0 , the refractive index delta Δ_1 of the central region 20 of the core, the refractive index delta Δ_2 of the intermediate region 22 of the core, and the maximum refractive index delta Δ_3 of the outer region of the core. The corresponding core structure for each example is also illustrated in Fig. 2. Table 2 also sets forth the inner radius of the down doped annular cladding region 14 as well as the minimum refractive index in region 14. Also set forth is the

ratio of the radius of the core to the inner radius of the annular region **14** (core/moat ratio). Also set forth in Table 2, for each of Examples 1 and 2, are the modeled zero dispersion wavelength, dispersion at 1310 nm, dispersion slope at 1310 nm, dispersion at 1550 nm, mode field diameter at 1310 nm, modeled cable cutoff wavelength and theoretical cutoff of the LP₁₁ mode, and modeled SBS threshold increase (SBSt) compared to approximately the same length of standard single mode fiber having an attenuation of 0.19 dB/km.

Table 2

	Example 3	Example 4	Example 5	Example 6	Example 7
Δ_0	0.46	0.46	0.55	0.4	0.4
R_1	0.48	0.5	0.35	0.33	0.33
Δ_1	0.55	0.56	0.56	0.71	0.72
R_2	2.35	2.33	2.33	2.35	2.1
Δ_2	0.22	0.22	0.22	0.22	0.23
R_3	3.65	3.6	3.63	3.63	3.35
Δ_3	0.388	0.404	0.44	0.43	0.41
R_4	4.56	4.45	4.38	4.38	4.17
R_5	9.6	9.63	9.38	11.33	13.65
W_5	4.18	2.65	2.72	2.4	3.7
Δ_4	-0.2	-0.2	-0.15	-0.31	-0.34
R_4/R_5	0.48	0.46	0.47	0.39	0.31

	Example 3	Example 4	Example 5	Example 6	Example 7
Disp 1310 (ps/nm/km)	-0.24	-0.29	0.00	-0.45	-0.61
Slope 1310 (ps/nm ² /km)	0.0928	0.0920	0.0906	0.0900	0.0873
Zero Dispersion (nm)	1313	1313	1310	1315	1317
MFD 1310 (microns)	9.18	9.04	9.20	9.20	9.25
MFD 1550 (microns)	10.39	10.23	10.40	10.40	10.45
Aeff 1550 (sq. microns)	82.9	80.4	84.9	84.9	85.8
Attn 1550 (dB/km)	0.193	0.194	0.193	0.194	0.194

SBS _t (dB)	4.00	3.91	4.23	4.29	4.13
LP ₁₁ cutoff (nm)	1248	1272	1253	1280	1235
cable cutoff (nm)	1202	1200	1180	1195	1200

[0049] Thus for the fibers shown in Examples 1-7, the absolute SBS threshold in dBm is greater than about $9.3 + 10\log[(1 - e^{-(0.19)(50)/4.343})/(1 - e^{-(\alpha)(L)/4.343})]$, wherein L is the length in km and α is the attenuation in dB/km at 1550 nm wherein the optical fibers have a fiber cutoff of less than 1400 nm.

[0050] It is to be understood that the foregoing description is exemplary of the invention only and is intended to provide an overview for the understanding of the nature and character of the invention as it is defined by the claims. For example, embodiments which employ a fluorine doped region 14 could alternatively or additionally employ a region 14 having non-periodically distributed holes, and vice versa. The accompanying drawings are included to provide a further understanding of the invention and are incorporated and constitute part of this specification. The drawings illustrate various features and embodiments of the invention which, together with their description, serve to explain the principals and operation of the invention. It will become apparent to those skilled in the art that various modifications to the preferred embodiment of the invention as described herein can be made without departing from the spirit or scope of the invention as defined by the appended claims.

What is claimed is:

1. An optical fiber for transmitting optical signals comprised of light, the optical fiber comprising:

a core region disposed about a longitudinal centerline and having a refractive index profile with a first refractive index, and

a cladding region surrounding the core region, the cladding region comprising at least one annular region having an index of refraction lower than that of the remainder of the cladding;

wherein the refractive index of the core is selected to provide: an absolute SBS threshold in dBm greater than about $9.3 + 10\log[(1-e^{-(0.19)(50)/4.343})/(1-e^{-(\alpha)(L)/4.343})]$, wherein L is the length in km and α is the attenuation in dB/km at 1550 nm wherein the optical fiber has a fiber cutoff of less than 1400 nm.

2. The optical fiber of claim 1, wherein the refractive index of the core is selected to provide: an absolute SBS threshold in dBm greater than about $9.8 + 10\log[(1-e^{-(0.19)(50)/4.343})/(1-e^{-(\alpha)(L)/4.343})]$, wherein L is the length in km and α is the attenuation in dB/km at 1550 nm.

3. The optical fiber of claim 1, wherein said at least one annular region in said cladding comprises fluorine.

4. The optical fiber of claim 1, wherein said at least one annular region in said cladding is formed by non-periodically disposed holes in said annular region.

5. The optical fiber of claim 1, wherein the core region comprises a central region having a maximum relative refractive index Δ_{1MAX} , an intermediate region surrounding and directly adjacent the central region, the intermediate region having a minimum relative refractive index Δ_{2MIN} , and an outer region surrounding and directly adjacent the intermediate region, the outer region having a maximum relative refractive index Δ_{3MAX} , wherein $\Delta_{1MAX} > \Delta_{2MIN}$ and $\Delta_{3MAX} > \Delta_{2MIN}$.

6. The optical fiber of Claim 1 wherein the optical fiber exhibits a cable cutoff of less than 1260 nm.
7. The optical fiber of Claim 1 wherein the optical fiber exhibits a 20 mm macrobend induced loss of less than 0.5 dB/turn at 1550 nm.
8. The optical fiber of Claim 1 wherein the optical fiber exhibits a 10 mm macrobend induced loss of less than 5 dB/turn at 1550 nm.
9. The optical fiber of Claim 1 wherein the optical fiber exhibits a zero dispersion wavelength of less than 1350 nm.
10. The optical fiber of Claim 1 wherein the non-periodically disposed holes have a maximum diameter of less than 2000 nm.
11. The optical fiber of Claim 1 wherein the non-periodically disposed holes have a mean diameter of less than 2000 nm.
12. The optical fiber of Claim 1 wherein the annular hole-containing region has a maximum radial width of less than 10 microns.
13. The optical fiber of Claim 1 wherein the annular hole-containing region has a regional void area percent of less than 20 percent.

14. A microstructured optical fiber for transmitting optical signals comprised of light, the optical fiber comprising:

a core region disposed about a longitudinal centerline, and

a cladding region surrounding the core region, the cladding region comprising an annular hole-containing region comprised of non-periodically disposed holes;

wherein the annular hole-containing region has a maximum radial width of less than 10 microns;

wherein the annular hole-containing region has a regional void area percent of less than 30 percent; and wherein the refractive index of the core is selected to provide: an absolute SBS threshold in dBm greater than about $9.3 + 10\log[(1 - e^{-(0.19)(50)/4.343}) / (1 - e^{-(\alpha)(L)/4.343})]$, wherein L is the length in km and α is the attenuation in dB/km at 1550 nm.

15. The optical fiber of Claim 14 wherein the annular hole-containing region has a maximum radial width of greater than 0.5 microns and less than 10 microns, and the non-periodically disposed holes have a mean diameter of less than 1550 nm.

16. The optical fiber of Claim 14 wherein the annular hole-containing region has a regional void area percent of greater than 0.05 percent and less than 20 percent.

17. The optical fiber of Claim 14 wherein the non-periodically disposed holes have a mean diameter of greater than 1 nm and less than 1550 nm.

18. The optical fiber of Claim 14 wherein the non-periodically disposed holes have a maximum diameter of less than 2000 nm.

19. The optical fiber of Claim 14 wherein said cladding region further comprises:

an inner annular hole-free region disposed between the core region and the annular hole-containing region; and

an outer annular hole-free region surrounding and directly adjacent the annular hole-containing region.

20. The optical fiber of Claim 14 wherein the inner annular hole-free region has a radial width greater than 1 μm .

-1/4

FIG. 1




FIG. 2




FIG. 3





FIG. 4



INTERNATIONAL SEARCH REPORT

International application No
PCT/US2008/002305

A. CLASSIFICATION OF SUBJECT MATTER
INV. G02B6/036 G02B6/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
G02B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2006/039664 A1 (BICKHAM SCOTT R [US] BICKHAM SCOTT ROBERTSON [US] ET AL) 23 February 2006 (2006-02-23) figures 12-15 paragraph [0008]	1-20
X	US 2004/218882 A1 (BICKHAM SCOTT R [US] ET AL) 4 November 2004 (2004-11-04) figures 12-15	1-20
X	US 6 959 135 B1 (BICKHAM SCOTT R [US] ET AL) 25 October 2005 (2005-10-25) * abstract *	1-20
X	WO 2004/100406 A (CORNING INC [US]; BICKHAM SCOTT R [US]; CHOWDHURY DIPAKBIN Q [US]; HOW) 18 November 2004 (2004-11-18) * abstract *	1-20
	-/-	

☒ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

25 June 2008

Date of mailing of the international search report

07/07/2008

Name and mailing address of the ISA/
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Luck, Wulf

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2008/002305

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 1 564 569 A (SAMSUNG ELECTRONICS CO LTD [KR]) 17 August 2005 (2005-08-17) * abstract *	14
A	EP 1 437 612 A (SUMITOMO ELECTRIC INDUSTRIES [JP]) 14 July 2004 (2004-07-14) * abstract *	14
A	WO 03/010576 A (PROXIMION FIBER OPTICS AB [SE]; HELMFRIED STEN [SE]; SAHLGREN BENGT [S]) 6 February 2003 (2003-02-06) * abstract *	14
A	US 2006/120677 A1 (BROENG JES [DK] ET AL) 8 June 2006 (2006-06-08) * abstract *	14
A	EP 1 291 686 A (SUMITOMO ELECTRIC INDUSTRIES [JP]) 12 March 2003 (2003-03-12) * abstract *	14
A	WO 2005/109056 A (PIRELLI & C SPA [IT]; TASSONE FRANCESCO MARIA [IT]) 17 November 2005 (2005-11-17) * abstract *	14
A	EP 1 276 978 A (DELPHI TECH INC [US]) 22 January 2003 (2003-01-22) * abstract *	14
A	WO 03/100488 A (CRYSTAL FIBRE AS [DK]; BROENG JES [DK]; SKOVGAARD PETER M W [DK]; KNUD) 4 December 2003 (2003-12-04) * abstract *	14
A	WO 02/084350 A (CRYSTAL FIBRE AS [DK]; LIBORI STIG EIGIL BARKOU [DK]; BROENG JES [DK];) 24 October 2002 (2002-10-24) * abstract *	14
A	EP 1 426 795 A (SUMITOMO ELECTRIC INDUSTRIES [JP]) 9 June 2004 (2004-06-09) * abstract *	14
A	IL-BUM KWON ET AL: "Analysis of brillouin frequency shift and longitudinal acoustic wave in a silica optical fiber with a triple-layered structure" JOURNAL OF LIGHTWAVE TECHNOLOGY, IEEE SERVICE CENTER, NEW YORK, NY, US, vol. 21, no. 8, 1 August 2003 (2003-08-01), pages 1779-1786, XP011099431 ISSN: 0733-8724 page 1779 - page 1781	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2008/002305

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2006039664 A1	23-02-2006	NONE	
US 2004218882 A1	04-11-2004	NONE	
US 6959135 B1	25-10-2005	WO 2006068914 A2	29-06-2006
WO 2004100406 A	18-11-2004	EP 1620960 A2	01-02-2006
		JP 2006525551 T	09-11-2006
		KR 20060006957 A	20-01-2006
EP 1564569 A	17-08-2005	CN 1654994 A	17-08-2005
		JP 2005227779 A	25-08-2005
		KR 20050081236 A	18-08-2005
		US 2005180710 A1	18-08-2005
EP 1437612 A	14-07-2004	AU 2004200003 A1	29-07-2004
		CN 1542471 A	03-11-2004
		JP 2004220026 A	05-08-2004
		KR 20040064650 A	19-07-2004
		US 2005238308 A1	27-10-2005
		US 2004136669 A1	15-07-2004
WO 03010576 A	06-02-2003	NONE	
US 2006120677 A1	08-06-2006	NONE	
EP 1291686 A	12-03-2003	AU 4693201 A	30-10-2001
		AU 2001246932 B2	22-09-2005
		WO 0179902 A1	25-10-2001
		JP 3786010 B2	14-06-2006
		US 6526209 B1	25-02-2003
WO 2005109056 A	17-11-2005	EP 1745316 A1	24-01-2007
		US 2008138022 A1	12-06-2008
EP 1276978 A	22-01-2003	WO 0179672 A1	25-10-2001
		US 6390078 B1	21-05-2002
WO 03100488 A	04-12-2003	AU 2003229545 A1	12-12-2003
WO 02084350 A	24-10-2002	CA 2443037 A1	24-10-2002
		CN 1535389 A	06-10-2004
		EP 1381894 A1	21-01-2004
		JP 2004522195 T	22-07-2004
EP 1426795 A	09-06-2004	AU 2003262469 A1	17-06-2004
		CN 1504784 A	16-06-2004
		DE 60312291 T2	08-11-2007
		DK 1426795 T3	18-06-2007
		JP 2004177817 A	24-06-2004
		KR 20040047530 A	05-06-2004
		US 2004105640 A1	03-06-2004