



(86) Date de dépôt PCT/PCT Filing Date: 2018/02/01
(87) Date publication PCT/PCT Publication Date: 2018/08/09
(45) Date de délivrance/Issue Date: 2023/11/21
(85) Entrée phase nationale/National Entry: 2019/07/04
(86) N° demande PCT/PCT Application No.: IB 2018/050622
(87) N° publication PCT/PCT Publication No.: 2018/142314
(30) Priorité/Priority: 2017/02/03 (US62/454,110)

(51) Cl.Int./Int.Cl. *B27K 5/00* (2006.01),
B27N 1/02 (2006.01), *C08L 25/04* (2006.01),
C08L 97/00 (2006.01)

(72) Inventeurs/Inventors:
MAYES, DUNCAN, FI;
PYNNONEN, JANNE, FI;
WEST, CHRISTOPHER H., US;
GARDNER, DOUGLAS J., US;
HAN, YOUSOO, US

(73) Propriétaires/Owners:
STORA ENSO OYJ, FI;
UNIVERSITY OF MAINE SYSTEM BOARD OF
TRUSTEES, US

(74) Agent: SMART & BIGGAR LP

(54) Titre : MATERIAU COMPOSITE ET PRODUIT COMPOSITE
(54) Title: A COMPOSITE MATERIAL AND COMPOSITE PRODUCT

(57) Abrégé/Abstract:

The present invention is directed to a composite material comprising a cellulosic material, high impact polystyrene (HIPS) and styrene maleic anhydride (SMA). The cellulosic material may be thermally modified prior to being incorporated into the composite material. The present invention is also directed to a composite product that comprises the composite material according to the invention.



(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property

Organization

International Bureau

(43) International Publication Date

09 August 2018 (09.08.2018)



(10) International Publication Number

WO 2018/142314 A1

(51) International Patent Classification:

B27K 5/00 (2006.01)

C08L 25/04 (2006.01)

B27N 1/02 (2006.01)

C08L 97/00 (2006.01)

Published:

— with international search report (Art. 21(3))

(21) International Application Number:

PCT/IB2018/050622

(22) International Filing Date:

01 February 2018 (01.02.2018)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

62/454,110

03 February 2017 (03.02.2017) US

(71) Applicants: STORA ENSO OYJ [FI/FI]; P.O. Box 309, 00101 Helsinki (FI). UNIVERSITY OF MAINE SYSTEM BOARD OF TRUSTEES [US/US]; 107 Maine Avenue, Bangor, Maine 04401 (US).

(72) Inventors: MAYES, Duncan; Cygnaeuksenkatu 8B, 23, 00101 Helsinki (FI). PYNNÖNEN, Janne; Pienimäentie 5, 37550 Lempäälä (FI). WEST, Christopher H.; 155 Dogtown Road, Detroit, Maine 04929 (US). GARDNER, Douglas J.; 484 Day Road, Brewer, Maine 04412 (US). HAN, Yousoo; 146 Lasalle Drive, Bangor, Maine (US).

(74) Agent: STEINRUD, Henrik; Stora Enso AB, Group IP, Box 9090, 65009 Karlstad (SE).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

(54) Title: A COMPOSITE MATERIAL AND COMPOSITE PRODUCT

(57) Abstract: The present invention is directed to a composite material comprising a cellulosic material, high impact polystyrene (HIPS) and styrene maleic anhydride (SMA). The cellulosic material may be thermally modified prior to being incorporated into the composite material. The present invention is also directed to a composite product that comprises the composite material according to the invention.



WO 2018/142314 A1

A COMPOSITE MATERIAL AND COMPOSITE PRODUCT

Field of the invention

5 The present invention is directed to a composite material comprising a cellulosic material, high impact polystyrene (HIPS) and styrene maleic anhydride (SMA). The cellulosic material may be thermally modified prior to being incorporated into the composite material. The present invention is also directed to a composite product that comprises the composite material according to the invention.

10

Background

15 Traditionally, fences, decks, doors, windows, cladding and siding are made of components fashioned from solid wood. These products are often considered more aesthetically appealing than those made of metal or cement, for example, metal fences or cement block walls or decks. However, after a period of time, solid wood products may naturally begin to break down from weather exposure and biological infestations. It is known that this
20 deterioration can be tempered by treating the wood with widely available weather resistant coatings, paints, varnishes, finishes and the like. Unfortunately, however, treated wood products can often deteriorate within a short period of time requiring partial or complete replacement. Maintenance of many solid wood materials that are suitable for fencing, decking, windows and
25 doors is costly. In addition, because of natural variations in wood, replacement of individual components may result in an inconsistent, uneven appearance to the products.

30 Many products, technologies and ideas are used to make extruded or molded thermoplastics as an alternative to wood in semi-structural outdoor applications such as decking, park walkways, children's playgrounds, seats and benches. The thermoplastic most widely used is polyethylene, typically a recycled product from HDPE, LDPE & LLDPE milk bottles, film etc. Other thermoplastics widely used include polystyrene, impact modified polystyrene,

PVC and polypropylene. Many systems also use inorganic fillers such as calcium carbonate, and talc or cellulosic filler, typically wood or other natural fibers, compounded into the thermoplastic to enhance properties and make the compound look more like the wooden lumber it replaces. These systems
5 are rapidly gaining market acceptance, especially in decks where they have advantages of long-term durability and reduced maintenance. They have an additional advantage because of recent health concerns regarding the chemicals and preservatives used to treat wood for outdoor applications and in view of the scarcity of durable hardwoods.

10

Many composites, such as cellulosic/polymer composites are used as replacements for all-natural wood, particleboard, wafer board, and other similar material. For example, US 3,908,902; US 4,091,153; US 4,686,251; US 4,708,623; US 5,002,713; US 5,087,400; US 5,151,238; US 5,417,904;
15 US 5,948,524; US 6,280,667; US 6,827,995 and US 6,936,200 relate to processes for making plastic/cellulose wood replacement products.

20

Solid composites of styrene-maleic anhydride and wood-based fillers are disclosed in US 3,765,934; US 3,894,975 and US 3,958,069; Canadian
Published Patent Application No. 2,626,992 A1 and "Properties of Styrene-Maleic Anhydride Copolymers Containing Wood-Based Fillers", Simonsen et al., Forest Products Journal, Vol. 48, No. 1, pp. 89-92, January, 1998.

25

As compared to natural woods, cellulosic/polymer composites offer superior resistance to wear and tear. In particular, cellulosic/polymer composites have enhanced resistance to moisture. In fact, it is well known that the retention of moisture is a primary cause of the warping, splintering, and discoloration of natural woods. Moreover, cellulosic/polymer composites have the appearance of natural wood, and they may be sawn, sanded, shaped, turned, fastened,
30 and finished in the same manner as natural woods. Cellulosic/polymer composites also have better surface wear resistance than solid wood, especially in applications like flooring and decking where regular abrasion occurs. Consequently, cellulosic/polymer composites are commonly used for applications such as interior and exterior decorative house moldings, picture
35 frames, furniture, porch decks, deck railings, window moldings, window components, door components, roofing structures, building siding and cladding, and other suitable indoor and outdoor components. Furthermore,

cellulosic/polymer composites may replace highly durable and scarce hardwoods, e.g. tropical hardwoods.

Those skilled in the art have recognized that excessive moisture content in a synthetic wood composition may result in a poor quality end product. In particular, excessive moisture content in a synthetic wood composition may result in an end component that is susceptible to swelling, cracking, and crumbling appearance. Consequently, it may be necessary to dry cellulosic material to a predetermined level prior to introducing it into the synthetic wood composition. Even after the cellulosic material is dried, it has a natural tendency to reabsorb moisture from the environment. As a result, it may also be necessary to store the dried cellulosic material in a moisture controlled environment to prevent the cellulosic material from reabsorbing additional moisture before being added to the synthetic wood composition. In light of these considerations, it may be difficult and costly to maintain sufficiently dry cellulosic material while shipping it between different locations.

Plastic fence components have been developed as alternatives or supplements to traditional, natural wood fences. For example, US 5,100,109 describes a method of constructing a fence by providing a flexible, plastic, rollable fence board that can be unrolled and fastened to spaced apart fence posts. The flexible fence board is made with height and width dimensions simulating a standard wooden board and with a length of 350 feet or more. According to this patent, the fence board is formed in a continuous extrusion process of a flexible thermoplastic material.

US 5,404,685 describes a wall or fence made in part of foamed polystyrene plastic components, more specifically, plastic columns and panels. Construction of a fence in accordance with this patent requires multiple steps. For example, wall or fence stability is achieved by pouring a reinforcing filler material, such as concrete, into a hollow of the polystyrene plastic columns after the columns have been secured to the ground. A hardened outer surface of the fence is achieved by applying an exterior finish, such as stucco or special exterior paint, to the fence or wall after the fence has been constructed.

However, the synthetic wood or wood composite products described above,

typically have disadvantages when their mechanical properties, especially when strength and stiffness are compared with the wood they replace.

Further, the wood/cellulosic composites described above are susceptible to creep when subjected to continuous loads and/or high ambient temperatures.

5 Additionally, these materials tend to warp after long term exposure to heat. Because of these structural limitations, the use of the synthetic wood products described above is often restricted to less structural applications. For example, in decks they are used for deck boards but typically cannot be used for the vertical posts and joists that bear the loads of the whole structure.

10 However, compared to products made of thermoplastic polymers, which typically have a high coefficient of thermal expansion, wood/cellulosic composites generally have improved thermal stability. Pure thermoplastic polymers have a high level of thermal expansion. The introduction of lignocellulosic fiber to the polymer reduces the thermal expansion coefficient.

15

US 8,221,663 describes a method of making foamed articles having a density of not more than 1.3 g/cm³.

20 One problem related to methods for preparing polymer-wood compositions is to ensure that the conditions are such that articles with desired properties, such as thermoplastic weldability, can be achieved. In some embodiments, it is important to be able to obtain symmetrical articles having fine details and specific profiles and shapes. A further problem relates to ensuring that a sufficiently high proportion of cellulosic fiber can be used, yet resulting in an
25 article with the desired properties.

Thus, there is a need in the art to provide composite materials and composite product that overcome the above-described problems, as well as methods of making such composite materials and composite products.

30

Summary of the invention

35 It is an objective of the present invention to provide a composite material comprising cellulosic fiber having improved properties, such as improved strength and stiffness properties as well as low creep.

Another object of the present invention is to provide a composite product comprising such a composite material.

5 These objectives and other advantages are achieved by the present invention.

10 The present invention is directed to a composite material comprising at least 20% by weight of a cellulosic material, at least 1% by weight and less than 20% by weight of styrene maleic anhydride and from 5% to 50% by weight of a high impact polystyrene. In one embodiment of the present invention, the composite material may comprise other fillers such as calcium carbonate and other inorganic fillers.

15 The cellulosic material may be thermally modified cellulosic material. The thermal modification is carried out by heat treatment, preferably at a temperature between 160-250°C, preferably between 200-230°C at atmospheric pressure or at a temperature above 120°C at an elevated pressure according to methods known in the art.

20 The composite material comprises at least 20% by weight of cellulosic material, preferably between 25-75% by weight and even more preferably between 40-65%, 45-65% or between 50-60% by weight of cellulosic material.

25 In one embodiment, the composite material comprises at least 2% and less than 20% by weight, such as from 2% to 15% by weight or from 2% to 10%, 5% to 10% or 2% to 7% by weight of styrene maleic anhydride (SMA).

30 The cellulosic material may consist of a single form of cellulosic material or for example a mixture of different types of fibers. The cellulosic material may for example be provided in the form of wood particles or pulp. Examples of pulp include mechanical pulp, semi-mechanical or chemical pulp, such as thermomechanical pulp, chemithermomechanical pulp or chemical pulp (manufactured in the kraft or sulfite process) or dissolving pulp. The wood
35 particles may for example be ground wood, wood flour or sawdust. The cellulosic material may be compacted before being used to prepare the composite material according to the present invention.

The cellulosic material may have a particle size below 1 mm, preferably below 0.50 mm and even more preferably below 0.25 mm or below 0.1 mm. It is preferred that the cellulosic material has a small size since a more even
5 dispersion and distribution of the cellulosic material in the composite material is achieved. If the cellulosic material is in the form of cellulosic fibers, the fibers preferably has a fiber length below 1 mm, preferably below 0.50 mm and even more preferably below 0.25 mm or below 0.1 mm.

10 The cellulosic material may be in the form of a powder. Thus, the cellulosic material may comprise cellulosic fibers that have been mechanically treated to produce a powder. The size of the cellulosic material is of importance to be able to obtain a composite material where the cellulosic material is evenly distributed. It has been found that if the cellulosic material is in the form of a
15 powder it is easy to achieve a good dispersion and mixture with the polymer.

The high impact polystyrene (HIPS) can be for example a graft copolymer of wherein polybutadiene has been added during polymerization to become chemically bonded to the polystyrene and which has subsequently been
20 mixed with normal polybutadiene. HIPS is commercially available, for example under the name Bextrene.

The SMA (styrene maleic anhydride) is a synthetic polymer that is built up of styrene and maleic anhydride monomers.
25

The present invention also relates to a process for producing a composite product which process comprises the steps of: providing a cellulosic material, high impact polystyrene (HIPS) and styrene maleic anhydride (SMA), feeding said cellulosic material, HIPS and SMA to an extruder and extruding the
30 composite product.

The temperature used in the extruder is preferably above 180°C.

35

The present invention is also directed to a composite material comprising: at least 20% by weight of a cellulosic material, at least 1% by weight and less than 20% by weight of styrene maleic anhydride, and from 5% to 50% by weight of a high impact polystyrene, wherein the cellulosic material is a thermally modified cellulose material that has been

5 thermally modified by heat treatment either at a temperature between 160-250°C at atmospheric pressure or at a temperature above 120°C at a pressure greater than atmospheric pressure.

The present invention also relates to a process for producing a composite product which process comprises the steps of: a) providing a cellulosic material, high impact

10 polystyrene (HIPS) and styrene maleic anhydride (SMA), wherein the cellulosic material is a thermally modified cellulose material that has been thermally modified by heat treatment at a temperature between 160-250°C at atmospheric pressure or at a temperature above 120°C at a pressure greater than atmospheric pressure, b) feeding said cellulosic material, HIPS and SMA to an extruder, and c) extruding the composite

15 product.

Detailed description

The present invention relates to a composite material comprising cellulosic material, high impact polystyrene (HIPS) and styrene maleic anhydride (SMA). It has surprisingly been found that the composite material according to the present invention provides enhanced strength and stiffness properties.

The process ability of the composite material according to the present invention is suitable for high strength composite profiles for applications such as windows and doors and heavier infrastructure applications where normal wood-polymer composites and plastics are not suitable.

The improved strength and stability observed is enhanced by an esterification reaction between the cellulosic material and matrix components. In one embodiment of the present invention, the gravimetric density of the composite material and composite product is higher than 1.0 g/cm³, such as higher than 1.3 g/cm³.

Furthermore, by using thermally modified cellulosic material in the composite, it has been found that a composite having particularly advantageous strength properties is achieved.

With thermally modified cellulosic material, it is meant that the cellulosic material has been thermally treated at an increased temperature between 160-250°C at atmospheric pressure or at a temperature above 120°C at an elevated pressure of above 1 bar. The cellulosic material can be thermally treated cellulosic fibers of any kind of cellulosic wood material. The thermally modified cellulosic fibers may be further treated to form said thermally modified cellulosic material, e.g. mechanically treated and/or chemically treated. The mechanical treatment of the thermally treated cellulosic fibers may be done to form a powder and one of the advantages with mechanically treating thermally modified cellulosic fibers are that they easily break into very small particles with unique shape. Size and shape are key parameters influencing numerous composite properties, such as strength and water uptake. Because of the very fine particle size and lack of resin compared to what is found in normal dried wood the risk of fiber bundling is greatly reduced when adding the thermally modified cellulosic material to the polymer

to form the composite material, which in turn leads to more even dispersion and distribution. Chemical treatment of the thermally treated cellulosic fibers may be done to improve the reactivity of the material. It may also be possible to thermally treat cellulosic fibers that have been mechanically or chemically treated, e.g. to thermally treat cellulosic fiber that have been ground into a powder.

The composite material may also comprise additives that will enhance the performance and process parameters of the composite. Possible additives may be lubricants, coupling agents, pigments, uv-stabilizers or blockers and/or fillers. In one embodiment of the present invention, the composite material comprises a flame retardant.

The present invention also relates to a process for producing a composite product which process comprises using an extruder to manufacture the composite product. It is possible to use any kind of extruder.

The composite material according to the present invention may for example be produced in the form of pellets or granules, using a compounding extruder. Such pellets or granules can be used to manufacture a composite product comprising the composite material. Such composite products can for example be manufactured by extrusion, injection moulding, rota moulding, 3D printing or form pressing. The composite material may also be produced in the form of a shaped composite product, for example by providing a profile die through which a shaped composite product is extruded. Such profiled composite products may be produced in variety of shapes and for multiple purposes.

The produced composite product can be used for the production of many different products, such as cladding, decking, window and door profiles, light poles, jetties, joinery, furniture etc. The produced composite products may be used for applications such as interior and exterior decorative house moldings, picture frames, furniture, porch decks, deck railings, window moldings, window components, door components, roofing structures, building siding and cladding, and other suitable indoor and outdoor components. The composite material and composite products according to the present invention may also be useful in shoring as well as in marine environments such as submerged structures. Furthermore, cellulosic/polymer composites according to the

present invention may replace highly durable and scarce hardwood, e.g. tropical hardwood.

5 Examples

Abbreviations:

SMA: styrene maleic anhydride (Xiran from Polyscope)

10 TW: thermally modified cellulosic material

HIPS: high impact polystyrene

MOE: modulus of elasticity

STD: standard deviation

WPC: wood-polymer composite

15 Avg: average

COV: coefficient of variance

Example 1

20

In this experiment, the mechanical properties of composite products comprising a composite material according to the present invention were investigated.

25 Thermally modified wood (HTW) fibers were used. The fibers were shavings from pine that had been thermally modified by heating to 212°C for 3 hours and subsequently ground in a hammer mill and passed through a screen.

The following formulations where prepared:

30

Table 1. Formulations of samples, % by weight.

Sample	Content of cellulosic material	SMA content	HIPS content
Control-pine	Pine 50%	0%	50%
SMA-0%	TW 50%	0%	50%
SMA-2.5%	TW 50%	2.5%	47.5%
SMA-5.0%	TW 50%	5.0%	45.0%
SMA-7.5%	TW 50%	7.5%	42.5%
SMA-10.0%	TW 50%	10.0%	40.0%
SMA-12.5%	TW 50%	12.5%	37.5%
SMA-15.0%	TW 50%	15.0%	35.0%

- 5 The specifications of the pilot extrusion system were as follows: with the following process parameters used in the extruder:

Table 2. Extrusion parameters, Woodtruder equipment. The cellulosic fibers were direct fed to the twin screw and the SMA was added via the single screw. Decking board composite products were produced.

Die part				WT 94 Twin-screw extruder										
Die 3	Die 2	Die 1	Clamp	Zone8	Zone7	Zone6	Zone5	Zone4	Zone3	Zone2	Zone1	RPM	Melt P.	Melt T.
200	200	200	210	200	190	190	185	180	180	170	165	37	psi	193
Output rate		Vacuum		T75 Single-screw extruder										
Lbs/hr		Inches Hg		Clamp	Adapt	Zone5	Zone4	Zone3	Zone2	Zone1		RPM	Melt P.	Melt T.
72 ~75		30 inch		210	210	210	200	195	190	185		17	psi	205

- 15 The flexural properties (flexural strength and flexural modulus) were determined for the samples:

Table 3. Flexural properties of samples and control/comparative samples.

Sample	Strength		MOE	
	Average, MPa	STD	Average, MPa	STD
Control-pine	31.07	1.36	4688	425
SMA-0%	31.26	1.17	5849	170
SMA-2.5%	45.71	3.26	6888	268
SMA-5%	49.82	1.80	6865	237
SMA-7.5%	50.26	1.80	6431	237
SMA-10%	50.29	1.99	6110	328
SMA-12.5%	49.85	2.86	5660	083
SMA-15%	49.01	2.14	5531	117
Foamed SMA-WPC*	24.82	-	3534	-
Commercially available WPC**	19.99	-	1379	-

* data from decking board samples made of NovaChem SMA and pine wood;
wood content 30% and specific gravity was 0.85

** commercially available product (polypropylene/polyethylene and 50% by weight of normal sawdust); data from technical data sheet of commercially available WPC

Example 2

The dimensional stability of the samples was determined.

The samples were first conditioned at room temperature and then immersed into water for a total of 28 days. The dimensional measurements were conducted at 24 hours, 7 days, 14 days, 21 days and 28 days for the water absorption and dimensional changes of width, length and thickness.

Table 4. Weight gain percentage of the samples soaked in water.

Sample	24 hours		7 days		14 days		21 days		28 days	
	Avg	COV	Avg	COV	Avg	COV	Avg	COV	Avg	COV
SMA 0%	0.085	4.47	0.525	2.38	0.822	2.16	1.131	3.54	1.222	3.07
SMA 2.5%	0.056	33.81	0.472	25.59	0.705	18.27	0.936	15.67	0.991	10.6
SMA 5%	0.049	36.39	0.381	16.89	0.613	13.91	0.817	3.35	0.884	9.62
SMA 7.5%	0.044	6.57	0.336	3.13	0.567	3.28	0.793	3.05	0.847	3.01
SMA 10%	0.051	11.07	0.363	8.16	0.568	8.71	0.799	6.12	0.884	7.23
SMA 12.5%	0.055	12.77	0.363	3.47	0.572	2.68	0.811	2.27	0.886	1.62
SMA 15%	0.058	8.70	0.355	1.63	0.603	2.09	0.818	1.83	0.888	1.08
Control- pine	0.300	13.39	1.385	8.59	2.028	7.80	2.646	7.49	2.817	7.61

Table 5. Dimensional change (thickness swelling), percentage, samples soaked in water.

Sample	24 hours		7 days		14 days	
	Avg	COV	Avg	COV	Avg	COV
SMA 0%	0.510	12.420	0.742	15.270	0.888	2.080
SMA 2.5%	0.474	19.440	0.612	17.780	0.668	15.610
SMA 5%	0.523	9.750	0.650	13.840	0.706	12.110
SMA 7.5%	0.531	8.470	0.617	9.440	0.690	9.740
SMA 10%	0.479	17.580	0.563	18.340	0.650	14.190
SMA 12.5%	0.420	18.240	0.540	9.840	0.612	7.820
SMA 15%	0.392	10.300	0.532	8.750	0.616	8.410
Control-pine	1.011	6.460	1.518	6.550	1.836	6.680

5

Sample	21 days		28 days	
	Avg	COV	Avg	COV
SMA 0%	0.955	9.050	1.041	6.86
SMA 2.5%	0.685	16.800	0.769	21.43
SMA 5%	0.770	13.680	0.809	13.13
SMA 7.5%	0.748	10.750	0.750	10.63
SMA 10%	0.712	12.770	0.768	13.62
SMA 12.5%	0.689	8.090	0.730	7.31
SMA 15%	0.680	9.500	0.728	7.38
Control-pine	2.150	8.440	2.245	8.23

10 It was found that the samples with thermally modified cellulosic material had less water absorption (weight gain) and dimensional changes compared to the sample made with regular pine.

The content of SMA significantly affected the water absorption (weight gain) and dimensional changes of the sample.

5 Example 3

The coefficient of thermal expansion (CTE) was determined in accordance with ASTM Standard D 696 and compared to other conventional plastic and composite products. The CTE is measured for two directions, lengthwise
10 (extrusion direction) and widthwise (cross direction to the extrusion).

Table 6. CTE values of the samples

Sample	CTE		
	Avg	STD	COV
Control-pine-length	2.76 E-05	5.16 E-06	18.71
Control-pine-width	6.96 E-05	2.23 E-07	0.32
SMA-0%-length	4.86 E-05	3.65 E-06	7.51
SMA-0%-width	6.94 E-05	3.07 E-06	4.42
SMA-2.5%-length	2.40 E-05	2.13 E-06	8.88
SMA-2.5%-width	6.62 E-05	2.16 E-06	3.26
SMA-5.0%-length	2.51 E-05	2.61 E-06	10.42
SMA-5.0%-width	6.68 E-05	7.61 E-07	1.14
SMA-7.5%-length	2.30 E-05	9.67 E-08	0.42
SMA-7.5%-width	6.65 E-05	1.32 E-06	1.98
SMA-10%-length	2.29 E-05	5.74 E-07	2.51
SMA-10%-width	6.72 E-05	4.77 E-07	0.71
SMA-12.5%-length	2.02 E-05	2.16 E-07	1.07
SMA-12.5%-width	6.47 E-05	1.15 E-06	1.77
SMA-15%-length	2.07 E-05	1.75 E-06	8.47
SMA-15%-width	6.46 E-05	3.48 E-06	5.39
PVC profile*	5.0 E-05		
Commercially available WPC**	2.0 E-05		

15

* the CTE value of the PVC profiles is assumed being lengthwise expansion unless the manufacturers mention the expansion direction.

** the CTE value of a commercially available WPC is assumed to be lengthwise expansion

- 5 It was found that the samples according to the present invention showed coefficient of thermal expansion similar to commercially available WPC and about 50% of a PVC profile which is a major advantage.
It was found that the CTE for extrusion (lengthwise) direction is much less than cross (widthwise) direction.

10

It was found that the samples with thermally modified cellulosic material showed lower CTE values than with the normal pine.

It was found that the content of SMA contributed to lower CTE of the samples.

15

Example 4

- 20 A study was carried out to estimate the feasibility of painting on the surfaces of composite products according to the present invention.

The following samples were prepared (weight-%):

Sample	Description	Note
HIPS-TW-WPC-SMA 2.5%	HIPS 47.5% with TW 50% / SMA 2.5%	Cut from decking boards
HIPS-TW-WPC-SMA 5.0%	HIPS 45% with TW 50% / SMA 5.0%	Cut from decking boards
HIPS-TW-WPC-SMA 10%	HIPS 40% with TW 50% / SMA 10%	Cut from decking boards
HIPS-TW-WPC-SMA 15%	HIPS 35% with TW 50% / SMA 15%	Cut from decking boards

25

SMA: styrene maleic anhydride (Xiran from Polyscope)

TW: thermally modified cellulosic material (*)

HIPS: high impact polystyrene

(*)_The fibers were shavings from pine that had been thermally modified by heating to 212°C for 3 hours and subsequently ground in a hammer mill and passed through a screen.

5 The painting/coating conditions were as follows:

	Paint brand	NuCoat water-based
	Paint product name	Super anti-heat Signal Black & Bar Red
10	Surface preparation	Scrubbed with Scotch Brite and wiped down with Zowo-Plast 1120 or used as supplied
	Spray rate	Spray booth 75° with 1.8 nozzle size
	Spray pressure	55 psi
	Room condition	Room temperature under RH 39%
	Cure temperature	90.5°F with RH 21%
15	Cure time	24 hours

Test method: ASTM D4541, Standard test method for pull-off strength of coatings using portable adhesion testers, was used. The portable adhesion
 20 tester was a pull-off tester, Model PosiTest AT-M from DeFelsko.

The following results were obtained:

Sample	Average pull-off stress
HIPS-TW-WPC-SMA 2.5%	237 psi
HIPS-TW-WPC-SMA 5.0%	312 psi
HIPS-TW-WPC-SMA 10%	335 psi
HIPS-TW-WPC-SMA 15%	373 psi

25

The pull-off test was conducted on the hard surfaces with and without treatment to evaluate the topological properties of the sample surfaces. The surface treatment was conducted by scrubbing the surface using Scotch Brite® sponges and wiped down with Zowo-Plast 1120, a water-
 30 based/biodegradable cleaning agent for cleaning and preparing prior to coating.

The following results were obtained for the treated surfaces:

Sample	Average pull-off stress
HIPS-TW-WPC-SMA 2.5%	555 psi
HIPS-TW-WPC-SMA 5.0%	463 psi
HIPS-TW-WPC-SMA 10%	677 psi
HIPS-TW-WPC-SMA 15%	646 psi

5 The pull-off stress of all samples are very high which represents the painting-ability of the composite products according to the present invention. As shown above, the SMA content and the surface treatment affect the bonding strength.

10 In view of the above detailed description of the present invention, other modifications and variations will become apparent to those skilled in the art. However, it should be apparent that such other modifications and variations may be effected without departing from the spirit and scope of the invention.

CLAIMS:

1. A composite material comprising:
at least 20% by weight of a cellulosic material,
at least 1% by weight and less than 20% by weight of styrene maleic anhydride,
5 and
from 5% to 50% by weight of a high impact polystyrene,
wherein the cellulosic material is a thermally modified cellulose material that has been
thermally modified by heat treatment either at a temperature between 160-250°C at
atmospheric pressure or at a temperature above 120°C at a pressure greater than
10 atmospheric pressure.
2. The composite material according to claim 1, wherein the cellulosic material has
been thermally modified by heat treatment at a temperature between 200-230°C at
atmospheric pressure.
3. The composite material according to claim 1, wherein the cellulosic material has
15 been thermally modified by heat treatment at a temperature above 120°C at a pressure
greater than atmospheric pressure.
4. The composite material according to any one of claims 1-3, wherein the
composite material comprises from 2% to 15% by weight of the styrene maleic
anhydride.
- 20 5. The composite material according to any one of claims 1-3, wherein the
composite material comprises from 5% to 10% by weight of the styrene maleic
anhydride.
6. The composite material according to any one of claims 1-5, wherein the
composite material comprises 25-75% by weight of the cellulosic material.
- 25 7. The composite material according to any one of claims 1-5, wherein the
composite material comprises 40-65% by weight of the cellulosic material.
8. The composite material according to any one of claims 1-5, wherein the
composite material comprises 45-65% by weight of the cellulosic material.

9. The composite material according to claim 8, wherein the composite material comprises 50-60% by weight of the cellulosic material.
10. The composite material according to any one of claims 1-9, wherein the composite material comprises 35-50% by weight of the high impact polystyrene.
- 5 11. The composite material according to any one of claims 1-10, wherein the cellulosic material has a particle size below 1 mm.
12. The composite material according to any one of claims 1-11, wherein the cellulosic material is in the form of a powder.
- 10 13. A composite product comprising the composite material as defined in any one of claims 1-12.
14. The composite product according to claim 13, for use in cladding, decking, window and door profiles, light poles, jetties, joinery, or furniture.
15. A process for producing a composite product which process comprises the steps of:
- 15 a) providing a cellulosic material, high impact polystyrene (HIPS) and styrene maleic anhydride (SMA), wherein the cellulosic material is a thermally modified cellulose material that has been thermally modified by heat treatment at a temperature between 160-250°C at atmospheric pressure or at a temperature above 120°C at a pressure greater than atmospheric pressure;
- 20 b) feeding said cellulosic material, HIPS and SMA to an extruder; and
- c) extruding the composite product.