



(86) **Date de dépôt PCT/PCT Filing Date:** 2014/01/17
(87) **Date publication PCT/PCT Publication Date:** 2014/07/24
(85) **Entrée phase nationale/National Entry:** 2015/07/09
(86) **N° demande PCT/PCT Application No.:** EP 2014/050958
(87) **N° publication PCT/PCT Publication No.:** 2014/111549
(30) **Priorité/Priority:** 2013/01/18 (EP13305069.0)

(51) **Cl.Int./Int.Cl.** **C08J 5/18** (2006.01),
B32B 27/30 (2006.01), **C08L 23/04** (2006.01)

(71) **Demandeur/Applicant:**
SARTORIUS STEDIM FMT SAS, FR

(72) **Inventeurs/Inventors:**
BARBAROUX, MAGALI, FR;
DELAUNAY, LUCIE, FR;
HUSEMANN, UTE, DE;
GRELLER, GERHARD, DE

(74) **Agent:** GOUDREAU GAGE DUBUC

(54) **Titre : FILM MULTICOUCHE COMPRENANT UNE COUCHE D'AME ET UNE COUCHE EXTERIEURE POUR LA PAROI D'UN
SACHET A USAGE UNIQUE**

(54) **Title: FILM COMPRISING A CONTACT LAYER FOR THE WALL OF A SINGLE-USE POUCH**

(57) **Abrégé/Abstract:**

The present invention relates to a multilayer film for manufacturing a pouch, said multilayer film comprising: a core layer, and an outer layer, wherein: the outer layer and the core layer are made integral with a tie layer, the core layer comprises (C) an ethylene vinyl alcohol copolymer having a content of ethylene in the range of 25 to 48 mol %, alone or in mixture with (D) an ionomer acid ethylene copolymer, the outer layer comprises (E) a polyolefin having a density in the range of 0.910g/cm³ to 0.940 g/cm³ or (F) a copolymer of ethylene and α -olefin having a density in the range of 0.870 g/cm³ to 0.910 g/cm³, or a mixture thereof, the tie layer comprises (G) a copolymer of polyolefin grafted with a carboxylic acid or an anhydride of carboxylic acid, alone or in mixture with (H) a copolymer of polyolefin. The invention also relates to the process for manufacturing such a film, as well the single-use pouch manufactured from that film.



(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

CORRECTED VERSION

(19) World Intellectual Property
Organization
International Bureau



WIPO | PCT



(10) International Publication Number
WO 2014/111549 A9

(43) International Publication Date
24 July 2014 (24.07.2014)

(51) International Patent Classification:
C08J 5/18 (2006.01) *C08L 23/04* (2006.01)

(21) International Application Number:
PCT/EP2014/050958

(22) International Filing Date:
17 January 2014 (17.01.2014)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
13305069.0 18 January 2013 (18.01.2013) EP

(71) Applicant: SARTORIUS STEDIM FMT SAS [FR/FR];
Avenue de Jouques, ZI des Paluds, F-13400 Aubagne
(FR).

(72) Inventors: BARBAROUX, Magali; Quartier des Tis-
serands, F-13112 La Destrousse (FR). DELAUNAY,
Lucie; Res. Les Patios d'Anais, Pont de l'Etoile, F-13360
Roquevaire (FR). HUSEMANN, Ute; Südring 10, 37079
Göttingen (DE). GRELLER, Gerhard; Adolf-Sievert-Str.
50, 37085 Göttingen (DE).

(74) Agents: ROCABOY, Nadine et al.; Cabinet Plasseraud,
52 rue de la Victoire, F-75440 Paris Cedex 09 (FR).

(81) Designated States (*unless otherwise indicated, for every
kind of national protection available*): AE, AG, AL, AM,
AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY,
BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM,
DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT,

HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR,
KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME,
MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ,
OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA,
SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM,
ZW.

(84) Designated States (*unless otherwise indicated, for every
kind of regional protection available*): ARIPO (BW, GH,
GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ,
UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ,
TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK,
EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV,
MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM,
TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,
KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(88) Date of publication of the revised international search
report:

31 December 2014

(48) Date of publication of this corrected version:

16 April 2015

(15) Information about Corrections:
see Notice of 16 April 2015

Previous Correction:
see Notice of 31 December 2014

(54) Title: FILM COMPRISING A CONTACT LAYER FOR THE WALL OF A SINGLE-USE POUCH

(57) Abstract: The present invention relates to a film for manufacturing a pouch, said film comprising a contact layer comprising (A) a copolymer of ethylene and a-olefin having a density in the range of 0.870 g/cm³ to 0.910 g/cm³, alone or in mixture with (B) a polyolefin having a density in the range of 0.910 g/cm³ to 0.940 g/cm³, said contact layer comprising less than 0.10 wt %, preferably less than 0.07 wt %, of additives able to release a degradation compound further to gamma irradiation in the range of 25 kGy - 50 kGy that can slow down or delay cellular growth. The invention also relates to the process for manufacturing such a film, as well the single-use pouch manufactured from that film.



WO 2014/111549 A9

Film comprising a contact layer for the wall of a single-use pouch

Field of the invention

5 The invention relates to a film for the wall of a single-use pouch which may be used for preparing, storing or conveying a cell media or a cell culture, as well as a process for manufacturing such a film.

The invention is in particular directed to a film comprising a contact layer suitable for being in contact with biopharmaceutical products without degrading said biopharmaceutical products. Preferably, the film of the
10 invention is a monolayer film.

The invention also relates to the single-use pouch manufactured from that film and its process of manufacturing.

15 Background

Single-use pouches are widely used in the field of cell culture, for instance in single-use bioreactors or for storing or conveying cell fluids, such as cell medium or cell culture.

20 Such pouches may comprise two large walls sealed to one another. Once expanded, they have a limited volume and remain relatively thin, which justifies the fact that they are often called 2D pouches (D meaning dimensions). 3D pouches are also known that comprise two end walls and a side wall that can be folded flat or deployed unfolded, sealed to one another, with the volume able to reach 3,000 liters, and even more. Such 3D pouches are described in the document WO00/04131 or are marketed by the company Sartorius
25 under the trademark FLEXEL® 3D.

The wall of a single-use pouch is generally composed of a multilayer film comprising a contact layer which in contact with the medium that fills the pouch, a barrier layer and an outer layer which is in contact with the external environment of the bag, the three layers being connected one to each other with a tie layer.
30

If the pouch is to be filled with a biopharmaceutical product, the contact layer should be made from a material that can be in contact with this biopharmaceutical product without causing degradation of the film and of the biopharmaceutical product. Furthermore, it must be sealable on itself. For that purpose, the material is generally selected from polyolefins, such as polyethylene.
35

The barrier layer provides a barrier to the passage of gases such as oxygen, carbon dioxide and is typically made from ethylene vinyl alcohol (EVOH).

The outer layer contributes to the mechanical strength of the pouch wall. For that purpose, it must be sufficiently flexible to withstand high mechanical stress but not be too much stretchable in order to prevent deformation of the pouch when it is filled with a product.
40

In the bioreactor field, the various systems mainly differ by their mode of stirring, which may involve a swinging movement, an orbital movement or an axial movement. Mechanical stresses may hence vary significantly from one system to another. In the liquid transport field, the mechanical stresses may also be
45

very high. In both fields, a film which is not able to withstand these mechanical stresses may result in leakage of the product outside the pouch.

5 Therefore, there is a need for a film which is able to withstand various mechanical stresses in order to be usable in a wide range of applications, such as in bioreactors whatever the mode of stirring, for preparing a solution either by liquid/liquid or solid/liquid stirring, for storing or conveying a fluid in a 2D or 3D pouch, for both small or large volumes.

10 Moreover, in the biopharmaceutical field, the single-use pouches are to be sterilized before use. Sterilization is generally performed either by gamma irradiation or by ethylene oxide treatment. Therefore, the material used in the various films composing the pouch should be able to withstand gamma radiation or ethylene oxide treatment without degrading their physical properties.

15 In the case of pouches whose contact film is made from polyethylene, the applicant of the present patent application has found that when gamma irradiation was used to sterilize the pouch, the cellular growth of a cell culture prepared in that pouch could be slowed down, in particular due to a lag phase occurring at the beginning of the cell culture.

20 Following extensive testing, the applicant of the present application has further found that this lag phase was in part due to a compound which is released by the contact film into the culture medium, said compound resulting from the degradation of an anti-oxidant of said contact film during the gamma irradiation of the pouch.

25 Therefore, there is also a need for a film which has no or limited impact on the cellular growth of a culture medium further to sterilization by gamma irradiation. In particular, there is a need for a film which releases no significant amounts of degradation compound further to gamma irradiation, said degradation compound being able to interfere with cellular growth.

Summary of the invention

30 The invention meets all these needs by providing a film for a single-use pouch, which shows remarkable mechanical properties, thereby allowing a wide range of applications, and which furthermore has no or limited impact on the cellular growth further to sterilization by gamma irradiation, thereby making it particularly suitable for preparing, storing or conveying a cellular medium.

35 One object of the present invention is a film for manufacturing a pouch, said film comprising a contact layer comprising (A) a copolymer of ethylene and α -olefin having a density in the range of 0.870 g/cm³ to 0.910 g/cm³, alone or in mixture with (B) a polyolefin having a density in the range of 0.910 g/cm³ to 0.940 g/cm³ said contact layer comprising less than 0.10 wt %, preferably less than 0.07 wt %, of additives able to
40 release a degradation compound further to gamma irradiation in the range of 25 kGy - 50 kGy, that can slow down or delay cellular growth.

In one embodiment, the additives able to release a degradation compound further to gamma irradiation that can slow down or delay cellular growth are antioxidants.

45

In one embodiment, said antioxidant is phosphite antioxidant.

In one embodiment, said antioxidant is tris(2,4-ditert-butylphenyl) phosphite.

- 5 In one embodiment, copolymer (A) is a plastomer polyolefin having from 4 to 8 carbon atoms, in particular a linear low density copolymer of ethylene and oct-1-ene made from a process utilizing a metallocene catalyst.

In one embodiment, polyolefin (B) is a homopolymer of ethylene, in particular a low density polymer of ethylene.

10

In one embodiment, the contact layer comprises a mixture of (A) and (B) with a mass ratio (B)/(A) less than or equal to 95/5, preferably in the range of 5/95 to 95/5, more preferably in the range of 0.2 to 5, even more preferably in the range of 0.2 to 2.

- 15 In one embodiment, the film of the invention is monolayer.

In one embodiment, the film of the invention is a multilayer film comprising one or several layers in addition to the contact layer, in particular a core layer able to provide a barrier to the passage of gases such as oxygen or carbon dioxide, an outer layer, wherein the contact layer and core layer are made integral with a first tie layer, and the outer layer and core layer are made integral with a second tie layer.

20

Another object of the present invention is a process for manufacturing the film of the invention, comprising extrusion of the contact layer.

- 25 Another object of the present invention is a process for manufacturing the multilayer film of the invention, comprising cast coextrusion of the contact layer, first tie layer, core layer, second tie layer and outer layer.

Another object of the present invention is a single-use pouch whose wall comprises the film of the invention.

- 30 Another object of the present invention is a bioreactor comprising the single-use pouch of the invention.

Detailed description of the invention

Unless otherwise mentioned, the density of polymers referred to in the present application is as measured according to the Standard Test Method ASTM D792 – 08.

- 35 According to the present invention, the expression “made integral with” means that the two layers are attached together either directly or indirectly, i.e. by means of one or several intermediate layers. Therefore, if applicable, the film of the invention may further comprise one or several intermediate layers between two of any layers of the film as defined above. Such intermediate layers may comprise a polymer chosen among one of the following polymers, or a mixture thereof:

- 40 - semi-crystalline thermoplastic polyolefins, such as polyethylene (PE), polypropylene (PP), polymethylpentene (PMP), or polybutene-1 (PB-1);
- elastomer polyolefins, such as polyisobutylene (PIB), ethylene-propylene (EPR or EPM), or ethylene-propylene-diene monomere (EPDM) ;

- Polyisobutylene (PIB) ;
- Polymers comprising ethylene as a comonomer, such as:
 - ethylene- vinyl acetate (EVA);
 - ethylene copolymers-acrylic esters, such as ethylene-methyl acrylate (EMA), ethylene-ethyl acrylate (EEA) ;
 - ethylene-acrylic ester –maleic anhydride (EEAMA); or
 - ethylene-polyvinyl alcohol (EVOH).

According to the invention, the expression “a layer comprises X” means that said layer comprises X in any amounts or is substantially composed of X.

CONTACT LAYER

According to the present invention, the contact layer comprises (A) a copolymer of ethylene and α -olefin having a density in the range of 0.870 g/cm³ to 0.910 g/cm³, alone or in mixture with (B) a polyolefin having a density in the range of 0.910 g/cm³ to 0.940 g/cm³.

Preferably, the copolymer (A) has a density in the range of 0.890 g/cm³ to 0.905 g/cm³, preferably a density in the range of 0.895 g/cm³ to 0.905 g/cm³.

Preferably, the polyolefin (B) has a density in the range of 0.915 g/cm³ to 0.935 g/cm³, preferably a density in the range of 0.920 g/cm³ to 0.930 g/cm³.

As previously mentioned, the contact layer should be made from a material that can be in contact with a biopharmaceutical product without causing degradation of the film and of the biopharmaceutical product.

Furthermore, it must be sealable on itself. For that purpose, a copolymer of ethylene and α -olefin (A) having a density in the range of 0.870 g/cm³ to 0.910 g/cm³ may be chosen among polyolefin plastomers. These resins are made through either the single site or Ziegler-natta catalysis process. They may be chosen in particular among copolymers of ethylene with one or more α -olefins having at least 3 carbon atoms, preferably from 4 carbon atoms to 8 carbon atoms, such as but-1-ene, hex-1-ene or oct-1-ene, more particularly among copolymers of ethylene and octene, ethylene and hexene, ethylene and butene or ethylene and propylene. Copolymer of ethylene and α -olefin (A) is more preferably a linear low density copolymer of ethylene and oct-1-ene made from a process utilizing a metallocene catalyst, commonly referred as mLLDPE-C8.

Suitable copolymers (A) are sold by The Dow Chemical Company under the trademark AFFINITY® or ENGAGE®, or by ExxonMobil Chemical under the trademark EXACT®.

In order to facilitate the processing of the contact layer and decrease its sticking effect, copolymer (A) may be mixed with a polyolefin (B) having a density in the range of 0.910 g/cm³ to 0.940 g/cm³. Polymer (B) may be chosen among homopolymers or copolymers of olefins, preferably among homopolymers of ethylene. Polyolefin (B) is more preferably a low density polymer of ethylene, commonly referred as LDPE. Suitable polyolefins (B) are sold for instance by LyondellBasel Industries under the trademark LUPOLEN® (more precisely LUPOLEN® 2426HK) or The DOW Chemical Company under the name DOW LDPE®.

The flexibility, sealability and sticking effect of the contact layer can be controlled by adjusting the proportion between (A) and (B).

- 5 In one embodiment, the contact layer comprises a mixture of (A) and (B) with a mass ratio (B)/(A) less than or equal to 95/5, preferably in the range of 5/95 to 95/5.

For a good compromise between flexibility, sealability and sticking effect, and thus cover a wide range of applications, the mass ratio (B)/(A) may be in the range of 0.2 to 5, preferably in the range of 0.2 to 2.

10

The contact layer may contain one or more conventional additives to protect the polymers such as antioxidants (- Octadecyl 3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate - Pentaerythritol tetrakis(3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate),- Tris(2,4-ditert-butylphenyl) phosphite,- Butylhydroxytoluène,- 1,3,5-Tris(3,5-di-tert-butyl-4-hydrox benzyl)-s-triazine-2,4,6-(1H,3H,5H)trione, - Ethylene bis[3,3-bis[3-(1,1-

15

dimethylethyl)-4-hydroxyphenyl]butanoate]) or to help processing of the layer, such as anti-blocks (such as silicon dioxide, magnesium silicate, calcium carbonate, calcium stearate, ethylene bisstearamide, stearyl erucamide, stearamide, erucamide, glycerol monostearate, zinc stearate, or silicone). Preferably the additives should be compliance with the European pharmacopoeia 6.0, 3.1.3 Polyolefines or 3.1.5 Polyethylene with additives for containers for parenteral preparations and for ophthalmic preparations.

20

Preferably, the amount of the additives in the contact layer should be less than 0.50 wt %, preferably less than 0.10 wt%, more preferably less than 0.07 wt%.

If the contact layer is intended to be in contact with a cell medium, the contact layer should not contain slip agents or phthalate as plasticizers because these additives may contain small molecular weight molecules able to move to the surface of the layer, thereby contaminating the cell medium.

25

Furthermore, the contact layer should contain no additives or limited amounts (less than 0.10 wt %, preferably less than 0.07 wt%) of additives able to release a degradation compound further to gamma irradiation in the range of 25 kGy – 50 kGy that can slow down or delay cellular growth.

30

Such degradation compounds able to slow down or delay cellular growth may be detected by testing the film in a Biostat® Cultibag RM system from Sartorius Stedim Biotech during 7 days, with Per-C6 cells line, by comparing with a control film (which does not delay or slow down cellular growth), such as EVA film BF1400 marketed by Renolit.

35

It is considered that cellular growth is slowed down or delayed when the lag phase is at least 24 hours.







Such degradations compounds may be released from antioxidants. Antioxidants are used to prevent polymer degradation which may be initiated by heat, light, impurities such as catalyst residue, or mechanical stress.

40

The contact layer preferably contains no antioxidant or limited amounts of antioxidant (less than 0.10 wt %, preferably less than 0.07 wt%). Table 1 provides examples of such oxidants.

45


Table 1

Chemical name	CAS n°	Chemical formula
Octadecyl 3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate	CAS n° 2082-79-3	
Pentaerythritol tetrakis(3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate)	CAS n° 6683-19-8	
Tris(2,4-ditert-butylphenyl) phosphite	CAS n° 31570-04-4	
Butylhydroxytoluène	CAS n° 128-37-0	
1,3,5-Tris(3,5-di-tert-butyl-4-hydroxybenzyl)-s-triazine-2,4,6-(1H,3H,5H)trione	CAS n° 27676-62-6	
Ethylene bis[3,3-bis(3-(1,1-dimethylethyl)-4-hydroxyphenyl)butanoate]	CAS n° 32509-66-3	

The antioxidants are classified into two types, primary and secondary, depending on the mechanism used to halt the degradation process. Degradation compounds able to slow down or delay cellular growth can be released from primary and secondary antioxidants, such as phenolic antioxidants or phosphite antioxidant.

- 5 In particular, the contact layer contains no or limited amounts (less than 0.01 wt %) of a secondary antioxidant, preferably of a phosphite antioxidant, such as tris(2,4-ditert-butylphenyl) phosphite.

Under gamma irradiation, tris(2,4-ditert-butylphenyl) phosphite is converted into a phosphate, which in turns releases degradation compounds as follows:



10

The thickness of the contact layer is from 150 μm and 300 μm , preferably from 200 and 250 μm , more preferably from 225 μm and 245 μm .

- 15 The contact layer may be manufactured by extrusion.

The contact layer of the film of the invention has one of its sides free, thereby forming one of the two the outer sides of the film.

- 20 In one embodiment, the film of the invention is monolayer and composed of the contact layer.

In another embodiment, the film of the invention is a multilayer film comprising one or several layers in addition to the contact layer, in particular a core layer able to provide a barrier to the passage of gases such as oxygen or carbon dioxide, and an outer layer, wherein the contact layer and core layer are made integral with a first tie layer, and the outer layer and core layer are made integral with a second tie layer.

25

In that case, the contact layer is preferably manufactured by cast extrusion with the other layers of the multilayer film, without the use of silicone in order to make the contact layer inert with regard to a cell medium.

5

OPTIONAL LAYERS

As mentioned above, the film of the invention may be a multilayer film comprising one or several layers in addition to the contact layer, in particular a core layer and an outer layer, wherein the contact layer and core layer are made integral with a first tie layer, and the outer layer and core layer are made integral with a second tie layer.

10

The core layer may comprise (C') a flex-crack resistant ethylene vinyl alcohol copolymer having a content of ethylene in the range of 25 to 48 mol % or a mixture of (C) an ethylene vinyl alcohol copolymer having a content of ethylene in the range of 25 to 48 mol % and (D) an ionomer acid ethylene copolymer.

15

The flex crack resistance is measured according to the Standard Test Method for Flex Durability of Flexible Barrier Materials ASTM F392 (2004). According to the present invention, a material is flex-crack resistant if the number of pine holes measured after 100 cycles according to the method of ASTM F392 (film sample : 30 μ m mono layer, test condition: 23°C, Gelbo flex tester: 440° twisting motion) is less than or equal to 30. It was found that the introduction of such a polymer into the core layer makes the multilayer film more resistant to mechanical stresses.

20

The ethylene vinyl alcohol copolymer (C) or (C') having a content of ethylene in the range of 25 to 48 mol % is used to provide a barrier to the passage of gases such as oxygen, carbon dioxide. Ethylene vinyl alcohol copolymers are commonly abbreviated EVOH. Preferably, the content of ethylene in copolymer (C) or (C') is in the range of 29 to 44 mol %, most preferably around 29 to 38 mol %. Suitable EVOH whose ethylene content is from 25 to 48 mol % are sold for instance by Nippon Goshei under the trademark SOARNOL®. Suitable EVOH whose ethylene content is from 27 to 48 mol % are sold for instance by Kuraray under the trademark EVAL®.

25

30

Advantageously, the copolymer (C) is flex-crack resistant.

Preferably, the flex crack resistant polymer (C) or (C') is such that its barrier properties are maintained even during or after torsion or twisting application movements.

35

The lower the content of ethylene in copolymer (C) or (C') is, the higher the gas barrier effect of the layer is, but at the same time the more rigid the core layer is. If the core layer is too rigid, it may crack or cause delamination within the multilayer film.

40

In order to limit this risk of cracking or delamination, copolymer (C) is mixed with an ionomer acid ethylene copolymer (D) which helps to absorb the mechanical stresses of the barrier layer. The copolymer (D) is particularly suitable because it mixes readily with copolymer (C) and displays good affinity with the tie layers.

By "ionomer acid ethylene copolymer", it is meant acid ethylene copolymer partially neutralized with metal salts such as zinc or sodium ions. Suitable copolymers (D) include acrylic acid copolymers of ethylene ionomers, wherein the carboxylate groups are associated with zinc cations. Such copolymers are sold for instance by DuPont Packaging & Industrial Polymers under the trademark SURLYN® or by The Dow Chemical Company under the trademark AMPLIFY® IO.

The flexibility and gas barrier effect of the film can be controlled by adjusting the proportion between (C) and (D).

In one embodiment, the core layer comprises a mixture of (C) an ethylene vinyl alcohol copolymer having a content of ethylene in the range of 25 to 48 mol % and (D) an ionomer acid ethylene copolymer with a mass ratio (C)/(D) in the range of 95/5 to 55/45.

For a good compromise between flexibility and gas barrier effect, and thus cover a wide range of applications, the mass ratio (C)/(D) may be in the range of 10 to 19, preferably in the range of 15 to 19.

The thickness of the core layer is from 5 μm and 50 μm , preferably from 15 and 40 μm , more preferably from 20 μm and 30 μm .

The outer layer may comprise (E) a polyolefin having a density in the range of 0.910 g/cm^3 to 0.940 g/cm^3 , alone or in mixture with (F) a copolymer of ethylene and α -olefin having a density in the range of 0.870 g/cm^3 to 0.910 g/cm^3 .

Preferably, the polyolefin (E) has a density in the range of 0.925 g/cm^3 to 0.940 g/cm^3 , more preferably a density in the range of 0.930 g/cm^3 to 0.940 g/cm^3 .

Preferably, the copolymer (F) has a density in the range of 0.890 g/cm^3 to 0.905 g/cm^3 , more preferably a density in the range of 0.895 g/cm^3 to 0.905 g/cm^3 .

Polyolefins (E) having a density in the range of 0.910 g/cm^3 to 0.940 g/cm^3 may be chosen among homopolymers or copolymers of olefins, preferably among copolymers of ethylene. A linear low density copolymer of ethylene is particularly suitable because it shows a better mechanical resistance to tensile stress. Preferred polyolefins (E) include copolymers of ethylene with one or more olefins having at least 3 carbon atoms, preferably from 4 carbon atoms to 8 carbon atoms, such as butene, hexene or octene.

Polyolefin (E) is more preferably a linear low density copolymer of ethylene and hexene, commonly referred as LLDPE-C6. Suitable polyolefins (E) are sold for instance by INEOS under the name INEOS LLDPE (more precisely INEOS LLDPE LL6930AA) or by the DOW Chemical Company under the trademark DOWLEX™ (more precisely DOWLEX™ SC 2108G).

Copolymers of ethylene and α -olefin (F) having a density in the range of 0.870 g/cm^3 to 0.910 g/cm^3 may be chosen among polyolefin plastomers. These resins are made through either the single site or Ziegler-natta catalysis process. They may be chosen in particular among copolymers of ethylene with one or more α -olefins having at least 3 carbon atoms, preferably from 4 carbon atoms to 8 carbon atoms, such as but-1-ene, hex-1-ene or oct-1-ene, more particularly among copolymers of ethylene and octene, ethylene and hexene, ethylene and butene or ethylene and propylene. Copolymer of ethylene and α -olefin (F) is more

preferably a linear low density copolymer of ethylene and oct-1-ene made from a process utilizing a metallocene catalyst, commonly referred as mLLDPE-C8. Suitable polyolefins (F) are sold for instance by The Dow Chemical Company under the trademark AFFINITY® or ENGAGE®, or by ExxonMobil Chemical under the trademark EXACT®.

5

The outer layer contributes to the mechanical strength of the pouch wall. For that purpose, it must be sufficiently flexible to withstand high mechanical stress but not be too much stretchable, i.e. sufficiently rigid, in order to prevent deformation of the pouch when it is filled with a product.

10

The polyolefin (E) gives to the film the desired rigidity, while copolymer (F) gives to the film the resistance to mechanical strength, in particular resistance to twist stress. The flexibility and rigidity of the film can be controlled by adjusting the right proportion between (E) and (F).

15

In some applications where the film should be able to resist to the pressure of the liquid contained in the pouch (for instance with high volumes of liquid), it is preferable to have an amount of polyolefin (E) which is higher than copolymer (F).

In other applications, where the film should withstand flexion and mechanical stress, it may be preferable to have an amount of copolymer (F) which is higher than polyolefin (E).

20

In one embodiment, the outer layer comprises a mixture of (E) and (F) with a mass ratio (E)/(F) higher than or equal to 5/95, preferably in the range of 5/95 to 100/0.

25

For a good compromise between flexibility and rigidity, and thus cover a wide range of applications, the mass ratio (E)/(F) may be in the range of 1 to 5, preferably in the range of 1 to 2.5.

30

The outer layer may contain one or more conventional additives to protect the polymers such as antioxydants (- Octadecyl 3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate - Pentaerythritol tetrakis(3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate),- Tris(2,4-ditert-butylphenyl) phosphite,- Butylhydroxytoluène,- 1,3,5-Tris(3,5-di-tert-butyl-4-hydrox benzyl)-s-triazine-2,4,6-(1H,3H,5H)trione, - Ethylene bis[3,3-bis[3-(1,1-dimethylethyl)-4-hydroxyphenyl]butanoate]) or to help processing of the layer, such as anti-blocks (such as silicon dioxide, magnesium silicate, calcium carbonate, calcium stearate, ethylene bisstearamide, stearyl erucamide, stearamide, erucamide, glycerol monostearate, zinc stearate, or silicone). Preferably the additives should be compliance with the European pharmacopoeia 6.0, 3.1.3 Polyolefines or 3.1.5 Polyethylene with additives for containers for parenteral preparations and for ophthalmic preparations. Preferably, the amount of the additives in the outer layer should be less than 0.50 wt %, preferably less than 0.10 wt%, more preferably less than 0.07 wt%.

35

40

Preferably, the additives are chosen among compositions which do not contain any compound susceptible to degradation under gamma irradiation.

The thickness of the outer layer is from 50 µm and 150 µm, in particular from 55 µm to 150 µm, preferably from 80 and 120 µm, more preferably from 90 µm and 110 µm.

The tie layer may comprise (G) a copolymer of polyolefin grafted with a carboxylic acid or an anhydride of carboxylic acid, alone or in mixture with (H) a copolymer of polyolefin.

5 The tie layer is able to seal the contact layer, core layer and outer layer between each other and to prevent separation of these layers during the use of the pouch.

In one embodiment, polyolefin (G) has a density in the range of 0.875 g/cm^3 to 0.940 g/cm^3 .

10 In one embodiment, polyolefin (H) has a density in the range of 0.870 g/cm^3 to 0.910 g/cm^3 .

In one embodiment, the first tie layer and second tie layer have identical compositions.

15 The binding properties are conferred by the copolymer (G) which is a copolymer of polyolefin grafted with a carboxylic acid or an anhydride of carboxylic acid. The copolymer of polyolefin grafted with a carboxylic acid or an anhydride of carboxylic acid is preferably a copolymer of ethylene, more particularly a copolymer of ethylene with one or more olefins having at least 3 carbon atoms, preferably from 4 carbon atoms to 8 carbon atoms, such as butene, hexene or octene, grafted with maleic acid anhydride. More preferably, the polymer (G) is a copolymer of ethylene grafted with maleic anhydride. Suitable polymers (G) are sold for instance by Dupont under the trademark BYNEL®, or by The Dow Chemical Company under the trademark
20 AMPLIFY™TY or AMPLIFY™GR.

For a better affinity with the contact layer, core layer and outer layer, and for a better flexibility of the film, the polymer (G) is mixed with copolymer (H).

25 Copolymer (H) may be chosen among polyolefin plastomers. These resins are made through either the single site or Ziegler-natta catalysis process. They may be chosen in particular among copolymers of ethylene with one or more α -olefins having at least 3 carbon atoms, preferably from 4 carbon atoms to 8 carbon atoms, such as but-1-ene, hex-1-ene or oct-1-ene, more particularly among copolymers of ethylene and octene, ethylene and hexene, ethylene and butene or ethylene and propylene. Copolymer of ethylene
30 and α -olefin (H) is more preferably a linear low density copolymer of ethylene and oct-1-ene made from a process utilizing a metallocene catalyst, commonly referred as mLLDPE-C8. Suitable polyolefins (H) are sold for instance by The Dow Chemical Company under the trademark AFFINITY® or ENGAGE®, or by ExxonMobil Chemical under the trademark EXACT®.

35 In one embodiment, the first tie layer and second tie layer comprise independently of each other a mixture of (G) and (H) with a mass ratio (H)/(G) less than 95/5, preferably in the range of 5/95 to 95/5.

For a good compromise between flexibility and sealability, and thus cover a wide range of applications, the mass ratio (H)/(G) may be in the range of range of 0.2 to 5, preferably in the range of 0.2 to 2.5.

40 The thickness of the tie layer is from 5 μm and 50 μm , preferably from 10 and 30 μm , more preferably from 15 μm and 25 μm .

The tie layer may be manufactured by extrusion. Preferably, the tie layer is manufactured by cast extrusion with the other layers of the multilayer film, without the use of silicone in order to make the contact layer inert with regard to a cell medium.

5 Hence, in one embodiment, the film of the invention is a multilayer film comprising a contact layer, a core layer and an outer layer, wherein the contact layer and the core layer are made integral with a first tie layer and the outer layer and the core layer are made integral with a second tie layer, and wherein the layers are as defined previously.

10 The layers may be processed into a multilayer film by standard extrusion techniques well known by the person skilled in the art including extrusion or coextrusion such as cast or blow extrusion, extrusion coating, extrusion coating and lamination or a combination thereof, for instance by co-extruding at least two layers and then coating on another layer, or by coextruding at least two layers, extruding another layer and then coating and laminating the coextruded layer and extruded layer together.

15 Preferably, the multilayer film is manufactured by using a cast coextrusion process.

Another object of the present invention is thus a process for manufacturing the multilayer film as described above, comprising cast coextrusion of the contact layer, first tie layer, core layer, second tie layer and outer layer.

20 The process should be conducted free of slip agents and other low molecular weight additives that may increase the extractables to an unacceptable level.

25 The multilayer film according to the invention is particularly suited for manufacturing single-use pouches, including 2D pouches or 3D pouches.

Another object of the present invention is thus a single-use pouch whose wall comprises the multilayer film as described above.

30 For that purpose, the thickness of the multilayer film is from 200 μm and 500 μm , preferably from 300 and 450 μm , more preferably from 350 μm and 450 μm .

35 The multilayer film of the invention is able to withstand various mechanical stresses making it usable in a wide range of applications, such as in bioreactors whatever the mode of stirring, for preparing a solution either by liquid/liquid or solid/liquid stirring, for storing or conveying a fluid in a 2D or 3D pouch, for both small or large volumes.

Such pouches may be manufactured according to standard techniques well known by the person skilled in the art.

40 The multilayer film of the invention is particularly suited for manufacturing single-use pouches intended to contain a cell medium or a cell culture as it has no or limited impact on the cellular growth of a culture medium further to sterilization by gamma irradiation. In particular, the contact layer of the multilayer film of the invention releases no or limited amount of degradation compound further to gamma irradiation, said degradation compound being able to interfere with cellular growth.

45

Brief description of the figures

Figure 1 represents the cell density of a culture medium as a function of time, said culture medium being grown in a pouch made with a multilayer film according to the invention, compared with a culture medium grown in a pouch of the prior art (EVA contact layer).

The invention will now be further described in the following examples. These examples are offered to illustrate the invention and should in no way be viewed as limiting the invention.

10

Example 1: Multilayer film comprising a contact layer according to the invention.

A multilayer film with a thickness of 400 μm was prepared and coextruded in accordance with the teaching of the present invention. The multilayer film has:

- 15 - an outer layer with a thickness of 100 μm comprising 98 wt% of LLDPE-C6 having a density of 0.936 g/cm^3 and 2 wt% of an anti-block resin,
- a core layer with a thickness of 25 μm comprising 95 wt % of EVOH having an ethylene contain of 38%mol and 5 wt % of PE ionomer zinc having a density of 0.950 g/cm^3 ,
- 20 - a contact layer with a thickness of 235 μm comprising 68 wt % of mLLDPE-C8 having a density of 0.902 g/cm^3 , 30 wt % of LDPE without additives having a density of 0.923 g/cm^3 and 2 wt% of an anti-block resin,
- a first tie layer between the contact layer and the core layer, said tie layer comprising 70 wt % of mLLDPE-C8 having a density of 0.902 g/cm^3 and 30 wt % LLDPE-MAH,
- 25 - a second tie layer between the contact layer and the core layer, said tie layer comprising 70 wt % of mLLDPE-C8 having a density of 0.902 g/cm^3 and 30 wt % of LLDPE-MAH.

LLDPE-C6 = linear low density copolymer of ethylene and hexene.

EVOH = ethylene vinyl alcohol polymer.

PE ionomer zinc = acrylic acid copolymers of ethylene ionomer, wherein the carboxylate groups are associated with zinc cations.

mLLDPE-C8 = linear low density copolymer of ethylene and oct-1-ene made from a process utilizing a metallocene catalyst.

LLDPE-MAH = linear low density copolymer of ethylene grafted with maleic anhydride.

LDPE = low density polymer of ethylene.

35

The contact layer of said film shows remarkable mechanical properties, thereby allowing a wide range of applications. It is able to withstand various mechanical stresses without resulting in leakage of the product outside the pouch.

40 Example 2: cell density

Three bags of 10 liters were manufactured with three different films A, B and C.

Film A is available on the market under the reference BF1400 (Renolit). It comprises an EVA contact layer.

45

Films B and C are multilayer films in accordance with the invention comprising a contact layer, a core layer, an outer layer, and 2 tie layers. Films B and C are identical except in the contact layer.

Film B has a thickness of 400 μm . Its contact layer has a thickness of 235 μm and comprises:

- 5 - mLLDPE-C8 having a density of 0.902 g/cm^3 and
 - less than 0,12 wt% of additives able to release a degradation compound further to gamma irradiation that can slow down or delay cellular growth.

Film C has a thickness of 400 μm . Its contact layer has a thickness of 235 μm and comprises:

- 10 - a mixture of mLLDPE-C8 having a density of 0.902 g/cm^3 and LDPE without additives having a density of 0.923 g/cm^3 ,
 - a maximum of 0,06 wt% of additives able to release a degradation compound further to gamma irradiation that can slow down or delay cellular growth.

15 mLLDPE-C8 = linear low density copolymer of ethylene and oct-1-ene made from a process utilizing a metallocene catalyst.

LDPE = low density polymer of ethylene (INEOS ELTEX MED PH23H630 by INEOS).

The cell culture was performed in a Cultibag RM 10L Optical design made with the above described three films and gamma irradiated at 25-40kGy.

20 The cells culture was performed in parallel with Biostat® Cultibag RM systems from Sartorius Stedim Biotech during 7 days, with Per-C6 cells line.

The cell density was measured by sampling at different dates in order to follow the growth behaviour.

Figure 1 represents the cell density as a function of time:

25

- ◆— Cell culture in a bag made with a film A
- Cell culture in a bag made with a film C
- ▲— Cell culture in a bag made with a film B

Results:

All along the cell culture, the viability of the cells was above 80%.

30 The cell culture performed in the bag made with the film A shows a good growth.

The cell culture performed in the bag made with the film B shows a bad growth.

The cell culture performed in the bag made with the film C shows good growth.

Figure 1 shows that the film B delays the cellular growth while film C has not impact on the cellular growth.

35 From these results it is considered that the delay on cellular growth is due to the content of additives in the contact layer. These additives are able to release degradation compounds further to gamma irradiation that slow down or delay cellular growth.

40 Therefore, it is preferable to limit the amount of additives able to release such degradation compounds further to gamma irradiation in the contact layer.

The films of the invention has no impact on cellular growth both shortly after gamma irradiation (within one week) and several months after gamma irradiation, which may not be the case for film A.

CLAIMS

1. A film for manufacturing a pouch, said film comprising a contact layer comprising (A) a copolymer of ethylene and α -olefin having a density in the range of 0.870 g/cm³ to 0.910 g/cm³, alone or in mixture with (B) a polyolefin having a density in the range of 0.910 g/cm³ to 0.940 g/cm³, said contact layer comprising less than 0.10 wt %, preferably less than 0.07 wt %, of additives able to release a degradation compound further to gamma irradiation in the range of 25 kGy - 50 kGy, that can slow down or delay cellular growth.
2. The film according to claim 1, wherein the additives able to release a degradation compound further to gamma irradiation that can slow down or delay cellular growth are antioxidants.
3. The film according to claims 1 or 2, wherein said antioxidant is phosphite antioxidant.
4. The film according to any one of claims 1 to 3, wherein said antioxidant is tris(2,4-ditert-butylphenyl) phosphite.
5. The film according to any one of claims 1 to 4, wherein the copolymer of ethylene and α -olefin (A) is a plastomer polyolefin having from 4 to 8 carbon atoms, in particular a linear low density copolymer of ethylene and oct-1-ene made from a process utilizing a metallocene catalyst.
6. The film according to any one of claims 1 to 5, wherein polyolefin (B) is a homopolymer of ethylene, in particular a low density polymer of ethylene.
7. The film according to any one of claims 1 to 6, wherein the contact layer comprises a mixture of (A) and (B) with a mass ratio (B)/(A) less than or equal to 95/5, preferably in the range of 5/95 to 95/5, more preferably in the range of 0.2 to 5, even more preferably in the range of 0.2 to 2.
8. The film according to any one of claims 1 to 7, wherein said film is monolayer.
9. The film according to any one of claims 1 to 7, wherein said film is a multilayer film comprising one or several layers in addition to the contact layer, in particular a core layer able to provide a barrier to the passage of gases such as oxygen or carbon dioxide, and an outer layer, wherein the contact layer and core layer are made integral with a first tie layer, and the outer layer and core layer are made integral with a second tie layer.
10. A process for manufacturing the film according to any one of claims 1 to 8, comprising extrusion of the contact layer.
11. A process for manufacturing the multilayer film according to claim 9, comprising coextrusion of the contact layer, first tie layer, core layer, second tie layer and outer layer.
12. A single-use pouch whose wall comprises the multilayer film according to anyone of claims 1 to 9.
13. A bioreactor comprising the single-use pouch according to claim 12.




Figure 1