

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
10 July 2008 (10.07.2008)

PCT

(10) International Publication Number
WO 2008/082872 A1

- (51) International Patent Classification:
D04H 3/16 (2006.01) D04H 3/14 (2006.01)
- (21) International Application Number:
PCT/US2007/087106
- (22) International Filing Date:
5 December 2007 (05.12.2007)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
11/617,274 28 December 2006 (28.12.2006) US
- (71) Applicant (for all designated States except US): 3M INNOVATIVE PROPERTIES COMPANY [US/US]; 3M Center, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).
- (72) Inventors: BERRIGAN, Michael R.; 3M CENTER, Post Office Box 33427, Saint Paul, MN 55133-3427 (US). STELTER, John D.; 3M CENTER, Post Office Box 33427, Saint Paul, MN 55133-3427 (US). EBBENS, Ruth A.; 3M CENTER, Post Office Box 33427, Saint Paul, MN 55133-3427 (US). FENNESSEY, Sian F.; 3M CENTER, Post Office Box 33427, Saint Paul, MN 55133-3427 (US).
- (74) Agents: BRONK, John M., et al.; 3M CENTER, Office Of Intellectual Property Counsel, Post Office Box 33427, Saint Paul, MN 55133-3427 (US).


- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii))

[Continued on next page]

(54) Title: DIMENSIONALLY STABLE BONDED NONWOVEN FIBROUS WEBS



(57) Abstract: A method for making a bonded nonwoven fibrous web comprising extruding melt blown fibers of a polymeric material, collecting the melt blown fibers as an initial nonwoven fibrous web, annealing the initial nonwoven fibrous web with a controlled heating and cooling operation, and collecting the dimensionally stable bonded nonwoven fibrous web is described. The bonded nonwoven fibrous web shrinkage is typically less than 4 percent relative to the initial nonwoven fibrous web.

WO 2008/082872 A1



Published:

- *with international search report*
- *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments*

DIMENSIONALLY STABLE BONDED NONWOVEN FIBROUS WEBS

Field

The present invention relates to bonded nonwoven fibrous webs.

5

Background

Typical melt spinning polymers, such as polyolefins, tend to be in a semi-crystalline state upon meltblown fiber extrusion (as measured by differential scanning calorimetry (DSC)). For polyolefins, this ordered state is due, in part, to a relatively high rate of crystallization and the extensional polymer chains oriented in the extrudate. In meltblown extrusion, extensional orientation is accomplished with high velocity, heated air in the elongational field. Extending polymer chains from the preferred random coiled configuration and crystal formation imparts internal stresses to the polymer. Provided the polymer is above its glass transition temperature (T_g) these stresses will dissipate. For meltblown polyolefins, the dissipation of stresses occurs spontaneously within a few days of web formation since the polymer's T_g is well below room temperature.

10

15

20

25

Melt blown polyethylene terephthalate (PET) generally exhibits a level of crystalline orientation commensurate with the strain level imparted during processing, and the time available for the polymer chains to relax during cooling. PET has a relatively slow rate of relaxation, a relatively low rate of crystallization, a relatively high melt temperature (T_m), and a glass transition temperature (T_g) above room temperature. The internal stresses from amorphous orientation within the elongational field are frozen-in place due to rapid cooling of the melt, thus retarding relaxation. As the T_g is approached and surpassed, the chains begin to relax. Annealing between T_g and T_m for a sufficient period of time allows the polymer to dissipate the internal stresses caused by elongational orientation, and for the chains to crystallize. The stress dissipation manifests itself in the form of shrinkage of the web's extruded dimensions, while crystallization of the polymer chains increases brittleness.

30

Efforts to provide a more stable and useful meltblown PET fiber, such as annealing a web while being held on a tentering structure has been described in U.S. Patent No. 5,958,322 (Thompson et al.), or forming strain induced crystals during fiber attenuation as described in U.S. Patent No. 6,667,254 (Thompson, Jr. et al.) and Japanese Kokai No. 3-

45768. Other techniques for extracting soluble fractions of drawn crystalline polymer in a heated solvent and applying a tensile stress to provide for a stable polyester nonwoven fibrous web have been described in U.S. Patent No. 3,823,210 (Hikaru Shii et al.), and by treating webs in solvent as described in U.S. Patent No. 5,010,165 (Pruett et al.).

5

Summary

The melt blown fibers of this disclosure are substantially free of strain induced crystallization, and are substantially unoriented in the bonded nonwoven fibrous web. In one aspect, this disclosure provides for a method for making a bonded nonwoven fibrous web comprising extruding a mass of melt blown fibers of a polymeric material, collecting the mass of melt blown fibers as an initial nonwoven fibrous web, where the fibers are substantially free of strain induced crystallization, annealing the initial nonwoven fibrous web with a controlled heating and cooling operation and collecting the dimensionally stable bonded nonwoven fibrous web. The controlled heating and cooling operation includes heating through the nonwoven fibrous web with a first fluid having a temperature above T_{cc} (cold crystallization temperature) of the polymeric material to decrease the orientation of the amorphous regions of the melt blown fibers forming a bonded nonwoven fibrous web, and cooling through the bonded nonwoven fibrous web with a second fluid having a temperature below the T_g of the polymeric material to retain the amorphous regions of the melt blown fibers.

10
15
20

In one embodiment, the dimensionally stable bonded nonwoven fibrous web shrinkage is less than 4 percent relative to the initial nonwoven fibrous web.

In one embodiment, the initial nonwoven fibrous web, the heated nonwoven fibrous web, the bonded nonwoven fibrous web, the cooled bonded nonwoven fibrous web, and the dimensionally stable bonded nonwoven fibrous web are unrestrained.

25

In another aspect, a bonded nonwoven fibrous web is described. The web comprises melt blown fibers having a diameter in a range from 1 to 20 micrometers. The fibers are substantially free of strain induced crystallization.

Nonwoven fibrous webs that are typically amorphous, such as polyethylene terephthalate (PET), tend to be in a nearly amorphous state upon melt blown fiber extrusion. The internal stresses from amorphous orientation within the elongational field are frozen-in due to rapid cooling of the melt, thus preventing relaxation, which cannot be

30

released until subsequent annealing above T_g . Annealing between the T_g and the T_m for sufficient periods allows the polymer to both crystallize and dissipate internal stresses caused by elongational orientation. This stress dissipation manifests itself in the form of shrinkage that can approach values exceeding 50 percent of the web's extruded
5 dimensions.

The fibers of this disclosure are substantially free of strain induced crystallization, and are substantially unoriented in the bonded nonwoven fibrous web. The fibers exiting the extruder die typically lack chain extension, and thus exhibit reduced amorphous orientation in the polymer chains as they are collected. The fibers of the web soften
10 during the controlled heating step to provide for bonding between the fibers, and for reduced orientation of the amorphous regions of the fibers. The fibers are relaxed for a period of time at a temperature above T_{cc} of the polymeric material. Immediately following the heating step, the fibers are cooled to a temperature below the T_g of the polymeric material to retain or lock in the reduced amorphous orientation resulting from
15 the heating step above. The controlled heating and cooling operation provides for a dimensionally stable bonded nonwoven fibrous web.

Brief Description of the Drawings

FIG. 1 is a schematic representation of a meltblown fiber apparatus for forming a
20 nonwoven fibrous web.

FIG. 2 is a schematic representation of an enlarged side view of a heat treating part of the apparatus of Figure 1.

FIG. 3 is a schematic representation (perspective view) of the apparatus of Figure
1.

FIG. 4 is a plot obtained by Differential Scanning Calorimetry (DSC) on fibers
25 from a poly(ethylene terephthalate) nonwoven fibrous web.

FIG. 5 is an azimuthal plot obtained by X-ray Diffraction (Reflectometry) of fibers from a poly(ethylene terephthalate) nonwoven fibrous web.

Detailed Description

For the following defined terms, these definitions shall be applied, unless a different definition is given in the claims or elsewhere in the specification.

The term “annealing” refers to a process of heating and/or cooling a polymeric material to a temperature to influence a set or one of desired properties. For example, a material may be annealed at a temperature to relax the polymer chains and subsequently cooled at a lower temperature to retain the properties achieved at the higher temperature.

5 The term “cold crystallization temperature (T_{cc})” refers to the temperature where the amorphous regions of polymer chains organize and orient above the T_g of a polymer as illustrated in a DSC (Differential Scanning Calorimetry) plot.

10 The term “cooling immediately” refers to rapidly cooling or quenching of melt blown fibers to retain their amorphous orientation without an intervening time interval following the heating operation. In one embodiment, the gas-withdrawal equipment is positioned down web from the heated gaseous stream so as to draw a cooling gas or other fluid, for example, ambient air, through the web promptly after it has been heated and thereby rapidly quench the fibers. The length of heating is controlled, for example, by the length of the heating region along the path of web travel and by the speed at which the web is moved through the heating region to the cooling region, to cause the intended softening and relaxing of the amorphous regions of the fibers.

15 The term “dimensionally stable” refers to a nonwoven fibrous web that exhibits preferably less than 4 percent shrinkage, more preferably less than 2 percent shrinkage, and most preferably less than 1 percent shrinkage, along its major surface when elevated to a temperature above the temperature at which the nonwoven fibrous web was annealed. The webs were prepared according to ASTM D 3776-96 and tested for shrinkage in accordance with ASTM D 1204-84. **Table 2** shows the results of web shrinkage testing.

20 The term “forcefully passing” refers to passing a liquid or gaseous stream through a web at a force in addition to the normal room pressure as applied to the fluid to propel the fluid through the web. The annealing step of the method includes passing the web on a conveyor through a device (for example, through air bonder) that provides a focused or knife-like heated gaseous stream issuing from the heater under pressure and engaging one side of the web, with gas-withdrawal apparatus on the other side of the web to assist in drawing the heated gas through the web. Generally, the heated stream extends across the width of the web. The heated stream may be subjected to special controls that modulate the flow, causing the heated gas to be distributed uniformly and at a controlled rate

25
30

through the width of the web to thoroughly, uniformly and rapidly heat the fibers of the web to a usefully high temperature.

The term “glass transition temperature (T_g)” refers to the temperature where a polymer changes to a viscous or rubbery condition from a glassy one.

5 The term “heating” refers to precisely controlled heated air (controlled volume, velocity, and temperature) of a through air bonder device.

The term “melting point or melting transition temperature (T_m)” refers to the temperature where the polymer transitions from a solid phase to a liquid phase.

10 The term “microfiber” refers to fibers having an effective fiber diameter of less than 20 micrometers.

The term “nonwoven fibrous web” refers to a textile structure produced by mechanically, chemically, and/or thermally bonding or interlocking polymeric fibers.

15 The term “period of time” refers to a predetermined amount of time to perform a desired function. For example, the nonwoven web of this disclosure is heated for a “period of time” to relax the amorphous orientation of the polymer chains and/or allow for bonding of the fibers of the web.

The term “polymeric” refers to a material that is not inorganic and contains repeating units, and further includes polymers, copolymers, and oligomers.

20 The term “substantially free” refers to zero or nearly no detectable amount of a material, quantity, or item. For example, the amount can be less than 2 percent, less than 0.5 percent, or less than 0.1 percent of the material, quantity, or item.

The term “substantially unoriented” refers to zero or nearly no detectable amount of a material, quantity, or item. For example, the amount can be less than 2 percent, less than 0.5 percent, or less than 0.1 percent of the material, quantity, or item.

25 The term “thermoplastic” refers to a polymeric material that reversibly softens when exposed to heat.

The term “unrestrained” refers to a condition wherein the web or fibers are not held or not restrained by a device, such as a tentering structure to achieve fiber orientation and crystallization.

30 The recitation of numerical ranges by endpoints includes all numbers subsumed within that range (for example, 1 to 5 includes 1, 1.5, 2, 2.75, 3, 3.8, 4, and 5).

As included in this specification and the appended claims, the singular forms “a”, “an”, and “the” include plural referents unless the content clearly dictates otherwise. Thus, for example, reference to a composition containing “a compound” includes a mixture of two or more compounds. As used in this specification and appended claims,
5 the term “or” is generally employed in its sense including “and/or” unless the content clearly dictates otherwise.

Unless otherwise indicated, all numbers expressing quantities or ingredients, measurement of properties and so forth used in the specification and claims are to be understood as being modified in all instances by the term “about.” Accordingly, unless
10 indicated to the contrary, the numerical parameters set forth in the foregoing specification and attached claims are approximations that can vary depending upon the desired properties sought to be obtained by those skilled in the art utilizing the teachings of the present disclosure. At the very least, and not as an attempt to limit the application of the doctrine of equivalents to the scope of the claims, each numerical parameter should at
15 least be construed in light of the number of reported significant digits and by applying ordinary rounding techniques. Notwithstanding that the numerical ranges and parameters setting forth the broad scope of the disclosure are approximations, the numerical values set forth in the specific examples are reported as precisely as possible. Any numerical value, however, inherently contains errors necessarily resulting from the standard deviations
20 found in their respective testing measurements.

A representative apparatus useful for preparing meltblown fibers or a melt blown fibrous web of this disclosure is illustrated in **FIG. 1**. Part of the apparatus, which forms the blown fibers, can be as described in Wentz, Van A., “Superfine Thermoplastic Fibers” in Industrial Engineering Chemistry, Vol. 48, page 1342-1346 (1956), and in Report No.
25 4364 of the Naval Research Laboratories, published May 25, 1954, entitled “Manufacture of Superfine Organic Fibers” by Wentz, V.A. et al. This portion of the illustrated apparatus comprises a die **10** which has a set of aligned side-by-side parallel die orifices **11**, one of which is seen in the sectional view through the die. The orifices **11** open from the central die cavity **12**. Fiber-forming material is introduced into the die cavity **12** from
30 an extruder **13**. An elongated (perpendicular to the page) opening or slot **15** disposed on either side of the row of orifices **11** conveys heated air at a very high velocity. Outer die lip **23** provides a structural limitation or feature for the dimension of slot **15**, and inner die

lip **24** provides a structural limitation or feature to assist in controlling the diameter of the stream **16** as it exits **11**. The air of slot **15**, called the primary air, impacts onto the extruded fiber forming material, and rapidly combines the extruded material into a mass of fibers.

5 From the melt blowing die **10**, the fibers travel in a stream **16** to a collector **18**. The fibers exit the orifices **11** of the die cavity **12** at a temperature above the melting transition temperature, T_m . Within 0.5 to 5 cm of the orifices **11**, the fibers of the stream **16** begin to decelerate, and generally cool below the T_m , where the fibers are substantially free of strain induced crystallization. As the melt blown fibers of the stream **16** approach
10 the collector **18**, they continue to decelerate, and generally approach temperatures below T_g (glass transition temperature) without notable fiber shrinkage. The lack of fiber orientation or attenuation from the process may contribute to a lack of strain induced crystallization in the material. The fibers are collected on the moving collector **18** as a web or mass of melt blown fibers **19**. The collector **18** may take the form of a finely
15 perforated cylindrical screen or drum, or a moving belt. Gas-withdrawal apparatus may be positioned behind the collector to assist in deposition of fibers and removal of gas, for example, the air in which the fibers are carried in the stream **16**. Further details of the melt blowing apparatus of **FIG. 1** are described in U.S. Patent No. 6,667,254 (Thompson et al.).

20 The fibers of this disclosure are not drawn or attenuated before they move onto the collector **18**. The primary air facilitates the movement and consolidation of fibers.

 After deposition of the fibers in the stream **16** to a collector **18**, the mass of fibers **19** is generally annealed as a web with a controlled heating and cooling operation.

 In one aspect, the mass of melt blown fibers **19** is transported on the collector **18**
25 and annealed through a heating and cooling operation as illustrated in **FIG. 2** and **FIG. 3**. The apparatus in **FIG. 2** and **FIG. 3** is referred to as a quenched flow heater, quenched heater or through air bonder. The collected mass of fibers **19** is first passed under a controlled-heating device **100** mounted above the collector **18**. The exemplary heating device **100** comprises a housing **101** that is divided into an upper plenum **102** and a lower
30 plenum **103**. The upper and lower plenums (**102** and **103**, respectively) are separated by a plate **104** perforated with a series of holes **105** that are typically uniform in size and

spacing. A gas, typically air, is fed into the upper plenum **102** through openings **106** from conduits **107**, and the plate functions as a flow distribution means to cause air fed into the upper plenum to be rather uniformly distributed when passed through the plate into the lower plenum **103**. Other useful flow distribution means include fins, baffles, manifolds, air dams, screens or sintered plates, that is, devices that even the distribution of air.

In the device **100** of **FIG. 2** and **FIG. 3**, the bottom wall **108** of the lower plenum **103** is formed with an elongated slot **109** through which an elongated or knife-like stream **110** of heated air from the lower plenum is blown onto the mass of fibers **19** traveling on the collector **18** below the heating device **100** (the mass **19** and collector **18** are shown partly broken away in **FIG. 3**). **FIG. 2** and **FIG. 3** are further described in U.S. Patent Application No. 11/457,899 (Berrigan et al.). The gas-exhaust **14** preferably extends sufficiently to lie under the slot **109** of the heating device **100** (as well as extending down-web a distance **118** beyond the heated stream **110** and through an area marked **120**). Heated air in the plenum is thus under an internal pressure within the plenum **103**, and at the slot **109** it is further under the exhaust vacuum of the gas-exhaust device **14**. To further control the exhaust force a perforated plate **111** may be positioned under the collector **18** to impose a kind of back pressure or flow-restriction means that contributes to spreading of the stream **110** of heated air in a desired uniformity over the width or heated area of the collected mass **19**. Other useful flow-restriction means include screens or sintered plates.

The number, size and density of openings in the plate **111** of the collector **18** may be varied in different areas to achieve desired control. Large amounts of air pass through the fiber forming apparatus and must be disposed of in the region **115** as the fibers reach the collector. Sufficient air passes through the web and collector in the region **116** to hold the web in place under the various streams of processing air. Sufficient openness is needed in the plate under the heat treating region **117** and cooling **118** to allow treating air to pass through the web, while sufficient resistance remains to assure that the air is more evenly distributed.

The amount and temperature of heated air passed through the mass of fibers **19** is chosen to lead to an appropriate modification of the morphology of the fibers. Particularly, the amount and temperature are chosen so that the fibers reach a specified

temperature by heating rapidly which will cause the fibers to soften and bond, as well as cause the fibers to relax their chains above the T_{cc} to decrease the orientation of the amorphous regions. The heating operation is followed by immediately cooling or quenching the fibers below their T_g .

5 To achieve the intended fiber morphology change throughout the collected mass **19**, the temperature-time conditions should be controlled over the whole heated area of the mass **19**. Best results have generally been obtained when the temperature of the stream **110** of heated air passing through the web is within a range of 5°C , and preferably within 2°C or even 1°C , across the width of the mass being treated (the temperature of the heated
10 air is often measured for convenient control of the operation at the entry point for the heated air into the housing **101**, but it also can be measured adjacent the collected web with thermocouples). In addition, the heating apparatus is operated to maintain a steady temperature in the stream over time, for example, by rapidly cycling the heater on and off to avoid over- or under- heating. Preferably, the temperature is held within 1°C of the
15 intended temperature when measured at one second time intervals. The temperature of the stream **110** of the heating operation is typically from 80°C to 400°C , more preferably from 90°C to 300°C , and most preferably from 100°C to 275°C , sufficient to relax the polymer chains and substantially remove or reduce any strain induced crystallization or amorphous orientation.

20 In one embodiment, the temperature of the mass of fibers **19** of the web (for example, nonwoven fibrous web) as a result of the stream **110** ranges from 70°C to 300°C , more preferably from 80°C to 300°C , and most preferably from 90°C to 285°C . The temperature of the fibers is sufficient to soften the fibers for bonding, and to relax the orientation of the amorphous regions of the polymer chains.

25 In order to further control the heating and to complete formation of the desired morphology of the fibers of the collected mass **19**, the mass is then subjected to cooling immediately after the application of the stream **110** of heated air to quench the fibers into a substantially unoriented morphology. Such cooling can generally be obtained by drawing air over and through the mass **19** as the mass **19** leaves the controlled hot air stream **110**.
30 Numeral **120** of **FIG. 2** represents an area in which ambient air is drawn by the air-exhaust device through the web. The gas-exhaust device **14** extends along the collector **18** for a distance **118** beyond the heating device to assure thorough cooling and cooling of the

whole mass **19** in the area **120**. Air can be drawn under the base of the housing **101**, for example, in the area marked **120a** on **FIG. 2**, so that it reaches the web directly after the web leaves the hot air stream **110**.

5 A purpose of the cooling is to rapidly remove heat from the web and the fibers, and thereby substantially limit the extent and nature of crystallization or molecular ordering that may subsequently occur in the fibers. Generally, annealing the web with a heating and cooling operation is performed while the web is moved through the operation on a conveyor, where cooling is performed before the web is wound into a storage roll at the end of the operation. The times of treatment depend on the speed at which a web is
10 moved through an operation, but generally the annealing operation (heating and cooling) is performed in a minute or less, and preferably in less than 15 seconds. The annealing operation is more preferably performed in less than 5 seconds, even more preferably less than 0.5 seconds, and most preferably less than 0.001 seconds.

In one embodiment, by heating for a period of time and cooling immediately from
15 the molten/softened state to a solidified state, the fibers are substantially unoriented and substantially free of strain induced crystallization. Desirably, the mass of fibers **19** is cooled by a fluid at a temperature of at least 100°C less than the T_g as determined by DSC. In one aspect, the cooling temperature ranges from -80°C to 65°C, more preferably from -70°C to 60°C, and most preferably from -50°C to 50°C. Also, the cooling fluid is
20 desirably applied for a time from 0.001 seconds to 15 seconds. The selected cooling fluid has sufficient heat capacity to rapidly solidify the fibers.

In one embodiment, the temperature of the fibers of the web range from -70 °C to 55 °C. More preferably, the fiber temperature ranges from -60 °C to 50 °C, and most preferably from -50 °C to 40 °C. The fiber temperature is sufficient to retain the reduced
25 amorphous orientation from the heating step described above.

A first fluid may be used to heat the nonwoven fibrous web, and a second fluid may be used to cool the nonwoven fibrous web. The first fluid and second fluid may be gases, liquids, or combinations thereof. The first fluid and second fluid may be the same fluid or different fluids for the heating and cooling of the web. Other fluids that may be
30 used include water sprayed onto the fibers, for example, heated water or steam to heat the fibers, and relatively cold water to cool or quench the fibers.

In one aspect, the annealing step comprises at least one of heating and cooling of the web. Additional annealing steps may be performed to affect the performance and properties of the web. Repeated annealing steps of heating and cooling will gradually reduce the T_{cc} as shown in a DSC plot of the fibers of the nonwoven web.

5 In one embodiment, the mass of melt blown fibers are immediately annealed. Immediate treatment (annealing of the web with controlled heating and cooling) of the web prevents physical aging to occur in web samples. A lack of aging may be evidenced by the retention of flexibility and strength of a web after heat aging.

10 In another embodiment, the mass of melt blown fibers may be aged for a period of time, then treated or annealed (controlled heating and cooling). In this instance, the web may become brittle upon aging due to physical aging phenomenon. Evidence of physical aging may be found through DSC analysis showing an endotherm at the T_{cc} and/or T_m of the polymeric material. However, the dimension stability of the bonded nonwoven fibrous web is generally maintained.

15 In one aspect, the dimensionally stable bonded nonwoven fibrous web is unrestrained during the annealing step. The web may be continuous in order to be wound onto a roll or collected in a sheet form.

20 A method for making dimensionally stable nonwoven fibrous webs is described in U.S. Patent No. 5,958,322 (Thompson et al.). Thompson describes crystallinity as a dimensional stability indicator for nonwoven fibrous webs, where tentering (for example, the web is restrained on a tentering structure) was used to provide a dimensionally stable web. Further in Thompson, fibers of webs exhibit the greatest dimensional stability when the fibers are highly crystalline, and have the greatest dimension change when the web is totally amorphous. The webs of Thompson comprise strain induced crystals formed while
25 annealing the web on a tentering structure.

30 Immediately after the heating and cooling operation, the web generally has a degree of bonding sufficient for the web to be handled, for example, removed from the collection screen and wound into a storage roll. In one aspect, the web may be collected onto a roll ranging from 2 meters per minute to 800 meters/minute, more preferably from 50 meters per minute to 600 meters per minute, and most preferably from 100 meters per minute to 300 meters per minute.

In one aspect, additional bonding or shaping of the fibers of the web may include providing it with a nonplanar shape or smoothing of its surface. The web may be configured into a persistent new configuration, that is, a self-sustaining configuration that the web will generally retain during use. In some cases, shaping means smoothing one or both surfaces of the web and in some cases compacting the web. In other cases, shaping involves configuring the web into a nonplanar shape such as perhaps as a cup shape forming a shaped article for use as a face mask. The fibrous character of the web is retained during shaping, though the fibers may receive a somewhat different cross-section through the pressure of the shaping operation. A molded article of the web may result in the absence of a cold-crystallization peak in a DSC plot.

Confirmation of the desired annealing operation and resulting morphology of the amorphous characterized phase can be determined with DSC (Differential Scanning Calorimetry) testing of representative fibers from a treated web, where treatment conditions can be adjusted based on the results from DSC. DSC was used to examine changes occurring in the webs of this disclosure. Generally, a test sample (for example, a small section of the fibrous web) is subjected to two heating cycles in the DSC equipment. A first heat is run where the sample as received is heated to a temperature greater than the melting point of the sample (as determined by the heat flow signal returning to a stable base line). The second heat, which is similar to the first heat, is conducted on the sample that was melted in the first heat and then cooled, typically to lower than room temperature. The first heat measures the characteristics of a nonwoven fibrous web of the disclosure directly after its completion, without having experienced additional thermal treatment. The second heat measures the basic properties of the material of the web, with any features that were imposed on the basic material by the processing to which the material was subjected during manufacture and treatment of a web of the disclosure having been erased by the melting of the sample that occurred during the first heat.

The webs were evaluated with Modulated Differential Scanning Calorimetry (MDSC) as illustrated in **FIG. 4**, where the method is further described in the Examples section. An untreated poly(ethylene terephthalate) (PET) web was analyzed in plot **310**. The first heat scan of plot **310** shows a T_g (**312**), a T_{cc} (**314**), and a T_m (**316**) at 80 °C, 115 °C, and 258 °C, respectively. The untreated PET web was extruded and collected without the controlled heating and cooling operation of this disclosure.

Similarly, plot **300** illustrated in **FIG. 4** shows a first heat scan of a treated PET web using the annealing process (heating and cooling operation) of this disclosure. In plot **300**, the T_g (302) at 80 °C shows an endotherm as the molecules in the sample's amorphous state transition from a glassy to a rubbery state. At the T_{cc} (**304**), the exotherm shows the molecules of the amorphous regions crystallizing or aligning at 115 °C. The T_m (**306**) shows an endotherm at 258 °C where the crystalline portions of the web melt. The controlled heating and cooling operation of this disclosure for the treated PET web (plot **300**) sample shows no substantial shift in the T_{cc} (**304**) or change in the size of the exotherm when compared to the untreated PET sample of plot **310**. The melt blown fibers of the treated PET web retain a substantial cold crystallization exotherm. The T_m (**306**) of plot **300** also shows no substantial shift in T_m as well as no change in the size of the endotherm relative to the T_m (**316**) of plot **310**; both plots remained relatively the same. Plot **300** shows the annealing process does not appreciably affect the crystalline structure or morphology of the fibrous web relative to the untreated web of plot **310**. Further, plot **300** shows no appreciable formation of strain induced crystals or chain extended crystals in the treated sample relative to plot **310** of the untreated PET web.

In one aspect, stepwise annealing may be needed to gradually relax the orientation of the amorphous segments present in the polymer fibers. The fibers of the web, which are heated for a period of time and immediately cooled, may require additional stepwise annealing treatment to reduce the T_{cc} .

Further confirmation of the effect of heating and cooling on nonwoven webs was observed using X-ray diffraction scattering as described in the Examples section. In **FIG. 5**, azimuthal plots of the diffraction data for treated (**410**) and untreated (**400**) PET webs are illustrated. Individual fiber bundles were prepared and examined at 90° and 270° angles (to the long axis of the fibers) for determining the crystalline order of the polymer chains. Plot **400** shows the untreated (**400**) PET fibers possessing a low level of crystalline order, and uniaxial preferred orientation at a 90° angle (**402**) and a 270° angle (**404**), respectively. The treated (**410**) fibers of the PET web possess a lower level of crystalline order and uniaxial preferred orientation at a 90° angle (**412**) and a 270° angle (**414**) in contrast to the untreated (**400**) fibers. A plot of the treated (**410**) fibers also shows a lowering of the crystalline regions or a reduction in the orientation of the amorphous regions present in the fibers with the annealing process (heating and cooling

operation) of this disclosure relative to untreated (400) PET fibers. Further, treated (410) PET fibers do not show an increase in the level of crystalline order or amorphous orientation.

5 Polymers suitable for use in this disclosure as polymeric material(s) include polyamides (for example, nylon 6, nylon 6,6, nylon 6,10); polyesters (for example, polyethylene terephthalate, polyethylene naphthalate, polytrimethylene terephthalate, polycyclohexylene dimethylene terephthalate, polybutylene terephthalate, polylactic acid and other aliphatic polyesters); polyurethanes; acrylics; acrylic copolymers; polystyrene; polyvinyl chloride; polystyrene-polybutadiene; polystyrene block copolymers; 10 polyetherketones; polycarbonates; cyclic polyolefins and combinations thereof. The fibers of the fibrous web may be formed from a single thermoplastic material or a blend of multiple thermoplastic materials, such as, for example, a blend of one or more of the above listed polymers or a blend of any one of the above listed polymers and a polyolefin. In one aspect, the fibers are extruded to have multiple layers of different polymeric 15 materials. The layers may be arranged concentrically or longitudinally along the fiber's length.

In one embodiment, the polymeric material comprises poly(ethylene terephthalate).

In one embodiment, the polymeric material comprises poly(lactic acid).

20 Fibers also may be formed from blends of materials, including materials into which certain additives have been blended, such as pigments or dyes. Bicomponent fibers, such as core-sheath or side-by-side bicomponent fibers, may be used ("bicomponent" herein includes fibers with two or more components, each occupying a cross section of the fiber and extending over the length of the fiber). However, this invention is most advantageous with monocomponent fibers (for example, where the melt blown fibers are at least 25 monocomponent), which have many benefits (less complexity in manufacture and composition), and can be conveniently bonded and given added bondability and shapeability. Different fiber-forming materials may be extruded through different orifices of the extrusion head so as to prepare webs that comprise a mixture of fibers. The use of staple fibers has permitted the preparation of thermally stable webs which maintain loft as 30 described in U.S. Patent No. 4,118,531 (Hauser et al.).

In one aspect, polyester meltblown nonwoven fibrous webs provide a unique combination of high strength, elongation, toughness, grab strength, and tear strength

compared to other nonwoven polymeric webs, such as polypropylene nonwoven webs. Polyester nonwoven webs can be made with a high degree of rigidity or stiffness as compared to olefinic webs. This stiffness is inherent in polyester due primarily to its higher modulus values. Additionally, flame retardant properties are more easily imparted
5 to polyester nonwoven fibrous webs as compared with olefinic fibrous webs.

The fibers prepared by the method of the disclosure may range widely in diameter. Microfiber sizes (about 10 micrometers or less in diameter) may be obtained and offer several benefits; but fibers of larger diameter can also be prepared, and are useful for certain applications. More preferably, the fiber diameters of this disclosure range from 1
10 micrometer to 20 micrometers, more preferably 1 micrometer to 10 micrometers, and most preferably 5 micrometers to 8 micrometers. Fibers of circular cross-section are most often prepared, but other cross-sectional shapes may also be used. The collected fibers may be continuous or essentially discontinuous.

The nonwoven fibrous webs described are dimensionally stable when processed
15 above their T_g . The web shrinkage is typically less than 4 percent, more preferably less than 2 percent, and most preferably less than 1 percent, along its major surface when elevated to a temperature above at which the web was annealed. Samples for dimensional stability are described in the Examples section.

In one embodiment, the nonwoven fibrous web is thermally stable at a temperature
20 up to 200 °C, and further described in the Examples section.

Some webs of this disclosure may include particulate matter, as disclosed in U.S. Patent No. 3,971,373 to provide enhanced filtration. The added particles may or may not be bonded to the fibers, for example, by controlling process conditions during web formation or by later heat treatments or molding operations. The added particulate matter
25 may also be a supersorbent material such as taught in U.S. Patent No. 4,429,001. In addition, additives may be incorporated into the fibers such as dyes, pigments, or flame-retarding agents.

Webs of this disclosure are especially useful as insulation, for example, acoustic or thermal insulation. Webs comprising a blend of crimped fibers and oriented melt-blown
30 fibers are especially useful in insulation and insulation applications. The addition of crimped fibers makes the web more bulky or lofty, which enhances insulating properties as described in U.S. Patent 6,667,254 (Thompson et al.). Insulating webs disclosed are

preferably 1 or 2 centimeters or more thick, though webs as thin as 5 millimeters in thickness have been used for insulating purposes. The substantially unoriented meltblown PET fibers described herein have a small diameter, which also enhances the insulating quality of the web by contributing to a large surface area per unit volume of material. The combination of bulk and small diameter gives good insulating properties. (Mixture of melt blown fibers and staple fibers are described in U.S. Patent No. 4,118,531 (Hauser et. al.).

Because of their dimensional stability under thermal stress, webs of this disclosure are particularly suited for lining chambers such as automobile engine compartments or small and large appliance housings, for example, air conditioners, dishwashers, and refrigerators. The webs also have increased tensile strength, durability and flexural strength. Their durability enhances their utility in insulation, providing, for example, increased resistance to wear and launderability. Other illustrative uses for webs are as acoustical dampers, filters and battery separators.

The invention will be further clarified by the following examples which are exemplary and not intended to limit the scope of the invention.

Examples

The present invention is more particularly described in the following examples that are intended as illustrations only, since numerous modifications and variations within the scope of the present invention will be apparent to those skilled in the art. Unless otherwise noted, all parts, percentages, and ratios reported in the following examples are on a weight basis, and all reagents used in the examples were obtained, or are available, from the chemical suppliers described below, or may be synthesized by conventional techniques.

Differential Scanning Calorimetry

Various measurements and tests were performed on representative nonwoven fibrous webs of the examples described below. Differential scanning calorimetry (DSC) was performed using a Modulated DSC TM system (Model Q1000 supplied by TA Instruments Inc., New Castle, DE). Test samples of about 2-4 milligrams were cut from a test web with a razor blade and tested using the conditions as described below:

For Examples 1 and 2, and Comparative Examples C1 and C2, the samples were heated from -10 °C to 300 °C at a heating rate of 4 °C /minute; a perturbation amplitude of plus-or-minus 0.636 °C; and a period of 60 seconds.

For Example 3 and Comparative Example C3, the samples were heated from -25 °C to 210 °C at a heating rate of 4 °C /minute; a perturbation amplitude of plus-or-minus 0.636 °C; and a period of 60 seconds.

A heat-cool-heat test cycle was used for the test samples.

X-ray Scattering (XRD, WAXS, SAXS, GIXD, Reflectometry, Microdiffraction)

Samples examined in a transmission geometry configuration were prepared as individual fiber bundles. Fiber bundles were prepared by removing collections of individual fibers from nonwoven webs and aligning the long axis of the fibers to form fiber bundles.

Reflection geometry data was collected in the form of a survey scan by use of a Philips (Panalytical, Natick, MA) vertical diffractometer, copper K α (alpha) radiation, and proportional detector registry of the scattered radiation. The diffractometer is fitted with variable incident beam slits, fixed diffracted beam slits, and graphite diffracted beam monochromator. The survey scan was conducted from 5 to 55 degrees (2 θ) using a 0.04 degree step size and 8) second dwell time. Reflection geometry data were processed using Jade (version 7.5, MDI, Livermore, CA) software suite. Transmission geometry data was collected using a Bruker-AXS (Madison, WI) GADDS microdiffraction system, copper K α (alpha) radiation, and HiStar 2D position sensitive detector registry of the scattered radiation. Samples were centered using a 6 cm sample to detector distance, where the detector was positioned at 0 degrees (2 θ) with no sample tilt employed. A graphite monochromated 300 micron incident X-ray beam was employed at generator settings of 50 kV and 50 mA. Data was accumulated for two hours. Transmission 2D (two dimensional) data were analyzed using Bruker-AXS GADDS (version 4.1, Madison, WI) software. Three hundred sixty degree azimuthal traces of the 2D data were taken using a 0.1 degree (chi) step size over a 1.5 degree (2 theta or 2 θ) wide scattering angle range.

Examples 1 – 3 and Comparative Examples 1 - 3

The nonwoven meltblown webs of the present invention can be prepared by a process similar to that taught in Wentz, Van A., "Superfine Thermoplastic Fibers" in Industrial Engineering Chemistry, Vol. 48, pages 1342 et seq (1956), or in Report No. 4364 of the Naval Research Laboratories, published May 25, 1954 entitled "Manufacture of Superfine Organic Fibers" by Wentz, Van. A. Boone, C. D., and Fluharty, E. L., except that a drilled die was preferably used. The thermoplastic material was extruded through the die into a high velocity stream of heated air which draws out and attenuates the fibers prior to their solidification and collection. The fibers were collected in a random fashion, such as on a perforated screen.

The apparatus shown in Figure 1 was used to prepare fibrous webs from polyethylene terephthalate and polylactic acid. Examples 1 - 2 and Comparative Examples 1 - 2 (C1 - C2) were prepared from poly(ethylene terephthalate) (PET) having a Melting Temperature (T_m) of 295 °C and an intrinsic viscosity of 0.61 (3M Polyester Resin 65100; 3M Company, St. Paul, MN). Example 3 and Comparative Example 3 (C3) were prepared from polylactic acid (PLA) Natureworks 6251D available from Natureworks, LLC, Minnetonka, MN.

Example 4

Example 4 was identical to Example 1 with the addition of staple fibers into the web following the procedures taught by U.S. Patent No. 4,118,531 (Hauser et al.). The staple fibers were from oriented poly(ethylene terephthalate) (4.7 decitex and a length of approximately 5 cm) crimped staple fibers (Kosa T224 fibers; Fiber Visions Incorporated, Covington, GA). The composition of the web was 50 % by mass of the fibers of Example 2 and 50% staple fibers.

Formation and Treatment of Nonwoven Fibrous Webs

Certain parts of the apparatus and the operating conditions are detailed in **Table 1**. Apparatus parameters not reported in the table are as follows. The plate **104** of **FIG. 2** contained 1/4-inch-diameter (0.64 centimeter) holes at a uniform spacing of 3/8 inch (0.95 centimeter) such as to constitute 40 % of the plate area. The collector **18** was a 50-inch-wide (1.27 meter), 40-mesh stainless steel woven belt in a chevron pattern having 0.43

mm by 0.60 mm openings (style 2055 from Albany International Engineered Fabrics, Portland, TN).

Fibers were deposited on the collector belt to form a mass **19** having a width of about 22 inches (55.9 centimeters). Section **115** of the plate **111** underlying the belt **18** has a machine-direction length of 14.5 inches (36.8 centimeters), and contained 1.59-
5 millimeter-diameter holes on centers spaced 2.78 millimeters at a uniform spacing such as to constitute 30 % of the plate area; section **116** had a length of 23.5 inches (about 60 centimeters) and contained 1.59-millimeter-diameter holes on centers spaced 3.18 millimeters at a uniform spacing such as to constitute 23 % of the plate area; and sections
10 **117** and **118** together had a length of about 9 inches (about 23 centimeters) and contained 3.97-millimeter-diameter holes at a uniform spacing with centers spaced 4.76 millimeters such that the holes constituted 63 % of the plate area; the machine-direction length of section **117** has a slot width in Table 1, 3.8 centimeters, leaving the length **118** of the quenching or cooling section as about 19.2 centimeters. The air-exhaust duct **14** of **FIG. 3**
15 had a width (transverse to the machine direction, which is the direction of movement of the collector belt) of 22 inches (55.9 centimeters) and a length sufficient for the distance **118** in **FIG. 3** to be about 19 centimeters.

The heating face velocity reported in **Table 1** was measured at the center of the slot **109** as shown in **FIG. 3** at a point about one-half inch (1.27 centimeter) above the
20 mass using a hot-wire anemometer; 10 measurements were taken over the width of the zone and arithmetically averaged. The cooling face velocity was measured in the same manner at the center (along the machine-direction axis) of the area **120** in **FIG. 2**. The temperatures reported in **Table 1** for the heating zones 1 - 6 are temperatures of the air entering the box **101** from the conduits **107**. There were six conduits **107** and temperature
25 of input air was measured at the entry point to the box **101** by open-junction thermocouples. The air exhaust length **120** in **FIG. 2** was 20.3 cm, the air exhaust vacuum was measured to be 280 mm water, and the cooling face velocity was measured at the midpoint of area **120** to be 530 meters per minute.

30

Table 1

Example No.	C1	1	C2	2	C3	3	4
Polymer	PET	PET	PET	PET	PLA	PLA	PET
Viscosity --MFI (PLA) (g/10 min.) --IV (PET)	0.61	0.61	0.61	0.61	27	27	0.61
Melt Temperature (°C)	291	291	297	297	218	218	297
Polymer Flow Rate (g/cm/hour)	107	107	178	178	178	178	178
Die to Collector Distance (cm)	24	24	30.5	30.5	34.3	34.3	30.5
Die air Temperature (°C)	357	357	310	310	236	236	310
Air volume (actual cubic meters/min.)	8.8	8.8	9.1	9.1	4.2	4.2	9.1
Collector speed (m/min.)	1.6	1.67	2.4	2.3	4.1	4.1	2.4
Average fiber diameter (micrometer)	14.9	14.7	9.8	9.8	11.3	11.3	
Basis weight (g/m²)	100	100	97	97	139	139	200
Thickness or loft (bulk density) (mm)	1.54	1.54	1.74	1.74	1.45	1.45	10.4
Distance from TAB* (bottom) to collector (cm)	1.9	1.9	1.9	1.9	1.9	1.9	1.9
Slot width (cm)	3.8	3.8	3.8	3.8	3.8	3.8	3.8
Slot length (cm)	55.9	55.9	55.9	55.9	55.9	55.9	55.9
Heating face velocity (m/min)	0	2600	0	2580	0	2630	2580
Average zone temperature (°C)		200.1		151.0		151.0	151.0

* Through Air Bonder

Shrinkage of Webs

Shrinkage of the webs was measured as a percentage of dimension loss from the initial sample dimensions. A sample of the web was die cut to a sample size of 10 cm square noting the machine direction of the web as prepared according to ASTM D 3776-96. The samples were tested according to ASTM D 1204-84. The samples were placed in an aluminum pan, which was lightly talced to prevent the sample from adhering to the pan. The sample was then placed in a convection oven held a constant temperature for 2 hours. The webs were removed from the oven and conditioned at approximately 22 °C and 50 % relative humidity for 24 hours. The webs were measured and the percent shrinkage was calculated by taking the amount of shrinkage divided by the sample length for both dimensions. The results are reported in **Table 2**. The annealing treatment of the webs reduces the shrinkage to a useful level, where the webs are stable at temperatures above their treatment temperatures.

Table 2

CD (Cross Direction)

^ MD (Machine Direction)

5

Example No.	C1	1	C2	2	C3	3	4
Percentage shrinkage @ 150 °C MD[^] (%)	46	4	44	2	38	2	1
Percentage shrinkage @ 150 °C CD[#] (%)	49	4	48	2	34	1	1
Average Shrinkage @ 150 °C (%)	47.5	4	46	2	36	1.5	1
Percentage shrinkage @ 180 °C MD (%)			2				2
Percentage shrinkage @ 180 °C CD (%)			2				1
Average Shrinkage @ 180 °C (%)			2				1.5
Percentage shrinkage @ 200 °C MD (%)			2				1
Percentage shrinkage @ 200 °C CD (%)			1				1
Average Shrinkage @ 200 °C (%)			1.5				1

Molding of Webs

10 The molding capabilities of the webs of Examples 2 and 4 were examined by molding representative samples into a respirator-shaped cup shape using a 130 °C mold temperature as shown in Table 3. The molding procedure is described in U.S. Patent Application No. 11/461,192 (Fox et al.). A two layer sample of Example 2 and two samples of Example 4 (4(#1) and 4(#2)) were molded using a five second molding cycle. The mold was closed for five seconds and when the mold was opened, the sample was

placed upon a room temperature mold for five seconds. The mold height was 5.7 centimeters and formed a generally oval shape with a minor axis of 11.5 centimeters and a major axis of 13 centimeters. There was a 0.5-centimeter gap between mold sections. The height of the molded cup was measured by clamping it to a table top, placing a flat blade on top of the molded cup, and measuring the distance from the table top to the knife blade. A 100 gram weight was then laid on the blade and the height measured again. **Table 3** reports the mold temperatures and the height measurements. The webs of Examples 2 and 4 replicated well the mold shape even when molded at a temperature of 130 °C. The molds of C1 and C2 tore when removed from the mold as a result of web shrinkage. The annealing treatment described in this disclosure provides for a moldable web, unlike that of the untreated webs.

Table 3

Example No.	Mold Temperature (°C)	Height (uncompressed) (cm)	Height (compressed) (cm)
2	130	5.7	5.2
4 (#1)	130	5.3	4.2
4 (#2)	130	5.2	4.4

Various modifications and alterations of this invention will be apparent to those skilled in the art without departing from the scope and spirit of this invention, and it should be understood that this invention is not limited to the illustrative embodiments set forth herein.

What is claimed is:

1. A method for making a bonded nonwoven fibrous web comprising the sequential steps:
 - 5 a) extruding melt blown fibers comprising a polymeric material;
 - b) collecting the melt blown fibers as an initial nonwoven fibrous web, wherein the fibers are substantially free of strain induced crystallization;
 - 10 c) annealing the initial nonwoven fibrous web with a controlled heating and cooling operation comprising:
 - i) heating through the initial nonwoven fibrous web with a first fluid having a temperature above a cold crystallization temperature (T_{cc}) of the polymeric material of step a) to decrease the orientation of amorphous regions of the melt blown fibers providing a bonded nonwoven fibrous web; and
 - 15 ii) cooling through the bonded nonwoven fibrous web with a second fluid having a temperature below a glass transition temperature (T_g) of the polymeric material of step a) to retain the amorphous regions of the melt blown fibers providing a cooled bonded nonwoven fibrous web; and
 - 20 d) collecting the cooled bonded nonwoven fibrous web providing a dimensionally stable bonded nonwoven fibrous web.
- 25 2. The method of claim 1, wherein melt blown fibers of the bonded nonwoven fibrous web are substantially unoriented.
3. The method of claim 1, wherein the initial nonwoven fibrous web, the bonded nonwoven fibrous web, the cooled bonded nonwoven fibrous web, and the
30 dimensionally stable bonded nonwoven fibrous web are unrestrained.

4. The method of claim 1, wherein the shrinkage of the dimensionally stable bonded nonwoven fibrous web is less than 4 percent relative to the initial nonwoven fibrous web.
5. The method of claim 1, wherein the melt blown fibers are at least monocomponent.
6. The method of claim 1, wherein the polymeric material is selected from the group consisting of polyesters, polyamides, cyclic polyolefins and combinations thereof.
7. The method of claim 1, wherein the polymeric material comprises poly(ethylene terephthalate).
8. The method of claim 1, wherein the polymeric material comprises poly(lactic acid).
9. The method of claim 1, wherein the diameter of the melt blown fibers is in a range of 1 micrometer to 20 micrometers.
10. A bonded nonwoven fibrous web comprising melt blown fibers having a diameter in a range of 1 micrometer to 20 micrometers, wherein the fibers are substantially free of strain induced crystallization.
11. The bonded nonwoven fibrous web of claim 10, wherein the melt blown fibers retain a substantial cold crystallization exotherm.
12. The bonded nonwoven fibrous web of claim 10, wherein the web is dimensionally stable at a temperature in a range of 80 °C to 200 °C for at least 2 hours.
13. An insulative article comprising the bonded nonwoven fibrous web of claim 10, and further comprising staple fibers.
14. A shaped article comprising the bonded nonwoven fibrous web of claim 10.

15. A dimensionally stable bonded nonwoven fibrous web prepared by the method of claim 1.




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US2007/087106**A. CLASSIFICATION OF SUBJECT MATTER****D04H 3/16(2006.01)i, D04H 3/14(2006.01)i**

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 8: D04H 3/16

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Korean utility models and applications for utility models since 1975

Japanese utility models and applications for utility models since 1975

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

eKIPASS(KIPO internal)

Keywords: nonwoven, web, melt blown, crystallization

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	KR 10-0581637 B (MINNESOTA MINING AND MANUFACTURING COM.) 12 May 2006 See claim 1 and abstract	1-15
A	JP 07-003534 A (TOYOBO CO., LTD.) 06 January 1995 See claim 1 and abstract	1-15
A	JP 05-171556 A (MITSUI PETROCHEM IND LTD.) 09 July 1993 See claim 1 and abstract	1-15
A	US 6,916,752 B2 (BERRIGAN M. R. et al.) 12 July 2005 See claim 1 and abstract	1-15

 Further documents are listed in the continuation of Box C. See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

30 APRIL 2008 (30.04.2008)

Date of mailing of the international search report

30 APRIL 2008 (30.04.2008)

Name and mailing address of the ISA/KR

Korean Intellectual Property Office
Government Complex-Daejeon, 139 Seonsa-ro, Seo-
gu, Daejeon 302-701, Republic of Korea

Facsimile No. 82-42-472-7140

Authorized officer

KIM, KEON HYEONG

Telephone No. 82-42-481-5624



INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/US2007/087106

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
KR 10-0581637 B1	12.05.2006	AU200013373A1	29.05.2000
		CA2348469AA	18.05.2000
		DE69926257T2	30.03.2006
		EP1131479B1	20.07.2005
		JP14529616	10.09.2002
		US6849324BB	01.02.2005
		W00028122A1	18.05.2000
		W0200028122A1	18.05.2000
JP 07003534 A	06.01.1995	JP07003534	06.01.1995
		JP7003534A2	06.01.1995
JP 05171556 A	09.07.1993	CA2085073AA	12.06.1993
		DE69227498T2	22.04.1999
		EP00546837B1	04.11.1998
		EP546837B1	04.11.1998
		JP5171556A2	09.07.1993
		KR1019930013312	21.07.1993
		KR940011591B1	22.12.1994
		US5306545A	26.04.1994
US 06916752 B2	12.07.2005	AU2003223614A1	12.12.2003
		AU2003223614B2	12.12.2003
		AU2003223614AA	12.12.2003
		AU2003223614BB	30.08.2007
		BR200311134A	22.02.2005
		CA2486414AA	04.12.2003
		CA2486414A1	04.12.2003
		CN1656260A	17.08.2005
		EP01509643A1	02.03.2005
		EP01509643B1	19.12.2007
		EP1509643A1	02.03.2005
		EP1509643B1	19.12.2007
		IL164917A0	18.12.2005
		JP17526919	08.09.2005
		JP2005526919T2	08.09.2005
		KR1020050007410	17.01.2005
		MXPA04011370A	17.02.2005
		US2003216096A1	20.11.2003
		US2003216096AA	20.11.2003
		US2005161156A1	28.07.2005
		US2005161156AA	28.07.2005
		US6916752BB	12.07.2005
		W003100141A1	04.12.2003
W02003100141A1	04.12.2003		
ZA200410158A	06.10.2005		