

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
14 May 2009 (14.05.2009)

PCT

(10) International Publication Number  
**WO 2009/059888 A1**

(51) International Patent Classification:  
D21H 21/10 (2006.01) B41M 5/26 (2006.01)

(21) International Application Number:  
PCT/EP2008/064166

(22) International Filing Date: 21 October 2008 (21.10.2008)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
07120159.4 7 November 2007 (07.11.2007) EP

(71) Applicant (for all designated States except US): CIBA HOLDING INC. [CH/CH]; Klybeckstrasse 141, CH-4057 Basel (CH).

(72) Inventor; and

(75) Inventor/Applicant (for US only): KÄSER, Adolf [CH/CH]; Spitzackerstrasse 118, CH-4103 Bottmingen (CH).

(74) Common Representative: CIBA HOLDING INC.; Patent Department, Klybeckstrasse 141, CH-4057 Basel (CH).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:  
— with international search report



WO 2009/059888 A1

(54) Title: NEW FIBER PRODUCTS

(57) Abstract: Fiber products, comprising in their body at least 20 % by weight of cellulose fibers, and adequate amounts of an acid and a cationic retention aid for the acid, can be marked by means of a laser beam.

New fiber products

The present invention relates to a fiber product comprising in its body at least 20 % by weight of cellulose fibers, and adequate amounts of an acid and a cationic retention aid for the acid; to a process for its manufacture; to a process for preparing a marked fiber product by means of a laser beam; to a marked fiber product obtained by said process; and to the use of said fiber product for exposing those parts of the fiber product, where a marking is intended, to energy by means of a laser beam.

Paper or paperboard packaging usually needs to be marked with information such as logos, bar codes, expiry dates or batch numbers. Traditionally, the marking of paper or paperboard packaging is achieved by various printing techniques for example ink-jet or thermal transfer printing, or by labelling. However, these traditional marking methods are more and more replaced by laser marking as laser marking has several advantages. For example, laser marking allows contact free and quick marking, even of packaging with an uneven surface. In addition, laser markings can be obtained that are so small that the markings are invisible or nearly invisible to the human eye.

One way to achieve laser marking of paper or paperboard packaging is by coating the paper or paper board packaging with a composition, which upon treatment with laser irradiation forms a visible marking on the parts of the coating that were exposed to the laser irradiation. For example, WO 2007/031454 describes substrates coated with a laser markable coating composition which comprises a salt of an amine and an acid, for example ammonium sulphate, a char forming compound, for example sucrose, and an acrylic binder.

Another way to achieve laser marking is by preparing paper or paperboard packaging comprising a material that forms a visible mark when exposed to laser irradiation, by adding this material to the cellulosic stock in the wet end section of the paper or paperboard production. For example, EP 0 894 896 describes laser-markable paper and paperboard comprising microparticulate aromatic polymers, for example polyphenylene sulphide, which is prepared by adding the microparticulate aromatic polymers in the wet end section in the preparation of the paper and paperboard. DE 197 04 478 describes laser-markable paper and paperboard comprising microparticulate inorganic material in the form of plates.

WO 2005/054576 A1 describes that fiber products can be made flame-retardant by applying a branched polyethyleneimine which contains primary, secondary or tertiary amino groups and which has a weight average molecular weight in the range from 5000 to 1500000, and in which the numerical ratio of secondary amino groups to primary amino groups is in the range from 1.00 : 1 to 2.50:1 and the numerical ratio of secondary amino groups to tertiary amino groups is in the range from 1.20 :1 to 2.00 :1, and a phosphonic acid carrying the functional group  $-PO(OH)_2$  directly bonded to a carbon atom of the acid.

Surprisingly, it has now been found that fiber (American English: fiber; British English: fibre) products comprising within the body of the fiber product adequate amounts of an acid and a retention aid (fixing agent) for the acid can be marked by laser irradiation.

Hence, the present invention relates to a process for preparing a marked fiber product comprising at least 20 % by weight of cellulose fibers, based on the weight of the anhydrous fiber product, comprising the steps of

i) incorporating adequate amounts of

a) at least one acid,

b) at least one cationic retention aid for the acid, and

c) if desired, further the body of the fiber product additives

into the body of the fiber product, and

ii) exposing those parts of the resulting fiber product, where a marking is intended, to energy by means of a laser beam,

and to a marked fiber product obtainable by this process.

The invention relates also to the use of a fiber product comprising at least 20 % by weight of cellulose fibers, based on the weight of the anhydrous fiber product, comprising in its body, i.e. not (only) in a potential coating on the fiber product, adequate amounts of at least one acid, at least one cationic retention aid for the acid, and if desired, further additives, for exposing those parts of the fiber product, where a marking is intended, to energy by means of a laser beam.

The invention relates also to a fiber product comprising at least 20 % by weight of cellulose fibers, based on the weight of the anhydrous fiber product, comprising in its body an adequate amount of at least one acid, between 1 and 2.8 %, preferably between 1 and 2.0

%, by weight based on 100 % anhydrous fiber substrate of a cationic retention aid for the acid, and if desired, further additives.

The invention relates also to a fiber product comprising at least 20 % by weight of cellulose fibers, based on the weight of the anhydrous fiber product, comprising in its body adequate amounts of at least one acid, a cationic retention aid for the acid, and if desired, further additives, with the proviso that

- i) said retention aid is different from a branched polyethyleneimine which contains primary, secondary or tertiary amino groups and which has a weight average molecular weight in the range from 5000 to 1500000, and in which the numerical ratio of secondary amino groups to primary amino groups is in the range from 1.00 : 1 to 2.50:1 and the numerical ratio of secondary amino groups to tertiary amino groups is in the range from 1.20 :1 to 2.00 :1, or
- ii) said acid does not have or carry the functional group  $-PO(OH)_2$  directly bonded to a carbon atom of the acid.

Preferably, the invention relates to the fiber products mentioned above, wherein the fiber product comprises in its body at least 20 % by weight of cellulose fibers, based on the weight of the anhydrous fiber product, a cationic retention aid for the acid (especially between 1 and 2.8 %, preferably between 1 and 2.0 %, by weight, based on 100 % anhydrous fiber substrate, of a cationic retention aid), and a total between 1 and 6.0 % by weight, based on 100% fiber substrate, of at least one acid; and if desired, further additives.

In comparison to control fiber products not containing an acid, the marked fiber products of the present invention exhibit considerably stronger marks.

The fiber product is preferably paper or board, like paperboard or cardboard. In the context of the invention described here, a fiber product comprising at least 20 % by weight of cellulose fibers is understood as meaning a product which contains from 20 to 100% by weight of cellulose fibers. This range for the content of the cellulose fibers is based on the anhydrous fiber product, i.e. based on the fiber product without water and without the acid, retention aid and further additives. The above definition is usual in the paper industry, i.e. the fibre substrate is always taken as 100% and then loaded with effect chemicals (additives).

Suitable acids need to have one or preferably more of the following qualities, i.e.

- a) a natural affinity to paper,
- b) a certain lipophilicity,
- c) a good retention in the paper making stock, e.g. by interaction with the added retention aid.

Suitable acids are e.g. polymers or oligomers with multiple acidic moieties or monomeric acids carrying at least two acidic moieties. Said acidic moieties are directly bound to a carbon atom of the acid and are e.g. selected from  $-\text{PO}(\text{OH})_2$ ,  $-\text{O}-\text{PO}(\text{OH})_2$ ,  $-\text{PHO}(\text{OH})$ ,  $-\text{SO}_2\text{OH}$ ,  $-\text{OSO}_2\text{OH}$ ,  $-\text{SOOH}$ ,  $-\text{COOH}$  (preferably selected from  $-\text{O}-\text{PO}(\text{OH})_2$ ,  $-\text{PHO}(\text{OH})$ ,  $-\text{SO}_2\text{OH}$ ,  $-\text{OSO}_2\text{OH}$ ,  $-\text{SOOH}$  and  $-\text{COOH}$ ), and boric acid groups and derivatives thereof, wherein the proton in the OH group of the before-mentioned acidic moieties may be at least partially, e.g. to about 50%, replaced by ammonium or a protonated amine.

Suitable acids are natural or synthetic acids, like

- a) polyphosphoric acids,
- b) homo- or copolymers based on ethenic acid monomers, such as vinyl phosphonic acid, vinylsulfuric acid ( $\text{H}_2\text{C}=\text{CH}-\text{OSO}_3\text{H}$ ), vinyl sulfonic acid ( $\text{H}_2\text{C}=\text{CH}-\text{SO}_3\text{H}$ ), methylallyl sulfonic acid (MAS), 2-acrylamido-2-methylpropanesulfonic acid (AMPS), styrenesulfonic acid, maleic acid, maleic acid anhydride, fumaric acid, or acrylic acid,
- c) copolymers based on neutral (ethenic) monomers, such as ethylene, butadiene, styrene, (meth)acrylamides, (meth)acrylates or maleic acid imide derivatives, or derivatives thereof, co-polymerised with the above-mentioned acid monomers, e.g. anionic PAMs, i.e. acrylamides co-polymerised with acrylic acid or with anionic acrylamide monomers, like 2-acrylamido-2-methyl-1-propanesulfonic acid, e.g. in the form of its sodium salt of the formula  $\text{CH}_2=\text{CH}-\text{CONH}-\text{CH}_2-\text{C}(\text{CH}_3)_2-\text{SO}_3\text{Na}$ , or
- d) sulfomethylated lignosulfonic acids, or sulfonated formaldehyde condensates.

Also suitable are monomeric acids carrying at least two of the above-mentioned acidic moieties, like phytic acid, or acids from the group of commercially available sequestering agents (which are described in Trends in Analytical Chemistry 22 (10), 2003, pp 708-722, and commercially available e.g. under the trade names Masquol or Briquest) including e.g. diethylenetriamine penta(methylenephosphonic acid) (DTPMP; also named diethylenetriaminepentakis [methylenephosphonic acid]), hexamethylenediamine

tetra(methylene-phosphonic acid) (HDTMP or HDTP), nitrilotris(methylene phosphonic acid), 1-hydroxyethyl(id)ene-1,1-diphosphonic acid (HEDP or HEDPA), amino-tri(methylene) phosphonic acid (ATMP), ethylene diamine tetra-(methylene) phosphonic acid (EDTP), 2-phosphono-1,2,4-butanetricarboxylic acid (PBTC), and monomeric acids of lipophilic character and with affinity to paper, e.g. 2-(4-aminophenyl)-6-methylbenzothiazole-7-sulfonic acid (sold under the trivial name dehydroparathiotoluidine sulfonic acid), abietic acid, and certain triazene derivatives, e.g. 1,3,5-triazene derivatives substituted e.g. by aliphatic, aromatic or aromatic-aliphatic amino groups, e.g. alkylamino groups, carrying at least one of the above-mentioned acidic moieties.

Preferred acids are e.g. polyphosphoric acid, phytic acid, diethylenetriamine penta(methylenephosphonic acid), hexamethylenediamine tetra(methylene-phosphonic acid), nitrilotris(methylene phosphonic acid), 1-hydroxyethyl(id)ene-1,1-diphosphonic acid, amino-tri(methylene) phosphonic acid, ethylene diamine tetra-(methylene) phosphonic acid, 2-phosphono-1,2,4-butanetricarboxylic acid, 2-(4-aminophenyl)-6-methylbenzothiazole-7-sulfonic acid (dehydroparathiotoluidine sulfonic acid), and abietic acid, wherein the proton in the OH group of the before-mentioned acids may be at least partially replaced by ammonium or a protonated amine.

Particularly preferred are polyphosphoric acid, phytic acid, 2-(4-aminophenyl)-6-methylbenzothiazole-7-sulfonic acid (dehydroparathiotoluidine sulfonic acid), and abietic acid, wherein the proton in the OH group of the before-mentioned acids may be at least partially replaced by ammonium or a protonated amine.

Most preferred are polyphosphoric acid and phytic acid, wherein the proton in the OH group of the before-mentioned acids may be at least partially replaced by ammonium or a protonated amine.

Also suitable are inorganic acids, like sulfuric, sulfurous, phosphoric, and phosphorous acid; polymolybdic acids, polytungstic acids and their precursors, phosphomolybdic acid, phosphotungstic acid, and boric acid derivatives.

An adequate amount of the acid is an amount sufficient to enable laser marking of the fiber product. The acid is usually added in an amount of about 1 to 10 %, preferably 1 to 6 %,

especially 2 to 6%, by weight based on 100 % by weight of anhydrous fiber substrate. Before addition to the fiber substrate the acid may be partially pre-neutralized with a suitable base, like ethanolamine. For example, up to about 50% of the acid may thus be pre-neutralized. Hence, an adequate amount of the acid means especially 1 to 10 %, preferably 1 to 6 %, particularly 2 to 6%, by weight based on 100 % by weight of anhydrous fiber substrate.

The cationic retention aid for the acid serves the purpose to retain the above-mentioned acid(s) with the cellulosic fibers.

Suitable cationic retention aids (cationic fixing agents) are e.g. natural or synthetic polymers with multiple cationic moieties, in particular natural and synthetic cationic polymers used in the paper making industry comprising a diversity of mol weights and charge densities as e.g. described in Handbook of Paper & Board, E. Holik, Wiley-VCH Verlag Weinheim, 2006, chapter 3: chemical additives: dry & wet strength agents, fixing agents, retention & drainage agents etc.

The above cationic retention aids comprise polymers having protonable functional groups or cationic groups and having a natural affinity for cellulosic fibers, like polyamines and polyimines, e.g. polyethylenimines (PEIs), polyvinylamines (PVams), polyallylamines (in particular poly(diallyldimethylammonium chlorides) [p-DADMACs]), epichlorohydrin based polyamines, dicyanodiamide based polyamines, cationic polyacrylamide based copolymers and terpolymers (so called cationic PAMs), cationic starches, and natural polymers with cationic character. Preferably, said cationic groups are non-quaternized amino functionalities.

Suitable polyethylenimines (PEIs) are e.g. branched polyethyleneimines containing primary, secondary and tertiary amino groups, e.g. high molecular weight polyethyleneimines like Lupasol® P, Lupasol® WF, or Lupasol® G500 available from BASF.

Suitable polyvinylamines (PVams) are e.g. unbranched polyethyleneamines derived from N-vinyl-formamide still carrying some residual non hydrolyzed formyl groups, like Luredur® VD, or Luredur® VI available from BASF.

Suitable polyallylamines (in particular poly(diallyldimethylammonium chlorides) are e.g.

Alcofix® 110, Alcofix® 111, Alcofix® 169, Alcofix® 161 (the latter is a copolymerisate with acrylamide) available from Ciba Specialty Chemicals.

Suitable epichlorohydrin based polyamines are e.g. copolymers derived from epichlorohydrin and dialkylamines such as dimethylamine, like Alcofix® 135, Alcofix® 159, Alcofix® 160, Tinofix® AP available from Ciba Specialty Chemicals. Structuring can be induced by replacing small amounts of the dialkylamine by di- or tri- amines such as ethylene diamine or diethylene triamine.

Suitable dicyanodiamide based polyamines are e.g. copolymers derived from dicyanodiamide, formaldehyde and ammoniumchloride, like Tinofix® WSP available from Ciba Specialty Chemicals, or from dicyanodiamide and alkylenetriamines e.g. diethylenetriamine, like Tinofix® ECO-N available from Ciba Specialty Chemicals.

Suitable cationic polyacrylamide based copolymers (cationic PAMs) are e.g. copolymers derived from acrylamide and a cationic monomer such as alkyl halide adducts of N,N-dialkylaminoalkyl(meth)acrylates, like N,N-dimethylaminoethylacrylate methyl chloride, or of dialkylamino-alkyl(meth)acrylamides, like dimethylaminopropylacrylamide, or of alkyldiallylamines, like methyldiallylamine.

Suitable cationic starches are e.g. derived from starch by reaction with glycidyl-trimethylammonium chloride (also called 2,3-epoxypropyl trimethyl ammonium chloride, cf. United States Patent 6,290,765), like Raifix 01035, Raifix 25015, and Raifix 25035 available from Ciba Specialty Chemicals.

Suitable natural polymers with cationic character are e.g. certain aminocellulose derivatives, like chitosan (which is a polyaminosaccharide derived from chitin).

Preferred cationic retention aids are polyamines such as polyethylenimines (PEIs).

An adequate amount of the cationic retention aid for the acid is an amount sufficient to retain the acid within the body of the fiber product. The cationic retention aid for the acid is e.g. used or present in an amount of about 0.3 to 7% by weight, preferably 1-2.8 %, most preferably 1-2%, by weight based on 100 % fiber substrate. Hence, an adequate amount of

the cationic retention aid for the acid means especially an amount of about 0.3 to 7% by weight, preferably 1-2.8 %, most preferably 1-2%, by weight based on 100 % fiber substrate.

Considering the relative amounts by weight of the acid versus the cationic retention aid for the acid, the acid is usually employed in an amount from about one-fold to about six-fold the amount by weight of the cationic retention aid for the acid, keeping in mind that the acid may be partially neutralized.

Preferred are fiber products wherein the retention aids for the acid are selected from polyvinylamines, polyallylamines, epichlorohydrin based polyamines, dicyanodiamide based polyamines, cationic polyacrylamide based copolymers and terpolymers, cationic starches, and natural polymers with cationic character.

If desired, the fiber product may further comprise additives. The additives that may be included in the fiber product of the present invention can be e.g. any component suitable for improving the performance of the fiber product, e.g. as described in Handbook of Paper & Board, E. Holik, Wiley-VCH Verlag Weinheim, 2006. Suitable additives are e.g. cationic coagulants, dry strength agents, retention aids (e.g. anionic inorganic microparticles) for the other additives, sizing agents; pH adjusting agents, such as inorganic or organic acids or bases; charge neutralizing agents, fillers, carbonizing agents, energy (e.g.heat) transfer agents, optical brighteners, dyes, dye fixatives, pigments, cross-linking agents, sequesterant agents, antiblocking materials, lubricants, flame retarding additives, stabilizers, antioxidants, rheology modifiers, wetting agents, biocides, smoke suppressants, and taggants.

It is possible that the same substance fulfils more than one function as an additive. For example, some substances can be both coagulants and retention aids. Other substances can be both fillers and pH adjusting agents, etc.

Said additives such as cationic coagulants, dry strength agents, retention aids, sizing agents, optical brighteners, fillers, and dye fixatives can be added to the stock in the wet end section. The order of addition and the specific addition points depend on the specific application, and are common papermaking practice.

Cationic coagulants are water-soluble low molecular weight compounds of relatively high cationic charge. The cationic coagulants can be inorganic compounds, like aluminium based fixing agents, such as aluminum sulfate, aluminium potassium sulfate (alum) or polyaluminium chloride (PAC) ; or an organic polymer such as polydiallyldimethylammoniumchloride, polyamidoamine/epichlorhydrin condensates or polyethyleneimine. The cationic coagulants are also usually added to the thick stock and serve to fix pitch and/or stickies.

Cationic coagulants, which are organic polymers, can also be added in order to neutralize the charge of the stock, which may be required, when, for example, an anionic retention aid of relatively high molecular weight is added later to the thin stock. In this case, the cationic coagulant is usually added very close to the dilution point to make thick stock into thin stock.

Examples of dry strength agents are water-soluble anionic copolymers of acrylamide of relatively low molecular weight (usually below one million g/mol) and polysaccharides of relatively high molecular weight. Examples of anionic copolymers of acrylamide are copolymers derived from acrylamide and an anionic monomer such as acrylic acid. The anionic copolymers of acrylamide are usually added to the thin stock. Examples of polysaccharides are carboxymethyl cellulose, guar gum derivatives and starch. Cationic starch, carboxymethyl cellulose and guar gum derivatives are usually added to the thick stock, whereas uncooked native starch can be sprayed on the forming web.

Preferably, retention aids are added in the wet end section in order to improve the retention of the acids, fines, fillers and fibers on the web. Examples of cationic retention aids for the acids in accordance with the present invention have been given above. Examples of retention aids for the (other) additives are water soluble polymers, anionic inorganic microparticles, polymeric organic microparticles and combinations thereof (retention systems). The retention aids are usually added to the thin stock, after the fan pump.

The water-soluble polymers used as retention aids can be non-ionic, cationic or anionic. Examples of non-ionic polymers are polyethylene oxide and polyacrylamide. Examples of anionic polymers are copolymers derived from acrylamide and an anionic monomer such as acrylic acid or 2-acrylamido-2 methyl-1-propane sulfonic acid. Preferably, the anionic

polymers used as retention aids are of relatively high molecular weight (usually above one million g/mol).

Examples of anionic inorganic microparticles are colloidal silica and swelling clays such as bentonite. Examples of polymeric organic microparticles are described above.

Two or more retention aids can be combined to form a retention system. Examples of retention systems are combinations of anionic water-soluble polymers and anionic inorganic microparticles and combinations of cationic water-soluble polymers, anionic water-soluble polymers and anionic inorganic microparticles. When anionic water-soluble polymers are added in combination with an anionic inorganic microparticle, the two components can be added simultaneously, or the anionic inorganic microparticle is added first, followed by the addition of the polymer. When the retention system also comprises a cationic water-soluble polymer, this cationic polymer is usually added before adding the anionic water-soluble polymer and the anionic inorganic microparticle.

Further examples of retention systems are combinations of cationic water-soluble polymers and polymeric organic microparticles and combinations of cationic water-soluble polymers, anionic water-soluble polymers and polymeric organic microparticles.

Preferably, the retention aid is a cationic water-soluble polymer or a retention system comprising a cationic water-soluble polymer.

Examples of sizing agents are natural sizing agents, such as rosin, and synthetic sizing agents, such as alkenyl succinic anhydride (ASA) and alkyl ketene dimer (AKD).

pH adjusting agents are e.g. inorganic or organic acids or bases.

Charge neutralizing agents are e.g. anionic charge neutralizing agents, like nanosilicas and bentonites. Charge neutralizing agents are advantageously used in combination with cationic PAMs, i.e. when the acids present in the fiber product are polyacrylamides co-polymerised with maleic acid or with anionic acrylamide monomers, like 2-acrylamido-2-methyl-1-propanesulfonic acid, e.g. in the form of its sodium salt of the formula  $\text{CH}_2=\text{CH}-\text{CONH}-\text{CH}_2-\text{C}(\text{CH}_3)_2-\text{SO}_3\text{Na}$ .

Examples of fillers are mineral silicates such as talc, mica and clay such as kaolin, calcium carbonate such as ground calcium carbonate (GCC) and precipitated calcium carbonate (PCC), and titanium dioxide. The filler is usually added into the thick stock.

Carbonizing agents are char forming compounds. A char forming compound is a compound which forms char upon energy treatment. Generally, a char forming compound is of high carbon and oxygen content. Preferred carbonizing agents for the present invention have adequate affinity for cellulosic fibres.

Examples of suitable char forming compounds are carbohydrates such as polysaccharides, and derivatives thereof. Examples of suitable polysaccharides are starch, gum arabic, dextrin and cyclodextrin.

Energy transfer agents, e.g. heat transfer agents, can absorb the incident energy and transfer this energy to the system thermally or otherwise, such as UV absorber or especially IR absorber.

An example of a UV absorber is 2-hydroxy-4-methoxybenzophenone.

IR absorbers can be organic or inorganic. Examples of organic IR absorbers are alkylated triphenyl phosphorothionates, for example as sold under the trade name Ciba® Irgalube® 211 or Carbon Black, for example as sold under the trade names Ciba® Microsol® Black 2B or Ciba® Microsol® Black C-E2.

Examples of inorganic IR absorbers are oxides, hydroxides, sulfides, sulfates and phosphates of metals such as copper, bismuth, iron, nickel, tin, zinc, manganese, zirconium and antimony, including antimony(V) oxide doped mica and tin(IV) oxide doped mica.

Examples of optical brighteners are stilbene derivatives such as sold, for example, under the tradename Ciba® Tinopal® CBS-X.

Pigments can be added as inorganic IR absorbers, for enhanced contrast between unimaged and imaged areas or as a security feature.

Examples of pigments which function as inorganic IR absorbers are kaolin, calcined kaolin, mica, aluminum oxide, aluminum hydroxide, aluminum silicates, talc, amorphous silica and colloidal silicon dioxide.

Examples of pigments which can be added for enhanced contrast between unimaged and imaged area are titan dioxide, calcium carbonate, barium sulfate, polystyrene resin, urea-formaldehyde resin, hollow plastic pigment.

Examples of pigments which can be added as a security feature are fluorescent pigments or magnetic pigments.

Sequesterant agents are e.g. diethylenetriaminepentaacetic acid (penta sodium salt).

Examples of rheology modifiers are xanthan gum, methylcellulose, hydroxypropyl methylcellulose, or acrylic polymers such as sold under the tradenames Ciba® Rheovis® 112, Ciba® Rheovis® 132 and Ciba® Rheovis® 152.

An example of a wetting agent is Ciba® Irgaclear® D, a sorbitol based clarifying agent,

Examples of biocides are Acticide® MBS, which includes a mixture of chloromethyl isothiazolinone and methyl isothiazolinone, Biocheck® 410, which includes a combination of 2-dibromo-2,4-dicyanobutane and 1,2-benzisothiazolin-3-one, Biocheck®721M, which includes a mixture of 1,2-dibromo-2,4-dicyanobutane and 2-bromo-2-nitro-1,3-propanediol and Metasol®TK 100, which includes 2-(4-thiazolyl)-benzimidazole.

An example of a smoke suppressant is ammonium octamolybdate.

Taggants are substances added to a product to indicate its source of manufacture.

The additives are no compulsory constituent of the fiber products according to the present invention, i.e. some of them may be present, if desired, but may be also missing. If they are employed, they are usually added in the amounts customary in the paper or board making art for the particular additive. Hence, as long as the additive does not have a negative influence

on the desired activity of the acid or the retention aid for the acid, an adequate amount of an additive is in the context of the present invention normally the amount customary in the paper or board making art for the particular additive. In case of such negative influence the amount of the additive has to be reduced until the negative influence has gone or has been reduced to an acceptable level. For example, care has to be taken that certain additives do not neutralize the whole acid employed.

Those parts of the resulting fiber product, where a marking is intended, are exposed to energy by means of a laser beam. Especially suitable are low energy lasers (0.3-50 mJ/cm<sup>2</sup> preferably 0.3-5 mJ/cm<sup>2</sup>), like CO<sub>2</sub> IR lasers (having e.g. wavelength: 10'600nm, power: 0.5 to 4 W, diameter of laser beam: 0.35 mm, line speed 300 to 1000 mm/s), but, if suitable laser light absorbents, i.e. absorbents tuned to the wave length of the desired laser, are added, other lasers, like YAG-lasers (yttrium-aluminium-garnet-lasers; YAG-lasers doped with neodyme [Nd:YAG-lasers] emit IR [infra-red] radiation of 1064 nm wave length) or diode lasers can be used as well.

Best marking results are obtained when the pH of the fiber stock comprising the acid, retention aid, and, if desired, further additives is about 5.0 to 6.5, preferably about 5.5 to 6.5, e.g. 6.0. A pH at the upper level of this range is often preferred by the user because acidic papers suffer from stability drawbacks.

The invention relates also to a process for preparing the fiber product of the present invention comprising mixing adequate amounts of the acid, retention aid, water, and, if desired, further additives with the fiber stock, e.g. paper stock, during fiber product making, e.g. papermaking, and isolating the fiber product. The adequate amounts of the acid, retention aid, and additives are as specified herein above.

The fiber product of the present invention is manufactured starting e.g. from a suspension, especially an aqueous suspension, comprising cellulose fibers, water and additives. Said fiber suspension usually comprises from 0.3 to 15 %, preferably 0.5 to 1.5 % by weight of cellulose fibers. This proportion of cellulose fibers in the suspension must be such that, after removal of the water, the finished fiber product contains at least 20 % by weight of cellulose fibers, based on the fiber product without water, acid, retention aid and further additives.

The cellulose fibers may e.g. comprise 30% sulfate long fiber and 70% sulfate short fiber milled to 35° SR.

On a laboratory scale one may e.g. proceed further as follows:

The suspension is stirred for some time, e.g. 1 hour, e.g. at room temperature. Thereafter, if desired, more water may be added, followed by an aqueous solution of the retention aid for the acid, e.g. an aqueous solution containing 5% by weight of Lupasol® P available from BASF, which is a high molecular weight polyethyleneimine. After a time sufficient to ensure that the retention aid is retained with the fibers, an aqueous solution of the acid, e.g. an aqueous solution containing 5% by weight of 1-hydroxyethylene-1,1-diphosphonic acid (HEDPA), are added. If necessary, the pH of the suspension is adjusted to about 5.5 to 6.5, preferably about 6.0. The acid may also be partially pre-neutralized, for example by reaction with a suitable amine, like ethanolamine. After stirring the suspension for a time sufficient to ensure that the acid is retained with the fibers, e.g. by way of reaction with the retention aid, and, if desired, after adding more water, the suspension may e.g. be filtered by suction to form a sheet of the fiber product, e.g. a sheet of paper, which may be dried e.g. at an elevated temperature, e.g. about 90 °C.

As evident from Table 1 further below, the paper thus obtained exhibits considerably stronger marks in comparison to control paper not treated with the acid and retention aid when exposed to a laser beam.

The above laboratory scale process may be adapted to industrial scale as is well known to a person skilled in the art (cf. e.g. Handbook of Paper & Board, E. Holik, Wiley-VCH Verlag, Weinheim, 2006).

The following Examples illustrate the invention.

#### Example 1

10 g of fiber raw material are suspended in 400 g of water at room temperature. The fiber material consists of 30% sulfate long fiber and 70% sulfate short fiber milled to 35° SR. This suspension is stirred for 1 hour. After addition of another 400 g of water 14 g of an aqueous solution containing 5% by weight (calculated on the basis of a 100% content of the active

substance, i.e. polyethyleneimine) of Lupasol® P available from BASF, which is a high molecular weight (average molecular weight of about 750,000) polyethyleneimine having a solids content of about 48-52 % by weight, are added. After 5 minutes 15 g of an aqueous solution containing 5% by weight 1-hydroxyethylene-1,1-diphosphonic acid (HEDPA) are added. The pH of the suspension is 6.0. The suspension is stirred for another 15 minutes, filled up with water to a weight of 1000 g and filtered by suction to form a paper sheet with a specific weight of 80 g/m<sup>2</sup>. The sheet is dried for 15 min at 90 °C. The sheet is then imaged using a CO<sub>2</sub> IR laser (wavelength: 10'600nm, power: 0.5 to 4 W, diameter of laser beam: 0.35 mm, line speed 300 to 1000 mm/s) to yield a high contrast brown marking which is a trace to distinctly stronger compared to untreated fiber used as a standard (cf. Table 1 further below).

If the pH value is adjusted with less acid, e.g. to a pH range of 7-8 the sheets produced show much weaker markings by laser imaging.

#### Examples 2 and 3

If 15 g of the 5% aqueous HEDPA solution in Example 1 are replaced by 19 g of a 5% aqueous solution of phytic acid, or by 11.6 g of a 5% aqueous solution of polyphosphoric acid (PPA; 5% stock solution prepared from 5 g of 83% PPA based on phosphorus oxide (P<sub>2</sub>O<sub>5</sub>) content diluted to 100 g by water), sheets are obtained, which mark considerably stronger using the above CO<sub>2</sub> IR laser.

#### Examples 4-6

These examples are prepared accordingly using the parameters as depicted in Table 1 and giving marking results with a CO<sub>2</sub> laser as shown in the same table.

#### Example 7 (with pre-neutralization of the acid)

10 g of fibre raw material are suspended in 400 g of water at room temperature. The fiber material consists of 30% sulfate long fiber and 70% sulfate short fiber milled to 35° SR. This suspension is stirred for 1 hour. After addition of another 400 g of water 5.6 g of an aqueous solution containing 5% by weight (calculated on the basis of 100% active substance) of Lupasol P®, BASF, is added. After 5 minutes 13 g of an aqueous solution containing 5% of 1-hydroxyethylene-1,1-diphosphonic acid (HEDPA), partially pre-neutralized with 0.19 g of ethanolamine to a pH of 2.4, are added. The pH of the final suspension is 6.0. The

suspension is stirred for another 15 minutes, filled up with water to a weight of 1000 g and filtered by suction to form a paper sheet with a specific weight of 80 g/m<sup>2</sup>. The sheet is dried for 15 minutes at 90 °C. The sheet is then imaged using a CO<sub>2</sub> IR laser (wavelength: 10'600nm, power: 0.5 to 4 W, diameter of laser beam: 0.35 mm, line speed 300 to 1000 mm/s) to yield a high contrast brown marking.

#### Examples 8-14

These examples are prepared according to Example 7 using the parameters as depicted in Table 1 and giving marking results with a CO<sub>2</sub> laser as shown in the same table.

Table 1: Experimental data, marking results

In Examples 1-14 the pH of the stock suspension before sheet formation is 6.0. The amount of polyphosphoric acid is calculated as P<sub>2</sub>O<sub>5</sub>.

#### **Amounts of additives per 1000 g of fiber**

Exam- ple	Amount of Lupa- sol P (100 %) [g]	Amount [g] (100 %) and kind of acid derivative	P de- tected on paper [%]	Degree of ex- haust- ion for phos- phoric acid [%]	Amount [g] and kind of amine (100%) used for neutralizing about half of the acid	pH of acid solution after partial neutrali- zation	Marking result on treated cellulose fibre relative to standard (1-4 W laser)
Stand- ard	0	0					standard
1	70	75, HEDPA	1.1	~55	0	-	trace to distinctively stronger
2	70	95, phytic acid	1.4	~60	0	-	considerably stronger
3	70	58, poly- phos- phoric acid	1.7	~80	0	-	considerably stronger

4	28	30, HEDPA	0.5	~55	0	-	trace stronger
5	28	38, phytic acid	0.6	~60	0	-	distinctively stronger
6	28	23.2, poly-phosphoric acid	0.7	~80	0	-	distinctively stronger
7	28	65, HEDPA	0.8	~45	19 ethanol-amine	2.4	trace stronger
8	28	82, phytic acid	1.1	~55	21.5 ethanol-amine	2.1	considerably stronger
9	28	79, phytic acid	1.0	~50	6.0 ammonia	2.1	considerably stronger
10	28	80, phytic acid	1.1	~55	18.3 oxybis-ethylamine	2.1	considerably stronger
11	28	35, poly-phosphoric acid	1.1	~80	11 ethanol-amine	1.4	considerably stronger
12	28	35, poly-phosphoric acid	1.1	~80	3.1 ammonia	1.4	considerably stronger
13	28	36, poly-phosphoric acid	1.1	~80	9.4 oxybis-ethylamine	1.4	considerably stronger
14	15	25, polyphosphoric	0.8	~80	19 ethanol-amine	3.2	distinctively to considerably

		acid					stronger
--	--	------	--	--	--	--	----------

**Claims**

1. A process for preparing a marked fiber product comprising at least 20 % by weight of cellulose fibers, based on the weight of the anhydrous fiber product, comprising the steps of

i) incorporating adequate amounts of

- a) at least one acid,
- b) at least one cationic retention aid for the acid, and
- c) if desired, further additives

into the body of the fiber product, and

ii) exposing those parts of the resulting fiber product, where a marking is intended, to energy by means of a laser beam.

2. Use of a fiber product comprising at least 20 % by weight of cellulose fibers, based on the weight of the anhydrous fiber product, comprising in its body adequate amounts of at least one acid, at least one cationic retention aid for the acid, and if desired, further additives, for exposing those parts of the fiber product, where a marking is intended, to energy by means of a laser beam.

3. A fiber product comprising at least 20 % by weight of cellulose fibers, based on the weight of the anhydrous fiber product, comprising in its body an adequate amount of at least one acid, between 1 and 2.8 % by weight based on 100% anhydrous fiber substrate of a cationic retention aid for the acid, and if desired, further additives.

4. A fiber product comprising at least 20 % by weight of cellulose fibers, based on the weight of the anhydrous fiber product, comprising in its body adequate amounts of at least one acid, a cationic retention aid for the acid, and if desired, further additives, with the proviso that

- i) said retention aid is different from a branched polyethyleneimine which contains primary, secondary or tertiary amino groups and which has a weight average molecular weight in the range from 5000 to 1500000, and in which the numerical ratio of secondary amino groups to primary amino groups is in the range from 1.00 : 1 to 2.50:1 and the numerical ratio of secondary amino groups to tertiary amino groups is in the range from 1.20 :1 to 2.00 :1, or
- ii) said acid does not have or carry the functional group  $-PO(OH)_2$  directly bonded to a carbon atom of the acid.

5. Process for preparing a fiber product as claimed in claim 3 or 4 comprising mixing adequate amounts of the acid, retention aid, water, and, if desired, further additives with the fiber stock during fiber product making and isolating the fiber product.
6. Process, use or fiber product according to any one of claims 1-5 wherein the fiber product is paper or board.
7. Process, use or fiber product according to any one of claims 1-6 wherein the acid is a polymer or oligomer with multiple acidic moieties selected from  $-\text{PO}(\text{OH})_2$ ,  $-\text{O}-\text{PO}(\text{OH})_2$ ,  $-\text{PHO}(\text{OH})$ ,  $-\text{SO}_2\text{OH}$ ,  $-\text{OSO}_2\text{OH}$ ,  $-\text{SOOH}$ ,  $-\text{COOH}$ , and boric acid groups and derivatives thereof, wherein the proton in the OH group of the before-mentioned acidic moieties may be at least partially replaced by ammonium or a protonated amine.
8. Process, use or fiber product according to any one of claims 1-6 wherein the acid is a polymer or oligomer with multiple acidic moieties selected from  $-\text{O}-\text{PO}(\text{OH})_2$ ,  $-\text{PHO}(\text{OH})$ ,  $-\text{SO}_2\text{OH}$ ,  $-\text{OSO}_2\text{OH}$ ,  $-\text{SOOH}$ ,  $-\text{COOH}$ , and boric acid groups and derivatives thereof, wherein the proton in the OH group of the before-mentioned acidic moieties may be at least partially replaced by ammonium or a protonated amine.
9. Process, use or fiber product according to any one of claims 1-6 wherein the acid is a monomeric acid carrying at least two acidic moieties selected from  $-\text{PO}(\text{OH})_2$ ,  $-\text{O}-\text{PO}(\text{OH})_2$ ,  $-\text{PHO}(\text{OH})$ ,  $-\text{SO}_2\text{OH}$ ,  $-\text{OSO}_2\text{OH}$ ,  $-\text{SOOH}$ , and  $-\text{COOH}$ , wherein the proton in the OH group of the before-mentioned acidic moieties may be at least partially replaced by ammonium or a protonated amine.
10. Process, use or fiber product according to any one of claims 1-6 wherein the acid is a monomeric acid carrying at least two acidic moieties selected from  $-\text{O}-\text{PO}(\text{OH})_2$ ,  $-\text{PHO}(\text{OH})$ ,  $-\text{SO}_2\text{OH}$ ,  $-\text{OSO}_2\text{OH}$ ,  $-\text{SOOH}$ , and  $-\text{COOH}$ , wherein the proton in the OH group of the before-mentioned acidic moieties may be at least partially replaced by ammonium or a protonated amine.
11. Process, use or fiber product according to any one of claims 1-6 wherein the acid is selected from

- a) polyphosphoric acids,
- b) homo- or copolymers based on acid monomers selected from vinyl phosphonic acid, vinylsulfuric acid, vinyl sulfonic acid, methylallyl sulfonic acid, 2-acrylamido-2-methylpropane-sulfonic acid, styrene sulfonic acid, maleic acid, maleic acid anhydride, fumaric acid, and acrylic acid,
- c) copolymers based on neutral monomers selected from ethylene, butadiene, styrene, (meth)acrylamides, (meth)acrylates, and maleic acid imide derivatives, and derivatives thereof, co-polymerised with the above-mentioned acid monomers, and
- d) sulfomethylated lignosulfonic acids, or sulfonated formaldehyde condensates.

12. Process, use or fiber product according to any one of claims 1-6 wherein the acid is polyphosphoric acid, phytic acid, diethylenetriamine penta(methylenephosphonic acid), hexamethylenediamine tetra(methylene-phosphonic acid), nitrilotris(methylene phosphonic acid), 1-hydroxyethyl(id)ene-1,1-diphosphonic acid, amino-tri(methylene) phosphonic acid, ethylene diamine tetra-(methylene) phosphonic acid, 2-phospono-1,2,4-butanetricarboxylic acid, 2-(4-aminophenyl)-6-methylbenzothiazole-7-sulfonic acid, and abietic acid, wherein the proton in the OH group of the before-mentioned acids may be at least partially replaced by ammonium or a protonated amine.

13. Process, use or fiber product according to any one of claims 1-6 wherein the acid is polyphosphoric acid, phytic acid, 2-(4-aminophenyl)-6-methylbenzothiazole-7-sulfonic acid, and abietic acid, wherein the proton in the OH group of the before-mentioned acids may be at least partially replaced by ammonium or a protonated amine.

14. Process, use or fiber product according to any one of claims 1-13 wherein the retention aid is selected from polymers having protonable functional groups or cationic groups and having a natural affinity for cellulosic fibers.

15. Process, use or fiber product according to claim 14, wherein said polymers are selected from polyamines and polyimines.

16. Process, use or fiber product according to claim 14, wherein said polymers are selected from polyethyleneimines, polyvinylamines, polyallylamines, epichlorohydrin based

polyamines, dicyanodiamide based polyamines, cationic polyacrylamide based copolymers and terpolymers, cationic starches, and natural polymers with cationic character.

17. Process, use or fiber product according to claim 14, wherein said polymers are selected from polyvinylamines, polyallylamines, epichlorohydrin based polyamines, dicyanodiamide based polyamines, cationic polyacrylamide based copolymers and terpolymers, cationic starches, and natural polymers with cationic character.

18. Process, use or fiber product according to any one of claims 1-17 wherein the fiber product comprises in its body at least 20 % by weight of cellulose fibers, based on the weight of the anhydrous fiber product, and at least one acid, between 1 and 2.0 % by weight based on 100% fiber substrate of a cationic retention aid for the acid, and, if desired, further additives.

19. Process, use or fiber product according to any one of claims 1-18 wherein the fiber product comprises in its body at least 20 % by weight of cellulose fibers, based on the weight of the anhydrous fiber product, a cationic retention aid for the acid, and a total between 1 and 6.0 % by weight, based on 100% fiber substrate, of at least one acid; and, if desired, further additives.

# INTERNATIONAL SEARCH REPORT

International application No <b>PCT/EP2008/064166</b>
--

**A. CLASSIFICATION OF SUBJECT MATTER**  
 INV. D21H21/10 B41M5/26

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)  
 B41M D21H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 894 896 A (MERCK PATENT GMBH [DE]) 3 February 1999 (1999-02-03) cited in the application column 1, paragraph 1 column 1, paragraph 4 - column 2, paragraph 12 column 3, paragraph 16 - column 5, paragraph 31 <div style="text-align: center; margin-top: 10px;">----- -/--</div>	1-5

Further documents are listed in the continuation of Box C.

See patent family annex.

\* Special categories of cited documents :

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*Z\* document member of the same patent family

Date of the actual completion of the international search

Date of mailing of the international search report

2 February 2009

12/02/2009

Name and mailing address of the ISA/  
 European Patent Office, P.B. 5818 Patentlaan 2  
 NL - 2280 HV Rijswijk  
 Tel. (+31-70) 340-2040,  
 Fax: (+31-70) 340-3016

Authorized officer  
  
 Beins, Ulrika

## INTERNATIONAL SEARCH REPORT

International application No  
PCT/EP2008/064166

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 2007/031454 A (CIBA SC HOLDING AG [CH]; O DONOGHUE KAREN [GB]; CAMPBELL JONATHAN [CH]) 22 March 2007 (2007-03-22) cited in the application page 1, line 2 - line 5 page 2, line 1 - line 33 page 5, line 18 - page 8, line 28 page 11, line 18 - line 28 page 12, line 25 - line 31 page 13, line 5 - line 12 page 13, line 30 - line 31 page 14, line 5 - line 17 -----	1-5
X	US 5 733 414 A (STOCKWELL JOHN OLIVER [GB]) 31 March 1998 (1998-03-31) column 1, line 19 - line 22 column 1, line 66 - column 2, line 10 -----	3-5
X	EP 0 372 715 A (HANDY CHEMICALS LTD [CA]) 13 June 1990 (1990-06-13) page 17, line 5 - line 46 -----	3-5
X	US 2 286 726 A (EMERSON GORDON WALLACE) 16 June 1942 (1942-06-16) page 1, line 37 - line 43 page 1, line 10 - page 2, line 15 page 2, line 65 - line 69 claim 2 -----	3-5
X	WO 2005/054576 A (CIBA SC PFERSEE GMBH [DE]; DERMEIK SALMAN [DE]; LEMMER KARL-HEINZ [DE]) 16 June 2005 (2005-06-16) cited in the application claim 1 -----	3
A	US 2005/186511 A1 (KHAN NAZIR [GB]) 25 August 2005 (2005-08-25) the whole document -----	1-5

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

Continuation of Box II.2

Claims Nos.: 6-19

Claims 6 to 19 claim "process, use of fiber product", however, it is not clear which claim category is meant, therefore leading to a lack of clarity according to Article 6 PCT.

The extent of the search was consequently limited to the clearly defined claims.

The applicant's attention is drawn to the fact that claims relating to inventions in respect of which no international search report has been established need not be the subject of an international preliminary examination (Rule 66.1(e) PCT). The applicant is advised that the EPO policy when acting as an International Preliminary Examining Authority is normally not to carry out a preliminary examination on matter which has not been searched. This is the case irrespective of whether or not the claims are amended following receipt of the search report or during any Chapter II procedure. If the application proceeds into the regional phase before the EPO, the applicant is reminded that a search may be carried out during examination before the EPO (see EPO Guideline C-VI, 8.2), should the problems which led to the Article 17(2)PCT declaration be overcome.

# INTERNATIONAL SEARCH REPORT

International application No.  
PCT/EP2008/064166

## Box No. II Observations where certain claims were found unsearchable (Continuation of item 2 of first sheet)

This international search report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1.  Claims Nos.:  
because they relate to subject matter not required to be searched by this Authority, namely:
  
2.  Claims Nos.: 6-19  
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:  
see FURTHER INFORMATION sheet PCT/ISA/210
  
3.  Claims Nos.:  
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

## Box No. III Observations where unity of invention is lacking (Continuation of item 3 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

1.  As all required additional search fees were timely paid by the applicant, this international search report covers allsearchable claims.
  
2.  As all searchable claims could be searched without effort justifying an additional fees, this Authority did not invite payment of additional fees.
  
3.  As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:
  
  
4.  No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

### Remark on Protest

- The additional search fees were accompanied by the applicant's protest and, where applicable, the payment of a protest fee.
- The additional search fees were accompanied by the applicant's protest but the applicable protest fee was not paid within the time limit specified in the invitation.
- No protest accompanied the payment of additional search fees.

## INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2008/064166

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0894896	A	03-02-1999	DE 19732860 A1 JP 11100796 A US 6306493 B1	04-02-1999 13-04-1999 23-10-2001
WO 2007031454	A	22-03-2007	AU 2006290828 A1 CA 2621341 A1 CN 101263010 A KR 20080046736 A	22-03-2007 22-03-2007 10-09-2008 27-05-2008
US 5733414	A	31-03-1998	AT 193915 T AU 701218 B2 AU 1583095 A BR 9505837 A CA 2159592 A1 DE 69517474 D1 DE 69517474 T2 DK 695385 T3 EP 0695385 A1 ES 2149346 T3 FI 954676 A WO 9521295 A1 JP 8508795 T NO 953935 A NZ 279257 A PH 31656 A PL 310978 A1 ZA 9500923 A	15-06-2000 21-01-1999 21-08-1995 27-02-1996 10-08-1995 20-07-2000 08-03-2001 30-10-2000 07-02-1996 01-11-2000 02-10-1995 10-08-1995 17-09-1996 03-10-1995 27-05-1998 12-01-1999 22-01-1996 06-02-1996
EP 0372715	A	13-06-1990	AU 618854 B2 AU 4396389 A BR 8905593 A CA 2001729 A1 CN 1042340 A DE 68914610 D1 DE 68914610 T2 DE 372715 T1 DK 548789 A FI 94046 B JP 2167814 A JP 6102534 B NO 894364 A NZ 231199 A US 4981675 A ZA 8908286 A	09-01-1992 10-05-1990 29-05-1990 03-05-1990 23-05-1990 19-05-1994 21-07-1994 17-01-1991 04-05-1990 31-03-1995 28-06-1990 14-12-1994 04-05-1990 27-11-1990 01-01-1991 25-07-1990
US 2286726	A	16-06-1942	NONE	
WO 2005054576	A	16-06-2005	AU 2004295417 A1 CA 2541504 A1 EP 1538261 A1 US 2007082139 A1	16-06-2005 16-06-2005 08-06-2005 12-04-2007
US 2005186511	A1	25-08-2005	NONE	