



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>7</sup> :</b>  <b>G03F 7/09</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 00/38016</b>  <b>(43) International Publication Date:</b> 29 June 2000 (29.06.00)
<b>(21) International Application Number:</b> PCT/US99/30296  <b>(22) International Filing Date:</b> 20 December 1999 (20.12.99)  <b>(30) Priority Data:</b> 09/205,006                      20 December 1998 (20.12.98)      US  <b>(71) Applicant:</b> ALLIEDSIGNAL INC. [US/US]; 101 Columbia Road, P.O. Box 2245, Morristown, NJ 07962-2245 (US).  <b>(72) Inventors:</b> SPEAR, Richard; 1437 Golden Meadow Square, San Jose, CA 95117 (US). KRAJEWSKI, Todd; Apartment 25, 465 Calderon Avenue, Mountain View, CA 94041 (US). HACKER, Nigel; 991 Lincoln Avenue, Palo Alto, CA 94201 (US).  <b>(74) Agents:</b> CRISS, Roger, H. et al.; AlliedSignal Inc. (Law Dept., Attn: A. Olinger), 101 Columbia Road, P.O. Box 2245, Morristown, NJ 07962-2245 (US).		<b>(81) Designated States:</b> AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
<b>(54) Title:</b> NOVOLAC POLYMER PLANARIZATION FILMS WITH HIGH TEMPERATURE STABILITY  <b>(57) Abstract</b>  <p>A process for forming a planarization film on a substrate that does not smoke or fume on heating includes applying a polymeric solution including a novolac resin having a weight average molecular weight between about 1000 and 3000 amu, which has been fractionated to remove molecules with molecular weight below about 350 amu, a surfactant selected from a group consisting of a non-fluorinated hydrocarbon, a fluorinated hydrocarbon and combinations thereof, and an optional organic solvent to a substrate, followed by heating the substrate.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

## NOVOLAC POLYMER PLANARIZATION FILMS WITH HIGH TEMPERATURE STABILITY

### BACKGROUND OF THE INVENTION

#### Field of the Invention

5           This invention relates generally to novolac polymer planarization films for microelectronic devices, such as integrated circuits, and more specifically to planarization films with high temperature stability.

#### Description of the Related Art

10           Novolac polymers have been used extensively in the manufacture of integrated circuits and other semiconductor and microelectronic devices. In particular, photoresists used for microlithographic patterning of semiconductor structures often contain a novolac component. See, for example, U. S. Patent No. 5,601,961 to Nakayama et al.

15           In addition, novolac polymers are also components of planarizing films used in the fabrication of microelectronic devices to provide a relatively flat surface. See, for example, U. S. Patent No. 5,276,126 and references therein. As the characteristic feature size on such devices becomes smaller, planarizing films are increasingly important in the device fabrication process. Low weight average molecular weight novolac polymers, i.e. those ranging between about 200 and about 2300 atomic mass units (amu) have been found to be useful in forming planarizing films because they tend to flow more readily  
20           than polymers having higher molecular weights.

25           In a typical process of forming a planarization film, a solution containing a novolac polymer is formulated with a surfactant. The surfactant-containing polymer solution is applied to a substrate by conventional spinning techniques. The polymer solution-coated substrate is heated to evaporate any residual solvent present in the film material and to reduce the viscosity of the film. The reduced viscosity causes the material to flow and enhances leveling of the film on the substrate. One difficulty in

using these novolac polymer formulations to form planarizing films is that fuming may be observed on heating. Thermally volatilized material is detrimental in that it may form particles that can lead to defects in the manufactured devices and may clog vacuum lines.

It would be desirable to provide a process of forming a planarizing film from a novolac polymer material that retains the excellent planarization of previous materials but does not fume or smoke on heating.

### **SUMMARY OF THE INVENTION**

In accordance with this invention, a process of forming a planarizing film on a substrate is provided, the process including first applying to the surface of the substrate a solution including a novolac resin having a weight average molecular weight between about 1000 and 3000 amu and wherein the novolac resin is fractionated to remove the molecules with molecular weight below about 350 amu and a surfactant selected from a group consisting of a non-fluorinated hydrocarbon, a fluorinated hydrocarbon and combinations thereof. The process additionally includes heating the solution-covered substrate to form a planarized film.

According to another aspect of the present invention, a substrate having a planarized film applied thereon is provided, the film comprising a novolac resin having a molecular weight between about 1000 and 3000 amu and wherein the novolac resin is fractionated to remove the molecules with molecular weight below about 350 amu and a surfactant selected from the group consisting of a non-fluorinated hydrocarbon, a fluorinated hydrocarbon and combinations thereof.

In yet another embodiment of the invention, there is provided a composition for use in the formation of planarizing films on substrates, the composition comprising the fractionated novolac resin as described above, a surfactant selected from the group consisting of a non-fluorinated hydrocarbon, a fluorinated hydrocarbon and combinations thereof, and an optional organic solvent. The novolac resins used in the composition according to the present invention are fractionated by extraction techniques such as

column extraction, liquid-liquid extraction, or supercritical fluid extraction to remove the fraction with molecular weight below about 350 amu.

Using the composition according to the present invention in forming planarizing films, no fuming or smoking is observed during the process of heating a coated substrate.

## 5 **DESCRIPTION OF THE PREFERRED EMBODIMENTS**

The process of forming a planarizing film according to this invention uses a composition including a novolac resin that has been fractionated to remove low molecular weight components and a surfactant. Novolac polymers and surfactants that can be used in this invention are described in detail in U. S. Application No. 08/271,291,  
10 entitled "Novolac Polymer Planarization Films for Microelectronic Structures", (denoted the '291 application), which is commonly assigned with the present application and is incorporated herein by reference.

As described above, novolac polymers with low molecular weights are especially useful in forming planarizing films because they tend to flow more readily than polymers  
15 having higher molecular weights. Polymer molecular weight, as used here, refers to weight average molecular weight, as determined, for example, by gel permeation chromatography, calibrated against polystyrene. According to the present invention, it has been determined that the lowest molecular weight fraction, that is those novolac molecules with molecular weight less than about 350 amu are thermally volatilized when  
20 the formulation containing novolac polymers is heated in forming planarizing films. Thus removal of the lowest molecular weight fraction overcomes the problem of fuming or smoking on heating a coated substrate.

Novolac polymers are commercially available or may be derived from reacting phenols or derivatives therefrom, such as ortho-, meta- and para cresol, with  
25 formaldehyde or with other aldehyde compounds. The lowest molecular weight fraction can be substantially removed by extraction techniques such as toluene extraction, column extraction, liquid-liquid extraction, and supercritical fluid extraction.

In the toluene extraction process, solid novolac resin is combined with toluene and heated to between approximately 75 and 80°C. The toluene is decanted and a second lot of toluene is added; the mixture is heated; and the toluene is decanted. The remaining solid is a novolac polymer with the lowest molecular weight fraction reduced. An  
5 alternative extraction process, column extraction, is performed on a mixture of polymer resin ground to a fine powder and dry silica gel, installed in a glass column. The mixture in the column is eluted with a first solvent mixture, for example, an ethyl acetate and hexane mixture, until a large volume of elution solvent is obtained, capturing the low molecular weight components. The column is then eluted with a second solvent, for  
10 example, methanol, from which the novolac polymer with the lowest molecular weight fraction removed is recovered.

In the liquid-liquid extraction process, the novolac polymer is combined with two solvents with different polarity, for example, ethyl acetate and hexane, and mixed with a sonicator. The contents separate into two phases; the polymer with the lowest molecular  
15 weight fraction removed is recovered from the bottom layer. A supercritical fluid extraction technique can also be used. In this process, flows of a polar solvent, such as ethyl acetate, ethanol, or methanol, and CO<sub>2</sub> are passed over a novolac polymer sample in an extractor vessel, heated to temperatures in the range between about 60 and 65°C and pressurized to about 200 to 300 bar. The remaining novolac polymer in the vessel is  
20 depleted of the low molecular weight component.

As reported in detail in the appended examples, extraction using the above techniques results in a novolac polymer with increased molecular weight and narrowed polydispersity. Polydispersity is defined as the ratio of the weight average molecular weight to the number average molecular weight. For example, extraction of the phenolic  
25 novolac denoted SD-333A, provided by Borden Chemical, Inc. increases the molecular weight from about 900 to between about 1300 and 1800, and decreases polydispersity from over 1.5 to less than 1.4, depending on the extraction method. The molecular weight distribution of molecules that make up the novolac resin may be determined using gel permeation chromatography (GPC). High performance liquid chromatography  
30 (HPLC) is used to determine the removal efficiency of the low molecular weight material

that causes fuming. Fractionation reduces the contribution in HPLC area per cent of molecules with molecular weight less than about 200 from over 20 % to less than about 4 % of the total molecular weight distribution and reduces the contribution of molecules with molecular weight less than about 350 from over 30% to less than about 10 %.

- 5 Furthermore, fractionation improves thermal stability of the novolac polymers as evidenced by increase in the glass transition temperature and decrease in the weight loss on heating.

Thus, the novolac polymers used in this invention are specified by their weight average molecular weight and by the fraction of molecules with molecular weight less  
10 than about 350, i.e. the lowest molecular weight fraction, remaining after fractionation. Novolac polymers with molecular weight between about 900 and about 2500, and preferably between about 1200 and 2300, and with the lowest fraction less than about 22%, and, preferably, less than about 15% are advantageously used.

The fractionated novolac polymer can be combined with a surfactant in  
15 formulating a coating solution for forming planarizing films. As described in the '291 application, surfactants suitable for this invention include non-fluorinated and fluorinated hydrocarbons and mixtures thereof. Suitable non-fluorinated hydrocarbon surfactants may be comprised of alkylated derivatives of organic acids and esters thereof having from about 5 to about 50 carbons, preferably from about 10 to about 30 carbons and  
20 combinations thereof. Suitable fluorinated hydrocarbon surfactants may be comprised of alkylated derivatives of organic acids and esters thereof having from about 5 to about 50 carbons, preferably from about 10 to about 30 carbons, and at least one carbon-fluorine bond, and combinations thereof. More specifically, particular fluorinated hydrocarbon surfactants include fluoroaliphatic oxyethylene adducts, fluorinated alkyl alkoxylates and  
25 sulfonamides containing from about 50 to about 20 carbon atoms, fluoroaliphatic polymeric esters derived from monomers comprised of partially fluorinated hydrocarbon chains containing from about 50 to about 20 carbon atoms with terminal ester groups attached thereto, fluoroaliphatic copolymers derived from monomers comprised of partially fluorinated hydrocarbon chains containing from about 5 to about 20 carbon  
30 atoms with terminal functional groups selected from esters and acids attached thereto,

and combinations thereof. These fluorinated surfactants are commercially available from 3M.

An organic solvent may optionally be included as a third component of the coating solution. Solvents suitable for this invention include aliphatic and aromatic hydrocarbons, alcohols, ketones, ester, ethers, ether alcohols, ether esters, alcohol esters, ketone esters, ketone ethers, ketone alcohols, amides, nitriles, and combinations thereof. More specifically, particular solvents include ethyl lactate, ethyl acetate, propyl acetate, butyl acetate, and combinations thereof.

The polymeric solution preferably contains from about 1 to about 90 percent, more preferably between from about 10 to about 50 percent, and most preferably from about 20 to about 40 percent, based upon the total weight of the solution, of the novolac polymer, and preferably from about 0.01 to about 5 percent, more preferably from about 0.1 to about 1 percent, and most preferably from about 0.3 to about 0.7 percent of surfactant. The optional solvent may be present in an amount ranging between about 10 to about 90 percent, preferably between about 50 to about 90 percent, and most preferably between about 60 to about 85 percent.

The polymeric solution may be applied to the substrate by any conventional means, such as spin-coating. Preferably, the solution is centrally applied to the substrate, which is then spun at speeds ranging between about 500 and about 6000 rpm, preferably between about 1500 and about 4000 rpm, for about 5 to about 60 seconds, preferably about 10 to about 30 seconds. Optionally, an additional, short, lower speed spin, between about 400 and 600 rpm for about 1 to about 5 seconds is used to spread the solution immediately after application.

Typically, the compositions of this invention are applied onto wafer substrates, such as silicon wafers which have a circuit pattern on their surface, to be processed into integrated circuits or other microelectronic devices.

The coated substrate is then heated by any conventional means. Preferably, the substrate is heated by placing it on a hot plate to heat the wafer from below. Typically,



this is done commercially via a conventional integrated spin-coater/hot plate system. The coated substrate is typically heated for about 0.5 minutes to about 5 minutes at temperatures ranging between about 50°C and about 300°C, preferably between about 100°C and 200°C. Alternatively, multiple hot plates, i.e. between about 2 and about 5 hot plates, may be used, with the same time and temperature ranges applying, and where the temperature of each subsequent hot plate is higher than the temperature of the previous one.

As illustrated in the following examples, no fumes are observed when formulations containing fractionated novolac polymers, according to the present invention, are coated on substrates and heated as described above to form a planarized film.

### EXAMPLES

Preparation of fractionated novolac polymers by toluene extraction, liquid-liquid extraction, column extraction, and supercritical fluid extraction is given in Examples 1-4, respectively. The phenolic novolac polymer, SD-333A, provided by Borden Chemical, Inc. was used in these examples. Characterization methods and properties of the fractionated polymers obtained in Examples 1-4 are given in Examples 5 and 6. The original phenolic novolac polymer and the fractionated polymers are formulated with a surfactant and solvent to form coating solutions. Formulation and performance of the coating solutions are reported in Example 7.

#### Example 1

Solid chunks of novolac polymer (206.5 g) were combined with 8 liters of toluene in a 12 liter round bottomed flask and heated to 75-80°C with stirring for 75 minutes. The solid melted above 55°C. The toluene was decanted and a second lot of 8 liters of toluene added, heated with stirring for 75 minutes, and decanted. The solid remaining in the flask was dissolved in methanol, roto-evaporated until a fluffy pink solid was obtained and dried overnight in a vacuum oven at 45°C (88.5g).

**Example 2**

Novolac polymer (182.34 g) was placed in a 12 liter round bottom flask. The solvent mixture 30% ethyl acetate/70% hexane, by volume, B & J brand ethyl acetate, Fisher Optima grade hexane, (10 liters) was added to the flask and the contents mixed with stirring for 4 hours. After thorough mixing, the contents separated into two phases, a dark viscous bottom layer and a cloudy white top layer. The bottom layer, containing the fractionated novolac polymer, was separated and the solvent removed by roto-evaporation. The yield was 49.6 g (27.2%).

10

**Example 3**

Solid novolac polymer ground to a fine powder (300g) was mixed with 1200 g of dry silica gel. A 2 inch layer of clean silica gel, slurried with 30% ethyl acetate/70% hexane, was installed in a large glass column (3 7/8 inch x 48 inches). The polymer/silica gel mix slurried with the same solvent was installed over the silica gel. The column was eluted with 30% ethyl acetate/70% hexane until 15 liters of elution solvent was collected. The column was next eluted with methanol and three 4 liter fractions were collected. The first two fractions were roto-evaporated until a solid was obtained: first fraction (153.4 g), second fraction (7.1 g) for a total yield of 160.5 g.

20

**Example 4**

Novolac polymer (19.3 g) was placed in a 50 cc sample cartridge and inserted in a 30 cc extractor vessel of a Marc Sims Dense Gas Management System, "supercritical fluid extraction apparatus", fitted with an Alltech model 426 standard HPLC pump for solvent addition. The extractor vessel was purged with CO<sub>2</sub> (Air Products, SFC grade) for 10 minutes at a flow rate of about 2g/min and heating started. The flow was then stopped and heating continued until the operating temperature of 60-61°C was obtained.

25

During heating the HPLC pump was primed with ethyl acetate (B&J brand). Pressure in the extractor vessel was 50-250 bar.

Extraction was performed in two stages. The first stage was started with CO<sub>2</sub> and ethyl acetate flows of 9.2-9.4 g/min and 1.0 ml/min, respectively at a pressure of 250 bar.

- 5 After 3597 g of CO<sub>2</sub> passed through the extractor, the temperature was increased to 62°C. After an additional 4023g of CO<sub>2</sub> passed through the extractor, the temperature was increased to 64-65°C, at which temperature, 4500 g of CO<sub>2</sub> were passed through the reactor. For the second stage, flows of 9.6-9.8 g/min and 3.0 ml/min of CO<sub>2</sub> and ethyl acetate, respectively, were maintained until 2057 g of CO<sub>2</sub> had passed through the
- 10 extractor. The vessel temperature was maintained at 62-63°C throughout the second stage. The yield of fractionated novolac polymer was 11.29 g.

### **Example 5**

- Weight average molecular weight ( $M_w$ ) and number average molecular weight
- 15 ( $M_n$ ) were determined by gel permeation chromatography (GPC) with respect to polystyrene. Glass transition temperature was determined by differential scanning calorimetry (DSC). The DSC measurement procedure included a 1 minute preheat at 250°C to remove any residual solvent, followed by a temperature scan from 25°C to 200°C at a rate of 10°C/minute. Thermal weight loss was determined by thermal
- 20 gravimetric analysis (TGA), in which sample weight was recorded as the temperature was raised from 30°C to 300°C at a rate of 10°C/minute. Final weight differential is recorded below in Table 1.

**Table 1. Characterization of Resin Material**

Material	$M_w$	$M_n$	Polydispersity	$T_g(^{\circ}\text{C})$	% Wt Loss
----------	-------	-------	----------------	-------------------------	-----------

Unfractionated	936	606	1.544	36.6	27.2
Example 1	1436	1055	1.361	72.4	15.2
Example 2	1730	1246	1.388	76.4	13.9
Example 3	1364	1072	1.273	73.8	13.4
Example 4	1301	916	1.419	64.9	13.0

### Example 6

Results of High Performance Liquid Chromatography (HPLC) analysis, obtained with a Hewlett-Packard HPLC Model 1100 are reported below in Table 2. Area percent  
 5 for peaks corresponding to specific molecular weights are given. Equal detector response for all molecular weights is assumed.

**Table 2. Characterization of Resin Material - HPLC Data**

<b>Material</b>	<b><math>M_w \approx 200</math> (area %)</b>	<b><math>M_w \approx 306</math> ( area %)</b>
Unfractionated	22.47	9.11
Example 1	3.05	4.67
Example 2	3.94	3.22
Example 3	0.08	4.13
Example 4	1.32	6.50

**Example 7**

Unfractionated novolac polymer resin and the fractionated polymers from Examples 1-4b were combined with the surfactant, the fluorinated ester derivative denoted FC-430, provided by 3M, and the solvent, ethyl lactate, to form coating solutions with the listed % solids and % solvent. 2-4 ml of the solution were dispensed at the center of 4 inch bare silicon wafers. The wafers were spun at 500 rpm for 2 seconds followed by a 20 second spin at 4000 rpm. The wafers were baked on a hot plate at 200°C for 120 seconds. Observations are given below in Table 3.

10

**Table 3. Performance of Coating Composition**

<b>Material</b>	<b>% Solid</b>	<b>% Solvent</b>	<b>Thickness (Å)</b>	<b>Smoke Observation</b>
Unfractionated	20.35	79.45	4253	Heavy for first 20 seconds
Unfractionated	36.82	62.98	14802	Heavy for first 60 seconds
Example 1	17.8	81.75	4323	None
Example 1	31.8	67.75	14523	None
Example 2	17.8	81.75	4261	None
Example 2	31.8	67.75	13977	None
Example 3	15.8	83.75	3875	None
Example 3	29.8	69.75	14785	None
Example 4	17.8	81.75	4136	None
Example 4	31.8	67.75	13550	None

As evidenced by the increase in glass transition temperature and decrease in thermal weight loss reported in Table 1, fractionation results in a novolac polymer resin with increased thermal stability. The results in Table 3 clearly demonstrate that using the coating composition with fractionated novolac polymer resin, according to the present  
5 invention, no smoking or fuming is observed during the process of heating a coated substrate.

**WHAT IS CLAIMED IS:**

1. A process of forming a planarized film on a substrate comprising:  
applying to a surface of said substrate a polymeric solution comprising a novolac resin having a weight average molecular weight between about 1000 and 3000 amu and wherein the novolac resin is fractionated to remove the molecules  
5 with molecular weight below about 350 amu and a surfactant selected from the group consisting of a non-fluorinated hydrocarbon, a fluorinated hydrocarbon and combinations thereof to form a coated substrate; and  
heating said coated substrate to form a planarized film on said surface.
2. The process of Claim 1 wherein said solution further comprises an  
10 organic solvent.
3. The process of Claim 2 wherein said novolac resin has a fraction with molecular weight below about 350 amu that is smaller than about 22% of the total.
4. The process of Claim 3 wherein said novolac resin has a fraction with molecular weight below about 350 amu that is smaller than about 15% of the total.
- 15 5. The process of Claim 2 wherein said novolac resin is a phenolic resin.
6. The process of Claim 2 wherein said novolac resin has a polydispersity of less than about 1.4.
7. The process of Claim 2 wherein said surfactant is a fluorinated ester derivative.
- 20 8. A substrate having a planarized film applied thereon, said film comprising a novolac resin having a weight average molecular weight between about 1000 and 3000 amu and wherein the novolac resin is fractionated to remove the molecules with molecular weight below about 350 amu and a surfactant selected from the group

consisting of a non-fluorinated hydrocarbon, a fluorinated hydrocarbon and combinations thereof.

9. The substrate of Claim 8 wherein said planarized film does not produce observable fumes or smoke when heated to a temperature of about 200°C for about 2  
5 minutes.

10. The substrate of Claim 8 wherein said novolac resin has a fraction with molecular weight below about 350 amu that is smaller than about 22% of the total.

11. The substrate of Claim 10 wherein said novolac resin has a fraction with molecular weight below about 350 amu that is smaller than about 15% of the total.

10 12. The substrate of Claim 8 wherein said novolac resin has a polydispersity of less than about 1.4.

13. The substrate of Claim 8 wherein said novolac resin is a phenolic resin.

14. A composition comprising  
from about 1 to about 90 weight percent of a novolac resin having a  
15 weight average molecular weight between about 1000 and 3000 amu and wherein the novolac resin is fractionated to remove the molecules with molecular weight below about 350 amu;

from about 0.01 to about 5 weight percent of a surfactant selected from the group consisting of a non-fluorinated hydrocarbon, a fluorinated hydrocarbon  
20 and combinations thereof; and

from about 0 to about 90 percent of an organic solvent.

15. The composition of Claim 14 wherein said novolac resin has a fraction with molecular weight below about 350 amu that is smaller than about 22% of the total.



16. The composition of Claim 15 wherein said novolac resin has a fraction with molecular weight below about 350 amu that is smaller than about 15% of the total.

17. The composition of Claim 15 wherein said novolac resin is fractionated by supercritical fluid extraction using a polar solvent.

5           18. The composition of Claim 14 wherein said novolac resin has a polydispersity of less than about 1.4.

19. The composition of Claim 14 wherein said novolac resin is a phenolic resin.

# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/US 99/30296

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 G03F7/09

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 G03F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	WO 96 02066 A (ALLIED SIGNAL INC) 25 January 1996 (1996-01-25) the whole document	1-19
Y	WO 98 27129 A (CLARIANT INT LTD) 25 June 1998 (1998-06-25)	1-19
X	the whole document	14-19
A	EP 0 727 711 A (OCG MICROELECTRONIC MATERIALS) 21 August 1996 (1996-08-21)	17
A	US 5 276 126 A (ROGLER ROBERT F) 4 January 1994 (1994-01-04) cited in the application	
A	EP 0 144 880 A (MERCK PATENT GMBH) 19 June 1985 (1985-06-19)	

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

6 April 2000

Date of mailing of the international search report

26/04/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Haenisch, U

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/30296

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9602066 A	25-01-1996	US 5858547 A AU 3093495 A EP 0769204 A JP 9507966 T	12-01-1999 09-02-1996 23-04-1997 12-08-1997
WO 9827129 A	25-06-1998	US 5910559 A EP 0948553 A	08-06-1999 13-10-1999
EP 0727711 A	21-08-1996	JP 8248633 A	27-09-1996
US 5276126 A	04-01-1994	NONE	
EP 0144880 A	19-06-1985	DE 3344202 A JP 6054383 B JP 60140235 A	20-06-1985 20-07-1994 25-07-1985