

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
5 October 2006 (05.10.2006)

PCT

(10) International Publication Number
WO 2006/103172 A1

(51) International Patent Classification:
C08F 10/02 (2006.01) **C08F 4/654** (2006.01)

(74) Agents: **GIBERTI, Stefano** et al.; Basell Poliolefine Italia s.r.l., Intellectual property, P.le Donegani 12, I-44100 Ferrara (IT).

(21) International Application Number:
PCT/EP2006/060740

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(22) International Filing Date: 15 March 2006 (15.03.2006)

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
05102480.0 30 March 2005 (30.03.2005) EP
60/667,269 1 April 2005 (01.04.2005) US

(71) Applicant (for all designated States except US): **BASELL POLIOLEFINE ITALIA S.R.L.** [IT/IT]; Basell Poliolefine Italia s.r.l, Intellectual Property, Via Pergolesi 25, I-20124 Milano (IT).

Declarations under Rule 4.17:

- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii))
- of inventorship (Rule 4.17(iv))

Published:

- with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: PROCESS FOR PREPARING CRYSTALLINE ETHYLENE (CO)POLYMERS

(57) Abstract: A process for preparing crystalline ethylene (co)polymers comprising (co)polymerizing ethylene in the presence of carried out in the presence catalyst system comprising (a) a solid catalyst component comprising Ti, Mg, halogen, ORI groups, where RI is a C1-C12 hydrocarbon group optionally containing heteroatoms, having ORI/Ti molar ratio of at least 0.5, an amount of titanium, with respect to the total weight of said solid catalyst component, higher than 4% by weight, and showing a specific pattern of the SS-NMR; and (b) an aluminum alkyl compound as a cocatalyst. The process allows to obtain in good yields ethylene polymers with narrow MWD.

WO 2006/103172 A1

TITLE

PROCESS FOR PREPARING CRYSTALLINE ETHYLENE (CO)POLYMERS

The present invention relates to process for preparing crystalline ethylene (co)polymers comprising polymerizing ethylene, optionally in mixture with olefins $\text{CH}_2=\text{CHR}$, wherein R is an alkyl, cycloalkyl or aryl radical having 2-12 carbon atoms, in the presence of a catalyst comprising Ti, Mg, halogen, OR^1 groups in a specific ratio. The process of the invention is suitable to prepare, in high yields, ethylene (co)polymers having narrow Molecular Weight Distribution (MWD) and showing a good comonomer distribution in and among the polymer chains. The MWD is an important characteristic of ethylene polymers in that it affects both the rheological behaviour, and therefore the processability, and the final mechanical properties. In particular, in the case of LLDPE, polymers with narrow MWD are suitable for films and injection molding in that deformation and shrinkage problems in the manufactured article are minimized. The width of the molecular weight distribution for the ethylene polymers is generally expressed as melt flow ratio F/E, which is the ratio between the melt index measured by a load of 21.6 Kg (melt index F) and that measured with a load of 2.16 Kg (melt index E). The measurements of melt index are carried out according to ASTM D-1238 and at 190°C. A catalyst component for preparing ethylene (co)polymers having narrow MWD is described in the European patent application EP-A-553805. The catalyst, comprising Ti, Mg, halogen, OR^1 groups is characterized by a ratio OR/Ti of at least 0.5, by a porosity (determined with mercury porosimeter) of from 0.35 to 0.7 which furthermore has a specific pore distribution. Said catalyst is obtained by a rather long process which comprises the preparation of a MgCl_2 -alcohol adduct having about 3 moles of alcohol which is first thermally dealcoholated up to an intermediate alcohol content and then chemically dealcoholated up to an almost complete extent. The so created porous precursor is then reacted with a titanium alkoxy compound in the presence of a halogenating agent and, optionally, of a reducing agent. The catalyst so obtained is able to produce ethylene (co)polymers with a narrow MWD but the polymerization activities are low. A polymerization process for the preparation of ethylene homopolymer is also described in USP 4,220,554. The catalysts used are obtained by reacting a large excess of TiCl_4 with catalyst precursors of general formula $\text{MgCl}_n(\text{OR})_{2-n}$ in the presence of an internal electron donor compound at high temperatures (120°C). The hydrogen response of the final

catalyst component however, is not satisfactory and therefore with the disclosed process a too high amount of molecular weight regulator would be needed to produce, in satisfactory yields, ethylene polymers with relatively low molecular weight. This would be a disadvantage when multimodal ethylene polymers should be produced.

In EP 301 894 a catalyst comprising Ti, Mg, halogen, OR groups (R is an aliphatic, aromatic or cycloaliphatic hydrocarbon radical) in which the Mg/Ti molar ratio is from 0.5 to 50 and the OR/Ti is from 1.5 to 5, is used for the preparation of amorphous ethylene copolymers. All the examples are directed to the production of amorphous copolymers and terpolymers with no indication about the suitability for the production of crystalline ethylene polymers with narrow molecular weight distribution.

It is therefore still felt the need of a catalyst component suited to form a catalyst system showing a good balance of polymerization activity, ability to form ethylene polymers with narrow MWD, good hydrogen response and high activity.

The applicant has surprisingly found a process satisfying the above-mentioned needs comprising the use of certain catalyst components characterized by a specific pattern when analyzed through the solid state NMR (SS-NMR). In particular, said process for the preparation of crystalline ethylene (co)polymers comprises polymerizing ethylene alone or in mixture with of olefins $\text{CH}_2=\text{CHR}$, in which R is hydrogen or a hydrocarbyl radical with 1-12 carbon atoms, in the presence of a catalyst system comprising (a) a solid catalyst component comprising Ti, Mg, halogen, OR^1 groups, where R^1 is a C1-C12 hydrocarbon group optionally containing heteroatoms, having OR^1/Ti molar ratio of at least 0.5, an amount of titanium, with respect to the total weight of said solid catalyst component, higher than 4% by weight, and showing in the pattern of the SS-NMR recorded under the conditions set forth below one or more signals (A) having a maximum in the region 60-75 (ppm) and one or more signals (B) having a maximum in the region 78-108 such that the ratio I^A/I^B , in which I^A is the integral of signals having the maximum in the region between 60 and 75 ppm and I^B is the integral of signals having the maximum of the region between 78 and 108 ppm, is higher than 0.8; and (b) an aluminum alkyl compound as a cocatalyst.

Preferably, the ratio I^A/I^B is higher than 1 and more preferably in the range 1-5. Generally, in correspondence with OR/Ti molar ratios in the range 0.5-2 the activity of the catalyst

component is higher particularly when the ratio I^A/I^B is higher than 1.2. Generally, for values of OR/Ti molar ratios higher than 2 the hydrogen response is improved particularly when the ratio I^A/I^B is from 1 to 2.

In a preferred aspect the amount of titanium, with respect to the total weight of said solid catalyst component, is higher than 5% and preferably higher than 6% by wt.

The applicant has also found that the catalyst components (a) to be used in the process of the invention, comprising Ti, Mg, halogen, OR^I groups, where R^I is a C1-C12 hydrocarbon group optionally containing heteroatoms, and at least 4% wt of Ti atoms, can also be characterized by the fact that are obtainable by reacting a titanium compound having at least a Ti-Cl bond with a catalyst precursors of formula MgCl_n(OR^I)_{2-n}, where n is from 0.5 to 1.5 and R^I has the meaning given above, under conditions such that the said product has a OR^I/Ti molar ratio of at least 0.5.

In a preferred embodiment of the invention R^I is a C1-C8 hydrocarbon group selected from alkyl groups. Among them particularly preferred are methyl, ethyl, n-propyl, n-butyl, i-butyl, and tert-butyl.

Moreover, said OR^I/Ti molar ratio is preferably higher than 1, very preferably higher than 1.5 and, especially higher than 2.

Among the titanium compounds containing at least one Ti-halogen bond, those having the formula Ti(OR^I)_{p-y}Cl_y, wherein R^I has the meaning given above, p is the titanium valence and y is a number comprised between 1 and p, are preferred. Particularly preferred are the titanium compounds in which y ranges from 2 to 4.

Among the catalyst precursors particularly preferred are those in which R^I is selected among a C1-C8 hydrocarbon group, preferably ethyl, and n ranges from 0.6 to 1.4, in particular from 0.7 to 1.3 and especially from 0.8 to 1.2. The said catalyst precursors can be generated by exchange reaction between organometallic compounds of formula Cl_mMgR_{2-m}, where m is from 0.5 to 1.5, and R is a hydrocarbon group, with an appropriate OR^I group source. The OR^I sources are for example R^IOH alcohols or, preferably, a silicon compound of formula (R^IO)_rSiR_{4-r} where r is from 1 to 4 and R^I has the meaning given above. In turn, as generally

known in the art, organometallic compounds of formula $\text{Cl}_m\text{MgR}_{2-m}$ can be obtained by the reaction between Mg metal and an organic chloride RCl, in which R is as defined above, optionally in the presence of suitable promoters. Preferably, the formation of $\text{Cl}_m\text{MgR}_{2-m}$ and the further exchange with the OR^I source takes place in one single step. The reaction can be carried out in a liquid inert medium such as hydrocarbon that is liquid at room temperature. Usually, upon a substantial amount of exchange with the OR source occurred, the catalyst precursors precipitate and can be easily isolated.

As mentioned above the reaction between titanium compound having at least a Ti-Cl bond and the catalyst precursor should be carried out under conditions such that the reaction product has a final OR^I/Ti molar ratio of at least 0.5 and preferably higher than 1. It is within the ordinary knowledge of the skilled in the art that there are several ways of obtaining the same results. Given that the titanium compound acts as a halogenating agent with respect to the precursor, it is in principle possible to obtain the desired final ratio either by using a limited molar amount of titanium compound or by keeping conditions such that the halogenation activity is depressed.

According to one preferred embodiment, the catalyst component is obtained by reacting the catalyst precursor with a titanium compound, preferably TiCl_4 , used in an amount such that the molar ratio between the titanium compound and the OR^I groups of the catalyst precursor is 4 or less. Preferably said ratio is lower than 3, and more preferably it ranges from 0.1 to 2.5. In this embodiment the reaction temperature is not particularly critical and can range from room temperature up to 150°C preferably in the range 40-120°C. In view of the limited amount of titanium compound, preferably TiCl_4 , it is preferred carrying out the reaction in an inert medium, that is liquid at least at the reaction temperature. Preferred inert medium are liquid aliphatic or aromatic hydrocarbons, optionally chlorinated, and among them those having from 3 to 20 carbon atoms. Especially preferred are propane, n-butane, n-pentane, n-hexane, n-heptane, benzene, toluene and isomers thereof. Mixture of two or more of said hydrocarbons can be used. Provided that the final OR^I/Ti molar ratio of at least 0.5 is maintained, the reaction medium can also comprise chlorinated compounds having a chlorinating ability inferior to that of TiCl_4 such as SiCl_4 , SnCl_4 and the like.

According to one preferred embodiment the catalyst component is obtained by reacting the catalyst precursor with a titanium compound, preferably TiCl_4 , used in amounts such the

molar ratio between the titanium compound and the OR^I groups of the catalyst precursor is higher than 4. The ratio can be higher than 6 and even higher than 10. In this embodiment the reaction temperature is kept at values lower than 100°C and preferably in the range 20-80°C. When using sufficient excess of liquid titanium compound, preferably TiCl₄, a liquid inert medium can be omitted as the titanium compound acts simultaneously as halogenating agent and reaction medium. However, if desired, a liquid inert medium as those disclosed above can be used also in this embodiment.

The solid catalyst components according to the present invention are converted into catalysts for the polymerization of olefins by reacting them with organoaluminum compounds according to known methods.

In particular, it is an object of the present invention a catalyst for the polymerization of olefins CH₂=CHR, in which R is hydrogen or a hydrocarbyl radical with 1-12 carbon atoms, comprising the product of the reaction between:

- (a) a solid catalyst component as described above,
- (b) an alkylaluminum compound and, optionally,
- (c) an external electron donor compound.

The alkyl-Al compound can be preferably selected from the trialkyl aluminum compounds such as for example trimethylaluminum (TMA), triethylaluminum (TEA), triisobutylaluminum (TIBA)), tri-n-butylaluminum, tri-n-hexylaluminum, tri-n-octylaluminum. Also alkylaluminum halides and in particular alkylaluminum chlorides such as diethylaluminum chloride (DEAC), diisobutylalumunum chloride, Al-sesquichloride and dimethylaluminum chloride (DMAC) can be used. It is also possible to use, and in certain cases preferred, mixtures of trialkylaluminum's with alkylaluminum halides. Among them mixtures between TEA and DEAC are particularly preferred.

The external electron donor compound can be equal to or different from the ED used in the solid catalyst component.

The above mentioned components (a)-(c) can be fed separately into the reactor where, under the polymerization conditions can exploit their activity.

The so formed catalyst system can be used directly in the main polymerization process or alternatively, it can be pre-polymerized beforehand. A pre-polymerization step is usually preferred when the main polymerization process is carried out in the gas phase. The prepolymerization can be carried out with any of the olefins $\text{CH}_2=\text{CHR}$, where R is H or a C1-C10 hydrocarbon group. In particular, it is especially preferred to pre-polymerize ethylene or mixtures thereof with one or more α -olefins, said mixtures containing up to 20% in moles of α -olefin, forming amounts of polymer from about 0.1 g per gram of solid component up to about 1000 g per gram of solid catalyst component. The pre-polymerization step can be carried out at temperatures from 0 to 80°C, preferably from 5 to 70°C, in the liquid or gas phase. The pre-polymerization step can be performed in-line as a part of a continuous polymerization process or separately in a batch process. The batch pre-polymerization of the catalyst of the invention with ethylene in order to produce an amount of polymer ranging from 0.5 to 20 g per gram of catalyst component is particularly preferred. Examples of gas-phase processes wherein it is possible to use the catalysts of the invention are described in WO 92/21706, USP 5,733,987 and WO 93/03078. These processes comprise a pre-contact step of the catalyst components, a pre-polymerization step and a gas phase polymerization step in one or more reactors in a series of fluidized or mechanically stirred bed. In a particular embodiment, the gas-phase process can be suitably carried out according to the following steps:

- (i) pre-polymerizing with one or more olefins of formula $\text{CH}_2=\text{CHR}$, where R is H or a C1-C10 hydrocarbon group, up to forming amounts of polymer from about 0.1 up to about 1000 g per gram of solid catalyst component (a); and
- (ii) polymerizing in the gas-phase ethylene, or mixtures thereof with α -olefins $\text{CH}_2=\text{CHR}$ in which R is a hydrocarbon radical having 1-10 carbon atoms, in one or more fluidized or mechanically stirred bed reactors, in the presence of the product coming from (i).

However, the catalysts of the invention are particularly suited for slurry polymerization in an inert medium such as propane, butane, pentane, hexane, heptane and mixtures thereof.

As already mentioned, the catalysts of the present invention are suitable for preparing crystalline ethylene polymers having the desired balance of catalyst activity, hydrogen response and suitable MWD. In particular it is possible to obtain a very narrow molecular weight distribution which is characterized by a F/E ratio of lower than 35 and in some cases

lower than 30. When the ethylene is polymerized together with a minor amount of an alpha olefin as comonomer, selected from propylene, butene-1, hexene-1 and octene-1, a linear low density polyethylene having a density lower than 0.940 g/cm³ with a very good quality is obtained which is indicated by the low ratio among weight of xylene soluble fraction and weight of comonomer in the chain. In addition, the catalyst of the invention also show a very good hydrogen response, i.e., the capability of producing low molecular weight polymers in dependence of a given content of molecular weight regulator (usually hydrogen) in the polymerization system. This feature is particularly useful when polymers with a bimodal molecular weight distribution are to be prepared in sequential polymerization steps. In this case, it is suitable to have a catalyst with a good hydrogen response because low molecular weight polymers are produced with a minor amount of Mw regulator and, as a consequence, with a higher activity.

Non limitative examples of other polymers that can be prepared with the catalyst of the invention are very-low-density and ultra-low-density polyethylenes (VLDPE and ULDPE, having a density lower than 0.920 g/cm³, to 0.880 g/cm³) consisting of copolymers of ethylene with one or more alpha-olefins having from 3 to 12 carbon atoms, having a mole content of units derived from ethylene of higher than 80%; high density ethylene polymers (HDPE, having a density higher than 0.940 g/cm³), comprising ethylene homopolymers and copolymers of ethylene with alpha-olefins having 3-12 carbon atoms; The following examples are given in order to further describe the present invention in a non-limiting manner.

CHARACTERIZATION

The properties are determined according to the following methods:

Melt Index: measured at 190°C according to ASTM D-1238 condition "E" (load of 2.16 Kg), "P" (load of 5.0 Kg) and "F" (load of 21.6 Kg);

Fraction soluble in xylene. The solubility in xylene at 25°C was determined according to the following method: About 2.5 g of polymer and 250 cm³ of o-xylene were placed in a round-bottomed flask provided with cooler and a reflux condenser and kept under nitrogen. The mixture obtained was heated to 135°C and was kept under stirring for about 60 minutes. The final solution was allowed to cool to 25°C under continuous stirring, and was then filtered. The filtrate was then evaporated in a nitrogen flow at 140°C to reach a constant weight. The content of said xylene-soluble fraction is expressed as a percentage of the original 2.5 grams.

Comonomer content

1-Butene or α -olefins were determined via Infrared Spectrometry.

Effective density: ASTM-D 1505

Thermal analysis: Calorimetric measurements were performed by using a differential scanning calorimeter DSC Perkin-Elmer. The instrument is calibrated with indium and tin standards. The weighted sample (5-10 mg), obtained from the Melt Index determination, was sealed into aluminum pans, thermostatted at 5°C for 3 minutes, heated to 200°C at 20°C/min and kept at that temperature for a time long enough (5 minutes) to allow a complete melting of all the crystallites. Successively, after cooling at 20°C/min to -20°C, the peak temperature was assumed as crystallization temperature (Tc). After standing 5 minutes at 0°C, the sample was heated to 200°C at a rate of 20°C/min. In this second heating run, the peak temperature was assumed as melting temperature (Tm) and the area as the global melting enthalpy (ΔH).

Determination of Mg, Ti: has been carried out via inductively coupled plasma emission spectroscopy (ICP).

Determination of Cl: has been carried out via potentiometric titration.

Determination of alkoxides (as ROH): via Gas-Chromatography analysis after hydrolysis of the catalyst.

Solid State NMR analysis. Solid state ^{13}C -NMR spectra were recorded on a Bruker DPX-200 spectrometer operating at 50.32 MHz in the Fourier transform mode. Samples were measured at room temperature in a 7 mm ZrO_2 rotor using a spinning speed of 4 KHz. Transients were accumulated using the cross polarization magic angle spinning technique (CP-MAS) with a recycle delay of 5 sec. and a contact time of 1 msec. All NMR experiments employed a proton decoupling field of sufficient magnitude to ensure full decoupling over the entire spectral width.

The rotors were prepared under nitrogen atmosphere.

Crystalline polyethylene in orthorhombic phase was taken as an external reference at 32.85 ppm from tetramethylsilane (TMS)

I_A is defined as the integral of the signals having the maximum in region between 60 and 75 ppm.

I_B is defined as the integral of the signals having the maximum in the region between 78 and 108 ppm.

EXAMPLES

All the solvent were deoxygenated, dried over LiAlH₄ and distilled under nitrogen atmosphere before the use.

TEA is Tris-Ethyl-Aluminum

TiBA is Tris-isoButyl-Aluminum

General preparation of the precursor

The synthesis of the precursor was performed as described in Example 1 of USP 4,220,554.

The so obtained support has the following composition:

Mg, 20.2 wt.%

Cl, 29.8 wt.%

EtO groups 41.5 wt.%

Example 1:

Into a 500 cm³ four-necked round flask, purged with nitrogen, 280 cm³ of heptane and 17.7 g (147 mg.at. of Mg) of the support previously prepared, were introduced at 25°C. Then, at the same temperature, 17 cm³ (0.154 mol.) of TiCl₄ were added under stirring. The temperature was raised to 50°C in 1 h and maintained for 2 hours. Then, the stirring was discontinued, the solid product was allowed to settle for 30 minutes and the supernatant liquid was siphoned off.

The solid was washed twice with anhydrous heptane (2 x 100 cm³) at 50 °C and three times at 25°C. Finally, the solid was dried under vacuum and analyzed. The results are reported in table 1.

Example 2-9

The procedure reported in Example 1 was repeated changing the solvent, TiCl₄ amount and temperature/time of treatment as reported in table 1.

Example 10

15.5 g of the support (129 mg.at. of Mg) were charged, under stirring at 0°C, to a 500 cm³ reactor containing 220 cm³ of pure SiCl₄ and 6.9 cm³ of pure TiCl₄ (62.5 mmol). The temperature was slowly raised to 40°C, then the temperature was kept constant for 4 hours. The stirring was discontinued, settling was allowed to occur and the liquid phase was removed at the temperature of 40°C. The residue was washed with anhydrous heptane, 150 cm³ at 40°C (twice) then 3 times (150 cm³ each time) with anhydrous heptane at room temperature. The residual solid component was vacuum dried at 50°C and analyzed. The catalyst characteristics are reported in table 1.

Example 11

In a 500 cm³ four-necked round flask equipped with a mechanical stirrer and purged with nitrogen, 220 cm³ of TiCl₄ were charged. The temperature was set at 0°C and 15.3 g (127 mg.at. of Mg) of the solid support were slowly fed. The temperature was raised to 40 °C and the mixture was stirred for 4 hours. Then, the stirring was discontinued, the solid product was allowed to settle and the supernatant liquid was siphoned off.

The solid was washed twice with anhydrous heptane (2 x 100 cm³) at 40°C and twice at 25 °C, recovered, dried under vacuum and analyzed. The characteristics are collected in table 1.

Comparative Example 1

A catalyst component was prepared according to the description of Example 2(a) of USP 4,220,554. The catalyst was used in the polymerization of ethylene according to the general polymerization procedure under the specific conditions reported in table 1.

Examples 12-14

The procedure reported in Example 11 was repeated changing the temperature and time of treatment as reported in table 1.

Examples 15-26 and comparison Example 2

Ethylene Polymerization: general procedure.

A 4.5 liter stainless-steel autoclave equipped with a stirrer, temperature and pressure indicator, feeding line for hexane, ethylene, and hydrogen, was used and purified by fluxing pure nitrogen at 70°C for 60 minutes. Then, 1550 cm³ of hexane containing 4.9 cm³ of 10 % by wt/vol TEA/hexane solution, was introduced at a temperature of 30°C under nitrogen flow. In a separate 200 cm³ round bottom glass bottle were successively introduced, 50 cm³ of anhydrous hexane, 1 cm³ of 10 % by wt/vol, TEA/hexane solution and about 0.010÷0.025g of the solid catalyst of table 1. They were mixed together, aged 10 minutes at room temperature and introduced under nitrogen flow into the reactor. The autoclave was closed, then the temperature was raised to 85°C, hydrogen (partial pressure as indicated in table 2) and ethylene (7.0 bars partial pressure) were added.

Under continuous stirring, the total pressure was maintained at 85°C for 120 minutes by feeding ethylene. At the end the reactor was depressurised and the temperature was dropped to 30°C. The recovered polymer was dried at 70°C under a nitrogen flow.

The amount of recovered polyethylene and the polymer characteristics are reported in table 2.

Example 27-31

Ethylene/α-olefin copolymerization: general procedure

A 4.5 liter stainless-steel autoclave equipped with a stirrer, temperature, pressure indicator, feeding line for ethylene, propane, 1-butene, hydrogen, and a steel vial for the injection of the catalyst, was purified by fluxing pure nitrogen at 70°C for 60 minutes. It was then washed with propane, heated to 75°C and finally loaded with 800 g of propane, 1-butene (the amount reported in table 3), ethylene (7.0 bar, partial pressure) and hydrogen (as in table 3).

In a 100 cm³ three neck glass flask were introduced in the following order, 50 cm³ of anhydrous hexane, the Al-alkyl/hexane solution (as reported in Table 3), optionally the external electron donor compound (table 3) and the solid catalyst 0.005-0.015 g (reported in table 3). They were mixed together and stirred at room temperature for 5 minutes and then introduced in the reactor through the steel vial by using a nitrogen overpressure.

Under continuous stirring, the total pressure was maintained constant at 75°C for 60 minutes by feeding ethylene. At the end the reactor was depressurized and the temperature was dropped to 30°C. The recovered polymer was dried at 70°C under a nitrogen flow and weighted. The polymer was characterized as reported in table 3.

Example 32

Following the procedure of example 1 and under the conditions of example 3, a solid catalyst component was achieved:

Mg, 15.5 wt.%; Ti, 7.8 wt.%; EtOH, 22.9 wt.% (EtO/Ti= 3.1 molar ratio) I_A/I_B (SS-NMR) = 1.34.

The solid catalyst was used in the ethylene/1-butene copolymerization in a fluidized gas-phase reactor as described in the following.

A 15.0 liter stainless-steel fluidized reactor equipped with gas-circulation system, cyclone separator, thermal exchanger, temperature and pressure indicator, feeding line for ethylene, propane, 1-butene, hydrogen, and a 1 L steel reactor for the catalyst pre-activation (prepolymerization if needed) and injection. The gas-phase apparatus was purified by fluxing pure nitrogen at 40°C for 12 hours and then was circulated a propane (10 bar, partial pressure) mixture containing 1.5 g of the same Aluminum alkyl used in polymerization, at 80°C for 30 minutes. It was then depressurized and the reactor washed with pure propane, heated to 75°C and finally loaded with propane (14.3 bar partial pressure), 1-butene (1.4 bar partial pressure), ethylene (3.8 bar, partial pressure) and hydrogen (0.5 bar, partial pressure).

In a 100 cm³ three neck glass flask were introduced in the following order, 20 cm³ of anhydrous hexane, 8.4 mmol of TiBA as hexane solution and 0.072 g of the solid component upper described. They were mixed together and stirred at room temperature for 5 minutes and then introduced in the preactivation reactor maintained in a propane flow.

The autoclave was closed and 100 g of propane were introduced at 40°C. The mixture was allowed stirring at 50°C for 30 minutes. The activated catalyst was then injected into the gas-phase reactor by using a propane overpressure (1 bar increase in the gas-phase reactor). The final pressure, in the fluidized reactor, was maintained constant at 80°C for 120 minutes by feeding a 7 wt.% 1-butene/ethylene mixture.

At the end, the reactor was depressurised and the temperature was dropped to 30°C. The recovered polymer was dried at 70°C under a nitrogen flow and weighted. 1170 g were achieved providing a mileage of 16.2 kg/gcat with the following characteristics:

MI E, 0.7 dg/min

MFR (MI F/MI E), 32.3

1-butene content, 7.2 wt.%

Xylene Soluble content, 3.7 wt.%

T_m, 120.5 °C

Table 1

Ex.	Catalyst preparation				Catalyst composition				SS-NMR	
	solvent	Ti/Mg m.r	Temp. °C	time h	Mg wt.%	Ti wt.%	EtOH wt.%	EtO/Ti m.r	I_A/I_B	
1	heptane	1.0	50	2	14.7	8.2	22.3	2.8	—	
2	heptane	0.45	70	2	15.0	7.4	33.1	4.7	1.32	
3	heptane	0.7	70	2	15.0	8.0	21.6	2.8	1.25	
4	heptane	2	70	2	15.1	8.4	15.9	2	1.21	
5	heptane	1	90	2	14.8	8.7	17.5	2.1	1.28	
6	decane	0.7	120	2	13.8	11.1	10.9	1.0	1.11	
7	toluene	0.7	40	4	16.0	7.2	22.2	3.2	1.62	
8	toluene	1.0	70	4	16.9	6.8	18.2	2.8	1.53	
9	toluene	7.8	40	4	15.9	8.8	18.9	2.2	1.19	
10	SiCl ₄	0.5	40	4	16.8	4.6	25.9	5.9	2.60	
11	TiCl ₄	15.7	40	4	16.2	7.6	17.8	2.4	1.60	
12	TiCl ₄	17.7	120	1/0.5/0.5	19.1	5.5	5.2	1.0	—	
13	TiCl ₄	20.7	135	2	18.1	7.2	4.0	0.6	>55	
14	TiCl ₄	31.3	90	4	17.2	7.4	12.4	1.7	1.35	
Comp.	TiCl ₄ /EB	10.2	120/120	2/2	21.6	3.2	3.0	1.0	—	

— not determined

Table 2

Ex.	Solid cat. component	Polymerization conditions			Polymer Characterization		
		H ₂ bar	Polymer g	Yield Kg/g _{cat}	MI E g/10'	MI F/MIP	MIF/MIE
15	1	4.00	630	36.8	17.8	--	--
16	2	3.0	480	25.7	3.60	9.9	28.9
17	4	3.00	605	27.5	14.6	--	28.8
18	5	4.00	580	48.3	16.5	11.4	35.2
19	6	3.00	400	20.7	2.5	10.3	30.9
20	8	3.00	540	27.4	11.60	10.2	30.0
21	9	3.00	510	26.0	11.10	10.2	31.8
22	10	3.00	610	29.8	4.40	9.8	27.3
23	11	3.00	537	51.6	19.20	9.9	29.2
24	12	4.00	550	26.4	10.40	10.9	32.5
25	13	3.00	484	32.0	1.8	10.6	32.5
26	14	3.00	410	38.6	18.80	9.9	29.3
Comp.		4.00	168	8.5	1.6	9.8	30.7

Table 3

Ex.	Polymerization conditions						Polymer Characterization				
	Solid cat. component	Cocatalyst	α -olefin	polymer	Yield	MIE	C_4	X.S	Tm		
	type	C_4^- g	H_2 Bar	time min	g	Kg/g^*h	g/10 ¹	wt.%	°C		
27	3	TEA (1)	180	1.00	61	180	33.4	4.3	8.1	6.7	123.5
28	5	TEA/DEAC/THF (2)	150.0	1.00	21	202	38.5	2.8	7.8	5.6	121.6
29	7	TEA/DEAC/THF (2)	180.0	1.50	88	190	14.7	2.4	6.8	4.7	—
30	10	TEA (1)	180.0	0.50	120	168	16.8	0.5	4.8	3.0	124.8
31	11	TEA/DEAC/THF (2)	180.0	1.5	57	176	21	3.4	7.8	6.0	122.5

Polym. Cond (1): Propane 800 g; TEA, 6.1 mmol; C_2H_4 7 bar; Temper. 75°C;Polym. Cond. (2): Propane 800 g; TEA, 5.7 mmol; THF, 1.7 mmol; DEAC, 2.7 mmol; C_2H_4 7 bar; Temper. 75°C;

CLAIMS

1. Process for the preparation of crystalline ethylene (co)polymers comprising polymerizing ethylene alone or in mixture with olefins $\text{CH}_2=\text{CHR}$, in which R is hydrogen or a hydrocarbyl radical with 1-12 carbon atoms, in the presence of a catalyst system comprising (a) a solid catalyst component comprising Ti, Mg, halogen, OR^1 groups, where R^1 is a C1-C12 hydrocarbon group optionally containing heteroatoms, having OR^1/Ti molar ratio of at least 0.5, an amount of titanium, with respect to the total weight of said solid catalyst component, higher than 4% by weight, and showing in the pattern of the SS-NMR recorded under the conditions set forth in the description one or more signals (A) having a maximum in the region 60-75 (ppm) and one or more signals (B) having a maximum in the region 78-108 (ppm) such that the ratio I^A/I^B , in which I^A is the integral of the signals having the maximum in the region between 60 and 75 ppm and I^B is the integral of the signals having the maximum in the region between 78 and 108 ppm, is higher than 0.8; and (b) an aluminum alkyl compound as a cocatalyst.
2. Process according to claim 1 in which the ratio I^A/I^B is higher than 1.
3. Process according to claim 1 in which the OR^1/Ti molar ratio is higher than 1
4. Process according to claim 1 in which R^1 is a C1-C8 hydrocarbon group selected from alkyl groups.
5. Process according to claim 1 in which the amount of titanium, with respect to the total weight of said solid catalyst component, is higher than 5%.
6. Process for the preparation of crystalline ethylene (co)polymers comprising polymerizing ethylene alone or in mixture with olefins $\text{CH}_2=\text{CHR}$, in which R is hydrogen or a hydrocarbyl radical with 1-12 carbon atoms, in the presence of a

catalyst system comprising (a) a solid catalyst component comprising Ti, Mg, halogen, OR^I groups, where R^I is a C1-C12 hydrocarbon group optionally containing heteroatoms, having OR^I/Ti molar ratio of at least 0.5, an amount of titanium, with respect to the total weight of said solid catalyst component, higher than 4% by weight, obtained by reacting a titanium compound having at least a Ti-Cl bond with a catalyst precursors of formula MgCl_n(OR^I)_{2-n}, where n is from 0.5 to 1.5 and R^I has the meaning given above, and (b) an aluminum alkyl compound as a cocatalyst.

7. Process according to claim 6 in which the titanium compounds are those having the formula Ti(OR^I)_{p-y}Cl_y, wherein R^I has the meaning given above, p is the titanium valence and y is a number comprised between 1 and p.
8. Process according to claim 6 obtained by reacting the catalyst precursor with a titanium compound, used in an amount such that the molar ratio between the titanium compound and the OR^I groups of the catalyst precursor is 4 or less.
9. Process according to claim 6 obtained by reacting the catalyst precursor with a titanium compound, used in amounts such the molar ratio between the titanium compound and the OR^I groups of the catalyst precursor is higher than 4 and the reaction temperature is lower than 100°C.
10. Process for the preparation of crystalline ethylene (co)polymers according to claim 1 or 6 comprising carrying out the slurry polymerization of ethylene alone or in mixture with olefins CH₂=CHR, in which R is hydrogen or a hydrocarbyl radical with 1-12 carbon atoms, in an inert medium.

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2006/060740

A. CLASSIFICATION OF SUBJECT MATTER
INV. C08F10/02 C08F4/654

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 553 805 A (SPHERILENE S.R.L; MONTELL TECHNOLOGY COMPANY BV) 4 August 1993 (1993-08-04) cited in the application example 4	1-10
X	US 5 118 768 A (JOB ET AL) 2 June 1992 (1992-06-02) the whole document	1-10
X	EP 0 423 786 A (HIMONT INCORPORATED; MONTELL NORTH AMERICA INC) 24 April 1991 (1991-04-24) examples 3,8,9	1-10
X	EP 0 444 606 A (MITSUI PETROCHEMICAL INDUSTRIES, LTD) 4 September 1991 (1991-09-04) the whole document	1-10



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

22 June 2006

Date of mailing of the international search report

30/06/2006

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Balmer, J-P

INTERNATIONAL SEARCH REPORT

Information on patent family members

 International application No
 PCT/EP2006/060740

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
EP 0553805	A	04-08-1993		AT 165103 T AU 655527 B2 AU 3215893 A BR 9300451 A CA 2088526 A1 CN 1075486 A CN 1120048 A DE 69317915 D1 DE 69317915 T2 DK 553805 T3 ES 2116359 T3 FI 930402 A IL 104561 A IT 1262935 B JP 3297120 B2 JP 6041217 A JP 3313170 B2 JP 7133313 A KR 268816 B1 MX 9300536 A1 NO 930349 A RU 2116319 C1 US 5578541 A ZA 9300665 A	15-05-1998 22-12-1994 05-08-1993 03-08-1993 01-08-1993 25-08-1993 10-04-1996 20-05-1998 05-11-1998 11-05-1998 16-07-1998 01-08-1993 31-08-1995 22-07-1996 02-07-2002 15-02-1994 12-08-2002 23-05-1995 16-10-2000 29-07-1994 02-08-1993 27-07-1998 26-11-1996 02-09-1993
US 5118768	A	02-06-1992		NONE	
EP 0423786	A	24-04-1991		AT 174605 T AU 639491 B2 AU 6373390 A BR 9005233 A CA 2025082 A1 CN 1051565 A CN 1108665 A CZ 9005047 A3 DE 69032839 D1 DE 69032839 T2 DK 423786 T3 ES 2126551 T3 HU 55806 A2 IL 95567 A JP 3051439 B2 JP 3140309 A KR 204444 B1 NO 904312 A PL 287366 A1 PL 167293 B1 PT 95617 A RO 106744 B1 US 6054406 A ZA 9007017 A	15-01-1999 29-07-1993 26-04-1991 17-09-1991 19-04-1991 22-05-1991 20-09-1995 15-12-1999 28-01-1999 08-07-1999 23-08-1999 01-04-1999 28-06-1991 27-02-1994 12-06-2000 14-06-1991 15-06-1999 19-04-1991 29-07-1991 31-08-1995 13-09-1991 30-06-1993 25-04-2000 25-09-1991
EP 0444606	A	04-09-1991		AT 138082 T CA 2037025 A1 CS 9100491 A2 DE 69119447 D1 DE 69119447 T2 HK 216196 A	15-06-1996 28-08-1991 15-10-1991 20-06-1996 17-10-1996 27-12-1996

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2006/060740

Patent document cited in search report	Publication date	Patent family member(s)		Publication date
EP 0444606	A	KR	9309263 B1	25-09-1993
		PL	289217 A1	24-08-1992
		RO	107953 B1	31-01-1994
		SG	43726 A1	14-11-1997
		US	5324805 A	28-06-1994