



US011088322B2

(12) **United States Patent**
Slovin et al.

(10) **Patent No.:** US 11,088,322 B2
(45) **Date of Patent:** Aug. 10, 2021

(54) **CAPACITIVE AND OHMIC TERMINALS IN A PHASE-CHANGE MATERIAL (PCM) RADIO FREQUENCY (RF) SWITCH**

(58) **Field of Classification Search**
None
See application file for complete search history.

(71) Applicant: **Newport Fab, LLC**, Newport Beach, CA (US)

(56) **References Cited**

(72) Inventors: **Gregory P. Slovin**, Irvine, CA (US); **Nabil El-Hinnawy**, Irvine, CA (US); **Jefferson E. Rose**, Hawthorne, CA (US); **David J. Howard**, Irvine, CA (US)

U.S. PATENT DOCUMENTS

7,761,067 B1 7/2010 Tsai et al.
9,368,720 B1* 6/2016 Moon H01L 45/16
(Continued)

(73) Assignee: **Newport Fab, LLC**, Newport Beach, CA (US)

OTHER PUBLICATIONS

Moon, et al. "Phase-Change RF Switches with Robust Switching Cycle Endurance," 2018 *IEEE Radio and Wireless Symposium (RWS)*, pp. 231-233, Jan. 2018, Anaheim, CA.

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(Continued)

Primary Examiner — Bradley Smith

(21) Appl. No.: **16/883,850**

(74) *Attorney, Agent, or Firm* — Farjami & Farjami LLP

(22) Filed: **May 26, 2020**

(57) **ABSTRACT**

(65) **Prior Publication Data**
US 2020/0287132 A1 Sep. 10, 2020

A radio frequency (RF) switch includes a phase-change material (PCM), a heating element underlying an active segment of the PCM and extending outward and transverse to the PCM, a capacitive RF terminal, and an ohmic RF terminal. The capacitive RF terminal can include a first trench metal liner situated on a first passive segment of the PCM, and a dielectric liner separating the first trench metal liner from a first trench metal plug. The ohmic RF terminal can include a second trench metal liner situated on a second passive segment of the PCM, and a second trench metal plug ohmically connected to the second trench metal liner. Alternatively, the capacitive RF terminal and the ohmic RF terminal can include lower metal portions and upper metal portions. A MIM capacitor can be formed by the upper metal portion of the capacitive RF terminal, an insulator, and a patterned top plate.


Related U.S. Application Data

(63) Continuation-in-part of application No. 16/271,505, filed on Feb. 8, 2019, now Pat. No. 10,937,960, which (Continued)

(51) **Int. Cl.**
H01L 45/00 (2006.01)

(52) **U.S. Cl.**
CPC **H01L 45/1253** (2013.01); **H01L 45/06** (2013.01); **H01L 45/1226** (2013.01); (Continued)

20 Claims, 22 Drawing Sheets



Related U.S. Application Data

is a continuation-in-part of application No. 16/103,490, filed on Aug. 14, 2018, now Pat. No. 10,476,001, and a continuation-in-part of application No. 16/103,587, filed on Aug. 14, 2018, now Pat. No. 10,461,253, and a continuation-in-part of application No. 16/103,646, filed on Aug. 14, 2018, now Pat. No. 10,475,993, and a continuation-in-part of application No. 16/114,106, filed on Aug. 27, 2018, now Pat. No. 10,707,125, and a continuation-in-part of application No. 16/231,112, filed on Dec. 21, 2018, now Pat. No. 10,770,389.

- (52) **U.S. Cl.**
 CPC **H01L 45/143** (2013.01); **H01L 45/144** (2013.01); **H01L 45/16** (2013.01)

- (56) **References Cited**

U.S. PATENT DOCUMENTS

10,505,106	B1	12/2019	Joshi	
2004/0113232	A1	6/2004	Johnson et al.	
2005/0212090	A1	9/2005	Friedrich et al.	
2007/0099405	A1*	5/2007	Oliva H01L 45/122 438/585
2007/0246766	A1	10/2007	Liu	
2008/0042243	A1	2/2008	Lee et al.	
2008/0142777	A1	6/2008	Park	

2008/0272355	A1	11/2008	Cho	
2008/0291718	A1	11/2008	Liu	
2009/0065761	A1	3/2009	Chen	
2009/0115052	A1	5/2009	Treece et al.	
2010/0238603	A1	9/2010	Chung	
2010/0246247	A1	9/2010	Kim	
2011/0097825	A1	4/2011	Cheng	
2012/0037872	A1	2/2012	Ikarashi	
2014/0110657	A1	4/2014	Redaelli	
2014/0191181	A1	7/2014	Moon	
2015/0022938	A1	1/2015	Okada et al.	
2015/0104921	A1	4/2015	Terai et al.	
2016/0056373	A1	2/2016	Goktepe	
2016/0300612	A1*	10/2016	Manipatruni G11C 11/1659
2018/0138894	A1	5/2018	Belot	
2018/0266974	A1	9/2018	Khosravani	
2019/0165264	A1	5/2019	Wu	
2019/0296718	A1	9/2019	Birkbeck et al.	

OTHER PUBLICATIONS

Wang, et al. "Directly Heated Four—Terminal Phase Change Switches," 2014 *IEEE MTT-S International Microwave Symposium (IMS2014)*, pp. 1-4, Jun. 2014, Tampa, FL.
 Tombak, et al. "Cellular Antenna Switches for Multimode Applications Based on a Silicon-on-insulator Technology," 2010 *IEEE Radio Frequency Integrated Circuits Symposium (RFIC)*, pp. 271-274, May 2010, Anaheim, CA.

* cited by examiner

Manufacturing Process for Capacitive RF Terminal and Ohmic RF Terminal in PCM RF Switch




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 9




FIG. 10




FIG. 11




FIG. 12




FIG. 13

Manufacturing Process for Capacitive RF Terminal and Ohmic RF Terminal in PCM RF Switch




FIG. 14




FIG. 15




FIG. 16




FIG. 17




FIG. 18




FIG. 19




FIG. 20




FIG. 21




FIG. 22

**CAPACITIVE AND OHMIC TERMINALS IN
A PHASE-CHANGE MATERIAL (PCM)
RADIO FREQUENCY (RF) SWITCH**

CLAIMS OF PRIORITY

This is a divisional of application Ser. No. 16/271,505 filed on Feb. 8, 2019. application Ser. No. 16/271,505 filed on Feb. 8, 2019 (“the parent application”) is a continuation-in-part of and claims the benefit of and priority to application Ser. No. 16/103,490 filed on Aug. 14, 2018, titled “Manufacturing RF Switch Based on Phase-Change Material.”. The parent application is also a continuation-in-part of and claims the benefit of and priority to application Ser. No. 16/103,587 filed on Aug. 14, 2018, titled “Design for High Reliability RF Switch Based on Phase-Change Material.”. The parent application is also a continuation-in-part of and claims the benefit of and priority to application Ser. No. 16/103,646 filed on Aug. 14, 2018, titled “PCM RF Switch Fabrication with Subtractively Formed Heater.”. The parent application is further a continuation-in-part of and claims the benefit of and priority to application Ser. No. 16/114,106 filed on Aug. 27, 2018, titled “Fabrication of Contacts in an RF Switch Having a Phase-Change Material (PCM) and a Heating Element.”. The parent application is also a continuation-in-part of and claims the benefit of and priority to application Ser. No. 16/231,121 filed on Dec. 21, 2018, titled “Phase-Change Material (PCM) Radio Frequency (RF) Switches with. Capacitively Coupled RF Terminals.”. The disclosures and contents of all of the above-identified applications are hereby incorporated fully by reference into the parent application and the present divisional application.

BACKGROUND

Phase-change materials (PCM) are capable of transforming from a crystalline phase to an amorphous phase. These two solid phases exhibit differences in electrical properties, and semiconductor devices can advantageously exploit these differences. Given the ever-increasing reliance on radio frequency (RF) communication, there is particular need for RF switching devices to exploit phase-change materials. However, the capability of phase-change materials for phase transformation depends heavily on how they are exposed to thermal energy and how they are allowed to release thermal energy. For example, in order to transform into an amorphous state, phase-change materials may need to achieve temperatures of approximately seven hundred degrees Celsius (700° C.) or more, and may need to cool down within hundreds of nanoseconds.

It is sometimes desirable to avoid fabricating only ohmic contacts for connecting to RF terminals of a PCM RF switch. In those instances, a robust capacitive (and non-ohmic) contact can be a good choice. However, capacitance fabrication techniques applicable to conventional semiconductor devices may not be optimum for, or easily compatible with, PCM RF switches, and may not properly utilize or take advantage of the unique structure, layout, and geometry of PCM RF switches. Moreover, it is often desirable to have both ohmic and capacitive contacts for connecting to RF terminals of PCM RF switches. As such, concurrently fabricating both capacitive and ohmic RF terminals in PCM RF switches can present additional and significant manufacturing challenges.

Thus, there is a need in the art to reliably and concurrently manufacture both capacitive and ohmic RF terminals for PCM RF switches.

SUMMARY

The present disclosure is directed to concurrent fabrication of and structure for capacitive terminals and ohmic terminals in a phase-change material (PCM) radio frequency (RF) switch, substantially as shown in and/or described in connection with at least one of the figures, and as set forth in the claims.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 illustrates a portion of a flowchart of an exemplary method for concurrently manufacturing both a capacitive radio frequency (RF) terminal and an ohmic RF terminal in a phase-change material (PCM) RF switch according to one implementation of the present application.

FIG. 2 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with an action in the flowchart of FIG. 1 according to one implementation of the present application.

FIG. 3 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with an action in the flowchart of FIG. 1 according to one implementation of the present application.

FIG. 4 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with an action in the flowchart of FIG. 1 according to one implementation of the present application.

FIG. 5 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with an action in the flowchart of FIG. 1 according to one implementation of the present application.

FIG. 6 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with an action in the flowchart of FIG. 1 according to one implementation of the present application.

FIG. 7 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with an action in the flowchart of FIG. 1 according to one implementation of the present application.

FIG. 8 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with an action in the flowchart of FIG. 1 according to one implementation of the present application.

FIG. 9 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with an action in the flowchart of FIG. 1 according to one implementation of the present application.

FIG. 10 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with an action in the flowchart of FIG. 1 according to one implementation of the present application.

FIG. 11 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with an action in the flowchart of FIG. 1 according to one implementation of the present application.

FIG. 12 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with an action in the flowchart of FIG. 1 according to one implementation of the present application.

FIG. 13 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with an

action in the flowchart of FIG. 1 according to one implementation of the present application.

FIG. 14 illustrates a portion of a flowchart of an exemplary method for concurrently manufacturing both a capacitive RF terminal and an ohmic RF terminal in a PCM RF switch according to one implementation of the present application.

FIG. 15 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with an action in the flowchart of FIG. 14 according to one implementation of the present application.

FIG. 16 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with an action in the flowchart of FIG. 14 according to one implementation of the present application.

FIG. 17 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with an action in the flowchart of FIG. 14 according to one implementation of the present application.

FIG. 18 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with an action in the flowchart of FIG. 14 according to one implementation of the present application.

FIG. 19 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with an action in the flowchart of FIG. 14 according to one implementation of the present application.

FIG. 20 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with an action in the flowchart of FIG. 14 according to one implementation of the present application.

FIG. 21 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with an action in the flowchart of FIG. 14 according to one implementation of the present application.

FIG. 22 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with an action in the flowchart of FIG. 14 according to one implementation of the present application.

DETAILED DESCRIPTION

The following description contains specific information pertaining to implementations in the present disclosure. The drawings in the present application and their accompanying detailed description are directed to merely exemplary implementations. Unless noted otherwise, like or corresponding elements among the figures may be indicated by like or corresponding reference numerals. Moreover, the drawings and illustrations in the present application are generally not to scale, and are not intended to correspond to actual relative dimensions.

FIG. 1 illustrates a portion of a flowchart of an exemplary method for concurrently manufacturing both a capacitive radio frequency (RF) terminal and an ohmic RF terminal in a phase-change material (PCM) RF switch according to one implementation of the present application. Certain details and features have been left out of the flowchart that are apparent to a person of ordinary skill in the art. For example, an action may consist of one or more sub-actions or may involve specialized equipment or materials, as known in the art. Moreover, some actions, such as masking and cleaning actions, are omitted so as not to distract from the illustrated actions. Actions 100 through 122 shown in the flowchart of FIG. 1 are sufficient to describe one implementation of the present inventive concepts, other implementations of the present inventive concepts may utilize actions different from

those shown in the flowchart of FIG. 1. Moreover, structures shown in FIGS. 2 through 13 illustrate the results of performing respective actions 100 through 122 in the flowchart of FIG. 1, respectively. For example, structure 200 shows a PCM RF switch structure after performing action 100, structure 222 shows a PCM RF switch structure after performing action 122, and so forth.

Referring to FIG. 2, PCM RF switch structure 200 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with action 100 in the flowchart of FIG. 1 according to one implementation of the present application. As shown in FIG. 2, PCM RF switch structure 200 includes substrate 224, lower dielectric 226, heating element 228, thermally conductive and electrically insulating layer 230, PCM 232 having active segment 234 and passive segments 236a and 236b, and optional contact uniformity support layer 238. PCM RF switch structure 200 may include other structures not shown in FIG. 2.

Substrate 224 is situated under lower dielectric 226. In one implementation, substrate 224 is an insulator, such as silicon oxide (SiO₂). In various implementations, substrate 224 is a silicon (Si), silicon-on-insulator (SOI), sapphire, complementary metal-oxide-semiconductor (CMOS), bipolar CMOS (BiCMOS), or group III-V substrate. In various implementations, a heat spreader is integrated with substrate 224, or substrate 224 itself performs as a heat spreader. Substrate 224 can have additional layers (not shown in FIG. 2). In one implementation, substrate 224 can comprise a plurality of interconnect metal levels and interlayer dielectric layers. Substrate 224 can also comprise a plurality of devices, such as integrated passive devices (IPDs) (not shown in FIG. 2).

Lower dielectric 226 is situated on top of substrate 224, and is adjacent to the sides of heating element 228. In the present implementation, lower dielectric 226 extends along the width of RF switch structure 200, and is also coplanar with heating element 228. In various implementations, lower dielectric 226 can have a relative width and/or a relative thickness greater or less than shown in FIG. 2. Lower dielectric 226 may comprise a material with thermal conductivity lower than that of thermally conductive and electrically insulating layer 230. In various implementations, lower dielectric 226 can comprise silicon oxide (SiO₂), silicon nitride (Si_xN_y), or another dielectric.

Heating element 228 is situated in lower dielectric 226. Heating element 228 also underlies active segment 234 of PCM 232. Heating element 228 generates a crystallizing heat pulse or an amorphizing heat pulse for transforming active segment 234 of PCM 232. Heating element 228 can comprise any material capable of Joule heating. Preferably, heating element 228 comprises a material that exhibits minimal or substantially no electromigration, thermal stress migration, and/or agglomeration. In various implementations, heating element 228 can comprise tungsten (W), molybdenum (Mo), titanium (Ti), titanium nitride (TiN), titanium tungsten (TiW), tantalum (Ta), nickel chromium (NiCr), or nickel chromium silicon (NiCrSi). For example, in one implementation, heating element 228 comprises tungsten lined with titanium and titanium nitride. Heating element 228 may be formed by a damascene process, a subtractive etch process, or any other suitable process. Heating element 228 can be connected to electrodes of a pulse generator (not shown in FIG. 2) that generates a crystallizing current pulse or an amorphizing voltage or current pulses.

Thermally conductive and electrically insulating layer 230 is situated on top of heating element 228 and lower

dielectric **226**, and under PCM **232** and, in particular, under active segment **234** of PCM **232**. Thermally conductive and electrically insulating layer **230** ensures efficient heat transfer from heating element **228** toward active segment **234** of PCM **232**, while electrically insulating heating element **228** from PCM **232**, and other neighboring structures. Thermally conductive and electrically insulating layer **230** can comprise any material with high thermal conductivity and high electrical resistivity. In various implementations, thermally conductive and electrically insulating layer **230** can comprise aluminum nitride (AlN), aluminum oxide (Al_{1-x}O_y), beryllium oxide (Be_xO_y), silicon carbide (SiC), diamond, or diamond-like carbon.

PCM **232** is situated on top of thermally conductive and electrically insulating layer **230**. PCM **232** also overlies heating element **228**. PCM **232** includes active segment **234** and passive segments **236a** and **236b**. Active segment **234** of PCM **232** approximately overlies heating element **228** and is approximately defined by heating element **228**. Passive segments **236a** and **236b** of PCM **232** extend outward and are transverse to heating element **228**. As used herein, “active segment” refers to a segment of PCM that transforms between crystalline and amorphous states, for example, in response to a crystallizing or an amorphizing heat pulse generated by heating element **228**, whereas “passive segment” refers to a segment of PCM that does not make such transformation and maintains a crystalline state (i.e., maintains a conductive state). With proper heat pulses and heat dissipation, active segment **234** of PCM **232** can transform between crystalline and amorphous states, allowing RF switch structure **200** to switch between ON and OFF states respectively.

PCM **232** can be germanium telluride (Ge_xTe_y), germanium antimony telluride (Ge_xSb_yTe_z), germanium selenide (Ge_xSe_y), or any other chalcogenide. In various implementations, PCM **232** can be germanium telluride having from forty percent to sixty percent germanium by composition (i.e., Ge_xTe_y, where 0.4 ≤ X ≤ 0.6 and Y = 1 - X). The material for PCM **232** can be chosen based upon ON state resistivity, OFF state electric field breakdown threshold, crystallization temperature, melting temperature, or other considerations. PCM **232** can be provided, for example, by physical vapor deposition (PVD), sputtering, chemical vapor deposition (CVD), evaporation, or atomic layer deposition (ALD). In one implementation, PCM **232** can have a thickness of approximately five hundred angstroms to approximately two thousand angstroms (500 Å-2000 Å). In other implementations, PCM **232** can have any other thicknesses. The thickness of PCM **232** can be chosen based upon sheet resistance, crystallization power, amorphization power, or other considerations. It is noted that in FIG. 2, current flowing in heating element **228** flows substantially under active segment **234** of PCM **232**.

Optional contact uniformity support layer **238** is situated over PCM **232**. In one implementation, optional contact uniformity support layer **238** comprises Si_xN_y. In another implementation, optional contact uniformity support layer **238** is a bi-layer that comprises oxide and nitride, such as SiO₂ under Si_xN_y. Optional contact uniformity support layer **238** can be provided, for example, by plasma enhanced CVD (PECVD) or high density plasma CVD (HDP-CVD). In one implementation, optional contact uniformity support layer **238** can have a thickness of approximately fifty angstroms to approximately one thousand two hundred and fifty angstroms (50 Å-1250 Å). By forming optional contact uniformity support layer **238** as shown in FIG. 2, PCM **232** will remain substantially intact, and uniform contact can be made

to passive segments **236a** and **236b** of PCM **232**, as described below. Optional contact uniformity support layer **238** is optional in that the inventive concepts of the present application may be implemented without forming optional contact uniformity support layer **238**, as described below.

Referring to FIG. 3, PCM RF switch structure **202** illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with action **102** in the flowchart of FIG. 1 according to one implementation of the present application. As shown in FIG. 3, RF terminal dielectric **240** is formed over PCM **232** and over optional contact uniformity support layer **238** (in case optional contact uniformity support layer **238** is used). RF terminal dielectric **240** is also formed over thermally conductive and electrically insulating layer **230**. In the present implementation, chemical machine polishing (CMP) is used to planarize RF terminal dielectric **240**. In various implementations, RF terminal dielectric **240** is SiO₂, Si_xN_y, or another dielectric. RF terminal dielectric **240** can be formed, for example, by PECVD or HDP-CVD. In one implementation, the deposition thickness of RF terminal dielectric **240** can range from approximately one half a micron to approximately two microns (0.5 μm-2 μm). In one implementation, a thickness of RF terminal dielectric **240** is significantly greater than a thickness of optional contact uniformity support layer **238**.

Referring to FIG. 4, PCM RF switch structure **204** illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with action **104** in the flowchart of FIG. 1 according to one implementation of the present application. As shown in FIG. 4, trenches or holes **242a** and **242b** are etched in RF terminal dielectric **240** and in optional contact uniformity support layer **238** (in case optional contact uniformity support layer **238** is used). Trenches or holes **242a** and **242b** extend to passive segment **236a** and **236b** respectively of PCM **232**.

In the present implementation, forming trenches **242a** and **242b** may comprise two different etching actions. In the first etching action, RF terminal dielectric **240** can be aggressively etched without having to accurately time the etching action. This etching action can use a selective etch, for example, a fluorine-based plasma dry etch, and optional contact uniformity support layer **238** can perform as an etch stop while RF terminal dielectric **240** is selectively etched. In the second etching action, optional contact uniformity support layer **238** is punch-through etched. As used herein, “punch-through” refers to a short etching action that can be accurately timed to stop at the top surface of PCM **232**. In RF switch structure **204**, trenches **242a** and **242b** are narrow and optional contact uniformity support layer **238** is thin. Thus, only a small volume of optional contact uniformity support layer **238** is etched, and the punch-through etching action is short and can be accurately timed. In one implementation, a chlorine-based plasma dry etch is used for this etching action.

Optional contact uniformity support layer **238** is optional in that the inventive concepts of the present application may be implemented without optional contact uniformity support layer **238**, and trenches **242a** and **242b** can extend through RF terminal dielectric **240** into PCM **232**. Because the ON state resistance (R_{ON}) of an RF switch depends heavily on the uniformity of contact made with PCM **232**, the R_{ON} will be significantly lower when optional contact uniformity support layer **238** is used.

Referring to FIG. 5, PCM RF switch structure **206** illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with action **106** in

the flowchart of FIG. 1 according to one implementation of the present application. As shown in FIG. 5, metal liner 244 is formed in trenches 242a and 242b, and on passive segments 236a and 236b of PCM 232. Metal liner 244 lines trenches 242a and 242b without completely filling trenches 242a and 242b. Metal liner 244 is also formed over RF terminal dielectric 240. In various implementations, metal liner 244 can comprise tungsten (W), molybdenum (Mo), titanium (Ti), titanium nitride (TiN), titanium tungsten (TiW), tantalum (Ta), cobalt (Co), nickel (Ni), nickel chromium (NiCr), or nickel chromium silicon (NiCrSi). For example, in one implementation, metal liner 244 comprises cobalt lined with titanium nitride and tungsten. Metal liner 244 may be formed by PVD, CVD, or any other suitable process.

Referring to FIG. 6, PCM RF switch structure 208 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with action 108 in the flowchart of FIG. 1 according to one implementation of the present application. As shown in FIG. 6, trench metal liners 246a and 246b are formed in trenches 242a and 242b respectively and on passive segments 236a and 236b respectively of PCM 232. Thus, trench metal liners 246a and 246b are ohmically connected to passive segments 236a and 236b respectively of PCM 232. In the present implementation, trench metal liners 246a and 246b are formed by removing a middle segment of metal liner 244 (shown in FIG. 5) on RF terminal dielectric 240 between trenches 242a and 242b, for example, using a chlorine based reactive ion etch (RIE). Outside trench 242a, trench metal liner extension 246x is situated over RF terminal dielectric 240 and integrally connected to trench metal liner 246a.

Referring to FIG. 7, PCM RF switch structure 210 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with action 110 in the flowchart of FIG. 1 according to one implementation of the present application. As shown in FIG. 7, dielectric liner 248 is formed on trench metal liners 246a and 246b in trenches 242a and 242b. Dielectric liner 248 is also formed on trench metal liner extension 246x and on RF terminal dielectric 240. Dielectric liner 248 lines trench metal liners 246a and 246b. In one implementation, dielectric liner 248 is silicon nitride. In various implementations, dielectric liner 248 is a high-k dielectric, such as tantalum pentoxide, aluminum oxide, hafnium oxide, zirconium oxide, zirconium aluminum silicate, hafnium silicate, hafnium aluminum silicate or another dielectric with a relatively high dielectric constant. In one implementation, the thickness of dielectric liner 248 can range from approximately two hundred angstroms to approximately six hundred angstroms (200 Å-600 Å). As further shown in FIG. 7, dielectric liner extension 248x is situated over trench metal liner extension 246x and integrally connected to dielectric liner 248.

Referring to FIG. 8, PCM RF switch structure 212 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with action 112 in the flowchart of FIG. 1 according to one implementation of the present application. As shown in FIG. 8, dielectric liner 248 is removed from trench metal liner 246b. In one implementation, a fluorine based RIE is used to remove dielectric liner 248 from trench metal liner 246b. Dielectric liner 248 remains on trench metal liner 246a. Notably, dielectric liner 248 remains with overplot 250 relative to trench metal liner 246a. Overplot 250 protects against shorting, as described below. Outside trench 242a, dielectric

liner extension 248x is situated over trench metal liner extension 246x and integrally connected to dielectric liner 248.

Referring to FIG. 9, PCM RF switch structure 214 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with action 114 in the flowchart of FIG. 1 according to one implementation of the present application. As shown in FIG. 9, metal 252 is deposited on dielectric liner 248 in trench 242a, and on trench metal liner 246b in trench 242b. Metal 252 fills trenches 242a and 242b. In various implementations, metal 252 can comprise aluminum (Al), copper (Cu), titanium (Ti), or titanium nitride (TiN). For example, in one implementation, metal 252 comprises a sequential stack of titanium, titanium nitride, aluminum, titanium, and titanium nitride. Metal 252 can be formed by PVD, or any other suitable process. In one implementation, the deposition thickness of metal 252 can be approximately one half a micron (0.5 μm).

Referring to FIG. 10, PCM RF switch structure 216 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with action 116 in the flowchart of FIG. 1 according to one implementation of the present application. As shown in FIG. 10, trench metal plug 254a is formed in trench 242a on dielectric liner 248, and trench metal plug 254b and is formed in trench 242b on trench metal liner 246b, thereby substantially completing capacitive RF terminal 256a and ohmic RF terminal 256b of PCM RF switch structure 216. Capacitive RF terminal 256a and ohmic RF terminal 256b provide RF signals to/from passive segments 236a and 236b respectively of PCM 232. Capacitive RF terminal 256a includes trench metal liner 246a, dielectric liner 248, and trench metal plug 254a that together form a trench capacitor. Dielectric liner 248 separates trench metal liner 246a from trench metal plug 254a. As such, trench metal liner 246a is ohmically separated from, but capacitively coupled to trench metal plug 254a. Ohmic RF terminal 256b includes trench metal liner 246b and trench metal plug 254b. Unlike trench metal liner 246a and trench metal plug 254a of capacitive RF terminal 256a, trench metal liner 246b and trench metal plug 254b of ohmic RF terminal 256b are ohmically coupled.

Capacitive RF terminal 256a also includes trench metal liner extension 246x, dielectric liner extension 248x, and trench metal plug extension 254x that further capacitively couple trench metal liner 246a to trench metal plug 254a. Trench metal liner extension 246x, dielectric liner extension 248x, and trench metal plug extension 254x are optional in that the inventive concepts of the present application may be implemented without them, and trench metal liner 246a would still capacitively couple to trench metal plug 254a. However, capacitive coupling between trench metal liner 246a and trench metal plug 254a is strengthened when trench metal liner extension 246x, dielectric liner extension 248x, and trench metal plug extension 254x are used. Although trench metal liner 246a, dielectric liner 248, and trench metal plug 254a are illustrated as integrally formed with trench metal liner extension 246x, dielectric liner extension 248x, and trench metal plug extension 254x respectively, in one implementation they may be different formations. For example, trench metal plug 254a may be situated in trench 242a and a metal may be subsequently formed over trench metal plug 254a to form trench metal plug extension 254x. In this example, trench metal plug 254a can comprise W, and trench metal plug extension 254x can comprise Al or Cu.

In the present implementation, trench metal plugs **254a** and **254b** are formed by removing a middle segment of metal **252** (shown in FIG. 9) between trenches **242a** and **242b**, for example, using a metal etch. Notably, dielectric liner **248** remains with underplot **258** relative to trench metal liner **246a**. Underplot **258** protects against breakdown, as described below. Outside trench **242a**, trench metal plug extension **254x** is situated over dielectric liner extension **248x** and integrally connected to trench metal plug **254a**.

Referring to FIG. 11, PCM RF switch structure **218** illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with action **118** in the flowchart of FIG. 1 according to one implementation of the present application. As shown in FIG. 11, interlayer dielectric **260** is formed over trench metal plugs **254a** and **254b**. In the present implementation, CMP is used to planarize interlayer dielectric **260**. Interlayer dielectric **260** provides insulation between trench metal plugs **254a** and **254b** and subsequently formed vias or interconnect metal (not shown in FIG. 11). In various implementations, interlayer dielectric **260** is SiO₂, Si_xN_y, or another dielectric. Interlayer dielectric **260** can be formed, for example, by PECVD or HDP-CVD. In one implementation, the deposition thickness of RF terminal dielectric **240** can be approximately one half a micron (0.5 μm).

Referring to FIG. 12, PCM RF switch structure **220** illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with action **120** in the flowchart of FIG. 1 according to one implementation of the present application. As shown in FIG. 12, interconnect holes **262a** and **262b** are etched in interlayer dielectric **260**. Interconnect holes **262a** and **262b** extend to trench metal plugs **254a** and **254b** respectively. In the present implementation, trench metal plug **254b** of ohmic RF terminal **256b** is situated lower in PCM RF switch structure **220** relative to trench metal plug **254a** of capacitive RF terminal **256a**, and interconnect hole **262b** is deeper than interconnect hole **262a** because capacitive RF terminal **256a** includes dielectric liner **248**. Interconnect holes **262a** and **262b** in interlayer dielectric **260** are selectively etched so that trench metal plug **254a** of capacitive RF terminal **256a** remains substantially undamaged while deeper interconnect hole **262b** is etched.

Referring to FIG. 13, PCM RF switch structure **222** illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with action **122** in the flowchart of FIG. 1 according to one implementation of the present application. As shown in FIG. 13, interconnect metals **264a** and **264b** are formed in interconnect holes **262a** and **262b** (labeled in FIG. 12) respectively and on trench metal plugs **254a** and **254b** respectively. In one implementation, a metal layer is deposited over interlayer dielectric **260** and in interconnect holes **262a** and **262b** (labeled in FIG. 12) over trench metal plugs **254a** and **254b**, and then a middle segment thereof between interconnect holes **262a** and **262b** (labeled in FIG. 12) is etched, thereby forming interconnect metals **264a** and **264b**. Interconnect metals **264a** and **264b** can be part of routing interconnects for routing electrical signals between capacitive RF terminal **256a** or ohmic RF terminal **256b** and various devices (not shown in FIG. 13) that may exist independent of PCM RF switch structure **222**. In various implementations, interconnect metals **264a** and **264b** can comprise Al and/or Cu. Interconnect metals **264a** and **264b** can be formed by PVD, or any other suitable process. In one implementation, the thickness of interconnect metals **264a** and **264b** can be approximately three microns (3 μm). In various implemen-

tations, PCM RF switch structure **222** can include more interconnect metals and/or more interlayer dielectrics than those shown in FIG. 13.

PCM RF switch structure **222** in FIG. 13 including one capacitive RF terminal **256a** and one ohmic RF terminal **256b**, and manufactured according to the flowchart in FIG. 1, provides several advantages. First, the trench capacitor of capacitive RF terminal **256a** capacitively couples trench metal liner **246a** to trench metal plug **254a**, creating part of an RF signal path of PCM RF switch structure **222**, despite that patterned trench metal liner **246a** and trench metal plug **254a** are ohmically separated from each other. Second, because capacitive RF terminal **256a** is directly connected to PCM **232** without any traces or interconnects, such as interconnect metals **264a** and **264b** intervening therebetween, routing resistance is lowered and the quality factor of the trench capacitor is high. Third, because PCM RF switch structure **222** in FIG. 13 includes one capacitive RF terminal **256a** and one ohmic RF terminal **256b**, two capacitive terminals are not placed in series in the RF signal path, and thus, do not halve the total capacitance of the switch. Fourth, compared to a manufacturing process that forms two capacitive RF terminals, a manufacturing process of the present application needs only a few additional steps to form one capacitive RF terminal **256a** and one ohmic RF terminal **256b**.

Fifth, overplot **250** of dielectric liner **248** protects capacitive RF terminal **256a** against shorting. A natural result of etching metal **252** (shown in FIG. 9) to form trench metal plugs **254a** and **254b** (shown in FIG. 10) is that stringers will form at an edge of trench metal plug **254a** and undesirably short to trench metal liner **246a**, which would result in “capacitive” RF terminal **256a** not forming a capacitor. Overplot **250** of dielectric liner **248** intervenes between the edge of trench metal plug **254a** and trench metal liner **246a**. Because dielectric liner **248** provides electrical insulation, a stringer would not couple to trench metal liner **246a** and would not cause a short.

Sixth, underplot **258** of trench metal plug **254a** protects capacitive RF terminal **256a** against breakdown. Dielectric liner **248** usually exhibits some defects or abnormalities near the sharp corner at the edge of trench metal liner **246a**, which would undesirably result in breakdown variations for the trench capacitor of capacitive RF terminal **256a**. Underplot **258** of trench metal plug **254a** ensures that trench metal plug **254a** is not situated over a sharp corner of dielectric liner **248**. As such, breakdown of capacitive RF terminal **256a** is more precisely controlled, and PCM RF switch structure **222** is more reliable.

Seventh, because PCM RF switch structure **222** utilizes trench metal liners **246a** and **246b** and trench metal plugs **254a** and **254b** in trenches **242a** and **242b**, more interface area is available to capacitively couple, and capacitance value of capacitive RF terminal **256a** is increased. Eighth, because PCM RF switch structure **222** utilizes a thin high-k dielectric liner **248**, the capacitive coupling between trench metal liner **246a** and trench metal plug **254a** is significantly increased. Ninth, because PCM RF switch structure **222** utilizes overhang regions, capacitive coupling between trench metal liner **246a** and trench metal plug **254a** is further increased.

FIG. 14 illustrates a portion of a flowchart of an exemplary method for concurrently manufacturing both a capacitive RF terminal and an ohmic RF terminal in a PCM RF switch according to one implementation of the present application. Certain details and features have been left out of the flowchart that are apparent to a person of ordinary skill

in the art. For example, an action may consist of one or more sub-actions or may involve specialized equipment or materials, as known in the art. Moreover, some actions, such as masking and cleaning actions, are omitted so as not to distract from the illustrated actions. Actions 166 through 180 shown in the flowchart of FIG. 14 are sufficient to describe one implementation of the present inventive concepts, other implementations of the present inventive concepts may utilize actions different from those shown in the flowchart of FIG. 14. Moreover, structures shown in FIGS. 15 through 22 illustrate the results of performing respective actions 166 through 180 in the flowchart of FIG. 14, respectively. For example, structure 266 shows a PCM RF switch structure after performing action 166, structure 280 shows a PCM RF switch structure after performing action 180, and so forth.

Referring to FIG. 15, PCM RF switch structure 266 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with action 166 in the flowchart of FIG. 14 according to one implementation of the present application. As shown in FIG. 15, PCM RF switch structure 266 includes substrate 224, lower dielectric 226, heating element 228, thermally conductive and electrically insulating layer 230, PCM 232 having active segment 234 and passive segments 236a and 236b, optional contact uniformity support layer 238, RF terminal dielectric 240, and trenches 242a and 242b. Action 166 in the flowchart of FIG. 14 generally corresponds to actions 100, 102, and 104 in the flowchart of FIG. 1. Accordingly, PCM RF switch structure 266 in FIG. 15 generally corresponds to PCM RF switch structure 204 in FIG. 4, and may have any implementations and advantages described above.

Referring to FIG. 16, PCM RF switch structure 268 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with action 168 in the flowchart of FIG. 14 according to one implementation of the present application. As shown in FIG. 16, lower metal portions 282a and 282b are formed in trenches 242a and 242b (shown in FIG. 15), and on passive segments 236a and 236b of PCM 232. Thus, lower metal portions 282a and 282b are ohmically connected to passive segments 236a and 236b respectively of PCM 232. Notably, lower metal portions 282a and 282b fill trenches 242a and 242b. In one implementation, lower metal portions 282a and 282b can be formed by depositing a metal, for example, using PVD, CVD, or any other suitable process, and then polishing the metal, for example, using CMP. In another implementation, lower metal portions 282a and 282b can be formed by a damascene process. In various implementations, lower metal portions 282a and 282b can comprise tungsten (W), aluminum (Al), copper (Cu), molybdenum (Mo), titanium (Ti), titanium nitride (TiN), titanium tungsten (TiW), tantalum (Ta), cobalt (Co), nickel (Ni), nickel chromium (NiCr), or nickel chromium silicon (NiCrSi).

Referring to FIG. 17, PCM RF switch structure 270 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with action 170 in the flowchart of FIG. 14 according to one implementation of the present application. As shown in FIG. 17, metal layer 284 is formed on lower metal portions 282a and 282b, and on RF terminal dielectric 240. In various implementations, metal layer 284 can comprise aluminum (Al), copper (Cu), titanium (Ti), or titanium nitride (TiN). For example, in one implementation, metal layer 284 comprises a sequential stack of titanium, titanium nitride, aluminum, titanium, and titanium nitride. In the present implementation, metal layer 284 is substantially planar. Metal layer 284 can be formed by

PVD, or any other suitable process. In one implementation, the thickness of metal layer 284 can be approximately one half a micron (0.5 μm).

Referring to FIG. 18, PCM RF switch structure 272 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with action 172 in the flowchart of FIG. 14 according to one implementation of the present application. As shown in FIG. 18, insulator 286 is formed on metal layer 284. In one implementation, insulator 286 is silicon nitride. In various implementations, insulator 286 is a high-k dielectric, such as tantalum pentoxide, aluminum oxide, hafnium oxide, zirconium oxide, zirconium aluminum silicate, hafnium silicate, hafnium aluminum silicate or another dielectric with a relatively high dielectric constant. In the present implementation, insulator 286 is substantially planar. Insulator 286 can be formed, for example, by PECVD or HDP-CVD. In one implementation, the thickness of insulator 286 can range from approximately two hundred angstroms to approximately six hundred angstroms (200 \AA -600 \AA).

Referring to FIG. 19, PCM RF switch structure 274 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with action 174 in the flowchart of FIG. 14 according to one implementation of the present application. As shown in FIG. 19, top metal 288 is formed on insulator 286. In various implementations, top metal 288 can comprise titanium nitride (TiN), tantalum nitride (TaN), or a stack comprising aluminum and titanium nitride or tantalum nitride. In the present implementation, top metal 288 is substantially planar. Top metal 288 can be formed by PVD, or any other suitable process. In one implementation, the thickness of top metal 288 can range from approximately five hundred angstroms to approximately one thousand angstroms (500 \AA -1000 \AA).

Referring to FIG. 20, PCM RF switch structure 276 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with action 176 in the flowchart of FIG. 14 according to one implementation of the present application. As shown in FIG. 20, top metal 288 (labeled in FIG. 19) is etched to form patterned top plate 290. Top metal 288 (labeled in FIG. 19) is etched overlying lower metal portion 282b, but remains overlying lower metal portion 282a, thereby forming patterned top plate 290. In the present implementation, insulator 286 is partially etched. In another implementation insulator 286 may remain substantially unetched.

Referring to FIG. 21, PCM RF switch structure 278 illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with action 178 in the flowchart of FIG. 14 according to one implementation of the present application. As shown in FIG. 21, metal layer 284 (labeled in FIG. 20) is etched to form upper metal portions 292a and 292b, thereby forming metal-insulator-metal (MIM) capacitor 296 by upper metal portion 292a, insulator 286, and patterned top plate 290. Etching metal layer 284 to form upper metal portions 292a and 292b also thereby substantially completes capacitive RF terminal 294a and ohmic RF terminal 294b of PCM RF switch structure 278. Capacitive RF terminal 294a and ohmic RF terminal 294b provide RF signals to/from passive segments 236a and 236b respectively of PCM 232. Capacitive RF terminal 294a includes lower metal portion 282a, upper metal portion 292a, insulator 286, and patterned top plate 290. Ohmic RF terminal 294b includes lower metal portion 282b and upper metal portion 292b.

In the present implementation, upper metal portions 292a and 292b are formed by removing a middle segment of metal

layer **284** (labeled in FIG. **20**) between lower metal portions **282a** and **282b**, for example, using a chlorine based RIE. In an alternative implementation, a single damascene process can be used to form upper metal portions **292a** and **292b** prior to depositing insulator **286**. Moreover, although lower metal portions **282a** and **282b** and upper metal portions **292a** and **292b** are separate formations in FIG. **21**, in other implementations they may be parts of the same formation. For example, lower metal portions **282a** and **282b** and upper metal portions **292a** and **292b** can be formed as a single metal using a dual damascene process. As another example, lower metal portions **282a** and **282b** and upper metal portions **292a** and **292b** can be formed as a single metal by depositing a metal layer in trenches **242a** and **242b** (labeled in FIG. **15**) and over RF terminal dielectric **240**, and then etching a middle segment thereof between trenches **242a** and **242b**. In these examples, lower metal portions **282a** and **282b** and upper metal portions **292a** and **292b** would not have a boundary interface. Although upper metal portions **292a** and **292b** have overplots relative to lower metal portions **282a** and **282b** in FIG. **21**, in various implementations, upper metal portions **292a** and **292b** can be aligned with lower metal portions **282a** and **282b**, or can have underplots relative to lower metal portions **282a** and **282b**.

Referring to FIG. **22**, PCM RF switch structure **280** illustrates a cross-sectional view of a portion of a PCM RF switch structure processed in accordance with action **180** in the flowchart of FIG. **14** according to one implementation of the present application. Action **180** in the flowchart of FIG. **14** generally corresponds to actions **118**, **120**, and **122** in the flowchart of FIG. **1**, and interlayer dielectric **260** and interconnect metals **264a** and **264b** in FIG. **22** generally correspond to interlayer dielectric **260** and interconnect metals **264a** and **264b** in FIG. **13**, except for differences described below.

As shown in FIG. **22**, interlayer dielectric **260** is formed over patterned top plate **290** of capacitive RF terminal **294a** and over upper metal portion **292b** of ohmic RF terminal **294b**. Thus, patterned top plate **290** of MIM capacitor **296** is situated within interlayer dielectric **260**. As used herein, "MIM capacitor" refers to a capacitor having a top plate formed within an interlayer dielectric where conventionally no metal (other than via or interconnect metal) exists, such as within interlayer dielectric **260**.

Interconnect metal **264a** is formed in an interconnect hole etched in interlayer dielectric **260**, and on patterned top plate **290** of capacitive RF terminal **294a**. Interconnect metal **264b** is formed in an interconnect hole etched in both interlayer dielectric **260** and insulator **286**, and on upper metal portion **292b** of ohmic RF terminal **294b**. In contrast to PCM RF switch structure **222** in FIG. **13** where interconnect metals **264a** and **264b** is connected to trench metal plugs **254a** and **254b** for capacitive RF terminal **256a** and ohmic RF terminal **256b**, in PCM RF switch structure **280** in FIG. **22**, interconnect metal **264b** is connected to upper metal portion **292b** of ohmic RF terminal **294b**, while interconnect metal **264a** is connected to patterned top plate **290** of capacitive RF terminal **294a**.

In the present implementation, upper metal portion **292b** of ohmic RF terminal **294b** is situated lower in PCM RF switch structure **280** relative to patterned top plate **290** of capacitive RF terminal **294a**, and interconnect metal **264b** extends deeper than interconnect metal **264a**, because capacitive RF terminal **294a** includes patterned top plate **290**. Patterned top plate **290** of capacitive RF terminal **294a** can perform as an etch stop while interlayer dielectric **260** and insulator **286** are selectively etched, so that patterned top

plate **290** of capacitive RF terminal **294a** remains substantially undamaged when deeper interconnect metal **264b** is formed.

PCM RF switch structure **280** in FIG. **22** provides advantages similar to PCM RF switch structure **222** in FIG. **13** in that PCM RF switch structure **280** in FIG. **22** includes one capacitive RF terminal **294a** and one ohmic RF terminal **294b** for providing RF signals to/from passive segments **236a** and **236b** respectively of PCM **232**. As described above, first, MIM capacitor **296** of capacitive RF terminal **294a** capacitively couples patterned top plate **290** to upper metal portion **292a**, creating part of an RF signal path of PCM RF switch structure **280**, despite the fact that patterned top plate **290** and upper metal portion **292a** are ohmically separated from each other. Second, because capacitive RF terminal **294a** is directly connected to PCM **232** without any traces or interconnects intervening therebetween, routing resistance is lowered and the quality factor of MIM capacitor **296** is high. Third, because PCM RF switch structure **280** in FIG. **22** includes one capacitive RF terminal **294a** and one ohmic RF terminal **294b**, two capacitive terminals are not placed in series in the RF signal path, and thus, do not halve the total capacitance of the switch. Fourth, compared to a manufacturing process that forms two capacitive RF terminals, a manufacturing process of the present application needs only a few additional steps to form one capacitive RF terminal **294a** and one ohmic RF terminal **294b**.

Additionally, PCM RF switch structure **280** in FIG. **22** provides several advantages over PCM RF switch structure **222** in FIG. **13**. First, because insulator **286** is only partially etched or substantially unetched after etching of patterned top plate **290**, there is little or no increase in leakage current of MIM capacitor **296** and little or no decrease in the breakdown voltage of MIM capacitor **296** due to an increase in defects or voids within insulator **286**. As such, the capacitance value of MIM capacitor **296** is more precisely controlled, and PCM RF switch structure **280** is more reliable.

Second, in contrast to trench metal liners **246a** and **246b** in PCM RF switch structure **220** in FIG. **12**, lower metal portions **282a** and **282b** of PCM RF switch structure **280** in FIG. **22** completely fill trenches. Accordingly metal layer **284**, insulator **286**, and top metal **288** (labeled in FIG. **19**) can be formed substantially planar. Manufacturing is simplified. And compared to dielectric liner **248** in FIG. **13** that has varying thickness in trenches **242a**, insulator **286** has more uniform thickness, resulting in less breakdown variations for the MIM capacitor **296** of capacitive RF terminal **294a**.

Third, MIM capacitor **296** formed by upper metal portion **292a**, insulator **286**, and patterned top plate **290** has a capacitance with significantly improved density. MIM capacitor **296** does not require addition of interlayer metal levels, and also does not use up lateral die space. MIM capacitor **296** advantageously increases routing capability because MIM capacitor **296** utilizes the space amply available between interlayer dielectrics, such as interlayer dielectric **260**.

Thus, various implementations of the present application achieve a method of concurrently manufacturing and a structure of a PCM RF switch having both capacitive and ohmic RF terminals that overcome the deficiencies in the art while preserving or improving RF performance.

From the above description it is manifest that various techniques can be used for implementing the concepts described in the present application without departing from the scope of those concepts. For example, a single capacitor

can be formed in the RF path near one RF terminal, while the other RF terminal only employs ohmic connections. Moreover, while the concepts have been described with specific reference to certain implementations, a person of ordinary skill in the art would recognize that changes can be made in form and detail without departing from the scope of those concepts. As such, the described implementations are to be considered in all respects as illustrative and not restrictive. It should also be understood that the present application is not limited to the particular implementations described above, but many rearrangements, modifications, and substitutions are possible without departing from the scope of the present disclosure.

The invention claimed is:

1. A radio frequency (RF) switch comprising:
 a phase-change material (PCM) and a heating element underlying an active segment of said PCM and extending outward and transverse to said PCM;
 a first RF terminal comprising a first lower metal portion connected to a first upper metal portion;
 a MIM capacitor formed by said first upper metal portion, an insulator, and a patterned top plate;
 said first lower metal portion being ohmically connected to a first passive segment of said PCM;
 a second RF terminal comprising a second lower metal portion connected to a second upper metal portion;
 said second lower metal portion being ohmically connected to a second passive segment of said PCM.

2. The RF switch of claim 1, wherein said patterned top plate is situated within an interlayer dielectric.

3. The RF switch of claim 1, further comprising a first interconnect metal ohmically connected to said patterned top plate, and a second interconnect metal ohmically connected to said second upper metal portion.

4. A method for manufacturing a capacitive RF terminal and an ohmic RF terminal in a PCM RF switch, said method comprising:

forming a first lower metal portion for said capacitive RF terminal and a second lower metal portion for said ohmic RF terminal;

forming a metal layer on said first and second lower metal portions;

forming an insulator on said metal layer;

forming a top metal on said insulator,

etching said top metal so as to form a patterned top plate for said capacitive RF terminal;

etching said metal layer so as to form a first upper metal portion for said capacitive RF terminal and a second upper metal portion for said ohmic RF terminal, thereby forming a MIM capacitor by said first upper metal portion, said insulator, and said patterned top plate.

5. The method of claim 4, wherein said patterned top plate is situated within an interlayer dielectric.

6. The method of claim 4, further comprising forming a first interconnect metal ohmically connected to said patterned top plate, and a second interconnect metal ohmically connected to said second upper metal portion.

7. The method of claim 4, wherein said first lower metal portion is ohmically connected to a first passive segment of a PCM, and said second lower metal portion is ohmically connected to a second passive segment of said PCM.

8. The RF switch of claim 1, wherein said PCM is selected from the group consisting of germanium telluride (Ge_xTe_y),

germanium antimony telluride ($\text{Ge}_x\text{Sb}_y\text{Te}_z$), germanium selenide (Ge_xSe_y), and any other chalcogenide.

9. The RF switch of claim 1, wherein said heating element comprises material selected from the group consisting of tungsten (W), molybdenum (Mo), titanium (Ti), titanium nitride (TiN), titanium tungsten (TiW), tantalum (Ta), nickel chromium (NiCr), and nickel chromium silicon (NiCrSi).

10. The RF switch of claim 1, further comprising a thermally conductive and electrically insulating layer situated between said heating element and said PCM.

11. The RF switch of claim 10, wherein said thermally conductive and electrically insulating layer comprises material selected from the group consisting of aluminum nitride (AlN), aluminum oxide (Al_xO_y), beryllium oxide (Be_xO_y), silicon carbide (SiC), diamond, and diamond-like carbon.

12. The method of claim 7, wherein said PCM is selected from the group consisting of germanium telluride (Ge_xTe_y), germanium antimony telluride ($\text{Ge}_x\text{Sb}_y\text{Te}_z$), germanium selenide (Ge_xSe_y), and any other chalcogenide.

13. The method of claim 7, wherein said PCM RF switch comprises a heating element underlying an active segment of said PCM.

14. The method of claim 13, wherein said heating element comprises material selected from the group consisting of tungsten (W), molybdenum (Mo), titanium (Ti), titanium nitride (TiN), titanium tungsten (TiW), tantalum (Ta), nickel chromium (NiCr), and nickel chromium silicon (NiCrSi).

15. The method of claim 13, further comprising a thermally conductive and electrically insulating layer situated between said heating element and said PCM.

16. A radio frequency (RF) switch comprising:

a phase-change material (PCM) and a heating element underlying an active segment of said PCM;

a first RF terminal capacitively coupled to a first passive segment of said PCM, said first RF terminal comprising an MIM capacitor;

a second RF terminal ohmically connected to a second passive segment of said PCM;

wherein said capacitively coupled first RF terminal and said ohmically connected second RF terminal are both situated on a same side of said PCM.

17. The RF switch of claim 16, wherein said PCM is selected from the group consisting of germanium telluride (Ge_xTe_y), germanium antimony telluride ($\text{Ge}_x\text{Sb}_y\text{Te}_z$), germanium selenide (Ge_xSe_y), and any other chalcogenide.

18. The RF switch of claim 16, wherein said heating element comprises material selected from the group consisting of tungsten (W), molybdenum (Mo), titanium (Ti), titanium nitride (TiN), titanium tungsten (TiW), tantalum (Ta), nickel chromium (NiCr), and nickel chromium silicon (NiCrSi).

19. The RF switch of claim 16, further comprising a thermally conductive and electrically insulating layer situated between said heating element and said PCM.

20. The RF switch of claim 19, wherein said thermally conductive and electrically insulating layer comprises material selected from the group consisting of aluminum nitride (AlN), aluminum oxide (Al_xO_y), beryllium oxide (Be_xO_y), silicon carbide (SiC), diamond, and diamond-like carbon.