



(22) Date de dépôt/Filing Date: 2013/12/18

(41) Mise à la disp. pub./Open to Public Insp.: 2014/08/08

(45) Date de délivrance/Issue Date: 2016/11/29

(30) Priorité/Priority: 2013/02/08 (US13/762,763)

(51) Cl.Int./Int.Cl. *G01N 3/00* (2006.01),
G01N 3/02 (2006.01)


(72) Inventeurs/Inventors:
SWEET, WILLIAM J., US;
HOUSEN, KEVIN RICHARD, US;
BOSSI, RICHARD HENRY, US

(73) Propriétaire/Owner:
THE BOEING COMPANY, US

(74) Agent: SMART & BIGGAR

(54) Titre : SYSTÈME D'INSPECTION D'HYDROCHOC

(54) Title: HYDROSHOCK INSPECTION SYSTEM



(57) Abrégé/Abstract:

A method and apparatus for testing a test object. A stress wave is generated in a fluid within a cavity in a structure. The stress wave is directed through the fluid within the cavity into the test object.

ABSTRACT

A method and apparatus for testing a test object. A stress wave is generated in a fluid within a cavity in a structure. The stress wave is directed through the fluid within the cavity into the test object.

HYDROSHOCK INSPECTION SYSTEM

BACKGROUND INFORMATION

1. Field:

The present disclosure relates generally to testing objects and, in particular, to testing the strength of bonds and objects. Still more particularly, the present disclosure relates to a method and apparatus for testing the strength of bonds in a bonded structure using tension waves.

2. Background:

A composite object may be comprised of one or more composite structures that are bonded to each other. The composite object is often required to withstand loads that may be encountered during normal or even abnormal use of the composite object. As a result, identifying the strength of bonds in the composite object nondestructively may be required to assess that the composite object is capable of withstanding those forces.

Nondestructive testing or Non-destructive testing (NDT) is a wide group of analysis techniques used in science and industry to evaluate the properties of a material, component or system without causing damage. Because NDT does not permanently alter the article being inspected, it is a highly valuable technique that can save both money and time in product evaluation, troubleshooting and research.

Nondestructive testing of the composite object is more desirable. If the bonds in the composite object meet the desired standard, the composite object remains useable. Nondestructive evaluations are typically selected to fit specific bond material rather than general testing for all parameters. For example, laser bond inspection is a method currently used for nondestructive evaluations of bonds in composite objects. Laser bond inspection tests the strength of bonds between composite structures within a composite object. In this technique, weak bonds may be “pulled apart” by tension waves traveling through the structure. Existing bond inspection devices have multiple draw backs including the fact that they are expensive to construct and operate, and their large footprint makes it difficult to inspect bonds with certain shapes.

Further, inspecting bonds on composite objects such as installed parts on an aircraft may be more difficult than desired because of the size and limited reach of these types of laser bond inspection systems. For example, parts with narrow flanges or angles may preclude placement of the laser bond inspection head in a location to perform the inspection.

5 Therefore, it would be desirable to have a method and apparatus that takes into account at least some of the issues discussed above, as well as other possible issues.

SUMMARY

10 In some illustrative embodiments, a method is provided for testing a test object. The method involves generating, via a capacitor or a wire at a first end of a structure, a stress wave within a cavity in the structure, wherein a surface of the test object is coupled to a second end of the structure opposite the first end of the structure. The method further involves setting a number of properties for the stress wave in a fluid within the cavity based on a configuration of the cavity, wherein the number of properties include a depth within the test object from the surface of the test
15 object at which the stress wave is focused in the test object. The method further involves directing the stress wave through the cavity into the test object to the depth within the test object.

In some illustrative embodiments, an apparatus is provided that includes an energy source including a capacitor or a wire at a first end of a structure. The structure has a cavity, wherein the energy source is configured to generate a stress wave that travels through the cavity into a test
20 object having a surface coupled to a second end of the structure opposite the first end of the structure. The structure is configured to set a number of properties for the stress wave in a fluid within the cavity based on a configuration of the cavity in the structure. The number of properties includes a depth within the test object from the surface of the test object at which the stress wave is focused in the test object.

25 In some illustrative embodiments, an apparatus is provided that includes a structure having a cavity operable to hold a fluid, and a wire at a first end of the cavity. The wire is configured to explode when a current flows through the wire to generate a stress wave that travels through the fluid within the cavity into a test object having a surface coupled to a second end of the structure opposite the first end of the structure. The structure is configured to set a number of properties for
30 the stress wave in the fluid within the cavity based on a configuration of the cavity in the structure.

The number of properties includes a depth within the test object from the surface of the test object at which the stress wave is focused in the test object.

The features and functions can be achieved independently in various embodiments of the present disclosure or may be combined in yet other embodiments in which further details can be
5 seen with reference to the following description and drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

The novel features believed characteristic of the illustrative embodiments are set forth in the appended claims. The illustrative embodiments, however, as well as a preferred mode of use,
10 further objectives and features thereof, will best be understood by reference to the following detailed description of an illustrative embodiment of the present disclosure when read in conjunction with the accompanying drawings, wherein:

Figure 1 is an illustration of an inspection environment in accordance with an illustrative embodiment;

15 **Figure 2** is an illustration of a block diagram of an inspection environment in accordance with an illustrative embodiment;

Figure 3 is an illustration of a block diagram of an inspection unit in accordance with an illustrative embodiment;

Figure 4 is an illustration of a test setup in accordance with an illustrative embodiment;

Figure 5 is an illustration of a cross-sectional view of a portion of an inspection environment in accordance with an illustrative embodiment;

Figure 6 is an illustration of a wave generator in accordance with an illustrative embodiment;

Figure 7 is an illustration of a cross-sectional view of a portion of a wave generator in accordance with an illustrative embodiment;

Figure 8 is an illustration of a wave generator in accordance with an illustrative embodiment;

Figure 9 is an illustration of a cross-sectional view of a wave generator in accordance with an illustrative embodiment;

Figure 10 is an illustration of another cross-sectional view of a wave generator in accordance with an illustrative embodiment;

Figure 11 is an illustration of a flowchart of a process for inspecting a test object in accordance with an illustrative embodiment;

Figure 12 is an illustration of a flowchart of a process for testing a test object in accordance with an illustrative embodiment;

Figure 13 is an illustration of a discharge of energy in a wave generator in accordance with an illustrative embodiment;

Figure 14 is an illustration of a block diagram of an aircraft manufacturing and service method in accordance with an illustrative embodiment; and

Figure 15 is an illustration of a block diagram of an aircraft in which an illustrative embodiment may be implemented.

DETAILED DESCRIPTION

With laser bond inspection, a laser beam is directed at the front surface of a composite object. The laser beam creates mechanical waves in the form of stress waves

that travel through the composite object toward the back surface of the composite object. When the stress wave reaches a back surface of the object under test, the stress wave is reflected back from that surface producing a tension wave that propagates back toward the front surface of the object. The tension waves apply tension to the internal structure of the object, including any bond lines between the front and back surface of the object. The tension waves may have a sufficient strength that is selected to determine whether bonds between the parts of the object have a desired strength.

Laser bond inspection may be considered a nondestructive testing method when the bonds between composite structures are sufficiently strong. If a tension wave encounters a bond within the composite object that has the desired strength, the bond remains intact and inconsistencies are absent. The composite object may be examined to determine whether any inconsistencies are present in the composite object. If the bond is sufficiently strong, the composite object is not altered and may be used in different applications. This composite object also may be certified as providing a selected strength value.

If the tension wave encounters a bond within the composite object that does not have the desired strength, an inconsistency may occur. If an inconsistency is present, the composite object does not have the desired strength and may be discarded, reworked, or otherwise processed.

Illustrative embodiments recognize and take into account one or more different considerations. For example, those embodiments recognize and take into account that stress waves may be generated using mechanisms other than a laser beam directed towards a test object. For example, the illustrative embodiments recognize and take into account that a stress wave may be generated through a fluid that is coupled to the test object.

One or more of the illustrative embodiments may employ a hydroshock technique to generate a stress wave. In one illustrative example, a stress wave is generated in a fluid within a cavity of a structure. The stress wave is directed through the fluid and the cavity into a test object. In one illustrative example, the structure with the cavity may take the form of a tube or cylinder.

With reference now to the figures and in particular, with reference to **Figure 1**, an illustration of an inspection environment is depicted in accordance with an illustrative

embodiment. Inspection environment **100** is an example of one environment in which an illustrative embodiment may be implemented.

In this illustrative example, fuselage **102** and skin panel **104** are examples of composite objects. These composite objects may be comprised of composite structures that are bonded to each other. In these illustrative examples, an inspection of these bonds in fuselage **102** and skin panel **104** may be made in accordance with an illustrative embodiment.

In this illustrative example, inspection system **106** is configured to inspect the bonds in fuselage **102** and skin panel **104**. As depicted, inspection system **106** includes inspection unit **107**, inspection unit **108**, inspection unit **110**, and computer **112**.

In this illustrative example, inspection unit **107** is a portable inspection unit operated by operator **114**. Operator **114** may place inspection unit **107** at a location on skin panel **104**. Operator **114** may then move a distance away from inspection unit **107**. This distance may be a distance that has been determined to be safe during operation of inspection unit **107**. Inspection unit **107** may then operate to perform inspection of bonds within skin panel **104**.

After the inspection of the bonds within skin panel **104** has taken place at the location that inspection unit **107** was placed by operator **114**, operator **114** may return to inspection unit **107** and move inspection unit **107** to another location on skin panel **104**.

In other illustrative examples, operator **114** may remain at the location or may hold inspection unit **107** during inspection of the bonds within skin panel **104** depending on the amount of energy generated by inspection unit **107** and the design of inspection unit **107**. A more detailed illustration of inspection unit **107** in section **115** is found in the description of **Figure 4** below.

Inspection unit **108** takes the form of an end effector for robotic arm **116**. Robotic arm **116** may move inspection unit **108** along fuselage **102** to perform inspections of bonds within fuselage **102**.

As depicted, inspection unit **110** takes the form of a crawler. Inspection unit **110** may move on fuselage **102** to perform inspections of bonds within fuselage **102**.

Information generated by inspection unit **107**, inspection unit **108**, and inspection unit **110** are sent to computer **112**. Initially, computer **112** may send commands to inspection unit **107**, inspection unit **108**, and inspection unit **110** to control the operation of these inspection units. The information and commands are sent over communications link **118**, communications link **120**, and communications link **122** in this illustrative example. As depicted, communications link **118** is a wired communications link. Communications link **120** and communications link **122** are wireless communications links.

The illustration of inspection environment **100** is only provided as an example of one type of environment in which an illustrative embodiment may be used to test bonds. One or more illustrative embodiments may be implemented in inspection environment **100** to inspect other types of objects other than aircraft parts. For example, the illustrative embodiments may be applied to testing bonds in a test object that may be selected from one of parts for an automobile, a building, a completed aircraft, a part installed on an aircraft, and other suitable types of objects that may contain bonds for which testing is desirable.

Turning next to **Figure 2**, an illustration of a block diagram of an inspection environment is depicted in accordance with an illustrative embodiment. Inspection environment **100** in **Figure 1** is an example of one implementation for inspection environment **200** shown in block form in **Figure 2**.

As depicted, inspection environment **200** includes inspection system **202**. Inspection system **202** is configured to test test object **204**. In particular, inspection system **202** is configured to test bond **206** in test object **204**.

In this illustrative example, bond **206** is present where first structure **208** and second structure **210** are bonded to each other at bond line **212**. Bond line **212** may be planar, nonplanar, or some combination thereof depending on the particular implementation.

In these illustrative examples, first structure **208** and second structure **210** may be bonded to each other in a number of different ways. For example, first structure **208** and second structure **210** may be bonded to each other using an adhesive.

Test object **204** may be comprised of any type of material. As depicted, test object **204** is composite object **214** in this illustrative example. Further, first structure **208** is first composite structure **216**, and second structure **210** is second composite structure **218**.

In this illustrative example, inspection system **202** includes computer system **220**, display system **224**, and group of inspection units **226**. As used herein, a “group of,” when used with reference items, means one or more items. For example, group of inspection units **226** is one or more inspection units.

Computer system **220** is configured to control the operation of group of inspection units **226**. Computer system **220** is one or more computers. When more than one computer is present in computer system **220**, those computers may communicate with each other using a communications medium such as a network.

In this illustrative example, stress wave **228** is generated by inspection unit **230** in group of inspection units **226** and directed into test object **204**. In the illustrative example, stress wave **228** is a wave that has a compressive component. Additionally, stress wave **228** also may have a tensile component at the tail or end of the wave.

Inspection unit **230** is a hardware system in these illustrative examples. In the illustrative examples, stress wave **228** generates a force on test object **204**.

Tension wave **232** is generated either as a part of stress wave **228** or when the compressive component of stress wave **228** encounters a boundary in test object **204**. This boundary may be, for example, the back wall of the test object **204** or some other suitable interface that may be within test object **204**. Tension wave **232** generates a force that applies tension to the internal structure of test object **204**. For example, tension wave **232** may pull at least one of first structure **208** and second structure **210** away from each other at bond line **212**. Tension wave **232** may result in a load that is applied to bond **206**. In the illustrative example, this load may be localized. The load may be considered to be localized when the load is applied to a specific area of the test object. In other words, the load maybe applied to an area rather than spread out throughout the test object.

As depicted, inspection unit **230** is also configured to measure at least one of stress wave **228** and tension wave **232** in test object **204**. As used herein, the phrase “at least one of,” when used with a list of items, means different combinations of one or more of the listed items may be used and only one of each item in the list may be needed. For example, “at least one of item A, item B, or item C” may include, without limitation, item A or item A and item B. This example also may include item A, item B, and item C or item B and

item C. In other examples, “at least one of” may be, for example, without limitation, two of item A, one of item B, and ten of item C; four of item B and seven of item C; and other suitable combinations. The item may be a particular object, thing, or a category. In other words, at least one of means any combination items and number of items may be used from the list but not all of the items in the list are required.

After stress wave **228** has been directed into test object **204** and tension wave **232** has traveled through test object **204**, inspection unit **230** may make measurements **236** of test object **204**. Inspection unit **230** may measure at least one of wave energy, front surface displacement or velocity, back-surface displacement or velocity, ultrasonic transmission, ultrasonic attenuation, and other suitable properties with respect to test object **204**.

Inspection unit **230** may send measurements **236** made of test object **204** after stress wave **228** and tension wave **232** have traveled through test object **204** to computer system **220** for storage. As depicted, computer system **220** may store at least one of information **238** and measurements **236**. In other illustrative examples, inspection unit **230** may store information **238**, measurements **236**, or both.

Display system **224** is a hardware system and may include one or more display devices. Display system **224** may be connected to computer system **220**, inspection unit **230**, or both of these systems. Display system **224** is configured to display information **238**. Information **238** is based on measurements **236** of test object **204**. In these illustrative examples, display system **224** may be, for example, selected from one of an oscilloscope, a tablet computer, a notebook computer, and a workstation.

With reference next to **Figure 3**, an illustration of an inspection unit is depicted in accordance with an illustrative embodiment. In this depicted example, an example of components that may be found in inspection unit **230** in **Figure 2** is shown.

In this illustrative example, inspection unit **230** comprises a number of different components. In this depicted example, inspection unit **230** includes wave generator **314** and measurement system **312**.

In this illustrative example, wave generator **314** in inspection unit **230** includes a number of different components. For example, wave generator in inspection unit **230** includes structure **300**, cavity **302**, and energy source **304**.

Structure **300** may be any structure in which cavity **302** is configured to hold fluid **306** within cavity **302**. Structure **300** may be comprised of any suitable material. For example, structure **300** may be comprised of a metal, plastic, titanium, steel, aluminum, polycarbonate, and other suitable materials.

In the illustrative example, structure **300** with cavity **302** has configuration **308**. As depicted, cavity **302** is configured to direct stress wave **228** through fluid **306** in cavity **302** into test object **204** in **Figure 2**. Fluid **306** may take various forms. For example, fluid **306** may be water, oil, and other suitable types of fluids.

Additionally, configuration **308** is selected to set number of properties **310** for stress wave **228**. Number of properties **310** for stress wave **228** is set as stress wave **228** travels through cavity **302** into test object **204**. As used herein, “a number of,” when used with reference to items, means one or more items. For example, number of properties **310** is one or more properties. In the illustrative example, number of properties **310** is selected from at least one of a magnitude of stress wave **228**, duration of stress wave **228**, a rise time for stress wave **228**, and the depth at which stress wave **228** is focused in the test object.

Measurement system **312** is a hardware system and is configured to measure at least one of stress wave **228** and tension wave **232** in test object **204** in **Figure 2**. Measurement system **312** may take various forms. For example, measurement system **312** may be selected from at least one of a laser interferometer, a transducer system, and other suitable types of systems that may measure at least one of stress wave **228** and tension wave **232** while those waves travel within test object **204** in **Figure 2**. The measurements may be surface displacements, surface velocities or internal material changes.

As depicted, wave generator **314** and measurement system **312** may be associated with platform **318**. Platform **318** may take various forms such as a housing, a frame, an end effector, a crawler, or some other suitable type of platform. Of course, in some illustrative examples, wave generator **314** and measurement system **312** may be separate components.

The illustration of inspection environment **200** and the different components in **Figures 2-3** are not meant to imply physical or architectural limitations to the manner in which an illustrative embodiment may be implemented. Other components in addition to or in place of the ones illustrated may be used. Some components may be unnecessary. Also,

the blocks are presented to illustrate some functional components. One or more of these blocks may be combined, divided, or combined and divided into different blocks when implemented in an illustrative embodiment.

For example, although only bond **206** is illustrated in the example in inspection environment **200** in **Figure 2**, one or more additional bonds may be present in addition to or in place of bond **206**. Further, test object **204** also may include one or more additional structures in addition to first structure **208** and second structure **210**. These additional structures may or may not be composite structures depending on the particular implementation.

As another illustrative example, in some illustrative examples, measurement system **312** may be a separate component outside of inspection unit **230**. In still other illustrative examples, the controller or processor also may be part of inspection unit **230**. In yet another illustrative example, display system **224** may be included as part of inspection unit **230** in **Figure 2**.

Turning now to **Figure 4**, an illustration of a test setup is depicted in accordance with an illustrative embodiment. In this depicted example, a more detailed illustration of inspection unit **107** operated by operator **114** from **Figure 1** is shown.

Also depicted in this view, inspection unit **107** includes a number of different components. For example, in inspection environment **400**, inspection unit **107** includes frame **401**, wave generator **402**, and measurement unit **404**.

As depicted, frame **401** is an example of one implementation for platform **318** shown in block form in **Figure 3**. Frame **401** is a portable frame. Frame **401** may be moved from location to location by operator **114** to inspect skin panel **104**.

Wave generator **402** and measurement unit **404** are associated with frame **401**. When one component is “associated” with another component, the association is a physical association in the depicted examples. For example, a first component, wave generator **402**, may be considered to be associated with a second component, frame **401**, by being secured to the second component, bonded to the second component, mounted to the second component, welded to the second component, fastened to the second component, and/or connected to the second component in some other suitable manner. The first component

also may be connected to the second component using a third component. The first component may also be considered to be associated with the second component by being formed as part of and/or an extension of the second component.

In this view, tube **406** and energy source **408** are shown. As depicted, tube **406** has a shape of a frustrum. Tube **406** is an example of a physical implementation for structure **300** shown in block form in **Figure 3**. Additionally, tube **406** has first end **410** and second end **412**.

Energy source **408** is configured to generate a stress wave. Energy source **408** is associated with first end **410**. Second end **412** is configured to be placed on surface **414** of skin panel **104** in this illustrative example.

As depicted, measurement unit **404** is hardware and is configured to make measurements of waves within skin panel **104** that are generated by wave generator **402**. Measurement unit **404** is an example of a physical implementation of measurement system **312** shown in block form in **Figure 3**. In this illustrative example, measurement unit **404** takes the form of a laser interferometer **416**.

As can be seen in this view, skin panel **104** is comprised of first composite structure **418** and second composite structure **420**. These two composite structures are bonded to each other at bond line **422** in this illustrative example. Inspection unit **107** is used to test the bond between first composite structure **418** and second composite structure **420**.

With reference now to **Figure 5**, an illustration of a cross-sectional view of a portion of an inspection environment is depicted in accordance with an illustrative embodiment. In this illustrative example, a cross-sectional view of some components in inspection environment **400** in **Figure 4** is seen taken along lines **5-5**.

In this cross-sectional view, cavity **500** of tube **406** is shown. Cavity **500** is an example of a physical implementation for cavity **302** shown in block form in **Figure 3**. As can be seen, fluid **502** is present in cavity **500**. In this example, fluid **502** takes the form of water. Of course, other types of fluids may be used depending on the particular implementation.

As depicted, plug **503** is associated with second end **412**. Plug **503** is a structure that is configured to hold fluid **502** within cavity **500** when second end **412** of tube **406** is

placed against surface **414** of skin panel **104**. In these illustrative examples, plug **503** may take various forms. As depicted, plug **503** seals second end **412**. In other illustrative examples, plug **503** may be a gasket that generates a seal when second end **412** is placed against surface **414** of skin panel **104**.

In this illustrative example, energy source **408** is a hardware device and is configured to generate stress wave **506**. In these illustrative examples, energy source **408** may generate energy in the form of an explosion or shockwave for a duration that is short enough to cause stress wave **506**. In this illustrative example, energy source **408** includes capacitor **504**. As depicted, capacitor **504** is in contact with fluid **502**.

When capacitor **504** is discharged, the energy from the discharge results in the generation of stress wave **506**. Stress wave **506** travels through fluid **502** within cavity **500** into the test object, which is skin panel **104** in this illustrative example. When plug **503** seals cavity **500**, plug **503** also may function as a coupler for stress wave **506**. When plug **503** performs this function, the selection of materials for plug **503** may be selected to have an acoustic impedance close to tube **406**. In other words, the selection of the material and shape of plug **503** may be selected to reduce reflection of stress wave **506**.

In this illustrative example, stress wave **506** travels through skin panel **104** until stress wave **506** reaches a feature. In this illustrative example, the feature is back surface **508**. At back surface **508**, tension wave **510** occurs during reflection of stress wave **506**. Tension wave **510** subjects bond **421** at bond line **422** to tensile stress in this illustrative example. In other words, tension wave **510** causes tension that pulls first composite structure **418** and second composite structure **420** away from each other.

In this illustrative example, the configuration of tube **406** with cavity **500** is selected to set properties for stress wave **506**. For example, the shape of tube **406** may be designed to focus the wave at a desired depth within skin panel **104**, such as at the depth where bond **421** is located. This wave may be at least one of a stress wave or a tensile wave. This focusing of the wave may optimize the inspection method by maximizing the stress at the location of interest, reducing the likelihood of unintended occurrences of undesired inconsistencies to the test object in regions away from the bond to be inspected.

In this illustrative example, wave generator **402** has height **513**. Wave generator **402** has width **514** at first end **410** and width **516** at second end **412**. As depicted, height **513** may be about several centimeters, width **514** may be about a few centimeters, and width **516** may be about 1 centimeter. Of course these dimensions may vary depending on the particular implementation. The dimension selected may vary depending on the particular implementation. In these illustrative examples, dimensions may be selected such that wave generator **402** may be easily positioned on different parts to provide a desired inspection of bonds in those parts.

Turning now to **Figure 6**, an illustration of a wave generator is depicted in accordance with an illustrative embodiment. As depicted, wave generator **600** is another example of an implementation for wave generator **314** shown in block form in **Figure 3**. Wave generator **600** comprises structure **602** having a cylindrical shape rather than a tube as depicted for wave generator **402** in **Figure 4**.

In this illustrative example, cavity **604** can be seen in phantom within structure **602**. As can be seen in this example, cavity **604** has an egg shape. This configuration of structure **602** is another example of another physical implementation for cavity **302** shown in block form in **Figure 3**.

Wire **606** extends through structure **602** into cavity **604**. Wire **606** is connected to wire **608** and wire **610**. Wire **608** and wire **610** are thicker than wire **606**. Wire **606** is an example of an implementation for energy source **304** shown in block form in **Figure 3**. Wire **606** is an exploding bridge wire which explodes when a current flows through wire **606**. This explosion is configured to generate a stress wave in a fluid within cavity **604**.

Also shown in phantom is gasket **612**. Gasket **612** is configured to seal cavity **604** at end **614** of cavity **604**.

As depicted, structure **602** has height **616** and diameter **618**. Height **616** may be about 3.7 centimeters, and diameter **618** may be about 7 centimeters in this illustrative example.

With reference now to **Figure 7**, an illustration of a cross-sectional view of a portion of wave generator **600** is depicted in accordance with an illustrative embodiment. A larger

view of cavity **604**, wire **606**, and gasket **612** can be seen. In particular, end **614** of cavity **604** has diameter **700**. Diameter **700** is about 1 centimeter in this illustrative example.

Turning now to **Figure 8**, an illustration of a wave generator is depicted in accordance with an illustrative embodiment. In this illustrative example, wave generator **800** is another example of a physical implementation for wave generator **314** shown in block form in **Figure 3**.

In this illustrative example, wave generator **800** has structure **801**. Structure **801** has a cuboid shape. In this particular example, structure **801** has height **802**, depth **804**, and width **806**. In this illustrative example, height **802** is about 1 centimeter, depth **804** is about 2 centimeters, and width **806** is about 2 centimeters. Of course, the values for these dimensions are only examples of one set of dimensions for height **802**, depth **804**, and width **806**. Other values for these dimensions may be used in other illustrative implementations.

Turning next to **Figure 9**, an illustration of a cross-sectional view of a wave generator is depicted in accordance with an illustrative embodiment. In this illustrative example, a cross-sectional view of structure **801** is shown taken along lines **9-9** in **Figure 8**.

In this illustrative example, cavity **900** has a conical shape. Energy source **902** takes the form of wire **904**. Wire **904** is configured to explode when a current is applied to wire **904**. This explosion is configured to generate a stress wave in a fluid within cavity **900**.

With reference now to **Figure 10**, an illustration of another cross-sectional view of a wave generator is depicted in accordance with an illustrative embodiment. In this illustrative example, an alternate cross-sectional view of structure **801** is shown taken along lines **10-10**.

In this cross-sectional view, cavity **1000** has a hemispherical shape. Energy source **1001** is wire **1002** in this example.

The different components shown in **Figures 1** and **Figures 4-10** may be combined with components in **Figures 2-3**, used with components in **Figures 2-3**, or a combination of the two. Additionally, some of the components in **Figures 1** and **Figures 4-10** may be

illustrative examples of how components shown in block form in **Figures 2-3** can be implemented as physical structures.

Turning next to **Figure 11**, an illustration of a flowchart of a process for inspecting a test object is depicted in accordance with an illustrative embodiment. The process illustrated in **Figure 11** may be implemented in inspection environment **200** in **Figure 2**. In particular, the process may be implemented to inspect test object **204** using inspection unit **230**.

The process begins by placing the inspection unit on a surface of the test object (operation **1100**). The process then generates a stress wave in a fluid within a cavity of a structure (operation **1102**). The process then directs the stress wave through the fluid and the cavity into the test object (operation **1104**). A number of properties for the stress wave in the fluid is set based on the configuration of the cavity in the structure. These properties are set as the stress wave travels through the fluid in the cavity. As a result, the stress wave causes a tension wave that encounters a bond in the test object. In the illustrative example, the tension wave that encounters the test object may be the tension wave caused by the stress wave reflecting from an interface such as a back wall. Further, in some illustrative examples, the tension wave also may be a component of the stress wave that encounters the bond as the stress wave travels towards the interface.

Measurements are made of the test object (operation **1106**). In operation **1106**, the measurements may be performed using any device configured to detect inconsistencies that may occur from the bond carrying the load caused by the tensile forces that may be applied by the tension wave. In one illustrative example, a laser interferometer is used to determine whether inconsistencies present after the stress wave travels through the test object and causes a tension wave to apply a load on the bond. Information based on measuring the test object is displayed (operation **1108**). The process also stores at least one of the information and the measurements (operation **1110**), with the process terminating thereafter.

These operations may be used to determine whether the bond in the test object can withstand loads within a desired amount or range. These different operations may be repeated any number of times. The operations may be repeated for different locations on a particular test object or on different test objects.

With reference now to **Figure 12**, an illustration of a flowchart of a process for testing a test object is depicted in accordance with an illustrative embodiment. This process may be implemented after a tension wave has been sent through a test object. The process illustrated in **Figure 12** may be implemented using inspection system **202** in **Figure 2**.

The process begins by sending a number of signals into the test object (operation **1200**). These signals may be sent using an ultrasonic transducer.

The process then detects response signals (operation **1202**). A determination is then made as to whether the response signals indicate that an inconsistency is present in the test object (operation **1204**). If an inconsistency is present, an indication is generated that the test object failed the test (operation **1206**), with the process terminating thereafter.

With reference again to operation **1204**, if an inconsistency is not present, the process generates an indication that the test object has passed the test (operation **1208**), with the process terminating thereafter. In this case, the bond in the test object has held up to the forces generated on the bond by the tension waves. As a result, this test object may be certified as withstanding the force selected for testing.

The flowcharts and block diagrams in the different depicted embodiments illustrate the architecture, functionality, and operation of some possible implementations of apparatuses and methods in an illustrative embodiment. In this regard, each block in the flowcharts or block diagrams may represent a module, a segment, a function, and/or a portion of an operation or step. For example, one or more of the blocks may be implemented as program code, in hardware, or a combination of the program code and hardware. When implemented in hardware, the hardware may, for example, take the form of integrated circuits that are manufactured or configured to perform one or more operations in the flowcharts or block diagrams. When implemented as a combination of program code and hardware, the implementation may take the form of firmware.

In some alternative implementations of an illustrative embodiment, the function or functions noted in the blocks may occur out of the order noted in the figures. For example, in some cases, two blocks shown in succession may be executed substantially concurrently, or the blocks may sometimes be performed in the reverse order, depending upon the

functionality involved. Also, other blocks may be added in addition to the illustrated blocks in a flowchart or block diagram.

For example, operation **1108** and operation **1110** are optional operations and may be omitted. Further, in other illustrative examples, an alert may be generated if a determination is made from the measurement of the different waves that the bond does not have a desired strength. Additionally, other types of measurement systems may be used depending on the particular implementation.

Turning now to **Figure 13**, an illustration of a discharge of energy in a wave generator is depicted in accordance with an illustrative embodiment. In this illustrative example, graph **1300** illustrates shape **1302** of a stress wave that is discharged into fluid **1304**. This stress is shown at a time of about 3.05×10^{-006} seconds after energy discharge.

Graph **1306** shows the stress in Gdyn/cm². In this illustrative example, 1 Gdyn/cm² is a measure of stress equivalent to 1 kilobar, or 1000 atm. As can be seen, the stress wave generated may be focused at a specific depth in a test object based on the configuration of the cavity. By varying the shape of the cavity, the focal point of the stress wave may be changed. This focal point may be at different locations such as at an interface, a back wall of an object, the bond line, or some other location depending on the particular implementation. The depth of the focal point may be selected to provide a desired testing of the bond line.

Illustrative embodiments of the disclosure may be described in the context of aircraft manufacturing and service method **1400** as shown in **Figure 14** and aircraft **1500** as shown in **Figure 15**. Turning first to **Figure 14**, an illustration of a block diagram of an aircraft manufacturing and service method is depicted in accordance with an illustrative embodiment. During pre-production, aircraft manufacturing and service method **1400** may include specification and design **1402** of aircraft **1500** in **Figure 15** and material procurement **1404**.

During production, component and subassembly manufacturing **1406** and system integration **1408** of aircraft **1500** in **Figure 15** takes place. Thereafter, aircraft **1500** in **Figure 15** may go through certification and delivery **1410** in order to be placed in service **1412**. While in service **1412** by a customer, aircraft **1500** in **Figure 15** is scheduled for

routine maintenance and service **1414**, which may include modification, reconfiguration, refurbishment, and other maintenance or service.

Each of the processes of aircraft manufacturing and service method **1400** may be performed or carried out by a system integrator, a third party, and/or an operator. In these examples, the operator may be a customer. For the purposes of this description, a system integrator may include, without limitation, any number of aircraft manufacturers and major-system subcontractors; a third party may include, without limitation, any number of vendors, subcontractors, and suppliers; and an operator may be an airline, a leasing company, a military entity, a service organization, and so on.

With reference now to **Figure 15**, an illustration of a block diagram of an aircraft is depicted in which an illustrative embodiment may be implemented. In this example, aircraft **1500** is produced by aircraft manufacturing and service method **1400** in **Figure 14** and may include airframe **1502** with systems **1504** and interior **1506**. Examples of systems **1504** include one or more of propulsion system **1508**, electrical system **1510**, hydraulic system **1512**, and environmental system **1514**. Any number of other systems may be included. Although an aerospace example is shown, different illustrative embodiments may be applied to other industries, such as the automotive industry.

Apparatuses and methods embodied herein may be employed during at least one of the stages of aircraft manufacturing and service method **1400** in **Figure 14**.

For example, the illustrative embodiments may be implemented to inspect the bonds in test objects such as aircraft parts during component and subassembly manufacturing **1406**. Further, different parts may be tested using an illustrative embodiment after or during installation of those parts as part of system integration **1408**. Further tests of parts may be made during certification and delivery **1410**. As another illustrative example, parts may be tested during maintenance and service **1414**. This testing may be performed on parts that may be inspected during maintenance and service **1414**. Further, parts may be tested using an illustrative embodiment for use in maintenance, upgrades, refurbishment, or other operations performed during maintenance and service **1414**.

Thus, the illustrative embodiments provide a method and apparatus for testing bonds in objects. In these illustrative examples, the wave generator may have a size that is smaller

than currently used in inspection systems such as laser bond inspection systems. The size of the wave generator in these illustrative examples may allow for testing of parts that have configurations or shapes that are more difficult for inspection with laser bond inspection systems. Further, the size of the wave generator in these illustrative examples may allow for inspections of objects, such as parts that have been installed in a structure such as an aircraft, a train, a building, a manufacturing facility, or some other type of structure.

The illustrative embodiments allow for the stress wave to have a number of properties such as magnitude of the stress wave, duration of the stress wave, a rise time for the stress wave, a focal point, and other suitable properties that may be set based on the configuration of the wave generator. In this manner, the different illustrative embodiments provide that wave generators may be used to test various bond strengths for bonds that may be in different locations in a test object.

The description of the different illustrative embodiments has been presented for purposes of illustration and description and is not intended to be exhaustive or limited to the embodiments in the form disclosed. Many modifications and variations will be apparent to those of ordinary skill in the art. Further, different illustrative embodiments may provide different features as compared to other illustrative embodiments. The embodiment or embodiments selected are chosen and described in order to best explain the principles of the embodiments, the practical application, and to enable others of ordinary skill in the art to understand the disclosure for various embodiments with various modifications as are suited to the particular use contemplated.

THE EMBODIMENTS OF THE INVENTION IN WHICH AN EXCLUSIVE PROPERTY OR PRIVILEGE IS CLAIMED ARE DEFINED AS FOLLOWS:

1. A method for testing a test object, the method comprising:

5

generating, via a capacitor or a wire at a first end of a structure, a stress wave within a cavity in the structure, wherein a surface of the test object is coupled to a second end of the structure opposite the first end of the structure;

10

setting a number of properties for the stress wave in a fluid within the cavity based on a configuration of the cavity, wherein the number of properties comprise a depth within the test object from the surface of the test object at which the stress wave is focused in the test object; and

15

directing the stress wave through the cavity into the test object to the depth within the test object.

2. The method of claim 1, wherein the wire is an exploding bridge configured to explode when a current flows through the wire.

20

3. The method of claim 1, wherein the cavity has a cross-sectional shape of a cone.

4. The method of any one of claims 1 to 3, wherein the number of properties further comprises a magnitude of the stress wave, a duration of the stress wave, or a rise time for the stress wave.

25

5. The method of any one of claims 1 to 4, wherein the directing step comprises:

30

directing the stress wave through a fluid within the cavity into the test object, wherein a tension wave occurs and encounters a bond in the test object.

6. The method of claim 5 further comprising:

measuring the test object.

7. The method of claim 6 further comprising:

5

displaying information based on measurements of the test object.

8. The method of claim 6 further comprising:

10

storing at least one of information or measurements of the test object.

9. The method of any one of claims 1 to 8, wherein the structure is a tube having the first end and the second end.

15 10. The method of any one of claims 1 to 9, wherein the cavity is filled with the fluid, and the stress wave is generated by a hydroshock technique.

11. An apparatus comprising:

20

an energy source comprising a capacitor or a wire at a first end of a structure; and

25

the structure having a cavity, wherein the energy source is configured to generate a stress wave that travels through the cavity into a test object having a surface coupled to a second end of the structure opposite the first end of the structure, wherein the structure is configured to set a number of properties for the stress wave in a fluid within the cavity based on a configuration of the cavity in the structure, and wherein the number of properties comprises a depth within the test object from the surface of the test object at which the stress wave is focused in the test object.

30 12. The apparatus of claim 11, wherein the number of properties further comprises a magnitude of the stress wave, a duration of the stress wave, or a rise time for the stress wave.

13. The apparatus of claim 11, wherein the structure is configured to direct the stress wave through the fluid within the cavity into the test object such that a tension wave occurs and encounters a bond in the test object.
- 5 14. The apparatus of claim 11 further comprising:

a measurement system configured to measure the test object.
- 10 15. The apparatus of claim 14, wherein the measurement system comprises:

a laser interferometer.
- 15 16. The apparatus of claim 14, wherein the measurement system is configured to store at least one of information or measurements of the test object.
17. The apparatus of claim 14 further comprising:

a display system configured to display information about the test object measured by the measurement system.
- 20 18. The apparatus of claim 17, wherein the display system is selected from one of an oscilloscope, a tablet computer, a notebook computer, or a workstation.
- 25 19. The apparatus of any one of claims 11 to 18, wherein the structure comprises:

a tube having the first end and the second end.
- 30 20. The apparatus of claim 19 further comprising:

a plug configured to be associated with the second end and to hold the fluid within the cavity.


21. An apparatus comprising:

a structure having a cavity operable to hold a fluid; and

5 a wire at a first end of the cavity;

wherein the wire is configured to explode when a current flows through the wire to generate a stress wave that travels through the fluid within the cavity into a test object having a surface coupled to a second end of the structure opposite the first end of the structure,
10 wherein the structure is configured to set a number of properties for the stress wave in the fluid within the cavity based on a configuration of the cavity in the structure, and wherein the number of properties comprises a depth within the test object from the surface of the test object at which the stress wave is focused in the test object.

15 **22.** The apparatus of any one of claims **11** to **21** wherein the cavity has a frustum shape.



2/11




FIG. 2

3/11




FIG. 3

4/11




FIG. 4




FIG. 5

6/11






FIG. 6



8/11




FIG. 9




FIG. 10




FIG. 12




FIG. 11

10/11




FIG. 13

11/11




FIG. 14




FIG. 15

