




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B05D 1/34, G03C 1/74, B05C 5/00		A1	(11) International Publication Number: WO 98/31472 (43) International Publication Date: 23 July 1998 (23.07.98)
(21) International Application Number: PCT/US97/19807	(22) International Filing Date: 30 October 1997 (30.10.97)	(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).	
(30) Priority Data: 08/784,672 21 January 1997 (21.01.97) US			
(71) Applicant: MINNESOTA MINING AND MANUFACTURING COMPANY [US/US]; 3M Center, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).			
(72) Inventors: JERRY, Glen, A.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). YAPEL, Robert, A.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). BHAVE, Aparna, V.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). WALLACE, Lawrence, B.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US).			
(74) Agents: HORNICKEL, John, H.; Minnesota Mining and Manufacturing Company, Office of Intellectual Property Counsel, P.O. Box 33427, Saint Paul, MN 55133-3427 (US) et al.			

(54) Title: METHOD FOR MINIMIZING WASTE WHEN COATING A FLUID WITH A SLIDE COATER



(57) Abstract

A method for minimizing waste resulting from defects caused at the edges of a coating on a substrate which was applied to the substrate (18) by a slide coater (34). A first fluid (55) flows through the first slot (46) main portion at a first flow rate and through the first slot end portions at flow rates which differ from the first flow rate. A second fluid (60) flows through a second slot (48) onto a second slide surface (53) positioned relative to the first slide surface (53) and oriented such that the second coating fluid flows from the second slide surface onto the first coating fluid.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

METHOD FOR MINIMIZING WASTE WHEN COATING A FLUID WITH A SLIDE COATER

5

Field of the Invention

The present invention relates to a method for minimizing waste when coating a fluid with a slide coater to create, for example, a photothermographic, thermographic, or photographic element, or a data storage element (e.g., a magnetic computer tape and floppy or rigid disks or diskettes, and the like).

Background of the Art

A construction of a known photothermographic dry silver film or paper product 10 is shown in Figure 1. This construction can be created by coating a plurality of layers onto a substrate. One of the layers is a photothermographic emulsion layer 14 made up of a photosensitized silver soap in a binder resin which can include toners, developers, sensitizers and stabilizers. To improve adhesion of the photothermographic emulsion layer 14 to the substrate, a primer layer 16 can be positioned between them. A topcoat layer 12 can be positioned above the photothermographic emulsion layer 14 and can be made up of a mar-resistant hard resin with toners and slip agents. The substrate 18 can be a paper-based substrate or a polymeric film-based substrate. An antihalation layer 20 can be applied to the surface of the substrate 18 opposite the surface on which to the primer, photothermographic emulsion, and topcoat layers 16, 14, 12 can be positioned. The compositions of layers 16, 14 and 12 are chosen for product performance reasons, and components comprising adjacent coating layers could be incompatible.

It is desirable to determine how to coat the fluids that form (i.e., the precursors) for the primer, photothermographic, and topcoat layers 16, 14, 12, respectively, using a simultaneous multilayer coating method. Slide coating is described in U.S. Patent No. 2,761,419 (Mercier et al., 5 1956) and elsewhere (see E. D. Cohen and E. B. Gutoff, *Modern Coating and Drying Technology*, VCH Publishers, 1992) and is a method for multilayer coating, i.e. it involves coating a plurality of fluid layers onto a substrate. The different fluids comprising the multiple layer precursors flow out of multiple slots that open out onto an inclined plane. The fluids 10 flow down the plane, across the coating gap and onto an upward moving substrate. It is claimed that the fluids do not mix on the plane, across the coating gap, or on the web, so that the final coating is composed of distinct superposed layers. A number of developments have been reported in this area regarding the use of slot steps, chamfers, and have 15 been described in literature (see E. D. Cohen and E. B. Gutoff, *op. cit.*).

The application of multilayer slide coating as described in the above references to the coating of a product such as is described in Figure 1, that involves coating layers comprising incompatible solutes in miscible solvents, can lead to a problem of "strikethrough" that is described 20 herewith. Incompatible solutes are solutes that do not mix in some or all concentration ranges, whereas miscible solvents are solvents that mix in any proportion.

Occasionally during coating, a disturbance causes one of the coating layers above the bottom-most coating layer to penetrate through 25 the bottom-most coating layer to the slide surface. When the solute of the coating layer(s) above the bottom-most coating layer is sufficiently incompatible with the solute of the bottom-most layer, the penetrating coating layer attaches to slide surface 53 and is not quickly self-cleaned by the bottom-most coating layer. This phenomenon is referred to as

strikethrough. (The term "self-clean" means the process which occurs when the flow of the bottom-most coating layer (or the bottom-most coating layer and one or more adjacent coating fluid layers) cleans off the penetrant coating fluid layer that sticks to the slide surface.)

5 When strikethrough occurs, the flow of the coating fluid down the slide surface 53 is disturbed which can lead to streaking defects in the coated product. Streaking defects can, in turn, reduce product quality to the point where the final product is outside specifications and cannot be used.

10 Another problem encountered during multilayer slide coating of product constructions involving different solvents in different layers is that the interdiffusion of solvents between these layers can cause phase separation of one or more solutes within one or more layers. This phase separation can result in the inability to coat such a construction using a
15 multi-layer coating technique due to formation of defects such as streaks or fish-eyes, or due to a disruption of flow and the intermixing of separate fluid layers.

Traditional slide coating is restricted to coating solutions that are relatively low in viscosity. The use of a "carrier layer" in slide coating
20 was first described by U.S. Patent No. 4,001,024 (Dittman and Rozzi, 1977), where the authors claimed an improvement over previously described method of slide coating "by coating the lowermost layer as a thin layer formed from a low viscosity composition and coating the layer above the lowermost layer as a thicker layer of higher viscosity."
25 Furthermore, the authors state that due to the "vortical action of the coating bead [that] is confined within the two bottom layers" intermixing occurs between the two bottom layers and the coating compositions of these two layers must be chosen such that "the interlayer mixing is not

harmful to the product." However, this patent does not address strikethrough or phase separation.

U.S. Patent No. 4,113,903 (Choinski, 1978) teaches that a low viscosity carrier layer tends to be unstable "in the bridge between the 5 coater lip and the web in the bead formed with a bead coater" and can limit the web speed at which the method can be applied. To overcome this problem, Choinski suggests use of a non-Newtonian pseudoplastic liquid as the carrier, such that it has a high viscosity on the slide and in the bead where the shear rate is low, and a low viscosity near the 10 dynamic contact line where the shear rate is high. In U.S. Patent No. 4,525,392 (Ishizaki and Fuchigami, 1985) it is further specified that the non-Newtonian (or shear thinning) carrier layer viscosity should be within 10 cp of the next layer at low shear rates, but lower at high shear rates. However, these patents do not address strikethrough or phase 15 separation.

Interlayer mixing between the bottom two layers "caused by a whirl formation in the meniscus" is cited as a limitation of the above 20 patents, and a method of overcoming this interlayer mixing by adjustment of coating gap is described in U.S. Patent No. 4,572,849 (Koepke et al., 1986). This method also employs a low viscosity accelerating layer as the lowermost layer over which other higher viscosity layers can be arranged. A slightly different layer arrangement is also described where a 25 low viscosity spreading layer is used as the uppermost layer in addition to the lowermost low viscosity accelerating layer. The same arrangement is used for curtain coating in related patent U.S. Patent No. 4,569,863 (Koepke et al., 1986). However, neither patent addresses the problem of strikethrough or phase separation that occurs on the slide surface.

U.S. Patent No. 4,863,765 (Ishizuka, 1988) teaches that using a thin layer of distilled water as carrier allows high coating speeds and also

eliminates mixing between the two lowermost layers. In related patents U.S. Patent No. 4,976,999 and U.S. Patent No. 4,977,852 (Ishizuka, 1990a and 1990b) the carrier slide construction with water as carrier (as described in U.S. patent No. 4,863,765) is used, and it is noted that 5 streaking is reduced by using smaller slot heights for the carrier layer and that bead edges are stabilized by extending the width of the carrier layer beyond the width of the other layers coated above the carrier. This patent also does not address strikethrough or phase separation.

In summary, U.S. Patent Nos. 4,001,024; 4,113,903; and 10 4,525,392 require that the composition of the two bottom layers be adjusted such that interlayer mixing between these layers in the coating bead not lead to defects in the product. U.S. Patent No. 4,572,849 (and related U.S. Patent No. 4,569,863) while not restricting layer composition, restrict the coating gap to the range 100 μm - 400 μm . 15 Likewise, U.S. Patent Nos. 4,863,765, 4,976,999 and 4,977,852, while not specifically requiring a composition adjustment, are restricted to aqueous solutions by use of distilled water as carrier. However, the problem of strikethrough that occurs with a product construction as shown in Figure 1 is not addressed by these patents. In other words, the 20 prior art as described in the above patents does not disclose the necessary criteria that will allow strikethrough-free manufacture of a product such as a photothermographic element that is illustrated in Figure 1. Furthermore, these patents do not address the problem of phase separation that can prevent the use of a multi-layer coating technique in 25 the manufacture of a product, such as the product illustrated in Figure 1.

It would be desirable to simultaneously apply such incompatible solutes in miscible solvents using multilayer coating techniques such as slide coating without occurrence of strikethrough or phase separation. It would also be desirable to continuously coat such compositions at wide

coating gaps (greater than 400 μm) to allow for coating over splices in the substrate without interruption in order to maximize productivity.

Moreover, it would be desirable to apply such layers from either organic solvent or aqueous medium, as required by product composition.

5 Still further, it would be desirable to reduce the waste of coating fluid(s) that results when it becomes necessary to interrupt the coating process. When slide coating is begun, a uniform, streak-free flow of each of the fluid layers on the slide surface is established. This is often a careful, tedious, and time-consuming process. Only after streak-free, 10 stable, uniform fluid flows are established is the coating die moved toward the moving web to form a coating bead and thus transfer the coating to the web. When coating must be interrupted during the normal course of coating operations, the coating die is retracted from the web.

Often when this is done, the flow of coating fluids is continued to 15 insure that pumping and streak-free, stable, uniform fluid flows are maintained. The coating fluid(s) are collected by a vacuum box trough or drain trough and drained to a scrap receptacle. This has the disadvantage of wasting coating fluid(s).

Alternatively, to minimize waste of coating fluid(s) during prolonged 20 pauses in coating, the flow of coating fluid(s) is often completely stopped and some covering such as tape is placed over the coating die slots to reduce drying. Unfortunately, this leads to contamination of the slide and slots by adhesive, particles, fibers etc. and is only marginally effective in preventing dry-out and/or coagulation in the slots. When coating is 25 resumed the tedious process of streak elimination must be repeated, and streak-free, stable, uniform fluid flows must be reestablished. This can, again, result in waste of coating fluid(s) and loss of production time.

Yet another alternative is to reduce rather than completely stop the flow of coating fluid(s). When this method is used with volatile organic

solvent based coatings, undesirable dry-out and/or coagulation of the coating fluid(s) on the slide surface and in the slide slots still occurs due to the rapid evaporation of the volatile organic solvent. Again, when coating is resumed streak elimination must be repeated, and stable fluid flows must be reestablished.

It would be desirable to find a method that avoids either the need for continuous flow of the coating fluid or streaks, dryout, etc. that can result during necessary interruptions to the coating process. This desire and other desires noted herein extend beyond the process of making photothermographic, thermographic, photographic, and data storage materials (such as magnetic storage media) to the preparation of other coated materials whose production involves similar problems.

SUMMARY OF THE INVENTION

The invention described here is a method for minimizing waste resulting from defects caused at the edges of a coating on a substrate which was applied to the substrate by a slide coater. The slide coater has at least first slot through which a first coating fluid flows and a second slot through which a second coating fluid flows. The first slot has first slot width which includes a first slot main portion and first slot right and left end portions. The method includes the step of flowing the first coating fluid through the first slot main portion at a first flow rate and onto a first slide surface and further onto the substrate. Another step involves flowing the first coating fluid through the first slot end portions onto the first slide surface and further onto the substrate. The first coating fluid flows from the first slot right end portion having a second flow rate and flows from the first slot left end portion having a third flow rate. The second and third flow rates are different from the first flow rate. Another step involves flowing the second coating fluid

through the second slot and onto a second slide surface. The second slide surface is positioned relative to the first slide surface and oriented such that the second coating fluid flows from the second slide surface onto the first coating fluid on the first slide surface and such that the first 5 and second coating fluids flow onto the substrate.

Other aspects, advantages, and benefits of the present invention are apparent from the drawings, detailed description, examples, and claims.

10

BRIEF DESCRIPTION OF THE DRAWINGS

The foregoing advantages, construction, and operation of the present invention will become more readily apparent from the following description and accompanying drawings.

Figure 1 is a schematic front view of a construction of a known 15 photothermographic element;

Figure 2 is a side sectional view of a slide coater in accordance with the present invention;

Figure 3 is a partial top view of a the slide coater shown in Figure 2;

20 Figure 4 is a partial side sectional view of the slide coater shown in Figure 2;

Figure 5 is a partial side sectional view of an embodiment of the slide coater shown in Figure 2;

25 Figure 6 is a partial side sectional view of an embodiment of the slide coater shown in Figure 2;

Figure 7 is a schematic view of an embodiment of the slide coater shown in Figure 2 and additional components;

Figure 8 is a partial top view of an embodiment of the slide coater shown in Figure 2;

Figure 9 is a side sectional schematic view of the slide coater shown in Figure 2 further including means for cleaning the slide coater;

5 Figure 10 is a perspective, partial, sectional view of an end of a die block and a cam used to apply pressure to an end seal in the manifold of the die slot;

Figure 11 is a partial top view of an embodiment of the slide coater shown in Figure 2 including a tapered slot;

Figure 12 is a perspective view of the tapered slot shown in Figure 11; and

10 Figure 13 is a partial side sectional view of an embodiment of a coating slot and coating surface.

DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

Slide Coating Apparatus

15 Figures 2 and 3 illustrate a slide coating apparatus 30 generally made up of a coating back-up roller 32 for the substrate 18, and a slide coater 34. The slide coater 34 includes five slide blocks 36, 38, 40, 42, 44 which define four fluid slots 46, 48, 50, 52 and a slide surface 53. The first slide block is adjacent to the coating back-up roller 32 and 20 includes a vacuum box 54 for adjusting the vacuum level by the slide coating apparatus 30. The vacuum box serves to maintain a differential pressure across the coating bead, thereby stabilizing it.

A first fluid 55 can be distributed to the first slot 46 via a first fluid supply 56 and a first manifold 58. A second fluid 60 can be distributed 25 to the second slot 48 via a second fluid supply 62 and a second manifold 64. A third fluid 66 can be distributed to the third fluid slot 50 via a third fluid supply 68 and a third fluid manifold 70. A fourth fluid 72 can be distributed to the fourth fluid slot 52 via a fourth fluid supply 74 and a fourth fluid manifold 76. This embodiment allows for the creation of up

to a four-layer fluid construction 78 including a first fluid layer 80 (a.k.a., a carrier layer), a second fluid layer 82, a third fluid layer 84, and a fourth fluid layer 86. Additional slide blocks can be added for the introduction of additional fluid layers, as required for product performance or ease of

5 operability.

The fluid manifolds 58, 64, 70 and 76 are designed to allow uniform width-wise distribution out of fluid slots 46, 48, 50, 52, respectively. This design is specific to the choice of slot height H (illustrated in Fig. 4) for the slots 46, 48, 50, 52. The slot height H is

10 made sufficiently small such that the pressure drop in the slot is much higher than the pressure drop across the manifold (without causing undue problems of non-uniformity due to machining limitations or bar deflection due to excessive pressure in the die slot). This ensures that the fluid distributes uniformly in the slot. It is known that slot heights are made

15 smaller when lower flow rates are desired.

The design of the fluid manifold can also be made specific to the rheology of the fluid that it will carry, taking into account material properties such as but not limited to zero-shear viscosity, the power law index, fluid elasticity, and extensional behavior. The fluid supply can be

20 located either at the end of the fluid manifold (end-fed design) or at the center of the fluid manifold (center-fed design). The principles of manifold design are also well-documented in literature (see for example, Gutoff, "Simplified Design of Coating Die Internals," *Journal of Imaging Science and Technology*, 1993, 37(6), 615-627) and could be used for all

25 die-fed coating processes such as but not limited to slide, extrusion, and curtain coating. Further details of a preferred manifold design are noted later within this disclosure.

The slide blocks 38, 40, 42, 44 can be configured to have specific slot heights H as depicted in Fig. 4, chosen amongst other reasons to

minimize pressure in the die manifolds and to overcome problems of non-uniformity due to machining limitations. The slot heights typically used range between 100 - 1500 μm . The slide blocks 38, 40, 42, 44 can also be arranged with a level offset so as to result in slot steps T, also 5 depicted in Fig. 4. These steps can aid the uniform flow of fluid down the slide surface 53 by minimizing the possibility of flow separation and fluid recirculation zones that can lead to streaking and other product defects. These slot steps can range from 100 - 2000 μm in height. The use of such steps is well-documented. Another method of minimizing the 10 occurrence of flow separation on the slide surface 53 is by machining chamfers C on the downstream side of a fluid slot, as depicted in Fig. 4 and could also be used in the embodiment of slide coating as described in this application.

In the machining of the slide blocks 36, 38, 40, 42, 44, the finish 15 of the block edges that form the edges of the fluid slots 46, 48, 50, and 52 are important, as is also the front edge of the front block 36 that is adjacent to backup roller 32. The presence of nicks, burrs or other defects on these edges can lead to streaking defects in the product. In order to avoid such defects, the edges are polished to a finish of less 20 than 0.02 μm . Details regarding the procedure for finishing the die edges are disclosed in PCT publications WO 96/39276 and WO 96/39275.

Figure 4 also illustrates the orientation of the slide coater 34 relative to the back-up roller 32, including the position angle P, attack angle A, and the slide angle S. (The slide angle S is the sum of the 25 position angle P and the attack angle A.) A negative position angle P is preferred so as to allow for increased wrap on the back-up roller and thereby greater stability for the coating operation. However, the method could also be used with a zero or positive position angle. The slide angle S determines the stability of the flow of fluids down the inclined slide

plane. A large slide angle S can lead to the development of surface wave instabilities and consequently coating defects. The slide angle is typically set in the range from slightly greater than zero to 45°. The distance between the slide coater 34 and the roll 32 at the point of closest approach is known as the gap G. The wet thickness W of each layer is the thickness on the surface of the coated substrate 18 substantially far away from the coated bead, but close enough before appreciable drying has occurred.

Other portions of the slide coating apparatus 30 deserve further discussion. Figures 5 and 6 illustrate portions of the slide coater which include durable, low surface energy portions 88. These portions 88 are intended to provide the desired surface energy properties to specific locations to uniformly pin the coating fluid to prevent build-up of dried material.

Figure 7 illustrates a particular type of end-fed manifold 100 and a recirculation loop 102. Note that the manifold 100 is shown as being inclined towards the outlet port 106 such that the depth of the slot L decreases from the inlet port 104 to the outlet port 106. The incline angle is carefully adjusted to take into account the pressure drop in the fluid as it traverses from the inlet port 104 of the manifold 100 to the outlet port 106 to ensure that the width-wise fluid distribution at the exit of the slot is uniform. With the illustrated manifold design, only a portion of the fluid that enters the manifold 100 leaves through the fluid slot (such as slots 46, 48, 50, or 52), while the remainder flows out through the outlet port 106 to the recirculation loop 102. The portion which flows through the outlet port 106 can be recirculated back to the inlet port 104 by a recirculation pump 108. The recirculation pump 108 can receive fresh fluid from a fluid reservoir 110 and fresh fluid pump 112. A fluid filter 114 and heat exchanger 116 can be included to filter and heat

or cool the fresh fluid before it mixes with the recycled fluid. In this case, the same principles that apply to the design of end-fed manifolds are still applicable. The manifold design, *i.e.* the cavity shape and angle of incline, however, depends not only on the choice of slot height and 5 fluid rheology, but on the percent recirculation used. The use of a similar recirculation loop for preventing agglomeration in the manifold during coating of highly shear-thinning magnetic materials is disclosed in U.S. Patent No. 4,623,501 (Ishizaki, 1986).

The flow of fluid down the slide surface 53 is aided by the use of 10 edge guides 119 at each edge of the surface, as shown in Figure 3 (and Figure 8). The edge guides 119 serve to pin the solution to the solid surface and result in a fixed width of coating and also stabilize the flow of fluid at the edges. The particular type of edge guide 119 illustrated in Figure 3 is commonly known in the coating art. Note that the edge 15 guides are straight, and direct flow perpendicular to the slots 46, 48, 50, 52 over the slide surface. The edge guides 119 can made of one material including metals such as steel, aluminum, etc.; polymers such as poly-tetrafluoroethylene (e.g., TEFLOTM), polyamide (e.g., NYLONTM), poly(methylene oxide) or polyacetal (e.g., DELRINTM), etc.; wood; 20 ceramic, etc., or can be made of more than one material such as steel coated with polytetrafluoroethylene.

The edge guides 119A can be of a convergent type, as illustrated in Figure 8. The angle of convergence θ can be between 0° and 90° , with 0° corresponding to the case of straight edge guides of Figure 3. 25 The angle θ can be chosen for increased stability of the coating bead edges by increasing coating thickness at the bead edges relative to the center. In other embodiments, the edge guides can include durable, low surface energy surfaces or portions as described previously. A cover or shroud over the slide coater 34 can be used (not shown).

Method of Multilayer Slide Coating

Using slide coating apparatus 30, a method has been developed to effectively coat, in a single pass, an organic solvent-based coating which, when dried (or otherwise solidified), creates the element 10 shown in

5 Figure 1 (except for antihalation layer 20). This method is especially effective when one or more of the carried fluid layers 82, 84, 86 contains dispersed or dissolved phases that are incompatible with the constituents of the first (or carrier) layer 80 and function by preventing or minimizing the intermixing of the fluid layers on the surface of the slide.

10 As used herein, incompatibility of the dispersed or dissolved phases means that the coating fluid layers that contain these substantially different dispersed or dissolved phases do not readily mix, although the solvents comprising the fluid layers (either the same or different) are miscible and readily interdiffuse. An example of such a system is a

15 multilayer coating where the first layer comprises VITEL™ PE2200 dissolved in MEK and the second layer comprises BUTVAR™ B-79 dissolved in MEK. Upon coating this system is prone to strikethrough.

One counter-example where strikethrough is not a problem is provided by conventional silver halide photographic constructions where

20 all layers contain a substantial gelatin component with water as the solvent. A second counter-example where strikethrough is not a problem is provided by two solutions or dispersions that differ only in solvent content (i.e., concentration) but are otherwise identical.

Furthermore, as used herein, "phase separation" means that an

25 interdiffusion of the different solvents in different fluid layers causes one or more of the solutes in one or more of the layers to spontaneously form a separate phase by the phenomenon of spinodal decomposition.

In systems that are prone to strikethrough, the disruption of the interface between the carrier layer and various carried layers eventually

leads to one or more of the carried fluid layers penetrating and sticking to the surface of the slide and causing excessive streaking and waste in the manufacture of the desired product (i.e., strikethrough). We have found that this phenomena of strikethrough can be minimized or prevented in

5 one of two ways:

- (1) by preventing the disruption of the interface due to naturally occurring disturbances, or
- (2) by sufficiently slowing the penetration of the carried fluid layers to the surface of the slide with respect to the average time 10 required for coating and drying.

A preferred additional aspect of the invention is the ability to "self-clean", that is, the flow of the bottom-most coating layer (or the bottom-most coating layer and one or more adjacent coating fluid layers) cleans off the penetrant coating fluid layer that sticks to the slide surface.

15 These methods of preventing strikethrough are described in the embodiments given below.

One embodiment of this method involves a first or carrier layer 80 which is more dense than upper or carried fluid layers 82, 84, 86 and which has a viscosity that is sufficiently low to allow coating at high 20 speeds. Any of carried layers 82, 84, 86 can be incompatible with first layer 80. Layers 82 and 80 can be incompatible, as can layers 84 and 82 and layers 86 and 84.

A further embodiment of the method involves a first layer 80 having a greater density than second layer 82, which has a greater 25 density than the third layer 84, which has greater density than the fourth layer 86.

A further embodiment of the method involves a layer of sufficient thickness, viscosity, or density such that a disturbance will not result in

contact of the slide surface 53 by any carried layer disposed above such layer.

Another embodiment involves a low viscosity, low density, first layer (also known as a carrier layer) 80 and a second layer 82 (i.e., a first 5 carried layer) which is self-cleaned by the first layer 80 and more dense than first layer 80 and third and fourth layers 84, 86. Layers 80 and 82 are compatible, and layer 84 and/or layer 86 can be incompatible with layer 80. A preferred embodiment involves a low viscosity, low density, first (or carrier) layer 80 and a second layer 82 (i.e. a first carried layer) 10 that is self-cleaned by the first layer 80, and which is more dense than first layer 80 and layer 84, and where layer 84 is more dense than layer 86. Layers 80 and 82 are compatible, layers 80 and 84 can be incompatible, and layers 84 and 86 can be incompatible.

Another embodiment involves a first carried layer which has a 15 sufficiently high viscosity and thickness such that a disturbance will not be allowed to result in contact between a carried layer 84 or 86 and the slide surface 53, thus preventing strikethrough.

In systems where phase separation can occur, particulates or gels can form within a layer leading to defects such as streaking, fish-eyes, or 20 even a complete disruption of flow and intermixing of separate fluid layers. To avoid such phase separation, one must judiciously choose the solvents and solutes in the different layers that are to be coated using a multi-layer coating technique, such that no solute (from any layer) phase separates in the entire range of concentration encountered during the 25 stages of coating and drying. Therefore, another embodiment of the present invention is making the proper choice of solvents within the different layers such that no solvent or combination of solvents causes phase separation in any of the layers.

While the examples shown below were carried out with fluids used to manufacture a photothermographic imaging element, the configurations and methods described herein for using slide coating apparatus 30 can be beneficial when coating other imaging materials such as thermographic, 5 photographic, photoresists, photopolymers, etc. or even other non-imaging materials such as magnetic, optical, or other recording materials, adhesives, and the like. The configurations and methods are particularly applicable when intermixing of multiple layers of fluids is undesirable and where strikethrough is a source of significant waste.

10 **Method of Minimizing Drying During Coating Start-up and Coating Pauses**

As previously noted, a sixth slide block (not shown) can be added to those shown in Figures 2 and 3 and can be positioned adjacent to the fifth slide block 44. The sixth slide block allows for the introduction of a fifth fluid (not shown) that can coat over the coating surfaces of the first, 15 second, third, fourth, and fifth slide blocks 36, 38, 40, 42, 44. The fifth fluid can be used to address the previously described problems of material waste, drying, and streaking that are encountered when it becomes necessary to interrupt the coating process. The fifth fluid can form a protective blanket over the other coating fluid(s) which minimizes, if not 20 eliminates, drying of these coating fluids on the slide surface and edge guides. The fifth fluid can also self-clean various slide surfaces of contaminants and debris and can pre-wet the slide surface(s) before the coating fluid(s) are introduced to the slide surface(s). Such a fluid can be thought of as a "minimizing fluid" as it minimizes or reduces defects 25 related to, for example, drying and poor wetting of the coating fluid(s), or related to the presence of contaminants or debris on the slide surface(s).

The fifth fluid can be directed down slide coater 34 when slide coater 34 is a sufficient distance from coating back-up roller 32 such that the fifth fluid does not contact back-up roller 32 or substrate 18, but

flows down the front of the first slide block 36 and into the vacuum box and drain.

The fifth fluid can be composed of a solvent compatible with the solvent system of the coating fluid(s) and can be dispensed at the start-

5 up of a coating run before the flows of the coating fluid(s) are begun; during a short pause in coating above the flows of the coating fluid(s); and alone with the flows of the coating fluid(s) turned off during a prolonged pause in coating or after a coating run has been completed.

The fifth fluid can be, for example, 100 percent solvent and can be

10 chosen to be miscible with solvents used for the coating fluid(s). It may be filtered in-line or pre-filtered so that no contaminating materials (e.g., particles, fibers) are introduced onto the coating surfaces.

When coating is begun the flow of fifth fluid is started first to completely pre-wet and clean the coating surface of slide coater 34. The

15 flow of coating fluid(s) are then started in order (fluid layers 1, 2, 3, 4, ...) and the flow of each of the fluid layers is established. The fifth fluid flow is then stopped and the coater die moved toward back-up roller 32 for pick-up of coating onto the web. Thus, the fifth fluid assists in the rapid establishment of streak free coating flows.

20 When coating is paused or stopped, the coating assembly is retracted from back-up roller 32, and the flow of the first, second, third, and fourth fluids 80, 82, 84, 86 is reduced or stopped to minimize the waste of coating fluid(s).

During a short pause in coating, the flow of the fifth fluid is started 25 while the flow of coating fluid(s) is substantially reduced. The blanket of solvent lying over the coating fluid(s) on the slide surface minimizes or eliminates drying, coagulation, or particle formation within a coating fluid(s) that can cause streaks when coating is resumed. For resuming coating, the fifth fluid flow is stopped, the flow of coating fluid(s) is

increased to normal levels, and the coater die is moved toward back-up roller 32 for pick-up of coating onto the web. Thus, the fifth fluid assists in the rapid re-establishment of streak free coating flows.

During a prolonged pause in coating, the flow of the fifth fluid is 5 started while the flow of coating fluid(s) is completely stopped, leaving only the continuous flow of the fifth fluid. In this manner the entire slide surface is self-cleaned by the continuous solvent flow and the drying of any residual coating fluid(s) on various surfaces of the slide coater is minimized, if not entirely prevented. When coating operation is to be 10 resumed, the coating fluid layers are restarted in order (fluid layers 1, 2, 3, 4, ...) while the fifth fluid flow is continued. After the coating flows are re-established, the fifth fluid flow is stopped and the coater die engaged to back-up roller 32 for pick-up of coating onto the web. Thus, the fifth fluid assists in the rapid re-establishment of streak free coating 15 flows.

It should be noted that the above discussion is only illustrative. For example, if only three slots of slide coater 34 shown in Figure 2 were required for a coating, the "minimizing" fluid (now a fourth fluid) could be dispensed from the fourth or fifth slot. Likewise, the "minimizing" fluid 20 could instead be a third fluid which minimizes the drying of a first and second fluid. Or, the "minimizing" fluid could instead be a second fluid which minimizes the drying of a single coating fluid.

Additionally, the solvent flow system need not even be made with same precision as the coating fluid system. Thus, the supply of the 25 solvent layer to the surface of the slide coater can be by any suitable means. For example, solvent can be delivered to the slide surface by using spray nozzles, porous wicks, porous metal inserts, etc.

Though the use of this cleaning/wetting method is exemplified above in slide coating, it can easily be adapted to operations of curtain- and extrusion-coating.

Method of Cleaning Coating Dies

5 When multilayer slide coating is completed the coating apparatus needs to be cleaned. Often this involves taking the coater apart and it is normal practice to disassemble the coating die and remove coating fluid remaining in the manifolds, slots, and on the slide surfaces, etc. The die is disassembled, cleaned, inspected, reassembled, and aligned prior to the
10 next coating run. This is a laborious, expensive, and time-consuming task. All of the handling required presents numerous opportunities for damage to the precision coating die parts that can necessitate repair and result in delays. If damage is not found until coating has begun, product that is outside specifications and cannot be used may be produced.

15 A method of clean-up following a coating run that avoids the problems of disassembly uses a cleaning construction shown in Figure 9. The coating die can be made such that it can be switched from coating mode to cleaning mode (e.g., the coating die can be made such that it can be switched between an end-fed mode, used during coating, to a
20 recirculation mode, used during cleaning).

25 This is accomplished by the use of removable, elastomeric, manifold-end seals 120 that can be compressed in place by rotating cam levers 121 (one shown to achieve sealing action), as shown in Figure 10. Removal of the removable, elastomeric end seals 120 (within a flow- through cavity) and replacement with closed end seals (not shown) from a side end of a die block allows for the quick conversion from a recirculation (or cleaning) mode to an end-fed (or coating) mode. (Figure 10 also shows that the end seal 120 includes a streamlined plug 122

which is useful to minimize a "dead zone" within the fluid flow path when in the coating mode.)

A tank 123 and a pump 124 force a cleaning fluid, such as a solvent (e.g., MEK), through one or more of the fluid slots at a rate 5 possibly greater than the coating rate. A spray shield 126 placed over the slide coater 34 prevents the cleaning fluid from spraying and directs the cleaning fluid down at least a portion of the surface 53 of the slide blocks. This method involves moving the coating back-up roller 32 away from the slide coater 34 and the cleaning fluid to be removed from the 10 surface of the slide coater 34 through a drain 128. The drain 128 can communicate with the tank 123 such that a cleaning fluid recirculation loop 130 can be formed. Optionally, a filter 132 can be included within the recirculation loop 130 to filter out the remaining liquid solute or dried solute particles.

15 This cleaning method can also be easily adapted to other coating methods, such as extrusion- and curtain-coating. One benefit is the reduction of damage to the coater resulting from either taking the coater apart or cleaning the coater with a damaging tool. Another benefit is repeatability, in that each coating run will begin after a consistent 20 cleaning process. Furthermore, this cleaning method can be faster and can, therefore, represent a savings in labor cost. Finally, this cleaning method can simply be more effective than conventional bar cleaning methods.

Method of Reducing Edge Waste In Slide Coating

25 One problem with multilayer coatings is the formation of coating thickness variations, namely an overly thick edge-bead of coating immediately adjacent to the edge of the coatings on a substrate. This edge-bead is a problem and results in transfer of insufficiently dried coating material (at the edges) onto the coating apparatus; poor take-up

on rolls; and hard-banding, blocking, and wrap-to-wrap adhesion problems in the wound roll of finished coated material. As a result a large amount of waste material must be slit from this edge-bead region of the coated substrate to afford material within product specifications.

5 U.S. Patent No. 4,313,980 (Willemsens, 1982) aims to reduce or prevent the formation of beaded edges by modifying the slot lengths such that the length of the top slot is greater than the length of at least one of the other slots and is not exceeded by the length of any other slot. Willemsens further states that the preferred embodiments of his invention

10 incorporates one or more of the following features: (a) The thickness of each layer of extra coating width is smaller than the thickness of each layer having less coating width; (b) The surface tension of the coating layer which directly contacts the web surface being coated is lower than the surface tension of that surface; and (c) The surface tension of each

15 layer having the extra coating width is lower than the surface tension of each layer having the lesser coating width. The optimum difference in the length of the slots must be determined empirically and is dependent on the material of the surface to be coated as well as the properties of the coating fluid. It should be noted that the slot length determines the

20 width of the coating.

U.S. Patent No. 5,389,150 (Baum et al., 1995) describes slot inserts to control slot length to adjust the width of a coating on a slide coater. They note that a slot can be angled inward or outward from the hopper center for edge control. However, they do not distinguish from

25 conventional slide coating where all the slots are of the same length while coating.

The present invention includes the understanding that a significantly reduced edge bead with monotonic increase in thickness to the targeted level can be best achieved by a gradual reduction of the flow

in a narrow region adjacent to the ends of the slot. By employing the present invention, non-uniform coating overthickness and edge bead formation can be substantially reduced by suitably adjusting the slot height and/or the slot depth to control the flow of coating fluids at the 5 ends of the coating slots.

A preferred method of controlling edge-thickness of a coating is by adjusting the slot height at the ends of the slot. Figure 11 shows a top view of the slide surface for a slide coater having four slots. The third slot height has been adjusted by adding wedge-shaped shims to provide a 10 reduction in the coating fluid flow onto the slide near the edges. This shim can held inside the slot by friction, with the help of pins, or by any other suitable means. The location and size of the wedge-shaped shims can be adjusted such that, for example, 90-99.5 percent of the slot has a 15 constant slot height and the remainder narrows as shown. Depending on the size of the slot, the narrowing can occur between, for example, from approximately 2.5 to 25.4 mm from the edge of the slot. It is preferable that the narrowing occur between approximately 5.1 to 12.7 mm, or even more preferably, from 5.1 to 7.6 mm.

It should also be noted than an advantage of the embodiment 20 shown in Figure 11 is that the coating fluid flow in the slot can be easily calculated as a function of the slot height. A perspective view of the "tapered" slot is depicted in Figure 12.

For this tapered slot, assuming (1) an infinite cavity manifold, (2) a 25 constant viscosity (or Newtonian) fluid, and (3) the end effects extend over a very small fraction of the taper, the flow rate at any width-wise position y is given by:

$$Q(y) = \frac{\Delta P}{12 \mu L} [f(y)]^3,$$

where $f(y)$ is defined for the tapered slot such that

$$f(y) = \left(\frac{2B}{W-V} \right) (2y + W), \text{ for } -\frac{W}{2} \leq y \leq -\frac{V}{2}$$


$$f(y) = 2B, \text{ for } -\frac{V}{2} \leq y \leq \frac{V}{2}$$

$$f(y) = \left(\frac{2B}{V-W} \right) (2y - W), \text{ for } \frac{V}{2} \leq y \leq \frac{W}{2}$$

and P is the pressure, Q is the volumetric flow rate, L is the slot depth, W is the total slot length, V is the slot length with a constant slot height, $2B$

5 is the slot height in the center of the slot, and μ is the Newtonian viscosity. Other formulae exist for more rheologically complex fluids. Also, other functional forms can be inserted instead of the form for $f(y)$ that is given above. The following plot indicates the predicted normalized flow rate versus the normalized distance for this type of a

10 chamfered slot for the case where $V/W = 0.98$.



The flow rate is reduced at the slot edges and substantially reduces the edge bead and the resultant slit waste. For instance, as shown in Examples 11 and 12 below, edge waste is reduced from about 3.5 cm to about 2 cm by the method of this invention. Likewise, the slot height can

5 be flared outwards to reduce resistance and increase flow at the edges, if so desired.

Yet another method of controlling edge-thickness of a coating is by adjusting the distance from the manifold to the slide surface. This distance is also known as the slot depth L, and can be increased near the

10 edges to reduce the flow of a fluid layer by increasing the resistance to flow near the edges, as illustrated in Figure 13. Control of edge-thickness can also be achieved by decreasing the slot length W and reducing the slot depth L to increase fluid flow at the ends of the slot by reducing the resistance to flow there (i.e., the combination of Figures 11

15 and 13). The location and extent of the slot depth increase shown in Figure 13 can be similar to the narrowing or tapering of the slot noted above and shown in Figures 11 and 12.

These methods can be used alone or in combination to give a desired coating profile. For example, a flared slot height at the slot ends

20 (to form a bowtie appearance) may be combined with an increased (or decreased) slot depth at the edges of the slot. The combination can provide more uniformity in the final coating on the substrate. It should also be noted that in all examples described below, the final coated thickness is modified from that extruded out of the slot by the flow action

25 on the slide and in the coating bead.

Objects and advantages of aspects of this invention will now be illustrated by the following examples, but the particular materials and amounts thereof recited in these examples, as well as other conditions and details, should not be construed to unduly limit this invention. As

previously noted, aspects of the techniques described above can be applied to other coating processes including curtain coating, extrusion coating, and other die-fed coating processes.

5

EXAMPLES

All materials used in the following examples are readily available from standard commercial sources, such as Aldrich Chemical Co. Milwaukee, WI, unless otherwise specified. All percentages are by weight unless otherwise indicated. The following additional terms and 10 materials were used.

Silver homogenates were prepared as described in PCT publications WO 95/22785 and WO 95/30931 and contained 20.8% pre-formed silver soap and 2.2% BUTVAR™ B-79 resin for Examples 2 and 9 and contained 25.2% pre-formed silver soap and 1.3% BUTVAR™ B-79 resin for the 15 Examples other than Examples 2 and 9.

Unless otherwise specified, all photothermographic emulsion layers and topcoat layers were prepared substantially as described in PCT publication WO 96/33442.

BUTVAR™ B-79 is a polyvinyl butyral resin available from Monsanto 20 Company, St. Louis, MO.

MEK is methyl ethyl ketone (2-butanone).

VITEL™ PE 2200 is a polyester resin available from Shell; Houston, TX.

Pentalyn-H is a penterythritol ester of a hydrogenated natural resin 25 and is available from Hercules, Inc.; Wilmington, DE.

Coatings were carried out on a slide coater to confirm the benefits provided by one configuration and method for using the slide coating apparatus 30.

Examples 1 and 2 are comparative examples and show a configuration and method for using the slide coating apparatus 30 (including the fluid compositions) to attempt to produce the product construction shown in Figure 1. The composition described in Example 1 includes the first fluid layer 80 which forms the primer layer 16 (shown in Figure 1) but which is incompatible with the second fluid 84 which forms the photographic emulsion layer 14 (shown in Figure 1). The compositions described in Example 2 include compatible first and second fluids 80, 82 which forms the primer layer 16 (shown in Figure 1), but which are incompatible with the third fluid 84 which forms the photothermographic emulsion layer 14 (shown in Figure 1). The first and second layers 80, 82 are compatible in that they have the same composition, but different percent solids. In both Examples 1 and 2 strikethrough is observed.

Examples 3-10 describe coating by the method of this invention whereby strikethrough is prevented. Examples 11 and 12 illustrate the invention whereby edge waste is substantially reduced.

Example 1 (Comparative)

Three solution layers were coated onto a blue tinted polyethylene terephthalate substrate (0.17 mm thick, 71 cm wide) with the preferred slide set-up as described, with a slide angle S (see Figure 4) of 25° and a position angle P of -7°. (The second fluid slot 48 was not required.) The slide set-up used is shown below in Table A-1.

Table A-1

Layer	Slot Height, mm	Slot Step, mm	Slide Angle S, °	Position Angle P, °
80	0.13	0	25	-7
84	0.64	1.52		
86	0.64	1.52		

The first layer 80 is a primer layer 16 (shown in Figure 1) and is a solution of VITEL™ PE2200 in MEK at 16.7% solids. It increases adhesion of the photothermographic emulsion layer 14 to the substrate 18. The second layer 84 is a photothermographic emulsion layer 14 (shown in Figure 1). The third layer 86 is a topcoat layer 12 (shown in Figure 1). Layer 82 shown in Figure 2 is not present in this example. The solution properties for the three coating layers are detailed in Table A-2, shown below. The reported value of viscosity is as measured by a Brookfield viscometer, at shear rate of approximately 1.0 s^{-1} , and the density is from a % solids vs. density curve for each of the layer formulations.

Table A-2

Layer	% solids	Viscosity, cP	Density, g/cm ³	Wet Thickness W, μm
80	16.7	10	0.86	5
84	37.0	1250	0.92	70.8
86	14	1010	0.85	22.8

Coating was carried out at 30.5 m/min. at a coating gap G of 0.25 mm from the back-up roller and an applied vacuum of 2.5 mm of H₂O across the coating bead. Strikethrough was observed on the slide surface 53 resulting in streaking and unacceptable coating quality.

Example 2 (Comparative)

Four solution layers were coated onto a clear polyethylene terephthalate substrate (0.05 mm thick, 21.6 cm wide) with the preferred slide set-up as described, with a slide angle S (see Figure 4) of 25° and a 5 position angle P of -7°. The slide set-up used is shown below in Table B-1.

Table B-1

Layer	Slot Height, mm	Slot Step, mm	Slide Angle S, °	Position Angle P, °
80	0.13	0	25	-7
82	0.13	0		
84	0.51	1.52		
86	0.38	1.52		

The first two layers 80 and 82 comprise the primer layer 16 (shown in Figure 1). Layer 80 is a solution of VITEL™ PE2200 resin in 10 MEK at 14.7% solids. Layer 82 is also a solution of VITEL™ PE2200 resin in MEK, but at 30.5% solids. Layer 82 is completely miscible with 15 Layer 80. The third layer 84 is a representative photothermographic emulsion layer 14 (shown in Figure 1). It was prepared as described below in Table B-3. Its density is greater than Layer 82 as described below in Table B-2. This emulsion layer does not contain developers, 20 stabilizers, antifoggants, etc.; but, it is otherwise identical to photothermographic emulsion layers used to produce photothermographic imaging materials. The fourth layer 86 is a topcoat layer 12 (shown in Figure 1). The solution properties for the four coating layers are detailed in Table B-2, shown below. The reported value of viscosity is as measured by a Brookfield viscometer, at shear rate of approximately

1.0 s⁻¹, and the density is from a % solids vs. density curve for each of the layer formulations.

Table B-2

Layer	% solids	Viscosity, cP	Density, g/cm ³	Wet Thickness W, μm
80	14.7	12	0.85	5.0
82	30.5	144	0.91	5.0
84	31.7	1086	0.92	71.7
86	14.6	1300	0.86	19.3

5 Coating was carried out at 30.5 m/min. at a coating gap G of 0.25 mm from the back-up roller and at an applied vacuum of 25 mm of H₂O across the coating bead. Strikethrough was observed on the slide surface resulting in streaking and unacceptable coating quality.

10 **TABLE B-3: Composition of Photothermographic Emulsion Layer 84**

Premix	Chemical Name	Wt. %
A	Silver Homogenate	69.52
B	Methanol	4.21
C	MEK	9.72
D	Butvar TM B-79	16.55

Example 3:

Four solution layers were coated onto a blue tinted polyethylene terephthalate substrate (0.17 mm thick, 71 cm wide) with the preferred 15 slide set-up as described, with a slide angle S (see Figure 4) of 25° and a

position angle P of -7°. The slide set-up used is shown below in Table C-1.

Table C-1

Layer	Slot Height, mm	Slot Step, mm	Slide Angle S, °	Position Angle P, °
80	0.13	0	25	-7
82	0.38	0		
84	0.64	1.52		
86	0.64	1.52		

5 As before, the first two layers 80 and 82 comprise the primer layer 16 (shown in Figure 1). Layer 80 is a solution of VITEL™ PE2200 resin in MEK at 16.7% solids. Layer 82 is also a solution of VITEL™ PE2200 resin in MEK, but at 42.7% solids. Layer 82 is completely miscible with Layer 80. The third layer 84 is a photothermographic emulsion layer 14 10 (shown in Figure 1). As shown in Table C-2, its density is less than that of Layer 82. The fourth layer 86 is a topcoat layer 12 (shown in Figure 1). The solution properties for the four coating layers are detailed in Table C-2, shown below. The reported value of viscosity is as measured by a Brookfield viscometer, at shear rate of approximately 1.0 s⁻¹, and the 15 density is from a % solids vs. density curve for each of the layer formulations.

Table C-2

Layer	% solids	Viscosity, cP	Density, g/cm ³	Wet Thickness W, μm
80	16.7	10	0.86	5
82	42.7	1400	0.96	7.5
84	37.0	1250	0.92	70.8
86	14	1010	0.85	22.8

Coating was carried out at 30.5 m/min. at a coating gap G of 0.25 mm from the back-up roller and an applied vacuum of 2.5 mm of H₂O across the coating bead. No strikethrough was observed on the slide surface and excellent coating quality was achieved.

Example 4:

Four solution layers were coated onto a blue tinted polyethylene terephthalate substrate (0.17 mm thick, 71 cm wide) with the preferred slide set-up as described, with a slide angle S (see Figure 4) of 25° and a position angle P of -7°. The slide set-up used is shown below in Table D-1.

Table D-1

Layer	Slot Height, mm	Slot Step, mm	Slide Angle S, °	Position Angle P, °
80	0.13	0	25	-7
82	0.38	0		
84	0.64	1.52		
86	0.64	1.52		

As before, the first two layers 80 and 82 comprise the primer layer 16 (shown in Figure 1). Layer 80 is a solution of VITEL™ PE2200 resin in

MEK at 14.0% solids. Layer 82 is also a solution of PE2200 resin in MEK, but at 33.0% solids. Layer 82 is completely miscible with Layer 80. The third layer 84 is a photothermographic emulsion layer 14 (shown in Figure 1). As shown below in Table D-2, its density is equal to that of 5 Layer 82. The fourth layer 86 is a topcoat layer 12 (shown in Figure 1). The solution properties for the four coating layers are detailed below in Table D-2. The reported value of viscosity is as measured by a Brookfield viscometer, at shear rate of approximately 1.0 s^{-1} , and the density is from a % solids vs. density curve for each of the layer formulations.

10

Table D-2

Layer	% solids	Viscosity, cP	Density, g/cm ³	Wet Thickness W, μm
80	14.0	7.5	0.85	5.0
82	33.0	300	0.92	1.5
84	37.3	1200	0.92	72.8
86	13.7	950	0.85	22.6

Coating was carried out at 30.5 m/min. at a coating gap G of 0.25 mm from the back-up roller and an applied vacuum of 13 mm of H₂O across the coating bead. No strikethrough was observed on the slide 15 surface and excellent coating quality was attained.

Example 5:

Four solution layers were coated onto a blue tinted polyethylene terephthalate substrate (0.17 mm thick, 71 cm wide) with the preferred slide set-up as described, with a slide angle S (see Figure 4) of 25° and a 20 position angle P of -7°. The slide set-up used is shown below in Table E-1.

Table E-1

Layer	Slot Height, mm	Slot Step, mm	Slide Angle S, °	Position Angle P, °
80	0.13	0	25	-7
82	0.38	0		
84	0.64	1.52		
86	0.64	1.52		

As before, the first two layers 80 and 82 comprise the primer layer 16 (shown in Figure 1). Layer 80 is a solution of VITEL™ PE2200 resin in 5 MEK at 10.6% solids. Layer 82 is also a solution of VITEL™ PE2200 resin in MEK, at 43.2% solids. Layer 82 is completely miscible with Layer 80. The third layer 84 is a photothermographic emulsion layer 14 (shown in Figure 1). As shown in Table E-2, its density is less than that of Layer 82. The fourth layer 86 is a topcoat layer 12 (shown in Figure 10 1). The solution properties for the four coating layers are shown below in Table E-2. The reported value of viscosity is as measured by a Brookfield viscometer, at shear rate of approximately 1.0 s^{-1} , and the density is from a % solids vs. density curve for each of the layer formulations.

Table E-2

Layer	% solids	Viscosity, cP	Density, g/cm ³	Wet Thickness W, μm
80	10.6	4	0.84	2.1
82	43.2	1775	0.96	2.5
84	35.1	1200	0.92	73.3
86	13.7	925	0.85	21.5

15

Coating was carried out at 30.5 m/min. at a coating gap G of 1.3 mm from the back-up roller and an applied vacuum of 18 mm of H₂O

across the coating bead. No strikethrough was observed on the slide surface, and excellent coating quality resulted.

Example 6:

Three solution layers were coated onto a blue tinted polyethylene 5 terephthalate substrate (6.8 mils thick, 28 inches wide) with the preferred slide set-up as described, with a slide angle S (see Figure 4) of 25° and a position angle P of -7°. The slide set-up used is shown below in Table F-1.

Table F-1

Layer	Slot Height, mm	Slot Step, mm	Slide Angle S, °	Position Angle P, °
80	0.13	0	25	-7
84	0.64	0.76		
86	0.64	0.76		

10

Layer 80 is a primer layer 16 (shown in Figure 1) and comprises a solution of Pentalyn-H resin in MEK at 50.0% solids. The second layer 15 84 is a photothermographic emulsion layer 14 (shown in Figure 1). The densities of solutions 80 and 84 are equal. The third layer 86 is a topcoat layer 12 (shown in Figure 1). The solution properties for the three coating layers are detailed in Table F-2, shown below. The reported value of viscosity is as measured by a Brookfield viscometer, at shear rate of approximately 1.0 s⁻¹, and the density is from a % solids vs. density curve for each of the layer formulations.

Table F-2

Layer	% solids	Viscosity, cP	Density, g/cm ³	Wet Thickness W, μm
80	50.0	5	0.92	9.6
84	37.3	1350	0.92	70.9
86	14	1010	0.85	21.7

Coating was carried out at 23 m/min. at a coating gap G of 0.25 mm from the back-up roller and an applied vacuum of 2.5 mm of H₂O across the coating bead. No strikethrough was observed on the slide surface and excellent coating quality was achieved.

Example 7

Three solution layers were coated onto a blue tinted polyethylene terephthalate substrate (0.17 mm thick, 71 cm wide) with the preferred slide set-up as described, with a slide angle S (see Figure 4) of 25° and a position angle P of -7°. This substrate had an antihalation back coat incorporating an antihalation dye. The slide set-up used is shown below in Table G-1.

Table G-1

Layer	Slot Height, mm	Slot Step, mm	Slide Angle S, °	Position Angle P, °
80	0.13	0	25	-7
84	0.64	1.52		
86	0.64	1.52		

15

The dried photothermographic element resulting from this coating does not contain a primer layer. The first and second layers 80 and 84 comprise a photothermographic emulsion layer 14 (shown in Figure 1).

Layer 84 was prepared substantially as described in U.S. Patent No. 5,541,054. Layer 80 was subsequently diluted from this solution to a lower % solids. The third layer 86 is a topcoat layer 12 (shown in Figure 1). It has a density lower than that of layer 84. The solution properties 5 for the three coating layers are detailed in Table G-2, shown below. The reported value of viscosity is as measured by a Brookfield viscometer, at shear rate of approximately 1.0 s^{-1} , and the density is from a % solids vs. density curve for each of the layer formulations.

Table G-2

Layer	% solids	Viscosity, cP	Density, g/cm ³	Wet Thickness W, μm
80	12.0	7.5	0.84	5.0
84	37.4	1025	0.93	72.3
86	13.7	888	0.85	21.6

10

Coating was carried out at 23 m/min. at a coating gap G of 0.25 mm from the back-up roller and an applied vacuum of 10 mm of H₂O across the coating bead. Note that in this example, the first carried layer, self-cleanable by the carrier layer, is of 72.3 μm thickness. No 15 strikethrough was observed on the slide surface and excellent coating quality was achieved.

Example 8:

Four solution layers were coated onto a blue tinted polyethylene terephthalate substrate (0.17 mm thick, 71 cm wide) with the preferred 20 slide set-up as described, with a slide angle S (see Figure 4) of 25° and a position angle P of -7°. The slide set-up used is shown below in Table H-1.

Table H-1

Layer	Slot Height, mm	Slot Step, mm	Slide Angle S, °	Position Angle P, °
80	0.13	0	25	-7
82	0.38	0		
84	0.64	1.52		
86	0.64	1.52		

As above, the first two layer 80 and 82 comprise the primer layer 16 (shown in Figure 1). Layer 80 is a solution of VITEL™ PE2200 resin in 5 MEK at 14.0% solids. Layer 82 is also a solution of VITEL™ PE2200 resin in MEK, but at 40.3% solids. The third layer 84 comprises a photo-thermographic emulsion layer 14 (shown in Figure 1). The fourth layer 86 is a topcoat layer 12 (shown in Figure 1). The solution properties for the four coating layers are detailed in Table H-2, shown below. The 10 reported value of viscosity is as measured by a Brookfield viscometer, at shear rate of approximately 1.0 s^{-1} , and the density is from a % solids vs. density curve for each of the layer formulations.

Table H-2

Layer	% solids	Viscosity, cP	Density, g/cm ³	Wet Thickness W, μm
80	14	7.5	0.85	5.0
82	40.3	1120	0.95	2.5
84	37.1	1120	0.92	71.8
86	12.7	1300	0.83	20.1

15 Coating was carried out at line speeds ranging from 30.5 m/min. at a coating gap G of 0.25 mm from the back-up roller and an applied vacuum of 30 mm of H₂O across the coating bead to 152 m/min. at a

coating gap G of 0.25 mm and an applied vacuum level of 63 mm of H₂O. No strikethrough was observed on the slide surface at any speed and excellent coating quality was achieved.

Example 9

5 The following example demonstrates that increased thickness of the first carried layer can slow penetration of further carried layers and prevent strikethrough.

The solutions prepared as described in Example 2 (Comparative) were coated onto a clear polyethylene terephthalate substrate (0.05 mm 10 thick, 22 cm wide) as described in Example 2 except that the wet thickness of layer 82 was increased from 5 µm to 17 µm. Coating was carried out at 30.5 m/min. at a coating gap G of 0.25 mm from the back-up roller and at an applied vacuum of 25 mm of H₂O across the coating bead. No strikethrough was observed on the slide surface and excellent 15 coating quality was achieved.

Example 10

Example 7 was repeated using pure MEK fed through slot 46. This example demonstrates the use of pure organic solvent as a carrier layer. The minimal strikethrough that was observed on the slide surface was 20 quickly self-cleaned and excellent coating quality was achieved.

Example 11

Three solution layers were coated onto a blue tinted polyethylene terephthalate substrate (0.17 mm thick, 71 cm wide) with the preferred slide set-up as described, with a slide angle S (see Figure 4) of 25° and a 25 position angle P of -7°. All the slots were of constant slot height across the full width. This substrate had an antihalation back coat incorporating an antihalation dye. The slide set-up used is shown below in Table I-1.

Table I-1

Layer	Slot Height, mm	Slot Step, mm	Slide Angle S, °	Position Angle P, °
80	0.13	0	25	-7
84	0.64	1.52		
86	0.64	1.52		


The dried photothermographic element resulting from this coating did not contain a primer layer. As before, the first and second layers 80 and 84 comprise a photothermographic emulsion layer 14 (shown in Figure 1). Layer 84 was prepared substantially as described in PCT publication WO 96/33442. Layer 80 was subsequently diluted from this solution to a lower % solids. The third layer 86 is a topcoat layer 12 (shown in Figure 1). The solution properties for the three coating layers are shown below in Table I-2. The reported value of viscosity is as measured by a Brookfield viscometer, at shear rate of approximately 1.0 s⁻¹ and the density is from a % solids vs. density curve for each of the layer formulations.

Table I-2

Layer	% solids	Viscosity, cP	Density, g/cm ³	Wet Thickness W, μm
80	10.99	6	0.83	5
84	36.7	1375	0.92	66.4
86	13.51	1400	0.85	23.91

15

Coating was carried out at 21 m/min. at a coating gap G of 0.25 mm from the back-up roller and an applied vacuum of 20 mm of H₂O across the coating bead. The optical density profile obtained with this conventional slot arrangement is shown in the plot below.



As seen, a heavy edge bead results and an edge waste of about 3.5 cm is created (before uniform coating weight is achieved).

5 Example 12

Three solution layers were coated onto a blue tinted polyethylene terephthalate substrate (0.17 thick, 71 cm wide). This substrate had an antihalation back coat incorporating an antihalation dye. The preferred slide set-up was used, as described, with a slide angle S (see Figure 4) of 10 25° and a position angle P of -7° . The slot height of slot 50 (see Figure 4) was modified with the help of a wedge-shaped shim to result in a slot shape described above in Figures 11 and 12, with $W = 63.5$ cm and $V = 62.2$ cm. The slot heights for the other slots were constant over their entire length. The slide set-up used is shown below in Table 15 J-1.

Table J-1

Layer	Slot Height, mm	Slot Step, mm	Slide Angle S, °	Position Angle P, °
80	0.13	0	25	-7
84	0.64	1.52		
86	0.64	1.52		

The dried photothermographic element resulting from this coating did not contain a primer layer. As before, the first and second layers 80 and 84 5 comprised a photothermographic emulsion layer 14 (shown in Figure 1). Layer 84 was prepared substantially as described in PCT publication WO 96/33442. Layer 80 was subsequently diluted from this solution to a lower % solids. The third layer 86 is a topcoat layer 12 (shown in Figure 1). The solution properties for the three coating layers are shown 10 below in Table J-2. The reported value of viscosity is as measured by a Brookfield viscometer, at shear rate of approximately 1.0 s^{-1} and the density is from a % solids vs. density curve for each of the layer formulations.

Table J-2

Layer	% solids	Viscosity, cP	Density, g/cm ³	Wet Thickness W, µm
80	9.13	6	0.82	5
84	35.61	1581	0.92	71.9
86	14.75	2000	0.85	25.9

15

Coating was carried out at 21 m/min. at a coating gap G of 0.25 mm from the back-up roller and an applied vacuum of 13 mm of H₂O across the coating bead. The optical density profile obtained with this chamfered slot arrangement is shown by the dashed line in the plot

shown above, which is entitled "Comparison of Edge Profile With Constant Shim Height Vs. Chamfered Shim Height." As seen, the heavy edge bead is virtually eliminated (replaced with a relatively immediate monotonic rise in thickness, and, therefore, in optical density) which 5 results in (a) reduced edge waste, in one case from about 3.5 cm to about 2 cm, (b) reduced inadvertent coating of idler rollers with a coating fluid, a.k.a. "pick-off", (c) reduced hardbanding.

Reasonable modifications and variations are possible from the foregoing disclosure without departing from either the spirit or scope of 10 the present invention as defined by the claims. For example, the invention is applicable to fluid systems other than the imaging systems described herein. One such fluid system is one used in the manufacture of data storage media or elements (e.g., magnetic computer tape, floppy or rigid disks or diskettes, and the like). Another such fluid system can 15 be one used in the manufacture of another form of imaging media (e.g., thermographic, photographic, and still other forms of imaging media or elements). A variety of other fluid systems (e.g., for photoresist elements) which can benefit by multi-layer coating techniques will benefit from the present invention.

WE CLAIM:

1. A method for minimizing waste resulting from defects caused at the edges of a coating on a substrate (18) which was applied to the substrate by a slide coater (34), the slide coater having at least first slot (46) through which a first coating fluid (55) flows and a second slot (48) through which a second coating fluid (60) flows, the first slot having first slot width which includes a first slot main portion and first slot right and left end portions, the method comprising the steps of:
 - 10 flowing the first coating fluid through the first slot main portion at a first flow rate and onto a first slide surface (53) and further onto the substrate;
 - 15 flowing the first coating fluid through the first slot end portions onto the first slide surface and further onto the substrate, the first coating fluid flowing from the first slot right end portion having a second flow rate and the first coating fluid flowing from the first slot left end portion having a third flow rate, the second and third flow rates being different from the first flow rate; and
 - 20 flowing the second coating fluid through the second slot and onto a second slide surface (53), the second slide surface being positioned relative to the first slide surface and oriented such that the second coating fluid flows from the second slide surface onto the first coating fluid on the first slide surface and such that the first and second coating fluids flow onto the substrate.
- 25 2. The method of claim 1, wherein the first flow rate is greater than the second and third flow rates.

3. The method of claim 2, wherein the second and third flow rates are substantially equal.

4. The method of claim 1, wherein the first flow rate and the 5 second and third flow rates causes the first coating fluid to have a fluid thickness which is generally uniform on the first slide surface adjacent the first slot main portion and which is generally decreasing on the first slide surface adjacent at least one of the first slot right and left portions.

10 5. The method of claim 4, wherein the fluid thickness is generally decreasing on first slide surface adjacent to both the first slot right and left portions.

6. The method of claim 1, wherein the difference between the 15 first flow rate and the second and third flow rates prevents the formation of a coating thickness at one or both of the edges of the coating fluid on the substrate which is sufficiently greater than the coating thickness between the two edges.

20 7. The method of claim 1, the first slot having a first slot height H, wherein the step of flowing the first coating fluid through the first slot right end portion at the second flow rate and through the first slot left end portion at the third flow rate comprises the steps of:

25 forming the first slot such that the first slot height at least at one of the first slot right and left end portions is less than the first slot height at the first slot main portion; and

flowing the first coating fluid through the first slot such that the first coating fluid flows onto the first slide surface.

8. The method of claim 7, the forming step forming the first slot such that the first slot height at the first slot right end portion and the first slot left portion is less than the first slot height at the first slot main portion.

5

9. The method of claim 7, wherein the first slot has first slot right and left edges, and wherein the forming step causes the first slot height to decrease within a range of between 2.5 and 25.4 mm from at least one of the first slot right and left edges.

10

10. The method of claim 9, wherein the forming step causes the first slot height to be uniform for approximately 90 percent of the first slot length and to be decreasing for approximately 10 percent of the first slot length.

15

11. The method of claim 1, wherein the first slot having a first slot length and the second slot having a second slot length which is substantially equal to the first slot length.

20

12. The method of claim 1, further comprising the step of flowing a third coating fluid (66) through a third slot (50) and onto a third slide surface (53), the third slide surface being positioned relative to the first and second slide surfaces and oriented such that the third coating fluid flows from the third slide surface onto the second coating fluid on the second slide surface and such that the first, second, and third coating fluids flow onto the substrate.

25
13. The method of claim 1, wherein the first and second coating fluids are fluids used in preparing an imaging element.

14. The method of claim 1, wherein the first and second coating fluids are fluids for preparing a data storage element.

5 15. The method of claim 1, the first slot having a first slot depth, wherein the step of flowing the first coating fluid through the first slot right end portion at the second flow rate and through the first slot left end portion at the third flow rate comprises the steps of:

10 forming the first slot such that the first slot depth at least at one of the first slot right and left end portions is greater than the first slot depth at the first slot main portion; and

flowing the first coating fluid through the first slot such that the first coating fluid flows onto the first slide surface.

15 16. The method of claim 15, the forming step forming the first slot such that the first slot depth at the first slot right end portion and the first slot left portion is greater than the first slot depth at the first slot main portion.

20 17. The method of claim 15, wherein the first slot has first slot right and left edges, and wherein the forming step causes the first slot depth to decrease within a range of between 5 and 13 mm from at least one of the first slot right and left end portions.

25 18. The method of claim 13, further comprising the steps of:
slitting the coated web to create at least one slit roll; and
converting the slit roll into sheets of sensitized imaging media.

19. The method of claim 14, further comprising the steps of:

slitting the coated web to create at least one slit roll; and
converting the slit roll into sheets of data storage media.

1 / 6




Fig. 1




Fig. 2




Fig. 3




Fig. 4




Fig. 5




Fig. 6




Fig. 7

4/6




Fig. 8




Fig. 9




Fig. 10






Fig. 11

6/6

**Fig. 12****Fig. 13**

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 97/19807

A. CLASSIFICATION OF SUBJECT MATTER
 IPC 6 B05D1/34 G03C1/74 B05C5/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
 IPC 6 B05C B05D G03C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DE 30 37 612 A (AGFA GEVAERT AG) 13 May 1982 see page 5, line 12 - page 8, line 24; figures 2,3 see page 9, line 22 - page 10, line 6 see page 11, line 1 - line 13 ---	1-19
A	US 4 297 396 A (TAKEHARA NOBUMITSU ET AL) 27 October 1981 see column 1, line 56 - column 2, line 16 see column 2, line 33 - line 61 see claims 1-8; figure 2 ---	1-19
A	US 4 313 980 A (WILLEMSENS KAREL S) 2 February 1982 see column 1, line 1 - column 2, line 68 see claims 5-10 see figures 3,4; example 2 ---	1-19
	-/-	

Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

° Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

1

Date of the actual completion of the international search

Date of mailing of the international search report

25 February 1998

20. 03. 98

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel: (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Lindner, T

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 97/19807

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 313 043 A (FUJI PHOTO FILM CO LTD) 26 April 1989 see page 2, line 37 - page 3, line 45 ---	1
A	EP 0 051 238 A (AGFA GEVAERT AG) 12 May 1982 see page 16, line 21 - page 19, line 15 see figures 3,4 ---	1
A	EP 0 084 450 A (TETRA PAK INT) 27 July 1983 see claims 1-4 see figures 3-5 -----	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 97/19807

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
DE 3037612 A	13-05-82	JP 1714916 C JP 3071185 B JP 57110364 A	27-11-92 12-11-91 09-07-82
US 4297396 A	27-10-81	JP 1187707 C JP 55084577 A JP 58022266 B DE 2950947 A GB 2037189 A,B	30-01-84 25-06-80 07-05-83 10-07-80 09-07-80
US 4313980 A	02-02-82	CA 1140001 A EP 0018029 A JP 1567743 C JP 55139865 A JP 63032511 B	25-01-83 29-10-80 10-07-90 01-11-80 30-06-88
EP 0313043 A	26-04-89	DE 3853978 D DE 3853978 T EP 0622667 A JP 1231962 A JP 2646251 B US 4977852 A US 4976999 A	20-07-95 02-11-95 02-11-94 18-09-89 27-08-97 18-12-90 11-12-90
EP 0051238 A	12-05-82	DE 3041721 A JP 57107263 A	09-06-82 03-07-82
EP 0084450 A	27-07-83	JP 58124618 A AU 556108 B AU 1024683 A BR 8300062 A GB 2114050 A,B	25-07-83 23-10-86 28-07-83 20-09-83 17-08-83