

(12) STANDARD PATENT
(19) AUSTRALIAN PATENT OFFICE

(11) Application No. **AU 2003200906 B2**

(54) Title
A Method for the Production of Powder with High Tannin Content and its Use

(51) International Patent Classification(s)
A23L 1/30 (2006.01) **C09J 161/06** (2006.01)
B02C 21/00 (2006.01) **C09J 197/00** (2006.01)
B07B 9/00 (2006.01) **C09J 197/02** (2006.01)
C08H 5/00 (2006.01) **C09J 199/00** (2006.01)
C08H 5/04 (2006.01) **C09J 201/00** (2006.01)
C08L 97/02 (2006.01) **C08L 61/00** (2006.01)
C09J 11/06 (2006.01) **C08L 61/06** (2006.01)
C09J 161/00 (2006.01) **C08L 97/00** (2006.01)

(21) Application No: **2003200906** (22) Date of Filing: **2003.03.07**

(30) Priority Data

(31) Number (32) Date (33) Country
2002-064178 **2002.03.08** **JP**

(43) Publication Date: **2003.09.25**

(43) Publication Journal Date: **2003.09.25**

(44) Accepted Journal Date: **2007.08.02**

(71) Applicant(s)
Monash University;Kabushiki Kaisha Wood One

(72) Inventor(s)
Tsunoda, Toshihiko;Jiang, Huijian;Lawson, Frank;Yano, Hiroyuki;Nakamoto, Yusho;Ono, Keiko;Uhlherr, Peter Heinz Theodore;Yazaki, Yoshikazu

(74) Agent / Attorney
Spruson & Ferguson, Level 35 St Martins Tower 31 Market Street, Sydney, NSW, 2000

(56) Related Art
WO 98/37148
US 2563086
EP 1245613 (AU equivalent 29260/02)

A Method for the Production of Powder with High Tannin Content and Its Use

Abstract

The present invention provides a method of producing powder with a high tannin content, the method including pulverising a tannin-containing plant such as bark of radiata pine (*Pinus radiata*) and
5 classifying the pulverised material into fine particles having a desired particle size, for example, fine particles having a particle diameter of 100µm to 1000µm or less, and powder with a high tannin content produced by such a method.

The thus obtained powder with a high tannin content exhibits excellent characteristics when used as an adhesive, a binder, etc. for wood materials.

AUSTRALIA

PATENTS ACT 1990

COMPLETE SPECIFICATION

FOR A STANDARD PATENT

ORIGINAL

Name and Address of Applicants:	Kabushiki Kaisha Wood One 1-1, Mokuzaiko-Minami Hatsukaichi-shi Hiroshima-ken Japan
	Monash University Wellington Road Clayton Victoria 3800 Australia
Actual Inventor(s):	Yusho Nakamoto, Toshihiko Tsunoda, Keiko Ono, Hiroyuki Yano, Yoshikazu Yazaki, Huijian Jiang, Frank Lawson and Peter Heinz Theodore Uhlherr
Address for Service:	Spruson & Ferguson St Martins Tower, Level 35 31 Market Street Sydney NSW 2000 (CCN 3710000177)
Invention Title:	A Method for the Production of Powder with High Tannin Content and its Use

The following statement is a full description of this invention, including the best method of performing it known to me/us:-

A METHOD FOR THE PRODUCTION OF POWDER WITH HIGH TANNIN CONTENT AND ITS USE

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to a method for the production of powder with high tannin content, powder with high tannin content obtained by the same method, and a use thereof. More specifically, the present invention relates to a method for the production of powder with high tannin content in an adhesive or a binder for wood as a main component, molding, a binder for molding, a filler an enhancer, a health-care food and a drug.

2. Description of the Related Art

Various components are widely present in plants. It is known that extraction of such components with solvents such as water, aqueous solvents and lower alcohols can give rise to a substance usually called tannin that can be used as an adhesive, a binder, a drug or the like.

In the case where tannin is used as a raw material of adhesives, binders or moldings, plant resources with much tannin contents, for example, bark or wood of mangrove, acacia, radiata pine (*Pinus radiata*), pine, larch, quebracho, eucalyptus, oak, or Japanese hemlock are crushed to a suitable particle size. Then, tannin is extracted therefrom with water, an aqueous solvent or organic solvent such as a lower alcohol and filtered. The tannin filtrate is concentrated and then used as high concentration tannin solutions or it is dried and then used as powdered tannin.

To efficiently extract tannin, it is advantageous to crush plant resources into particles as small as possible so that an extraction solvent can sufficiently and speedily penetrate into the substances to be extracted, i.e., the plant resources. Although the particle size distribution of plant resources after crushing may be different depending on the kind of plant resource, such as bark, it has been known that a filter having a pore diameter of 20 to 60 μm is suitable for the filtration of tannin solutions in a filtration step after the extraction. However, use of such a filter could in some cases result in formation of a large amount of fine powder that is so fine as to cause the problem of clogging of the filter, so that efficient filtration cannot be performed.

Conventionally, the extraction has been performed after removing the fine particles obtained after the pulverization. However, mere removal of the fine

particles not only results in a great loss of raw material but also raises a problem of causing environmental pollution when they are discarded.

SUMMARY OF THE INVENTION

5 According to a first aspect of the present invention, there is provided a method for the production of powder with a high tannin content, the powder having a particle size of 70 μm or less, comprising crushing a tannin-containing plant resource and classifying the pulverized plant resource.

10 According to a second aspect of the present invention, there is provided powder with a high tannin content, the powder having a particle size of 70 μm or less, obtained by a production method according to the first aspect.

According to a third aspect of the present invention, there is provided a method of using powder with a high tannin content according to the second aspect as a substitute for conventional tannin.

15 According to a fourth aspect of the present invention, there is provided use of a powder with a high tannin content, the powder having a particle size of 70 μm or less, as a substitute for conventional tannin.

A basic objective of the present invention is to effectively utilize such a fine particle fraction obtained after crushing of a plant resource.

20 Therefore, an objective of the present invention is to provide a method for production of powder with a high tannin content, which is free of the above-mentioned problems.

Another objective of the present invention is to provide powder with a high tannin content produced by such a method.

25 Still another objective of the present invention is to provide a method of using such powder.

Under the circumstances, the inventors of the present invention have made extensive studies with a view to effective utilization of the above-mentioned fine particles formed when a plant resource is crushed into particles having a particle size suitable for the extraction of tannin which is conventionally performed. That is, the inventors
30 extracted the fine particles with methanol by a conventional method to obtain tannin and then examined the Stiasny values of the obtained tannin (ratio of tannin contained in the extract that reacts with aldehyde). As a result, it was revealed that the methanol extract was obtained from the fine particles at high yields and the Stiasny value of tannin thereof
35 was very high.

Accordingly, the inventors prepared a liquid from the powder fraction of the pulverized and classified fine particles without extraction as a main component of an adhesive and performed adhesive tests, the results of which revealed that the liquid had an adhesive strength identical to or higher than that of the conventional tannin adhesive.

5 Further, the inventors have confirmed that adhesives prepared by adding the powder fraction of the mechanically crushed and classified fine particles to conventional tannin as a filler or adhesive enhancer also have an adhesive strength identical to or higher than that of conventional tannin adhesives.

10 Similarly, also in the case of adhesives composed of a synthetic phenol resin adhesive and the above-mentioned powder fraction added thereto as a filler or adhesive enhancer, improvements in adhesive strength and water resistance have been observed.

Therefore, the present invention provides a method for production of powder with a high tannin content, comprising crushing a tannin-containing plant resource and classifying the pulverized plant resource.

The present invention also provides powder with a high tannin content obtained by the above-mentioned production method.

Furthermore, the present invention provides a method of using the powder with a high tannin content as a substitute for tannin.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

The present invention can be applied to various plant resources with tannin without any particular limitations. Therefore, preferred plant resources are those plants conventionally used for the extraction of tannin. Furthermore, to obtain a fine powder fraction having characteristics that can be utilized for adhesives, binders, moldings, etc., bark and wood of mangrove, acacia, radiata pine (*Pinus radiata*), pine, larch, eucalyptus, oak, hemlock, quebracho, and the like are desirable. In particular, the bark thereof is preferable from the viewpoint of utilization of resources and availability of powder with high tannin content.

In crushing of plant resources, in a case of plant resources with high tannin contents, e.g., forest resources, bark, etc. are crushed as they are or after adjustment to a suitable moisture content, into a particle size of 1 mm or less or formed into a fiber by a hammer mill, a Wiley mill, a ball mill, a roller mill or a high speed rotary grinder and used.

The method for crushing is not particularly limited; however, crushing may be performed preferably by a method in which no high temperature is reached at the time of crushing, and for a short time.

The plant resources crushed to a size of 1 mm or less is fed to a classifier and classified into fine particle powder having a particle size of 10 to 1000 μm , preferably not greater than 100 μm , and more preferably 50 to 80 μm or less by a screen classifier such as a rotary drum screen or a sieve shaker, or a dry classifier based on, for example, gravitational classification, inertial classification or centrifugal classification.

The method of classification is not particularly limited but is advantageously performed for a short time and by a method in which no high temperature is reached at the time of classification, mainly based on mechanical classification of particle size.

Furthermore, since the particle size of fractions of particles with high tannin

content may vary depending on the kind of plant resource and configuration of particles after crushing, the particle size for the classification is not particularly limited. The particle size of fine powder that is used as it is for adhesives, binders, moldings, etc. is preferably 100 μm or less, more preferably 60 to 70 μm or less. Those fractions with a particle size of 100 to 1000 μm may be recycled to be used in the step of tannin extraction.

The particles after classification may further be crushed depending on the purpose for which they are subsequently used.

The tannin content (Stiasny value) of the extractives which is extracted with methanol from the fine powder with high tannin content obtained by the present invention, which reacts with aldehyde is 80% or more (preferably 90% or more), to 106.8% which is a theoretical value of a reaction product with aldehyde in case where the tannin is 100% catechine as a standard (weight percentage: this applies to rest of the specification).

A mixed solution of the fine powder with high tannin content and an aqueous solution as an adhesive and a binder desirably has a viscosity of 6000 mPa.s or less which is suitable for coating in an extruder or a flow coater of a coating apparatus. A mixed solution with a solids content of 35 to 45% produces with an adhesion strength equal to that of phenol resin. An adhesive, which is prepared from the fine powder with high tannin content obtained by the present invention, has good processing properties as well as good coating properties. Such an adhesive has high adhesion strength to wood test pieces, and wood failure is also observed. Furthermore, the fine powder with high tannin content obtained by the present invention may be added to tannin adhesives and other resins, for example, synthetic formaldehyde resin. They can be mixed at a ratio in the range of (tannin or synthetic resin) : (powder with high tannin content) = 1:99 to 99:1.

The reason that the fine particles obtained by the method of the present invention have high tannin content has not been elucidated in detail yet. Presumably, the portion of a plant resource containing a significant amount of tannin is more easily crushed than the other portions thereof. Therefore, fine particles portion generated upon crushing into a size suitable for filtration after extraction in a conventional tannin extraction operation may be used. Alternatively, as in the case of outer bark of radiata pine (*Pinus radiata*), the content of tannin may be measured in advance and only the portions of the bark that are known to have high tannin contents may be crushed and used.

The powder with high tannin content obtained by the production method of the present invention can be used in various materials such as an adhesive, a binder, molding, a binder for molding, a filler, an enhancer, a health-care food, and a drug either singly or as an enhancer or filler to the conventional tannin powder or high concentration tannin solution.

Examples

Hereinafter, the present invention will be described by way of illustrative examples. It should be noted that the present invention is not limited thereto. Particularly, here, bark of radiata pine (*Pinus radiata*) and of acacia (*Acacia mangium*) is divided into outer and inner bark and experiments on the outer bark, which contains more tannin than the inner bark, will be explained. However, the bark can be crushed directly without dividing into outer bark and inner bark and then classified into a predetermined particle size to obtain bark as a fine powder with high tannin content. In the following examples, unless otherwise specified, "%" and "parts" denote "% by weight" and "parts by weight".

Example 1

As a plant resource containing tannin, radiata pine (*Pinus radiata*) bark discarded and discharged in large amounts in the step of processing wood was used. The bark was separated into the outer bark that is corky and has higher tannin content and the inner bark that is fibrous and has lower tannin content by the method described in Japanese Patent Application Laid-open No. 2002-302497. The separated outer bark of radiata pine (*Pinus radiata*) was dried to have a moisture content of 20% or less and then crushed in a hammer mill so as to pass through a 1.6 mm mesh screen. The outer bark powder pulverized to a particle size of 1.6 mm or less was classified into eight particle size fractions in a sieve shaker (Fisher-Wheeler Sieve Shaker) provided with seven sieves (Endecotts BS410) of 38, 45, 53, 63, 75, 90 and 106 μ m mesh openings, respectively.

The eight particle size fractions obtained by use of the above-mentioned seven types of sieves were each extracted with methanol for 15 minutes to obtain tannin/methanol solutions. Methanol was evaporated from the tannin/methanol solutions to obtain concentrated tannin solutions, which then were subjected to freeze drying to obtain tannin powder. Table 1 shows the yield of extractives by such methanol extraction (tannin powder), with respect to the total dry weight of the bark,

and the Stiasny value of tannin thereof. As can be seen from Table 1, the fractions of high classification yields were fractions with a particle size of not smaller than 106 μ m and of 53 μ m to 63 μ m and, furthermore, fractions having high methanol extract yields were fractions with a particle size of not greater than 63 μ m. The fraction having the highest Stiasny value of tannin was the outer bark powder fraction with a particle size of 53 μ m to 63 μ m. The fine powder with a particle size of not greater than 63 μ m causes clogging when filtration is performed through a filter with a pore size of 20 μ m to 60 μ m in the conventional tannin extraction.

Table 1

Particle size distribution, extractive yield and Stiasny values of the powder from radiata pine (*Pinus radiata*) outer bark

Particle size (μ m)	Classification yield (%)	Extractives	
		Extract yield (%)	Stiasny values* (%)
>106	36.6	38.9	95.33
90-106	7.0	36.8	91.62
75-90	4.7	37.3	91.18
63-75	16.9	44.1	98.31
53-63	34.8	69.5	103.4
45-53	0.22	68.7	-
38-45	0.04	-	-
<38	0.005	-	-

* Stiasny value of 106.8% for 100% catechin

Water was added to prepare slurry such that the obtained resin powder with a particle size of 53 μ m to 63 μ m occupies a solid content of 40% of the resulting mixture. Then, 0.5part of sodium hydroxide and 10 parts of paraformaldehyde were mixed with respect to 100 parts of the outer bark powder with the slurry to prepare an adhesive (radiata pine (*Pinus radiata*) outer bark powder adhesive). Mixing examples and liquid viscosity of the adhesives are shown in Table 2.

On the other hand, the outer bark powder having a particle size greater than 63 μ m was extracted with methanol to obtain a tannin/methanol solution, from which methanol was then evaporated, followed by subjecting the residue to freeze drying to obtain a tannin powder. Similarly, by using the obtained tannin powder, a tannin adhesive (radiata pine (*Pinus radiata*) outer bark tannin adhesive) based on the formulation shown in Table 2 was obtained.

As can be seen from Table 2, it is revealed that the adhesive containing the outer bark powder with a particle size of 53 to 63 μm had a viscosity identical with that of the conventional tannin adhesive, even without adding fillers such as coconut shell flour, wheat flour, and macadamia nuts shell flour. This viscosity was within the range of 500 to 6,000 mPa.s, which is suitable for a coating apparatus such as an extruder or a flow coater.

Table 2 An adhesive formulation from Radiata pine (*Pinus radiata*) outer bark

Formulation	The outer bark powder adhesive	The outer bark tannin adhesive
Outer bark powder (53-63 μm)	100 parts	0 part
Extract	0 part	100 parts
Sodium hydroxide	0.5 part	0.5 part
Paraformaldehyde	10 parts	10 parts
Coconut shell flour	0 part	0 part
Wheat flour	0 part	0 part
Macadamia Nuts shell flour	0 part	10 parts
Water	150 parts	150 parts
Solids content in an adhesive liquid	30 - 40 (%)	30 - 40 (%)
Viscosity (mPa.s, 25°C)	1000 - 6000	1000 - 6000

The normal state and boiling adhesion test results of each adhesive formulated according to Table 2 are shown in Table 3. Table 3 also shows the results of the same tests on a commercially available phenol resin adhesive. As can be seen from Table 3, in the normal state and under boiling conditions, the adhesives of the present invention exhibited an adhesive strength and wood failure which are both identical with or higher than those of the conventional tannin adhesive or phenol resin adhesive.

The adhesion strength test was conducted in accordance with Japanese Agricultural Standard (JAS). Veneers of radiata pine (*Pinus radiata*) were used as test pieces (specimen). Each veneer was coated with an adhesive in an amount of 150 to 200 g/m², and pressed under a cold pressure of 0.8 MPa for 5 minutes and

under a hot pressure of 1.0 MPa at 140°C for 7 minutes to be bonded to each other. The adhesion strength test was conducted with respect to 10 test pieces in dry strength (in which the test pieces were as initially produced) and 10 test pieces after boiling in water for 72 hours. Table 3 shows average results.

In each column of the adhesive test in Table 3, the numerical values in the upper rows indicate adhesive strength (kgf/cm²) and the numerical values in the brackets in the lower rows indicate wood failure (%) (the same applies to the subsequent tables).

Table 3 Bark/formaldehyde adhesive using radiata pine (*Pinus radiata*)
outer bark

Test veneer	Test conditions	Adhesion test (kgf/cm ²) (Wood failure(%))		
		Radiata pine (<i>Pinus radiata</i>) outer bark powder adhesive	Radiata pine (<i>Pinus radiata</i>) outer bark tannin adhesive	Phenol Resin adhesive
Radiata pine (<i>Pinus radiata</i>)	Normal state	19 (80)	17 (90)	15 (90)
	Boiling	10 (60)	12 (70)	10 (60)
Kapur	Normal state	21 (80)	25 (80)	23 (75)
	Boiling	16 (60)	17 (60)	15 (60)

Example 2

The fraction with high tannin content, 53-63 μm powder, of radiata pine (*Pinus radiata*) outer bark obtained in Example 1 was mixed with tannin powder obtained by methanol extraction of the bark or with commercially available phenol resin to prepare adhesives and their adhesive strength was examined. Table 4 shows mixing examples of adhesives and viscosity after mixing with adhesive liquid at a solids content of 40%.

As can be seen from Table 4, the adhesive liquid with the outer bark powder showed coatable viscosity.

Furthermore, the normal state and boiling adhesion test results of each adhesive formulated according to Table 4 are shown in Table 5. As can be seen from Table 5, in the normal state and under boiling conditions, the adhesives of the present invention exhibited an adhesive strength and wood failure which are both identical with or higher than those of the conventional tannin adhesive or phenol resin adhesive.

Table 4

Mixing samples of a bark adhesives using
Radiata Pine (*Pinus radiata*) outer bark

	Formulation	Mixing example 1	Mixing example 2	Mixing example 3
5				
10	Outer bark powder (53-63 μ m) Extract Commercially available phenol resin Sodium hydroxide Paraformaldehyde Coconut shell flour Wheat flour Macadamia nuts shell flour Water	50 parts 50 parts 0 part 0.5 parts 10.0 parts 0 part 0 part 0 part 150 parts	50 parts 0 part 50 parts 0.5 parts 10.0 parts 0 part 0 part 0 part 150 parts	70 parts 30 parts 0 part 0.5 parts 10.0 parts 0 part 0 part 0 150 parts
15	Solids content in an adhesive liquid	30 – 40 (%)	30 - 40(%)	30 - 40(%)
	Viscosity (mPa·s, 25°C)	2000 - 6000	2000 - 6000	3000 - 6000

Table 5 Radiata pine (*Pinus radiata*) outer bark/ and bark extract/ formaldehyde adhesives

5	Test veneer	Test conditions	Adhesion test: (kgf/cm ²) (Wood failure(%))		
			Mixing example 1	Mixing example 2	Mixing Example 3
10	Radiata pine (<i>Pinus radiata</i>)	Normal state	18 (80)	20 (80)	20 (70)
		Boiling	10 (60)	12 (60)	11 (70)
15	Kapur	Normal state	21 (80)	25 (90)	22 (80)
		Boiling	13 (60)	12 (70)	14 (70)
20					

Example 3

Acacia mangium bark was used as a plant resource. The bark was separated into outer bark having a high tannin content and inner bark having a low tannin content. The separated *Acacia mangium* outer bark was dried at 40°C so as to have a moisture content of 10 to 15% and then crushed in a Wiley mill by use of a 0.5 mm mesh screen. The thus obtained crushed *Acacia mangium* outer bark powder was charged to a sieve shaker (Fisher Wheeler Sieve Shaker) provided with four sieves of 63, 125, 250 and 500 µm mesh opening, and classified for a suitable time.

Five particle size fractions obtained by use of the four kinds of sieves were each extracted with methanol on a warm bath at 30°C for 1 hour to obtain tannin/methanol-extracted solutions. After evaporation of methanol and addition of a small amount of water, the extracted solutions were subjected to freeze drying to obtain tannin powders. Table 6 shows yields and Stiasny values of the extracts (tannin powders) obtained by extraction with methanol, based on the dry weight of total bark.

As can be seen from Table 6, the bark particle size fraction with a particle size of not greater than 63 µm, which could cause clogging when filtration is performed through a filter with a pore size of 20 to 60 µm in the conventional tannin extraction, had a high yield and a high Stiasny value of tannin when extracted with methanol.

Table 6 Particle size of outer bark powder, extractive yield and Stiasny value from *Acacia mangium*

Particle size (µm)	Classification yield (%)	Extract	
		Yield (%)	Stiasny value (%)
250 - 500	28.3	32.6	88.0
125 - 250	24.7	32.5	94.4
63 - 125	17.7	29.2	96.5
<63	29.3	49.4 - 55.1	97.5

Furthermore, a slurry was prepared such that the obtained resin powder with a particle size of not greater than 63 µm occupies a solid content of 40% of the resulting mixture. Then, 0.9 part of sodium hydroxide and 10 parts of

paraformaldehyde were mixed with respect to 100 parts of the outer bark powder with the slurry to prepare an adhesive. Table 7 shows mixing examples and paste viscosities of the adhesives.

With respect to outer bark powder having a size of greater than 63 μm , extraction with methanol was performed to obtain a tannin/methanol extracted solution, from which methanol was then evaporated, followed by adding a small amount of water thereto and then subjecting the residue to freeze drying to obtain tannin powder. Similarly, by using the tannin powder, a tannin adhesive based on the formulation shown in Table 7 was obtained.

As can be seen from Table 7, it was revealed that an adhesive containing the outer bark powder having a particle size of not greater than 63 μm had a viscosity identical with that of the conventional tannin adhesive, even without adding fillers such as coconut shell flour and wheat flour. This viscosity was within the range of 500 to 6,000 mPa.s, which is suitable for a coating apparatus such as an extruder or a flow coater.

Table 7 The outer bark adhesive formulation from *Acacia mangium*

Formulation	<i>Acacia mangium</i> outer bark powder adhesive	<i>Acacia mangium</i> outer bark tannin adhesive
Outer bark powder (<63 μm)	100 parts	0 part
Extract	0 part	100 parts
Sodium hydroxide	0.9 part	0.9 part
Paraformaldehyde	10 parts	10 parts
Coconut shell flour	0 part	0 part
Wheat flour	0 part	0 part
Macadamia nuts shell flour	0 part	10 parts
Water	140 parts	140 parts
Solids content in an adhesive liquid	30 - 40 (%)	30 - 40 (%)
Viscosity (mPa.s, 25°C)	3000 - 6000	4000 - 6000

The normal state and hot water and boiling adhesive test results of each adhesive formulated according to Table 7 are shown in Table 8. The adhesive tests

were performed according to JIS K-6851. As can be seen from Table 8, in the normal state and under hot water and boiling conditions, the adhesives of the present invention exhibited an adhesive strength and wood failure which are both identical with or higher than those of the conventional acacia tannin adhesive or phenol resin adhesive.

Table 8 *Acacia mangium* outer bark/ and outer bark extract/ formaldehyde adhesives

Test veneer	Test conditions	Adhesion test (kgf/cm ²)	
		<i>Acacia mangium</i> outer bark powder adhesive	Acacia tannin adhesive
Red meranti	Normal state	15.4	12.0
	Hot water	12.4	6.8
	Boiling	11.7	7.1

Example 4

Acacia mangium barks were used as a plant resource. The bark was separated into outer bark having a high tannin content and inner bark having a low tannin content. The separated *Acacia mangium* outer bark was dried at 40°C so as to have a moisture content of 10 to 15% and then crushed in a Wiley mill by use of a 0.5 mm mesh screen. Out of the thus crushed *Acacia mangium* outer bark powders, those which passed through a sieve of 63 µm mesh were used to produce moldings. More particularly, 0.5 g of paraformaldehyde was added to 5 g of the *Acacia mangium* powder and was well mixed. Then, the mixture was charged in a cylindrical mold having a diameter of 50 mm and pressed at a pressing pressure of 100 MPa and at a temperature of 160°C for 30 minutes to obtain moldings of about 2 mm in thickness. The density of the obtained moldings was about 1.4 g/cm³.

A sample having a width of 10 mm and a length of 40 mm was prepared from the moldings and the flexural strength of it was determined by a centrally concentrated load method. Young's modulus in flexure and flexural strength of the sample were 4 to 5 GPa and 40 to 50 MPa, respectively. The flexural strength increased by 30 to

40% by addition of 30% of wood flour (particle diameter: 63 μm or less) to the outer bark powder. Water absorbing rate and thickness swelling rate of the outer bark powder moldings after 1 hour's boiling were 3 to 4% and 4 to 5%, respectively. The water resistance value of the sample was substantially identical with that of novolak type phenol resin moldings containing 50% of wood flour prepared as a comparison. Thus, it was revealed that the molded product from *Acacia mangium* outer bark powder has excellent water resistance.

Example 5

Formaldehyde catching effect was measured.

The radiata pine (*Pinus radiata*) outer bark powder (particle size: 53 to 63 μm) of the present invention or conventional macadamia nuts shell flour was added as an additive to a commercially available phenol resin adhesive to prepare an adhesive paste. By using this adhesive paste, radiata pine (*Pinus radiata*) veneers each having a thickness of 4.0 mm were laminated to make a 5-ply plywood laminate. Mixing conditions of the adhesive are shown in Table 9.

For each sample board cut out from the thus made plywood laminate, the formaldehyde exhalation amount thereof was measured according to JAS and compared. As a result, it was revealed that the sample board made by laminating the veneers (developed product) with the adhesive containing the radiata pine (*Pinus radiata*) outer bark powder had a very small formaldehyde exhalation amount, which easily satisfied FCO (0.5 mg/l) or less according to the prescription by JAS.

The results of measurement of each test board are shown in Table 9. In Table 9, the conventional product indicates a plywood laminate laminated with an adhesive containing macadamia nuts shell flour.

Table 9

	Developed product	Conventional product
5		
	Commercially available phenol resin	100 parts
	Macadamia nuts shell flour	0 part
10		
	Radiata pine (<i>Pinus radiata</i>) outer bark powder (53 to 63 μ m)	10.0 parts
	Formaldehyde emission (mg/l)	0.10
		0.38

15 According to the present invention, mere crushing of a plant resource containing tannin and classification of fine particles having a certain particle size or less can give rise to powder with a high tannin content. Although it depends on the tannin content thereof, the obtained powder with a high tannin content, like the conventional tannin powder, can be used as an adhesive, binder, etc. or it can form

20 moldings by itself. Therefore, the present invention has various advantages, for example, in that the steps of extraction, concentration, drying, etc. needed in the conventional production method for tannin are unnecessary.

The claims defining the invention are as follows:

1. A method for the production of powder with a high tannin content, the powder having a particle size of 70 μm or less, comprising crushing a tannin-containing plant resource and classifying the pulverized plant resource.
- 5 2. A method for the production according to claim 1, wherein the powder has a particle size of no greater than 63 μm .
3. A method for the production according to claim 1 or claim 2, wherein the pulverization is mechanical pulverization.
4. A method for the production according to claim 3, wherein the mechanical
10 pulverization is performed by use of an apparatus selected from the group consisting of a hammer mill, a Wiley mill, a ball mill, a roller mill, and a high speed rotary crusher.
5. A method for the production according to any one of claims 1 to 4, wherein the classification is performed by use of a classifier.
6. A method for the production according to claim 5, wherein the classifier is
15 one selected from the group consisting of a screen classifier and a dry classifier based on gravitational classification, inertial classification and centrifugal classification.
7. A method for the production according to claim 6, wherein the screen classifier is a rotary drum screen or a sieve shaker.
8. A method for the production of powder with a high tannin content, said
20 method as claimed in claim 1 and substantially as hereinbefore described with reference to any one of the examples.
9. Powder with a high tannin content, the powder having a particle size of 70 μm or less, obtained by a production method according to any one of claims 1 to 8.
10. A method of using powder with a high tannin content according to claim 9 as
25 a substitute for conventional tannin.
11. A method according to claim 10, wherein the powder with a high tannin content is used as a substitute for conventional tannin, in one material selected from the group consisting of an adhesive, a binder, a moulded material, a binder for moulded materials, a filler, an adhesive enhancer, a health-care food, and a drug.
- 30 12. Use of a powder with a high tannin content, the powder having a particle size of 70 μm or less, as a substitute for conventional tannin.
13. Use according to claim 12, wherein the powder has a particle size of no greater than 63 μm .
14. Use according to claim 12 or claim 13, wherein the powder with a high tannin
35 content is used as a substitute for conventional tannin, in one material selected from the

group consisting of an adhesive, a binder, a molded material, a binder for molded materials, a filler, an adhesive enhancer, a health-care food, and a drug.

15. Use according to claim 12, substantially as hereinbefore described with reference to any one of the examples.

5

Dated 18 July 2007
Kabushiki Kaisha Wood One,
Monash University

Patent Attorneys for the Applicant/Nominated Person
SPRUSON & FERGUSON

10