



(86) Date de dépôt PCT/PCT Filing Date: 2007/06/12
(87) Date publication PCT/PCT Publication Date: 2008/01/10
(45) Date de délivrance/Issue Date: 2013/08/13
(85) Entrée phase nationale/National Entry: 2008/12/16
(86) N° demande PCT/PCT Application No.: EP 2007/055740
(87) N° publication PCT/PCT Publication No.: 2008/003567
(30) Priorité/Priority: 2006/07/04 (EP06116587.4)

(51) Cl.Int./Int.Cl. *C08G 18/36* (2006.01),
C08G 18/66 (2006.01)
(72) Inventeurs/Inventors:
ANDRIES, KRIS, BE;
MACKEN, JOHAN ANTOINE STEFAAN, BE
(73) Propriétaire/Owner:
HUNTSMAN INTERNATIONAL LLC, US
(74) Agent: SMART & BIGGAR

(54) Titre : PROCÉDE DE FABRICATION DE MOUSSES VISCOELASTIQUES
(54) Title: PROCESS FOR MAKING VISCO-ELASTIC FOAMS

(57) **Abrégé/Abstract:**

Process for making a slabstock, visco-elastic, flexible, polyurethane foam which process comprises reacting a polyisocyanate and a polyol at an index of 60 -95 and using a blowing agent, wherein 5-50 and preferably 10-40 % by weight of the polyol used is castor oil. The foams and a polyol composition are claimed as well.



(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
10 January 2008 (10.01.2008)

PCT

(10) International Publication Number
WO 2008/003567 A1

- (51) International Patent Classification:
C08G 18/36 (2006.01) *C08G 18/66* (2006.01)
- (21) International Application Number:
PCT/EP2007/055740
- (22) International Filing Date: 12 June 2007 (12.06.2007)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
06116587.4 4 July 2006 (04.07.2006) EP
- (71) Applicant (for all designated States except US): **HUNTS-
MAN INTERNATIONAL LLC** [—/US]; 500 Huntsman
Way, Salt Lake City, Utah 84108 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **ANDRIES,
Kris** [BE/BE]; Boonhof 16, B-3294 Molenstede (BE).
MACKEN, Johan Antoine Stefaan [BE/BE]; Lipsestraat
155, B-3150 Tildonk (BE).
- (74) Agents: **BAKEN, Philippus, Johannes, Leonardus,
Henricus** et al.; Everslaan 45, B-3078 Everberg (BE).
- (81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,

AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH,
CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG,
ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL,
IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK,
LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW,
MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL,
PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY,
TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA,
ZM, ZW.

- (84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, PL,
PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM,
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declaration under Rule 4.17:

— of inventorship (Rule 4.17(iv))

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: PROCESS FOR MAKING VISCO-ELASTIC FOAMS

(57) Abstract: Process for making a slabstock, visco-elastic, flexible, polyurethane foam which process comprises reacting a poly-
isocyanate and a polyol at an index of 60 -95 and using a blowing agent, wherein 5-50 and preferably 10-40 % by weight of the
polyol used is castor oil. The foams and a polyol composition are claimed as well.



WO 2008/003567 A1

85871-138

1

PROCESS FOR MAKING VISCO-ELASTIC FOAMS

The present invention is related to a novel process to prepare slabstock, visco-elastic foams. Such foams are traditionally made from polyether polyols which are made from ingredients obtained from treatment of crude oil.

Since crude oil is a resource which is not infinitely available there is a need to look for replacement. Surprisingly, we have found that (unmodified) castor oil is a good alternative for part of the polyether polyols used in slabstock, visco-elastic foams. Further the foams are more attractive from an olfaction point of view.

DE-19936481 proposes the use of modified castor oil in making sound insulating foams. In the examples a small amount of castor oil was employed. Visco-elastic foams have not been mentioned. DE-3316652 discloses the used of castor oil in making sound insulating foams having a density of at least 120 kg/m^3 . The use of castor oil in substantial amount in making slabstock, visco-elastic foams has never been proposed.

Therefore, according to one aspect, the present invention relates to a process for making a slabstock, visco-elastic, flexible, polyurethane foam comprising: reacting a polyisocyanate and a polyol at an index of 60-95 and using a blowing agent, wherein the polyol is a polyol composition comprising:

- b1) a polyoxyethylene-polyoxypropylene polyol, having an average nominal hydroxy functionality of 2-4 and an average equivalent weight of 1000-3000, wherein the oxyethylene (EO) is present as tipped EO and/or random EO, the total EO content being 50-90 % by weight;
- b2) a polyoxyethylene-polyoxypropylene polyol, having an average nominal hydroxy functionality of 2-4 and an average equivalent weight of 1000-3000, wherein the EO is present as random EO and/or tipped EO, the total EO content being between 5 and 25 % by weight; and
- b3) castor oil; and optionally

85871-138

2

b4) a polyoxypropylene polyol, having an average nominal hydroxy functionality of 3-6 and an average equivalent weight of 100-600; and optionally

b5) a polyoxyalkyleneglycol having an average molecular weight from 150 to 1200; the amounts of these compounds b1, b2, b3, b4 and b5 being (based on the combined weights of b1, b2, b3, b4 and b5): b1 : 10-40 wt %, b2 : 10-40 wt %, b3 : 5-50 wt %, b4 : 0-40 wt %, b5 : 0-30 wt %. The foams preferably have a density of 30-100 and more preferably of 40-90 kg/m³. The present invention further relates to the foams obtained according to this process.

According to another aspect, the present invention relates to a visco-elastic foam made by the process as defined herein.

10 According to another aspect, the present invention relates to a polyol composition comprising:

b1) a polyoxy ethylene-polyoxypropylene polyol, having an average nominal hydroxy functionality of 2-4 and an average equivalent weight of 1000-3000, wherein the oxyethylene (EO) is present as tipped EO and/or random EO, the total EO content being 50-90 % by weight;

b2) a polyoxyethylene-polyoxypropylene polyol, having an average nominal hydroxy functionality of 2-4 and an average equivalent weight of 1000-3000, wherein the EO is present as random EO and/or tipped EO, the total EO content being between 5 and 25 % by weight; and

b3) castor oil; and optionally

b4) a polyoxypropylene polyol, having an average nominal hydroxy functionality of 3-6 and an average equivalent weight of 100-600; and optionally

20 b5) a polyoxyalkyleneglycol having an average molecular weight from 150 to 1200; the amounts of these compounds b1, b2, b3, b4 and b5 being (based on the combined weights of b1, b2, b3, b4 and b5): b1 : 10-40 wt %, b2 : 10-40 wt %, b3 : 5-50 wt %, b4 : 0-40 wt %, b5 : 0-30 wt %.

85871-138

2a

In the context of the present invention the following terms have the following meaning:

- 1) isocyanate index or NCO index or index : the ratio of NCO-groups over isocyanate-reactive hydrogen atoms present in a formulation, given as a percentage :

$$5 \quad \frac{[\text{NCO}] \times 100}{[\text{active hydrogen}]} \quad (\%).$$

In other words the NCO-index expresses the percentage of isocyanate actually used in a formulation with respect to the amount of isocyanate theoretically required for reacting with the stoichiometric amount of isocyanate-reactive hydrogen used in a formulation.

10 It should be observed that the isocyanate index as used herein is considered from the point of view of the actual polymerisation process preparing the foam involving the isocyanate ingredient and the isocyanate-reactive ingredients. Any isocyanate groups consumed in a preliminary step to produce modified polyisocyanates (including such isocyanate-derivatives referred to in the art as prepolymers) or any active hydrogens consumed in a preliminary step (e.g. reacted with isocyanate to produce modified polyols) are not taken into account in the
15 calculation of the isocyanate index. Only the free isocyanate groups and the free isocyanate-reactive hydrogens (including those of the water) present at the actual polymerisation stage are taken into account.

- 2) The expression “isocyanate-reactive hydrogen atoms” as used herein for the purpose of calculating the isocyanate index refers to the total of active hydrogen atoms in hydroxyl and amine groups present in the reactive compositions; this means that for the purpose of calculating the isocyanate index at the actual
5 polymerisation process one hydroxyl group is considered to comprise one reactive hydrogen, one primary amine group is considered to comprise one reactive hydrogen and one water molecule is considered to comprise two active hydrogens.
- 3) Reaction system : a combination of components wherein the polyisocyanates are
10 kept in one or more containers separate from the isocyanate-reactive components.
- 4) The expression “polyurethane foam” as used herein refers to products as obtained by reacting polyisocyanates with isocyanate-reactive hydrogen containing compounds, using foaming agents, and in particular includes cellular products
15 obtained with water as reactive foaming agent (involving a reaction of water with isocyanate groups yielding urea linkages and carbon dioxide and producing polyurea-urethane foams).
- 5) The term “average nominal hydroxyl functionality” is used herein to indicate the
20 number average functionality (number of hydroxyl groups per molecule) of the polyol or polyol composition on the assumption that this is the number average functionality (number of active hydrogen atoms per molecule) of the initiator(s) used in their preparation although in practice it will often be somewhat less because of some terminal unsaturation.
25
- 6) The word “average” refers to number average unless indicated otherwise.
- 7) “Density” is measured according to ISO 845 and is the core density unless
30 specified otherwise.

- 8) A visco-elastic foam is defined as a foam having a resilience of at most 40 %, as measured according to ISO 8307 and a hysteresis loss of more than 40 %, as measured according to ISO 3386-1.
- 5 9) The following way of describing polyols is used in the present application : A PO-EO polyol is a polyol having first a PO block attached to the initiator followed by an EO block. A PO-PO/EO polyol is a polyol having first a PO block and then a block of randomly distributed PO and EO. A PO-PO/EO-EO polyol is a polyol having first a PO block, then a block of randomly distributed PO and EO and then
10 a block of EO. In the above descriptions only one tail of a polyol is described (seen from the initiator); the nominal hydroxyl functionality will determine how many of such tails will be present. PO stands for oxypropylene and EO for oxyethylene in this context.
- 15 10) Castor oil refers to unmodified castor oil which means that no chemical modifications, like alkoxylation, took place.
Unmodified castor oils include castor oils which have been treated by physico-chemical means like purification and discoloration.
- 20 11) Slabstock foam : any foam made under conditions as described in the Polyurethane Handbook by Dr. G. Oertel, 2nd edition, Hauser Publishers, 1993, Section 5.1 "Slabstock Foams" (starting at page 178).

The polyisocyanates preferably are selected from aromatic polyisocyanates like toluene
25 diisocyanate and preferably diphenylmethane diisocyanate (MDI), mixtures of MDI with homologues thereof having an isocyanate functionality of 3 or more, which mixtures are widely known as crude or polymeric MDI, and isocyanate-terminated variants of these polyisocyanates, such variants containing urethane, uretonimine, carbodiimide, urea, isocyanurate, allophanate and/or biuret groups. Mixtures of these polyisocyanates may be
30 used as well.

Most preferably the polyisocyanate is selected from 1) a diphenylmethane diisocyanate comprising at least 40%, preferably at least 60 % and most preferably at least 80 % by weight of 4,4'-diphenylmethane diisocyanate and the following preferred variants of such diphenylmethane diisocyanate : 2) a carbodiimide and/or uretonimine modified variant of polyisocyanate 1), the variant having an NCO value of 20% by weight or more; 3) a urethane modified variant of polyisocyanate 1), the variant having an NCO value of 20% by weight or more and being the reaction product of an excess of polyisocyanate 1) and of a polyol having an average nominal hydroxyl functionality of 2-4 and an average molecular weight of less than 1000; 4) a prepolymer having an NCO value of 10% by weight or more and preferably of 15 % by weight or more and which is the reaction product of an excess of any of the aforementioned polyisocyanates 1-3) and of a polyol having an average nominal functionality of 2-6, an average molecular weight of 1000-12000 and preferably an hydroxyl value of 15 to 60 mg KOH/g; 5) diphenylmethane diisocyanates comprising homologues having 3 or more isocyanate groups; and 6) mixtures of any of the aforementioned polyisocyanates.

Polyisocyanate 1) comprises at least 40% by weight of 4,4'-MDI. Such polyisocyanates are known in the art and include pure 4,4'-MDI and isomeric mixtures of 4,4'-MDI and up to 60% by weight of 2,4'-MDI and 2,2'-MDI. It is to be noted that the amount of 2,2'-MDI in the isomeric mixtures is rather at an impurity level and in general will not exceed 2% by weight, the remainder being 2,4'-MDI and 4,4'-MDI. Polyisocyanates as these are known in the art and commercially available; for example SuprasecTM MPR ex Huntsman Polyurethanes, which is a business of Huntsman International LLC (who owns the Suprasec trademark).

The carbodiimide and/or uretonimine modified variants of the above polyisocyanate 1) are also known in the art and commercially available; e.g. Suprasec 2020, ex Huntsman.

Urethane modified variants of the above polyisocyanate 1) are also known in the art, see e.g. The ICI Polyurethanes Book by G. Woods 1990, 2nd edition, pages 32-35.

Aforementioned prepolymers of polyisocyanate 1) having an NCO value of 10 % by weight or more are also known in the art. Preferably the polyol used for making these prepolymers is selected from polyester polyols and polyether polyols.

Diphenylmethane diisocyanates comprising homologues having 3 or more isocyanate groups are widely known in the art as crude or polymeric MDI and are commercially available; e.g. Suprasec 2185 and Suprasec DNR ex Huntsman.

Mixtures of the aforementioned polyisocyanates may be used as well, see e.g. The ICI
5 Polyurethanes Book by G. Woods 1990, 2nd edition, pages 32-35. An example of such a commercially available polyisocyanate is Suprasec 2021 ex Huntsman.

The polyol used is a polyol composition comprising

b1) a polyoxyethylene-polyoxypropylene polyol, having an average nominal
10 hydroxy functionality of 2-4 and an average equivalent weight of 1000-3000, wherein the oxyethylene (EO) is present as tipped EO and/or random EO, the total EO content being 50-90 % by weight;

b2) a polyoxyethylene-polyoxypropylene polyol, having an average nominal
hydroxy functionality of 2-4 and an average equivalent weight of 1000-3000, wherein the
15 EO is present as random EO and/or tipped EO, the total EO content being between 5 and 25 % by weight; and

b3) castor oil; and optionally

b4) a polyoxypropylene polyol, having an average nominal hydroxy
functionality of 3-6 and an average equivalent weight of 100-600; and optionally

20 b5) a polyoxyalkyleneglycol having an average molecular weight from 150 to 1200; the amounts of these compounds b1, b2, b3, b4 and b5 being (based on the combined weights of b1, b2, b3, b4 and b5); b1 : 10-40 wt %, b2 : 10-40 wt %, b3 : 5-50 wt %, b4 : 0-40 wt %, b5 : 0-30 wt %. This polyol composition also forms part of the present invention.

25

Polyol b1 is an EO rich polyol. It can be prepared by known methods. It comprises PO and EO, where the EO can be random, tipped, or both. Preferably the EO is random in majority. The EO content is 50-90 % by weight (over the total oxyalkylene units present). Such polyols are known and commercially available; e.g. DaltocelTM 444 and 555 ex
30 Huntsman (Daltocel is a trademark of Huntsman International LLC).

Polyol b2 can have a structure of the type PO-PO/EO-EO, PO/EO-EO, PO-EO or PO/EO. The total EO content is between 5 and 25 % by weight (over the total oxyalkylene units present). Such polyols are known and commercially available; e.g. Daltocel F435 and F428 ex Huntsman.

- 5 Castor oil preferably is used in an amount of 10-40 % by weight based on the combined weights of b1, b2, b3, b4 and b5.

Polyol b4 is known and commercially available; e.g. DaltolacTM R251 ex Huntsman.

- 10 Polyol b5 is a polyoxyalkyleneglycol such as polyoxyethylene glycol (PEG) or polyoxypropylene glycol (PPG). A preferred polyol is a PEG diol.

Each component b1, b2, b4 and b5 may be comprised of mixtures. Dispersed material can also be present. This is known as polymer-modified polyol, and comprise e.g. SAN or
15 PIPA (Poly Isocyanate Poly Addition), or PHD (Polyurea Dispersion). The polymer-modified polyols which are particularly interesting in accordance with the invention are products obtained by in situ polymerisation of styrene and/or acrylonitrile in poly(oxyethylene/oxypropylene)polyols and products obtained by in situ reaction between a polyisocyanate and an amino- or hydroxy-functional compound (such as
20 triethanolamine) in a poly(oxyethylene/ oxypropylene)polyol. The solids content (based on the total polyol weight b1+b2+b4+b5) can vary within broad limits, e.g. from 5 to 50 %. Particle sizes of the dispersed polymer of less than 50 microns are preferred. Mixtures can be used as well.

- 25 The invention also relates to a specific polyol mixture, comprising the five polyols together, according to the following proportions, expressed on the basis of the combined weights of the polyols:

- b1 : 10-40 % by weight
b2 : 10-40 % by weight
30 b3 : 5-50 % by weight and preferably 10-40 % by weight
b4 : 0-40 % by weight

b5 : 0-30 % by weight.

Water is preferably used as the blowing agent. Inert gases like carbon dioxide may be added if needed. It is appropriate to use from 0.5 to 10 %, preferably from 0.5 to 5 % by weight of water based on the weight of the total polyol component (prereacted and not prereacted, i.e. the total starting polyol or total starting isocyanate-reactive compounds), where the water can optionally be used in conjunction with inert gas.

Other conventional ingredients (additives and/or auxiliaries) may be used in making the polyurethanes. These include catalysts, for example, tertiary amines and organic tin compounds, surfactants, cross linking or chain extending agents, for example, low molecular weight compounds such as other diols, triols (having a molecular weight below those specified for b1-b3) and diamines, fire retardants, for example, halogenated alkyl phosphates and melamine, fillers and pigments. Foam stabilizers, for example polysiloxane-polyalkylene oxide block copolymers, may be used to stabilize or regulate the cells of the foam.

The amount of these minor ingredients used will depend on the nature of the product required and may be varied within limits well known to a polyurethane foam technologist.

These components, notably the polyols b1, b2, b3, b4 and b5 can be added in any order. The polyols can be added one after the other, or part by part, in any order (for example, part of b1, then the remainder of b1 together with the all of b2+b3+b4+b5 or all of b2 then all of b1 then all of b3 then all of b4 then all of b5).

The components of the polyurethane forming reaction mixture may be mixed together in any convenient manner; the individual components may be pre-blended so as to reduce the number of component streams which are to be brought together in the final mixing step. It is often convenient to have a two-stream system whereby one stream comprises the polyisocyanate or polyisocyanate prepolymer and the second stream comprises all the other components of the reaction mixture. The foams may be made according to the so

called semi- or quasi-prepolymer process or the prepolymer process wherein part or all of the compounds b1-b5 are prereacted with the polyisocyanate and wherein the semi- or quasi-prepolymer or prepolymer is subsequently reacted with water and the remaining part of the compounds b1-b5, if any.

5

The foams may be used in the furniture industries in seating, in cushioning and in particular in mattresses.

The invention is illustrated with the following examples.

10

Example 1

The following polyisocyanate mixture was made by combining and mixing the following ingredients (amounts are in parts by weight) :

15 30.1 pbw of Suprasec 2185, 51.65 pbw of MDI comprising 17 % wt of 2,4'-MDI and 18.25 pbw of a prepolymer, having an NCO value of about 13 % by weight, were mixed. The prepolymer was made by reacting about 27 pbw of MDI (2,4'-MDI = 15 %w), about 16.5 pbw of Suprasec 2185 and about 57 pbw of Daltocel F428.

20 Then the following polyol composition was made by combining and mixing the following ingredients: amount (in parts by weight):

	Caradol SA 36-11 (b2 polyol); from Shell	30
	Caradol MD 36-02 (b1 polyol); from Shell	30
	Caradol SH 250-05 (b4 polyol); from Shell	25
25	PEG 400 (b5 polyol)	10
	Castor oil ex Alberdingk-Boley	20
	Water	2.25
	Dabco 33 LV (catalyst ex Air Products)	0.5
	Niax A1 (catalyst ex Osi)	0.25
30	Tegostab B8716LF (surfactant from Goldschmidt)	0.25

65 parts by weight of the polyisocyanate was reacted with the polyol composition using a multi-component discontinuous slabstock device with a foaming box having dimensions 50x50x50 cm. The block obtained was left for 24h under ambient conditions before cutting and testing. The foams obtained had a core density of 48 kg/m³ (ISO 845), a
5 resilience of 14 % (ISO 8307) and a hysteresis loss of 58 % (ISO 3386-1).

Example 2 (comparative)

Example 1 was repeated with the proviso that all the Caradol MD 36-02 was replaced with Caradol SA 36-11; the reaction was also conducted at index 87. The reaction was conducted in a bucket on the bench. The foam obtained showed recession to an extent
10 that it would not be able to make suitable slabstock foams from such a composition and that no useful foam was obtained.

85871-138

11

CLAIMS

1. A process for making a slabstock, visco-elastic, flexible, polyurethane foam, comprising:
reacting a polyisocyanate and a polyol at an index of 60-95 and using a blowing agent, wherein the
5 polyol is a polyol composition comprising:
- b1) a polyoxyethylene-polyoxypropylene polyol, having an average nominal hydroxy functionality
of 2-4 and an average equivalent weight of 1000-3000, wherein the oxyethylene (EO) is present as
tipped EO and/or random EO, the total EO content being 50-90 % by weight;
 - b2) a polyoxyethylene-polyoxypropylene polyol, having an average nominal hydroxy functionality
10 of 2-4 and an average equivalent weight of 1000-3000, wherein the EO is present as random EO
and/or tipped EO, the total EO content being between 5 and 25 % by weight; and
 - b3) castor oil; and optionally
 - b4) a polyoxypropylene polyol, having an average nominal hydroxy functionality of 3-6 and an
average equivalent weight of 100-600; and optionally
 - 15 b5) a polyoxyalkyleneglycol having an average molecular weight from 150 to 1200; the amounts
of these compounds b1, b2, b3, b4 and b5 being (based on the combined weights of b1, b2, b3, b4
and b5): b1 : 10-40 wt %, b2 : 10-40 wt %, b3 : 5-50 wt %, b4 : 0-40 wt %, b5 : 0-30 wt %.
2. The process according to claim 1, wherein the density of the foam is 30-100 kg/m³.
3. The process according to claim 1 or 2, wherein the polyisocyanate is selected from the group
20 consisting of diphenylmethane diisocyanate (MDI); mixtures of MDI with homologues thereof
having an isocyanate functionality of 3 or more; isocyanate-terminated variants of these
polyisocyanates, the variants containing urethane, uretonimine, carbodiimide, urea, isocyanurate,
allophanate and/or biuret groups; and mixtures thereof.
4. The process according to any one of claims 1 to 3, wherein the blowing agent is water.

85871-138

12

5. The process according to any one of claims 1 to 4, wherein the amount of castor oil is 10-40 % by weight.
6. A visco-elastic foam made according to the process of any one of claims 1 to 5.
7. A polyol composition comprising:
- 5 b1) a polyoxyethylene-polyoxypropylene polyol, having an average nominal hydroxy functionality of 2-4 and an average equivalent weight of 1000-3000, wherein the oxyethylene (EO) is present as tipped EO and/or random EO, the total EO content being 50-90 % by weight;
- b2) a polyoxyethylene-polyoxypropylene polyol, having an average nominal hydroxy functionality of 2-4 and an average equivalent weight of 1000-3000, wherein the EO is present as random EO
10 and/or tipped EO, the total EO content being between 5 and 25 % by weight; and
- b3) castor oil; and optionally
- b4) a polyoxypropylene polyol, having an average nominal hydroxy functionality of 3-6 and an average equivalent weight of 100-600; and optionally
- b5) a polyoxyalkyleneglycol having an average molecular weight from 150 to 1200; the amounts
15 of these compounds b1, b2, b3, b4 and b5 being (based on the combined weights of b1, b2, b3, b4 and b5): b1 : 10-40 wt %, b2 : 10-40 wt %, b3 : 5-50 wt %, b4 : 0-40 wt %, b5 : 0-30 wt %.
8. The polyol composition according to claim 7, wherein the amount of castor oil is 10- 40 % by weight.