

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
8 November 2001 (08.11.2001)

PCT

(10) International Publication Number
WO 01/83608 A1(51) International Patent Classification⁷: C08K 5/5415,
C07F 7/08, C08L 83/04, C07F 7/18

(21) International Application Number: PCT/EP01/04606

(22) International Filing Date: 24 April 2001 (24.04.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
00401160.7 27 April 2000 (27.04.2000) EP

(71) Applicant (for all designated States except US): DOW CORNING CORPORATION [US/US]; Midland, MI 48611 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): CHEVALIER,



Pierre [FR/GB]; 5 Plymouth Road, Penarth CF64 3DA (GB). MACKINNON, Iain, A. [GB/GB]; 39 Samson Street, Llantwit Major CF61 2SH (GB). ZHU, Bishong [CN/US]; 1212 Marriet Ct, Midland, MI 48640 (US). CORRIU, Robert, Jean-Pierre [FR/FR]; 246, rue de l'Esperou, F-34090 Montpellier (FR). CERVEAU, Genevieve, Marie-Louise, Emile [FR/FR]; Clos Saint Joseph C, 749, avenue du Pic Saint Loup, F-34090 Montpellier (FR). DABIENS, Bertrand, François [FR/FR]; Résidence La Musardière BA A1, 43, avenue du Professor Grasset, F-34000 Montpellier (FR).

(74) Agents: DAVIES, Peter, V. et al.; Dow Corning Limited, Cardiff Road, Barry CF63 2YL (GB).


(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX,

[Continued on next page]

(54) Title: CURABLE SILICONE RESIN COMPOSITION AND REACTIVE SILICON COMPOUNDS



(57) **Abstract:** A curable silicone resin composition comprises (A) an uncured silicone resin having units of the formula $(R^*)_a(R)_bSiO_{(4-a-b)/2}$, where each R^* is a functional group capable of reacting with Si-OH and/or Si-alkoxy groups and each R is a nonfunctional monovalent hydrocarbon group, $a+b$ is from 1.0 to 3.0 and each molecule of uncured silicone resin contains an average of at least two groups R^* , and (B) a silanol or hydrolysable compound of the formula (I) where R' represents a hydroxyl group or a hydrolysable group; each R'' represents hydrogen, a monovalent hydrocarbon which optionally is substituted, or a group within the above definition of R' ; and Ar is a substantially nonflexible linkage including at least one para-arylene moiety, so that the groups $(R')_2R''Si-$ are spatially separated.



WO 01/83608 A1



MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI,

SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG)

— of inventorship (Rule 4.17(iv)) for US only

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

- 1 -

CURABLE SILICONE RESIN COMPOSITION
AND REACTIVE SILICON COMPOUNDS

FIELD OF THE INVENTION

5 [0001] This invention relates to curable silicone resin compositions and to reactive silicon compounds useful in such curable compositions.

BACKGROUND OF THE INVENTION

10 [0002] Curable silicone resins such as silsesquioxane resins are used in applications which take advantage of their heat and fire resistant properties, for example in fibre reinforced composites for electrical laminates and structural components for automotive, aircraft and naval 15 use, and as interlayer dielectric materials and as abrasion resistant coatings. The resins cure to a rigid product. There is a need for silicone resin compositions of improved mechanical properties, such as increased flexural strength, fracture toughness, modulus and/or mechanical damping, 20 without substantial loss of heat and fire resistance.

[0003] The toughness of a silicone resin has been increased by a rubber component, as described in US 5747608 or US 5830950 or by a silicone fluid as described in US 5034061 or CA 691206.

25 [0004] GB 1119666 describes a resinous polymer comprising the reaction product of a compound of the formula $(R)_n(X)_{(3-n)}Si-R'-Si(X)_{(3-n)}(R)_n$, wherein R is a monovalent hydrocarbon group, R' is phenylene, diphenylene or diphenylene oxide, X is hydroxy or alkoxy and n is 1 or 2 30 and a silane of the general formula $(R'')_mSi(Y)_{4-m}$, wherein R'' is a hydrocarbyl or substituted hydrocarbyl group, Y is alkoxy, acyloxy or hydroxy and m=0-2. GB1101589 describes a process for the production of an organosilicon resin by


- 2 -

heating in the presence of a solvent a compound of the formula $R_1(R_2)_2Si-R-Si(R_2)_2R_1$ where R is phenylene, diphenylene or diphenylene oxide, R1 is a monovalent hydrocarbon or substituted hydrocarbon group and R2 is 5 alkoxy or hydroxy, with a compound of the formula $R_4(R_3)_2Si-R-Si(R_3)_2R_4$ where each R3 is a monovalent hydrocarbon or substituted hydrocarbon group and R4 is acyloxy, alkoxy or hydroxy.

10 SUMMARY OF THE INVENTION

[0005] A curable silicone resin composition according to the present invention comprises (A) an uncured silicone resin having units of the formula $(R^*)_a(R)_bSiO_{(4-a-b)/2}$, where each R^* is a functional group capable of reacting with Si-OH and/or Si-alkoxy groups and each R is a nonfunctional monovalent hydrocarbon group, $a+b$ is from 1.0 to 3.0 and each molecule of uncured silicone resin contains an average of at least two groups R^* , and (B) a silanol or hydrolysable compound of the formula

20



25

where each R' represents a hydroxyl group or a hydrolysable group; each R'' represents hydrogen, a monovalent hydrocarbon which optionally is substituted, or a group within the above 30 definition of R'; and Ar is a substantially nonflexible linkage including at least one para-arylene moiety, so that the groups $(R')_2R''Si-$ are spatially separated.

[0006] The compound (B) reacts with the functional groups R* of the silicone resin to crosslink the resin (A) to a

- 3 -

structure having improved mechanical properties and generally less brittle than that obtained by curing the resin (A) alone. The groups $(R')_2R''Si-$ are spatially separated by the nonflexible linkage Ar so that 5 intramolecular self-reaction of the groups $(R')_2R''Si-$ is avoided.

BRIEF DESCRIPTION OF THE DRAWINGS

[0007] Figure 1 is a graph showing the dynamic mechanical 10 analysis results of Example 21.

[0008] Figure 2 is a graph showing the dynamic mechanical analysis results of Example 22.

DETAILED DESCRIPTION OF THE INVENTION


[0009] The nonflexible linkage Ar can be a simple p-phenylene moiety or can contain two or more phenylene groups linked in an array in such a way that the array is held in a substantially linear conformation, that is the linkage between the phenylene groups does not contain any atoms 15 about which the parts of the molecule can freely rotate, such as a carbon atom positioned between two C-C single bonds. The p-phenylene groups can be part of a fused ring system such as a 1,4-naphthylene or 1,10-anthracene linkage, and the term "para-arylene moiety" includes other fused ring 20 aromatic linkages in which the $(R')_2R''Si-$ groups are maintained spatially separated such as a 1,5- or 2,6-naphthylene linkage or even a metallocene, e.g. ferrocene 25 linkage in which the $(R')_2R''Si-$ groups are bonded to different cyclopentadiene rings.

[0010] The compounds (B) in which the group R'' is a hydroxyl group and Ar contains two or more phenylene groups per molecule are new compounds. The invention thus includes 30 an organosilicon compound of the formula $(HO)_3Si-Ar'-Si(OH)_3$

- 4 -

wherein Ar' is a linkage containing two or more phenylene moieties held in a substantially linear conformation so that the (R')₃Si- groups are spatially separated.

[0011] All the compounds (B) in which Ar comprises two or 5 more para-arylene moieties joined by an organic linkage which does not allow free rotation are new compounds. The invention thus includes an organosilicon compound of the formula



wherein R' and R'' are defined as in Claim 1, each Ap is 15 a para-arylene moiety, and X is a substantially inflexible linkage having at least two carbon atoms so that the groups (R')₂R''Si- are spatially separated.

[0012] The structure of the linkage X is such that in combination with the adjacent phenylene groups there is 20 provided a substantially linear rigid-rod array. It is preferred that there are from 2 to 4 phenylene groups, more preferably only 2 phenylene groups, per molecule. Preferably X comprises a direct bond or a linkage comprising a carbon-carbon double bond, for example vinylene -CH=CH-, 25 or one or two carbon-carbon triple bonds, for example an acetylene or butadiyne linkage. Where X comprises a C=C double bond, the phenylene groups are generally positioned trans- to one another; although this arrangement is not strictly linear, it holds the para-(hydroxysilyl) substituents on the phenylene groups apart from each other and is "substantially linear" within the terms of this invention.

[0013] The para-phenylene groups Ph or any phenylene group within linkage Ar can be substituted by one or more

- 5 -

alkyl, for example methyl, ethyl, butyl, hexyl or dodecyl, aryl, aralkyl or alkenyl group, although the phenylene groups are preferably unsubstituted.

[0014] Examples of preferred organobis(silane triol)s

5 according to the invention include

4,4'-bis(trihydroxysilyl)biphenyl,

4,4'-bis(trihydroxysilyl)stilbene,

bis(4-trihydroxysilylphenyl)acetylene and

1,4-bis(4-trihydroxysilylphenyl)butadiyne.

10 **[0015]** The organobis(silane triol)s of the invention can be prepared by, for example, the hydrolysis of corresponding organobis(trialkoxysilyl) and organobis(trichlorosilyl) compounds. An organobis(trialkoxysilyl) precursor can for example be hydrolysed by the methods described by Hyde as disclosed in J.Am.Chem.Soc. 1953, 75, at page 2166 or Tyler as disclosed in J.Am.Chem.Soc. 1955, 77, at page 770.

[0016] Examples of organobis(trialkoxysilyl) compounds

which can be used as compound (B) include

4,4'-bis(trimethoxysilyl)biphenyl,

20 4,4'-bis(trimethoxysilyl)stilbene,

bis(4-trimethoxysilylphenyl)acetylene and

1,4-bis(4-trimethoxysilylphenyl)butadiyne

Bis(trimethoxysilylphenyl)-substituted acetylenic compounds can be prepared from the condensation reaction of

25 para-bromo(trimethoxysilyl) benzene or

para-iodo(trimethoxysilyl) benzene with

para-(trimethoxysilyl)phenylacetylene. Bis(trimethoxysilyl) substituted diphenylbutadiynes can be prepared by the homo coupling reaction of para-(trimethoxysilyl)phenylacetylene.

30 **[0017]** Hydrolysis can take place under mild conditions,

even by the use of water alone, although it is preferred

that a catalyst such as an organic acid, particularly acetic acid, is present in order to facilitate the hydrolysis

- 6 -

reaction. It is preferred that from 0.1 to 5% by weight of catalyst based on the weight of water present is used in the reaction mixture, more preferably from 0.25 to 2%.

5 [0018] The relative proportions of water and organobis(trialkoxysilyl) precursor may vary between wide limits. Generally at least 6 moles water is present per mole of organobis(trialkoxysilane) and sufficient water may be used for the bis(trihydroxysilyl)arene product to dissolve in the aqueous phase.

10 [0019] The hydrolysis of the organobis(trialkoxysilane) is preferably carried out in the presence of solvent, most preferably a dipolar aprotic organic solvent such as diethyl ether or dichloromethane. The reaction temperature is preferably in the range from 0°C to 40°C, for example 15 ambient temperatures. The water and catalyst may be incorporated separately into the reaction mixture or can be pre-mixed prior to addition to the organobis(trialkoxysilyl) precursor. The reaction period for the hydrolysis to reach completion (i.e. the hydrolysis of all the alkoxy groups 20 present on the organobis(trialkoxysilyl) precursor) is generally from about 30 minutes up to 1 month and the preferred reaction period is from about 1 hour to about 4 days, most preferably from 4 to 24 hours.

25 [0020] Upon completion of the hydrolysis reaction, the organobis(silane triol) may be recovered from the reaction mixture by conventional means, for example, by filtration or evaporation.

30 [0021] In a preferred procedure organobis(trialkoxysilane) in ether is added drop-wise quickly to a 0.5 % acetic acid/water solution at 20°C. The mixture is then stirred thoroughly until the resulting organobis(silane triol) precipitates out in the aqueous

- 7 -

phase. After filtration and drying overnight at 25°C the organobis(silane triol) is recovered.

[0022] An alternative method of making the organobis(silane triol) is from a organobis(trichlorosilyl) precursor. This method includes the hydrolysis reaction of an organobis(trichlorosilyl) compound with a water/aniline mixture to form the organobis(silane triol). The reaction is based on the method of Takiguchi as disclosed in J.Am.Chem.Soc. 1959, 81, at page 2359.

10 Organobis(trichlorosilane) can be dissolved in dry diethyl ether and added drop-wise to an emulsion of a stoichiometric amount of water and aniline at a temperature of 0°C. After removal of anilinium salts by filtration from the reaction mixture, organobis(silane triol) is recovered.

15 The bis((hydrocarbyldihydroxysilyl)phenyl) compounds, that is those compounds (B) in which R" is a monovalent hydrocarbon group, can be prepared by analogous procedures. For example bis(4-(methyldimethoxysilyl)phenyl)acetylene can be prepared by condensation of para-

20 bromo(methyldimethoxysilyl)benzene with para-(methyldimethoxysilyl)phenylacetylene and can be hydrolysed to bis(4-(methyldihydroxysilyl)phenyl)acetylene by the procedures described above.

[0023] The compounds (B) according to this invention are effective in crosslinking the silicone resin (A) and have high stability against intramolecular self-condensation. The invention thus includes a process for forming a cured resin composition comprising mixing (A) and (B) and curing the resulting composition under conditions such that (A) and (B) are copolymerised.

[0024] (A) is an uncured silicone resin having units of the formula $(R^*)_a(R)_bSiO_{(4-a-b)/2}$, where each R* is a functional group capable of reacting with Si-OH and/or Si-

- 8 -

alkoxy groups and each R is a nonfunctional monovalent hydrocarbon group and a+b is from 1.0 to 3.0. Each molecule of uncured silicone resin contains an average of at least two groups R*. The groups R* can be -OH groups, alkoxy groups or H atoms bonded to Si. Typically, R is selected from alkyl and aryl groups. Suitable alkyl groups include methyl, ethyl, isopropyl, n-butyl and isobutyl. Suitable aryl groups are exemplified by phenyl. Organosilicone resins, particularly those prepared by acid hydrolysis and condensation, generally include a considerable concentration of residual hydroxyl groups which can react with the hydroxysilyl or alkoxy silyl groups of the compound (B) through a condensation cure system.

[0025] The amount of (A) in the curable system is generally 5 to 96%, preferably 50 to 95%, by weight. Most preferably, the weight ratio of (A) to (B) is 5:1 to 20:1.

[0026] The curable silicone resin composition of the invention preferably contains a catalyst so that condensation curing can be carried out at reduced, e.g. ambient temperature. The catalyst can be a metal ester or alkoxide of a Group IVB metal such as zirconium, hafnium or titanium, for example titanium tetrabutoxide, a metal carboxylate such as zinc octoate, choline octoate, a strong acid such as sulphuric or phosphoric acid or a base such as KOH, CsOH, a metal silanolate, calcined lime or an amine or quaternary base, for example tetramethyl ammonium hydroxide. The catalyst can generally be used at up to 2% by weight based on reagents, preferably 0.02 to 0.4%.

[0027] The curable composition may additionally contain a silicone rubber, for example a rubber as described in US5747608 or US5830950. The rubber generally has terminal functional groups capable of reacting with the hydroxyl groups of silicone resin (A). The silicone rubber, if used, can be present at up to 30% by weight, for example 5 to 20%.

[0028] The curable composition can optionally contain a solvent at up to 90%, preferably up to 60% of the composition. For example a substrate having a cure silicone resin coated thereon can be prepared by mixing (A) and (B) in a solvent, coating the resulting solution on the substrate, and drying the coating and subjecting it to curing conditions. A moulded cured silicone resin can be produced by mixing (A) and (B) in a solvent, casting the resulting solution in a mould, removing the solvent and curing the composition in the mould. The solvent is generally a polar organic solvent, for example an amide such as formamide, dimethylformamide or dimethylacetamide, a halogenated hydrocarbon such as dichloromethane or 1,1,1-trichloroethane, an alcohol such as methanol, ethanol, isopropanol or t-butanol, an aromatic hydrocarbon such as toluene or xylene, a glycol ether such as 2-methoxypropanol, 2-butoxypropanol, butoxyethanol or dipropylene glycol methyl ether, or a sulphoxide such as dimethyl sulphoxide. The more polar solvents such as alcohols, formamide or dimethyl sulphoxide may be required to dissolve the organobis(silanetriol)s.

[0029] The curable composition can be coated on a substrate, for example as a solution, and cured to form a thin film on the substrate, or can be cured in a mould to form a shaped silicone resin article.

[0030] The novel compounds of the formula $(R')_3Si-Ar'-Si(R')_3$ can also be cured alone to produce strong solid resins by condensation of the R' groups. If curing is carried out in a solvent such as formamide, a gel is produced which can be powdered and dried to recover the solid resin, which contains extended chains containing arylene linkages and silicate crosslinks.

- 10 -

[0031] The compounds (B), particularly the bis(trihydroxysilyl)arene compounds and the bis(dihydroxysilyl)arene compounds, have X-ray patterns showing that they are ordered in the solid state. It is 5 believed that resins formed by polymerisation of the bis(trihydroxysilyl)arene compounds are also ordered in the solid state, and that the cured compositions of the invention formed from a silicone resin and compound (B) also show ordering in the solid state. These polymers and cured 10 resin compositions thereby give optical effects which can be utilised in electro-optic products.

[0032] There now follows a number of examples in which all parts and percentages are given by weight unless otherwise indicated.

15

Example 1

Preparation of 4,4'-bis(trihydroxysilyl)biphenyl

[0033] To a flask fitted with a dropping funnel, mechanical stirrer and temperature probe was added a 20 solution of 4,4'-bis(trimethoxysilyl)biphenyl (1g, 2.53 mmol., prepared as described by Corriu et al., Chem. Mater. (1992) 4, 1217-1224) in ether (3 ml) at a temperature of 20°C. The dropping funnel was charged with a 0.5 % acetic acid solution (1.10 ml). The acetic acid solution was 25 quickly added dropwise to the flask and the reaction mixture separated into two phases. The white biphasic mixture was well agitated for a period of twenty-four hours at a temperature of 20°C. During this period, a colourless solid precipitated out in the aqueous phase. The reaction mixture 30 was filtered and the recovered precipitate was washed three times each with ethanol, acetone and ether and then dried overnight at a temperature of 20°C to give a white crystalline solid.

- 11 -

[0034] ^1H NMR (DMSO-d6) analysis of the solid gave two signals at 7.69 (4H, d), 7.63 (4H, d) and 6.43 ppm (6H, s) representing the aryl protons of phenyl groups and hydroxyl groups respectively and indicated the conservation of the 5 molecular structure of the precursor, 4,4'-bis(trimethoxysilyl)biphenyl and the presence of 6 hydroxyl groups. ^{13}C NMR (DMSO-d6) analysis gave 4 signals at 141.2, 136.8, 135.5 and 126.3 ppm corresponding to the 4 aromatic carbon atoms of the phenyl groups and there was no 10 signal present for the methoxy group of the pre-cursor. ^{29}Si NMR gave a singlet at -54.3 ppm corresponding to a silanetriol unit. Fourier Transform Infrared (FTIR) spectrum gave a strong broad band at 3219 cm^{-1} attributable to OH stretching frequencies involved in hydrogen bonding. 15 Analysis by ^1H , ^{13}C and ^{29}Si NMR and FTIR identified the solid as 4,4'-bis(trihydroxysilyl)biphenyl obtained at a 95% yield. Anal. Calc.; for $\text{C}_{12}\text{H}_{14}\text{O}_6\text{Si}_2$: C, 46.44; H, 4.54 ; Si, 18.09 %. Found; C, 45.44; H, 4.70 ; Si, 18.20 %.

20 Example 2

[0035] 4,4'-bis-(trimethoxysilyl)stilbene was prepared as follows :
A solution of 4-(trimethoxysilyl)styrene (1.5g, 6.7 mmol, prepared as described by Corriu et al., Chem. Comm, (1996), 25 15, 1845-1846) and 4-bromo(1-trimethoxysilyl)benzene were dissolved in dry toluene (15 ml). Palladium acetate (10 mg, $4.45\text{ }10^{-5}$ mol), dry triethylamine (1.35 g, 13.3 mmol) and tri-orthotolylphosphine (TOP) (0.08 g, $2.67\text{ }10^{-5}$ mol) were added all at once successively (following the Heck reaction 30 as disclosed in ref. R. F. Heck, Org. React, 1982, **27**, 345). The brown suspension was heated during 24 hours at 110°C . The yellow suspension was filtered at room temperature under silanized silica. The solvent was pumped off under vacuum

- 12 -

and a yellow powder was obtained in quantitative yield (2.97 g, 6.7 mmol).

[0036] ^1H NMR (CDCl_3 , δ , ppm) 7.69 (2H, d), 7.58 (2H, d), 7.20 (2H, s), 3.65 (18H, s). ^{13}C NMR (CDCl_3 , δ , ppm) 55.1, 5 111.9, 114.0, 125.2, 129.6, 139.7. ^{29}Si NMR (CDCl_3 , δ , ppm).- 55.4. Anal. Calc.; for $\text{C}_{20}\text{H}_{28}\text{O}_6\text{Si}_2$: C, 57.12; H, 6.71 %. Found; C, 57.86; H, 6.48 %.

Example 3

10 Preparation of 4,4'-bis-(trihydroxysilyl)stilbene)

[0037] The procedure of Example 1 was repeated employing 4,4'-bis(trimethoxysilyl)stilbene) in place of bis(trimethoxysilyl)biphenyl (2g, 4.75 mmol) and using a 1% acetic acid solution (9 ml) to give a ratio of 2.94 equivalents of stilbene to 1 equivalent of acetic acid. The reaction mixture was stirred for a period of 10 days and a yellow coloured powder was recovered at 70% yield.(1.12g, 3.32mmol)

[0038] ^1H NMR (DMSO-d_6 , δ , ppm) 7.69 (4H, d); 7.63 (4H, d); 7.28 (2H, s) ; 6.41 (6H, s). ^{13}C NMR (DMSO-d_6 , δ , ppm) 138.1, 137.5, 135.1, 129.3, 126.0. ^{29}Si NMR (DMSO-d_6 , δ , ppm) -54.3. Anal. Calc.; for $\text{C}_{14}\text{H}_{16}\text{O}_6\text{Si}_2$: C, 49.98; H, 4.80; Si, 16.70 %. Found; C, 50.46; H, 4.95 ; Si, 16.90 %.

25 Example 4 - Preparation of 4,4'-bis(trimethoxysilyl)diphenylacetylene

[1-(4-trimethoxysilyl)phenyl]-2-trimethylsilyl]acetylene

[0039] A solution of [1-(4-bromophenyl)-2-trimethylsilyl]acetylene (17g, 0.067mol) in dry THF (60 ml) was added dropwise to a suspension of chlorotrimethoxysilane (16g, 0.1 mol) and magnesium chips (2.45g, 0.1 mol) in dry THF (60 ml) at 10°C. The mixture was then stirred at room temperature for one day. After

- 13 -

evaporation of the solvent, the brown mixture was extracted with 200 ml of dry pentane and filtered. The solvent was then pumped off and the brown oil was distilled under vacuum (B.p 78-81°C / 10⁻¹ mbar) to afford a colourless oil in 46% 5 yield (9g, 0.031mol).

[0040] ¹H NMR (CDCl₃, δ, ppm) 7.60 (2H, d); 7.47 (2H, d); 3.65 (9H, s) ; 0.28 (9H, s). ¹³C NMR (CDCl₃, δ, ppm) 134.9, 131.7, 130.8, 125.7, 105.3, 96.0, 51.2 ; 0.3. ²⁹Si NMR (CDCl₃, δ, ppm) -17.32, -54.8. Anal. Calc.; for C₁₄H₂₂O₃Si₂: 10 C, 57.08; H, 7.52%. Found; C, 57.07; H, 7.52 %.

4-(trimethoxysilyl)phenylacetylene

[0041] A solution of [1-(4-trimethoxysilyl)phenyl]-2-trimethylsilyl]acetylene (19.80g, 0.067 mol) in 41.8 ml of dry methanol was stirred for 4 hours with potassium 15 carbonate (0.84g, 6.07 mmol) at room temperature. The white suspension was concentrated under vacuum and the residue was extracted with 50 ml of dry pentane. After filtration, the solvent was removed under vacuum to give a crystalline beige 20 powder. This crude solid was crystallised in dry hexane and afforded white crystals of 4-(trimethoxysilyl)phenylacetylene in 72% yield (10.76 g, 0.048 mol). M.p. = 38-39°C.

[0042] ¹H NMR (CDCl₃, δ, ppm) 7.62 (2H, d); 7.53 (2H, d); 3.65 (9H, s) ; 3.17 (1H, s). ¹³C NMR (CDCl₃, δ, ppm) 135.0, 25 131.9, 130.8, 124.7, 83.8, 78.8 ; 51.3. ²⁹Si NMR (CDCl₃, δ, ppm)-55.03. Anal. Calc.; for C₁₁H₁₄O₃Si: C, 59.44; H, 6.34, Si, 12.64%. Found; C, 59.85; H, 6.30, Si, 13.30 %.

4,4'-bis-(trimethoxysilyl)diphenylacetylene

[0043] A solution of 4-(trimethoxysilyl)phenylacetylene 30 (1.03g, 4.62 mmol) in dry triethylamine (13.5ml) with a stoichiometric amount of 4-iodo(1-trimethoxysilyl)benzene (1.5g, 4.62 mmol) was stirred for a few minutes. 3 % molar of CuI (26 mg, 0.138 mmol) and bis-

- 14 -

(triphenylphosphine)palladium chloride II (100 mg, 0.138 mmol) were added all at once, the final brown suspension was stirred vigorously for 8 hours at ~ 20°C. The brown suspension was concentrated under vacuum and the dark residue was extracted with 50 ml of dry toluene.

5 [0044] The yellow suspension was filtered on silanized silica and concentrated under vacuum. The expected product was obtained as a fine yellow powder (1.88 g, 4.49 mmol) in 97 % yield.

10 [0045] ^1H NMR (CDCl_3 , δ , ppm) 7.68 (4H, m); 7.59 (4H, d); 3.67 (18H, s). ^{13}C NMR (CDCl_3 , δ , ppm) 135.1, 131.4, 130.2, 125.7, 90.9, 51.3. ^{29}Si NMR (CDCl_3 , δ , ppm) -54.8. Anal. Calc.; for $\text{C}_{20}\text{H}_{26}\text{O}_6\text{Si}_2$: C, 57.39; H, 6.16; Si, 13.42 %. Found; C, 57.23; H, 5.85 ; Si, 13.45 %.

15

Example 5

4,4'-bis-(trimethoxysilyl)diphenylbut-1,3-diyne

20 [0046] 2g (9 mmol) of 4-(trimethoxysilyl)phenylacetylene, one equivalent of chloroacetone (0.67g, 9 mmol), two equivalents of dry triethylamine (2.51 ml), 7.6 % molar of CuI (130 mg, 0.68 mmol) and 3 % molar of tetrakis-(triphenylphosphine)palladium (312 mg, 27 mmol) were added all at once. The final black solution was stirred for 24 hours at 20°C.

25 [0047] The resulting black suspension was concentrated under vacuum and the dark residue was extracted with 50 ml of dry pentane. The residual dark suspension was filtered on silanized silica and concentrated under vacuum. The black crude oil was crystallised twice in dry pentane and afforded the expected product as a yellow fine powder in 67 % yield (1.58 g, 3.31 mmol) (M.p 57-59°C). ^1H NMR (CDCl_3 , δ , ppm) 7.66 (4H, d); 7.56 (4H, d); 3.66 (18H, s). ^{13}C NMR (CDCl_3 , δ , ppm) 135.1, 132.2, 131.5, 124.2, 82.2, 75.3,

- 15 -

51.3. ^{29}Si NMR (CDCl_3 , δ , ppm) -55.3. Anal. Calc.; for $\text{C}_{25}\text{H}_{26}\text{O}_6\text{Si}_2$: C, 62.74; H, 5.40; Si, 11.73 %. Found; C, 60.05; H, 5.56; Si, 13.20 %.

5 Example 6

1,4-bis-[2-(4-trimethoxysilylphenyl)ethynyl]benzene

[0048] A solution of 4-(trimethoxysilyl)phenylacetylene (1g, 4.50 mmol) in dry triethylamine (12.5ml) with a 0.5 eq. of 1,4-diiodobenzene (0.74g, 2.25 mmol) was stirred for few 10 minutes.

[0049] 5% molar of CuI (21 mg, 0.112 mmol) and bis-(triphenylphosphine)palladium chloride II (80 mg, 0.112 mmol) were added all at once, the final brown suspension was stirred vigorously for 8 hours at $\sim 20^\circ\text{C}$. The brown 15 suspension was concentrated under vacuum and the dark residue was extracted with 50 ml of dry toluene. The yellow suspension was filtered on silanized silica and concentrated under vacuum. The expected product was obtained as a fine yellow-orange powder. Crystallisation in hexane / dichloromethane gave the expected product as an orange 20 powder (1.88g, 4.49 mmol) in 97 % yield. M.p. = 164-166°C. ^1H NMR (CDCl_3 , δ , ppm) 7.69 (4H, d), 7.59 (4H, d), 7.55 (4H, s), 3.67 (18 H, s). ^{13}C NMR (CDCl_3 , δ , ppm) 135.1, 132.0, 131.4, 130.4, 125.6, 123.5, 91.6, 90.8, 51.3. ^{29}Si NMR 25 (CDCl₃, δ , ppm) -55.9. Anal. Calc.; for $\text{C}_{28}\text{H}_{30}\text{O}_6\text{Si}_2$: C, 64.48; H, 5.78; Si, 10.83 %. Found; C, 63.42; H, 5.73; Si, 11.75 %.

Example 7

4,4'-bis-(trihydroxysilyl)diphenylacetylene

30 [0050] A solution of 4,4'-bis-(trimethoxysilyl)diphenylacetylene (1.58 g, 3.77 mmol) in 10 ml of ether was stirred vigorously with 29 ml of 0.5 % acetic acid solution for 41 days. The beige suspension was

- 16 -

filtered and the resulting solid was washed three times with acetone and ether. The resulting beige solid was dried for one day under vacuum at room temperature and yield (970 mg, 2.9 mmol) (77 %). ^1H NMR (DMSO-d₆, δ , ppm) 7.63 (4H, d); 5 7.50 (4H, d), 6.52 (6H, s). ^{13}C NMR (DMSO-d₆, δ , ppm) 139.3, 135.2, 130.9, 123.6, 90.7. ^{29}Si NMR (DMSO-d₆, δ , ppm) -55.2. IRFT (KCl, cm^{-1}) $\nu(\text{Si-OH})$, 3195; $\nu(\text{C=C}_{\text{Ar}})$, 1601; $\nu(\text{Si-C}_{\text{Ar}})$, 1128. Anal. Calcd. ; For $\text{C}_{14}\text{H}_{14}\text{O}_6\text{Si}_2$: C, 50.24 ; H, 4.22 % ; Si, 16.70. Found : C, 48.99 ; H, 3.96; Si, 15.00 %.

10

Example 8

4,4'-bis-(trihydroxysilyl)diphenylbut-1,3-diyne

[0051] A solution of 4,4'-bis-(trimethoxysilyl)diphenylbut-1,3-diyne (1.15 g, 2.40 mmol) 15 in 10 ml of ether was stirred vigorously with 13.70 ml of 0.5 % acetic acid solution for 36 days. The beige suspension was filtered and the solid was washed three times with ethanol, acetone and ether. The resulting beige crystalline solid was dried for one day under vacuum at room 20 temperature and the expected product was obtained in 65 % yield (750 mg, 1.56 mmol).

[0052] ^1H NMR (DMSO-d₆, δ , ppm) 7.65 (4H, d); 7.57 (4H, d); 6.58 (6H, s). ^{13}C NMR (DMSO-d₆, δ , ppm) 140.9, 135.2, 131.9, 121.6, 83.1, 74.7. ^{29}Si NMR (DMSO-d₆, δ , ppm) -55.6. 25 IRFT (KCl, cm^{-1}) $\nu(\text{Si-OH})$, 3208 ; $\nu(\text{C=C}_{\text{Ar}})$, 1594; $\nu(\text{Si-C}_{\text{Ar}})$, 1126. Anal. Calcd. ; For $\text{C}_{16}\text{H}_{14}\text{O}_6\text{Si}_2$: C, 53.62 ; H, 3.93 ; Si, 15.67 %. Found : C, 53.04 ; H, 3.75; Si, 16.35 %.

Example 9

1,1'-bis-(trihydroxysilyl)ferrocene

[0053] A solution of 1,1' bis-(trimethoxysilyl)ferrocene (1.25g, 2.93 mmol) in 3 ml of ether was stirred vigorously

- 17 -

with 1.37 ml of 0.5 % acetic acid solution for 75 days. The final orange suspension was filtered and the solid was washed three times with ethanol, acetone and ether.

[0054] The resulting orange crystalline solid was dried 5 for one day under vacuum at room temperature and the expected product was obtained in 69 % yield (0.59 g, 2 mmol).

[0055] ^1H NMR (DMSO-d₆, δ , ppm) 4.3 (4H); 4.2 (4H); 6.46 (6H, s). ^{13}C NMR (DMSO-d₆, δ , ppm) 74.8, 71.3, 68.6. ^{29}Si NMR 10 (DMSO-d₆, δ , ppm) -54.2.

Example 10

Chloromethyldiisopropylloxysilane

[0056] A solution of trichloromethylsilane (29.9 g, 200 mmol) in 200 ml of anhydrous pentane was placed in a schlenck tube under an argon atmosphere at 0°C. A solution of 2.2 equivalents of dry isopropanol (26.4 g, 440 mmol) was then added dropwise. The evolution of HCl was trapped by a concentrated solution of NaOH. At the end of addition the 20 reaction mixture was allowed to warm to room temperature and then stirred during 24 hours. After this time the colourless solution was evaporated under vacuum (2 mBar) to give a colourless oil (36g). It consisted in a mixture of chloromethyldiisopropylloxysilane (~80 %) and 25 methyltriisopropylloxysilane (~20 %). ^1H NMR (CDCl₃, δ , ppm) : 4.37 (2H, sept), 1.26 (12H, d), 0.48 (3H, s).

4-bromo-1-(methyldiisopropylloxysilyl)benzene

[0057] A solution of 4-bromophenyl magnesium bromide (7.82g, 50 mmol) in THF (100 ml) was added at 0°C to a 30 solution of chloromethyldiisopropylloxysilane (10g, 48 mmol). The mixture was stirred at room temperature for 24 hours. After evaporation of the solvent, the yellow solid was extracted by 200 ml of dry pentane and filtered. The

- 18 -

solvent was then pumped off to afford a yellow oil. Residual 1,4-dibromobenzene was sublimated under vacuum at 80°C to give 4-bromo-1-(methyldiisopropylloxysilyl)benzene as a colourless oil in 33 % yield (5.1g, 16 mmol). ¹H NMR

5 (CDCl₃, δ, ppm) 7.52 (4H, m) ; 4.22 (2H, heptuplet); 1.24 (12H, d); 0.39 (3H, s). ¹³C NMR (CDCl₃, δ, ppm) 136.1, 134.5, 131.3, 125.1, 65.8, 26.1, -2.8. ²⁹Si NMR (CDCl₃, δ, ppm) - 21.8..

4-iodo-1-(methyldiisopropylloxysilyl)benzene

10 [0058] A solution of 4-bromo-1-(methyldiisopropylloxysilyl)benzene (13.35g, 42.1 mmol) in THF (85 ml) was added slowly dropwise at 0°C to a suspension of magnesium chips (1.53g, 63.1 mmol) in THF (10 ml). After one hour, the Grignard reagent of 4-bromo-1-(methyldiisopropylloxysilyl)benzene was added dropwise at 0°C to iodine (13.87g, 54 mmol) dissolved in 50 ml of dry THF. After stirring during four hours, the solvent was pumped off and the residue was extracted with dry pentane (200 ml) and filtered. The yellow solution was concentrated to afford 4-iodo-1-(methyldiisopropylloxysilyl)benzene as a yellow oil of in 84 % yield. ¹H NMR (CDCl₃, δ, ppm) 7.76 (2H, d); 7.42 (2H, d); 4.21 (2H, heptuplet); 1.23 (12H, t); 0.37 (3H, s).

4-iodo-1-(methyldimethoxysilyl)benzene

15 [0059] Compound 4-iodo-1-(methyldiisopropylloxysilyl)benzene (11.27g, 35.5mmol) was dissolved in dry methanol (12.87g, 400 mmol). 1 % molar of p-toluene sulfonic acid (53 mg, 0.3 mmol) was added all at once. The yellow suspension was stirred for 4 hours. The organic solvent was pumped off and the corresponding crude 30 orange oil was distilled under vacuum (B.p. 59-69°C, 3.10⁻¹ mbar) to afford 4-iodo-1-(methyldimethoxysilyl)benzene as a colourless oil (9g, 30 mmol) in 82 % yield. ¹H NMR (CDCl₃, δ, ppm) 7.78 (2H, d); 7.37 (2H, d); 3.58 (6H, s); 0.37 (3H, s).

- 19 -

[1-(4-(methyldimethoxysilyl)phenyl), 2-trimethylsilyl]acetylene

[0060] A solution of 4-iodo-1-(methyldimethoxysilyl)benzene (5.38g, 17.4 mmol) dissolved in dry triethylamine (50 ml) with a stoichiometric amount of trimethylsilylacetylene (1.76g, 17.4 mmol) was added all at once to give a colourless solution. 2.5 % molar of CuI (85 mg, 0.44 mmol) and bis-(triphenylphosphine)palladium chloride II (320 mg, 0.44 mmol) were added and the final brown suspension was stirred vigorously for 2 hours at ~ 20°C. The brown suspension was concentrated under vacuum and the residue was extracted with 150 ml of dry pentane. The suspension was filtered on silanized silica and concentrated under vacuum. The expected product [1-(4-(methyldimethoxysilyl)phenyl), 2-trimethylsilyl]acetylene was obtained as a greenish oil (1.88 g, 4.49 mmol) in quantitative yield. ^1H NMR (CDCl_3 , δ , ppm) 7.59 (2H, d); 7.49 (2H, d); 3.58 (6H, s); 0.39 (3H, s); 0.29 (9H, s).

4-(methyldimethoxysilyl)phenylacetylene

[0061] A solution of [1-(4-(methyldimethoxysilyl)phenyl), 2-trimethylsilyl]acetylene (5g, 17.80 mmol) in 11 ml of dry methanol was stirred for 3.5 hours with potassium carbonate (224 mg, 1.62 mmol) at room temperature. The dark suspension was concentrated under vacuum and the residue was extracted with 60 ml of dry hexane. After filtration, the solvent was removed under vacuum to give 4-(methyldimethoxysilyl)phenylacetylene as a red oil (2.8g, 13.5 mmol) in 75 % yield. ^1H NMR (CDCl_3 , δ , ppm) 7.59 (2H, d); 7.55 (2H, d); 3.59 (6H, s); 3.16 (1 H, s); 0.39 (3H, s).

4,4'-bis-(methyldimethoxysilyl)diphenylacetylene

[0062] A solution of [1-(4-(methyldimethoxysilyl)phenyl), 2-trimethylsilyl]acetylene (0.96g, 4.64 mmol) in dry triethylamine (15 ml) with a

- 20 -

stoichiometric amount of 4-iodo-1-(methyldimethoxysilyl)benzene (1.43g, 4.64 mmol) was stirred during few minutes. 2.5 % molar of CuI (23 mg, 0.12 mmol) and bis-(triphenylphosphine)palladium chloride II (82 mg, 0.12 mmol) were added all at once, the final beige suspension was stirred vigorously for 15 hours at ~ 20°C. The corresponding suspension was filtered on silanized silica and concentrated under vacuum. The expected product 4,4'-bis-(methyldimethoxysilyl)diphenylacetylene was obtained as an orange oil (1.72g, 4.44 mmol) in 96 % yield.

¹H NMR (CDCl₃, δ, ppm) 7.65 (4H, m); 7.57 (4H, d); 3.60 (12H, s); 0.40 (6H, s). ¹³C NMR (CDCl₃, δ, ppm) 134.69, 134.32, 131.35, 112.24, 90.73, 50.98, -4.79. ²⁹Si NMR (CDCl₃, δ, ppm) -14.46.

15

Example 11

4,4'-bis-(methyldimethoxysilyl)diphenylbut-1,3-diyne

[0063] In a schlenk tube under argon, 1.66 g (8.04 mmol) of 4-(methyldimethoxysilyl)phenylacetylene, one equivalent of chloroacetone (0.745g, 8.04 mmol), two equivalents of dry ethylamine (2.3 ml), 7.6 % molar of CuI (116 mg, 0.61 mmol) and tetrakis-(triphenylphosphine) palladium 0 (280 mg, 0.61 mmol) were added all at once. The final black solution was stirred for 4.5 hours at ~ 20°C. The residual dark suspension was filtered on silanized silica and concentrated under vacuum to afford a crude yellow oil. It was crystallised two times in dry pentane and afforded 4,4'-bis-(methyldimethoxysilyl)diphenylbut-1,3-diyne as a yellow fine powder (1g, 2.43 mmol) (M.p. 85-86°C) in 61 % yield. ¹H NMR (CDCl₃, δ, ppm) 7.64 (4H, d); 7.57 (4H, d); 3.60 (12H, s); 0.39 (6H, s). ²⁹Si NMR (CDCl₃, δ, ppm) -14.80.

- 21 -

Example 12

4,4'-bis-(methyldihydroxysilyl)diphenylacetylene

[0064] A suspension of 4,4'-bis-(methyldimethoxysilyl)diphenylacetylene (1.62g, 4.2 mmol) in 8 ml of ether was stirred vigorously with 6.65 ml of 0.5 % acetic acid solution for 55 days. The beige suspension was filtered and the solid was washed three times with acetone and ether. The resulting fine beige solid was dried for one day under vacuum at room temperature and gave 4,4'-bis-(methyldihydroxysilyl)diphenylacetylene in 30 % yield (410 mg, 1.26 mmol). ^1H NMR (DMSO- d_6 , δ , ppm) 7.63 (4H, s); 7.54 (4H, s); 6.49 (4H, s); 0.19 (6H, s). ^{13}C NMR (DMSO- d_6 , δ , ppm) 141.2, 134.5, 131.2, 123.7, 90.8, 0.18. ^{29}Si NMR (DMSO- d_6 , δ , ppm) -21.7.

15

Example 13

1,4-bis-(dimethoxymethylsilyl)benzene

[0065] A solution of 1,4-dibromobenzene (24.75 g, 105 mmol) in 60 ml of anhydrous THF, was added dropwise to a suspension of magnesium (12.60 g, 518 mmol) and methyltrimethoxysilane (28.60 g, 210 mmol) in 20 ml of anhydrous THF at 0°C. The suspension was then stirred 24 hours at 20°C. The solvent was pumped off under vacuum (2 mBar), the reaction mixture was then taken up with 250 ml of dry pentane. The green suspension was filtered. The filtrate was evaporated under vacuum (2 mBar) to give a pale yellow oil which was distilled. (B.p. 105-110°C/5 10^{-1} mBar) (7.38 g, 26.5 mmol) of 1,4-bis-(dimethoxymethylsilyl)benzene were obtained as a colourless oil which crystallised at room temperature in 25% yield. ^1H NMR (CDCl_3 , δ , ppm) : 7.67 (4H, s), 3.60 (12H, s), 0.39 (6H, s). ^{29}Si NMR (CDCl_3 , δ , ppm) : -14.90. Anal. Calc. For

- 22 -

$C_{12}H_{22}O_4Si_2$: C, 50.35; H, 7.69; Si, 19.58 %. Found: C, 50.30; H, 7.64; Si, 20.01 %.

Example 14

1,4-bis-(dimethoxymethylsilyl)biphenyl

5 [0066] A solution of 4,4'-dibromobiphenyl (25 g, 80 mmol) in 120 ml of anhydrous THF, was added dropwise to a suspension of magnesium (7.80 g, 321 mmol) and methyltrimethoxysilane (30 g, 220 mmol) in 50 ml of anhydrous THF at 0°C. The pale green suspension was then 10 stirred 24 hours at 20°C. The solvent was pumped off under vacuum (2 mBar), the reaction mixture was then taken up with 200 ml of dry pentane. The grew suspension was filtered. The filtrate was evaporated under vacuum (2 mBar) to give a pale yellow oil which was distilled. (B.p. 63-171°C/5 10^{-1} 15 mBar) (2.8 g, 28 mmol) of 1,4-bis-(dimethoxymethylsilyl)biphenyl were obtained as a colourless oil in 10% yield. 1H NMR ($CDCl_3$, δ , ppm) : 7.72 (4H, d), 7.67 (4H, d), 3.65 (12H, s), 0.44 (6H, s). ^{29}Si NMR ($CDCl_3$, δ , ppm) : -14.7.

20

Example 15

4,4'-bis-(methyldihydroxysilyl)benzene:

25 [0067] A suspension of 4,4'-bis-(methyldimethoxysilyl)benzene (1g, 3.49 mmol) in 5 ml of ether was stirred vigorously with 1.6 ml of 0.5 % acetic acid solution for two hours. The white suspension was filtered and the solid was washed three times with acetone and ether.

30 [0068] The resulting fine white solid was dried for one day under vacuum at room temperature and gave 4,4'-bis-(methyldihydroxysilyl)benzene in 95 % yield (0.76g, 3.31 mmol). 1H NMR ($DMSO-d_6$, δ , ppm) 7.53 (4H, s); 6.32 (4H, s); 0.14 (6H, s). ^{13}C NMR ($DMSO-d_6$, δ , ppm) 141, 133.2, 0.35. ^{29}Si

- 23 -

NMR (DMSO-d₆, δ, ppm) -21.28. Anal. Calcd. ; For C₈H₁₄O₄Si₂ : C, 41.71; H, 6.12; Si, 25.38 %. Found: C, 41.51; H, 6.19; Si, 25.30 %.

5 Example 16

4,4'-bis-(methyldihydroxysilyl)biphenyl:

[0069] A suspension of 4,4'-bis-

(methyldimethoxysilyl)biphenyl (2.4g, 6.62 mmol) in 5 ml of ether was stirred vigorously with 3 ml of 0.5 % acetic acid 10 solution for 32 days. The white suspension was filtered and the solid was washed three times with acetone and ether. The resulting fine white solid was dried for one day under vacuum at room temperature and gave 4,4'-bis-(methyldihydroxysilyl)biphenyl in 32% yield (0.65g, 2.10 15 mmol). ¹H NMR (DMSO-d₆, δ, ppm) 7.66 (8H, s); 6.40 (4H, s); 0.19 (6H, s). ¹³C NMR (DMSO-d₆, δ, ppm) 144.7, 139.3, 134.9, 126.6, 0.38. ²⁹Si NMR (DMSO-d₆, δ, ppm) -21.22. Anal. Calcd. ; For C₁₄H₁₈O₄Si₂ : C, 54.87; H, 5.92; Si, 18.33 %. Found: C, 54.82; H, 5.79; Si, 18.80 %.

20

Example 17

4-(methyldiisopropylloxysilyl)styrene

[0070] A solution of 4-chlorostyrene (10 g, 72 mmol) in

25 40 ml of anhydrous THF, was added dropwise to a suspension of magnesium chips (2.07 g, 86.4 mmol) and chloromethyldiisopropylloxysilane (28.2 g, 144 mmol) in 50 ml of anhydrous THF at 0°C. The suspension was then stirred 24 hours at 20°C. The solvent was pumped off under vacuum (2 mBar), the reaction mixture was then taken up with 200 ml of 30 dry pentane. The suspension was filtered. The filtrate was evaporated under vacuum (2 mBar) to give an oil which was distilled. (Eb. 70-75°C/5 10⁻² mBar) (8.23 g, 31 mmol) of 4-(methyldiisopropylloxysilyl)styrene were obtained as a

- 24 -

colourless oil in 51% yield. ^1H NMR (CDCl_3 , δ , ppm) : 7.65 (2H, d), 7.44 (2H, d), 6.75 (1H, dd), 5.80 (1H, d), 5.30 (1H, d), 4.22 (1H, heptuplet), 1.22 (12H, d), 0.39 (3H, s).

4-(methyldimethoxysilyl)styrene

5 [0071] Compound 4-(methyldiisopropylloxysilyl)styrene (8.23g, 31mmol) was dissolved in dry methanol (10 ml,). 1 % molar of p-toluene sulfonic acid (17 mg) was added all at once. The yellow suspension was stirred for 4 hours. The organic solvent was pumped off and the corresponding crude 10 oil was distilled under vacuum (B.p. 70-80°C, 5.10^{-2} mbar) to afford 4-(methyldimethoxysilyl)styrene as a yellow oil (4g, 20 mmol) in 65 % yield. ^1H NMR (CDCl_3 , δ , ppm) 7.64 (2H, d); 7.49 (2H, d); 6.77 (1H, dd), 5.84 (1H, d), 5.33 (1H, d), 3.60 (6H, s); 0.39 (3H, s).

15 4-bromo1-(methyldimethoxysilyl)benzene

[0072] Compound 4-bromo1-(methyldiisopropylloxysilyl)benzene (5g, 16mmol) was dissolved in dry methanol (20 ml). 1 % molar of p-toluene sulfonic acid (30 mg,) was added all at once. The 20 suspension was stirred for 4 hours. The organic solvent was pumped off and the corresponding crude oil was 4-bromo1-(methyldimethoxysilyl)benzene (2g, 8 mmol) in 50 % yield. ^1H NMR (CDCl_3 , δ , ppm) 7.56 (4H, m); 3.59 (6H, s); 0.38 (3H, s).

4,4'-bis(methyldimethoxysilyl)stilbene

25 [0073] A solution of 4-(methyldimethoxysilyl)styrene (1.52g, 7.2 mmol) and 4-bromo1-(methyldiisopropylloxysilyl)benzene (1.9g, 7.2mmol) was dissolved in 15ml toluene. Palladium acetate (81mg, $3.6 \cdot 10^{-4}$ mol), dry triethylamine (4.39g, 43.2mmol) and tri-30 orthotolylphosphine (TOP) (438mg, $1.5 \cdot 10^{-3}$ mol) were added all at once successively. The suspension was heated during 24 hours at 120°C. The resulting suspension was filtered at room temperature over silanized silica. The solvent was

- 25 -

pumped off under vacuum and a yellow powder was recovered. It was recrystallized in pentane. 4,4'-bis(methyldimethoxysilyl)stilbene (1.54g, 3.96mmol) was obtained (yield 55%). ^1H NMR (CDCl_3 , δ , ppm) 7.65 (4H, d); 5 7.61 (4H, d), 7.19 (2H, s), 3.60 (12H, s); 0.39 (3H, s).

Example 18

[0074] 4,4'-bis(methyldihydroxysilyl)stilbene was prepared from 4,4'-bis-(methyldimethoxysilyl)stilbene by the 10 procedure of Example 16. 4,4'-bis-(methyldihydroxysilyl)stilbene had ^1H NMR (DMSO-d_6 , δ , ppm) 7.68 (4H, d); 7.59 (4H, d), 7.29 (2H, s), 6.37 (4H, s); 0.39 (6H, s). ^{13}C NMR (DMSO-d_6 , δ , ppm) 139.7, 138.1, 134.7, 129.5, 126.4, 0.02. ^{29}Si NMR (DMSO-d_6 , δ , ppm) -21.36.

15

Examples 19 to 22 - Resin Compositions

[0075] 90 wt.% of the base resin [$(\text{PhSiO}_{3/2})_{0.40}(\text{MeSiO}_{3/2})_{0.45}(\text{PhMeSiO})_{0.1}(\text{Ph}_2\text{SiO})_{0.05}$] was mixed with 10 wt.% of a compound (B) as a solution in an 20 appropriate solvent as listed below, together with 0.2 wt.% of a mixture of zinc dioctoate and choline octoate) as the curing catalyst.

[0076] Example 19 - 1,4-bis(dimethoxymethylsilyl)benzene prepared in Example 13; solvent tetrahydrofuran (THF)

25 **[0077]** Example 20 - 4,4'-bis(trimethoxysilyl)biphenyl prepared as described by Corriu et al., Chem. Mater., (1992), 4, 1217-1224; solvent toluene.

[0078] Example 21 - 4,4'-bis(trihydroxysilyl)diphenylbut-1,3-diyne prepared in Example 8; solvent dimethylsulphoxide 30 (DMSO)

[0079] Example 22 - 1,4-bis(trihydroxysilyl)benzene ; solvent DMSO

- 26 -

[0080] After mixing the majority of the solvent was removed at 80°C under vacuum and the resin blend was cured through a fourteen day curing cycle. During cure, the temperature was gradually raised from 80 °C to 260 °C to 5 obtain a cured cast plate. Specimens for dynamic mechanical analysis (DMA) were obtained by cutting 1x6x25 mm pieces from the casting. DMA was done from -155 °C to 500 °C at 1 Hz in a tensile mode; the oscillation amplitude was 5 microns. The storage modulus and loss factor $\tan \delta$ were 10 recorded. For flexural testing, the three point bending test was performed on an Instron 8562 (Trade Mark) test machine per ASTM standard D 790. The plane strain fracture toughness, K_{IC} , was obtained per ASTM D 5045, and the critical strain energy release rate, G_{IC} , (fracture energy) 15 was calculated from K_{IC} based on Linear Elastic Fracture Mechanics assumptions.

[0081] A base resin casting without addition of compound (B) was also cured and analysed in the same way as a 20 comparison.

- 27 -

[0082] The results for Examples 19 and 20 are shown in Table 1 below

Table 1

5

	Example 19	Cured base resin	Example 20
Young's Modulus (GPa)	1.82	1.88	1.73
Strain at break %	2.80	2.46	2.54
Flexural strength (MPa)	37.8	37.7	33.9
Fracture toughness K_{Ic} , ($\text{MPam}^{1/2}$)	0.260	0.253	0.308
Fracture Energy (J/m^2)	42.5	38.3	54.8

[0083] It can be seen that the incorporation of each compound (B) into the resin structure slightly lowers the resin's Young's modulus, but increases the fracture 10 toughness (K_{Ic}) and the critical energy release rate G_{Ic} . The fracture toughness K_{Ic} measures the difficulty of initiating a crack in the material, while the G_{Ic} measures how much energy per unit area it needs to propagate a crack in the material once the crack is initiated. The modified 15 resin of Example 19 is slightly tougher than the unmodified resin, and the modified resin of Example 20 is substantially tougher than the unmodified resin.

[0084] For Example 21, the storage modulus (1A) and loss 20 factor ($\tan \delta$, (2A)) of the modified resin are plotted in Figure 1, together with the storage modulus (1C) and loss factor (2C) of the unmodified resin. The high temperature transition peak of the $\tan \delta$ curve was much enhanced by the incorporation of the 4,4'-bis(trihydroxysilyl)diphenylbut-

- 28 -


1,3-diyne. The addition of this modifier significantly enhances the mechanical damping capability of the resin in the temperature range 150-350°C. This damping capability is important for applications where mechanical vibration needs 5 to be mitigated.

[0085] For Example 22, the storage modulus (1B) and loss factor(2B) of the modified resin are plotted in Figure 2, together with the storage modulus (1C) and loss factor (2C) 10 of the unmodified resin. With 10 wt.% 1,4-bis(trihydroxysilyl)benzene reacted into the resin, the storage modulus is much higher, approximately twice that of the unmodified resin throughout the whole temperature range, even though the modulus dependence on temperature was quite 15 similar and no obvious shift of glass transition temperature was seen. Both had a glass transition temperature at about 100 °C. The much higher modulus above the glass transition temperature indicated a higher crosslink density in the modified resin.

- 29 -

CLAIMS

1. A curable silicone resin composition comprising (A) an uncured silicone resin having units of the formula $(R^*)_a(R)_bSiO_{(4-a-b)/2}$, where each R^* is a functional group capable of reacting with Si-OH and/or Si-alkoxy groups and each R is a nonfunctional monovalent hydrocarbon group, $a+b$ is from 1.0 to 3.0 and each molecule of uncured silicone resin contains an average of at least two groups R^* , and (B) a silanol or hydrolysable compound of the formula




where each R' represents a hydroxyl group or a hydrolysable group; each R'' represents hydrogen, a monovalent hydrocarbon which optionally is substituted, or a group within the above definition of R' ; and Ar is a substantially nonflexible linkage including at least one para-arylene moiety, so that the groups $(R')_2R''Si-$ are spatially separated.

2. A composition according to claim 1, characterised in that Ar is a 1,4-phenylene linkage which is optionally substituted by one or more alkyl, aryl, aralkyl or alkenyl group or may be part of a fused ring system.
3. A composition according to claim 1, characterised in that Ar comprises two to four 1,4-phenylene moieties, each optionally substituted by one or more alkyl, aryl, aralkyl or alkenyl group, linked in a substantially linear conformation.

- 30 -

4. A composition according to claim 3, characterised in that the 1,4-phenylene moieties are linked by a direct bond or by an acetylene or butadiyne linkage or by an optionally substituted vinylene linkage.
5. A composition according to any of claims 1 to 4, characterised in that R' is a hydroxyl group or an alkoxy group having 1 to 6 carbon atoms.
6. composition according to any of claims 1 to 5, characterised in that R" is an alkyl group having 1 to 6 carbon atoms or a phenyl group.
7. A composition according to any of Claims 1 to 6, characterised in that the uncured silicone resin has the empirical formula $(R^*)_a(R)_bSiO_{(4-a-b)/2}$ where a+b is between 0.8 and 1.6.
8. Use of a silanol or hydrolysable compound of the formula




where R', R" and Ar are defined as in claim 1, as a toughening agent for a curable silicone resin.

9. An organosilicon compound of the formula $(HO)_3Si-Ar'-Si(OH)_3$ wherein Ar' is a linkage containing two or more phenylene moieties held in a substantially linear conformation so that the silanetriol groups are spatially separated.

10. An organobis(silanetriol) according to claim 9, characterised in that Ar comprises two to four 1,4-phenylene groups linked by a direct bond or by an acetylene or butadiyne linkage or by a vinylene linkage, each 1,4-phenylene group being optionally substituted by one or more alkyl, aryl, aralkyl or alkenyl group or being optionally part of a fused ring system.
11. An organosilicon compound of the formula
$$\begin{array}{c} \text{R}'' & & \text{R}'' \\ | & & | \\ \text{R}' - \text{Si} - \text{Ap} - \text{X} - \text{Ap} - \text{Si} - \text{R}' \\ | & & | \\ \text{R}' & & \text{R}' \end{array}$$
wherein R' and R'' are defined as in Claim 1, each Ap is a para-arylene moiety, and X is a substantially inflexible linkage having at least two carbon atoms so that the groups $(\text{R}')_2\text{R}''\text{Si}-$ are spatially separated.
12. An organosilicon compound according to Claim 11, characterised in that X comprises at least one acetylene, butadiyne or vinylene linkage and/or a para-arylene moiety.
13. An organosilicon compound according to Claim 11 or Claim 12, characterised in that Ar is a 1,4-phenylene linkage which is optionally substituted by one or more alkyl, aryl, aralkyl or alkenyl group or may be part of a fused ring system.
14. A process for forming a cured silicone resin composition, comprising mixing (A) an uncured silicone resin having units of the formula $(\text{R}^*)_a(\text{R})_b\text{SiO}_{(4-a-b)/2}$,

where each R* is a functional group capable of reacting with Si-OH and/or Si-alkoxy groups and each R is a nonfunctional monovalent hydrocarbon group, a+b is from 1.0 to 3.0 and each molecule of uncured silicone resin contains an average of at least two groups R*, with (B) a silanol or hydrolysable compound of the formula



where each R' represents a hydroxyl group or a hydrolysable group; each R'' represents hydrogen, a monovalent hydrocarbon which optionally is substituted, or a group within the above definition of R'; and Ar is a substantially nonflexible linkage including at least one para-arylene moiety, so that the groups $(\text{R}')_2\text{R}''\text{Si}-$ are spatially separated, and curing the composition under conditions such that (A) and (B) are copolymerised.

15. A process according to claim 14 for preparing a substrate having a cured silicone resin film thereon, characterised in that (A) and (B) are mixed in a solvent, the resulting solution is coated on the substrate, and the coating is dried and subjected to curing conditions.
16. A process according to claim 14 for producing a moulded cured silicone resin, characterised in that (A) and (B) are mixed in a solvent, the resulting solution is cast in a mould, solvent is removed and the composition is cured in the mould.

Fig 1





FIG 2



INTERNATIONAL SEARCH REPORT

In National Application No
PCT/EP 01/04606A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C08K5/5415 C07F7/08 C08L83/04 C07F7/18

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 C08G C08L C08K C07F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, COMPENDEX, INSPEC

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category ^o	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 3 464 937 A (BAMFORD WILLIAM RANDALL ET AL) 2 September 1969 (1969-09-02) column 1, line 34 -column 2, line 11; claims 1-11; examples 5-10 --- -/-	1-3, 5, 14-16

 Further documents are listed in the continuation of box C. Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search 24 September 2001	Date of mailing of the international search report 04/10/2001
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016	Authorized officer Seiberlich, P

INTERNATIONAL SEARCH REPORT

Int. Application No.
PCT/EP 01/04606

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	<p>DVORNIC P R ET AL: "EXACTLY ALTERNATING SILARYLENE-SILOXANE POLYMERS. \RELATIONSHIPS BETWEEN POLYMER STRUCTURE AND GLASS TRANSITION TEMPERATURE" MACROMOLECULES, AMERICAN CHEMICAL SOCIETY. EASTON, US, vol. 25, no. 14, 6 July 1992 (1992-07-06), pages 3769-3778, XP000281747 ISSN: 0024-9297 page 3770, left-hand column, paragraphs 2-4 page 3773, right-hand column, paragraph 4 -page 3774, left-hand column, paragraph 1; table III page 3773, right-hand column, paragraphs 2,3; figure 2</p> <p>---</p>	1-3,5, 14-16
A	<p>CORRIU R: "THERMAL ISOMERIZATION OF ALTERNATING SILPHENYLENE-SILOXANE COPOLYMER" JOURNAL OF POLYMER SCIENCE, POLYMER CHEMISTRY EDITION, JOHN WILEY AND SONS. NEW YORK, US, vol. 32, no. 1, 15 January 1994 (1994-01-15), pages 187-191, XP000418025 ISSN: 0887-624X the whole document</p> <p>---</p>	1-3,5, 14-16
A	<p>DVORNIC P R ET AL: "EXACTLY ALTERNATING SILARYLENE-SILOXANE POLYMERS. 10 SYNTHESIS AND CHARACTERIZATION OF SILPHENYLENE-SILOXANE POLYMERS CONTAINING FLUOROALKYL AND HYDRIDO SIDE GROUPS" MACROMOLECULES, AMERICAN CHEMICAL SOCIETY. EASTON, US, vol. 27, no. 20, 26 September 1994 (1994-09-26), pages 5833-5838, XP000474818 ISSN: 0024-9297 the whole document</p> <p>---</p>	1-16
A	<p>CERVEAU G ET AL: "SOL-GEL PROCESS: TEMPERATURE EFFECT ON TEXTURAL PROPERTIES OF A MONOPHASIC HYBRID MATERIAL" CHEM. COMMUN., THE ROYAL SOCIETY OF CHEMISTRY, 26 July 1999 (1999-07-26), pages 2081-2082, XP001021012 the whole document</p> <p>-----</p>	1-16

INTERNATIONAL SEARCH REPORT

Information on patent family members

In ional Application No
PCT/EP 01/04606

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 3464937 A	02-09-1969	GB 1119666 A DE 1620913 A FR 1488808 A NL 6611054 A	10-07-1968 21-05-1970 07-02-1967