



(22) Date de dépôt/Filing Date: 1999/09/14

(41) Mise à la disp. pub./Open to Public Insp.: 2000/04/09

(45) Date de délivrance/Issue Date: 2010/01/12

(30) Priorité/Priority: 1998/10/09 (US60/103,761)

(51) Cl.Int./Int.Cl. *C08G 63/08* (2006.01),
A61L 17/00 (2006.01), *A61L 17/12* (2006.01),
C08G 63/64 (2006.01), *C08G 63/664* (2006.01),
C08G 64/18 (2006.01), *C08G 65/26* (2006.01),
C08G 81/00 (2006.01), *C08L 67/04* (2006.01),
D01F 6/84 (2006.01)


(72) Inventeurs/Inventors:
ROBY, MARK, US;
JONN, JERRY YING, US

(73) Propriétaire/Owner:
UNITED STATES SURGICAL CORPORATION, US

(74) Agent: MCFADDEN, FINCHAM

(54) Titre : COPOLYMERES SEQUENCES ET ARTICLES CHIRURGICAUX QUI EN SONT FABRIQUES

(54) Title: BLOCK COPOLYMERS AND SURGICAL ARTICLES THEREFROM



(57) Abrégé/Abstract:

A method for making bioabsorbable block copolymer includes extruding a mixture of first polymeric component particles with second polymeric component particles under conditions sufficient to cause transesterification. The resulting block copolymer filaments can be used to form surgical sutures.



ABSTRACT

5 A method for making bioabsorbable block copolymer includes extruding a mixture of first polymeric component particles with second polymeric component particles under conditions sufficient to cause transesterification. The resulting block copolymer filaments can be used to form surgical sutures.

BLOCK COPOLYMERS AND SURGICAL ARTICLES THEREFROMBACKGROUND1. Technical Field

5 The present disclosure relates to methods for making block copolymers for use in producing surgical articles such as sutures, and more particularly to a method for making bioabsorbable block copolymers by transesterifying two or more pre-polymers.

2. Background of Related Art

10 Methods for making monofilaments that are suitable surgical sutures generally include the steps of extruding at least one bioabsorbable or nonbioabsorbable polymer to provide filaments, drawing, or stretching the solidified filaments to achieve molecular orientation and annealing the drawn filaments to relieve internal stresses. See, e.g.
15 U.S. Pat. Nos. 3,092,891, 3,106,442, 3,630,205, 4,911,165, 5,217,485 and U.K. Patent Specification No. 1,588,081 and European Patent Application No. 415,783.

20 Examples of copolymers used to fabricate surgical articles such as sutures include, for example, diblock copolymers, symbolized by an AB block structure, or triblock copolymers, symbolized by an ABA block structure, wherein A and B represent polymeric chains having repeating units of a given type wherein the A chain and the B chain are each

normally derived from different monomer components of different combinations of monomers. See, e.g., U.S. Patent Nos. 4,826,945 to Cohn et al. and 4,438,253 to Casey et al.

5 Transesterification that occurs in bioabsorbable polyesters produces a high degree of shuffling and randomness which prevents the resulting transesterfied copolymer from having a well defined block structure. See, e.g., U.S. Patent No. 5,252,701 to Jarrett et al. Such randomness also affects the properties of the final surgical product, such as in vivo strength retention as well as other chemical and physical properties such as solubility, brittleness, and rate of absorption. It would be desirable to have a simple method to make a surgical article from a bioabsorbable block copolymer through a transesterification reaction while maintaining a well defined block structure.

10

15

SUMMARY

Methods for making a bioabsorbable block copolymer are provided herein. The methods include melt extrusion of two polymeric components at time and temperature conditions such as to effect transesterification and formation of a copolymer having well defined block structure with little shuffling between the blocks. The polymeric components can each be a homopolymer or a copolymer.

20

BRIEF DESCRIPTIONS OF THE DRAWINGS

Various embodiments are described herein with reference to the drawings, wherein

Fig. 1 is a schematic illustration of an apparatus which is suitable for carrying out the method described herein to form a filament;

Fig. 2 is a schematic illustration of further processing, including stretching and heating, of the resulting filament.

DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

Block copolymers are made using the methods described herein by mixing pellets or powder of a first polymeric component with pellets or powder of a second polymeric component, loading the mixed pellets or powder into an extruder, extruding the mixture of polymers and optionally quenching the extruded copolymer. The temperature and duration of heating within the extruder are controlled so as to effect transesterification of the two polymeric components while maintaining a well defined block structure of the resulting copolymer.

The extrusion temperature must be at least a minimum to accomplish transesterification, yet it should not be so high as to degrade the polyester starting materials or

to generate substantial shuffling of the molecular structure of the starting polyesters. The term "shuffling" as used herein refers to mixing of the A block with the B block of the copolymer so that conventional block structure is lost and a random or segmented $(AB)_n$ structure is produced.

While some small degree of shuffling may, as a practical matter, be unavoidable, substantial shuffling will convert conventional block structures (e.g., diblock AB or triblock ABA, or ABAB or ABABA, molecular structures etc.) to segmented block $(AB)_n$ or other random-type structures and should be avoided. Generally, the operating temperature ranges from about 50°C to about 240°C, preferably from about 180°C to about 220°C.

The residence time of the two polymeric starting components within the extruder should be sufficient to accomplish transesterification but insufficient to generate a substantial amount of shuffling or loss of block structure in the resulting copolymer. Suitable residence times will vary depending upon a number of factors such as the precise nature of the starting polyesters and the extrusion temperature and physical shape and size of the polymeric particles. The conditions employed should ensure a complete melt of the polymer mixture and a good mixing of the polymer starting materials. Generally, the higher the extrusion

temperature, the shorter the residence time needed to obtain a desired degree of transesterification and vice versa. The residence time will normally be in the range of about 2 to about 20 minutes, preferably about 4 to about 10 minutes.

5 The quench bath, which is provided to quickly cool the exiting filament, can be a bath of water maintained at a temperature of from about 25°C to about 28°C.

10 The first and second polymeric components must be capable of undergoing transesterification to produce a block copolymer and can include any monomer or combinations of monomers known to form bioabsorbable polymers. The first and second polymeric components can be bioabsorbable homopolymers such as, for example, polyglycolide, polylactide, polydioxanone, polycaprolactone, polyalkylene
15 oxide or polytrimethylene carbonate. Moreover, one or both of the first and second polyester components can be a copolymer made from a combination of monomers known to form bioabsorbable polymers. The aforementioned polymer starting materials are known to those with skill in the art and are
20 in some cases commercially available in pellet or powder form. It should, of course, be understood that more than two polymeric starting materials can be employed to produce block copolymers having an ABC, ABCD, etc. structures. Addition of a catalyst is not generally necessary where the

polymer used for mixing contains residual catalyst.

However, small amounts of catalyst can be used if desired, to accelerate the transesterification in order to reduce the residence time.

5 Generally, the specific operating temperatures used to perform transesterification will depend on the particular mixture of polymer components and the ratios being used. The temperatures will typically be between the minimum melting temperature of the higher melting polymer and the maximum melting temperature of the lower melting
10 polymer. For example, in the case of polymer components polydioxanone and polyglycolide, the temperatures will range from about 100°C, i.e., the minimum melting temperature for polydioxanone, to about 230°C, i.e., the maximum melting
15 temperature of polyglycolide. In the event a greater amount of one polymer component is used, the operating temperature will approach the maximum operating temperature of that polymer component. Thus, e.g., in the case of polyglycolide being the major amount of the two polymer components used,
20 the operating temperature will be closer to 230°C.

By keeping the processing temperature within the operating range given above shuffling can be kept below about 10%. That is, 90% or more of the resulting block copolymer will maintain the well defined block structure

dictated by the polymeric starting materials with 10% or less having a segmented $(AB)_n$ or other type structure. The block structure of the resulting polymer can be measured by methods known to those skilled in the art such as, for
5 example, ^{13}C NMR.

Extrusion apparatus suitable for use in the method described herein are known and described, for example, in U.S. Patent Nos. 5,217,485 and 5,456,696.

Fig. 1 schematically illustrates a particularly
10 useful apparatus for extrusion and quenching of a filament. Extruder unit 10 is of a known or conventional type and is equipped with controls for regulating the temperature of barrel 11 in various zones thereof, e.g., progressively higher temperatures in three consecutive
15 zones A, B and C along the length of the barrel. Pellets or powder of polymer are introduced to the extruder through drier-hopper 12. Suitable polymers are discussed hereinbelow.

Motor-driven metering pump 13 delivers melt
20 extruded polymer at a constant rate to spin pack 14 and thereafter through a spinneret 15 possessing one or more orifices of desired diameter to provide a molten filament 16 which then enters quench bath 17 where the filament solidifies. The quench bath is preferred, but optional,
25 and

preferably contains water. Shapes other than filaments can also be formed by an appropriately chosen die.

5 The distance filament 16 travels after emerging from spinneret 15 to the point where it enters quench bath 17, i.e. the air gap, can vary and can advantageously be from about 0.5 to about 100 cm. If desired, a chimney (not shown), or shield, can be provided to reduce the length of the air gap, e.g. from 1 to 10 cm, thereby isolating filament 16 from contact with air currents which might otherwise affect the cooling of the filament 16 in an unpredictable manner. Filament 16 is passed through quench bath 17 around driven roller 18 and over idle rollers 19 and 20. Optionally, a wiper (not shown) may remove excess water from the filament 16 as it is removed from quench bath 17. On exiting the quench bath the filament can be sent on for further processing such as aging and/or stretching operations.

15 For example, referring to Fig. 2, after the filament 16 exiting the quench bath 17 is passed over idler rollers 19 and 20, it is thereafter wrapped around a first godet 21. A nip roll 22 is provided to prevent slippage which might otherwise result from the subsequent stretching operation. Filament 16 passing from godet 21 is stretched in order to effect its orientation and thereby increase its

5 tensile strength. Thus, in one type of stretching
operation, generally suitable for smaller sutures, e.g.,
sizes 4/0 to 8/0, filament 16 is drawn through heating unit
23, which can be an oven chamber or a hot liquid (such as
water and glycerol) trough, by means of second godet 24
which rotates at a higher speed than first godet 21, thereby
stretching the filament from three to nine times its
original length. Where heating unit 23 is an oven chamber,
its temperature is advantageously maintained at from about
10 40°C to about 140°C and preferably from about 50°C to about
120°C. In the case of larger sutures, e.g., sizes 2 to 3/0,
it is preferred that heating unit 23 be a hot liquid trough
or bath which is maintained at a temperature of from about
30°C to about 98°C and preferably from about 40°C to about
15 90°C.

After the above mentioned operation it is
preferred to pass the filament 16 through a second heating
unit 25, e.g., maintained at a temperature of from about
40°C to about 140°C and preferably from about 50°C to about
20 120°C, by means of a third godet 26 to heat-treat the
filament 16 prior to the equilibration and annealing
operations. This second heat treatment results in on-line
relaxation, or shrinkage, of the filament, e.g., for a
recovery of from about 85 to about 97 percent, and

preferably from about 90 to about 95 percent, of the stretched length of the filament. In order to accommodate this on-line shrinkage in the filament, the third godet is driven at a speed which is somewhat less than that of the second godet.

Following stretching and orientation (and, optionally, the aforescribed second heat treating step), filament 16 is taken up on a spool which is then set aside for a period of time sufficient to permit the filament to achieve a condition of equilibration. While the period of equilibration may vary depending on the particular copolymer composition employed and/or the conditions under which the copolymer is extruded, cooled and oriented, in most cases storage of the filament following its orientation for at about 2 hours, preferably at least about 24 hours and more preferably at least about 3 days. It is generally preferred that the spooled filament be stored at ambient temperature, e.g., 18°C-23°C., and a dew point below -12° C.

Thereafter, annealing may be accomplished by shrinkage of the suture, e.g., for a recovery of from about 75 to about 95 percent, and preferably from about 80 to about 90 percent, of its stretched length.

In carrying out the annealing operation, the desired length of equilibrated suture may be wound around a

creel and the creel placed in a heating cabinet circulated with nitrogen and maintained at the desired temperature, e.g., 70°C. After a suitable period of residency in the heating cabinet, e.g., about 20 minutes to 24 hours, the suture will have undergone shrinkage, e.g., to about 85% of the stretched length for sutures of sizes 2 to 3/0, to about 90% of the stretched length for sutures of sizes 4/0 and 5/0 and essentially no shrinkage in the case of sutures of sizes 6/0 to 8/0. The creel may be rotated within the heating cabinet in order to insure uniform heating of the filament or the cabinet may be of the circulating hot air type in which case uniform heating of the filament will be achieved without the need to rotate the creel. Thereafter, the creel with its annealed suture is removed from the heating cabinet and when returned to room temperature, the suture is removed from the creel, conveniently by cutting the wound filament at opposite ends of the creel.

The filament formed from the block copolymer described herein can be used as a monofilament or it can be combined with other filaments to form a suture. For example, the filament can be interwoven, knitted or braided with filaments of the same or different chemical composition to achieve optimum absorption characteristics. Spinning and braiding of fibers to form multifilament sutures can be

accomplished by any known technique such as those described in U.S. Patent Nos. 5,019,093 and 5,059,213.

The following examples will illustrate the features of this method.

5

EXAMPLE 1

Monofilaments of a block copolymer of polyglycolide (first block) and poly(trimethylene carbonate/dioxanone) (second block) are prepared as follows:

A mixture of 60% by weight polyglycolide pellets and 40% by weight of pellets of a random copolymer of 65 mole % trimethylene carbonate/35 mole % dioxanone is prepared. Pellets of the aforementioned polymers may be prepared by conventional polymerization techniques known in the art. For example, a method for making particles of bioabsorbable polymer is disclosed in U.S. Patent No. 5,342,557 to Kennedy. The pellet mixture is then loaded into the hopper of an extruder such as that described above, and processed under the following conditions to provide a size 3/0 monofilament suture.

25

		<u>Process Conditions</u>
5	Extruder screw, rpm	3.1
	Barrel temperature, °C, zone A	195
	Barrel temperature, °C, zone B	200
	Barrel temperature, °C, zone C	208
	Barrel temperature, psi	1400
	Barrel melt temperature, °C	210
	Pump size, cc per revolution	0.16
10	Pump rpm	12.6
	Pump temperature, °C	209
	Pump pressure, psi	1400
	Pump melt temperature, °C	202
	Block temperature, °C	209
15	Clamp temperature, °C	208
	Adapter temperature, °C	208
	Filter type	Stainless
	Filter screen, microns	20
	Spinneret orifice diameter, mm	1.25
20	Number of spinneret orifices	1
	Spinneret temperature, °C	208
	Spinneret pressure, psi	900
	Spinneret melt temperature, °C	208
	Output, lb/hr per orifice	0.5
	Air gap, cm	5.0

Quench bath temperature, °C	17
Driven roller, depth	20
Driven roller, rpm	3

5 The resulting filaments are quenched, dried and
stored on a spool.

EXAMPLE II

Monofilaments of a block copolymer of
polyglycolide (first block) and poly(glycolide-co-lactide)
are prepared as follows:

10 A mixture of 65% by weight polyglycolide pellets
and 32% by weight of a random copolymer of 50 mole %
glycolide/50 mole % lactide is prepared. Pellets of the
aforementioned polymers may be prepared by conventional
polymerization techniques known in the art. The pellet
15 mixture is loaded into the hopper of an extruder such as
that described hereinabove, and processed under the
following conditions.

		<u>Process Conditions</u>
	Extruder screw, rpm	3
	Barrel temperature, °C, zone A	225
	Barrel temperature, °C, zone B	226
5	Barrel temperature, °C, zone C	226
	Barrel pressure, psi	750
	Barrel melt temperature, °C	226
	Pump size, cc per revolution	0.16
	Pump rpm	37
10	Pump temperature, °C	225
	Pump pressure, psi	1000
	Pump melt temperature, °C	226
	Block temperature, °C	226
	Clamp temperature, °C	227
15	Adapter temperature, °C	225
	Filter type	Stainless
	Filter screen, microns	20
	Spinneret orifice diameter, mm	0.25
	Number of spinneret orifices	40
20	Spinneret temperature, °C	228
	Spinneret pressure, psi	1500
	Spinneret melt temperature, °C	226
	Output, lb/hr per orifice	1
	Quench temperature, °C	Air quench - ambient

The resulting filaments are quenched, dried and stored on a spool.

While the above description contains many specifics and examples, these specifics and examples should not be construed as limitations on the scope of the invention, but merely as exemplifications of preferred embodiments thereof. Those skilled in the art will envision many other possible variations that are within the scope and spirit of the invention as defined by the claims appended hereto.

CLAIMS:

1. A method for making a bioabsorbable block copolymer filament comprising:

a) providing a mixture of particles of a first bioabsorbable polymeric component and particles of a second bioabsorbable polymeric component;

b) extruding said mixture of particles at a temperature of from about 50°C to about 240°C for a period of time of from about 2 minutes to about 20 minutes to transesterify the first and second polymeric components to produce the bioabsorbable block copolymer filament.

2. The method of claim 1 wherein the first and second polymeric components are both homopolymers.

3. The method of claim 1 wherein at least one of the first and second polymeric components is a copolymer.

4. The method of claim 1 wherein the first and second polymeric components are polymers made from one or more monomers selected from the group consisting of glycolide, glycolic acid, lactide, lactic acid, caprolactone, dioxanone, polyalkylene oxide and trimethylene carbonate.

5. The method of claim 1 wherein the extruding step is conducted at a temperature in the range of about 180°C to about 220°C.

6. The method of claim 1 further including the step of quenching the block copolymer filament.

7. The method of claim 1 further including the step of stretching the filament.

8. The method of claim 7 wherein said stretching is performed while heating the filament to a temperature of from about 40°C to about 140°C.

9. The method of claim 7 further including the steps of relaxing the stretched filament.

10. The method of claim 9 wherein the relaxing is performed while heating the filament to a temperature of from about 40°C to about 140°C.

11. The method of claim 1 further including the step of annealing the filament.




Fig 1




FIG. 2

