




(86) Date de dépôt PCT/PCT Filing Date: 2001/03/14
(87) Date publication PCT/PCT Publication Date: 2001/11/08
(45) Date de délivrance/Issue Date: 2011/01/25
(85) Entrée phase nationale/National Entry: 2002/10/25
(86) N° demande PCT/PCT Application No.: US 2001/008132
(87) N° publication PCT/PCT Publication No.: 2001/084655
(30) Priorité/Priority: 2000/04/27 (US09/559,861)

(51) Cl.Int./Int.Cl. *C01B 25/455* (2006.01),
C01B 25/45 (2006.01), *H01M 10/0525* (2010.01),
H01M 4/136 (2010.01), *H01M 4/58* (2010.01),
H01M 10/0585 (2010.01)
(72) Inventeurs/Inventors:
BARKER, JEREMY, GB;
SAIDI, YAZID M., US;
SWOYER, JEFFREY L., US
(73) Propriétaire/Owner:
VALENCE TECHNOLOGY, INC., US
(74) Agent: MCFADDEN, FINCHAM

(54) Titre : MATERIAUX A BASE DE FLUOROPHOSPHATE DE LITHIUM ET MODE DE PREPARATION
CORRESPONDANT

(54) Title: LITHIUM METAL FLUOROPHOSPHATE MATERIALS AND PREPARATION THEREOF



(57) Abrégé/Abstract:

The invention provides new and novel lithium-metal-fluorophosphates which, upon electrochemical interaction, release lithium ions, and are capable of reversibly cycling lithium ions. The invention provides a rechargeable lithium battery which comprises an electrode formed from the novel lithium-metal-fluorophosphates. The lithium-metal-fluorophosphates comprise lithium and at least one other metal besides lithium.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
8 November 2001 (08.11.2001)

PCT

(10) International Publication Number
WO 01/84655 A1

(51) International Patent Classification⁷: H01M 4/58,
C01B 25/26

(21) International Application Number: PCT/US01/08132

(22) International Filing Date: 14 March 2001 (14.03.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
09/559,861 27 April 2000 (27.04.2000) US

(63) Related by continuation (CON) or continuation-in-part
(CIP) to earlier application:
US 09/559,861 (CON)
Filed on 27 April 2000 (27.04.2000)

(71) Applicant (for all designated States except US): VA-
LENCE TECHNOLOGY, INC. [US/US]; 301 Conestoga
Way, Henderson, NV 89015 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): BARKER, Jeremy
[GB/GB]; 5 Little Acreage, Oxford OX3 0PS (GB). SAIDI,
Yazid, M. [DZ/US]; 301 Conestoga Way, Henderson, NV
89015 (US). SWOYER, Jeffrey, L. [US/US]; 301 Con-
estoga Way, Henderson, NV 89015 (US).


(74) Agents: DESCHERE, Linda, M. et al.; Harness, Dickey
& Pierce, P.L.C., 5445 Corporate Drive, Suite 400, Troy,
MI 48098 (US).

(81) Designated States (national): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM,
HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK,
LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX,
MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL,
TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,

[Continued on next page]

(54) Title: LITHIUM METAL FLUOROPHOSPHATE MATERIALS AND PREPARATION THEREOF



(57) Abstract: The invention provides new and novel lithium-metal-fluorophosphates which, upon electrochemical interaction, release lithium ions, and are capable of reversibly cycling lithium ions. The invention provides a rechargeable lithium battery which comprises an electrode formed from the novel lithium-metal-fluorophosphates. The lithium-metal-fluorophosphates comprise lithium and at least one other metal besides lithium.

WO 01/84655 A1

WO 01/84655 A1



IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

Published:

- *with international search report*
- *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments*

**LITHIUM METAL FLUOROPHOSPHATE
MATERIALS AND PREPARATION THEREOF**

Field of the Invention

5 This invention relates to improved materials
usable as electrode active materials, and electrodes
formed from it for electrochemical cells in batteries.

Background of the Invention

10 Lithium batteries are prepared from one or more
lithium electrochemical cells containing
electrochemically active (electroactive) materials. Such
cells typically include an anode (negative electrode), a
cathode (positive electrode), and an electrolyte
interposed between spaced apart positive and negative
15 electrodes. Batteries with anodes of metallic lithium
and containing metal chalcogenide cathode active material
are known. The electrolyte typically comprises a salt of
lithium dissolved in one or more solvents, typically
nonaqueous (aprotic) organic solvents. Other
20 electrolytes are solid electrolytes typically called
polymeric matrixes that contain an ionic conductive
medium, typically a metallic powder or salt, in
combination with a polymer that itself may be ionically
conductive which is electrically insulating. By
25 convention, during discharge of the cell, the negative
electrode of the cell is defined as the anode. Cells
having a metallic lithium anode and metal chalcogenide
cathode are charged in an initial condition. During
discharge, lithium ions from the metallic anode pass

through the liquid electrolyte to the electrochemically active (electroactive) material of the cathode whereupon they release electrical energy to an external circuit.

It has recently been suggested to replace the lithium metal anode with an insertion anode, such as a lithium metal chalcogenide or lithium metal oxide. Carbon anodes, such as coke and graphite, are also insertion materials. Such negative electrodes are used with lithium- containing insertion cathodes, in order to form an electroactive couple in a cell. Such cells, in an initial condition, are not charged. In order to be used to deliver electrochemical energy, such cells must be charged in order to transfer lithium to the anode from the lithium- containing cathode. During discharge the lithium is transferred from the anode back to the cathode. During a subsequent recharge, the lithium is transferred back to the anode where it reinserts. Upon subsequent charge and discharge, the lithium ions (Li^+) are transported between the electrodes. Such rechargeable batteries, having no free metallic species are called rechargeable ion batteries or rocking chair batteries. See U.S. Patent Nos. 5,418,090; 4,464,447; 4,194,062; and 5,130,211.

Preferred positive electrode active materials include LiCoO_2 , LiMn_2O_4 , and LiNiO_2 . The cobalt compounds are relatively expensive and the nickel compounds are difficult to synthesize. A relatively economical positive electrode is LiMn_2O_4 , for which methods of synthesis are known. The lithium cobalt oxide (LiCoO_2), the lithium manganese oxide (LiMn_2O_4), and the lithium nickel oxide (LiNiO_2) all have a common disadvantage in that the charge capacity of a cell comprising such

cathodes suffers a significant loss in capacity. That is, the initial capacity available (amp hours/gram) from LiMn_2O_4 , LiNiO_2 , and LiCoO_2 is less than the theoretical capacity because significantly less than 1 atomic unit of lithium engages in the electrochemical reaction. Such an initial capacity value is significantly diminished during the first cycle operation and such capacity further diminishes on every successive cycle of operation. For LiNiO_2 and LiCoO_2 only about 0.5 atomic units of lithium is reversibly cycled during cell operation. Many attempts have been made to reduce capacity fading, for example, as described in U.S. Patent No. 4,828,834 by Nagaura et al. However, the presently known and commonly used, alkali transition metal oxide compounds suffer from relatively low capacity. Therefore, there remains the difficulty of obtaining a lithium-containing electrode material having acceptable capacity without disadvantage of significant capacity loss when used in a cell.

Summary of the Invention

The invention provides novel lithium-metal-fluorophosphate materials which, upon electrochemical interaction, release lithium ions, and are capable of reversibly cycling lithium ions. The invention provides a rechargeable lithium battery which comprises an electrode formed from the novel lithium-metal-fluorophosphates. Methods for making the novel lithium-metal-fluorophosphates and methods for using such lithium-metal-fluorophosphates in electrochemical cells are also provided. Accordingly, the invention provides a rechargeable lithium battery which comprises an electrolyte; a first electrode having a compatible active material; and a second electrode comprising the novel lithium-metal-fluorophosphate materials. The novel materials, preferably used as a positive electrode active material, reversibly cycle lithium ions with the compatible negative electrode active material. Desirably, the lithium-metal-fluorophosphate is represented by the nominal general formula $\text{LiM}_{1-y}\text{MI}_y\text{PO}_4\text{F}$ where $0 \leq y \leq 1$. Such compounds include LiMPO_4F for $y = 0$. Such compounds are also represented by $\text{Li}_{1-x}\text{MPO}_4\text{F}$ and $\text{Li}_{1-x}\text{M}_{1-y}\text{MI}_y\text{PO}_4\text{F}$, where in an initial condition, "x" is essentially zero; and during cycling a quantity of "x" lithium is released where $0 \leq x \leq 1$. Correspondingly, M has more than one oxidation state in the lithium-metal-fluorophosphate compound, and more than one oxidation state above the ground state M^0 . The term oxidation state and valence state are used in the art interchangeably. Also, MI may have more than one oxidation state, and more than one oxidation state above the ground state MI^0 .

Desirably, M is selected from V (vanadium), Cr (chromium), Fe (iron), Ti (titanium), Mn (manganese), Co (cobalt), Ni (nickel), Nb (niobium), Mo (molybdenum), Ru (ruthenium), Rh (rhodium) and mixtures thereof.

5 Preferably, M is selected from the group V, Cr, Fe, Ti, Mn, Co, and Ni. As can be seen, M is preferably selected from the first row of transition metals, and M preferably initially has a +3 oxidation state. In another preferred aspect, M is a metal having a +3 oxidation state and
10 having more than one oxidation state, and is oxidizable from its oxidation state in lithium-metal-fluorophosphate compound. In another aspect, MI is a metal having a +3 oxidation state, and desirably MI is an element selected from the group V, Cr, Fe, Ti, Mn, Co, Ni, Nb, Mo, Ru, Rh,
15 B (boron) and Al (aluminum).

In a preferred aspect, the product $\text{LiM}_{1-y}\text{MI}_y\text{PO}_4\text{F}$ is a triclinic structure. In another aspect, the "nominal general formula" refers to the fact that the relative proportions of the atomic species may vary
20 slightly on the order of up to 5 percent, or more typically, 1 percent to 3 percent. In another aspect the term "general" refers to the family of compounds with M, MI, and y representing variations therein. The expressions y and 1-y signify that the relative amount of
25 M and MI may vary and that $0 \leq y \leq 1$. In addition, M may be a mixture of metals meeting the earlier stated criteria for M. In addition, MI may be a mixture of elements meeting the earlier stated criteria for MI.

The active material of the counter electrode is
30 any material compatible with the lithium-metal-fluorophosphate of the invention. Where the lithium-metal-fluorophosphate is used as a positive electrode

active material, metallic lithium may be used as the negative electrode active material where lithium is removed and added to the metallic negative electrode during use of the cell. The negative electrode is desirably a nonmetallic insertion compound. Desirably, the negative electrode comprises an active material from the group consisting of metal oxide, particularly transition metal oxide, metal chalcogenide, carbon, graphite, and mixtures thereof. It is preferred that the anode active material comprises a carbonaceous material such as graphite. The lithium-metal-fluorophosphate of the invention may also be used as a negative electrode material.

The starting (precursor) materials include a lithium containing compound, and a metal phosphate compound. Preferably, the lithium containing compound is in particle form, and an example is lithium salt. A particular example of a lithium salt is lithium fluoride (LiF). Preferably, the metal phosphate compound is in particle form, and examples include metal phosphate salt, such as FePO_4 and CrPO_4 . The lithium compound and the metal phosphate compound are mixed in a proportion which provides the stated general formula.

In one aspect, the starting materials are intimately mixed and then reacted together where the reaction is initiated by heat. The mixed powders are pressed into a pellet. The pellet is then heated to an elevated temperature. This reaction can be run under an air atmosphere, or can be run under a non-oxidizing atmosphere. The precursors are commercially available, and include, for example, a lithium fluoride salt, and metal phosphate, such as CrPO_4 , FePO_4 , or MnPO_4 .

In another aspect, the metal phosphate salt used as a precursor for the lithium metal phosphate reaction can be formed either by a carbothermal reaction, or by a hydrogen reduction reaction. Preferably, the phosphate-containing anion compound is in particle form, and examples include metal phosphate salt, diammonium hydrogen phosphate (DAHP), and ammonium dihydrogen phosphate (ADHP). The metal compound for making the precursor are typically metal oxides. In the carbo-thermal reaction, the starting materials are mixed together with carbon, which is included in an amount sufficient to reduce the metal oxide to metal phosphate. The starting materials for the formation of the metal phosphates are generally crystals, granules, and powders and are generally referred to as being in particle form. Although many types of phosphate salts are known, it is preferred to use diammonium hydrogen phosphate (DAHP), or ammonium dihydrogen phosphate (ADHP). Both DAHP and ADHP meet the preferred criteria that the starting materials decompose to liberate the phosphate anion which may then react with the metal oxide compound. Exemplary metal compounds are Fe_2O_3 , Fe_3O_4 , V_2O_5 , VO_2 , MnO_2 , Mn_2O_3 , TiO_2 , Ti_2O_3 , Cr_2O_3 , CoO , $\text{Ni}_3(\text{PO}_4)_2$, Nb_2O_5 , Mo_2O_3 , V_2O_3 , FeO , Co_3O_4 , CrO_3 , Nb_2O_3 , MoO_3 . The starting materials are available from a number of sources. For example, the metal oxides, such as vanadium pentoxide or iron oxide, are available from suppliers including Kerr McGee, Johnson Matthey, or Alpha Products of Davers, Massachusetts.

Objects, features, and advantages of the invention include an electrochemical cell or battery based on lithium-metal-fluorophosphates. Another object is to provide a cathode active material which combines the advantages of good discharge capacity and capacity

retention. It is also an object of the present invention to provide positive electrodes which can be manufactured economically. Another object is to provide a cathode active material which can be rapidly and cheaply produced and lends itself to commercial scale production for preparation of large quantities.

These and other objects, features, and advantages will become apparent from the following description of the preferred embodiments, claims, and accompanying drawings.

Brief Description of the Drawings

Figure 1 shows the results of an x-ray diffraction analysis, of LiVPO_4F prepared as above, using $\text{CuK}\alpha$ radiation, $\lambda = 1.5404 \text{ \AA}$. Bars refer to simulated pattern from refined cell parameters SG = P-1 (triclinic) (1). The values are $a = 5.1738 \text{ \AA}$ (0.002), $b = 5.3096 \text{ \AA}$ (0.002), $c = 7.2503 \text{ \AA}$ (0.001); the angle $\alpha = 72.4794$ (0.06), $\beta = 107.7677$ (0.04), $\gamma = 81.3757$ (0.04), cell volume = $174.35 \text{ \AA}^3$. The crystal system is triclinic.

Figure 2 is a voltage/capacity plot of LiVPO_4F containing cathode cycled with a lithium metal anode in a range of 3.0 to 4.4 volts. The cathode contained 29.4 mg of LiVPO_4F active material prepared by the method described above.

Figure 3 displays the differential capacity during cell charge and discharge vs. cell voltage for the electrochemical cell containing LiVPO_4F .

Figure 4 shows the results of an x-ray diffraction analysis, of LiFePO_4F prepared as above, using $\text{CuK}\alpha$ radiation, $\lambda = 1.5404 \text{ \AA}$. Bars refer to simulated pattern from refined cell parameters SG = P-1 (triclinic). The values are $a = 5.1528 \text{ \AA}$ (0.002), $b = 5.3031 \text{ \AA}$ (0.002), $c = 7.4966 \text{ \AA}$ (0.003); the angle $\alpha = 67.001^\circ$ (0.02), $\beta = 67.164^\circ$ (0.03), $\gamma = 81.512^\circ$ (0.02), cell volume = $173.79 \text{ \AA}^3$. The crystal system is triclinic.

Figure 5 shows the results of an x-ray diffraction analysis, of LiTiPO_4F prepared as above,

10

using CuK α radiation, $\lambda = 1.5404 \text{ \AA}$. The x-ray diffraction pattern was triclinic.

Figure 6 shows the results of an x-ray diffraction analysis, of LiCrPO₄F prepared as above, using CuK α radiation, $\lambda = 1.5404 \text{ \AA}$. Bars refer to simulated pattern from refined cell parameters SG = P-1 (triclinic). The values are $a = 4.996 \text{ \AA}$ (0.002), $b = 5.307 \text{ \AA}$ (0.002), $c = 6.923 \text{ \AA}$ (0.004); the angle $\alpha = 71.600^\circ$ (0.06), $\beta = 100.71^\circ$ (0.04), $\gamma = 78.546^\circ$ (0.05), cell volume = $164.54 \text{ \AA}^3$. The crystal system is triclinic.

Figure 7 is a diagrammatic representation of a typical laminated lithium-ion battery cell structure.

Figure 8 is a diagrammatic representation of a typical multi-cell battery cell structure.

Detailed Description of the Preferred Embodiments

The present invention provides lithium-metal-fluorophosphates, which are usable as electrode active materials, for lithium (Li^+) ion removal and insertion.

5 Upon extraction of the lithium ions from the lithium-metal-fluorophosphates, significant capacity is achieved. In one aspect of the invention, electrochemical energy is provided when combined with a suitable counter electrode by extraction of a quantity x of lithium from lithium-

10 metal-fluorophosphates $\text{Li}_{1-x}\text{M}_{1-y}\text{MI}_y\text{PO}_4\text{F}$. When a quantity of lithium is removed per formula unit of the lithium-metal-fluorophosphate, metal M is oxidized. Accordingly, during cycling, charge and discharge, the value of x varies as x greater than or equal to 0 and less than or

15 equal to 1.

In another aspect, the invention provides a lithium ion battery which comprises an electrolyte; a negative electrode having an insertion active material; and a positive electrode comprising a lithium-metal-

20 fluorophosphate active material characterized by an ability to release lithium ions for insertion into the negative electrode active material. The lithium-metal-fluorophosphate is desirably represented by the aforesaid nominal general formula $\text{LiM}_{1-y}\text{MI}_y\text{PO}_4\text{F}$. Desirably, the

25 metal M is selected from the group: Ti, V, Cr, Mn, Fe, Co, Ni, Nb, Mo, and mixtures thereof. Preferably the metal M is selected from the group: Ti, V, Cr, Mn, Fe, Co, Ni, and mixtures thereof. Although the metals M and MI may be the same, it is preferred that M and MI be

30 different, and desirably MI is an element selected from the group: Ti, V, Cr, Mn, Fe, Co, Ni, Nb, Mo, Al, B, and mixtures thereof.

The present invention provides a new material, a lithium metal fluorophosphate, and demonstrates that with this new material significant capacity as a cathode active material is utilizable and maintained.

5 A preferred approach for making the $\text{LiM}_{1-y}\text{MI}_y\text{PO}_4\text{F}$ is a two staged approach (Example I). The first stage (Reaction 1a) involves the creation of the metal phosphate precursor, followed by the second stage (Reaction 1b) of reacting the metal phosphate with the
10 commercially available lithium fluoride to produce the lithium metal fluorophosphate. The basic procedure is described with reference to exemplary starting materials, but is not limited thereby. In the first stage, the basic process comprises reacting a metal compound, for
15 example vanadium pentoxide or ferric oxide, with a phosphoric acid derivative, preferably a phosphoric acid ammonium salt, such as ammonium dihydrogen phosphate (ADHP) or diammonium hydrogen phosphate (DAHP). The powders were intimately mixed and dry ground for about 30
20 minutes to form a homogeneous mixture of the starting materials. Then the mixed powders were pressed into pellets. The reaction was conducted by heating the pellets in an oven at a preferred heating rate to an elevated temperature, and held at such elevated
25 temperature for several hours. A preferred ramp rate of $2^\circ\text{C}/\text{minute}$ was used to heat to a preferred temperature of 300°C . The reaction was carried out under a reducing atmosphere of hydrogen gas. The flow rate will depend on the size of the oven and the quantity needed to maintain
30 the atmosphere. The pellets were allowed to cool to ambient temperature, then re-ground and repressed into pellets. The reaction was continued by reheating the pellets in an oven at a preferred heating rate to a

second elevated temperature, and held at such elevated temperature for several hours to complete the reaction. A preferred ramp rate of 2°C/minute was used to heat to a preferred second elevated temperature is 850°C. The
5 reaction was carried out under a reducing atmosphere of hydrogen gas. The pellets were then allowed to cool to ambient temperature. A preferred rate of cooling was about 2°C/minute.

A preferred approach for the second stage
10 (Reaction 1b) for making the $\text{LiM}_{1-y}\text{MI}_y\text{PO}_4\text{F}$ is to start with the commercially available precursor, lithium fluoride LiF and mix with the metal phosphate MPO_4 . The precursors were intimately mixed and dry ground for about 30 minutes. The mixture was then pressed into pellets.
15 Reaction was conducted by heating in an oven at a preferred ramped heating rate to an elevated temperature, and held at such elevated temperature for fifteen minutes to complete formation of the reaction product. A preferred ramp rate of 2°C/minute was used to heat to a
20 preferred temperature of 700°C. The entire reaction was conducted under a normal air atmosphere. A covered nickel crucible to limit oxygen availability was used. In an alternative, a covered ceramic crucible can be used. The pellet was removed from the oven and allowed
25 to cool to room temperature. Preferred cooling rates are from about 2°C/minute to about 60°C/minute, with a more preferred rate of about 50°C/minute.

In another variation, the precursor metal phosphate was created prior to the creation of the
30 lithium-metal-fluorophosphate using the carbo-thermal method in a two staged approach (Example II). The first stage (Reaction 2a) involves the creation of the metal

phosphate precursor, followed by the second stage of reacting the metal phosphate with the commercially available lithium fluoride to produce the lithium metal fluorophosphate. The basic procedure is described with reference to exemplary starting materials, but is not limited thereby. In the first stage, the basic process comprises reacting a metal compound, for example vanadium pentoxide or ferric oxide, with a phosphoric acid derivative, preferably a phosphoric acid ammonium salt, such as ammonium dihydrogen phosphate (ADHP) or diammonium hydrogen phosphate (DAHP). The powders were intimately mixed and dry ground for about 30 minutes to form a homogeneous mixture of the starting materials. Then the mixed powders were pressed into pellets. The reaction was conducted by heating the pellets in an oven at a preferred heating rate to an elevated temperature, and held at such elevated temperature for several hours. A preferred ramp rate of 2°C/minute was used to heat to a preferred temperature of 300°C.

The reaction was carried out under a non-oxidizing atmosphere of argon gas. The flow rate will depend on the size of the oven and the quantity needed to maintain the atmosphere.

The pellets were allowed to cool to ambient temperature, then re-ground and repressed into pellets. The reaction was continued by reheating the pellets in an oven at a preferred heating rate to a second elevated temperature, and held at such elevated temperature for several hours to complete the reaction. A preferred ramp rate of 2°C/minute was used to heat to a preferred second elevated temperature was 850°C. The reaction was carried out under a non-oxidizing atmosphere of argon gas. After

15

heating for a preferred time of 8 hours, the pellets were allowed to cool to ambient temperature at a preferred rate of 2°C/minute.

A preferred approach for the second stage (Example II, Reaction 2b) for making the $\text{LiM}_{1-y}\text{MI}_y\text{PO}_4\text{F}$ is to start with the commercially available precursor, lithium fluoride LiF and mix with the metal phosphate MPO_4 . The precursors were intimately mixed and dry ground for 30 minutes. The mixture was then pressed into pellets. Reaction was conducted by heating in an oven at a preferred ramped heating rate to an elevated temperature, and held at such elevated temperature for fifteen minutes to complete formation of the reaction product. A preferred ramp rate of 2°C/minute was used to heat to a preferred temperature of 700°C. The entire reaction was conducted under an air atmosphere, but a covered crucible was used to limit oxygen availability. The pellet was removed from the oven and allowed to cool to room temperature.

In a variation of the second stage, lithium carbonate and ammonium fluoride were used in place of lithium fluoride (Example IV). The precursors were intimately mixed and dry ground for about 30 minutes. The mixture is then pressed into pellets. Reaction was conducted by heating in an oven at a preferred ramped heating rate (of 2°C/minute) to an elevated temperature, and held at such elevated temperature for about 15 minutes to complete formation of the reaction product. A preferred elevated temperature was 700°C. The reaction was conducted under an air atmosphere in a covered crucible to limit oxygen availability. The pellet was

removed from the oven and allowed to cool to room temperature. Refer to Reaction 4 herein.

A process for making lithium mixed-metal fluorophosphate, such as lithium aluminum vanadium fluorophosphate, the precursors aluminum phosphate and vanadium phosphate were made separately, then mixed with lithium fluoride (Example III, Reaction 3b). The vanadium phosphate was made as described in reaction 1(a) or reaction 2(a). The basic procedure for making aluminum phosphate is described with reference to exemplary starting materials, but is not limited thereby (Example III, Reaction 3a). The aluminum phosphate was made by intimately mixing aluminum hydroxide and ammonium dihydrogen phosphate powders, and dry grounding them for about 30 minutes. The mixed powders were then pressed into pellets. The reaction was conducted by heating the pellets in an oven at a preferred heating rate to an elevated temperature, and held at that elevated temperature for several hours. The reaction was carried out under an air atmosphere. The pellets were allowed to cool to ambient temperature, and then ground into powder. Exemplary and preferred ramp rates, elevated reaction temperatures and reaction times are described herein. In one aspect, a ramp rate of 2°C/minute was used to heat to an elevated temperature of about 950°C and allowed to dwell for 8 hours. The precursor was then allowed to cool to room temperature. Refer to Reaction 3(a) herein.

A preferred approach for making the lithium aluminum transition metal fluorophosphate was to use the aluminum phosphate and the transition metal phosphate generated above, and mix them with lithium fluoride (Reaction 3b). The powders were intimately mixed and dry

ground for about 30 minutes. The mixture was then pressed into pellets. Reaction was conducted by heating in an oven at a preferred ramped heating rate to an elevated temperature, and held at such elevated temperature for about fifteen minutes to complete the formation of the reaction product. The entire reaction was completed under a normal air atmosphere. The pellet was removed from the oven and allowed to cool to room temperature. Exemplary and preferred reaction conditions are described herein. In one aspect, a ramp rate of 2°C/minute was used to heat to an elevated temperature of 700°C and was allowed to dwell for 15 minutes. Refer to Reaction 3(b) herein. Recent research has indicated that doping of materials with non-transition metals or other elements, such as boron, tends to increase the operating voltage. Substitution of non-transition elements such as aluminum for transition metals tends to stabilize the structure of cathode active materials. This aids the stability and cyclability of the materials.

The general aspects of the above synthesis route are applicable to a variety of starting materials. The metal compounds are reduced in the presence of a reducing agent, such as hydrogen or carbon. The same considerations apply to other metal and phosphate containing starting materials. The thermodynamic considerations such as ease of reduction, of the selected starting materials, the reaction kinetics, and the melting point of the salts will cause adjustment in the general procedure, such as the amount of reducing agent, the temperature of the reaction, and the dwell time.

Referring back to the discussion of the reactions for generating the precursor metal-phosphates,

Reactions 1(a) and 2(a), the reaction is initially conducted at a relatively low temperature from 200°C to 500°C, preferably around 300°C, cooled to ambient temperature, then conducted at a relatively high temperature from 700°C to a temperature below the melting point of the metal phosphate, preferably around 850°C. The melting point of the metal phosphates is believed to be in the range of 950°C to 1050°C. It is preferred to heat the starting materials at a ramp rate of a fraction of a degree to 10°C per minute and preferably about 2°C per minute. After reaction, the products are cooled to ambient temperature with a cooling rate similar to the ramp rate, and preferably around 2°C/minute.

Referring back to the discussion of the lithium fluoride and metal phosphate reaction (Reactions 1b, 2b, 3b, and 4), the temperature should be run at 400°C or greater but below the melting point of the metal phosphate, and preferably at about 700°C. It is preferred to heat the precursors at a ramp rate of a fraction of a degree to 10°C per minute and preferably about 2°C per minute. Once the desired temperature is attained, the reactions are held at the reaction temperature from 10 minutes to several hours, and preferably around 15 minutes. The time being dependent on the reaction temperature chosen. The heating may be conducted under an air atmosphere, or if desired may be conducted under a non-oxidizing or inert atmosphere. After reaction, the products are cooled from the elevated temperature to ambient (room) temperature (i.e. 10°C to 40°C). Desirably, the cooling occurs at a rate of about 50°C/minute. Such cooling has been found to be adequate to achieve the desired structure of the final product. It is also possible to quench the products at a cooling

rate on the order of about 100°C/minute. In some instances, such rapid cooling may be preferred.

As an alternative to the two stage process for producing the lithium metal fluorophosphate, a single stage process is used (Example V, Reaction 5). A mixture was made of a metal compound, for example vanadium pentoxide, ammonium dihydrogen phosphate, lithium fluoride and carbon. The mixture was dry ground for about 30 minutes to intimately mix the powders. The powders were pressed into pellets. The reaction was conducted by heating the pellets in an oven at a preferred rate to a first elevated temperature for several hours. A preferred temperature is 300°C. The reaction was carried out under a non-oxidizing atmosphere. The flow rate will depend on the size of the oven and the quantity needed to maintain the temperature. The pellets were allowed to cool, then re-ground and repressed into pellets. The reaction was continued by reheating the pellets in an oven at a preferred heating rate to a second elevated temperature, and held at such elevated temperature for several hours to complete the reaction. A preferred second elevated temperature is 850°C. The reaction was carried out under a non-oxidizing atmosphere. In one aspect, a ramp rate of 2°C/minute was used to heat to an elevated temperature of about 300°C and allowed to dwell for 3 hours. The precursor material was allowed to cool to room temperature, and subsequently heated to 850°C along with a dwell time of 8 hours. Refer to Reaction 5 herein.

Figures 1 through **6** which will be described more particularly below show the characterization data and capacity in actual use for the cathode materials

(positive electrodes) of the invention. Some tests were conducted in a cell comprising a lithium metal counter electrode (negative electrode). All of the cells had an EC/DMC (2:1) 1 molar LiPF_6 electrolyte.

5 Typical cell configurations will now be described with reference to **Figures 7 and 8**; and such battery or cell utilizes the novel active material of the invention. Note that the preferred cell arrangement described here is illustrative and the invention is not
10 limited thereby. Experiments are often performed, based on full and half cell arrangements, as per the following description. For test purposes, test cells are often fabricated using lithium metal electrodes. When forming cells for use as batteries, it is preferred to use an
15 insertion positive electrode as per the invention and a graphitic carbon negative electrode.

A typical laminated battery cell structure 10 is depicted in **Figure 7**. It comprises a negative electrode side 12, a positive electrode side 14, and an
20 electrolyte/separator 16 there between. Negative electrode side 12 includes current collector 18, and positive electrode side 14 includes current collector 22. A copper collector foil 18, preferably in the form of an open mesh grid, upon which is laid a negative electrode
25 membrane 20 comprising an insertion material such as carbon or graphite or low-voltage lithium insertion compound, dispersed in a polymeric binder matrix. An electrolyte/separator film 16 membrane is preferably a plasticized copolymer. This electrolyte/separator
30 preferably comprises a polymeric separator and a suitable electrolyte for ion transport. The electrolyte/separator is positioned upon the electrode element and is covered

with a positive electrode membrane 24 comprising a composition of a finely divided lithium insertion compound in a polymeric binder matrix. An aluminum collector foil or grid 22 completes the assembly.

5 Protective bagging material 40 covers the cell and prevents infiltration of air and moisture.

In another embodiment, a multi-cell battery configuration as per **Figure 8** is prepared with copper current collector 51, negative electrode 53,
10 electrolyte/separator 55, positive electrode 57, and aluminum current collector 59. Tabs 52 and 58 of the current collector elements form respective terminals for the battery structure. As used herein, the terms "cell" and "battery" refer to an individual cell comprising
15 anode/electrolyte/cathode and also refer to a multi-cell arrangement in a stack.

The relative weight proportions of the components of the positive electrode are generally: 50-90% by weight active material; 5-30% carbon black as the
20 electric conductive diluent; and 3-20% binder chosen to hold all particulate materials in contact with one another without degrading ionic conductivity. Stated ranges are not critical, and the amount of active material in an electrode may range from 25-95 weight
25 percent. The negative electrode comprises about 50-95% by weight of a preferred graphite, with the balance constituted by the binder. A typical electrolyte separator film comprises approximately two parts polymer for every one part of a preferred fumed silica. The
30 conductive solvent comprises any number of suitable solvents and salts. Desirable solvents and salts are described in U.S. Patent Nos. 5,643,695 and 5,418,091.

One example is a mixture of EC:DMC:LiPF₆ in a weight ratio of about 60:30:10.

Solvents are selected to be used individually or in mixtures, and include dimethyl carbonate (DMC),
5 diethylcarbonate (DEC), dipropylcarbonate (DPC), ethylmethylcarbonate (EMC), ethylene carbonate (EC), propylene carbonate (PC), butylene carbonate, lactones, esters, glymes, sulfoxides, sulfolanes, etc. The preferred solvents are EC/DMC, EC/DEC, EC/DPC and EC/EMC.
10 The salt content ranges from 5% to 65% by weight, preferably from 8% to 35% by weight.

Those skilled in the art will understand that any number of methods are used to form films from the casting solution using conventional meter bar or doctor
15 blade apparatus. It is usually sufficient to air-dry the films at moderate temperature to yield self-supporting films of copolymer composition. Lamination of assembled cell structures is accomplished by conventional means by pressing between metal plates at a temperature of about
20 120-160°C. Subsequent to lamination, the battery cell material may be stored either with the retained plasticizer or as a dry sheet after extraction of the plasticizer with a selective low-boiling point solvent. The plasticizer extraction solvent is not critical, and
25 methanol or ether are often used.

Separator membrane element 16 is generally polymeric and prepared from a composition comprising a copolymer. A preferred composition is the 75 to 92% vinylidene fluoride with 8 to 25% hexafluoropropylene
30 copolymer (available commercially from Atochem North America as KynarTM FLEX) and an organic solvent

plasticizer. Such a copolymer composition is also preferred for the preparation of the electrode membrane elements, since subsequent laminate interface compatibility is ensured. The plasticizing solvent may
5 be one of the various organic compounds commonly used as solvents for electrolyte salts, e.g., propylene carbonate or ethylene carbonate, as well as mixtures of these compounds. Higher-boiling plasticizer compounds such as dibutyl phthalate, dimethyl phthalate, diethyl phthalate,
10 and tris butoxyethyl phosphate are particularly suitable. Inorganic filler adjuncts, such as fumed alumina or silanized fumed silica, may be used to enhance the physical strength and melt viscosity of a separator membrane and, in some compositions, to increase the
15 subsequent level of electrolyte solution absorption.

In the construction of a lithium-ion battery, a current collector layer of aluminum foil or grid is overlaid with a positive electrode film, or membrane, separately prepared as a coated layer of a dispersion of
20 insertion electrode composition. This is typically an insertion compound such as LiMn_2O_4 (LMO), LiCoO_2 , or LiNiO_2 , powder in a copolymer matrix solution, which is dried to form the positive electrode. An electrolyte/separator membrane is formed as a dried
25 coating of a composition comprising a solution containing VdF:HFP copolymer and a plasticizer solvent is then overlaid on the positive electrode film. A negative electrode membrane formed as a dried coating of a powdered carbon or other negative electrode material
30 dispersion in a VdF:HFP copolymer matrix solution is similarly overlaid on the separator membrane layer. A copper current collector foil or grid is laid upon the negative electrode layer to complete the cell assembly.

Therefore, the VdF:HFP copolymer composition is used as a binder in all of the major cell components, positive electrode film, negative electrode film, and electrolyte/separator membrane. The assembled components are then heated under pressure to achieve heat-fusion bonding between the plasticized copolymer matrix electrode and electrolyte components, and to the collector grids, to thereby form an effective laminate of cell elements. This produces an essentially unitary and flexible battery cell structure.

Examples of forming cells containing metallic lithium anode, insertion electrodes, solid electrolytes and liquid electrolytes can be found in U.S. Patent Nos. 4,668,595; 4,830,939; 4,935,317; 4,990,413; 4,792,504; 5,037,712; 5,262,253, 5,300,373; 5,435,054; 5,463,179; 5,399,447; 5,482,795 and 5,411,820. Note that the older generation of cells contained organic polymeric and inorganic electrolyte matrix materials, with the polymeric being most preferred. The polyethylene oxide of 5,411,820 is an example. More modern examples are the VdF:HFP polymeric matrix. Examples of casting, lamination and formation of cells using VdF:HFP are as described in U.S. Patent Nos. 5,418,091; 5,460,904, 5,456,000; and 5,540,741; assigned to Bell Communications Research.

As described earlier, the electrochemical cell operated as per the invention, may be prepared in a variety of ways. In one embodiment, the negative electrode may be metallic lithium. In more desirable embodiments, the negative electrode is an insertion


25

active material, such as, metal oxides and graphite. When a metal oxide active material is used, the components of the electrode are the metal oxide, electrically conductive carbon, and binder, in proportions similar to that described above for the positive electrode. In a preferred embodiment, the negative electrode active material is graphite particles. For test purposes, test cells are often fabricated using lithium metal electrodes. When forming cells for use as batteries, it is preferred to use an insertion metal oxide positive electrode and a graphitic carbon negative electrode. Various methods for fabricating electrochemical cells and batteries and for forming electrode components are described herein. The invention is not, however, limited by any particular fabrication method.

Formation of Active Materials

Example I

Reaction 1(a) - Using hydrogen to form precursors



(a) Pre-mix reactants in following proportions using ball mill. Thus,

$$0.5 \text{ mol V}_2\text{O}_5 = 90.94 \text{ g}$$

$$1.0 \text{ mol NH}_4\text{H}_2\text{PO}_4 = 115.03 \text{ g}$$

(b) Pelletize the power mixture.

(c) Heat to 300°C at a rate of 2°C/minute in a flowing H₂ atmosphere. Dwell for 8 hours at 300°C.

26

- (d) Cool at 2°C/minute to room temperature.
- (e) Powderize and re-pelletize.
- (f) Heat to 850°C in a flowing H₂ atmosphere at a rate of 2°C/minute. Dwell for 8 hours at 850°C.
- (g) Cool at 2°C/minute to room temperature.


Reaction 1(b) - formation of lithium vanadium fluorophosphate



- (a) Pre-mix reactants in equi-molar portions using a ball mill. Thus,
- | | | |
|------------------------|---|----------|
| 1 mol LiF | = | 25.94 g |
| 1 mol VPO ₄ | = | 145.91 g |
- (b) Pelletize powder mixture.
- (c) Heat to 700°C at a rate of 2°C/minute in an air atmosphere in a covered nickel crucible. Dwell for 15 minutes at 700°C.
- (d) Cool to room temperature at about 50°C/minute.
- (e) Powderize pellet.

20 Example II

Reaction 2(a) - Using a carbothermal method to form precursors.



- (a) Pre-mix reactants in the following proportions using ball mill. Thus,
- | | | |
|--|---|----------|
| 0.5 mol V ₂ O ₅ | = | 90.94 g |
| 1.0 mol NH ₄ H ₂ PO ₄ | = | 115.03 g |

27

1.0 mol carbon = 12.0 g

(Use 10% excess carbon → 13.2 g)

- (b) Pelletize powder mixture
- (c) Heat pellet to 300°C at a rate of 2°C/minute in an inert atmosphere (e.g., argon). Dwell for 3 hours at 300°C.
- (d) Cool to room temperature at 2°C/minute.
- (e) Powderize and re-pelletize.
- (f) Heat pellet to 850°C at a rate of 2°C/minute in an inert atmosphere (e.g. argon). Dwell for 8 hours at 850°C under an argon atmosphere.
- (g) Cool to room temperature at 2°C/minute.
- (h) Powderize pellet.

Reaction 2(b) - formation of lithium vanadium fluorophosphate



- (a) Pre-mix reactants in equi-molar portions using a ball mill. Thus,
- 1 mol LiF = 25.94 g
- 1 mol VPO₄ = 145.91 g
- (b) Pelletize powder mixture.
- (c) Heat to 700°C at a rate of 2°C/minute in an air atmosphere in a nickel crucible. Dwell for 15 minutes at 700°C.
- (d) Cool to room temperature at about 50°C/minute.
- (e) Powderize pellet.

Example III

Reaction 3(a) - Formation of aluminum phosphate.

28



(a) Premix reactants in equi-molar portions using a ball mill. Thus,

5 1.0 mol $\text{Al}(\text{OH})_3$ = 78.0 g
 1.0 mol $\text{NH}_4\text{H}_2\text{PO}_4$ = 115.03 g

(b) Pelletize powder mixture.

(c) Heat to 950°C at a rate of 2°C/minute in an air atmosphere. Dwell for 8 hours at 950°C.

10 (d) Cool to room temperature at about 50°C/minute.

(e) Powderize.

Reaction 3(b) - Formation of lithium vanadium aluminum fluorophosphate



(a) Pre-mix reactants in the following proportions using ball mill. Thus,

20 0.9 mol VPO_4 = 131.3 g
 0.1 mol AlPO_4 = 12.2 g
 1.0 mol LiF = 25.9 g

(b) Pelletize powder mixture.

(c) Heat to 700°C at a rate of 2°C/minute in a nickel crucible in either an air or inert atmosphere. Dwell for 15 minutes at 700°C.


25 (d) Cool to room temperature at about 50°C/minute.

(e) Powderize.

Example IV

Reaction 4 - Production of lithium vanadium fluorophosphate in an alternate formulation.

29



- (a) Pre-mix reactants in the following proportions using a ball mill. Thus,

5	0.5 mol Li_2CO_3	=	37.0 g
	1.0 mol NH_4F	=	37.0 g
	1.0 mol VPO_4	=	145.9 g

- (b) Pelletize powder mixture.


- (c) Heat to 700°C at a rate of 2°C/minutes in an air atmosphere. Dwell for 15 minutes at 700°C.

- (d) Cool to room temperature.

- (e) Powderize pellet.

Example V

Reaction 5 - Single step preparation of lithium vanadium fluorophosphate using lithium fluoride in a carbothermal method.



- (a) Pre-mix reactants in the following proportions using a ball mill. Thus,

20	0.5 mol V_2O_5	=	90.94 g
	1.0 mol $\text{NH}_4\text{H}_2\text{PO}_4$	=	115.03 g
	1.0 mol LiF	=	25.94 g
	1.0 mol carbon	=	12.0 g

(Use 10% excess carbon → 13.2 g)

- (b) Pelletize powder mixture.

- (c) Heat pellet to 300°C at a rate of 2°C/minute in an inert atmosphere. Dwell for 3 hours at 300°C.

- (d) Cool to room temperature at 2°C/minute.

30

- (e) Powderize and repelletize.
- (f) Heat pellet to 750°C at a rate of 2°C/minute in an inert atmosphere (e.g. argon). Dwell for 1 hour at 750°C under an argon atmosphere.
- 5 (g) Cool to room temperature at 2°C/minute.
- (h) Powderize pellet.

Example VI


Reaction 6a - Formation of iron phosphate.



- 10 (a) Pre-mix reactants in the following proportions using a ball mill. Thus,

0.5 mol Fe_2O_3	=	79.8 g
1.0 mol $(\text{NH}_4)_2 \text{ HPO}_4$	=	132.1 g
- (b) Pelletize powder mixture.
- 15 (c) Heat to 300°C at 2°C/minute in air atmosphere. Dwell 8 hours and cool to room temperature.
- (d) Re-pelletize.
- (e) Heat to 900°C at 2°C/minute in air atmosphere. Dwell 8 hours and cool to room temperature.
- 20 (f) Powderize.

Reaction 6b - Formation of LiFePO_4F



- (a) Pre-mix reactants in the following proportions using a ball mill. Thus,

1 mol FePO_4	=	150.8 g
1 mol LiF	=	25.9 g
- (b) Pelletize.
- (c) Heat to 700°C at 2°C/minute in air atmosphere.
- (d) 15 minute dwell.
- 25

31

- (e) Cool to room temperature.
- (f) Powderize.

Example VII

Reaction 7a - Formation of titanium phosphate.

- 5 $\text{TiO}_2 + \text{NH}_4\text{H}_2\text{PO}_4 + 0.5 \text{ H}_2 \rightarrow \text{TiPO}_4 + \text{NH}_3 + 2 \text{ H}_2\text{O}$
- (a) Pre-mix reactants in the following proportions
using a ball mill. Thus,

1.0 mol TiO_2	=	79.9 g
1.0 mol $\text{NH}_4\text{H}_2\text{PO}_4$	=	115.0 g
 - 10 (b) Pelletize powder mixture.
 - (c) Heat to 300°C at 2°C/minute in air atmosphere.
Dwell for 3 hours.
 - (d) Cool to room temperature.
 - (e) Re-pelletize.
 - 15 (f) Heat to 850°C at 2°C/minute in H_2 atmosphere.
Dwell for 8 hours.
 - (g) Cool to room temperature.
 - (h) Powderize.

Reaction 7b - Formation of LiTiPO_4F .

- 20 $\text{TiPO}_4 + \text{LiF} \rightarrow \text{LiTiPO}_4\text{F}$
- (a) Pre-mix reactants in the following proportions
using a ball mill. Thus,

1 mol TiPO_4	=	142.9 g
1 mol LiF	=	25.9 g
 - 25 (b) Pelletize powder mixture.
 - (c) Heat to 700°C at 2°C/minute in inert
atmosphere.
 - (d) No dwell.
 - (e) Cool to room temperature.

(f) Powderize.

Example VIII

Reaction 8a - Formation of chromium phosphate.



5 (a) Pre-mix reactants in the following proportions using a ball mill. Thus,

$$0.5 \text{ mol Cr}_2\text{O}_3 = 76.0 \text{ g}$$

$$1.0 \text{ mol } (\text{NH}_4)_2\text{HPO}_4 = 132.1 \text{ g}$$

(b) Pelletize powder mixture.


10 (c) Heat to 500°C at 2°C/minute in air atmosphere. Dwell 6 hours and cool to room temperature.

(d) Re-pelletize.

(e) Heat to 1050°C at 2°C/minute in air atmosphere. Dwell 6 hours and cool to room temperature.

15 (f) Powderize.

Reaction 8b - Formation of LiCrPO₄F



(a) Pre-mix reactants in the following proportions using a ball mill. Thus,

20 $1 \text{ mol CrPO}_4 = 147.0 \text{ g}$

$$1 \text{ mol LiF} = 25.9 \text{ g}$$

(b) Pelletize powder mixture.

(c) Heat to 700°C at 2°C/minute in air atmosphere.

(d) 15 minute dwell.

25 (e) Cool to room temperature.

(f) Powderize.

**Characterization of Active Materials
and Formation and Testing of Cells**

Referring to **Figure 1**, the final product LiVPO_4F , prepared from VPO_4 metal compound per Reaction 1(b), appeared black in color. The product is a material with a triclinic crystal structure. The triclinic unit cell crystal structure is characterized by a lack of symmetry. In a triclinic crystal structure, $a \neq b \neq c$, and $\alpha \neq \beta \neq \gamma \neq 90^\circ$. This product's $\text{CuK}\alpha$ x-ray diffraction (XRD) pattern contained all of the peaks expected for this material as shown in **Figure 1**. The pattern evident in **Figure 1** is consistent with the single phase triclinic phosphate LiVPO_4F . This is evidenced by the position of the peaks in terms of the scattering angle 2θ (theta), x axis. Here the space group and the lattice parameters from XRD refinement are consistent with the triclinic structure. The values are $a = 5.1738 \text{ \AA} (0.002)$, $b = 5.3096 \text{ \AA} (0.002)$, $c = 7.2503 \text{ \AA} (0.001)$; the angle $\alpha = 72.4794 (0.06)$, $\beta = 107.7677 (0.04)$, $\gamma = 81.3757 (0.04)$, cell volume = $174.35 \text{ \AA}^3$.

The x-ray pattern demonstrates that the product of the invention was indeed the nominal formula LiVPO_4F . The term "nominal formula" refers to the fact that the relative proportion of atomic species may vary slightly on the order of up to 5 percent, or more typically, 1 percent to 3 percent. In another aspect, any portion of P (phosphorous) may be substituted by Si (silicon), S (sulfur) and/or As (arsenic).

The LiVPO_4F , prepared as described immediately above, was tested in an electrochemical cell. The positive electrode was prepared as described above, using

22.5mg of active material. The positive electrode contained, on a weight % basis, 80% active material, 8% carbon black, and 12% Kynar. Kynar is commercially available PVdF:HFP copolymers used as binder material.

5 The negative electrode was metallic lithium. The electrolyte was 2:1 weight ratio mixture of EC and DMC within which was dissolved 1 molar LiPF_6 . The cells were cycled between 3.5 and 4.4 with performance as shown in **Figure 2**. **Figure 2** is an Electrochemical Voltage

10 Spectroscopy (EVS) voltage/capacity profile for a cell with cathode material formed with LiVPO_4F . **Figure 2** shows the results of the first cycle with the critical limiting current density less than 0.1 milliamps per square centimeter with $\pm 10\text{mV}$ steps between about 3.0 and

15 4.4 volts based upon 29.4 milligrams of the LiVPO_4F active material in the cathode (positive electrode). In an as prepared, as assembled, initial condition, the positive electrode active material is LiVPO_4F . The lithium is extracted from the LiVPO_4F during charging of

20 the cell. When fully charged, about 0.75 unit of lithium had been removed per formula unit. Consequently, the positive electrode active material corresponds to $\text{Li}_{1-x}\text{VPO}_4\text{F}$ where x appears to be equal to about 0.75, when the cathode material is at 4.4 volts versus Li/Li^+ . The

25 extraction represents approximately 129 milliamp hours per gram corresponding to about 3.8 milliamp hours based on 29.4 milligrams active material. Next, the cell is discharged whereupon a quantity of lithium is re-inserted into the LiVPO_4F . The re-insertion corresponds to

30 approximately 109 milliamp hours per gram proportional to the insertion of essentially all of the lithium. The bottom of the curve corresponds to approximately 3.0 volts.

Figure 3 is an Electrochemical Voltage Spectroscopy differential capacity plot based on **Figure 2**. As can be seen from **Figure 3**, the relatively symmetrical nature of the peaks indicates good electrical reversibility. There are small peak separations (charge/discharge), and good correspondence between peaks above and below the zero axis. There are essentially no peaks that can be related to irreversible reactions, since peaks above the axis (cell charge) have corresponding peaks below the axis (cell discharge), and there is very little separation between the peaks above and below the axis. This shows that the LiVPO_4F is high quality electrode material.

Referring to **Figure 4**, the final product LiFePO_4F , prepared from FePO_4 metal compound per Reaction 6(b), appeared brown in color. (Reactions 6a and 6b are carried out in the same manner as reactions 1a and 1b.) The product is a material with a triclinic crystal structure. This product's $\text{CuK}\alpha$ x-ray diffraction pattern contained all of the peaks expected for this material as shown in **Figure 4**. The pattern evident in **Figure 4** is consistent with the single phase triclinic phosphate LiFePO_4F . This is evidenced by the position of the peaks in terms of the scattering angle 2θ (theta), x axis. Here the space group and the lattice parameters from XRD refinement are consistent with the triclinic structure. The values are $a = 5.1528 \text{ \AA} (0.002)$, $b = 5.3031 \text{ \AA} (0.002)$, $c = 7.4966 \text{ \AA} (0.003)$; the angle $\alpha = 67.001^\circ (0.02)$, $\beta = 67.164^\circ (0.03)$, $\gamma = 81.512^\circ (0.02)$, cell volume = $173.79 \text{ \AA}^3$. The x-ray pattern demonstrates that the product of the invention was indeed the nominal formula LiFePO_4F .

Referring to **Figure 5**, the final product LiTiPO_4F , prepared from TiPO_4 metal compound per Reaction 7(b), appeared green in color. (Reactions 7a and 7b are carried out in the same manner as reactions 1a and 1b.)

5 The product is a material with a triclinic crystal structure. This product's $\text{CuK}\alpha$ x-ray diffraction (XRD) pattern contained all of the peaks expected for this material as shown in **Figure 5**. The pattern evident in **Figure 5** is consistent with the single phase triclinic

10 phosphate LiTiPO_4F . This is evidenced by the position of the peaks in terms of the scattering angle 2θ (theta), x axis. The x-ray diffraction pattern was triclinic.

Referring to **Figure 6**, the final product LiCrPO_4F , prepared from CrPO_4 metal compound per Reaction 8(b), appeared green in color. (Reactions 8a and 8b are carried out in the same manner as reactions 1a and 1b.)

15 The product is a material with a triclinic crystal structure. This product's $\text{CuK}\alpha$ x-ray diffraction pattern contained all of the peaks expected for this material as shown in **Figure 6**. The pattern evident in **Figure 6** is consistent with the single phase triclinic phosphate LiCrPO_4F . This is evidenced by the position of the peaks in terms of the scattering angle 2θ (theta), x axis.

20 Here the space group and the lattice parameters from XRD refinement are consistent with the triclinic structure. The values are $a = 4.996 \text{ \AA} (0.002)$, $b = 5.307 \text{ \AA} (0.002)$, $c = 6.923 \text{ \AA} (0.004)$; the angle $\alpha = 71.600^\circ (0.06)$, $\beta = 100.71^\circ (0.04)$, $\gamma = 78.546^\circ (0.05)$, cell volume = $164.54 \text{ \AA}^3$. The x-ray pattern demonstrates that the product of

25 the invention was indeed the nominal formula LiCrPO_4F .

30

As demonstrated by the above example, the methods described herein have successfully been used to

make the $\text{LiM}_{1-y}\text{MI}_y\text{PO}_4\text{F}$ compounds. These methods produce products which are essentially homogeneous, single phase compounds. Although small amounts of other materials or phases may be present, such does not alter the essential character of the products so produced.

In summary, the invention provides new compounds $\text{LiM}_a\text{MI}_b\text{PO}_4\text{F}$, more specifically, $\text{LiM}_{1-y}\text{MI}_y\text{PO}_4\text{F}$, which are adaptable to commercial scale production. The new compounds are triclinic compounds as demonstrated by XRD analysis. The new materials demonstrate relatively high specific capacity coupled to a desirable voltage range and energetic reversibility. These properties make these materials excellent candidates as cathode active compound for lithium ion applications. The new materials of the invention are easily and conveniently produced from available precursors with no loss of weight, or generation of waste products. The precursors can be produced by methods, such as carbothermal reduction. In other words, this invention provides new compounds capable of being commercially and economically produced for use in batteries. In addition, the use of lighter non-transition metals and elements mixed with the transition metal in the lithium metal fluorophosphate provides for structural stability and better recycling of the lithium ions.

While this invention has been described in terms of certain embodiments thereof, it is not intended that it be limited to the above description, but rather only to the extent set forth in the following claims.

The embodiments of the invention in which an exclusive property or privilege is claimed are defined in the following claims.

- 39 -

CLAIMS:

1. A compound represented by the nominal general formula $\text{LiM}_{1-y}\text{MI}_y\text{PO}_4\text{F}$ where $0 < y < 1$ and where M is selected from the group consisting of Mn, V, Cr, Ti, Fe, Co, Ni, and mixtures thereof, and where MI is selected from the group consisting of Mn, V, Cr, Ti, Fe, Co, Ni, Nb, Mo, Al, B, and mixtures thereof.

2. The compound of claim 1, wherein M has a +3 oxidation state.

3. The compound of claim 1, wherein MI has a +3 oxidation state.

4. The compound of claim 1, wherein M is selected from the group consisting of Fe, Co, Mn and mixtures thereof.

5. The compound of claim 1, wherein M is a mixture of Fe and Co.

6. The compound of claim 1, wherein M is Fe.

7. The compound of claim 1 having the nominal formula $\text{LiV}_{0.9}\text{Al}_{0.1}\text{PO}_4\text{F}$.

8. An electrode comprising a binder, an electrically conductive carbonaceous material and an

active material represented by the nominal general formula $\text{LiM}_{1-y}\text{MI}_y\text{PO}_4\text{F}$ where $0 < y < 1$ and where M is selected from the group consisting of Mn, V, Cr, Ti, Fe, Co, Ni, and mixtures thereof, and where MI is selected from the group consisting of Mn, V, Cr, Ti, Fe, Co, Ni, Nb, Mo, Al, B, and mixtures thereof.

9. The electrode of claim 8, wherein M has a +3 oxidation state.

10. The electrode of claim 8, wherein MI has a +3 oxidation state.

11. The electrode of claim 8, wherein M is selected from the group consisting of Fe, Co, Mn and mixtures thereof.

12. The electrode of claim 8, wherein M is a mixture of Fe and Co.

13. The electrode of claim 8, wherein M is Fe.

14. The electrode of claim 8, wherein said active material comprises a compound having the nominal formula $\text{LiV}_{0.9}\text{Al}_{0.1}\text{PO}_4\text{F}$.

15. A lithium ion battery comprising:
a first electrode comprising a binder, an electrically conductive carbonaceous material, and an active material represented by the general formula $\text{LiM}_{1-y}\text{MI}_y\text{PO}_4\text{F}$ where $0 < y < 1$ and where M is selected from the group consisting of Mn, V, Cr, Ti, Fe, Co, Ni, and mixtures thereof, and where MI is selected from the group consisting

of Mn, V, Cr, Ti, Fe, Co, Ni, Nb, Mo, Al, B, and mixtures thereof;

a second electrode which is a counter-electrode to said first electrode; and

an electrolyte between said electrodes.

16. The battery of claim 15, wherein M has a +3 oxidation state.

17. The battery of claim 15, wherein MI has a +3 oxidation state.

18. The battery of claim 15, wherein M is selected from the group consisting of Fe, Co, Mn and mixtures thereof.

19. The battery of claim 15, wherein M is a mixture of Fe and Co.

20. The battery of claim 15, wherein M is Fe.

21. The battery of claim 15, wherein said active material comprises a compound having the nominal formula $\text{LiV}_{0.9}\text{Al}_{0.1}\text{PO}_4\text{F}$.

22. A lithium metal fluorophosphate compound represented by the nominal general formula $\text{LiM}_{1-y}\text{MI}_y\text{PO}_4\text{F}$ where $0 < y < 1$ and where M is selected from the group consisting of Mn, V, Cr, Ti, Fe, Co, Ni, and mixtures thereof, and where MI is selected from the group consisting of Mn, V, Cr, Ti, Fe, Co, Ni, Nb, Mo, Al, B, and mixtures thereof made by a process comprising the steps of:

reacting a metal compound with a phosphate containing compound and lithium fluoride to form the lithium metal fluorophosphate compound.

23. The compound of claim 1 having the nominal formula LiMnPO_4F .

24. The compound of claim 1 having the nominal formula LiVPO_4F .

25. The compound of claim 1 having the nominal formula LiCrPO_4F .

26. The compound of claim 1 having the nominal formula LiTiPO_4F .

27. The compound of claim 1, wherein (a) M has more than one oxidation state above a ground state M^0 ; and (b) MI is selected from the group consisting of Mn, V, Cr, Ti, Fe, Co, Ni, Nb, Mo, Al, B, and mixtures thereof, with the proviso that when M is Fe, MI is selected from the group consisting of Mn, V, Cr, Ti, Co, Ni, Nb, Mo, Al, B and mixtures thereof.

28. The compound of claim 27, wherein M has a +3 oxidation state.

29. The compound of claim 28, wherein MI has a +3 oxidation state.

30. The compound of claim 27, wherein M and MI are different elements.

31. The compound of claim 27, wherein M is selected from the group consisting of Mn, V, Cr, Ti, Fe, Co and Ni.

32. The compound of claim 27, wherein M is selected from the group consisting of Fe, Co, Mn, and mixtures thereof.

33. The compound of claim 27, wherein M is a mixture of Fe and Co.

34. The compound of claim 29, wherein M is Fe.

35. The compound of claim 33 or 34, wherein MI is Al.

36. The compound of claim 27, wherein the compound is represented by the nominal formula LiMnPO_4F .

37. The compound of claim 27, wherein the compound is represented by the nominal formula LiVPO_4F .

38. The compound of claim 27, wherein the compound is represented by the nominal formula LiCrPO_4F .

39. The compound of claim 27, wherein the compound is represented by the nominal formula LiTiPO_4F .

40. The compound of claim 27, wherein the compound is represented by the nominal formula $\text{LiV}_{0.9}\text{Al}_{0.1}\text{PO}_4\text{F}$.

41. The compound of claim 27, wherein the composition has a triclinic structure.

1/8




Figure 1

2/8



LiVPO₄F 700C/15mins/Box Oven 29.4 mg active

Figure 2

LiVPO₄F



3/8

Figure 3






Figure 4

5/8

 LiTiPO_4F 

2-Theta (°)

Figure 5

6/8




Figure 6

7/8




Figure 7

8/8




Figure 8

