

(12) STANDARD PATENT
(19) AUSTRALIAN PATENT OFFICE

(11) Application No. **AU 2004215696 B2**

(54) Title
Method for coating metallic surfaces with a composition that is rich in polymers

(51) International Patent Classification(s)
C09D 5/08 (2006.01) **C23C 22/60** (2006.01)
C09D 4/00 (2006.01) **C23C 22/68** (2006.01)
C23C 22/50 (2006.01) **C23C 22/74** (2006.01)
C23C 22/53 (2006.01) **C23C 22/83** (2006.01)

(21) Application No: **2004215696** (22) Date of Filing: **2004.02.25**

(87) WIPO No: **WO04/076568**

(30) Priority Data

(31) Number	(32) Date	(33) Country
103 32 744.4	2003.07.17	DE
103 08 237.9	2003.02.25	DE

(43) Publication Date: **2004.09.10**

(44) Accepted Journal Date: **2010.11.25**

(71) Applicant(s)
Chemetall GmbH

(72) Inventor(s)
Domes, Heribert;Schneider, Julia

(74) Agent / Attorney
Watermark Patent and Trade Marks Attorneys, Level 2 302 Burwood Road, Hawthorn, VIC, 3122

(56) Related Art
DE 3151115
DE 10149148
EP 1130132

(12) NACH DEM VERTRAG ÜBER DIE INTERNATIONALE ZUSAMMENARBEIT AUF DEM GEBIET DES
PATENTWESENS (PCT) VERÖFFENTLICHTE INTERNATIONALE ANMELDUNG

(19) Weltorganisation für geistiges Eigentum
Internationales Büro



(43) Internationales Veröffentlichungsdatum
10. September 2004 (10.09.2004)

PCT

(10) Internationale Veröffentlichungsnummer
WO 2004/076568 A1

(51) Internationale Patentklassifikation⁷: **C09D 5/08**

(21) Internationales Aktenzeichen: PCT/EP2004/001829

(22) Internationales Anmeldedatum:
25. Februar 2004 (25.02.2004)

(25) Einreichungssprache: Deutsch

(26) Veröffentlichungssprache: Deutsch

(30) Angaben zur Priorität:
103 08 237.9 25. Februar 2003 (25.02.2003) DE
103 32 744.4 17. Juli 2003 (17.07.2003) DE

(71) Anmelder (für alle Bestimmungsstaaten mit Ausnahme von
US): **CHEMETALL GMBH** [DE/DE]; Trakehner Strasse
3, 60487 Frankfurt am Main (DE).

(72) Erfinder; und

(75) Erfinder/Anmelder (nur für US): **DOMES, Heribert**
[DE/DE]; Sudetenstrasse 27, 35789 Weilmünster (DE).
SCHNEIDER, Julia [DE/DE]; Bernardstrasse 39, 63067
Offenbach (DE).

(74) Anwalt: **UPPENA, Franz**; c/o Dynamit Nobel Aktiengesellschaft, Patente, Marken & Lizenzen, 53839 Troisdorf (DE).

(81) Bestimmungsstaaten (soweit nicht anders angegeben, für jede verfügbare nationale Schutzrechtsart): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Bestimmungsstaaten (soweit nicht anders angegeben, für jede verfügbare regionale Schutzrechtsart): ARIPO (BW, GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), eurasisches (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), europäisches (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Veröffentlicht:

— mit internationalem Recherchenbericht

Zur Erklärung der Zweibuchstaben-Codes und der anderen Abkürzungen wird auf die Erklärungen ("Guidance Notes on Codes and Abbreviations") am Anfang jeder regulären Ausgabe der PCT-Gazette verwiesen.

(54) Title: METHOD FOR COATING METALLIC SURFACES WITH A COMPOSITION THAT IS RICH IN POLYMERS

(54) Bezeichnung: VERFAHREN ZUR BESCHICHTUNG VON METALLISCHEN OBERFLÄCHEN MIT EINER ZUSAMMENSETZUNG REICH AN POLYMER

(57) Abstract: The invention relates to a method for coating a metallic surface with an aqueous composition for pretreating before applying another coating or for treating said metallic surface. In addition to water, the composition contains: a) at least one hydrolyzable or at least partially hydrolyzed silane; b) at least one metal chelate; c) at least one organic film former, and; d) at least one long-chain alcohol that serves as a film forming aid. The unsoiled, scoured, cleaned and/or pretreated metallic surface is brought into contact with the aqueous composition and a film is formed on the metallic surface, is subsequently dried, compacted in part or completely by film formation and, if necessary, additionally hardened. The dried and, if necessary, additionally hardened film has a layer thickness ranging from 0.01 to 10 µm. The invention also relates to corresponding aqueous compositions.

(57) Zusammenfassung: Die Erfindung betrifft ein Verfahren zur Beschichtung einer metallischen Oberfläche mit einer wässrigen Zusammensetzung zur Vorbehandlung vor einer weiteren Beschichtung oder zur Behandlung, bei der die Zusammensetzung neben Wasser a) mindestens ein hydrolysierbares oder zumindest teilweise hydrolysiertes Silan, b) mindestens ein Metallchelat, c) mindestens einen organischen Filmbildner und d) mindestens einem langkettigen Alkohol als Filmbildungshilfsmittel enthält, wobei die saubere, gebeizte, gereinigte oder/und vorbehandelte metallische Oberfläche mit der wässrigen Zusammensetzung in Kontakt gebracht und ein Film auf der metallischen Oberfläche ausgebildet wird, der anschließend getrocknet wird, teilweise oder gänzlich durch Verfilmen verdichtet wird, und ggf. zusätzlich ausgehärtet wird, wobei der getrocknete und ggf. auch ausgehärtete Film eine Schichtdicke im Bereich von 0,01 bis 10 µm aufweist. Ferner betrifft die Erfindung entsprechende wässrige Zusammensetzungen.



WO 2004/076568 A1

**Process for coating metallic surfaces with a composition
rich in polymer**

5 The invention relates to a process for coating metallic
surfaces with an aqueous composition containing silane and
metal chelate and organic film-forming agent. The invention
furthermore relates to corresponding aqueous compositions and
to the use of the substrates coated by the process according
10 to the invention.

The processes most frequently employed hitherto on metals, in
particular metal strip, for surface treatment or pretreatment
before lacquering are based on the use of chromium(III)
15 or/and chromium (VI) compounds together with various
additives. Because of the toxicological and ecological risks
which such processes involve, and moreover because of the
foreseeable legal restrictions in respect of the use of
chromate-containing processes, alternatives to these
20 processes have already been sought for a relatively long time
in all fields of metal surface treatment.

The use of silanes in aqueous compositions for the
preparation of siloxane-rich corrosion protection coatings is
25 known in principle. These coatings have proved themselves,
but the processes for coating with an aqueous composition
containing predominantly silane are in some cases difficult
to use. This coating is not always formed with optimum
properties. Furthermore, there may be problems in being able
30 to characterize adequately the very thin transparent silane
coatings on the metal substrate and defects thereof with the
naked eye or with optical aids. The corrosion protection and
the lacquer adhesion of the siloxane-rich coatings formed are
very often, but not always, high and in some cases not
35 sufficiently high for particular uses even with suitable
application.

In designing silane-containing aqueous compositions, a small or large added amount of at least one component chosen from the group consisting of monomers, oligomers and polymers has moreover proved appropriate. In such
5 compositions the nature and amount of the silane addition is sometimes of decisive importance for success. However, the added amounts of silane for this purpose are conventionally comparatively low - usually only up to 5 wt.% - and then act as a "coupling agent",
10 where the adhesion-promoting action, in particular between the metallic substrate and lacquer and optionally between the pigment and organic lacquer constituents, should prevail, but in some cases also a low crosslinking action may occur to a minor extent.
15 Silane additions are predominantly added to thermosetting resin systems.

Resin mixtures in which resins are blended with inorganic acids in order also to achieve in this manner
20 a pickling attack and therefore a better contact of the resin layer directly with the metallic surface are moreover also known. These compositions have the disadvantage that because of the pickling attack during the contact between the treatment liquid (dispersion)
25 and the substrate, contamination occurs. This leads to concentration of metals in the treatment liquid and as a result to a permanent change in the chemical composition of the treatment liquid, as a result of which the corrosion protection is significantly impaired. By the
30 pickling attack, these metals are dissolved out of the metallic surface of the substrates to be treated.

Another disadvantage is that the surfaces can discolour to a dark colour, under certain circumstances to dark
35 grey to anthracite-coloured, specifically in the case of aluminium or aluminium-containing alloys. The dark-discoloured metal surfaces cannot be employed for decorative uses since the discoloration itself is

undesirable for aesthetic reasons. The dark coloration is visible with varying intensity, depending on the thickness of the layer applied. This effect, called darkening, should as far as possible be avoided.

5

DE-A-198 14 605 describes a sealing composition for metallic surfaces which contains, in addition to at least one solvent, at least one silane derivative and colloidal silica or/and colloidal silicate. In the
10 examples, the content of silane(s) is 20 wt.% (about 200 g/l) and that of silica sol or silicate in the range from 10 to 40 wt.%. A suggested addition of wax to reduce the coefficient of friction or of organic binder as a wetting agent, such as e.g. polypropylene,
15 polyethylene, polyethylene oxide or modified polysiloxane, or for other reasons not mentioned with binders not mentioned in more detail, was not employed in the examples. The examples mention no polymeric substances beyond the silanes.

20

The doctrine of DE-A1-41 38 218 is a solution containing organofunctional polysiloxane and titanatic acid esters and/or titanium chelate for use as an after-dipping agent for chromated or passivated zinc-containing layers
25 on steel components.

US 5,053,081 relates to a process for coating a metallic surface, which has already been pretreated e.g. with a phosphate layer, with an after-rinsing solution based on
30 a content of 3-aminopropyltriethoxysilane and, in comparison with this, a significantly lower content of titanium chelate prepared with tetraalkyl titanate, beta-diketone and alkanolamine.

35 DE-A1-101 49 148 describes aqueous coating compositions based on organic film-forming agent, fine inorganic particles and lubricant or/and organic corrosion inhibitor, which, in spite of the

2004215696 21 Oct 2010

compounds, produced outstanding results of corrosion resistance, adhesive strength and shapability, inter alia on Galvalume® steel sheets, but nevertheless still showed an
5 inadequate corrosion resistance of an organic film of about 1 µm layer thickness on hot-galvanized, electrolytically galvanized, Galvalume®-coated or Galfan®-coated metallic strips, that is to say on metallic surfaces which are difficult to protect against corrosion. The compositions,
10 their constituents and the properties of the raw materials and coatings of this publication are expressly included in this Application.

EP 1 130 132 A1 describes compositions which also contain a
15 zirconium or/and titanium compound in addition to a silane and silicon dioxide. However, among the zirconium and titanium compounds mentioned there, there are no chelates, with the exception of zirconium acetylacetonate. The effect of an addition of zirconium acetylacetonate, however, does
20 not emerge therefrom.

The teaching of DE 31 51 115 A1 is steel sheets which have a chromate film and, on top of this as a second covering, a coating based on colloidal SiO₂, resin, silane and optionally
25 chelate.

It is an object of the invention to overcome at least some of the disadvantages of the prior art, and in particular to propose a process for coating metallic surfaces which is also
30 suitable for high coating speeds such as are used for metallic strips, which can be used largely or completely without chromium(VI) compounds, which is as far as possible also free from inorganic and organic acids and which as far as possible can be employed easily on a large industrial
35 scale. The object is in particular to increase the corrosion resistance of chromate-free organic coatings of less than 10 µm, and in particular of less than 3 µm dry film thickness, such

that coatings on hot-galvanized, electrolytically galvanized or Galfan[®]-coated metallic strips also experience a corrosion protection equivalent to that of chromate-containing organic coatings.

5

It has been found, surprisingly, that the addition of at least one chelate, in particular a titanium and/or zirconium chelate, to a silane-containing aqueous composition significantly improves the corrosion resistance and also the lacquer adhesion of the film formed therefrom. The addition of an organic corrosion inhibitor can usually also be omitted here - except in the case of coating of bright steel.

10

Accordingly in a first aspect of the invention there is provided a process for the pre-treatment or treatment of a metallic surface by coating with an aqueous composition substantially free from chromium(VI) compounds, wherein the process comprises the steps of:

(i) bringing a clean, pickled, cleaned and/or pre-treated metallic surface into contact with the aqueous composition such as to form a film on the metallic surface; and

(ii) drying and partly or completely compacting the film and optionally curing the film to an extent wherein the dried and optionally cured film has a layer thickness in the range from 0.01 to 10 μm ;

20

25

characterized in that the aqueous composition contains:

30

- a) at least one hydrolysable or at least partly hydrolysed silane;
- b) at least one metal chelate that is stable in aqueous dispersions in the presence of components a), c) and d), and wherein the metal chelate is functional to improve the corrosion resistance and adhesion of the film;

35

2004215696 21 Oct 2010

2004215696 21 Oct 2010

5a

- 5 c) at least one organic film-forming agent which contains at least one water-soluble or water-dispersed organic polymer and/or copolymer with an acid number in the range from 3 to 250, whereby the content of organic film-forming agent, based on the solids content of the composition, is > 45 wt.%; and
- 10 d) at least one long-chain alcohol as a film-forming auxiliary.

15 In a second aspect of the invention there is provided an aqueous composition for the pretreatment of a metallic surface before a further coating or for treatment of that surface to form a film on the metallic surface, characterized in that the composition contains, in addition to water,

- 20 a) at least one hydrolysable or at least partly hydrolysed silane;
- 25 b) at least one metal chelate that is stable in aqueous dispersions in the presence of components a), c) and d) and wherein the metal chelate is functional to improve the corrosion resistance and adhesion of the film;
- 30 c) at least one organic film-forming agent which contains at least one water-soluble or water-dispersed organic polymer or/and copolymer with an acid number in the range from 3 to 250, the content of organic film-forming agent, based on the solids content of the composition, being > 45 wt.%; and
- d) at least one long-chain alcohol as a film-forming auxiliary.

35 It has furthermore been found, surprisingly, that it was possible also to improve the corrosion resistance of the film formed from the aqueous composition containing at least one silane but no organic polymer very significantly if at

2004215696 21 Oct 2010

5b

least one chelate, in particular a titanium or/and zirconium chelate, is also added.

5 The object is achieved with a process for coating a metallic surface, in particular of aluminium, iron, copper, magnesium, nickel, titanium, tin, zinc or alloys containing aluminium, iron, copper, magnesium, nickel, titanium, tin or/and zinc, with an aqueous composition, which can be largely or completely free from chromium(VI) compounds, for
10 pretreatment before a further coating or for treatment in which the body to be coated optionally - especially a strip or strip section - is shaped after the coating, which is characterized in that the composition contains, in addition to water,

15 a) at least one hydrolysable or at least partly hydrolysed silane,

b) at least one metal chelate which has only a low reactivity in the aqueous composition,

5 c) at least one organic film-forming agent which contains at least one water-soluble or water-dispersed organic polymer or/and copolymer with an acid number in the range from 3 to 250 and wherein the content of organic film-forming agent, based on the solids content of the composition, is > 45 wt.%,
10 and

d) at least one long-chain alcohol as a film-forming auxiliary,

15 wherein the clean, pickled, cleaned or/and pretreated metallic surface is brought into contact with the aqueous composition and a film is formed on the metallic surface, which is then dried and partly or completely compacted by formation of a film - during which it
20 cures, and optionally is additionally cured,

wherein the dried and optionally also cured film has a layer thickness in the range from 0.01 to 10 μm , determined by detachment of a defined area of the cured
25 film and weighing or by determination of the silicon content of the coating e.g. with x-ray fluorescence analysis and corresponding conversion.

The object is moreover achieved with an aqueous
30 composition for pretreatment of a metallic surface before a further coating or for treatment of that surface, which is characterized in that the composition contains, in addition to water,

35 a) at least one hydrolysable or at least partly hydrolysed silane,

6a

b) at least one metal chelate which has only a low reactivity in the aqueous composition,

5 c) at least one organic film-forming agent which contains at least one water-soluble or water-dispersed organic polymer or/and copolymer with an acid number in the range from 3 to 250, the content of organic film-forming agent, based on the solids content of the composition, being > 45 wt.%, and

10

d) at least one long-chain alcohol as a film-forming agent.

15 The amounts ratio of a) to b), in each case including the reaction products formed therefrom, is preferably in the range from 0.1 : 1 to 10 : 1, particularly preferably in the amounts ratio of 0.2 : 1 to 8 : 1, very particularly preferably in the amounts ratio of 0.3 : 1 to 7 : 1, in particular 0.4 : 1, 0.6 : 1,

0.8 : 1, 1 : 1, 1.2 : 1, 1.6 : 1, 2 : 1, 3 : 1, 4 : 1,
5 : 1 or 6 : 1.

In each case amounts of silane(s) and chelate(s), in
5 each case including the reaction products formed
therefrom, independently of one another of 0.05 to
5 wt.%, based on the wet film, are particularly
preferred, very particularly preferably in each case
independently of one another amounts of 0.08 to 4 wt.%,
10 in particular about in each case independently of one
another amounts of 0.1, 0.2, 0.3, 0.5, 0.8, 1, 1.5, 2,
2.5, 3 or 3.5 wt.%.

In each case amounts of silane(s) and chelate(s), in
15 each case including the reaction products formed
therefrom, independently of one another of 0.2 to
15 wt.%, based on the solids content, are particularly
preferred, very particularly preferably in each case
independently of one another amounts of 0.3 to 11 wt.%,
20 in particular about in each case independently of one
another amounts of 0.5, 0.8, 1, 1.5, 2, 2.5, 3, 3.5, 4,
4.5, 5, 5.5, 6, 6.5, 7, 7.5, 8, 8.5, 9, 9.5, 10 or
10.5 wt.%.

25 Preferably, at least one silane is chosen which is
compatible with water, i.e. that the at least one silane
and, where appropriate, its hydrolysis and condensation
products are miscible with the components of the aqueous
composition without problems and are stable for several
30 weeks, and that it allows formation of a defect-free wet
film and dry film which, in particular, is closed,
uniform and free from craters. In particular, at least
one silane is chosen which renders possible a high
corrosion resistance, in particular in combination with
35 the at least one chelate chosen.

Preferably, at least one chelate is chosen that is
stable for a duration of several weeks in aqueous

dispersions in the presence of the other components of the aqueous composition and which renders possible a high corrosion resistance. It is furthermore advantageous if both the at least one silane and the at least one chelate on the one hand can bond chemically to the intended metallic surface which is to be brought into contact therewith and optionally can also bond chemically to the lacquer subsequently to be applied. The at least one metal chelate is, in particular, one of Al, B, Ca, Fe, Hf, La, Mg, Mn, Si, Ti, Y, Zn, Zr or/and at least one lanthanide, such as Ce, or such as a Ce-containing lanthanide mixture, particularly preferably chosen from the group consisting of Al, Hf, Mn, Si, Ti, Y and Zr.

The concentrates of the aqueous compositions containing predominantly silane and chelate and of the part components as the starting substance for polymer-containing compositions preferably have a water content in the range from 20 to 85 wt.%, in particular 30 to 80 wt.%. The concentrates preferably contain the at least one silane, including the reaction products formed therefrom, in a content in the range from 1 to 60 wt.%, particularly preferably in the range from 3 to 45 wt.%, very particularly preferably in the range from 6 to 45 wt.%, above all in the range from 8 to 32 wt.%, in particular of about 8, 10, 12, 14, 16, 18, 20, 22, 24, 26, 28, 30 or 32.5 wt.%, and the at least one chelate, optionally including the reaction products formed therefrom, in the range from 1 to 50 wt.%, particularly preferably in the range from 2 to 40 wt.%, very particularly preferably in the range from 3 to 30 wt.%, above all in the range from 5 to 25 wt.%, in particular about 7.5, 10, 12, 14, 16, 18, 20 or 22.5 wt.%.

The bath compositions of the aqueous compositions containing predominantly silane and chelate preferably have a water content in the range from 80 to 99.9 wt.%,

preferably in the range from 90 to 99.8 wt.%, particularly preferably in the range from 94 to 99.7 wt.%, above all in the range from 96 to 99.6 wt.%, in particular of about 95, 95.5, 96, 96.5, 97, 97.5, 97.9, 98.2, 98.5, 98.8, 99.1 or 99.4 wt.%.
5

The bath compositions preferably contain the at least one silane, including the reaction products formed therefrom, in a content in the range from 0.01 to 10 wt.%, particularly preferably in the range from 0.05 to 7 wt.%, very particularly preferably in the range from 0.1 to 5 wt.%, above all in the range from 0.2 to 4 wt.%, in particular of about 0.4, 0.6, 0.8, 1.0, 1.1, 1.2, 1.3, 1.4, 1.5, 1.6, 1.7, 1.8, 1.9, 2.0, 2.1, 2.2, 2.4, 2.6, 2.8, 3.0, 3.2, 3.4, 3.6 or 3.8 wt.%, and the at least one chelate, including the reaction products possibly formed therefrom, in the range from 0.01 to 10 wt.%, particularly preferably in the range from 0.05 to 7 wt.%, very particularly preferably in the range from 0.1 to 5 wt.%, above all in the range from 0.2 to 4 wt.%, in particular of about 0.3, 0.4, 0.5, 0.6, 0.7, 0.8, 0.9, 1.0, 1.1, 1.2, 1.3, 1.4, 1.6, 1.8, 2.0, 2.2, 2.4, 2.6, 2.8, 3.0, 3.2, 3.4, 3.6 or 3.8 wt.%.
10
15
20

The contents of the at least one silane and of the at least one chelate, in each case including the reaction products formed therefrom, in particular those of titanium, hafnium or/and zirconium, preferably make up at least 20 wt.%, in particular at least 30 wt.%, particularly preferably at least 40 wt.%, very particularly preferably at least 50 wt.%, above all in each case at least 60, 70, 80, 90, 94, 95, 96, 97, 98 or 99 wt.% of the solids contents of this composition. This composition particularly preferably substantially contains water, in each case at least one silane and/or reaction products thereof, at least one chelate, where appropriate including the reaction products formed therefrom, and optionally contents of substances chosen
25
30
35

from the group consisting of alcohols, acids, such as carboxylic and fatty acids, such as acetic acid, and/or mineral acids, and other substances which influence the pH, such as ammonia, and additives and impurities. The total content of further compounds, including additives, in addition to silane and chelate is usually up to 20 wt.% of the solids content of silane and chelate, preferably up to 15 wt.%, particularly preferably up to 10 wt.%, very particularly preferably up to 5 wt.%, above all up to 1 or 2 wt.%.

Although the ratio of the at least one silane, including the reaction products formed therefrom, to the at least one chelate, optionally including the reaction products formed therefrom, can preferably be in the range from 0.8 : 1 to 1.2 : 1, it has surprisingly become clear that this ratio can also be, in particular, in the range from 0.2 : 1 to 0.5 : 1 or 2 : 1 to 5 : 1, since in certain situations there may be an optimum there.

The pH of this bath composition can be, in particular, in the range from 3 to 9.5, preferably in the range from 3.5 to 9, in particular in the range from 4 to 8.8. To adjust the pH, inter alia, an addition of a weak acid or of a dilute strong acid or an acid mixture can be added. In particular, at least one acid, such as carboxylic or fatty acids, such as acetic acid, or/and mineral acids, and other substances which influence the pH, such as ammonia, can be used. The bath composition can in some cases be adjusted down to pH values of about 3.5 by addition of acid if the chemical system tolerates the pH chosen and remains stable. However, if the acid is added only for neutralization, no or virtually no pickling attack takes place. A solvent, such as an alcohol, can preferably also be added to stabilize the silane.

The coatings formed with these bath compositions typically have a layer thickness in the range from 0.01 to 1 μm or to 0.6 μm , usually 0.015 to 0.25 μm .

- 5 The addition of the at least one silane a) offers the advantage that adhesion bridges are formed between the substrate and the dried protective film and to lacquer layers or/and coatings of plastic possibly subsequently applied, as a result of which an improved lacquer
10 adhesion is also achieved. A further advantage is that suitable silanes/siloxanes generate crosslinkings like adhesion bridges within the dried protective film, which considerably improve the strength and/or the flexibility of the coating composite and the adhesion to the
15 substrate, as a result of which an improved adhesion is achieved in many lacquer systems.

The aqueous composition which contains predominantly chelate and silane or predominantly synthetic resin and
20 in addition chelate and silane preferably contains in each case at least one acyloxysilane, one alkoxysilane, one silane with at least one amine group, such as an aminoalkylsilane, one silane with at least one succinic acid group or/and succinic acid anhydride group, one
25 bis-silyl-silane, one silane with at least one epoxide group, such as a glycidoxysilane, one (meth)acrylato-silane, one multi-silyl-silane, one ureidosilane, one vinylsilane or/and at least one silanol or/and at least one siloxane of a composition corresponding chemically
30 to the abovementioned silanes. The reaction products of the silanes are known in principle in such systems and are therefore not mentioned individually. They are therefore also not referred to further in the following, but are included under the term "silane(s)".

35

The composition can contain e.g. at least one silane mixed with a content of at least one alcohol, such as ethanol, methanol or/and propanol, of up to 8 wt.%,

based on the silane content, preferably up to 5 wt.%, particularly preferably up to 1 wt.%, very particularly preferably up to 0.5 wt.%. In particular, the mixture can contain e.g. at least one silane chosen from at least one amino-silane, such as e.g. bis-amino-silane, without or with at least one alkoxy-silane, such as e.g. trialkoxy-silyl-propyl-tetrasulfane, or at least one vinylsilane and at least one bis-silyl-aminosilane or at least one bis-silyl-polysulfur-silane and/or at least one bis-silyl-aminosilane or at least one aminosilane and at least one multi-silyl-functional silane. Those silanes/siloxanes which have a chain length in the range from 2 to 5 C atoms and contain a functional group which is suitable for reaction with polymers are preferred in particular.

The aqueous composition preferably contains at least one silane chosen from the group consisting of

glycidoxyalkyltrialkoxysilane,
methacryloxyalkyltrialkoxysilane,
(trialkoxysilyl)alkyl-succinic acid-silane,
aminoalkylaminoalkylalkyldialkoxysilane,
(epoxycycloalkyl)alkyltrialkoxysilane,
bis-(trialkoxysilylalkyl)amine,
bis-(trialkoxysilyl)ethane,
(epoxyalkyl)trialkoxysilane,
aminoalkyltrialkoxysilane,
ureidoalkyltrialkoxysilane,
N-(trialkoxysilylalkyl)alkylenediamine,
N-(aminoalkyl)aminoalkyltrialkoxysilane,
N-(trialkoxysilylalkyl)dialkylenetriamine,
poly(aminoalkyl)alkyldialkoxysilane,
tris(trialkoxysilyl)alkyl isocyanurate,
ureidoalkyltrialkoxysilane and
acetoxysilane.

The aqueous composition preferably contains at least one silane chosen from the group consisting of

- 5 3-glycidoxypropyltriethoxysilane,
 3-glycidoxypropyltrimethoxysilane,
 3-methacryloxypropyltriethoxysilane,
 3-methacryloxypropyltrimethoxysilane,
 3-(triethoxysilyl)propyl-succinic acid-silane,
 aminoethylaminopropylmethyldiethoxysilane,
10 aminoethylaminopropylmethyldimethoxysilane,
 beta-(3,4-epoxycyclohexyl)ethyltriethoxysilane,
 beta-(3,4-epoxycyclohexyl)ethyltrimethoxysilane,
 beta-(3,4-epoxycyclohexyl)methyltriethoxysilane,
 beta-(3,4-epoxycyclohexyl)methyltrimethoxysilane,
15 gamma-(3,4-epoxycyclohexyl)propyltriethoxysilane,
 gamma-(3,4-epoxycyclohexyl)propyltrimethoxysilane,
 bis(triethoxysilylpropyl)amine,
 bis(trimethoxysilylpropyl)amine,
 (3,4-epoxybutyl)triethoxysilane,
20 (3,4-epoxybutyl)trimethoxysilane,
 gamma-aminopropyltriethoxysilane,
 gamma-aminopropyltrimethoxysilane,
 gamma-ureidopropyltrialkoxysilane,
 N-(3-(trimethoxysilyl)propyl)ethylenediamine,
25 N-beta-(aminoethyl)-gamma-aminopropyltriethoxy-
 silane,
 N-beta-(aminoethyl)-gamma-aminopropyltrimethoxy-
 silane,
 N-(gamma-triethoxysilylpropyl)diethylenetriamine,
30 N-(gamma-trimethoxysilylpropyl)diethylenetriamine,
 N-(gamma-triethoxysilylpropyl)dimethylenetriamine,
 N-(gamma-trimethoxysilylpropyl)dimethylenetriamine,
 poly(aminoalkyl)ethyldialkoxysilane,
 poly(aminoalkyl)methyldialkoxysilane,
35 tris(3-(triethoxysilyl)propyl) isocyanurate,
 tris(3-(trimethoxysilyl)propyl) isocyanurate and
 vinyltriacetoxysilane.

The silanes contained in the aqueous composition (concentrate or bath) are monomers, oligomers, polymers, copolymers or/and reaction products with further components on the basis of hydrolysis reactions, condensation reactions or/and further reactions. The reactions take place above all in the solution, during drying or optionally curing of the coating. In the context of this Application, the term "silane" is used here for silanes, silanols, siloxanes, polysiloxanes and reaction products and derivatives thereof, which are often "silane" mixtures. Because of the often very complex chemical reactions which occur here, and the very expensive analyses and working, the particular further silanes or other reaction products cannot be described.

Instead of a content of at least one fluorine-free silane in the content of silanes, however, this content may contain only fluorine-containing silanes, or at least, instead of fluorine-free silanes, at least one fluorine-containing silane.

The aqueous composition preferably then contains at least one silane chosen from the fluorine-containing silanes: from in each case at least one acyloxysilane, one alkoxysilane, one silane having at least one amino group, such as an aminoalkylsilane, one silane having at least one succinic acid group or/and succinic acid anhydride group, one bis-silyl-silane, a silane having at least one epoxide group, such as a glycidoxysilane, one (meth)acrylato-silane, one multi-silyl-silane, one ureidosilane, one vinylsilane or/and at least one silanol or/and at least one siloxane or polysiloxane of a composition which corresponds chemically to the abovementioned silanes, which in each case contains at least one group having one or having at least one fluorine atom.

In particular, the aqueous composition then contains at least one fluoroalkoxyalkylsilane, at least one silane having 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12 or 13 fluorine atoms per silane, at least one perfluorinated silane, at least one mono-fluorosilane, at least one fluorosilane based on ethoxysilane or/and based on methoxysilane or/and at least one fluorosilane having at least one functional group, such e.g. an amino group, in particular as a cocondensate, such as e.g.

10 a fluoroalkyldialkoxysilane,
a fluoroaminoalkylpropyltrialkoxysilane,
a fluoromethanesulfonate,
a fluoropropylalkyldialkoxysilane,
a triphenylfluorosilane, a trialkoxyfluorosilane,
15 a trialkylfluorosilane or/and
a tridecafluorooctyltrialkoxysilane.

The composition particularly preferably then contains at least one fluorine-containing silane which contains at least two amino groups and at least one optionally fluorinated ethyl or/and at least one optionally fluorinated methyl group.

20

The content of the at least one silane, including the reaction products formed therefrom, in the aqueous composition is preferably 0.1 to 80 g/l, in particular 0.2 to 50 g/l, particularly preferably 0.3 to 35 g/l, very particularly preferably 0.5 to 20 g/l, above all 1 to 10 g/l.

25

30 Preferably, the bath compositions which have a relatively low or high content of film-forming agent contain the silanes, including the reaction products optionally formed therefrom with other components, in a content in the range from 0.01 to 10 wt.%, particularly preferably in the range from 0.05 to 7 wt.%, very particularly preferably in the range from 0.1 to 5 wt.%, above all in the range from 0.2 to 4 wt.%, in particular

35

of about 0.4, 0.6, 0.8, 1.0, 1.1, 1.2, 1.3, 1.4, 1.5,
1.6, 1.7, 1.8, 1.9, 2.0, 2.1, 2.2, 2.4, 2.6, 2.8, 3.0,
3.2, 3.4, 3.6 or 3.8 wt.%, and the at least one chelate,
including the reaction products optionally formed
5 therefrom, in the range from 0.01 to 10 wt.%,
particularly preferably in the range from 0.05 to 7
wt.%, very particularly preferably in the range from 0.1
to 5 wt.%, above all in the range from 0.2 to 4 wt.%, in
particular of about 0.3, 0.4, 0.5, 0.6, 0.7, 0.8, 0.9,
10 1.0, 1.1, 1.2, 1.3, 1.4, 1.6, 1.8, 2.0, 2.2, 2.4, 2.6,
2.8, 3.0, 3.2, 3.4, 3.6 or 3.8 wt.%.

The content of the at least one metal chelate b),
optionally including the reaction products formed
15 therefrom, in the aqueous composition is preferably 0.05
to 80 g/l, in particular 0.1 to 50 g/l.

The at least one metal chelate is preferably chosen from
chelate complexes based on acetylacetonates,
20 acetoacetates, acetates, alkylenediamines, amines,
lactates, carboxylic acids, citrates or/and glycols.

The at least one metal chelate is preferably based on
25 acetylacetonate,
alkali metal lactate,
alkanolamine,
alkyl acetoacetate,
alkylenediamine tetraacetate,
30 ammonium lactate,
citrate,
dialkyl citrate,
dialkyl ester-citrate,
dialkylenetriamine,
35 diisoalkoxybisalkyl acetoacetate,
diisopropoxybisalkyl acetoacetate,
di-n-alkoxy-bisalkyl acetoacetate,
hydroxyalkylenediamine triacetate,

trialkanolamine or/and
trialkylenetetramine.

These metal chelates serve in particular to stabilize
5 the organometallic compound in water and to bond to the
metallic surface or to the lacquer or to a corresponding
coating applied. They are particularly suitable if they
have only a low reactivity in the aqueous composition
and if they are at least partly decomposed within the
10 process conditions used and the metal ions for the
bonding or/and chemical reaction are liberated. If they
are too reactive, the organometallic compounds react
prematurely with other chemical compounds, such as
silanes. Preferably, the chelates are hydrophilic,
15 stable to hydrolysis, stable to water or/and form stable
hydrolysates. Preferably, a silane or a chelate is
chosen which is compatible with water and moreover with
the organic film-forming agent chosen and which has the
same properties as mentioned before for the silane or
20 chelate.

Preferably, the amounts ratio of a) to b), in each case
including the reaction products formed therefrom, is in
the range from 0.1 : 1 to 10 : 1, particularly
25 preferably in the amounts ratio of 0.2 : 1 to 8 : 1,
very particularly preferably in the amounts ratio of
0.3 : 1 to 7 : 1, in particular about 0.4 : 1, 0.6 : 1,
0.8 : 1, 1 : 1, 1.2 : 1, 1.6 : 1, 2 : 1, 3 : 1, 4 : 1, 5
: 1 or 6 : 1.

30 Particularly preferably, in each case amounts of
silane(s) and chelate(s), in each case including the
reaction products formed therefrom, are contained
independently of one another in the range from 0.05 to
35 5 wt.%, based on the wet film, very particularly
preferably in each case independently of one another
amounts of 0.08 to 4 wt.%, in particular about in each

case independently of one another amounts of 0.1, 0.2, 0.3, 0.5, 0.8, 1, 1.5, 2, 2.5, 3 or 3.5 wt. %.

- Particularly preferably, in each case amounts of silane(s) and chelate(s), in each case including the reaction products formed therefrom, are contained independently of one another in the range from 0.2 to 15 wt. %, based on the dry substance content, very particularly preferably in each case independently of one another amounts of 0.3 to 11 wt. %, in particular about in each case independently of one another amounts of 0.5, 0.8, 1, 1.5, 2, 2.5, 3, 3.5, 4, 4.5, 5, 5.5, 6, 6.5, 7, 7.5, 8, 8.5, 9, 9.5, 10 or 10.5 wt. %.
- 15 In particular, in the compositions having a comparatively high film-forming agent content, an amounts ratio of components $[a) + b)] : c)$, in each case including the reaction products formed therefrom and based on the wet film, of 1 : 70 or of 2 : 70 to 20 : 70 is particularly preferred, very particularly preferably in an amounts ratio of 3.5 : 70 to 17 : 70, in particular about 5 : 70, 6 : 70, 7 : 70, 8 : 70, 9 : 70, 10 : 70, 11 : 70, 12 : 70 and 14 : 70. It may be preferable here for either component a) to component b), or vice versa, to assume values of the content which are higher by the factor 1.2 to 4 than that of the other component. An amounts ratio of components $[a) + b)] : c)$, in each case including the reaction products formed therefrom and based on the solids content, of 2 : 70 to 20 : 70 is particularly preferred, very particularly preferably in an amounts ratio of 3.5 : 70 to 17 : 70, in particular about 5 : 70, 6 : 70, 7 : 70, 8 : 70, 9 : 70, 10 : 70, 11 : 70, 12 : 70 and 14 : 70.
- 35 In particular, in the compositions having a relatively low film-forming agent content, however, the amounts ratio of components $[a) + b)] : c)$, in each case including the reaction products formed therefrom and based on the

wet film, can be particularly preferably in the range from $\geq 0.2 : 7$ and up to $20 : 7$, very particularly preferably in the amounts ratio of $\geq 0.5 : 7$ and up to $12 : 7$ or of $\geq 1 : 7$ and up to $8 : 7$, in particular about $0.4 : 7$, $0.6 : 7$, $0.8 : 7$, $1.2 : 7$, $1.5 : 7$, $2 : 7$, $3 : 7$, $4 : 7$, $5 : 7$, $6 : 7$, $7 : 7$, $9 : 7$, $10 : 7$, $11 : 7$, $13 : 7$, $14 : 7$ and $16 : 7$. It may be preferable here for either component a) to component b) or vice versa to assume content values which are higher than the other component by a factor of 1.2 to 4.

The contents of component a), including the reaction products formed therefrom and based on the solids content, are particularly preferably in the range from 0.4 to 10 wt.%, very particularly preferably in the range from 0.8 to 8 wt.%, in particular about 1.2, 1.5, 1.8, 2.1, 2.4, 2.7, 3, 3.3, 3.6, 3.9, 4.2, 4.5, 4.8, 5.1, 5.5, 6, 6.5, 7 or 7.5 wt.%.
15

The contents of component b), including the reaction products formed therefrom and based on the solids content, are particularly preferably in the range from 0.3 to 10 wt.%, very particularly preferably in the range from 0.8 to 8 wt.%, in particular about 1.2, 1.5, 1.8, 2.1, 2.4, 2.7, 3, 3.3, 3.6, 3.9, 4.2, 4.5, 4.8, 5.1, 5.5, 6, 6.5, 7 or 7.5 wt.%.
20
25

In particular, in the compositions having a comparatively high film-forming agent content, the contents of component c), based on the solids content, are particularly preferably in the range from 10 to 95 wt.%, very particularly preferably in the range from 30 to 90 wt.%, in particular about 35, 40, 45, 50, 55, 60, 63, 66, 69, 72, 75, 78, 81, 84 or 87 wt.%.
30

In particular, in the compositions having a comparatively high film-forming agent content, the contents of component d) - at least one long-chain
35

alcohol - based on the solids content, are particularly preferably in the range from 0.01 to 2 wt.%, very particularly preferably in the range from 0.1 to 1 wt.%, in particular about 0.12, 0.15, 0.18, 0.21, 0.24, 0.27,
5 0.30, 0.33, 0.36, 0.39, 0.42, 0.45, 0.48, 0.51, 0.55, 0.60, 0.65, 0.7, 0.75, 0.8, 0.9 or 0.95 wt.%.

The aqueous composition, which can serve as a bath composition or/and as a concentrate, preferably contains
10 the organic film-forming agent c) in a content of 0.1 to 980 g/l, particularly preferably in a range from 2 to 600 g/l, very particularly preferably 50 to 550 g/l, in particular 150 to 450 g/l. Preferably, 2 to 100 parts of the organic film-forming agent are added,
15 particularly preferably 10 to 60 parts, very particularly preferably 15 to 45 parts, per 100 parts by weight of water. In particular, in the case of the compositions having a relatively low film-forming agent content, however, the aqueous composition, which can
20 serve as a bath composition or/and as a concentrate, preferably contains the organic film-forming agent c) in a content of ≥ 0.01 and up to 98 g/l, particularly preferably in a range from ≥ 0.1 and up to 60 g/l, very particularly preferably from ≥ 0.5 and up to 50 g/l, in
25 particular from ≥ 2 and up to 45 g/l.

Under certain circumstances, the highest contents of organic film-forming agent can occur in particular in UV-curing systems without or in systems with only low
30 volatile contents, such as organic solvents or/and residual monomers. Coatings which are predominantly or solely film-formed during drying or optionally cured in part thermo-physically are particularly preferred for the process according to the invention. In the context
35 of this Application, the term copolymers preferably also includes block copolymers and graft copolymers.

The organic film-forming agent preferably contains at least a proportion of at least one polymer or/and at least one copolymer with an acid number in the range from 3 to 120, particularly preferably in the range from 3 to 80, very particularly preferably in the range from 4 to 60.

The organic film-forming agent preferably contains at least one proportion of at least one polymer or/and at least one copolymer with a minimum film-forming temperature MFT in the range from - 10 to + 99°C, particularly preferably in the range from 0 to 90°C, in particular from 5°C; it is very particularly advantageous if the organic film-forming agent contains at least two in particular thermoplastic polymers or/and copolymers at least in the initial stage - since the thermoplastic constituents can at least partly lose or reduce their thermoplastic properties during the further treatment and reaction - which - where a minimum film-forming temperature can be stated - have a minimum film-forming temperature in the range from 5 to 95°C, in particular of at least 10°C, where at least one of these polymers or/and copolymers, compared with at least a second of these polymers or/and copolymers, A) has a minimum film-forming temperature which differs from that of the other component by at least 20°C, B) has a glass transition temperature which differs from that of the other component by at least 20°C, or/and C) has a melting point which differs from that of the other component by at least 20°C. Preferably, one of these at least two components has a film-forming temperature in the range from 10 to 40°C and the other a film-forming temperature in the range from 45 to 85°C. Long-chain alcohols can help here to lower the glass transition temperatures temporarily and optionally also to match them somewhat to one another. After application, the long-chain alcohols can escape and then leave behind a film of higher glass transition temperature than during the application. These dried films are then not too

flexible and too tacky. The glass transition temperatures and the melting points of these synthetic resins are often about in the region of the film-forming temperature, that is to say usually in the range from
5 0 to 110°C.

In another preferred embodiment, a mixture of organic film-forming agents in which at least some of the film-forming agents have a glass transition temperature T_g of
10 substantially the same or/and a similar T_g can be employed. It is particularly preferable here for at least some of the organic film-forming agents to have a glass transition temperature T_g in the range from 10 to 70°C, very particularly preferably in the range from 15
15 to 65°C, in particular in the range from 20 to 60°C. The organic film-forming agent then preferably contains at least a proportion of at least one polymer or/and at least one copolymer having a minimum film-forming temperature MFT in the range from - 10 to + 99°C,
20 particularly preferably in the range from 0 to 90°C, in particular from 5°C or from 10°C. It is particularly preferable here for at least two, if not all, of the organic film-forming agents to have a minimum film-forming temperature in one of these temperature ranges -
25 if a minimum film-forming temperature can be stated.

It is particularly advantageous if all the organic film-forming agents form a film during drying. It is particularly preferable if synthetic resins which have
30 thermoplastic properties to the extent of at least 80 wt.%, in particular to the extent of at least 90 wt.%, are added to the aqueous composition.

The organic film-forming agent is preferably formed from
35 at least one component in the form of in each case at least one solution, dispersion, emulsion, microemulsion and/or suspension which is added to the aqueous composition. The term dispersion here also includes the

sub-terms emulsion, solution, microemulsion and suspension.

The acid number of the synthetic resins is preferably 3 to 100, particularly preferably 3 to 60 or 4 to 50. In particular, copolymers with an acid number in the range from 3 to 50 are added to the aqueous composition. The components of the organic film-forming agent which are to be added are optionally already partly neutralized.

10 The organic film-forming agent can preferably contain a proportion of at least one copolymer with an acid number in the range from 3 to 80, in particular to the extent of at least 50 wt.% of the synthetic resins added. In a high range of the acid number it is usually not

15 necessary to stabilize a film-forming agent cationically, anionically or/and sterically. At a low acid number, however, such a stabilization is often necessary. It is then advantageous to employ already (partly) stabilized synthetic resins or mixtures

20 thereof.

The aqueous composition preferably contains at least one synthetic resin, such as organic polymer, copolymer or/and mixture thereof, in particular a synthetic resin

25 based on acrylate, ethylene, polyester, polyurethane, silicone polyester, epoxide, phenol, styrene, melamine-formaldehyde, urea-formaldehyde or/and vinyl. The organic film-forming agent can preferably be a synthetic resin mixture of at least one polymer or/and at least

30 one copolymer, which in each case independently of one another contains a proportion of synthetic resin based on acrylate, epoxide, ethylene, urea-formaldehyde, phenol, polyester, polyurethane, styrene, styrene-butadiene or/and vinyl. This can also be here a

35 cationically, anionically or/and sterically stabilized synthetic resin or polymer or/and dispersion thereof or even solution thereof. The term acrylate in the context of this Application includes acrylic acid ester,

Application includes acrylic acid ester, polyacrylic acid, methacrylic acid ester and methacrylate.

The organic film-forming agent can preferably contain at
5 least one component based on

acrylic-polyester-polyurethane copolymer,
acrylic-polyester-polyurethane-styrene
copolymer,
10 acrylic acid ester,
acrylic acid ester-methacrylic acid ester,
optionally with free acids or/and
acrylonitrile,
ethylene-acrylic mixture,
15 ethylene-acrylic copolymer,
ethylene-acrylic-polyester copolymer,
ethylene-acrylic-polyurethane copolymer,
ethylene-acrylic-polyester-polyurethane
copolymer
20 ethylene-acrylic-polyester-polyurethane-
styrene copolymer,
ethylene-acrylic-styrene copolymer
polyester resins with free carboxyl groups
combined with melamine-formaldehyde resins,
25 a synthetic resin mixture or/and copolymer
based on acrylate and styrene,
a synthetic resin mixture or/and copolymer
based on styrene-butadiene,
a synthetic resin mixture or/and copolymer of
30 acrylate and epoxide,
based on an acrylic-modified polyester
containing carboxyl groups together with
melamine-formaldehyde and ethylene-acrylic
copolymer,
35 polycarbonate-polyurethane,
polyester-polyurethane,
styrene,
styrene-vinyl acetate,

vinyl acetate,
vinyl ester or/and
vinyl ether.

5 However, the organic film-forming agent can also preferably contain as the synthetic resin a content of organic polymer, copolymer or/and mixtures thereof based on polyethyleneimine, polyvinyl alcohol,
polyvinylphenol, polyvinylpyrrolidone or/and
10 polyaspartic acid, in particular copolymers with a phosphorus-containing vinyl compound. A conductive polymer is preferably also added to the aqueous composition.

15 A synthetic resin based on acrylate or based on ethylene-acrylic acid with a melting point in the range from 60 to 95°C or a synthetic resin with a melting point in the range from 20 to 160°C, in particular in the range from 60 to 120°C, is very particularly
20 preferred.

Preferably, at least 30 wt.% of the organic film-forming agent added can contain thermoplastic resins from which films can be formed, particularly preferably to the
25 extent of at least 50 wt.%, very particularly preferably to the extent of at least 70 wt.%, above all to the extent of at least 90 or to the extent of at least 95 wt.%. In addition, the organic film-forming agent can also contain contents, in certain circumstances
30 residual contents, of in each case at least one monomer, oligomer, emulsifier, further additive for dispersions, one curing agent, photoinitiator or/and one cationically polymerisable substance. The content of monomer, oligomer, emulsifier and further additive for
35 dispersions is usually less than 5 wt.%, often less than 2 wt.%, possibly less than 1 wt.%. The composition of curing agents and correspondingly crosslinkable

2004215696 22 Apr 2010

substances then optionally also added and the corresponding measures for this are known in principle.

5 The molecular weights of the synthetic resins added can preferably be in the range of at least 1,000 u, particularly preferably of at least 5,000 u, very particularly preferably from 20,000 to 200,000 u. The individual thermoplastic components of the organic film-forming agent which are added to the aqueous composition preferably have molecular weights
10 in the range from 20,000 to 200,000 u, in particular in the range from 50,000 to 150,000 u. The number of monomeric units per molecule for polymeric materials is defined as "u".

15 The organic film-forming agent can preferably contain at least 40 wt.% of high molecular weight polymers, particularly preferably at least 55 wt.%, very particularly preferably at least 70 wt.%, above all at least 85 wt.%, in particular at least 95 wt.%. In particular, if at least
20 85 wt.% of the organic film-forming agent comprises high-molecular-weight polymers, it is usually not necessary to add curing agents, such as isocyanates, or photoinitiators, such as benzophenones, for thermal or free-radical crosslinking, and correspondingly crosslinkable synthetic
25 resins in order to achieve the outstanding properties of the coating according to the invention, since it is then possible to form, by the film formation, a closed, solid, high-quality film without carrying out crosslinking.

30 During film formation, which takes place in particular during drying, the organic microparticles add on to one another and compact to form a closed pore-free film, if the choice of polymers and film-forming auxiliary is suitable and the process is operated under suitable conditions. The
35 expert is familiar in principle with these classes of substance and working conditions. The fact that this film can have exceptionally high-quality

properties, in spite of such a low layer thickness, preferably in the range from 0.5 to 3 μm , is demonstrated by the embodiment examples. To the knowledge of the Applicant, no substantially organic, chromate-free coating with a layer thickness of less than 4 μm dry film thickness has hitherto been disclosed for the coating on metallic strips of such high lacquer adhesion and corrosion resistance which predominantly contains polymers which have undergone film formation.

5 The coating according to the invention is at least equivalent to a chromate-containing organic coating.

10

The final drying of such films can take many days, while substantial drying can already be completed in a few seconds. Curing here can, under certain circumstances, take several weeks until the final drying and curing state is achieved if no thermal or free-radical crosslinking occurs here. If required, the curing can additionally be accelerated or intensified, as a result of crosslinking, by irradiation, e.g. with UV radiation, or by heating, or/and also to a small extent by addition of and reaction with e.g. compounds containing free NCO groups with the hydroxyl groups of the polymers containing hydroxyl groups.

15

20

25 The coating is preferably largely or completely cured by drying and film formation. Alternatively, however, the coating can be hardened or cured partly by drying and film formation and partly by actinic radiation, cationic polymerization or/and thermal crosslinking. In this case, at least one photoinitiator or/and at least one curing agent and correspondingly crosslinkable resin are optionally added to the aqueous composition.

30

35 The pH of the organic film-forming agent in an aqueous formulation, without addition of further compounds, is usually in the range from 0.5 to 12. The pH of the aqueous composition which contains predominantly

synthetic resins and also silane and chelate as solids contents is preferably in the range from 1 to 6 or 6 to 10.5 - depending on whether the procedure takes place in the acid or rather basic range, particularly preferably in the range from 6.5 to 9.5, very particularly preferably in the range from 7 to 9.2.

In one embodiment variant, the organic film-forming agent preferably contains only water-soluble synthetic resins, in particular those which are stable in solutions with pH values of ≤ 9 , or/and the organic film-forming agent contains at least one synthetic resin which contains hydroxyl groups. However, if the pH should have fallen due to storage of the synthetic resins or mixtures, it may be helpful to bring the pH, especially that of the dispersion which is otherwise ready-to-use, back into a more alkaline range e.g. by addition of sodium hydroxide solution. The organic film-forming agent can also be of a composition such that it contains - optionally only - water-soluble synthetic resin, in particular one which is stable in solutions with pH values of ≤ 5 .

Preferably, the acid groups of the synthetic resins are or/and will be neutralized with ammonia, with amines or alkanolamines, such as e.g. morpholine, dimethylethanolamine, diethylethanolamine or triethanolamine, or/and with alkali metal compounds, such as e.g. sodium hydroxide. These additives then act as a stabilizer.

Film formation is understood as meaning film formation from a material with a high organic content, such as a polymer dispersion, during which above all polymer particles are converted into a uniform film, preferably at room temperature or slightly elevated temperature. Fusion of the comparatively large polymer particles is often referred to here. Film formation takes place here from an aqueous medium during drying and optionally with

plasticizing of the polymer particles by the remaining film-forming auxiliary. The film formation can be improved by the use of thermoplastic polymers or copolymers or/and by addition of substances which serve as temporary plasticizers. Film-forming auxiliaries act as specific solvents which soften the surface of the polymer particles and thus render possible fusion thereof. It is advantageous here if these plasticizers on the one hand remain in the aqueous composition for a sufficiently long period of time to be able to act on the polymer particles for a long period of time and then evaporate and thus escape from the film. It is furthermore advantageous if a residual water content is also present for a sufficiently long period of time during the drying process. In a suitable film formation, a transparent film is formed, but no milky-white or even pulverulent film, which is an indication of an impaired film formation. For film formation which is as perfect as possible, the temperature of the wet film applied to a surface must be above the minimum film temperature (MFT), since only then are the polymer particles soft enough to coalesce. It is particularly advantageous here if these plasticizers do not or virtually do not modify the pH of the aqueous composition. The choice of suitable film-forming auxiliary is not easy here, a mixture of at least two film-forming auxiliaries often being necessary. Film-forming auxiliaries which are particularly advantageous are so-called long-chain alcohols, in particular those having 4 to 20 C atoms, such as a butanediol, a butyl glycol, a butyl diglycol, an ethylene glycol ether, such as ethylene glycol monobutyl ether, ethylene glycol monoethyl ether, ethylene glycol monomethyl ether, ethyl glycol propyl ether, ethylene glycol hexyl ether, diethylene glycol methyl ether, diethylene glycol ethyl ether, diethylene glycol butyl ether, diethylene glycol hexyl ether, or a polypropylene glycol ether, such as propylene glycol monomethyl ether, dipropylene glycol

monomethyl ether, tripropylene glycol monomethyl ether,
propylene glycol monobutyl ether, dipropylene glycol
monobutyl ether, tripropylene glycol monobutyl ether,
propylene glycol monopropyl ether, dipropylene glycol
5 monopropyl ether, tripropylene glycol monopropyl ether,
propylene glycol phenyl ether, trimethylpentanediol
diisobutyrate, a polytetrahydrofuran, a polyether-polyol
or/and a polyester-polyol. In contrast to film
formation, temperatures of at least 120°C are
10 conventionally required for crosslinking for
thermosetting organic coatings.

In the processes according to the invention relating to
compositions which contain predominantly chelate and
15 silane or predominantly synthetic resin and in addition
chelate and silane, the aqueous composition can contain
at least one component e) chosen from the group
consisting of

- 20 e₁) at least one inorganic compound in particle form
with an average particle diameter, measured on a
scanning electron microscope, in the range from
0.005 to 0.3 µm diameter,
- e₂) at least one lubricant,
- 25 e₃) at least one organic corrosion inhibitor,
- e₄) at least one anticorrosion pigment,
- e₅) at least one agent for neutralization or/and for
steric stabilization of the synthetic resins,
- e₆) at least one organic solvent,
- 30 e₇) at least one siloxane and
- e₈) at least one chromium(VI) compound.

Preferably, a finely divided powder, a dispersion or a
suspension, such as e.g. a carbonate, oxide, silicate or
35 sulfate, in particular colloidal or/and amorphous
particles, is added as the inorganic compound in
particle form e₁). Particles based on at least one
compound of aluminium, barium, cerium, calcium,

lanthanum, silicon, titanium, yttrium, zinc or/and zirconium are preferably added as the inorganic compound in particle form. Particles based on aluminium oxide, barium sulfate, cerium dioxide, silicon dioxide, silicate, titanium oxide, yttrium oxide, zinc oxide or/and zirconium oxide are preferably added as the inorganic compound in particle form.

Preferably, particles with an average particle size in the range from 6 to 200 nm are used as the inorganic compound in particle form, particularly preferably in the range from 7 to 150 nm, very particularly preferably in the range from 8 to 90 nm, even more preferably in the range from 8 to 60 nm, above all preferably in the range from 10 to 25 nm. These particles can also be in the form of a gel or sol. The particles can be stabilized e.g. under alkaline conditions, in order to achieve a better dispersion. An addition of boron for dispersing of the inorganic compound in particle form was not necessary and also has not been used in the examples. It is preferable for larger particles to have a rather platelet-shaped or longitudinal grain form.

The aqueous composition, which can serve as a bath composition or/and as a concentrate, preferably contains the at least one inorganic compound in particle form in a content of 0.1 to 500 g/l, particularly preferably in a range from 10 to 200 g/l, very particularly preferably 30 to 100 g/l, above all in the range from 3 to 60 g/l. Preferably, 0.1 to 50 parts of the at least one inorganic compound in particle form, particularly preferably 0.5 to 20 parts, very particularly preferably 0.8 to 10 parts, are added per 100 parts by weight of water. Among the inorganic compounds in particle form, those which maintain the transparency of the coating according to the invention, that is to say are colourless or white, such as e.g. aluminium oxide, barium sulfate, silicate, silicon dioxide, colloidal

silicon dioxide, zinc oxide or/and zirconium oxide, are preferred in particular in order to maintain the visual character of the metallic surface visibly as far as possible without falsification.

5

Particles with a relatively high or high electrical conductivity, which are optionally also added, such as those of iron oxide, iron phosphide, tungsten, zinc and zinc alloy, can also be chosen for use for welding so that they have an average particle size such that they optionally project somewhat more out of the layer according to the invention.

10

The ratio of the contents of organic film-forming agent to contents of inorganic compounds in particle form in the aqueous composition can vary within wide ranges; in particular, it can be $\leq 25 : 1$. Preferably, this ratio is in a range from $\geq 0.05 : 1$ and up to $15 : 1$, particularly preferably in a range from $\geq 0.2 : 1$ and up to $12 : 1$, very particularly preferably in a range from $\geq 0.5 : 1$ and up to $10 : 1$, in particular in a range from $\geq 1 : 1$ and up to $8 : 1$.

15

20

The ratio of the contents of at least one silane to contents of inorganic compounds in particle form in the aqueous composition can likewise vary within wide limits; in particular, it can be $\leq 25 : 1$. This ratio is preferably in a range from $\geq 0.01 : 1$ and up to $15 : 1$, particularly preferably in a range from $\geq 0.05 : 1$ and up to $8 : 1$, very particularly preferably in a range from $\geq 0.08 : 1$ and up to $4 : 1$, in particular in a range from $\geq 0.1 : 1$ and up to $2 : 1$.

25

30

Preferably, at least one wax chosen from the group consisting of paraffins, polyethylenes and polypropylenes is used as the lubricant e_2), in particular an oxidized wax, the content of waxes in the aqueous composition preferably being in the range from

35

0.01 to 5 wt.%, particularly preferably in the range from 0.02 to 3.5 wt.%, very particularly preferably in the range from 0.05 to 2 wt.%. Preferably, the melting point of the wax employed as a lubricant is in the range
5 from 40 to 165°C, particularly preferably in the range from 50 to 160°C, in particular in the range from 120 to 150°C. It is particularly advantageous to add, in addition to a lubricant with a melting point in the range from 120 to 165°C, a lubricant with a melting
10 point in the range from 45 to 95°C or with a glass transition temperature in the range from -20 to +60°C, in particular in amounts of 2 to 30 wt.%, preferably 5 to 20 wt.% of the total solids content. However, the latter can also advantageously be employed by itself.

15 It is particularly advantageous to employ the wax as an aqueous or as a cationically, anionically or/and sterically stabilized dispersion, because it can then easily be kept in homogeneous distribution in the
20 aqueous composition. The aqueous composition preferably contains the at least one lubricant, which optionally can also simultaneously be a shaping agent, in a content in the range from 0.1 to 25 g/l and particularly preferably in a content in the range from 1 to 15 g/l.
25 However, a wax content is usually only advantageous if the coating according to the invention is a treatment layer, since the wax content in a pretreatment layer can be a disadvantage during lacquering. A lubricant or/and shaping agent can be added to reduce the coefficient of
30 friction of the coating, in particular during shaping. Paraffin, polyethylene and oxidized polyethylene, inter alia, are recommended for this.

Preferably, at least one wax together with a polymer
35 mixture containing ethylene and acrylic acid or/and a copolymer, such as ethylene/acrylic-acid copolymer, is employed as the lubricant, optionally at least one further synthetic resin being added, in particular in an

amounts ratio of wax to the copolymer containing ethylene and acrylic acid of 0.02 : 1 to 2 : 1, particularly preferably 0.05 : 1 to 1 : 1, very particularly preferably 0.1 : 1 to 0.5 : 1.

5

The ratio of the contents of organic film-forming agent to contents of lubricant in the aqueous composition (bath composition) can vary within wide ranges; in particular it can be $\geq 2 : 1$. Preferably, this ratio is
10 in a range from 3 : 1 to 50 : 1, particularly preferably in a range from 10 : 1 to 20 : 1.

The aqueous composition preferably contains at least one organic corrosion inhibitor e_3), in particular based on
15 amine(s), preferably at least one alkanolamine - preferably a long-chain alkanolamine, at least one TPA-amine complex, such as acid adduct-4-oxo-4-p-tolyl butyrate-4-ethylmorpholine, at least one zinc salt of aminocarboxylate, of 5-nitro-isophthalic acid or of
20 cyanic acid, at least one polymeric ammonium salt with fatty acid, at least one metal salt of a sulfonic acid, such as dodecyl-naphthalenesulfonic acid, at least one amino and transition metal complex of toluenepropionic acid, 2-mercapto-benzothiazolyl-succinic acid or at
25 least one of its amino salts, at least one conductive polymer or/and at least one thiol, it being possible for the content of organic corrosion inhibitors in the aqueous composition preferably to be in the range from 0.01 to 5 wt.%, particularly preferably in the range
30 from 0.02 to 3 wt.%, very particularly preferably in the range from 0.05 to 1.5 wt.%.

The at least one organic corrosion inhibitor is preferably not readily volatile at room temperature. It
35 may furthermore be advantageous if it is readily soluble in water or/and readily dispersible in water, in particular to the extent of more than 20 g/l. Compounds which are particularly preferred are, inter alia,

alkylaminoethanols, such as dimethylaminoethanol, and complexes based on a TPA-amine, such as N-ethylmorpholine complex with 4-methyl- γ -oxo-benzenebutanoic acid. This corrosion inhibitor can be added in order to effect or to intensify still further a relatively powerful corrosion inhibition. The addition of the at least one organic corrosion inhibitor is usually necessary only for metallic surfaces which are very difficult to protect, such as bright steel surfaces, because of the very high corrosion-inhibiting action of the compositions according to the invention. It is advantageous if non-galvanized steel surfaces, in particular cold-rolled steel (CRS), are to be coated.

The ratio of the contents of organic film-forming agent to contents of at least one organic corrosion inhibitor in the aqueous composition (bath composition) can vary within wide ranges; in particular it can be $\leq 500 : 1$. This ratio is preferably in a range from $5 : 1$ to $400 : 1$, particularly preferably in a range from $10 : 1$ to $100 : 1$.

The aqueous composition preferably contains 0.1 to 80 g/l of the at least one anticorrosion pigment e_4). These include, in particular, various silicates, based on aluminium silicates, alumo-silicates, alumo-alkaline earth metal silicates and alkaline earth metal silicates. The anticorrosion pigments preferably have an average particle diameter, measured on a scanning electron microscope, in the range from 0.01 to $0.5 \mu\text{m}$ diameter, in particular in the range from 0.02 to $0.3 \mu\text{m}$. The various types of anticorrosion pigments are known in principle. However, an addition of at least one of these pigments does not seem to be necessary in principle, but renders alternative embodiment variants possible.

The agents for neutralization and/or steric stabilization of the acid groups of the synthetic resins with an acid number in particular in the range from 5 to 50 e₅) can be, inter alia, slowly volatilizing
5 alkanolamines and hydroxides, such as sodium hydroxide solution and potassium hydroxide solution, but preferably rapidly volatilizing alkanolamines, ammonia and compounds based on morpholine and alkanolamines. They have the effect that the neutralized synthetic
10 resins become water-miscible or, at an acid number from about 150, are also water-soluble.

At least one organic solvent e₆) can optionally also be added in the process according to the invention. At
15 least one water-miscible or/and water-soluble alcohol, one glycol ether or N-methylpyrrolidone or/and water can be used as the organic solvent for the organic polymers, and in the case of the use of a solvent mixture, in particular a mixture of at least one long-chain alcohol,
20 such as e.g. propylene glycol, one ester-alcohol, one glycol ether or/and butanediol with water. Preferably, however, in many cases only water is added, without any organic solvent. If an organic solvent is used, the content thereof is preferably 0.1 to 10 wt.%, in
25 particular 0.25 to 5 wt.%, very particularly preferably 0.4 to 3 wt.%. For strip production it is preferable rather to employ only water and almost no or no organic solvent, possibly apart from small amounts of alcohol.

30 It is furthermore advantageous to add at least one wetting agent e₇) in order to be able to apply the wet film uniformly in the area extent and in the layer thickness as well as densely and without defects. Many wetting agents are suitable in principle for this,
35 preferably acrylates, silanes, polysiloxanes, long-chain alcohols, which reduce the surface tension of the aqueous composition.

The coatings according to the invention can be largely or completely free not only from chromium(VI) compounds but also from chromium(III) compounds without thereby losing quality. Although it is not normally intended in the context of the invention to add environmentally hazardous chromium compounds e₈), such as, in particular, those of Cr⁶⁺, in rare cases of use this can nevertheless be provided at the request of the customer. The aqueous composition, which is preferably free or largely free from chromium(VI) compounds, has only a chromium content of up to 0.05 wt.% on chromium-free metallic surfaces and a chromium content of up to 0.2 wt.% on chromium-containing metallic surfaces; chromium contents occurring in the bath can be dissolved out of the metallic surface by pickling attack, can originate in traces from impurity contents or can arrive carried in from previous baths or from tanks and pipelines. Preferably, no chromium is consciously added to the aqueous composition.

However, the process according to the invention can also advantageously be employed with a content of at least one chromium-containing compound if the corrosion protection is to be retained in a wide range and with a high reliability, in particular on damage to the protective layer which can be caused by mechanical stresses during transportation, storage and assembly of the substrates treated on the substrate surface with the treatment liquid according to the invention. Sodium bichromate, potassium bichromate or/and ammonium bichromate, for example, can then be added. The content of chromium(VI) compounds is then preferably 0.01 to 100 g/l, particularly preferably 0.1 to 30 g/l.

Preferably, the aqueous composition can also contain at least one basic crosslinking agent based on titanium, hafnium or/and zirconium as the cation or/and based on carbonate or ammonium carbonate as the anion, the

content of such crosslinking agents in the aqueous composition preferably being in the range from 0.01 to 3 wt.%, particularly preferably in the range from 0.02 to 1.8 wt.%, very particularly preferably in the range from 0.05 to 1 wt.%.

Preferably, the aqueous composition contains at least one additive, in particular at least one chosen from the group consisting of at least one biocide, at least one defoamer or/and at least one wetting agent.

Preferably, no acids, in particular no inorganic acids or/and organic carboxylic acids, are added to the aqueous composition - under certain circumstances with the exception of the traces of acids contained hidden in the raw materials. In particular, it is free or largely free from inorganic acids or/and organic carboxylic acids, above all free from inorganic acids.

The aqueous composition according to the invention is preferably free from additions of free fluoride, complex fluoride, such as e.g. hexafluorotitanic acid or hexafluorozirconic acid, or/and fluoride bonded in other ways.

Preferably, the aqueous composition is free or largely free from heavy metals. In particular, contents of cadmium, nickel, cobalt or/and copper should be kept extremely low and should not be added. However, for the compositions according to the invention the pickling attack is usually so low that no steel-refining agents, such as e.g. chromium or nickel, can be dissolved out of a steel surface.

Particularly advantageous compositions according to the invention substantially contain, inter alia, at least one copolymer, e.g. based on acrylic-polyester-polyurethane, styrene, styrene-acrylate or/and

- ethylene-acrylate, as a film-forming agent, at least one silane, at least one chelate, at least one film-forming auxiliary based on a long-chain alcohol, at least one inorganic compound in particle form, in particular based on aluminium oxide, aluminium phosphide, iron oxide, iron phosphide, mica, lanthanide oxide(s), e.g. based on cerium oxide, molybdenum sulfide, graphite, carbon black, silicate, silicon dioxide, colloidal silicon dioxide, zinc oxide or/and zirconium oxide, optionally at least one lubricant, such as wax, optionally at least one wetting agent, such as polysiloxanes, optionally at least one organic corrosion inhibitor and optionally further additives, such as, inter alia, a defoamer.
- 15 The metallic surface is preferably in a freshly produced, clean or in a cleaned state. The term "clean metallic surface" here means a non-cleaned metallic, e.g. freshly galvanized surface on which no cleaning is necessary, or a freshly cleaned surface.
- 20 Preferably, the aqueous composition is applied directly to the metallic surface without applying a pretreatment composition beforehand. For some uses it may nevertheless be advantageous to apply at least one pretreatment layer, e.g. based on an alkali metal phosphating, a zinc-containing phosphating, a pretreatment containing rare earths, such as cerium, and/or at least one silane beforehand.
- 25
- 30 To prepare the bath composition from a concentrate primarily by dilution with water or for a topping-up solution for adjusting the bath composition during relatively long operation of a bath, aqueous compositions which contain most or almost all of the constituents of the bath composition but as a rule not the at least one organic compound in particle form, which is preferably kept separately and added separately, are preferably used. Reaction and drying
- 35

accelerators, such as e.g. the morpholine salt of paratoluenesulfonic acid, can also advantageously be added separately. The concentrate and the topping-up solution preferably have a concentration which is concentrated five times to ten times, in respect of the individual constituents, as greatly as the bath composition. In some cases, however, the "concentrate" can also be used directly as the bath composition, optionally after a small dilution by e.g. 5 to 30%.

10

In the process according to the invention, the aqueous composition can preferably be applied to the metallic surface at a temperature in the range from 5 to 50°C, particularly preferably in the range from 10 to 40°C, very particularly preferably in the range from 18 to 25°C, or at 30 to 95°C. In the process according to the invention, the metallic surface can preferably be kept at temperatures in the range from 5 to 60°C during application of the coating, particularly preferably in the range from 10 to 55°C, very particularly preferably in the range from 18 to 25°C, or under certain circumstances also at 50 to 120°C. In the process according to the invention, the coated metallic surface can preferably be dried at a temperature in the range from 20 to 400°C for the circulating air temperature, preferably in the range from 40 to 120°C, or in the range from 140 to 350°C, very particularly preferably at 60 to 100°C or at 160 to 300°C for the PMT (peak metal temperature) - depending on the chemical composition of the organic film-forming agent. The dwell time needed for drying is substantially inversely proportional to the drying temperature: e.g. for strip-like material 1 to 3 s at 100°C or 1 to 20 s at 250°C, depending on the chemical composition of the synthetic resins or polymers, or 30 min at 20°C, while polyester resins with free hydroxyl groups in combination with melamine-formaldehyde resins cannot be dried at temperatures below 120°C. On the other hand, coated shaped

35

components, inter alia depending on the wall thickness, must be dried for significantly longer. Drying equipment based on circulating air, induction, infra-red or/and microwaves are particularly suitable for the drying. In the process according to the invention, the coated strips can preferably be wound up to a coil, optionally after cooling to a temperature in the range from 40 to 70°C.

10 In the process according to the invention, the aqueous composition can preferably be applied by rolling on, flooding, knife-coating on, spraying, misting, brushing or dipping and optionally by subsequent squeezing off with a roller.

15 The layer thickness of the coating according to the invention is preferably in the range from 0.1 to 6 μm , particularly preferably in the range from 0.2 to 5 μm , very particularly preferably in the range from 0.25 to 4 μm , in particular in the range from 0.3 to 2.5 μm .

The dried and optionally also cured film preferably has a pendulum hardness of 30 to 190 s, preferably 50 to 180 s, measured with a König pendulum hardness tester in accordance with DIN 53157. However, in some cases the König pendulum hardness is preferably in the range from 60 to 150 s, particularly preferably in the range from 80 to 120 s. Values of the pendulum hardness in the range from 100 to 150 s often occur in UV-crosslinkable coatings, while values of the pendulum hardness in the range from 40 to 80 s may occur in the coatings which are not UV-crosslinkable or are based e.g. on polymer dispersions which do not or scarcely crosslink chemically. The layers produced according to the invention are to be tested only on test specimens with chemically the same but sufficiently thick layers, but not on thin coatings in the range up to 10 μm thickness.

The dried and optionally also cured film preferably has a flexibility such that on bending over a conical mandrel in a mandrel flex test substantially according to DIN ISO 6860 for a mandrel of 3.2 mm to 38 mm diameter - but without tearing the test area - no cracks longer than 2 mm are formed that are detectable during subsequent wetting with copper sulfate by a change in colour as a result of deposition of copper on the cracked-open metallic surface. The term "substantially" here means that thicker films are conventionally characterized, and for this reason a copper sulfate test also follows here, which can reveal the defects which otherwise under certain circumstances are not visible. Demonstration of the flexibility by using the mandrel flex test and subsequent dipping of the regions shaped in this manner in a copper sulfate solution to detect defects provides a reproducible test result and has the advantage that no expensive corrosion tests, e.g. lasting 240 h, which in some cases, depending on the chemical composition and roughness of the metallic surface, can lead to different results which therefore can be compared with one another to only a limited extent, are necessary for this. In the case of baser metallic surfaces, such as aluminium alloys, for this test it is necessary first to clean the metallic surface once by pickling before the coating, in order substantially to remove the oxide layer.

The area proportions of the detached area in the T-bend test on shaped components (metal sheets) coated according to the invention and then with coil coating lacquer are preferably only up to 8%, particularly preferably up to 5%, very particularly preferably up to 2%, but the best values are at approximately 0%, so that then usually only cracks occur. A coil coating lacquer based on silicone polyester can preferably be employed for this, in particular for comparative tests in tests typical for coated coils. The absence of cracking or

the size of the cracks here, however, also depends largely on the nature of the lacquer employed.

- In the process according to the invention, in each case at least one coating of printing ink, foil, lacquer, lacquer-like material, powder coating, adhesive or/and adhesive carrier can preferably be applied to the dried and optionally also cured film.
- 10 In each case at least one coating of lacquer, polymer, paint, functional coatings of plastic, adhesive or/and adhesive carrier, such as e.g. a self-adhesive film, can be applied to the partly or completely dried or cured film, in particular a wet lacquer, a powder coating, a coating of plastic, an adhesive, inter alia for foil coating. The metal components coated according to the invention with the aqueous composition, in particular strips or strip sections, can be shaped, lacquered, coated with polymers, such as e.g. PVC, printed, glued, hot-soldered, welded or/and joined to one another or to other elements by clinching or other joining techniques. These processes are known in principle for coating of metallic strip for architectural uses. As a rule, lacquering or coating of another type is first carried out, and then shaping. If the coating according to the invention is lacquered or coated with plastic, solder or weld connections usually cannot be established without the coatings being removed at least locally, unless, for electrical welding, a high content of conductive particles or/and conductive polymer is incorporated into the film according to the invention and the subsequent coating is exceptionally thin.
- 15
20
25
30

- The substrates coated according to the invention can preferably be used as wire, strip, sheet metal or a component for a wire coil, a braided wire, a steel strip, a metal sheet, a lining, a screen, a vehicle body or a component of a vehicle body, a component of a
- 35

vehicle, trailer, mobile home or missile, a cover, a housing, a lamp, a light, a traffic light element, a piece of furniture or furniture element, an element of a domestic appliance, a frame, a profile, a shaped component of complicated geometry, a crash barrier, heater or fence element, a bumper, a component of or with at least one tube or/and a profile, a window, door or bicycle frame or an item of hardware, such as a screw, nut, flange, spring, or a spectacle frame.

The process according to the invention is an alternative to on the one hand the chromate-rich acid-free and on the other hand acid-containing processes mentioned, in particular in the field of surface pretreatment of metal strip before lacquering, and compared with these gives comparably good results in respect of corrosion protection and lacquer adhesion.

It is moreover possible to employ the process according to the invention for treatment of metal surfaces cleaned in the conventional manner but without subsequent after-treatment, such as rinsing with water or a suitable after-rinsing solution. The process according to the invention is particularly suitable for application of the treatment solution by means of squeeze-off rollers or by means of a so-called roll coater, it being possible for the treatment solution to be dried directly after the application without further intermediate process steps (Dry in Place technology). By this means, the process is simplified considerably e.g. compared with conventional spraying or dipping processes, in particular those with subsequent rinsing operations, such as e.g. a chromating or zinc phosphating, and only very small amounts of rinsing water for cleaning the unit after the end of work are produced, since no rinsing process after the application is necessary, which also represents an advantage compared with the already established chromium-free processes which

operate by the spraying process with after-rinsing solutions. These rinsing waters can be added again to a new batch of the bath composition.

- 5 It is easily possible here to employ the polymeric, optionally chromate-free coating according to the invention without prior application of an additional pretreatment layer, so that an outstanding permanent protection of the metallic surfaces, and in particular
10 on AlSi, ZnAl, such as Galfan[®], AlZn, such as Galvalume[®], ZnFe, ZnNi, such as Galvanneal[®] and other Zn alloys as metallic coatings or Al and Zn coatings, is possible, which can be achieved by application of a polymer-containing coating. Moreover, the coating
15 according to the invention has also proved particularly suitable for metallic surfaces which are highly susceptible to corrosion, such as those of iron and steel alloys, in particular on cold-rolled steel, it then being advantageous to add at least one corrosion
20 inhibitor to the aqueous composition. Flash rust formation during drying of the treatment liquid on cold-rolled steel (CRS) can be suppressed by this means.

- A less expensive and more environment-friendly corrosion
25 protection which also does not require an expensive UV curing but can be cured adequately solely with drying and film formation and optionally additionally with the "usual chemical" curing, which is often called "thermal crosslinking", can thus be achieved. In some cases,
30 however, it may be of interest to obtain a harder coating quickly in a particular process step. It can then be advantageous if at least one photoinitiator is added and at least one UV-curable polymer component is chosen in order to achieve a partial crosslinking on the
35 basis of actinic radiation, in particular UV radiation. The coating according to the invention can then be cured partly by actinic radiation and partly by drying and film formation or by thermal crosslinking. This can be

of importance in particular during application to fast-running belt lines or for the first crosslinking (= curing). The content of so-called UV crosslinking here can be 0 to 50% of the total possible curing, preferably 10 to 40%.

The polymeric and largely or completely chromate-free coating according to the invention furthermore has the advantage that - especially at a layer thickness in the range from 0.5 to 3 μm - it is transparent and light-coloured, so that the metallic character and the typical structure e.g. of a galvanized or a Galvalume[®] surface can still be seen accurately and unchanged or virtually unchanged through the coating. Furthermore, such thin coatings can also be welded without problems.

The polymeric coating according to the invention moreover is very readily shapable, so that it can be adjusted such that after the coating, drying and optionally curing and optionally also in the long term it is in a relatively plastic and not in a hard, brittle state.

The polymer-containing coating according to the invention can be readily over-lacquered with most lacquers or plastics. The polymer-containing coating according to the invention can be after-lacquered or coated with plastic, such as PVC, by application processes such as e.g. powder coating, wet lacquering, flooding, rolling, brushing or dipping. The cured coatings produced by this means which are applied to the polymer-containing coating according to the invention, it often also being possible to apply two or three layers of lacquer or plastic, usually have a total layer thickness in the range from 5 to 1,500 μm .

The polymeric coating according to the invention can also be foamed on the reverse without problems, e.g.

with polyurethane insulating foam, for the production of 2-sheet sandwich elements, or can readily be glued with the conventional construction adhesives such as are employed e.g. in vehicle construction.

5

The coatings according to the invention can be employed above all as primer layers. They are outstandingly suitable without, but also with, at least one previously applied pretreatment layer. This pretreatment layer can then be, inter alia, a coating based on phosphate, in particular ZnMnNi phosphate, or based on phosphonate, silane or/and a mixture based on a fluoride complex, corrosion inhibitor, phosphate, polymer or/and finely divided particles.

15

Pretreatment layers or primer layers which, together with the subsequently applied lacquer, resulted in a coating system equivalent to the best chromium-containing coating systems are achieved with the coatings according to the invention.

20

The process according to the invention furthermore has the advantage over the processes described and/or practised to date that on an aluminium-rich substrate or on a substrate coated with an aluminium-containing alloy - in particular a substrate of steel - it caused no darkening of the substrate surface and also no milky-white matting of the substrate surface and can therefore be employed for decoration of buildings or/and building components without additional colouring lacquering. The aesthetics of the metal surface remain unchanged.

25

30

The coatings according to the invention are exceptionally inexpensive, environment-friendly and readily usable on a large industrial scale.

35

It was surprising that in spite of a layer thickness of only approx. 0.5 to 2 μm , it was possible to produce an

2004215696 22 Apr 2010

48

exceptionally high-quality chromium-free film, with a synthetic resin coating according to the invention.

5 It was very surprising that by the addition of metal chelate to the aqueous composition it was possible to achieve a significant increase in the corrosion protection and also lacquer adhesion of the film formed therefrom - both in the case of aqueous compositions that contain predominantly chelate and silane and in the case of those that contain
10 predominantly synthetic resin and in addition chelate and silane.

The adhesion-promoting action of the silanes and of their reaction products, in particular between the metallic
15 substrate and lacquer and optionally between pigment and organic lacquer constituents, should also prevail in the compositions such as are described here in the embodiment examples, or even occur by itself, as long as polymers and chelate are not simultaneously present. It had not been
20 expected that at high contents of high molecular weight polymers and copolymers, without the presence of low molecular weight organic contents, a significant improvement in the film properties would be achieved by the addition of chelate. The high molecular weight polymers and copolymers
25 are possibly crosslinked by the presence of chelate, which is particularly advantageous in particular for those film-forming systems which have no contents of curing agent and photoinitiator. Exposure to relatively high temperatures, such as are otherwise used for thermal crosslinking, and
30 free-radical irradiation, which are an additional expensive process step, can be avoided by this means.

Examples and comparison examples:

35 In the present application, the examples 1-3 and 5-7 show the effect of the combination of silane plus metal chelate in comparison to comparison example 4 having only a silane content. The examples 8-36 show the effect of the combination

2004215696 22 Apr 2010

48a

- of silane plus metal chelate plus copolymers plus long-chain alcohols in comparison to the comparison examples 21-35 for comparable silane-free compositions. Tables 3, 4, 4a, 5, 5a and 5b clearly show worse data for silane-free compositions, as the data for salt spray tests (corrosion) and adhesion (DIN EN ISO 2409) have always higher data = worse results than such containing metal chelate plus silane. Please note that the polysiloxane added is used as a wetting or flow control agent, not as the silane according to the invention. Vice versa, in examples 1-3 and 5-7 of the combination of silane plus metal chelate in comparison to comparison example 4 having only a silane content, the corrosion resistance of table 1 -last lines- is much worse too.
- The examples described below are intended to explain the subject matter of the invention in more detail.

A) Compositions substantially based on chelate and silane:

5 For preparation of aqueous concentrates, at least one partly hydrolysed silane was aged for at least two weeks and optionally also thereby hydrolysed. Thereafter, a metal chelate according to table 1 was added. The concentrates were then diluted with water, and an agent
10 which adapts the pH, such as ammonia, was optionally added in order to obtain ready-to-use treatment liquids. In each case 3 metal sheets of hot-galvanized steel or of Galvalume® steel sheet were then brought into contact by rolling on and drying on the corresponding treatment
15 liquid at 25°C. The metal sheets treated in this way were dried here at 90°C PMT and then tested for their corrosion protection.

Examples E 1 to E 8, including comparison example CE 4,
20 show the influence of the addition of chelate or of chelate and polymer mixture. In examples E 9 to E 12 and E 13 to E 17, the amounts of silane and chelate were increased and at the same time the addition of inorganic particles was reduced, these two series differing by
25 different amounts of polymer mixture added. Finally, the layer thicknesses were varied in examples E 9 and E 18 to E 20.

2004215696 21 Oct 2010

50

Table 1: Compositions based on chelate and silane and in some cases also inorganic particles, data in wt.% for concentrates and g/l for the treatment baths

Examples/comparison example	CE 1	CE 2	CE 3	CE 4	CE 5	CE 6	CE 7	E 8	E 9	E 10	E 11	E 12	E 13	E 14	E 15	E 16	E 17	E 18	E 19	E 20
Concentrates																				
Organofunct. silane A	15	15	15	30	-	15	15	3.3	1.7	5.1	7.5	11.6	2	1.2	3.3	5.1	7.8	1.7	1.7	1.7
Organofunct. silane B	-	-	-	-	15	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Titanium chelate D	17.5	17.5	17.5	-	-	-	-	3.9	2	5.9	8.8	13.7	3.1	1.3	3.9	5.9	9.1	2	2	2
Zirconium chelate E	-	-	-	-	17.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Zirconium chelate F	-	-	-	-	-	17.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Titanium chelate G	-	-	-	-	-	-	17.5	-	-	-	-	-	-	-	-	-	-	-	-	-
SiO ₂ particles <0.2 μm	-	-	-	-	-	-	-	11	13	9	6	-	7	9	6	4	-	13	13	13
Ethanol/methanol	not added, may be formed																			
Ammonia	small amounts added to adjust the pH to 8.3																			
Polymer mixture	-	-	-	-	-	-	-	7	7	7	7	7	4.5	4.5	4.5	4.5	4.5	7	7	7
Water	67.5	67.5	67.5	70.0	67.5	67.5	67.5	74.8	76.3	73	70.7	67.7	83.4	84	82.3	80.5	78.6	76.3	76.3	78.3
Total	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100
Batches for the treatment baths																				
Concentrate	10	20	30	20	20	20	20	53	53	53	53	53	53	53	53	53	53	40	27	13
Water	90	80	70	80	80	80	80	47	47	47	47	47	47	47	47	47	47	60	73	87

2004215696 21 Oct 2010

51

Examples/comparison example	CE 1	CE 2	CE 3	CE 4	CE 5	CE 6	CE 7	E 8	E 9	E 10	E 11	E 12	E 13	E 14	E 15	E 16	E 17	E 18	E 19	E 20
Treatment baths																				
Water	958	936	904	936	938	938	936	886.6	874.5	857.0	844.8	828.8	912.2	915.3	906.3	896.8	886.7	905.1	836.1	969.3
Organometal comp.	17	34	51	-	34	34	34	20.7	10.6	31.3	46.6	72.6	16.4	6.9	20.7	31.3	48.2	8.0	5.4	2.6
Silane	15	30	45	64	30	30	30	17.5	9.0	27.0	39.8	61.5	10.8	8.4	17.5	27.0	41.3	8.8	4.8	2.2
Acrylic-polyester-polyurethane copolymer	-	-	-	-	-	-	-	15	15	15	15	15	8.7	8.7	9.7	9.7	8.7	11.4	7.7	3.7
Styrene-acrylate copolymer	-	-	-	-	-	-	-	16.7	16.7	16.7	16.7	16.7	10.7	10.7	10.7	10.7	10.7	12.6	8.4	4.1
Colloidal SiO ₂	-	-	-	-	-	-	-	58.3	68.0	47.7	31.8	-	37.1	47.7	31.8	21.2	-	52	35.1	18.9
Polysiloxane	-	-	-	-	-	-	-	1	1	1	1	1	0.8	0.8	0.8	0.8	0.8	0.8	0.5	0.2
Diacetamer	-	-	-	-	-	-	-	1	1	1	1	1	0.5	0.6	0.6	0.6	0.6	0.8	0.5	0.2
Long-chain alcohol	-	-	-	-	-	-	-	3.8	8.3	8.3	8.3	3.3	2.1	2.1	2.1	2.1	2.1	2.5	1.7	0.8
pH	8.3	8.3	8.3	8.3	8.3	8.3	8.3	8.3	8.3	8.3	8.3	8.3	8.3	8.3	8.3	8.3	8.3	8.3	8.3	8.3
Film properties																				
Layer weight, g/m ²	0.2	0.4	0.8	0.2	0.4	0.4	0.4	0.8	0.8	0.8	0.8	0.8	0.8	0.5	0.5	0.5	0.5	0.8	0.4	0.2
Salt spray test ASTM B117-73: Area of corrosion in % after	48 h	10	<2	0	30	<2	<2	0	0	0	20	30	0	0	0	0	30	40	0	0
	96 h	20	10	<2	60	10	10	0	0	0	30	40	0	0	0	0	40	60	0	<2
	120 h	40	20	5	90	20	20	<2	0	<2	50	60	0	0	0	0	50	80	0	5
	240 h	60	40	10	100	40	40	10	0	10	70	80	10	<2	10	70	100	<2	6	10
	360 h	100	60	30	100	60	60	60	20	<2	30	100	100	20	5	30	100	100	5	10

The film formed here was transparent, uniform and closed. The films formed showed no coloration and showed no darkening of the underlying metallic surface. This is particularly advantageous in order to be able to see structure, gloss and colour of the metallic surface practically unchanged through the coating. The combination of chelate and silane already resulted in a very clear improvement in the corrosion protection at very low layer thicknesses compared with a composition which is free from organometallic compounds. Further examples moreover showed that in particular a higher addition of inorganic particles, in this case based on SiO_2 having an average particle size in the range from 10 to 20 nm, made a further additional contribution to the improvement in corrosion resistance. It was surprising here that beyond small additions of such particles, an increase in the content of inorganic particles also rendered possible a clear increase in corrosion protection. Astonishingly, in spite of the sometimes high content of inorganic particles, a closed and nevertheless flexible film which was resistant to mechanical influences was possible after the coating had formed a film. The layer weight approximately divided by 1.1 gives the layer thickness in μm . The area proportions of the corrosion were estimated visually. Due to the comparatively low contents of synthetic resin(s), this thin film has rather the properties of a passivation instead of a thin organic coating, which can be shaped. The film of example 9 about $0.75 \mu\text{m}$ thin is indeed thicker than a typical chromate-rich inorganic passivation, but shows at least the same good corrosion resistance and furthermore, in contrast to the chromate-rich layer, can readily be shaped.

B) Compositions substantially based on chelate, silane and organic polymer: Treatment or pretreatment of hot-galvanized, alloy-galvanized and electrolytically galvanized steel sheets:

5

The concentrations and compositions stated relate to the treatment solution itself and not to any preparation solutions of higher concentration used. All the concentration data are to be understood as solids contents, i.e. the concentrations relate to the weight contents of the active components, regardless of whether the raw materials employed were present in dilute form, e.g. as aqueous solutions. In addition to the compositions listed in the following, in commercial practice it may be necessary or desirable to add further additives or to adapt the amounts accordingly, for example either to increase the total amount of additives or e.g. to increase the amount of defoamer or/and flow control agent, such as e.g. a polysiloxane.

20

The synthetic resins employed were: a styrene-acrylate copolymer with a glass transition temperature in the range from 15 to 25°C, with a minimum film-forming temperature (MFT) in the range from 15 to 20°C and with an average particle size in the range from 120 to 180 nm, an acrylic-polyester-polyurethane copolymer with a blocking point in the range from 140 to 180°C, an MFT in the range from 35 to 40°C and a glass transition temperature in the range from 20 to 60°C, an ethylene-acrylic copolymer without a pronounced minimum film-forming temperature but with a melting point in the range from 70 to 90°C, and an acrylate with comparatively few hydroxyl groups, which could be crosslinked with a melamine resin, and with a number of OH groups (hydroxyl number) in the range from 20 to 60, calculated for the solid resin. The styrene-butadiene copolymer has a glass transition temperature in the range from -20 to +20°C and an acid number in the range

from 5 to 30; on the basis of the content of carboxyl groups, this copolymer is additionally crosslinkable e.g. with melamine resins or with isocyanate-containing polymers. The copolymer based on epoxide-acrylate has
5 an acid number in the range from 10 to 18 and a glass transition temperature of between 25 and 40°C. This copolymer for coating steel in particular gives the coating according to the invention a higher chemical resistance, especially in the basic range, and improves
10 the adhesion properties to the metallic substrate. Two different trialkoxysilanes with in each case one epoxide group were used as the organofunctional silane A and B and an ethylenediamine-silane was used as the organofunctional silane C.

15 The pyrogenic silica had a BET value in the range from 90 to 130 m²/g, the colloidal silicon dioxide had an average particle size in the range from 10 to 20 nm. The oxidized polyethylene served as a lubricant and
20 shaping agent (wax) and had a melting point in the range from 60 to 165°C, preferably in the range from 80 to 110 or even up to 150°C, particularly preferably in the range from 100 to 140°C. The polysiloxane employed was a polyether-modified dimethylpolysiloxane and served as
25 a wetting agent and flow control agent for the wet film during application. The defoamer was a mixture of hydrocarbons, hydrophobic silica, oxalized compounds and nonionic emulsifiers. A butyl ether based on propylene glycol or a mixture with a similar glycol ether of even
30 faster volatility than this butyl ether was used as the long-chain alcohol for the film formation.

Steel sheets which were obtained from commercially available cold rolled and subsequently a) alloy-
35 galvanized steel strip with 55 wt.% Al in AlZn (Galvalume®), with 5 wt.% Al in ZA (Galfan®), with approx. 2 wt.% Al in ZnAl (crack-free steel), b) hot-galvanized steel strip c) hot-aluminized steel strip and

d) electrolytically galvanized steel strip, which were oiled for the purpose of protection during storage, were first degreased in a mildly alkaline spray cleaner, rinsed with water, dried at elevated temperature and then treated with the aqueous composition according to the invention. A defined amount of the aqueous composition (bath composition) was applied here with the aid of a roll coater such that a wet film thickness of approx. 10 ml/m² resulted, the concentration being doubled for a dry film thickness of 2 g/m². The constituents were mixed in part in the sequence stated and the pH of the solution was then in each case adjusted to 8.0 to 8.5 with an ammonia solution or a solution of rapidly volatilizing alkanolamine. The wet film was then dried on at temperatures in the range from 80 to 100°C PMT, subjected to film formation and cured. Selected compositions of the bath composition are mentioned in table 2. The steel sheets treated in this manner were then tested for their corrosion protection and their mechanical properties (table 3). However, only the results on hot-galvanized steel sheets are shown in this table, because these are among the materials which are most difficult to protect against corrosion and among the materials tested, in addition to electrolytically galvanized steel sheets, gave the worst results. However, since electrolytically galvanized steel sheets are normally never installed outside without subsequent lacquering because of their increased susceptibility to corrosion, testing of hot-galvanized steel sheets which are relatively difficult to render resistant to corrosion and nowadays are employed more frequently without lacquering is the most appropriate.

Table 2: Composition of the aqueous treatment liquid of the examples and comparison examples,
data in g/l

[illegible]

[illegible]

Results of the tests on hot-galvanized metal sheets and on Galvalume® steel sheets:

The dry layer application of the dried, film-formed and cured polymer-containing coatings on hot-galvanized metal sheets (HDG) in each case gave values in the range from 950 to 1,050 mg/m² or from 1,900 to 2,100 mg/m² for the virtually 1 or virtually 2 µm thick films respectively in all the experiments - apart from in comparison example 4. The dried films had a layer thickness in the range from 0.8 to 1 µm or from 1.7 to 2 µm. All the coatings were transparent, colourless and uniform. They showed a slight silk gloss, so that the optical character of the metallic surface remained detectable practically unchanged.

To evaluate the shapability of the film of the treatment liquid applied and dried on the Galvalume® substrate surface, the pin-on-disc test was employed. Galvalume® was employed because, on the basis of its high aluminium content, this coating is more difficult to shape on steel sheet than the other zinc-containing alloys mentioned here. This laboratory test method enables the investigations to be carried out under reproducible conditions which can be adhered to within very narrow limits. The results determined can thereby be compared with one another in an optimum manner.

Test method in the pin-on-disc test:

A steel ball with a diameter of 7.5 mm circulates in circles on the steel surface, which has been treated with the aqueous organic composition, under a pressure of 20 N at a speed of 10 mm/s at a room temperature of 20 - 22°C and a relative atmospheric humidity of 35 to 40%. During the measurement the coefficient of friction arising due to the movement of the steel ball on the

organic coating under the conditions described is measured and recorded with the aid of a computer.

An organic film is desired, prepared with the aqueous
5 treatment liquid, which after drying and film formation

1. shows the lowest possible coefficient of friction,
where

10 2. the coefficient of friction should remain largely
constant during the longest possible shaping time
and, in spite of the friction and roughening of the
surface of the organic coating with the ball,
should not rise to a relatively high degree -
15 measured in the pin-on-disc test by the number of
circuits the ball can cover before a coefficient of
friction of 0.4 is measured.

20 Table 3: Test results of the non-lacquered, organically
treated hot-galvanized steel sheets in respect of
corrosion protection, friction and shapability, in E 37
Galvalume® steel sheets for comparison.

Examples	Dry layer application 1 g/m ² : Salt spray test ASTM B 117-73			Dry layer application 2 g/m ² : Salt spray test ASTM B 117-73			Pin-on-disc test: Starting coefficient of friction	Pin-on-disc test: Number of circular movements until the coefficient of friction of 0.40 is exceeded
	120 h	240 h	360 h	120 h	240 h	360 h		
E 21	5	15	30	0	0	0	0.16	140
E 22	<2	10	15	0	0	0	0.16	140
E 23	0	0	<2	0	0	0	0.16	140
E 24	0	0	<2	0	0	0	0.16	140
E 25	0	0	<2	0	0	0	0.16	140
E 26	0	0	<2	0	0	0	0.16	140
E 27	0	0	<2	0	0	0	0.16	140
E 28	0	0	<2	0	0	0	0.16	10
E 29	0	0	<2	0	0	0	0.16	50
E 30	0	0	<2	0	0	0	0.16	120
E 31	0	0	<2	0	0	0	0.16	140
E 32	0	0	<2	0	0	0	0.16	140
E 33	0	0	<2	0	0	0	0.16	140
E 34	0	0	<2	0	0	0	0.16	140
E 35	0	0	<2	0	0	0	0.16	140
E 36	0	0	<2	0	0	0	0.16	140
E 37	0	0	0*	0	0	0	0.16	140

Comparison examples	Dry layer application 1 g/m ² : Salt spray test ASTM B 117-73 Area of corrosion in % after			Dry layer application 2 g/m ² : Salt spray test ASTM B 117-73 Area of corrosion in % after			Pin-on-disc test: Starting coefficient of friction	Pin-on-disc test: Number of circular movements until the coefficient of friction of 0.40 is exceeded
	120 h	240 h	360 h	120 h	240 h	360 h		
CE 21	80	100	100	10	20	30	0.16	140
CE 22	80	100	100	5	10	20	0.16	140
CE 23	20	40	60	0	< 2	5	0.16	140
CE 24	20	40	60	0	< 2	5	0.16	140
CE 25	20	40	60	0	< 2	5	0.16	140
CE 26	20	40	60	0	< 2	5	0.16	140
CE 27	20	40	60	0	< 2	5	0.16	140
CE 28	80	100	100	10	20	40	0.16	140
CE 29	20	40	60	5	10	20	0.16	140
CE 30	20	40	60	0	5	10	0.16	10
CE 31	20	40	60	0	< 2	5	0.16	50
CE 32	20	40	60	0	< 2	5	0.16	120
CE 33	20	40	60	0	< 2	5	0.16	140
CE 34	100	100	100	100	100	100	0.16	140
CE 35	20	40	60	0	< 2	5	>0.8	Not applicable

In E 37, instead of the hot-galvanized steel sheets, Galvalume[®] steel sheets which had been coated as described for E 23 were used. In the salt spray test, a low point corrosion which made up < 2 per cent of the area resulted only in a test time of 720 h.

The combination of chelate and silane resulted in a very clear improvement in the corrosion protection, as can be seen from the comparison of examples E 23 and E37 in comparison, so that in the case of the aqueous compositions according to the invention containing organic polymer, it was possible to leave out the organic corrosion inhibitor, apart from for the treatment of non-coated steel, without sacrificing corrosion resistance. Furthermore, it was found in the pin-on-disc test, surprisingly, that a combination of oxidized polyethylene and an ethylene-acrylic acid copolymer is particularly advantageous, if the copolymer content is not too low, for ensuring a permanent lowering of the coefficient of friction during a long-lasting shaping process. The test results showed that the most difficult shaping processes for production of elements of extreme geometry can be carried out even without abrasion of metal from the substrate surface, which allows the production of mouldings with aesthetically pleasing surfaces by shaping processes after the organic coating.

Further tests were furthermore carried out to evaluate the lacquer adhesion and corrosion resistance of metal sheets pretreated organically with the aqueous composition and subsequently coated with white lacquer:

A large part of the substrate surfaces treated with the treatment liquids on hot-galvanized steel sheets was over-lacquered with lacquer systems which are employed in general industry for the production of consumer goods, such as e.g. washing machines, refrigerators,

shelf systems or office furniture, from steel. The lacquer systems employed here were a) a white thermally crosslinking acrylic lacquer based on organic solvents and acrylic resin solutions of $40 \pm 5 \mu\text{m}$ dry layer thickness after 20 min at 180°C stoving temperature or b) a white powder coating based on a polyester-epoxide mixed powder of $60 \pm 5 \mu\text{m}$ dry layer thickness after 20 min at 180°C stoving temperature, which are employed commercially for coating so-called white goods. In CE 36, hot-galvanized steel sheets which were coated only with the particular lacquer, without organic pretreatment, were employed here. In E 37, instead of the hot-galvanized steel sheets, Galvalume[®] steel sheets which had been coated as described for E 23 were used for comparison.

Tables 4/4a: Results of the corrosion tests and the adhesion tests on alternate exposure at 20°C in normal atmospheric humidity and at 40°C in 100% atmospheric humidity after coating with the acrylic lacquer or with the powder coating on pretreatment layers about $1 \mu\text{m}$ thick.

Examples/ comparison examples with acrylic lacquer	Dry layer application 1 g/m ² : Salt spray test ASTM B 117-73		Damp heat alternating atmosphere according to DIN 50017 KFW 20 cycles			
	Under-migration in mm after 360h		Cross-hatch in Gt at 1 mm grid distance according to DIN EN ISO 2409		Corrosion: Under-migration in mm	
	Crack	Cut edge	Before KFW test	After KFW test	At crack	At cut edge
E 23	10	8	Gt 1	Gt 1	0	0
E 29	9	8	Gt 1	Gt 1	0	0
E 30	11	8	Gt 1	Gt 1	0	0
E 31	12	7	Gt 1	Gt 1	0	0
E 32	10	9	Gt 1	Gt 1	0	0
E 33	9	8	Gt 1	Gt 1	0	0
E 34	12	8	Gt 1	Gt 1	0	0
E 35	12	7	Gt 1	Gt 1	0	0
E 36	11	8	Gt 1	Gt 1	0	0
E 37	8	5	Gt 1	Gt 1	0	0
CE 24	15	12	Gt 1	Gt 2	1	1
CE 31	17	12	Gt 1	Gt 3	2	1
CE 32	16	13	Gt 1	Gt 2	1	2
CE 33	18	12	Gt 1	Gt 3	2	1
CE 34	30	20	Gt 1	Gt 2	3	5
CE 35	16	11	Gt 1	Gt 3	2	4
CE 36	detached over a large area	detached over a large area	Gt 1	Gt 5	10 blistering	8 blistering

Examples/ comparison examples with powder coating	Dry layer application 1 g/m ² : Salt spray test ASTM B 117-73			Damp heat alternating atmosphere according to DIN 50017 KFW 20 cycles	
	Under-migration in mm after 360h		Cross-hatch in Gt at 2 mm grid distance according to DIN EN ISO 2409	Corrosion: Under-migration in mm	
	Crack	Cut edge		Before KFW test	After KFW test
E 23	1	1	Gt 0	Gt 0	0
E 29	1	2	Gt 0	Gt 0	0
E 30	1	1	Gt 0	Gt 0	0
E 31	2	1	Gt 0	Gt 0	0
E 32	2	2	Gt 0	Gt 0	0
E 33	1	1	Gt 0	Gt 0	0
E 34	1	1	Gt 0	Gt 0	0
E 35	2	2	Gt 0	Gt 0	0
E 36	1	2	Gt 0	Gt 0	0
E 37	0	0	Gt 0	Gt 0	0
CE 24	5	4	Gt 0	Gt 2	0
CE 31	4	4	Gt 0	Gt 1	1
CE 32	3	3	Gt 0	Gt 2	0
CE 33	4	4	Gt 0	Gt 2	1
CE 34	3	3	Gt 0	Gt 2	0
CE 35	3	4	Gt 0	Gt 2	0
CE 36	detached over a large area	detached over a large area	Gt 2	Gt 5	5

The results of the salt spray test on over-lacquered metal sheets show that the acrylic lacquer coating as expected did not ensure quite such a good corrosion resistance as the powder coating. However, how much the silane chelate pretreatment makes up can be seen by comparison of the examples according to the invention with comparison example 36. The corrosion data of the salt spray test can be classified as very good to excellent.

10

Since no difference occurs in the lacquer adhesion results before and after the damp heat alternating test, the rating Gt 1 is primarily to be attributed to the lacquer and not to the pretreatment, where Gt 1 is to be regarded as good. The results of the damp heat alternating atmosphere tests show very good to excellent lacquer adhesion values, especially when the lacquer quality, the particularly corrosion-sensitive metallic surface and the exceptionally thin organic pretreatment layer at about 1 μm are taken into account. The damp heat alternating atmosphere test in respect of under-migration is too insensitive for this type of corrosion testing on systems which are so good.

15

20

25 All the results of tables 4/4a show, in comparison with tests on the best chromate-containing organic coatings of the same layer thickness, which contain polymers which are *per se* of a very high polymeric quality, that the now chromate-free organic coatings without exception are already equivalent in corrosion protection and in lacquer adhesion to the chromate-containing coatings at a layer thickness of about 1 μm layer thickness. It is thus ensured that an equivalent substitution of environment-friendly materials is possible without problems in series production. To the knowledge of the Applicant, such a result for organic coatings has not yet hitherto been achieved anywhere!

30

35

22 Apr 2010
2004215696

Tables 5, 5a and 5b show the composition of the aqueous treatment liquids in selected Examples and Comparative Examples, test results on non-purified but aqueous treated Examples and Comparative Examples of Table 5 and test results for E30 and E50 compared with CE48 and CE49 purified and aqueous treated HDG. The results show for the present application on the one hand example E30, for hot dip galvanized steel sheets which corresponds to the chelate-free comparison example CE48 and on the other side the chelate-free example CE49, on a galvanized steel sheet and a chelate-containing example E50 for galvanized steel sheets. For the comparison examples CE40 and CE41 and for the examples E42 to E47 for hot dip galvanized steel sheets (HDG) were coated, which were treated as for the examples E21 and E36 of the present application. The examples CE 40, E42, E44 and E46 show compositions without respectively increasing the content of chelate with constant contents of silane, but without the addition of a corrosion inhibitor. Examples CE 41, E43, E45 and E47 disclose compositions without respectively increasing the content of chelate with constant contents of silane and of a corrosion inhibitor.

The addition of a corrosion inhibitor, on the base of an amine complex resulted in HDG sheets not having a measurable effect on the corrosion resistance which is different to other kinds of metallic surfaces; whereas the addition of the chelate caused a significant increase of the corrosion resistance.

These coatings showed coating thicknesses in the range of from 0.8 to 1 μm and that for such thin coatings it is very difficult to gain a good corrosion resistance. In opposite hereto, at a coating thickness of about 3 μm , there is only about half of the corrosion resistance effect per coating

2004215696 22 Apr 2010

.67a

thickness unit necessary to gain the same good corrosion resistance. As several primer or lacquer coatings typically show in comparison hereto a thickness in the range of from 5 to 40 μm , the corrosion resistance effect of such coatings need only a comparably small corrosion resistance effect per coating thickness unit.

It had not been expected that by having high contents of high molecular polymers/copolymers, without the presence of low molecular polymers/copolymers, with a chelate addition a significant improvement in the coating properties could be reached. The experimental results showed that without addition of a chelate, there is only a low corrosion resistance for such compositions. But the relatively small addition of about 3% of solid content was sufficient to improve corrosion resistance and even paint adhesion.

In Tables 5, 5a and 5b, the corrosion resistance starting from E30 of the corresponding chelate-free CE48 is significantly worse. Starting from the chelate-free example E5 of D3, here CE49, the corrosion resistance of the corresponding chelate-containing E50 is significantly better. Because of the very high content of SiO_2 , the corrosion resistance is excellent, but the paint adhesion of the paint layer upon it measured by "Gitterschnitt" of CE49 and of E50 are affected. For all data of corrosion resistance and paint adhesion, the smaller data the better.

The addition of a long-chain alcohol caused the improvement of the corrosion resistance in dependence of the specific polymer/copolymer-system and further condition of at least 5%, mostly even for the systems mentioned in the examples of from 50 to 100 %.

2004215696 22 Apr 2010

67b

But polyvinyl alcohol is not a long-chain alcohol in the sense of the present application. Because of the homogenization of the organic film by the addition of the long-chain alcohol it can be understood that even the paint adhesion to the next following paint layer is improved, which is generally higher than for non-filmformed organic coatings which contain organic particles and many inhomogenities.

It is moreover to be taken into account that the organic films according to the invention have a very high resistance to weathering and, in contrast to many other organic coatings, can be employed in the long term outside and under UV irradiation. Many lacquer systems, crosslinked thermally and by free radicals, such as those based on epoxy resins, are of only limited suitability for use outside.

2004215696 22 Apr 2010

67c

Table 5: Composition of the aqueous treatment liquids (data in g/L)

Examples and comparison examples	CE 40	CE 41	E 42	E 43	E 44	E 45	E 46	E 47	CE 48	E 30	CE 49	E 50
Water content of solvents in Gew.-%	900	900	900	900	900	900	900	900	903	900	909	906
Acryl-polyester-polyurethane-copolymerisate	31.0	29.0	29.5	27.5	28.0	26.0	26.5	24.5	44.6	44.6	27.3	27.3
Styrene acrylate	16.6	14.6	12.6	10.6	16.6	16.6	14.6	12.6	-	-	-	-
Ethylene-acrylic acid polymerisate	28.0	28.0	28.0	28.0	28.0	28.0	28.0	28.0	28.0	28.0	27.3	27.3
Colloidal SiO ₂	9.3	9.3	9.3	9.3	9.3	9.3	9.3	9.3	9.3	9.3	22.7	22.7
Oxidized polyethylene	5.8	5.8	5.8	5.8	5.8	5.8	5.8	5.8	5.8	5.8	4.5	4.5
Titanium chelate D	-	-	1.5	1.5	3.0	3.0	4.5	4.5	-	3.0	-	3.0
Corrosion inhibitor	-	2.0	-	2.0	-	2.0	0	2.0	-	-	-	-
Organofunctional silane A	4.0	4.0	4.0	4.0	4.0	4.0	4.0	4.0	4.0	4.0	3.6	3.6
Polysiloxane	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	0.9	0.9
Defoamer	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	0.9	0.9
Long-chain alcohol	3.3	3.3	3.3	3.3	3.3	3.3	3.3	3.3	3.3	3.3	3.6	3.6

2004215696 22 Apr 2010

67d

Table 5a: Test results on non-painted, but with an aqueous treatment liquid coated hot dip galvanized resp. zinc alloy galvanized steel sheets for bare corrosion protection (= without additional paint layer), friction and forming behaviour

Examples/ comparison examples	Dry layer application 1 g/m²: Salt spray test ASTM B 117-73			Dry layer application 2 g/m²: Salt spray test ASTM B 117-73			Pin-On-Disc Test: Starting coefficient of friction	Pin-On-Disc Test: Number of circular movements until coefficient of friction of 0.40 is exceeded
	Area of corrosion in % after			Area of corrosion in % after				
	120 h	240 h	360 h	120 h	240 h	360 h		
	120 h	240 h	360 h	120 h	240 h	360 h		
CE 40	80	100	100	60	80	100	0.16	140
CE 41	80	100	100	60	80	100	0.16	140
E 42	30	50	80	20	30	60	0.16	140
E 43	30	50	80	20	30	60	0.16	140
E 44	0	0	< 2	0	0	0	0.16	140
E 45	0	0	< 2	0	0	0	0.16	140
E 46	0	0	< 2	0	0	0	0.16	140
E 47	0	0	< 2	0	0	0	0.16	10
CE 48	30	40	60	10	20	35	0.16	120
E 30	0	0	2	0	0	0	0.16	120
CE 49	15	20	30	5	10	20	0.16	120
E 50	0	0	< 2	0	0	0	0.16	120

2004215696 22 Apr 2010

67e

Table 5b: Test results on painted, but with an aqueous treatment liquid coated hot dip galvanized resp. zinc alloy galvanized steel sheets for corrosion protection (= with additional paint layer) and paint adhesion

Examples/ comparison examples with acrylic paint	Dry layer application 1 g/m ² : Salt spray test ASTM B 117-73		Damp heat alternating atmosphere test according to DIN 50017 KFW 20 cycles			
	Under-migration in mm after 360 h		Cross-hatch in Gt at 1 mm grid distance according to DIN EN ISO 2409		Corrosion: Under-migration in mm	
	at scribe	at cut edge	before KFW test	after KFW test	at scribe	at cut edge
CE 48	15	12	Gt 1	Gt 3	2	2
E 30	11	8	Gt 1	Gt 1	0	0
CE 49	20	18	Gt 2	Gt 4	5	5
E 50	12	10	Gt 2	Gt 2	2	2

THE CLAIMS DEFINING THE INVENTION ARE AS FOLLOWS:

1. A process for the pre-treatment or treatment of a
5 metallic surface by coating with an aqueous composition
substantially free from chromium(VI) compounds, wherein
the process comprises the steps of:
(i) bringing a clean, pickled, cleaned and/or pre-
10 treated metallic surface into contact with the aqueous
composition such as to form a film on the metallic
surface; and
(ii) drying and partly or completely compacting the film
and optionally curing the film to an extent wherein the
15 dried and optionally cured film has a layer thickness in
the range from 0.01 to 10 μm ;
- characterized in that the aqueous composition contains:
- a) at least one hydrolysable or at least partly
20 hydrolysed silane;
- b) at least one metal chelate that is stable in
aqueous dispersions in the presence of components
a), c) and d), and wherein the metal chelate is
25 functional to improve the corrosion resistance and
adhesion of the film;
- c) at least one organic film-forming agent which
contains at least one water-soluble or water-
dispersed organic polymer and/or copolymer with an
acid number in the range from 3 to 250, whereby
30 the content of organic film-forming agent, based
on the solids content of the composition, is > 45
wt.%; and
- d) at least one long-chain alcohol as a film-forming
35 auxiliary.
2. The process according to claim 1, characterized in that
the at least one metal chelate is chosen from chelate
complexes based on acetylacetonates, acetoacetates,
acetates, alkylenediamines, amines, lactates,
40 carboxylic acids, citrates and/or glycols, the content of

the at least one chelate in the aqueous composition, including the reaction products possibly formed therefrom, is between being 0.1 to 80 g/l.

- 5 3. The process according to claim 1 or 2, characterized in that the organic film-forming agent is a synthetic resin mixture of at least one polymer and/or at least one copolymer which includes a synthetic resin based on acrylate, epoxide, ethylene, urea-formaldehyde, phenol, polyester, polyurethane, styrene, styrene-butadiene and/or vinyl.
- 10
- 15 4. The process according to any one of claims 1 to 3, characterized in that the organic film-forming agent further comprises as a synthetic resin a content of organic polymer, copolymer and/or mixtures thereof based on polyethyleneimine, polyvinyl alcohol, polyvinyl-phenol, polyvinylpyrrolidone and/or polyaspartic acid, in particular copolymers with a phosphorus-containing vinyl compound.
- 20
- 25 5. The process according to any one of claims 1 to 4, characterized in that the organic film-forming agent comprises at least one copolymer with an acid number in the range from 3 to 80, and where the co-polymer in particular is at least 50 wt.% of the synthetic resins added.
- 30 6. The process according to any one of claims 1 to 5, characterized in that the aqueous composition further comprises at least one component e) selected from the group consisting of:
- 35 e1) at least one inorganic compound in particle form with an average particle diameter, measured on a scanning electron microscope, in the range from 0.005 to 0.3 μm diameter;
- 40 e2) at least one lubricant;
- e3) at least one organic corrosion inhibitor;
- e4) at least one anticorrosion pigment;

2004215696 21 Oct 2010

70

- e5) at least one agent for neutralization and/or for steric stabilization of the synthetic resins;
e6) at least one organic solvent;
e7) at least one siloxane; and
5 e8) at least one chromium(VI) compound.
7. The process according to any one of claims 1 to 6, characterized in that the organic film-forming agent comprises at least one component based on:
- 10 acrylic-polyester-polyurethane copolymer,
acrylic-polyester-polyurethane-styrene copolymer,
acrylic acid ester,
acrylic acid ester-methacrylic acid ester, optionally
15 with free acids and/or acrylonitrile,
ethylene-acrylic mixture,
ethylene-acrylic copolymer,
ethylene-acrylic-polyester copolymer,
ethylene-acrylic-polyurethane copolymer,
20 ethylene-acrylic-polyester-polyurethane copolymer,
ethylene-acrylic-polyester-polyurethane-styrene copolymer,
ethylene-acrylic-styrene copolymer,
polyester resins with free carboxyl groups combined with
25 melamine-formaldehyde resins,
a synthetic resin mixture and/or copolymer based on acrylate and styrene,
a synthetic resin mixture and/or copolymer based on styrene-butadiene,
30 a synthetic resin mixture and/or copolymer of acrylate and epoxide,
based on an acrylic-modified polyester containing carboxyl groups together with melamine-formaldehyde and ethylene-acrylic copolymer,
35 polycarbonate-polyurethane,
polyester-polyurethane,
styrene,
styrene-vinyl acetate,
vinyl acetate,
40 vinyl ester and/or

vinyl ether.

8. The process according to any one of claims 1 to 7,
characterized in that at least 30 wt.% of the organic
film-forming agent consists of film-formable
thermoplastic resins.
9. The process according to any one of claims 1 to 8,
characterized in that the molecular weights of the
synthetic resins added are in the range of at least 1,000
u.
10. The process according to any one of claims 1 to 9,
characterized in that the organic film-forming agents
added consist of at least 40 wt.% of high-molecular-
weight polymers.
11. The process according to any one of claims 1 to 10,
characterized in that the acid groups of the synthetic
resins are stabilized with a compound selected from the
group consisting of ammonia, amines, morpholine,
dimethylethanolamine, diethylethanolamine, triethanol-
amine, and/or with alkali metal compounds.
12. The process according to any one of claims 1 to 11,
characterized in that the aqueous composition contains
0.1 to 980 g/l of the organic film-forming agent.
13. The process according to any one of claims 1 to 12,
characterized in that the aqueous composition contains at
least one acyloxysilane, one alkoxysilane, one silane
with at least one amino group, one silane with at least
one succinic acid group and/or succinic acid anhydride
group, one bis-silyl-silane, one silane with at least one
epoxide group, one (meth)acrylato-silane, one multi-
silyl-silane, one ureidosilane, one vinylsilane and/or at
least one silanol and/or at least one siloxane of a
composition which corresponds chemically to that of the
abovementioned silanes.

2004215696 21 Oct 2010

14. The process according to any one of claims 1 to 13, characterized in that the composition contains at least one silane chosen from the group consisting of:

5 glycidoxyalkyltrialkoxysilane,
methacryloxyalkyltrialkoxysilane,
(trialkoxysilyl)alkyl-succinic acid-silane,
aminoalkylaminoalkylalkyldialkoxysilane,
epoxycycloalkyl)alkyltrialkoxysilane,
10 bis-(trialkoxysilylalkyl)amine,
bis-(trialkoxysilyl)ethane,
(epoxyalkyl)trialkoxysilane,
aminoalkyltrialkoxysilane,
ureidoalkyltrialkoxysilane,
15 N-(trialkoxysilylalkyl)alkylenediamine,
N-(aminoalkyl)aminoalkyltrialkoxysilane,
N-(trialkoxysilylalkyl)dialkylenetriamine,
poly(aminoalkyl)alkyldialkoxysilane,
tris(trialkoxysilyl)alkyl isocyanurate,
20 ureidoalkyltrialkoxysilane and
acetoxysilane.

15. The process according to any one of claims 1 to 14, characterized in that the composition contains at least one silane chosen from the group consisting of:

3-glycidoxypropyltriethoxysilane,
3-glycidoxypropyltrimethoxysilane,
3-methacryloxypropyltriethoxysilane,
30 3-methacryloxypropyltrimethoxysilane,
3-(triethoxysilyl)propyl-succinic acid-silane,
aminoethylaminopropylmethyldiethoxysilane
aminoethylaminopropylmethyldimethoxysilane,
beta-(3,4-epoxycyclohexyl)ethyltriethoxy-silane,
35 beta-(3,4-epoxycyclohexyl)ethyltrimethoxy-silane,
beta-(3,4-epoxycyclohexyl)methyltriethoxy-silane,
beta-(3,4-epoxycyclohexyl)methyltrimethoxy-silane,
gamma-(3,4-epoxycyclohexyl)propyltriethoxysilane,
gamma-(3,4-epoxycyclohexyl)propyltrimethoxysilane,
40 bis(triethoxysilylpropyl)amine,

2004215696 21 Oct 2010

73

- bis(trimethoxysilylpropyl)amine,
 (3,4-epoxybutyl)triethoxysilane,
 (3,4-epoxybutyl)trimethoxysilane,
 gamma-aminopropyltriethoxysilane,
 5 gamma-aminopropyltrimethoxysilane,
 gamma-ureidopropyltrialkoxysilane,
 N-(3-(trimethoxysilyl)propyl)ethylenediamine,
 N-beta-(aminoethyl)-gamma-aminopropyltri-ethoxy-silane,
 N-beta-(aminoethyl)-gamma-aminopropyltri-methoxysilane,
 10 N-(gamma-triethoxysilylpropyl)diethylene-triamine,
 N-(gamma-trimethoxysilylpropyl)diethylene-triamine,
 N-(gamma-triethoxysilylpropyl)dimethylene-triamine,
 N-(gamma-trimethoxysilylpropyl)dimethylene-triamine,
 15 poly(aminoalkyl)ethyldialkoxysilane,
 poly(aminoalkyl)methyldialkoxysilane,
 tris(3-(triethoxysilyl)propyl) isocyanurate
 tris(3-(trimethoxysilyl)propyl) isocyanurate and
 vinyltriacetoxysilane.
- 20 16. The process according to any one of claims 1 to 15,
 characterized in that the content of the at least one
 silane in the aqueous composition, including the reaction
 products formed therefrom, is between 0.1 to 50 g/l.
- 25 17. The process according to any one of claims 1 to 16,
 characterized in that the at least one metal chelate is
 chosen from the group consisting of:
- 30 acetylacetonate,
 alkali metal lactate,
 alkanolamine,
 alkyl acetoacetate,
 alkylenediamine tetraacetate,
 ammonium lactate,
 35 citrate,
 dialkyl citrate,
 dialkyl ester-citrate,
 dialkylenetriamine,
 diisalkoxybisalkyl acetoacetate,
 40 diisopropoxybisalkyl acetoacetate,

2004215696 21 Oct 2010

74

di-n-alkoxy-bisalkyl acetoacetate,
hydroxyalkylenediamine triacetate,
trialkanolamine and/or
trialkylenetetramine.

5

18. The process according to any one of claims 6 to 17,
characterized in that a finely divided powder, a
dispersion or a suspension, such as a carbonate, oxide,
silicate or sulfate, in particular colloidal and/or
10 amorphous particles, is added as inorganic compound in
particle form.

19. The process according to any one of claims 6 to 18,
characterized in that the at least one inorganic compound
15 in particle form is selected from the group consisting of
aluminium, barium, cerium, calcium, lanthanum, silicon,
titanium, yttrium, zinc and/or zirconium.

20. The process according to claim 19, characterized in that
20 the particles are selected from the group consisting of
aluminium oxide, barium sulfate, cerium dioxide, silicon
dioxide, silicate, titanium oxide, yttrium oxide, zinc
oxide and/or zirconium oxide.

21. The process according to any one of claims 6 to 20,
characterized in that the aqueous composition contains
0.1 to 500 g/l of the at least one inorganic compound in
particle form.

22. The process according to any one of claims 6 to 21,
characterized in that the aqueous composition contains at
least one organic corrosion inhibitor selected from the
group consisting of a) amine(s), preferably at least one
alkanolamine, preferably a long-chain alkanolamine, b) at
35 least one TPA-amine complex, such as acid adduct-4-oxo-4-
p-tolyl butyrate-4-ethylmorpholine, c) at least one
alkylaminoethanol, d) at least one zinc salt of
aminocarboxylate, of 5-nitro-isophthalic acid or of
cyanic acid, e) at least one polymeric amino salt with
40 fatty acid, f) at least one metal salt of a sulfonic

2004215696 21 Oct 2010

75

- acid, such as dodecyl-naphthalenesulfonic acid, g) at least one amino and transition metal complex of toluenepropionic acid, 2-mercapto-benzothiazolyl-succinic acid or at least one of its ammonium salts, h) at least one conductive polymer and/or i) at least one thiol, the content of organic corrosion inhibitors in the aqueous composition being in the range from 0.01 to 5 wt.%. 5
23. The process according to any one of claims 1 to 22, characterized in that the aqueous composition contains at least one basic crosslinking agent based on titanium, hafnium and/or zirconium as the cation and/or based on carbonate or ammonium carbonate as the anion, the content of such crosslinking agents in the aqueous composition preferably being in the range from 0.01 to 3 wt.%. 10 15
24. The process according to any one of claims 1 to 23, characterized in that no inorganic acids and/or organic carboxylic acids are added to the aqueous composition. 20
25. The process according to any one of claims 1 to 24, characterized in that at least one long-chain alcohol selected from the group consisting of diols, such as block copolymers of ethylene oxide and propylene oxide, butanediols, propanediols and/or decanediols, butyl glycols, butyl diglycols, ester-alcohols, ethylene glycols, ethylene glycol ethers, glycol ethers, such as di- and triethylene glycols with their mono- and diethers and dimethyl ethers, polyethers, polyethylene glycols, polyethylene glycol ethers, polyglycols, polypropylene glycols, propylene glycols, propylene glycol ethers, polypropylene glycol ethers, glycol ethers, trimethylpentanediol diisobutyrate and derivatives thereof, is used as the film-forming auxiliary, the content of long-chain alcohols in the aqueous composition being in the range from 0.01 to 10 wt.%. 25 30 35
26. The process according to any one of claims 6 to 25, characterized in that the at least one lubricant is selected from at least one wax chosen from the group 40

2004215696 21 Oct 2010

76

consisting of paraffins, polyethylenes and polypropylenes, in particular an oxidized wax, wherein the content of waxes in the aqueous composition being in the range from 0.01 to 5 wt.%,

5

27. The process according to any one of claims 6 to 25, characterized in that the lubricant is selected from at least one wax together with a polymer mixture and/or copolymer comprising ethylene and acrylic acid.

10

28. The process according to any one of claims 1 to 27, characterized in that the coating is cured partly by a) drying and film formation; and b) partly by actinic radiation, cationic polymerization and/or thermal crosslinking.

15

29. The process according to any one of claims 1 to 28, characterized in that the aqueous composition further comprises at least one additive selected from the group consisting of at least one biocide, at least one defoamer and/or at least one wetting agent.

20

30. The process according to any one of claims 1 to 29, characterized in that the aqueous composition is applied to the metallic surface at a temperature in the range from 5 to 50°C.

25

31. The process according to any one of claims 1 to 30, characterized in that the metallic surface is kept at a temperature in the range from 5 to 60°C during application of the coating.

30

32. The process according to any one of claims 1 to 31, characterized in that circulating air temperature used for drying the coated metallic surface is in the range from 20 to 400°C.

35

33. The process according to any one of claims 1 to 32, characterized in that the coated strips are wound up to a

2004215696 21 Oct 2010

77

coil, optionally after cooling to a temperature in the range from 40 to 70°C.

- 5 34. The process according to any one of claims 1 to 33, characterized in that the aqueous composition is applied by rolling on, flooding, knife-coating on, spraying, misting, brushing or dipping and optionally by subsequent squeezing off with a roll.
- 10 35. The process according to any one of claims 1 to 34, characterized in that the dried, and optionally cured film, has a pendulum hardness of 30 to 190 s, measured with a König pendulum hardness tester in accordance with DIN 53157.
- 15 36. The process according to any one of claims 1 to 35, characterized in that the dried, and optionally cured film, has a flexibility such that on bending over a conical mandrel in a mandrel flex test substantially in accordance with DIN ISO 6860 for a mandrel of 3.2 mm to 20 38 mm diameter - but without tearing the test area - no cracks longer than 2 mm which are detectable by a colour change due to the deposition to copper on the torn-open metallic surface following wetting with copper sulphate.
- 25 37. The process according to any one of claims 1 to 36, characterized in that at least one coating of printing ink, foil, lacquer, lacquer-like material, powder coating, adhesive and/or adhesive carrier is applied to 30 the dried, and optionally cured film.
- 35 38. The process according to any one of claims 1 to 37, characterized in that the coated metal components, strips or strip sections are shaped, lacquered, coated with polymers, such as PVC, printed, glued, hot-soldered, welded and/or joined to one another or to other elements by clinching or other joining techniques.
- 40 39. An aqueous composition for the pretreatment of a metallic surface before a further coating or for treatment of that

2004215696 21 Oct 2010

78

surface to form a film on the metallic surface, characterized in that the composition contains, in addition to water:

- 5 a) at least one hydrolysable or at least partly hydrolysed silane;
- b) at least one metal chelate that is stable in aqueous dispersions in the presence of components a), c) and d) and wherein the metal chelate is functional to improve the corrosion resistance and adhesion of the film;
- 10 c) at least one organic film-forming agent which contains at least one water-soluble or water-dispersed organic polymer or/and copolymer with an acid number in the range from 3 to 250, the content of organic film-forming agent, based on the solids content of the composition, being > 45 wt.%; and
- 15 d) at least one long-chain alcohol as a film-forming auxiliary.
- 20
40. Use of the substrates coated by the process according to any one of claims 1 to 38 as wire, strip, sheet metal or a component for a wire coil, a wire braid, a steel strip, a metal sheet, a lining, a screen, a vehicle body or a component of a vehicle body, a component of a vehicle, trailer, mobile home or missile, a cover, a housing, a lamp, a light, a traffic light element, a piece of furniture or furniture element, an element of a domestic appliance, a frame, a profile, a shaped component of complicated geometry, a crash barrier, heater or fence element, a bumper, a component of or with at least one tube or/and a profile, a window, door or bicycle frame or an item of hardware, such as a screw, nut, flange, spring, or a spectacle frame.
- 25
- 30
- 35
41. An aqueous composition for the pre-treatment or treatment of a metallic surface before a further coating or treatment of that surface substantially as hereinbefore

79

described with reference to the Examples, but excluding
Examples 42 to 50 and Comparative Examples.

5

CHEMETALL GMBH

WATERMARK PATENT & TRADE MARK ATTORNEYS

P26003AU00

2004215696 21 Oct 2010