

[19] Patents Registry
The Hong Kong Special Administrative Region
香港特別行政區
專利註冊處

[11] 1035552 B
EP 1100856 B1

[12]

STANDARD PATENT SPECIFICATION
標準專利說明書

[21] Application No. 申請編號
01106226.2

[51] Int.C1.⁸ C10M C10N

[22] Date of filing 提交日期
04.09.2001

[54] DIESEL ENGINE CYLINDER OILS 柴油機氣缸油

[30] Priority 優先權

11.06.1998 US 09/095825

[43] Date of publication of application 申請發表日期

04.01.2002

[45] Publication of the grant of the patent 批予專利的發表日期

27.01.2017

EP Application No. & Date 歐洲專利申請編號及日期

EP 99955490.0 02.06.1999

EP Publication No. & Date 歐洲專利申請發表編號及日期

EP 1100856 23.05.2001

Date of Grant in Designated Patent Office 指定專利當局批予專利日期

17.02.2016

[73] Proprietor 專利所有人

ExxonMobil Oil Corporation

3225 Gallows Road

Fairfax, Virginia 22037

UNITED STATES/UNITED STATES OF AMERICA

[72] Inventor 發明人

VINCENT M. CAREY

JOHN THOMAS FOGARTY

[74] Agent and / or address for service 代理人及/或送達地址

MARKS & CLERK

Level 9, Cyberport 1

100 Cyberport Road

Pok Fu Lam HONG KONG

(19)



(11)

EP 1 100 856 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention of the grant of the patent:
17.02.2016 Bulletin 2016/07

(21) Application number: **99955490.0**

(22) Date of filing: **02.06.1999**

(51) Int Cl.:

| | |
|---|---|
| C10M 169/04 <small>(2006.01)</small> | <i>C10M 169/04</i> <small>(2006.01)</small> |
| <i>C10M 101/02</i> <small>(2006.01)</small> | <i>C10M 133/12</i> <small>(2006.01)</small> |
| <i>C10M 133/56</i> <small>(2006.01)</small> | <i>C10M 145/06</i> <small>(2006.01)</small> |
| <i>C10M 159/22</i> <small>(2006.01)</small> | <i>C10M 159/24</i> <small>(2006.01)</small> |
| <i>C10N 20/02</i> <small>(2006.01)</small> | <i>C10N 30/02</i> <small>(2006.01)</small> |
| <i>C10N 30/04</i> <small>(2006.01)</small> | |

(86) International application number:
PCT/US1999/012145

(87) International publication number:
WO 1999/064543 (16.12.1999 Gazette 1999/50)

(54) **DIESEL ENGINE CYLINDER OILS**

ÖL FÜR ZYLINDER EINES DIESELMOTORS

HUILES POUR CYLINDRES DE MOTEUR DIESEL

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**

(30) Priority: **11.06.1998 US 95825**

(43) Date of publication of application:
23.05.2001 Bulletin 2001/21

(73) Proprietor: **ExxonMobil Oil Corporation
Fairfax, VA 22037 (US)**

(72) Inventors:
• **CAREY, Vincent M.
Sewell, NJ 08080-1622 (US)**
• **FOGARTY, John, Thomas
Mullica Hill, NJ 08062 (US)**

(74) Representative: **Jones, Helen M.M.
Gill Jennings & Every LLP
The Broadgate Tower
20 Primrose Street
London EC2A 2ES (GB)**

(56) References cited:
**EP-A- 0 331 359 EP-A- 0 369 804
EP-A- 0 839 894 US-A- 2 957 930
US-A- 3 361 669 US-A- 3 852 204
US-A- 3 878 115**

• **R.M. MORTIER et al., CHEMISTRY AND
TECHNOLOGY OF LUBRICANTS, 1992, pages
243-245, XP002919444.**

Remarks:

The file contains technical information submitted after the application was filed and not included in this specification

EP 1 100 856 B1

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

[0001] This invention relates to diesel engine cylinder oils.

[0002] In large, slow speed diesel engines of the crosshead type used in marine and heavy stationary applications, the cylinders are lubricated separately from the other engine components. The cylinders are lubricated on a total loss basis with the cylinder oil being injected separately to quills on each cylinder by means of lubricators positioned around the cylinder liner. Oil is distributed to the lubricators by means of pumps which are, in modern engine designs, actuated to apply the oil directly onto the rings to reduce wastage of the oil. The high stresses encountered in these engines and the use of heavy residual fuels create the need for lubricants with a high detergency and neutralizing capability even though the oils are exposed to thermal and other stresses only for short periods of time. Residual fuels commonly used in these slow speed diesel engines typically contain significant quantities of sulfur which, in the combustion process, combines with water to form sulfuric acid, the presence of which leads to corrosive wear. Cylinder oils contain high alkalinity reserves for neutralizing this acid, which is reflected in the total base number (TBN) of these oils, typically in the range of at least 30mg KOH/g, usually from 60 to 100 mg KOH/g, which is normally adequate with fuels containing two to three percent sulfur. When higher sulfur residual fuels are being used cylinder oils with TBN values of 70 are normally used although oils with TBN values up to and exceeding 100 mg KOH/g may be used, especially with high peak cylinder power ratings of 3,500kw per cylinder or more.

[0003] A requirement of these cylinder oils is that they should be thin enough to spread efficiently over the cylinder surface but yet thick enough to provide a continuous hydrodynamic film that will not evaporate off the walls of the upper cylinder when exposed to high combustion temperatures. Normally, oils with a viscosity grade of SAE 50 are satisfactory for lubricating both older and newer types of engine although heavier oils such as SAE 60 are contemplated. The SAE 50 grade corresponds to oils with kinematic viscosities within the range of 18.5 to 21.9 mm²/s (100°C), with the minimum at the lower end of the range being set by engine builder specifications and the upper limit by the SAE grade specification. Similarly, the SAE 60 oils will have kinematic viscosities extending over the range 21.9 to 26.1 mm²/s (100°C). The SAE 50 oils therefore correspond to a nominal 20 mm²/s (100°C) oil, and the SAE 60 oils to a nominal 24 mm²/s (100°C) oil; oils of these grades represent the nominal viscosity targets for the oils of the present invention. Another requirement for the oils is that they should not produce deposits which will lead to PIBton and/or port fouling. For this reason, good oxidation and thermal stability are required, manifested in actual performance by low PIBton ring groove packing as well as by reduced liner wear and minimized port fouling tendency.

[0004] In order to achieve the desired viscosity in the final product, relatively heavy base oils (heavy neutrals) are required. Bright stock may be used to supplement the viscosity of medium heavy neutrals if extra heavy neutrals are not available to provide the desired basestock viscosity. However, bright stocks are generally unsatisfactory in cylinder oil performance because of their poor oxidative and thermal stability and although other high viscosity oils could be used to boost the basestock viscosity, for example, high viscosity synthetic polyalphaolefin (PAO's), these are very costly, given the total loss usage of the cylinder oil. Another alternative would be to increase the viscosity contribution from the additives by an increased dispersant treat rate but again, the economics are not favorable to this as a technical solution.

[0005] US-A-3878115 discloses a marine diesel lubricant which utilizes polybutenes to improve deposit formation.

[0006] EP-A-0331359 discloses diesel oils and indicates improved viscosity, deposit, wear and oxidation properties when high molecular weight polybutene is included in the composition.

[0007] US-A-3852204 discloses marine diesel lubricants, in which polybutene (viscosity 30-600 SSU/210 F; MVW 25-950) is utilized to reduce deposits on the cylinder.

[0008] We have now developed improved diesel cylinder oils, useful in marine and heavy, low speed stationary diesels, which can be made from medium to medium heavy neutral base oils, typically from 65 to 110 mm²/s (300 to 500 SUS) without the need for extra heavy neutrals and which can be formulated without the use of bright stock in order to provide the desired final viscosity. Compared to current commercial products, the oils according to the present invention exhibit improved deposit characteristics, improved PIBton cleanliness, and improved load carrying as well as providing protection against corrosive, friction and abrasive wear under severe operating conditions. In use, they are expected to result in improved engine wear characteristics as indicated by PISon ring wear, cylinder liner wear, and PISon ring groove packing. Port cleanliness will also be improved.

[0009] According to the present invention, the diesel cylinder oils are produced with a kinematic viscosity in the range from 15 to 27mm²/s (100°C), corresponding to viscosity grades of SAE 50 or SAE 60. For these viscosity grades, the kinematic viscosity will normally be from 18.5 to 21.9 to 21 mm²/s (100°) for a nominal 20 mm²/s oil (SAE 50) and from 21.9 to 26.1 mm²/s (100°) for a nominal 24 mm²/s oil (SAE 60). The viscosity index of the improved oils is at least 95 and usually at least 100 and may be higher, typically from 105 to 120 with most of the oils having a viscosity index in the range of 105 to 115.

[0010] The present cylinder oils use a neutral base stock of 65 to 150 mm²/s (300 to 700 SUS) (40°C (100°F)) viscosity, eliminating the need to go to extra heavy neutral base oils of higher viscosity. Normally, the base stock will comprise at least 60 wt percent of the finished oil, usually 60 to 70 percent by weight. Because of its inferior stability, bright stock is

EP 1 100 856 B1

not a preferred option for viscosity control and if used at all, for example with the lightest neutrals, should be used in only minor amounts, typically not more than ten percent by weight of the formulation. The neutrals used as the main component of the oils will normally have viscosities in the range of 65 to 130 mm²/s (300 to 600 SUS) (40 °C (100°F)) although with the lower viscosity neutrals, it will be necessary to use a higher treat rate for the viscosity control component and possibly some of the other additives in order to achieve the final product viscosity.

[0011] The neutral base stocks will normally be API Group I or Group II base stocks; in view of the total loss usage of the cylinder oils, there is no advantage to the use of the higher quality Group III base stocks and, in fact, because of additive solvency problems associated with the highly paraffinic character of the Group III stocks, they are not normally preferred. Group I base stocks contains less than 90 percent saturates and/or greater than 0.0 percent sulfur and have a viscosity index greater than or equal to 80 and less than 120. Group II base stocks contain greater than or equal to 90 percent saturates and less than or equal to 0.03 percent sulfur with a viscosity index greater than or equal to 80 and less than 120.

[0012] A feature of the present cylinder oils is the use of polyisobutylene (PIB) in combination with the neutral base stock. The amount of PIB will normally be from 1 to 20 wt percent of the finished oil, generally from 4 to 15 wt percent, and in most cases from 4 to 12 wt percent of the finished oil. Polyisobutylene is a commercially available material from several manufacturers. The PIB used in the present formulations is a viscous oil-miscible liquid, with a weight molecular weight in the range of 1,000 to 8,000, usually 1,500 to 6,000, and a viscosity in the range of typically 2,000 to 6,000 mm²/s (100°C) (ASTM D-445). In most cases, the molecular weight will be in the range of 2,000 to 5,000 and the kinematic viscosity should be selected to be in the range of 3,000 to 4,500 mm²/s. The more viscous PIB's may be used to provide a greater contribution to product viscosity than the less viscous ones, and may therefore be used preferentially with the lighter neutral base stocks, for example, the 65 to 110 mm²/s (300-500 SUS) neutrals. In addition, the higher viscosity PIB's e.g., the PIB's of over 4,000 mm²/s viscosity may be used in lower amounts, resulting in improved product economics. Typically, the PIB's with a viscosity in the range of 3,000 to 5,000 mm²/s will be used in amounts from 4 to 6 wt. percent of the finished formulation, using neutral base stocks in the range of 110 to 130 mm²/s (500 to 600 SUS). With base stocks below 110 mm²/s (500 SUS), from 5 to 12 percent of the PIB will normally be satisfactory, the amount selected being dependent on the viscosity of the polymer. With methacrylate thickeners, the molecular weights will normally be higher but in any event, the molecular weight and the content of the thickener should together be sufficient to confer the desired viscosity on the oil.

[0013] In addition to the neutral base stock and the PIB component, the cylinder oils also preferably contain an additive package comprising a detergent component or components, an antioxidant, an antiwear agent, a dispersant, all of which are conventional in type, usage and treat rates. The detergent component or components preferably comprise one or more overbased phenates, phenylates, salicylates or sulfonates in order to confer the desired detergency and alkalinity characteristics on the finished oil. The overbased phenates and sulfonates are the preferred overbased detergents, most typically calcium carbonate, used alone or in combination with one another. These overbased metal salts are normally based on sodium, magnesium or calcium or barium, with preference given to calcium. The preferred detergents are the phenates with TBN values of at least 200, preferably at least 250, sulfonates with TBN values of at least 300 and mixtures of these. The total base number (mg KOH/g) for all the components of the detergent package should be at least 100 and preferably at least 200. Commercially available phenates sulfonates of these types with TBN values in the range of 100 to 500 are readily available commercially and are suitable. Commercial detergents normally contain an added defoamant, usually a silicone defoamant so that a defoamant component is normally also present in the finished defoamant so that a defoamant component is normally also present in the finished oils.

[0014] The total amount of the detergent package will normally be in the range of 15 to 35, generally 17 to 32, weight percent of the total lubricant, usually from 22 to 28 percent.

[0015] In addition to the detergent package, the oils preferably also include a dispersant. The preferred class of dispersants are the succinimides, which are the acylated amines or derivatives obtained by reaction of a carboxylic acylating agent, preferably a hydrocarbon-substituted succinic acid acylating agent with at least one amine containing a hydrogen attached to a nitrogen group. The nitrogen-containing carboxylic dispersants useful in the present cylinder oils are conventional in type; they are widely commercially available and have been described in many U.S. patents including 3,172,892; 3,341,542; 3,630,904; 3,215,707; 3,444,170; 3,632,51.1; 3,219,666; 3,454,607; 3,787,374; 3,316,177; 3,541,012 and 3,234,435. The preferred succinimide dispersants of this type are generally represented by succinimides (e.g., polyisobutylene succinic acid/anhydride (PIBSA)-polyamine having a PIBSA molecular weight of 700 to 2500). The dispersants may be borated or non-borated. Metal-blocked succinimides such as the zinc-blocked succinimides have better thermal stability and are preferred. The dispersant can be present in the amount of 0.5 to 5 weight percent, more preferably in the amount of 0.5 to 2 weight percent, e.g. 1 weight percent.

[0016] The oils also contain an antioxidant component in order to stabilize the oil and prevent deposit formation under the high temperatures encountered in the combustion chamber. The antioxidant may be either phenolic or aminic in character. The preferred phenolic compounds are the hindered phenolics which are the ones which contain a sterically hindered hydroxyl group, and these include those derivatives of dihydroxy aryl compounds in which the hydroxyl groups

are in the o- or p-position to each other. Typical phenolic antioxidants include the hindered phenols substituted with tertiary alkyl groups and the alkylene coupled derivatives of these hindered phenols. Examples of phenolic materials of this type include materials such as the tertiary alkylphenols e.g., o,o'-ditertiary alkyl phenols such as ditert-butyl phenol. 2-t-butyl-4-heptyl phenol; 2-t-butyl-4-octyl phenol; 2-t-butyl-4-dodecyl phenol; 2,6-di-t-butyl-4-heptyl phenol; 2,6-di-t-butyl-4-dodecyl phenol; 2-methyl-6-di-t-butyl-4-heptyl phenol; and 2-methyl-6-di-t-butyl-4-dodecyl phenol. Examples of ortho coupled phenols include: 2,2'-bis(6-t-butyl-4-heptyl phenol); 2,2'-bis(6-t-butyl-4-octyl phenol); and 2,2'-bis(6-t-butyl-4-dodecyl phenol) and phenolic esters.

[0017] Non-phenolic oxidation inhibitors, especially the aromatic amine antioxidants may also be used either as such or in combination with the phenolics. Typical examples of non-phenolic antioxidants include: alkylated and non-alkylated aromatic amines such as the aromatic monoamines of the formula $R^3R^4R^5N$ where R^3 is an aliphatic, aromatic or substituted aromatic group, R^4 is an aromatic or a substituted aromatic group, and R^5 is H, alkyl, aryl or $R^6S(O)_xR^7$ where R^6 is an alkylene, alkenylene, or aralkylene group, R^7 is a higher alkyl group, or an alkenyl, aryl, or alkaryl group, and x is 0, 1 or 2. The aliphatic group R^3 may contain from 1 to 20 carbon atoms, and preferably contains from 6 to 12 carbon atoms. The aliphatic group is a saturated aliphatic group. Preferably, both R^3 and R^4 are aromatic or substituted aromatic groups, and the aromatic group may be a fused ring aromatic group such as naphthyl. Aromatic groups R^3 and R^4 may be joined together with other groups such as S.

[0018] Typical aromatic amine antioxidants have alkyl substituent groups of at least 4 carbon atoms. Examples of aliphatic groups include butyl, hexyl, heptyl, octyl, nonyl, and decyl. Generally, the aliphatic groups will not contain more than 14 carbon atoms. The general types of amine antioxidants useful in the present compositions include diphenylamines, phenyl naphthylamines, phenothiazines, imidodibenzyls and diphenyl phenylene diamines. Mixtures of two or more aromatic amines are also useful. Polymeric amine antioxidants can also be used. Particular examples of aromatic amine antioxidants useful in the present invention include: the dialkyl diphenyl amines such as dibutyl, octyl butyl, or dioctyl diphenyl amine, p,p'-dioctyldiphenylamine; octylphenyl-beta-naphthylamine; t-octylphenyl-alpha-naphthylamine; phenyl-alphanaphthylamine; phenyl-beta-naphthylamine; p-octyl phenyl-alpha-naphthylamine; 4-octylphenyl-l-octyl-beta-naphthylamine. In these amines, the alkyl substituents are usually sterically hindered tertiary alkyl groups.

[0019] Normally, the total amount of antioxidant will not exceed 1 wt. percent of the total composition and normally will be not more than 0.5 wt. percent. Usually, from 0.3 to 0.5 wt. percent antioxidant is suitable.

[0020] It is desirable to include an antiwear and/or antiscuffing agent in the oils in order to reduce PIBton ring and cylinder liner wear and provide cylinder liner scuffing protection; for this purpose the sulfur-containing antiwear agents are preferred. Antiwear additives such as the metal dithiophosphates (e.g. zinc dialkyl dithiophosphate, ZDDP), metal dithiocarbonates, metal xanthates or tricrecylphosphate, as a non-sulfur containing antiwear agent, may be included. The sulfurised olefins such as sulfurised isobutylene also constitute a useful class of antiwear agents that are of utility in these cylinder oils and are readily available commercially. Other sulfur containing antiwear agents such as the dibenzyl sulfides can also be used. The antiwear additives can be present in the amount of 0.01 to 1.0 weight percent, usually 0.05 to 0.25 weight percent.

[0021] One embodiment of a nominal 20 mm²/s marine diesel cylinder oil has a viscosity index of at least 100, a total base number of at least 70 mg KOH/g and which comprises, in weight percent, from 65 to 70 percent of a neutral base oil having a viscosity from 85 to 130 mm²/s (400 to 600 SUS) (40°C (100°F)), from 4 to 6 percent of a polyisobutylene having a viscosity from 4,000 to 4,500 mm²/s (100°C), from 20 to 25 percent of an overbased detergent package comprising a combination of an overbased phenate having a TBN of at least 250 and a sulfonate detergent having a TBN of at least 400, from 0.5 to 2.0 percent of a polyisobutenyl substituted succinimide dispersant, from 0.1 to 0.5 percent of a sulfurized isobutylene antiwear agent, and from 0.1 to 1.0 percent of an aromatic amine antioxidant.

[0022] Another preferred embodiment of a nominal 20 mm²/s marine diesel cylinder oil has a viscosity index of at least 100, a total base number of at least 70 mg KOH/g and which comprises, in weight percent, from 65 to 70 percent of a neutral base oil having a viscosity from 85 to 130 mm²/s (400 to 600 SUS) (40°C (100°F)), from 4 to 5 percent of a polyisobutylene having a viscosity from 4,000 to 4,500 mm²/s (100°C), from 20 to 25 percent of an overbased detergent package comprising a combination of an overbased phenate having a TBN of at least 250 and a sulfonate detergent having a TBN of at least 400, from 0.5 to 1.0 percent of a polyisobutenyl substituted succinimide dispersant, from 0.1 to 0.5 percent of a sulfurized isobutylene antiwear agent, and from 0.1 to 0.5 percent of an aromatic amine antioxidant.

[0023] Another preferred embodiment of a nominal 20 mm²/s marine diesel cylinder oil has a viscosity index of at least 100, a total base number of at least 70 mg KOH/g and which comprises, in weight percent, from 60 to 65 percent of a neutral base oil having a viscosity from 65 to 85 mm²/s (300 to 400 SUS) (40 °C (100 °F)), from 8 to 12 percent of a polyisobutylene having a viscosity from 3,000 to 3,500 mm²/s (100°C), from 20 to 28 percent of an overbased detergent package comprising a combination of an overbased phenate having a TBN of at least 250 and a sulfonate detergent having a TBN of at least 400, from 0.5 to 2.0 percent of a polyisobutenyl antiwear agent, and from 0.1 to 1.0 percent of an aromatic amine antioxidant.

[0024] Other conventional additives may be present for their own functionality, if desired.

[0025] In terms of performance, the present cylinder oils exhibit improved PISTon ring and cylinder liner wear charac-

EP 1 100 856 B1

teristics compared to previous cylinder oils and they are notably improved in respect to PISTon groove packing ratings and other performance characteristics desirable in cylinder oils for slow speed diesel engines. These improvements in performance are demonstrated in the following comparative examples.

5 Example 1

[0026] An oil according to the present invention was formulated and compared in bench and engine testing with a known cylinder oil (Comparative Oil A). The compositions and test results are shown below in Table 1.

| Table 1 | | | |
|---|-------------|-----------|----------------------|
| Formulation Comparison | | | |
| | Camp. Oil A | Example 1 | |
| Component Description, wt. per. | | | |
| Detergent, dispersant, antiwear, antioxidant package | 19.20 | 19.20 | |
| Sulfonate (300 - 400 TBN)* | 6-9 | 6-9 | |
| 850N Base Oil, Group 1 | 72.50 | | |
| SOON Base Oil, Group 1 | | 68.00 | |
| Polyisobutylene | | 4.50 | |
| * Preblend to provide 25 TBN sulfonate to finished oil | | | |
| Performance Characteristics | | | Effect of PIB |
| KV @ 100C, mm ² /s | 20.5 | 20.5 | Maintain KV |
| Viscosity Index | 101 | 106 | Improved |
| B-10 Vise Increase | 30 | 30 | Equal |
| Hot Tube Rating | 3 | 3 | Equal |
| 30-day Storage Haze/Deposits | Nil/Nil | Nil/Nil | Equal |
| Oven Gel Deposits | None | None | Equal |
| Water Separation, % Clear Oil | 99.0 | 98.9 | Equal |
| Full-Scale Engine Testing | | | |
| Av. Ring Wear, mm/1000 hrs | 0.30 | 0.22 | Improved |
| Av. Liner Wear, mm/1000 hrs | 0.029 | 0.028 | Equal |
| PIBton Demerit Rating | 2.4 | 2.3 | Equal |
| PIBton Top Groove Fill, % | 57 | 46 | Improved |
| Polyisobutylene, m.w. 2,000- 2,500, KV (99°C) 4069-4382 | | | |

Example 2

[0027] A Further comparison was made between the conventional commercial cylinder oil and an oil according to the invention.

| Formulation Comparison | | | |
|--------------------------|-------------|-----------|--|
| | Comp. Oil A | Example 2 | |
| Component Description | | | |
| Sulfonate (300-400 TBN)* | 6-9 | 6-9 | |

EP 1 100 856 B1

(continued)

| | | | | |
|----|--|-------------|-----------|----------------------|
| | Component Description | Comp. Oil A | Example 2 | |
| 5 | Detergent, dispersant, antiwear, antioxidant package | 19.20 | 19.20 | |
| | 850N Base Oil, Group 1 | 72.50 | | |
| | 500N Base Oil, Group 2 | | 69.80 | |
| 10 | Polyisobutylene | | 4.50 | |
| | *Preblend to provide 25 TBN sulphonate to finished oil | | | |
| | Performance Characteristics | | | Effect of PIB |
| 15 | KV @ 100C, mm ² /s | 20.5 | 20.5 | Maintain KV |
| | Viscosity Index | 101 | 114 | Improved |
| | B-10 Visc Increase | 27 | 24 | Improved |
| 20 | Hot Tube Rating | 3 | 24 | Equal |
| | 30-day Storage Haze/Deposits | Nil/Nil | Nil/Nil | Equal |
| | Oven Gel Deposits | None | None | Equal |
| | Water Separation, % Clear Oil | 99.0 | 98.6 | Equal |
| 25 | | | | |
| | <u>Full-Scale Engine Testing</u> | | | |
| | Av. Ring Wear, mm/1000 hrs | 0.47 | .045 | Equal |
| 30 | Av. Ring Liner, mm/1000 hrs | 0.04 | 0.02 | Improved |
| | PIBton Demerit Rating | 3.4 | 3.0 | Improved |
| | PIBton Top Groove Fill, % | 61 | 36 | Improved |
| 35 | Notes: | | | |
| | Polyisobutylene, m.w. 2,000-2,500, KV (99°C) 4069-4382 | | | |

Example 3

[0028] A comparison was made between another conventional commercial cylinder oil, Comparison Oil B, and another oil according to the invention.

| | | | | |
|----|--|----------------|-----------|--|
| | | Table 3 | | |
| 45 | Formulation Comparison | | | |
| | | | | |
| | Component Description, wt. pet. | Comp. Oil B | Example 3 | |
| | Phenate (255 TBN) | 17.70 | 17.70 | |
| 50 | Sulfonate (300-400TBN) | 6.50 | 6.50 | |
| | Detergent, dispersant, antiwear, antioxidant package | 19.20 | 19.20 | |
| | 850N Base Oil, Group 1 | 74.30 | | |
| 55 | 300N Base Oil, Group 1 | | 63.10 | |
| | Polyisobutylene, m.w. 2060 av., KV (99 °C) | | 11.20 | |

EP 1 100 856 B1

(continued)

5
10
15
20

| Component Description, wt. pet. | Camp. Oil B | Example 3 | |
|-------------------------------------|-------------|-----------|----------------------|
| | | | |
| Performance Characteristic s | | | Effect of PIB |
| KV@ 100C, mm ² /s | 20.5 | 20.5 | Maintain KV |
| Viscosity Index | 101 | 113 | Improved |
| 30-day Storage Haze/Deposits | Nil/Nil | Trace/Nil | Equal |
| Oven Gel Deposits | None | None | Equal |
| | | | |
| Full-Scale Engine Testing | | | |
| Av. Ring Wear, mm/1000 hrs | 0.36 | 0.39 | Equal |
| Av. Liner Wear, mm/1000 hrs | 0.03 | 0.02 | Equal |
| PIBton Demerit Rating | 3.4 | 2.9 | Improved |
| PIBton Top Groove Fill, % | 60 | 53 | Improved |

Outline of Test Procedures

25
30
35
40

[0029] In the B-10 test, 50 ml. of oil is placed in a glass all together with iron, copper, and aluminum catalysts and a weight lead corrosion specimen. The cell and its contents are placed in a bath maintained at 191° C. and 10 liters/hr of dried air is bubbled through the sample for 24 hours. The cell is removed from the bath and the catalyst assembly is removed from the cell. The oil is examined for the presence of sludge and the Kinematic Viscosity at 100 °C. (ASTM D 445) determined. The lead specimen is cleaned and weighed to determine the loss in weight.

Hot Tube Test

[0030] Lubricating oil and house air are fed at controlled rates through a heated Pyrex[®] glass capillary tube. The oil and air are brought together via a Pyrex[®] glass tee that is connected to the bottom of the capillary tube. As the oil is metered into the glass tee, the air picks up the oil and carries it up through the vertical glass capillary tube which passes through an electrically heated and temperature controlled aluminum block. The heated oil and air mixture then exits from the top of the glass capillary into a collecting beaker for the oxidized oil. At test completion, the glass capillary tubes are removed from the heating block then flushed with ASTM naphtha and rated for laquer and carbon deposits, using reference standards. A rating scale from 1 to 10 is used, 1 being clean and 10 being the worst with heavy black carbon/coke deposits.

Claims

45
50
55

1. A diesel cylinder oil, having a viscosity of 15 to 27 mm²/s, a viscosity index of at least 95 and a total base number of at least 40 mg KOH/g, which comprises an API Group I or Group II neutral base stock of viscosity in the range 65 to 150 mm²/s (300 to 700 SUS) (40°C (100°F)), from 2 to 15 wt.% of the oil of an oil-soluble, liquid polyisobutylene having a viscosity from 1,500 to 8,000 mm²/s (100°C), and a molecular weight in the range 1,000 to 8,000, and an aromatic amine antioxidant component.
2. A diesel cylinder oil according to claim 1, wherein the amount of the aromatic amine antioxidant compound is from 0.1 to 1 weight percent of the oil.
3. A diesel cylinder oil according to claim 1 which comprises from 60 to 70 wt.percent of the base stock oil.
4. A diesel cylinder oil according to claim 2 in which the basestock is an API Group I or Group II oil having a viscosity of 65 to 130 mm²/s (300 to 600 SUS) (40°C (100°F)).

EP 1 100 856 B1

5. A diesel cylinder oil according to Claim 1 having a viscosity of 19 to 21 mm²/s (100°C).
6. A diesel cylinder oil according to claim 1 which includes from 4 to 12 wt.percent of the oil of a polyisobutylene having a viscosity of 2,000 to 5,000 mm²/s (100°C).
7. A diesel cylinder oil according to claim 1 which has a total base number of 40 to 100 mg KOH/g.
8. A diesel cylinder oil according to claim 1 which includes an additive package comprising at least one overbased detergent having a TBN of at least 200 mg KOH/g, a dispersant, an antioxidant and antiwear agent.

Patentansprüche

1. Ein Dieselylinderöl mit einer Viskosität von 15 bis 27 mm²/s, einem Viskositätsindex von mindestens 95 und einer Basenzahl von mindestens 40 mg KOH/g, das ein neutrales Grundöl der API-Gruppe I oder Gruppe II mit einer Viskosität im Bereich von 65 bis 150 mm²/s (300 bis 700 SUS) (40°C (100°F)), 2 bis 15 Gew.-% des Öls eines öllöslichen, flüssigen Polyisobutylens mit einer Viskosität von ca. 1500 bis 8000 mm²/s (100°C) und eine Molekülmasse im Bereich von 1000 bis 8000 und einen aromatischen Amin-Antioxidans-Bestandteil aufweist.
2. Ein Dieselylinderöl entsprechend Anspruch 1, wobei die Menge der aromatischen Amin-Antioxidans-Verbindung zwischen 0,1 bis 1 Gewichtsprozent des Öls ausmacht.
3. Ein Dieselylinderöl entsprechend Anspruch 1, das zwischen 60 bis 70 Gew.-% des Grundöls umfasst.
4. Ein Dieselylinderöl entsprechend Anspruch 2, bei dem das Grundöl ein Öl der API-Gruppe I oder Gruppe II mit einer Viskosität von 65 bis 130 mm²/s (300 bis 600 SUS) (40°C (100°F)) ist.
5. Ein Dieselylinderöl entsprechend Anspruch 1 mit einer Viskosität von 19 bis 21 mm²/s (100°C).
6. Ein Dieselylinderöl entsprechend Anspruch 1, das zwischen 4 bis 12 Gew.-% des Öls eines Polyisobutylens mit einer Viskosität von 2000 bis 5000 mm²/s enthält.
7. Ein Dieselylinderöl entsprechend Anspruch 1, das eine Basenzahl von 40 bis 100 mg KOG/g hat.
8. Ein Dieselylinderöl entsprechend Anspruch 1, das ein Zusatzstoffpaket enthält, das zumindest ein überbasisches Detergenz mit einer TBN von mindestens 200 mg KOG/g, ein Dispergiermittel, ein Antioxidans und ein Verschleißschutzmittel enthält.

Revendications

1. Huile pour cylindre de moteur Diesel ayant une viscosité qui va de de 15 à 27 mm²/s, un indice de viscosité d'au moins de 95 et un indice d'alcalinité d'au moins 40 mg KOH/g, qui comprend une huile de base neutre du groupe I ou du groupe II de la classification API dont la viscosité est dans la plage de 65 à 150 mm²/s (300 à 700 SUS) [40 °C (100 °F)], de 2 à 15 % en poids de l'huile d'un polyisobutylène liquide soluble dans l'huile dont la viscosité va de 1 500 à 8 000 mm²/s (100 °C) et dont le poids moléculaire est dans la plage de 1 000 à 8 000 et un composant amine aromatique antioxydant.
2. Huile pour cylindre de moteur Diesel selon la revendication 1, dans laquelle la quantité du composant amine aromatique antioxydant est de 0,1 à 1 pour cent en poids de l'huile.
3. Huile pour cylindre de moteur Diesel selon la revendication 1, qui comprend de 60 à 70 pour cent en poids de l'huile de base.
4. Huile pour cylindre de moteur Diesel selon la revendication 2, dans laquelle l'huile de base est une huile du groupe I ou du groupe II de la classification API dont la viscosité va de 65 à 130 mm²/s (300 à 600 SUS) [40 °C (100 °F)].
5. Huile pour cylindre de moteur Diesel selon la revendication 1, dont la viscosité va de 19 à 21 mm²/s (100 °C).

EP 1 100 856 B1

6. Huile pour cylindre de moteur Diesel selon la revendication 1, qui inclut de 4 à 12 pour cent en poids de l'huile d'un polyisobutylène dont la viscosité va de 2 000 à 5 000 mm²/s (100 °C).
7. Huile pour cylindre de moteur Diesel selon la revendication 1, dont l'indice d'alcalinité va de 40 à 100 mg KOH/g.
8. Huile pour cylindre de moteur Diesel selon la revendication 1, qui inclut un paquet d'additifs comprenant au moins un détergent surbasé ayant un indice d'alcalinité d'au moins 200 mg KOH/g, un dispersant, un agent antioxydant et un agent anti-usure.

5

10

15

20

25

30

35

40

45

50

55

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 3878115 A [0005]
- EP 0331359 A [0006]
- US 3852204 A [0007]
- US 3172892 A [0015]
- US 3341542 A [0015]
- US 3630904 A [0015]
- US 3215707 A [0015]
- US 3444170 A [0015]
- US 363251 A [0015]
- US 3219666 A [0015]
- US 3454607 A [0015]
- US 3787374 A [0015]
- US 3316177 A [0015]
- US 3541012 A [0015]
- US 3234435 A [0015]