



Office de la Propriété  
Intellectuelle  
du Canada

Un organisme  
d'Industrie Canada

Canadian  
Intellectual Property  
Office

An agency of  
Industry Canada

CA 2077875 C 2004/03/30

(11)(21) **2 077 875**

(12) **BREVET CANADIEN  
CANADIAN PATENT**

(13) **C**

(22) Date de dépôt/Filing Date: 1992/09/09

(41) Mise à la disp. pub./Open to Public Insp.: 1993/03/11

(45) Date de délivrance/Issue Date: 2004/03/30

(30) Priorité/Priority: 1991/09/10 (757,243) US

(51) Cl.Int.<sup>5</sup>/Int.Cl.<sup>5</sup> A24D 1/02, D21H 11/16

(72) Inventeurs/Inventors:  
BALDWIN, SHERYL D., US;  
GAUTAM, NAVIN, US;  
HOUGHTON, KENNETH S., US;  
ROGERS, ROBERT M., US;  
RYDER, JUDITH L., US

(73) Propriétaire/Owner:  
PHILIP MORRIS PRODUCTS INC., US

(74) Agent: RIDOUT & MAYBEE LLP

(54) Titre : PAPIER A CIGARETTES SERVANT A REDUIRE LA VITESSE DE COMBUSTION ET METHODE DE  
FABRICATION DE CELUI-CI

(54) Title: SMOKING ARTICLE WRAPPER FOR CONTROLLING BURN RATE AND METHOD FOR MAKING SAME

(57) **Abrégé/Abstract:**

This invention relates to the control of the burn rate of a cigarette. The burn rate is controlled by the use of a paper wrapper to which regions of cellulosic material is applied and bonded. The cellulosic material is applied during a manufacturing step for the base paper wrapper, either off or on-line of the paper wrapper-forming machine.



2077875

Abstract Of The Disclosure

This invention relates to the control of the burn rate of a cigarette. The burn rate is controlled by the use of a paper wrapper to which regions of  
5 cellulosic material is applied and bonded. The cellulosic material is applied during a manufacturing step for the base paper wrapper, either off or on-line of the paper wrapper-forming machine.

AS FILED

EXPRESS MAIL LABEL  
No. FB324252984  
PM-1479SMOKING ARTICLE WRAPPER FOR CONTROLLING  
BURN RATE AND METHOD FOR MAKING SAMEBackground Of The Invention

The present invention relates to a paper  
5 wrapper construction for use in conjunction with a  
smoking article, such as a cigarette. Specifically the  
paper wrapper of this invention can be used to  
effectively control the burn rate of the smoking  
article. The paper wrapper of the present invention  
10 comprises cellulosic material which is applied to  
regions of a base paper web.

It is beneficial to make cigarettes in  
commercial quantities which will have a reduced burn  
rate if not drawn on by the smoker but which look,  
15 feel, taste and burn like conventional cigarettes when  
being drawn on by the smoker at normal intervals. It  
is recognized by those skilled in the art that the  
wrapper configuration and construction strongly  
influences these characteristics.

20 Cigarette wrappers, i.e., papers, have known  
burn characteristics, including burn rates and static  
burn capabilities. There have been various attempts to  
modify the burn characteristics of such wrappers.  
These attempts have employed a variety of wrapper  
25 configurations and constructions.

For example, it is known that the burn  
characteristics can be modified by adding fillers,

- 2 -

coatings, or additives to the papers. Weinert United States Patent No. 4,489,650 refers to a self-extinguishing cigarette in which the interior surface of the wrapper is coated with clay. In Cohn United States Patent No. 4,044,778, the cigarette wrapper referred to includes rings or areas coated with deposits from an alkali silicate solution which renders the wrapper non-burning in the coated areas.

In Adams et al. United States Patent No. 4,889,145, the cigarette wrapper referred to includes an area containing a coating of a porosity reducing composition. The coating is comprised of a non-polymer with a polymer binder. Examples of the non-polymer were given as a fatty alcohol and a fatty acid salt.

Durocher United States Patent No. 4,615,345 refers to another attempt to modify the burn characteristics of wrappers. In Durocher the wrapper is made of a cellulose fiber base which normally does not sustain burning when the wrapper is incorporated into a cigarette. This type of wrapper is treated in selected zones with an alkali metal burn promoter such as the potassium salt of citric acid. It is referred to therein that a cigarette made with a wrapper so treated will smolder without being drawn on by the smoker when in the treated zone but when the treated zone is consumed will extinguish itself unless the cigarette is drawn on by the smoker.

Baker et al. United States Patent No. 4,077,414 also refers to a wrapper with modified burn characteristics. In Baker, a wrapper with inherently high porosity is modified by treating the paper with what was referred to as a "gel-forming" substance so as to produce bands of low porosity regions. The "gel-forming" substances disclosed in Baker were all soluble



- 3 -

in water and thus were solutions, as opposed to slurries, when applied to the cigarette paper wrapper.

In addition to modifying wrapper burn characteristics by adding fillers, coatings or burn additives directly to the base paper web, burn characteristics have been shown to be able to be modified by applying to the base paper web a strip or patch of a paper having different characteristics than the base web to be modified. For example, it is shown in Canadian patent application No. 2,054,219 filed on October 28, 1991 and laid open on May 01, 1992, that cigarette paper can be modified by applying strips of a different paper at periodically spaced positions across the width of the paper web, so that cigarettes produced from the paper web have periodically spaced circumferential bands on the inside of the paper for modifying the burning characteristics of the paper and the cigarette. One treated paper material suitable for forming the periodically spaced strips is described in Hampl United States Patent No. 4,739,775. However, the wrappers discussed in Hampl were formed by the adhesion of the treated paper material to the base paper web by a process which would be difficult and costly to use for mass production.

As discussed above, various types of cigarette wrapper configurations have been proposed for modifying the burn characteristics of cigarettes. However, these wrappers have various problems and disadvantages. Although the wrappers of Weinert and Cohn produce cigarettes with modified burn characteristics, they do not look, feel, taste and burn like conventional cigarettes when being drawn on by the smoker. Although the wrappers of Durocher solve some of the problems exhibited by the Weinert and Cohn wrappers, Durocher did not disclose a process for making such cigarette wrappers in commercial quantities. In addition, although Canadian patent application No. 2,054,219 discloses commercially feasible methods that can produce wrappers with both

- 4 -

modified burn characteristics and that look, feel, taste and burn like a conventional cigarette when being drawn on by the smoker, such methods are not the only solutions to the problems discussed. Additionally, the wrappers and coatings referred to in Baker et al. and Adams et al. are not the only types that can potentially modify the burn rate of a cigarette.

Johnson United States Patent No. 4,861,427 refers to a fibrous web product with bacterial cellulose as a surface treatment. In Johnson the bacterial cellulose treatment referred to is applied to the entire web. The resulting coating web is used as printing materials which have gloss, smoothness, ink receptivity and surface strength.

Johnson does not refer to the application of the cellulose to papers in selected portions of the web, i.e., in bands or other patterns, nor does Johnson refer to burn control properties that such an application of bacterial cellulose will impart to the resulting paper. Johnson does not disclose the use of the coated web for cigarette paper.

It would be desirable to provide a paper wrapper for a smoking article that effectively controls the burn rate of the smoking article.

It would also be desirable to provide a paper wrapper for a smoking article that looks, feels, tastes and burns like a conventional cigarette when being drawn on by the smoker.

It would further be desirable to provide a paper wrapper in which burn rate control can be achieved economically with mass-production techniques.

#### Summary Of The Invention

It is an object of this invention to provide a paper wrapper for a smoking article that can modify the burn characteristics of the smoking article.



- 5 -

It is also an object of this invention to provide such wrappers that, when used to make cigarettes, provides a cigarette with the further advantage of looking, feeling, tasting and burning like a conventional cigarette when being drawn on by the smoker at normal intervals.

It is also an object of this invention to provide a paper wrapper in which a banded area for controlling burn rate can be applied during manufacture of the base paper wrapper, either off or on-line of the paper machine, but beyond the wet end of the paper machine.

Furthermore, it is an object of this invention to provide a banded paper wrapper that can be manufactured in commercial quantities and in conjunction with commercial cigarette making operations without the need for non-conventional apparatuses.

In accordance with one aspect of the present invention, there is provided a paper wrapper for a smoking article comprising a paper base web having one or more regions of microfibrillated fibrous cellulose bonded to the paper base web, the said regions being provided by a microfibrillated fibrous cellulose suspension applied directly to the paper base web, the regions of fibrous cellulose adding between about 0.5 g/m<sup>2</sup> and about 10 g/m<sup>2</sup> dry weight on top of the base paper.

The fibrous cellulose can be selected from the group consisting of microcrystalline cellulose and bacterial cellulose as well as other new forms of fibrous cellulose capable of forming a stable suspension in liquid and thus capable of being printed or coated onto a base paper web. This paper wrapper can be incorporated into a smoking article comprising a tobacco filler and said paper wrapper.

In addition, a method for making the smoking article wrapper is also provided. This method comprises the steps of advancing the base paper web along a travel path and applying a stable suspension of microfibrillated

- 6 -

cellulosic material in a liquid directly to the base paper web at a position on the path to form one or more regions of microfibrillated fibrous cellulose on the web, the regions of microfibrillated fibrous cellulose adding between about 0.5 g/m<sup>2</sup> and about 10 g/m<sup>2</sup> dry weight on top of the base paper.

The fibrous cellulose-applying position can comprise applying a slurry of cellulosic material and water to the said base paper web and thus form the smoking article wrapper.

The paper wrapper of this invention may be used for cigarettes of any length of circumference and having different fillers, such as tobacco, expanded tobacco, a variety of tobacco blend types, reconstituted tobacco materials, non-tobacco filler materials and combinations thereof.

#### Detailed Description Of The Invention

Paper consists of a web of cellulosic fibers held together by hydrogen bonding. A paper web without an inorganic filler such as calcium carbonate is non-porous and either does not burn or burns very slowly. The calcium carbonate, or other inorganic filler, present in cigarette paper disrupts the fiber bonding and opens the structure of the paper to allow the entry of air to support combustion. The invention disclosed herein consists of the application of additional cellulose fibers, fibrils or microfibrils onto the surface of a base paper web in order to modify and tailor the burn characteristics of the resulting paper web. When such a paper web is incorporated into the



wrapper of a smoking article, the burn characteristics of the resulting smoking article are also modified.

As used herein, the term "fibrous cellulose" is defined to mean cellulose in the form of either  
5 fibers, fibrils or microfibrils, or any combination thereof in various states of subdivision. "Fibrils" are the threadlike elements of the wall of the cellulose fiber visible with an optical microscope. Upon examination by electron microscopy "fibrils" are  
10 found to consist of still finer "microfibrils."

The base paper web of the present invention is a conventional cigarette paper onto which is applied a slurry of fibrous cellulose (i.e., fibers, fibrils, or microfibrils, or any combination thereof in various  
15 states of subdivision). A main advantage of the present invention is that the fibrous cellulose can be applied by means of various conventional coating or printing techniques. Furthermore, the fibers, fibrils or microfibrils can be applied on-line or off-line of  
20 the base paper making apparatus beyond the wet end of the paper machine. As a result of the above advantages, smoking articles incorporating the wrappers disclosed herein can be mass produced.

A unique aspect of the present invention is  
25 that the application of the slurry of fibrous cellulose under the processes disclosed herein results in a dense mat of fibers, fibrils or microfibrils present on the surface of the base paper web as revealed by scanning electron microscopy studies. It is believed that the  
30 dense mat of fibrous cellulose which contains no inorganic filler or added burn chemicals, provides a region which slows combustion. The dense mat of fibrous cellulose then can be used to control the burn rate of a cigarette. A smoking article incorporating a  
35 wrapper with the dense mat of fibrous cellulose of the

present invention can thus have simplified burn rate control. Burn rate control can be modified or tailored to the extent desired by optimizing the application level of the fibrous cellulose or the width and spacing  
5 of the regions or bands of the dense mat of fibrous cellulose.

The cigarette with which the paper wrapper of this invention may be used may be of any length or circumference. Preferably, the circumference of the  
10 cigarette may be in the range from about 15 millimeters to about 28 millimeters. In addition, the cigarettes with which the paper wrapper of this invention may be used may contain various fillers such as tobacco, expanded tobacco, a variety of tobacco blend types,  
15 reconstituted tobacco materials, non-tobacco filler materials and combinations thereof.

The paper wrappers of this invention may be made from flax or other cellulosic fibers, such as wood pulp or esparto, and an inorganic filler, typically  
20 calcium carbonate, with a loading of between about 20 percent by weight and about 40 percent by weight. Other suitable conventional mineral fillers, or a combination of fillers, may be used such as the various phases of calcium or magnesium carbonates, or the like,  
25 along with hydroxides of magnesium or the like. Burn additives such as citrates, phosphates, succinates or the like may also be used in the paper wrappers.

Cigarette papers in use cover a wide range in porosity and burn rate. The inherent porosity of the  
30 paper varies from about 2 to about 150 Coresta units. Papers with lower values for inherent porosity require less added fibrous cellulose in the banded region to control the burn rate than papers with higher values. Therefore simple experimentation will be required to  
35 adjust the level of slurry applied to the base paper

based on the type of base paper used and the desired burn characteristics. Preferably, the base paper should have a basis weight of about 25 to about 30 g/m<sup>2</sup>; the inherent porosity should be in the range from about 20 to about 60 Corresta units; the calcium carbonate concentration should be in the range from about 25 to about 37 percent; and the citrate concentration should be in the range from about 0.5 to about 3 percent. In the Examples discussed below, the base paper (referred to as "conventional cigarette wrapper") had the following characteristics unless specifically stated otherwise: basis weight of about 25 g/m<sup>2</sup>, inherent porosity in the range from about 25 to about 30 Corresta units, calcium carbonate concentration in the range from about 25 to about 30 percent and citrate concentration in the range from about 0.5 to about 3 percent.

The addition of a fibrous cellulose to form regions or bands in the paper wrapper has been found to affect the burn rate of the resulting cigarette. A slurry of the fibrous cellulose is applied to the paper wrapper, in the desired locations and patterns, during or after the initial manufacturing of the base paper wrapper. If the slurry is applied during the initial manufacturing, this step should preferably be performed beyond the wet end of the base paper making apparatus.

Any cellulose material capable of forming a suspension in a liquid which is sufficiently stable for coating or printing may be used. Preferably, the cellulose material is suspended in water, thus forming a stable slurry since cellulose is insoluble in water. A first preferred cellulosic material is microcrystalline cellulose. Most preferably, it is a microcrystalline cellulose in combination with a binder to form a colloidal suspension of cellulose and binder.



Such a preferred cellulosic material is AVICEL™ CL-611 cellulose available from the FMC Corporation of Philadelphia, Pennsylvania. AVICEL™ CL-611 is a colloidal dispersion of microcrystalline cellulose co-processed with sodium carboxymethyl cellulose (about 10 to about 15 % by weight). A second preferred cellulosic material is a bacterial cellulose material. Such a preferred bacterial cellulose is CELLULON™ available from the Weyerhaeuser Company of Tacoma, Washington. CELLULON™ fiber is available in the solid composition form of from about 15 to about 20 wt.% of bacterial cellulose and about 79 to about 85 wt.% water. A third cellulosic material capable of forming a stable suspension is Buckeye™ Expanded Fibers, which is a highly refined and fibrillated cellulose made using mechanical abrasion and supplied by Proctor and Gamble Co. of Cincinnati, Ohio. A fourth cellulosic material capable of forming a stable suspension is the new form of microcrystalline cellulose FIRBROCELL™ developed and sold by Resources Industries Inc. (Emerson, New Jersey).

In addition to the specific types of cellulosic material disclosed in the preceding paragraph, this invention contemplates that there are other novel forms of cellulosic material that are capable of forming a stable suspension in liquid and thus capable of being able to be incorporated into the smoking article wrappers of the present invention. The only requirement on the cellulosic material is that it must be able to form a sufficiently stable suspension in a liquid so that the suspension can be printed or coated onto the base paper web of the present invention.

The ability of the cellulosic material of the present invention to form a stable suspension is a

unique feature of this invention. If the cellulosic material is not capable of forming a stable suspension in liquid then the cellulosic material will either "settle out" of solution or "dissolve" into solution.

5 Excessive "settling" of the fibrous cellulose would destroy the potential to print or coat cellulose in the fibrous form onto a base paper web as disclosed in the present invention. It should be noted that the materials disclosed herein generally do require  
10 considerable agitation to maintain the suspension and are not permanently stable as is a solution or a true gel, but they are intermediate in character compared to those materials and to totally heterogeneous slurries.

If the fibrous cellulose "settles out" of  
15 solution, then the fibrous cellulose will collect at the bottom of the mixing apparatus or will plug orifices of spray/application devices and thus would be incapable of being printed or coated onto a base paper web using conventional printing or coating techniques,  
20 which is a unique aspect of the present invention. Furthermore, even if this first printing/coating problem were surmounted then a second problem would still exist. This later problem is a result of the fact that adhesion of the fibrous cellulose to the base  
25 paper web would be difficult without the addition of a binding material to the fibrous cellulose. This is a result of the fact that a key feature of the present invention is that the fibrous celluloses disclosed herein are capable of bonding, with or without the  
30 addition of a binding material, to an underlying base paper web. Such bonding (generally hydrogen bonding) is possible because of the high surface area or the high degree of refining of the fibrous cellulose materials disclosed herein compared to that of  
35 conventional paper making fibers. Because of these



- 12 -

characteristics they are inherently capable of hydrating extensively and thus are able to form more stable suspensions in water than are conventional paper making fibers. The ability of the cellulose materials contemplated by this invention to hydrate extensively is believed to be related to the increase in surface area of cellulose when cellulose fibers undergo refining or other processes. Refinement creates a high degree of fibrillation and/or exposes microfibrils along the cellulose fiber and thus results in an increase in surface area. It is believed that this increase in surface area creates more sites for hydration of the fibers in the slurry or suspension and thus increases the swelling of the fibers which augments the stabilization of the slurry or suspension and thus allows the fibrous cellulose to adhere to an underlying base paper web. The adhesion of the refined fibrous cellulose to an underlying base paper web allows regions of burn rate altering material to be formed on a smoking article wrapper. A desirable feature of this burn altering region is that it does not include any material that is foreign to the base paper web: it only includes fibrous cellulose with or without binder.

25           If the fibrous cellulose material does form a sufficiently stable suspension in liquid (i.e., does not "settle out" rapidly) then the suspension will be able to be coated or printed on to a base paper web and form regions of fibrous cellulose capable of altering and tailoring the burn rate of a smoking article. 30           Because of the increase in surface area of refined cellulose materials there are more sites for hydrogen bonding to take place, and thus more sites for adhesion to occur to an underlying base paper web without or 35           with minimal need for a binder. In summary, any new or



novel fibrous cellulosic material that exhibits the properties discussed herein is capable of being incorporated into the smoking article of this invention.

5 Homogenization of the cellulosic material prior to slurry make-up has been found to enhance the rheological properties of the slurry and therefore allows for a greater flexibility in slurry application techniques. Binders which may be used with the  
10 cellulosic material are carboxymethyl cellulose (CMC), hydroxypropyl cellulose, starch, guar, or various other polysaccharide binders or the like. Preferably, the binder is CMC or hydroxypropyl cellulose.

A slurry of the cellulosic material is made  
15 by first mixing the cellulose with water. The concentration of solid added to the water is between about 0.5 wt.% and about 10 wt.%, depending upon the specific type of cellulosic material. For example, for CELLULON™ the preferred concentration is between about  
20 0.5 wt.% and about 1.5 wt.%, while for AVICEL™ CL-611 the preferred concentration is between about 5 wt.% and 10 wt.%. The desired concentration of solid cellulosic material which should be added to the water is also dependant upon the particular slurry application  
25 process used, as would be expected to one of ordinary skill in the art.

The addition of a binder material to the slurry causes the slurry to exhibit improved rheological properties and therefore allows for a  
30 greater range of application techniques to be employed, such as conventional paper coating or printing techniques, i.e., gravure or flexigraphic coating, or other suitable coating or printing techniques.

If the cellulosic material was not co-  
35 processed with a binder during its manufacturing

process, then binder can be added to the slurry. If the cellulosic material was co-processed with a binder during manufacture, as is the case for AVICEL™ CL-611 which contains approximately 10-15 % by weight CMC, then adding binder to the slurry may not be necessary to achieve the desired rheological properties for application of the slurry to the base paper web. The total amount of binder present in the slurry should be in the range from about 0.1 % to about 10 %, by weight. Preferably, the amount of binder present should be in the range from about 0.5 % to about 2 %, by weight.

The binder may be omitted from the slurry for some cellulosic materials, if desired, and the cellulosic slurry can then be applied to the paper by techniques such as a spraying operation or extrusion-type process such as those used in the application of hot melt materials. Although the application options are more limited when the binder is omitted from the cellulosic slurry, the advantages to omitting it are that the taste of the smoking article may be improved and that one less processing step is required for fabrication of the smoking article wrapper.

After the cellulosic slurry is formed, either with or without binder, it is then applied to the base paper web by the processes discussed herein. After the slurry is applied to the base paper web, the slurry can be dried using a drum dryer or infrared heater, or the like, as in conventional paper manufacturing. Typically between about 10 g/m<sup>2</sup> and about 200 g/m<sup>2</sup> wet weight of the cellulosic slurry is applied to the paper to result in dry weight of cellulosic material of between about 0.5 g/m<sup>2</sup> and about 10 g/m<sup>2</sup>. The preferred wet weight is dependant upon the particular type and concentration of cellulosic slurry employed. For example, for a slurry with about 1.0 % CELLULON™ ,

- 15 -

one will need about  $100 \text{ g/m}^2$  wet weight to result in a dry weight of about  $1 \text{ g/m}^2$ ; whereas for a slurry with about 6 % AVICEL™ CL-611, one will need about  $17 \text{ g/m}^2$  to result in a dry weight of about  $1 \text{ g/m}^2$ .

5           The cellulosic slurry may be applied to form bands at any desired interval and width depending on the particular desired burn control rate. Preferably, bands are applied at intervals of about 10 mm to about 25 mm. The width of the band may be varied depending  
10 on the type of cigarette and paper used in addition to the type and level of slurry applied. Preferably the width of the band is about 5 mm to about 10 mm.

          The following Examples serve to illustrate the preparation and application of the cellulosic  
15 slurry to the base paper.

#### EXAMPLES

##### Example 1

          A slurry of CELLULON™ containing 0.5% of solids was applied to a conventional cigarette wrapper  
20 using a plastic template and draw-down rod coating method. The template used in this example had 5 mm wide open areas that were spaced 21 mm apart. The template was laid over the cigarette wrapper in such a way that the template's open areas were parallel to the  
25 cross-direction of the wrapper. The CELLULON™ slurry is poured on to the plastic template and then applied by a lab scale draw-down rod coater (the rod moves in a direction parallel to the template's open areas). The slurry was then applied onto the cigarette wrapper  
30 through the open areas of the template and, after drying, appear as cross-directional bands of CELLULON™. The add-on level in the band areas was approximately  $1.0 \text{ g/m}^2$  on top of  $25 \text{ g/m}^2$  base sheet (i.e., the band



- 16 -

areas had a basis weight of 26 g/m<sup>2</sup> while the non-band areas had a basis weight of only 25 g/m<sup>2</sup>). Cigarettes were hand-made (diameter of 24.8 mm) using the wrapper described above and a conventional tobacco blend. The  
5 cigarettes showed a reduction of the static burn rate in the regions of the band.

#### Example 2

A slurry of CELLULON™ containing 0.9% solids was applied to a conventional cigarette wrapper using  
10 the method described above in Example 1. The add-on level in the banded areas was approximately 2.0 g/m<sup>2</sup> on top of a 25 g/m<sup>2</sup> base sheet (i.e., the band areas had a basis weight of 27 g/m<sup>2</sup> while the non-band areas had a basis weight of only 25 g/m<sup>2</sup>). Cigarettes were hand-  
15 made using the wrapper described above and a conventional tobacco blend. The cigarettes showed a reduction of the static burn rate in the regions of the band.

#### Example 3

20 A slurry of BUCKEYE™ Expanded Fibers containing 2.3% solids was applied to a conventional cigarette wrapper using the method described above in Example 1. The add-on level in the band areas was approximately 7.0 g/m<sup>2</sup> on top of a 25 g/m<sup>2</sup> base sheet  
25 (i.e., the band areas had a basis weight of 32 g/m<sup>2</sup> while the non-band areas had a basis weight of only 25 g/m<sup>2</sup>). Cigarettes were hand-made using the wrapper described above and a conventional tobacco blend. The cigarettes showed a reduction of the static burn rate  
30 in the regions of the band.

Example 4

A slurry of AVICEL™ CL-611 containing 5.0% solids was applied to a conventional cigarette wrapper using the method described in Example 1. The add-on level in the band areas was approximately 3.5 g/m<sup>2</sup> on top of a 25 g/m<sup>2</sup> base sheet (i.e., the band areas had a basis weight of 28.5 g/m<sup>2</sup> while the non-band areas had a basis weight of only 25 g/m<sup>2</sup>). Cigarettes were hand-made using the wrapper described above and a conventional tobacco blend. The cigarettes showed a reduction of the static burn rate in the regions of the band.

Example 5

A slurry of AVICEL™ CL-611 containing 8.0% solids was applied to a conventional cigarette wrapper using a gravure roll. The cross-directional bands of AVICEL™ cellulose after application by the gravure roll were approximately 7 mm wide. The add-on level was approximately 1.5 g/m<sup>2</sup> on top of a 25 g/m<sup>2</sup> (i.e., the band areas had a basis weight of 26.5 g/m<sup>2</sup> while the non-band areas had a basis weight of only 25 g/m<sup>2</sup>). Machine-made cigarettes were made using the wrapper described above and a conventional tobacco blend. The cigarettes showed a reduction of the static burn rate in the regions of the band.

Example 6

A slurry of AVICEL™ CL-611 containing 4.0% solids was applied to a conventional cigarette wrapper using a soft rubber covered grooved roll at the size-press. The soft rubber covered roll had 3.2 mm wide and 0.18 mm deep grooves. The paper passes between the grooved roll and a plain roll. The grooves were filled

with the AVICEL™ slurry and the excess was removed by a doctoring blade. The AVICEL™ was transferred onto the paper at the size-press nip and dried using can driers. The bands of AVICEL™ on paper were approximately 5 mm  
5 wide. The add-on level in the band areas was less than  $2 \text{ g/m}^2$  on top of  $25 \text{ g/m}^2$  base sheet. The actual application levels in the band were not determined for these samples due to the limited supply of samples. Machine-made cigarettes were made using the wrapper  
10 described above and a conventional tobacco blend. The cigarettes showed a reduction of the static burn rate in the regions of the band.

#### Example 7

A slurry of AVICEL™ CL-611 containing 10 %  
15 solids was applied to a high basis weight cigarette wrapper ( $45 \text{ g/m}^2$ , 8 Coresta) using a modified gravure roller.

The roller was smooth except for 10 mm wide (measured around perimeter of the roller) and 55.5 mm  
20 long (measured along the axis of the roller) grooves which were 0.5 mm deep. These grooves were spaced 31.9 mm apart, centerline to centerline around the roller. A rubber covered pressure roller was pressed against the grooved roller. The 4-inch wide paper was  
25 fed onto the grooved roller before the nip point. The grooves were filled with slurry which was then transferred to the paper. The depth of the roller groove, concentration of slurry, and release characteristics of the roller all affected the  
30 thickness of the material deposited onto the paper, as would be expected to one of ordinary skill in the art.

The add-on level in the band area was approximately  $5.8 \text{ g/m}^2$  on top of the  $45 \text{ g/m}^2$  base sheet. Handmade cigarettes were made with the above described



- 19 -

wrapper and a conventional tobacco blend. The cigarettes showed a reduction of the static burn rate in the regions of the band.

#### Example 8

5           Three different slurries of AVICEL™ CL-611 containing three different concentrations of solid were applied to a conventional cigarette wrapper using a gravure roll. The cross-directional bands of AVICEL™ cellulose after application were approximately 7 mm  
10 wide. The add-on levels were approximately 1 g/m<sup>2</sup>, 1.5 g/m<sup>2</sup>, and 2.0 g/m<sup>2</sup> on top of the 25 g/m<sup>2</sup> base paper, so that the banded areas had a basis weight of approximately 26 g/m<sup>2</sup>, 26.5 g/m<sup>2</sup>, 27 g/m<sup>2</sup>, while the non-banded areas were only 25 g/m<sup>2</sup>. Machine-made  
15 cigarettes using the above-described wrapper and conventional tobacco blend were analyzed for burn rate in the static mode. The cigarettes showed a reduction of the static burn rate in the regions of the band. The degree of burn rate reduction achieved was  
20 dependent on the application level of the AVICEL™.

#### Example 9

Machine made cigarettes were prepared from 25 g/m<sup>2</sup> basis weight, 30 Coresta porosity papers to which KLUCEL™ (hydroxypropyl cellulose from Aqualon  
25 Company, Wilmington, Delaware) was applied to the surface of the paper using a solution of about 6-8 percent in water. This resulted in a film application level of about 2.5 g/m<sup>2</sup>. The solution of KLUCEL™ was applied by gravure printing techniques in 7 mm wide  
30 bands. The cigarettes so produced showed no reduction of the static burn rate in the regions of the band.

It should be noted that the "film former" KLUCEL™ (hydroxypropyl cellulose) is a water soluble

- 20 -

thermoplastic polymer. Because KLUCEL™ is soluble in water, it forms a solution and not a slurry. As such, it produces a film on the surface of the base paper web, as shown by microscopic analysis, as opposed to  
5 the fibrous mats formed by the slurries of this invention.

One skilled in the art will appreciate that the present invention can be practiced by other than the described embodiments, which are presented for  
10 purposes of illustration and not of limitation, and the present invention is limited only by the claims that follow.

**CLAIMS**

1. A paper wrapper for a smoking article comprising a paper base web having one or more regions of microfibrillated fibrous cellulose bonded to the paper base web, the said regions being provided by a microfibrillated fibrous cellulose suspension applied directly to the paper base web, the regions of fibrous cellulose adding between 0.5 g/m<sup>2</sup> and 10 g/m<sup>2</sup> dry weight on top of the base paper.
2. A wrapper according to claim 1 wherein the regions of microfibrillated fibrous cellulose include a binder.
3. A wrapper according to claim 2 wherein the binder is carboxymethyl cellulose, hydroxypropyl cellulose, starch or guar.
4. A method for making a smoking article paper wrapper according to any preceding claim characterised by:
  - a) advancing the base paper web along a travel path, and
  - b) applying a stable suspension of microfibrillated cellulosic material in a liquid directly to the base paper web at a position on the path to form one or more regions of microfibrillated fibrous cellulose on the web, the regions of microfibrillated fibrous cellulose adding between 0.5 g/m<sup>2</sup> and 10 g/m<sup>2</sup> dry weight on top of the base paper.
5. A method according to claim 4 wherein the stable suspension is a slurry of microfibrillated cellulosic material and water.
6. A method according to claim 5 wherein the suspension contains from 0.5 wt.% to 10 wt.% microfibrillated cellulosic material.



- 22 -

7. A method according to claim 4, 5 or 6 wherein step b) comprises applying to the base paper web a suspension of microfibrillated cellulosic material, water and a binder.
8. A method according to claim 7 wherein the binder is carboxymethyl cellulose, hydroxypropyl cellulose, starch or guar.
9. A method according to claim 7 or 8 wherein the suspension contains from 0.1 wt.% to 10 wt.%, binder.
10. A method according to claim 7, 8 or 9 wherein the suspension contains from 0.5 wt.% to 2 wt.%, binder.
11. A method according to any one of claims 4 to 10 wherein the suspension is applied by coating, by printing, by a gravure roll, or by a rubber-covered grooved roll.
12. A method according to any one of claims 4 to 11 further comprising a preliminary step prior to step a) of manufacturing the base paper web with a paper making apparatus having a wet end, wherein the microfibrillated cellulose-applying position is located on-line and beyond the wet end of the paper making apparatus.
13. A method according to any one of claims 4 to 11 wherein the base paper web is manufactured by a paper making apparatus and the microfibrillated cellulosic material of step b) is applied off-line of the paper making apparatus.
14. A smoking article comprising a tobacco filler and a paper wrapper according to any one of claims 1 to 3.