



(22) Date de dépôt/Filing Date: 2003/09/09

(41) Mise à la disp. pub./Open to Public Insp.: 2004/03/19

(45) Date de délivrance/Issue Date: 2013/01/08

(30) Priorité/Priority: 2002/09/19 (US10/246,943)

(51) Cl.Int./Int.Cl. *C04B 24/26* (2006.01),
C04B 28/02 (2006.01), *C04B 7/02* (2006.01),
C08L 53/02 (2006.01), *C09K 8/46* (2006.01)

(72) Inventeurs/Inventors:
REDDY, B. RAGHAVA, US;
RAVI, KRISHNA M., US

(73) Propriétaire/Owner:
HALLIBURTON ENERGY SERVICES, INC., US

(74) Agent: NORTON ROSE CANADA
S.E.N.C.R.L., S.R.L./LLP

(54) Titre : MELANGES ELASTOMERES POUR AMELIORER L'ELASTICITE DU CIMENT

(54) Title: ELASTOMERIC ADMIXTURES FOR IMPROVING CEMENT ELASTICITY

(57) **Abrégé/Abstract:**

A method and cementing composition is provided for sealing a subterranean zone penetrated by a well bore, wherein the cementing composition comprises a mixture of cementitious material, acrylonitrile butadiene styrene (ABS), and sufficient water to form a slurry.

ABSTRACT

A method and cementing composition is provided for sealing a subterranean zone penetrated by a well bore, wherein the cementing composition comprises a mixture of cementitious material, acrylonitrile butadiene styrene (ABS), and sufficient water to form a slurry.

Elastomeric Admixtures for Improving Cement Elasticity

Background

The present embodiment relates generally to a cementing composition for sealing a subterranean zone penetrated by a well bore.

In the drilling and completion of an oil or gas well, a cementing composition is often introduced in the well bore for cementing pipe string or casing. In this process, known as "primary cementing," the cementing composition is pumped into the annular space between the walls of the well bore and the casing. The cementing composition sets in the annular space, supporting and positioning the casing, and forming a substantially impermeable barrier, or cement sheath, which isolates the well bore into subterranean zones. Thus, the undesirable migration of fluids between zones is prevented after primary cementing.

Changes in pressure or temperature in the well bore over the life of the well can result in compromised zonal isolation. Also, activities undertaken in the well bore, such as pressure testing, well completion operations, hydraulic fracturing, and hydrocarbon production can affect zonal isolation. Such compromised zonal isolation is often evident as cracking or plastic deformation in the cementing composition, or de-bonding between the cementing composition and either the well bore or the casing.

As the name implies, cementing compositions are made chiefly of cement. Due to its incompressible nature, neat cement is undesirable for use where there is a chance of expansion or contraction in the well bore. Cement has a high Young's modulus, and fractures at slight strains when subjected to stresses ("brittle failure"). When the imposed stresses exceed the stress at which the cement fails, the cement sheath can no longer provide zonal isolation. While the Young's modulus of cementing compositions can be lowered by adding silica compositions, such silica treated cementing compositions ("water-extended slurries") suffer from lower compressive and tensile strengths.

Therefore, a cementing composition that can provide greater elasticity and compressibility, while retaining high compressive and tensile strengths, is desirable for primary cementing.

Description

A cementing composition for sealing a subterranean zone penetrated by a well bore according to the present embodiment comprises a mixture of cementitious material

("cement"), acrylonitrile butadiene styrene (ABS) polymer, and sufficient water to form a slurry.

In another embodiment, ABS is added to water-extended slurries to create a cementing composition with a lower Young's modulus while achieving high compressive and tensile strengths.

A variety of cements can be used with the present embodiments, including cements comprised of calcium, aluminum, silicon, oxygen, and/or sulfur which set and harden by reaction with water. Such hydraulic cements include Portland cements, pozzolan cements, gypsum cements, aluminous cements, silica cements, and alkaline cements. Portland cements of the type defined and described in API Specification 10, 5th Edition, July 1, 1990, of the American Petroleum Institute are preferred. API Portland cements include Classes A, B, C, G, and H, of which API Classes A, G, and H are particularly preferred for the present embodiment. The desired amount of cement is understandably dependent on the cementing operation.

ABS used with the present embodiments is often produced as a composite material. In the production of such a composite material, a preformed elastomer such as polybutadiene or styrene butadiene rubber is used as a substrate, and styrene and acrylonitrile monomers are grafted onto the substrate by polymerization. In addition, styrene and acrylonitrile that fail to graft to the substrate copolymerize to form a matrix, with the grafted substrate dispersed in the matrix. Higher levels of butadiene in the final product increases the elastomeric properties of the composite material. In contrast, higher levels of styrene and acrylonitrile in the final product decrease the elastomeric properties of the composite material. As can be appreciated, the character of the ABS varies by the composition of the composite material, and thus affects the mechanical properties of the cementing composition.

ABS is normally sold in a fine particulate or pellet form. ABS with particle sizes ranging from 5-500 microns is preferable. More preferably, the particle size is in the 50-300 micron range, and most preferably in the 100-250 micron range. Such ABS is widely available commercially. Some examples of commercially available ABS includes BLENDEX 338TM ABS made with a 70% polybutadiene substrate (the remaining 30% being a mixture of styrene and acrylonitrile), 180 micron particle size ("Type I"), BLENDEX 336TM ABS made with a 65% styrene-butadiene rubber substrate, 180 micron particle size ("Type

II”), BLENDEX 415TM ABS made with a 65% styrene-butadiene rubber substrate, 250 micron particle size (“Type III”), and BLENDEX 102STM ABS with a 35% styrene-butadiene rubber substrate, less than 1 mm particle size (“Type IV”), all available from GE Specialty Chemicals, Parkersburg, West Va., U.S.A. ABS is present in an amount that is 5-30% by weight of the cement in a particular cementing composition.

Water in the cementing composition is present in an amount sufficient to make a slurry which is pumpable for introduction down hole. The water used to form a slurry in the present embodiment can be fresh water, unsaturated salt solution, including brines and seawater, and saturated salt solution. Generally, any type of water can be used, provided that it does not contain an excess of compounds, well known to those skilled in the art, that adversely affect properties of the cementing composition. The water is present in an amount of about 38-70% by weight of the cement, and more preferably in an amount of about 60% by weight of the cement.

A variety of additives may be added to the cementing composition to alter its physical properties. Such additives may include slurry density modifying materials (e.g., silica flour, silica fume, sodium silicate, microfine sand, iron oxides and manganese oxides), dispersing agents, set retarding agents, set accelerating agents, fluid loss control agents, strength retrogression control agents, and viscosifying agents well known to those skilled in the art.

The following example is illustrative of the methods and compositions discussed above.

EXAMPLE 1

Class G cement, silica flour, and the components in the amounts listed in TABLE 1 were added to form seven batches. The batches were prepared according to API Specification RP 10B, 22nd Edition, 1997, of the American Petroleum Institute. For example, Batch 6 was prepared by combining 500 grams of Class G cement, 175 grams of silica flour, 50 grams of Type IV ABS (Particle size, <1 mm), and 317 grams of tap water in a Waring blender to obtain a slurry with density of 14.8 pounds per gallon. All batches had the same density.

ABS Types I-IV are described above. ABS Type V has a high butadiene content and a density of 1.040 g/cc, with a particle size less than 500 microns, and is available from Sigma-Aldrich Co., St. Louis, Mo., U.S.A.

To test each batch for various strength parameters, a portion of each batch was placed

into a corresponding 2"x2" brass mold, and another portion of each batch was placed into a corresponding cylindrical plastic container provided with a lid. The seven molds and seven cylinders were cured in a 180°F water bath for 24 hours to form samples of the batches.

Using the above-described samples, the strength parameters were measured by a strength testing instrument manufactured by Tinius Olsen, Willow Grove, Penn., U.S.A., according to the American Society for Testing and Materials ASTM C109 procedure. The tensile strengths were measured on the same instrument according to the ASTM C190-97 procedure. The burst strengths were measured on an MTS load frame instrument manufactured by MTS Systems Corporation, Eden Prairie, Minn., U.S.A. The Young's modulus, Poisson's ratio, Brazilian tensile strength, and permeability were also determined for each batch, and are listed in **TABLE 1**.

TABLE 1

Components	Batch 1	Batch 2	Batch 3	Batch 4	Batch 5	Batch 6	Batch 7
Water %bwoc	72	62.5	61.6	61.6	58	63.3	58
ABS Type	--	Type I	Type II	Type III	Type III	Type IV	Type V
ABS %bwoc	--	10	10	10	15	10	15
Compressive strength, psi	1320	1950	1750	1800	2060	1990	2680
Tensile strength, psi	--	270	284	284	--	300	--
Burst strength, psi	--	264	255	270	--	--	--
Young's modulus	0.460	0.858	0.861	0.720	0.427	0.728	0.879
Poisson's ratio	0.114	0.139	0.142	0.128	0.118	0.130	0.138
Brazilian tensile strength, psi	98	210	194	220	180	255	222
Permeability, mD	--	0.020	0.016	0.020	--	--	--

TABLE 1 shows that Batch 1, the water-extended slurry, had poor compressive strength, even though the Young's modulus value was low. This can result in failure of the cement sheath to provide effective zonal isolation. In contrast, the ABS batches, Batches 2-7, had much higher compressive strengths, and favorable tensile strengths (where measured). **TABLE 1** also shows that selection of the ABS type affects the mechanical properties of the cementing composition, thus allowing the cementing composition to be tailored to suit conditions in a particular well bore.

It is speculated that the acrylonitrile in ABS hydrolyzes in the cement slurries and generates carboxylates which facilitate bonding of the normally incompatible elastomer to the cement. Such bonding may allow dissipation of imposed stresses, thus preventing brittle failure of the cement sheath.

Using the raw stress-strain data used in the determination of the compressive strength, Young's modulus, and Poisson's ratios listed in **TABLE 1**, the areas under the curves extending from no stress to the maximum stress (reached at the ultimate yield point) in the

axial stress-strain and radial stress-strain graphs were determined, and the values are listed in **TABLE 2**. The Young's modulus and Poisson's ratio listed in **TABLE 2** correspond to the values observed at the maximum stress. Batch 7 was not tested.

TABLE 2

Components	Batch 1	Batch 2	Batch 3	Batch 4	Batch 5	Batch 6
Stress at ultimate yield point, psi	1130	2070	2080	1690	1300	2370
Area under curve for axial displacement at ultimate yield point, Kpsi x microinch/inch	2270	6000	4730	4290	3662	7280
Area under curve for radial displacement at ultimate yield point, Kpsi x microinch/inch	640	1430	750	1135	1050	1000
Poisson's ratio at ultimate yield point	0.210	0.207	0.143	0.220	0.219	0.128
Young's modulus at ultimate yield point, psi	0.336e+6	0.476e+6	0.580e+6	0.444e+6	0.298e+6	0.510e+6

The maximum stress at the ultimate yield point indicates the ability of the cementing composition to absorb the imposed stresses without failing, and the ABS containing Batches 2-6 all showed greater stress values than Batch 1. The resiliency of the composition is indicated by higher ratios of the area under radial stress-strain curve to the area under axial stress-strain curve. While the ability of Batches 2-6 to plastically deform without failing could not be directly quantified, it was apparent that they plastically deformed past the load bearing stage.

Although only a few exemplary embodiments of this invention have been described in detail above, those skilled in the art will readily appreciate that many other modifications are possible in the exemplary embodiments without materially departing from the novel teachings and advantages of this invention. Accordingly, all such modifications are intended to be included within the scope of this invention as defined in the following claims.

CLAIMS:

1. A method of sealing a subterranean zone penetrated by a well bore comprising:
preparing a cementing composition comprising cement, acrylonitrile butadiene styrene polymer, and water, the acrylonitrile butadiene styrene polymer being present in a range of 5% to 30% by weight of the cement, the water being present in an amount sufficient to form a slurry;
placing the cementing composition into the subterranean zone; and
allowing the cementing composition to set therein.
2. The method of claim 1 wherein the cementing composition further comprises silica flour.
3. The method of claim 1 wherein the cement is Portland cement, pozzolan cement, gypsum cement, aluminous cement, silica cement, or alkaline cement.
4. The method of claim 1 wherein the acrylonitrile butadiene styrene polymer is made with a 70% polybutadiene substrate.
5. The method of claim 1 wherein the acrylonitrile butadiene styrene polymer is made with a 65% styrene-butadiene rubber substrate.
6. The method of claim 1 wherein the acrylonitrile butadiene styrene polymer is made with a 35% styrene-butadiene rubber substrate.
7. The method of claim 1 wherein the water is present in a range of 38% to 70% by weight of the cement.
8. The method of claim 1 wherein the cementing composition further comprises a density modifying material, dispersing agent, set retarding agent, set accelerating agent, fluid loss control agent, strength retrogression control agent or viscosifying agent.

9. The method of claim 1 wherein the acrylonitrile butadiene styrene polymer has a particle size in the range of 5 microns to 1 mm.
10. The method of claim 1 wherein the cementing composition further comprises silica flour, silica fume, sodium silicate, microfine sand, iron oxide or manganese oxide.
11. A wellbore cement composition comprising:
 - cement;
 - acrylonitrile butadiene styrene polymer present in particulate form in a range of 5% to 30% by weight of the cement; and
 - water present in a range of about 38% to about 70% by weight of the cement, wherein the cement, the acrylonitrile butadiene styrene polymer in particulate form, and the water are present in relative amounts effective to provide the cement composition with a strength sufficient to achieve zonal isolation in a wellbore penetrating a subterranean zone.
12. The composition of claim 11 wherein the cement is Portland cement, pozzolan cement, gypsum cement, aluminous cement, silica cement, or alkaline cement.
13. The composition of claim 11 wherein the acrylonitrile butadiene styrene polymer is made with a 70% polybutadiene substrate.
14. The composition of claim 11 wherein the acrylonitrile butadiene styrene polymer is made with a 65% styrene-butadiene rubber substrate.
15. The composition of claim 11 wherein the acrylonitrile butadiene styrene polymer is made with a 35% styrene-butadiene rubber substrate.
16. The composition of claim 11 wherein the acrylonitrile butadiene styrene polymer has a particle size in the range of 5 microns to 500 microns.

17. The composition of claim 11 wherein the acrylonitrile butadiene styrene polymer has a particle size in the range of 50 microns to 300 microns.
18. The composition of claim 11 wherein the acrylonitrile butadiene styrene polymer has a particle size in the range of 100 microns to 250 microns.
19. The composition of claim 11 wherein the acrylonitrile butadiene styrene polymer is present in a range of 10% to 15% by weight of the cement.
20. The composition of claim 11 further comprising a density modifying material, dispersing agent, set retarding agent, set accelerating agent, fluid loss control agent, strength retrogression control agent or viscosifying agent.
21. The composition of claim 11 further comprising silica flour, silica fume, sodium silicate, microfine sand, iron oxide or manganese oxide.
22. The composition of claim 11 further comprising silica flour.
23. The composition of claim 11, wherein the acrylonitrile butadiene styrene polymer has a particle size of less than 1 mm.
24. A method of sealing a subterranean zone penetrated by a well bore comprising:
preparing a cementing composition comprising cement, acrylonitrile butadiene styrene polymer, and water, wherein the cement is Portland cement, pozzolan cement, gypsum cement, aluminous cement, silica cement, or alkaline cement, wherein the acrylonitrile butadiene styrene polymer is present in a range of 5% to 30% by weight of the cement, and wherein water is present in an amount sufficient to provide a slurry;
placing the cementing composition into the subterranean zone; and
allowing the cementing composition to set therein.
25. The method of claim 24 wherein the acrylonitrile butadiene styrene polymer is made with a 70% polybutadiene substrate.

26. The method of claim 24 wherein the acrylonitrile butadiene styrene polymer is made with a 65% styrene-butadiene rubber substrate.
27. The method of claim 24 wherein the acrylonitrile butadiene styrene polymer is made with a 35% styrene-butadiene rubber substrate.
28. The method of claim 24 wherein the water is present in a range of about 38% to about 70% by weight of the cement.
29. The method of claim 24 wherein the acrylonitrile butadiene styrene polymer is present in a range of 10% to 15% by weight of the cement.
30. The method of claim 24 wherein the acrylonitrile butadiene styrene polymer has a particle size in the range of 5 microns to 500 microns.
31. The method of claim 24 wherein the acrylonitrile butadiene styrene polymer has a particle size in the range of 50 microns to 300 microns.
32. The method of claim 24 wherein the acrylonitrile butadiene styrene polymer has a particle size in the range of 100 microns to 250 microns.
33. The method of claim 24 wherein the cementing composition further comprises silica flour, silica fume, sodium silicate, microfine sand, iron oxide or manganese oxide.
34. The method of claim 24 wherein the cement is Portland cement.
35. The method of claim 24 wherein the acrylonitrile butadiene styrene polymer has a particle size in the range of 5 microns to 1 mm.

36. The method of claim 24 wherein the cementing composition further comprises a density modifying material, dispersing agent, set retarding agent, set accelerating agent, fluid loss control agent, strength retrogression control agent or viscosifying agent.

37. The method of claim 1 or 24, wherein the acrylonitrile butadiene styrene polymer has a particle size of less than 1 mm.

38. The method of claim 1, wherein the acrylonitrile butadiene styrene polymer is present in a range of 10% to 15% by weight of the cement.