



US 20090043009A1

(19) **United States**

(12) **Patent Application Publication**
Sang

(10) **Pub. No.: US 2009/0043009 A1**

(43) **Pub. Date: Feb. 12, 2009**

(54) **ONE-COMPONENT SELF-ETCHING
ADHESIVE**

(60) Provisional application No. 60/618,649, filed on Oct.
14, 2004.

(76) Inventor: **Junjie Sang**, Magnolia, DE (US)

Publication Classification

Correspondence Address:
DENTSPLY INTERNATIONAL INC
570 WEST COLLEGE AVENUE
YORK, PA 17404

(51) **Int. Cl.**
A61K 6/00 (2006.01)

(52) **U.S. Cl.** **523/118**

(21) Appl. No.: **12/284,854**

(57) **ABSTRACT**

(22) Filed: **Sep. 25, 2008**

Related U.S. Application Data

(63) Continuation of application No. 11/545,669, filed on
Oct. 10, 2006, now abandoned, which is a continuation
of application No. 11/432,928, filed on May 12, 2006,
now abandoned, which is a continuation of application
No. 11/402,127, filed on Apr. 10, 2006, now aban-
doned, which is a continuation of application No.
11/244,937, filed on Oct. 6, 2005, now abandoned.

A one-part, self-etching dental adhesive having improved
performance such as adhesion performance with a simple
one-coat application, without the need of separate acid-etch-
ing, a priming pre-treatment, or bonding step. The invention
provides such improvements due to a function of the pH
balance of the system in combination with an acid stable
photoinitiating system. More specifically, the performance
and pH balance is achieved through the employment of a
hydrolytically stable, acidic, high-strength adhesive mono-
mer (such as PENTA), with a stable, bifunctional, hydrophilic
monomer (such as AHPMA) that yields greater crosslinking.

ONE-COMPONENT SELF-ETCHING ADHESIVE

RELATED APPLICATIONS

[0001] This application claims the benefit of U.S. application Ser. No. 11/545,669 filed Oct. 10, 2006 which is a continuation of U.S. application Ser. No. 11/432,928 filed May 12, 2006, which is a continuation of U.S. application Ser. No. 11/402,127 filed Apr. 10, 2006, which is a continuation of U.S. application Ser. No. 11/244,937 filed Oct. 6, 2005 which claims benefit of U.S. Provisional Application Ser. No. 60/618,649 filed Oct. 14, 2004.

TECHNICAL FIELD

[0002] A one-part, self-etching dental adhesive having improved performance such as adhesion performance with a simple one-coat application, without the need of separate acid-etching, a priming pre-treatment, or bonding step. The invention provides such improvements due to a function of the pH balance of the system in combination with an acid stable photoinitiating system. More specifically, the performance and pH balance is achieved through the employment of a hydrolytically stable, acidic, high-strength adhesive monomer (such as PENTA), with a stable, bifunctional, hydrophilic monomer (such as AHPMA) that yields greater crosslinking.

BACKGROUND OF THE INVENTION

[0003] Typically, the procedure for dental composite restorations using a total etch adhesive involves acid etching the tooth using phosphoric acid followed by water rinsing and drying. Subsequently, a primer is applied and dried followed by the application of a bonding agent, which is light cured. Finally, the composite restoration is applied, cured and polished. Overall, there are many steps to complete a dental restoration. Unfortunately, with each additional step the process becomes more difficult increasing the risk for failure. In general, the primary goal of this project is to reduce the number of steps associated with the application of the dental adhesive.

[0004] In order to accomplish this objective, the number of components to be used for priming and bonding were combined into one-bottle as exemplified by the Prime & Bond® brand adhesive (Dentsply). However, etching must still be conducted prior to the application and curing of the single component priming. The process is further simplified by combining the priming and etching into a one-component self-etching system. For example, ClearFil SE Bond (Kuraray) is a 2-component system, which consists of a self-etching primer and bonding liquid. In this 2-step system the self-etching primer is applied followed by the application of the bonding agent.

[0005] ClearFil SE Bond is indicated for direct light cured composite restoration bonding only. For indirect restoration bonding, Kuraray recommends using ClearFil Liner Bond 2V that is a multi-component (Primers A and B, Bond Liquid A and B) which involves a multi-step application for self-etching adhesive system.

[0006] Similarly, Adper Prompt L-Pop (3M ESPE), a 2-component/one-pack/one-step self-etching priming adhesive, is supplied in a unit dose blister package that consists of

two-predosed compartments, for the two liquids A and B. Prompt L-Pop is only indicated for bonding direct, light cured composite restorations.

[0007] The 1P-SEA product developed at L.D. Caulk further simplifies the technique for applying dental adhesives by incorporating the etching, priming and bonding components into a single component bottle or unit dose package. More specifically, the application technique is reduced from the complex series of events previously described to apply, dry and cure. The Caulk 1P-SEA is differentiated from the only currently marketed single component self-etching adhesive (i-Bond Heraeus Kulzer), through chemistry (see Table 1 for preferred formulation and raw material ranges) and performance (see Tables 2-7). It exhibits performance (microleakage and shear bond strength) which is superior to i-Bond and comparable to the leading 2-component systems available in the dental market.

[0008] Ref. U.S. Pat. No. 6,387,979 by K. Hino (Kuraray Co. Ltd., Japan), issued May 14, 2002.

[0009] Abstract: A tooth treated with a bonding composition with high initial bonding strength and good bonding durability comprising a mixture of polymerizable compound having an acid group, a water-soluble film-forming agent, water, and a curing agent, in which the calcium salt of the acid is insoluble in water, and the film-forming agent is a polymerizable compound miscible with a physiological saline solution, does not require any pre-treatment such as acid-etching or priming treatment.

[0010] This patent states that the active ingredients of the composition in a single package may degrade or polymerize while stored. To prevent this, the constituent ingredients of the composition may be divided into two or more parts. The plural parts are separately packaged and stored in different packages. For their use, the plural parts taken out of the individual packages may be applied to one and the same object in sequence; or they may be blended into one mixture just before use.

SUMMARY OF THE INVENTION

[0011] 1P-SEA materials according to the invention can achieve good adhesion performance with a simple one-coat application, without the need of using phosphoric acid tooth gel.

PREFERRED EMBODIMENTS FOR CARRYING OUT THE INVENTION

[0012] For One-component Visible Light Cure Self-Etching Adhesive (1P-SEA) according to the invention, it is indicated to bond VLC composite/comonomer direct restorations to human teeth substrate (enamel and dentine) without the need of separate acid-etching or priming pre-treatment teeth bonding step. When used with a separate Self-Cure Activator component, the 1P-SEA can also bond for cemented indirect restorations (prefabricated metal/porcelain/composite Inlays/Onlays/Veneers/Crowns/Bridges) to human teeth substrate (enamel and dentine) without separate acid etching or priming pre-treatment step. In addition, 1P-SEA can also be used as a cavity varnish.

TABLE 1

Prototype Formulation of One-Component Self-Etching Adhesive				
Raw Material	Chemical Name	CAS #	Formulation Ranges	Preferred % Weight
UDMA	2-Methyl-acrylic acid 1-methyl-2-{3,5,5-trimethyl-6-[1-methyl-2-(2-methyl-acryloyloxy)-ethoxycarbonyl amino]-hexylcarbamoyloxy}-ethyl ester	105883-40-7	5-15	10.50
PENTA	2-Methyl-acrylic acid 4-(2-methyl-acryloyloxy)-2,2,3-tris-(2-methyl-acryloyloxymethyl)-3-phosphonooxymethyl-butyl ester	87699-25-0	8-20	12.80
HEMA	2-Methyl-acrylic acid 2-hydroxy-ethyl ester	868-77-9	0-5	3.20
AHPMA	2-Methyl-acrylic acid 3-acryloyloxy-2-hydroxy-propyl ester	1709-71-3	5-15	9.50
TMPTMA	2-Methyl-acrylic acid 2,2-bis-(2-methyl-acryloyloxymethyl)-butyl ester	3290-92-4	0-5	1.60
L-TPO	(Diphenyl-phosphinoyl)-(2,4,6-trimethyl-phenyl)-methanone	75980-60-8	0.1-2.0	0.99
CQ	Bicyclo [2,2,1] heptane-2,3 dione, 1,1,7-trimethyl	10373-78-1	0.05-0.50	0.19
DMABN	4-Dimethylamino-benzonitrile	1197-19-9	0.1-1.2	0.79
BHT	Phenol, 2,6-bis (1,1-dimethylethyl-4-methyl)	128-37-0	0.01-0.2	0.13
CAF	Hexadecyl-ammonium; fluoride	3151-59-5	0-1.0	0.30
Water	Water	7732-18-5	5-20	12.60
Acetone	2-Propanone	67-64-1	20-60	47.40
Total				100

Physical Properties and Characteristics

[0013] True one-component self-etching bonding agent in both bottle and unit dose package

[0014] No mixing or rinsing requirement prior to application

[0015] One-coat/One-step simple and robust technique

[0016] VLC direct bond strength equal or better than Xeno III and other 2-component competitors

[0017] Indirect bond strength (when used with separate SCA component) equivalent to that of P&B NT/SCA Dual Cure adhesive

[0018] Low film thickness (<15 μm)

[0019] Fluoride releasing

[0020] Microleakage at least as good as the current P&B NT and Xeno III systems

Comparison to Competitive Products

[0021] In Vitro shear bond strength before and after thermocycling was tested on 1P-SEA and other dental adhesives. The data is shown in Tables 2, 3, 4 and 7. Seven dental adhesives were selected: 1P-SEA (Dentsply), Xeno III (Dentsply), Prime & Bond NT (P&B NT, Dentsply), Prompt L-Pop (L-Pop, 3M ESPE), ClearFil SE Bond (SE, Kuraray), One-up Bond F (OBF, Tokuyama), i-Bond (IB, Heraeus Kulzer).

TABLE 2

24 hour Bond Strength (MPa) of Composite to Human Enamel and Dentin with Various Self-Etching Adhesives




TABLE 3

Thermal Cycled (1800X, 55/5° C.) Bond Strength* (MPa) of Composite to Human Enamel and Dentin with Various Self-Etching Adhesives





TABLE 4



[0022] In general, the previous adhesion data and graphs indicate that the 1P-SEA prototypes exhibit comparable performance to the leading currently marketed, 2-component, self-etching adhesive products.

[0023] The single-component self-etching adhesive (1P-SEA) prototype demonstrates an improvement to the existing commercial self-etching adhesive products. The new self-etching adhesive material achieves good adhesion performance with a simple one-coat application, without the need of separate acid-etching, a priming pre-treatment, or bonding step.

[0024] 1P-SEA is a light cured self-etching adhesive contained in a single package (bottle or single unit-dose) which is applied onto dentin and/or enamel surfaces to bond direct light cure composite restorations. The 1P-SEA is easily differentiated from the prior art which divides the active ingredients of the composition into two or more parts (in different packages) to avoid composition degradation or polymerization. The 1P-SEA is designed to overcome the single package storage stability issues through optimization of the formulation to provide competitive self-etching adhesion performance without presenting the stability issues commonly associated with other self-etching adhesives contained in a single package.

[0025] The improved performance in conjunction with other feature/benefits previously identified in the 1P-SEA is a function of the pH balance of the system in combination with an acid stable photoinitiating system. More specifically, the performance and pH balance is achieved primarily through the employment of the hydrolytically stable, acidic, high-strength adhesive monomer (PENTA), with a stable, bifunctional, hydrophilic monomer (AHPMA) that yields greater crosslinking.

[0026] Optimally, a minimal amount of water has been incorporated into a water-miscible polar aprotic organic solvent, e.g., acetone to facilitate etching. In addition, micro- or nanosized fillers and fluoride-releasing agents can also be incorporated into the 1P-SEA composition to enhance performance and inhibit secondary caries through releasing fluoride.

[0027] Optionally, a separate self-curing activator component can be utilized with the 1P-SEA to facilitate the use of this product for indirect self cure applications (prefabricated metal/porcelain/composite Inlays/Onlays/Veneers/Crowns/Bridges). The 1P-SEA exhibits superior bonding performance over other single component self-etching (prior art) products. More specifically, the 1P-SEA yields high initial and sustained long-term bonding performance (enamel bond strength ≥ 20 MPa and dentin bond strength ≥ 15 MPa). As previously discussed, the new 1P-SEA product achieves good adhesion with a simple "one-coat" one-step application technique, without separate acid-etching or priming.

[0028] The bonding performance of the 1P-SEA is sustained after excessive thermal stressing (5000 cycles at 55° C.). In addition, this product has demonstrated excellent shelf storage stability withstanding 3 weeks at 50° C. without a significant decrease in performance while -Bond (Kulzer), the only commercial single-component SEA gelled after storage at 50 248C for a week. In comparison with current commercial self-etching adhesive products, the 1P-SEA exhibits comparable or superior bonding performance, storage stability and shelf life.

[0029] Table 5 shows 24-hr dentin shear bond strength of 1P-SEA after storage at different temperatures and for different time duration. Table 6 compares bond strength of three different experimental 1P-SEA differing only in aromatic amines. DHEPT and EDAB are two most commonly used co-initiators for CQ. The formulations containing either DHEPT or EDAB did not lead to acceptable balanced properties. Only the formulation incorporating DMABN exhibits the superior balance of bond strength, storage stability and compatibility with different curing lights, e.g., QTH light and LED light. DMABN is the first time ever used in any dental adhesive.

TABLE 5


24 hr Dentin SBS of 1P-SEA in MPa (Mean $\pm$ Stdev.)				
Time (week)	37° C.	45° C.	50° C.	60° C.
0	17.6 $\pm$ 5.2	17.6 $\pm$ 5.2	17.6 $\pm$ 5.2	17.6 $\pm$ 5.2
1	NT	NT	NT	18.8 $\pm$ 7.5
1.5	NT	NT	NT	17.5 $\pm$ 4.6
2	NT	NT	17.8 $\pm$ 5.8	12.3 $\pm$ 4.2
3	NT	19.4 $\pm$ 9.2	18.1 $\pm$ 7.2	10.8 $\pm$ 3.5
3.5	NT	16.6 $\pm$ 3.8	17.9 $\pm$ 6.8	NT
4	NT	17.8 $\pm$ 5.1	8.2 (2.2)	NT
6	16.8 $\pm$ 7.0	15.0 $\pm$ 5.6	NT	NT
7	NT	16.7 $\pm$ 5.0	NT	NT
8	24.0 $\pm$ 2.8	17.5 $\pm$ 5.2	NT	NT
10	15.5 $\pm$ 4.8	7.3 $\pm$ 3.9	NT	NT
11	17.5 $\pm$ 4.6	NT	NT	NT
12	12.7 $\pm$ 3.8	NT	NT	NT

TABLE 6

24 hr Shear Bond Strength of 1P-SEA Containing Different Co-initiators					
Sample I.D.			1P-SEA containing DMABN	1P-SEA containing DHEPT	1P-SEA containing EDAB
Human Dentin	RT stored	QTH Light	23.2 (3.9)	NT	17.0 (7.5)
SBS (MPa):		LED Light	22.0 (4.0)	NT	15.6 (5.7)
Mean (SD)	50° C. 3 weeks	QTH Light	15.3 (4.2)	NT	14.5 (6.9)
		LED Light	15.8 (6.1)	NT	16.8 (6.8)
Human Enamel	RT stored	QTH Light	26.4 (5.3)	13.5 (6.7)	32.7 (7.2)
SBS (MPa):		LED Light	32.0 (3.0)	NT	30.1 (7.3)
Mean (SD)	50° C. 3 weeks	QTH Light	26.7 (5.3)	NT	7.6 (2.0)
		LED Light	35.3 (7.9)	NT	24.8 (13.3)

[0030] SEA exhibits excellent shear bond strength on both dentin and enamel when used with Self-Cure Activator to bond resin cements (i.e. Calibra). Table 7 illustrates that SEA has improved bonding performance in comparison to Prime & Bond NT for bonding Calibra to tooth substrates.

TABLE 7



Packaging Addendum

[0031] The minimum design specifications for SEA require a unit-dose packaging format similar to the system currently used for Prime & Bond® NT. Dentsply International, under U.S. Pat. No. 6,372,816 has patented this system (packaging), Waltz, et al., as of Apr. 16, 2002. The ideal requirements for packaging are defined as “integral brush unit-dose” (IB unit-dose). Patent application Ser. No. 10/668,946, Pierson, et al., Sep. 23, 2003, has been submitted for the IB unit-dose packaging under case number LDC-922-E.

What is claimed is:

1. A one-part, self-etching dental adhesive comprising a hydrolytically stable, acidic, high-strength adhesive monomer and a stable, bifunctional, hydrophilic monomer.

2. An adhesive as in claim 1, wherein said acidic monomer is PENTA.

3. An adhesive as in claim 1, wherein said bifunctional, hydrophilic monomer is AHPMA.

* * * * *