

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
4 December 2008 (04.12.2008)

PCT

(10) International Publication Number
WO 2008/145225 A2

(51) International Patent Classification:

C07C 69/92 (2006.01) C08F 32/00 (2006.01)
C07C 229/42 (2006.01) C09K 19/12 (2006.01)
C07D 471/04 (2006.01) C09K 19/38 (2006.01)

(74) Agent: VEENSTRA, Eva; Rolic Technologies Ltd.,
Patent Department, Gewerbestrasse 18, 4123 Allschwil
(CH).

(21) International Application Number:

PCT/EP2008/002836

(22) International Filing Date: 10 April 2008 (10.04.2008)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:

07109002.1 25 May 2007 (25.05.2007) EP
07118632.4 16 October 2007 (16.10.2007) EP

(71) Applicant (for all designated States except US): **ROLIC AG** [CH/CH]; Chamerstrasse 50, CH-6300 Zug (CH).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **ECKERT, Jean-François** [FR/FR]; 43, rue des Fauvettes, 67750 Kientzville (FR). **MARCK, Guy** [FR/FR]; 63A, rue de Landser, F-68440 Schlierbach (FR). **MÜLLER, Olivier** [FR/FR]; 15, rue Principale, 68610 Lautenbach (FR).


(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— without international search report and to be republished upon receipt of that report

(54) Title: PHOTOCROSSLINKABLE MATERIALS COMPRISING ALICYCLIC GROUP



(57) Abstract: A diamine compound of formula (I) is proposed as well as polymers, copolymers, polyamic acids, polyamic acid esters, or polyimides based on such compound.

Photocrosslinkable materials comprising alicyclic group

5 The invention relates to diamine compounds, represented by the general formula (I),
and also relates to oligomers, polymers and copolymers from the class of polyamic
acids, polyamic acid esters or polyimides (and any mixtures thereof) obtained by the
reaction of a diamine compound represented by the general formula (I) and optionally
of one or more additional other diamines, with one or more tetracarboxylic acid
anhydrides, and to the use of these diamine compounds, oligomers, polymers and
10 copolymers for the preparation of orientation layers for liquid crystals and in the
construction of unstructured and structured optical elements and multi-layer systems.

Liquid crystal displays (LCDs) are becoming increasingly dominant in advanced
visualization devices. LCDs offer favourable characteristics with respect to image
15 quality (high luminance, high resolution, colour and grey scale capability), power
consumption as well as dimensions and weight (flat panel displays). The use of
commercial LCDs has become widespread, e.g. in automotive and telecommunication
instruments, as well as in monitors of notebooks, desktop computers, television sets,
etc. Today the need for LCDs in television applications is rapidly growing. Recently
20 developed LCD modes possess high potentials in achieving fast response times, wide
viewing angles and high luminance. Amongst other newly developed LCD modes, the
MVA (multi-domain vertical alignment) mode appears to be the most promising for the
use in modern television applications.

25 In the MVA mode the liquid crystal molecules are usually nearly vertically aligned with
respect to the surface of the substrates. By using protrusions (or other alignment
subdivisions) on the surface of the substrate, the liquid crystal molecules become
locally pre-tilted within a single cell in more than one direction, leading to domains
switchable in different directions. This multi-domain configuration exhibits very good
30 display performance, with wide viewing angles of up to 160° in any direction, short
response times (below 20 ms), high contrast ratios (up to 700:1) and high brightness.

However, by means of using protrusions only, it is difficult to clearly define the domain space within a single pixel. Therefore the MVA mode demands additional manufacturing steps to ensure shape effects as well as electrical field effects on both the upper and lower substrate; hence all in all leading to complex manufacturing procedures.

In order to by-pass this technical challenge, the availability of an alignment layer would be desirable, which directly leads to pre-defined alignment directions within each pixel domain and having well controllable off-axis angles with respect to the normal axis of the substrate.

Methods for the preparation of orientation layers for liquid crystal materials are well known to the skilled person. Customarily used uniaxially rubbed polymer orientation layers, such as for example polyimides, however, do have a series of disadvantages, like the formation and deposition of dust during the rubbing process and concomitant partial destruction of the thin film transistors. Scratches due to brushing is another issue associated with this technique, which is particularly evident when the pixels are of the order of 10 microns or even lower, like e.g. in micro-display applications. Because of the strong optical magnification, which is required to visualize the displayed information, scratches easily become visible and are also the cause for the reduction of the contrast level. Furthermore, the rubbing process does not allow the production of structured layers.

The production procedure for obtaining orientation layers in which the direction of orientation is induced by irradiation with polarized light is not faced with the problems inherent to the rubbing process. With the irradiation technique it is furthermore also possible to create areas having different orientation and thus to structure the orientation layer as described for example in Jpn. J. Appl. Phys., 31 (1992), 2155–64 (Schadt et al).

Using the linearly photo-polymerizable alignment (LPP) technique, the possibility of realizing a four-domain vertical aligned nematic (VAN) LCD was demonstrated some years ago (K. Schmitt, M. Schadt; Proceedings of EuroDisplay 99, 6-9 September,

1999). The four-domain VAN-LCD exhibits an excellent off-state angular brightness performance.

5 Apart from the current display performance requirements to be fulfilled in modern TV applications, the use of appropriate LPP materials is furthermore also guided by the necessity to achieve specific optical and electro-optical properties, e.g. with respect to the compatibility with the TFT (thin film transistors). Other important characteristics of the materials must also be taken into consideration, i.e. those crucial parameters directly related to and dependent on the molecular properties of the material.

10

Primarily such characteristics are:

- High voltage holding ratio (VHR), i.e. VHR of > 90 % (measured at 80° C)
- High stability of the induced pre-tilt angle against light and heat
- Low alignment energy profile (short irradiation time and/or low irradiation energy)

15

In the case of LCDs of thin-film transistor type a certain amount of charge is applied over the course of a very short period of time to the electrodes of a pixel and must not subsequently drain away by means of the resistance of the liquid crystal. The ability to hold that charge and thus to hold the voltage drop over the liquid crystal is quantified by what is known as the "voltage holding ratio" (VHR). It is the ratio of the RMS-voltage (root mean square voltage) at a pixel within one frame period and the initial value of the voltage applied.

20

Photo-reactive materials for orientation layers with improved voltage holding ratios (VHR) are described in WO-A-99/49360, US 6,066,696, US 6,027,772, WO-A-99/15576 and WO-A-99/51662. In WO-A-99/49360, US 6,066,696 and US 6,027,772 blends of polymeric compounds are described, containing photo-reactive polymers and polyimides.


25

30 In WO-A-99/15576 and WO-A-99/51662 polyimides having photo-reactive cinnamate groups incorporated in their side chains are described. WO-A-99/15576 for instance discloses photo-active polymers which contain as side-chain specific photo-cross-

linkable groups and of which a typical monomer unit is 6-{2-methoxy-4-[(1E)-3-methoxy-3-oxoprop-1-enyl]phenoxy}hexyl 3,5-diaminebenzoate.

In the above cited references it was generally demonstrated that in order to achieve the aforementioned important parameters, molecular structures combining firstly a polyamic/polyimide backbone (i.e. delivering molecular polarity) and secondly side chains with an incorporated photo-reactive group, such as a cinnamic acid residue, are suitable for the general concept of planar orientation [requiring only slight pretilt angles, like e.g. being used in TN (twisted nematic) devices]. However, these types of molecular structures, primarily developed for TN applications, cannot directly be utilized in MVA applications.

Thus, the present invention relates to diamine compound of formula (I):



(I)

wherein,


- 20 A represents an unsubstituted or substituted carbocyclic or heterocyclic aromatic group selected from a monocyclic ring of five or six atoms, two adjacent monocyclic rings of five or six atoms, a bicyclic ring system of eight, nine or ten atoms, or a tricyclic ring system of thirteen or fourteen atoms;

- 5 B represents a straight-chain or branched C₁-C₁₆alkyl group, which is unsubstituted or substituted by di-(C₁-C₁₆alkyl)amino, C₁-C₆alkyloxy, nitro, cyano, fluoro and/or chlorine; and wherein one or more -CH₂- group may independently from each other be replaced by a linking group;
- Q represents an alicyclic group, which is unsubstituted or substituted by di-(C₁-C₁₆alkyl)amino, C₁-C₆alkyloxy, nitro, cyano, fluoro and/or chlorine; and wherein one or more -CH₂- group may independently from each other be replaced by a linking group;
- 10 D represents an unsubstituted or substituted, aliphatic, aromatic and/or alicyclic diamine group having from 1 to 40 carbon atoms;
- preferably D represents an unsubstituted or substituted, aliphatic, aromatic and/or alicyclic diamine group having from 1 to 40 carbon atoms, wherein the
- 15 diamine group comprises an aliphatic group, which may comprise one or more heteroatom and/or bridging group;
and/or an aromatic group;
and/or an alicyclic group;
- 20 E represents an aromatic group, an oxygen atom, a sulphur atom, -NH-, -N(C₁-C₆alkyl)-, -CR²R³, wherein R² and R³ are independently from each other hydrogen or a cyclic, straight-chain or branched, substituted or unsubstituted C₁-C₂₄alkyl, wherein one or more -CH₂- group(s) may be independently from each other replaced
- 25 by a linking group, and with the proviso that at least one of R² and R³ is not hydrogen;
- S¹, S² each independently from each other represents a spacer unit;
- X, Y each independently from each other represents hydrogen, fluorine, chlorine, cyano, unsubstituted or with fluorine substituted C₁-C₁₂alkyl, in which one or
- 30 more -CH₂- groups may be replaced by a linking group;
- n₁ represents 0, 1, 2, 3 or 4, preferably n₁ is 1 and n is 1 or 2;

n represents 1, 2, 3 or 4, preferably n₁ is 1 and n is 1 or 2;
with the proviso that if n is 2, 3, or 4, each A, B, x₁, E, S¹, S², X, Y are identical or different; and if n₁ is 2, 3 or 4 each B, x₁ is identical or different;
preferably,

5 wherein, if n > 1, compound (I) has several side-chains [wherein side-chain has the meaning of structures (I) without the group D], which are linked to residue D at one atomic position within group D, e.g. two or three side chains linked to one single carbon atom within group D, or they can be linked to group D at different atomic positions within group D, e.g. at adjacent atomic positions within group D, or/and they
10 can linked spaced further apart.

In a preferred embodiment the present invention relates to Diamine compound of formula (I):



wherein,

- A represents a unsubstituted or substituted carbocyclic or heterocyclic aromatic group selected from a monocyclic ring of five or six atoms, two adjacent
20 monocyclic rings of five or six atoms, a bicyclic ring system of eight, nine or ten atoms, or a tricyclic ring system of thirteen or fourteen atoms;
- B represents a straight-chain or branched C₁-C₁₆alkyl, which is unsubstituted or substituted by di-(C₁-C₁₆alkyl)amino, C₁-C₆alkyloxy, nitro, cyano and/or chlorine or fluorine; and wherein one or more -CH₂- group may independently
25 be replaced by a linking group;
- Q represents an unsubstituted alicyclic group, which is or substituted by

di-(C₁-C₁₆alkyl)amino, C₁-C₆alkyloxy, nitro, cyano, fluoro and/or chlorine; and wherein one or more -CH₂- group may independently from each other be replaced by a linking group;

5 D represents unsubstituted or substituted aliphatic, aromatic or alicyclic diamine group having from 1 to 40 carbon atoms,

E represents an aromatic group, an oxygen atom, a sulphur atom, -NH-,
-N(C₁-C₆alkyl)-, -CR²R³,
wherein R² and R³ are independently from each other hydrogen or a cyclic,
straight-chain or branched, substituted or unsubstituted C₁-C₂₄alkyl, wherein
10 one or more -CH₂- groups may be replaced by a linking group, and with the proviso that at least one of R² and R³ is not hydrogen;

S¹, S² each independently from each other represents a spacer unit;

X, Y each independently from each other represents hydrogen, fluorine, chlorine,
cyano, unsubstituted or with fluorine substituted C₁-C₁₂alkyl, in which one or
15 more -CH₂- groups may be replaced by a linking group;

n is 1, 2, 3 or 4,

with the proviso that if n is 2, 3, or 4, each A, B, x₁, D, E, S¹, S², X, Y may be identical or different.

20

The term "linking group", as used in the context of the present invention is preferably be selected

from -O-, -CO-, -CO-O-, -O-CO-, --N< , -NR¹-, -NR¹-CO-, -CO-NR¹-, -NR¹-CO-O-,
-O-CO-NR¹-, -NR¹-CO-NR¹-, -CH=CH-, -C≡C-, -O-CO-O-, and -Si(CH₃)₂-O-Si(CH₃)₂-,
25 and wherein:

R¹ represents a hydrogen atom or C₁-C₆alkyl;

with the proviso that oxygen atoms of linking groups are not directly linked to each other.

30

The term "spacer unit" as used in the context of the present invention, is preferably a single bond, a cyclic, straight-chain or branched, substituted or unsubstituted C₁-C₂₄alkylen, wherein one or more, preferably non-adjacent, -CH₂- groups may independently from each other be replaced by a linking group as described above
 5 and/or a non-aromatic, aromatic, unsubstituted or substituted carbocyclic or heterocyclic group connected via bridging groups.

More preferably, the spacer unit is a cyclic, straight-chain or branched, substituted or unsubstituted C₁-C₂₄alkylen, wherein one or more, preferably non-adjacent, -CH₂-
 10 groups may independently from each other be replaced by a linking group and/or a non-aromatic, aromatic, unsubstituted or substituted carbocyclic or heterocyclic group connected via bridging groups.

A bridging group as used in the context of the present invention is preferably selected from -CH(OH)-, -CO-, -CH₂(CO)-, -SO-, -CH₂(SO)-, -SO₂-, -CH₂(SO₂)-, -COO-, -OCO-,
 15 -COCF₂-, -CF₂CO-, -S-CO-, -CO-S-, -SOO-, -OSO-, -SOS-, -O-CO-O-, -CH₂-CH₂-, -OCH₂-, -CH₂O-, -CH=CH-, -C≡C-, -CH=CH-COO-, -OCO-CH=CH-, -CH=N-, -C(CH₃)=N-, -N=N- or a single bond; or a cyclic, straight-chain or branched, substituted or unsubstituted C₁-C₂₄alkylen, wherein one or more -CH₂- groups may independently
 20 from each other be replaced by a linking group as described above.

Alkyl, alkyloxy, alkylcarbonyloxy, acryloyloxyalkoxy, acryloyloxyalkyl, acryloyloxyalken, alkyloxycarbonyloxy, alkylacryloyloxy, methacryloyloxyalkoxy, methacryloyloxyalkyl, methacryloyloxyalken, alkylmethacryloyloxy, alkylmethacryloyloxy, alkylvinyl,
 25 alkylvinylloxy and alkylallyloxy and alkylene, as used in the context of the present invention denote with their alkyl residue, respectively their alkylene residue, a cyclic, straight-chain or branched, substituted or unsubstituted alkyl, respectively alkylene, in which one or more, preferably non-adjacent, -CH₂- group may be replaced by a linking group.

Further, the alkyl residue is for example C₁-C₄₀alkyl, especially C₁-C₃₀alkyl, preferably C₁-C₂₀alkyl, more preferably C₁-C₁₆alkyl, most preferably C₁-C₁₀alkyl and especially most preferably C₁-C₆alkyl. Accordingly alkylen is for example C₁-C₄₀alkylen, especially

C₁-C₃₀alkylen, preferably C₁-C₂₀alkylen, more preferably C₁-C₁₆alkylen, most preferably C₁-C₁₀alkylen and especially most preferably C₁-C₆alkylen.

5 In the context of the present invention the definitions for alkyl given below, are applicable to alkylene in analogy.

C₁-C₆alkyl is for example methyl, ethyl, propyl, isopropyl, butyl, sec.-butyl, tert.-butyl, pentyl or hexyl.

10 C₁-C₁₀alkyl is for example methyl, ethyl, propyl, isopropyl, butyl, sec.-butyl, tert.-butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl.

15 C₁-C₁₆alkyl is for example methyl, ethyl, propyl, isopropyl, butyl, sec.-butyl, tert.-butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl or hexadecyl.

20 C₁-C₂₀alkyl is for example methyl, ethyl, propyl, isopropyl, butyl, sec.-butyl, tert.-butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, nondecyl, eicosyl.

C₁-C₂₄alkyl is for example methyl, ethyl, propyl, isopropyl, butyl, sec.-butyl, tert.-butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, nondecyl, eicosyl.

25 C₁-C₃₀alkyl is for example methyl, ethyl, propyl, isopropyl, butyl, sec.-butyl, tert.-butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, nondecyl, eicosyl, heneicosyl, tricosyl, tetracosyl, pentacosyl, hexacosyl, heptacosyl, octacosyl, nonacosyl or triacontyl.

30 C₁-C₄₀alkyl is for example methyl, ethyl, propyl, isopropyl, butyl, sec.-butyl, tert.-butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, nondecyl, eicosyl, heneicosyl, tricosyl,

tetracosyl, pentacosyl, hexacosyl, heptacosyl, octacosyl, nonacosyl, triacontyl or tetracontyl.

C₁-C₂₀acryloyloxyalkylene, preferably C₁-C₁₀acryloyloxyalkylene,

5 C₁- C₆ acryloyloxyalkylene is for example acryloyloxymethylen, acryloyloxyethylene, acryloyloxypropylene, acryloyloxyisopropylene, acryloyloxybutylene, acryloyloxy-sec.-butylene, acryloyloxypentylene, acryloyloxyhexylene, acryloyloxyheptylene, acryloyloxyoctylene, acryloyloxynonylene, acryloyloxydecylene, acryloyloxyundecylene, acryloyloxydodecane, acryloyloxytridecylene, acryloyloxytetradecylene,
10 acryloyloxypentyldecane, acryloyloxyhexadecylene, acryloyloxyheptadecylene, acryloyloxyoctadecylene, acryloyloxynondecylene, acryloyloxyeicosylene.

C₁-C₂₀methacryloyloxyalkylene, preferably C₁-C₁₀methacryloyloxyalkylene,

C₁- C₆ methacryloyloxyalkylene is for example methacryloyloxymethylen,
15 methacryloyloxyethylene, methacryloyloxypropylene, methacryloyloxyisopropylene, methacryloyloxybutylene, methacryloyloxy-sec.-butylene, methacryloyloxypentylene, methacryloyloxyhexylene, methacryloyloxyheptylene, methacryloyloxyoctylene, methacryloyloxynonylene, methacryloyloxydecylene, methacryloyloxyundecylene, methacryloyloxydodecane, methacryloyloxytridecylene, methacryloyloxytetradecylene,
20 methacryloyloxypentyldecane, methacryloyloxyhexadecylene, methacryloyloxyheptadecylene, methacryloyloxyoctadecylene, methacryloyloxynondecylene, methacryloyloxyeicosylene.

C₁-C₂₀acryloyloxyalkoxy, preferably C₁-C₁₀acryloyloxyalkoxy,

25 C₁- C₆ acryloyloxyalkoxy is for example acryloyloxymethoxy, acryloyloxyethoxy, acryloyloxypropoxy, acryloyloxyisopropoxy, acryloyloxybutoxy, acryloyloxy-sec.-butoxy, acryloyloxypentoxy, acryloyloxyhexoxy, acryloyloxyheptoxy, acryloyloxyoctoxy, acryloyloxynonoxo, acryloyloxydecoxy, acryloyloxyundecoxy, acryloyloxydodecanoxy, acryloyloxytridecyloxy.

30

C₁-C₂₀methacryloyloxyalkoxy, preferably C₁-C₁₀methacryloyloxyalkoxy,

C₁- C₆ methacryloyloxyalkoxy is for example methacryloyloxymethoxy, methacryloyloxyethoxy, methacryloyloxypropoxy, methacryloyloxyisopropoxy, methacryloyloxybutoxy, methacryloyloxy-sec.-butoxy, methacryloyloxypentoxy,

methacryloyloxyhexoxy, methacryloyloxyheptoxy, methacryloyloxyoctoxy, methacryloyloxynonoxo, methacryloyloxydecoxy, methacryloyloxyundecoxy, methacryloyloxydodecanoxy, methacryloyloxytridecyloxy.

- 5 An aliphatic group is for example a saturated or unsaturated, mono-, bi-, tri-, tetra-, penta-, hexa-, hepta-, octa-, nona-, deca-valent alkyl, alkylene, alkyloxy, alkylcarbonyloxy, acryloyloxy, alkylacryl, alkylmethacryl, alkyl(en)acryl(en), alkyl(en)methacryl(en), alkyloxy carbonyloxy, alkyloxy carbonyloxy methacryloyloxy, alkylvinyl, alkylvinylloxy or alkylallyloxy, which may comprise one or more heteroatom
10 and/or bridging group.

- An alicyclic group is preferably a non-aromatic group or unit. Preferably an alicyclic group is a non-aromatic carbocyclic or heterocyclic group and represents for example ring systems, with 3 to 30 carbon atoms, preferably 3 to 20 carbon atoms, more
15 preferably 3 to 10 carbon atoms and most preferably 3 to 6 carbon atoms, as for example cyclopropane, cyclobutane, cyclopentane, cyclopentene, cyclohexane, cyclohexene, cyclohexadiene, decaline, tetrahydrofuran, dioxane, pyrrolidine, piperidine or a steroidal skeleton such as cholesterol. More preferably an alicyclic group is a cyclopentane, cyclopentene, cyclohexane, cyclohexene, cyclohexadiene,
20 decaline, tetrahydrofuran, dioxane and most preferably cyclohexane.

Further preferred is an alicyclic group, especially cyclohexyl or cyclohexyl, which is substituted with fluoro.

- 25 The term "aromatic", as used in the context of the present invention, preferably denotes unsubstituted or substituted carbocyclic and heterocyclic groups, incorporating five, six, ten or 14 ring atoms, e.g. furan, benzene or phenylene, pyridine, pyrimidine, naphthalene, which may form ring assemblies, such as biphenylene or triphenylene, which are uninterrupted or interrupted by at least a single heteroatom and/or at least a
30 single bridging group; or fused polycyclic systems, such as phenanthrene, tetraline. Preferably aromatic groups are benzene, phenylene, biphenylene or triphenylene. More preferred aromatic groups are benzene, phenylene and biphenylene.

A carbocyclic or heterocyclic aromatic group incorporates preferably five, six, ten or 14 ring atoms, as for example furan, benzene, pyridine, triazine, pyrimidine, naphthalene, phenanthrene, biphenylene or tetraline units, preferably naphthalene, phenanthrene, biphenylene or phenylene, more preferably naphthalene, biphenylene or phenylene, and most preferably phenylene.

The carbocyclic or heterocyclic aromatic group is for example unsubstituted or mono- or poly-substituted. Preferred substituents of carbocyclic or heterocyclic aromatic groups are at least one halogen, hydroxyl, a polar group, acryloyloxy, alkylacryloyloxy, alkoxy, alkylcarbonyloxy, alkyloxy carbonyloxy, alkyloxocarbonyloxy, methacryloyloxy, vinyl, vinyloxy and/or allyloxy group, wherein the alkyl residue has preferably from 1 to 20 carbon atoms, and more preferably having from 1 to 10 carbon atoms. Preferred polar groups are nitro, cyano or a carboxy group, and/or a cyclic, straight-chain or branched C₁-C₃₀alkyl, which is unsubstituted, mono- or poly-substituted. Preferred substituents of C₁-C₃₀alkyl are methyl, fluorine and/or chlorine, wherein one or more, preferably non-adjacent, -CH₂- group may independently of each other be replaced by a linking group. Preferably, the linking group is selected from -O-, -CO-, -COO- and/or -OCO-.

A monocyclic ring of five or six atoms is for example furan, benzene, preferably phenylene, pyridine, pyrimidine.

A bicyclic ring system of eight, nine or ten atoms is for example naphthalene, biphenylene or tetraline.

A tricyclic ring system of thirteen or fourteen atoms is for example phenanthrene.

The term "phenylene", as used in the context of the present invention, preferably denotes a 1,2-, 1,3- or 1,4-phenylene group, which is optionally substituted. It is preferred that the phenylene group is either a 1,3- or a 1,4-phenylene group. 1,4-phenylene groups are especially preferred.

The term "halogen" denotes a chloro, fluoro, bromo or iodo substituent, preferably a chloro or fluoro substituent.

The term "polar group", as used in the context of the present invention primarily denotes a group like a nitro, cyano, or a carboxy group.

- 5 The term "heteroatom", as used in the context of the present invention primarily denotes oxygen, sulphur and nitrogen, preferably oxygen and nitrogen, in the latter case preferably in the form of -NH-.

- 10 The term "optionally substituted" as used in the context of the present invention primarily means substituted by lower alkyl, such as C₁-C₆alkyl, lower alkoxy, such as C₁-C₆alkoxy, hydroxy, halogen or by a polar group as defined above.

- 15 The term "diamine" or "diamine compound" is to be understood as designating a chemical structure which has at least two amino groups, i.e. which may also have 3 or more amino groups. The at least two amino groups are preferably able to react with e.g. anhydrides as outlined in more detail below.

- 20 The term "dinitro" or "dinitro compound" is to be understood as designating a chemical structure which has at least two nitro groups, i.e. which may also have 3 or more nitro groups, and wherein the dinitro group is a precursor compound of the "diamino compound". The dinitro compound is conventionally converted to the diamino compound by reduction methods known in the art.

- 25 With respect to straight chain or branched alkyl, alkylene, alkoxy, alkylcarbonyloxy, acryloyloxyalkoxy, acryloyloxyalkyl, acryloyloxyalkene, alkyloxycarbonyloxy, alkylacryloyloxy, methacryloyloxyalkoxy, methacryloyloxyalkyl, methacryloyloxyalkene, alkylmethacryloyloxy, alkylmethacryloyloxy, alkylvinyl, alkylvinylloxy, alkylallyloxy and alkylene groups it is repeatedly pointed out that some or several of the -CH₂- groups may be replaced e.g. by heteroatoms, but also by other groups, preferably bridging groups. In such cases it is generally preferred that such replacement groups are not
30 directly linked to each other. It is alternatively preferred that heteroatoms, and in

particular oxygen atoms are not directly linked to each other.

Preferably, A is unsubstituted or substituted phenanthrylene, naphthylene, biphenylene or phenylene, wherein the preferred substituent(s) is(are) a halogen atom, a hydroxy group and/or by a polar group, wherein the polar group is preferably nitro, cyano, carboxy; and/or by acryloyloxy, alkylacryl, alkylmethacryl, alkyl(en)acryl, alkyl(en)methacryl, acrylenacryl, methacrylenalkyl, methacryloyloxy, vinyl, vinyloxy, allyl, allyloxy, and/or by a cyclic, straight-chain or branched alkyl, which is unsubstituted, mono- or poly-substituted by fluorine and/or chlorine, having from 1 to 20 carbon atoms, wherein one or more, preferably non-adjacent, -CH₂- groups may independently be replaced by a linking group and or an aromatic or an alicyclic group, preferably the linking group is selected from -O-, -CO-, -CO-O-, -O-CO-.

More preferably A is substituted or unsubstituted naphthylene, biphenylene or phenylene, wherein the preferred substituent(s) is(are) halogen atom, hydroxy group and/or by acryloyloxy, alkylacryl, alkylmethacryl, acrylenacryl, methacrylenalkyl, methacryloyloxy, straight-chain or branched alkyl, alkoxy, alkylcarbonyloxy, and/or alkyloxycarbonyl groups, wherein the alkyl residue has from 1 to 20 carbon atoms.

Most preferably A is substituted or unsubstituted phenylene, preferably 1,4-phenylene, wherein the preferred substituent(s) is(are) a halogen atom, and/or by acryloyloxy or methacryloyloxy, and/or by an alkoxy, alkylacryl, alkylmethacryl, acrylenacryl, methacrylenalkyl, alkylcarbonyloxy, and/or alkyloxycarbonyl groups, wherein the alkyl residue has from 1 to 10 carbon atoms.

A preferred embodiment of the present invention concerns a diamine compound of formula (I) wherein B is

represents a straight-chain or branched C₁-C₁₆alkyl group or C₁-C₁₆fluoralkyl group, wherein the fluoralkyl group has terminal units selected from -CF₂H and -CF₃, preferably selected from -CF₂H or -CF₃, -CF₂CF₃, -CF₂CHF₂, -(CF₂)₂CF₃, -(CF₂)₂CHF₂, -(CF₂)₃CHF₂, -(CF₂)₃CF₃, -CF(CF₃)₂ and -CF₂(CHF)CF₃.

Preferably B is a straight-chain or branched C₁-C₁₂alkyl or C₁-C₁₂fluoralkyl group, wherein the fluoralkyl group has one or more, preferably non-adjacent, -CH₂- group(s) may independently from each other be replaced by a group selected from
 5 -O-, -CO-, -CO-O-, -O-CO-, -NR¹-, -NR¹-CO-, -CO-NR¹-, -NR¹-CO-O-, -O-CO-NR¹-,
 -NR¹-CO-NR¹-, -CH=CH-, -C≡C-, -O-CO-O-, and -Si(CH₃)₂-O-Si(CH₃)₂-, an aromatic and an alicyclic group; and wherein:

R¹ represents a hydrogen atom or C₁-C₆alkyl;

with the proviso that oxygen atoms are not directly linked to each other; and wherein the fluoralkyl group has terminal units selected from -CF₂H and -CF₃, preferably
 10 selected from -CF₂H or -CF₃, -CF₂CF₃, -CF₂CHF₂, -(CF₂)₂CF₃, -(CF₂)₂CHF₂, -
 (CF₂)₃CHF₂, -(CF₂)₃CF₃, -CF(CF₃)₂ and -CF₂(CHF)CF₃.

More preferably, B is a straight-chain or branched C₁-C₁₂alkyl or a C₁-C₁₂fluoralkyl group, wherein one or more, preferably non-adjacent, -CH₂- group(s) may be replaced
 15 by a group selected from

from -O-, -CO-, -CO-O-, -O-CO-, -NR¹-, -NR¹-CO-, -CO-NR¹- or -CH=CH- wherein:

R¹ represents a hydrogen atom or C₁-C₆alkyl;

with the proviso that oxygen atoms are not directly linked to each other.

20 Most preferably, B is a straight-chain or branched C₁-C₈alkyl or a C₁-C₈fluoralkyl, wherein one or more, preferably non-adjacent, -CH₂- group(s) may be replaced by a group selected from

from -O-, -CO-, -CO-O-, -O-CO-, -NR¹-, -NR¹-CO-, -CO-NR¹- or -CH=CH- wherein:

R¹ represents a hydrogen atom or C₁-C₆alkyl;

25 with the proviso that oxygen atoms are not directly linked to each other other; and wherein the fluoralkyl group has terminal units selected from -CF₂H and -CF₃, preferably selected from -CF₂H or -CF₃, -CF₂CF₃, -CF₂CHF₂, -(CF₂)₂CF₃, -
 (CF₂)₂CHF₂, -(CF₂)₃CHF₂, -(CF₂)₃CF₃, -CF(CF₃)₂ and -CF₂(CHF)CF₃.

30 .
 Especially most preferably, B is a straight-chain or branched C₁-C₈alkyl or a C₁-C₈fluoralkyl, wherein one or more, preferably non-adjacent, the -CH₂- group may be replaced by a group selected from -O-, -CO-, -CO-O-, -O-CO-, and -CH=CH-, with the proviso that oxygen atoms are not directly linked to each other.

Further preferred is B:

methy, ethyl, propyl, isopropyl, butyl, sec.-butyl, tert.-butyl, pentyl, iso-pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, nondecyl, eicosyl, heneicosyl, tricosyl, tetracosyl, pentacosyl, hexacosyl, heptacosyl, octacosyl, nonacosyl or triacontyl;

methoxy, ethoxy, propoxy, butoxy, pentoxy, hexoxy, heptoxy, nonoxy;

methylen carbamate; ethylen carbamate; propylen carbamate; butylen carbamate; pentylen carbamate; hexylen carbamate;

methyloxy; ethyloxy; propyloxy; butyloxy; pentyloxy; hexyloxy;

but-2-enyl; pent-1-enyl; hex-1-enyl; hept-1-enyl; acetylaminomethoxy; acetylaminopropoxy; acetylaminobutoxy; pent-4-enoxy; pent-4-enyloxy; hex-5-enoxy or pent-5-enyloxy.

Further preferred is B, which is substituted with fluoro:

trifluoromethyl; 2,2,2-trifluoroethyl; difluoromethyl; pentafluoroethyl; 2,2-tetrafluoroethyl; 3,2-tetrafluoroethyl; 3,3,3-trifluoropropyl; 2,2,3,3-tetrafluoropropyl; 2,2,3,3,3-pentafluoropropyl; hexafluoropropyl; heptafluoropropyl; 4,4,4-trifluorobutyl; tetrafluorobutyl; 3,3,4,4,4-pentafluorobutyl; hexafluorobutyl; 2,2,3,3,4,4,4-heptafluorobutyl; 5,5,5-trifluoropentyl; tetrafluoropentyl; 4,4,5,5,5-pentafluoropentyl; hexafluoropentyl; 3,3,4,4,5,5,5-heptafluoropentyl; 6,6,6-trifluorohexyl; tetrafluorohexyl; 5,5,6,6,6-pentafluorohexyl; hexafluorohexyl; 4,4,5,5,6,6,6-heptafluorohexyl; nonafluorohexyl;

1-trifluoro-1,2,2,2-tetrafluoroethoxy, 2-trifluoro-2,3,3,3-tetrafluoropropoxy, 3-trifluoro-3,4,4,4-tetrafluorobutoxy, 4-trifluoro-4,5,5,5-tetrafluoropentoxy, 5-trifluoro-5,6,6,6-tetrafluorohexoxy, 6-trifluoro-6,7,7,7-tetrafluoroheptoxy, 7-trifluoro-7,8,8,8-tetrafluorononoxy;

fluoroalkoxy derivatives, such as

trifluoromethoxy; 2,2,2-trifluoroethoxy; difluoromethoxy; pentafluoroethoxy; 1,1,2,2-tetrafluoroethoxy; 2,2,2,1-tetrafluoroethoxy; 3,3,3-trifluoropropoxy; 2,2,3,3-tetrafluoropropoxy; 2,2,3,3,3-pentafluoropropoxy; hexafluoropropoxyl; heptafluoropropoxy; 4,4,4-trifluorobutoxy; tetrafluorobutoxy; 3,3,4,4,4-pentafluorobutoxy; 2,2,3,3,4,4-hexafluorobutoxy; 2,2,3,3,4,4,4-heptafluorobutoxy; 5,5,5-trifluoropentoxyl; tetrafluoropentoxyl; 4,4,5,5,5-pentafluoropentoxyl; hexafluoropentoxyl; 3,3,4,4,5,5,5-heptafluoropentoxyl; 6,6,6-trifluorohexoxyl; tetrafluorohexoxyl; 5,5,6,6,6-pentafluorohexoxyl; hexafluorohexoxyl; 4,4,5,5,6,6,6-heptafluorohexoxyl; nonafluorohexoxyl;

10

trifluoromethylen carbamate; 2,2,2-trifluoroethylen carbamate; difluoromethylen carbamate; pentafluoroethylen carbamate; 2,2-tetrafluoroethylen carbamate; 3,2-tetrafluoroethylen carbamate; 3,3,3-trifluoropropylen carbamate; 2,2,3,3-tetrafluoropropylen carbamate; 2,2,3,3,3-pentafluoropropylen carbamate; hexafluoropropylen carbamate; heptafluoropropylen carbamate; 4,4,4-trifluorobutylen carbamate; tetrafluorobutylen carbamate; 3,3,4,4,4-pentafluorobutylen carbamate; hexafluorobutylen carbamate; 2,2,3,3,4,4,4-heptafluorobutylen carbamate; 5,5,5-trifluoropentylen carbamate; tetrafluoropentylen carbamate; 4,4,5,5,5-pentafluoropentylen carbamate; hexafluoropentylen carbamate; 3,3,4,4,5,5,5-heptafluoropentylen carbamate; 6,6,6-trifluorohexylen carbamate; tetrafluorohexylen carbamate; 5,5,6,6,6-pentafluorohexylen carbamate; hexafluorohexylen carbamate; 4,4,5,5,6,6,6-heptafluorohexylen carbamate; nonafluorohexylen carbamate;


fluoroalkyloxy derivatives, such as

trifluoromethyloxy; 2,2,2-trifluoroethyloxy; pentafluoroethyloxy; 1,1,2,2-tetrafluoroethyloxy; 2,2,2,1-tetrafluoroethyloxy; 3,3,3-trifluoropropyloxy; tetrafluoropropyloxy; 2,2,3,3,3-pentafluoropropyloxy; hexafluoropropyloxy; 1,1,2,2,3,3,3-heptafluoropropyloxy; 4,4,4-trifluorobutyloxy; tetrafluorobutyloxy; 3,3,4,4,4-pentafluorobutyloxy; hexafluorobutyloxy; 2,2,3,3,4,4,4-heptafluorobutyloxy; 5,5,5-trifluoropentyloxy; tetrafluoropentyloxy; 4,4,5,5,5-pentafluoropentyloxy; hexafluoropentyloxy; 3,3,4,4,5,5,5-heptafluoropentyloxy; 6,6,6-trifluorohexyloxy; tetrafluorohexyloxy; 5,5,6,6,6-pentafluorohexyloxy; hexafluorohexyloxy; 4,4,5,5,6,6,6-heptafluorohexyloxy; trifluoroacetyl; nonafluorohexyloxy;

4,4,4-trifluorobut-2-enyl; 5,5,5-trifluoropent-1-enyl; 6,6,6-trifluorohex-1-enyl; 7,7,7-trifluorohept-1-enyl; trifluoroacetylaminomethoxy; trifluoroacetylaminoethoxy; trifluoroacetylaminopropoxy; trifluoroacetylaminobutoxy; 2-fluoroethyl; 3-fluoropropyl; 4-fluorobutyl; 5-fluoropentyl; 6-fluorohexyl; 2-fluoroethoxy; 3-fluoropropoxy; 4-fluorobutoxy; 5-fluoropentoxo; 6-fluorohexyloxy; 4-fluorobut-1-enyl; 5-fluoropent-1-enyl; 6-fluorohex-1-enyl; 7-fluorohept-1-enyl; 4,4,4-trifluoro-3-(trifluoromethyl)butoxy; 4,5,5-trifluoropent-4-enoxy; 4,5,5-trifluoropent-4-enoyloxy; 5,6,6-trifluorohex-5-enoxy or 5,6,6-trifluoropent-5-enoyloxy.

Especially preferred are fluoroalkoxy, preferably trifluor- and pentafluoro fluoroalkoxy derivatives, especially preferred are 5,5,5-trifluoropentoxo and 4,4,5,5,5-pentafluoropentoxo.

D is preferably selected from formula (III):



wherein:

R^5 , R^6 each independently from each other represents a hydrogen atom or C_1 - C_6 alkyl;

Sp^1 , Sp^2 each independently from each other represent a single bond or an unsubstituted or substituted straight-chain or branched C_1 - C_{20} alkylene, in which one or more

-CH₂-group may independently from each other be replaced by a linking group, and

k^1 , k^2 each independently is an integer having a value of 0 or 1; and

X^1 , X^2 each independently represents a linking spacer, preferably selected from -O-, -S-, -NH-, N(CH₃)-, -CH(OH)-, -CO-, -CH₂(CO)-, -SO-, -CH₂(SO)-, -SO₂-, -CH₂(SO₂)-, -COO-, -OCO-, -OCO-O-, -S-CO-, -CO-S-, -SOO-, -OSO-, -SOS-, -CH₂-CH₂-, -OCH₂-, -CH₂O-, -CH=CH-, or -C≡C- or a single bond; and


t^1 , t^2 each independently is an integer having a value of 0 or 1; and

- C^3 , C^4 each independently represents a non-aromatic, aromatic, substituted or unsubstituted carbocyclic or heterocyclic group, which may have a side chain T, and
- Z^3 represents a bridging group; and
- 5 Z^4 represents a substituted or unsubstituted straight-chain or branched C_1 - C_{20} alkylene group, in which one or more $-CH_2-$ group may independently from each other be replaced by a non-aromatic, aromatic, unsubstituted or substituted carbocyclic or heterocyclic group; and/or a heteroatom and/or by a bridging group as described above; preferably, Z^4 has one of the meanings of
- 10 Z^3 or represents an unsubstituted or substituted straight-chain or branched C_1 - C_{14} alkylene group, in which one or more, preferably non-adjacent, $-CH_2-$ group may be replaced by an oxygen atom and/or one or more carbon-carbon single bond is replaced by a carbon-carbon double or a carbon-carbon triple bond; and
- 15 a_3 , a_4 are independently integers from 0 to 3, such that $a_3 + a_4 \leq 4$; and wherein D is at least once linked to at least one group S^1 in formula (I) via group Sp^1 and/or Sp^2 ; and/or linked via at least one non-aromatic, aromatic, substituted or unsubstituted carbocyclic or heterocyclic group of C^3 and/or of group C^4 , and/or linked via at least one side chain T of group C^4 and/or of group C^3 ;
- 20 and/or linked via group Z^4 ; and at least one of k^1 , k^2 , a^3 and a^4 is not equal to zero; and wherein
- linking group and bridging group are as described above,
- and preferably compound of formula (I), wherein preferably, if $n > 1$, then the side chains [i.e. structures (I) without the group D] can either be linked to the group
- 25 D at one atomic position within group D, e.g. two or three side chains connected to one single carbon atom within group D, or they can be linked to group D at different atomic positions within group D, e.g. at adjacent atomic positions within group D, but also spaced further apart.
- 30 The term "side chain", T, represents a substituted or unsubstituted straight-chain or branched C_1 - C_{20} alkylene group(s), in which one or more $-CH_2-$ group may independently from each other be replaced by a non-aromatic, aromatic, unsubstituted or substituted carbocyclic or heterocyclic group, or a heteroatom and/or by a bridging group, which is at least once linked to at least one group S^1 in formula (I).

Preferably D is selected from formula (III), wherein:

C³, C⁴ independently from each other are selected from a compound of group

5 G², wherein group G² denotes:



10

wherein

"—" denotes the connecting bonds of C³ and C⁴ to the adjacent groups of compound of formula (III) as described above; and

15

L is -CH₃, -COCH₃, -OCH₃, nitro, cyano, halogen, CH₂=CH-, CH₂=C(CH₃)-, CH₂=CH-(CO)O-, CH₂=CH-O-, -NR⁵R⁶, CH₂=C(CH₃)-(CO)O-, CH₂=C(CH₃)-O-,

wherein:

5 R⁵, R⁶ each independently from each other represents a hydrogen atom or C₁-C₆alkyl;

T represents a substituted or unsubstituted straight-chain or branched C₁-C₂₀alkylene group, in which one or more -CH₂- group may independently from each other be replaced by a non-aromatic, aromatic, unsubstituted or substituted carbocyclic or heterocyclic group, or a heteroatom and/or by a bridging group;

m is an integer from 0 to 2; preferably 1 or 0; and more preferably 0;

u₁ is an integer from 0 to 4, with the proviso that m + u₁ is ≤4; and

u₂ is an integer from 0 to 3; with the proviso that m + u₂ is ≤3; and

15 u₃ is an integer from 0 to 2; with the proviso that m + u₃ is ≤2.

D is more preferably selected from the following group of structures: substituted or unsubstituted o-phenylenediamine, p-phenylenediamine, m-phenylenediamine, biphenyldiamine, aminophenylen-Z⁴-phenylenamino, wherein Z⁴ has the same meaning and preferences as given above; naphthylenediamine, benzidine, diaminofluorene, 3,4-diaminobenzoic acid, 3,4-diaminobenzyl alcohol dihydrochloride, 2,4-diaminobenzoic acid, L-(+)-threo-2-amino-1-(4-aminophenyl)-1,3-propanediol, p-aminobenzoic acid, [3,5-3h]-4-amino-2-methoxybenzoic acid, L-(+)-threo-2-(N,N-dimethylamino)-1-(4-aminophenyl)-1,3-propanediol, 2,7-diaminofluorene, 25 4,4'-diaminooctafluorobiphenyl, 3,3'-diaminobenzidine, 2,7-diamino-9-fluorenone, 3,5,3',5'-tetrabromo-biphenyl-4,4'-diamine, 2,2'-dichloro[1,1'-biphenyl]-4,4'-diamine, 3,9-diamino-1,11-dimethyl-5,7-dihydro-dibenzo(a,c)cyclohepten-6-one, dibenzo(1,2)dithiine-3,8-diamine, 3,3'-diaminobenzophenone, 3,3'-diaminodiphenylmethane, 4,4-bis-(3-amino-4-hydroxyphenyl)-valeric acid, 30 2,2-bis(3-amino-4-hydroxyphenyl)hexafluoropropane, 2,2-bis(3-amino-4-methylphenyl)hexafluoropropane, tetrabromo methylenedianiline, 2,7-diamino-9-fluorenone, 2,2-bis(3-aminophenyl)hexafluoropropane, bis-(3-amino-4-chloro-phenyl)-methanone,


bis-(3-amino-4-dimethylamino-phenyl)-methanone,
 3-[3-amino-5-(trifluoromethyl)benzyl]-5-(trifluoromethyl)aniline,
 1,5-diaminonaphthalene, benzidine-3,3'-dicarboxylic acid,
 4,4'-diamino-1,1'-binaphthyl, 4,4'-diaminodiphenyl-3,3'-diglycolic acid, dihydroethidium,
 5 o-dianisidine, 2,2'-dichloro-5,5'-dimethoxybenzidine,
 3-methoxybenzidine, 3,3'-dichlorobenzidine (diphenyl-d6),
 2,2'-bis(trifluoromethyl)benzidine, 3,3'-bis(trifluoromethyl)benzidine, 3,3'-
 dichlorobenzidine-d6, tetramethylbenzidine, di-(aminophenyl)alkylen
 and

- 10 from amino compounds listed below, which do not carry two amino groups
 and are taken as derivatives with at least one additional amino group:
 aniline, 4-amino-2,3,5,6-tetrafluorobenzoic acid, 4-amino-3,5-diiodobenzoic
 acid, 4-amino-3-methylbenzoic acid, 4-amino-2-chlorobenzoic acid,
 4-aminosalicylic acid, 4-aminobenzoic acid, 4-aminophthalic acid, 1-(4-
 15 aminophenyl)ethanol, 4-aminobenzyl alcohol, 4-amino-3-methoxybenzoic
 acid, 4-aminophenyl ethyl carbinol, 4-amino-3-nitrobenzoic acid, 4-amino-3,5-
 dinitrobenzoic acid, 4-amino-3,5-dichlorobenzoic acid, 4-amino-3-
 hydroxybenzoic acid, 4-aminobenzyl alcohol hydrochloride, 4-aminobenzoic
 acid hydrochloride, pararosaniline base, 4-amino-5-chloro-2-methoxybenzoic
 20 acid, 4-(hexafluoro-2-hydroxyisopropyl)aniline, piperazine-p-amino benzoate,
 4-amino-3,5-dibromobenzoic acid, isonicotinic acid hydrazide p-amino-
 salicylate salt, 4-amino-3,5-diiodosalicylic acid, 4-amino-2-methoxybenzoic
 acid, 2-[2-(4-aminophenyl)-2-hydroxy-1-(hydroxymethyl)ethyl]isoindoline-1,3-
 dione, 4-amino-2-nitrobenzoic acid, ethyl 2-(4-aminophenyl)-3,3,3-trifluoro-2-
 25 hydroxypropanoate, ethyl 2-(4-amino-3-methylphenyl)-3,3,3-trifluoro-2-
 hydroxypropanoate, ethyl 2-(4-amino-3-methoxyphenyl)-3,3,3-trifluoro-2-
 hydroxypropanoate, 4-aminonaphthalene-1,8-dicarboxylic acid, 4-amino-3-
 chloro-5-methylbenzoic acid, 4-amino-2,6-dimethylbenzoic acid, 4-amino-3-
 fluorobenzoic acid, 4-amino-5-bromo-2-methoxybenzenecarboxylic acid,
 30 3,3'-tolidine-5-sulfonic acid,
 or their derivatives, again with the proviso that compounds listed which do not
 carry two amino groups are taken as derivatives with at least one additional
 amino group.

The diamine groups D are commercial available or accessible by known methods. The second amino group is accessible for example by substitution reaction.

D is further more preferably selected from the group of the following compounds:

5



wherein

L, L₁, L₂ and L₃ are independently from each other -CH₃, -COCH₃, -OCH₃, nitro, cyano, halogen, CH₂=CH-, CH₂=C(CH₃)-, CH₂=CH-(CO)O-, CH₂=CH-O-, -NR⁵R⁶, CH₂=C(CH₃)-(CO)O- or CH₂=C(CH₃)-O-,

5 T, T₁, T₂ and T₃ are independently from each other a substituted or unsubstituted straight-chain or branched C₁-C₂₀alkylene group, in which one or more -CH₂- group(s) may independently from each other be replaced by a non-aromatic, aromatic, unsubstituted or substituted carbocyclic or heterocyclic group, and/or a heteroatom and/or by a bridging group;

M represents H, C₁-C₆alkyl, CF₃,

10 "—" is a single bond,

q is an integer of 1 or 2; and

q₁, q₂ and q₃ are independently from each other an integer from 0 to 2; preferably 1 or 2;

m is an integer of 1 or 2;

m₁, m₂ and m₃ are independently from each other an integer from 0 to 2; preferably 1 or

15 2;

u₃, u₃' and u₃'' are independently from each other an integer from 0 to 2;

R⁵, R⁶ and Z⁴ are as described above; and wherein

D is at least once linked to at least one group S¹ in formula (I) via a single bond "—"; or via a side chain T, T₁, T₂ or T₃; or via group Z⁴;

20 with the proviso that










u₃ + q, or u₃ + m is ≤ 4;

u₃ + q₁ and/or u₃' + q₂ or/and u₃ + m₁, or/and u₃' + m₂, or/and u₃'' + q₃, or/and u₃'' + m₃ is ≤ 4;

q₁ + q₂, and m₁ + m₂; and q₁ + q₂ + q₃, and m₁ + m₂ + m₃ is ≥ 1.

25

Most preferred are diamine compounds according to the invention, wherein D is a selected from the group of the following compounds:



and

"—" denotes the linking(s) of D to S¹ in compound (I) and represents a single bond;
and

S⁰ represents a single bond or a spacer unit, which is a straight-chain or branched, substituted or unsubstituted C₁-C₂₄alkylen, preferably C₁-C₆alkylen, wherein one or more, preferably non-adjacent, -CH₂- group may be replaced by a linking group, preferably replaced by -O-, -O(CO)-, -(CO)O-, -NR₁CO-, -CONR₁-, wherein R₁ is hydrogen or C₁-C₆alkyl; most preferably S⁰ is a single bond;

M represents a H, C₁-C₂₄alkyl and CF₃;

L is -CH₃, -COCH₃, -OCH₃, nitro, cyano, halogen, CH₂=CH-, CH₂=C(CH₃)-, CH₂=CH-(CO)O-, CH₂=CH-O-, -NR⁵R⁶, CH₂=C(CH₃)-(CO)O- or CH₂=C(CH₃)-O-,


wherein:

R⁵, R⁶ each independently from each other represents a hydrogen atom or C₁-C₆alkyl;

u₃ is an integer from 0 to 2.

E preferably represents an phenylene, an oxygen atom or a -N(H)- group, more preferred E is oxygen or a -N(H)- group, and most preferred E is oxygen.

Preferably, S¹, S² each independently from each other represents a single bond or a spacer unit, which is a cyclic, straight-chain or branched, substituted or unsubstituted C₁-C₂₄alkylen, in which one or more, preferably non-adjacent, -CH₂- group may be replaced by a linking group, and/or a non-aromatic, aromatic, unsubstituted or substituted carbocyclic or heterocyclic group of formula (IV):



wherein:

C¹, C² each independently represents a non-aromatic, aromatic, optionally substituted carbocyclic or heterocyclic group, preferably connected to each other via the bridging groups Z¹ and Z² and/or Z^{1a}, preferably C¹ and C² are


connected at the opposite positions via the bridging groups Z^1 and Z^2 and/or Z^{1a} , so that groups S^1 and/or S^2 have a long molecular axis, and

Z^1, Z^2, Z^{1a} each independently represents a bridging group, preferably selected from $-\text{CH}(\text{OH})-$, $-\text{CH}_2-$, $-\text{O}-$, $-\text{CO}-$, $-\text{CH}_2(\text{CO})-$, $-\text{SO}-$, $-\text{CH}_2(\text{SO})-$, $-\text{SO}_2-$, $-\text{CH}_2(\text{SO}_2)-$, $-\text{COO}-$, $-\text{OCO}-$, $-\text{COCF}_2-$, $-\text{CF}_2\text{CO}-$, $-\text{S-CO}-$, $-\text{CO-S}-$, $-\text{SOO}-$, $-\text{OSO}-$, $-\text{SOS}-$, $-\text{CH}_2\text{-CH}_2-$, $-\text{OCH}_2-$, $-\text{CH}_2\text{O}-$, $-\text{CH=CH}-$, $-\text{C}\equiv\text{C}-$, $-\text{CH=CH-COO}-$, $-\text{OCO-CH=CH}-$, $-\text{CH=N}-$, $-\text{C}(\text{CH}_3)=\text{N}-$, $-\text{O-CO-O}-$, $-\text{N=N}-$ or a single bond; and

a_1, a_2, a_3 each independently represents an integer from 0 to 3, such that $a_1 + a_2 + a_3 \leq 6$, wherein preferably S^2 is linked to A via Z^1 ; preferably a_3 is 0 and $a_1 + a_2 \leq 4$.

More preferred S^1 represents a straight-chain or branched $\text{C}_1\text{-C}_{24}$ alkylen, wherein one or more $-\text{CH}_2-$ group may independently be replaced by a linking group or/and a group represented by the formula (IV), wherein:

C^1, C^2 are selected from a compound of group G^1 , wherein group G^1 is:



wherein:

"—" denotes the connecting bonds of C¹ and C² to the adjacent groups in formula (IV); and

5 L is -CH₃, -OCH₃, -COCH₃, nitro, cyano, halogen, CH₂=CH-, CH₂=C(CH₃)-, CH₂=CH-(CO)O-, CH₂=CH-O-, CH₂=C(CH₃)-(CO)O-, or CH₂=C(CH₃)-O-,

u₁ is an integer from 0 to 4; and

u₂ is an integer from 0 to 3; and

u₃ is an integer from 0 to 2; and

10

Z¹, Z², Z^{1a} each independently represents -O-, -CO-, -COO-, -OCO-, -COCF₂-, -CF₂CO-, -CH₂-CH₂-, -OCH₂-, -CH₂O-, -CH=CH-, -C≡C-, -CH=CH-COO-, -OCO-CH=CH- or a single bond; with the proviso that heteroatoms are not directly linked to each other, and

15

a₁, a₂, a₃ each independently represents an integer from 0 to 3, such that a₁ + a₂ + a₃ ≤ 6; preferably a₃ is 0 and a¹ + a² ≤ 4.

Most preferred S¹ represents a single bond or a spacer unit such as a straight-chain or branched C₁-C₁₄alkylen, wherein one or more, preferably non adjacent, -CH₂-
20 group may independently be replaced by a linking group and/or a group represented by formula (IV), wherein:

C¹, C² each independently represents a 1,4-phenylene, 2-methoxy-1,4-phenylene, 1,4-cyclohexylene or a 4,4'-biphenylene group; and

25

Z¹, Z², Z^{1a} each independently represents -COO-, -OCO-, -CH₂-CH₂-, -OCH₂-, -CH₂O-, -CH=CH-, -C≡C-, -CH=CH-COO-, -OCO-CH=CH- or a single bond; and

a₁, a₂, a₃ are independently 0 or 1, preferably a₃ is 0.

30

Especially most preferred S¹ represents a straight-chain C₁-C₁₂alkylen, wherein one or more -CH₂- groups may be replaced by -O-, -O(CO)-, -(CO)O-, -NR₁CO-, -CONR₁-, wherein R₁ is hydrogen or C₁-C₆alkyl or a group of formula (IV), wherein:

C¹, C² each independently represents 1,4-phenylene; and

5 Z¹, Z², Z^{1a} each independently represents -COO-, -OCO-, -CH₂-CH₂-, -OCH₂-,
 -CH₂O-, -CH=CH-, -C≡C-, -CH=CH-COO-, -OCO-CH=CH-, or a single bond;
 and

a₁, a₂, a₃ are independently 0 or 1, preferably a₃ is 0.

10 More preferred S² represents a spacer unit such as a straight-chain or branched
 C₁-C₂₄alkylen, wherein one or more -CH₂- groups is independently replaced by a
 group represented by the formula (IV), wherein:

C¹, C² are selected from group G¹, with the above given meaning; and

15 Z¹, Z², Z^{1a} each independently represents -O-, -CO-, -COO-, -OCO-, -COCF₂-,
 -CF₂CO-, -CH₂-CH₂-, -OCH₂-, -CH₂O-, -CH=CH-, -C≡C-, -CH=CH-COO-,
 -OCO-CH=CH- or a single bond; with the proviso that heteroatoms are not
 directly linked to each other, and

20 a₁, a₂, a₃ are each independently represents an integer from 0 to 3, such that
 a₁ + a₂ + a₃ ≤ 6, and preferably a₁ + a₂ ≤ 4 and a₃ is 0; and wherein
 preferably S² is linked to A via Z¹.


25 Most preferred S² represents a straight-chain or branched
 C₁-C₁₂alkylen, wherein one or more -CH₂- group is independently be replaced by a
 group represented by the formula (IV), and more most preferred S² represents a
 group of formula (IV), wherein

30 C¹, C² each independently represents a 1,4-phenylene which is unsubstituted or
 mono or poly-substituted by a halogen atom, and/or by an alkoxy,
 alkylcarbonyloxy or an alkyloxycarbonyl group, having from 1 to 10 carbon
 atoms, 1,4-cyclohexylene or a 4,4'-biphenylene group; and

Z^1, Z^2, Z^{1a} each independently represents $-\text{COO}-, -\text{OCO}-, -\text{CH}_2-\text{CH}_2-, -\text{OCH}_2-,$
 $-\text{CH}_2\text{O}-, -\text{CH}=\text{CH}-, -\text{C}\equiv\text{C}-, -\text{CH}=\text{CH}-\text{COO}-, -\text{OCO}-\text{CH}=\text{CH}-$ or a single bond;
 and

5 a_1, a_2, a_3 are independently 0 or 1, wherein preferably S^2 is linked to A via Z^1 .

Especially most preferred S^2 represents a group of formula (IVa)




10 wherein:

C^1 represents a non-aromatic, aromatic, unsubstituted or substituted carbocyclic
 or heterocyclic group, preferably selected from a compound of group G1, and

15 Z^1, Z^{1a} each independently from each other represent $-\text{COO}-, -\text{OCO}-,$
 $-\text{OCO}(\text{C}_1-\text{C}_8)\text{alkyl}, -\text{COOCH}_2(\text{C}_1-\text{C}_8)\text{alkyl}-, -\text{CH}_2-\text{CH}_2-, -\text{OCH}_2-, -\text{CH}_2\text{O}-, -\text{CH}=\text{CH}-,$
 $-\text{C}\equiv\text{C}-, -\text{CH}=\text{CH}-\text{COO}-, -\text{OCO}-\text{CH}=\text{CH}-$, or a single bond, or a straight-chain or
 branched, substituted or unsubstituted C_1-C_8 alkylen, wherein one or more $-\text{CH}_2-$ group
 may independently from each other be replaced by a linking group, preferably by $-\text{O}-$,
 as described above;

20 a_1, a_3 represents independently from each other 1, wherein preferably S^2 is linked to
 A via Z^1 .

Further, especially most preferred S^2 represents a group of formula (IVa)



25 wherein:

C^1 represents a 1,4-phenylene which is unsubstituted or mono or poly-substituted
 by a halogen atom, and/or by an alkoxy, alkylcarbonyloxy or an
 alkyloxycarbonyl group, having from 1 to 10 carbon atoms,

30 Z^1, Z^{1a} each independently from each other represent $-\text{COO}-, -\text{OCO}-,$
 $-\text{CH}_2-\text{CH}_2-, -\text{OCH}_2-, -\text{CH}_2\text{O}-, -\text{CH}=\text{CH}-, -\text{C}\equiv\text{C}-, -\text{CH}=\text{CH}-\text{COO}-,$
 $-\text{OCO}-\text{CH}=\text{CH}-$, or a single bond, or a straight-chain or branched, substituted
 or unsubstituted C_1-C_8 alkylen, wherein one or more $-\text{CH}_2-$ group may

independently from each other be replaced by a linking group as described above, preferably by -O-, -COO-, -OCO-,

5 a₁, a₃ represents idenpendently from each other 1, wherein preferably S² is linked to A via Z¹.

10 Another preferred embodiment of the present invention relates to a diamine compound (I), referring to any of the preceding definitions comprising these diamine compounds, wherein

15 A represents phenanthrylene, biphenylene, naphthylene, or phenylene, which is unsubstituted or mono- or poly-substituted by a halogen atom, hydroxy group and/or by a polar group, preferably nitro, cyano, carboxy; and/or by acryloyloxy, methacryloyloxy, vinyl, vinyloxy, allyl, allyloxy, and/or by a cyclic, straight-chain or branched C₁-C₁₂alkyl residue, which is unsubstituted, mono- or poly-substituted by fluorine and/or chlorine, wherein one or more -CH₂- group may independently be replaced by a linking group and or an aromatic or an alicyclic group,

and

20 B represents a straight-chain or branched C₁-C₁₂alkyl group, which is unsubstituted or substituted by di-(C₁-C₁₆alkyl)amino, C₁-C₆alkyloxy, nitro, cyano, fluorine and/or chlorine; and wherein one or more -CH₂- group may independently from each other be replaced by a linking group selected from -O-, -CO-, -CO-O-, -O-CO-, -NR¹-, -NR¹-CO-, -CO-NR¹- and -CH=CH-, wherein:


25 R¹ represents a hydrogen atom or C₁-C₆alkyl; with the proviso that oxygen atoms are not directly linked to each other; and wherein the C₁-C₁₂fluoralkyl group has terminal units selected from -CF₂H and -CF₃, preferably selected from

30 -CF₂H or -CF₃, -CF₂CF₃, -CF₂CHF₂, -(CF₂)₂CF₃, -(CF₂)₂CHF₂, -(CF₂)₃CHF₂, -(CF₂)₃CF₃, -CF(CF₃)₂ and -CF₂(CHF)CF₃,

Q represents an alicyclic group represents an unsubstituted alicyclic group, which is or substituted by

di-(C₁-C₁₆alkyl)amino, C₁-C₆alkyloxy, nitro, cyano, fluoro and/or chlorine; and wherein one or more -CH₂- group may independently from each other be replaced by a linking group;

5 D represents an optionally substituted aliphatic, aromatic or alicyclic diamine group having from 1 to 40 carbon atoms selected from formula (III),



wherein

k¹, k² are 0 or 1, and

t¹, t² are 0, and

10 R⁵, R⁶ are identical and represent a hydrogen atom, a methyl, an ethyl or an isopropyl group; and

C³, C⁴ independently from each other are selected from compound of a group G² as described above;

15 Z³ represents a group selected from -CH(OH)-, -CH(CH₃)-, -C(CH₃)₂-, -CO-, -COO-, -OCO-, -COCF₂-, -CF₂CO- or a single bond; and

Z⁴ has one of the meanings of Z³ or represents a substituted or unsubstituted straight-chain or branched C₁-C₂₀alkylene, in which one or more, preferably non-adjacent, -CH₂- group may independently from each other be replaced by cyclohexylen, phenylen, aromatic or non-aromatic N-heterocycle; or
20 by a heteroatom and/or by an oxygen atom; and/or one or more carbon-carbon single bond is replaced by a carbon-carbon double or a carbon-carbon triple bond;


a³, a⁴ each independently represents an integer from 0 to 2 such that a³ + a⁴ ≤ 3;

25 Sp¹, Sp², X¹, X² have the same meaning as described above;

E represents an phenylene, an oxygen atom or a -N(H)- group;

30 S¹ represents a single bond or a cyclic, straight-chain or branched, substituted or unsubstituted C₁-C₂₄alkylen, wherein one or more -CH₂- group may independently from each other be replaced by a linking group as described above;

S² represents a non-aromatic, aromatic, unsubstituted or substituted carbocyclic or heterocyclic group of formula (IV):



wherein:

5 C^1 , C^2 each independently represents a non-aromatic, aromatic, unsubstituted or substituted carbocyclic or heterocyclic group, and

Z^1 , Z^2 , Z^{1a} each independently represents a bridging group, and

10 a^1 , a^2 , a^3 each independently represents an integer from 0 to 3, such that $a^1 + a^2 + a^3 \leq 6$, preferably $a^1 + a^2 \leq 4$ and a^3 is 0; wherein the bridging groups Z^1 , Z^{1a} and Z^2 are as described above,

X, Y are hydrogen atoms, and

15

n is 1, 2 or 3, and n_1 is 1 or 2; preferably n_1 is 1.

with the proviso that if n is 2 or 3 each A, B, x_1 , D, E, S^1 and S^2 may be identical or different, and if n_1 is 2 each B, x_1 may be identical or different.

20

A more preferred embodiment of the present invention relates to diamine compounds (I), referring to any of the preceding definitions, and to alignment materials comprising these diamine compounds wherein

25

A represents a biphenylene, naphthylene or phenylene group, which is unsubstituted or mono- or poly-substituted by a halogen atom, a hydroxy group, and/or by acryloyloxy, and/or methacryloyloxy groups, and/or by straight-chain or branched alkyl, alkoxy, alkylcarbonyloxy, and/or alkyloxycarbonyl groups having from 1 to 20 carbon atoms,

30

B represents a straight-chain or branched C_1 - C_8 alkyl group, which is unsubstituted or substituted by di- $(C_1$ - C_{16} alkyl)amino, C_1 - C_6 alkyloxy, nitro, cyano, fluoro and/or chlorine; and wherein one or more $-CH_2-$ group may independently from each other be

replaced by a linking group selected from -O-, -CO-, -CO-O-, -O-CO-, -NR¹-, -NR¹-CO-, -CO-NR¹- and -CH=CH-, wherein:

R¹ represents a hydrogen atom or C₁-C₈alkyl;
with the proviso that oxygen atoms are not directly linked to each other; and

5 Q represents an alicyclic group represents an unsubstituted alicyclic group, which is or substituted by di-(C₁-C₁₆alkyl)amino, C₁-C₆alkyloxy, nitro, cyano, fluoro and/or chlorine; and wherein one or more -CH₂- group may independently from each other be replaced by a linking group;

10 D represents an optionally substituted aliphatic, aromatic or alicyclic diamine group having from 1 to 40 carbon atoms, represented by formula (III) and is most preferably selected from the following group of structures: substituted or unsubstituted o- phenylenediamine, p-phenylenediamine, m-phenylenediamine, aminophenylen-Z⁴-phenylenamino; or m-phenylenediamine with a substituted or unsubstituted straight-chain or
15 branched C₁-C₂₀alkylene group, in which one or more -CH₂- group may independently from each other be replaced by a non-aromatic, aromatic, unsubstituted or substituted carbocyclic or heterocyclic group, or a heteroatom and/or by a bridging group; wherein Z⁴ has the above given meaning;

20 benzidine, diaminofluorene, 3,4-diaminobenzoic acid, 3,4-diaminobenzyl alcohol dihydrochloride, 2,4-diaminobenzoic acid, L-(+)-threo-2-amino-1-(4-aminophenyl)-1,3-propanediol, p-aminobenzoic acid, [3,5-3h]-4-amino-2-methoxybenzoic acid, L-(+)-threo-2-(N,N-dimethylamino)-1-(4-aminophenyl)-1,3-propanediol, 2,7-diaminofluorene, 4,4'-diaminooctafluorobiphenyl, 3,3'-diaminobenzidine, 2,7-diamine-9-fluorenone, 3,5,3',5'-tetrabromo-biphenyl-4,4'-diamine, 2,2'-dichloro[1,1'-biphenyl]-4,4'-diamine, 3,9-diamine-1,11-dimethyl-5,7-dihydro-dibenzo(a,c)cyclohepten-6-one, dibenzo(1,2)dithiine-3,8-diamine, 3,3'-diaminobenzophenone, 3,3'-diaminediphenylmethane, 4,4-bis-(3-amino-4-hydroxyphenyl)-valeric acid,

30 2,2-bis(3-amino-4-hydroxyphenyl)hexafluoropropane, 2,2-bis(3-amino-4-methylphenyl)hexafluoropropane, tetrabromo methylenedianiline, 2,7-diamine-9-fluorenone, 2,2-bis(3-aminophenyl)hexafluoropropane, bis-(3-amino-4-chloro-phenyl)-methanone, bis-(3-amino-4-dimethylamino-phenyl)-methanone,

3-[3-amino-5-(trifluoromethyl)benzyl]-5-(trifluoromethyl)aniline,
 1,5-diaminonaphthalene, benzidine-3,3'-dicarboxylic acid,
 4,4'-diamino-1,1'-binaphthyl, 4,4'-diaminediphenyl-3,3'-diglycolic acid,
 dihydroethidium, o-dianisidine, 2,2'-dichloro-5,5'-dimethoxybenzidine,
 3-methoxybenzidine, 3,3'-dichlorobenzidine (diphenyl-d6),
 2,2'-bis(trifluoromethyl)benzidine, 3,3'-bis(trifluoromethyl)benzidine, 3,3'-
 dichlorobenzidine-d6, tetramethylbenzidine, di-(aminophenyl)alkylen

and

from amino compounds listed below, which do not carry two amino groups
 and are taken as derivatives with at least one additional amino group:
 aniline, 4-amino-2,3,5,6-tetrafluorobenzoic acid, 4-amino-3,5-diiodobenzoic
 acid, 4-amino-3-methylbenzoic acid, 4-amino-2-chlorobenzoic acid, 4-
 aminosalicylic acid, 4-aminobenzoic acid, 4-aminophthalic acid, 1-(4-
 aminophenyl)ethanol, 4-aminobenzyl alcohol, 4-amino-3-methoxybenzoic
 acid, 4-aminophenyl ethyl carbinol, 4-amino-3-nitrobenzoic acid, 4-amino-3,5-
 dinitrobenzoic acid, 4-amino-3,5-dichlorobenzoic acid, 4-amino-3-
 hydroxybenzoic acid, 4-aminobenzyl alcohol hydrochloride, 4-aminobenzoic
 acid hydrochloride, pararosaniline base, 4-amino-5-chloro-2-methoxybenzoic
 acid, 4-(hexafluoro-2-hydroxyisopropyl)aniline, piperazine-p-amino benzoate,
 4-amino-3,5-dibromobenzoic acid, isonicotinic acid hydrazide p-amino-
 salicylate salt, 4-amino-3,5-diiodosalicylic acid, 4-amino-2-methoxybenzoic
 acid, 2-[2-(4-aminophenyl)-2-hydroxy-1-(hydroxymethyl)ethyl]isoindoline-1,3-
 dione, 4-amino-2-nitrobenzoic acid, ethyl 2-(4-aminophenyl)-3,3,3-trifluoro-2-
 hydroxypropanoate, ethyl 2-(4-amino-3-methylphenyl)-3,3,3-trifluoro-2-
 hydroxypropanoate, ethyl 2-(4-amino-3-methoxyphenyl)-3,3,3-trifluoro-2-
 hydroxypropanoate, 4-aminonaphthalene-1,8-dicarboxylic acid, 4-amino-3-
 chloro-5-methylbenzoic acid, 4-amino-2,6-dimethylbenzoic acid, 4-amino-3-
 fluorobenzoic acid, 4-amino-5-bromo-2-methoxybenzenecarboxylic acid,
 3,3'-tolidine-5-sulfonic acid,
 or their derivatives, again with the proviso that compounds listed which do not
 carry two amino groups are taken as derivatives with at least one additional
 amino group, and

E represents an oxygen atom or a -N(H)- group;

S¹ represents a spacer unit such a straight-chain or branched C₁-C₁₄alkylene groups, wherein one or more -CH₂- groups may independently be replaced by a group represented by formula (IV) as defined above, wherein:

5

C¹, C² each independently represents a 1,4-phenylene, 2-methoxy-1,4-phenylene, 1,4-cyclohexylene or a 4,4'-biphenylene group; and

10

Z¹, Z², Z^{1a} each independently represents -COO-, -OCO-, -CH₂-CH₂-, -OCH₂-, -CH₂O-, -CH=CH-, -C≡C-, -CH=CH-COO-, -OCO-CH=CH- or a single bond; and

a¹, a², a³ are independently 0 or 1; preferably a³ is 0,

15

S² represents a spacer unit of formula (IV) as defined above, wherein preferably S² is linked to A via Z¹; and wherein C¹, C² each independently represents a 1,4-phenylene which is unsubstituted or mono or poly-substituted by a halogen atom, and/or by an alkoxy, alkylcarbonyloxy or an alkyloxycarbonyl group, having from 1 to 10 carbon atoms, 1,4-cyclohexylene or a 4,4'-biphenylene group; and

20

Z¹, Z², Z^{1a} each independently represents -O-, -COO-, -OCO-, -CH₂-CH₂-, -OCH₂-, -CH₂O-, -CH=CH-, -C≡C-, -CH=CH-COO-, -OCO-CH=CH- or a single bond; and

25

a¹, a², a³ are independently 0 or 1; preferably a³ is 0,

n is 1 or 2, and n₁ is 1, or 2, preferably 1;

with the proviso that if n is 2 or 3 each A, B, x₁, D, E, S¹, S², X, Y may be identical or different; and if n₁ is 2 each B, x₁ is identical or different.

30

Another preferred embodiment of the present invention relates to a diamine compound represented by one of the general formula (I), referring to any of the preceding

definitions, and preferably to alignment materials comprising this diamine compound wherein

A represents 1,4-phenylene, which is unsubstituted or mono- or poly-substituted by a halogen atom, and/or by acryloyloxy or methacryloyloxy, and/or by an alkoxy, alkylcarbonyloxy or an alkyloxycarbonyl group, having from 1 to 10 carbon atoms,

B represents a straight-chain or branched C₁-C₈alkyl group, which is unsubstituted or substituted by

di-(C₁-C₁₆alkyl)amino, C₁-C₆alkyloxy, nitro, cyano fluorine and/or chlorine; and

wherein one or more -CH₂- group may independently from each other be replaced by a linking group selected from -O-, -CO-, -CO-O-, -O-CO-, -NR¹-, -NR¹-CO-, -CO-NR¹- and -CH=CH-, wherein:

R¹ represents a hydrogen atom or C₁-C₆alkyl;

with the proviso that oxygen atoms are not directly linked to each other;

and

wherein the C₁-C₁₂fluoralkyl group has terminal units selected from -CF₂H and -CF₃, preferably selected from

-CF₂H or -CF₃, -CF₂CF₃, -CF₂CHF₂, -(CF₂)₂CF₃, -(CF₂)₂CHF₂, -(CF₂)₃CHF₂, -(CF₂)₃CF₃, -CF(CF₃)₂ and -CF₂(CHF)CF₃,

Q represents an alicyclic group represents an unsubstituted alicyclic group, which is or substituted by

di-(C₁-C₁₆alkyl)amino, C₁-C₆alkyloxy, nitro, cyano, fluoro and/or chlorine; and

wherein one or more -CH₂- group may independently from each other be replaced by a linking group;

D represents an unsubstituted o-phenylenediamine, p-phenylenediamine, m-phenylenediamine, biphenyldiamine, aminophenylene-Z⁴-phenylenamino, naphthylenediamine, or a m-phenylenediamine with a substituted or unsubstituted straight-chain or branched C₁-C₂₀alkylene group, in which one or more -CH₂- group may independently from each other be replaced by a non-aromatic, aromatic, unsubstituted or substituted carbocyclic or heterocyclic group, or a heteroatom and/or by a bridging group;

wherein

Z⁴ is as defined above;

E represents an oxygen atom;

S¹ represents a single bond or a straight-chain C₁-C₈alkylene group, wherein one -CH₂- group may be replaced by -O-, -OCO-, -COO-, -NR₁CO-, -CONR₁-, wherein R₁ is hydrogen or C₁-C₆alkyl,

S² is replaced by a group of formula (IVa) as described above,

5 wherein:

C¹ represents a 1,4-phenylene which is unsubstituted or mono or poly-substituted by a halogen atom, and/or by an alkoxy, alkylcarbonyloxy or an alkyloxycarbonyl group, having from 1 to 10 carbon atoms,

10 Z¹, Z^{1a} represents -O-, -COO-, -OCO-, -COO(C₁-C₆)alkylen-, -OCO(C₁-C₆)alkylen-, -CH₂-CH₂-, -OCH₂-, -CH₂O-, -CH=CH-, -C≡C-, -CH=CH-COO-, -OCO-CH=CH-, or a single bond;

X, Y are hydrogen atoms, and

n is 1 or 2, and n₁ is 1 or 2 and preferably 1;

15 with the proviso that if n or n₁ is 2 each A, B, x₁, D, E, S¹ and S² may be identical or different; and if n₁ is 2 each B, x₁ is identical or different.

Most preferred embodiment of the present invention relates to diamine compounds represented by one of the general formula (I), referring to any of the preceding definitions, and to alignment materials comprising these diamine compounds wherein

20 S² is replaced by a group of formula (IV), wherein:

C¹ represents 1,4-phenylene; and


Z¹, Z^{1a} represent each independently from each other -O-, -COO-, -OCO-, -CH₂-CH₂-, -OCH₂-, -CH₂O-, -CH=CH-, -C≡C-, -CH=CH-COO-, -OCO-CH=CH-, or a single bond;

25 a₁ represents 1, and a₃ represents 0


S² is linked to A via Z¹.

Especially most preferred embodiment of the present invention relates to Diamine compounds of formulae (VI), (VII), (VIII), (IX), (IXa), (X), (XI), (XIa), (XIb) and (Xlc)


30



(VI)




(VII)







(VIII)

5




(IX)






(Xla)



(Xlb)





wherein

A, B, Q, n1, D, E, M, S², S¹, S⁰, X and Y, R⁵, R⁶ and Z⁴ have the above given meanings and preferences as given above; preferably n1 is 1;

L is -CH₃, -OCH₃, -COCH₃, nitro, cyano, halogen, CH₂=CH-, CH₂=C(CH₃)-, CH₂=CH-(CO)O-, CH₂=CH-O-, CH₂=C(CH₃)-(CO)O-, or CH₂=C(CH₃)-O-,

u3 is an integer from 0 to 2.

10 Further, especially most preferred embodiment of the present invention relates to diamine compounds of formulae (XII) or (XIIa)



wherein B, Q, n_1 , D, E, S^1 , X, Y, Z^1 , Z^{1a} , L, a_3 , u_1 and u_2 , have the above given meanings and preferences

and wherein Q is most preferably cyclohexylen and Z^1 , Z^{1a} is preferably $-\text{COO}-$, $-\text{OCO}$, $-\text{O}-$, or a single covalent bond and a_3 is 1.

5


Preferred diamine compounds of formula (XII) are compounds, wherein Z^1 is $-\text{COO}-$, $-\text{OCO}-$, $-\text{OCO}(\text{C}_1\text{-C}_6)\text{alkylen}$ or $-\text{COO}(\text{C}_1\text{-C}_6)\text{alkylen}$, or a single bond, or a straight-chain or branched, substituted or unsubstituted $\text{C}_1\text{-C}_8\text{alkylen}$, wherein one or more $-\text{CH}_2-$ group may independently from each other be replaced independently from each other by a linking group, preferably by $-\text{O}-$.





10





Further preferred are diamine compounds of formulae (XII) or (XIIa), wherein Q is an alicyclic group with 3 to 10 carbon atoms, more preferably, wherein Q is cyclohexyl.


15

Especially very most preferred diamine is













or



5



wherein B, n¹, Q, S¹, S⁰ has the above given meanings and preferences;

especially most preferred S^1 represents a branched-chain or straight-chain C_1 - C_{12} alkylen, wherein one or more $-CH_2-$ group may be replaced by $-O-$, $-O(CO)-$, $-(CO)O-$, $-NR_1CO-$, $-CONR_1-$, wherein R_1 is hydrogen or C_1 - C_6 alkyl or a group of formula (IV), wherein:

5

C^1 , C^2 each independently represents 1,4-phenylene; and

Z^1 , Z^2 , Z^{1a} each independently represents $-COO-$, $-OCO-$, $-CH_2-CH_2-$, $-OCH_2-$, $-CH_2O-$, $-CH=CH-$, $-C\equiv C-$, $-CH=CH-COO-$, $-OCO-CH=CH-$, or a single bond;
and

10

a_1 , a_2 , a_3 are independently 0 or 1, preferably a_3 is 0;

B represents a straight-chain or branched C_1 - C_8 alkyl group, which is unsubstituted or substituted by

di- $(C_1$ - C_{16} alkyl)amino, C_1 - C_6 alkyloxy, nitro, cyano, fluoro and/or chlorine; and

15

wherein one or more $-CH_2-$ group may independently be replaced by a linking group selected from $-O-$, $-CO-$, $-CO-O-$, $-O-CO-$, $-NR^1-$, $-NR^1-CO-$, $-CO-NR^1-$ and $-CH=CH-$, wherein:

R^1 represents a hydrogen atom or C_1 - C_6 alkyl;

with the proviso that oxygen atoms are not directly linked to each other; more

20

preferred **B** represents a straight-chain or branched C_1 - C_8 alkyl group which is unsubstituted or substituted by fluoro, especially at the end of the alkyl chain, wherein one or more $-CH_2-$ group may independently be replaced by a linking group selected from $-O-$, $-CO-$, $-CO-O-$, $-O-CO-$ and $-CH=CH-$,

Q has the above given meanings and preferences; and is most preferably substituted or unsubstituted cyclohexylen.

25

A further preferred embodiment of the present invention relates to diamine (I) for accessing good applicatory performance such as thermal stability, printability or coatability, or ACM, VHR or RDC.

30

The present invention also relates to the use of diamine (I) for the preparation of polymers according to the invention for orientation layers for liquid crystals, wherein the polymers have ACM values after 600 hours of ≤ 0.15 , more preferably ≤ 0.1 and most preferably ≤ 0.08 .

VHR, ACM and RDC are commonly known values in the technical field of liquid crystal displays and will be described as following:

VHR:

- 5 In the case of liquid crystal displays of thin-film transistor type a certain amount of charge is applied over the course of a very short period of time to the electrodes of a pixel and must not subsequently drain away by means of the resistance of the liquid crystal. The ability to hold that charge and thus to hold the voltage drop over the liquid crystal is quantified by what is known as the "voltage holding ratio" (VHR). It is the ratio
10 of the RMS-voltage (root mean square voltage) at a pixel within one frame period and the initial value of the voltage applied.

- ACM (AlternativeCurrentMemory): An AC (AlternativeCurrent) voltage of 7 Volts (1kHz) is applied to the cell for 700 hours. The pre-tilt angle of the cell is measured
15 before and after the application of the AC stress. The ACM performance is expressed in terms of a pretilt angle difference, $\Delta\theta$.

- RDC (ResidualDirectCurrent): An adjustable DC (DirectCurrent)-component of $V=2V_{DC}$ is added to the symmetric square wave signal of $V=2.8V(30Hz)$, the
20 fluctuations of light transmitted by the test cell can be eliminated or at least minimized by adequate selection of the external DC component. The external DC-voltage for which the flicker is eliminated or minimized by compensation of the internal residual DC-voltage is taken to be equivalent to the internal residual DC-voltage.

- 25 Preferred are non-ionic surfactants not having any negative impact on Voltage Holding Ratio (VHR), Residual DC (RDC) or AC Memory (ACM) are non-ionic surfactants.

- Another preferred embodiment of the present invention relates to diamine compounds represented by the general formula (I), which may be used in the subsequent
30 manufacturing processes as such or in combination with one or more additional other diamines, preferably those of formula (L) as given below.

The diamine (L) represents an optionally substituted aliphatic, aromatic or alicyclic diamino group having from 1 to 40 carbon atoms and preferably made from or selected

from the following group of structures: aniline, p-phenylenediamine, m-phenylenediamine, benzidine, diaminofluorene, or their derivatives, with the proviso that compounds listed which do not carry two amino groups are taken as derivatives with at least one additional amino group, and more preferably made from or selected from the following commercially available amino compounds (example of suppliers: Aldrich, ABCR, ACROS, Fluka) which can also be used as comonomers:

- 4-amino-2,3,5,6-tetrafluorobenzoic acid
- 4-amino-3,5-diiodobenzoic acid, 3,4-diaminobenzoic acid
- 10 4-amino-3-methylbenzoic acid,
- 4-amino-2-chlorobenzoic acid
- 4-aminosalicylic acid
- 4-aminobenzoic acid
- 4-aminophthalic acid
- 15 1-(4-aminophenyl)ethanol
- 4-aminobenzyl alcohol
- 4-amino-3-methoxybenzoic acid
- 4-aminophenyl ethyl carbinol
- 4-amino-3-nitrobenzoic acid
- 20 4-amino-3,5-dinitrobenzoic acid
- 4-amino-3,5-dichlorobenzoic acid
- 4-amino-3-hydroxybenzoic acid
- 4-aminobenzyl alcohol hydrochloride
- 4-aminobenzoic acid hydrochloride
- 25 pararosaniline base
- 4-amino-5-chloro-2-methoxybenzoic acid
- 4-(hexafluoro-2-hydroxyisopropyl)aniline
- piperazine-p-amino benzoate
- 4-amino-3,5-dibromobenzoic acid
- 30 isonicotinic acid hydrazide p-aminosalicylate salt
- 4-amino-3,5-diiodosalicylic acid
- 4-amino-2-methoxybenzoic acid
- 2-[2-(4-aminophenyl)-2-hydroxy-1-(hydroxymethyl)ethyl]isoindoline-1,3-dione
- 4-amino-2-nitrobenzoic acid

- 2,4-diaminobenzoic acid
p-aminobenzoic acid,
[3,5-3h]-4-amino-2-methoxybenzoic acid
L-(+)-threo-2-amino-1-(4-aminophenyl)-1,3-propanediol
5 L-(+)-threo-2-(N,N-dimethylamino)-1-(4-aminophenyl)-1,3-propanediol
ethyl 2-(4-aminophenyl)-3,3,3-trifluoro-2-hydroxypropanoate
ethyl 2-(4-amino-3-methylphenyl)-3,3,3-trifluoro-2-hydroxypropanoate
ethyl 2-(4-amino-3-methoxyphenyl)-3,3,3-trifluoro-2-hydroxypropanoate
3,4-diaminobenzyl alcohol dihydrochloride
10 4-aminonaphthalene-1,8-dicarboxylic acid
4-amino-3-chloro-5-methylbenzoic acid
4-amino-2,6-dimethylbenzoic acid
4-amino-3-fluorobenzoic acid
4-amino-5-bromo-2-methoxybenzenecarboxylic acid
15 2,7-diaminofluorene
4,4'-diaminooctafluorobiphenyl
3,3'-diaminobenzidine
3,3',5,5'-tetramethylbenzidine
3,3'-dimethoxybenzidine
20 o-tolidine
3,3'-dinitrobenzidine
2-nitrobenzidine
3,3'-dihydroxybenzidine
o-tolidine sulfone
25 benzidine,
3,3'-dichlorobenzidine
2,2',5,5'-tetrachlorobenzidine,
benzidine-3,3'-dicarboxylic acid
4,4'-diamino-1,1'-binaphthyl
30 4,4'-diaminodiphenyl-3,3'-diglycolic acid
dihydroethidium
o-dianisidine
2,2'-dichloro-5,5'-dimethoxybenzidine
3-methoxybenzidine

- 3,3'-dichlorobenzidine (diphenyl-d6),
 2,7-diamino-9-fluorenone
 3,5,3',5'-tetrabromo-biphenyl-4,4'-diamine
 2,2'-bis(trifluoromethyl)benzidine
 5 2,2'-dichloro[1,1'-biphenyl]-4,4'-diamine
 3,9-diamino-1,11-dimethyl-5,7-dihydro-dibenzo(a,c)cyclohepten-6-one
 3,3'-bis(trifluoromethyl)benzidine
 dibenzo(1,2)dithiine-3,8-diamine
 3,3'-tolidine-5-sulfonic acid
 10 3,3'-dichlorobenzidine-d6
 tetramethylbenzidine
 3,3'-diaminobenzophenone, 3,3'-diaminodiphenylmethane,
 4,4-bis-(3-amino-4-hydroxyphenyl)-valeric acid
 2,2-bis(3-amino-4-hydroxyphenyl)hexafluoropropane
 15 2,2-bis(3-amino-4-methylphenyl)hexafluoropropane
 tetrabromo methylenedianiline
 2,7-diamino-9-fluorenone
 2,2-bis(3-aminophenyl)hexafluoropropane
 bis-(3-amino-4-chloro-phenyl)-methanone
 20 bis-(3-amino-4-dimethylamino-phenyl)-methanone
 3-[3-amino-5-(trifluoromethyl)benzyl]-5-(trifluoromethyl)aniline
 1,5-diaminonaphthalene

- or their derivatives, again with the proviso that compounds listed which do not carry
 25 two amino groups are taken as derivatives with at least one additional amino group.

Preferred examples of additional other diamines (L) are:

- ethylenediamine, 1,3-propylenediamine, 1,4-butylenediamine, 1,5-pentylenediamine,
 1,6-hexylenediamine, 1,7-heptylenediamine, 1,8-oxylenediamine,
 30 1,9-nonylenediamine, 1,10-decylenediamine, 1,11-undecylenediamine,
 1,12-dodecylenediamine, α,α' -diamino-m-xylene, α,α' -diamino-p-xylene, (5-amino-
 2,2,4-trimethylcyclopentyl)methylamine, 1,2-diaminocyclohexane,
 4,4'-diaminodicyclohexylmethane, 1,3-bis(methylamino)cyclohexane,
 4,9-dioxadodecane-1,12-diamine, 3,5-diaminobenzoic acid methyl ester,

- 3,5-diaminobenzoic acid hexyl ester, 3,5-diaminobenzoic acid dodecyl ester,
 3,5-diaminobenzoic acid isopropyl ester, 4,4'-methylenedianiline, 4,4'-ethylenedianiline,
 4,4'-diamino-3,3'-dimethyldiphenylmethane, 3,3',5,5'-tetramethylbenzidine,
 4,4'-diaminodiphenyl sulfone, 4,4'-diaminodiphenyl ether,
 5 1,5-diaminonaphthalene, 3,3'-dimethyl-4,4'-diaminobiphenyl,
 3,4'-diaminodiphenyl ether, 3,3'-diaminobenzophenone, 4,4'-diaminobenzophenone,
 4,4'-diamino-2,2'-dimethylbibenzyl, bis[4-(4-aminophenoxy)phenyl] sulfone,
 1,4-bis(4-aminophenoxy)benzene, 1,3-bis(4-aminophenoxy)benzene,
 1,3-bis(3-aminophenoxy)benzene, 2,7-diaminofluorene,
 10 9,9-bis(4-aminophenyl)fluorene, 4,4'-methylenebis(2-chloroaniline),
 4,4'-bis(4-aminophenoxy)biphenyl, 2,2',5,5'-tetrachloro-4,4'-diaminobiphenyl,
 2,2'-dichloro-4,4'-diamino-5,5'-dimethoxybiphenyl, 3,3'-dimethoxy-4,4'-diaminobiphenyl,
 4,4'-(1,4-phenyleneisopropylidene)bisaniiline,
 4,4'-(1,3-phenyleneisopropylidene)bisaniiline,
 15 2,2-bis[4-(4-aminophenoxy)phenyl]propane,
 2,2-bis[3-(4-aminophenoxy)phenyl]hexafluoropropane,
 2,2-bis[3-amino-4-methylphenyl]hexafluoropropane,
 2,2-bis(4-aminophenyl)hexafluoropropane,
 2,2'-bis[4-(4-amino-2-trifluoromethylphenoxy)phenyl]hexafluoropropane,
 20 4,4'-diamino-2,2'-bis(trifluoromethyl)biphenyl, and
 4,4'-bis[(4-amino-2-trifluoromethyl)phenoxy]-2,3,5,6,2',3',5',6'-octafluorobiphenyl;

as well as diamines (L) disclosed in US 6,340,506, WO 00/59966 and WO 01/53384,
 all of which are explicitly incorporated herein by reference;

25

The diamine compounds (L) according to the present invention may be prepared using
 methods that are known to a person skilled in the art.

In addition, preferred diamines (L) are the commercially available ones listed below:

30

Polymers

Poly(3,3',4,4'-benzophenonetetracarboxylic dianhydride-co-4,4'-oxydianiline/1,3-
 phenylenediamine), amic acid solution

Poly(3,3',4,4'-benzophenonetetracarboxylic dianhydride-co-4,4'-oxydianiline/1,3-
 phenylenediamine), amic acid solution

Poly(pyromellitic dianhydride-co-4,4'-oxydianiline), amic acid solution

Aromatic diamine

- 2,7-diaminofluorene
- 5 1,5-diaminoanthraquinone
- 2,6-diaminoanthraquinone
- pararosaniline hydrochloride
- 3,6-acridinediamine
- 4,4'-diaminooctafluorobiphenyl
- 10 2,2'-dithiodianiline
- 3,3',5,5'-tetramethylbenzidine
- 3,3'-diaminodiphenyl sulfone
- 4,4'-diamino-2,2'-dimethylbibenzyl
- 4,4'-diaminodiphenyl ether
- 15 4,4'-dithiodianiline
- 4,4'-diaminodiphenyl sulfone
- 4,4'-diaminodiphenylmethane
- 4,4'-ethylenedianiline
- 3,3'-dimethoxybenzidine
- 20 2,2'-dithiobis(1-naphthylamine)
- 3,7-diamino-2-methoxyfluorene
- 3,6-diamino-10-methylacridinium chloride
- propidium iodide
- o-dianisidine dihydrochloride
- 25 2,7-diaminofluorene dihydrochloride
- pararosaniline acetate
- 3,6-diamino-10-methylacridinium chloride hydrochloride
- proflavine dihydrochloride
- o-tolidine dihydrochloride
- 30 3,3',5,5'-tetramethylbenzidine dihydrochloride
- 3,3'-diaminobenzidine tetrahydrochloride
- 4,4'-diaminostilbene dihydrochloride
- 4,4'-diaminodiphenylamine sulfate
- proflavine hemisulfate
- 35 2,2'-ethylenedianiline diphosphate
- 1,5-diamino-4,8-dihydroxyanthraquinone
- o-tolidine

- 3,3'-diaminobenzophenone
3,3'-diaminodiphenylmethane
3,4'-diaminodiphenylmethane
2,2-bis[4-(4-aminophenoxy)phenyl]hexafluoropropane
5 4,4'-diamino-1,1'-dianthramide
3,3'-dinitrobenzidine
4,4'-diamino-5,5'-dimethyl-2,2'-biphenyldisulfonic acid
4,4'-diaminostilbene-2,2'-disulfonic acid
3-amino-4-hydroxyphenyl sulfone
10 4,4-bis-(3-amino-4-hydroxyphenyl)-valeric acid
2,2'-diamino-4,4'-difluorobibenzyl
2-amino-4-chlorophenyl disulfide
3,3'-(decamethylenedioxy)dianiline
3,3'-(pentamethylenedioxy)dianiline
15 4-(p-aminoanilino)-3-sulfoaniline
4-[3-(4-aminophenoxy)propoxy]aniline
2-nitrobenzidine
benzidine-3-sulfonic acid
4,4'-diaminodiphenyl sulfide
20 4,4'-diaminobenzanilide
n,n'-bis(3-aminophenylsulfonyl)ethylenediamine
2,2'-biphenyldiamine
3,4'-diaminodiphenyl ether
proflavine hemisulphate
25 phenosafranin
4,4'-diaminobenzophenone
2,2-bis(4-aminophenyl)hexafluoropropane
2,2-bis(3-amino-4-hydroxyphenyl)hexafluoropropane
2,2-bis(3-amino-4-methylphenyl)hexafluoropropane
30 3,3'-dihydroxybenzidine
3,3'-diamino-4,4'-dihydroxybiphenyl
4,4'-bis(4-aminophenoxy)biphenyl
2,2-bis[4-(4-aminophenoxy)phenyl]propane
1,4-bis(4-aminophenoxy)benzene
35 1,3-bis(4-aminophenoxy)benzene
bis[4-(4-aminophenoxy)phenyl]sulfone
9,9-bis(4-aminophenyl)fluorene

- o-tolidine sulfone
benzidine
3,3'-dichlorobenzidine dihydrochloride
benzidine dihydrochloride
- 5 3,6-thioxanthenediamine-10,10-dioxide
4,4'-diamino-2,2'-biphenyldisulfonic acid
4,4'-azodianiline
2,5-bis-(4-aminophenyl)-(1,3,4)oxadiazole
3,3'-dimethylnaphthidine
- 10 benzidine sulfate
1,3-bis(3-aminophenoxy)benzene
3,3'-dichlorobenzidine
2,2',5,5'-tetrachlorobenzidine
4,4'-diamino-1,1'-binaphthyl
- 15 diamine bordeaux
benzoflavin
chrysaniline
2,2'-thiobis(5-aminobenzenesulfonic acid)
4,4'-methylene-bis(2-chloroaniline)
- 20 tetrabromo methylenedianiline
4,4'-diamino-3,3'-dinitrodiphenyl ether
benzidine pyrophosphate
3,6-diaminothioxanthene-10-dioxide, dihyd
4,4''-diamino-p-terphenyl
- 25 1,8-diamino-4,5-dihydroxyanthraquinone
bis(p-aminophenoxy)dimethylsilane
bis[4-(3-aminophenoxy)phenyl]sulfone
4,4'-methylenedi-2,6-xylylidine
2-aminobenzaldehyde-ethylene-diimine
- 30 3-methylbenzidine dihydrochloride
3,3'-diethylbenzidine dihydrochloride
3,6-diaminoacridine hydrochloride
4,4'-diamino-5,5'-dimethyl-2,2'-biphenyl disulfonic acid disodium salt
4,4'-methylenebis(3-chloro-2,6-diethylaniline)
- 35 4,4'-methylene-bis-(2,6-diethylaniline)
4,4'-methylenebis-(2,6-diisopropylaniline)
toluylenediamine

- 3,8-diamino-6-phenylphenanthridine
 thionin perchlorate
 dihydroethidium
 thionin
- 5 4,4-diamino benzene sulfonyl anilide
 o-dianisidine hcl
 2,2'-dichloro-5,5'-dimethoxybenzidine
 3-methoxybenzidine
 2,2'-(hexamethylenedioxy)dianiline
- 10 2,2'-(pentamethylenedioxy)dianiline
 2,2'-(ethylenedioxy)dianiline
 4-[4-(4-aminophenoxy)butoxy]aniline
 2,2'-diamino-4'-methoxy-4-methylbenzanilide
 5,5'-dimethyl-2,2'-dinitrobenzidine
- 15 n,n'-bis(2-aminophenyl)-1,3-propanediamine
 3,4'-diaminochalcone
 2,3',4,5',6-pentaphenyl-3,4'-biphenyldiamine
 2-([1-(4-(1-[(2-aminophenyl)thio]-2-nitroethyl)phenyl)-2-nitroethyl]thio)anilin
 2-((2-[(2-aminophenyl)thio]ethyl)thio)aniline
- 20 2-((4-[(2-aminophenyl)thio]but-2-enyl)thio)aniline
 4,4'-diamino-3,3'-dimethyldiphenyl methane
 2,2'-diamino-bibenzyl
 trimethylene bis(4-aminobenzoate)
 fluoresceinamine
- 25 benzidines mixture
 3-nitro-4,4'-methylenedianiline
 4,4-diamino-2,2'-dichlorodiphenyl disulfide
 1,6-diaminopyrene
 1,8-diaminopyrene
- 30 3,6-diaminocarbazole
 4,4'(5')-diamino-[2,4]-dibenzo-18-crown-6,dihydrochloride
 4,4'-diaminostilbene-2,2'-disulfonic acid, disodium salt
 (r)-(+)-2,2'-diamino-1,1'-binaphthyl
 proflavine hemisulfate dihydrate
- 35 3,6-diaminoacridine hemisulfate hemihydrate
 dimidium bromide monohydrate
 o-tolidine dihydrochloride hydrate

- 3,3',5,5'-tetramethylbenzidine dihydrochloride hydrate
 3,3'-diaminobenzidine tetrahydrochloride dihydrate
 3,6-[bis(4-amino-3-(sodiumsulphonato)phenylamino)]-2,5-dichloro 4-benzoquinone
 2,2'-dimethylbenzidine hydrochloride
 5 2,2'-(phenylmethylenebis)bis(4-methylaniline)
 3,4'-diaminobiphenyl
 2,7-diamino-9-fluorenone
 n,n'-bis(2-aminophenyl)oxamide
 2-[2-(2-aminophenyl)diaz-1-enyl]aniline
 10 3,5,3',5'-tetrabromo-biphenyl-4,4'-diamine
 n,n'-bis(4-aminophenyl)-1,3-bis(aminomethyl)benzene dihydrochloride
 4',4''(5'')-diaminodibenzo-15-crown-5
 2,2'-bis(trifluoromethyl)benzidine
 bis(4-amino-2,3-dichlorophenyl)methane
 15 alpha,alpha'-bis(4-aminophenyl)-1,4-diisopropylbenzene
 2,2-bis(3-aminophenyl)hexafluoropropane
 3,10-diamino-6,13-dichlorobenzo[5,6][1,4]oxazino[2,3-b]phenoxazine-4,11-dis ulfo
 n1-(2-amino-4-methylphenyl)-2-aminobenzamide
 n1-(2-amino-4-chlorophenyl)-2-aminobenzamide
 20 2,2'-dichloro[1,1'-biphenyl]-4,4'-diamine
 4,4'(5')-diaminodibenzo-15-crown-5 dihydrochloride
 rcl s19,413-1
 bis-(4-amino-3-nitro-phenyl)-methanone
 bis-(3-amino-4-chloro-phenyl)-methanone
 25 bis-(3-amino-4-dimethylamino-phenyl)-methanone
 n,n'-bis-(4-amino-2-chloro-phenyl)-isophthalamide
 n,n'-bis-(4-amino-2-chloro-phenyl)-terephthalamide
 3,9-diamino-1,11-dimethyl-5,7-dihydro-dibenzo(a,c)cyclohepten-6-one
 2-aminobenzaldehyde n-[(z)-(2-aminophenyl)methylidene]hydrazone
 30 3,3'-bis(trifluoromethyl)benzidine
 dicarboxidine 2 hcl
 4,4'-(1,3-phenylenediisopropylidene)bisaniline
 1,4-phenylenebis[[4-(4-aminophenoxy)phenyl]methanone]
 2-((5-[(2-aminophenyl)thio]-3,4-dinitro-2-thienyl)thio)aniline
 35 n'1-(2-aminobenzoyl)-2-aminobenzene-1-carbohydrazide
 2-[4-(5-amino-1h-benzimidazol-2-yl)phenyl]-1h-benzimidazol-5-amine
 4-[4-(4-aminophenoxy)-2,3,5,6-tetrafluorophenoxy]aniline

- 3,3'-dinitro-4,4'-diaminodiphenyl sulfone
 3,3',4,4'-tetraaminodiphenylsulfone
 4-[1-(4-aminophenyl)-1-methylethyl]aniline
 3,3-diamino diphenyl urea
 5 bis(4-aminophenyl)acetylene
 dibenzo(1,2)dithiine-3,8-diamine
 ethidium homodimer-2
 4,4'-bis-(2-aminobenzenesulfonyl)bis-phenolester
 neopentyl glycol bis(4-aminophenyl) ether
 10 2,2'-oxydianiline
 4,4'-diaminodiphenylamine-2,2-disulphonic acid
 4,4-diamino diphenyl urea
 3,3'-tolidine-5-sulfonic acid
 n1-(3-[(2-aminobenzoyl)amino]propyl)-2-aminobenzamide
 15 2-((6-[(2-aminophenyl)sulfanyl]-5-nitro-2-pyridyl)sulfanyl)aniline
 2-((6-amino-1,3-benzothiazol-2-yl)dithio)-1,3-benzothiazol-6-ylamine
 tetramethylbenzidine
 2-([6-[(2-aminophenyl)sulfanyl]-3,5-di(trifluoromethyl)-2-pyridyl]sulfanyl) anil
 3,6-diaminothioxanthene-10-dioxide dihydrochloride
 20 m-tolidine dihydrochloride hydrate
 2-amino-n-[2-amino-4-(trifluoromethyl)phenyl]-5-methylbenzamide
 2-([2-[(2-aminophenyl)thio]-6-nitro-4-(trifluoromethyl)phenyl]thio)aniline
 2-([3-([(2-aminophenyl)thio]methyl)-2,4,6-trimethylbenzyl]thio)aniline
 3-[3-amino-5-(trifluoromethyl)benzyl]-5-(trifluoromethyl)aniline
 25 2-((5-[(2-aminophenyl)thio]-4-chloro-2-nitrophenyl)thio)aniline
 4-(1-(4-aminophenyl)-2-[4-(dimethylamino)phenyl]vinyl)aniline
 1,5-bis(4-aminophenoxy)pentane
 2,3'-dichlorobenzidine dihydrochloride
 3,3'-diamono-4,4'-dichlorodiphenyl sulfone
 30 3-(bis-(4-amino-phenyl)-methyl)-2,3-dihydro-isoindol-1-one
 4,4-diamino diphenyl-2-sulphonic acid
 4,4'-diamino-diphenylene-cyclohexane
 4,5'-diamino-(1,1')bianthracenyl-9,10,9',10'-tetraone
 35 **Alicyclic diamines**
 4,4'-methylenebis(cyclohexylamine)
 4,4'-methylenebis(2-methylcyclohexylamine)

Aliphatic diamines

- 1,8-diamino-p-menthane
 4,4'-methylenebis(cyclohexylamine)
 5 d-cystine
 l-cystine dimethyl ester dihydrochloride
 neamine
 bis(2-aminopropyl)amine
 (h-cys-beta-na)₂ 2 hcl
 10 l-cystine dibenzyl ester ditosylate
 1.4-diaminocyclohexane
 (h-cys-pna)₂
 dl-2-aminopropionic anhydride
 l-cystine(di-b-naphthylamide)hydrochloride
 15 l-cystine-bis-p-nitroanilide dihydrobromide
 l-cystine diethyl ester dihydrochloride
 trans-1,4-cyclohexanediamine
 4,4'-methylenebis(2-methylcyclohexylamine)
 l-leucinethiol, oxidized dihydrochloride
 20 1,3-diaminoadamantane dihydrochloride
 l-leucinethiol disulfide 2 hcl
 l-cystine disodium salt, monohydrate
 l-homocystine methylester hydrochloride
 1,3-adamantanediamine
 25 tetracyclo[8.2.1.1(8,11).0(2,7)]tetradeca-2,4,6-triene-10,11-diamine
 tricyclo[3.3.1.0(3,7)]nonane-3,7-diamine

From the class of commercially available diamines (L) preferred are the below listed ones:

30 **Alicyclic diamines**

- 4,4'-methylenebis(cyclohexylamine)
 4,4'-methylenebis(2-methylcyclohexylamine)

Aliphatic diamines

- 35 4,4'-methylenebis(cyclohexylamine)
 1.4-diaminocyclohexane
 trans-1,4-cyclohexanediamine

4,4'-methylenebis(2-methylcyclohexylamine)
1,3-adamantanediamine

Aromatic diamines

- 5 2,7-diaminofluorene
 2,6-diaminoanthraquinone
 4,4'-diaminooctafluorobiphenyl
 4,4'-diaminodiphenyl ether
 4,4'-dithiodianiline
- 10 4,4'-diaminodiphenylmethane
 4,4'-ethylenedianiline
 3,3'-dimethoxybenzidine
 o-tolidine
 3,3'-diaminobenzophenone
- 15 3,3'-diaminodiphenylmethane
 3,4'-diaminodiphenylmethane
 2,2-bis[4-(4-aminophenoxy)phenyl]hexafluoropropane
 4-[3-(4-aminophenoxy)propoxy]aniline
 4,4'-diaminodiphenyl sulfide
- 20 4,4'-diaminobenzophenone
 2,2-bis(4-aminophenyl)hexafluoropropane
 4,4'-bis(4-aminophenoxy)biphenyl
 2,2-bis[4-(4-aminophenoxy)phenyl]propane
 1,4-bis(4-aminophenoxy)benzene
- 25 1,3-bis(4-aminophenoxy)benzene
 bis[4-(4-aminophenoxy)phenyl]sulfone
 9,9-bis(4-aminophenyl)fluorene
 benzidine
 4,4'-azodianiline
- 30 1,3-bis(3-aminophenoxy)benzene
 4,4'-diamino-1,1'-binaphthyl
 4,4''-diamino-p-terphenyl
 bis(p-aminophenoxy)dimethylsilane
 4-[4-(4-aminophenoxy)butoxy]aniline
- 35 3,4'-diaminochalcone
 trimethylene bis(4-aminobenzoate)
 3,4'-diaminobiphenyl

- 2,7-diamino-9-fluorenone
 4',4''(5'')-diaminodibenzo-15-crown-5
 2,2'-bis(trifluoromethyl)benzidine
 alpha,alpha'-bis(4-aminophenyl)-1,4-diisopropylbenzene
 5 3,3'-bis(trifluoromethyl)benzidine
 4,4'-(1,3-phenylenediisopropylidene)bis(aniline)
 1,4-phenylenebis[[4-(4-aminophenoxy)phenyl]methanone]
 4-[4-(4-aminophenoxy)-2,3,5,6-tetrafluorophenoxy]aniline
 4-[1-(4-aminophenyl)-1-methylethyl]aniline
 10 neopentyl glycol bis(4-aminophenyl) ether
 4,4-diamino diphenyl ur
 1,5-bis(4-aminophenoxy)pentane

From the class of commercially available diamines (L) more preferred are the below listed ones:

15

Aromatic diamines

- 2,7-diaminofluorene
 4,4'-diaminooctafluorobiphenyl
 4,4'-diaminodiphenyl ether
 20 4,4'-diaminodiphenylmethane
 4,4'-ethylenedianiline
 3,3'-diaminobenzophenone
 4-[3-(4-aminophenoxy)propoxy]aniline
 4,4'-diaminodiphenyl sulfide
 25 4,4'-diaminobenzophenone
 2,2-bis(4-aminophenyl)hexafluoropropane
 4,4'-bis(4-aminophenoxy)biphenyl
 2,2-bis[4-(4-aminophenoxy)phenyl]propane
 1,4-bis(4-aminophenoxy)benzene
 30 1,3-bis(4-aminophenoxy)benzene
 9,9-bis(4-aminophenyl)fluorene
 benzidine
 bis(p-aminophenoxy)dimethylsilane
 4-[4-(4-aminophenoxy)butoxy]aniline
 35 3,4'-diaminochalcone
 trimethylene bis(4-aminobenzoate)
 3,4'-diaminobiphenyl

2,7-diamino-9-fluorenone
4',4''(5'')-diaminodibenzo-15-crown-5
4-[4-(4-aminophenoxy)-2,3,5,6-tetrafluorophenoxy]aniline
4-[1-(4-aminophenyl)-1-methylethyl]aniline
5 1,5-bis(4-aminophenoxy)pentane

Aliphatic diamines

4,4'-methylenebis(cyclohexylamine)
1.4-diaminocyclohexane

10

Alicyclic diamines

4,4'-methylenebis(cyclohexylamine)

15

A further embodiment of the present invention is a composition comprising at least one diamine (I) and optionally at least one further diamine, which is different from (I) or/and an additive.

Preferably, the further diamine is of formula (L).

20

Additives such as silane-containing compounds and epoxy-containing crosslinking agents may be added.

Suitable silane-containing additives are described in Plast. Eng. 36 (1996), (Polyimides, fundamentals and applications), Marcel Dekker, Inc.

25

Suitable epoxy-containing cross-linking additives include 4,4'-methylene-bis-(N,N-diglycidylaniline), trimethylolpropane triglycidyl ether, benzene-1,2,4,5-tetracarboxylic acid 1,2,4,5-N,N'-diglycidyl diimide, polyethylene glycol diglycidyl ether, N,N-diglycidylcyclohexylamine and the like.

30


Additional additives are photo-sensitizers, photo-radical generators, cationic photo-initiators.

35


Suitable photo-active additives include 2,2-dimethoxyphenylethanone, a mixture of diphenylmethanone and N,N-dimethylbenzenamine or ethyl 4-(dimethylamino)-

benzoate, xanthone, thioxanthone, Irgacure® 184, 369, 500, 651 and 907 (Ciba), Michler's ketone, triaryl sulfonium salt and the like.


Further the present invention relates to a process for the preparation of a diamine compound (XII) as defined above comprising contacting a compound of formula (XIV)




with a dinitro compound of formula (XVI)



and then converting the obtained dinitro compound of formula (XVIa)



in the corresponding diamino compound of formula (XII)



wherein

F, x₁, n₁, n, B, Q, D, , X, Y, Z¹, Z^{1a}, L, u₁, u₂, a₃ and S¹ have the same meanings and preferences as given above, and wherein D1 has the same meaning and

preferences as D as given above, with the proviso that the two amino groups of D are replaced by two nitro groups.

5 The reaction between compounds (XIV) and (XVI) can be conducted in many known ways (see J. March, Advanced Organic Chemistry, second edition, pages 363 and 365).

Usually, compounds (XIV) and (XVI) are contacted with a dehydrating agent.

10 Commonly known dehydrating agents can be used. Preferred are EDC, 1-(3-dimethylaminopropyl)-3-ethylcarbodiimide hydrochloride or DCC, dicyclohexylcarbodiimide, trifluoroacetic anhydride, $\text{H}_3\text{BO}_3\text{-H}_2\text{SO}_4$, polymer-protected AlCl_3 , pyridinium salts- Bu_3N or N,N-carbonyldiimidazole.

15 In general, the reaction of compounds (XIV) and (XVI) is conducted in a solvent.

Usually organic solvents, such as for example toluene, xylene, pyridine, halogenalkane, such as dichloromethane, trichloroethane, acetone or dimethylformamide are used.

20 The conversion of nitro compounds to amino compounds is commonly known and for example described J. March, Advanced Organic Chemistry, 1977, pages 1125 and 1126). Further, the conversion can be conducted in analogy to the process described in WO 98/13331 and WO 96/36597.

25 Further, the present invention relates to compounds of formulae (XIV) and (XVI), and (XVIa) as given above.

30 In addition, the present invention relates to polymer, copolymer and oligomer comprising diamine (I) as one of the basic building blocks.

Preferred polymer, copolymer and oligomer comprise diamine (I) and a tetracarboxylic acid anhydride as basic building blocks.


Preferably, the polymer, copolymer or oligomer is comprising diamine (I) as one basic building block are in the context of the invention a polyamic acid, polyamic ester, polyimide or a mixture thereof, preferably a mixture of polyamic acid and polyamic ester and/or polyimide. More preferred is a mixture of polyamic acid and polyimide.

5

In the context of the present invention the term "polyimide" has the meaning of partially or complete imidised polyamic acid or polyamic ester. In analogy, the term "imidisation" has in the context of the present invention the meaning of partially or complete imidisation.

10

Preferably, the tetracarboxylic acid anhydride is of formula (V)



15

(V)

wherein:

T represents a tetravalent organic radical.

The tetravalent organic radical T is preferably derived from an aliphatic, alicyclic or aromatic tetracarboxylic acid dianhydride.

20

Preferred examples of aliphatic or alicyclic tetracarboxylic acid dianhydrides are:

1,1,4,4-butanetetracarboxylic acid dianhydride,

ethylenemaleic acid dianhydride,

25

1,2,3,4-cyclobutanetetracarboxylic acid dianhydride,

1,2,3,4-cyclopentanetetracarboxylic acid dianhydride,

2,3,5-tricarboxycyclopentylacetic acid dianhydride,

tetrahydro-4,8-methanofuro[3,4-d]oxepine-1,3,5,7-tetrone,

3-(carboxymethyl)-1,2,4-cyclopentanetricarboxylic acid 1,4:2,3-dianhydride,

30

hexahydrofuro[3',4':4,5]cyclopenta[1,2-c]pyran-1,3,4,6-tetrone,

- 3,5,6-tricarboxynorbornylacetic acid dianhydride,
 2,3,4,5-tetrahydrofuran-tetracarboxylic acid dianhydride,
 rel-[1S,5R,6R]-3-oxabicyclo[3.2.1]octane-2,4-dione-6-spiro-3'-
 (tetrahydrofuran-2',5'-dione),
 5 4-(2,5-dioxotetrahydrofuran-3-yl)-tetrahydronaphthalene-1,2-dicarboxylic acid dianhydride,
 5-(2,5-dioxotetrahydrofuran-3-yl)-3-methyl-3-cyclohexene-1,2-dicarboxylic acid dianhydride,
 bicyclo[2.2.2]oct-7-ene-2,3,5,6-tetracarboxylic acid dianhydride,
 10 bicyclo[2.2.2]octane-2,3,5,6-tetracarboxylic acid dianhydride,
 1,8-dimethylbicyclo[2.2.2]oct-7-ene-2,3,5,6-tetracarboxylic acid dianhydride,
 pyromellitic acid dianhydride,
 3,3',4,4'-benzophenonetetracarboxylic acid dianhydride,
 4,4'-oxydiphthalic acid dianhydride,
 15 3,3',4,4'-diphenylsulfonetetracarboxylic acid dianhydride,
 1,4,5,8-naphthalenetetracarboxylic acid dianhydride,
 2,3,6,7-naphthalenetetracarboxylic acid dianhydride,
 3,3',4,4'-dimethyldiphenylsilanetetracarboxylic acid dianhydride,
 3,3',4,4'-tetraphenylsilanetetracarboxylic acid dianhydride,
 20 1,2,3,4-furantetracarboxylic acid dianhydride,
 4,4'-bis(3,4-dicarboxyphenoxy)diphenyl sulfide dianhydride,
 4,4'-bis(3,4-dicarboxyphenoxy)diphenyl sulfone dianhydride,
 4,4'-bis(3,4-dicarboxyphenoxy)diphenylpropane dianhydride,
 3,3',4,4'-biphenyltetracarboxylic acid dianhydride,
 25 ethylene glycol bis(trimellitic acid) dianhydride,
 4,4'-(1,4-phenylene)bis(phthalic acid) dianhydride,
 4,4'-(1,3-phenylene)bis(phthalic acid) dianhydride,
 4,4'-(hexafluoroisopropylidene)diphthalic acid dianhydride,
 4-*tert*-butyl-6-(2,5-dioxotetrahydro-3-furanyl)-2-benzofuran-1,3-dione,
 30 5-(2,5-dioxotetrahydro-3-furanyl)-3a,4,5,9b-tetrahydronaphtho[1,2-*c*]furan-1,3-dione,
 5-(2,5-dioxotetrahydro-3-furanyl)-5-methyl-3a,4,5,9b-tetrahydronaphtho[1,2-*c*]furan-1,3-dione,
 5-(2,5-dioxotetrahydro-3-furanyl)-6-methylhexahydro-2-benzofuran-1,3-dione,

- 5-(2,5-dioxotetrahydro-3-furanyl)-7-methyl-3a,4,5,7a-tetrahydro-2-benzofuran-1,3-dione,
 6-(2,5-dioxotetrahydro-3-furanyl)-4-methylhexahydro-2-benzofuran-1,3-dione,
 9-isopropyloctahydro-4,8-ethenofuro[3',4':3,4]cyclobuta[1,2-f][2]benzofuran-
 5 1,3,5,7-tetrone,
 1,2,5,6-cyclooctanetetracarboxylic acid dianhydride,
 octahydro-4,8-ethenofuro[3',4':3,4]cyclobuta[1,2-f][2]benzofuran-1,3,5,7-tetrone,
 octahydrofuro[3',4':3,4]cyclobuta[1,2-f][2]benzofuran-1,3,5,7-tetrone,
 tetrahydro-3,3'-bifuran-2,2',5,5'-tetrone,
 10 4,4'-oxydi(1,4-phenylene)bis(phthalic acid) dianhydride, and
 4,4'-methylenedi(1,4-phenylene)bis(phthalic acid) dianhydride.

Preferred examples of aromatic tetracarboxylic acid dianhydrides are:

- 15 pyromellitic acid dianhydride,
 3,3',4,4'-benzophenonetetracarboxylic acid dianhydride,
 4,4'-oxydiphthalic acid dianhydride,
 3,3',4,4'-diphenylsulfonetetracarboxylic acid dianhydride,
 1,4,5,8-naphthalenetetracarboxylic acid dianhydride,
 20 2,3,6,7-naphthalenetetracarboxylic acid dianhydride,
 3,3',4,4'-dimethyldiphenylsilanetetracarboxylic acid dianhydride,
 3,3',4,4'-tetraphenylsilanetetracarboxylic acid dianhydride,
 1,2,3,4-furantetracarboxylic acid dianhydride,
 4,4'-bis(3,4-dicarboxyphenoxy)diphenyl sulfide dianhydride,
 25 4,4'-bis(3,4-dicarboxyphenoxy)diphenyl sulfone dianhydride,
 4,4'-bis(3,4-dicarboxyphenoxy)diphenylpropane dianhydride,
 3,3',4,4'-biphenyltetracarboxylic acid dianhydride,
 ethylene glycol bis(trimellitic acid) dianhydride,
 4,4'-(1,4-phenylene)bis(phthalic acid) dianhydride,
 30 4,4'-(1,3-phenylene)bis(phthalic acid) dianhydride,
 4,4'-(hexafluoroisopropylidene)diphthalic acid dianhydride,
 4,4'-oxydi(1,4-phenylene)bis(phthalic acid) dianhydride,
 4,4'-methylenedi(1,4-phenylene)bis(phthalic acid) dianhydride,
 4-tert-butyl-6-(2,5-dioxotetrahydro-3-furanyl)-2-benzofuran-1,3-dione,

and the like.

More preferably the tetracarboxylic acid dianhydrides used to form the tetravalent organic radical T are selected from:

5

1,2,3,4-cyclobutanetetracarboxylic acid dianhydride,
1,2,3,4-cyclopentanetetracarboxylic acid dianhydride,
2,3,5-tricarboxycyclopentylacetic acid dianhydride,
tetrahydro-4,8-methanofuro[3,4-d]oxepine-1,3,5,7-tetrone,

10

3-(carboxymethyl)-1,2,4-cyclopentanetricarboxylic acid 1,4:2,3-dianhydride,
hexahydrofuro[3',4':4,5]cyclopenta[1,2-c]pyran-1,3,4,6-tetrone,
5-(2,5-dioxotetrahydrofuran-3-yl)-3-methyl-3-cyclohexene-1,2-
dicarboxylic acid dianhydride,
pyromellitic acid dianhydride,

15

4-(2,5-dioxotetrahydrofuran-3-yl)tetrahydronaphthalene-1,2-
dicarboxylic acid dianhydride,
5-(2,5-dioxotetrahydro-3-furanyl)-5-methyl-3a,4,5,9b-tetrahydronaphtho[1,2-
c]furan-1,3-dione,
5-(2,5-dioxotetrahydro-3-furanyl)-3a,4,5,9b-tetrahydronaphtho[1,2-c]furan-1,3-
dione,
20 5-(2,5-dioxotetrahydro-3-furanyl)-7-methyl-3a,4,5,7a-tetrahydro-2-benzofuran-
1,3-dione,
4-tert-butyl-6-(2,5-dioxotetrahydro-3-furanyl)-2-benzofuran-1,3-dione,
4,4'-(hexafluoroisopropylidene)diphthalic acid dianhydride and
25 bicyclo[2.2.2]oct-7-ene-2,3,5,6-tetracarboxylic acid dianhydride.

The polymer, copolymer or oligomer, especially the polyamic acid, polyamic acid ester and polyimide and mixtures thereof may be prepared in line with known methods, such as those described in Plast. Eng. 36 (1996), (Polyimides, fundamentals and applications), Marcel Dekker, Inc.

30

For example, the amidisation, poly-condensation reaction for the preparation of the polyamic acids is carried out in solution in a polar aprotic organic solvent, such as γ -butyrolactone, N,N-dimethylacetamide, N-methylpyrrolidone or N,N-dimethyl-

formamide. In most cases equimolar amounts of the anhydride and the diamine are used, i.e. one amino group per anhydride group. If it is desired to stabilize the molecular weight of the polymer, copolymer or oligomer, it is possible for that purpose to either add an excess or a less-than-stoichiometric amount of one of the two components or to add a mono-functional compound in the form of a dicarboxylic acid monoanhydride or in the form of a monoamine. Examples of such mono-functional compounds are maleic acid anhydride, phthalic acid anhydride, aniline and the like. Preferably the reaction is carried out at temperatures of less than 100 °C.

The imidisation, cyclisation of the polyamic acids to form the polyimides can be carried out by heating, i.e. by condensation with removal of water or by other imidisation reactions using appropriate reagents.

Partially imidisation is achieved for example, if the imidisation is carried out purely thermally, the imidisation of the polyamic acids may not always be complete, i.e. the resulting polyimides may still contain proportions of polyamic acid.

Complete imidisation reactions are carried out at temperatures between 60 and 250 °C, preferably at temperatures of less than 200 °C.

In order to achieve imidisation at lower temperatures additional reagents that facilitate the removal of water are added to the reaction mixture. Such reagents are, for example, mixtures consisting of acid anhydrides, such as acetic acid anhydride, propionic acid anhydride, phthalic acid anhydride, trifluoroacetic acid anhydride or tertiary amines, such as triethylamine, trimethylamine, tributylamine, pyridine, N,N-dimethylaniline, lutidine, collidine etc. The amount of aforementioned additional reagents that facilitate the removal of water is preferably at least four equivalents of acid anhydride and two equivalents of amine per equivalent of polyamic acid to be condensed.

The imidization degree of each polymer used in the liquid crystal alignment agent of the invention can be arbitrarily adjusted by controlling the catalyst amount, reaction time and reaction temperature employed in production of the polymer. In the present description, "imidization degree" of polymer refers to a proportion (expressed in %) of the number of recurring units of polymer forming an imide ring or an isoimide ring to the number of total recurring units of polymer. In the present description, the

- imidization degree of a polyamic acid not subjected to dehydration and ring closure is 0%. The imidization degree of each polymer is determined by dissolving the polymer in deuterated dimethyl sulfoxide, subjecting the resulting solution to ¹H-NMR measurement at a room temperature using tetramethylsilane as a standard substance, and calculating from the following formula.

$$\text{Imidization degree (\%)} = 1 - (A^1/A^2 \times B) \times 100$$

- 10 A^1 : Peak area based on protons of NH groups (in the vicinity of 10ppm)
 A^2 : Peak area based of one proton of acrylate double bond (in the vicinity of 6.5 ppm).
 B: Proportion of the number of acrylate protons to one proton of NH group in the polymer precursor

- 15 The imidization degree is usually in the range of 1 to 99%, preferably 5 to 50%, more preferably 10 to 40%.

The present invention concerns a process for the preparation of a polymer, copolymer or oligomer comprising polymerisation of a diamine (I).

- 20 Preferably the polymerisation of a diamine (I) comprises
- a) amidisation of at least one diamine (I) to polyamic acid or a polyamic ester, and
 - b) imidisation of the obtained polyamic acid or ester, to a polyimide, or
 - c) imidisation of the diamine (I) to polyimide.

- 25 In a more preferred embodiment of the invention, the polymersiation of the diamine comprises the amidisation of at least one diamine (I) with tetracarboxylic acid anhydride, preferably tetracarboxylic acid anhydride (V), and/or the imidisation, preferably by elevated temperature.

- 30 In a further more preferred embodiment of the invention, the polymersiation of the diamine comprises the amidisation of a diamine (I) with tetracarboxylic acid anhydride, preferably tetracarboxylic acid anhydride (V), and/or the imidisation, preferably by elevated temperature, and wherein the amidisation and/or imidisation is optionally conducted

- in the presence of additives as given above, and/or
- in the presence of a further diamine, which is different from that of formula (I), preferably in the presence of at least one diamine (L) and/or
- in the presence of a further polymer, copolymer or oligomer comprising as one
5 basic building block a diamine (L), or a further polymer, copolymer or oligomer, which is different from a polyamic acid, polyamic ester or a polyimide, more preferably a further polymer, copolymer or oligomer, which is selected from the group of which is selected from the group of polymers include polyacrylates, polymethacrylates, polyacrylamides, polymethacrylamides, polyvinylether and
10 polyvinylester, polyallylether and ester, polystyrenes, polysiloxanes, polyimides, polyamic acids and their esters, polyamidimides, polymaleic acids, polyfumaric acids polyurethanes and derivatives thereof.

Preferably, the further polymer, copolymer or oligomer comprises as basic building
15 block a diamine (L) and a tetracarboxylic acid anhydride, preferably a tetracarboxylic acid anhydride of formula (V).

This polymer, copolymer or oligomer is prepared in analogy to the polymer, copolymer or oligomer of the invention comprising diamine (I).

- 20 The imidisation is conducted after or during amidisation. In general, the imidisation is conducted after amidisation.

Preferred is the partially imidisation of polyamic acid or polyamic ester.

- 25 If the polymer is prepared only by imidisation, diamine (I) will be contacted with an imidisation compound, with at least two polymerisable functional groups, such as for example, carbonyl groups or halogen groups.

- 30 More preferably, the present invention concerns a process for the preparation of a polymer, copolymer or oligomer comprising polymerisation of a diamine (I) and tetracarboxylic acid anhydride, preferably tetracarboxylic acid anhydride (V).

Another embodiment of the present invention relates to a copolymer comprising diamine (I). Preferred is a copolymer, comprising at least two diamines (I).

A further embodiment of the present invention relates to a polymer, copolymer or oligomer, or to blends obtainable according to the processes and preferred processes of the invention.

5

Preferably, blends are obtainable by reaction of at least two different diamine (I), or by reaction of at least one diamine (I) with a polymer, copolymer or oligomer comprising as basic building block at least one diamine (L).

10

Preferably, the present invention concerns polymer, copolymer or oligomer, comprising in their polymer-, copolymer- or oligomer-side-chains at least one photo-reactive group. Preferably, the photo-reactive group of the side chains are photo-isomerized and/or crosslinked, more preferably photo-dimerized, by exposure to aligning light.

15

The term photoreactive groups has the meaning of groups, which are able to react by interaction with light.

The treatment with aligning light may be conducted in a single step or in several separate steps. In a preferred embodiment of the invention the treatment with aligning light is conducted in a single step.

20

In the context of the present invention photo-reactive group has preferably the meaning of a dimerizable, isomerizable, polymerizable and/or cross-linkable group.

25

In the context of the present invention, aligning light is light of wavelengths, which can initiate photoalignment. Preferably, the wavelengths are in the UV-A, UVB and/or UV/C-range, or in the visible range. It depends on the photoalignment compound, which wavelengths are appropriate. Preferably, the photo-reactive groups are sensitive to visible and/or UV light. A further embodiment of the invention concerns the generating of aligning light by laser light.

30

The instant direction of the aligning light may be normal to the substrate or at any oblique angle.

For generating tilt angles, preferably the aligning light is exposed from oblique angles.

More preferably, aligning light is at least partially linearly polarized, elliptically polarized, such as for example circularly polarized, or non-polarized; most preferably at least

5 circular or partially linearly polarized light, or non-polarized light exposed obliquely. Especially, most preferred aligning light denotes substantially polarised light, especially linearly polarised light; or aligning light denotes non-polarised light, which is applied by an oblique irradiation.

10 In a more preferred embodiment of the invention the polymer, copolymer or oligomer is treated with polarised light, especially linearly polarised light, or by oblique radiation with non-polarised light.

Further preferred are polymers, copolymers or oligomers of the present invention,

15 - wherein at least 30%, preferably at least 75 % of the repeating units include a side chain with a photo-reactive group; and/or

- wherein, the photo-reactive groups are able to undergo photo-dimerisation, preferably photo-cyclisation, in particular [2+2]-photo-cyclisation; and/or

20

- wherein the polymer or oligomer is a polymer gel or a polymer network, or an oligomer gel or an oligomer network, respectively; and/or

25

- wherein the polymer, copolymer or oligomer has an intrinsic viscosity in the range of 0.05 to 10 dL/g, preferably in the range of 0.05 to 5 dL/g; and/or

- wherein the polymer, copolymer or oligomer contains from 2 to 2000 repeating units, especially from 3 to 200 repeating units; and/or

30

- wherein the polymer, copolymer or oligomer is in the form of a homopolymer or of a copolymer, preferably of a statistical copolymer; and/or

- wherein the polymer, copolymer or oligomer is cross-linkable or cross-linked;

A further preferred embodiment of the present invention concerns polymers, copolymers or oligomers, having an intrinsic viscosity preferably in the range of 0.05 to 10 dL/g, more preferably in the range of 0.05 to 5 dL/g. Herein, the intrinsic viscosity ($\eta_{inh} = \ln \eta_{rel}/C$) is determined by measuring a solution containing a polymer or an oligomer in a concentration of 0.5 g/100 ml solution for the evaluation of its viscosity at 30 °C using N-methyl-2-pyrrolidone as solvent.

In addition, a preferred embodiment of the present invention concerns polymers, copolymers or oligomers, containing from 2 to 2000 repeating units, especially from 3 to 200 repeating units.

The side-chain polymers or oligomers according the invention can be present in the form of homopolymers as well as in the form of copolymers. The term "copolymers" is to be understood as meaning especially statistical copolymers.

Further, the present invention concerns a composition, especially a blend, comprising

- a polymer, copolymer or oligomer according to definition and preferences of the invention, comprising at least a diamine (I) as basic building block, or
- a polymer, copolymer or oligomer according to definition and preferences of the invention, obtainable by the processes of the invention, and
- preferably in addition comprising and a further diamine, which is different from diamine (I), preferably a diamine (L).

The further polymer, copolymer or oligomer comprising as one basic building block a diamine (L) has the same preferences as given above.

Preferably, the present invention concerns a composition, especially a blend, comprising

- a polymer, copolymer or oligomer according to definition and preferences of the invention, comprising at least a diamine (I) as basic building block, or
- a polymer, copolymer or oligomer according to definition and preferences of the invention, obtainable by the processes of the invention,
- and/or a further polymer, copolymer or oligomer comprising as one basic building block a further diamine, which is different from diamine (I), preferably a

5 diamine (L), or a further polymer, copolymer or oligomer, which is different from a polyamic acid, polyamic ester or a polyimide, more preferably a further polymer, copolymer or oligomer, which is selected from the group of polyacrylate, polystyrol, polyester, polyurethane, polyethylene, polypropylene, polyvinylchloride, polytetrafluoroethylene, polycarbonate, polyterephthalate and dendrimers.

10 Further preferably, the present invention concerns a composition, especially a blend, comprising

- a polymer, copolymer or oligomer according to definition and preferences of the invention, comprising at least a diamine (I) as basic building block, or
- a polymer, copolymer or oligomer according to definition and preferences of the invention, obtainable by the processes of the invention,
- 15 - and optionally a further diamine, which is different from diamine (I), preferably a diamine (L),
- and an additive, preferably silane-containing compounds,
- and/or a further polymer, copolymer or oligomer comprising as one basic building block a further diamine, which is different from diamine (I),
- 20 preferably at least one diamine (L),
- and/or a further polymer, copolymer or oligomer, which is different from a polyamic acid, polyamic ester or a polyimide, more preferably a further polymer, copolymer or oligomer, which is selected from the group of polymers include polyacrylates, polymethacrylates, polyacrylamides, polymethacrylamides,
- 25 polyvinylether and polyvinylester, polyallylether and ester, polystyrenes, polysiloxanes, polyimides, polyamic acids and their esters, polyamidimides, polymaleic acids, polyfumaric acids polyurethanes and derivatives thereof,
- and/or photo-active polymers, photo-active oligomers and/or photo-active monomers,
- 30 - and/or cross-linking agents, preferably epoxy-containing cross-linking agents, most preferably selected from the group:
4,4'-methylene-bis-(N,N-diglycidylaniline), trimethylolpropane triglycidyl ether, benzene-1,2,4,5-tetracarboxylic acid 1,2,4,5-N,N'-diglycidylidimide, polyethylene glycol diglycidyl ether, N,N-diglycidylcyclohexylamine.

The polymers or oligomers according to the invention may be used in form of polymer layers or oligomer layers alone or in combination with other polymers, oligomers, monomers, photo-active polymers, photo-active oligomers and/or photo-active monomers, depending upon the application to which the polymer or oligomer layer is to be added. Therefore it is understood that by varying the composition of the polymer or oligomer layer it is possible to control specific and desired properties, such as an induced pre-tilt angle, good surface wetting, a high voltage holding ratio, a specific anchoring energy, etc.

Polymer or oligomer layers may readily be prepared from the polymers or oligomers of the present invention and a further embodiment of the invention relates to a polymer or oligomer layer comprising a polymer or oligomer according to the present invention, which is preferably prepared by treatment with aligning light. Preferably, the invention relates to a polymer or oligomer layer comprising a polymer or oligomer according to the present invention in a cross-linked and/or isomerized form.

The polymer or oligomer layer is preferably prepared by applying one or more polymers or oligomers according to the invention to a support and, after imidisation or without imidisation, treating, preferably cross-linking and /or isomerising, the polymer or oligomer or polymer mixture or oligomer mixture by irradiation with aligning light.

In general, transparent support such as glass or plastic substrates, optionally coated with indium tin oxide (ITO) are used.

Further, it is possible to vary the direction of orientation and the tilt angle within the polymer or oligomer layer by controlling the direction of the irradiation of the aligning light. It is understood that by selectively irradiating specific regions of the polymer or oligomer layer very specific regions of the layer can be aligned. In this way, layers with a defined tilt angle can be provided. The induced orientation and tilt angle are retained in the polymer or oligomer layer by the process, especially by the process of cross-

linking.

Method for the preparation of a polymer, copolymer or oligomer according to the invention, wherein in a polycondensation reaction a diamine (I) is reacted with one or
5 more tetracarboxylic acid anhydrides of the general formula (V), optionally in the presence of one or more additional other diamines.

Further, the present invention preferably concerns a method, wherein a poly-
condensation reaction for the preparation of the polyamic acids is carried out in
10 solution in a polar aprotic organic solvent, preferably selected from γ -butyrolactone, N,N-dimethylacetamide, N-methylpyrrolidone or N,N-dimethylformamide.

Preferably, the present invention concerns a method, wherein subsequent to the poly-
condensation cyclisation with removal of water is carried out thermally under formation
15 of a polyimide.

More preferably, the present invention concerns a method, wherein imidisation is
carried out prior or after the application of the polymer, copolymer or oligomer to a
support.

20

Further preferred methods of the invention relates to

- a method for the preparation of a polymer layer or oligomer layer, which are vertically aligned;
- a method for the preparation of multi-domain vertical alignment of a polymer layer or
25 oligomer layer;
- a method for the preparation of a polymer layer or oligomer layer with tilted optical axis.

A further embodiment of the present invention concerns a polymer, copolymer or
30 oligomer layer, in particular orientation layer, comprising at least one polymer, copolymer or oligomer according to the present invention.

It is understood that the polymer or oligomer layers of the present invention (in form of

a polymer gel, a polymer network, a polymer film, etc.) can also be used as orientation layers for liquid crystals. A further preferred embodiment of the invention relates to an orientation layer comprising one or more polymers or oligomers according to the invention, preferably in a cross-linked form. Such orientation layers can be used in the manufacture of unstructured or structured optical-or electro-optical elements, preferably in the production of hybrid layer elements.

In addition, the present invention concerns a method for the preparation of a polymer layer or oligomer layer, wherein one or more polymers, copolymers or oligomers according to the present invention is applied to a support, preferably from a solution of the polymer or oligomer material and subsequent evaporation of the solvent, and wherein, after any imidisation step which may be necessary, the polymer or oligomer or polymer mixture or oligomer mixture treated with aligning light, and preferably isomerized and/or cross-linked by irradiation with aligning light.

A preferred method of the present invention concerns a method, wherein the direction of orientation and the tilt angle within the polymer layer or oligomer layer is varied by controlling the direction of the irradiation with aligning light, and/or wherein by selectively irradiating specific regions of the polymer layer or oligomer layer specific regions of the layer are aligned.

The orientation layers are suitably prepared from a solution of the polymer or oligomer material. The polymer or oligomer solution is applied to a support optionally coated with an electrode [for example a glass plate coated with indium–tin oxide (ITO)] so that homogeneous layers of 0.05 to 50 μm thickness are produced. In this process different coating techniques like spin-coating, meniscus-coating, wire-coating, slot-coating, offset-printing, flexo-printing, gravur-printing may be used. Then, or optionally after a prior imidisation step, the regions to be oriented are irradiated, for example, with a high-pressure mercury vapour lamp, a xenon lamp or a pulsed UV laser, using a polarizer and optionally a mask for creating images of structures.

Further, the present invention concerns the use of a polymer layer, copolymer or oligomer layer according to the present invention, preferably in cross-linked form, as an orientation layer for liquid crystals.

- 5 Further, the present invention concerns preferably the use of a polymer layer, copolymer or oligomer layer for the induction of vertical alignment of adjacent liquid crystalline layers, in particular for operating a cell in MVA mode.

- 10 The irradiation time is dependent upon the output of the individual lamps and can vary from a few seconds to several hours. The photo-reaction (dimerisation, polymersiation, cross-linking) can also be carried out, however, by irradiation of the homogeneous layer using filters that, for example, allow only the radiation suitable for the cross--linking reaction to pass through.

- 15 It is understood that the polymer or oligomer layers of the invention may be used in the production of optical or electro-optical devices having at least one orientation layer as well as unstructured and structured optical elements and multi-layer systems.

- 20 The present invention concerns the use of a polymer layer, copolymer or oligomer layer as an orientation layer for liquid crystals.

Preferred is the use for the induction of vertical alignment of adjacent liquid crystalline layers.

- 25 A further embodiment of the invention relates to an optical or electro-optical device comprising one or more polymers or oligomers according to the present invention in cross-linked form. The electro-optical devices may comprise more than one layer. The layer, or each of the layers may contain one or more regions of different spatial orientation.

- 30 Preferably, the present invention concerns an optical and electro-optical unstructured or structured constructional elements, preferably liquid crystal display cells, multi-layer and hybrid layer elements, comprising at least one polymer layer, copolymer or oligomer layer according to the present invention.

More preferably, the present invention concerns an orientation layer, comprising at least one polymer layer, copolymer or oligomer layer according to the present invention.

5


The advantages of the present invention could not be foreseen by a skilled person. It has surprisingly been found, that in addition to the polyamic/polyimide backbone, the introduction of an organofluorine group into a peripheral position of the polymer side groups having specific molecular architecture plays a predominant role in obtaining

10 MVA materials having optimised properties, such as the required high voltage holding ratios, the adjustable pre-tilt angles required for the MVA mode and their stability to light and heat.

EXAMPLE 1


Synthesis

5 1.1 Preparation of 4-Formylphenyl-4-pentylcyclohexanecarboxylate



23.19 g (189.9 mmol) of 4-hydroxybenzaldehyde, 35.00 g (189.9 mmol) of 4-pentylcyclohexanecarboxylic acid, 1.16 g (9.5 mmol) of 4-Dimethylaminopyridine are dissolved in 500 ml of dichloromethane. 40.00 g (208.9 mmol) of N-(3-Dimethylaminopropyl)-N'-ethylcarbodiimide hydrochloride (EDC hydrochloride) are added at 0°C. The solution is stirred for 1 h at 0°C and allowed to stir at room temperature overnight. After 22 hours at room temperature the reaction mixture was partitioned between dichloromethane and water; the organic phase is washed repeatedly with water, dried over sodium sulphate, filtered and concentrated by rotary evaporation give 45.0 g 4-Formylphenyl-4-pentylcyclohexanecarboxylate.

1.2 Preparation of (2E)-3-(4-[(4-pentylcyclohexyl)carbonyl]oxy)phenyl]acrylic acid



45.00 g (148.8 mMol) of 4-Formylphenyl-4-pentylcyclohexanecarboxylate and 33.6 g (322.9 mMol) of Malonic acid are dissolved in 61.1 ml (759.7 mMol) of Pyridine. 7.9 ml (95.0 mMol) of Pyrrolidine are added to the suspension which is allowed to react at 90°C under argon for 2.5 h. The yellow solution is then thrown on ice. The solution is carefully acidified to pH=1-2 with a 25% HCl solution and is stirred for 15 min. The

product is filtrated off and dried at room temperature under vacuum to give 35.4 g (2E)-3-(4-{{(4-pentylcyclohexyl)carbonyl}oxy}phenyl)acrylic acid of as white powder.

5 The following acrylic acid are synthesized in an analogous manner:

(2E)-3-(4-{{(4-methylcyclohexyl)carbonyl}oxy}phenyl)acrylic acid

(2E)-3-(4-{{(4-ethylcyclohexyl)carbonyl}oxy}phenyl)acrylic acid

(2E)-3-(4-{{(4-propylcyclohexyl)carbonyl}oxy}phenyl)acrylic acid

10 (2E)-3-(4-{{(4-butylcyclohexyl)carbonyl}oxy}phenyl)acrylic acid

(2E)-3-(4-{{(4-hexylcyclohexyl)carbonyl}oxy}phenyl)acrylic acid

(2E)-3-(4-{{(4-heptylcyclohexyl)carbonyl}oxy}phenyl)acrylic acid

(2E)-3-(4-{{(4-octylcyclohexyl)carbonyl}oxy}phenyl)acrylic acid

(2E)-3-(4-{{(4-vinylcyclohexyl)carbonyl}oxy}phenyl)acrylic acid

15 (2E)-3-(4-{{(4-prop-2-enylcyclohexyl)carbonyl}oxy}phenyl)acrylic acid

(2E)-3-(4-{{(4-but-3-enylcyclohexyl)carbonyl}oxy}phenyl)acrylic acid

(2E)-3-(4-{{(4-pent-4-enylcyclohexyl)carbonyl}oxy}phenyl)acrylic acid

(2E)-3-(4-{{(4-hex-5-enylcyclohexyl)carbonyl}oxy}phenyl)acrylic acid

(2E)-3-(4-{{(4-hept-6-enylcyclohexyl)carbonyl}oxy}phenyl)acrylic acid

20 (2E)-3-(4-{{(4-oct-7-enylcyclohexyl)carbonyl}oxy}phenyl)acrylic acid

(2E)-3-(4-{{(4-methyloxycyclohexyl)carbonyl}oxy}phenyl)acrylic acid

(2E)-3-(4-{{(4-ethyloxycyclohexyl)carbonyl}oxy}phenyl)acrylic acid

(2E)-3-(4-{{(4-propyloxycyclohexyl)carbonyl}oxy}phenyl)acrylic acid

(2E)-3-(4-{{(4-butyloxycyclohexyl)carbonyl}oxy}phenyl)acrylic acid

25 (2E)-3-(4-{{(4-pentyloxycyclohexyl)carbonyl}oxy}phenyl)acrylic acid

(2E)-3-(4-{{(4-hexyloxycyclohexyl)carbonyl}oxy}phenyl)acrylic acid

(2E)-3-(4-{{(4-heptyloxycyclohexyl)carbonyl}oxy}phenyl)acrylic acid

(2E)-3-(4-{{(4-octyloxycyclohexyl)carbonyl}oxy}phenyl)acrylic acid

(2E)-3-(4-{{(4-allyloxycyclohexyl)carbonyl}oxy}phenyl)acrylic acid

30 (2E)-3-(4-{{(4-but-3-enyloxycyclohexyl)carbonyl}oxy}phenyl)acrylic acid

(2E)-3-(4-{{(4-pent-4-enyloxycyclohexyl)carbonyl}oxy}phenyl)acrylic acid

(2E)-3-(4-{{(4-hex-5-enyloxycyclohexyl)carbonyl}oxy}phenyl)acrylic acid

(2E)-3-(4-{{(4-hept-6-enyloxycyclohexyl)carbonyl}oxy}phenyl)acrylic acid

(2E)-3-(4-{{(4-oct-7-enyloxycyclohexyl)carbonyl}oxy}phenyl)acrylic acid

- (2E)-3-(4-[[4-(3-methoxypropyl)cyclohexyl]carbonyl]oxy}phenyl)acrylic acid
(2E) 3-(4-[[4-(3-trifluoromethoxycyclohexyl)carbonyl]oxy}phenyl)acrylic acid
(2E) 3-(4-[[4-(2,2,2-trifluoroethoxy)cyclohexyl]carbonyl]oxy}phenyl)acrylic acid
(2E) 3-(4-[[4-(2,2,2-trifluoroethoxy)cyclohexyl]carbonyl]oxy}phenyl)acrylic acid
5 (2E) 3-(4-[[4-(2,2,2-trifluoropropoxy)cyclohexyl]carbonyl]oxy}phenyl)acrylic acid
(2E) 3-(4-[[4-(4,4,4-trifluorobutoxy)cyclohexyl]carbonyl]oxy}phenyl)acrylic acid
(2E) 3-(4-[[4-(5,5,5-trifluoropentyloxy)cyclohexyl]carbonyl]oxy}phenyl)acrylic acid
(2E) 3-(4-[[4-(4,4,5,5,5-pentafluoropentyloxy)cyclohexyl]carbonyl]oxy}phenyl)acrylic acid
acid
10 (2E) 3-(4-[[4-(1,1,2,2-tetrafluoroethoxy)cyclohexyl]carbonyl]oxy}phenyl)acrylic acid
(2E) 3-(4-[[4-(1,1,2,2-tetrafluoropropoxy)cyclohexyl]carbonyl]oxy}phenyl)acrylic acid
(2E) 3-(4-[[4-(4,4,5,5,6,6-heptafluorohexyloxy)cyclohexyl]carbonyl]oxy}phenyl)acrylic acid
(2E) 3-(4-[[4-(3-trifluoromethylcyclohexyl)carbonyl]oxy}phenyl)acrylic acid
15 (2E) 3-(4-[[4-(2,2,2-trifluoropropyl)cyclohexyl]carbonyl]oxy}phenyl)acrylic acid
(2E) 3-(4-[[4-(4,4,4-trifluorobutyl)cyclohexyl]carbonyl]oxy}phenyl)acrylic acid
(2E) 3-(4-[[4-(5,5,5-trifluoropentyl)cyclohexyl]carbonyl]oxy}phenyl)acrylic acid
(2E) 3-(4-[[4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl]carbonyl]oxy}phenyl)acrylic acid

20 (2E)-3-(4-[[4-(4-methylcyclohexyl)oxy]carbonyl]phenyl)acrylic acid
(2E)-3-(4-[[4-(4-ethylcyclohexyl)oxy]carbonyl]phenyl)acrylic acid
(2E)-3-(4-[[4-(4-propylcyclohexyl)oxy]carbonyl]phenyl)acrylic acid
(2E)-3-(4-[[4-(4-butylcyclohexyl)oxy]carbonyl]phenyl)acrylic acid
(2E)-3-(4-[[4-(4-hexylcyclohexyl)oxy]carbonyl]phenyl)acrylic acid
25 (2E)-3-(4-[[4-(4-heptylcyclohexyl)oxy]carbonyl]phenyl)acrylic acid
(2E)-3-(4-[[4-(4-octylcyclohexyl)oxy]carbonyl]phenyl)acrylic acid
(2E)-3-(4-[[4-(4-vinylcyclohexyl)oxy]carbonyl]phenyl)acrylic acid
(2E)-3-(4-[[4-(4-prop-2-enylcyclohexyl)oxy]carbonyl]phenyl)acrylic acid
(2E)-3-(4-[[4-(4-but-3-enylcyclohexyl)oxy]carbonyl]phenyl)acrylic acid
30 (2E)-3-(4-[[4-(4-pent-4-enylcyclohexyl)oxy]carbonyl]phenyl)acrylic acid
(2E)-3-(4-[[4-(4-hex-5-enylcyclohexyl)oxy]carbonyl]phenyl)acrylic acid
(2E)-3-(4-[[4-(4-hept-6-enylcyclohexyl)oxy]carbonyl]phenyl)acrylic acid
(2E)-3-(4-[[4-(4-oct-7-enylcyclohexyl)oxy]carbonyl]phenyl)acrylic acid
(2E)-3-(4-[[4-(4-methyloxycyclohexyl)oxy]carbonyl]phenyl)acrylic acid

- (2E)-3-(4-[(4-ethyloxycyclohexyl)oxy]carbonyl}phenyl)acrylic acid
 (2E)-3-(4-[(4-propyloxycyclohexyl)oxy]carbonyl}phenyl)acrylic acid
 (2E)-3-(4-[(4-butyloxycyclohexyl)oxy]carbonyl}phenyl)acrylic acid
 (2E)-3-(4-[(4-pentyloxycyclohexyl)oxy]carbonyl}phenyl)acrylic acid
 5 (2E)-3-(4-[(4-hexyloxycyclohexyl)oxy]carbonyl}phenyl)acrylic acid
 (2E)-3-(4-[(4-heptyloxycyclohexyl)oxy]carbonyl}phenyl)acrylic acid
 (2E)-3-(4-[(4-octyloxycyclohexyl)oxy]carbonyl}phenyl)acrylic acid
 (2E)-3-(4-[(4-allyloxycyclohexyl)oxy]carbonyl}phenyl)acrylic acid
 (2E)-3-(4-[(4-but-3-enyloxycyclohexyl)oxy]carbonyl}phenyl)acrylic acid
 10 (2E)-3-(4-[(4-pent-4-enyloxycyclohexyl)oxy]carbonyl}phenyl)acrylic acid
 (2E)-3-(4-[(4-hex-5-enyloxycyclohexyl)oxy]carbonyl}phenyl)acrylic acid
 (2E)-3-(4-[(4-hept-6-enyloxycyclohexyl)oxy]carbonyl}phenyl)acrylic acid
 (2E)-3-(4-[(4-oct-7-enyloxycyclohexyl)oxy]carbonyl}phenyl)acrylic acid
 (2E)-3-(4-[(4(3-methoxypropyl)cyclohexyl)oxy]carbonyl}phenyl)acrylic acid
 15 (2E) 3-(4-[(4-trifluoromethoxycyclohexyl)oxy]carbonyl}phenyl)acrylic acid
 (2E) 3-(4-[(4--(2,2,2-trifluoroethoxy)cyclohexyl)oxy]carbonyl}phenyl)acrylic acid
 (2E) 3-{4-[(4-(2,2,2-trifluoroethoxy)cyclohexyl)oxyl]}carbonyl}phenyl}acrylic acid
 (2E) 3-{4-[(4-(2,2,2-trifluoropropoxy)cyclohexyl)oxyl]}carbonyl}phenyl}acrylic acid
 (2E) 3-{4-[(4-(-(4,4,4-trifluorobutoxy)cyclohexyl)oxyl]}carbonyl}phenyl}acrylic acid
 20 (2E) 3-{4-[(4-(5,5,5-trifluoropentyloxy)cyclohexyl)oxyl]}carbonyl}phenyl}acrylic acid
 (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentoxy)cyclohexyl)oxyl]}carbonyl}phenyl}acrylic acid
 acid
 (2E) 3-{4-[(4-(1,1,2,2-tetrafluoroethoxy)cyclohexyl)oxyl]}carbonyl} phenyl}acrylic acid
 (2E) 3-{4-[(4-(1,1,2,2-tetrafluoropropoxy)cyclohexyl)oxyl]}carbonyl} phenyl}acrylic acid
 25 (2E) 3-{4-[(4-(4,4,5,5,6,6-heptafluorohexyloxy)cyclohexyl)oxyl]}carbonyl}
 phenyl}acrylic acid
 (2E) 3-(4-[(4-trifluoromethylcyclohexyl)oxy]carbonyl}phenyl)acrylic acid
 (2E) 3-{4-[(4-(2,2,2-trifluoropropyl)cyclohexyl)oxyl]}carbonyl}phenyl}acrylic acid
 (2E) 3-{4-[(4-(-(4,4,4-trifluorobutyl)cyclohexyl)oxyl]}carbonyl}phenyl}acrylic acid
 30 (2E) 3-{4-[(4-(5,5,5-trifluoropentyl)cyclohexyl)oxyl]}carbonyl}phenyl}acrylic acid
 (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)oxyl]}carbonyl}phenyl}acrylic acid

 (2E)-3-(4-[(4-methylcyclohexyl)methoxy]phenyl)acrylic acid
 (2E)-3-(4-[(4-ethylcyclohexyl)methoxy]phenyl)acrylic acid

- (2E)-3-(4-[(4-propylcyclohexyl)methoxy]phenyl)acrylic acid
(2E)-3-(4-[(4-butylcyclohexyl)methoxy]phenyl)acrylic acid
(2E)-3-(4-[(4-hexylcyclohexyl)methoxy]phenyl)acrylic acid
(2E)-3-(4-[(4-heptylcyclohexyl)methoxy]phenyl)acrylic acid
5 (2E)-3-(4-[(4-octylcyclohexyl)methoxy]phenyl)acrylic acid
(2E)-3-(4-[(4-vinylcyclohexyl)methoxy]phenyl)acrylic acid
(2E)-3-(4-[(4-prop-2-enylcyclohexyl)methoxy]phenyl)acrylic acid
(2E)-3-(4-[(4-but-3-enylcyclohexyl)methoxy]phenyl)acrylic acid
(2E)-3-(4-[(4-pent-4-enylcyclohexyl)methoxy]phenyl)acrylic acid
10 (2E)-3-(4-[(4-hex-5-enylcyclohexyl)methoxy]phenyl)acrylic acid
(2E)-3-(4-[(4-hept-6-enylcyclohexyl)methoxy]phenyl)acrylic acid
(2E)-3-(4-[(4-oct-7-enylcyclohexyl)methoxy]phenyl)acrylic acid
(2E)-3-(4-[(4-methyloxycyclohexyl)methoxy]phenyl)acrylic acid
(2E)-3-(4-[(4-ethyloxycyclohexyl)methoxy]phenyl)acrylic acid
15 (2E)-3-(4-[(4-propyloxycyclohexyl)methoxy]phenyl)acrylic acid
(2E)-3-(4-[(4-butyloxycyclohexyl)methoxy]phenyl)acrylic acid
(2E)-3-(4-[(4-pentyloxycyclohexyl)methoxy]phenyl)acrylic acid
(2E)-3-(4-[(4-hexyloxycyclohexyl)methoxy]phenyl)acrylic acid
(2E)-3-(4-[(4-heptyloxycyclohexyl)methoxy]phenyl)acrylic acid
20 (2E)-3-(4-[(4-octyloxycyclohexyl)methoxy]phenyl)acrylic acid
(2E)-3-(4-[(4-allyloxycyclohexyl)methoxy]phenyl)acrylic acid
(2E)-3-(4-[(4-but-3-enyloxycyclohexyl)methoxy]phenyl)acrylic acid
(2E)-3-(4-[(4-pent-4-enyloxycyclohexyl)methoxy]phenyl)acrylic acid
(2E)-3-(4-[(4-hex-5-enyloxycyclohexyl)methoxy]phenyl)acrylic acid
25 (2E)-3-(4-[(4-hept-6-enyloxycyclohexyl)methoxy]phenyl)acrylic acid
(2E)-3-(4-[(4-oct-7-enyloxycyclohexyl)methoxy]phenyl)acrylic acid
(2E)-3-(4-[(4-(3-methoxypropyl)cyclohexyl)methoxy]phenyl)acrylic acid
(2E) 3-(4-[(4-(trifluoromethoxycyclohexyl)methoxy]phenyl)acrylic acid
(2E) 3-(4-[(4-((2,2,2-trifluoroethoxy)cyclohexyl)methoxy]phenyl)acrylic acid
30 (2E) 3-(4-[(4-(trifluoromethylcyclohexyl)methoxy]phenyl)acrylic acid
(2E) 3-(4-[(4-(2,2,2-trifluoropropyl)cyclohexyl)methoxy]phenyl)acrylic acid
(2E) 3-(4-[(4-(4,4,4-trifluorobutyl)cyclohexyl)methoxy]phenyl)acrylic acid
(2E) 3-(4-[(4-(5,5,5-trifluoropentyl)cyclohexyl)methoxy]phenyl)acrylic acid
(2E) 3-(4-[(4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)methoxy]phenyl)acrylic acid

EXAMPLE 2


Synthesis

5

Preparation of 6-[[[(2E)-3-{4-[(4-pentylcyclohexyl)carbonyl]oxy}phenyl}prop-2-enoyl]oxy]]hexyl 3,5-diaminobenzoate

10

2.1 Preparation of (2E)-3-{4-[(ethoxycarbonyl)oxy]phenyl}acrylic acid




15

67 g (0.41 mol) p-cumaric acid are added to a mixture of 50.4 g (0.90 mol) potassium hydroxide and 600 ml water. 53.1 g (0.50 mol) ethyl chloroformate are added dropwise at 0°C. The reaction temperature rises to 10°C. The reaction mixture is subsequently allowed to react for 2 hours at 25°C and acidified to pH=1 with 200 ml hydrochloric acid 7 N. The product is filtered off, washed with water and dried under vacuum to give 95.3 g of (2E)-3-{4-[(ethoxycarbonyl)oxy]phenyl}acrylic acid as white powder.

20


2.2 Preparation of 6-hydroxyhexyl 3,5-dinitrobenzoate

25




357.70 g (1.686 Mol) of 3,5-dinitrobenzoic acid are suspended in 750 ml of 1-methyl-2-pyrrolidone. The suspension is stirred up to 50°C. 386.36 g (4.599 Mol) of sodium hydrogen carbonate are added and the mixture was heated up to 90°C. 22.50 g (0.150 Mol) of sodium iodide and 204.0 ml (1.533 Mol) of 6-chlorohexanol are added to the reaction mixture which is heated to 100°C for 1 h. After 1 h of reaction, the reaction is complete and the orange suspension is thrown on 2 l of ice and 1 l of water. The product is filtrated, washed water and dried at 50°C under vacuum for 24 h to give 425.0 g (91%) of 6-hydroxyhexyl 3,5-dinitrobenzoate as a rose powder.

2.3 Preparation of 6-(((2E)-{4-[(ethoxycarbonyl)oxy]phenyl}prop-2-enoyl)oxy)hexyl 3,5-dinitrobenzoate




4.53 g (0.0145 Mol) of 6-hydroxyhexyl 3,5-dinitrobenzoate, 3.44 g (0.0145 Mol) of 4-ethylcarbonatecinnamic acid, 0.177 g (0.0015 Mol) of 4-Dimethylaminopyridine are dissolved in 40 ml of dichloromethane. 3.04 g (0.0159 Mol) of N-(3-Dimethylaminopropyl)-N'-ethylcarbodiimide hydrochloride (EDC hydrochloride) are added at 0°C. The solution is stirred for 1 h at 0°C and allowed to stir at room temperature overnight. After 22 hours at room temperature the reaction mixture is partitioned between dichloromethane and water; the organic phase is washed repeatedly with water, dried over sodium sulphate, filtered and concentrated by rotary evaporation. The residue is dissolved ethyl acetate. The product is precipitated with Hexane at 0°C. The precipitated is filtrated and dried under vacuum overnight to give 4.2 g (55%) of 6-(((2E)-{4-[(ethoxycarbonyl)oxy]phenyl}prop-2-enoyl)oxy)hexyl 3,5-dinitrobenzoate as a light-yellow powder.

2.4 Preparation of 6-(((2E)-{4-hydroxyphenyl}prop-2-enoyl)oxy)hexyl 3,5-dinitrobenzoate



43.20 g (0.081 Mol) of 6-(((2E)-4-((ethoxycarbonyloxy)phenyl)prop-2-en-1-yl)oxy)hexyl
 3,5-dinitrobenzoate are dissolved in 66 ml (0.815 Mol) of pyridine and 400 ml of
 acetone at room temperature. 61 ml (0.815 Mol) of ammonium hydroxide solution 25%
 are added dropwise to the solution at room temperature. After 12h reaction, the
 mixture is thrown on water and acidified by the addition of HCl 25% (up to pH=3-4). A
 paste is obtained which is filtrated and dissolved in ethyl acetate and extracted with
 water. The organic phase is dried with sodium sulfate, filtrated, concentrated by rotary
 evaporation. Filtration of the residue over silica gel with tert-Butyl methyl ether as
 eluant and crystallization of the residue in 200 ml of ethyl acetate and 1200 ml of
 hexane at 0°C give 15.84 g of 6-(((2E)-4-(4-hydroxyphenyl)prop-2-en-1-yl)oxy)hexyl 3,5-
 dinitrobenzoate as yellow crystals.


2.5 Preparation of 6-(((2E)-3-(4-((4-butylcyclohexyl)carbonyloxy)phenyl)prop-2-en-1-yl)oxy)hexyl 3,5-dinitrobenzoate



6.94 g (0.035 Mol) 4-pentylcyclohexanecarboxylic acid of are suspended in
 100 ml of dichloromethane. 0.42 g (0.0035 Mol) of 4-Dimethylaminopyridine are added
 at room temperature. 7.98 g (0.04163 Mol) of N-(3-Dimethylaminopropyl)-N'-
 ethylcarbodiimide hydrochloride (EDC hydrochloride) are added at 0°C. The solution is
 stirred for 1 h at 0°C. 15.90g (0.0347 Mol) of 6-(((2E)-4-(4-hydroxyphenyl)prop-2-
 en-1-yl)oxy)hexyl 3,5-dinitrobenzoate dissolved in 50 ml of dichloromethane are added
 dropwise to the solution at 0°C and allowed to stir at room temperature overnight. After
 22 hours at room temperature the reaction mixture is partitioned between

dichloromethane and water. The mixture is acidified with HCl 25%. The organic phase is washed repeatedly with water, dried over sodium sulphate, filtered and concentrated by rotary evaporation. Chromatography of the residue on 600 g silica gel using toluene:ethyl acetate(99:1) as eluant and crystallization from ethyl acetate/hexane (1:2) yielded 6-[[[(2E)-3-{4-[[4-(4-pentylcyclohexyl)carbonyl]oxy}phenyl]prop-2-enoyl]oxy]]hexyl 3,5-dinitrobenzoate.

2.6 Preparation of 6-[[[(2E)-3-{4-[[4-(4-pentylcyclohexyl)carbonyl]oxy}phenyl]prop-2-enoyl]oxy]]hexyl 3,5-diaminobenzoate



17.24 g (0.027 Mol) of 6-[[[(2E)-3-{4-[[4-(4-pentylcyclohexyl)carbonyl]oxy}phenyl]prop-2-enoyl]oxy]]hexyl 3,5-dinitrobenzoate are dissolved in a mixture of 350 ml of N,N-dimethylformamide and 25 ml water. 44.28 g (0.164 Mol) ferric chloride hexahydrate are added. 17.85 g (0.273 Mol) Zinc powder are added portionwise within 40 min. The mixture is allowed to react for 2 hours. The reaction mixture is then partitioned between ethyl acetate and water and filtered. The organic phase is washed repeatedly with water, dried over sodium sulfate, filtered and concentrated by rotary evaporation. Chromatography of the residue on 400 g silica gel using toluene:ethyl acetate(2:1) as eluant yielded 6-[[[(2E)-3-{4-[[4-(4-pentylcyclohexyl)carbonyl]oxy}phenyl]prop-2-enoyl]oxy]]hexyl 3,5-diaminobenzoate.

The following diamines are synthesized in an analogous manner:

2-[[[(2E)-3-{4-[[4-(4-ethylcyclohexyl)carbonyl]oxy}phenyl]prop-2-enoyl]oxy]]ethyl 3,5-diaminobenzoate

3-[[[(2E)-3-{4-[[4-(4-ethylcyclohexyl)carbonyl]oxy}phenyl]prop-2-enoyl]oxy]]propyl 3,5-diaminobenzoate

4-[[[(2E)-3-{4-[[4-(4-ethylcyclohexyl)carbonyl]oxy}phenyl]prop-2-enoyl]oxy]]butyl 3,5-diaminobenzoate

- 6-((((2E)-3-{4-(((4-ethylcyclohexyl)carbonyl)oxy)}phenyl}prop-2-enoyl)oxy))hexyl 3,5-diaminobenzoate
- 11-((((2E)-3-{4-(((4-ethylcyclohexyl)carbonyl)oxy)}phenyl}prop-2-enoyl)oxy))undecyl 3,5-diaminobenzoate
- 5 2-((((2E)-3-{4-(((4-propylcyclohexyl)carbonyl)oxy)}phenyl}prop-2-enoyl)oxy))ethyl 3,5-diaminobenzoate
- 3-((((2E)-3-{4-(((4-propylcyclohexyl)carbonyl)oxy)}phenyl}prop-2-enoyl)oxy))propyl 3,5-diaminobenzoate
- 4-((((2E)-3-{4-(((4-propylcyclohexyl)carbonyl)oxy)}phenyl}prop-2-enoyl)oxy))butyl 3,5-diaminobenzoate
- 10 6-((((2E)-3-{4-(((4-propylcyclohexyl)carbonyl)oxy)}phenyl}prop-2-enoyl)oxy))hexyl 3,5-diaminobenzoate
- 8-((((2E)-3-{4-(((4-propylcyclohexyl)carbonyl)oxy)}phenyl}prop-2-enoyl)oxy))octyl 3,5-diaminobenzoate
- 15 2-((((2E)-3-{4-(((4-prop-2-enylcyclohexyl)carbonyl)oxy)}phenyl}prop-2-enoyl)oxy))ethyl 3,5-diaminobenzoate
- 3-((((2E)-3-{4-(((4-prop-2-enylcyclohexyl)carbonyl)oxy)}phenyl}prop-2-enoyl)oxy))propyl 3,5-diaminobenzoate
- 4-((((2E)-3-{4-(((4-prop-2-enylcyclohexyl)carbonyl)oxy)}phenyl}prop-2-enoyl)oxy))butyl 3,5-diaminobenzoate
- 20 6-((((2E)-3-{4-(((4-prop-2-enylcyclohexyl)carbonyl)oxy)}phenyl}prop-2-enoyl)oxy))hexyl 3,5-diaminobenzoate
- 11-((((2E)-3-{4-(((4-prop-2-enylcyclohexyl)carbonyl)oxy)}phenyl}prop-2-enoyl)oxy))undecyl 3,5-diaminobenzoate
- 25 2-((((2E)-3-{4-(((4-trifluoromethylcyclohexyl)carbonyl)oxy)}phenyl}prop-2-enoyl)oxy))ethyl 3,5-diaminobenzoate
- 3-((((2E)-3-{4-(((4-trifluoromethylcyclohexyl)carbonyl)oxy)}phenyl}prop-2-enoyl)oxy))propyl 3,5-diaminobenzoate
- 4-((((2E)-3-{4-(((4-trifluoromethylcyclohexyl)carbonyl)oxy)}phenyl}prop-2-enoyl)oxy))butyl 3,5-diaminobenzoate
- 30 6-((((2E)-3-{4-(((4-trifluoromethylcyclohexyl)carbonyl)oxy)}phenyl}prop-2-enoyl)oxy))hexyl 3,5-diaminobenzoate
- 11-((((2E)-3-{4-(((4-trifluoromethylcyclohexyl)carbonyl)oxy)}phenyl}prop-2-enoyl)oxy))undecyl 3,5-diaminobenzoate

- 2-((((2E)-3-{4-(((4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl]oxy})ethyl 3,5-diaminobenzoate
- 3-((((2E)-3-{4-(((4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl]oxy})propyl 3,5-diaminobenzoate
- 5 4-((((2E)-3-{4-(((4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl]oxy})butyl 3,5-diaminobenzoate
- 6-((((2E)-3-{4-(((4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl]oxy})hexyl 3,5-diaminobenzoate
- 8-((((2E)-3-{4-(((4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl]oxy})octyl 3,5-diaminobenzoate
- 10 2-((((2E)-3-{4-(((4-(4,4,4-trifluorobutoxy)cyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl]oxy})ethyl 3,5-diaminobenzoate
- 3-((((2E)-3-{4-(((4-(4,4,4-trifluorobutoxy)cyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl]oxy})propyl 3,5-diaminobenzoate
- 15 4-((((2E)-3-{4-(((4-(4,4,4-trifluorobutoxy)cyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl]oxy})butyl 3,5-diaminobenzoate
- 6-((((2E)-3-{4-(((4-(4,4,4-trifluorobutoxy)cyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl]oxy})hexyl 3,5-diaminobenzoate
- 8-((((2E)-3-{4-(((4-(4,4,4-trifluorobutoxy)cyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl]oxy})octyl 3,5-diaminobenzoate
- 20 2-((((2E)-3-{4-(((4-ethylcyclohexyl)methoxy}phenyl)prop-2-enoyl]oxy})ethyl 3,5-diaminobenzoate
- 3-((((2E)-3-{4-(((4-ethylcyclohexyl)methoxy}phenyl)prop-2-enoyl]oxy})propyl 3,5-diaminobenzoate
- 25 4-((((2E)-3-{4-(((4-ethylcyclohexyl)methoxy}phenyl)prop-2-enoyl]oxy})butyl 3,5-diaminobenzoate
- 6-((((2E)-3-{4-(((4-ethylcyclohexyl)methoxy}phenyl)prop-2-enoyl]oxy})hexyl 3,5-diaminobenzoate
- 30 11-((((2E)-3-{4-(((4-ethylcyclohexyl)methoxy}phenyl)prop-2-enoyl]oxy})undecyl 3,5-diaminobenzoate
- 2-((((2E)-3-{4-(((4-propylcyclohexyl)methoxy}phenyl)prop-2-enoyl]oxy})ethyl 3,5-diaminobenzoate

- 3-[[[(2E)-3-{4-[(4-propylcyclohexyl)methoxy]phenyl}prop-2-enoyl)oxy]]propyl 3,5-diaminobenzoate
- 4-[[[(2E)-3-{4-[(4-propylcyclohexyl)methoxy]phenyl}prop-2-enoyl)oxy]]butyl 3,5-diaminobenzoate
- 5 6-[[[(2E)-3-{4-[(4-propylcyclohexyl)methoxy]phenyl}prop-2-enoyl)oxy]]hexyl 3,5-diaminobenzoate
- 8-[[[(2E)-3-{4-[(4-propylcyclohexyl)methoxy]phenyl}prop-2-enoyl)oxy]]octyl 3,5-diaminobenzoate
- 2-[[[(2E)-3-{4-[(4-prop-2-enylcyclohexyl)methoxy]phenyl}prop-2-enoyl)oxy]]ethyl 3,5-diaminobenzoate
- 10 3-[[[(2E)-3-{4-[(4-prop-2-enylcyclohexyl)methoxy]phenyl}prop-2-enoyl)oxy]]propyl 3,5-diaminobenzoate
- 4-[[[(2E)-3-{4-[(4-prop-2-enylcyclohexyl)methoxy]phenyl}prop-2-enoyl)oxy]]butyl 3,5-diaminobenzoate
- 15 6-[[[(2E)-3-{4-[(4-prop-2-enylcyclohexyl)methoxy]phenyl}prop-2-enoyl)oxy]]hexyl 3,5-diaminobenzoate
- 11-[[[(2E)-3-{4-[(4-prop-2-enylcyclohexyl)methoxy]phenyl}prop-2-enoyl)oxy]]undecyl 3,5-diaminobenzoate
- 2-[[[(2E)-3-{4-[(4-trifluoromethylcyclohexyl)methoxy]phenyl}prop-2-enoyl)oxy]]ethyl 3,5-diaminobenzoate
- 20 3-[[[(2E)-3-{4-[(4-trifluoromethylcyclohexyl)methoxy]phenyl}prop-2-enoyl)oxy]]propyl 3,5-diaminobenzoate
- 4-[[[(2E)-3-{4-[(4-trifluoromethylcyclohexyl)methoxy]phenyl}prop-2-enoyl)oxy]]butyl 3,5-diaminobenzoate
- 25 6-[[[(2E)-3-{4-[(4-trifluoromethylcyclohexyl)methoxy]phenyl}prop-2-enoyl)oxy]]hexyl 3,5-diaminobenzoate
- 11-[[[(2E)-3-{4-[(4-trifluoromethylcyclohexyl)methoxy]phenyl}prop-2-enoyl)oxy]]undecyl 3,5-diaminobenzoate
- 2-[[[(2E)-3-{4-[(4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)methoxy]phenyl}prop-2-enoyl)oxy]]ethyl 3,5-diaminobenzoate
- 30 3-[[[(2E)-3-{4-[(4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)methoxy]phenyl}prop-2-enoyl)oxy]]propyl 3,5-diaminobenzoate
- 4-[[[(2E)-3-{4-[(4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)methoxy]phenyl}prop-2-enoyl)oxy]]butyl 3,5-diaminobenzoate

6-[[[(2E)-3-{4-[(4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)methoxy]phenyl}prop-2-enoyl)oxy]]hexyl 3,5-diaminobenzoate

8-[[[(2E)-3-{4-[(4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)methoxy]phenyl}prop-2-enoyl)oxy]]octyl 3,5-diaminobenzoate

5 2-[[[(2E)-3-{4-[(4-(4,4,4-trifluorobutoxy)cyclohexyl)methoxy]phenyl}prop-2-enoyl)oxy]]ethyl 3,5-diaminobenzoate

3-[[[(2E)-3-{4-[(4-(4,4,4-trifluorobutoxy)cyclohexyl)methoxy]phenyl}prop-2-enoyl)oxy]]propyl 3,5-diaminobenzoate

10 4-[[[(2E)-3-{4-[(4-(4,4,4-trifluorobutoxy)cyclohexyl)methoxy]phenyl}prop-2-enoyl)oxy]]butyl 3,5-diaminobenzoate

6-[[[(2E)-3-{4-[(4-(4,4,4-trifluorobutoxy)cyclohexyl)methoxy]phenyl}prop-2-enoyl)oxy]]hexyl 3,5-diaminobenzoate

8-[[[(2E)-3-{4-[(4-(4,4,4-trifluorobutoxy)cyclohexyl)methoxy]phenyl}prop-2-enoyl)oxy]]octyl 3,5-diaminobenzoate

15


EXAMPLE 3

Synthesis

20 Preparation of 3,5-Diaminobenzyl (2E)-3-(4-[(4-pentylcyclohexyl)carbonyl]oxy)phenyl)acrylate


3.1 Preparation of 3,5-dinitrobenzyl (2E)-3-(4-[(4-pentylcyclohexyl)carbonyl]oxy)phenyl)acrylate

25



1.00 g (5.10 mmol) of 3,5-dinitrobenzylalcohol, 1.75 g (5.10 mmol) of (2E)-3-(4-((4-pentylcyclohexyl)carbonyl]oxy} phenyl)acrylic acid, 62 mg (0.51 mmol) of 4-Dimethylaminopyridine are dissolved in 10 ml of dichloromethane. 1.07 g (56.0 mmol) of N-(3-Dimethylaminopropyl)-N'-ethylcarbodiimide hydrochloride (EDC hydrochloride) are added at 0°C. The solution is stirred for 1 h at 0°C and allowed to stir at room temperature overnight. After 22 hours at room temperature the reaction mixture is partitioned between dichloromethane and water. The organic phase is washed repeatedly with water, dried over sodium sulphate, filtered and concentrated by rotary evaporation to yield 3,5-dinitrobenzyl (2E)-3-(4-((4-pentylcyclohexyl)carbonyl]oxy} phenyl)acrylate.

3.2 Preparation of 3,5-Diaminobenzyl (2E)-3-(4-((4-pentylcyclohexyl)carbonyl]oxy} phenyl)acrylate



4.80 g (9.2 mmol) of 3,5-dinitrobenzyl (2E)-3-(4-((4-pentylcyclohexyl)carbonyl]oxy} phenyl)acrylate are dissolved in a mixture of 55 ml of N,N-dimethylformamide and 6 ml water. 14.98 g (55.3 mmol) ferric chloride hexahydrate are added. 6.03 g (91.8 mmol) Zinc powder are added portionwise within 40 min. The mixture is allowed to react for 2 hours. The reaction mixture is then partitioned between ethyl acetate and water and filtered. The organic phase is washed repeatedly with water, dried over sodium sulfate, filtered and concentrated by rotary evaporation. Chromatography of the residue on 200 g silica gel using toluene:ethyl acetate(1:1) as eluant and crystallization from ethylacetate:hexane mixture yielded 3,5-Diaminobenzyl (2E)-3-(4-((4-pentylcyclohexyl)carbonyl]oxy} phenyl)acrylate.

The following diamines are synthesized in an analogous manner:

- 3,5-Diaminobenzyl (2E)-3-(4-{{(4-methylcyclohexyl)carbonyl}oxy}phenyl)acrylate
 3,5-Diaminobenzyl (2E)-3-(4-{{(4-ethylcyclohexyl)carbonyl}oxy}phenyl)acrylate
 5 3,5-Diaminobenzyl (2E)-3-(4-{{(4-propylcyclohexyl)carbonyl}oxy}phenyl)acrylate
 3,5-Diaminobenzyl (2E)-3-(4-{{(4-butylcyclohexyl)carbonyl}oxy}phenyl)acrylate
 3,5-Diaminobenzyl (2E)-3-(4-{{(4-pentylcyclohexyl)carbonyl}oxy}phenyl)acrylate
 3,5-Diaminobenzyl (2E)-3-(4-{{(4-hexylcyclohexyl)carbonyl}oxy}phenyl)acrylate
 3,5-Diaminobenzyl (2E)-3-(4-{{(4-heptylcyclohexyl)carbonyl}oxy}phenyl)acrylate
 10 3,5-Diaminobenzyl (2E)-3-(4-{{(4-octylcyclohexyl)carbonyl}oxy}phenyl)acrylate
 3,5-Diaminobenzyl (2E)-3-(4-{{(4-vinylcyclohexyl)carbonyl}oxy}phenyl)acrylate
 3,5-Diaminobenzyl (2E)-3-(4-{{(4-prop-2-enylcyclohexyl)carbonyl}oxy}phenyl)acrylate
 3,5-Diaminobenzyl (2E)-3-(4-{{(4-but-3-enylcyclohexyl)carbonyl}oxy}phenyl)acrylate
 3,5-Diaminobenzyl (2E)-3-(4-{{(4-pent-4-enylcyclohexyl)carbonyl}oxy}phenyl)acrylate
 15 3,5-Diaminobenzyl (2E)-3-(4-{{(4-hex-5-enylcyclohexyl)carbonyl}oxy}phenyl)acrylate
 3,5-Diaminobenzyl (2E)-3-(4-{{(4-hept-6-enylcyclohexyl)carbonyl}oxy}phenyl)acrylate
 3,5-Diaminobenzyl (2E)-3-(4-{{(4-oct-7-enylcyclohexyl)carbonyl}oxy}phenyl)acrylate
 3,5-Diaminobenzyl (2E)-3-(4-{{(4-methyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
 3,5-Diaminobenzyl (2E)-3-(4-{{(4-ethyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
 20 3,5-Diaminobenzyl (2E)-3-(4-{{(4-propyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
 3,5-Diaminobenzyl (2E)-3-(4-{{(4-butyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
 3,5-Diaminobenzyl (2E)-3-(4-{{(4-pentyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
 3,5-Diaminobenzyl (2E)-3-(4-{{(4-hexyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
 3,5-Diaminobenzyl (2E)-3-(4-{{(4-heptyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
 25 3,5-Diaminobenzyl (2E)-3-(4-{{(4-octyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
 3,5-Diaminobenzyl (2E)-3-(4-{{(4-allyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
 3,5-Diaminobenzyl (2E)-3-(4-{{(4-but-3-enyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
 3,5-Diaminobenzyl (2E)-3-(4-{{(4-pent-4-enyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
 30 3,5-Diaminobenzyl (2E)-3-(4-{{(4-hex-5-enyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
 3,5-Diaminobenzyl (2E)-3-(4-{{(4-hept-6-enyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
 3,5-Diaminobenzyl (2E)-3-(4-{{(4-oct-7-enyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate

- 3,5-Diaminobenzyl (2E) 3-(4-[(4-trifluoromethoxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 3,5-Diaminobenzyl (2E) 3-(4-[(4-(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl]oxy}phenyl)acrylate
- 5 3,5-Diaminobenzyl (2E) 3-(4-[(4-(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl]oxy}phenyl)acrylate
- 3,5-Diaminobenzyl (2E) 3-(4-[(4-(2,2,2-trifluoropropoxy)cyclohexyl)carbonyl]oxy}phenyl)acrylate
- 3,5-Diaminobenzyl (2E) 3-(4-[(4-(4,4,4-trifluorobutoxy)cyclohexyl)carbonyl]oxy}phenyl)acrylate
- 10 3,5-Diaminobenzyl (2E) 3-(4-[(4-(5,5,5-trifluoropentyloxy)cyclohexyl)carbonyl]oxy}phenyl)acrylate
- 3,5-Diaminobenzyl (2E) 3-(4-[(4-(4,4,5,5,5-pentafluoropentyloxy)cyclohexyl)carbonyl]oxy}phenyl)acrylate
- 15 3,5-Diaminobenzyl (2E) 3-(4-[(4-(1,1,2,2-tetrafluoroethoxy)cyclohexyl)carbonyl]oxy}phenyl)acrylate
- 3,5-Diaminobenzyl (2E) 3-(4-[(4-(1,1,2,2-tetrafluoropropoxy)cyclohexyl)carbonyl]oxy}phenyl)acrylate
- 20 3,5-Diaminobenzyl (2E) 3-(4-[(4-(4,4,5,5,6,6,6-heptafluorohexyloxy)cyclohexyl)carbonyl]oxy}phenyl)acrylate
- 3,5-Diaminobenzyl (2E) 3-(4-[(4-trifluoromethylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 3,5-Diaminobenzyl (2E) 3-(4-[(4-(2,2,2-trifluoropropyl)cyclohexyl)carbonyl]oxy}phenyl)acrylate
- 25 3,5-Diaminobenzyl (2E) 3-(4-[(4-(4,4,4-trifluorobutyl)cyclohexyl)carbonyl]oxy}phenyl)acrylate
- 3,5-Diaminobenzyl (2E) 3-(4-[(4-(5,5,5-trifluoropentyl)cyclohexyl)carbonyl]oxy}phenyl)acrylate
- 3,5-Diaminobenzyl (2E) 3-(4-[(4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)carbonyl]oxy}phenyl)acrylate
- 30 2,5-Diaminobenzyl (2E)-3-(4-[(4-methylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2,5-Diaminobenzyl (2E)-3-(4-[(4-ethylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2,5-Diaminobenzyl (2E)-3-(4-[(4-propylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2,5-Diaminobenzyl (2E)-3-(4-[(4-butylcyclohexyl)carbonyl]oxy}phenyl)acrylate

- 2,5-Diaminobenzyl (2E)-3-(4-{{(4-pentylcyclohexyl)carbonyl]oxy}phenyl)acrylate
 2,5-Diaminobenzyl (2E)-3-(4-{{(4-hexylcyclohexyl)carbonyl]oxy}phenyl)acrylate
 2,5-Diaminobenzyl (2E)-3-(4-{{(4-heptylcyclohexyl)carbonyl]oxy}phenyl)acrylate
 2,5-Diaminobenzyl (2E)-3-(4-{{(4-octylcyclohexyl)carbonyl]oxy}phenyl)acrylate
 5 2,5-Diaminobenzyl (2E)-3-(4-{{(4-vinylcyclohexyl)carbonyl]oxy}phenyl)acrylate
 2,5-Diaminobenzyl (2E)-3-(4-{{(4-prop-2-enylcyclohexyl)carbonyl]oxy}phenyl)acrylate
 2,5-Diaminobenzyl (2E)-3-(4-{{(4-but-3-enylcyclohexyl)carbonyl]oxy}phenyl)acrylate
 2,5-Diaminobenzyl (2E)-3-(4-{{(4-pent-4-enylcyclohexyl)carbonyl]oxy}phenyl)acrylate
 2,5-Diaminobenzyl (2E)-3-(4-{{(4-hex-5-enylcyclohexyl)carbonyl]oxy}phenyl)acrylate
 10 2,5-Diaminobenzyl (2E)-3-(4-{{(4-hept-6-enylcyclohexyl)carbonyl]oxy}phenyl)acrylate
 2,5-Diaminobenzyl (2E)-3-(4-{{(4-oct-7-enylcyclohexyl)carbonyl]oxy}phenyl)acrylate
 2,5-Diaminobenzyl (2E)-3-(4-{{(4-methyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
 2,5-Diaminobenzyl (2E)-3-(4-{{(4-ethyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
 2,5-Diaminobenzyl (2E)-3-(4-{{(4-propyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
 15 2,5-Diaminobenzyl (2E)-3-(4-{{(4-butyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
 2,5-Diaminobenzyl (2E)-3-(4-{{(4-pentyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
 2,5-Diaminobenzyl (2E)-3-(4-{{(4-hexyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
 2,5-Diaminobenzyl (2E)-3-(4-{{(4-heptyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
 2,5-Diaminobenzyl (2E)-3-(4-{{(4-octyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
 20 2,5-Diaminobenzyl (2E)-3-(4-{{(4-allyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
 2,5-Diaminobenzyl (2E)-3-(4-{{(4-but-3-enyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
 2,5-Diaminobenzyl (2E)-3-(4-{{(4-pent-4-enyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
 2,5-Diaminobenzyl (2E)-3-(4-{{(4-hex-5-enyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
 25 2,5-Diaminobenzyl (2E)-3-(4-{{(4-hept-6-enyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
 2,5-Diaminobenzyl (2E)-3-(4-{{(4-oct-7-enyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
 2,5-Diaminobenzyl (2E) 3-(4-{{(4-trifluoromethoxycyclohexyl)carbonyl]oxy}phenyl)acrylate
 30 2,5-Diaminobenzyl (2E) 3-(4-{{(4-(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl]oxy}phenyl)acrylate
 2,5-Diaminobenzyl (2E) 3-{4-[(4-(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl]oxy}phenyl}acrylate

- 2,5-Diaminobenzyl (2E) 3-{4-[(4-(2,2,2-trifluoropropoxy)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2,5-Diaminobenzyl (2E) 3-{4-[(4-(4,4,4-trifluorobutoxy)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 5 2,5-Diaminobenzyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyloxy)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2,5-Diaminobenzyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentoxy)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2,5-Diaminobenzyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoroethoxy)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 10 2,5-Diaminobenzyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoropropoxy)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2,5-Diaminobenzyl (2E) 3-{4-[(4-(4,4,5,5,6,6,6-heptafluorohexyloxy)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 15 2,5-Diaminobenzyl (2E) 3-{4-[(4-(4-trifluoromethylcyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2,5-Diaminobenzyl (2E) 3-{4-[(4-(2,2,2-trifluoropropyl)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2,5-Diaminobenzyl (2E) 3-{4-[(4-(4,4,4-trifluorobutyl)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 20 2,5-Diaminobenzyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyl)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2,5-Diaminobenzyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-[(4-methylcyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 25 2,4-Diaminobenzyl (2E)-3-(4-[(4-ethylcyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-[(4-propylcyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-[(4-butylcyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-[(4-pentylcyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-[(4-hexylcyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 30 2,4-Diaminobenzyl (2E)-3-(4-[(4-heptylcyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-[(4-octylcyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-[(4-vinylcyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-[(4-prop-2-enylcyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-[(4-but-3-enylcyclohexyl)carbonyl]}oxy}phenyl}acrylate

- 2,4-Diaminobenzyl (2E)-3-(4-{{(4-pent-4-enylcyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{{(4-hex-5-enylcyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{{(4-hept-6-enylcyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{{(4-oct-7-enylcyclohexyl)carbonyl}oxy}phenyl)acrylate
- 5 2,4-Diaminobenzyl (2E)-3-(4-{{(4-methyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{{(4-ethyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{{(4-propyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{{(4-butyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{{(4-pentyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
- 10 2,4-Diaminobenzyl (2E)-3-(4-{{(4-hexyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{{(4-heptyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{{(4-octyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{{(4-allyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{{(4-but-3-enyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
- 15 2,4-Diaminobenzyl (2E)-3-(4-{{(4-pent-4-enyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{{(4-hex-5-enyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{{(4-hept-6-enyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
- 20 2,4-Diaminobenzyl (2E)-3-(4-{{(4-oct-7-enyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2,4-Diaminobenzyl (2E) 3-(4-{{(4-trifluoromethoxycyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2,4-Diaminobenzyl (2E) 3-(4-{{(4-(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl}oxy}phenyl)acrylate
- 25 2,4-Diaminobenzyl (2E) 3-{4-[(4-(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2,4-Diaminobenzyl (2E) 3-{4-[(4-(2,2,2-trifluoropropoxy)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2,4-Diaminobenzyl (2E) 3-{4-[(4-(4,4,4-trifluorobutoxy)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 30 2,4-Diaminobenzyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyloxy)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2,4-Diaminobenzyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentoxy)cyclohexyl)carbonyl]}oxy}phenyl}acrylate

- 2,4-Diaminobenzyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoroethoxy)cyclohexyl)carbonyl]}oxy} phenyl}acrylate
- 2,4-Diaminobenzyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoropropoxy)cyclohexyl)carbonyl]}oxy} phenyl}acrylate
- 5 2,4-Diaminobenzyl (2E) 3-{4-[(4-(4,4,5,5,6,6,6-heptafluorohexyloxy)cyclohexyl)carbonyl]}oxy} phenyl}acrylate
- 2,4-Diaminobenzyl (2E) 3-(4-{[(4-trifluoromethylcyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2,4-Diaminobenzyl (2E) 3-{4-[(4-(2,2,2-trifluoropropyl)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 10 2,4-Diaminobenzyl (2E) 3-{4-[(4-(4,4,4-trifluorobutyl)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2,4-Diaminobenzyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyl)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2,4-Diaminobenzyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 15
- 3,5-Diaminobenzyl (2E)-3-(4-{[(4-methylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 3,5-Diaminobenzyl (2E)-3-(4-{[(4-ethylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 20 3,5-Diaminobenzyl (2E)-3-(4-{[(4-propylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 3,5-Diaminobenzyl (2E)-3-(4-{[(4-butylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 3,5-Diaminobenzyl (2E)-3-(4-{[(4-pentylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 3,5-Diaminobenzyl (2E)-3-(4-{[(4-hexylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 3,5-Diaminobenzyl (2E)-3-(4-{[(4-heptylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 25 3,5-Diaminobenzyl (2E)-3-(4-{[(4-octylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 3,5-Diaminobenzyl (2E)-3-(4-{[(4-vinylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 3,5-Diaminobenzyl (2E)-3-(4-{[(4-prop-2-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 3,5-Diaminobenzyl (2E)-3-(4-{[(4-but-3-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 3,5-Diaminobenzyl (2E)-3-(4-{[(4-pent-4-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 30 3,5-Diaminobenzyl (2E)-3-(4-{[(4-hex-5-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 3,5-Diaminobenzyl (2E)-3-(4-{[(4-hept-6-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 3,5-Diaminobenzyl (2E)-3-(4-{[(4-oct-7-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 3,5-Diaminobenzyl (2E)-3-(4-{[(4-methyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 3,5-Diaminobenzyl (2E)-3-(4-{[(4-ethyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate

- 3,5-Diaminobenzyl (2E)-3-(4-[[4-propyloxycyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 3,5-Diaminobenzyl (2E)-3-(4-[[4-butyloxycyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 3,5-Diaminobenzyl (2E)-3-(4-[[4-pentyloxycyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 3,5-Diaminobenzyl (2E)-3-(4-[[4-hexyloxycyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 5 3,5-Diaminobenzyl (2E)-3-(4-[[4-heptyloxycyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 3,5-Diaminobenzyl (2E)-3-(4-[[4-octyloxycyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 3,5-Diaminobenzyl (2E)-3-(4-[[4-allyloxycyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 3,5-Diaminobenzyl (2E)-3-(4-[[4-but-3-enyloxycyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 3,5-Diaminobenzyl (2E)-3-(4-[[4-pent-4-
- 10 enyloxycyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 3,5-Diaminobenzyl (2E)-3-(4-[[4-hex-5-
- enyloxycyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 3,5-Diaminobenzyl (2E)-3-(4-[[4-hept-6-
- enyloxycyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 15 3,5-Diaminobenzyl (2E)-3-(4-[[4-oct-7-enyloxycyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 3,5-Diaminobenzyl (2E) 3-(4-[[4-
- trifluoromethoxycyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 3,5-Diaminobenzyl (2E) 3-(4-[[4--(2,2,2-
- trifluoroethoxy)cyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 20 3,5-Diaminobenzyl (2E) 3-{4-[(4-(2,2,2-
- trifluoroethoxy)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 3,5-Diaminobenzyl (2E) 3-{4-[(4-(2,2,2-
- trifluoropropoxy)cyclohexyl]oxyl]carbonyl}phenyl}acrylate
- 3,5-Diaminobenzyl (2E) 3-{4-[(4-(4,4,4-
- 25 trifluorobutoxy)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 3,5-Diaminobenzyl (2E) 3-{4-[(4-(5,5,5-
- trifluoropentyloxy)cyclohexyl]oxyl]carbonyl}phenyl}acrylate
- 3,5-Diaminobenzyl (2E) 3-{4-[(4-(4,4,5,5,5-
- 30 pentafluoropentoxy)cyclohexyl]oxyl]carbonyl}phenyl}acrylate
- 3,5-Diaminobenzyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoroethoxy)cyclohexyl)carbonyl]oxy}
- phenyl}acrylate
- 3,5-Diaminobenzyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoropropoxy)cyclohexyl]oxyl]carbonyl}
- phenyl}acrylate

- 3,5-Diaminobenzyl (2E) 3-{4-[(4-(4,4,5,5,6,6,6-heptafluorohexyloxy)cyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 3,5-Diaminobenzyl (2E) 3-(4-[(4-trifluoromethylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 5 3,5-Diaminobenzyl (2E) 3-{4-[(4-(2,2,2-trifluoropropyl)cyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 3,5-Diaminobenzyl (2E) 3-{4-[(4-(4,4,4-trifluorobutyl)cyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 3,5-Diaminobenzyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyl)cyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 10 3,5-Diaminobenzyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2,5-Diaminobenzyl (2E)-3-(4-[(4-methylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2,5-Diaminobenzyl (2E)-3-(4-[(4-ethylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 15 2,5-Diaminobenzyl (2E)-3-(4-[(4-propylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2,5-Diaminobenzyl (2E)-3-(4-[(4-butylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2,5-Diaminobenzyl (2E)-3-(4-[(4-pentylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2,5-Diaminobenzyl (2E)-3-(4-[(4-hexylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2,5-Diaminobenzyl (2E)-3-(4-[(4-heptylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 20 2,5-Diaminobenzyl (2E)-3-(4-[(4-octylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2,5-Diaminobenzyl (2E)-3-(4-[(4-vinylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2,5-Diaminobenzyl (2E)-3-(4-[(4-prop-2-enylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2,5-Diaminobenzyl (2E)-3-(4-[(4-but-3-enylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2,5-Diaminobenzyl (2E)-3-(4-[(4-pent-4-enylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 25 2,5-Diaminobenzyl (2E)-3-(4-[(4-hex-5-enylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2,5-Diaminobenzyl (2E)-3-(4-[(4-hept-6-enylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2,5-Diaminobenzyl (2E)-3-(4-[(4-oct-7-enylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2,5-Diaminobenzyl (2E)-3-(4-[(4-methyloxycyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2,5-Diaminobenzyl (2E)-3-(4-[(4-ethyloxycyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 30 2,5-Diaminobenzyl (2E)-3-(4-[(4-propyloxycyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2,5-Diaminobenzyl (2E)-3-(4-[(4-butyloxycyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2,5-Diaminobenzyl (2E)-3-(4-[(4-pentyloxycyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2,5-Diaminobenzyl (2E)-3-(4-[(4-hexyloxycyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2,5-Diaminobenzyl (2E)-3-(4-[(4-heptyloxycyclohexyl)oxyl]carbonyl}phenyl}acrylate

- 2,5-Diaminobenzyl (2E)-3-(4-{{(4-octyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
 2,5-Diaminobenzyl (2E)-3-(4-{{(4-allyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
 2,5-Diaminobenzyl (2E)-3-(4-{{(4-but-3-enyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
 2,5-Diaminobenzyl (2E)-3-(4-{{(4-pent-4-
 5 enyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
 2,5-Diaminobenzyl (2E)-3-(4-{{(4-hex-5-
 enyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
 2,5-Diaminobenzyl (2E)-3-(4-{{(4-hept-6-
 enyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
 10 2,5-Diaminobenzyl (2E)-3-(4-{{(4-oct-7-enyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
 2,5-Diaminobenzyl (2E) 3-(4-{{(4-
 trifluoromethoxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
 2,5-Diaminobenzyl (2E) 3-(4-{{(4--(2,2,2-
 trifluoroethoxy)cyclohexyl)oxyl}carbonyl}phenyl)acrylate
 15 2,5-Diaminobenzyl (2E) 3-{4-[(4-(2,2,2-
 trifluoroethoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
 2,5-Diaminobenzyl (2E) 3-{4-[(4-(2,2,2-
 trifluoropropoxy)cyclohexyl)oxyl]]carbonyl}phenyl}acrylate
 2,5-Diaminobenzyl (2E) 3-{4-[(4-(4,4,4-
 20 trifluorobutoxy)cyclohexyl)oxyl]]carbonyl}phenyl}acrylate
 2,5-Diaminobenzyl (2E) 3-{4-[(4-(5,5,5-
 trifluoropentyloxy)cyclohexyl)oxyl]]carbonyl}phenyl}acrylate
 2,5-Diaminobenzyl (2E) 3-{4-[(4-(4,4,5,5,5-
 pentafluoropentyloxy)cyclohexyl)oxyl]]carbonyl}phenyl}acrylate
 25 2,5-Diaminobenzyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoroethoxy)cyclohexyl)carbonyl]]oxy}
 phenyl}acrylate
 2,5-Diaminobenzyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoropropoxy)cyclohexyl)oxyl]]carbonyl}
 phenyl}acrylate
 2,5-Diaminobenzyl (2E) 3-{4-[(4-(4,4,5,5,6,6,6-
 30 heptafluorohexyloxy)cyclohexyl)oxyl]]carbonyl} phenyl}acrylate
 2,5-Diaminobenzyl (2E) 3-(4-{{(4-
 trifluoromethylcyclohexyl)oxyl}carbonyl}phenyl)acrylate
 2,5-Diaminobenzyl (2E) 3-{4-[(4-(2,2,2-
 trifluoropropyl)cyclohexyl)oxyl]]carbonyl}phenyl}acrylate

- 2,5-Diaminobenzyl (2E) 3-{4-[(4-(4,4,4-trifluorobutyl)cyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2,5-Diaminobenzyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyl)cyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 5 2,5-Diaminobenzyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{[(4-methylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{[(4-ethylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{[(4-propylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 10 2,4-Diaminobenzyl (2E)-3-(4-{[(4-butylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{[(4-pentylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{[(4-hexylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{[(4-heptylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{[(4-octylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 15 2,4-Diaminobenzyl (2E)-3-(4-{[(4-vinylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{[(4-prop-2-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{[(4-but-3-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{[(4-pent-4-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{[(4-hex-5-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 20 2,4-Diaminobenzyl (2E)-3-(4-{[(4-hept-6-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{[(4-oct-7-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{[(4-methyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{[(4-ethyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{[(4-propyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 25 2,4-Diaminobenzyl (2E)-3-(4-{[(4-butyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{[(4-pentyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{[(4-hexyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{[(4-heptyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{[(4-octyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 30 2,4-Diaminobenzyl (2E)-3-(4-{[(4-allyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{[(4-but-3-enyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-{[(4-pent-4-enyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate

- 2,4-Diaminobenzyl (2E)-3-(4-[(4-hex-5-enyloxy)cyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 2,4-Diaminobenzyl (2E)-3-(4-[(4-hept-6-enyloxy)cyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 5 2,4-Diaminobenzyl (2E)-3-(4-[(4-oct-7-enyloxy)cyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 2,4-Diaminobenzyl (2E) 3-(4-[(4-trifluoromethoxycyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 2,4-Diaminobenzyl (2E) 3-(4-[(4-(2,2,2-trifluoroethoxy)cyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 10 2,4-Diaminobenzyl (2E) 3-{4-[(4-(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 2,4-Diaminobenzyl (2E) 3-{4-[(4-(2,2,2-trifluoropropoxy)cyclohexyl]oxyl]]carbonyl}phenyl}acrylate
- 2,4-Diaminobenzyl (2E) 3-{4-[(4-(4,4,4-trifluorobutoxy)cyclohexyl]oxyl]]carbonyl}phenyl}acrylate
- 15 2,4-Diaminobenzyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyloxy)cyclohexyl]oxyl]]carbonyl}phenyl}acrylate
- 2,4-Diaminobenzyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentoxy)cyclohexyl]oxyl]]carbonyl}phenyl}acrylate
- 20 2,4-Diaminobenzyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoroethoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 2,4-Diaminobenzyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoropropoxy)cyclohexyl]oxyl]]carbonyl}phenyl}acrylate
- 2,4-Diaminobenzyl (2E) 3-{4-[(4-(4,4,5,5,6,6,6-heptafluorohexyloxy)cyclohexyl]oxyl]]carbonyl}phenyl}acrylate
- 25 2,4-Diaminobenzyl (2E) 3-(4-[(4-trifluoromethylcyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 2,4-Diaminobenzyl (2E) 3-{4-[(4-(2,2,2-trifluoropropyl)cyclohexyl]oxyl]]carbonyl}phenyl}acrylate
- 30 2,4-Diaminobenzyl (2E) 3-{4-[(4-(4,4,4-trifluorobutyl)cyclohexyl]oxyl]]carbonyl}phenyl}acrylate
- 2,4-Diaminobenzyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyl)cyclohexyl]oxyl]]carbonyl}phenyl}acrylate


2,4-Diaminobenzyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)oxy]}carbonyl}phenyl}acrylate

EXAMPLE 4

5 Synthesis


Preparation of 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{[(4-butylcyclohexyl)carbonyl]oxy}phenyl)acrylate

10 4.1 Preparation of 2-(2,4-dinitrophenyl)ethanol




22.6 g (100 mmol) 2,4-dinitrophenylacetic acid are dissolved in 150 ml tetrahydrofuran and added dropwise in a the course of 2 hours to 300 ml (300 mmol) of a borane-tetrahydrofuran complex 1.0 M solution in tetrahydrofuran. After 3 hours at 25°C, 200 ml water are carefully added. The reaction mixture is then partitioned between ethyl acetate and water; the organic phase was washed repeatedly with water, dried over sodium sulfate, filtered and concentrated by rotary evaporation. Chromatography of the residue on 400 g silica gel using toluene:ethyl acetate 1:1 as eluant and crystallization form ethylacetate:hexane mixture to yield 20.7 g (98%) of 2-(2,4-dinitrophenyl)ethanol as yellowish crystals.

25 4.2 Preparation of 2-(2,4-Dinitrophenyl)ethyl (2E)-3-(4-{[(4-butylcyclohexyl)carbonyl]oxy}phenyl)acrylate



6.67 g (20.19 mmol) of (2E)-3-(4-[[4-butylcyclohexyl]carbonyl]oxy} phenyl)acrylic acid are dissolved in 50 ml of toluene. 2.20 ml (30.3 mmol) of thionylchloride are added. The solution is stirred for 1 h at 80°C. the excess auf thionylchloride was removed bei distillation at 150°C. At 60°C, 4.28 g (20.19 mmol) of 2-(2,4-dinitrophenyl)ethanol, 250 mg (2.02 mmol) of 4-Dimethylaminopyridine and 6.5 ml pyridine were added. The mixture was allowed to react at 60°C overnight. The reaction mixture is partitioned between ethyl acetate and Ice water. The mixture is acidified by the addition of HCl 25% (up to pH=1). The organic phase is washed repeatedly with water, dried over sodium sulphate, filtered and concentrated by rotary evaporation. Chromatography of the residue on 500 g silica gel using toluene:ethyl acetate 9:1 as eluant and crystallization form ethylacetate:hexane mixture yielded 6.14 g of 2-(2,4-Dinitrophenyl)ethyl (2E)-3-(4-[[4-butylcyclohexyl) carbonyl]oxy}phenyl)acrylate as yellowish crystals.

4.3 Preparation of 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-[[4-butylcyclohexyl) carbonyl]oxy}phenyl)acrylate



4.39 g (8.38 mmol) of 2-(2,4-Dinitrophenyl)ethyl (2E)-3-(4-[[4-butylcyclohexyl) carbonyl]oxy}phenyl)acrylate are dissolved in a mixture of 54 ml of N,N-dimethylformamide and 6 ml water. 13.9 g (51.4 mmol) ferric chloride hexahydrate are added. 5.60 g (85.7 mmol) Zinc powder are added portionwise within 60 min. The mixture is allowed to react for 2 hours. The reaction mixture is then partitioned between ethyl acetate and water and filtered. The organic phase is washed repeatedly with water, dried over sodium sulfate, filtered and concentrated by rotary evaporation. Filtration of the residue on 200 g silica gel using toluene:ethyl acetate(1:3) as eluant and crystallization form ethylacetate:hexane mixture yielded 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-[[4-butylcyclohexyl)carbonyl]oxy}phenyl)acrylate as yellowish crystals

The following diamines are synthesized in an analogous manner:

- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-methylcyclohexyl)carbonyl}oxy}phenyl)acrylate
- 5 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-ethylcyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-propylcyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-pentylcyclohexyl)carbonyl}oxy}phenyl)acrylate
- 10 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-pentylcyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-hexylcyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-heptylcyclohexyl)carbonyl}oxy}phenyl)acrylate
- 15 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-octylcyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-vinylcyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-prop-2-enylcyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-but-3-enylcyclohexyl)carbonyl}oxy}phenyl)acrylate
- 20 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-pent-4-enylcyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-hex-5-enylcyclohexyl)carbonyl}oxy}phenyl)acrylate
- 25 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-hept-6-enylcyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-oct-7-enylcyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-methyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
- 30 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-ethyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-propyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate

- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-[(4-butylloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-[(4-pentylloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 5 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-[(4-hexylloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-[(4-heptyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-[(4-octylloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 10 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-[(4-allyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-[(4-but-3-enylloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 15 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-[(4-pent-4-enylloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-[(4-hex-5-enylloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-[(4-hept-6-enylloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 20 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-[(4-oct-7-enylloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E) 3-(4-[(4-trifluoromethoxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 25 2-(2,4-Diaminophenyl)ethyl (2E) 3-(4-[(4--(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E) 3-(4-[(4-(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl])oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E) 3-(4-[(4-(2,2,2-trifluoropropoxy)cyclohexyl)carbonyl])oxy}phenyl)acrylate
- 30 2-(2,4-Diaminophenyl)ethyl (2E) 3-(4-[(4-(4,4,4-trifluorobutoxy)cyclohexyl)carbonyl])oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E) 3-(4-[(4-(5,5,5-trifluoropentyl)oxy)cyclohexyl)carbonyl])oxy}phenyl)acrylate

- 2-(2,4-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentoxy)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoroethoxy)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 5 2-(2,4-Diaminophenyl)ethyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoropropoxy)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,5,5,6,6,6-heptafluorohexyloxy)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E) 3-{4-[(4-trifluoromethylcyclohexyl)carbonyl]oxy}phenyl}acrylate
- 10 2-(2,4-Diaminophenyl)ethyl (2E) 3-{4-[(4-(2,2,2-trifluoropropyl)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,4-trifluorobutyl)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 15 2-(2,4-Diaminophenyl)ethyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyl)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-methylcyclohexyl)carbonyl]oxy}phenyl}acrylate
- 20 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-ethylcyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-propylcyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-butylcyclohexyl)carbonyl]oxy}phenyl}acrylate
- 25 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-pentylcyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-hexylcyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-heptylcyclohexyl)carbonyl]oxy}phenyl}acrylate
- 30 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-octylcyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-vinylcyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-prop-2-enylcyclohexyl)carbonyl]oxy}phenyl}acrylate

2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-but-3-
enylcyclohexyl)carbonyl}oxy}phenyl)acrylate

2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-pent-4-
enylcyclohexyl)carbonyl}oxy}phenyl)acrylate

5 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-hex-5-
enylcyclohexyl)carbonyl}oxy}phenyl)acrylate

2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-hept-6-
enylcyclohexyl)carbonyl}oxy}phenyl)acrylate

10 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-oct-7-
enylcyclohexyl)carbonyl}oxy}phenyl)acrylate

2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-
methyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate

2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-
ethyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate

15 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-
propyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate

2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-
butyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate

20 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-
pentyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate

2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-
hexyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate

2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-
heptyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate

25 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-
octyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate

2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-
allyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate

30 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-but-3-
enyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate

2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-pent-4-
enyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate

2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-hex-5-
enyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate

- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-hept-6-enyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-oct-7-enyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 5 2-(3,5-Diaminophenyl)ethyl (2E) 3-(4-[(4-trifluoromethoxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E) 3-(4-[(4-(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 10 2-(3,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(2,2,2-trifluoropropoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,4-trifluorobutoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 15 2-(3,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyloxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoroethoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 20 2-(3,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoropropoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,5,5,6,6,6-heptafluorohexyloxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 25 2-(3,5-Diaminophenyl)ethyl (2E) 3-(4-[(4-trifluoromethylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(2,2,2-trifluoropropyl)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,4-trifluorobutyl)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 30 2-(3,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyl)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)carbonyl]]oxy}phenyl}acrylate

- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-methylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-ethylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-propylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 5 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-butylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-pentylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-hexylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 10 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-heptylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-octylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-vinylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-prop-2-enylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 15 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-but-3-enylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-pent-4-enylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 20 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-hex-5-enylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-hept-6-enylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-oct-7-enylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 25 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-methyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-ethyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 30 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-propyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-butyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate

- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-pentyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-hexyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 5 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-heptyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-octyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-allyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 10 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-but-3-enyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-pent-4-enyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 15 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-hex-5-enyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-hept-6-enyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-oct-7-enyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 20 2-(2,5-Diaminophenyl)ethyl (2E) 3-(4-[(4-trifluoromethoxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E) 3-(4-[(4--(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl]oxy}phenyl)acrylate
- 25 2-(2,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(2,2,2-trifluoropropoxy)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(-4,4,4-trifluorobutoxy)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 30 2-(2,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyloxy)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentoxy)cyclohexyl)carbonyl]oxy}phenyl}acrylate

- 2-(2,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoroethoxy)cyclohexyl)carbonyl]oxy} phenyl}acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoropropoxy)cyclohexyl)carbonyl]oxy} phenyl}acrylate
- 5 2-(2,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,5,5,6,6,6-heptafluorohexyloxy)cyclohexyl)carbonyl]oxy} phenyl}acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E) 3-(4-{[(4-trifluoromethylcyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(2,2,2-trifluoropropyl)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 10 2-(2,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,4-trifluorobutyl)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyl)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 15 2-(2,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{[(4-methylcyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{[(4-ethylcyclohexyl)carbonyl]oxy}phenyl}acrylate
- 20 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{[(4-propylcyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{[(4-butylcyclohexyl)carbonyl]oxy}phenyl}acrylate
- 25 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{[(4-pentylcyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{[(4-hexylcyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{[(4-heptylcyclohexyl)carbonyl]oxy}phenyl}acrylate
- 30 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{[(4-octylcyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{[(4-vinylcyclohexyl)carbonyl]oxy}phenyl}acrylate

- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{{(4-prop-2-enylcyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{{(4-but-3-enylcyclohexyl)carbonyl}oxy}phenyl)acrylate
- 5 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{{(4-pent-4-enylcyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{{(4-hex-5-enylcyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{{(4-hept-6-enylcyclohexyl)carbonyl}oxy}phenyl)acrylate
- 10 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{{(4-oct-7-enylcyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{{(4-methyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
- 15 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{{(4-ethyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{{(4-propyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{{(4-butyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
- 20 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{{(4-pentyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{{(4-hexyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
- 25 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{{(4-heptyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{{(4-octyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{{(4-allyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
- 30 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{{(4-but-3-enyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{{(4-pent-4-enyloxycyclohexyl)carbonyl}oxy}phenyl)acrylate

- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-[(4-hex-5-enyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-[(4-hept-6-enyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 5 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-[(4-oct-7-enyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E) 3-(4-[(4-trifluoromethoxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E) 3-(4-[(4--(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl]oxy}phenyl)acrylate
- 10 2-(3,5-Diaminophenyl)propyl (2E) 3-{4-[(4-(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)propyl (2E) 3-{4-[(4-(2,2,2-trifluoropropoxy)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 15 2-(3,5-Diaminophenyl)propyl (2E) 3-{4-[(4-(4,4,4-trifluorobutoxy)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)propyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyloxy)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)propyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentoxy)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 20 2-(3,5-Diaminophenyl)propyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoroethoxy)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)propyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoropropoxy)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 25 2-(3,5-Diaminophenyl)propyl (2E) 3-{4-[(4-(4,4,5,5,6,6,6-heptafluorohexyloxy)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)propyl (2E) 3-(4-[(4-trifluoromethylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E) 3-{4-[(4-(2,2,2-trifluoropropyl)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 30 2-(3,5-Diaminophenyl)propyl (2E) 3-{4-[(4-(4,4,4-trifluorobutyl)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)propyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyl)cyclohexyl)carbonyl]oxy}phenyl}acrylate

- 2-(3,5-Diaminophenyl)propyl (2E)-3-{4-[(4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-methylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 5 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-ethylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-propylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-butylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-pentylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 10 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-hexylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-heptylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 15 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-octylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-vinylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-prop-2-enylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-but-3-enylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 20 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-pent-4-enylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-hex-5-enylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 25 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-hept-6-enylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-oct-7-enylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-methyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 30 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-ethyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-propyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate

- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-[(4-butylloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-[(4-pentylloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 5 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-[(4-hexylloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-[(4-heptyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-[(4-octylloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 10 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-[(4-allyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-[(4-but-3-enylloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 15 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-[(4-pent-4-enylloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-[(4-hex-5-enylloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-[(4-hept-6-enylloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 20 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-[(4-oct-7-enylloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E) 3-(4-[(4-trifluoromethoxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 25 2-(3,5-Diaminophenyl)hexyl (2E) 3-(4-[(4-(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E) 3-{4-[(4-(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E) 3-{4-[(4-(2,2,2-trifluoropropoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 30 2-(3,5-Diaminophenyl)hexyl (2E) 3-{4-[(4-(4,4,4-trifluorobutoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyloxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate

- 2-(3,5-Diaminophenyl)hexyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentoxy)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoroethoxy)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 5 2-(3,5-Diaminophenyl)hexyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoropropoxy)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E) 3-{4-[(4-(4,4,5,5,6,6,6-heptafluorohexyloxy)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E) 3-(4-{[(4-trifluoromethylcyclohexyl)carbonyl]oxy}phenyl}acrylate
- 10 2-(3,5-Diaminophenyl)hexyl (2E) 3-{4-[(4-(2,2,2-trifluoropropyl)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E) 3-{4-[(4-(4,4,4-trifluorobutyl)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 15 2-(3,5-Diaminophenyl)hexyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyl)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 20 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-{[(4-methylcyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-{[(4-ethylcyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-{[(4-propylcyclohexyl)carbonyl]oxy}phenyl}acrylate
- 25 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-{[(4-pentylcyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-{[(4-pentylcyclohexyl)carbonyl]oxy}phenyl}acrylate
- 30 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-{[(4-hexylcyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-{[(4-heptylcyclohexyl)carbonyl]oxy}phenyl}acrylate

- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-[[4-octylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-[[4-vinylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 5 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-[[4-prop-2-enylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-[[4-but-3-enylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-[[4-pent-4-enylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 10 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-[[4-hex-5-enylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-[[4-hept-6-enylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 15 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-[[4-oct-7-enylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-[[4-methyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-[[4-ethyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 20 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-[[4-propyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-[[4-butyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 25 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-[[4-pentyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-[[4-hexyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-[[4-heptyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 30 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-[[4-octyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-[[4-allyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate

- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-[(4-but-3-enyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-[(4-pent-4-enyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 5 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-[(4-hex-5-enyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-[(4-hept-6-enyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E)-3-(4-[(4-oct-7-enyloxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 10 2-(2,4-Diaminophenyl)-2-methylpropyl (2E) 3-(4-[(4-trifluoromethoxycyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E) 3-(4-[(4--(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl]oxy}phenyl)acrylate
- 15 2-(2,4-Diaminophenyl)-2-methylpropyl (2E) 3-{4-[(4-(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E) 3-{4-[(4-(2,2,2-trifluoropropoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E) 3-{4-[(4-(4,4,4-trifluorobutoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 20 2-(2,4-Diaminophenyl)-2-methylpropyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyloxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 25 2-(2,4-Diaminophenyl)-2-methylpropyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoroethoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoropropoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E) 3-{4-[(4-(4,4,5,5,6,6,6-heptafluorohexyloxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 30 2-(2,4-Diaminophenyl)-2-methylpropyl (2E) 3-(4-[(4-trifluoromethylcyclohexyl)carbonyl]oxy}phenyl)acrylate
- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E) 3-{4-[(4-(2,2,2-trifluoropropyl)cyclohexyl)carbonyl]]oxy}phenyl}acrylate

- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E) 3-{4-[(4-(4,4,4-trifluorobutyl)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(2,4-Diaminophenyl)-2-methylpropyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyl)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 5 2-(2,4-Diaminophenyl)-2-methylpropyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)carbonyl]oxy}phenyl}acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{[(4-methylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 10 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{[(4-ethylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{[(4-propylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{[(4-pentylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 15 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{[(4-pentylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{[(4-hexylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{[(4-heptylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 20 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{[(4-octylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{[(4-vinylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{[(4-prop-2-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 25 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{[(4-but-3-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{[(4-pent-4-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{[(4-hex-5-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 30 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{[(4-hept-6-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{[(4-oct-7-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate

- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-methyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-ethyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 5 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-propyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-butyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-pentyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 10 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-hexyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-heptyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 15 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-octyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-allyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-but-3-enyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 20 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-pent-4-enyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-hex-5-enyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 25 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-hept-6-enyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-{{(4-oct-7-enyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E) 3-(4-{{(4-trifluoromethoxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 30 2-(2,4-Diaminophenyl)ethyl (2E) 3-(4-{{(4--(2,2,2-trifluoroethoxy)cyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E) 3-{4-[(4-(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl]}oxyphenyl}acrylate

- 2-(2,4-Diaminophenyl)ethyl (2E) 3-{4-[(4-(2,2,2-trifluoropropoxy)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,4-trifluorobutoxy)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 5 2-(2,4-Diaminophenyl)ethyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyloxy)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentoxy)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoroethoxy)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 10 2-(2,4-Diaminophenyl)ethyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoropropoxy)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,5,5,6,6,6-heptafluorohexyloxy)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 15 2-(2,4-Diaminophenyl)ethyl (2E) 3-{4-[(4-trifluoromethylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E) 3-{4-[(4-(2,2,2-trifluoropropyl)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,4-trifluorobutyl)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 20 2-(2,4-Diaminophenyl)ethyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyl)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2-(2,4-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 25 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-{[(4-methylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-{[(4-ethylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-{[(4-propylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 30 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-{[(4-butylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-{[(4-pentylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-{[(4-hexylcyclohexyl)oxyl]carbonyl}phenyl}acrylate

- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-heptylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-octylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-vinylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 5 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-prop-2-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-but-3-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-pent-4-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 10 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-hex-5-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-hept-6-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 15 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-oct-7-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-methyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-ethyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 20 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-propyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-butyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 25 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-pentyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-hexyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-heptyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 30 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-octyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-allyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate

- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-but-3-enyloxy)cyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-pent-4-enyloxy)cyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 5 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-hex-5-enyloxy)cyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-hept-6-enyloxy)cyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E)-3-(4-[(4-oct-7-enyloxy)cyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 10 2-(3,5-Diaminophenyl)ethyl (2E) 3-(4-[(4-trifluoromethoxycyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E) 3-(4-[(4--(2,2,2-trifluoroethoxy)cyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 15 2-(3,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(2,2,2-trifluoropropoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,4-trifluorobutoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 20 2-(3,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyloxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 25 2-(3,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoroethoxy)cyclohexyl)carbonyl]]oxy} phenyl}acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoropropoxy)cyclohexyl)carbonyl]]oxy} phenyl}acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,5,5,6,6,6-heptafluorohexyloxy)cyclohexyl)carbonyl]]oxy} phenyl}acrylate
- 30 2-(3,5-Diaminophenyl)ethyl (2E) 3-(4-[(4-trifluoromethyl)cyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(2,2,2-trifluoropropyl)cyclohexyl)carbonyl]]oxy}phenyl}acrylate

- 2-(3,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,4-trifluorobutyl)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyl)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 5 2-(3,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{[(4-methylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{[(4-ethylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 10 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{[(4-propylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{[(4-butylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{[(4-pentylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 15 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{[(4-hexylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{[(4-heptylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{[(4-octylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 20 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{[(4-vinylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{[(4-prop-2-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{[(4-but-3-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 25 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{[(4-pent-4-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{[(4-hex-5-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{[(4-hept-6-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 30 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{[(4-oct-7-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{[(4-methyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate

- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-ethyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-propyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 5 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-butyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-pentyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-hexyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 10 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-heptyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-octyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 15 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-allyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-but-3-enyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-pent-4-enyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 20 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-hex-5-enyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-hept-6-enyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 25 2-(2,5-Diaminophenyl)ethyl (2E)-3-(4-{{(4-oct-7-enyloxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E) 3-(4-{{(4-trifluoromethoxycyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E) 3-(4-{{(4--(2,2,2-trifluoroethoxy)cyclohexyl)oxyl}carbonyl}phenyl)acrylate
- 30 2-(2,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(2,2,2-trifluoropropoxy)cyclohexyl)carbonyl]}oxy}phenyl}acrylate

- 2-(2,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,4-trifluorobutoxy)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyloxy)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 5 2-(2,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentoxy)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoroethoxy)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoropropoxy)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 10 2-(2,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,5,5,6,6,6-heptafluorohexyloxy)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E) 3-(4-{[(4-trifluoromethylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 15 2-(2,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(2,2,2-trifluoropropyl)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,4-trifluorobutyl)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2-(2,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyl)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 20 2-(2,5-Diaminophenyl)ethyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)carbonyl]}oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{[(4-methylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 25 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{[(4-ethylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{[(4-propylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{[(4-butylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 30 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{[(4-pentylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-{[(4-hexylcyclohexyl)oxyl]carbonyl}phenyl}acrylate

- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-[(4-heptylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-[(4-octylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 5 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-[(4-vinylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-[(4-prop-2-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-[(4-but-3-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 10 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-[(4-pent-4-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-[(4-hex-5-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 15 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-[(4-hept-6-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-[(4-oct-7-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-[(4-methyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 20 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-[(4-ethyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-[(4-propyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 25 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-[(4-butyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-[(4-pentyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-[(4-hexyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 30 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-[(4-heptyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-[(4-octyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate

- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-[(4-allyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-[(4-but-3-enyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 5 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-[(4-pent-4-enyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-[(4-hex-5-enyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-[(4-hept-6-enyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 10 2-(3,5-Diaminophenyl)propyl (2E)-3-(4-[(4-oct-7-enyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E) 3-(4-[(4-trifluoromethoxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 15 2-(3,5-Diaminophenyl)propyl (2E) 3-(4-[(4--(2,2,2-trifluoroethoxy)cyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E) 3-(4-[(4-(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl]]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E) 3-(4-[(4-(2,2,2-trifluoropropoxy)cyclohexyl)carbonyl]]oxy}phenyl)acrylate
- 20 2-(3,5-Diaminophenyl)propyl (2E) 3-(4-[(4-(4,4,4-trifluorobutoxy)cyclohexyl)carbonyl]]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E) 3-(4-[(4-(5,5,5-trifluoropentyloxy)cyclohexyl)carbonyl]]oxy}phenyl)acrylate
- 25 2-(3,5-Diaminophenyl)propyl (2E) 3-(4-[(4-(4,4,5,5,5-pentafluoropentoxy)cyclohexyl)carbonyl]]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E) 3-(4-[(4-(1,1,2,2-tetrafluoroethoxy)cyclohexyl)carbonyl]]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E) 3-(4-[(4-(1,1,2,2-tetrafluoropropoxy)cyclohexyl)carbonyl]]oxy}phenyl)acrylate
- 30 2-(3,5-Diaminophenyl)propyl (2E) 3-(4-[(4-(4,4,5,5,6,6,6-heptafluorohexyloxy)cyclohexyl)carbonyl]]oxy}phenyl)acrylate
- 2-(3,5-Diaminophenyl)propyl (2E) 3-(4-[(4-trifluoromethylcyclohexyl)oxyl]carbonyl}phenyl)acrylate

2-(3,5-Diaminophenyl)propyl (2E) 3-{4-[(4-(2,2,2-trifluoropropyl)cyclohexyl)carbonyl]}oxy}phenyl}acrylate

2-(3,5-Diaminophenyl)propyl (2E) 3-{4-[(4-(4,4,4-trifluorobutyl)cyclohexyl)carbonyl]}oxy}phenyl}acrylate

5 2-(3,5-Diaminophenyl)propyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyl)cyclohexyl)carbonyl]}oxy}phenyl}acrylate

2-(3,5-Diaminophenyl)propyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)carbonyl]}oxy}phenyl}acrylate

10 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-methylcyclohexyl)oxyl]carbonyl}phenyl)acrylate

2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-ethylcyclohexyl)oxyl]carbonyl}phenyl)acrylate

2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-propylcyclohexyl)oxyl]carbonyl}phenyl)acrylate

15 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-butylcyclohexyl)oxyl]carbonyl}phenyl)acrylate

2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-pentylcyclohexyl)oxyl]carbonyl}phenyl)acrylate

20 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-hexylcyclohexyl)oxyl]carbonyl}phenyl)acrylate

2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-heptylcyclohexyl)oxyl]carbonyl}phenyl)acrylate

2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-octylcyclohexyl)oxyl]carbonyl}phenyl)acrylate

2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-vinylcyclohexyl)oxyl]carbonyl}phenyl)acrylate

25 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-prop-2-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate

2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-but-3-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate

30 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-pent-4-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate

2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-hex-5-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate

2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-{[(4-hept-6-enylcyclohexyl)oxyl]carbonyl}phenyl)acrylate

- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-[[4-(oct-7-enyl)cyclohexyl]oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-[[4-(methyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 5 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-[[4-(ethyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-[[4-(propyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-[[4-(butyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 10 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-[[4-(pentyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-[[4-(hexyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 15 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-[[4-(heptyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-[[4-(octyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-[[4-(allyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 20 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-[[4-(but-3-enyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-[[4-(pent-4-enyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 25 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-[[4-(hex-5-enyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-[[4-(hept-6-enyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E)-3-(4-[[4-(oct-7-enyloxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 30 2-(3,5-Diaminophenyl)hexyl (2E) 3-(4-[[4-(trifluoromethoxycyclohexyl)oxyl]carbonyl}phenyl)acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E) 3-(4-[[4-(2,2,2-trifluoroethoxy)cyclohexyl]oxyl]carbonyl}phenyl)acrylate

- 2-(3,5-Diaminophenyl)hexyl (2E) 3-{4-[(4-(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E) 3-{4-[(4-(2,2,2-trifluoropropoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 5 2-(3,5-Diaminophenyl)hexyl (2E) 3-{4-[(4-(-(4,4,4-trifluorobutoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyloxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 10 2-(3,5-Diaminophenyl)hexyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoroethoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E) 3-{4-[(4-(1,1,2,2-tetrafluoropropoxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 15 2-(3,5-Diaminophenyl)hexyl (2E) 3-{4-[(4-(4,4,5,5,6,6,6-heptafluorohexyloxy)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E) 3-{4-[(4-trifluoromethylcyclohexyl)oxyl]carbonyl}phenyl}acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E) 3-{4-[(4-(2,2,2-trifluoropropyl)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 20 2-(3,5-Diaminophenyl)hexyl (2E) 3-{4-[(4-(-(4,4,4-trifluorobutyl)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 2-(3,5-Diaminophenyl)hexyl (2E) 3-{4-[(4-(5,5,5-trifluoropentyl)cyclohexyl)carbonyl]]oxy}phenyl}acrylate
- 25 2-(3,5-Diaminophenyl)hexyl (2E) 3-{4-[(4-(4,4,5,5,5-pentafluoropentyl)cyclohexyl)carbonyl]]oxy}phenyl}acrylate


EXAMPLE 5

Synthesis

Preparation of 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-{4-[(4,4,4-trifluorobutoxy)benzoyl]oxy}phenyl]prop-2-enoyl] propanediol

5.1 Preparation of 2,2-dimethyl-5,5-bis(4-nitrobenzyl)-1,3-dioxane-4,6-dione


5



15.0 g (69.4 mmol) of 4-nitrobenzylbromide and 5.00 g (34.7 mmol) of Meldrum's acid are dissolved in 100 ml 2-butanone. 4.40 g (104.1 mmol) potassium carbonate are added, the resulting suspension is heated to 50°C and allowed to react for 2.5 hours. After cooling to room temperature, 100 ml water are added. The product is collected by filtration and washed with a lot of water. 12.3 g (85 %) of 2,2-dimethyl-5,5-bis(4-nitrobenzyl)-1,3-dioxane-4,6-dione as yellowish powder is used without further purification.

15

5.2 Preparation of 2,2-bis(4-nitrobenzyl)malonic acid



20


2.185 g (52.07 mmol) of lithium hydroxide are added to a suspension of 10.79 g (26.04 mmol) of 2,2-dimethyl-5,5-bis(4-nitrobenzyl)-1,3-dioxane-4,6-dione and 110 ml mixture of tetrahydrofuran: water 9:1. The mixture is subsequently allowed to react for 21.5 hours at 25°C, added to 500 ml water and acidified to pH=1 with 20 ml hydrochloric acid 3N. The mixture is partitioned between water and ethyl acetate; the organic phase is washed repeatedly with water, dried over sodium sulfate, filtered and concentrated

25

by rotary evaporation. The residue 9.54 g (98%) of 2,2-bis(4-nitrobenzyl)malonic acid as white powder is used without further purification.

5.3 Preparation of 2,2-bis(4-nitrobenzyl)-1,3-propanediol


5



4.00 g (10.69 mmol) 2,2-bis(4-nitrobenzyl)malonic acid are dissolved in 40 ml tetrahydrofuran and added dropwise in a the course of 2 hours to 64.1 ml (64.1 mmol) of a borane-tetrahydrofuran complex 1.0 M solution in tetrahydrofuran. After 19 hours at 25°C, 50 ml water are carefully added. The reaction mixture is then partitioned between ethyl acetate and water; the organic phase is washed repeatedly with water, dried over sodium sulfate, filtered and concentrated by rotary evaporation. The residue, 3.77 g (97%) of 2,2-bis(4-nitrobenzyl)-1,3-propanediol as white powder is used without further purification.

15


5.4 Preparation 2,2-bis(4-nitrobenzyl)-1,3 di[(2E)-3-(4-[(4-butylcyclohexyl)carbonyl]oxy)phenyl }prop-2-enoyl] propanediol



20

3.90g (11.30 mmol) of 2,2-bis(4-nitrobenzyl)-1,3-propanediol, 7.81 g (23.6 mmol) of (2E)-3-(4-((4-butylcyclohexyl)carbonyl)oxy)phenyl)acrylic, 280 mg (2.30 mmol) of 4-Dimethylaminopyridine are dissolved in 100 ml of dichloromethane. 7.55 g (39.4 mmol) of N-(3-Dimethylaminopropyl)-N'-ethylcarbodiimide hydrochloride (EDC hydrochloride) are added at 0°C. The solution is stirred for 1 h at 0°C and allowed to stir at room temperature overnight. After 22 hours at room temperature the reaction mixture is partitioned between dichloromethane and water. The organic phase is washed repeatedly with water, dried over sodium sulphate, filtered and concentrated by rotary evaporation. Chromatography of the residue on 150 g silica gel using toluene:ethyl acetate 9:1 as eluant to yield 3.43 g 2,2-bis(4-nitrobenzyl)-1,3 di[(2E)-3-(4-((4-butylcyclohexyl)carbonyl)oxy)phenyl]prop-2-enoyl] propanediol as white crystals

5.5 Preparation of 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-((4-butylcyclohexyl)carbonyl)oxy)phenyl]prop-2-enoyl] propanediol



1.94 g (2.00 mmol) 2,2-bis(4-nitrobenzyl)-1,3 di[(2E)-3-(4-((4-butylcyclohexyl)carbonyl)oxy)phenyl]prop-2-enoyl] propanediol are dissolved in a mixture of 25 ml of N,N-dimethylformamide and 3 ml water. 3.25 g (12.01 mmol) ferric chloride hexahydrate are added. 1.31 g (20.02 mmol) Zinc powder are added portionwise within 40 min. The mixture is allowed to react for 2 hours. The reaction mixture is then partitioned between ethyl acetate and water and filtered. The organic phase is washed repeatedly with water, dried over sodium sulfate, filtered and concentrated by rotary evaporation. Chromatography of the residue on 100 g silica gel using toluene:ethyl acetate 1:1 as eluant and crystallization from ethylacetate:hexane

mixture to yield 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-[(4-butylcyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl] propanediol.

5 The following diamines are synthesized in an analogous manner:

2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-[(4-methylcyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl] propanediol

10 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-[(4-ethylcyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl] propanediol

2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-[(4-propylcyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl] propanediol

2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-[(4-butylcyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl] propanediol

15 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-[(4-hexylcyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl] propanediol

2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-[(4-heptylcyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl] propanediol

20 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-[(4-octylcyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl] propanediol

2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-[(4-vinylcyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl] propanediol

2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-[(4-prop-2-enylcyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl] propanediol

25 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-[(4-but-3-enylcyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl] propanediol

2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-[(4-pent-4-enylcyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl] propanediol

30 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-[(4-hex-5-enylcyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl] propanediol

2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-[(4-hept-6-enylcyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl] propanediol

- 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-{{(4-oct-7-enylcyclohexyl)carbonyl}oxy}phenyl
)prop-2-enoyl] propanediol
- 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-{{(4-methyloxycyclohexyl)carbonyl}oxy}phenyl
)prop-2-enoyl] propanediol
- 5 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-{{(4-ethyloxycyclohexyl)carbonyl}oxy}phenyl
)prop-2-enoyl] propanediol
- 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-{{(4-propyloxycyclohexyl)carbonyl}oxy}phenyl
)prop-2-enoyl] propanediol
- 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-{{(4-butyloxycyclohexyl)carbonyl}oxy}phenyl
)prop-2-enoyl] propanediol
- 10 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-{{(4-pentyloxycyclohexyl)carbonyl}oxy}phenyl
)prop-2-enoyl] propanediol
- 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-{{(4-hexyloxycyclohexyl)carbonyl}oxy}phenyl
)prop-2-enoyl] propanediol
- 15 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-{{(4-heptyloxycyclohexyl)carbonyl}oxy}phenyl
)prop-2-enoyl] propanediol
- 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-{{(4-octyloxycyclohexyl)carbonyl}oxy}phenyl
)prop-2-enoyl] propanediol
- 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-{{(4-allyloxycyclohexyl)carbonyl}oxy}phenyl
)prop-2-enoyl] propanediol
- 20 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-{{(4-but-3-
 enyloxycyclohexyl)carbonyl}oxy}phenyl)prop-2-enoyl] propanediol
- 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-{{(4-pent-4-
 enyloxycyclohexyl)carbonyl}oxy}phenyl)prop-2-enoyl] propanediol
- 25 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-{{(4-hex-5-
 enyloxycyclohexyl)carbonyl}oxy}phenyl)prop-2-enoyl] propanediol
- 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-{{(4-hept-6-
 enyloxycyclohexyl)carbonyl}oxy}phenyl)prop-2-enoyl] propanediol
- 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-{{(4-oct-7-
 enyloxycyclohexyl)carbonyl}oxy}phenyl)prop-2-enoyl] propanediol
- 30 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-{{(4(3-
 methoxypropyl)cyclohexyl)carbonyl}oxy}phenyl)prop-2-enoyl] propanediol
- 2,2-bis(4-aminobenzyl)-1,3 di[(2E) 3-(4-{{(4-
 trifluoromethoxycyclohexyl)carbonyl}oxy}phenyl)prop-2-enoyl] propanediol


- 2,2-bis(4-aminobenzyl)-1,3 di[(2E) 3-(4-[(4-(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl] propanediol
- 2,2-bis(4-aminobenzyl)-1,3 di[(2E) 3-{4-[(4-(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl] propanediol
- 5 2,2-bis(4-aminobenzyl)-1,3 di[(2E) 3-{4-[(4-(2,2,2-trifluoropropoxy)cyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl] propanediol
- 2,2-bis(4-aminobenzyl)-1,3 di[(2E) 3-{4-[(4-(4,4,4-trifluorobutoxy)cyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl] propanediol
- 2,2-bis(4-aminobenzyl)-1,3 di[(2E) 3-{4-[(4-(5,5,5-trifluoropentyloxy)cyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl] propanediol
- 10 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-[(4-butylcyclohexyl)oxyl]carbonyl}phenyl)prop-2-enoyl] propanediol
- 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-[(4-hexylcyclohexyl)oxyl]carbonyl}phenyl)prop-2-enoyl] propanediol
- 15 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-[(4-heptylcyclohexyl)oxyl]carbonyl}phenyl)prop-2-enoyl] propanediol
- 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-[(4-octylcyclohexyl)oxyl]carbonyl}phenyl)prop-2-enoyl] propanediol
- 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-[(4-butylcyclohexyl)methoxyl]phenyl)prop-2-enoyl] propanediol
- 20 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-[(4-hexylcyclohexyl)methoxyl]phenyl)prop-2-enoyl] propanediol
- 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-[(4-heptylcyclohexyl)methoxyl]phenyl)prop-2-enoyl] propanediol
- 25 2,2-bis(4-aminobenzyl)-1,3 di[(2E)-3-(4-[(4-octylcyclohexyl)methoxyl]phenyl)prop-2-enoyl] propanediol

EXAMPLE 6

30

Synthesis


6.1 Preparation of 4,4'-Dinitro-1,1'-biphenyl-2,2'-dicarboxylic acid



30.0g (120.13 mmol) Diphenic acid are dissolved at room temperature in 469 g (4.59
5 mol) concentrated sulfuric acid (96%). The solution is cooled to -15°C and a mixture of
92.4g (1.011 mol) concentrated nitric acid (69%) and 12.0 g (0.117 mol) concentrated
sulfuric acid (96%) is added slowly so that the mixture temperature is maintained below
 0°C . After the addition the solution is allowed to react at room temperature for 24h.
After the mixture is poured onto crushed ice, the precipitate that formed i collected by
10 filtration, washed with water and dried at room temperature under vacuum for 10 h.


6.2 Preparation of 2,2'-bis(hydroxymethyl)-4,4'-Dinitro 1,1'-biphenyl

15



3.6 g (10.83 mmol) 4,4'-Dinitro-1,1'-biphenyl-2,2'-dicarboxylic acid are dissolved in 25 ml tetrahydrofuran and added dropwise in the course of 1 hour to 65 ml (65.02 mmol) of a borane-tetrahydrofuran complex 1.0 M solution in tetrahydrofuran. After 19 hours at 25°C, 50 ml water are carefully added. After 1 h the solution is acidified to pH=1-2 with 10 ml 1N HCl solution and allowed to stir for 30 min. The reaction mixture is then partitioned between ethyl acetate and water; the organic phase is washed repeatedly with water, dried over sodium sulfate, filtered and concentrated by rotary evaporation. The residue, 4.2 g of 2,2'-bis(hydroxymethyl-4,4'-Dinitro 1,1'-biphenyl as white powder is used without further purification.


6.3 Preparation of 2,2'-bis[(2E)-3-(4-[(4-butylcyclohexyl)carbonyl]oxy)phenyl]prop-2-enoyl]methyl 4,4'-Dinitro 1,1'-biphenyl



7.30 g (22.9 mmol) of (2E)-3-(4-[(4-butylcyclohexyl)carbonyl]oxy) phenyl)acrylic acid are dissolved in 80 ml of toluene. 2.30 ml (31.5 mmol) of thionylchloride are added. The solution is stirred for 1 h at 80°C. the excess thionylchloride was removed by distillation at 150°C. At 60°C, 3.20 g (10.52 mmol) of 2,2'-bis(hydroxymethyl-4,4'-Dinitro 1,1'-biphenyl, 250 mg (2.02 mmol) of 4-Dimethylaminopyridine and 6.8 ml pyridine were added. The mixture was allowed to react at 60°C overnight. The reaction mixture is partitioned between ethyl acetate and ice water. The mixture is acidified by the addition of HCl 25% (up to pH=1). The organic phase is washed repeatedly with water, dried over sodium sulphate, filtered and concentrated by rotary evaporation. Chromatography of the residue on 500 g silica gel using toluene:ethyl acetate 9:1 as eluant and crystallization from ethylacetate:hexane mixture yielded 3.8 g of 2,2'-

bis[(2E)-3-(4-[[4-butylcyclohexyl]carbonyl]oxy}phenyl)prop-2-enoyl]methyl 4,4'-Dinitro 1,1'-biphenyl as yellowish crystals..

5 6.4 Preparation 2,2'-bis[(2E)-3-(4-[[4-butylcyclohexyl]carbonyl]oxy}phenyl)prop-2-enoyl]methyl 4,4'-Diamino 1,1'-biphenyl



10 1.99 g (2.14 mol) of 2,2'-bis[(2E)-3-(4-[[4-butylcyclohexyl]carbonyl]oxy}phenyl)prop-2-enoyl]methyl 4,4'-Dinitro 1,1'-biphenyl are dissolved in a mixture of 40 ml of N,N-dimethylformamide and 3 ml water. 3.48 g (12.8 mmol) ferric chloride hexahydrate are added. 1.40 g (21.4 mmol) Zinc powder are added portionwise within 40 min. The mixture is allowed to react for 2 hours. The reaction mixture is then partitioned
15 between ethyl acetate and water and filtered. The organic phase is washed repeatedly with water, dried over sodium sulfate, filtered and concentrated by rotary evaporation. Chromatography of the residue on silica gel yield 2,2'-bis[(2E)-3-(4-[[4-butylcyclohexyl]carbonyl]oxy}phenyl)prop-2-enoyl]methyl 4,4'-Diamino 1,1'-biphenyl .


20

EXAMPLE 7

Synthesis

Preparation of 2-(2,4-Diaminophenyl)- 1,3 di[(2E)-3-(4-[[4-butylcyclohexyl]carbonyl]oxy}phenyl)}prop-2-enoyl] propanediol

7.1 Preparation of 2-(2,4-Dinitrophenyl)- 1,3 di[(2E)-3-(4-[(4-butylcyclohexyl)carbonyl]oxy}phenyl)}prop-2-enoyl] propanediol



5

0.71 g (2.9 mmol) of 2-(4-nitrophenyl)-1,3-propanediol, 2.0 g (6.08 mmol) of (2E)-3-(4-[(4-butylcyclohexyl)carbonyl]oxy}phenyl)acrylic acid, 70 mg (0.6 mmol) of 4-Dimethylaminopyridine are dissolved in 20 ml of dichloromethane. 1.38 g (7.22 mmol) of N-(3-Dimethylaminopropyl)-N'-ethylcarbodiimide hydrochloride (EDC hydrochloride)


10

are added at 0°C. The solution is stirred for 1 h at 0°C and allowed to stir at room temperature overnight. After 22 hours at room temperature the reaction mixture is partitioned between dichloromethane and water. The organic phase is washed repeatedly with water, dried over sodium sulphate, filtered and concentrated by rotary evaporation. Crystallization from Acetonitrile yield 2.00 g 2-(2,4-Dinitrophenyl)- 1,3 di[(2E)-3-(4-[(4-butylcyclohexyl)carbonyl]oxy}phenyl)}prop-2-enoyl] propanediol as white crystals.

15

7.2 Preparation of 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-butylcyclohexyl)carbonyl]oxy}phenyl)}prop-2-enoyl] propanediol

20



6.6 g (7.64 mmol) of 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-butylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol are dissolved in a mixture of 45 ml of N,N-dimethylformamide and 5 ml water. 12.39 g (45.84 mmol) ferric chloride hexahydrate are added. 4.99 g (76.4 mmol) Zinc powder are added
 5 portionwise within 40 min. The mixture is allowed to react for 2 hours. The reaction mixture is then partitioned between ethyl acetate and water and filtered. The organic phase is washed repeatedly with water, dried over sodium sulfate, filtered and concentrated by rotary evaporation. Chromatography of the residue on silica gel yield
 10 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-butylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol.

The following diamines are synthesized in an analogous manner:

- 15 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-methylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-ethylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-propylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
 20 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-butylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-hexylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
 25 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-heptylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-octylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-vinylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
 30 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-prop-2-enylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-but-3-enylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol

- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-pent-4-enylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-hex-5-enylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 5 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-hept-6-enylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-oct-7-enylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-methyloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 10 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-ethyloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-propyloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 15 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-butyloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-pentyloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-hexyloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 20 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-heptyloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-octyloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 25 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-allyloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-but-3-enyloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-pent-4-enyloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 30 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-hex-5-enyloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-hept-6-enyloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol

- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-oct-7-enyloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4(3-methoxypropyl)cyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 5 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-trifluoromethoxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 10 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-methylcyclohexyl)methoxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-ethylcyclohexyl)methoxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-propylcyclohexyl)methoxy}phenyl))prop-2-enoyl] propanediol
- 15 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-butylcyclohexyl)methoxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-hexylcyclohexyl)methoxy}phenyl))prop-2-enoyl] propanediol
- 20 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-heptylcyclohexyl)methoxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-octylcyclohexyl)methoxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-vinylcyclohexyl)methoxy}phenyl))prop-2-enoyl] propanediol
- 25 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-prop-2-enylcyclohexyl)methoxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-but-3-enylcyclohexyl)methoxy}phenyl))prop-2-enoyl] propanediol
- 30 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-pent-4-enylcyclohexyl)methoxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-hex-5-enylcyclohexyl)methoxy}phenyl))prop-2-enoyl] propanediol

- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-((4-hept-6-enylcyclohexyl)methoxy)phenyl)prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-((4-oct-7-enylcyclohexyl)methoxy)phenyl)prop-2-enoyl] propanediol
- 5 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-((4-methyloxycyclohexyl)methoxy)phenyl)prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-((4-ethyloxycyclohexyl)methoxy)phenyl)prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-((4-propyloxycyclohexyl)methoxy)phenyl)prop-2-enoyl] propanediol
- 10 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-((4-butyloxycyclohexyl)methoxy)phenyl)prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-((4-pentyloxycyclohexyl)methoxy)phenyl)prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-((4-hexyloxycyclohexyl)methoxy)phenyl)prop-2-enoyl] propanediol
- 15 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-((4-heptyloxycyclohexyl)methoxy)phenyl)prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-((4-octyloxycyclohexyl)methoxy)phenyl)prop-2-enoyl] propanediol
- 20 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-((4-allyloxycyclohexyl)methoxy)phenyl)prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-((4-but-3-enyloxycyclohexyl)methoxy)phenyl)prop-2-enoyl] propanediol
- 25 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-((4-pent-4-enyloxycyclohexyl)methoxy)phenyl)prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-((4-hex-5-enyloxycyclohexyl)methoxy)phenyl)prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-((4-hept-6-enyloxycyclohexyl)methoxy)phenyl)prop-2-enoyl] propanediol
- 30 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-((4-oct-7-enyloxycyclohexyl)methoxy)phenyl)prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-((4-(3-methoxypropyl)cyclohexyl)methoxy)phenyl)prop-2-enoyl] propanediol

- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-{(4-trifluoromethoxycyclohexyl)methoxy}phenyl)prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-{(4--(2,2-trifluoroethoxy)cyclohexyl)methoxy}phenyl)prop-2-enoyl] propanediol
- 5 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-{[(4-methylcyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-{[(4-ethylcyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-{[(4-propylcyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 10 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-{[(4-butylcyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-{[(4-hexylcyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 15 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-{[(4-heptylcyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-{[(4-octylcyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-{[(4-vinylcyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 20 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-{[(4-prop-2-enylcyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-{[(4-but-3-enylcyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 25 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-{[(4-pent-4-enylcyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-{[(4-hex-5-enylcyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-{[(4-hept-6-enylcyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 30 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-{[(4-oct-7-enylcyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-{[(4-methyloxycyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol

- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-ethyloxycyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-propyloxycyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 5 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-butyloxycyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-pentyloxycyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-hexyloxycyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 10 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-heptyloxycyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-octyloxycyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 15 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-allyloxycyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-but-3-enyloxycyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-pent-4-enyloxycyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 20 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-hex-5-enyloxycyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-hept-6-enyloxycyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 25 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-oct-7-enyloxycyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4(3-methoxypropyl)cyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-trifluoromethoxycyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 30 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-(2,2,2-trifluoroethoxy)cyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[(4-trifluoromethylcyclohexyl)oxy]carbonyl}phenyl))prop-2-enoyl] propanediol

- 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-methylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-ethylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 5 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-propylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-butylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-hexylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 10 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-heptylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-octylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 15 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-vinylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-prop-2-enylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-but-3-enylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 20 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-pent-4-enylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-hex-5-enylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 25 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-hept-6-enylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-oct-7-enylcyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-methyloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 30 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-ethyloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-propyloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol

- 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-butylloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-pentylloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 5 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-hexylloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-heptyloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 10 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-octylloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-allyloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-but-3-enyloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 15 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-pent-4-enyloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-hex-5-enyloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-hept-6-enyloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 20 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-oct-7-enyloxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminobenzyl)-1,3 di[(2E)-3-(4-[(4-(3-methoxypropyl)cyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 25 2-(2,4-Diaminobenzyl)-1,3 di[(2E) 3-(4-[(4-trifluoromethoxycyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol
- 2-(2,4-Diaminobenzyl)-1,3 di[(2E) 3-(4-[(4--(2,2,2-trifluoroethoxy)cyclohexyl)carbonyl]oxy}phenyl))prop-2-enoyl] propanediol

30


EXAMPLE 8

Polymersiation Step A (formation of the Polyamic Acid)

379.5 mg (1.935 mmol) of 1,2,3,4-cyclobutanetetracarboxylic acid dianhydride is added to a solution of 1.00 g (2.15 mmol) of 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-
 5 butylcyclohexyl)carbonyloxy} phenyl)acrylate in 2.00 ml of 1-methyl-2-pyrrolidone (NMP). Stirring is then carried out at 0 °C for 2 hours. Then another 42.5 mg (0.215 mmol) of 1,2,3,4-cyclobutanetetracarboxylic acid dianhydride are added. The mixture is subsequently allowed to react for 21 hours at room temperature. The polymer mixture is diluted with 10 ml THF, precipitated into 800 ml water to yield, after drying at room temperature under vacuum, 1.35 g of Polyamic Acid 1 in the form of a
 10 white powder; $[\eta] = 0.85$ dL/g


Analogous to EXAMPLE 8 the following diamines are used for the preparation of Polyamic Acid with 1,2,3,4-cyclobutanetetracarboxylic acid dianhydride

15 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-[[4-ethylcyclohexyl)carbonyloxy} phenyl)acrylate



20 Yield Polyamic acid 2 in the form of a white powder; $[\eta] = 0.36$ dL/g


2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-[[4-heptylcyclohexyl)carbonyloxy} phenyl)acrylate



25


Yield Polyamic acid 3 in the form of a white powder; $[\eta] = 0.51$ dL/g

3-[[[(2E)-3-{4-[[[(4-butylcyclohexyl)carbonyl]oxy}phenyl]prop-2-enoyl]oxy}]propyl 3,5-diaminobenzoate



5 Yield Polyamic acid 4 in the form of a white powder; $[\eta] = 0.52 \text{ dL/g}$


2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-[[[(4-butylcyclohexyl)carbonyl]oxy}phenyl])prop-2-enoyl] propanediol



10

Yield Polyamic acid 5 in the form of a white powder; $[\eta] = 0.23 \text{ dL/g}$

2-(3,5-Diaminophenyl)ethyl (2E) 3-(4-[[[(4-trifluorocyclohexyl)carbonyl]oxy}phenyl]acrylate




15

Yield Polyamic acid 6 in the form of a white powder; $[\eta] = 0.40 \text{ dL/g}$

2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-[[[(4-heptylcyclohexyl)carbonyl]oxy}phenyl]acrylate

20




Yield Polyamic acid 7 in the form of a white powder; $[\eta] = 0.31 \text{ dL/g}$

5

EXAMPLE 9

Analogous to EXAMPLE 8 the following diamines are used for the preparation of Polyamic Acid with 2,3,5-tricarboxycyclopentylacetic acid dianhydride


10 2-(2,4-Diaminophenyl)ethyl (2E)-3-(4-((4-butylcyclohexyl) carbonyl)oxy)phenyl)acrylate



yield Polyamic acid 8 as white powder; $[\eta] = 0.24 \text{ dL/g}$


3,5-Diaminobenzyl (2E)-3-(4-((4-butylcyclohexyl)carbonyl)oxy) phenyl)acrylate

15




Yield Polyamic acid 9 in the form of a white powder; $[\eta] = 0.58 \text{ dL/g}$

20 2-(2,4-Diaminophenyl)-1,3 di[(2E)-3-(4-((4-butylcyclohexyl)carbonyl)oxy)phenyl]}prop-2-enoyl] propanediol




Yield Polyamic acid 10 in the form of a white powder; $[\eta] = 0.13 \text{ dL/g}$

- 5 2-(2,4-Diaminophenyl)ethyl (2E) 3-{4-[(4-{(4,4,4-trifluorobutoxy)cyclohexyl}carbonyl)]oxy}phenyl}acrylate



Yield Polyamic acid 11 in the form of a white powder; $[\eta] = 0.18 \text{ dL/g}$

- 10 2,2'-bis[(2E)-3-(4-{[(4-butylcyclohexyl)carbonyl]oxy}phenyl)prop-2-enoyl]methyl 4,4'-Diamino 1,1'-biphenyl



Yield Polyamic acid 12 in the form of a white powder; $[\eta] = 1.06 \text{ dL/g}$

15

EXAMPLE 10

Polymerisation Step B (Formation of the Polyimide)

0.59 g of Polyamic Acid No. 1 obtained in above EXAMPLE 5 are dissolved in 3 ml of 1-methyl-2-pyrrolidone (NMP). There to are added 0.28 g (3.57 mmol, 4 equivalent) of pyridine and 364 mg (3.57 mmol, 4 equivalent) acetic acid anhydride, and the dehydration and ring closure is carried out at 80°C for 2 h. The polymer mixture is
5 diluted with 1.5 ml NMP, precipitated into 100 ml diethyl ether and collected by filtration. The polymer is reprecipitated from THF (10 ml) into 200 ml water to yield, after drying at room temperature under vacuum, 0.55 g Polyimide No 1;
[η] = 0.80 dL/g, Imidization degree ID=100%

10

EXAMPLE 11

Preparation of an orientation layer for vertical alignment

15

A 4% solution of LPP (see molecular structure on figure 1)in a solvent mixture of N-Methyl-2-Pyrrolidone (NMP) and Butylglycol (BC) in a ratio of 1: 9 by weight was prepared. This LPP solution was filtered over a 2 μ m Teflon filter and applied to two indium tin oxide (ITO) coated rectangular glass plates by spin coating at 1350 rpm for 30 seconds. The resulting films were then pre-dried for 5 minutes at 130°C and further post-baked for 40 minutes at 200°C.

20

Both ITO covered glass plates were irradiated with polarised UV light at a dose of 48mJ/cm². The direction of incidence of the light being inclined by 40° relative to the plate normal and the incidence plane was parallel to the short side of the substrate. The two irradiated plates were used to build a cell of 20 μ m spacing in an anti-parallel manner such that the irradiated surfaces were facing each other. The cell was then capillary filled with liquid crystal mixture MLC6610 from Merck in the isotropic phase at
25 105°C. The cell was then gradually cooled down at a rate of 0.1°C/min from T=105°C to T=85°C and at a rate of 2 C/min from T=85°C to room temperature. When arranged between crossed polarisers , the cell appeared uniformly black for every angle between the short edge of the cell and the polariser transmission axis, as long as viewed from the vertical. In conclusion, the liquid crystal mixture was aligned
30 homeotropically.

When the short edge of the cell was set at 45° to the polariser axis and an AC voltage of 7V and 90Hz was applied, the liquid crystals switched and caused the cell to appear

green (high order birefringence). No defects or tilt domains were observed. Brightness and colour of the switched cell changed asymmetrically when viewed from opposite, but equal oblique angles along a plane parallel to the short edge of the cell. Contrary, no asymmetry was found when viewed obliquely from opposite angles within a plane parallel to the long edge of the cell. When the switched cell with its short edge was aligned parallel or perpendicular to one of the polariser transmission axes the cell appeared dark again. From above observations we concluded that LC alignment capability was induced in the thin film on the substrate due to irradiation with slantwise incident polarized light. The azimuthal alignment direction was parallel to the plane of incidence of the uv-light.

From tilt angle evaluation by means of the crystal rotation method a tilt angle value of 88.2° with respect to the substrate surface was obtained. The direction of the LC molecules was in between the surface normal and the direction of the incident light.





Figure 1 : Molecular structure of the LPP.

CLAIMS

1. Diamine compound of formula (I):



5

(I)

wherein,

- 10 A represents an unsubstituted or substituted carbocyclic or heterocyclic aromatic group selected from a monocyclic ring of five or six atoms, two adjacent monocyclic rings of five or six atoms, a bicyclic ring system of eight, nine or ten atoms, or a tricyclic ring system of thirteen or fourteen atoms;
- 15 B represents a straight-chain or branched C₁-C₁₆alkyl group, which is unsubstituted or substituted by di-(C₁-C₁₆alkyl)amino, C₁-C₆alkyloxy, nitro, cyano, fluoro and/or chlorine; and wherein one or more -CH₂- group may independently from each other be replaced by a linking group;
- 20 Q represents an alicyclic group, which unsubstituted is or substituted by di-(C₁-C₁₆alkyl)amino, C₁-C₆alkyloxy, nitro, cyano, fluoro and/or chlorine; and wherein one or more -CH₂- group may independently from each other be replaced by a linking group;

- D represents an unsubstituted or substituted, aliphatic, aromatic and/or alicyclic diamine group having from 1 to 40 carbon atoms,
- E represents an aromatic group, an oxygen atom, a sulphur atom, -NH-,
-N(C₁-C₆alkyl)-, -CR²R³,
- 5 wherein R² and R³ are independently from each other hydrogen or a cyclic, straight-chain or branched, substituted or unsubstituted C₁-C₂₄alkyl, wherein one or more -CH₂- group(s) may be independently from each other replaced by a linking group, and with the proviso that at least one of R² and R³ is not hydrogen;
- 10 S¹, S² each independently from each other represents a spacer unit;
- X, Y each independently from each other represents hydrogen, fluorine, chlorine, cyano, unsubstituted or with fluorine substituted C₁-C₁₂alkyl, in which one or more -CH₂- groups may be replaced by a linking group;
- n₁ represents 0, 1, 2, 3 or 4, preferably n₁ is 1 and n is 1 or 2;
- 15 n represents 1, 2, 3 or 4, preferably n₁ is 1 and n is 1 or 2; with the proviso that if n is 2, 3, or 4, each A, B, x₁, D, E, S¹, S², X, Y are identical or different; and if n₁ is 2, 3 or 4 each B, x₁ is identical or different.

2. Diamine compound according to claim 1, wherein the linking group is selected
- 20 from -O-, -CO-, -CO-O-, -O-CO-, $\text{--}\text{N}<$, -NR¹-, -NR¹-CO-, -CO-NR¹-, -NR¹-CO-O-, -O-CO-NR¹-, -NR¹-CO-NR¹-, -CH=CH-, -C≡C-, -O-CO-O-, and -Si(CH₃)₂-O-Si(CH₃)₂-, and wherein:


- R¹ represents a hydrogen atom or C₁-C₆alkyl;
- 25 with the proviso that oxygen atoms of linking groups are not directly linked to each other.

3. Diamine compound according to claim 1, wherein the spacer unit is a single bond, a cyclic, straight-chain or branched, substituted or unsubstituted C₁-C₂₄alkylen,
- 30 wherein one or more -CH₂- group may independently from each other be replaced by a linking group as described in claim 2 and/or an non-aromatic, aromatic, unsubstituted or substituted carbocyclic or heterocyclic group connected via bridging groups.

4. Diamine compound according to claim 3, wherein the bridging group is selected from -CH(OH)-, -CO-, -CH₂(CO)-, -SO-, -CH₂(SO)-, -SO₂-, -CH₂(SO₂)-, -COO-, -OCO-, -COCF₂-, -CF₂CO-, -S-CO-, -CO-S-, -SOO-, -OSO-, -SOS-, -O-CO-O-, -CH₂-CH₂-,
 5 -OCH₂-, -CH₂O-, -CH=CH-, -C≡C-, -CH=CH-COO-, -OCO-CH=CH-, -CH=N-,
 -C(CH₃)=N-, -N=N- or a single bond; or a cyclic, straight-chain or branched, substituted or unsubstituted C₁-C₂₄alkylen, wherein one or more -CH₂- group may independently from each other be replaced independently from each other by a linking group as described in claim 2.

10

5. Diamine compound according to any of the preceding claims, wherein
 D is preferably selected from formula (III):



15

wherein:

R⁵, R⁶ each independently from each other represents a hydrogen atom or C₁-C₆alkyl;

Sp¹, Sp² each independently from each other represent a single bond or an
 20 unsubstituted or substituted straight-chain or branched C₁-C₂₀alkylene, in which one or more -CH₂-group may independently from each other be replaced by a linking group, and

k¹, k² each independently is an integer having a value of 0 or 1; and

X¹, X² each independently represents a linking spacer, and

25 t¹, t² each independently is an integer having a value of 0 or 1; and

C³, C⁴ each independently represents a non-aromatic, aromatic, substituted or unsubstituted carbocyclic or heterocyclic group, which may have a side chain T, and

Z³ represents a bridging group; and

30 Z⁴ represents a substituted or unsubstituted straight-chain or branched C₁-C₂₀alkylene group, in which one or more -CH₂- group may independently from each other be replaced by a non-aromatic, aromatic, unsubstituted or

substituted carbocyclic or heterocyclic group; and/or a heteroatom and/or by a bridging group; and

a₃, a₄ are independently integers from 0 to 3, such that $a_3 + a_4 \leq 4$; and wherein


D is at least once linked to at least one group S¹ in formula (I) via group Sp¹

5 and/or group Sp²; and/or linked via at least one non-aromatic, aromatic, substituted or unsubstituted carbocyclic or heterocyclic group of C³ and/or group of C⁴, and/or linked via at least one side chain T of group C⁴ and/or group of C³; and/or linked via group Z⁴; and at least one of k¹, k², a³ and a⁴ is not equal to zero; and wherein

10 linking group is as defined in claim 2, and bridging group is as defined in claim 4.

6. Diamine compound according to claim 5, wherein the side chain, T, represents a substituted or unsubstituted straight-chain or branched C₁-C₂₀alkylene group, in which one or more -CH₂- group(s) may independently from each other be replaced by
15 a non-aromatic, aromatic, unsubstituted or substituted carbocyclic or heterocyclic group, or a heteroatom and/or by a bridging group, which is at least once linked to at least once group S¹ in formula (I) as described in claim 1.

7. Diamine compound according to claims 5 and 6, wherein C³, C⁴ independently
20 from each other are selected from a compound of group G², wherein G² is:



5 **wherein:**

“—” denotes the connecting bonds of C³ and C⁴ to the adjacent groups of compound of formula (III) as described in claim 5; and

10 L is -CH₃, -COCH₃, -OCH₃, nitro, cyano, halogen, CH₂=CH-, CH₂=C(CH₃)-, CH₂=CH-(CO)O-, CH₂=CH-O-, -NR⁵R⁶, CH₂=C(CH₃)-(CO)O-, CH₂=C(CH₃)-O-,

wherein:

R⁵, R⁶ each independently from each other represents a hydrogen atom or C₁-C₆alkyl;

T represents a substituted or unsubstituted straight-chain or branched C₁-C₂₀alkylene group, in which one or more -CH₂- group may independently from each other be replaced by a non-aromatic, aromatic, unsubstituted or substituted carbocyclic or heterocyclic group, or a heteroatom and/or by a bridging group;


m is an integer from 0 to 2;

u₁ is an integer from 0 to 4, with the proviso that m + u₁ is ≤4; and

u₂ is an integer from 0 to 3; with the proviso that m + u₂ is ≤3; and

u₃ is an integer from 0 to 2; with the proviso that m + u₃ is ≤2.

8. Diamine compound according to any of the preceding claims, wherein D is a selected the group of the following compounds:



wherein

L, L_1, L_2 and L_3 are independently from each other $-CH_3$, $-COCH_3$, $-OCH_3$, nitro, cyano, halogen, $CH_2=CH-$, $CH_2=C(CH_3)-$, $CH_2=CH-(CO)O-$, $CH_2=CH-O-$, $-NR^5R^6$, $CH_2=C(CH_3)-(CO)O-$ or $CH_2=C(CH_3)-O-$,

5

T, T_1, T_2 and T_3 are independently from each other a substituted or unsubstituted straight-chain or branched C_1 - C_{20} alkylene group, in which one or more $-CH_2-$ group(s) may independently from each other be replaced by a non-aromatic, aromatic,

unsubstituted or substituted carbocyclic or heterocyclic group, and/or a heteroatom and/or by a bridging group;

M represents H, C₁-C₆alkyl, CF₃,

"—" is a single bond,

5 q is an integer of 1 or 2; and

q₁, q₂ and q₃ are independently from each other an integer from 0 to 2;

m is an integer of 1 or 2;

m₁, m₂ and m₃ are independently from each other an integer from 0 to 2;

u₃, u₃' and u₃'' are independently from each other an integer from 0 to 2;

10 R⁵, R⁶ and Z⁴ are as described above; and wherein

D is at least once linked to at least one group S¹ in formula (I), as described in claim 1, via a single bond "—"; or via a side chain T, T₁, T₂ or T₃; or via group Z⁴;

with the proviso that

15 u₃ + q, or u₃ + m is ≤ 4;

u₃ + q₁ and/or u₃' + q₂ or/and u₃ + m₁, or/and u₃' + m₂, or/and u₃'' + q₃, or/and u₃'' + m₃ is ≤ 4;

q₁ + q₂, and m₁ + m₂; and q₁ + q₂ + q₃, and m₁ + m₂ + m₃ is ≥ 1.

20 9. Diamine compound according to any of the preceding claims, wherein Q is an alicyclic group having 3 to 20 carbon atoms.

10. Diamine compound according to any of the preceding claims, wherein

S¹, S² each independently from each other represents a single bond or a cyclic,

25 straight-chain or branched, substituted or unsubstituted C₁-C₂₄alkylen, in which one or more -CH₂- group may independently from each other be replaced by a linking group, and/or a non-aromatic, aromatic, unsubstituted or substituted carbocyclic or heterocyclic group of formula (IV):

30
$$-(Z^1-C^1)_{a1}-(Z^2-C^2)_{a2}-(Z^{1a})_{a3}- \quad (IV)$$

wherein:

C¹, C² each independently represents a non-aromatic, aromatic, unsubstituted or substituted carbocyclic or heterocyclic group, and




Z¹, Z², Z^{1a} each independently represents a bridging group, and

5


a₁, a₂, a₃ each independently represents an integer from 0 to 3, a₁ + a₂ + a₃ ≤ 6, wherein the bridging groups Z¹, Z^{1a} and Z² are as described in claim 4.

11. Diamine compound according to any preceding claim, which is a compound of formulae (VI), (VII), (VIII), (IX), (IXa), (X), (XI), (XIa), (XIb) and (XIc)


10




15






(IX)




(IXa)



(X)





wherein

A, B, Q, n1, D, E, S², S¹, X and Y have the above given meanings as in claim 1 and

5 R⁵, R⁶ and Z⁴ have the same meanings as in claim 5; and


S⁰, represents a single bond or a spacer unit, which is a straight-chain or
branched, substituted or unsubstituted C₁-C₂₄alkylen, preferably C₁-C₆alkylen,
wherein one or more, preferably non-adjacent, -CH₂- group may be replaced
by a linking group,


10 M represents H, C₁-C₆alky, CF₃,

L is -CH₃, -OCH₃, -COCH₃, nitro, cyano, halogen, CH₂=CH-, CH₂=C(CH₃)-,
CH₂=CH-(CO)O-, CH₂=CH-O-, CH₂=C(CH₃)-(CO)O-, or CH₂=C(CH₃)-O-,

u₃ is an integer from 0 to 2.

15 12. Diamine compound according to any preceding claim, which is a compound of
formula formulae (XII) or (XIIa)
















(XIIa)

wherein B, Q n, n1, D, E, S¹, X, and Y have the above given meanings as in claim 1
 and Z¹, Z^{1a} and a₃ has the same meaning as in claim 10, and L, u₁ and u₂ have the
 5 same meanings as in claim 7.





13. Diamine compound according to any preceding claim, selected from







5 or



- 5 wherein S¹ and Q has the above given meaning as in claim 1 and S⁰, represents a single bond or a spacer unit, which is a straight-chain or branched, substituted or unsubstituted C₁-C₂₄alkylen, preferably C₁-C₆alkylen, wherein one or more, preferably non-adjacent, -CH₂- group may be replaced by a linking group,
- 10 B represents a straight-chain or branched C₁-C₈alkyl group, which is unsubstituted or substituted by di-(C₁-C₁₆alkyl)amino, C₁-C₆alkyloxy, nitro, cyano, fluoro and/or chlorine; and wherein one or more -CH₂- group may independently be replaced by a linking

group selected from -O-, -CO-, -CO-O-, -O-CO-, -NR¹-, -NR¹-CO-, -CO-NR¹- and -CH=CH-, wherein:

R¹ represents a hydrogen atom or C₁-C₆alkyl;

with the proviso that oxygen atoms are not directly linked to each other.

5


14. Polymer, copolymer or oligomer comprising diamine (I) according to any of the preceding claims, as one basic building block.

10


15. Polymer, copolymer or oligomer according to claim 14, which is a polyamic acid, polyamic ester, polyimide or a mixture of polyamic acid and polyamic ester and/or polyimide.

16. A process for the preparation of diamine compound (XII) as defined in claim 12 comprising comprising contacting a compound of formula (XIV)

15




with a dinitro compound of formula (XVI)




and then converting the obtained dinitro compound of formula (XVIa)

20



in the corresponding diamino compound of formula (XII)



wherein

n_1 , n , B, D, Q, X, Y, L, u_1 , u_2 and S^1 have the same meaning as in claim 11, Z^1 , Z^{1a} and a_3 has the same meaning as in claim 10, and wherein D1 has the same meaning as D as in claim 7, with the proviso that the two amino groups of D are replaced by two nitro groups.

17. Compound of formula (XIV) and compound of formula (XVIa) as defined in claim 16.

18. Composition comprising at least one diamine (I) and optionally at least one further diamine, which is different from (I) or/and an additive.

19. Process for the preparation of a polymer, copolymer or oligomer comprising polymerisation of a diamine (I).

20. Polymer, copolymer or oligomer obtainable by reaction according to claim 19 comprising a diamine of compound (I) according to any of the preceding claims.

21. Polymer, copolymer or oligomer according to claim 20 or prepared according to claim 19, which is a polymer gel or a polymer network, copolymer gel or a copolymer network, or an oligomer gel or an oligomer network.

22. Polymer, copolymer or oligomer according to any of claims 20 or 21 or prepared according to claim 19, which is able to undergo photocyclization.

23. Composition, especially a blend, comprising

- a polymer, copolymer or oligomer comprising at least a diamine (I) according to claim 1 as basic building block, or
- a polymer, copolymer or oligomer obtainable according to claim 20 .

5 24. Method for the preparation of a polymer, copolymer or oligomer according to any of claims 20 or 22 or prepared according to claim 19, wherein in a polycondensation reaction a diamine (I) according to claim 1 is reacted with one or more tetracarboxylic acid anhydride, optionally in the presence of one or more additional other diamines.

10 25. Polymer, copolymer or oligomer layer, comprising at least one polymer, copolymer or oligomer according to any of claims 20 or 22 or prepared according to claim 19.

15 26. Method for the preparation of a polymer layer or oligomer layer, wherein one or more polymers, copolymers or oligomers according to any of claims 20 or 22 or prepared according to claim 19 is applied to a support, and wherein, the polymer or oligomer or polymer mixture or oligomer mixture is treated with aligning light.

20 27. Polymer, copolymer or oligomer layer obtainable by the method according to claim 26.

25 28. Optical and electro-optical unstructured or structured constructional elements, preferably liquid crystal display cells, multi-layer and hybrid layer elements, comprising at least one polymer layer, copolymer or oligomer layer according to claim 27.

29. Orientation layer, comprising at least one polymer layer, copolymer or oligomer layer according to claim 27.

30 30. Use of diamine (I) for the preparation of polymers according to claim 20-22, 25 and 27 for orientation layers for liquid crystals, wherein the polymers have ACM values after 600 hours of ≤ 0.15 .