

12 **EUROPEAN PATENT APPLICATION**

21 Application number: **83101510.2**

51 Int. Cl.³: **D 02 G 1/02**

22 Date of filing: **17.02.83**


30 Priority: **19.02.82 JP 24561/82**
10.06.82 JP 98510/82
07.08.82 JP 137611/82
02.10.82 JP 172518/82
 43 Date of publication of application:
31.08.83 Bulletin 83/35
 84 Designated Contracting States:
AT BE CH DE FR GB IT LI LU NL SE

71 Applicant: **Asahi Kasei Kogyo Kabushiki Kaisha**
2-6, Dojimahama 1-chome Kita-ku
Osaka-shi Osaka 530(JP)
 72 Inventor: **Ukai, Norio**
Hamayama apt. 111 4, Midorigaoka-cho 2-chome
Nobeoka-shi Miyazaki-ken(JP)
 72 Inventor: **Tomizuka, Katsushige**
5-11, Sanban-cho, Hiyoshidai
Takatsuki-shi Osaka(JP)
 72 Inventor: **Kuriki, Tomio**
40-15, Amanogahra-cho 2-chome
Katano-shi Osaka(JP)
 72 Inventor: **Kamide, Kenji**
7-26, Asukanokita 1-chome
Ikoma-shi Nara-ken(JP)
 74 Representative: **Werner, Hans-Karsten, Dr. et al,**
Deichmannhaus am Hauptbahnhof
D-5000 Köln 1(DE)

54 **Process and apparatus for producing easily dyeable polyester false-twisted yarns.**

57 A false-twisted polyester yarn is produced by a process wherein a yarn consisting of an as-spun polyester fiber having a mean birefringence index (Δn) of at least 15×10^{-3} but less than 150×10^{-3} is continuously subjected to (1) heat treatment, (2) cooling and (3) false twisting or draw-false twisting. The apparatus used comprises a feed yarn creel (8), a false twisting heater (13) and an optional stabilizing heater, a false twisting element (14) and a winder (16), wherein a heat-treating heater (9) of the non-contact type is arranged upstream of the false twisting heater (13) and between the false twisting heater (13) and the feed yarn creel (8), at a height substantially equal to the height of the feed yarn creel (8) so that the heat-treating heater (9) confronts the false twisting heater (13). A false-twisted polyester yarn having good dyeing properties and mechanical and thermal properties can be produced at a high efficiency and with a good operation adaptability.

Fig. 6



PROCESS AND APPARATUS FOR PRODUCING EASILY
DYEABLE POLYESTER FALSE-TWISTED YARNS

BACKGROUND OF THE INVENTION

This invention relates to a process for producing a false-twisted polyester yarn wherein an as-spun polyester yarn is subjected in succession to heat treatment, cooling
5 and then false twisting or draw-false twisting, and an apparatus for carrying out this process.

More particularly, the present invention relates to a process for producing a false-twisted polyester yarn having a practically sufficient tenacity and a good dyeability,
10 particularly such that the false-twisted polyester yarn is capable of being dyed under normal pressure, wherein a yarn consisting of an as-spun polyester fiber having a mean birefringence index (Δn) of at least 15×10^{-3} but less than 150×10^{-3} , especially one which has been spun at a spinning
15 speed of at least 2,500 m/min but less than 7,000 m/min is subjected to (1) heat treatment, (2) cooling and (3) false twisting or draw-false twisting in succession, and also relates to an apparatus suitable for carrying out this process.

20 Polyester fibers are excellent in mechanical and thermal properties and they have been used in not only the field of clothing articles but also the field of industrial materials. However, the polyester fibers are poor in the dyeability, and especially, fibers composed of a polyethylene
25 terephthalate homopolymer are difficult to dye and they can be dyed only under a high pressure at a high temperature such as about 130°C.

As means for improving this poor dyeability of polyester fibers, there has been proposed a method in which a carrier
30 is added to a dyeing liquor. However, this method has problems in that the carrier is irritating, the operation environment is contaminated and worsened, disposal of the waste dyeing liquor is difficult and the color fastness is

degraded.

It is known that the dyeability of polyester fibers can be improved by copolymerizing polyethylene terephthalate with isophthalic acid having a metal sulfonate group or
5 polyether. However, these modified polyester fibers still cannot be dyed under normal pressure.

These defects of the conventional polyester fibers are observed in not only flat yarns but also false-twisted yarns.

10 SUMMARY OF THE INVENTION

It is a primary object of the present invention to provide a process and an apparatus for producing a false-twisted polyester yarn having a good dyeability, particularly being capable of being dyed under normal
15 pressure to give an excellent color fastness and retaining excellent mechanical and thermal properties of polyester fibers, at a high efficiency and with a good operation adaptability.

Other objects and advantages of the present invention
20 will be apparent from the following description.

In accordance with one fundamental aspect of the present invention, there is provided a process for the production of a false-twisted polyester yarn, which comprises subjecting a yarn consisting of an as-spun polyester fiber
25 having a mean birefringence index (Δn) of at least 15×10^{-3} but less than 150×10^{-3} to (1) heat treatment, (2) cooling and (3) false twisting treatment or draw-false twisting in succession.

In accordance with another fundamental aspect of the
30 present invention, there is provided a false twisting apparatus which comprises a feed yarn creel, a false twisting heater and an optional stabilizing heater, a false twisting element and a winder, wherein a heat-treating heater of the non-contact type is arranged upstream of the false twisting
35 heater and between the false twisting heater and the feed yarn creel, at a height substantially equal to the height of the feed yarn creel so that the heat-treating heater

confronts the false twisting heater.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a diagram illustrating one embodiment of the spinning and winding device for a polyester yarn;

5 Fig. 2 is a graph illustrating the relationship between the spinning speed (m/min) and the degree of crystallinity ($\chi_c\%$) of the yarn before the heat treatment;

Fig. 3 is a graph illustrating the relationship between the spinning speed (m/min) and the mean birefringence index
10 (Δn) of the yarn before the heat treatment;

Figs. 4 and 5 are graphs illustrating the relationship between the heat treatment time and the degree of crystallinity ($\chi_c\%$) of a polyethylene terephthalate fiber and the relationship between the heat treatment time and
15 $(\tan \delta)_{\max}$ and $T_{\max}$ ($^{\circ}\text{C}$), respectively, which are observed when a polyethylene terephthalate fiber spun at a spinning speed of 3,500 m/min is heat-treated in air maintained at 260°C at an elongation ratio of 12%, each numerical value in Fig. 5 representing the heat treatment time (second);

20 Fig. 6 is a diagram illustrating another embodiment of the process of the present invention in which a twisted yarn is treated by using a heat-treating heater of the contact type;

Fig. 7 is a diagram showing a modified embodiment of
25 Fig. 6 where the treatment of a twisted yarn is carried out by using a heat-treating heater of the non-contact type;

Fig. 8 is a diagram illustrating an embodiment of the process of the present invention, in which a crimp-setting treatment by a stabilizing heater is carried out subsequently
30 to the false twisting or draw-false twisting treatment;

Fig. 9 is a diagram showing another embodiment of the process of the present invention, in which the yarn is heat-treated by a slit or hollow tubular heat-treating heater of the non-contact type.

35 Fig. 10 is a diagram illustrating one example of the conventional false twisting apparatus provided with a pre-heating heater;

Figs. 11 and 12 are diagrams showing embodiments of the apparatus of the present invention in which heat treatment, cooling and false twisting or draw-false twisting are carried out in a continuous manner;

5 Fig. 13 shows a $\tan \delta$ -temperature curve of a polyester fiber, in which the logarithms of $\tan \delta$ are plotted on the ordinate and the temperatures ($^{\circ}\text{C}$) are plotted on the abscissa and in which (A) shows the false-twisted yarn obtained according to the process of the present invention,
10 (B) shows the drawn yarn prepared according to the conventional process, (C) shows the as-spun yarn (i.e., undrawn yarn) spun at a spinning speed of 1,500 m/min and (D) shows the $\tan \delta$ -temperature curve of the as-spun yarn (P.O.Y.) spun at a spinning speed of 3,000 m/min;

15 Fig. 14 is an example of an interference fringe pattern used for measuring the distribution of the refractive index ($n_{\parallel}$ or $n_{\perp}$) in the direction of the radius of the cross-section of a polyester fiber, in which (a) is a view showing the cross-section and (b) is a view showing an
20 interference fringe pattern; and

Fig. 15 is an example of the X-ray diffraction-intensity curve of a polyester fiber, in which (a) represents the crystalline region and (b) represents the amorphous region.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

25 The "polyester fiber" used in the present invention means not only a fiber made of a polyethylene terephthalate homopolymer but also a fiber made of a copolyester comprising ethylene terephthalate as the main repeating unit component and up to 15% by weight of a third copolymerized component.
30 As the third component, at least one member selected from isophthalic acid, adipic acid, oxalic acid, trimellitic acid, pyromellitic acid, p-hydroxybenzoic acid, 2,6-naphthalene-dicarboxylic acid, 5-sodium-sulfoisophthalic acid, sebacic acid, azelaic acid and 2,5-dimethyl-
35 -terephthalic acid may be used instead of a part of terephthalic acid, and at least one member selected from diethylene glycol, propylene glycol, 1,4-butanediol, 1,4-

-dihydroxymethylcyclohexane and polyoxyethylene glycol may be used instead of a part of ethylene glycol.

Furthermore, a fiber of a polymer such as mentioned above used in the present invention may comprise additives customarily added to synthetic fibers, such as a delustering agent, an antistatic agent and a stabilizer.

The dyeability of a fiber of a polyester comprising main repeating units of ethylene terephthalate and a third copolymerized component as mentioned above is improved over the dyeability of a fiber of a homopolyester of ethylene terephthalate, and the degree of the improvement of the dyeability varies according to the kind of the copolymerized component and the weight proportion thereof. More specifically, of components to be copolymerized instead of a part of terephthalic acid, an acid free of an aromatic ring, such as adipic acid or sebacic acid, gives a higher degree of the improvement of the dyeability than an acid containing an aromatic ring, and of acids containing an aromatic ring, an acid having a substituent as a side chain on the aromatic ring gives a higher degree of the improvement of the dyeability than an aromatic ring-containing acid free of such a substituent. Of components to be copolymerized instead of a part of ethylene glycol, a component having a higher molecular weight, such as polyoxyethylene glycol, gives a higher degree of the improvement of the dyeability than a component having a lower molecular weight, such as diethylene glycol. Ordinarily, the larger the weight proportion of the third component, the higher the degree of the improvement of the dyeability.

In the case where the dyeability of a polyester fiber is improved by copolymerization of a third component such as mentioned above, with increase of the proportion of the third component, spinning becomes difficult and the manufacturing cost is increased. Furthermore, the thermal and mechanical properties of the obtained copolyester fiber are lower than those of a fiber of a polyethylene terephthalate homopolymer. Moreover, if the weight

proportion of the third copolymerized component exceeds 15%, the melting point is drastically lowered. For example, when at least 16% by weight of isophthalic acid is copolymerized as a part of terephthalic acid and the formed copolyester is spun and drawn according to customary procedures, the melting point of the resulting polyester fiber is 230°C or lower, and the heat resistance is drastically degraded with reduction of the mechanical properties. Accordingly, in the present invention, from the viewpoint of the adaptability to the heat treatment or the false twisting or draw-false twisting treatment, the weight proportion of the third copolymerized component should be up to 15%, preferably up to 5%, more preferably 0%. Namely, a polyethylene terephthalate homopolymer is most preferred.

The polyester yarn used in the present invention is a multifilament yarn consisting of at least two single filaments. The size of the single filament is 0.01 to 10 deniers and the cross-section of the single filament may be either circular or non-circular.

An as-spun polyester yarn having a Δn value of at least 15×10^{-3} but less than 150×10^{-3} , which is used in the present invention, may be obtained by performing spinning and winding at a spinning speed of at least 2,500 m/min but less than 7,000 m/min, for example, in an apparatus as shown in Fig. 1. In Fig. 1, reference numerals 1, 2, 3, 4, 5 and 6 represent a spin head, a spinneret, a spun filament being solidified, a fluid sucking device for cooling and sucking a bundle of filaments being solidified, a wound yarn package and a friction roll rotated at a surface speed equal to the winding speed.

By the term "spinning speed" is meant a surface speed of a winding friction roll 6 when the spinning-winding operation is carried out according to the apparatus shown in Fig. 1.

The spinning operation conducted at a spinning speed of 7,000 m/min or higher is not advantageous from the industrial viewpoint because the equipment cost of the winding device

is increased and close attention should be paid to the control and maintenance of various conditions at the spinning step. At the present, therefore, spinning speeds of less than 7,000 m/min are advantageous.

5 The as-spun polyester yarn having a Δn value of at least 15×10^{-3} but less than 150×10^{-3} , which is obtained by the above-mentioned spinning operation, is subjected to the heat treatment without passage through any special drawing step prior to the heat treatment.

10 The heat treatment of the present invention is accomplished, for example, by heat-treating the polyester yarn having the above-mentioned Δn value in a heated tubular heater or slit heater without being contacted with the surface of the heater; passing the yarn through heated air
15 or super-heated steam or allowing the yarn to travel while contacting it with a heated metal plate.

When the yarn is passed through the heated tubular or slit heater, the temperature of the heater is adjusted to 190 to 300°C. An optimum heat treatment temperature varies
20 depending upon such factors as the Δn value of the fiber, the composition of the copolymer, the heat treatment time, the fiber elongation ratio, the fineness of the single filament and the fineness of the yarn.

Fig. 3 shows the relationship between the spinning
25 speed (m/min) and the Δn value of a 35-d/7-f multi-filament yarn having a filament section of a circular shape, which is obtained by spinning a polyethylene terephthalate homopolymer having an intrinsic viscosity of 0.63 dl/g as measured at 35°C in a 2/1 mixed solvent of phenol/tetrachloroethane at
30 various spinning speeds by using the spinning apparatus shown in Fig. 1. From Fig. 3, it is seen that the spinning speed providing a Δn value of 50×10^{-3} is about 4,000 m/min and the spinning speed providing a Δn value of 15×10^{-3} is about 2,500 m/min. Fig. 2 shows the relationship between
35 the spinning speed (m/min) and the degree of crystallinity χ_c (%) determined from the X-ray diffraction curve, which is observed when spinning is carried out in the same manner as

described above. From Fig. 2, it is seen that a polyethylene terephthalate fiber spun at a spinning speed of at least about 4,000 m/min, that is, a polyethylene terephthalate fiber having a Δn value of at least 50×10^{-3} , has a X_c value of at least 50%, and the structure of the fiber is substantially completed. However, a polyethylene terephthalate fiber spun at a spinning speed of at least about 2,500 but less than about 4,000 m/min may be regarded as an incomplete fiber in which the structure of the fiber is being formed. Accordingly, the polyester fiber having a Δn value of at least 15×10^{-3} but less than 50×10^{-3} , that is, the polyester fiber spun at a spinning speed of at least about 2,500 but less than about 4,000 m/min, is different from the polyester fiber having a Δn value of at least 50×10^{-3} , that is, the polyester fiber spun at a spinning speed of at least 4,000 m/min, and should be drawn at the heat treatment. A polyester fiber having a Δn value of less than 15×10^{-3} , that is, a polyester fiber spun at a spinning speed of less than about 2,500 m/min, is composed substantially of an amorphous portion and the degree of orientation of the molecule chain is low. Therefore, if this polyester fiber is subjected to the heat treatment according to the present invention, partial fusion is caused and the tenacity and elongation are extremely low.

Since a polyethylene terephthalate homopolymer fiber having a Δn value of at least 50×10^{-3} has a substantially completed fiber structure, when the fiber is passed through a tubular or slit heater maintained at a temperature of 220 to 300°C over a period of 0.4 to 2 seconds while adjusting the fiber elongation ratio in the range of from -10% to +4% during the heat treatment, the heat-treated fiber comes to have an increased degree of crystallinity and an increased refractive index. Namely, the fiber structure is more completed. Moreover, the structure of the amorphous region dominating the dyeability of the fiber is relaxed so that the fiber can be dyed even under normal pressure with a disperse dye. The dynamic loss tangent ($\tan \delta$)-temperature

characteristic is suitable for defining the structure of the amorphous portion.

There have been reported several studies made on the relationship between the dyeability of a fiber with a
5 disperse dye and the viscoelasticity of the fiber [for example, K. Kamide and S. Manabe, "Fine Structure of Amorphous Region of Fiber Revealed by Dynamic Dispersion", Sen-i Gakkaishi, 34, page 70 (1978)]. According to these studies, it is generally considered that the larger the
10 value of $\tan \delta$ relating to a mechanical absorption due to the microbrownian movement of the main chain and the lower the temperature position of the mechanical absorption, the more improved the dyeability. According to our study, it has been found that parameters of a polyester fiber before
15 the false twisting treatment or the draw-false twisting treatment, which are preferred from the viewpoint of the fine structure, are as follows. Namely, the peak value of $\tan \delta$, i.e., $(\tan \delta)_{\max}$, in the $\tan \delta$ -temperature curve is at least 0.10, the temperature $T_{\max}$ at which $\tan \delta$ shows a
20 peak is not higher than 115°C, the value of $\tan \delta$ at 220°C, i.e., $\tan \delta_{220}$, is not more than 0.055, the value of c is at least 50% and the value of Δn is at least 35×10^{-3} . If a fiber having such parameters is subjected to the false twisting treatment or draw-false twisting treatment, a fiber
25 dyeable under normal pressure can be obtained. An as-spun polyester fiber spun at a spinning speed of less than about 4,500 m/min have the $(\tan \delta)_{\max}$ and $T_{\max}$ values falling within the above-mentioned ranges, but $\tan \delta_{220}$ exceeds 0.055 and both or either of χc and Δn is less than the above
30 lower limit and the mechanical properties are low and the stability against heat is insufficient. If this polyester fiber is subjected to the false twisting treatment or draw-false twisting treatment, the structure is greatly changed by influences of heat received during the treatment,
35 $(\tan \delta)_{\max}$ becomes less than 0.14 and $T_{\max}$ becomes higher than 130°C, and the false-twisted yarn cannot be dyed under normal pressure.

The polyester fiber heat-treated according to the process of the present invention is characterized as possessing a $(\tan \delta)_{\max}$ value of at least 0.10, a $T_{\max}$ value not higher than 115°C, a $\tan \delta_{220}$ value not more than 0.055, a χ_c value of at least 50% and a Δn value of at least 35×10^{-3} , and, if cooling described below is performed, even after the false twisting treatment or draw-false twisting treatment, the polyester fiber can be dyed under normal pressure.

The conditions of the heat treatment of an as-spun fiber having a Δn value of at least 50×10^{-3} but less than 150×10^{-3} for obtaining an easily dyeable polyethylene terephthalate fiber having the above-mentioned fine structure are as described hereinbefore, when the fiber is passed through a tubular or slit heater. In the process of the present invention in which the cooling treatment and the false twisting treatment or draw-false twisting treatment is carried out successively after the heat treatment, from the viewpoints of the cooling time, the time required for the false twisting or draw-false twisting treatment, the capacity of the apparatus and the properties and quality of the obtained false-twisted yarn, it is preferred that the heater temperature be 230 to 270°C, more preferably 240 to 260°C, the heat treatment time be 0.4 to 1.5 seconds, more preferably 0.6 to 1.3 seconds, and the elongation ratio be -8 to +3%, more preferably -6 to +1%.

When the fiber to be heat-treated is a copolyester fiber, a temperature lower than the above-mentioned heat treatment temperature by the difference between the melting point of the polyethylene terephthalate fiber and the melting point of the copolyester fiber is adopted for the heat treatment. For example, the melting point of a fiber obtained by copolymerizing polyethylene terephthalate with 5% by weight of isophthalic acid and spinning the copolyester at a spinning speed of 6,000 m/min is 247°C, which is lower by about 10°C than the melting point of a fiber of a polyethylene terephthalate homopolymer. Accordingly, a

temperature suitably adopted for the heat treatment in the tubular heater is 230 to 250°C. The melting point of a fiber obtained by copolymerizing polyethylene terephthalate with 12% by weight of isophthalic acid and spinning the
5 copolyester in the same manner as described above is 232°C, which is lower by about 25°C than the melting point of the fiber of a polyethylene terephthalate homopolymer, and a temperature suitable for the heat treatment of the fiber of this copolyester is 215 to 235°C. As is seen from this
10 reduction of the melting point, copolyesters as described above are sensitive to heat, and therefore, in the heat treatment of fibers of these copolyesters, closed attention should be paid to the control of the heat treatment temperature. The treatment time and elongation ratio to be
15 adopted for the heat treatment of copolyester fibers may be the same as those adopted for the heat treatment of fibers of a polyethylene terphthalate homopolymer.

The structure of an ordinary as-spun polyester fiber having a Δn value of at least 15×10^{-3} but less than
20 50×10^{-3} and consisting of single filaments having a circular section and a size of at least 1 denier is not completed and the χ_c value is low. In the present invention, such a fiber should be drawn by 5 to 200% at the heat treatment. If the heat treatment is carried out
25 without effecting this drawing, crystals are not sufficiently grown or developed, and therefore, the fiber is partially fused and the mechanical properties are drastically degraded.

However, if the above-mentioned fiber is heat-treated while drawing it by 5 to 200%, fusion of the fiber is not
30 caused, and there is obtained a fiber to be preferably subjected to the false twisting treatment or draw-false twisting treatment in the present invention, in which the $(\tan \delta)_{\max}$ value is at least 0.10, the $T_{\max}$ value is less than 115°C, the $\tan \delta_{220}$ value is less than 0.055, the χ_c
35 value is at least 50% and the Δn value is at least 50×10^{-3} .

The temperature adopted for heat-treating a polyester fiber spun at a spinning speed of at least 2,500 m/min but

less than 4,000 m/min may be the same as the temperature to be adopted for heat-treating a polyethylene terephthalate homopolymer fiber spun at a spinning speed of at least 4,500 m/min. However, if the heat treatment is carried out
5 in a tubular heater or in heated air, it is preferred that the heat treatment temperature be in the range of 190 to 270°C, more preferably 200 to 260°C.

Fig. 4 illustrates the relationship between the heat treatment time (second) and the χ_c value (%) of the fiber,
10 which is observed when a polyethylene terephthalate homopolymer fiber spun at a spinning speed of 3,500 m/min is heat-treated in air heated at 260°C under an elongation ratio of 12%. From Fig. 4, it is seen that the χ_c value is increased as the treatment time is prolonged and if the heat
15 treatment time is 0.2 second, the χ_c value is substantially equal to the χ_c value of the fiber spun at a spinning speed of 4,000 m/min, that is, 50%. It also is seen that the χ_c value is gradually increased with prolongation of the treatment time and the χ_c value is 72% if the treatment time
20 is 0.77 second. Fig. 5 illustrates the relationship of the treatment time to $(\tan \delta)_{\max}$ and $T_{\max}$ values, which is observed when the above-mentioned fiber is heat-treated in the same manner as described above. The numerical values in Fig. 5 represent the heat treatment time (seconds). From
25 Fig. 5, it is seen that with prolongation of the treatment time, $(\tan \delta)_{\max}$ decreases but $T_{\max}$ increases, and that if the treatment time is 0.2 to 0.3 second or longer, $(\tan \delta)_{\max}$ changes only to a minor extent but $T_{\max}$ decreases. Namely, the heat treatment time region of up to 0.2 - 0.3
30 second is the region causing the structural change conventionally considered to be due to the heat treatment, that is, the region where the structure is made dense by the heat treatment. If the heat treatment time is further prolonged beyond the above region, crystals are developed but the
35 amorphous portion is relaxed. This phenomenon is one discovered for the first time by us. Accordingly, in case of a polyester yarn spun at a spinning speed of at least

2,500 m/min but less than 4,000 m/min, it is necessary that the heat treatment time should be longer by at least 0.2 second than the heat treatment time for the polyester yarn spun at a spinning speed of at least 4,000 m/min, and thus,
5 it is preferred that the polyester yarn be heat-treated for 0.4 to 2.0 seconds.

In case of a copolyester yarn spun at a spinning speed of at least 2,500 m/min but less than 4,000 m/min, it is preferred that the heat treatment temperature may be lowered
10 according to the proportion of the copolymerized component as described above with respect to the polyester yarn spun at a spinning speed of at least 4,000 m/min.

Incidentally, the $\tan \delta$ -temperature characteristics and the methods for measuring χ_c and Δn will be described
15 hereinafter.

The foregoing heat treatment conditions are those for an ordinary polyester fiber in which the section of the filament has a circular shape and the size of the single filament is at least 1 denier. In case of a polyester fiber
20 having a non-circular section such as a triangular or pentagonal section or a polyester fiber having a circular section but a size smaller than 1 denier, since the outer periphery of the fiber per unit sectional area is larger than that of the above-mentioned ordinary fiber and the
25 influence of heat on the fiber is increased, it is permissible that the heat treatment temperature may be lowered by about 5 to about 10°C or the treatment time may be shortened by 0.1 to 0.2 second.

In the process of the present invention, the heat
30 treatment may also be carried out in super-heated steam or a mixed atmosphere of super-heated steam and hot air. In this case, the heat treatment time and the fiber elongation ratio during the heat treatment are the same as in case of the heat treatment conducted in the tubular or slit heater or
35 heated air, but it is preferred that the heat treatment temperature be selected within the range of from (230 - 50Z)°C to (290 - 50Z)°C in which Z stands for the

mole fraction of super-heated steam in the heat-treating medium. Since steam has a larger heat capacity than that of air and exerts a higher heat-treating effect on the fiber, even if the heat treatment temperature is lower than that adopted when the heat-treating medium consists of air alone,
5 a satisfactory heat-treating effect can be attained.

In the process of the present invention, the as-spun polyester filament yarn having a Δn value of at least 15×10^{-3} but less than 150×10^{-3} may be heat-treated in
10 the twisted state. In this case, it is preferred that the twist number be at least 3% of the twist number at the false twisting treatment or draw-false twisting treatment. The twist number T at the false twisting treatment or draw-false twisting treatment is 80 to 120% of

$$\left(\frac{2300}{\sqrt{d}} + 590 \right) \text{ t/m}$$

in which d represents the denier of the false-twisted yarn, and this twist number is the number of twists present between the false twisting heater and the false twisting
20 element. Of course, this twisted polyester yarn may be heat-treated by passing it through the tubular heater without contact with the heater or by passing it through heated air, super-heated steam or a mixture thereof. However, if the spinning speed is at least 4,000 m/min, the
25 resulting yarn may be contacted with the heater during the heat treatment. In contrast, in case of an untwisted yarn, the contact with a heated metal plate or the like is not preferred because formation of fluffs or local fusion of the fiber cannot be avoided. Even in case of a twisted as-spun
30 fiber, if the fiber is obtained at a spinning speed less than 4,000 m/min, the structure of the fiber is incomplete as pointed out hereinbefore, fusion or formation of fluffs is readily caused, and therefore, it is not preferred to heat-treat the fiber while contacting it with a heated metal
35 plate. In the case where a yarn spun at a spinning speed of at least 4,000 m/min from a polyethylene terephthalate homopolymer is heat-treated in the twisted state while

contacting it with a heated metal plate, even if the heat treatment is carried out at a high speed, the filaments of the yarn are not caught or rising of some filaments is not caused, and therefore, reduction of the operation

5 adaptability can be avoided. Furthermore, in this case, since the heat conduction efficiency is improved, the heat treatment time can be shortened to about 0.2 second.

Accordingly, the length of the heater can be shortened. In this case, if the heat treatment is carried out under no
10 substantial drawing, the dyability is further improved.

As the means for twisting the yarn in this embodiment, there may be adopted a method in which the yarn is twisted before the heat treatment, but, when the false twisting treatment or draw-false twisting treatment is conducted
15 successively after the heat treatment and cooling as in the present invention, there may preferably be adopted a manner wherein twists given by the false twisting are extended to the heat treatment zone.

Figs. 6 and 7 illustrate embodiments in which the
20 process of the present invention is carried out while twists given at the draw-false twisting step are extended to the heat treatment zone.

Referring to Fig. 6, a travelling yarn 7 unwound from a wound yarn package 5 is passed through a feed roller (R_1) 8
25 and through a heat-treating heater 9 provided with a metal plate while being contacted therewith. When the yarn 7 is passed through the heat-treating heater 9, twists propagated from a false twisting element 14 are given to the yarn 7. After the yarn 7 is heated in the heat-treating heater 9 in
30 the twisted state, the yarn 7 is cooled by the atmosphere in the room and is guided into a false twisting heater 13 through a twist stop guide 11. If this cooling treatment is not effected and the twist stop guide 10 is not disposed, the drawing tension is extended into the heat-treating
35 heater 9. In the false twisting heater 13, the yarn is heated to a temperature higher than the glass transition point to initiate drawing. The point at which drawing is

initiated is the drawing point 12. After passage through the false twisting heater 13, the yarn is cooled again by the atmosphere in the room, and just after passage through the false twisting element 14, the yarn is untwisted and is
5 then wound through a delivery roller 15 to form a package 17 of the drawn and false-twisted yarn. In Fig. 6, reference numeral 16 represents a winding friction roller (R_3).

Fig. 7 is a diagram illustrating another embodiment of the process of the present invention. The apparatus shown
10 in Fig. 7 is the same as the apparatus shown in Fig. 6 except that the heat-treating heater 9 is of the non-contact heating type.

In the case where the heat treatment is carried out in the twisted state, the heat treatment temperature and
15 drawing ratio are the same as those adopted in the heat treatment conducted in heated air. If the yarn is contacted with the heater surface, the heat treatment time may be shortened by about 0.2 second as compared with the heat-treatment time required when the fiber is not contacted
20 with the heater surface.

It is only when the polyester yarn is passed through the drawing step after spinning that the Δn value of the polyester fiber exceeds 150×10^{-3} , and any as-spun polyester yarn cannot have a Δn value exceeding 150×10^{-3} .
25 More specifically, as shown in Fig. 3, in case of the as-spun yarn, the Δn value is at a peak when the spinning speed is about 7,000 m/min and the peak Δn value is about 120×10^{-3} . In the case where the filament denier is less than 1 denier, since the draft ratio is increased at the
30 spinning step, even an as-spun yarn has a Δn value larger than that shown in Fig. 3 but the largest value is less than 150×10^{-3} .

It is very difficult to prepare an easily-dyeable false-twisted polyester yarn from a polyester fiber having
35 a Δn value of at least 150×10^{-3} , that is, a polyester fiber which has been drawn after the spinning step, according to a process similar to that of the present

invention. In the fiber which has been drawn after the spinning step, the fine structure thereof, especially the structure of the amorphous region, is very dense and compact, and ordinarily, as shown in Fig. 13, the $(\tan \delta)_{\max}$ value is about 0.1 and the $T_{\max}$ value is at least 130°C. When it is intended to improve the dyeability of a spun and drawn polyester yarn having a Δn value of at least 150×10^{-3} by the heat treatment, it is necessary to relax the yarn by about 50% at the heat treatment, and in this case, even if the dyeability is improved, the mechanical properties are low and, for example, the tenacity is less than 2.5 g/d. Moreover, uneven dyeing is readily caused in the longitudinal direction of the yarn. Accordingly, it is practically impossible to prepare an easily-dyeable false-twisted polyester yarn from a polyester fiber having a Δn value of at least 150×10^{-3} according to the process of the present invention.

In the present invention, it is indispensable that the heat-treated polyester yarn be cooled continuously after the heat treatment. By the term "continuously" used in the present invention, it is meant that after one step has been completed, a yarn is continuously transferred to the subsequent step without winding of the yarn, i.e., without interruption of the yarn travelling. Namely, the yarn which has been heat-treated in the above-mentioned manner is transferred to the cooling step without winding of the yarn.

Either natural cooling or forced cooling may be adopted for cooling the heat-treated yarn.

By the term "natural cooling", it is meant that the yarn is naturally cooled in the following manner. Ordinarily, the process of the present invention is carried out according to embodiments illustrated in Figs. 6, 7, 8 and 9. In the embodiment illustrated in Figs. 8 and 9, the yarn 7 travels in the room temperature atmosphere during the passage of from the slit heater 11 to the false twisting heater 11. In this embodiment, by the term "natural cooling", it is meant that the yarn 7 is cooled in the room

temperature atmosphere while it travels from the outlet of the slit heater 9 to the inlet of the false twisting heater 13. Similarly, in the embodiment illustrated in Figs. 6 and 7, the yarn 7 travels in the room temperature atmosphere during the passage of from the heater 9 to the false twisting heater 13. In this embodiment, by the term "natural cooling", it meant that the yarn 7 is cooled while it travels from the outlet of the slit heater 9 to the inlet of the false twisting heater 13.

Adoption of natural cooling is advantageous in that a cooling device need not be disposed and the deviation of the quality among lots can be reduced. In case of natural cooling, the cooling time (A) is important, and a good dyeability can always be attained if natural cooling is carried out so that the cooling time (A) satisfies the following requirement:

$$A \geq \frac{7 - V}{4(V - 2.0)} \text{ (seconds)}$$

wherein V stands for the spinning speed (km/min) for the polyester yarn.

By the term "cooling time (A)" used herein is meant a time required for the yarn to travel from the outlet of the heat-treating heater to the inlet of the false twisting heater.

The reason why it is preferred that the cooling time (A) should satisfy the above requirement is as follows. As pointed out hereinbefore, in an as-spun polyester yarn having a Δn value of at least 15×10^{-3} but less than 50×10^{-3} , that is, a polyester yarn spun at a spinning speed of at least about 2,500 m/min but less than about 4,000 m/min, the χ_c value is small and the structure of the fiber is incomplete, and the yarn should be drawn in the heat treatment step. When the yarn is drawn in the heat treatment step, if the yarn is subjected to the false twisting treatment or draw-false twisting treatment after the heat treatment without performing cooling, especially in case of a small elongation ratio, the molecule chain of the fiber which has been drawn and oriented in the heat treatment

step is relaxed and the mechanical properties are often reduced. Accordingly, in the case where the heat treatment is carried out under elongation, that is, in case of a yarn spun at a spinning speed of at least about 2,500 m/min but
5 less than about 4,000 m/min, cooling is especially preferred, and a relatively long cooling time is preferred. Drawing is not particularly necessary in case of a polyester yarn having a Δn value of at least 50×10^{-3} , that is, a polyester yarn spun at a spinning speed of at least about 4,000 m/min.

10 In this case, the lower the spinning speed, the less the relaxation of the amorphous region caused by the heat treatment, and the higher the spinning speed, the larger the relaxation of the amorphous region caused by the heat treatment. Accordingly, when the spinning speed is higher,
15 the improvement of the dyeability by the heat treatment is increased. The reason is that in the as-spun polyester yarn spun at a spinning speed of at least about 4,000 m/min, the higher the spinning speed, the more relaxed the amorphous region, and the dyeability is accordingly improved. Even
20 this as-spun yarn, however, cannot be dyed under normal pressure before the heat treatment of the present invention.

As is seen from the foregoing description, in case of the as-spun yarn spun at a spinning speed of at least about 4,000 m/min, a higher spinning speed results in a better
25 dyeability, and therefore, the tendency of the change of the structure in the fiber during the period of from the termination of the heat treatment to the initiation of the false twisting treatment or draw-false twisting treatment is smaller as the spinning speed is higher. Accordingly, in
30 the case where the easily-dyeable structure formed at the heat treatment step is set by cooling, a longer cooling time becomes necessary as the spinning speed is lower. If the yarn is sufficiently cooled below 70°C, namely below the second transition point of the polyester after the heat
35 treatment, the structure is changed and the easily-dyeable structure of the amorphous region is completely formed. If cooling is not sufficient, the easily-dyeability structure

is not completed, and if the yarn is subsequently guided to the false twisting or draw-false twisting step in the state where the easily dyeable structure is still incomplete, the easily dyeable structure being set is destroyed at the false twisting step or draw-false twisting step. In case of a fiber where the easily dyeable structure is completed by cooling after the heat treatment, even if the yarn is successively guided to the false twisting or draw-false twisting step, the good dyeability of the false-twisted yarn is maintained at a high level.

Ordinarily, by the term "natural cooling" is meant cooling conducted in a room temperature atmosphere, and the temperature of the room temperature atmosphere is in the range of $20^{\circ}\text{C} \pm 15^{\circ}\text{C}$.

In case of forced cooling, the cooling time is shorter than in natural cooling, and forced cooling is advantageous in that the speed of the false-twisted yarn can be increased and the structure of the entire apparatus of the present invention can be made compact.

By "forced cooling" is meant cooling to be conducted by using any apparatus or device for increasing the cooling effect and shortening the cooling time. From the viewpoint of the cooling effect, a lower cooling temperature is preferred, and ordinarily, it is preferred that forced cooling be carried out at a temperature lower than the level causing dewing resulting in yarn unevenness, for example, at a temperature lower by 5 to 10°C than room temperature. As the forced cooling method, there can be mentioned a method in which a cold plate maintained at a temperature lower by 5 to 10°C than room temperature is inserted, for example, between the slit heater 9 and first feed roller (R_1) shown in Fig. 9, and a method in which air maintained at a temperature lower by 5 to 10°C than room temperature is blown against the yarn while it travels from the outlet of the slit heater 9 to the inlet of the false twisting heater 11. Of course, the effect attained by forced cooling is the same as the above-mentioned effect attained by natural

cooling.

The polyester yarn which has thus been heat-treated and subsequently cooled is continuously subjected to the false twisting treatment or draw-false twisting treatment.

5 By the term "draw-false twisting treatment" used in the present invention is meant a so-called in-draw-false twisting treatment where false twisting is carried out while simultaneously effecting drawing (that is, false twisting carried out at a draw ratio higher than 1.0). Furthermore, by the
10 term "false twisting treatment" is meant a false twisting treatment which is carried out at a draw ratio of up to 1.0. The false twisting system employed may be any of the conventional pin type, friction type and apron nip type false twisting systems. It is preferred that the twist
15 number be about 80 to about 120% of

$$\left(\frac{23000}{\sqrt{d}} + 590\right) \text{ t/m,}$$

in which d stands for the calculated denier of the yarn after the false twisting treatment, and that the
20 temperature of the false twisting heater be 180 to 240°C. However, it is preferred that the heater temperature at the false twisting treatment or draw-false twisting treatment be lower than the heat treatment temperature. If the heater temperature at the false twisting or draw-false twisting
25 treatment is higher than the temperature of the preceding heat treatment, it happens that the easily-dyeable structure of the fiber formed at the heat treatment and set at the cooling treatment is greatly changed to a structure of a poor dyeability. Of course, even if the heater temperature
30 at the false twisting treatment or draw-false twisting treatment is lower than the heat treatment temperature, the structure of the fiber is changed more or less, but the good dyeability is not degraded at all.

Whether or not the polyester yarn heat-treated and
35 subsequently cooled is drawn at the false twisting step in the present invention is determined according to the elongation at break of the fiber after cooling. If the

elongation at break of the fiber after cooling exceeds 30%, drawing is effected at the false twisting treatment. In contrast, if the elongation at break of the fiber is not more than 30%, the yarn is ordinarily overfed. As the
5 elongation is high, the draw ratio is increased. The elongation at break of the fiber after cooling is changed according to the spinning speed and the heat treatment conditions, and ordinarily, a higher spinning speed, a higher heat treatment temperature and a higher drawing ratio
10 at the heat treatment result in a lower elongation at break.

Of course, there may be adopted a method in which a stabilizing heater is used at the false twisting treatment or draw-false twisting treatment to effect heat setting of the false-twisted yarn.

15 The fine structure of the false-twisted yarn obtained according to the above-mentioned process of the present invention is characterized in that the amorphous region is relaxed. Namely, it now has been found that the $(\tan \delta)_{\max}$ value determined from the $\tan \delta$ -temperature curve is at
20 least 0.08 and the relationship of $(\tan \delta)_{\max} \geq 1 \times 10^{-2}$ ($T_{\max} - 105$) is established. The false-twisted polyester yarn having the above-mentioned structure for the amorphous region is rendered easily dyeable and capable of being dyed under normal pressure with a disperse dye.

25 By the term "capable of being dyed under normal pressure", it is meant that the amount of the dye adsorbed when the false-twisted yarn obtained according to the process of the present invention is dyed at 100°C for 60 minutes is equal to or larger than the amount of the dye
30 adsorbed when a yarn obtained by subjecting a conventional drawn yarn of a polyethylene terephthalate homopolymer to a customary false twisting treatment is dyed at 130°C for 60 minutes. This property is evaluated according to a method described below. For example, a false-twisted yarn
35 of polyethylene terephthalate copolymerized with a metal sulfonate-containing compound, such as sodium sulfonated isophthalic acid, prepared according to the present

invention, can be dyed with a cationic or basic dye under normal pressure. Incidentally, in the conventional false-twisted polyester yarn, the $(\tan \delta)_{\max}$ value is about 0.10 and $T_{\max}$ value is 130 to 140°C, and this false-twisted yarn cannot be dyed under normal pressure.

In the process of the present invention, the above-mentioned as-spun polyester yarn is continuously subjected to heat treatment, cooling and false twisting or draw-false twisting. This process in which these three steps are continuously conducted is economically advantageous over the process in which these steps are conducted in a discontinuous manner, because the labor cost and energy cost can be reduced and the area occupied by the apparatus as a whole can be decreased. Moreover, handling of the yarn is facilitated and the frequency for a worker to touch the yarn is reduced, resulting in decrease of yarn defects.

The threading property required for carrying out these three steps in a continuous manner is approximately similar to the threading property required for ordinary false twisting or draw-false twisting, and the collecting property of the yarn is rather increased by the heat treatment. Therefore, occurrence of yarn breakage or formation of fluffs is reduced and the operation adaptability is improved.

In a certain conventional false twisting apparatus, there is adopted a system in which a pre-heating heater or heating roller is disposed upstream of a false twisting heater to pre-heat a yarn prior to the false twisting heater. In this conventional technique, the pre-heating treatment is carried out so as to increase the false twisting speed, and the pre-heating temperature is lower than the temperature of the false twisting heater and the pre-heating time is very short. Moreover, since it is necessary to shift the pre-heated yarn to the false twisting heater before it is cooled, the distance between the pre-heating heater and the false twisting heater is short. The process of the present invention cannot be performed in this conventional apparatus.

The process of the present invention will now be described with reference to embodiments illustrated in the accompanying drawings.

Referring to Fig. 8, a yarn 7 unwound from a package 5, which has been spun at a spinning speed of at least 2,500 m/min but less than 7,000 m/min, is heat-treated while it travels through the central portion of a slit heater 9 disposed between second feed rollers (R_0) 8 and first feed rollers (R_1) 10 without being contacted with the heater 9. At this time, since the surface speeds of the second feed rollers (R_0) 8 and first feed rollers (R_1) 10 are set at certain levels, the yarn is heat-treated at a constant draw ratio.

Then, the yarn is sufficiently cooled in a room temperature atmosphere while it travels from the slit heater 9 to the false twisting heater 11, and the easily dyeable structure by the heat treatment is set and completed. The yarn is then introduced into the false twisting or draw-false twisting zone comprising the first feed rollers (R_1) 10, a false twisting heater 11, a false twisting element 12 and first delivery rollers (R_2) 13.

The yarn just coming from the first delivery rollers (R_2) 13 has a very high stretchability but since the residual torque in the yarn is very large, the knitting property of the yarn is sometimes very poor. Accordingly, in order to remove the residual torque, the yarn may be passed through a stabilizing heater 14 in the non-contact state between the first delivery rollers (R_2) 13 and second delivery rollers (R_3) 15. After the torque has thus been reduced, the yarn is brought into contact with a winding friction roll (R_4) 16, whereby the false-twisted yarn or the drawn and false-twisted yarn is wound at a certain winding rate to form a package 17.

We made researches with a view to developing apparatuses for advantageously carrying out the process of the present invention, and it has been found that especially good results can be obtained by a false twisting apparatus which comprises a feed yarn creel, a false twisting heater or a

false twisting heater plus a stabilizing heater and a winder, wherein a heat-treating heater of the non-contact type is arranged upstream of the false twisting heater between the false twisting heater and the feed yarn creel at
5 a height substantially equal to the height of the feed yarn creel so that the heat-treating heater confronts the false twisting heater. In this false twisting apparatus, it is preferred that the heat-treating heater be arranged at a height substantially equal to the height of the false
10 twisting heater.

In an ordinary false twisting apparatus for a synthetic multifilament yarn, a false twisting heater, a false twisting element, an optional stabilizing heater and a winder are arranged in this order along a travel passage for a filament
15 yarn taken out from a package on a feed yarn creel. Recently, with increase of the false twisting speed, a yarn to be treated is pre-heated, or in order to obtain a variety of modified false-twisted yarns such as a fused yarn, a fluffy yarn and a distorted yarn, a yarn to be introduced
20 into a false twisting zone is pre-heated by a heat-treating heater such as a hot plate or a hot roller and is then subjected to the false twisting treatment.

Fig. 10 is a diagram illustrating one example of a conventional false twisting apparatus provided with a heat-
25 -treating heater such as mentioned above. In another conventional false twisting apparatus which is the same as that shown in Fig. 10 except that the false twisting apparatus is not provided with a heat-treating heater A, in order to simplify the operation by a worker, a feed yarn
30 creel B, a winder C, a false twisting heater D, a false twisting element E, a heat-setting heater F and feed rollers r_1 through r_4 are arranged on both the sides of an operation passage G. In the conventional false twisting apparatus provided with the heat-treating heater A as shown in Fig. 10,
35 the heat-treating heater A is arranged above between the feed yarn creel B and the false twisting zone as shown in Fig. 10 so that the operation can be performed in the same

manner as in the above-mentioned false twisting apparatus not provided with the heat-treating heater. In the conventional false twisting apparatus provided with the heat-treating heater, however, formation of fluffs or yarn breakage is frequently caused and no good adaptability to the false twisting operation can be obtained. Furthermore, a sufficient easy dyeability cannot be obtained, and the obtained false-twisted yarn is insufficient in the tight spot, the level dyeing property and the yields of dyeing level. These defects are especially prominent when the heat treatment temperature is elevated or the length of the heat-treating heater is increased for enhancing the heat treatment effect. Recently, the operation speed of the false twisting treatment is increased or a variety of modified false twisted yarns differing in the function and form are prepared, and therefore, development of a false twisting apparatus provided with a heat-treating heater, in which the foregoing defects are eliminated, is eagerly desired.

We made basic studies on the false twisting process including the heat treatment with a view to meeting the above demand, and as the result, it has been found that the heat-treating heater attached in the upper portion complicates the heated air current in the vicinity of the false twisting apparatus and introduces the air current into the feed yarn creel to evaporate an oil from the feed yarn and that by re-adhesion of the evaporated oil to the running yarn and also by false twisting of the yarn in the insufficiently cooled state, the foregoing defects are caused. It has also been found that if the heat-treating heater is arranged at a specific position in a specific direction so that certain requirements are satisfied and if a yarn cooling zone is formed between the heat-treating heater and the false twisting heater, the above demand is completely met.

Thus, the false twisting apparatus of the present invention has been completed based on these findings, which

apparatus comprises a feed yarn creel, a false twisting heater or a false twisting heater plus a stabilizing heater, a false twisting element and a winder, wherein a heat-treating heater of the non-contact type is arranged upstream
5 of the false twisting heater and between the false twisting heater and the feed yarn creel, at a height substantially equal to the height of the feed yarn creel so that the heat-treating heater confronts the false twisting heater, and a yarn cooling zone is formed between the heat-treating
10 heater and the false twisting heater.

The present false twisting apparatus will now be described with reference to embodiments illustrated in the accompanying drawings.

Fig. 11 is a diagram illustrating one embodiment of the
15 present false twisting apparatus and Fig. 12 is a diagram illustrating another embodiment of the present false twisting apparatus. In the drawings, reference numeral 1 represents a feed yarn creel on which feed yarn packages 2 are mounted. A feed yarn 23 in the form of multifilaments is taken out
20 from the feed yarn package 2.

The direction of the feed yarn creel 1 is opposite to the direction of the feed yarn creel in Fig. 10. However, this direction is not particularly critical, so far as the operation of exchanging feed yarn packages 2 on the feed
25 yarn creel 1 is possible. Reference numeral 4 represents a false twisting heater for false-twisting the supplied yarn 3 in the heated state, and ordinarily, a hot plate or hot tube is used as the false twisting heater. A false twisting element 5 is disposed to give false twists to the supplied
30 yarn 3. Reference numeral 6 represents a stabilizing heater for heat-setting the false twist-untwisted state in the supplied yarn 3, and ordinarily, a heater of the non-contact type is used as the stabilizing heater 6. In case of some kinds of synthetic fibers, this stabilizing heater 6 may be
35 omitted. Reference numerals 7, 8 and 9 represent an operation passage, a winder and a heat-treating heater, respectively. As shown in Figs. 11 and 12, the heat-

-treating heater 9 is arranged upstream of the false twisting heater 4 in the running passage of the yarn 3 indicated by arrow X between the false twisting heater 4 and the feed yarn creel 1 at a height substantially equal to the height of the feed yarn creel 1 so that the heat-treating heater 9 confronts the false twisting heater 4. If the heat-treating heater 9 is arranged so that the above-mentioned positional requirements are satisfied, important effects of the present invention are attained as described below. If the heat-treating heater 9 is arranged so that it confronts the false twisting heater 4, the operation can be facilitated by the provision of the operation passage 7 arranged below and between the two heaters 4 and 9. In this case, the heat-treating heater 9 and the feed yarn creel 1 are located on the same side with respect to the operation passage 7. If the position of the heat-treating heater 9 is thus specified, a yarn cooling zone can be formed between the outlet of the heat-treating heater 9 and the inlet of the false twisting heater 4. A heater of the non-contact type is used as the heat-treating heater 9. As the heater of the non-contact type, there are preferably used, for example, a groove-shaped heater in which a yarn is passed through a groove of a heater plate without being contacted therewith, a hollow pipe-shaped heater in which a yarn is passed through the hollow portion of the heater with no contact with the heater wall and a box-shaped heater having a relatively large size, through which a plurality of yarns are passed with no contact with the heater wall. Of course, other heaters of the non-contact type may be used. Since the heat-treating heater 9 is of the non-contact type, the heating efficiency of the heat-treating heater 9 is low. Accordingly, it is preferred that the length of the heat-treating heater 9 be equal to or larger than the length of the false twisting heater 4.

Feed rollers 10, 11, 12, 13 and 14 are rotated at predetermined peripheral speeds to allow the feed yarn 3 to travel and to give a predetermined drawing or relaxation to

the yarn in a preset section. Guide pins 15 are disposed to allow the feed yarn 3 to travel along a predetermined course in co-operation with the feed rollers, while changing the running direction of the yarn 3.

5 In the false twisting apparatus of the present invention, effects described below are attained by dint of the above-mentioned structure. As is seen from the embodiments illustrated in Figs. 11 and 12, the heat-treating heater 9 and false twisting heater 4 are arranged
10 to confront each other, for example, with the operation passage 7 being interposed therebetween, as shown in the drawings. Accordingly, air above the operation passage 7, which is a space interposed between the two heaters 9 and 4, is heated by the heat radiated from both the heaters to form
15 a rising air current in the direction indicated by arrow Y. Therefore, a descending current of cold air flowing in the direction of arrow Z is present on the side of the feed yarn creel 1 on the back of the heat-treating heater 9 and on the back side of the false twisting heater 4. Consequently, the
20 feed yarn package 2 is not allowed to fall in contact with heated air but is rather cooled by cold air, and hence, an oil on the feed yarn is not evaporated and no change of the yarn quality is caused, with the result that at the subsequent false twisting step, formation of fluffs and
25 occurrence of yarn breakage are minimized and a false-twisted yarn having excellent properties can be obtained. In the case where the heat-treating heater 9 is arranged to confront the false twisting heater 4 at the substantially same height, as shown in Fig. 12, the mist of the oil
30 evaporated while the feed yarn 3 is passed through one heater does not adhere to the feed yarn 3 which is being passed through the other heater, and the feed yarn 3 stably travels in the state where an appropriate amount of the oil is uniformly applied to the feed yarn 3. Accordingly, a
35 uniform false-twisted yarn free of tight spots, which is excellent in the dyeability, can be obtained according to the preferred embodiment shown in Fig. 12.

In each of the embodiments shown in Figs. 11 and 12, the feed yarn 3 is sufficiently cooled by natural cooling while it travels from the heat-treating heater 9 to the false twisting heater 4, and there can be obtained a false-
5 -twisted yarn having an excellent dyeability.

Definitions of the structural properties, mechanical properties, false twisting or draw-false twisting properties and other parameters of fibers and yarns used in the present invention and obtained yarns, and methods for determining
10 these parameters, will now be described.

A. Dynamic Mechanical Loss Tangent ($\tan \delta$):

The dynamic mechanical loss tangent ($\tan \delta$) can be measured by using an apparatus for measuring the dynamic viscoelasticity, manufactured by Toyo Baldwin,
15 Rheo-Vibron DDV-IIc, at a frequency of 110 Hz in dry air at a temperature-elevating rate of 10°C/min.

A peak temperature ($T_{\max}$) of $\tan \delta$ and a peak value [$(\tan \delta)_{\max}$] of $\tan \delta$ are obtained from the $\tan \delta$ -
-temperature curve. Typical instances of the $\tan \delta$ -
20 -temperature curve are shown in Fig. 13, in which (A) is a curve of a false-twisted polyester yarn prepared according to the present invention, (B) is a curve of a conventional drawn fiber, (C) is a curve of an undrawn fiber spun at a spinning speed of 1,500 m/min and (D) is a curve of a
25 partially oriented fiber spun at a spinning speed of 3,000 m/min.

B. Degree of Crystallinity (χ_c):

The χ_c value can be determined by measuring the X-ray diffraction intensity in the equatorial direction
30 by the reflection method. The measurement is carried out by using an X-ray generator ("RU-200PL" manufactured by Rigaku Denki), a goniometer ("SG-9R" manufactured by Rigaku Denki), a scintillation counter and a pulse height analyzer. Cu-K α (wavelength $\lambda = 1.5418 \text{ \AA}$) monochromatized by a nickel filter
35 is used for the measurement. A fiber sample is set in a sample holder composed of aluminum so that the fiber axis is perpendicular to the plane of the diffraction. The thickness

of the sample is adjusted to about 0.5 mm.

The X-ray generator is operated at 30 KV and 80 mA. The diffraction intensity is recorded from 7° to 35° of 2θ at a scanning speed of 1°/min, a chart speed of 10 mm/min, a time constant of 1 second, a divergent slit of 1/2°, a receiving slit of 0.3 mm and a scattering slit of 1/2°. The full scale deflection of the recorder is set so that the entire diffraction curve remains on the scale.

Generally, a polyethylene terephthalate fiber has three major reflections on the equatorial line in the range of from 17° to 26° of 2θ at faces of (100), (010) and (110). Fig. 15 is an example of the curve of the X-ray diffraction intensity of a polyethylene terephthalate fiber, in which (a) indicates a portion of the X-ray diffraction intensity attributed to the crystalline region and (b) indicates a portion of the X-ray diffraction intensity attributed to the amorphous region.

A base line is established by drawing a straight line between 7° and 35° of 2θ on the diffraction intensity curve. As shown in Fig. 15, the crystalline portion (a) and the amorphous portion (b) are separated by drawing a straight line along the tail of the lower angle and the tail of the higher angle from the peak point positioned near the angle of 20° of 2θ. The χ_c value is represented by an area analysis method according to the following equation:

$$\chi_c (\%) = \frac{\text{scattering intensity of crystalline portion} \times 100}{\text{total scattering intensity}}$$

C. Mean Birefringence Index (Δn):

According to the interference fringe method using a transmission quantitative type interference microscope (for example, an interference microscope "Interphako" manufactured by Carl-Zeiss Yena Co., East Germany), the distribution of the mean refractive index, observed from the side face of a fiber, can be determined.

The refractive index of fibers is

characterized by a refractive index $n_{\parallel}$ to polarized light having an electric field vector in the direction parallel to the fiber axis and a refractive index $n_{\perp}$ to polarized light having an electric field vector
5 in the direction perpendicular to the fiber axis.

All the measurements described herein are performed by using green radiation (wavelength $\lambda = 546 \text{ m}\mu$). The fiber to be tested is immersed in a sealing medium being inert to fibers and having a refractive index (N)
10 giving a deviation of the interference fringe in the range of 0.2 to 2.0 times the wavelength by using optically flat slide glass and cover glass.

The refractive index (N) of the medium is a value measured at 20°C by an Abbe refractometer
15 using green radiation (wavelength $\lambda = 546 \text{ m}\mu$).

Several filaments are immersed in the sealing medium so that the filaments are not in contact with one another. The fiber should be disposed so that the fiber axis is perpendicular to the optical axis
20 of the interference microscope and the interference fringe. The pattern of the interference fringe is photographed and enlarged at about 1,500 magnifications for analysis.

Referring to Fig. 14, the optical pass
25 difference R is represented by the following formula:

$$R = \frac{d}{D} \lambda = n_{\parallel} \text{ (or } n_{\perp}) - N t$$

wherein N is the refractive index of the sealing medium, $n_{\parallel}$ or ($n_{\perp}$) is the refractive index between the points S' and S" on the periphery
30 of the fiber, t is the thickness between the points S' and S",

λ is the wavelength of the radiation used, D is the distance (corresponding to 1λ) between parallel interference fringes of the background and d is the deviation of the interference fringe
35 by the fiber.

From the optical path differences at

respective portions in the range of from the center (R_0) of the fiber to the periphery (R_1) of the fiber, in which R_1 is the radius of the fiber, the distribution of the refractive index $n_{//}$ or $n_{\perp}$ of the fiber at each portion can be

5 determined. When r is the distance between the center of the fiber and each portion, the refractive index at the center of the fiber, i.e., $X = r/R = 0$, is defined as the mean refractive index $n_{//}(0)$ or $n_{\perp}(0)$. X is 1 at the position on the periphery of the fiber but X is a value of 0
10 to 1 at the other position of the fiber. For example,

$n_{//}(0.8)$ or $n_{\perp}(0.8)$ represents the refractive index at the position of $X = 0.8$. From the mean refractive indexes $n_{//}(0)$ and $n_{\perp}(0)$, the mean birefringence index (Δn) is represented as

15
$$\Delta n = n_{//}(0) - n_{\perp}(0).$$

Incidentally, in Fig. 14, reference numerals 31, 32 and 33 represent the fiber, the interference fringe by the sealing medium and the interference fringe by the fiber, respectively.

20 Furthermore, $n(0.8-0)$ means a difference in n between $X=0$ and $X=0.8$. With a fiber having a modified cross-section, the refractive index determined by the Becke line method is defined as $X=0.8$, and the refractive index of the medium at $R=0$, i.e., $d=0$, observed by an interference
25 microscope, is defined as a refractive index at $X=0$.

D. Dyeability:

The dyeability is evaluated by a dye up-take ratio. A sample is dyed with a disperse dye (Resolin Blue FBL, C.I. Disperse 56, supplied by Bayer AG, West
30 Germany) at a dye concentration of 3% owf and a liquor ratio of 1 to 50 at 100°C. Further, 1 g/l of a dispersing agent (Disper TL) is added to the dyeing liquor and the pH value is adjusted to 6 by addition of acetic acid. After a
predetermined period of time (i.e., one hour), the dyeing
35 liquor is sampled and the amount of the dye left in the dyeing liquor is measured by the absorbance at 625 mμ, and the amount of the dye taken up is calculated by subtracting

the amount of the dye left in the dyeing liquor from the amount of the dye used for the dyeing operation. The dye up-take ratio (%) is calculated by dividing this amount of the dye taken up by the amount employed of the dye and
5 multiplying the result by 100. The sample fiber is formed into a knitted fabric, and the fabric is scoured with 2 g/l of "Scourol FC-250" (supplied by KAO-ATLAS) at 60°C for 20 minutes, dried and conditioned at a relative humidity of 65% and a temperature of 20°C for 24 hours, and the sample
10 fabric is then tested.

When a typical conventional drawn and false-twisted polyester yarn is dyed under the above conditions at 130°C for 60 minutes, the dye up-take ratio is 83%. If the dye up-take ratio of the sample is higher than 83%, it
15 is judged that the dyeability of the fiber is good and the fiber can be dyed under normal pressure.

E. Tenacity:

The tenacity is measured by using a tensile testing machine ("Tensilon UTM-II-20" manufactured by Toyo
20 Baldwin) at an initial length of 20 cm and a tensile velocity of 20 mm/min. The initial length of 20 cm employed is the length of the crimp elongated.

F. Crimp Retention:

Of the crimp appearance ratios described in
25 Japanese Unexamined Patent Publication No. 35,112/73, the $CD_{5.0}$ value is employed.

First, the $CD_{5.0}$ value of a textured yarn from the false twisting step or draw-false twisting step is measured, and this value is designated as α . Then, the
30 textured yarn is immersed in boiling water at 100°C under a load of 0.01 g/d for 1 minute. Then, the yarn is naturally dried at a temperature of 20°C and a relative humidity of 60% in the free state without the load, and the $CD_{5.0}$ value is measured again. This value is designated as β . The
35 crimp retention of the textured yarn is expressed by the following formula:

$$\text{Crimp retention (\%)} = \beta / \alpha \times 100$$

Ordinarily, if the crimp retention is at least 65%, it is judged that the crimp retaining property is good.

G. Threading Property:

The easiness in the threading operation is qualitatively judged according to the three-staged method. If the easiness in the threading operation is comparable to that in case of a conventional false-twisted or drawn and false-twisted polyester yarn, the sample is indicated by mark "A". If the sample is fused by contact with the tube heater or broken or fluffs are formed and the threading operation becomes very difficult, the sample is indicated by mark "B". A sample having a threading property intermediate between those of the above-mentioned two samples is indicated by mark "C".

H. Formation of Fluffs:

1 kg of a false-twisted or drawn and false-twisted yarn is wound up in a parallel cheese form, and the number of broken filaments present on both the end faces of the cheese is counted and the counted number is designated as the number of fluffs. Accordingly, the unit is expressed by fluffs/kg. If the number of fluffs is not smaller than 5.0 fluffs/kg, troubles are readily caused at the subsequent knitting or weaving step. Therefore, it is indispensable that the fluff number should be smaller than 5.0 fluffs/kg.

I. Tight Spots:

100 m of a false-twisted yarn is wound on a black plate, and 100 m of the same false-twisted yarn is on another black plate. The number of tight spots on the two plates is counted. When the average number on the two plates is 0, the sample is indicated by mark "A". If the average number is larger than 0 but not larger than 3, the sample is indicated by mark "B". If the number is larger than 3, the sample is indicated by mark "C". A sample indicated by mark A can be practically used in any field without any trouble, but in case of a sample indicated by mark B, fields of products to which the sample can be applied are limited.

J. Yield of Acceptable Dyeing Level:

A standard yarn and sample yarns are knitted separately by using a one feeder knitting machine. The knitted fabrics are scoured under the same conditions as used in the test of dyeability (item D). After scouring, the standard fabric and the sample fabrics are dyed simultaneously in the same dyeing liquor. The dyeing conditions are as follows.

10 Foron Navy S-GL 1% owf
 (Disperse dye, supplied by Sandoz SA, Switzerland)
 Liquor ratio: 1 to 5
 Dyeing temperature: 100°C
 Dyeing time: 60 min.

15 The dyed fabrics are dried and then the colour differences (tolerance indexes) between the standard fabric and the respective samples fabrics are measured. The yield (Y) of acceptable dyeing level is calculated by the following equation.

20
$$Y(\%) = \frac{\text{Number of the samples exhibiting colour difference of below 1 NBS unit}}{\text{Total number of the samples tested}} \times 100$$

K. Evenness of Dyeing

Evenness of dyeing is evaluated on the knitted fabrics dyed by the procedure described in the preceding item J. and having a cylindrical form of four inches in diameter and one inch length. The colour differences (tolerance indexes) between the adjacent courses in each sample fabric are measured. Samples having the colour differences all falling below 1 NBS unit are indicated by mark "good". Samples in which at least a colour difference exceeding 1 NBS unit has been observed are indicated by mark "poor".

35 The present invention will now be described in detail with reference to the following Examples that by no means limit the scope of the invention.

Example 1

Polyethylene terephthalate having an intrinsic viscosity $[\eta]$ of 0.68 dl/g as measured at 35°C in a 2/1 mixed solvent of phenol/tetrachloroethane was spun under conditions shown in Table 1 by using the spinning and winding apparatus shown in Fig. 1 to obtain a polyester filament yarn shown in Table 1.

Table 1

<u>Symbol of Yarn</u>	<u>A</u>	<u>B</u>	<u>C</u>
Extrusion Rate (g/min)	79.0	86.0	103.3
Spinning Speed V (km/min)	3.0	4.5	6.0
Denier/Filament	237/48	172/48	155/48
Mean Birefringence Index Δn ($\times 10^{-3}$)	20	69	105

The yarns A, B and C shown in Table 1 were treated by using the apparatus shown in Fig. 9 and Table 2 under conditions shown in Table 3. The treating temperature was room temperature, 20°C.

The obtained results are shown in Table 4.

Table 2

Yarn Path	As shown in Fig. 9
Slit Heat Position	Variable (L is variable)
Slit Heater Length (m)	1.1
Slit Heater Temperature (°C)	260
False Twisting Heater Length (m)	1.0
False Twisting Heater Temperature (°C)	200
Winding Ratio (%) $(\frac{R_2 - R_4}{R_2} \times 100)$	+4%
Spindle Head Rotation Number (rpm)	375,000
Twist Number (T/m)	2,500
Yarn Speed (m/min) (surface speed of R_2)	150

Table 3

Yarn	A	B	C
Draw Ratio (R_1/R_0) at Heat Treatment	1.400	1.000	0.980
Tension (g/d) at Heat Treatment	0.15	0.05	0.03
Cooling Length L (m)	Varied as shown in Table 4		
Draw Ratio (R_2/R_1) at Draw-False Twisting	1.130	1.150	1.050

25 In Table 3, the tension at the heat treatment was obtained by dividing the tension at the outlet of the slit heater 9 in Fig. 9 by the denier of the filament yarn after the heat treatment.

Table 4

Yarn	L (m)	0.1	0.16	0.2	0.4	0.8	1.1	1.6	2.5	3.0
Cooling Time (sec)		0.04	0.064	0.08	0.16	0.32	0.44	0.64	1.00	1.20
Dye Up-Take Ratio (%)		-	-	-	-	81.1	81.6	82.3	83.5	84.2
Tenacity (g/d)	A	-	-	-	-	3.23	3.20	3.18	3.15	3.13
Dye Up-Take Ratio (%)		-	-	-	81.9	82.6	83.1	83.9	-	-
Tenacity (g/d)	B	-	-	-	3.25	3.24	3.23	3.21	-	-
Dye Up-Take Ratio (%)		82.7	83.2	83.2	83.4	83.7	-	-	-	-
Tenacity (g/d)	C	3.33	3.32	3.32	3.32	3.31	-	-	-	-

In case of $V = 3.0$ (yarn A), the critical cooling time A is 1.0 second, in case of $V = 4.5$ (yarn B), the critical cooling time A is 0.48 second, and in case of $V = 6.0$ (yarn C), the critical cooling time A is 0.063 second.

- 5 From Table 4, it is seen that when a polyester filament yarn is heat-treated and subsequently subjected to the false twisting treatment or draw-false twisting treatment to obtain an easily dyeable false-twisted yarn, if natural cooling is carried out after the heat treatment for a time of A
 10 $(= \frac{7 - V}{4(V - 2.0)} \text{ second})$ or longer, there can be obtained a false-twisted yarn having a practically sufficient tenacity and a good dyeability.

Example 2

- 15 In the same manner as in Example 1, the yarn B of Example 1 was treated under conditions shown in Tables 2 and 3 by using the apparatus shown in Fig. 9. Incidentally, the cooling length L was 1.6 m, the cooling time A was 0.64 second and the cooling conditions were as shown in Table 5.

Table 5

	Run No.	
	2-(1)	2-(2)
Cooling Conditions	Natural cooling in room temperature (20°C) atmosphere	Hot air maintained at 210°C was blown against yarn 7 uniformly throughout cooling length L (heating)

The obtained results are shown in Table 6.

Table 6

	Run No.	
	<u>2-(1)</u>	<u>2-(2)</u>
Dye Up-Take Ratio (%) of Textured Yarn	83.9	58.2
Tenacity (g/d) of Textured Yarn	3.21	3.08
Crimp Retention (%) of Textured Yarn	70.3	63.8

From the results shown in Table 6, it is seen that when a polyester filament yarn is heat-treated and subsequently subjected to the false twisting treatment or draw-false twisting treatment, if the yarn is once cooled after the heat treatment, there can be obtained a false-twisted yarn having a practically sufficient strength and good crimp retention and dyeability.

Example 3

In the same manner as in Example 1, the yarn B of Example 1 was treated under conditions shown in Tables 2 and 3 by using the apparatus shown in Fig. 9. The cooling conditions adopted were as shown in Table 7.

The obtained results are shown in Table 8.

Table 7

	Run No.			
	<u>3-(1)</u>	<u>3-(2)</u>	<u>3-(3)</u>	<u>3-(4)</u>
Cooling Conditions	Cold air maintained at 7°C was blown against yarn uniformly throughout cooling length L		Natural cooling in room temperature (20°C) atmosphere	
Cooling Length (m)	0.4	1.1	0.4	1.1
Cooling Time (sec)	0.16	0.44	0.16	0.44

Table 8

	Run No.			
	<u>3-(1)</u>	<u>3-(2)</u>	<u>3-(3)</u>	<u>3-(4)</u>
Dye Up-Take Ratio (%) of Textured Yarn	83.6	85.7	81.9	83.1
Tenacity (g/d) of Textured Yarn	3.22	3.20	3.25	3.23
Crimp Retention (%) of Textured Yarn	68.9	70.2	72.5	73.2

From the results shown in Table 8, it is seen that a higher cooling effect is attained by forced cooling than by

atural cooling and in case of forced cooling, therefore, the cooling length and cooling time can be shortened. It will also readily be understood that according to the process of the present invention, there can be obtained a false-twisted
5 yarn having a practically sufficient tenacity, and good crimp retaining property and dyeability.

Example 4

Copolymerization was carried out by substituting a part of terephthalic acid of ethylene terephthalate by isophthalic
10 acid to obtain four kinds of polymers having isophthalic acid contents of 3, 6, 12 and 18% by weight, respectively. These polymers were independently melt-spun at a spinning speed of 5,000 m/min by using the spinning apparatus shown in Fig. 1 to obtain 4 kinds of 75 d/36 f as-spun yarns.
15 The Δn values of the respective yarns are shown in Table 9.

These yarns were independently heat-treated at a heat treatment temperature of 240°C for a treatment time of 0.9 second at an elongation ratio of 0% by using the apparatus shown in Fig. 9, and they were naturally cooled for 0.64
20 second in an atmosphere maintained at 20°C. Subsequently, the yarns were false-twisted at a false twisting heater temperature of 205°C at a draw ratio of 0% and a twist number of 3250 t/m.

The dye up-take ratios and tenacities of the respective
25 yarns are shown in Table 9.

Table 9

Isophthalic Acid Content (% by weight)	3	6	12	18
Δn of As-Spun Yarn	80×10^{-3}	78×10^{-3}	70×10^{-3}	65×10^{-3}
Tenacity (g/d)	3.8	3.3	3.1	2.6
Dye Up-Take Ratio (%)	87	89	90	93

From the results shown in Table 9, it is seen that when
35 isophthalic acid is copolymerized in an amount outside the range specified in the present invention, for example, 18% by weight, the tenacity is lower than 3 g/d even if the

treatment of the present invention is carried out, and practical use of the obtained yarn involves problems, while if the isophthalic acid content is within the range specified in the present invention, the tenacity is higher than 3 g/d and the obtained yarn can be dyed under normal pressure.

Example 5

Polyethylene terephthalate having an intrinsic viscosity $[\eta]$ of 0.64 dl/g was melt-extruded from a spinneret having 32 holes 0.35 mm in diameter at a spinning temperature of 298°C, and the spun yarn was cooled to be solidified by an air current maintained at 25°C and supplied in the direction parallel to the running direction of the yarn. Then, an oiling agent was applied to the yarn and the yarn was wound at a speed of 3,000 to 6,000 m/min. The obtained polyester multifilament yarn composed of 32 filaments having properties shown in Table 10 was treated by using an apparatus shown in Fig. 7 and Table 11 under conditions shown in Table 12. The obtained results are shown in Table 13. During the false twisting treatment, twists given to the yarn were propagated upstream to the heat-treating heater, and the twists shown in Table 12 were given to the yarn at the heat treatment.

Table 10

	As-Spun Yarn			
	A	B	C	D
Winding Speed (km/min)	3	4	5	6
Extrusion Rate (g/min)	81.7	87.6	94.4	105
Apparent Denier (d)	245	197	170	158
Mean Birefringence Index Δn ($\times 10^{-3}$)	19	48	82	103

Table 11

	<u>Treating Method</u>	
	<u>(I)</u>	<u>(II)</u>
Heat-Treating Heater Length (m)	1	Heat-treating heater was not used
Heat-Treating Heater Temperature (°C)	250	
Flase Twisting Heater Temperature (°C)	200	200
Winding Ratio* (%) [$\frac{R_2 - R_3}{R_2} \times 100$]	+4	+4
False Twisting Heater Length (m)	1	1
Twist Numbers (t/m)	2500	2500
<u>Note*</u> R_2: surface speed (m/min) of delivery roller (15) shown in Fig. 7 R_3: surface speed (m/min) of winding friction roller (16) shown in Fig. 7		

Table 12

Run No.	Comparison			Present Invention			Comparison		
	1	2	3	4	5	6	7		
As-Spun Yarn	A	B	C	D	B	C	D		
Treating Method	(I)	(I)	(I)	(I)	(II)	(II)	(II)		
Rotation Number (rpm) ₄ of Spindle Head (x 10 ⁴)	25	25	25	25	25	25	25		
Surface Speed (m/min) of Delivery Roller	100	100	100	100	100	100	100		
Surface Speed (m/min) of Feed Roller	61.2	76.2	88.3	95.0	76.2	88.3	95.0		
Draw Ratio (R ₂ /R ₁)	1.633	1.313	1.133	1.053	1.313	1.133	1.053		
Heat Treatment Time (sec)	0.98	0.79	0.68	0.63	Heat treatment was not effected				
Twist Number (t/m) on Heat-Treating Heater	79	83	85	87	-				

Table 13

	Comparison	Present Invention				Comparison	
Run No.	1	2	3	4	5	6	7
Threading Property	C	A	A	A	A	A	A
Dye Up-Take Ratio (%)	Threading Operation Impossible	91	87	83	58	63	67

From the results shown in Table 13, it is seen that according to the process of the present invention, a textured polyester yarn having a highly improved dyeability can be obtained. It also is seen that even when the process of the present invention is adopted, in case of a feed yarn spun at a spinning speed of less than 4,000 m/sec, the yarn hanging property is poor and the operation adaptability is inferior.

Example 6

Polyethylene terephthalate having an intrinsic viscosity $[\eta]$ of 0.65 dl/g was extruded at a spinning temperature of 300°C from a spinneret having 36 Y-shaped orifices, and the spun yarn was cooled and solidified by cold air maintained at 18°C and supplied in the direction parallel to the running direction of the yarn. An oiling agent was applied to the yarn, and the yarn was wound at a speed of 5,500 m/min to obtain a yarn comprising single filaments having a triangular section and having a total denier of 50 deniers.

The yarn was subjected to heat treatment, cooling and false twisting in the apparatus shown in Fig. 9. The heat treatment temperature was 248°C, the heat treatment time was 0.84 second, and cooling was carried out for 0.9 second in an atmosphere maintained at 23°C. The false twisting heater temperature was 210°C, the twist number was 3,800 t/m and the draw ratio at the false twisting treatment was 0%. The tenacity of the obtained false-twisted yarn was 3.7 g/d and the dye up-take ratio was 87%. Thus, it was found that the false-twisted yarn had a practically sufficient tenacity and

could be dyed under normal pressure.

Example 7

Polyethylene terephthalate having an intrinsic viscosity
[η] of 0.67 dl/g was extruded at a spinning temperature of
5 302°C through a spinneret having 36 orifices 0.35 mm in
inner diameter, and the spun yarn was cooled and solidified
by cold air maintained at 20°C and supplied in the direction
parallel to the running direction of the yarn. Five kinds
of 75 d/36 f multifilament yarns were prepared by adopting
10 spinning speeds of 2,000, 3,000, 4,000, 5,000 and 6,000 m/min.
The Δn values of the respective yarns are shown in Table 14.
These yarns were subjected to heat treatment, cooling and
false twisting or draw-false twisting under conditions shown
in Table 14 by using the apparatus shown in Fig. 9. The
15 tenacities and dye up-take ratios of the obtained false-
-twisted yarns are shown in Table 14.

For comparison, the same polyethylene terephthalate was
spun at a spinning speed of 1,300 m/min and drawn at a draw
ratio of 3.6, and the obtained yarn was similarly treated
20 under conditions shown in Table 14. The Δn value of the
drawn yarn and the tenacity and dye up-take ratio of the
false-twisted yarn are shown in Table 14.

Table 14

Spinning Speed (m/min)	2,000	2,000	3,000	3,000	4,000	5,000	6,000	1,300 (drawn)	1,300 (drawn)
$n \times 10^{-3}$	9	9	18	18	53	84	102	168	168
Heat Treatment Temperature (°C)	245	245	245	245	245	245	245	245	245
Heat Treatment Time (sec)	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1	1.1
Draw Ratio (%) at Heat Treatment	35	0	35	0	0	0	0	0	-50
Cooling Time* (sec)	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
False Twisting Heater Temperature (°C)	215	215	215	215	215	215	215	215	215
Twist Number (T/m)	3500	3500	3500	3500	3500	3500	3500	3500	3500
Draw Ratio (%) at Halse Twist Treatment	Threading Operation impossible								
Tenacity (g/d)			3.3	2.6	3.6	3.9	4.1	4.2	2.5
Dye Up-Take Ratio (%)			85	82	87	86	86	44	80

* Note Cooling was effected by natural cooling at room temperature (23°C).

From the results shown in Table 14, it is seen that in case of the yarn obtained at a spinning speed of 2,000 m/min outside the range specified in the present invention and having a Δn value of 9×10^{-3} , partial melting was caused at the heat treatment and the yarn broke, and therefore, the yarn hanging operation was impossible.

In case of the yarn obtained at a spinning speed of 3,000 m/min and having a Δn value of 18×10^{-3} , the tenacity was higher than 3 g/d if the elongation rate at the heat treatment was 35%, but if the elongation rate at the heat treatment was 0%, the tenacity was less than 3 g/d.

In case of the yarn spun at a spinning speed of 4,000 m/min or higher and having a Δn value of at least 50×10^{-3} , a false-twisted yarn excellent in the tenacity and dye up-take ratio was obtained even if the elongation at the heat treatment was 0%.

In case of the comparative polyester yarn spun at a spinning speed of 1,300 m/min and then drawn, which had a Δn value of 170×10^{-3} , the dyeability was extremely low if the draw ratio at the heat treatment was 0%, and when the yarn was relaxed by 50% at the heat treatment (the drawing ratio was -50%), the dyeability was improved but the false-twisted yarn was not dyeable under normal pressure, and the tenacity of the false-twisted yarn was very low.

Example 8

The 75 d/36 f multifilament yarn spun at a spinning speed of 6,000 m/min and having Δn value of 102×10^{-3} , which was obtained in Example 7, was treated in the same manner as described in Example 7 except that the heat treatment temperature was changed as shown in Table 15. The tenacities and dye up-take ratios of the obtained false-twisted yarns are shown in Table 15.

Table 15

Heat Treatment Temperature (°C)	188	221	236	248	253
Tenacity (g/d)	4.7	4.4	4.2	4.1	3.9
Dye Up-Take Ratio (%)	73	83	85	87	88

From the results shown in Table 15, it is seen that if the heat treatment is carried out at 221°C or higher and then, cooling and false twisting are performed a false-
10 -twisted yarn having a higher dye up-take ratio can be obtained.

Example 9

The 75 d/36 f multifilament yarn spun at a spinning speed of 6,000 m/min and having a n value of 102×10^{-3} ,
15 which was obtained in Example 7, was treated in the same manner as described in Example 7 except that the heat treatment conditions were changed as shown in Table 16. The tenacity and dye up-take ratio of the obtained false-twisted yarn are shown in Table 16.

Table 16

Heat Treatment Temperature (°C)	225	225	225	225	250	250	250	250
Heat Treatment Time (sec)	1.0	1.5	2.0	2.0	0.5	1.0	1.5	1.5
(%) at Heat Treatment	-5	-5	-5	+2	-5	-5	-5	+2
Tenacity (g/d)	4.6	4.4	4.3	4.6	4.5	4.2	3.9	4.5
Dye Up-Take Ratio (%)	85	86	87	83	84	88	90	85

Example 10

Polyethylene terephthalate having an intrinsic viscosity
35 of 0.635 dl/g as measured at 35°C in a 2/1 mixed solvent of phenol/tetrachloroethane was melt-extruded from a spinneret having 36 holes 0.35 mm in diameter at a spinning

temperature of 303°C, and the spun yarn was cooled to be solidified by an air current maintained at 20°C and fed in the direction parallel to the running direction of the yarn. An oiling agent was applied to the yarn and the yarn was wound. Three sets of the extrusion rate and winding speed shown in Table 17 were adopted, and three kinds of 75 d/36 f as-spun yarns X, Y and Z were obtained. These yarns were false-twisted to highly crimped set yarns by using the false twisting apparatus of the present invention shown in Table 18 or the conventional heat-treating heater-provided false twisting apparatus shown in Table 18 under conditions (a), (b) or (c) shown in Table 19. The obtained results are shown in Table 20.

Table 17

Feed As-Spun Yarn	X	Y	Z
Extrusion Rate (g/min)	50.0	33.3	41.7
Winding Speed (km/min)	6	4	5
Mean Birefringence Index ($\times 10^{-3}$)	103	51	85

Table 18

False Twisting Apparatus	No. 1 (present invention)	No. 2 (conventional apparatus)
Structure	Shown in Fig. 11	Shown in Fig. 10
Type of Heat-Treating Heater	Non-contact type (hollow pipe)	Contact type
Heat-Treating Heater Length (m)	1.55	0.6
False Twisting Heater Length (m)	0.95	0.95
Heat-Setting Heater Length (m)	0.6	0.6

Table 19

False Twisting Apparatus	No. 1 (present invention)			No. 2 (conventional apparatus)		
	a	b	c	a	b	c
Treating Conditions	a	b	c	a	b	c
Feed As-Spun Yarn	X	Y	Z	X	Y	Z
Rotation Number (rpm) of Spindle Head ($\times 10^4$)	50	50	50	50	50	50
Heat-Treating Heater Temperature ($^{\circ}\text{C}$)	250	250	250	200	200	200
$\frac{R_{-1} - R_0}{R_0} \times 100 (\%)$	+2	0	+1	-	-	-
$\frac{R_{-1} - R_1}{R_1} \times 100 (\%)$	-	-	-	0	0	0
R_2/R_1 (draw ratio)	1.04	1.30	1.12	1.04	1.30	1.12
False Twisting Heater Temperature ($^{\circ}\text{C}$)	205	205	205	205	205	205
Twist Number (T/m)	3,200	3,800	3,350	3,200	3,800	3,350
Heat-Setting Heater Temperature ($^{\circ}\text{C}$)	185	185	185	185	185	185
$\frac{R_2 - R_3}{R_2} \times 100 (\%)$	+20	+20	+20	+20	+20	+20
$\frac{R_2 - R_4}{R_2} \times 100 (\%)$	+9.5	+9.5	+9.5	+9.5	+9.5	+9.5

Note

(1) R_0 , R_{-1} , R_1 , R_2 , R_3 and R_4 in Table 19 show peripheral speeds (the unit is omitted) of the following members shown in Figs. 10 and 11.

	<u>Fig. 11 (Apparatus No. 1)</u>	<u>Fig. 10 (Apparatus No. 2)</u>
R_{-1}	Feed roller 10	Feed roller r_1
R_0	Feed roller 11	-
R_1	Feed roller 12	Feed roller r_2
R_2	Feed roller 13	Feed roller r_3
R_3	Feed roller 14	Feed roller r_4
R_4	Winder 8	Winder C

(2) In the apparatus No. 1, the R_1/R_0 ratio was adjusted to 1.0.

Table 20

False Twisting Apparatus	No. 1 (present invention)			No. 2 (conventional apparatus)		
	a	b	c	a	b	c
Treating Conditions						
Fluff Formation (fluffs/kg)	1.02	1.53	1.20	9.87	Many	Many
Yarn Breakage (times/216 spindles x 1 hour)	0.25	0.23	0.19	1.24	5.31	3.78
Tight Spots	A	A	A	B	C	B
Evenness of Dyeing	Good	Good	Good	Poor	Poor	Poor
Yield of Acceptable Dyeing level (%)	96	90	93	85	78	82
Dye Up-Take Ratio (%)	83	93	88	Not measured		

Note

The term "many" in the column of the fluff formation indicates "at least 10 fluffs/kg".

30 From the results shown in Table 20, it is seen that the false twisting apparatus according to the present invention is excellent over the conventional heat-treating heater-
 -provided false twisting apparatus because formation of fluffs and occurrence of yarn breakage are remarkably
 35 reduced and good false twisting properties can be obtained, and the false-twisted yarn obtained by using the false twisting apparatus of the present invention is highly

improved in the tight spot property, evenness of dyeing, yield of acceptable dyeing level and dyeability.

Example 11

- 5 The as-spun yarn Y of Example 10 was subjected to the partially molten-false twisting by using the apparatus No. 1 or No. 2 used in Example 10 to obtain a linen-like partially molten-false-twisted yarn. Treating conditions were as follows.

Rotation number of spindle head:	300,000 rpm
$(R_{-1} - R_0)/R_0 \times 100$:	0% (apparatus No. 1)
R_1/R_0 :	1.0 (apparatus No. 1)
$(R_{-1} - R_1)/R_1 \times 100$:	0% (apparatus No. 2)
R_2/R_1 (draw ratio):	1.26
False twisting heater temperature:	200°C
Twist number:	3,350 t/m
Stabilizing heater temperature:	180°C
$(R_2 - R_3)/R_2 \times 100$:	+10%
$(R_2 - R_4)/R_2 \times 100$:	+6%

- 25 The above conditions were commonly adopted in both the apparatuses, but the heat-treating temperature was different between the two apparatuses. Namely, this temperature was 265°C in the apparatus No. 1 and 220°C in the apparatus No. 2.

The obtained results are shown in Table 21.

Table 21

	Apparatus No. 1 (present invention)	Apparatus No. 2 (conventional apparatus)
Fluff Formation (fluffs/kg)	1.78	Many
Yarn Breakage (times/216 spindles x 1 hour)	0.33	9.34
Dye Take-Up Ratio (%)	85	66

Note

In case of partially molten-false-twisted yarns, the level dyeing property was not measured or evaluated because of the tight spots and irregular dyeing inherent of partially molten-false-twisted yarns.

From the results shown in Table 21, it is seen that even in case of the partially molten-false twisting treatment, the false twisting apparatus of the present invention is advantageous over the conventional heat-treating heater-provided false twisting apparatus in that formation of fluffs and occurrence of yarn breakage are remarkably reduced, the adaptability to the false twisting treatment is improved and the dye up-take ratio of the obtained yarn is enhanced.

Example 12

Polyethylene terephthalate having an intrinsic viscosity of 0.65 dl/g was melt-extruded from a spinneret having 24 orifices, each 0.23 mm in diameter at a spinning temperature of 300°C. The yarn extruded was cooled and solidified with a stream of air at 20°C supplied in parallel to the direction of the running yarn, and then the yarn was wound at a winding speed of 4,500 m/min. to give multifilaments of 50d/24f by using the spinning apparatus shown in Fig. 1. A mean birefringence index Δn of the yarn was 71×10^{-3} . The wound yarn was subjected to heat treatment for 0.8 second at an elongation ratio of 0% by passing through a heat treating heater 9 as shown in Fig. 9, which was placed in an atmos-

phere of mixed gas containing 80 mol% of super heated steam and 20 mol% of air heated at 235°C. Subsequently the yarn was naturally cooled for 1.2 second in an atmosphere maintained at 25°C, and then the yarn was false-twisted at a
5 false twisting temperature of 212°C at a draw ratio of 7% and a twisting number of 3,900 t/m. The tenacity and dye up-take ratio of the false-twisted yarn are 3.3 g/d and 87%, respectively.

CLAIMS

1. A process for producing a false-twisted polyester yarn, which comprises continuously subjecting a yarn consisting of an as-spun polyester fiber having a mean birefringence index (Δn) of at least 15×10^{-3} but less than 150×10^{-3} to (1) heat treatment, (2) cooling and (3) false twisting or draw-false twisting.

2. A process for producing a false-twisted polyester yarn according to claim 1, wherein the as-spun polyester yarn is one which has been spun at a spinning speed of at least 2,500 m/min but less than 7,000 m/min.

3. A process for producing a false-twisted polyester yarn according to claim 1 or 2, wherein cooling is natural cooling conducted at a temperature of $20 \pm 15^\circ\text{C}$ for the period of A satisfying the following formula:

$$A \text{ (second)} \geq \frac{7 - V}{4(V - 2.0)}$$

wherein V stands for the spinning speed expressed in the unit of km/min.

4. A process for producing a false-twisted polyester yarn according to claim 1 or 2, wherein cooling is forced cooling.

5. A process for producing a false-twisted polyester yarn according to any of claims 1 through 4, wherein said heat treatment is carried out in an atmosphere maintained at a temperature of 190 to 300°C .

6. A process for producing a false-twisted polyester yarn according to any of claims 1 through 5, wherein the mean birefringence index (Δn) of the as-spun polyester yarn is at least 50×10^{-3} but less than 150×10^{-3} .

7. A process for producing a false-twisted polyester yarn according to any of claims 1 through 6, wherein the as-spun polyester yarn is one which has been spun at a spinning speed of at least 4,000 m/min but less than 7,000 m/min.

8. A process for producing a false-twisted polyester

yarn according to claim 1, wherein the heat treatment of the as-spun polyester yarn is carried out in a twisted state.

9. A process for producing a false-twisted polyester yarn according to claim 8, wherein the as-spun polyester
5 yarn is one which has been spun at a spinning speed of at least 4,000 m/min but less than 7,000 m/min.

10. A process for producing a false-twisted polyester yarn according to any of claims 6 through 9, wherein the heat treatment of the as-spun polyester yarn is carried out
10 at a yarn elongation ratio of -8% to +3%.

11. A process for producing a false-twisted polyester yarn according to claim 9, wherein the heat treatment of the as-spun polyester yarn is carried out in a twisted state without no substantial elongation.

15 12. A process for producing a false-twisted polyester yarn according to claim 11, wherein the heat treatment of the as-spun polyester yarn is carried out while the yarn is contacted with the surface of a heater.

13. A process for producing a false-twisted polyester
20 yarn according to any of claims 6 through 12, wherein the heat treatment of the as-spun polyester yarn is carried out for a period of 0.2 to 2.0 seconds.

14. A process for producing a false-twisted polyester yarn according to claim 1, wherein a yarn consisting of an
25 as-spun polyester fiber having a mean birefringence index (Δn) of at least 15×10^{-3} but less than 50×10^{-3} is heat-treated in an atmosphere maintained at 200 to 260°C under elongation at an elongation ratio of 5 to 200% with no contact with the surface of a heater, the yarn is
30 subsequently cooled to a temperature of not higher than 35°C and is then subjected to the draw-false twisting treatment.

15. A process for producing a false-twisted polyester yarn according to claim 14, wherein the as-spun polyester yarn is one which has been spun at a spinning speed of at
35 least 2,500 m/min but not higher than 4,000 m/min.

16. A process for producing a false-twisted polyester yarn according to claim 14 or 15, wherein the heat treatment

of the as-spun polyester yarn is carried out for a period of 0.4 to 2 seconds.

17. A process for producing a false-twisted polyester yarn according to any of claims 1 through 4, wherein the
5 heat treatment of the as-spun polyester yarn is carried out in an atmosphere of super-heated steam or a mixture of super-heated steam and hot air.

18. A process for producing a false-twisted polyester yarn according to claim 17, wherein the heat treatment of
10 the as-spun polyester yarn is carried out at a temperature in the range of from $(230 - 50Z)^{\circ}\text{C}$ to $(290 - 50Z)^{\circ}\text{C}$ in which Z stands for the mole fraction of super-heated steam.

19. A process for producing a false-twisted polyester yarn according to any of claims 1 through 18, wherein
15 constituent single filaments of the as-spun polyester yarn have a circular cross-section and a size of at least one denier.

20. A process for producing a false-twisted polyester yarn according to any of claims 1 through 18, wherein
20 constituent single filaments of the as-spun polyester yarn have a circular cross-section and a size of at least 0.01 denier but less than one denier.

21. A process for producing a false-twisted polyester yarn according to any of claims 1 through 18, wherein
25 constituent single filaments of the as-spun polyester yarn have a non-circular cross-section.

22. A process for producing a false-twisted polyester yarn according to any of claims 1 through 21, wherein the
as-spun polyester yarn is composed of a polyethylene
30 terephthalate homopolymer.

23. A process for producing a false-twisted polyester yarn according to any of claims 1 through 21, wherein the
as-spun polyester yarn is composed of a copolyester
comprising main repeating units of ethylene terephthalate
35 and less than 5% by weight of the other copolymerized component.

24. A process for producing a false-twisted polyester

yarn according to any of claims 1 through 21, wherein the as-spun polyester yarn is composed of a copolyester comprising main repeating units of ethylene terephthalate and 5 to 15% by weight of the other copolymerized component.

5 25. A false twisting apparatus which comprises a feed yarn creel, a false twisting heater and an optional stabilizing heater, a false twisting element and a winder, wherein a heat-treating heater of the non-contact type is arranged upstream of the false twisting heater and between
10 the false twisting heater and the feed yarn creel, at a height substantially equal to the height of the feed yarn creel so that the heat-treating heater confronts the false twisting heater.

26. A false twisting apparatus according to claim 25,
15 wherein the heat-treating heater is arranged at a height substantially equal to the height of the false twisting heater.

27. A false twisting apparatus according to claim 25 or 26, wherein a heating plate of the heat-treating heater
20 has a groove through which a polyester yarn is capable of passing without contact with the surface of said heating plate.


28. A false twisting apparatus according to claim 25 or 26, wherein the heat-treating heater has a hollow pipe
25 shape such that a polyester yarn is capable of passing there-through without contact with the surface of said heater.

29. A false twisting apparatus according to claim 25 or 26, wherein the yarn-cooling length corresponding to the distance between the outlet of the heat-treating heater and
30 the inlet of the false twisting heater is at least 0.7 m.

30. A false twisting apparatus according to claim 25 or 26, wherein a yarn-cooling plate maintained at 5 to 35°C is arranged between the outlet of the heat-treating heater and the inlet of the false twisting heater.

35 31. A false twisting apparatus according to claim 25 or 26, wherein the length of the heat-treating heater is at least 0.5 m.


1/15

Fig. 1

2/15

0087124


Fig. 2



3/15


0087124

Fig. 3



4/15

Fig. 4



5//5

0087124

Fig. 5






Fig. 6



7/15

0087124


Fig. 7



8/15


0087124

Fig. 8




9/15

Fig. 9



10/15


Fig. 10



11/15

0087124

Fig. 11



[illegible]



Fig. 13

Fig. 14



15/15

0087124

Fig. 15

