

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
30 October 2008 (30.10.2008)

PCT

(10) International Publication Number
WO 2008/128977 A1

(51) International Patent Classification:
G03G 7/00 (2006.01) **G03G 15/16** (2006.01)
G03G 8/00 (2006.01)

(74) Agent: **SCHALKWIJK, Pieter Cornelis**; Akzo Nobel N.V., Intellectual Property Department (AIP), P.O. Box 9300, NL-6800 SB Arnhem (NL).

(21) International Application Number:
PCT/EP2008/054698

(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(22) International Filing Date: 18 April 2008 (18.04.2008)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
07106687.2 23 April 2007 (23.04.2007) EP
60/928,748 10 May 2007 (10.05.2007) US

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (*for all designated States except US*):
AKZO NOBEL COATINGS INTERNATIONAL B.V. [NL/NL]; Velperweg 76, NL-6824 BM Arnhem (NL).

(72) Inventor; and

(75) Inventor/Applicant (*for US only*): **KITTLE, Kevin Jeffrey** [GB/GB]; 19 Denwick Close, Chester-le-Street Durham DH2 3TL (GB).

Published:

— with international search report

(54) Title: PROCESS FOR APPLYING A POWDER COATING

(57) Abstract: A process for coating a substrate comprising the sequential steps of (a) providing a transfer sheet provided with a printed powder coating, (b) applying the transfersheet onto the substrate with the powder coating in contact with the substrate, (c) removing the transfer sheet from the powder coating and (d) curing the powder coating on the substrate.



ACO 3228 R

PROCESS FOR APPLYING A POWDER COATING

The present invention pertains to a process for applying a powder coating onto a substrate.

5

Conventionally, powder coatings are applied onto substrates using spray guns or fluidised beds. Both these processes have the disadvantage that they can only deposit powder coatings in a single colour on the entire substrate. Any lettering or other decoration will have to be applied in a separate process step.

10

US 5,955,152 provides an alternative method for applying a powder coating onto a substrate. This reference describes a method wherein a powder coating is applied onto a substrate via an electrostatic printing process comprising forming an electrostatic latent image on a light-sensitive body, developing the electrostatic latent image by making a thermosetting powder coating material adhere under electrostatic force to the light-sensitive body, transferring the powder coating material on the light-sensitive body onto the substrate to be coated, and curing the powder coating in such a way that it adheres to the substrate. The reference also describes a method wherein the powder coating material on the light-sensitive body is transferred onto a transfer sheet, and the powder coating material is cured as it is pressed against the substrate to be coated, thereby baking the powder coating material onto the substrate; followed by peeling the transfer sheet from the cured coating layer.

15

20

25

While the transfer sheet process described in US 5,955,152 makes it possible to deposit powder coatings with different colours onto a single substrate in a single step, it appears that it still has some disadvantages.

In the first place, it appears that when the transfer sheet is used to apply a decoration on part of a coated substrate, e.g., a logo onto an already coated refrigerator door, the decoration has an added-on appearance which is not attractive.

30

ACO 3228 R

2

Further, the application of adjoining transfer sheets, for example when providing a pattern on a very large substrate, is difficult with the method described in this reference. If the transfer sheets are applied simultaneously it is difficult to properly adjoin the patterns, because the transfer sheets are in the way. When
5 the transfer sheets are applied sequentially, that is, one sheet is applied, the coating is cured, the transfer sheet is removed, and the second sheet is applied, good results will also not be obtained because the different patterns will be subjected to different curing conditions.

10 Further, it sometimes occurs that during curing the powder coating layer is fixed not only to the substrate to be coated, but also to the transfer sheet in such a manner that the transfer sheet cannot be removed without damaging the decoration applied via the powder coating layer. Because the powder coating layer at that point in time is already cured, the decoration cannot be removed
15 anymore. This problem can be alleviated by removing the transfer sheet when the coating layer is still warm, but this places restrictions on process flexibility which are not always desired.

A further disadvantage of the process described in this reference is that it
20 places stringent requirements on the properties of the transfer sheet, as the transfer sheet should be able to withstand the conditions prevailing during curing of the powder coating layer without deforming, tearing, melting, or showing any other behaviour which would detrimentally affect the properties of the final coating or the possibilities for removing the transfer sheet. US
25 5,955,152 mentions Teflon™ films and heat-resistant silicon-based films, which are quite expensive.

These problems are solved by the process of the present invention. The present invention provides a process for coating a substrate comprising the sequential
30 steps of providing a transfer sheet provided with a printed powder coating, applying the transfer sheet onto the substrate with the powder coating in contact

ACO 3228 R

3

with the substrate, removing the transfer sheet from the powder coating, and curing the powder coating on the substrate.

5 A characterising feature of the process of the invention is that the transfer sheet is removed from the powder coating before the powder coating is cured. This leads to a number of advantages.

In the first place, it was found that when the powder coating is cured only after the transfer sheet is removed, the surface properties of the cured powder coating will match those of any underlying coating layer. This means that even
10 when only part of a substrate is provided with a decoration via a transfer sheet, the decoration will form an integral part of the coated substrate, which makes for a much more sophisticated appearance. Further, also when the entire surface of a substrate is provided with a powder coating decoration via the method according to the invention, the resulting decoration has more depth and
15 character of image as compared to the relatively flat results obtained via the method described in US 5,955,152.

In the method of this invention it is also easy to decorations adjoining each other. This can be done by repeating the deposition part of the process, comprising the steps of applying the transfer sheet onto the substrate with the
20 powder coating in contact with the substrate and removing the transfer sheet from the powder coating as many times as desired, and then subjecting the entire decorated substrate to a curing step. As each transfer sheet is applied after the previous transfer sheet has been removed, matching the patterns of the adjoining sheets is not hard. As all decorations will be cured simultaneously,
25 the effects associated with different curing conditions will not occur.

Further, if the powder coating layer is damaged during removal of the transfer sheet, the fact that the powder coating is at that point in time not cured may make for easier removal of the powder coating, so that the substrate can be cleaned and the transfer re-applied.

30 Additionally, the material of which the transfer sheet is made can be optimised for printing and transfer properties, without having to withstand the conditions

ACO 3228 R

4

prevailing during curing, making a wider selection of materials available for use in the process.

The process according to the invention allows the application of any design in
5 one or more colours onto a substrate in a single step.

Further advantages associated with the process of the present invention will become apparent from the document below.

10 In the first step of the process according to the invention, a transfer sheet with a printed powder coating is provided. The printing process can be any conventional printing process via which powder materials are applied onto a substrate. Suitable printing processes include those comprising the following steps. In a first step an electrostatic latent image is formed on a light-sensitive
15 body. In a second step the electrostatic latent image is developed by letting the powder coating adhere under electrostatic force to the light-sensitive body. Then, the powder coating material on the light-sensitive body is transferred onto the transfer sheet. For more details on suitable printing processes reference is made to US 5,955,152.

20

In one embodiment a plurality of powder coatings of different colours are sequentially printed onto the transfer sheet, for example by means of the latent-image forming step, developing step and transfer step. Then the plurality of powder coatings are transferred onto the substrate, followed by removal of the
25 transfer sheet and curing. This provides an easy method of providing a substrate coated with a design containing multiple colours. It should also be noted that the use of a transfer sheet makes for a more risk-free coating process than direct coating onto the substrate, in that a miss-print on a transfer sheet is less expensive than a miss-print on a final substrate.

30

ACO 3228 R

5

In one embodiment that substrate is provided with a coating before it is subjected to the process according to the invention. This base coat may have any color, but especially when it is white, base colour of the substrate will not influence the colour of the final coated substrate. The base coat may be a fully
5 cured coating layer (preferably a powder coating), it may have been only partially cured, or it may be a melted uncured powder coating. The latter is preferred.

In one embodiment the plurality of types of powder coating materials include
10 powder coating materials of the standard printing colours cyan, yellow, magenta, and black. This will allow the provision of any desired colour on a white substrate.

In one embodiment of the present invention the powder coating on the transfer
15 sheet is submitted to a temporary fixing step in which the powder coating is heated to a temperature below its curing temperature in such a way that it is temporarily fixed on the transfer sheet. The powder coating is heated sufficiently to induce some flow between the powder coating particles, but insufficiently to cause any substantial curing of the powder coating. If so desired, the powder
20 coating is pressed to the transfer sheet during the temporary fixing step, e.g., by using rollers.

If so desired, a protective sheet may be applied onto the powder coating layer to protect the coating layer against being damaged. This may be of interest for
25 the powder coating as such and for the powder coating layer after it has been submitted to a temporary fixing step.

Any suitable material can be used for the protective sheet, as long as it can be removed from the powder coating layer without damaging it. Suitable materials will be evident to the skilled person and include conventional release paper
30 such as waxed paper or grease-proof paper.

ACO 3228 R

6

The next step in the process according to the invention is applying the transfer sheet on the substrate with the powder coating in contact with the substrate. The transfer sheet may be applied to a flat surface, but may also be folded around a three-dimensional structure.

- 5 How this process step should be carried out will be evident to the skilled person. It may be appropriate to press the transfer sheet against the substrate using rollers or other pressure-generating apparatus. It is also possible, as is known in the art, to cover the substrate with the transfer sheet and then apply a vacuum to press the transfer sheet to the substrate. To increase the adherence of the
- 10 powder coating to the substrate is necessary for the powder coating to be heated above its melt temperature while in contact with the substrate. In general, the conditions during this transfer step should be chosen such that no substantial curing of the powder coating is observed. In general this means that this process should be done quite rapid and the temperature should not be
- 15 chosen too high. In general, the powder coating is heated to a temperature of at least 2°C above the melt temperature, preferably at least 5°C, more preferably at least 10°C. In general, a higher temperature is preferred as this will increase the adherence of the powder coating to the substrate.
- Since it is not intended to cure the powder coating at this stage, the temperature
- 20 of the powder coating should be kept substantially below its curing temperature, e.g., at least 2°C below its curing temperature, preferably at least 5°C, more preferably at least 10°C.

- Then, the transfer sheet is removed from the powder coating. This should be
- 25 done at a temperature below the melt temperature of the powder coating, e.g., at least 2°C below the melt temperature, preferably at least 5°C, more preferably at least 10°C.

The powder coating layer will be retained on the substrate.

- 30 Finally, the powder coating layer is subjected to a curing step in which the powder coating is cured to provide internal integrity and adhesion to the

ACO 3228 R

7

substrate. Preferably, heat curing is used. Curing powder coatings is standard technology and requires no further elucidation.

5 In a further embodiment, another powder coating layer is applied using a transfer sheet, before the curing step of the first coating layer that was applied via a transfer sheet powder coating. In such process sequential layers of powder coating are applied using a transfer sheet before the final curing step. This embodiment enables the preparation of a powder coating layer on a substrate with various textures and/or the building of a 3-dimensional structure
10 in the coating layer on the substrate.

This embodiment can be characterised as a process having the sequential steps of

1. providing a transfer sheet provided with a printed powder coating
2. applying the transfer sheet onto the substrate with the powder coating in
15 contact with the substrate
3. removing the transfer sheet from the powder coating
4. applying another transfer sheet provided with a printed powder coating onto the previously coated substrate with the powder coating in contact with the previously coated substrate
- 20 5. removing the transfer sheet from the powder coating.
6. curing the powder coating on the substrate

Further steps 4 and 5 can be introduced once initial steps 4 and 5 have been completed.

25 The powder coating used in the process according to the invention is a thermosetting powder coating composition which comprises a resin and a curing agent therefore. This differentiates powder coatings from conventional toners: the latter do not contain a curing agent.

The powder coating may further comprise one or more of the conventional
30 powder coating additives like pigments, fillers, and opacifiers.

ACO 3228 R

8

The present invention is not limited to the embodiments discussed above. For example, there is no limitation on the colours of the powder coating materials.

If so desired, the substrate may be pre-coated with liquid coatings or powder coatings via conventional methods. It may be preferred for the substrate to have
5 been provided with a coating layer with a thickness of 1-200 microns, in particular 10-150 microns. The coating layer being a powder coating layer may be particularly preferred.

ACO 3228 R

9

CLAIMS

1. A process for coating a substrate comprising the sequential steps of
 - providing a transfer sheet provided with a printed powder coating
 - 5 • applying the transfer sheet onto the substrate with the powder coating in contact with the substrate
 - removing the transfer sheet from the powder coating
 - curing the powder coating on the substrate
- 10 2. The process of claim 1 wherein the transfer sheet provided with a printed coating is provided by a process comprising the steps of forming an electrostatic latent image on a light-sensitive body, developing the electrostatic latent image by making the powder coating adhere to the light-sensitive body, and transferring the powder coating on the light-sensitive body onto the transfer sheet.
- 15 3. The process of claim 1 or 2 wherein a plurality of powder coatings of different colours are sequentially printed onto the transfer sheet.
- 20 4. The process of claim 3 wherein the plurality of types of powder coating include powder coatings of the standard printing colours cyan, yellow, magenta, and black.
- 25 6. The process of any one of the preceding claims wherein the transfer sheet is folded around a three-dimensional structure,
5. The process of any one of the preceding claims wherein the powder coating is temporarily fixed to the transfer sheet by way of a temporary fixing step in which the powder coating is heated to a temperature below its curing temperature.
- 30

ACO 3228 R

10

6. The process of any one of the preceding claims wherein the substrate to be coated has a coating layer, in particular a powder coating layer, with a thickness of 1-200 microns.
- 5 7. The process of any one of the preceding claims wherein after the transfer sheet is removed from the powder coating, the following sequential steps are inserted before the curing of the powder coating on the substrate
- 10
- applying another transfer sheet provided with a printed powder coating onto the previously coated substrate with the powder coating in contact with the previously coated substrate
 - removing the transfer sheet from the powder coating.
8. Coated substrate obtainable by the process of any one of the preceding claims.

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2008/054698

A. CLASSIFICATION OF SUBJECT MATTER INV. G03G7/00 G03G8/00 G03G15/16		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) G03G		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used) EPO-Internal, WPI Data		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 955 152 A (YASUDA ET AL.) 21 September 1999 (1999-09-21) cited in the application column 5, line 51 - column 9, line 58; claims 1,2; figures 1-3 -----	1-9
X	US 5 358 820 A (BUGNER ET AL.) 25 October 1994 (1994-10-25) column 10, line 24 - line 34 column 16, line 16 - line 27 -----	1-8
X	EP 0 433 950 A (KODAK) 26 June 1991 (1991-06-26) column 14, line 32 - line 43 column 29, line 52 - column 30, line 2 ----- -/--	1,2,5,6, 8
☒ Further documents are listed in the continuation of Box C. ☒ See patent family annex.		
* Special categories of cited documents : *A* document defining the general state of the art which is not considered to be of particular relevance *E* earlier document but published on or after the international filing date *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) *O* document referring to an oral disclosure, use, exhibition or other means *P* document published prior to the international filing date but later than the priority date claimed *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. *&* document member of the same patent family		
Date of the actual completion of the international search 15 May 2008		Date of mailing of the international search report 26/05/2008
Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016		Authorized officer Magrizo, Simeon

INTERNATIONAL SEARCH REPORT

International application No

PCT/EP2008/054698

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 456 987 A (BADESHA) 10 October 1995 (1995-10-10) column 11, line 26 - line 32 column 16, line 43 - line 51 -----	1, 2, 5, 6, 8
X	EP 1 296 202 A (RICOH) 26 March 2003 (2003-03-26) column 25, line 52 - column 26, line 3 -----	1, 2, 5, 8, 9
X	US 5 284 731 A (TYAGI ET AL.) 8 February 1994 (1994-02-08) column 6, line 1 - line 13 -----	1, 2, 5, 8
X	US 5 099 336 A (MORIYA) 24 March 1992 (1992-03-24) column 8, line 52 - line 61 -----	1, 2, 5, 8
X	US 3 877 416 A (DONOHUE ET AL.) 15 April 1975 (1975-04-15) column 5, line 42 - line 67 -----	1, 2, 5, 8
X	GB 2 337 962 A (KELLY) 8 December 1999 (1999-12-08) page 1; claim 1 -----	1, 2, 5, 8
X	JP 2001 117298 A (SHARP) 27 April 2001 (2001-04-27) paragraph [0026] -----	1, 2, 5, 8
X	JP 10 340012 A (CANON) 22 December 1998 (1998-12-22) paragraphs [0022] - [0029]; figure 1 -----	1, 2, 5, 8

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2008/054698

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5955152	A	21-09-1999	NONE
US 5358820	A	25-10-1994	NONE
EP 0433950	A	26-06-1991	DE 69020871 D1 17-08-1995 DE 69020871 T2 28-03-1996 JP 3290684 A 20-12-1991 US 5037718 A 06-08-1991
US 5456987	A	10-10-1995	NONE
EP 1296202	A	26-03-2003	US 6801742 B1 05-10-2004
US 5284731	A	08-02-1994	NONE
US 5099336	A	24-03-1992	JP 2163764 A 25-06-1990
US 3877416	A	15-04-1975	AU 6811974 A 23-10-1975 BE 814054 A1 16-08-1974 BR 7403269 A 30-12-1975 CA 1017198 A1 13-09-1977 CH 573612 A5 15-03-1976 DE 2418264 A1 07-11-1974 FR 2226698 A1 15-11-1974 GB 1445671 A 11-08-1976 IT 1009955 B 20-12-1976 JP 50019456 A 28-02-1975 NL 7403494 A 25-10-1974
GB 2337962	A	08-12-1999	NONE
JP 2001117298	A	27-04-2001	NONE
JP 10340012	A	22-12-1998	NONE