

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization

International Bureau



(10) International Publication Number

WO 2014/161905 A1

(43) International Publication Date
9 October 2014 (09.10.2014)

(51) International Patent Classification:
C08F 4/657 (2006.01) *C08F 10/06* (2006.01)

(21) International Application Number:
PCT/EP2014/056625

(22) International Filing Date:
2 April 2014 (02.04.2014)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
13162413.2 5 April 2013 (05.04.2013) EP

(71) Applicant: **BASELL POLIOLEFINE ITALIA S.R.L.**
[IT/IT]; Via Soperga 14/A, I-20127 Milano (IT).

(72) Inventors: **GUIDOTTI, Simona**; C/O Basell Poliolefine Italia S.r.l., P.le G. Donegani, 12, I-44122 Ferrara (IT). **LIGUORI, Dario**; C/O Basell Poliolefine Italia S.r.l., P.le G. Donegani, 12, I-44122 Ferrara (IT). **MORINI, Giampiero**; C/O Basell Poliolefine Italia S.r.l., P.le G. Donegani, 12, I-44122 Ferrara (IT). **PIEMONTESSI, Fabrizio**; C/O Basell Poliolefine Italia S.r.l., P.le G. Donegani, 12, I-44122 Ferrara (IT).

(74) Agent: **GIBERTI, Stefano**; Basell Poliolefine Italia S.r.l., Intellectual Property, P.le Donegani 12, I-44122 Ferrara (IT).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))



WO 2014/161905 A1

(54) Title: CATALYST COMPONENTS FOR THE POLYMERIZATION OF OLEFINS

(57) Abstract: A solid catalyst component for the (co)polymerization of olefins $\text{CH}_2=\text{CHR}$, in which R is a hydrocarbyl radical with 1-12 carbon atoms, optionally in mixture with ethylene, comprising Ti, Mg, Cu, Cl, and an electron donor compound characterized by the fact that the Cu/Ti weight ratio is lower than 0.5.

CATALYST COMPONENTS FOR THE POLYMERIZATION OF OLEFINS

FIELD OF THE INVENTION

[0001] The present invention relates to catalyst components for the (co)polymerization of olefins, in particular propylene, comprising Mg, Cu, Ti and halogen elements and at least an electron donor compound. The present invention further relates to the catalysts obtained from said components and to their use in processes for the (co)polymerization of olefins in particular propylene.

BACKGROUND OF THE INVENTION

[0002] Catalyst components for the stereospecific polymerization of olefins, such as propylene, are widely known in the art and they are of the Ziegler-Natta category type. The first catalyst of this type widely used in the industry was based on the use of solid $TiCl_3$ obtained by reduction of $TiCl_4$ with aluminum alkyls. The activity and stereospecificity of the catalysts were not so high so that the polymer had to be subject to a deashing treatment to remove the catalyst residues and to a washing step for removing the atactic polymer produced. Nowadays, the most spread out catalyst family used industrially comprises a solid catalyst component, constituted by a magnesium dihalide on which are supported a titanium compound and an internal electron donor compound, used in combination with an Al-alkyl compound. Conventionally these catalysts are used together with an external donor (for example an alkoxy silane) which helps in obtaining higher isotacticity. One of the preferred classes of internal donors is constituted by the esters of phthalic acid, diisobutylphthalate being the most used. The phthalates are used as internal donors in combination with alkylalkoxysilanes as external donor. This catalyst system is capable of giving good performances in terms of activity, and propylene polymers with high isotacticity and xylene insolubility. It is however of general interest the possibility of increasing the intrinsic capability of the solid catalyst components, particularly of those based on donors different from phthalates, to produce stereoregular polymers. In fact, an intrinsically more stereospecific catalyst component would allow to use a lower amount of stereoregulating external donor to

reach the target of polymer xylene insolubility and this, in turn, would be translated into the possibility of obtaining a higher plant productivity.

[0003] Based on this, it would be very convenient to find a way of improving the stereospecificity of a solid catalyst component and in particular it would be convenient that this method be of a wide applicability.

[0004] Since the discovery of magnesium chloride based supports numerous attempts have been made to include in it additional compounds with the aim of imparting new or modified properties to the final catalysts.

[0005] In US 4,613,655 substantial amounts (30% by weight or higher) of different inorganic compounds and, among them Cu_2Cl_2 (table VII), is mixed with MgCl_2 and then ground in the presence of TiCl_4 in order to produce a catalyst. Apart from the effect of dilution of MgCl_2 , the catalyst, used in the ethylene polymerization, the catalyst did not show any improvement from the presence of Cu_2Cl_2 .

[0006] JP2010-155949 discloses the preparation of solid catalysts components according to several techniques all of them having in common the use of copper containing compounds at various stages of preparation. Depending on the preparation technique and specific ingredients, the final amount of Cu in the catalyst (table 1 and 2) and its relative ratio with Ti may vary from Cu/Ti weight ratio of 1.91 (Ex.1, the highest) to 0.55 (Ex. 7, the lowest).

[0007] According to this reference, the catalyst components containing Cu allows to get increase in the catalyst activity while the stereospecificity is maintained at the same level of the comparative catalyst (not containing Cu) or slightly increased. This is confirmed by the review carried out on examples 1-3 and comparative example 1 in table 1 (all catalyst prepared with the same technique) showing that an increase in stereospecificity with respect to the catalyst not containing Cu (Comparative 1; CXS 2.3) was obtained only for the catalysts (1-2) in which the weight ratio Cu/Ti was higher than 1 and in particular the trend clearly shows a linear decrease of stereospecificity (expressed by increasing values of CXS i.e., amount of low crystallinity soluble matter) going from Cu/Ti weight ratio of 1.91 (EX. 1 CXS1.1) to weight ratio Cu/Ti 0.77 (EX3, CXS 2.3 as in the comparative example 1). It has to

be reported that when the catalyst is prepared according to a different technique (Example 4) the increase in stereospecificity with respect to catalyst not containing Cu (comparative example 2) is not seen at all. In addition, when the catalyst is prepared according to a still different technique and the Cu/Ti weight ratio is 0.55 the stereospecificity with respect to the same catalyst without Cu (comparative example 5) is even slightly worsened.

[0008] The same teaching described above is also reported in JP2010—155948 and JP2010-155950.

[0009] Now the applicant has surprisingly found that it is possible to increase the stereospecificity of catalyst components based on Mg containing support on which are supported titanium atoms and donors by modifying it with specific amounts of Cu compounds.

SUMMARY OF THE INVENTION

[0010] It is therefore an object of the present invention a solid catalyst component comprising Ti, Mg, Cu, Cl, and an electron donor compound characterized by the fact that the Cu/Ti weight ratio is lower than 0.5.

DETAILED DESCRIPTION OF THE INVENTION

[0011] Preferably, in the catalyst component of the present invention the Cu/Ti weight ratio ranges from 0.1 to 0.45.

[0012] Preferably the amount of Cu is lower than 2%, more preferably equal to or lower than 1.8 and especially lower than 1.5% based on the total weight of the solid catalyst component. The Cu/Mg molar ratio preferably ranges from 0.001 to 0.05.

[0013] Preferably, more than 60% and more preferably more than 70% of the titanium atoms are in +4 valence state. The total amount of Ti is typically equal to or higher than 0.5 and preferably higher than 0.8%wt with respect to the total weight of the solid catalyst component. In a specific embodiment it ranges from 0.5 to 3% more preferably from higher than 0.8 to 2.5% and especially in the range in the range

1.1- 2.5%wt. This latter range is particularly preferred in combination with the use of cu atoms deriving from CuCl₂ and esters of optionally substituted aromatic mono or polycarboxylic acids as internal donors.


[0014] The particles of solid component have substantially spherical morphology and average diameter comprised between 5 and 150 μm , preferably from 20 to 100 μm and more preferably from 30 to 90 μm . As particles having substantially spherical morphology, those are meant wherein the ratio between the greater axis and the smaller axis is equal to or lower than 1.5 and preferably lower than 1.3.

[0015] The Mg atoms preferably derive from magnesium chloride, preferably from magnesium dichloride and more preferably from magnesium dichloride in active form meaning that it is characterized by X-ray spectra in which the most intense diffraction line which appears in the spectrum of the non active chloride (lattice distanced of 2,56 \AA) is diminished in intensity and is broadened to such an extent that it becomes totally or partially merged with the reflection line falling at lattice distance (d) of 2.95 \AA . When the merging is complete the single broad peak generated has the maximum of intensity which is shifted towards angles lower than those of the most intense line.

[0016] The titanium atoms preferably derive from titanium compounds of formula Ti(OR)_nX_{4-n} in which n is comprised between 0 and 4; X is halogen and R is an hydrocarbon radical, preferably alkyl, radical having 1-10 carbon atoms or a COR group. Among them, particularly preferred are titanium compounds having at least one Ti-halogen bond such as titanium tetrahalides or halogenalcohohlates. Preferred specific titanium compounds are TiCl₄, and Ti(OEt)Cl₃.

[0017] The components of the invention also comprise an electron donor compound (internal donor), selected from esters, ethers, amines, silanes and ketones or mixtures thereof. Particularly preferred classes are alkyl and aryl esters of optionally substituted aromatic mono or polycarboxylic acids such as for example esters of benzoic and phthalic acids, and esters of aliphatic acids selected from malonic, glutaric and maleic acids. Specific examples of such esters are n-butylphthalate, di-isobutylphthalate, di-n-octylphthalate, ethyl-benzoate and p-ethoxy ethyl-benzoate. Also, the diesters disclosed in WO2010/078494 and US 7,388,061 can be used. Among

this class, particularly preferred are the 2,4-pentanediol dibenzoate derivatives. Moreover, can be advantageously used also the 1,3 diethers of the formula:



[0018] wherein R, R^I, R^{II}, R^{III}, R^{IV} and R^V equal or different to each other, are hydrogen or hydrocarbon radicals having from 1 to 18 carbon atoms, and R^{VI} and R^{VII}, equal or different from each other, have the same meaning of R-R^V except that they cannot be hydrogen; one or more of the R-R^{VII} groups can be linked to form a cycle. The 1,3-diethers in which R^{VI} and R^{VII} are selected from C₁-C₄ alkyl radicals are particularly preferred.

[0019] Preferably, the final amount of electron donor compound in the solid catalyst component ranges from 1 to 25% by weight preferably in the range from 3 to 20% by weight.

[0020] The Cu atoms preferably derive from one or more Cu compounds not having Cu-carbon bonds. In particular the Cu compounds can be selected from Cu halides, Cu carbonate, Cu acetate, Cu nitrate, Cu oxide, Cu sulphate, Cu sulfide. Compounds in which Cu has the valence +2 are preferred. Among Cu halides, preferred are Cu dichloride and Cu dibromide. The most preferred Cu compounds are CuO, CuCl₂, and Cu diacetate. It is particularly preferred to use compounds in which Cu has the valence +2 in such an amount to leave less than 1.5% wt of Cu in the final solid catalyst component.

[0021] The preparation of the solid catalyst component can be carried out according to several methods.

[0022] According to one of these methods, the magnesium dichloride in an anhydrous state, the titanium compound, the Cu compound and the electron donor compounds are milled together under conditions in which activation of the magnesium dichloride occurs. The so obtained product can be treated one or more

times with an excess of $TiCl_4$ at a temperature between 80 and 135°C. This treatment is followed by washings with hydrocarbon solvents until chloride ions disappeared. According to a further method, the product obtained by co-milling the magnesium chloride in an anhydrous state, the titanium compound, the Cu compound and the electron donor compounds are treated with halogenated hydrocarbons such as 1,2-dichloroethane, chlorobenzene, dichloromethane etc. The treatment is carried out for a time between 1 and 4 hours and at temperature of from 40°C to the boiling point of the halogenated hydrocarbon. Any Cu compound of the invention can be used in the comilling technique, and CuO and $CuCl_2$ are the most preferred. When using the milling technique for preparing the catalyst component the final amount of Cu preferably range from 0.1 to 1.5% by weight and the preferred internal donors are the alkyl esters of phthalic acids.

[0023] According to another preferred method, the solid catalyst component can be prepared by reacting a titanium compound of formula $Ti(OR)_{q-y}X_y$, where q is the valence of titanium and y is a number between 1 and q, preferably $TiCl_4$, with a magnesium chloride deriving from an adduct of formula $MgCl_2 \cdot pROH$, where p is a number between 0.1 and 6, preferably from 2 to 3.5, and R is a hydrocarbon radical having 1-18 carbon atoms. The adduct can be suitably prepared in spherical form by mixing alcohol and magnesium chloride, operating under stirring conditions at the melting temperature of the adduct (100-130°C). Then, the adduct is mixed with an inert hydrocarbon immiscible with the adduct thereby creating an emulsion which is quickly quenched causing the solidification of the adduct in form of spherical particles. Examples of spherical adducts prepared according to this procedure are described in USP 4,399,054 and USP 4,469,648. The so obtained adduct can be directly reacted with Ti compound by suspending the adduct (dealcoholated or as such) in cold $TiCl_4$ (generally 0°C); the mixture is heated up to 80-130°C and kept at this temperature for 0.5-2 hours. The treatment with $TiCl_4$ can be carried out one or more times. The electron donor compound is added in the desired ratios during the treatment with $TiCl_4$. Several ways are available to add the Cu compound. According to the preferred option, the Cu compound is incorporated directly into the $MgCl_2 \cdot pROH$ adduct during its preparation. In particular, the Cu compound can be

added at the initial stage of adduct preparation by mixing it together with $MgCl_2$ and the alcohol. Alternatively, it can be added to the molten adduct before the emulsification step. Preferred Cu compound to be incorporated directly into the $MgCl_2 \bullet pROH$ adduct are $CuCl_2$, CuO and $Cu(AcO)_2$. When using CuO it is preferred although not strictly necessary use it in very small particle size and in particular in the form of nano particles i.e, particles having at least one dimension in the range of nanometers.

[0024] The preparation of catalyst components in spherical form are described for example in European Patent Applications EP-A-395083, EP-A-553805, EP-A-553806, EPA601525 and WO98/44001.

[0025] The solid catalyst component has an average particle size ranging from 5 to 120 μm and more preferably from 10 to 100 μm .

[0026] As mentioned, in any of these preparation methods the desired electron donor compounds can be added as such or, in an alternative way, can be obtained *in situ* by using an appropriate precursor capable of being transformed in the desired electron donor compound by means, for example, of known chemical reactions such as etherification, alkylation, esterification, transesterification etc.

[0027] Regardless of the preparation method used, the final amount of the electron donor compound is such that its molar ratio with respect to the $TiCl_4$ is from 0.01 to 2, preferably from 0.05 to 1.2.

[0028] The solid catalyst components according to the present invention are converted into catalysts for the polymerization of olefins by reacting them with organoaluminum compounds according to known methods.

[0029] In particular, an object of the present invention is a catalyst for the polymerization of olefins $CH_2=CHR$, in which R is a hydrocarbyl radical with 1-12 carbon atoms, optionally in mixture with ethylene, comprising the product obtained by contacting:

- (i) the solid catalyst component as disclosed above and
- (ii) an alkylaluminum compound and,
- (iii) an external electron donor compound.

[0030] The alkyl-Al compound (ii) is preferably chosen among the trialkyl aluminum compounds such as for example triethylaluminum, triisobutylaluminum, tri-n-butylaluminum, tri-n-hexylaluminum, tri-n-octylaluminum. It is also possible to use alkylaluminum halides, alkylaluminum hydrides or alkylaluminum sesquichlorides, such as AlEt_2Cl and $\text{Al}_2\text{Et}_3\text{Cl}_3$, possibly in mixture with the above cited trialkylaluminums.

[0031] Suitable external electron-donor compounds include silicon compounds, ethers, esters, amines, heterocyclic compounds and particularly 2,2,6,6-tetramethylpiperidine and ketones.

[0032] Another class of preferred external donor compounds is that of silicon compounds of formula $(\text{R}_6)_a(\text{R}_7)_b\text{Si}(\text{OR}_8)_c$, where a and b are integers from 0 to 2, c is an integer from 1 to 4 and the sum (a+b+c) is 4; R_6 , R_7 , and R_8 , are alkyl, cycloalkyl or aryl radicals with 1-18 carbon atoms optionally containing heteroatoms. Particularly preferred are the silicon compounds in which a is 1, b is 1, c is 2, at least one of R_6 and R_7 is selected from branched alkyl, cycloalkyl or aryl groups with 3-10 carbon atoms optionally containing heteroatoms and R_8 is a $\text{C}_1\text{-C}_{10}$ alkyl group, in particular methyl. Examples of such preferred silicon compounds are methylcyclohexyldimethoxysilane (C donor), diphenyldimethoxysilane, methyl-t-butyldimethoxysilane, dicyclopentyldimethoxysilane (D donor), diisopropyldimethoxysilane, (2-ethylpiperidinyl)t-butyldimethoxysilane, (2-ethylpiperidinyl)hexyldimethoxysilane, (3,3,3-trifluoro-n-propyl)(2-ethylpiperidinyl)dimethoxysilane, methyl(3,3,3-trifluoro-n-propyl)dimethoxysilane. Moreover, the silicon compounds in which a is 0, c is 3, R_7 is a branched alkyl or cycloalkyl group, optionally containing heteroatoms, and R_8 is methyl are also preferred. Examples of such preferred silicon compounds are cyclohexyltrimethoxysilane, t-butytrimethoxysilane and thexytrimethoxysilane.

[0033] The electron donor compound (iii) is used in such an amount to give a molar ratio between the organoaluminum compound and said electron donor compound (iii) of from 0.1 to 500, preferably from 1 to 300 and more preferably from 3 to 100.

[0034] Therefore, it constitutes a further object of the present invention a process for the (co)polymerization of olefins $\text{CH}_2=\text{CHR}$, in which R is hydrogen or a

hydrocarbyl radical with 1-12 carbon atoms, carried out in the presence of a catalyst comprising the product of the reaction between:

- (i) the solid catalyst component of the invention;
- (ii) an alkylaluminum compound and,
- (iii) optionally an electron-donor compound (external donor).

[0035] The polymerization process can be carried out according to known techniques for example slurry polymerization using as diluent an inert hydrocarbon solvent, or bulk polymerization using the liquid monomer (for example propylene) as a reaction medium. Moreover, it is possible to carry out the polymerization process in gas-phase operating in one or more fluidized or mechanically agitated bed reactors.

[0036] The polymerization is generally carried out at temperature of from 20 to 120°C, preferably of from 40 to 80°C. When the polymerization is carried out in gas-phase the operating pressure is generally between 0.5 and 5 MPa, preferably between 1 and 4 MPa. In the bulk polymerization the operating pressure is generally between 1 and 8 MPa, preferably between 1.5 and 5 MPa.

[0037] As already explained, the catalyst of the invention show, in propylene homopolymerization an increased activity/stereospecificity balance particularly due to increased stereospecificity compared with prior art catalysts not containing Cu atoms or containing a too high amount of Cu. It has been also observed that the catalyst of the invention show a particularly interesting behavior also in the copolymerization of propylene with minor amounts of ethylene and/or other olefins $\text{CH}_2=\text{CHR}$ for the preparation of propylene copolymers containing up to 10% weight of ethylene and/or said $\text{CH}_2=\text{CHR}$ olefins different from propylene.

The following examples are given in order to better illustrate the invention without limiting it.

EXAMPLES

CHARACTERIZATIONS**[0038] Determination of Mg, Ti_(TOT) and Cu**

The determination of Mg, Ti_(TOT) and Cu content in the solid catalyst component has been carried out via inductively coupled plasma emission spectroscopy on "I.C.P Spectrometer ARL Accuris".

The sample was prepared by analytically weighting, in a "Fluxy" platinum crucible", 0.1÷0.3 grams of catalyst and 2 grams of lithium metaborate/tetraborate 1/1 mixture. After addition of some drops of KI solution, the crucible is inserted in a special apparatus "Claisse Fluxy" for the complete burning. The residue is collected with a 5% v/v HNO₃ solution and then analyzed via ICP at the following wavelengths: Magnesium, 279.08 nm; Titanium, 368.52 nm; Copper, 327.40 nm.

[0039] Determination of internal donor content

The determination of the content of internal donor in the solid catalytic compound was done through gas chromatography. The solid component was dissolved in acetone, an internal standard was added, and a sample of the organic phase was analyzed in a gas chromatograph, to determine the amount of donor present at the starting catalyst compound.

[0040] Determination of X.I.

2.5 g of polymer and 250 ml of o-xylene were placed in a round-bottomed flask provided with a cooler and a reflux condenser and kept under nitrogen. The obtained mixture was heated to 135°C and was kept under stirring for about 60 minutes. The final solution was allowed to cool to 25°C under continuous stirring, and the insoluble polymer was then filtered. The filtrate was then evaporated in a nitrogen flow at 140°C to reach a constant weight. The content of said xylene-soluble fraction is expressed as a percentage of the original 2.5 grams and then, by difference, the X.I. %.

EXAMPLES

[0041] Procedure for the preparation of the phthalate-based milled solid catalyst component

Magnesium dichloride anhydrous, diisobutylphthalate in amount such as to have a Mg/DIBP molar ratio of 17 were introduced into a four ball mill together with a copper compound of the type and amount indicated in Table 1. The components were milled together at room temperature for 6 h. The resulting solid catalyst precursors were treated with an excess of $TiCl_4$: the temperature was raised to 100°C and maintained for 2 h. Thereafter, stirring was stopped, the solid product was allowed to settled and the supernatant liquid was siphoned off at 100°C. After the supernatant was removed, additional fresh $TiCl_4$ was added to reach the initial liquid volume again. The mixture was then heated at 120°C and kept at this temperature for 1 hour. Stirring was stopped again, the solid was allowed to settle and the supernatant liquid was siphoned off. The solid was washed with anhydrous hexane six times in temperature gradient down to 60°C and one time at room temperature. The obtained solid was then dried under vacuum and analyzed.

[0042] Procedure for the preparation of the diether-based milled solid catalyst component

Magnesium dichloride anhydrous, 9,9-bis(methoxymethyl)fluorene in amount such as to have a Mg/diether molar ratio of 17 were introduced into a four ball mill together with a copper compound of the type and amount indicated in Table 2. The components were milled together at room temperature for 6 h. The resulting solid catalyst precursors were treated with an excess of $TiCl_4$: the temperature was raised to 100°C and maintained for 2 h. Thereafter, stirring was stopped, the solid product was allowed to settled and the supernatant liquid was siphoned off at 100°C. After the supernatant was removed, additional fresh $TiCl_4$ was added to reach the initial liquid volume again. The mixture was then heated at 110°C and kept at this temperature for 1 hour. Stirring was stopped again, the solid was allowed to settle and the supernatant liquid was siphoned off. The solid was washed with anhydrous

hexane six times in temperature gradient down to 60°C and one time at room temperature. The obtained solid was then dried under vacuum and analyzed.

[0043] Procedure for the preparation of the spherical adduct

Microspheroidal $MgCl_2 \cdot pC_2H_5OH$ adduct was prepared according to the method described in Example 2 of WO98/44009, but operating on larger scale and optionally adding a copper compound of the type and amount indicated in Tables 3 and 4.

[0044] Procedure for the preparation of the phthalate-based solid catalyst component from the spherical adduct

Into a 500 ml round bottom flask, equipped with mechanical stirrer, cooler and thermometer 300 ml of $TiCl_4$ were introduced at room temperature under nitrogen atmosphere. After cooling to 0°C, while stirring, diisobutylphthalate and 9.0 g of the spherical adduct (prepared as described above) were sequentially added into the flask. The amount of charged internal donor was such to meet a Mg/donor molar ratio of 8. The temperature was raised to 100°C and maintained for 2 hours. Thereafter, stirring was stopped, the solid product was allowed to settle and the supernatant liquid was siphoned off at 100°C. After the supernatant was removed, additional fresh $TiCl_4$ was added to reach the initial liquid volume again. The mixture was then heated at 120°C and kept at this temperature for 1 hour. Stirring was stopped again, the solid was allowed to settle and the supernatant liquid was siphoned off. The solid was washed with anhydrous hexane six times in temperature gradient down to 60°C and one time at room temperature. The obtained solid was then dried under vacuum and analyzed.

[0045] Procedure for the preparation of the diether-based solid catalyst component from the spherical adduct

Into a 500 ml round bottom flask, equipped with mechanical stirrer, cooler and thermometer 300 ml of $TiCl_4$ were introduced at room temperature under nitrogen atmosphere. After cooling to 0°C, while stirring, 9,9-bis(methoxymethyl)fluorene and 9.0 g of the spherical adduct (prepared as described above) were sequentially added into the flask. The amount of charged internal donor was such as to have a Mg/donor molar ratio of 6. The temperature was raised to 100°C and maintained for 2 hours. Thereafter, stirring was stopped, the solid product was allowed to settle and

the supernatant liquid was siphoned off at 100°C. After the supernatant was removed, additional fresh TiCl₄ was added to reach the initial liquid volume again. The mixture was then heated at temperature in the range of 110°C and kept at this temperature for 1 hour. Stirring was stopped again, the solid was allowed to settle and the supernatant liquid was siphoned off. The solid was washed with anhydrous hexane six times in temperature gradient down to 60°C and one time at room temperature. The obtained solid was then dried under vacuum and analyzed.

[0046] General procedure for the polymerization of propylene

A 4-liter steel autoclave equipped with a stirrer, pressure gauge, thermometer, catalyst feeding system, monomer feeding lines and thermostating jacket, was purged with nitrogen flow at 70°C for one hour. A suspension containing 75 ml of anhydrous hexane, 0.76 g of AlEt₃ (6.66 mmol), 0.33 mmol of external donor and 0.006 ÷ 0.010 g of solid catalyst component, previously precontacted for 5 minutes, was charged. Either dicyclopentyldimethoxysilane, D donor, or cyclohexylmethyldimethoxysilane, C donor, were used as external donor as specified in Tables 1 and 2. All tests reported in Table 3 were carried out with C donor, while some tests described in Tables 2 and 4 were carried out without any external donor. The autoclave was closed and the desired amount of hydrogen was added (in particular, 2 NL in D donor tests, 1.5 NL in C donor tests and 1.25 NL in tests without external donor were used). Then, under stirring, 1.2 kg of liquid propylene was fed. The temperature was raised to 70°C in about 10 minutes and the polymerization was carried out at this temperature for 2 hours. At the end of the polymerization, the non-reacted propylene was removed; the polymer was recovered and dried at 70°C under vacuum for 3 hours. Then the polymer was weighed and characterized.

[0047] Examples 1 – 2 and Comparative Examples C1 – C4

The phthalate-based milled solid catalyst components were prepared using the general method described above. Their composition and related propylene polymerization performance are indicated in Table 1.

[0048] Examples 3 – 5 and Comparative Examples C5 – C10

The diether-based milled solid catalyst components were prepared using the general method described above. Their composition and related propylene polymerization performance are indicated in Table 2.

[0049] Examples 6-15 and Comparative Examples C11 – C13

The phthalate-based solid catalyst components were prepared from spherical adducts $\text{MgCl}_2 \cdot \text{pC}_2\text{H}_5\text{OH}$ using the general method described above. The only difference was in Example 14 where 10.0 g of spherical support (instead of 9.0) were reacted with an initial amount of 250 cm^3 of TiCl_4 (instead of 300 cm^3) Their composition and related propylene polymerization performance are indicated in Table 3.

[0050] Examples 16-23 and Comparative Examples C14 – C17

The diether-based solid catalyst components were prepared from spherical adducts $\text{MgCl}_2 \cdot \text{pC}_2\text{H}_5\text{OH}$ using the general method described above. Their composition and related propylene polymerization performance are indicated in Table 4.

Table 1: Phthalate-based milled solid catalyst components

	Milling Conditions		Solid Catalyst Component					Polymerization		
	Cu compound	Cu/Mg % mol	Mg %wt.	Ti %wt.	Cu %wt.	DIBP %wt.	Cu/Ti wt./wt.	ED type	Mileage Kg/g	XI %wt.
Ex. 1	CuCl_2	1.2	21.4	1.9	0.51	6.5	0.26	D	54	98.2
Ex. 2								C	43	97.3
C1	CuCl_2	3.8	20.4	1.7	2.00	6.7	1.18	D	24	97.7
C2								C	21	96.9
C3	none	–	20.6	2.1	–	6.8	–	D	39	97.6
C4								C	32	96.8

DIBP = diisobutyl phthalate

Table 2: Diether-based milled solid catalyst components

	Milling Conditions		Solid Catalyst Component					Polymerization		
	Cu Comp.	Cu/Mg % mol	Mg %wt.	Ti %wt.	Cu %wt.	Diether %wt.	Cu/Ti wt./wt.	ED type	Mileage Kg/g	XI %wt.
Ex. 3	CuCl2	1.8	20.9	1.7	0.56	5.3	0.32	D	35	97.4
Ex. 4								C	35	97.6
Ex. 5								none	48	96.1
C5	CuCl2	3.5	20.3	1.5	1.33	5.3	0.87	D	32	97.9
C6								C	32	97.5
C7								none	40	95.0
C8	none	-	22.3	1.2	-	5.2	-	D	21	97.7
C9								C	20	97.3
C10								none	34	95.0

Diether = 9,9-bis(methoxymethyl)fluorene

Table 3: Phthalate-based solid catalyst components from spherical adducts

	Support Synthesis		Support Composition			Solid Catalyst Component					Polymerization	
	Cu Comp.	Cu/ Mg % mol	Mg % wt.	Cu % wt.	EtOH/ Mg m.r.	Mg % wt.	Ti % wt.	Cu % wt.	DIBP % wt.	Cu/Ti wt./wt.	Mileage Kg/g	XI %wt.
Ex. 6	CuO	2.0	10.2	0.45	2.9	18.3	2.6	0.73	11.6	0.28	74	97.9
Ex. 7		3.0	9.7	0.70	3.3	18.6	2.6	1.15	11.7	0.45	65	98.1
Ex. 8	Cu(OAc) ₂	1.0	10.3	0.20	2.9	19.0	2.2	0.36	10.6	0.16	74	98.3
Ex. 9		2.0	10.2	0.50	3.0	18.5	2.5	0.68	12.2	0.27	73	97.9
Ex. 10		3.0	10.3	0.75	3.0	17.8	2.6	1.26	11.3	0.48	74	97.9
Ex. 11	CuCl ₂	1.0	10.6	0.30	2.9	18.3	2.6	0.45	10.9	0.17	67	98.0
Ex. 12		2.0	10.3	0.55	3.0	18.4	3.0	0.93	8.8	0.31	65	98.0
Ex. 13		3.0	10.0	0.70	3.1	18.3	2.7	1.30	10.3	0.48	62	98.2
Ex. 14		2.0	10.5	0.5	2.8	18.4	2.4	0.92	12.3	0.39	83	98.5
C11	none	—	10.3	—	2.9	18.8	2.9	—	13.6	—	83	97.6

	Support Synthesis		Support Composition			Solid Catalyst Component					Polymerization	
	Cu Comp.	Cu/ Mg % mol	Mg % wt	Cu % wt	EtOH/ Mg m.r.	Mg % wt.	Ti % wt	Cu % wt	DIBP % wt	Cu/Ti wt./wt	Mileage Kg/g	XI %wt.
Ex. 15	Cu(OAc) ₂	2.0	12.0	0.60	2.2	18.4	2.3	0.82	11.3	0.36	66	98.2
C12	Cu(OAc) ₂	3.0	12.1	0.90	2.0	18.9	2.0	1.28	8.1	0.63	62	97.6
C13	none	—	12.2	—	2.1	19.6	2.8	—	10.3	—	67	97.6

DIBP = diisobutyl phthalate. External donor = cyclohexylmethyldimethoxysilane (C donor)

Table 4: Diether-based solid catalyst components from spherical adducts

Support Synthesis			Support Composition			Solid Catalyst Component					Polymerization		
Cu compd	Cu/Mg % mol	Mg % wt.	Cu % wt.	EtO H/M g m.r.	Mg % wt	Ti % wt	Cu % wt.	Diether %wt.	Cu/Ti wt./wt	ED type	Mileage Kg/g	XI %wt.	
Ex. 16	Cu(OAc) ₂	1.0	10.3	0.20	2.9	15.5	4.2	0.2 1	12.8	0.05	D	93	98.7
Ex. 17											none	135	97.0
Ex. 18		3.0	10.3	0.75	3.0	15.1	3.7	0.7 7	15.8	0.21	D	108	98.4
Ex. 19											none	140	97.5
Ex. 20	CuCl ₂	2.0	10.3	0.55	3.0	15.2	4.1	0.5 2	17.5	0.13	D	107	98.9
Ex. 21											none	145	97.9
C14	none	-	10.2	-	3.0	14.3	5.5	-	16.4	-	D	84	98.2
C15											none	143	96.0


Support Synthesis			Support Composition			Solid Catalyst Component					Polymerization		
Cu Comp.	Cu/Mg % mol	Mg % wt.	Cu % wt.	EtOH/Mg m.r.	Mg % wt.	Ti % wt.	Cu % wt.	Diether %wt.	Cu/Ti wt./wt	ED type	Mileage Kg/g	XI %wt.	
Ex. 22	Cu(OAc) ₂	3.0	12.1	0.90	2.0	15.7	3.6	0.7 3	11.5	0.21	D	74	98.6
Ex. 23											none	120	96.2
C16	none	-	12.8	-	2.0	15.0	5.5	-	10.8	-	D	60	97.8
C17											none	97	94.0

Diether = 9,9-bis(methoxymethyl)fluorene

CLAIMS

What is claimed is:

1. A solid catalyst component for the (co)polymerization of olefins $\text{CH}_2=\text{CHR}$, in which R is a hydrocarbyl radical with 1-12 carbon atoms, optionally in mixture with ethylene, comprising Ti, Mg, Cu, Cl, and an electron donor compound characterized by the fact that the Cu/Ti weight ratio is lower than 0.5.
2. The solid catalyst component of claim 1 in which the Cu/Ti weight ratio ranges from 0.1 to 0.45.
3. The solid catalyst component of claim 1 in which the amount of Cu is lower than 2% by weight based on the total weight of solid catalyst component.
4. The solid catalyst component of claim 1 in which the Cu/Mg molar ratio ranges from 0.001 to 0.05.
5. The solid catalyst component of claim 1 in which the Cu atoms derive from one or more Cu compounds not having Cu-carbon bonds.
6. The solid catalyst component of claim 5 in which the Cu compounds can be selected from Cu halides, Cu acetate, Cu oxide.
7. The solid catalyst component of claim 1 or 3 in which the Cu atoms have valence +2.
8. The solid catalyst component of claim 1 in which electron donor compound is selected from esters, ethers, amines, silanes and ketones or mixtures thereof.
9. The solid catalyst component of claim 1 in which electron donor compound is chosen from the group consisting of alkyl and aryl esters of optionally substituted aromatic mono or polycarboxylic acids, esters of malonic acids, esters of glutaric acids and esters of maleic acids and 1,3 diethers of the formula:



wherein R, R^I, R^{II}, R^{III}, R^{IV} and R^V equal or different to each other, are hydrogen or hydrocarbon radicals having from 1 to 18 carbon atoms, and R^{VI} and R^{VII}, equal or different from each other, have the same meaning of R-R^V except that they cannot be hydrogen; one or more of the R-R^{VII} groups can be linked to form a cycle.

10. A catalyst for the polymerization of olefins CH₂=CHR, in which R is a hydrocarbyl radical with 1-12 carbon atoms, optionally in mixture with ethylene, comprising the product obtained by contacting:
 - (i) the solid catalyst component according to anyone of claims 1-7;
 - (ii) an alkylaluminum compound and,
 - (iii) optionally an external electron donor compound.
11. The catalyst according to claim 9 in which the alkyl-Al compound (ii) is chosen among the trialkyl aluminum compounds.
12. The catalyst according to claim 10 in which the external donor compounds is selected from silicon compounds of formula (R₆)_a(R₇)_bSi(OR₈)_c, where a and b are integers from 0 to 2, c is an integer from 1 to 4 and the sum (a+b+c) is 4; R₆, R₇, and R₈, are alkyl, cycloalkyl or aryl radicals with 1-18 carbon atoms optionally containing heteroatoms.
13. A process for the (co)polymerization of olefins CH₂=CHR, in which R is hydrogen or a hydrocarbyl radical with 1-12 carbon atoms, carried out in the presence of the catalyst according to anyone of claims 10-12.

14. A process according to claim 13 in which propylene and small amounts of ethylene and/or other olefins $\text{CH}_2=\text{CHR}$ are copolymerized to produce propylene copolymers containing up to 10% weight of ethylene and/or said $\text{CH}_2=\text{CHR}$ olefins different from propylene.

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2014/056625

A. CLASSIFICATION OF SUBJECT MATTER
INV. C08F4/657 C08F10/06
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, WPI Data, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>DATABASE WPI Week 201050 Thomson Scientific, London, GB; AN 2010-J17500 XP002714812, -& JP 2010 155949 A (JAPAN POLYCHEM CORP) 15 July 2010 (2010-07-15) cited in the application abstract paragraph [0102] - paragraph [0125] claims 1-10</p> <p>-----</p> <p style="text-align: center;">-/-</p>	1-14



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier application or patent but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search	Date of mailing of the international search report
7 May 2014	13/05/2014
Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer Gamb, Véronique

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2014/056625

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	K. SOGA ET AL.: "The effect of magnesium chloride on the polymerization of alpha-olefins", INT. CONGR. CATAL. PROC., vol. 5, 1984, pages V349-V358, XP009173488, FRG pages V-354 -----	1-14
X, P L	US 2013/244863 A1 (XU DEMIN [US]) 19 September 2013 (2013-09-19) example 16; table 1 claims 1,6,8,13-15,23 paragraph [0036] -----	1-3,5-14

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No
PCT/EP2014/056625

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 2010155949	A 15-07-2010	NONE	
US 2013244863	A1 19-09-2013	NONE	