



HU000035680T2

(19) **HU**(11) Lajstromszám: **E 035 680**(13) **T2****MAGYARORSZÁG**
Szellemi Tulajdon Nemzeti Hivatala**EURÓPAI SZABADALOM**
SZÖVEGÉNEK FORDÍTÁSA(21) Magyar ügyszám: **E 12 846661**
(22) A bejelentés napja: **2012. 09. 20.**(51) Int. Cl.: **C07C 5/27** (2006.01)
C07C 15/08 (2006.01)(96) Az európai bejelentés bejelentési száma:
EP 20120846661(86) A nemzetközi (PCT) bejelentési szám:
PCT/US 12/056178(97) Az európai bejelentés közzétételi adatai:
EP 2773603 A1 **2013. 05. 10.**(87) A nemzetközi közzétételi szám:
WO 13066509(97) Az európai szabadalom megadásának meghirdetési adatai:
EP 2773603 B1 **2017. 05. 17.**

(30) Elsőbbségi adatok: 201113286553 2011. 11. 01. US
(72) Feltalálók(k): BOGDAN, Paula L., Des Plaines, Illinois 60017-5017 (US) WANG, Hui, Des Plaines, Illinois 60017-5017 (US) WILLIS, Richard R., Des Plaines, Illinois 60017-5017 (US)

(73) Jogosult(ak): UOP LLC, Des Plaines, Illinois 60017-5017 (US)

(74) Képviselő: Danubia Szabadalmi és Jogi Iroda Kft., Budapest

(54) **Katalizátor és eljárás szénhidrogének átalakítására**

Az európai szabadalom ellen, megadásának az Európai Szabadalmi Közlönyben való meghirdetésétől számított kilenc hónapon belül, felszólalást lehet benyújtani az Európai Szabadalmi Hivatalnál. (Európai Szabadalmi Egyezmény 99. cikk(1))

A fordítást a szabadalmat az 1995. évi XXXIII. törvény 84/H. §-a szerint nyújtotta be. A fordítás tartalmi helyességét a Szellemi Tulajdon Nemzeti Hivatala nem vizsgálta.

(19)



(11)

EP 2 773 603 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention of the grant of the patent:
17.05.2017 Bulletin 2017/20

(51) Int Cl.:
C07C 5/27 (2006.01) C07C 15/08 (2006.01)

(21) Application number: **12846661.2**

(86) International application number:
PCT/US2012/056178

(22) Date of filing: **20.09.2012**

(87) International publication number:
WO 2013/066509 (10.05.2013 Gazette 2013/19)

(54) CATALYST AND PROCESS FOR HYDROCARBON CONVERSION

**KATALYSATOR UND VERFAHREN ZUR UMWANDLUNG VON KOHLENWASSERSTOFFEN
CATALYSEUR ET PROCÉDÉ DE CONVERSION D'HYDROCARBURES**

(84) Designated Contracting States:
**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO RS SE SI SK SM TR**

- **WANG, Hui**
Des Plaines, Illinois 60017-5017 (US)
- **WILLIS, Richard R.**
Des Plaines, Illinois 60017-5017 (US)

(30) Priority: **01.11.2011 US 201113286553**

(74) Representative: **Boult Wade Tennant
Verulam Gardens
70 Gray's Inn Road
London WC1X 8BT (GB)**

(43) Date of publication of application:
10.09.2014 Bulletin 2014/37

(73) Proprietor: **UOP LLC**
Des Plaines, Illinois 60017-5017 (US)

(56) References cited:
**RU-C2- 2 233 260 US-A- 3 909 450
US-A1- 2007 060 778 US-A1- 2011 245 565
US-B2- 7 939 701**

(72) Inventors:
• **BOGDAN, Paula L.**
Des Plaines, Illinois 60017-5017 (US)

EP 2 773 603 B1

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

FIELD OF THE INVENTION

5 **[0001]** This invention relates to catalysts and processes for hydrocarbon conversion. More specifically, the invention discloses catalysts for the efficient conversion of ethylbenzene and isomerization of xylenes.

BACKGROUND OF THE INVENTION

10 **[0002]** Zeolites are widely used as catalysts for various types of hydrocarbon-conversion processes such as isomerization, reforming, hydrogenation, alkylation, transalkylation, cracking and hydrocracking. In addition, zeolitic materials are used as adsorbents in various petroleum and chemical separation processes. Selectivity in catalysis or separation is conferred by the interstitial spaces or channels formed by the network of crystalline aluminosilicates. Zeolites also may comprise materials in which the silica and alumina portions have been replaced in whole or in part with other oxides; germanium oxide, tin oxide, and mixtures thereof can replace the silica portion and gallium oxide, indium oxide, boron oxide, iron oxide, and mixtures thereof can replace the alumina portion.

15 **[0003]** The practical applications of pure zeolites are severely limited because of mechanical-strength limitations. Mechanical strength may be conferred by forming the zeolite in the presence of a non-zeolitic binder and drying and calcining the resulting extrudate pill, sphere, or extrudate. Examples of such binders include materials such as alumina, silica, titanium, and various types of clays. However, the effectiveness of a bound zeolite in terms of activity, selectivity, or activity maintenance, can be reduced because the binder dilutes the adsorptive properties of the zeolite. In addition, since the bound zeolite is prepared by extruding the zeolite with the binder and subsequently drying and calcining the extrudate, the amorphous binder can penetrate the pores of the zeolite, otherwise block access to the pores of the zeolite, or slow the rate of mass transfer to the pores of the zeolite which can reduce the effectiveness of the zeolite. Still further, when a bound zeolite is used in catalytic processes, the binder may affect the chemical reactions that are taking place within the zeolite and also may catalyze undesirable reactions which can result in the formation of undesirable products.

20 **[0004]** A key application of zeolitic catalysts is in the conversion of C₈ aromatics to obtain individual xylene isomers. The xylenes, para-xylene, meta-xylene and ortho-xylene, are important intermediates which find wide and varied application in chemical syntheses. Para-xylene upon oxidation yields terephthalic acid which is used in the manufacture of synthetic textile fibers and resins. Meta-xylene is used in the manufacture of plasticizers, azo dyes, wood preservers, etc. Ortho-xylene is feedstock for phthalic anhydride production.

25 **[0005]** The catalytic reforming of petroleum naphtha is an important source of C₈ aromatics. Xylene isomers in C₈ aromatics from catalytic reforming or other sources generally do not match demand proportions as chemical intermediates, and further comprise ethylbenzene which is difficult to separate or to convert. Para-xylene in particular is a major chemical intermediate with rapidly growing demand, but amounts to only 15-20% of a typical C₈ -aromatics stream. Adjustment of isomer ratio to demand can be effected by combining xylene-isomer recovery, such as adsorption for para-xylene recovery, with isomerization to yield an additional quantity of the desired isomer. Isomerization converts a non-equilibrium mixture of the xylene isomers which is lean in the desired xylene isomer to a mixture which approaches equilibrium concentrations. The approach to equilibrium that is used is an optimized compromise between high C₈ cyclic loss at high conversion (i.e. very close approach to equilibrium) and high utility costs due to the large recycle rate of unconverted C₈ aromatics.

30 **[0006]** Processes for conversion of C₈ aromatics ordinarily are classified by the manner of converting ethylbenzene associated with the xylene isomers. Ethylbenzene is not easily isomerized to xylenes, but it normally is converted in the process unit because separation from the xylenes by superfractionation or adsorption is very expensive. One approach is to react the ethylbenzene to form a xylene mixture via conversion to and reconversion from naphthenes in the presence of a solid acid catalyst with a hydrogenation-dehydrogenation function. An alternative widely used approach is to dealkylate ethylbenzene to form principally benzene while isomerizing xylenes to a near-equilibrium mixture. The former approach enhances xylene yield by forming xylenes from ethylbenzene; the latter approach commonly results in higher ethylbenzene conversion, thus lowering the quantity of recycle to the para-xylene recovery unit and concomitant processing costs.

35 **[0007]** Hydrogen generally is present in the conversion process reactants to aid in the reaction and maintain catalyst stability. Although xylenes may be isomerized in the absence of hydrogen under some circumstances with resulting cost savings, ethylbenzene conversion generally requires the presence of hydrogen. Two-stage processing units may be justified in some cases to obtain both high conversion and ethylbenzene yield. In any case, the search continues for more effective catalysts and processes.

40 **[0008]** US 2011/245565 discloses a process for xylene and ethylbenzene isomerization using UZM-35.

45 **[0009]** RU 2233260 discloses the selective isomerization of xylenes and conversion of ethylbenzene.

[0010] US 3909450 discloses a method of catalyst manufacture.

SUMMARY OF THE INVENTION

5 [0011] A principal object of the present invention is to provide a novel catalyst effective for the conversion of hydrocarbons. More specifically, the invention comprises a process for the conversion of alkylaromatic hydrocarbons and particularly for the processing of C₈ aromatics to increase the concentration of a desired xylene isomer with reduced aromatic losses and lowered processing costs.

10 [0012] This invention is based on the discovery that conversion of ethylbenzene in connection with xylene isomerization can be effected with a catalyst comprising a binderless zeolite having specific characteristics of porosity and crystallinity gradient.

15 [0013] Accordingly, one embodiment of the invention is a process for the conversion of a non-equilibrium C₈-aromatic feedstock comprising contacting the feedstock with a catalyst bed, comprising particles of an unbound zeolitic aluminosilicate having an particle intrusion pore volume of at least 0.65 cc/gram and a particle crystallinity gradient increasing in the proportion of crystallinity from a low-crystallinity inner portion to a high-crystallinity outer portion, in a conversion zone at conversion conditions comprising a temperature of from 340°C. to 500°C, a pressure of from 100 kPa to 5 MPa, and a mass hourly space velocity of from 2 to 50 hr⁻¹ in the presence of hydrogen to convert ethylbenzene and obtain an isomerized product comprising a higher proportion of at least one xylene isomer than in the feedstock.

20 [0014] A more specific embodiment is a process for the conversion of a non-equilibrium C₈-aromatic feedstock comprising contacting the feedstock with a catalyst bed, comprising particles of an unbound zeolitic aluminosilicate having an particle intrusion pore volume of at least 0.65 cc/gram and a particle crystallinity gradient increasing in the proportion of crystallinity from an inner portion having relative crystallinity from 10 to 50 weight percent to a high-crystallinity 500-micron outer portion having relative crystallinity from 90 to 100 weight percent, in a conversion zone at conversion conditions comprising a temperature of from 340°C. to 500°C, a pressure of from 100 kPa to 5 MPa, and a mass hourly space velocity of from 2 to 50 h⁻¹ in the presence of hydrogen to convert ethylbenzene and obtain an isomerized product comprising a higher proportion of at least one xylene isomer than in the feedstock.

25 [0015] A yet more specific embodiment is a process for the conversion of a non-equilibrium C₈-aromatic feedstock comprising contacting the feedstock with a catalyst bed, comprising particles of an unbound zeolitic aluminosilicate having an particle intrusion pore volume of at least 0.65 cc/gram and a particle crystallinity gradient increasing in the proportion of crystallinity from an inner portion having relative crystallinity from 10 to 50 weight percent to a high-crystallinity 100-micron outer portion having relative crystallinity from 90 to 100 weight percent, in a conversion zone at conversion conditions comprising a temperature of from 340°C. to 500°C, a pressure of from 100 kPa to 5 MPa, and a mass hourly space velocity of from 2 to 50 hr⁻¹ in the presence of hydrogen to convert ethylbenzene with a xylene loss of less than 0.02 per % ethylbenzene conversion and obtain an isomerized product comprising a higher proportion of at least one xylene isomer than in the feedstock.

30 [0016] Other specific embodiments will become clear from the following detailed description of the invention.

BRIEF DESCRIPTION OF THE ILLUSTRATION

35 [0017] Figure 1 shows characteristics of a particle of the invention.

DETAILED DESCRIPTION OF THE INVENTION

40 [0018] Binderless spherical zeolitic particles of the invention feature high catalytic activity and selectivity for the conversion of hydrocarbons and especially for the conversion of aromatic hydrocarbons. Examples of zeolites comprising catalysts of the invention include those having Si:Al₂ ratios greater than 10, and often greater than 20, such as the MFI, MEL, EUO, FER, MFS, MTT, MTW, TON, MOR and FAU types of zeolites as framework type as described in Atlas of Zeolite Framework Types, 6th Revised Edition, C.H. Baerlocher, L.B. McCusker, and D.H. Olson, editors, Elsevier (2007). Pentasil zeolites such as MFI, MEL, MTW and TON are preferred, and MFI-type zeolites, such as ZSM-5, silicalite, Borolite C, TS-1, ZSM-12, SSZ-25, PSH-3, and ITQ-1 are especially preferred.

45 [0019] Preparing the preferred catalyst of the invention first comprises forming a reaction mixture of aluminum and silicon. The sources of aluminum include but are not limited to aluminum alkoxides, precipitated aluminas, aluminum metal, aluminum salts and alumina sols. Specific examples of aluminum alkoxides include, but are not limited to aluminum sec-butoxide and aluminum ortho isopropoxide. Sources of silica include but are not limited to tetraethylorthosilicate, colloidal silica, precipitated silica, alkali silicates, HiSil and Ultrasil. The ratio Si/Al may range from 3 to 100, and preferably from 8 to 50.

50 [0020] The silica-alumina mixture preferably contains substantially no zeolite, as described hereinabove, or structure-directing agent, as described herein below, although it is within the scope of the invention that relatively small amounts

of such materials are present.

5 [0021] A preferred method comprises preparation of an amorphous silica-alumina by means well known in the art. For example, the procedure set forth in US 3,909,450 may be used. This procedure involves making an aluminum sol by digesting aluminum in an aqueous hydrochloric acid solution at reflux temperature to form a sol with a predetermined aluminum/chloride ratio. This aluminum sol is mixed with a silicon sol which has been prepared, for example, by the acidification of water glass. Gelling agents such as hexamethylenetetraamine, urea or mixtures thereof are added and the sol mixture dispersed as droplets in a hot oil bath where gelation occurs with the formation of spheroidal particles. The gelling agent increases the pH of the sol droplets, causing the droplets to gel. This sol-gel process sets the alumina and silica. Further details regarding the oil drop method may be found in U.S. Pat. No. 2,620,314.

10 [0022] Although the above procedure provides an amorphous silica-alumina composition in the form of spheres, the amorphous silica-alumina may be in any form such as extrudate, irregularly shaped particles, pills or tablets as long as these correspond respectively to the form of the finished catalyst. It is especially preferred to use spheres prepared as described above.

15 [0023] The spheres are continuously withdrawn from the oil bath and typically subjected to specific aging and drying treatment in oil and an aqueous ammonia solution to effect the catalyst of the invention. The resulting aged and gelled particles are then washed and dried at a relatively low temperature of 90°C to 150°C and subjected to a calcination procedure at a temperature of 400°C to 700°C for a period of 1 to 20 hours. This provides an amorphous silica-alumina composition. These amorphous silica-alumina compositions are characterized in that they have an apparent bulk density of 0.3 to 0.5 g/cc and a pore volume of 0.4 to 1.0 cc/g.

20 [0024] The catalyst preferably is binderless, i.e., comprises a form suitable for a hydrocarbon-conversion process without the substantial presence of inert components enabling the shape of the finished catalyst. If present, such components are present in a minor amount, e.g., less than 50 mass-%, preferably less than 10 mass-%, and most preferably less than 7 mass-% based upon the mass of the catalyst. Any inert components preferably comprise unconverted material from crystallization of a preformed sphere.

25 [0025] Binderless catalysts are prepared from extrudates or spherical particles composed of, for example, amorphous or crystalline silica and alumina or amorphous silica alumina oxide sources. A mineralizing agent, such as an amine, sodium hydroxide and/or sodium fluoride, tetraalkyl ammonium hydroxide or bromide, the alkyl groups preferably containing 2-5 carbon atoms, and water are also required in order to convert the silica and alumina components into binderless aluminosilicate zeolite particles. The mineralizing agent and water may be incorporated into the spherical particles or extrudates during the forming process, or they can be added later either as a solution, multiple solutions, steam, vapor or any combination thereof. Seeds, nucleating agents, and/or structure directing agents can also be added in small quantities, but in general these are not necessary and/or their use can be avoided. The resulting product may then be optionally calcined in air at temperatures of 400-550°C for a period of 10-40 hours to remove tetraalkylammonium cations.

30 [0026] The product can be further treated in order to remove aluminum and optionally inserting silicon thereby increasing the Si/Al ratio and thus modifying the acidity and ion exchange properties of the zeolites. These treatments include: a) contacting with a fluorosilicate solution or slurry; b) calcining or steaming followed by acid extraction or ion-exchange; c) acid extraction or d) any combination of these treatments in any order.

35 [0027] Catalysts of the invention feature exceptionally high macroporosity and high intrusion volumes, measured in accordance with ASTM D4284 Standard Test Method for Determining Pore Volume Distribution of Catalyst by Mercury Intrusion Porosimetry corresponding to intrusion of a volume of mercury which is characteristic of the existence of mesopores and macropores into the catalyst. The particle intrusion pore volume generally is at least 0.60 cc/gram, preferably at least 0.65 cc/gram, and more preferably greater than 0.70 cc/gram. These characteristics lead to high conversion of ethylbenzene in a C₈-aromatics mixture compared to catalysts prepared by binding a zeolite.

40 [0028] A gradient of crystallinity preferably is determined by Scanning Electron Microscopy ("SEM"). SEM determinations of local crystallinity are effected on at least three sample particles from a bed of catalyst particles. Samples are selected from the bed by techniques known to those of ordinary skill in the art. The SEM data show the crystallinity of any one point within a catalyst particle, based on the crystallinity in relation to the position relative to the diameter of the particle. Measurement of the gradient is effected as the average of the gradient at given levels in at least three catalyst particles, and are useful for making relative comparisons of crystallinity. The particle crystallinity gradient increases in the proportion of crystallinity from a low-crystallinity inner portion having crystallinity from 10 to 50 weight percent to a high-crystallinity outer portion having a crystallinity from 90 to 100 weight percent; the inner portion may comprise 50% of the volume of the particle. This gradient contrasts with a catalyst having a outer layer of zeolite over an amorphous center.

45 [0029] Figure 1 illustrates a particle of the invention which has been sliced to demonstrate the gradient of the invention. The outer portion of the particle shows a high degree of crystallinity, while the central portion shows only a few crystals. The proportion of crystals increases as observations move toward the outer portion.

50 [0030] Catalysts of the invention preferably contain a metal component, comprising one or more metals selected from Group VIII (IUPAC 8-10), Group VIB (IUPAC 6), and Group VIIB (IUPAC 7) metals. One or more of the platinum-group

metals, including one or more of platinum, palladium, rhodium, ruthenium, osmium, and iridium, are particularly favored components of the present catalyst. The preferred platinum-group metals are platinum and palladium, with platinum being especially preferred. The platinum-group metal component may exist within the final catalyst composite as a compound such as an oxide, sulfide, halide, oxysulfide, etc., or as an elemental metal or in combination with one or more other ingredients of the catalyst composite. It is believed that the best results are obtained when substantially all of the platinum-group metal component exists in a reduced state. The platinum-group metal component generally comprises from 10 to 5000 mass-ppm (parts per million) of the final catalyst composite, calculated on an elemental basis, with a level of 100 to 2000 mass-ppm being particularly suitable. When using a platinum component, levels of 200 to 800 mass-ppm of platinum on the catalyst on an elemental basis are favored; and levels of 200 to 500 mass-ppm are especially favored.

[0031] The hydrogenation metal component may be incorporated into the catalyst composite in any suitable manner. One method of preparing the catalyst involves the utilization of a water-soluble, decomposable compound of the hydrogenation metal to impregnate the calcined sieve/binder composite.

[0032] It is within the scope of the present invention that the catalyst composites may contain, in addition, metal modifiers such as one or more of rhenium, tin, germanium, lead, cobalt, nickel, indium, gallium, zinc, uranium, dysprosium, thallium, and mixtures thereof. Catalytically effective amounts of such metal modifiers may be incorporated into the catalysts by any means known in the art to effect a homogeneous or stratified distribution.

[0033] In an alternative embodiment, the catalyst may comprise a dispersed, selectively sulfided rhenium component. The rhenium (calculated as the elemental metal) is present in an amount of between 0.05 and 5, preferably 0.4 to 4, mass of the catalyst and the atomic ratio of sulfur to rhenium is between 0.2:1 to 0.7:1, preferably 0.25:1 to 0.5:1. The first sulfiding of the alternative catalyst preferably employs a highly dilute sulfiding gas under sulfiding conditions, passing the sulfur-containing gas over the catalyst, e.g., at a weight hourly space velocity of at least 0.5 hr⁻¹ and a temperature of at least 100°C as known in the art. Reducing conditions may be provided by the presence of at least one of hydrocarbon and hydrogen in the substantial absence of an oxidizing component. The sulfiding gas frequently contains less than 5000, more preferably less than 500, parts per million by mole (ppm-mole) sulfur.

[0034] The catalysts of the present invention may contain a halogen component, comprising fluorine, chlorine, bromine or iodine or mixtures thereof, with chlorine being preferred. Preferably, however, the catalyst contains no added halogen other than that associated with other catalyst components.

[0035] The catalyst composite is dried, preferably at a temperature of from 100° to 320°C for a period of from 2 to 24 or more hours. If desired, the catalyst may be calcined at a temperature of from 400° to 650°C in an air atmosphere for a period of from 0.1 to 10 hours. Steam may also be present during the calcination, e.g., from 0.5 to 20, say, 1 to 10, mol-% steam based on the air. Where the catalyst contains a minor amount of platinum group metal, the resultant calcined composites often are subjected to a substantially water-free reduction step to ensure a uniform and finely divided dispersion of the optional metallic components. The reducing agent contacts the catalyst at conditions, including a temperature of from 200° to 650°C and for a period of from 0.5 to 10 hours, effective to reduce substantially all of the platinum group metal component, if present, to the metallic state.

[0036] Efficient conversion of ethylbenzene in a C₈-aromatic mixture in combination with isomerization of xylenes is a particularly preferred application of the present catalyst. Feedstocks to the preferred aromatics-conversion process comprise non-equilibrium xylene and ethylbenzene. These aromatic compounds are in a non-equilibrium mixture, i.e., at least one C₈-aromatic isomer is present in a concentration that differs substantially from the equilibrium concentration at isomerization conditions. Thus, a non-equilibrium xylene composition exists where one or two of the xylene isomers are in less than equilibrium proportion with respect to the other xylene isomer or isomers. The xylene in less than equilibrium proportion may be any of the para-, meta- and ortho-isomers. As the demand for para- and ortho-xylenes is greater than that for meta-xylene, usually, the feedstocks will contain meta-xylene. Generally the mixture will have an ethylbenzene content of 1 to 60 mass-%, an ortho-xylene content of 0 to 35 mass-%, a meta-xylene content of 20 to 95 mass-% and a para-xylene content of 0 to 30 mass-%. Usually, the non-equilibrium mixture is prepared by removal of para-, ortho- and/or meta-xylene from a fresh C₈ aromatic mixture obtained from an aromatics-production process. The feedstocks may contain other components, including, but not limited to naphthenes and acyclic paraffins, as well as higher and lower molecular weight aromatics.

[0037] The alkylaromatic hydrocarbons may be used in the present invention as found in appropriate fractions from various refinery petroleum streams, e.g., as individual components or as certain boiling-range fractions obtained by the selective fractionation and distillation of catalytically cracked or reformed hydrocarbons.

According to the process of the present invention, the alkylaromatic hydrocarbon feed mixture, preferably in admixture with hydrogen, is contacted with a catalyst of the invention in an alkylaromatic hydrocarbon conversion zone. Contacting may be effected using the catalyst in a fixed-bed system, a moving-bed system, a fluidized-bed system, or in a batch-type operation. In view of the danger of attrition loss of the valuable catalyst and of the simpler operation, it is preferred to use a fixed-bed system. In this system, a hydrogen-rich gas and the feed mixture are preheated by suitable heating means to the desired reaction temperature and then passed into a conversion zone containing a fixed bed of catalyst.

EP 2 773 603 B1

The conversion may be effected in one or more separate reactors with suitable means therebetween to ensure that the desired conversion temperature is maintained at the entrance to each zone.

[0038] The reactants may be contacted with a catalyst bed in either upward-, downward-, or radial-flow fashion, and the reactants may be in the liquid phase, a mixed liquid-vapor phase, or a vapor phase when contacted with the catalyst.

The reactants preferably are partially or wholly in the vapor phase.

[0039] The alkylaromatic feed mixture, preferably a non-equilibrium mixture of C₈ aromatics, is contacted with the conversion catalyst at suitable alkylaromatic-conversion conditions. Such conditions comprise a temperature ranging from 100° to 600°C or more, and preferably is in the range of from 340° to 500°C. The pressure generally is from 100 kPa to 10 MPa, and more usually no more than 5 MPa. Sufficient catalyst is contained in the conversion zone to provide a mass hourly space velocity with respect to the hydrocarbon feed mixture of from 0.5 to 100 hr⁻¹, and preferably 2 to 50 hr⁻¹; favorable results have been obtained at mass hourly space velocities of at least 10 hr⁻¹ and higher. The hydrocarbon feed mixture optimally is reacted in admixture with hydrogen at a hydrogen/hydrocarbon mole ratio of 0.05:1 to 10:1 or more, and preferably at least 0.05; inert diluents such as nitrogen, argon and light hydrocarbons also may be present.

[0040] Usually the conversion conditions are sufficient to convert at least 50, preferably between 60 and 90, percent of the ethylbenzene in the feed stream. The present process features a high degree of removal of the ethyl radical from ethylbenzene with low formation of toluene and heavy alkylbenzene byproducts. Generally the conversion conditions do not result in a xylene equilibrium being reached. The conversion process generally converts ethylbenzene with a % xylene loss of less than 0.025, and preferably less than 0.02, per % ethylbenzene conversion.

[0041] It is within the invention that an alkylaromatic hydrocarbon feed mixture is contacted sequentially with two or more catalysts in a conversion zone followed by a subsequent xylene-isomerization zone to achieve the objectives of the invention. Such a two-catalyst system is particularly effective through efficient ethylbenzene conversion followed by effective xylene isomerization in a low-ethylbenzene C₈-aromatics mixture. Contacting may be effected in either zone using the catalyst system in a fixed-bed system, a moving-bed system, a fluidized-bed system, slurry system, an ebullated-bed system or in a batch-type operation, but it is preferred to use a fixed-bed system in both zones. The first conversion zone preferably contains a catalyst of the invention operating at conditions effective to convert ethylbenzene as well as to isomerize xylenes as described hereinabove. The first conversion zone yields an intermediate stream, and at least part of and preferably the entire intermediate stream without further processing is contacted in a second conversion zone containing an isomerization catalyst. The isomerization zone may comprise a single reactor or two or more separate reactors with suitable means therebetween to achieve an improved approach to xylene equilibrium. The two catalysts preferably are contained within the same reactor.

[0042] The isomerization zone preferably contains a catalyst particularly effective for xylene isomerization, ethylbenzene having been converted in the first zone. Any catalyst effective for this purpose may be used, including known zeolitic aluminosilicates selected from MFI, MEL, EUO, FER, MFS, MTT, MTW, TON, MOR and FAU types with pentasil zeolites MFI and MTW being preferred. The reactants may contact the second catalyst in liquid phase, a mixed liquid-vapor phase, or a vapor phase. Operating conditions generally are within the range described above for the catalyst of the invention, with a lower temperature in the range of 200° to 400°C being preferred to achieve para-xylene ratios in the upper range described hereinabove.

[0043] The particular scheme employed to recover an isomerized product from the effluent of the reactors is not deemed to be critical to the instant invention, and any effective recovery scheme known in the art may be used. Typically, the conversion product is fractionated to remove light by-products such as alkanes, naphthenes, benzene and toluene, and heavy byproducts to obtain a C₈ isomer product. Heavy byproducts include dimethylethylbenzene and trimethylbenzene.

In some instances, certain product species such as ortho-xylene or dimethyl ethyl benzene may be recovered from the isomerized product by selective fractionation. The product from conversion of C₈ aromatics usually is processed to selectively recover the para-xylene isomer, optionally by crystallization. Selective adsorption is preferred using crystalline aluminosilicates according to US 3,201,491. Improvements and alternatives within the preferred adsorption recovery process are described in US 3,626,020, US 3,696,107, US 4,039,599, US 4,184,943, US 4,381,419 and US 4,402,832.

EXAMPLES

[0044] The following examples are presented only to illustrate certain specific embodiments of the invention, and should not be construed to limit the scope of the invention as set forth in the claims.

Example 1

[0045] A first catalyst of the invention was prepared as follows: into a 125 mL Teflon liner, 11.8 grams of propylamine and 4.0 grams of 10% NaCl aqueous solution were mixed. To that mixture, 8.0 grams of calcined oil-dropped spheres

with Si/Al₂ ratio of 80 were added and totally covered by the liquid phase. The Teflon liner was then loaded into a Parr reactor and heated to 175°C for 10 days. After being cooled to room temperature, the spheres were filtered and washed with deionized water. The calcined particles of catalyst contained 70% MFI by x-ray diffraction. The catalyst was finished by impregnating 111 grams of the calcined product with a 200 milliliters aqueous solution containing 0.08 grams of tetraamineplatinum chloride and 9.41 grams of NH₄NO₃ followed by evaporation at 100° C to yield a final platinum level of 0.04 mass percent on the finished catalyst particles. The impregnated samples then were subjected, as described in Example 1 of US 7,939,701, to a two-stage calcination and an 88°C ammonium ion exchange followed by a 480°C oxidation and a 4-hour 425°C reduction. The catalyst had an ASTM D4284 intrusion volume of 0.718 cc/gram and a platinum content of 220 ppm and is designated as Catalyst A.

Example 2

[0046] A second catalyst of the invention was prepared as follows: into a 125 mL Teflon liner, 15 grams of butylamine and 10 grams of 20% NaCl aqueous solution were mixed. To that mixture, 12 grams of calcined oil-dropped spheres with Si/Al₂ of 40 were added and totally covered by the liquid phase. The Teflon liner was then loaded into a Parr reactor and heated to 175°C for 10 days. After being cooled to room temperature, the spheres were filtered and washed with DI water. The calcined particles of catalyst contained 50% MFI by x-ray diffraction. The catalyst was finished by impregnating 111 grams of the calcined product with a 200 milliliters aqueous solution containing 0.08 grams of tetraamineplatinum chloride and 9.41 grams of NH₄NO₃ followed by evaporation at 100°C to yield a final platinum level of 0.04 mass percent on the finished catalyst particles. The impregnated samples then were subjected, as described in Example 1 of U.S. Patent 7,939,701, to a two-stage calcination and an 88°C ammonium ion exchange followed by a 480°C oxidation and a 4-hour 425°C reduction. The catalyst had an ASTM D4284 intrusion volume of 0.743 cc/gram and a platinum content of 350 ppm and is designated as Catalyst B.

Example 3

[0047] Performance of catalysts of the invention was compared to a reference catalyst of the known art prepared according to Example 2 of U.S. Patent 7,939,701. The tests each were affected by isomerizing a feed stream having the substantial absence of para-xylene and containing 15 mass-percent ethylbenzene, 25 mass-percent ortho-xylene and 60 mass-percent meta-xylene. The tests were conducted at a hydrogen to hydrocarbon ratio of 4 to 1, a weight hourly space velocity of 7 and pressure of 0.7 MPa gauge. Ethylbenzene conversion of 70% was effected at test temperatures ranging from 375° to 400°C. Performance was measured as the loss of xylenes and concomitant yield of byproduct toluene and heavy alkylbenzene as follows:

Catalyst	A	B	Reference
Temperature, °C	375	388	371
Para-xylene/xylenes, %	16	6	24
Xylene loss, %	1.1	0.4	1.9
Toluene+heavy byproduct, mass-%	0.9	0.3	1.7

[0048] Both catalysts of the invention demonstrate lower xylene loss and byproduct yield than the reference catalyst while converting ethylbenzene and increasing the proportion of para-xylene in the product. Note that the ratios of xylene loss to ethylbenzene conversion were, respectively, 0.016, 0.006, and 0.027.

Claims

1. A process for the conversion of a non-equilibrium C₈-aromatic feedstock comprising contacting the feedstock with a catalyst bed, comprising particles of an unbound zeolitic aluminosilicate having an particle intrusion pore volume of at least 0.65 cc/gram and a particle crystallinity gradient increasing in the proportion of crystallinity from a low-crystallinity inner portion to a high-crystallinity outer portion, in a conversion zone at conversion conditions comprising a temperature of from 340°C. to 500°C, a pressure of from 100 kPa to 5 MPa, and a mass hourly space velocity of from 2 to 50 hr⁻¹ in the presence of hydrogen to convert ethylbenzene with low xylene loss and obtain an isomerized product comprising a higher proportion of at least one xylene isomer than in the feedstock.
2. The process of claim 1 wherein the particle intrusion pore volume is at least 0.7 cc/gram.

EP 2 773 603 B1

3. The process of claim 1 wherein an inner portion of the catalyst particle is defined as the portion of the particle corresponding to the volume enclosed by half of the radius of the particle.
- 5 4. The process of claim 1 wherein the inner portion of the catalyst particle is defined as the inner 50 % of the volume of the catalyst particle.
5. The process of one of claim 3 or 4 wherein the relative crystallinity of the inner portion of the catalyst particle is from 10 to 50%.
- 10 6. The process of one of claim 3 or 4 wherein the relative crystallinity of the outer portion of the catalyst particle is from 90 to 100%.
7. The process of one of claim 1 or 2 wherein the catalyst has a spherical configuration.
- 15 8. The process of one of claim 7 wherein the spherical configuration of the catalyst comprises characteristics of oil dropping.
9. The process of one of claim 1 or 2 wherein the % xylene loss is less than 0.02% per % ethylbenzene conversion.

20

Patentansprüche

1. Katalysator zur Umwandlung von nicht im Gleichgewicht befindlichem C₈-aromatischem Einsatzmaterial, umfassend Kontaktieren des Einsatzmaterials mit einem Katalysatorbett, das Partikel eines ungebundenen zeolithischen Aluminosilikats mit einem Intrusionsporenvolumen des Partikels von mindestens 0,65 cm³/g und einem Kristallinitätsgradienten des Partikels umfasst, der im Anteil der Kristallinität von einem inneren Anteil mit niedriger Kristallinität zu einem äußeren Anteil mit hoher Kristallinität ansteigt, in einer Umwandlungszone unter Umwandlungsbedingungen, die eine Temperatur von 340 °C bis 500 °C, einen Druck von 100 kPa bis 5 MPa und einen stündlichen Massendurchsatz von 2 bis 50 h⁻¹ umfassen, in Gegenwart von Wasserstoff, um Ethylbenzol mit niedrigem Xylolverlust umzuwandeln und ein isomerisiertes Produkt zu erhalten, das einen höheren Anteil an mindestens einem Xylolisomer als in dem Einsatzmaterial umfasst.
- 25 2. Verfahren nach Anspruch 1, wobei das Intrusionsporenvolumen des Partikels mindestens 0,7 cm³/g beträgt.
- 35 3. Verfahren nach Anspruch 1, wobei ein innerer Anteil des Katalysatorpartikels definiert ist als der Anteil des Partikels, welcher dem Volumen entspricht, das durch die Hälfte des Radius des Partikels eingenommen wird.
4. Verfahren nach Anspruch 1, wobei der innere Anteil des Katalysatorpartikels als die inneren 50 % des Volumens des Katalysatorpartikels definiert ist.
- 40 5. Verfahren nach einem der Ansprüche 3 oder 4, wobei die relative Kristallinität des inneren Anteils des Katalysatorpartikels 10 bis 50 % beträgt.
6. Verfahren nach einem der Ansprüche 3 bis 4, wobei die relative Kristallinität des äußeren Anteils des Katalysatorpartikels 90 bis 100 % beträgt.
- 45 7. Verfahren nach einem der Ansprüche 1 oder 2, wobei der Katalysator eine kugelförmige Konfiguration aufweist.
8. Verfahren nach Anspruch 7, wobei die kugelförmige Konfiguration des Katalysators Charakteristika von Öltröpfen umfasst.
- 50 9. Verfahren nach einem der Ansprüche 1 oder 2, wobei der % Xylolverlust weniger als 0,02 % pro % Ethylbenzolumwandlung beträgt.

55


Revendications

1. Procédé de conversion d'une charge aromatique en C₈ hors équilibre comprenant la mise en contact de la charge

EP 2 773 603 B1

avec un lit de catalyseur comprenant des particules d'un aluminosilicate zéolithique non lié ayant un volume de pores d'intrusion des particules d'au moins $0,65 \text{ cm}^3/\text{g}$ et un gradient de cristallinité des particules augmentant en proportion de cristallinité d'une partie intérieure de faible cristallinité à une partie extérieure de forte cristallinité, dans une zone de conversion dans des conditions de conversion comprenant une température de $340 \text{ }^\circ\text{C}$ à $500 \text{ }^\circ\text{C}$, une pression de 100 kPa à 5 MPa , et une vitesse spatiale horaire massique de 2 à 50 h^{-1} en présence d'hydrogène pour convertir de l'éthylbenzène avec une perte limitée en xylène et obtenir un produit isomérisé comprenant une plus forte proportion d'au moins un isomère de xylène que dans la charge.

2. Procédé de la revendication 1 dans lequel le volume de pores d'intrusion des particules est d'au moins $0,7 \text{ cm}^3/\text{g}$.
3. Procédé de la revendication 1 dans lequel une partie intérieure de la particule de catalyseur est définie comme la partie de la particule correspondant au volume circonscrit par la moitié du rayon de la particule.
4. Procédé de la revendication 1 dans lequel la partie intérieure de la particule de catalyseur est définie comme les 50% intérieurs du volume de la particule de catalyseur.
5. Procédé de la revendication 3 ou 4 dans lequel la cristallinité relative de la partie intérieure de la particule de catalyseur est de 10 à 50% .
6. Procédé de la revendication 3 ou 4 dans lequel la cristallinité relative de la partie extérieure de la particule de catalyseur est de 90 à 100% .
7. Procédé de la revendication 1 ou 2 dans lequel le catalyseur a une configuration sphérique.
8. Procédé de la revendication 7 dans lequel la configuration sphérique du catalyseur comprend des caractéristiques de formation de gouttes dans l'huile.
9. Procédé de la revendication 1 ou 2 dans lequel le $\%$ de perte de xylène est inférieur à $0,02 \%$ par $\%$ de conversion d'éthylbenzène.



REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 2011245565 A [0008]
- RU 2233260 [0009]
- US 3909450 A [0010] [0021]
- US 2620314 A [0021]
- US 3201491 A [0043]
- US 3626020 A [0043]
- US 3696107 A [0043]
- US 4039599 A [0043]
- US 4184943 A [0043]
- US 4381419 A [0043]
- US 4402832 A [0043]
- US 7939701 B [0045] [0046] [0047]

Non-patent literature cited in the description

- Atlas of Zeolite Framework Types. Elsevier, 2007 [0018]

Szabadalmi igénypontok

1. Eljárás nem egyensúlyi állapotban lévő C_6 -aromás nyersanyag átalakítására, amelynek során a nyersanyagot érintkeztetjük egy katalizátorággal, amely nem kötött zeolitikus alumíniumszilikát szemcséit tartalmazza, a szemcsék intruziós pórustérfogata legalább $0,65 \text{ cm}^3/\text{g}$ és kristályossági gradiense növekvő a kristályosodás arányában alacsonyán kristályosodott belső résziől magasan kristályosodott külső részig, egy átalakítási zónában olyan átalakítási körülmények között, amelyek magukban foglalnak 340°C és 500°C közötti hőmérsékletet, 100 kPa és 5 MPa közötti nyomást és $2 - 50 \text{ óra}^{-1}$ óránkénti tömegáramot, hidrogén jelenlétében, hogy az etilbenzol csekély xilol-vesztéssel átalakítható legyen és olyan izomerizált termék képződjön, amely nagyobb arányban tartalmaz legalább egy xilol izomert, mint a nyersanyag.

2. Az 1. igénypont szerinti eljárás, ahol a szemcsék intruziós pórustérfogata legalább $0,7 \text{ cm}^3/\text{g}$.

3. Az 1. igénypont szerinti eljárás, ahol a katalizátorszemcsék belső része úgy van definiálva, mint a szemcse azon része, amely megfelel a szemcse sugarának fele által határolt térfogatnak.

4. Az 1. igénypont szerinti eljárás, ahol a katalizátorszemcse belső része úgy van definiálva, mint a katalizátorszemcse térfogatának belső 50 %-a.


5. A 3. vagy 4. igénypont szerinti eljárás, ahol a katalizátorszemcse belső részének relatív kristályossága 10 - 50%.

6. A 3. vagy 4. igénypont szerinti eljárás, ahol a katalizátorszemcse külső részének relatív kristályossága 90 - 100%.

7. Az 1. vagy 2. igénypont szerinti eljárás, ahol a katalizátor gömbalakú konfigurációjú.

8. A 7. igénypont szerinti eljárás, ahol a katalizátor gömbalakú konfigurációja magában foglalja olajcseppek jellemzőit.

9. Az 1. vagy 2. igénypont szerinti eljárás, ahol a %-os xilol veszteség kisebb mint 0,02% a %-os etilbenzol átalakulásra vonatkoztatva.



SZTNH-100071580