

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
4 June 2009 (04.06.2009)

PCT

(10) International Publication Number
WO 2009/070078 A1

(51) International Patent Classification:

C21D 1/673 (2006.01) *C21D 8/00* (2006.01)
B21D 22/00 (2006.01) *C23C 8/80* (2006.01)
B21D 47/01 (2006.01)

(74) Agent: ÅSLUND, Roland; Gestamp Hardtech AB, Box 828, S-971 25 Luleå (SE).

(21) International Application Number:

PCT/SE2008/000637

(22) International Filing Date:

11 November 2008 (11.11.2008)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

0702597-6 26 November 2007 (26.11.2007) SE

(71) Applicant (for all designated States except US): **GESTAMP HARDTECH AB** [SE/SE]; Box 828, S-971 25 Luleå (SE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **ÅKERSTRÖM, Paul** [SE/SE]; Olovsvägen 8, S-955 31 Råneå (SE).
LARSSON, Jan, Erik [SE/SE]; Rektorsgatan 18, S-972 42 Luleå (SE).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report



WO 2009/070078 A1

(54) Title: A METHOD OF PRODUCING A PAINTED STEEL SHEET PRODUCT OF HIGH STRENGTH

(57) Abstract: A high-strength product of sheet steel is produced in the press hardening process. A blank is heated to reach austenite structure and hot-stamped in a pair of cooled tools. The product is kept in the tools to rapidly be cooled to harden with the tools as a fixture. The blank has a surface of black oxide before it is shaped and the shaped product is painted directly on the black surface.

A method of producing a painted steel sheet product of high strength

Background of the invention and a brief description of the invention

Press-hardening is an established method of shaping and hardening blanks of sheet steel to a high strength product. This method is used in particular for producing high-strength beams and rails and other components for the vehicle industry. A corrosion protection is often needed and can be provided by painting when the skin, that is, the thick and brittle oxide formed in the process, has been removed by abrasive blasting.

According to the invention, a thin and smooth layer of black oxide can be established before the hot stamping and then the product can be painted directly on this oxide layer. In this way, a corrosion protection can be achieved that is in parity with or even better than the protection that can be provided by abrasive blasting and subsequent painting. It is also a less costly method.

Black oxide is well known for example from US 7,115,174 B2 and comprises FeO as a main component. The teaching of US 7,115,174 B2 is incorporated by way of reference.

The invention is defined by the claims.

Description of the invention

In one way of carrying out the invention, a steel strip is used that is pre-oxidized to have a black oxide surface, that is, a thin smooth layer of black oxide. This oxide is not brittle and porous as ordinary oxide and it does not absorb moisture. A blank is cut from this strip and the blank is heated to austenite state in a furnace with inert or slightly reducing or possibly slightly oxidizing atmosphere. The furnace may have sections with sequentially varying atmosphere. The heated blank is quickly moved to the shaping pair of tools in which it is hot stamped. The pair of tools is cooled, usually by internal water channels coupled to an external

source, and the shaped product is kept in the tools with the tools as a fixture until the product has hardened by being rapidly cooled. Martensite is dominant in the hardened structure.

In another way of carrying out the invention, the blank is cut from an unoxidized strip, and heated to austenite state in a furnace with a slightly oxidizing atmosphere so that the black oxide is formed in the furnace. Also in this case, the furnace may have sections with sequentially varying atmosphere.

In both examples, the blank with a surface of black oxide can be moved from the furnace to the stamping tools so fast that a protective atmosphere is not needed for the transport, but a protective atmosphere may be preferable.

Claims

1. A method of producing a painted high strength product of sheet steel, wherein a sheet steel blank is heated to austenitic state and hot stamped and hardened in a cooled pair of tools,
characterised in
that a blank is used that has a black oxide layer of 1-5 μm , and the shaped and hardened product is painted on the black oxide layer.
2. A method according to claim 1, **characterised in** that the blank is cut from a strip having a surface of black oxide, and the blank is heated in a furnace with inert or slightly oxidising atmosphere.
3. A method according to claim 1, **characterised in** that the blank is cut from an unoxidised band and the blank is heated in a furnace with a slightly oxidising atmosphere.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/SE2008/000637

A. CLASSIFICATION OF SUBJECT MATTER

IPC: see extra sheet

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC: C21D, B21D, C23C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-INTERNAL, WPI DATA, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	JP 2034793 A, KOBE STEEL LTD, 1990-02-05: (abstract) Retrieved from: WPI database, WEEK 199011 AN 1990-080469 --	1-3
A	US 20070000117 A1 (BRANDSTATTER W. ET AL), 4 January 2007 (04.01.2007) --	1-3
A	EP 1439240 A1 (SUMITOMO METAL INDUSTRIES, LTD.), 21 July 2004 (21.07.2004) --	1-3
A	US 6695931 B1 (RAVENSCROFT K.N. ET AL), 24 February 2004 (24.02.2004) -- -----	1-3

Further documents are listed in the continuation of Box C. See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

11 March 2009

Date of mailing of the international search report

11-03-2009

Name and mailing address of the ISA/

Swedish Patent Office

Box 5055, S-102 42 STOCKHOLM

Facsimile No. +46 8 666 02 86

Authorized officer

Kristina Nordén/ELY

Telephone No. +46 8 782 25 00

International patent classification (IPC)

C21D 1/673 (2006.01)

B21D 22/00 (2006.01)

B21D 47/01 (2006.01)

C21D 8/00 (2006.01)

C23C 8/80 (2006.01)

Download your patent documents at www.prv.se

The cited patent documents can be downloaded:

- From "Cited documents" found under our online services at www.prv.se (English version)
- From "Anförda dokument" found under "e-tjänster" at www.prv.se (Swedish version)

Use the application number as username. The password is **FBFCOINIOA**.

Paper copies can be ordered at a cost of 50 SEK per copy from PRV InterPat (telephone number 08-782 28 85).

Cited literature, if any, will be enclosed in paper form.

INTERNATIONAL SEARCH REPORT
Information on patent family members

International application No.
PCT/SE2008/000637

US 20070000117 A1 04/01/2007 NONE

EP 1439240 A1 21/07/2004 CN 1575348 A 02/02/2005
CN 100434564 C 19/11/2008
KR 20060090309 A 10/08/2006
US 20040166360 A 26/08/2004
US 20050252262 A 17/11/2005
WO 03035922 A 01/05/2003

US 6695931 B1 24/02/2004 NONE